United States Patent Office.

SAMUEL L. CROCKER, OF TAUNTON, MASSACHUSETTS.

CUT NAILS FROM MUNTZ'S METAL.

Specification forming part of Letters Patent No. 6,354, dated April 17, 1849.

To all whom it may concern:

Be it known that I, Samuel L. Crocker, of Taunton, in the county of Bristol and State of Massachusetts, have invented a new and useful Yellow-Metal Sheathing-Nail, which, by means of a nail-cutting engine, is cut from yellow sheathing metal; and I do hereby declare that the same is fully described in the follow-

ing specification.

The yellow-metal above referred to is a composition of about sixty parts of copper and forty parts of zinc. It is rolled into plates of sufficient thickness and shape to be cut up into nails. It is such a composition as is now extensively used in lieu of sheet-copper for the sheathing of navigable vessels. When in a cold state this composition cannot be used for the manufacture of cut nails in a nail-cutting machine, the great frangibility of the metal preventing the nails from being cut and headed. I have discovered that by heating it to redness, or thereabout, and while so heated introducing it into the nail-machine, it may be safely cut up into nail-blanks and each of said blanks headed by the machine

blanks headed by the machine.

In consequence of the difficulties heretofore supposed to exist in the manufacture of yellow-metal nails, it has been customary to cast or found nails made from a composition of copper, zinc, and some other metal, it having been discovered that nails could not be made to advantage by casting them from copper and zinc combined together in the proportion of sixty parts of the former to forty of the latter. To do so either a different proportion of copper and zinc or an addition of some other metal was requisite. After the nails have been thus made they are again heated to or about redness, and when so heated are plunged into cold water, and in consequence thereof their brittleness is so overcome as to render them capable of being bent or driven without that danger of being broken under such operations as the common cast composition nails would be subject to. This mode of making a nail of the yellowmetal enables me to produce one which although it may have but two-thirds the amount of metal in it that a cast composition nail may have, yet it will possess quite as much, if not more, strength. This renders my yellow-metal nails much cheaper than the cast nails, beside being a far better article, particularly on ac-

count of the perfection with which the head is made, the cast composition nail having its head rough and jagged, and so much so that in consequence thereof a great objection arises to their

use as sheathing-nails.

I would further remark that the rough state in which the heads of the cast composition nails are generally found tends to render foul the bottom of a vessel. The heads of the composition nails cannot be smoothed without much expense, to which my yellow-metal nail is not subject, owing to the perfection with which the head of it can be formed by the nail-machine. The yellow-metal nail, made of copper and zinc in the same, or substantially the same, proportions as they are combined in order to produce the yellow-metal sheathing, prevents, when it is used to confine the yellow-metal sheathing to a vessel's bottom, any galvanic action such as takes place when either copper or composition nails are used. This galvanic action destroys the metal, but protects the nails. When the metals are combined in the nail in different proportions to what they are in the sheathing more or less galvanic action accrues, this always tending to the destruction of the metal immediately around the nails. So when the metals—that is, copper and zinc—are combined with some other metal—tin, for instance which they must be in order to enable them to be cast into nails in a workman-like manner or to advantage, such nails, when used to secure sheathing to the bottom of a vessel, are liable to the effects of galvanic action and soon destroy the metal near the brads, whereas my improved yellow-metal nail, being made of the same material as the sheathing and combined in the same proportions, is not only not subject to galvanic action, but is more durable in consequence thereof, and can be made as strong as the composition nail with a much less quantity of metal. Consequently it is not only cheaper than either the composition or the copper nails, but possesses advantages of strength and durability which they do not. The cast composition nail, owing to its brittleness, cannot be driven without great care, whereas my yellow-metal nail, being tougher and more malleable, can be driven without the same difficulty.

I wish it distinctly understood that I lay no claim to the invention of either a cast-copper nail, or a cast composition nail made of copper

and zinc combined in different proportions from that in which they are combined in the yellow-metal known as "Muntz's sheathing metal," or combined in the same proportions and with some other metal; but

What I do claim as my invention is-

The new article of manufacture hereinabove described—viz., a yellow-metal nail made by cutting and heading it in a nail machine, meaning by the term "yellow-metal" a metal

composed of copper and zinc in the proportions in which they are usually combined in the manufacture of the well-known Muntz's sheathing metal.

In testimony whereof I have hereto set my signature this 24th day of March; A. D. 1849.

SAML. L. CROCKER.

Witnesses:

JAMES P. ELLIS, GEO. M. WOODWARD.