
(No Model.)

C. A. VON WELSBACH.

COMPOUND FOR MAKING INCANDESCENT DEVICES.

No. 377,698.

Patented Feb. 7, 1888.



Witnesses. Schrt Gruntt, Percy B. Hills. Inventor.
Carl Auer von Welsbach.
By
Janus L. Norn's!
Atty.

United States Patent Office.

CARL AUER VON WELSBACH, OF VIENNA, AUSTRIA-HUNGARY, ASSIGNOR TO THE WELSBACH INCANDESCENT GAS LIGHT COMPANY.

COMPOUND FOR MAKING INCANDESCENT DEVICES.

SPECIFICATION forming part of Letters Patent No. 377,698, dated February 7, 1888.

Application filed February 2, 1887. Serial No. 226,317. (No specimens.) Patented in France November 4, 1885, No. 172,064; in Belgium November 4, 1885, No. 70,739, and September 9, 1886, No. 74,502; in England December 12, 1885, No. 15,286, and March 13, 1886, No. 3,592; in Italy February 23, 1886, XXXVIII, 310, and October 13, 1886, XL, 415; in Cape of Good Hope March 4, 1886, No. 6/205; in Victoria March 17, 1886, No. 4,472; in Tasmania March 24, 1886, No. 398/9; in South Australia May 3, 1886, No. 678; in New South Wales May 11, 1886, No. 1,829/2; in New Zealand June 11, 1886, No. 1,863; in Queensland June 28, 1886, No. 106; in Finland July 10, 1886, No. 261; in Spain August 10, 1886, No. 9,031/5,858; in Norway August 25, 1886, No. 88, and in India September 2, 1886, No. 1,145.

To all whom it may concern: Be it known that I, CARL AUER VON WELS-BACH, a subject of the Emperor of Austria-Hungary, residing at Vienna, in the Empire of 5 Austria-Hungary, have invented new and useful Improvements in Compounds for Making Incandescent Devices, (for which I have obtained patents in France dated November 4, 1885, No. 172,064; in Belgium November 4, 10 1885, No. 70,739; in Italy February 23, 1886, Vol. XXXVIII, No. 310; in France, Certificate of Addition, April 22, 1886, No. 172,064; in Belgium, Certificate of Addition, September 9, 1886, No. 74,502; in Spain August 10, 1886, 15 No. 9,031/5,858; in Italy, Certificate of Addition, October 13, 1886, Vol. XL, No. 415; in Finland July 10, 1886, No. 261; in Norway August 25, 1886, No. 88; in Victoria March 17, 1886, No. 4,472; in New South Wales May 11, 20 1886, No. 1,829/2; in Tasmania March 24, 1886, No. 398/9; in Queensland June 28, 1886, No. 106; in New Zealand June 11, 1886, No. 1,863; in Cape of Good Hope March 4, 1886, No. 6/205; in India September 2/9, 1886, 25 No. 40—1886/1,145; in South Australia May 3, 1886, No. 678; in Great Britain December 12, 1885, No. 15,286, and in Great Britain, by application for patent, March 13, 1886, No. 3,592,) of which the following is a specification.

30 In my application for Letters Patent filed June 8, 1886, Serial No. 204,558, I set forth a method of making incandescents especially adapted for gas-burners by impregnating a fabric or thread with a solution of the salts of 35 the rarer metals which produce earthy oxides and subsequently burning away the combustible fabric or thread, leaving a skeleton hood or frame of the indestructible and infusible products resulting from the decomposition of the 40 salts of the metals—that is, a skeleton frame of the earthy oxides of lanthanum and yttriumso that when such hood or frame is heated to incandescence a brilliant and intense light is produced. Such a frame is illustrated in the 45 accompanying drawing.

The object of my invention is to provide a novel compound or solution for impregnating the fabric, thread, or other combustible fibrous substance which gives form to the earthy oxides for producing the incandescent device. 50 I have discovered that the combined properties of the oxide of lanthanum and oxide of yttrium, when employed according to my invention, provide an incandescent device that is very valuable as an illuminant when ren- 55 dered incandescent by the flame from a gasburner.

My present invention therefore consists in an incandescent composed of a mixture of the oxides of lanthanum and yttrium in about equal 6c proportions.

The invention also consists in a filament, fabric, or textile frame of combustible material impregnated with the salts of lanthanum and yttrium in aqueous solution in about 65 equal proportions.

The combined properties of the oxides thus formed into an incandescent device according to the method set forth produce the following results: First, if heated by the flame from any 70 ordinary gas-burner, a highly-intense, almost white, light is obtained; second, the substances are incombustible and infusible, and do not volatilize; third, the substances do not produce scale or ash after burning several hundreds 75 of hours, nor do they evince any decrease of power of emittance, but remain altogether perfect, and, fourth, the substances can without any change be exposed for any length of time to the influence of atmosphericair, so long as the 80 latter is in a condition for inhalation.

The proportions of the oxides produced by the decomposition of the salts set forth may be varied; but I have found that equal, or approximately equal, proportions of the two ox- 85 ides give satisfactory results.

The combined substances may be employed in connection with gas-burners in various ways. For example, the burner may be composed of a tubular skeleton hood or frame, as 90 shown in the accompanying drawing, in which the figure is an elevation of the device supported by a wire frame adapted to be suspended over the flame of a gas-burner, so as to become heated by such flame to incandescence, causing it to give out great and brilliant light. The hood may be made of light network fabric or threads or other combustible material—such as cotton—impregnated with a solution of the salts of lanthanum and yttrium, and then exposed to the heat of a flame, so that the fabric or threads are soon consumed, leaving a skeleton hood or frame consisting of the incombustible and infusible earthy oxides resulting from the decomposition of the salts of

said metals—that is to say, a hood or frame of the oxides of lanthanum and yttrium. This hood or frame, though light and fragile, will remain effective as an illuminant for hundreds of hours.

In preparing the aqueous or other solution different salts of the metals may be employed. Nitrates of the metals are generally soluble. So, also, but to a less degree, are sulphates, iodides, and bromides.

I do not here claim the method of making

this hood or frame, as such constitutes the subject-matter of my application for patent filed June 8, 1886, Serial No. 204,588.

I am aware that it has been proposed to use 30 zirconia in making incandescent devices, and such I disclaim.

Having thus described my invention, what I claim is—

- 1. An incandescent composed of a mixture 35 of the oxides of lanthanum and yttrium in about equal proportions, substantially as described.
- 2. A filament, fabric, or textile frame of combustible material impregnated with the 40 salts of lanthanum and yttrium in aqueous solution in about equal proportions, substantially as set forth.

In testimony whereof I have signed my name to this specification in the presence of two subscribing witnesses, this 13th day of January, A. D. 1887.

CARL AUER VON WELSBACH.

Witnesses:

EDWARD P. MACLEAN, Jos. B. Bourne.