United States Patent Office.

LEWIS BROWN, OF LANDING, NEW JERSEY, ASSIGNOR TO THE AMERICAN FORCITE POWDER MANUFACTURING COMPANY, OF NEW YORK, N. Y.

NITRO-GLYCERINE BLASTING-POWDER.

SPECIFICATION forming part of Letters Patent No. 478,844, dated July 12, 1892.

Application filed September 5, 1891. Serial No. 404,886. (No specimens.)

To all whom it may concern:

Be it known that I, Lewis Brown, of Landing, in the county of Morris and State of New Jersey, have invented a new and useful Improvement in Mixtures for use in the Manufacture of Nitro-Glycerine Blasting-Powder, of which the following is a specification.

My invention relates to an improvement in mixtures for use in the manufacture of nitroglycerine blasting-powder for the purpose of grading the quickness and energy of its explosive force and protecting it from deterioration under the influence of the weather.

The auxiliary mixture used for the purpose 15 of absorbing the nitro-glycerine and preparing it to receive the grading and coating mixture forms the subject-matter of a separate application filed of even date herewith, Serial No. 404,885, the present application embrac-20 ing only the grading and coating mixture. The formula for this grading and coating mixture may be stated as follows: seventythree parts, by weight, of nitrate of soda; one part, by weight, of wood pulp; twelve parts, by 25 weight, of sulphur; eleven parts, by weight, of rosin; three parts, by weight, of paraffine. When the above-name ingredients have been assembled in powdered form and thoroughly mixed into a homogeneous mass under the 30 influence of sufficient heat to render the par-

affine liquid, it possesses the properties required for grading the energy and quickness of the explosion. The wood pulp serves as a pore-maker, enabling the rosin and paraffine to come into more perfect contact with the 35 entire mass of the nitrate of soda and sulphur. The rosin serves as a binder and the paraffine forms a water-proof coating, preventing deterioration of the mixture while awaiting use. In practice a portion of this mix-40 ture, depending upon the grade of energy or quickness required, is incorporated with the mixture which holds the nitro-glycerine absorbed therein, to complete the powder for the market and for use.

While the above-stated proportions are at present preferred, variations therefrom may be made with more or less successful results. I do not, therefore, wish to limit myself to the exact proportions named; but

What I claim is—

The grading and coating mixture comprising nitrate of soda, wood pulp, sulphur, rosin, and paraffine, combined in the proportions substantially as set forth.

LEWIS BROWN.

Witnesses:
FREDK. HAYNES,
GEORGE BARRY.