



US010154863B2

(12) **United States Patent**
Fallin et al.

(10) **Patent No.:** **US 10,154,863 B2**
(45) **Date of Patent:** **Dec. 18, 2018**

(54) **FLEXIBLE BONE SCREW**

(2013.01); *A61B 2017/00526* (2013.01); *A61B 2017/00907* (2013.01); *A61B 2017/8655* (2013.01)

(71) Applicant: **IntraFuse, LLC**, Logan, UT (US)

(72) Inventors: **T. Wade Fallin**, Hyde Park, UT (US);
M. Mary Sinnott, Logan, UT (US);
Robert W. Hoy, Essex Junction, VT (US)

(58) **Field of Classification Search**
CPC .. *A61B 17/7208*; *A61B 17/7283*; *A61B 17/80*
See application file for complete search history.

(73) Assignee: **INTRAFUSE, LLC**, Logan, UT (US)

(56) **References Cited**

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

U.S. PATENT DOCUMENTS

2,267,925 A 12/1941 Johnston
3,051,169 A * 8/1962 Grath *A61B 17/742*
606/65

(Continued)

(21) Appl. No.: **15/285,608**

FOREIGN PATENT DOCUMENTS

(22) Filed: **Oct. 5, 2016**

WO WO2006124764 A1 11/2006
WO WO2008064346 A2 5/2008

(65) **Prior Publication Data**

US 2017/0056077 A1 Mar. 2, 2017

(Continued)

Related U.S. Application Data

OTHER PUBLICATIONS

(63) Continuation-in-part of application No. 15/197,879, filed on Jun. 30, 2016.

Materials Data Book, 2003 Edition. Cambridge University Engineering Department. p. 11.*

(Continued)

(60) Provisional application No. 62/191,904, filed on Jul. 13, 2015, provisional application No. 62/238,780, filed on Oct. 8, 2015.

Primary Examiner — David W Bates
(74) *Attorney, Agent, or Firm* — David Meibos;
Maywood IP Law


(51) **Int. Cl.**
A61B 17/72 (2006.01)
A61B 17/86 (2006.01)
A61B 17/17 (2006.01)
A61B 17/00 (2006.01)

(57) **ABSTRACT**

Examples of devices and methods for stabilizing a fracture in a bone include a body having an elongate distal portion having an outer surface defining a screw thread and an elongate proximal portion having a non-threaded outer surface. In one example, a passage is formed through the proximal portion transverse to the longitudinal axis from a first opening on the surface of the proximal portion to a second opening on the surface of the proximal portion.

(52) **U.S. Cl.**
CPC *A61B 17/7208* (2013.01); *A61B 17/1725* (2013.01); *A61B 17/725* (2013.01); *A61B 17/7225* (2013.01); *A61B 17/7291* (2013.01); *A61B 17/863* (2013.01); *A61B 17/8685*

21 Claims, 16 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

3,118,444 A	1/1964	Serrato, Jr.	6,416,517 B2	7/2002	Harder	
3,456,272 A	7/1969	Wendt	6,447,514 B1	9/2002	Stalcup	
3,680,553 A	8/1972	Seppo	6,447,515 B1	9/2002	Meldrum	
3,717,146 A	2/1973	Halloran	6,447,518 B1	9/2002	Krause	
3,760,802 A	9/1973	Fischer	6,517,541 B1	2/2003	Sesic	
3,763,855 A	10/1973	McAtee	6,524,313 B1	2/2003	Fassier	
3,779,239 A	12/1973	Fischer	6,551,321 B1	4/2003	Burkinshaw	
3,805,775 A	4/1974	Fischer	6,554,833 B2	4/2003	Levy	
4,016,874 A	4/1977	Maffei	6,605,090 B1	8/2003	Trieu	
4,170,990 A	10/1979	Baumgart	6,613,052 B1	9/2003	Kinnett	
4,175,555 A	11/1979	Herbert	6,623,505 B2	9/2003	Scribner	
4,212,294 A	7/1980	Murphy	6,632,235 B2	10/2003	Weikel	
4,262,665 A	4/1981	Roalstad	6,656,184 B1	12/2003	White	
4,328,839 A	5/1982	Lyons	6,736,819 B2	5/2004	Tipirneni	
4,453,539 A	6/1984	Raftopoulos	6,749,611 B2	6/2004	Venturini	
4,457,301 A	7/1984	Walker	6,790,210 B1	9/2004	Cragg	
4,463,753 A	8/1984	Gustilo	6,824,568 B1 *	11/2004	Albrektsson	A61F 2/3601 623/23.15
4,475,545 A	10/1984	Ender	6,852,115 B2	2/2005	Kinnett	
4,483,335 A	11/1984	Tornier	6,875,215 B2	4/2005	Taras	
4,492,226 A	1/1985	Belykh	6,899,719 B2	5/2005	Reiley	
4,590,930 A	5/1986	Kurth	6,949,100 B1	9/2005	Venturini	
4,697,585 A	10/1987	Williams	6,949,101 B2	9/2005	McCleary	
4,706,659 A	11/1987	Matthews	6,955,513 B2	10/2005	Niku	
4,751,922 A	6/1988	DiPietropolo	7,041,106 B1	5/2006	Carver	
4,858,602 A	8/1989	Seidel	7,044,954 B2	5/2006	Reiley	
4,947,502 A	8/1990	Engelhardt	7,156,861 B2	1/2007	Scribner	
4,959,064 A	9/1990	Engelhardt	7,175,626 B2	2/2007	Neff	
4,978,350 A *	12/1990	Wagenknecht	7,249,923 B2	7/2007	Niku	
		A61B 17/8635	7,255,712 B1	8/2007	Steinberg	
		411/387.7	7,527,611 B2	5/2009	Sweeney	
5,017,057 A	5/1991	Kryger	7,527,627 B2	5/2009	Ferrante	
5,019,079 A *	5/1991	Ross	7,534,244 B2	5/2009	Ferrante	
		A61B 17/863	7,534,245 B2	5/2009	Chappuis	
		411/389	7,588,577 B2	9/2009	Fencl	
5,032,133 A	7/1991	Carbone	7,591,823 B2	9/2009	Tipirneni	
5,053,035 A	10/1991	McLaren	7,621,912 B2	11/2009	Harms	
5,061,137 A	10/1991	Gourd	7,625,395 B2	12/2009	Mückter	
5,116,336 A	5/1992	Frigg	7,632,277 B2	12/2009	Woll	
5,116,378 A	5/1992	Carbone	7,666,205 B2	2/2010	Weikel	
5,259,398 A	11/1993	Vrespa	7,682,364 B2	3/2010	Reiley	
5,281,225 A	1/1994	Vicenzi	7,722,611 B2	5/2010	Cavallazzi	
5,312,255 A	5/1994	Bauer	7,727,263 B2	6/2010	Cragg	
5,334,184 A	8/1994	Bimman	7,744,599 B2	6/2010	Cragg	
5,356,127 A	10/1994	Moore	7,766,968 B2	8/2010	Sweeney	
5,374,235 A	12/1994	Ahrens	7,776,042 B2 *	8/2010	Ainsworth	A61B 17/70 606/249
5,397,328 A	3/1995	Behrens	7,780,667 B2	8/2010	Watanabe	
5,409,490 A	4/1995	Ethridge	7,799,053 B2	9/2010	Haid, Jr.	
5,415,660 A	5/1995	Campbell	7,819,874 B2	10/2010	Woll	
5,437,674 A	8/1995	Worcel	7,842,095 B2	11/2010	Klein	
5,480,400 A	1/1996	Berger	7,846,162 B2	12/2010	Nelson	
5,527,316 A	6/1996	Stone	7,883,509 B2	2/2011	Ferrante	
5,549,702 A *	8/1996	Ries	7,901,412 B2	3/2011	Tipirneni	
		A61F 2/3676	7,909,825 B2	3/2011	Saravia	
		623/23.32	7,914,533 B2	3/2011	Nelson	
5,575,790 A	11/1996	Chen	7,918,853 B2	4/2011	Watanabe	
5,603,715 A	2/1997	Kessler	7,931,652 B2	4/2011	Ferrante	
5,681,289 A	10/1997	Wilcox	7,942,875 B2	5/2011	Nelson	
5,709,687 A	1/1998	Pennig	8,007,498 B2	8/2011	Mische	
5,827,289 A	10/1998	Reiley	8,012,155 B2	9/2011	Prygoski	
5,871,486 A	2/1999	Huebner	8,034,071 B2	10/2011	Scribner	
5,891,101 A	4/1999	Wilcox	8,062,270 B2	11/2011	Sweeney	
5,895,375 A	4/1999	Wilcox	8,066,748 B2	11/2011	Lieberman	
5,972,015 A	10/1999	Scribner	8,083,742 B2	12/2011	Martin	
5,993,450 A	11/1999	Worcel	8,105,326 B2	1/2012	Ferrante	
6,030,162 A	2/2000	Huebner	8,109,936 B2	2/2012	Tipirneni	
6,053,922 A	4/2000	Krause	8,128,626 B2	3/2012	Justin	
6,162,234 A	12/2000	Freedland	8,128,627 B2	3/2012	Justin	
6,197,031 B1	3/2001	Barrette	8,147,492 B2	4/2012	Justin	
6,224,600 B1	5/2001	Protogirou	8,162,943 B2	4/2012	Justin	
6,245,112 B1 *	6/2001	Doubler	8,167,881 B2	5/2012	Justin	
		A61F 2/30721	8,187,275 B2	5/2012	Ferrante	
		623/22.41	8,197,523 B2	6/2012	Bottlang	
6,248,110 B1	6/2001	Reiley	8,206,389 B2	6/2012	Huebner	
6,280,456 B1	8/2001	Scribner	8,221,419 B2	7/2012	Frigg	
6,299,615 B1	10/2001	Huebner	8,246,691 B2	8/2012	Mangiardi	
6,319,255 B1	11/2001	Grundei	8,287,538 B2	10/2012	Brenzel	
6,322,562 B1	11/2001	Wolter	8,287,539 B2	10/2012	Nelson	
6,338,732 B1	1/2002	Yang				
6,368,326 B1	4/2002	Dakin				

(56)	References Cited				
			2002/0143335	A1*	10/2002 von Hoffmann A61B 17/68 606/67
	U.S. PATENT DOCUMENTS		2002/0198527	A1	12/2002 Muckter
			2003/0187447	A1	10/2003 Ferrante
			2003/0229372	A1	12/2003 Reiley
8,287,541	B2	10/2012 Nelson	2004/0049192	A1	3/2004 Shimizu
8,298,234	B2	10/2012 Ferrante	2004/0122455	A1	6/2004 Lin
8,303,589	B2	11/2012 Tyber	2004/0127898	A1	7/2004 Adam
8,313,488	B2	11/2012 Schlienger	2004/0167519	A1	8/2004 Weiner
8,317,789	B2	11/2012 LeCronier	2005/0055024	A1	3/2005 James
8,317,846	B2	11/2012 Bottlang	2005/0119662	A1	6/2005 Reiley
8,328,806	B2	12/2012 Tyber	2005/0131267	A1	6/2005 Talmadge
8,343,197	B2	1/2013 Gonzalez-Hernandez	2005/0131268	A1	6/2005 Talmadge
8,343,199	B2	1/2013 Tyber	2005/0165402	A1*	7/2005 Taras A61B 17/1637 606/312
8,382,760	B2	2/2013 Mantovani			
8,388,620	B2	3/2013 Brunnarius			
8,398,690	B2	3/2013 Bottlang	2005/0165405	A1	7/2005 Tsou
8,403,938	B2	3/2013 Aeschlimann	2005/0182402	A1	8/2005 Hansson
8,430,879	B2	4/2013 Stoneburner	2005/0209629	A1	9/2005 Kerr
8,435,238	B2	5/2013 Dejardin	2006/0149265	A1	7/2006 James
8,435,272	B2	5/2013 Dougherty	2006/0155281	A1	7/2006 Kaup
8,439,916	B2	5/2013 Coati	2006/0173291	A1	8/2006 Glossop
8,439,917	B2	5/2013 Saravia	2006/0235460	A1	10/2006 Reiley
8,449,574	B2	5/2013 Biedermann	2006/0271061	A1	11/2006 Beyar
8,460,293	B2	6/2013 Coati	2006/0293667	A1	12/2006 Vignery
8,496,657	B2	7/2013 Bonutti	2007/0005146	A1	1/2007 Heyligers
8,496,658	B2	7/2013 Stoneburner	2007/0016190	A1	1/2007 Martinez
8,496,712	B2	7/2013 Reiley	2007/0016204	A1	1/2007 Martinez
8,507,614	B2	8/2013 Shalaby	2007/0060941	A1	3/2007 Reiley
8,529,611	B2	9/2013 Champagne	2007/0083207	A1	4/2007 Ziolo
8,545,499	B2	10/2013 Lozier	2007/0276382	A1*	11/2007 Mikhail A61B 17/1725 606/62
8,568,413	B2	10/2013 Mazur			
8,597,337	B2	12/2013 Champagne	2008/0004626	A1	1/2008 Glazer
8,608,743	B2	12/2013 Baumgartner	2008/0039941	A1	2/2008 Steinberg
8,617,161	B2	12/2013 Ferrante	2008/0051825	A1	2/2008 Reiley
8,617,585	B2	12/2013 Boden	2008/0058823	A1	3/2008 Reiley
8,622,739	B2	1/2014 Karmon	2008/0058824	A1	3/2008 Reiley
8,632,543	B2	1/2014 Metzinger	2008/0058828	A1	3/2008 Reiley
8,632,570	B2	1/2014 Biedermann	2008/0109008	A1	5/2008 Schwager
8,652,141	B2	2/2014 Rush	2008/0125805	A1	5/2008 Mische
8,663,224	B2	3/2014 Overes	2008/0132896	A1	6/2008 Bowen
8,663,326	B2	3/2014 Osman	2008/0140078	A1	6/2008 Nelson
8,679,120	B2	3/2014 Frigg	2008/0149115	A1	6/2008 Hauck
8,679,167	B2	3/2014 Tipirneni	2008/0188895	A1	8/2008 Cragg
8,696,719	B2	4/2014 Lofthouse	2008/0221620	A1	9/2008 Krause
8,702,768	B2	4/2014 Tipirneni	2008/0234752	A1	9/2008 Dahners
8,709,055	B2	4/2014 Beyar	2008/0249574	A1	10/2008 Krause et al.
8,721,690	B2	5/2014 Harms	2008/0249580	A1	10/2008 Evans
8,734,497	B2	5/2014 Goel	2008/0255555	A1	10/2008 Justis
8,740,955	B2	6/2014 Bottlang	2008/0269759	A1	10/2008 Reiley
8,784,491	B2	7/2014 Biedermann	2008/0269795	A1	10/2008 Reiley
8,801,722	B2	8/2014 Aeschlimann	2008/0269796	A1	10/2008 Reiley
8,808,337	B2	8/2014 Sweeney	2009/0005782	A1	1/2009 Chirico
8,808,338	B2*	8/2014 Martin A61B 17/1717 606/301	2009/0005821	A1	1/2009 Chirico
			2009/0012564	A1	1/2009 Chirico
8,821,494	B2	9/2014 Pilgeram	2009/0018542	A1	1/2009 Saravia
8,828,067	B2	9/2014 Tipirneni	2009/0062868	A1*	3/2009 Casutt A61B 17/7001 606/316
8,834,468	B2	9/2014 Justin			
8,840,612	B2	9/2014 Tontz	2009/0062928	A1	3/2009 Pitkin
8,870,836	B2	10/2014 Sweeney	2009/0076517	A1	3/2009 Reiley
8,888,815	B2	11/2014 Holmes, Jr.	2009/0131991	A1	5/2009 Tipirneni
8,900,233	B2	12/2014 Logan	2009/0143781	A1	6/2009 Mische
8,939,978	B2	1/2015 Watanabe	2009/0149890	A1*	6/2009 Martin A61B 17/1717 606/316
8,961,516	B2	2/2015 Nelson			
8,979,930	B2	3/2015 Glazer	2009/0157078	A1	6/2009 Mikol
8,992,615	B2	3/2015 Pitkin	2009/0264937	A1	10/2009 Parrott
8,998,999	B2	4/2015 Lewis	2010/0016905	A1*	1/2010 Greenhalgh A61B 17/8858 606/313
9,033,984	B2	5/2015 Overes			
9,060,820	B2	6/2015 Nelson	2010/0023057	A1	1/2010 Aeschlimann
9,072,510	B2	7/2015 Thornes	2010/0069970	A1	3/2010 Lewis
9,155,574	B2*	10/2015 Saravia A61B 17/7208	2010/0076503	A1	3/2010 Beyar
9,241,806	B2*	1/2016 Suh A61B 17/8625	2010/0082036	A1	4/2010 Reiley
9,314,286	B2	4/2016 Bottlang	2010/0114097	A1	5/2010 Siravo
9,408,599	B2*	8/2016 Kaiser A61B 17/0401	2010/0114181	A1	5/2010 Lob
9,421,045	B2	8/2016 Justin	2010/0121326	A1	5/2010 Woll
9,433,451	B2*	9/2016 Ehmke A61B 17/746	2010/0137862	A1	6/2010 Diao
9,498,264	B2	11/2016 Harshman, et al.	2010/0145396	A1	6/2010 Thornes
9,522,019	B2*	12/2016 Biedermann A61B 17/7031	2010/0168755	A1	7/2010 Reiley
10,034,699	B2*	7/2018 Mazzuca A61B 17/8625	2010/0179551	A1	7/2010 Keller
			2010/0211076	A1	8/2010 Germain

(56)

References Cited

U.S. PATENT DOCUMENTS

2010/0228301 A1 9/2010 Greenhalgh
 2010/0256731 A1 10/2010 Mangiardi
 2010/0274246 A1 10/2010 Beyar
 2010/0286692 A1 11/2010 Greenhalgh
 2010/0292695 A1* 11/2010 May A61B 17/1642
 606/64
 2010/0312292 A1 12/2010 Tipirneni
 2010/0318087 A1 12/2010 Scribner
 2011/0009865 A1 1/2011 Orfaly
 2011/0009907 A1 1/2011 Klein
 2011/0118740 A1 5/2011 Rabiner
 2011/0144703 A1* 6/2011 Krause A61B 17/8625
 606/309
 2011/0160728 A1* 6/2011 Blitz A61B 17/1725
 606/64
 2011/0172667 A1 7/2011 Richards
 2011/0178520 A1 7/2011 Taylor
 2011/0184472 A1 7/2011 Niederberger
 2011/0196371 A1 8/2011 Forsell
 2011/0196435 A1 8/2011 Forsell
 2011/0218585 A1 9/2011 Krinke
 2011/0257689 A1* 10/2011 Fiechter A61B 17/866
 606/301
 2011/0282346 A1 11/2011 Pham
 2011/0282398 A1 11/2011 Overes
 2011/0295255 A1 12/2011 Roberts
 2011/0306975 A1 12/2011 Kaikkonen
 2012/0029432 A1 2/2012 Sweeney
 2012/0029579 A1 2/2012 Bottlang
 2012/0065638 A1 3/2012 Moore
 2012/0065692 A1 3/2012 Champagne
 2012/0101534 A1* 4/2012 Pitbladdo A61B 17/864
 606/309
 2012/0123481 A1 5/2012 Lin
 2012/0172936 A1 7/2012 Horrell
 2012/0203346 A1 8/2012 Kraus
 2012/0209267 A1 8/2012 Lee
 2012/0221009 A1 8/2012 Tada
 2012/0226362 A1 9/2012 Mische
 2012/0232533 A1 9/2012 Veldman
 2012/0232597 A1 9/2012 Saidha
 2012/0239037 A1 9/2012 Justin
 2012/0239038 A1 9/2012 Saravia
 2012/0289961 A1 11/2012 Frigg
 2013/0035689 A1 2/2013 Nanavati
 2013/0041412 A1 2/2013 Moumene
 2013/0079829 A1 3/2013 Globerman
 2013/0123785 A1* 5/2013 Fonte A61B 17/72
 606/63
 2013/0123857 A1 5/2013 Biedermann
 2013/0131678 A1 5/2013 Dahners
 2013/0184765 A1 7/2013 Beyar
 2013/0190762 A1 7/2013 Frankle
 2013/0190874 A1* 7/2013 Glazer A61F 2/442
 623/17.11
 2013/0218214 A1 8/2013 Beyar
 2013/0226180 A1 8/2013 Lee
 2013/0231665 A1 9/2013 Saravia
 2013/0231666 A1 9/2013 Lee
 2013/0237813 A1 9/2013 Beyar
 2013/0267953 A1 10/2013 Brenzel
 2013/0296863 A1 11/2013 Globerman
 2013/0296952 A1 11/2013 Globerman
 2013/0297035 A1 11/2013 Reiley
 2013/0317556 A1 11/2013 Goldzak
 2013/0325007 A1 12/2013 Beyar
 2013/0325077 A1 12/2013 Champagne
 2013/0340240 A1 12/2013 Irawan
 2014/0031823 A1 1/2014 Mazur
 2014/0058390 A1 2/2014 Taylor
 2014/0058391 A1 2/2014 Appenzeller
 2014/0058432 A1 2/2014 Scribner
 2014/0074252 A1 3/2014 Baumgartner
 2014/0106306 A1 4/2014 Karmon

2014/0114312 A1* 4/2014 Krause A61B 17/8625
 606/62
 2014/0128870 A1 5/2014 Brenzel
 2014/0131909 A1 5/2014 Osman
 2014/0039495 A1 6/2014 Bonutti
 2014/0163557 A1 6/2014 Beyar
 2014/0163624 A1* 6/2014 Siegal A61B 17/7032
 606/304
 2014/0180428 A1 6/2014 McCormick
 2014/0188113 A1 7/2014 Overes
 2014/0188180 A1* 7/2014 Biedermann A61B 17/8625
 606/328
 2014/0194877 A1 7/2014 Mangiardi
 2014/0207138 A1 7/2014 Justin
 2014/0222001 A1 8/2014 Beyar
 2014/0222080 A1 8/2014 Biedermann
 2014/0222091 A1 8/2014 Champagne
 2014/0249529 A1 9/2014 LeCronier
 2014/0288651 A1 9/2014 Biedermann
 2014/0316469 A1 10/2014 Harms
 2014/0336653 A1 11/2014 Bromer
 2014/0336663 A1 11/2014 Mayer
 2014/0358146 A1 12/2014 Meek
 2014/0371747 A1 12/2014 Martin
 2015/0005827 A1 1/2015 Lin
 2015/0012048 A1* 1/2015 Huebner A61B 17/864
 606/304
 2015/0039033 A1 2/2015 McCombs et al.
 2015/0045791 A1 2/2015 Mangiardi
 2015/0045792 A1 2/2015 Mangiardi
 2015/0066097 A1 3/2015 Biedermann
 2015/0105830 A1 4/2015 Biedermann
 2015/0133937 A1 5/2015 Benedict
 2015/0250503 A1 9/2015 Tipirneni
 2015/0257800 A1* 9/2015 Harshman A61B 17/7208
 606/62
 2015/0374411 A1* 12/2015 Ehmke A61B 17/686
 606/329
 2016/0128742 A9 5/2016 Justin
 2016/0317201 A1 11/2016 Justin

FOREIGN PATENT DOCUMENTS

WO WO2008064347 A2 5/2008
 WO WO2008064350 A2 5/2008
 WO WO2009009772 A1 1/2009
 WO WO2009076086 A1 6/2009
 WO WO2009152270 A1 12/2009
 WO WO2009152272 A1 12/2009
 WO WO2009152273 A1 12/2009
 WO WO2010037038 A2 4/2010
 WO WO2010062379 A1 6/2010
 WO WO2010099239 A3 1/2011
 WO WO2011116078 A1 9/2011
 WO WO2011154891 A2 12/2011
 WO WO2012051137 A1 4/2012
 WO WO2012069727 A1 5/2012
 WO WO2012089330 A1 7/2012
 WO WO2012089331 A1 7/2012
 WO WO2012091681 A3 8/2012
 WO WO2012107913 A2 8/2012
 WO WO2012156915 A2 11/2012
 WO WO2013063145 A1 5/2013
 WO WO2013074884 A1 5/2013
 WO WO2013166328 A1 11/2013
 WO WO2014031947 A1 2/2014
 WO WO2014031951 A1 2/2014
 WO WO2014060576 A1 4/2014
 WO WO2014060578 A1 4/2014
 WO WO2014151907 A2 9/2014
 WO WO2015029042 A1 3/2015

OTHER PUBLICATIONS

International Search Report and Written Opinion for International Application No. PCT/US2016/041162 dated Oct. 12, 2016, 18 pp.

(56)

References Cited

OTHER PUBLICATIONS

EPIFISA Centromedullary Nail, FH Orthopedics, www.f-h-fr, May 2005, 2 pp.

Dual-Trak Clavicle Screw Surgical Technique, Acumed, www.acumed.net, Sep. 2014, 12 pp.

Fibul Rod System Surgical Technique, Acumed, www.acumed.net, Apr. 2014, 8 pp.

Polarus Plus Humeral Rod, Acumed, www.acumed.net, Nov. 2008, 12 pp.

Asloum, Y., et al., "Internal Fixation of the Fibula in Ankle Fractures. A Prospective, Randomized and Comparative Study: Plating Versus Nailing", Orthopaedics & Traumatology: Surgery & Research 100(2014) S255-S259.

Rockwood Clavicle Pin, Design Rationale and Surgical Technique, Biomet Orthopedics, www.biomet.com, Aug. 31, 2012, 24 pp.

Distal Radius 3D Fracture Management System Surgical Technique, Conventus Orthopaedics, www.conventusortho.com, 12 pp.

Clavicle Fracture Repair Device, Sonoma Orthopedic Products, Inc., www.sonomaorthopedics.com, 2011, 6 pp.

The Nancy Nail Surgical Technique, DePuy Products, www.jnjgateway.com, 1999, 6 pp.

Hand Innovations Minimally Invasive Dorsal Endoplate Surgical Technique, Hand Innovations, www.handinnovations.com, 14 pp.

Latif, Girgis, et al., "The Effect of Percutaneous Screw Fixation of Lateral Malleolus on Ankle Fracture Healing and Function", Surgical Science, 2013, 4, 365-370, 2013.

Ankle Fracture System Abbreviated Surgical Technique, Sonoma Orthopedic Products, Inc., www.sonomaorthopedics.com, 2015, 20 pp.

Fracture and Fixation Products, ConMed Linvatec, 7 pp.

Flexible Radial Nail Enclouage Radial Souple, www.evolutisfrance.com, 4 pp.

Olecranon Threaded Compression Rod: O'Rod, Acumed, www.acumed.net, Jul. 2010, 8 pp.

Piccolo Composite Made of Carbon Fibers Reinforced Polymer, CarboFix Orthopedics, Ltd., www.carbo-fix.com, Sep. 2011, 4 pp.

Darden Business Publishing—University of Virginia, UVA-QA-0811, Oct. 20, 2014, 10 pp.

IP-XS Nail Compression Nail System Surgical Technique and Product Information, Smith & Nephew GmbH, www.smith-nephew.de Apr. 2004, 24 pp.

Trigen Intertan Intertrochanteric Antegrade Nail Surgical Technique, Smith & Nephew, Inc., www.smith-nephew.com, 2012, 46 pp.

S.S.T. Small Bone Locking Nail Fibula Nail Surgical Technique, Biomet, Inc., www.biomet.com, 12 pp.

MetaFLEX Percutaneous Flexible IM Nail System for Metacarpal and Metatarsal Fractures, Small Bone Innovations, www.totalsmallbone.com, Apr. 2007, 2 pp.

Improved Healing of Clavicle Fractures using an Implantable Pre-Curved Intramedullary Rod, Upstate Medical University, www.upstate.edu, 1 pp.

The Titanium Flexible Humeral Nail System, Synthes (USA), Jul. 1999, 4 pp.





The Next Generation in Foot & Ankle Repair and Reconstruction Technology, Arthrex, www.arthrex.com, 2016, 76 pp.

Trim-It Drill Pin Fixation, , 1 pp.

Micronail II Intramedullary Distal Radius System Surgical Technique, Wright Medical Technology, Inc., www.wmt.com, Jun. 15, 2014, 20 pp.

Wrist Fracture Nail, Sonoma Orthopedic Products, Inc., www.sonomaorthopedics.com, 2013, 15 pp.

* cited by examiner






Fig. 5




Fig. 6




Fig. 7




Fig. 8

Fig. 9

Fig. 10




Fig. 11




Fig. 12




Fig. 13




Fig. 14




Fig. 15




Fig. 16




Fig. 17




Fig. 18




Fig. 19




Fig. 20




Fig. 21




Fig. 22




Fig. 23




Fig. 24




Fig. 25




Fig. 26




Fig. 27




Fig. 28







Fig. 29






Fig. 33




Fig. 34




Fig. 35




Fig. 36




Fig. 37




Fig. 38

Fig. 39




Fig. 41




Fig. 40




Fig. 43






Fig. 42






Fig. 48

Fig. 46




Fig. 49

Fig. 47

1**FLEXIBLE BONE SCREW****CROSS-REFERENCE TO RELATED APPLICATIONS**

This application is a continuation-in-part of U.S. patent application Ser. No. 15/197,879, filed Jun. 30, 2016, which claims the benefit of U.S. Provisional Application No. 62/191,904, filed Jul. 13, 2015, and U.S. Provisional Application No. 62/238,780, filed Oct. 8, 2015, all of which are hereby incorporated by reference.

FIELD OF THE INVENTION

Examples of the invention relate generally to orthopedic devices for the surgical treatment of bone and, more particularly, to the stabilization of bones with an intramedullary device.

BACKGROUND

Orthopedic medicine provides a wide array of implants that can be attached to bone to repair fractures. External fixation involves the attachment of a device that protrudes out of the skin, and therefore carries significant risk of infection. Many fractures in long bones can be repaired through the use of bone plates, which are implanted and attached to lie directly on the bone surface. The bone plate then remains in the body long enough to allow the fractured bone to heal properly. Unfortunately, such bone plates often require the surgical exposure of substantially the entire length of bone to which the plate is to be attached. Such exposure typically results in a lengthy and painful healing process, which must often be repeated when the implantation site is again exposed to allow removal of the plate. There is a need in the art for implants and related instruments that do not require such broad exposure of the fractured bone, while minimizing the probability of infection by avoiding elements that must protrude through the skin as the bone heals.

SUMMARY

Examples of the invention provide devices and methods for stabilizing first and second bone portions relative to one another.

In one example of the invention, a device for stabilizing a fracture in a bone includes a body having an elongate distal portion having an outer surface defining a screw thread and an elongate proximal portion having a non-threaded outer surface.

In another example of the invention, a passage is formed through the proximal portion transverse to the longitudinal axis from a first opening on the surface of the proximal portion to a second opening on the surface of the proximal portion.

In another example of the invention, a method of stabilizing a fractured long bone having an intramedullary canal, comprises providing a bone implant comprising a body defining a longitudinal axis extending between a proximal end and a distal end; an elongate distal portion of the body having an outer surface defining a screw thread, the screw thread having a minor diameter and a major diameter; and an elongate proximal portion of the body having a non-threaded outer surface, a passage formed through the proximal portion transverse to the longitudinal axis from a first opening on the surface of the proximal portion to a second opening

2

on the surface of the proximal portion; and inserting the bone implant into an intramedullary canal of a bone so that the proximal portion spans a fracture in the bone.

BRIEF DESCRIPTION OF THE DRAWINGS

Various examples of the invention will be discussed with reference to the appended drawings. These drawings depict only illustrative examples of the invention and are not to be considered limiting of its scope.

FIG. 1 is a side elevation view of a screw according to one example of the invention;

FIG. 2 is a detail view of the screw of FIG. 1;

FIG. 3 is a detail view of the screw of FIG. 1;

FIG. 4 is an end view of the screw of FIG. 1;

FIGS. 5-7 are side elevation views of a set of differently sized screws like that of FIG. 1;

FIGS. 8-10 are partial sectional views showing the insertion of the screw of FIG. 1 into bone;

FIGS. 11-35 illustrate a surgical procedure utilizing the bone screw of FIG. 1;

FIG. 36 is a perspective view of a screw according to one example of the invention;

FIG. 37 is a top plan view of the screw of FIG. 36;

FIG. 38 is a side elevation view of the screw of FIG. 36;

FIG. 39 is an end view of the screw of FIG. 36;

FIG. 40 is a sectional view taken along line 40-40 of FIG. 37;

FIG. 41 is an exploded sectional view taken along line 40-40 of FIG. 37;

FIG. 42 is a cross sectional view of a screw according to one example of the invention;

FIG. 43 is an exploded cross sectional view of the screw of FIG. 42;

FIG. 44 is an exploded side view of a screw according to one example of the invention;

FIG. 45 is an assembled sectional view taken along line 45-45 of FIG. 44;

FIG. 46 is an exploded side view of a screw according to one example of the invention;

FIG. 47 is an assembled sectional view taken along line 47-47 of FIG. 46;

FIG. 48 is an end view of the screw of FIG. 46; and

FIG. 49 is a cross sectional view taken along line 49-49 of FIG. 47.

DESCRIPTION OF THE ILLUSTRATIVE EXAMPLES

The term "transverse" is used herein to mean not parallel. FIGS. 1-4 depict a bone screw 100 according to one example of the invention having an elongate body 102 with a distal portion 104, a mid-portion 106 and a proximal portion 108 spaced longitudinally relative to a longitudinal axis 110. The distal portion 104 includes a helical thread 112 having a major diameter 114, a minor diameter 116, and a pitch 128. The mid-portion 106 has a non-threaded outer surface 118 with an outer diameter 120. In the illustrative example of FIGS. 1-4, the mid-portion outer diameter 120 is equal to or greater than the thread major diameter 114. The distal threaded portion 104 is operable to bend as it is threaded into a bone to follow a curved path. For example, the bending stiffness of the distal threaded portion 104 is such that it will bend to follow a curved path in human bone. Such a curved path may be defined, for example, by a curved hole in the bone, a guide wire, or a natural bone feature such as a non-linear intramedullary canal bounded by cortical bone.

This is distinct from prior art screws which if started on a curved path in human bone would, when advanced, continue in a straight line and thus deviate from the curved path and form their own, straight, path through the bone. Preferably the bending stiffness of the threaded distal portion **104** is lower than the bending stiffness of the mid-portion **106**. The relatively lower bending stiffness of the threaded distal portion **104** causes the threaded distal portion to bend to follow a curved path while the relatively higher bending stiffness of the mid-portion causes the mid-portion to remain straight to stabilize first and second bone portions relative to one another at a bone interface such as at a fracture, osteotomy, or fusion site. The difference in bending stiffness between the threaded distal portion **104** and the mid-portion **106** may be achieved in different ways. For example, the threaded distal portion **104** and the mid-portion **106** may be made of different materials and/or may have different sectional moduli. In the illustrative example of FIGS. 1-4, the threaded distal portion **104** and the mid-portion **106** have different sectional moduli. The threaded distal portion minor diameter **116** is less than the outer diameter **120** of the mid-portion **106** and the threaded distal portion major diameter is less than or equal to the outer diameter **120** of the mid-portion **106**. Preferably, the ratio of the bending stiffness of the mid-portion **106** to the bending stiffness of the threaded distal portion **104** is in the range of 1.5:1 to 100:1. More preferably, the ratio is in the range of 2:1 to 20:1. For example, screws suitable for internal fixation of a clavicle fracture and that fall within these ranges may have a major diameter **114** in the range of 4-6.5 mm, a minor diameter **116** in the range of 2.5-3.5 and a cannulation **101** with a diameter in the range of 1-2 mm. Preferably, the screw **100** is made of a polymer.

Table 1 compares the calculated load required to bend a cantilevered tube of 3 mm outside diameter and 1.5 mm inside diameter around a radius of 50 mm and an arc length of 26 mm. The titanium and stainless steel alloys are predicted to have a required load approximately 10 times that of the PEEK and PLLA. These loads would be greater than the bone could withstand and a threaded device made of those materials would not follow a curved path in the bone but would instead cause the bone to fail. In the case of the highly cold worked stainless steel, even if the bone could withstand the load, the screw would fail since the minimum bend radius before failure of the screw is greater than 50 mm.

TABLE 1

Load at 50 mm bend radius						
Material	Yield Stress (MPa)	Failure Stress (MPa)	Yield Strain (%)	Failure Strain (%)	Flexural Modulus (MPa)	Load (N)
PEEK ASTM F2026	100	115	2.5%	20%	4	9.8
PLLA Ti—6Al—4V ELI ASTM F136	90	100	2.6%	25%	3.5	8.7
316LVM Stainless Steel ASTM F899	880	990	0.8%	14%	114	91.7
	1468	1696	0.7%	3%	197	Not possible

Another way to quantify the bending stiffness of the threaded distal portion **104** is by the amount of torque

required to turn the threaded distal portion **104** into a curved bone hole having a specified radius of curvature. For example, the threaded distal portion **104** preferably requires a torque less than 20 in-lbs to turn the distal threaded portion **104** into a bone to follow a curved path having a radius of curvature of 50 mm. More preferably the required torque is less than 10 in-lbs. More preferably the required torque is less than 5 in-lbs. More preferably the required torque is approximately 2 in-lbs.

Table 2 compares the measured torque required to advance a threaded tube 25 mm into a 50 mm threaded radius formed in a rigid test block. The tubes were all machined to the same geometry but of different materials. The thread major diameter was 4.25 mm, the minor diameter was 3.0 mm and the inner diameter of the tube was 1.5 mm. A rigid block was prepared having a curved, threaded path. Such a path has a pitch that is wider on the outside of the curve and a pitch that is narrower on the inside of the curve corresponding to the shape of the screw thread when it is curved. Multiple samples of each screw were inserted into the block over an arc length of 25 mm. The maximum torque for each revolution was measured and it was found that the torque increased for each revolution. In Table 2, the range is the range of torque values from the first to the last revolution. The average is the average of the torque values for all revolutions. The peak is the highest torque value and in all cases occurred in the last revolution. However, the torque values for each material were relatively constant over the last few revolutions. The titanium and stainless steel alloys had measured torque values approximately 10 times that of the PEEK. These tests were conducted using a threaded block made of tool steel with a strength greater than that of the materials being tested in order to compare the torque values. As pointed out relative to Table 1, the loads generated from the metal implants would be greater than the bone could withstand and a threaded device as described herein made of these metals would not follow a curved path in the bone but would instead cause the bone to fail.

TABLE 2

Torque to thread around rigid 50 mm radius			
Material	Range (in-lbs)	Average (in-lbs)	Peak (in-lbs)
PEEK ASTM F2026	0-2.0	1.4	2.0
Ti—6Al—4V ELI ASTM F136	0.7-25	16	25
316LVM Stainless Steel ASTM F899	0.5-20	13	20

In addition to bending stiffness advantages, having the threaded distal portion major diameter less than or equal to the outer diameter **120** of the mid-portion **106** allows the distal threaded portion **104** to pass through a passage in a bone that will be a sliding or press fit with the mid-portion **106**. A screw so configured, as shown in the illustrative example of FIGS. 1-4, can have an intramedullary canal filling mid-portion **106** providing solid support to a bone interface and a relatively bendable distal threaded portion **104** following a curved path such as for threading into a distal portion of a curved bone to secure the screw in the bone.

The proximal portion **108** may be identical to the mid-portion **106**. Alternatively, the proximal portion may have a positive driver engagement feature (not shown) such as

internal or external non-circular surfaces, profiles, or holes. For example, an internal or external slotted, threaded, triangular, square, hexagonal, hexalobular, or other drive feature may be provided. In addition, as shown in the illustrative example of FIGS. 1-4, the proximal portion 108 may include an optional external helical thread 122 able to engage a bone portion to provide proximal fixation of the screw. For example, the proximal thread 122 may have a major diameter 124, a minor diameter 126, and a pitch 130 wherein the proximal thread minor diameter 126 is equal to the mid-portion outer diameter 120. In the illustrative example of FIGS. 1-4, the mid-portion outer diameter 120 is equal to the proximal thread minor diameter 126 and the distal thread major diameter 114. The proximal portion may alternatively, or in addition, receive a locking member such as a pin or screw transverse to the longitudinal axis to lock a proximal bone portion to the nail. The locking member may be drilled through the proximal portion. Preferably, the proximal portion has one or more transverse holes formed through it for receiving the locking member.

The distal and proximal thread pitches 128, 130 may advantageously be the same or different depending on the application. For example, to stabilize a fracture, the screw 100 may be inserted into a bone across the fracture so that the distal thread 112 is engaged with bone distal to the fracture and the proximal thread 122 is engaged with bone proximal to the fracture. If the bone portions on either side of the fracture are reduced to a desired final position prior to inserting the screw 100, then it is advantageous for the thread pitches 128, 130 to be equal so that insertion of the screw does not change the relative positions of the bone portions. If on the other hand, it is desirable to move the bone portions relative to one another by the action of inserting the screw then it is advantageous for the pitches 128, 130 to be different. For example, to move the bone portions closer together to reduce the fracture, the distal thread pitch 128 may be made greater than the proximal thread pitch 130 so that with the distal thread 112 engaged distally and the proximal thread 122 engaged proximally, further advancing the screw causes the distal bone portion to move proximally relative to the screw faster than the proximal bone portion moves proximally and thus move the bone portions closer together. Alternatively, to move the bone portions further apart to distract the fracture, the distal thread pitch 128 may be made smaller than the proximal thread pitch 130 so that with the distal thread 112 engaged distally and the proximal thread 122 engaged proximally, further advancing the screw causes the distal bone portion to move proximally relative to the screw more slowly than the proximal bone portion moves proximally and thus move the bone portions further apart. Preferably, the bone screw 100 has a through bore, or cannulation 101, coaxial with the longitudinal axis 110 to permit the bone screw 100 to be inserted over a guide wire.

The bone screw 100 of FIGS. 1-4, may advantageously be provided in a set containing a plurality of bone screws as shown in the illustrative example of FIGS. 5-7. For example, it is advantageous in a surgical procedure to minimize the number of steps and the amount of time needed to complete the procedure. In a bone fixation procedure, a surgeon often makes an initial sizing decision based on medical imaging. During the procedure, it may become expedient to change the predetermined size based on observation of the surgical site or the fit of trial implants or instruments. For example, a surgeon may determine initially that a smaller bone screw is appropriate. However, during preparation of the site, the surgeon may determine that a larger screw will better grip

the bone or fill, for example, a canal in the bone. The illustrative set of bone screws shown in FIGS. 5-7 facilitates changing between sizes. Each screw 140, 150, 160 in the set has a minor diameter 142, 152, 162, a major diameter 144, 154, 164, and a pitch 146, 156, 166. The minor diameters 142, 152, 162 are equal to one another so that a single diameter drill will provide an initial bore hole appropriate for all the screws in the set. The pitches 146, 156, 166 are equal to one another so that all of the screws in the set will threadably engage a helical thread of the same pitch. The major diameters 144, 154, 164 may increase to provide progressively more bone purchase or, for example, to span increasing larger intramedullary canals. For example, with the set of screws of the illustrative example of FIGS. 5-7, a surgeon may drill a hole equal to the minor diameters 142, 152, 162 and then tap the hole with a tap corresponding to the thread of the smallest major diameter screw 140. The tactile feedback received by the surgeon as the tap is inserted will indicate to the surgeon if the thread major diameter is sufficient to provide a desired level of bone engagement. For example, the surgeon can feel if the tap is engaging the cortical walls of an intramedullary canal or if the tap is in softer cancellous bone. If the surgeon determines that greater engagement is desired, the surgeon can next tap the hole with a tap corresponding to the thread of the next larger major diameter screw 150. Since the minor diameters 142, 152, 162 and thread pitches 146, 156, 166 are the same for all of the screws in the set, the next tap will thread into the previously tapped hole and increase the bone thread major diameter without damaging the bone thread. Once the desired bone engagement is achieved, the surgeon may then insert the desired screw 140, 150, 160. If in tapping the larger major diameter thread, the surgeon determines that the bone is providing too much resistance, the surgeon may revert to the smaller sized screw since the threads are still compatible. Alternatively to using a separate tap, the screw threads may be configured as self-tapping so that the screws may be threaded directly into the bored hole.

In addition to the sizing advantages of having the same minor diameter 142, 152, 162 across a family of screws, it is also advantageous because the distal threaded portion of each screw will have a similar bending stiffness to each of the other screws 140, 150, 160 since the continuous wall of the minor diameter contributes much more to the bending stiffness than the helical thread itself. This similar bending stiffness means that they can be inserted around a similar bending radius with a similar torque.

In the illustrative example of FIGS. 5-7, each screw 140, 150, 160 has a mid-portion diameter 148, 158, 168 equal to the corresponding major diameter 144, 154, 164. The increasing mid-portion diameters provide progressively less flexible mid-portions across the set of screws and, for example, canal filling for increasingly larger bones if used in the intramedullary canal. If the screws incorporate the optional increasing mid-portion diameter as shown, then it is desirable to re-drill the mid-portion of the bone hole to accommodate the mid-portion when an increase in screw size is desired. However, the distal, threaded portion of the bone hole does not need to be re-drilled so the screw threads will not be damaged by drilling.

Alternatively to, or in addition to, the threaded distal portion 104 and mid-portion 106 having different sectional moduli, the threaded distal portion 104 and mid-portion 106 may have different material properties such as two different materials or different conditions of the same material to produce a difference in bending stiffness between them.

In the illustrative example of FIGS. 36-41, a screw 170 has separate first and second members 172, 174 permanently joined together. The first member 172 includes an elongate body 176 with a proximal end 178, a distal end 180, a longitudinal axis 182, and an axial through bore 184. The proximal end 178 of the first member includes a pair of transverse through bores 181, 183. Each transverse bore 181, 183 defines a longitudinal axis and the axes form an angle 185 between them about the longitudinal axis 182 as best seen in FIG. 39. Providing more than one transverse through bore increases options for attaching the screw to bone fragments and options for fixation direction. Both bores may be used for fixation or the one that is most conveniently located. Preferably the angle 185 is in the range of 0 to 90 degrees. More preferably the angle 185 is in the range of 20 to 90 degrees. In the illustrative example of FIGS. 36-41, the angle 185 is 45 degrees. The proximal end 178 also includes opposed flats 187 for engaging a driver in torque transmitting relationship. An internal thread 189 within the bore 184 is engageable with, e.g., a threaded draw bar to secure the first member to a driver.

The second member 174 includes an elongate body 186 with a proximal end 188, a distal end 190, a longitudinal axis 192, an external helical thread 194, and an axial through bore 196. The distal end 180 of the first member 172 and the proximal end 188 of the second member 174 may have complementary geometries to aid in joining them. In the illustrative example of FIGS. 36-41, the distal end 180 of the first member has a stepped conical taper and the proximal end 188 of the second member has a corresponding stepped conical socket 198. The mating surfaces may be any suitable shape as determined by the materials and joining technique including but not limited to plug and socket joints (as shown), scarf joints, butt joints, dovetail joints, finger joints, and lap joints. The joint may be reinforced with a third component such as an adhesive, pin, or key. The joint may be formed by mechanical interlock, chemical bonding, molding, welding or other suitable joining process. The final assembled screw 170, has a distal portion 191, a mid-portion 193, and a proximal portion 195 and may have the thread forms, diameters, and relationships as described relative to the examples of FIGS. 1-7.

The first and second components 172, 174 may be made of different materials or different conditions of the same material. For example, they may be made of polymers, metals, or ceramics. Metals may include stainless steel alloys, titanium, titanium alloys, cobalt-chromium steel alloys, nickel-titanium alloys, and/or others. Polymers may include nonresorbable polymers including polyolefins, polyesters, polyimides, polyamides, polyacrylates, poly(ketones), fluropolymers, siloxane based polymers, and/or others. Polymers may include resorbable polymers including polyesters (e.g. lactide and glycolide), polyanhydrides, poly(aminoacid) polymers (e.g. tyrosine based polymers), and/or others. Other possible materials include nonresorbable and resorbable ceramics (e.g. hydroxyapatite and calcium sulfate) or biocompatible glasses. They may be made of homogenous materials or reinforced materials. They may be made of crystallographically different materials such as annealed versus cold worked. It is preferable for the mid portion 193 to have a higher bending stiffness than the distal portion 191 and the distal portion should have a bending stiffness low enough for it to be inserted along a curved path in bone.

In a first example, the first component may be made of a metal with a relatively high degree of cold work and the second component of a metal with a relatively low amount

of cold work such as for example annealed and cold worked stainless steel. The components may be joined for example by welding. However, as discussed relative to Table 1, most metals are far too stiff to allow threading along a curved path in a bone within suitable torsional loads.

Preferably the distal portion is made of a polymer. In a second example, the first component is made of a metal, such as stainless steel or a titanium alloy, and the second component is made of a polymer such as polyetheretherketone (PEEK) or a polylactide polymer (e.g. PLLA). The components may be joined such as for example by threading them together.

Preferably both components are made of polymers. In a third example, the first and second components are both made of non-resorbable polymers. For example, the first component may be made of fiber reinforced PEEK (e.g. Invibio PEEK-Optima™ Ultra-Reinforced) and the second component may be made of neat (unreinforced) PEEK (e.g. Invibio PEEK-Optima™ Natural). The fiber reinforced PEEK is strong while the neat PEEK is relatively flexible allowing it to be easily threaded around a curved path even while having a relatively large bone filling diameter. The components may be joined, e.g. by molding the components as a continuous matrix with first component fiber reinforcement and second component neat polymer with polymer chains extending across the joint interface. In the example of FIGS. 36-41, the second component is relatively more transparent to laser radiation than the first component and the parts are joined by laser welding at the conical interface. The laser energy passes relatively easily through the second component and is absorbed by the first component so that localized heating at the conical interface takes place causing the polymer constituent of the two components to fuse together.

In a fourth example, the mid-portion and distal portion are made of resorbable polymers. For example, the mid-portion may be made of a glass fiber reinforced PLLA (e.g. Corbion-Purac FiberLive™) and the distal portion may be made of neat PLLA.

Alternatively, the first member 172 and second member 174 may form one continuous part with different properties between first and second portions. The difference in properties may be achieved, for example, by different processing (e.g. thermal processing) or blending materials. For example, different polymers may be combined in a single injection mold cavity and formed together. The polymers may be blended so that there is a transition between them. In another example, stiffening and/or strengthening material, e.g. fibers, whiskers, and/or granules, may be selectively incorporated in, e.g., the first portion.

FIGS. 42 and 43 illustrate an example of a screw 270 similar to that of FIGS. 36-41 except that the first member 272 is not cannulated, the first member 272 extends the full length of the second member 274, and the transverse holes 281, 283 are coplanar. The screw 270 may be assembled as with the prior example including by using complimentary screw threads in the proximal region of the second member 274 and mid portion of the first member 272 as indicated by reference number 250. The screw 270 of the example of FIGS. 42 and 43 may include any of the materials and features described relative to the prior examples. If, for example, the first member 272 is made of a radiographically more opaque material than the second member 274, then the first member will provide a radiographic marker over the entire length of the screw 270 that may be radiographically visualized during and after surgery to confirm screw placement. For example, a metal first component and polymer

second component would provide for radiographic visualization of the metal first component. It has been found by the present inventors that the bending stiffness of the distal end of the screw is not materially changed by eliminating the axial through bore of the first component and is essentially unchanged when the bending stiffness of a guide wire is accounted for which was optionally used with the previous cannulated screw examples. The guide wire is not necessary inasmuch as the screw 270 will follow a curved hole prepared to receive it. The transverse holes 181, 183 may be provided in any number or not at all as desired but it has been found that one is sufficient and two provides the user with additional fixation choice.

FIGS. 44 and 45 illustrate a bone implant 400 useful for stabilizing bone fractures according to one example of the invention. The bone implant 400 includes a body 402 defining a longitudinal axis 404 extending between a proximal end 406 and a distal end 408. The body has an elongate distal portion 410 having an outer surface 412 defining a screw thread 414 having a minor diameter 416 and a major diameter 418. The body has an elongate proximal portion 430 having a non-threaded outer surface 432. Passages 434 and 436 are each formed through the proximal portion 430 transverse to the longitudinal axis from a first opening 438, 440 on the surface of the proximal portion to a second opening 442, 444 on the surface of the proximal portion. A driver engaging feature is formed at the proximal end for engaging a driver in torque transmitting relationship. The driver engaging feature may be a male feature or a female feature. Preferably it is a polygonal feature engageable with a correspondingly shaped driver. In the example of FIGS. 44 and 45, the driver engaging feature is a hexagonal socket 446 formed in the proximal end of the implant. The socket 446 includes a threaded recess 448 for threaded engagement with other tools such as a driver retaining draw rod, a cross pinning guide, or the like. The distal portion is responsive to rotation of the implant to thread into a bone and advance the bone implant into the bone. This rotary advancement action is advantageous compared to typical bone nails that are impacted into the bone since the threaded advancement is less stressful to the bone and surrounding tissues. As the distal portion is threaded into the bone, it pulls the proximal portion into the bone. The distal threaded portion is anchored in the bone by the thread 414. The smooth proximal portion may be positioned to span a fracture so that, for example, no sharp edges are engaged with the fracture and no stress concentrating features that might weaken the implant span the fracture.

In the example of FIGS. 44 and 45, the proximal portion has a length 450 measured from the free proximal end 406 to the proximal start 452 of the threads of the distal portion. The proximal portion has a maximum diameter. For example for a conical or cylindrical proximal portion the maximum diameter is simply the largest diameter along the proximal portion. For an ovoid proximal portion, the maximum diameter would be the major diameter of the elliptical cross section. For other shapes, such as fluted proximal portions, the maximum diameter is the maximum dimension normal to the longitudinal axis 404 of the proximal portion. The maximum diameter is preferably constant over a portion of the proximal portion length to provide a uniform thickness for spanning a fracture. For example, the maximum diameter is preferably uniform over at least one-fourth of the proximal portion length; more preferably at least one-third; more preferably at least one-half; more preferably more than one-half. In the illustrative example of FIGS. 44 and 45, the proximal portion has a constant cylindrical diameter over its

entire length. The driver engaging feature preferably has a maximum dimension normal to the longitudinal axis that is less than or equal to the maximum diameter of the proximal portion so that, for example, the proximal end of the bone implant may be seated below the bone surface.

The bone implant may be a unitary construct, like shown in the illustrative example of FIGS. 1-4, in which the proximal and distal portions are formed of one continuous material. Optionally, the proximal and distal portions may be separate components joined together as shown in the example of FIG. 36 and the example of FIG. 42. In the illustrative example of FIGS. 44 and 45, the bone implant includes a sleeve 460 surrounding a separate core 462. The sleeve and core are joined together to form the body. Various methods may be used to join the sleeve and core. For example, they may be threaded, pinned, bonded, welded, or otherwise joined. In the example of FIGS. 44 and 45, the sleeve is threaded onto the core via an internal thread 464 and corresponding male thread 466 formed on the core. The sleeve is further pinned to the core with a pin 468 pressed through holes 470, 472 in the sleeve wall and in the core.

As described relative to previous examples, it is desirable for the distal portion to have a lower bending resistance than the proximal portion. In one example, the sleeve is at least partially formed of a polymer and the core is at least partially formed of a metal. In the example of FIGS. 44 and 45, the sleeve is machined from a polymer and includes the distal screw thread while the core is machined from a metal and includes the proximal portion. In one example, the core is made of a biocompatible titanium alloy and the sleeve is made of a biocompatible polyaryletherketone polymer such as, for example, polyetheretherketone. In another example, the core is made of a suitable biocompatible metal and the sleeve is made of a resorbable polymer so that, over time, the sleeve will resorb in the patient's body and allow gradually increasing motion of the bone and load transfer to the bone to promote healing. The core may extend partway toward the distal end as in the example of FIG. 36, all the way to the distal end as in the example of FIG. 42, or it may extend past the distal end as in the example of FIGS. 44 and 45. With the tip 480 of the core extending beyond the distal end, the tip 480 provides an easier start of the implant into a hole in the bone and, as shown in the example of FIGS. 44 and 45, the tip 480 provides a smooth bearing surface for following a curved path in a bone.

FIGS. 46 and 47 illustrate a bone implant 500 similar to that of FIGS. 44 and 45. The bone implant 500 includes a core 502 and a sleeve 504. In the example of FIGS. 44 and 45, the smooth proximal portion 506 is more evenly proportioned over the core and sleeve. Also, the core steps up more gradually in diameter from the distal end 508 to the proximal end 510 resulting in a more gradual transition in bending stiffness over three zones. In a first zone 512, a relatively thin portion of the core is surrounded by a relatively thick portion of the sleeve. In a second zone 514, a relatively thicker portion of the core is surrounded by a relatively thinner portion of the sleeve. In a third zone 516, only a relatively thicker portion of the core remains. Also, in the example of FIGS. 46 and 47 a slip resisting feature is provided on the core and a polymer sleeve is molded to the core so that the polymer and slip resisting feature interdigitate. The slip resisting feature may be knurling, threads, grooves, splines, spikes, holes, or other features. The slip resisting feature may be oriented to enhance torque transfer, longitudinal force transfer, or otherwise oriented. In the example of FIGS. 46 and 47, the slip resisting feature includes longitudinal splines 518 to enhance the ability to

11

transfer torque between the core and sleeve. Longitudinal force transfer is sufficiently accommodated by the bonding of the sleeve to the core during the molding process.

In use, the preceding implants may be provided in an appropriate size and inserted into a bone to span a fracture in the bone. Preferably the proximal portion of the implant spans the fracture. The arrangement of a smooth proximal portion and a threaded distal portion permits rotating the bone implant to cause the threaded distal portion to engage the bone and pull the proximal portion of the bone implant into a positioning spanning the fracture. In the case of an implant comprising a resorbable polymer, the polymer will resorb over time in the patient to gradually transfer load to and permit motion of the bone to enhance healing of the fracture. One or more pins or screws may be inserted so that they extend through one or more of the passages in the proximal end, for example the proximal passages **434**, **436** in the example of FIGS. **44-45**, and through a portion of the bone to fix the bone to the proximal portion of the implant. For example with the distal end of the bone implant fixed by engagement of the threads in a distal portion of the bone a proximal portion of the bone may be secured with pins or screws as described. This may be used to hold compression or distraction on bone portions on opposing sides of the fracture or to attach loose bone fragments.

FIGS. **8-10** illustrate an implant being inserted into first and second bone portions **200**, **202** having a bone interface **204** between them. The implant could be any of the examples of FIGS. **1**, **36**, **42**, **44**, and **46** and the variations described herein. In the particular example of FIGS. **8-10**, bone screw **100** is shown. A first or proximal bore **206** is formed in the first bone portion **200**, across the bone interface **204**, and into the second bone portion **202**. A second or distal bore **208** extends distally from the proximal bore **206** defining a curved path **210**. The screw **100** is advanced through the proximal bore **206** until the distal screw threads engage the distal bore **208** as shown in FIG. **9**. Further advancing the screw **100** causes it to bend to follow the curved path **210** as shown in FIG. **10**. Having a straight portion of the path, and thus the straight mid portion of the screw **100**, spanning the bone interface results in a zero stress and strain state at the bone interface which prevents separation of the bone portions **200**, **202** at the interface **204**.

FIGS. **11-35** depict an illustrative method of using an implant to fix a fractured clavicle. The implant could be any of the examples of FIGS. **1**, **36**, **42**, **44**, and **46** and the variations described herein. In the particular example of FIGS. **11-35**, bone screw **100** is shown. A patient is placed in a beach chair position with the head rotated away from the operative side. A bolster is placed between the shoulder blades and head allowing the injured shoulder girdle to retract posteriorly. A C-arm is positioned to enable anterior-posterior (AP) and cephalic views of the operative site. A 2-3 cm incision **300** is made at the fracture site along Langer's Lines running perpendicular to the long axis of the clavicle to expose the fracture site (FIG. **10**). The platysma muscle is freed from the skin and split between its fibers. The middle branch of the supraclavicular nerve is identified and retracted.

The medial end **302** of the lateral fragment **304** of the fractured clavicle is elevated from the fracture site incision (FIG. **12**).

A K-wire **306**, e.g. a 1.4 mm K-wire, is drilled into the canal of the lateral fragment **304** and advanced through the dorsolateral cortex **308** and out through the skin (FIG. **13**).

12

A wire driver is attached to the lateral portion of the K-wire and used to back the wire out until it is lateral to the fracture **310** (FIG. **14**). Bone clamps are used at the incision site to reduce the fracture and clamp the bone fragments in position. Proper reduction is confirmed with AP and cephalic radiographic views.

The K-wire **306** is advanced until it is preferably at least 20 mm medial to the fracture (FIG. **15**).

A first dilator **312**, e.g. a 3.2 mm dilator, is placed over the K-wire and advanced until it contacts the bone (FIGS. **16-17**).

A second dilator **314**, e.g. a 4.5 mm dilator, is placed over the first dilator **312** and advanced until it contacts the bone (FIG. **18**).

A drill guide **316** is placed over the second dilator **314** and advanced until it contacts the bone (FIG. **19**).

The first dilator **312** is removed and a first lateral drill **318**, corresponding to the minor diameter of the distal screw threads, e.g. a 3.2 mm drill, is advanced over the K-wire into the bone, preferably at least 20 mm medial to the fracture. A drill depth mark readable adjacent the drill guide may be noted as a reference for implant sizing (FIG. **20**).

The K-wire is removed and replaced with a flexible guide wire **320**, e.g. a nitinol guide wire, sized to fit within the screw cannulation, e.g. a 1.4 mm guide wire. The flexible guide wire **320** is advanced through the first lateral drill and further along the intramedullary canal of the medial bone fragment and will curve to follow the intramedullary canal to define a curved path in the bone. Preferably, the guide wire is advanced approximately 30 mm medial to the tip of the first lateral drill **318** (FIG. **21**).

The first lateral drill **318** is removed and a flexible shaft reamer **322**, corresponding to the minor diameter of the distal screw threads, is guided over the flexible guide wire **320** to ream the medial portion of the curved path (FIG. **22**). The flexible reamer **322** and second dilator **314** are then removed.

A second lateral drill **324**, having a diameter corresponding to the diameter of the mid-portion of the screw, e.g. a 4.5 mm drill, is guided over the flexible guide wire to enlarge the bone hole laterally to receive the mid-portion and proximal portion of the screw **100**. The second lateral drill **324** is advanced the same distance as the first lateral drill (FIG. **23**). The drilling step may be monitored in A/P and cephalic views with the C-arm to avoid perforating the bone cortex as the second lateral drill **324** is advanced into the medial bone fragment **326**.

A flexible tap **328**, having cutting threads corresponding to the distal threads of the screw **100** is guided over the flexible guide wire to cut threads into the medial bone fragment along the curved path (FIG. **24**). The tap may serve as a trial implant and provides tactile feedback regarding the fit of the implant in the bone. If it is determined that a larger screw is desirable, subsequent larger second drills may be used to re-drill the lateral straight portion and subsequent larger flexible taps may be used to increase the distal thread major diameter without having to re-ream the medial curved portion of the bone hole. Once a desired level of thread purchase and canal filling are achieved, a depth mark readable adjacent the drill guide may be noted as a reference for the required implant length. If a screw **100** with a proximal threaded portion is used, a lateral tap may be used to tap the lateral bone fragment to receive the proximal threads.

The screw **100** is attached to an inserter **330** and guided over the flexible guide wire until it is fully seated in the prepared threads in the medial bone fragment (FIGS. **25** and

13

26). Optionally, the screw **100** may be axially driven with a mallet through the lateral bone fragment until just short of the distal thread engagement. The screw **100** may then be threaded into full engagement with the prepared threads in the medial fragment. Radiographic visualization may be used to ensure that the fracture is fully reduced and anatomically aligned in length and rotation.

If a proximally threaded screw has not been used, or if additional fixation is otherwise desired, cross fixation may be used. For example, a cross fixation guide **340** may be engaged with the implant inserter **330** (FIG. 27). The cross fixation guide may include a knob **342** that threadingly engages the implant inserter **330** and a cross fixation guide sleeve **344** that abuts the lateral bone fragment adjacent the bone hole entrance. Rotating the knob **342** moves the cross fixation guide sleeve **344** and implant inserter **330** axially relative to one another. With the cross fixation guide sleeve **344** abutting the lateral bone fragment **304**, the implant inserter, implant, and medial bone fragment **326** will be drawn laterally and the lateral bone fragment **304** will be pressed medially to apply compression across the fracture.

Inner and outer drill sleeves **346**, **348** are advanced through the guide **340** until they abut the bone (FIG. 28). In the case of a screw such as the examples of FIGS. 36, 42, 44 and 46 having one or more preformed transverse bores, the cross fixation guide may have one or more targeting holes positioned to align with the one or more transverse bores. In the case of a screw such as the example of FIG. 1 not having preformed transverse bores, cross fixation may be inserted directly through the screw **100** forming a transverse bore intraoperatively.

For example, a cross fixation wire **350** may be guided through the drill sleeves, through the near cortex, through the mid or proximal portions of the screw, and into the far cortex of the lateral bone fragment (FIG. 29). If wire cross fixation is adequate, the cross fixation guide may be removed and the wire may be trimmed flush with the bone surface.

However, if screw cross fixation is desired, a screw depth gauge **352** may be placed over the cross fixation wire to measure the projecting portion of the guide wire to determine the required screw length for bi-cortical fixation (FIG. 30).

A countersink tool **354** may be used to create a countersink for a cross fixation bone screw **356** (FIG. 31).

The appropriate length cross fixation screw **356** may then be guided over the cross fixation wire **350** and seated into the bone (FIG. 32). These steps may be repeated to place additional screws if desired.

FIGS. 33 and 34 illustrate the location of the screw **100** and cross fixation screws **356** relative to the lateral and medial bone fragments.

FIG. 35 illustrates the cross fixation screws **356** in the screw **100** without the bone to obscure the view. Preferably the screw **100** is made of a relatively soft material, e.g. a polymer, that facilitates arbitrary placement of the cross fixation screws at any desired location.

Various examples have been presented to aid in illustrating the invention. These various examples are illustrative but not comprehensive and variations may be made within the scope of the invention. For example, the various features described relative to each example may be interchanged among the examples.

What is claimed is:

1. A bone screw for stabilizing bone fractures, the bone screw comprising:

14

a body defining a longitudinal axis extending between a proximal end and a distal end;
an elongate proximal portion of the body comprising a first material; and

an elongate distal portion of the body comprising a second material different from the first material such that a material composition of the body varies along a length of the body, the elongate distal portion having an outer surface defining a helical distal screw thread formed on a threaded distal portion, wherein the threaded distal portion is formed entirely of the second material, the helical distal screw thread having a minor diameter and a major diameter, wherein the second material has a lower stiffness than the first material, and

wherein a part of the body that is proximal to the helical distal screw thread has a diameter that is greater than the minor diameter of the helical distal screw thread.

2. The bone screw of claim 1 further comprising a passage formed through the elongate proximal portion transverse to the longitudinal axis from a first opening on an outer surface of the elongate proximal portion to a second opening on the outer surface of the elongate proximal portion.

3. The bone screw of claim 1 wherein the body comprises a sleeve surrounding a separate core, the sleeve and core being joined together to form the body.

4. The bone screw of claim 3 wherein the helical distal screw thread is formed on the sleeve.

5. The bone screw of claim 4 wherein the elongate proximal portion comprises the core extending proximally from the sleeve.

6. The bone screw of claim 4 wherein the sleeve comprises a polymeric material, the helical distal screw thread being formed in the polymeric material of the helical distal screw thread.

7. The bone screw of claim 6 wherein the core comprises a metal.

8. The bone screw of claim 6 wherein the sleeve comprises a resorbable polymer.

9. The bone screw of claim 8 wherein the core comprises a reinforced polymer.

10. The bone screw of claim 6 wherein the core comprises a slip resisting feature formed on a surface of the core and the sleeve is molded onto the core so that the polymeric material and slip resisting feature interdigitate.

11. The bone screw of claim 6 wherein the polymeric material comprises polyetheretherketone and the core comprises titanium.

12. The bone screw of claim 3 wherein the sleeve is pinned to the core.

13. The bone screw of claim 3 wherein the sleeve is threaded onto the core.

14. A bone screw for stabilizing bone fractures, the bone screw comprising:

a body defining a longitudinal axis extending between a proximal end and a distal end;
an elongate proximal portion of the body comprising a first material; and

an elongate distal portion of the body comprising a second material such that the elongate distal portion of the body has a second bending stiffness less than half of a first bending stiffness of the elongate proximal portion, the elongate distal portion having an outer surface defining a helical distal screw thread formed on a threaded distal portion, wherein the threaded distal portion is formed entirely of the second material, the helical distal screw thread having a minor diameter and

15

a major diameter, and wherein the helical distal screw thread has a length, along the longitudinal axis, at least twice its minor diameter.

15. The bone screw of claim 14 further comprising a passage formed through the elongate proximal portion transverse to the longitudinal axis from a first opening on an outer surface of the elongate proximal portion to a second opening on the outer surface of the elongate proximal portion.

16. The bone screw of claim 14 wherein the body comprises a sleeve surrounding a separate core, the sleeve and core being joined together to form the body.

17. The bone screw of claim 16, wherein the core is formed of the first material; the sleeve is formed of the second material; the first material comprises titanium; and the second material comprises polyetheretherketone.

18. The bone screw of claim 17, wherein the sleeve is secured to the core via at least one selection from the group consisting of:

a pin passing through aligned holes in the sleeve and the core; and sleeve threads of the sleeve that engage core threads of the core.

19. A bone screw for stabilizing bone fractures, the bone screw comprising:

a body defining a longitudinal axis extending between a proximal end and a distal end;

an elongate proximal portion of the body comprising a first material comprising a metal; and

an elongate distal portion of the body comprising a second material comprising a polymer, the elongate distal portion having an outer surface defining a helical distal screw thread formed on a threaded distal portion, wherein the threaded distal portion is formed entirely of the second material, the helical distal screw thread having a minor diameter and a major diameter;

16

wherein the first material is not present in the elongate distal portion, or is present in the elongate distal portion with a second thickness, perpendicular to the longitudinal axis, that is less than a first thickness, perpendicular to the longitudinal axis, of the first material within the elongate proximal portion, and

wherein a part of the body that is proximal to the helical distal screw thread has a diameter that is greater than the minor diameter of the helical distal screw thread.

20. The bone screw of claim 19 wherein:

the body comprises a sleeve surrounding a separate core, the sleeve and core being joined together to form the body;

the core is formed of the first material;

the sleeve is formed of the second material;

the helical distal screw thread is formed on the sleeve; and the elongate proximal portion comprises the core extending proximally from the sleeve.

21. A bone screw for stabilizing bone fractures, the bone screw consisting essentially of:

a body defining a longitudinal axis extending between an elongate proximal portion and an elongate distal portion, the body comprising:

a core, formed of a metal, extending at least through the elongate proximal portion; and

a sleeve, formed of a polymer, surrounding and immovably joined to the core and extending through the elongate proximal portion and the elongate distal portion;

wherein:

the elongate distal portion comprises an outer surface defining a helical distal screw thread; and

the elongate distal portion is sufficiently flexible to bend in response to insertion of the distal end into a curved portion of a hole in human bone.

* * * * *