



US010221085B2

(12) **United States Patent**
Hwang et al.

(10) **Patent No.:** **US 10,221,085 B2**
(45) **Date of Patent:** **Mar. 5, 2019**

(54) **APPARATUS AND METHODS FOR PROCESSING MOLTEN MATERIAL**

(71) Applicant: **Corning Incorporated**, Corning, NY (US)

(72) Inventors: **Jaesoo Hwang**, Asan-si (KR);
Jaeyoung Kim, Asan-si (KR);
Bonhyoung Koo, Yongin-si (KR)

(73) Assignee: **CORNING INCORPORATED**,
Corning, NY (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **15/481,790**

(22) Filed: **Apr. 7, 2017**

(65) **Prior Publication Data**

US 2017/0210659 A1 Jul. 27, 2017

Related U.S. Application Data

(62) Division of application No. 14/684,924, filed on Apr. 13, 2015, now Pat. No. 9,586,846.

(51) **Int. Cl.**

C03B 5/23 (2006.01)

C03B 5/04 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **C03B 5/23** (2013.01); **C03B 5/04** (2013.01); **C03B 5/16** (2013.01); **C03B 5/167** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC F15D 1/0005; F15D 1/04; Y10S 165/161; Y10S 165/409; Y10S 165/412; Y10S 165/416

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,893,061 A 2/1933 Peiler
3,805,072 A 4/1974 Goerens et al.

(Continued)

FOREIGN PATENT DOCUMENTS

JP 2003054955 2/2003

OTHER PUBLICATIONS

Arya Alborz, "Heat Exchangers", http://aryaalborz.com/projects_HeatExchangers.html, per WaybackMachine available Aug. 27, 2014.

(Continued)


Primary Examiner — Lisa L Herring

(74) *Attorney, Agent, or Firm* — Kevin M. Able

(57) **ABSTRACT**

Methods of processing molten material comprising the step (I) of flowing molten material through an interior of a conduit from a first station to a second station of a glass manufacturing apparatus and the step (II) of cooling the molten material within the interior of the conduit by passing a cooling fluid along an exterior of the conduit. The method further includes the step (III) of directing a travel path of the cooling fluid toward a vertical plane passing through the conduit. In further examples, a glass manufacturing apparatus comprises a first station, a second station, and a conduit configured to provide a travel path for molten material traveling from the first station to the second station. The glass manufacturing apparatus further comprises at least one baffle configured to direct a travel path of cooling fluid toward a vertical plane passing through the conduit.

29 Claims, 5 Drawing Sheets



(51)	Int. Cl.		8,127,572 B2	3/2012	Dorfeld et al.
	<i>C03B 5/16</i>	(2006.01)	8,683,827 B2	4/2014	De Angelis et al.
	<i>C03B 5/43</i>	(2006.01)	8,695,378 B2	4/2014	Thomas
	<i>C03B 5/44</i>	(2006.01)	8,720,225 B2	5/2014	Pitbladdo
	<i>C03B 5/167</i>	(2006.01)	2007/0149380 A1	6/2007	Dorfeld et al.
	<i>C03B 7/06</i>	(2006.01)	2008/0190593 A1*	8/2008	Wang F28D 7/1607
	<i>C03B 17/06</i>	(2006.01)			165/159
(52)	U.S. Cl.		2010/0192633 A1	8/2010	DeAngelis et al.
	CPC	<i>C03B 5/43</i> (2013.01); <i>C03B 5/44</i>	2011/0094720 A1	4/2011	Wang et al.
		(2013.01); <i>C03B 7/06</i> (2013.01); <i>C03B 17/064</i>	2014/0123710 A1	5/2014	Lineman et al.
		(2013.01)	2014/0144183 A1	5/2014	Demirbas et al.

OTHER PUBLICATIONS

(56) **References Cited**
U.S. PATENT DOCUMENTS
7,454,925 B2 11/2008 DeAngelis et al.

International Search Report and Written Opinion PCT/US2016/026901 dated Jul. 11, 2016.

* cited by examiner




FIG. 1




FIG. 2




FIG. 5

APPARATUS AND METHODS FOR PROCESSING MOLTEN MATERIAL

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a divisional of U.S. patent application Ser. No. 14/684,924, filed on Apr. 13, 2015, the content of which is relied upon and incorporated herein by reference in its entirety and the benefit of priority under 35 U.S.C. § 120 is hereby claimed.

FIELD

The present disclosure relates generally to apparatus and methods of processing molten material and, more particularly, to apparatus and methods of processing molten material flowing through an interior of a conduit.

BACKGROUND

It is known to manufacture glass ribbon from molten material. Typically, molten material is processed with a glass manufacturing apparatus including several stations arranged in series. In some examples, a pair of stations are joined with a conduit providing a travel path for molten material traveling from a first station to a second station.

SUMMARY

The following presents a simplified summary of the disclosure in order to provide a basic understanding of some example aspects described in the detailed description.

In accordance with a first aspect, a method of processing molten material comprises the step (I) of flowing molten material through an interior of a conduit from a first station to a second station of a glass manufacturing apparatus. The method further includes the step (II) of cooling the molten material within the interior of the conduit by passing a cooling fluid along an exterior of the conduit. The method still further includes the step (III) of directing a travel path of the cooling fluid toward a vertical plane passing through the conduit.

In one example of the first aspect at least one baffle directs the travel path of the cooling fluid during step (III).

In another example of the first aspect, the at least one baffle includes a first baffle, and step (III) includes directing a first portion of the travel path of the cooling fluid from a first lateral side portion of the conduit toward the vertical plane with the first baffle. In another example, the at least one baffle further includes a second baffle, and step (III) further includes directing a second portion of the travel path of the cooling fluid from a second lateral side portion of the conduit toward the vertical plane with the second baffle.

In yet another example of the first aspect, the at least one baffle includes a deflection panel extending at an angle relative to a travel path of the molten material flowing through the interior of the conduit, and step (III) includes directing the travel path of the cooling fluid with the deflection panel of the baffle. In another example, the at least one baffle further includes a shroud at least partially extending over a top portion of the conduit, and step (III) includes routing the travel path of the cooling fluid with the shroud to be directed by the deflection panel.

In another example of the first aspect, step (III) further directs the travel path of the cooling fluid over a top portion of the conduit.

In still another example of the first aspect, the vertical plane bisects the conduit.

In yet another example of the first aspect, the cooling fluid travels in a direction from the second station toward the first station.

In a further example of the first aspect, the cooling fluid may be substantially free from oxygen. In one example, the cooling fluid comprises nitrogen.

The first aspect can be provided alone or in combination with one or any combination of the examples of the first aspect discussed above.

In accordance with a second aspect, a glass manufacturing apparatus comprises a first station, a second station, and a conduit configured to provide a travel path for molten material traveling from the first station to the second station. The glass manufacturing apparatus further comprises at least one baffle configured to direct a travel path of cooling fluid toward a vertical plane passing through the conduit.

In one example of the second aspect, the first station comprises a mixing chamber.

In another example of the second aspect, the second station comprises a delivery vessel.

In still another example of the second aspect, the at least one baffle includes a deflection panel extending at an angle relative to the travel path provided by the conduit. In one example, an outer end of the deflection panel may be laterally positioned outside the travel path for the molten material. In another example, the deflection panel includes a concave inner surface facing toward the vertical plane.

In another example of the second aspect, the at least one baffle includes a shroud at least partially extending over a top portion of the conduit. In one example, the at least one baffle further includes a deflection panel extending away from the shroud at an angle relative to the travel path of the conduit.

In still another example of the second aspect, the at least one baffle includes a first baffle including a first deflection panel extending at a first angle relative to the travel path provided by the conduit and a second baffle including a second deflection panel extending at a second angle relative to the travel path provided by the conduit, wherein the first deflection panel and the second deflection panel converge toward one another.

The second aspect can be provided alone or in combination with one or any combination of examples of the second aspect discussed above.

It is to be understood that both the foregoing general description and the following detailed description present embodiments of the present disclosure, and are intended to provide an overview or framework for understanding the nature and character of the embodiments as they are described and claimed. The accompanying drawings are included to provide a further understanding of the embodiments, and are incorporated into and constitute a part of this specification. The drawings illustrate various embodiments of the disclosure, and together with the description serve to explain the principles and operations thereof.

BRIEF DESCRIPTION OF THE DRAWINGS

These and other features, aspects and advantages of the present disclosure are better understood when the following detailed description is read with reference to the accompanying drawings, in which:

FIG. 1 schematically illustrates an example glass manufacturing apparatus;

3

FIG. 2 illustrates a cross-sectional perspective view of the glass manufacturing apparatus along line 2-2 of FIG. 1;

FIG. 3 is a schematic perspective view illustrating a travel path of cooling fluid being directed toward a vertical plane through a conduit;

FIG. 4 schematically illustrates a top view of FIG. 3; and

FIG. 5 illustrates an example baffle configured to direct the travel path of the cooling fluid.

DETAILED DESCRIPTION

Apparatus and methods will now be described more fully hereinafter with reference to the accompanying drawings in which example embodiments of the disclosure are shown. Whenever possible, the same reference numerals are used throughout the drawings to refer to the same or like parts. However, the claims may be embodied in many different forms and should not be construed as limited to the embodiments set forth herein.

Glass sheets produced by apparatus and methods of the present disclosure are commonly used, for example, in display applications, for example liquid crystal displays (LCDs), electrophoretic displays (EPD), organic light emitting diode displays (OLEDs), plasma display panels (PDPs), or the like. In some examples, glass sheets may be separated from a glass ribbon produced by a glass manufacturing apparatus.

In some embodiments, the glass manufacturing apparatus can comprise a slot draw apparatus, float bath apparatus, down-draw apparatus, up-draw apparatus, press-rolling apparatus or other glass manufacturing apparatus as are generally known in the art. By way of example, FIG. 1 schematically illustrates a glass manufacturing apparatus 101 for processing a quantity of molten material for fusion drawing a glass ribbon 103 for subsequent processing into glass sheets 104. The glass manufacturing apparatus 101 can include one or more features shown in FIG. 1. For instance, the glass manufacturing apparatus 101 (e.g., the illustrated fusion down-draw apparatus) can include one or any plurality of the illustrated stations (e.g., a melting vessel 105, a fining vessel 127, a mixing chamber 131, a delivery vessel 133 and a forming vessel 143) and/or features associated with the stations. For example, as shown in FIG. 1, the glass manufacturing apparatus 101 can include all of the illustrated stations arranged in series wherein molten material may sequentially travel through the stations to produce the glass ribbon 103 from the molten material 121.

The melting vessel 105 may be configured to receive batch material 107 from a storage bin 109. The batch material 107 can be introduced by a batch delivery device 111 powered by a motor 113 to introduce a desired amount of batch material 107 into the melting vessel 105, as indicated by arrow 117. The melting vessel 105 may then melt the batch material 107 into the molten material 121.

The fusion draw apparatus 101 can also include the fining vessel 127 that can be located downstream from the melting vessel 105 and coupled to the melting vessel 105 by way of a first conduit 129. In some examples, the molten material 121 may be gravity fed from the melting vessel 105 to the fining vessel 127 by way of the first conduit 129. For instance, gravity may act to drive the molten material 121 to pass through an interior of the first conduit 129 from the melting vessel 105 to the fining vessel 127. Within the fining vessel 127, bubbles may be removed from the molten material 121 by various techniques.

The fusion draw apparatus can further include the mixing chamber 131 that may be located downstream from the

4

fining vessel 127. The mixing chamber 131 can be used to provide a homogeneous molten material composition, thereby reducing or eliminating cords of inhomogeneity that may otherwise exist within the fined molten material exiting the fining vessel. As shown, the fining vessel 127 may be coupled to the mixing chamber 131 by way of a second conduit 135. In some examples, the molten material 121 may be gravity fed from the fining vessel 127 to the mixing chamber 131 by way of the second conduit 135. For instance, gravity may act to drive the molten material 121 to pass through an interior of the second conduit 135 from the fining vessel 127 to the mixing chamber 131.

The fusion draw apparatus can further include the delivery vessel 133 that may be located downstream from the mixing chamber 131. The delivery vessel 133 may condition the molten material 121 to be fed into a forming device. For instance, the delivery vessel 133 can act as an accumulator and/or flow controller to adjust and provide a consistent flow of molten material 121 to the forming vessel 143. As shown, the mixing chamber 131 may be coupled to the delivery vessel 133 by way of a third conduit 137. In some examples, molten material 121 may be gravity fed from the mixing chamber 131 to the delivery vessel 133 by way of the third conduit 137. For instance, gravity may act to drive the molten material 121 to pass through an interior of the third conduit 137 from the mixing chamber 131 to the delivery vessel 133.

As further illustrated, a downcomer 139 can be positioned to deliver the molten material 121 from the delivery vessel 133 to an inlet 141 of the forming vessel 143 of a fusion draw machine 140. As discussed more fully below, the fusion draw machine 140 may be configured to draw the molten material 121 into a glass ribbon 103.

The conduits (e.g., the first conduit 129, the second conduit 135, and the third conduit 137) of the glass manufacturing apparatus 101 can include an interior surface comprising a wide variety of shapes. For instance, a cross-sectional profile shape of the interior surface taken perpendicular to a travel path provided for the molten material can comprise a circular shape or a non-circular shape (e.g., an oblong shape, an elliptical shape or other shape configuration). In some examples, the same or geometrically similar cross-sectional profile shape may exist along a length of the conduit. In other examples, geometrically different cross-sectional profile shapes may exist along a length of the conduit. Providing the conduit with a cross-sectional profile shape that is non-circular can increase the efficiency of transferring heat from the molten glass in the conduit by providing a greater surface area to the conduit.

The melting vessel 105 and the forming vessel 143 are typically made from a refractory material, for example refractory (e.g. ceramic) brick. The glass manufacturing apparatus 101 may further include components that are typically made from platinum or platinum-containing metals for example platinum-rhodium, platinum-iridium and combinations thereof, but which may also comprise such refractory metals for example molybdenum, palladium, rhenium, tantalum, titanium, tungsten, ruthenium, osmium, zirconium, and alloys thereof and/or zirconium dioxide. The platinum-containing components can include one or more of the first conduit 129, the fining vessel 127, the second conduit 135, the mixing chamber 131, the third conduit 137, the delivery vessel 133, the downcomer 139 and the inlet 141.

FIG. 2 is a cross-sectional perspective view of the glass manufacturing apparatus 101 along line 2-2 of FIG. 1. As shown, the forming vessel 143 includes a forming wedge

5

201 comprising a pair of downwardly inclined forming surface portions **203**, **205** extending between opposed ends of the forming wedge **201**. The pair of downwardly inclined forming surface portions **203**, **205** converge along a draw direction **207** to form a root **209**. A draw plane **211** extends through the root **209** wherein the glass ribbon **103** may be drawn in the draw direction **207** along the draw plane **211**. As shown, the draw plane **211** can bisect the root **209** although the draw plane **211** may extend at other orientations with respect to the root **209**.

Referring to FIG. 2, in one example, the molten material **121** can flow into a trough **200** of the forming vessel **143**. The molten material **121** can then simultaneously flow over corresponding weirs **202a**, **202b** and downward over the outer surfaces **204a**, **204b** of the corresponding weirs **202a**, **202b**. Respective streams of molten material then flow along the downwardly inclined forming surface portions **203**, **205** to the root **209** of the forming vessel **143**, where the flows converge and fuse into the glass ribbon **103**. The glass ribbon **103** may then be drawn off the root **209** in the draw plane **211** along draw direction **207**.

As shown in FIG. 2, the glass ribbon **103** can be drawn from the root **209** with a first major surface **213** and a second major surface **215**. As shown, the first major surface **213** and the second major surface **215** face opposite directions with a thickness **217** defined between the first major surface **213** and the second major surface **215**. Although aspects of the disclosure may be beneficial to produce many alternative thicknesses (e.g., including thicknesses of greater than 1 mm or less than 50 μm , including all ranges and sub-ranges therebetween), in some examples, the thickness **217**, for example a thickness at a central portion of glass ribbon **103**, can be less than or equal to about 1 mm, for example, from about 50 μm to about 750 μm , for example from about 100 μm to about 700 μm , for example from about 200 μm to about 600 μm , for example from about 300 μm to about 500 μm .

In one example, glass ribbon **103** drawn off the root **209** may be separated into individual glass sheets **104** with a glass separation apparatus **145**. Alternatively, although not shown, the glass ribbon may be passed through further processing stations and/or may be stored as a roll of glass ribbon rather than being immediately separated into individual glass sheets **104**.

In some examples, there may be a desire to cool molten material traveling within one or more of the conduits (e.g., the first conduit **129**, second conduit **135**, third conduit **137**, etc.) between adjacent stations (e.g., the melting vessel **105**, the fining vessel **127**, the mixing chamber **131**, the delivery vessel **133** and the forming vessel **143**) of the glass manufacturing apparatus **101**. Discussion of cooling will be described with respect to the third conduit **137** extending between a first station (e.g., the mixing chamber **131**) and a second station (e.g., the delivery vessel **133**) of the glass manufacturing apparatus **101**. Although not shown, the concepts of the disclosure may be applied to any of the other illustrated conduits (e.g., the first conduit **129**, the second conduit **135**) or any other conduit in other example glass manufacturing apparatus. Moreover, the illustrated stations are only one example configuration wherein the stations are arranged in series with the fining vessel **127** positioned downstream from the melting vessel **105**, the mixing chamber **131** positioned downstream from the fining vessel **127**, the delivery vessel **133** positioned downstream from the mixing chamber **131**, and the forming vessel **143** positioned downstream from the delivery vessel **133**. In some examples, more or less stations may be provided and/or the

6

stations may be arranged in a different order wherein concepts of the disclosure may be applied to cool molten glass within a conduit providing a travel path for molten material traveling between stations in the series of stations.

Turning to FIG. 3, by way of example, the glass manufacturing apparatus **101** includes a first station that may comprise the illustrated mixing chamber **131**. The glass manufacturing apparatus **101** may further include a second station that may comprise the illustrated delivery vessel **133**. The glass manufacturing apparatus still further includes the third conduit **137**. As illustrated schematically in FIG. 3, the third conduit **137** can be configured to provide a travel path **301** for the molten material **121** traveling in a direction **315** from the first station to the second station.

There may be a desire to lower the temperature of the molten material **121** from a relatively high temperature in the mixing chamber **131** to a relatively low temperature in the delivery vessel **133**. Lowering the temperature of the molten material **121** can be desirable to provide a desired molten material property (e.g., viscosity) for processing the molten material **121** into the glass ribbon **103** with the fusion draw machine **140**.

In one example, cooling fluid **303**, such as gas, may be passed along an exterior **305** of the conduit **137** to achieve an increased cooling rate of the molten material within the conduit **137**. Indeed, a relatively cool fluid may pass along the conduit **137** to provide convective heat transfer, thereby removing heat from the conduit **137** that consequently reduces the temperature of the molten material **121** within the interior of the conduit **137**. The conduit **137** may include a core **307** fabricated from refractory metals (e.g., platinum or platinum-containing metals) that defines the interior of the conduit defining the travel path **301**. The conduit **137** can include other features such as coverings, coatings, or support structures in addition to the core **307**. For instance, as partially schematically illustrated, the conduit may include support structures **306** that may facilitate support of a core **307** of the conduit **137**. The cooling fluid **303** may be passed along the exterior **305** of the conduit **137** such as the exterior of the core **307**, the support structures **306** or other features of the conduit **137**.

As shown in FIG. 3, the conduit **137** may optionally be placed within a containment area **309**. As further shown in FIG. 3, the first station (e.g., the mixing chamber **131**) and the second station (e.g., the delivery vessel **133**) may also be placed in the containment area **309**. Placing the conduit **137**, the first station and the second station within the containment area **309** can help guide a controlled quantity of fluid to travel along a travel path from an upstream portion **311** of the containment area **309** to a downstream portion **313** of the containment area **309**. Moreover, the containment area **309** can be designed to place the conduit **137**, first station and second station within an atmosphere that may be substantially free from oxygen. As such, oxidation of portions of the glass manufacturing apparatus **101** can be minimized, such as prevented, to avoid contaminating the molten material being processed by the glass manufacturing apparatus **101**. In some examples, the cooling fluid may be substantially free from oxygen and comprise an inert gas, such as nitrogen, although the cooling fluid may comprise other chemical elements in further examples.

In operation, molten material **121** may travel along the travel path **301** of the conduit **137** in the direction **315** from the first station (e.g., the mixing chamber **131**) toward the second station (e.g., the delivery vessel **133**). Optionally, the cooling fluid may travel along a path in a direction from the second station toward the first station. Providing a cooling

fluid that flows in the general opposite direction of the flow of molten material can provide enhanced convective heat transfer near the second station since the temperature difference between the cooling fluid and the conduit **137** will be higher near the second station than near the first station.

There is a desire to quickly and efficiently reduce the temperature of the molten material **121** within the interior of the conduit **137** to provide the desired temperature in the second station (e.g., delivery vessel **133**). Providing increased heat transfer can allow for increased flow of molten material within the conduit, thereby allowing for an increase rate of glass ribbon production. Moreover, providing increased heat transfer can reduce the length of the conduit that needs to be provided. Indeed, a relatively long conduit used to cool with a less efficient technique may be significantly shortened with more efficient heat transfer. Providing a relatively short conduit can be beneficial to reduce the quantity of expensive refractory metals used to produce the conduit.

As can be appreciated by FIGS. **3** and **4**, the conduit **137** may include a height "H" that may be less than the width "W". Such designs may be beneficial to provide an oblong or elliptical shape that can provide enhanced heat transfer of the molten material traveling within the conduit. In order to increase heat transfer, the glass manufacturing apparatus **101** may include at least one baffle configured to direct a travel path **317** of the cooling fluid **303** toward a vertical plane **319** passing through the conduit **137**. As shown, the vertical plane **319** passes through the top and bottom of the conduit **137** transverse to the width "W" of the conduit **137**. Moreover, as shown in FIG. **4**, in some examples, the vertical plane **319** bisects the conduit **137**. Directing the cooling fluid **303** toward the vertical plane **319** can encourage the cooling fluid to travel along the relatively greater width "W" of the conduit **137** to enhance heat transfer.

As shown in FIGS. **4** and **5** the baffle **323** can include a deflection panel **501** that may extend at an angle "A" relative to the travel path **301** provided by the conduit **137**. The angle "A" can be measured by a surface extending from the deflection panel **501**. For instance, in the illustrated example, the angle "A" can be measured from a surface that extends tangent to a curved surface of the deflection panel **501**. As illustrated, the angle "A" can be an acute angle that permits gradual diversion of the cooling fluid **303** toward the vertical plane **319**. Moreover, as shown, the deflection panel **501** can include a concave inner surface **503** facing toward the vertical plane **319**. The concave inner surface **503** can further provide a gradual diversion of the cooling fluid **303** to reduce an undesired restriction of fluid flow. In other embodiments, the deflection panel **501** and inner surface **503** can be substantially straight.

As further illustrated, the baffle can include an optional shroud **505** that may at least partially extend over the top portion **321** of the conduit **137**. The shroud **505** may route the travel path of the cooling fluid into the deflection panel **501**. As shown in FIG. **4**, the deflection panel **501** can extend away from the shroud **505** at the angle "A" relative to the travel path of the conduit. Furthermore, an outer end **401** of the deflection panel **501** may be laterally positioned outside the travel path for the molten material. Indeed, in one example, the deflection panel **501** may extend away from the shroud at an angle with the outer end **401** actually abutting a lateral side **403** of the conduit **137**. Positioning the outer end **401** to be laterally positioned outside the travel path, such as abutting the lateral side **403** of the conduit **137**, can help direct a significant portion, such as all, of the corresponding cooling fluid toward the vertical plane **319**. As

such, the baffle can direct the cooling fluid to travel along the top portion **321** (or bottom portion) of the conduit rather than the lateral sides **403** that has a greater surface area than the lateral sides of the conduit, thereby providing increased convective heat transfer.

Although a single deflection panel may be provided, as shown in FIGS. **3** and **4**, the at least one baffle can include a first baffle **324a** and a second baffle **324b**. As shown in FIG. **4**, the first baffle **324a** can be associated with a first lateral side portion **403a** of the conduit **137** and the second baffle **324b** can be associated with a second lateral side portion **403b** of the conduit **137**. As shown, the first baffle **324a** can be identical or similar to the baffle **323** illustrated in FIG. **5**. Likewise, the second baffle **324b** can be similar or identical to a mirror image of the baffle **323** illustrated in FIG. **5**. As shown in FIG. **4**, the first baffle **324a** includes a first deflection panel extending at a first angle (e.g., angle "A") relative to the travel path provided by the conduit **137** and the second baffle **324b** likewise includes a second deflection panel **501** extending at a second angle (e.g., angle "A") relative to the travel path provided by the conduit **137**. As shown, the first deflection panel and the second deflection panel may converge toward one another.

Methods of processing molten material will now be discussed. The method can include the step of flowing molten material **121** through an interior of a conduit from a first station to a second station of the glass manufacturing apparatus. The first station can comprise the melting vessel **105**, the fining vessel **127**, the mixing chamber **131**, the delivery vessel **133**, or other station of the glass manufacturing apparatus. The second station can comprise the fining vessel **127**, the mixing chamber **131**, the delivery vessel **133**, the forming vessel **143**, or other station of the glass manufacturing apparatus. For example, as shown in FIGS. **1**, **3** and **4**, the first station can comprise the mixing chamber **131** and the second station can comprise the delivery vessel **133** positioned downstream from the mixing chamber **131**. Referring to FIG. **3**, molten material flows through the interior of the conduit **137** along the travel path **301** from the first station (e.g., the mixing chamber **131**) to the second station (e.g., the delivery vessel **133**) of the glass manufacturing apparatus **101**.

The method further includes the step of cooling the molten material **121** within the interior of the conduit **137** by passing the cooling fluid **303** along the exterior **305** of the conduit **137**. Optionally, the cooling fluid may be substantially free from oxygen. In some particular examples, the cooling fluid may comprise nitrogen although other chemical elements may be used that inhibit, such as prevent, oxidation of the conduit **137**. As shown in FIG. **3**, the cooling fluid may optionally travel in a direction from the second station (e.g., the delivery vessel **133**) to the first station (e.g., the mixing chamber **131**). As mentioned previously, providing opposite flow directions of the cooling fluid and the molten material may enhance the temperature differential, and consequently the heat transfer rate, at the portion of the conduit adjacent the delivery vessel **133**.

The method can further include the step of directing the travel path **317** of the cooling fluid **303** toward the vertical plane **319** passing through the conduit **137**. In one example, the at least one baffle **324a**, **324b** directs the travel path **317** of the cooling fluid **303**. For instance, as shown in FIGS. **3** and **4**, the at least one baffle can include the first baffle **324a** that directs at least a first portion **317a** of the travel path **317** of the cooling fluid **303** from the first lateral side portion **403a** of the conduit **137** toward the vertical plane **319**. In another example, as further illustrated in FIGS. **3** and **4**, the

at least one baffle can further include the second baffle **324b** that similarly directs a second portion **317b** of the travel path **317** of the cooling fluid **303** from the second lateral side portion **403b** of the conduit **137** toward the vertical plane **319**. As shown in FIG. 4, the first portion **317a** and the second portion **317b** of the travel path **317** may converge together towards the vertical plane **319** passing through the conduit **137**. Indeed, first and second portions **317a**, **317b** of the travel path may be directed away from a lateral location outside the vertical footprint of the conduit **137** shown in FIG. 4 (i.e., laterally outside the first and second lateral side portions **403a**, **403b**) toward the vertical plane **319** passing through the conduit **137**. Consequently, portions of the cooling fluid traveling along the first and second portions **317a**, **317b** of the travel path can be redirected to travel along the top portion **321** (or bottom portion) of the conduit to increase the rate of heat transfer. For example, as mentioned previously, the top portion **321** and/or the bottom portion may have a larger surface area when compared to the first and second lateral side portions **403a**, **403b**. Consequently increased heat transfer rates can be achieved by directing the cooling fluid to travel along the top portion and/or the bottom portion of the conduit rather than traveling along one or both of the lateral side portions.

Still further, directing cooling fluid to travel along the top and/or bottom portions may reduce or prevent formation of stagnant areas with little or no flow of cooling fluid. Indeed, the redirected cooling fluid will provide increased cooling fluid flow across the otherwise stagnant areas to further increase the rate of convective heat transfer.

In examples, with a concave inner surface **503**, the deflection panels **501** may provide a relatively smooth transition to avoid eddies, turbulence and/or pressure drops that may otherwise occur with an abrupt change in direction by other panel configurations. Although not shown, the deflection panel may comprise a substantially flat panel although other configurations may be provided in further examples.

In further examples, the baffle can include the shroud **505** discussed above. If provided, the shroud can route the travel path of the cooling fluid into the deflection panel, wherein the deflection panel subsequently directs the travel path toward the vertical plane **219** passing through the conduit **137**.

It will be apparent to those skilled in the art that various modifications and variations can be made to the present disclosure without departing from the spirit and scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this disclosure provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. A glass manufacturing apparatus comprising:
 - a first station;
 - a second station;
 - a conduit configured to provide a travel path for molten material traveling from the first station to the second station; and
 - at least one baffle configured to direct a travel path of cooling fluid toward a vertical plane passing through the conduit, the at least one baffle comprising a deflection panel extending at an angle relative to the travel path of the molten material provided by the conduit, and the deflection panel comprising a concave inner surface facing toward the vertical plane.
2. The glass manufacturing apparatus of claim 1, wherein the first station comprises a mixing chamber.

3. The glass manufacturing apparatus of claim 1, wherein the second station comprises a delivery vessel.

4. The glass manufacturing apparatus of claim 1, wherein an outer end of the deflection panel is laterally positioned outside the travel path for the molten material.

5. The glass manufacturing apparatus of claim 1, wherein the at least one baffle comprises a shroud at least partially extending over a top portion of the conduit.

6. The glass manufacturing apparatus of claim 5, wherein the deflection panel extends away from the shroud at an angle relative to the travel path of the conduit.

7. The glass manufacturing apparatus of claim 1, wherein a portion of the deflection panel extends in a direction of the travel path of the cooling fluid and inwardly toward a lateral side of the conduit to an outer end that is laterally positioned outside of the travel path of the molten material.

8. The glass manufacturing apparatus of claim 1, wherein the outer end of the deflection panel abuts the lateral side of the conduit.

9. A glass manufacturing apparatus comprising:

- a first station;
- a second station;
- a conduit configured to provide a travel path for molten material traveling from the first station to the second station; and

at least one baffle configured to direct a travel path of cooling fluid toward a vertical plane passing through the conduit, the at least one baffle comprising a deflection panel extending at an angle relative to the travel path of the molten material provided by the conduit, a portion of the deflection panel extends in a direction of the travel path of the cooling fluid and inwardly toward a lateral side of the conduit to an outer end that is laterally positioned outside of the travel path of the molten material, and abutting the lateral side of the conduit.

10. The glass manufacturing apparatus of claim 9, wherein the first station comprises a mixing chamber.

11. The glass manufacturing apparatus of claim 9, wherein the second station comprises a delivery vessel.

12. The glass manufacturing apparatus of claim 9, wherein an outer end of the deflection panel is laterally positioned outside the travel path for the molten material.

13. The glass manufacturing apparatus of claim 9, wherein the deflection panel includes a concave inner surface facing toward the vertical plane.

14. The glass manufacturing apparatus of claim 9, wherein the at least one baffle includes a shroud at least partially extending over a top portion of the conduit.

15. The glass manufacturing apparatus of claim 14, wherein the deflection panel extends away from the shroud at an angle relative to the travel path of the conduit.

16. The glass manufacturing apparatus of claim 9, wherein a portion of the deflection panel extends in a direction of the travel path of the cooling fluid and inwardly toward a lateral side of the conduit to an outer end that is laterally positioned outside of the travel path of the molten material.

17. The glass manufacturing apparatus of claim 16, wherein the outer end of the deflection panel abuts the lateral side of the conduit.

18. A glass manufacturing apparatus comprising:

- a first station;
- a second station;
- a conduit configured to provide a travel path for molten material traveling from the first station to the second station; and

11

a first baffle configured to direct a first travel path of cooling fluid toward a vertical plane passing through the conduit and bisecting the conduit, the first baffle comprising a first deflection panel extending at a first angle relative to the travel path of the molten material provided by the conduit, and the first baffle further comprising a first shroud at least partially extending over a top portion of the conduit;

a second baffle configured to direct a second travel path of cooling fluid toward the vertical plane passing through the conduit, the second baffle comprising a second deflection panel extending at a second angle relative to the travel path provided by the conduit, the first deflection panel and the second deflection panel converging toward one another.

19. The glass manufacturing apparatus of claim 18, wherein the second baffle comprises a second shroud at least partially extending over the top portion of the conduit.

20. The glass manufacturing apparatus of claim 18, wherein the first and second deflection panels include first and second concave inner surfaces, respectively, facing toward the vertical plane.

21. A glass manufacturing apparatus comprising:

a first station;

a second station;

a conduit configured to provide a travel path for molten material traveling from the first station to the second station;

a first baffle configured to direct a first travel path of cooling fluid toward a vertical plane passing through the conduit, the first baffle comprising a first deflection panel extending at a first angle relative to the travel path of the molten material provided by the conduit; and

a second baffle configured to direct a second travel path of cooling fluid toward the vertical plane passing through the conduit, the second baffle comprising a second deflection panel extending at a second angle relative to the travel path provided by the conduit, the first deflection panel and the second deflection panel converging toward one another and comprising first and second concave inner surfaces, respectively, facing toward the vertical plane.

12

22. The glass manufacturing apparatus of claim 21, wherein the vertical plane bisects the conduit.

23. The glass manufacturing apparatus of claim 21, wherein the first baffle comprises a first shroud at least partially extending over a top portion of the conduit.

24. The glass manufacturing apparatus of claim 23, wherein the second baffle comprises a second shroud at least partially extending over the top portion of the conduit.

25. A glass manufacturing apparatus comprising:

a first station;

a second station;

a conduit configured to provide a travel path for molten material traveling from the first station to the second station; and

a first baffle configured to direct a first travel path of cooling fluid toward a vertical plane passing through the conduit, the first baffle comprising a first deflection panel extending at a first angle relative to the travel path of the molten material provided by the conduit;

a second baffle configured to direct a second travel path of cooling fluid toward the vertical plane passing through the conduit, the second baffle comprising a second deflection panel extending at a second angle relative to the travel path provided by the conduit, the first deflection panel and the second deflection panel converging toward one another, and the second deflection panel is a mirror image of the first deflection panel about the vertical plane.

26. The glass manufacturing apparatus of claim 25, wherein the vertical plane bisects the conduit.

27. The glass manufacturing apparatus of claim 25, wherein the first baffle comprises a first shroud at least partially extending over a top portion of the conduit.

28. The glass manufacturing apparatus of claim 27, wherein the second baffle comprises a second shroud at least partially extending over the top portion of the conduit.

29. The glass manufacturing apparatus of claim 25, wherein the first and second deflection panels include first and second concave inner surfaces, respectively, facing toward the vertical plane.

* * * * *