

US010385335B2

(12) **United States Patent**
McGall

(10) **Patent No.:** **US 10,385,335 B2**
(45) **Date of Patent:** ***Aug. 20, 2019**

(54) **MODIFIED SURFACES**

(71) Applicant: **CENTRILLION TECHNOLOGY HOLDINGS CORPORATION**, Grand Cayman (KY)

(72) Inventor: **Glenn McGall**, Palo Alto, CA (US)

(73) Assignee: **CENTRILLION TECHNOLOGY HOLDINGS CORPORATION**, Grand Cayman (KY)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 122 days.

This patent is subject to a terminal disclaimer.

(52) **U.S. Cl.**
CPC **C12N 15/1093** (2013.01); **C08F 220/58** (2013.01); **C12Q 1/686** (2013.01); (Continued)

(58) **Field of Classification Search**
None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,469,863 A 9/1984 Ts'O et al.
4,988,617 A 1/1991 Landegren et al.
(Continued)

FOREIGN PATENT DOCUMENTS

CN 102224257 A 10/2011
EP 1291354 A2 3/2003
(Continued)

OTHER PUBLICATIONS

Mardis. Next-generation DNA sequencing methods. *Annu Rev Genomics Hum Genet.* 2008;9:387-402. doi: 10.1146/annurev.genom.9.081307.164359.

(Continued)

(21) Appl. No.: **15/101,168**

(22) PCT Filed: **Dec. 5, 2014**

(86) PCT No.: **PCT/US2014/068947**

§ 371 (c)(1),
(2) Date: **Jun. 2, 2016**

(87) PCT Pub. No.: **WO2015/085268**

PCT Pub. Date: **Jun. 11, 2015**

(65) **Prior Publication Data**

US 2016/0298110 A1 Oct. 13, 2016

Related U.S. Application Data

(60) Provisional application No. 61/979,431, filed on Apr. 14, 2014, provisional application No. 61/912,027, filed on Dec. 5, 2013.

(51) **Int. Cl.**
C12Q 1/68 (2018.01)
C12N 15/10 (2006.01)

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,469,863 A 9/1984 Ts'O et al.
4,988,617 A 1/1991 Landegren et al.
(Continued)

FOREIGN PATENT DOCUMENTS

CN 102224257 A 10/2011
EP 1291354 A2 3/2003
(Continued)

OTHER PUBLICATIONS

Mardis. Next-generation DNA sequencing methods. *Annu Rev Genomics Hum Genet.* 2008;9:387-402. doi: 10.1146/annurev.genom.9.081307.164359.

(Continued)


Primary Examiner — Aaron A Priest

(74) *Attorney, Agent, or Firm* — Wilson Sonsini Goodrich & Rosati

(57) **ABSTRACT**

Provided herein are methods and compositions for coating surfaces with polymers. The methods and compositions are suited for conducting biological reactions.

17 Claims, 4 Drawing Sheets



<p>(51) Int. Cl. <i>C08F 220/58</i> (2006.01) <i>C40B 50/18</i> (2006.01) <i>C12Q 1/686</i> (2018.01) <i>C12Q 1/6874</i> (2018.01) <i>C12Q 1/6834</i> (2018.01) <i>C09D 4/00</i> (2006.01) <i>C08F 220/56</i> (2006.01)</p> <p>(52) U.S. Cl. CPC <i>C12Q 1/6834</i> (2013.01); <i>C12Q 1/6874</i> (2013.01); <i>C40B 50/18</i> (2013.01); <i>B01J 2219/00626</i> (2013.01); <i>B01J 2219/00637</i> (2013.01); <i>B01J 2219/00659</i> (2013.01); <i>B01J 2219/00722</i> (2013.01); <i>C08F 220/56</i> (2013.01); <i>C09D 4/00</i> (2013.01)</p> <p>(56) References Cited</p> <p>U.S. PATENT DOCUMENTS</p> <p>5,034,506 A 7/1991 Summerton et al. 5,216,141 A 6/1993 Benner 5,235,033 A 8/1993 Summerton et al. 5,242,794 A 9/1993 Whiteley et al. 5,386,023 A 1/1995 Sanghvi et al. 5,476,930 A 12/1995 Letsinger et al. 5,478,893 A 12/1995 Ghosh et al. 5,494,810 A 2/1996 Barany et al. 5,602,240 A 2/1997 De Mesmaeker et al. 5,637,684 A 6/1997 Cook et al. 5,644,048 A 7/1997 Yau 5,712,124 A 1/1998 Walker 5,750,341 A 5/1998 Macevicz 5,780,613 A 7/1998 Letsinger et al. 5,795,714 A 8/1998 Cantor et al. 5,969,119 A 10/1999 Macevicz 6,262,216 B1 7/2001 McGall 6,306,597 B1 10/2001 Macevicz 6,410,278 B1 6/2002 Notomi et al. 6,511,803 B1 1/2003 Church et al. 6,582,938 B1 6/2003 Su et al. 6,692,914 B1 2/2004 Klaerner et al. 6,994,964 B1 2/2006 Chang et al. 7,048,481 B2 5/2006 Sugata et al. 7,170,050 B2 1/2007 Turner et al. 7,211,390 B2 5/2007 Rothberg et al. 7,244,559 B2 7/2007 Rothberg et al. 7,244,567 B2 7/2007 Chen et al. 7,250,253 B1 7/2007 Klapproth et al. 7,264,929 B2 9/2007 Rothberg et al. 7,302,146 B2 11/2007 Turner et al. 7,313,308 B2 12/2007 Turner et al. 7,315,019 B2 1/2008 Turner et al. 7,323,305 B2 1/2008 Leamon et al. 7,335,762 B2 2/2008 Rothberg et al. 7,405,281 B2 7/2008 Xu et al. 7,462,452 B2 12/2008 Williams et al. 7,462,468 B1 12/2008 Williams et al. 7,476,503 B2 1/2009 Turner et al. 7,476,504 B2 1/2009 Turner 7,670,770 B2 3/2010 Chou et al. 7,713,689 B2 5/2010 Chilkoti RE42,315 E 5/2011 Lopez et al. 8,367,314 B2 2/2013 Chilkoti 9,328,382 B2 5/2016 Drmanac et al. 2002/0068290 A1 6/2002 Yarovinsky 2002/0132245 A1* 9/2002 Boles C12Q 1/6834 435/6.12</p> <p>2003/0082576 A1 5/2003 Jones et al. 2004/0171053 A1 9/2004 Hu 2004/0185260 A1 9/2004 Luzinov et al. 2005/0084912 A1 4/2005 Poponin 2005/0158879 A1 7/2005 Klaerner et al. 2005/0244863 A1 11/2005 Mir 2006/0205089 A1 9/2006 Dratz et al.</p>	<p>2008/0206764 A1 8/2008 Williams et al. 2009/0002935 A1 1/2009 Cheng 2009/0024331 A1 1/2009 Tomaney et al. 2009/0026082 A1 1/2009 Rothberg et al. 2009/0029385 A1 1/2009 Christians et al. 2009/0068655 A1 3/2009 Williams et al. 2009/0121133 A1 5/2009 Amirparviz 2009/0181861 A1 7/2009 Li et al. 2009/0326208 A1 12/2009 Carrino et al. 2010/0022412 A1 1/2010 Rigatti et al. 2010/0173394 A1 7/2010 Colston, Jr. et al. 2010/0203597 A1 8/2010 Chen et al. 2010/0208724 A1 8/2010 Booth et al. 2010/0240827 A1 9/2010 Barwick et al. 2010/0268478 A1 10/2010 Andregg et al. 2011/0046324 A1 2/2011 Matyjaszewski et al. 2011/0143966 A1 6/2011 McGall et al. 2011/0143967 A1* 6/2011 McGall C07F 7/188 506/32</p> <p>2011/0172119 A1* 7/2011 Boutell C12Q 1/6806 506/9</p> <p>2012/0004132 A1 1/2012 Zhang et al. 2012/0021200 A1* 1/2012 Koberstein C08G 77/045 428/220</p> <p>2012/0208724 A1 8/2012 Steemers et al. 2012/0258313 A1* 10/2012 Wen C09D 131/00 428/412</p> <p>2012/0270964 A1 10/2012 Piletsky et al. 2013/0143771 A1 6/2013 Chilkoti 2013/0157870 A1 6/2013 Pushkarev et al. 2013/0165350 A1* 6/2013 Kuimelis C40B 50/18 506/32</p> <p>2013/0171461 A1* 7/2013 Dach B05D 1/36 428/520</p> <p>2013/0172214 A1 7/2013 Ye et al. 2013/0211006 A1 8/2013 Menchen et al. 2013/0244249 A1 9/2013 Jiang et al. 2014/0186940 A1 7/2014 Goel 2014/0357523 A1 12/2014 Zeiner et al. 2015/0141269 A1 5/2015 Soldatov et al. 2016/0046985 A1 2/2016 Drmanac et al. 2016/0168632 A1 6/2016 Edwards 2016/0244548 A1* 8/2016 Boniface B01J 20/3204 2016/0303534 A1 10/2016 Zhou et al. 2016/0369334 A1 12/2016 Zhou et al. 2017/0016063 A1 1/2017 McGall et al. 2017/0022554 A1 1/2017 Drmanac et al.</p> <p>FOREIGN PATENT DOCUMENTS</p> <p>EP 1655069 A1 5/2006 WO WO-9844151 A1* 10/1998 C12Q 1/6834 WO WO-0102452 A1 1/2001 WO WO-0227026 A2 4/2002 WO WO-03010203 A1 2/2003 WO WO-2004067759 A2 8/2004 WO WO-2004081183 A2 9/2004 WO WO-2007060456 A1 5/2007 WO WO-2007133831 A2 11/2007 WO WO-2008022332 A2 2/2008 WO WO-2010003132 A1 1/2010 WO WO-2010058342 A1 5/2010 WO WO-2010100265 A1 9/2010 WO WO-2012106546 A2 8/2012 WO WO-2012134602 A2 10/2012 WO WO-2012140224 A1 10/2012 WO WO-2013056090 A1 4/2013 WO WO-2013063382 A2 5/2013 WO WO-2012106546 A3 11/2013 WO WO-2013184754 A2 12/2013 WO WO-2015017759 A1 2/2015 WO WO-2015085268 A1 6/2015 WO WO-2015085274 A1 6/2015 WO WO-2015085275 A2 6/2015</p>
--	---

(56)

References Cited

FOREIGN PATENT DOCUMENTS

WO WO-2015085275 A3 9/2015
 WO WO-2016201111 A1 12/2016

OTHER PUBLICATIONS

Allemand, J. F., Bensimon, D., Jullien, L., Bensimon, A. & Croquette, V. pH-dependent specific binding and combing of DNA. *Biophys J* 73, 2064-2070, (1997).

Bolli, et al. α -Bicyclo-DNA: Synthesis, Characterization, and Pairing Properties of α -DNA-Analogues with Restricted Conformational Flexibility in the Sugar—Phosphate Backbone. *Carbohydrate Modifications in Antisense Research*. ACS Symposium Series, vol. 580. Chapter 7, pp. 100-117.

Compton. Nucleic acid sequence-based amplification. *Nature*. Mar. 7, 1991;350(6313):91-2.

Cullen, et al. Polymeric brushes as functional templates for immobilizing ribonuclease A: study of binding kinetics and activity. *Langmuir*. Feb. 5, 2008;24(3):913-20. Epub Dec. 13, 2007.

Dempcy et al. Synthesis of a thymidyl pentamer of deoxyribonucleic guanidine and binding studies with DNA homopolynucleotides. *PNAS US* 92:6097-6101 (1995).

Epicentre, DNA topoisomerase I, 2012. *Vaccinia*, Cat. Nos. VT710500, VT7101K and VT7105K.

European search report and search opinion dated Aug. 24, 2017 for EP Application No. 14867494.8.

European search report and search opinion dated Aug. 25, 2017 for EP Application No. EP14867116.7.

European search report with written opinion dated Jul. 17, 2017 for EP14868406.

Herdewijn, et al. Hexopyranosyl-Like Oligonucleotides. *Carbohydrate Modifications in Antisense Research*. ACS Symposium Series, vol. 580. Chapter 6, pp. 80-99.

Maddry, et al. Synthesis of Nonionic Oligonucleotide Analogues. *Carbohydrate Modifications in Antisense Research*. ACS Symposium Series, vol. 580. Chapter 3, pp. 40-51.

Mesmaeker, et al. Novel Backbone Replacements for Oligonucleotides. *Carbohydrate Modifications in Antisense Research*. ACS Symposium Series, vol. 580. Chapter 2, pp. 24-39.

Office action dated Sep. 21, 2017 for U.S. Appl. No. 15/178,411.

United Kingdom combined search and examination report dated Jul. 3, 2017 for GB1613408.

Yuan, et al. Polymer-functionalized silica nanosphere labels for ultrasensitive detection of tumor necrosis factor- α . *Anal Chem*. Sep. 1, 2011;83(17):6800-9. doi: 10.1021/ac201558w. Epub Aug. 15, 2011.

Office Action dated Nov. 3, 2017 for CN Patent Application No. 201480074638.8.

Akeroyd, et al. The combination of living radical polymerization and click chemistry for the synthesis of advanced macromolecular architectures. *European Polymer Journal*. 2011; 47.6: 1207-1231.

Anonymous. Topomize DNA library prep kit. Nov. 10, 2015.

Sawai, H., Synthesis and properties of oligoadenylic acids containing 2'-5' phosphoramidate linkage. *The chemical society of Japan*. 1984.805-808.

Ayres, et al. Polymer brushes: Applications in biomaterials and nanotechnology. *Polym. Chem*. 2010; 1: 769-777.

Barbey, et al. Polymer brushes via surface-initiated controlled radical polymerization: synthesis, characterization, properties, and applications. *Chem Rev*. Nov. 2009;109(11):5437-5527. doi: 10.1021/cr900045a.

Beaucage, et al. *Tetrahedron Letters*. 1981; 22:1859-1862.

Bensimon, A. et al. Alignment and sensitive detection of DNA by a moving interface. *Science* 265, 2096-2098, (1994).

Bentley, et al. Accurate whole human genome sequencing using reversible terminator chemistry. *Nature*. Nov. 6, 2008;456(7218):53-9.

Braunecker, et al. Controlled/living radical polymerization: features, developments, and perspectives. *Progress in Polymer Science*. 2007; 32.1: 93-146.

Brill, et al., Synthesis of Oligodeoxynucleoside phosphorodithioates via thioamidites. *Journal American Chemical society*. 111; 1989.

Brown, et al., Chemical synthesis and cloning of a tyrosine tRNA gene. *Methods of enzymology*. Academic press. 1979.

Carlsson, et al., Screening for genetic mutations. *Scientific correspondence*. *Nature*. 1996; 380:207.

Co-pending U.S. Appl. No. 62/012,238, filed Jun. 13, 2014.

Co-pending U.S. Appl. No. 62/173,140, filed Jun. 9, 2015.

Co-pending U.S. Appl. No. 61/979,448, filed Apr. 14, 2014.

Ding, et al., Single-molecule mechanical identification and sequencing. *Nature Methods*. Apr. 2012; 9(4): 367-372.

Eckstein, F., *Oligonucleotides and Analogues: A Practical Approach*, Oxford University Press. 1991.

Edmondson, et al. Polymer brushes via surface-initiated polymerizations. *Chem Soc Rev*. Jan. 10, 2004;33(1):14-22. Epub Dec. 2, 2003.

Egholm, et al., Peptide nucleic acids (PNA). Oligonucleotide analogs with an achiral. *Journal American Chemical Society*. 1992: 114 (5); pp. 1895-1897.

Egholm, et al., PNA hybridizes to complementary oligonucleotides obeying the Watson-Crick hydrogen-bonding rules. *Nature*. Oct. 7, 1993;365(6446):566-8.

European Search Report and search opinion dated Sep. 29, 2016 for International Application EP 16173782.0.

Ferree, et al., Electrokinetic Stretching of Tethered DNA. *Biophys J*. Oct. 2003; 85(4): 2539-2546.

Fodor, S. P. et al. Light-directed, spatially addressable parallel chemical synthesis. *Science* 251, 767-773, (1991).

Galvin, et al. Applications of surface-grafted macromolecules derived from post-polymerization modification reactions. *Progress in Polymer Science*. 2012; 37.7: 871-906.

Gao, et al., In Situ synthesis of oligonucleotide microarrays. *Biopolymers*. 2004. 73; 579-596.

Gueroui, et al., Observation by fluorescence microscopy of transcription on single combed DNA. *Proceedings of the National Academy of Sciences of the United States of America* 99, 6005-6010, (2002).

Haber, et al., Magnetic tweezers for DNA micromanipulation. *Review of scientific instruments*. 2000. 71:4561.

Henry, et al. Three-dimensional arrangement of short DNA oligonucleotides at surfaces via the synthesis of DNA-branched polyacrylamide brushes by SI-ATRP. *Macromol Rapid Commun*. Sep. 15, 2011;32(18):1405-10. doi: 10.1002/marc.201100317. Epub Jul. 28, 2011.

Horn, et al., Oligonucleotides with Alternating Anionic and Cationic Phosphoramidate Linkages: Synthesis and Hybridization of Stereouniform Isomers. *Tetrahedron letters*. 1996. 37:6; 743-746.

International search report and written opinion dated Feb. 24, 2015 for PCT/US14/068947.

International search report and written opinion dated Apr. 28, 2015 for PCT Application No. PCT/US14/068954.

International search report and written opinion dated Jun. 25, 2015 for PCT Application No. PCT/US14/068955.

International Search Report and Written Opinion dated Sep. 23, 2016 for International Application PCT/US2016/036709.

Jeffs, et al., Unusual conformation of a 3'-thioformacetal linkage in a DNA duplex*. *Journal of Biomolecular NMR*. 1994. 17-34.

Jenkins, et al., The Biosynthesis of Carbocyclic Nucleosides. *Chemical society reviews*. 1995; 169-176.

Kiedrowski, et al. Parabolic growth of a self-replicating hexadeoxynucleotide bearing a 3'-5'-phosphoramidate linkage. *Angew. Chem*. 1991; 4:30.

Kim et al., Multiplexed single-molecule assay for enzymatic activity on flow-stretched DNA. *Nat Methods*. May 2007;4(5):397-9. Epub Apr. 15, 2007.

Kizhakkedathu, et al. Poly(oligo(ethylene glycol)acrylamide) Brushes by Surface Initiated Polymerization: Effect of Macromonomer Chain Length on Brush Growth and Protein Adsorption from Blood Plasma. *Langmuir*. 2009; 25: 3794-3801.

(56)

References Cited

OTHER PUBLICATIONS

- Koshkin, et al. LNA (Locked Nucleic Acid): An RNA Mimic Forming Exceedingly Stable LNA: LNA Duplexes. *Journal American Chemical Society* 1998; 120:13252-3.
- Lee, et al. Immobilization of Amine-modified Oligonucleotides on Bifunctional Polymer Brushes Synthesized by Surface-initiated Polymerization. *Bull. Korean Chem. Soc.* 2012; 33(6): 2043-6.
- Letsinger et al., Cationic oligonucleotides. *J. Am. Chem. Soc.* 1988; 110(3):4470-4471.
- Letsinger et al., Effects of pendant groups at phosphorus on binding properties of d-ApA analogues. *Nucleic Acids Res.* Apr. 25, 1986; 14(8):3487-99.
- Letsinger et al., Hybridization of Alternating Cationic/Anionic Oligonucleotide to RNA Segments. *Nucleosides & Nucleotides.* 13:1597 (1994).
- Letsinger, et al., Nucleotide chemistry. XVI. Phosphoramidate analogs of oligonucleotides. *J. Org. Chem.*, 1970, 35(11), pp. 3800-3803.
- Mag et al., Synthesis and selective cleavage of an oligodeoxynucleotide containing a bridged internucleotide 5'-phosphorothioate linkage. *Nucleic Acids Res.* 19:1437 (1991).
- Mansfeld, et al. Clickable initiators, monomers and polymers in controlled radical polymerizations—a prospective combination in polymer science. *Polymer Chemistry.* 2010; 1.10: 1560-1598.
- Marguiles, et al. Genome sequencing in microfabricated high-density picolitre reactors. *Nature.* Sep. 15, 2005; 437(7057):376-80. Epub Jul. 31, 2005.
- McGall, G. H. & Christians, F. C. High-density genechip oligonucleotide probe arrays. *Adv Biochem Eng. Biotechnol* 77, 21-42, (2002).
- Meier, et al., Peptide nucleic acids (PNAs)-Unusual properties nonionic oligonucleotide analogues. *Angew. Chemical. Int. Ed. Engl.* 1992; 31:8.
- Mesmaeker, et al. Comparison of rigid and flexible backbones in antisense oligonucleotides. *Bioorganic and medical chemistry.* 1994. 4;3:395-398.
- Michalet, X. et al. Dynamic molecular combing: stretching the whole human genome for high-resolution studies. *Science* 277, 1518-1523, (1997).
- Mitra, et al. In situ localized amplification and contact replication of many individual DNA molecules. *Nucleic Acids Res.* Dec. 15, 1999; 27(24):e34.
- Narang, et al., Improved Phosphotriester Method for the Synthesis of Gene Fragments. *Methods in enzymology.* 1979. 68:90-98.
- Nuwaysir, et al., Gene expression analysis using oligonucleotide arrays produced by maskless photolithography. *Genome Res.* 2002. 12, 1749-1755.
- Office action dated Mar. 28, 2017 for CN Application No. 201480074638.8.
- Olivier, et al. Surface-initiated controlled polymerization as a convenient method for designing functional polymer brushes: From self-assembled monolayers to patterned surfaces. *Progress in polymer science.* 2012; 37.1: 157-181.
- Orski, et al. High Density Scaffolding of Functional Polymer Brushes: Surface Initiated Atom Transfer Radical Polymerization of Active Esters. *Langmuir.* 2010; 26(3): 2136-2143.
- Pauwels et al., Biological activity of new 2-5A analogues. *Chimica scripta.* 1986. 26: 141-145.
- Payne, et al., Molecular Threading: Mechanical Extraction, Stretching and Placement of DNA Molecules from a Liquid-Air Interface. *PLoS ONE* 8(7): e69058.
- Premier Biosoft. Accelerating research in life sciences. 1994. Available at <http://www.premierbiosoft.com/netprimer/index.html>. Accessed on Oct. 18, 2016.
- Proudnikov, et al. Immobilization of DNA in polyacrylamide gel for the manufacture of DNA and DNA-oligonucleotide microchips. *Anal Biochem.* May 15, 1998; 259(1):34-41.
- Prucker, et al. Polymer Layers through Self-Assembled Monolayers of Initiators. *Langmuir.* 1998; 14(24): 6893-6898.
- Rawls, et al. Optimistic about antisense: promising clinical results and chemical strategies for further improvements delight antisense drug researchers. *C&EN.* 1997. 35-39.
- Rehman, et al. Immobilization of acrylamide-modified oligonucleotides by co-polymerization. *Nucleic Acids Res.* Jan. 15, 1999; 27(2):649-55.
- Reisner, et al. DNA confinement in nanochannels: physics and biological applications. *Rep. Prog. Phys.* 2012. 75:10.
- Rodriguez-Emmenegger, et al. Substrate-independent approach for the generation of functional protein resistant surfaces. *Biomacromolecules.* Apr. 11, 2011; 12(4):1058-66. doi: 10.1021/bm101406m. Epub Mar. 25, 2011.
- Ruhe, et al. Functional Polymer Brushes. *Journal of Macromolecular Science, Part C: Polymer Reviews.* 2002; 42.1: 91-138.
- Seiffert, S. & Oppermann, W. Amine-Functionalized Polyacrylamide for Labeling and Crosslinking Purposes. *Macromolecular Chemistry and Physics* 208, 1744-1752, (2007).
- Senaratne, et al. Self-assembled monolayers and polymer brushes in biotechnology: current applications and future perspectives. *Biomacromolecules.* 2005; 6.5: 2427-2448.
- Shapiro, et al. SNP genotyping by multiplexed solid-phase amplification and fluorescent minisequencing. *Genome Res.* Nov. 2001; 11(11):1926-34.
- Soni, et al., Progress toward ultrafast DNA sequencing using solid-state nanopores. *Clin Chem.* Nov. 2007; 53(11):1996-2001. Epub Sep. 21, 2007.
- Sprinzi, et al., Enzymatic Incorporation of ATP and CTP Analogues into the 3' End of tRNA. *Eur. J. Biochem.* 81, 579-589 (1977).
- Thomson, et al. Oligonucleotide and polymer functionalized nanoparticles for amplification-free detection of DNA. *Biomacromolecules.* Jun. 11, 2012; 13(6):1981-9. doi: 10.1021/bm300717f. Epub May 30, 2012.
- Timofeev, et al. Regioselective immobilization of short oligonucleotides to acrylic copolymer gels. *Nucleic Acids Res.* Aug. 15, 1996; 24(16):3142-8.
- Walker et al., Strand displacement amplification—an isothermal, in vitro DNA amplification technique. *Nucl. Acids Res.* (1992) 20 (7): 1691-1696. doi: 10.1093/nar/20.7.1691.
- Wang et al., Stretching DNA with optical tweezers. *Biophys J.* Mar. 1997; 72(3): 1335-1346.
- Westin et al., Anchored multiplex amplification on a microelectronic chip array. *Nature Biotechnology* 18, 199-204 (2000).
- Zhang, et al., Assembly of Highly Aligned DNA Strands onto Si Chips. *Langmuir*; 2005, 21(9), pp. 4180-4184.
- Zhang, et al., Preparation of megabase-sized DNA from a variety of organisms using the nuclei method for advanced genomics research. *Nature Protocols* 7, 467-478 (2012).
- CN201480074638.8 Office Action dated Jul. 12, 2018 (w/ English translation).
- Gunderson, et al. A genome-wide scalable SNP genotyping assay using microarray technology. *Nat Genet* 37(5):549-554 (2005).
- Office action dated Jul. 2, 2018 for U.S. Appl. No. 15/101,671. EP14867116.7 Office Action dated Aug. 31, 2018.
- EP14867494.8 Office Action dated Aug. 30, 2018.

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4

1

MODIFIED SURFACES

CROSS-REFERENCE

This application claims the benefit of U.S. Provisional Application No. 61/912,027, filed Dec. 5, 2013, and U.S. Provisional Application No. 61/979,431, filed Apr. 14, 2014, which applications are incorporated herein by reference.

BACKGROUND

In many sequencing by synthesis (SBS) systems, clonal amplification and SBS are performed in glass flow cell channels. PCR primers are attached to the inner surface of the channels via a passively bound polymer coating. Weakly bound polymer chains are washed away prior to use, but the remaining polymer can become depleted to varying extents during extensive cycles of SBS, causing progressive loss of signal. This is a particular concern when high pH and elevated temperature conditions are employed.

SUMMARY

Methods and compositions are provided for fabricating polymer coatings by surface initiated polymerization incorporating biomolecules. In some cases, the compositions and methods are useful in performing nucleic acid reactions and sequencing by synthesis. In some cases, the compositions and methods are useful in providing coatings that are robust.

An aspect of the present disclosure provides a composition, comprising: a surface with a 10 or more nucleic acid molecules coupled thereto, wherein at least 90% of the nucleic acid molecules remain intact and coupled to the surface after at least 30 PCR cycles, wherein each PCR cycle comprises the following reaction conditions: (a) a denaturation step at a temperature of at least 85° C. for at least 15 seconds; (b) an annealing step at a temperature of at least 50° C. for at least 15 seconds; and (c) an extension step at a temperature of at least 70° C. for at least 30 seconds.

In some embodiments of aspects provided herein, the surface is covered with a polymer brush. In some embodiments of aspects provided herein, the polymer brush comprises acrylamide. In some embodiments of aspects provided herein, the polymer brush further comprises N-(2-hydroxyethyl)acrylamide. In some embodiments of aspects provided herein, at least 1,000 different nucleic acid molecules are coupled to the surface. In some embodiments of aspects provided herein, at least 100,000 different nucleic acid molecules are coupled to the surface. In some embodiments of aspects provided herein, at least 1,000,000 different nucleic acid molecules are coupled to the surface.

An aspect of the present disclosure provides a method for performing an enzymatic reaction, comprising: (a) providing a substrate having a polymer brush coating and a plurality of biomolecules coupled to the polymer brush; and (b) performing one or more enzymatic reactions with the biomolecules on the substrate.

In some embodiments of aspects provided herein, the biomolecules are selected from the group consisting of: oligonucleotides, polynucleotides, aptamers, proteins, and antibodies. In some embodiments of aspects provided herein, the enzymatic reaction is selected from the group consisting of: polymerase chain reaction, sequencing reaction, ligation reaction, extension reaction, and transcription reaction. In some embodiments of aspects provided herein, further comprises applying heat to the substrate. In some

2

embodiments of aspects provided herein, at least 90% of the biomolecules are retained with at least 90% integrity after 25 cycles of polymerase chain reactions. In some embodiments of aspects provided herein, the substrate comprises at least 1,000,000 different types of biomolecules, and wherein each biomolecule is an oligonucleotide. In some embodiments of aspects provided herein, the enzymatic reaction is an extension reaction.

An aspect of the present disclosure provides a method for making a modified surface, comprising: (a) providing a surface; (b) covalently bonding initiator species to the surface; (c) conducting surface initiated polymerization of a polymer from the initiator species, thereby producing a polymer coating comprising a plurality of polymer chains; and (d) coupling two or more different biomolecules to the polymer coating.

An aspect of the present disclosure provides a method for making a modified surface, comprising: (a) providing a surface; (b) covalently bonding initiator species to the surface; (c) conducting surface initiated polymerization of a mixture two or more different types of acrylamide monomers from the initiator species, thereby producing a polymer coating comprising a plurality of polymer chains; and (d) coupling biomolecules to the polymer coating.

In some embodiments of aspects provided herein, the biomolecules are selected from the group consisting of: oligonucleotides, polynucleotides, aptamers, proteins, and antibodies. In some embodiments of aspects provided herein, the two or more different biomolecules are two different oligonucleotides. In some embodiments of aspects provided herein, the two or more different types of acrylamide monomers are selected from the group consisting of: acrylamide, N-(2-hydroxyethyl)acrylamide, ethylene glycol acrylamide, and hydroxyethylmethacrylate (HEMA). In some embodiments of aspects provided herein, the surface is selected from the group consisting of glass, silica, titanium oxide, aluminum oxide, indium tin oxide (ITO), silicon, polydimethylsiloxane (PDMS), polystyrene, polycyclicolefins, polymethylmethacrylate (PMMA), titanium, and gold. In some embodiments of aspects provided herein, the surface comprises glass. In some embodiments of aspects provided herein, the surface comprises silicon. In some embodiments of aspects provided herein, the surface is selected from the group consisting of: flow cells, sequencing flow cells, flow channels, microfluidic channels, capillary tubes, piezoelectric surfaces, wells, microwells, microwell arrays, microarrays, chips, wafers, non-magnetic beads, magnetic beads, ferromagnetic beads, paramagnetic beads, superparamagnetic beads, and polymer gels. In some embodiments of aspects provided herein, the initiator species comprises an organosilane. In some embodiments of aspects provided herein, the initiator species comprises the molecule shown in FIG. 1. In some embodiments of aspects provided herein, the surface initiated polymerization comprises atom-transfer radical polymerization (ATRP). In some embodiments of aspects provided herein, the surface initiated polymerization comprises reversible addition fragmentation chain-transfer (RAFT). In some embodiments of aspects provided herein, the biomolecules comprise 5' acrydite modified oligonucleotides. In some embodiments of aspects provided herein, the biomolecules comprise antibodies. In some embodiments of aspects provided herein, the biomolecules comprise peptides. In some embodiments of aspects provided herein, the biomolecules comprise aptamers. In some embodiments of aspects provided herein,

the coupling of the biomolecules comprises incorporation of acrydite-modified biomolecules during polymerization. In some embodiments of aspects provided herein, the biomolecules comprises reaction at bromoacetyl sites. In some

embodiments of aspects provided herein, the coupling of the biomolecules comprises reaction at azide sites. In some embodiments of aspects provided herein, the coupling of the biomolecules comprises azide-alkyne Huisgen cycloaddition.

An aspect of the present disclosure provides a composition, comprising: (a) a surface; (b) a polymer coating covalently bound to the surface, formed by surface-initiated polymerization, wherein the polymer coating comprises 2 or more different types of acrylamide monomers; and (c) a biomolecule coupled to the polymer coating.

An aspect of the present disclosure provides a composition, comprising: (a) a surface; (b) a polymer coating covalently bound to the surface, formed by surface-initiated polymerization; and (c) at least two different biomolecules coupled to the polymer coating.

In some embodiments of aspects provided herein, the biomolecule comprises an oligonucleotide. In some embodiments of aspects provided herein, the oligonucleotide is coupled to the polymer at its 5' end. In some embodiments of aspects provided herein, the oligonucleotide is coupled to the polymer at its 3' end. In some embodiments of aspects provided herein, the biomolecule comprises an antibody. In some embodiments of aspects provided herein, the biomolecule comprises an aptamer. In some embodiments of aspects provided herein, the at least two different biomolecules comprise oligonucleotides. In some embodiments of aspects provided herein, the oligonucleotides are coupled to the polymer coating at their 5' ends. In some embodiments of aspects provided herein, the oligonucleotides are coupled to the polymer coating at their 3' ends. In some embodiments of aspects provided herein, the at least two different biomolecules comprise antibodies. In some embodiments of aspects provided herein, the at least two different biomolecules comprise aptamers. In some embodiments of aspects provided herein, the surface comprises glass. In some embodiments of aspects provided herein, the surface comprises silicon. In some embodiments of aspects provided herein, the polymer coating comprises polyacrylamide. In some embodiments of aspects provided herein, the polymer coating comprises PMMA. In some embodiments of aspects provided herein, the polymer coating comprises polystyrene. In some embodiments of aspects provided herein, the surface-initiated polymerization comprises atom-transfer radical polymerization (ATRP). In some embodiments of aspects provided herein, the surface-initiated polymerization comprises reversible addition fragmentation chain-transfer (RAFT).

INCORPORATION BY REFERENCE

All publications, patents, and patent applications mentioned in this specification are herein incorporated by reference to the same extent as if each individual publication, patent, or patent application was specifically and individually indicated to be incorporated by reference.

BRIEF DESCRIPTION OF THE DRAWINGS

The novel features of the invention are set forth with particularity in the appended claims. A better understanding of the features and advantages of the present invention will be obtained by reference to the following detailed descrip-

tion that sets forth illustrative embodiments, in which the principles of the invention are utilized, and the accompanying drawings of which:

FIG. 1 shows an example of an initiator silane.

FIG. 2 shows an example of a phosphorylcholine-acrylamide monomer.

FIG. 3 shows an example of a betaine-acrylamide monomer.

FIG. 4 shows an example of a process for producing a polyacrylamide surface coating with oligonucleotides.

DETAILED DESCRIPTION OF THE INVENTION

Overview

This disclosure provides methods and compositions for improved polymer coatings on surfaces. The polymer coatings can be generated via surface-initiated polymerization (SIP) via initiator species bound to a surface. The polymer coatings can incorporate modified monomers to modulate physicochemical properties of the coatings. The polymer coatings can incorporate oligonucleotides.

Surfaces

The methods and compositions provided in this disclosure can comprise creating a polymer coating on a surface. The surface can comprise glass, silica, titanium oxide, aluminum oxide, indium tin oxide (ITO), silicon, polydimethylsiloxane (PDMS), polystyrene, polyolefins, such as Poly(methylpentene) (PMP) and Zeonor™, cyclic olefin copolymer such as Topas™, polymethylmethacrylate (PMMA), other plastics, titanium, gold, other metals, or other suitable materials. The surface can be flat or round, continuous or non-continuous, smooth or rough. Examples of surfaces include flow cells, sequencing flow cells, flow channels, microfluidic channels, capillary tubes, piezoelectric surfaces, wells, microwells, microwell arrays, microarrays, chips, wafers, non-magnetic beads, magnetic beads, ferromagnetic beads, paramagnetic beads, superparamagnetic beads, and polymer gels.

Initiator Species Attachment

The methods and compositions provided in this disclosure can comprise initiator species for bonding to a support surface. In some cases, the initiator species comprises at least one organosilane. The organosilane can comprise one surface-bonding group, resulting in a mono-pedal structure. The organosilane can comprise two surface-bonding groups, resulting in a bi-pedal structure. The organosilane can comprise three surface-bonding groups, resulting in a tri-pedal structure. The surface bonding group can comprise MeO_3Si (e.g. see FIG. 1, item [0100]). The surface bonding group can comprise $(\text{MeO})_3\text{Si}$. The surface bonding group can comprise $(\text{EtO})_3\text{Si}$. The surface bonding group can comprise $(\text{AcO})_3\text{Si}$. The surface bonding group can comprise $(\text{Me}_2\text{N})_3\text{Si}$. The surface bonding group can comprise $(\text{HO})_3\text{Si}$. For cases where the organosilane comprises multiple surface bonding groups, the surface bonding groups can be the same or can be different. The organosilane can comprise the silane reagent shown in FIG. 1. In some cases, the initiator species comprises at least one organophosphonic acid, wherein the surface bonding group comprises $(\text{HO})_2\text{P}(=\text{O})$. The organophosphonic acid can comprise one surface-bonding group, resulting in a mono-pedal structure. The organophosphonic acid can comprise two surface-bonding groups, resulting in a bi-pedal structure. The organophosphonic acid can comprise three surface-bonding groups, resulting in a tri-pedal structure.

Silane treatment of substrates (e.g., glass substrates) can be performed with a silane solution, such as a solution of

silane in ethanol, water, or a mixture thereof. Prior to treatment with a silane solution, a substrate can be cleaned. Cleaning can be performed by immersion in sulfuric-peroxide solution. For attachment of an initiator species to a plastic substrate, a thin film of silica can be applied to the surface. Silica can be deposited by a variety of methods, such as vacuum deposition methods including but not limited to chemical vapor deposition (CVD), sputtering, and electron-beam evaporation. Silane treatment can then be performed on the deposited silica layer.

Surface-Initiated Polymerization (SIP)

The methods and compositions provided in this disclosure can comprise forming a polymer coating from surface-bound initiator species. The resulting polymer coatings can comprise linear chains. The resulting polymer coatings can comprise lightly branched chains. The polymer coatings can form polymer brush thin-films. The polymer coatings can include some cross-linking. The polymer coatings can form a graft structure. The polymer coatings can form a network structure. The polymer coatings can form a branched structure. The polymers can comprise homogenous polymers. The polymers can comprise block copolymers. The polymers can comprise gradient copolymers. The polymers can comprise periodic copolymers. The polymers can comprise statistical copolymers.

Polymer coatings can comprise polymer molecules of a particular length or range of lengths. Polymer molecules can have a length of at least 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, 100, 110, 120, 130, 140, 150, 160, 170, 180, 190, 200, 250, 300, 350, 400, 450, or 500 backbone atoms or molecules (e.g., carbons). Polymer molecules can have a length of at most 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, 100, 110, 120, 130, 140, 150, 160, 170, 180, 190, 200, 250, 300, 350, 400, 450, or 500 backbone atoms or molecules (e.g., carbons). Polymer molecules can have a length of at least 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, 100, 110, 120, 130, 140, 150, 160, 170, 180, 190, 200, 250, 300, 350, 400, 450, or 500 monomer units (e.g., acrylamide molecules). Polymer molecules can have a length of at most 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, 100, 110, 120, 130, 140, 150, 160, 170, 180, 190, 200, 250, 300, 350, 400, 450, or 500 monomer units (e.g., acrylamide molecules).

The polymer can comprise polyacrylamide (PA). The polymer can comprise polymethylmethacrylate (PMMA). The polymer can comprise polystyrene (PS). The polymer can comprise polyethylene glycol (PEG). The polymer can comprise polyacrylonitrile (PAN). The polymer can comprise poly(styrene-*r*-acrylonitrile) (PSAN). The polymer can comprise a single type of polymer. The polymer can comprise multiple types of polymer. The polymer can comprise any of the polymers described in “Ayres, N. (2010). Polymer brushes: Applications in biomaterials and nanotechnology. *Polymer Chemistry*, 1(6), 769-777,” or in “Barbey, R., Lavanant, L., Paripovic, D., Schuwer, N., Sugnaux, C., Tugulu, S., & Klok, H. A. (2009). Polymer brushes via surface-initiated controlled radical polymerization: synthesis, characterization, properties, and applications. *Chemical reviews*, 109(11), 5437-5527.”

The polymerization can comprise methods to control polymer chain length, coating uniformity, or other properties. The polymerization can comprise controlled radical

polymerization (CRP). The polymerization can comprise atom-transfer radical polymerization (ATRP). The polymerization can comprise reversible addition fragmentation chain-transfer (RAFT). The polymerization can comprise living polymerization processes, including those described in “Ayres, N. (2010). Polymer brushes: Applications in biomaterials and nanotechnology. *Polymer Chemistry*, 1(6), 769-777,” or in “Barbey, R., Lavanant, L., Paripovic, D., Schuwer, N., Sugnaux, C., Tugulu, S., & Klok, H. A. (2009). Polymer brushes via surface-initiated controlled radical polymerization: synthesis, characterization, properties, and applications. *Chemical reviews*, 109(11), 5437-5527.”

Incorporation of Biomolecules

Biomolecules can be coupled to the polymer coatings described in this disclosure. The biomolecules can comprise antibodies. The biomolecules can comprise proteins. The biomolecules can comprise peptides. The biomolecules can comprise enzymes. The biomolecules can comprise aptamers. The biomolecules can comprise oligonucleotides.

Oligonucleotides can be coupled to the polymer coatings described in this disclosure. The oligonucleotides can comprise primers. The oligonucleotides can comprise cleavable linkages. Cleavable linkages can be enzymatically cleavable. The oligonucleotides can comprise at least 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 25, 30, 35, 40, 45, 50, 55, or 60 bases. The oligonucleotides can vary in length, such as from 3 to 5 bases, from 1 to 50 bases, from 6 to 12 bases, from 8 to 12 bases, from 15 to 25 bases, from 25 to 35 bases, from 35 to 45 bases, or from 45 to 55 bases. The individual oligonucleotides coupled to the coatings can differ from each other in length.

Biomolecules (e.g., oligonucleotides) can be incorporated into the polymer coatings during the polymerization process. For example, 5'-acrydite-modified oligonucleotides chains can be added during the polymerization process to allow the incorporation of the oligonucleotides into the polymerizing polyacrylamide structure. In some cases, oligonucleotides are coupled to the polymer coating at the 5' end. In some cases, oligonucleotides are coupled to the polymer coating at the 3' end. In some cases, some oligonucleotides are coupled to the polymer coating at the 3' end and some oligonucleotides are coupled to the polymer coating at the 5' end.

Biomolecules (e.g., oligonucleotides) can be incorporated into the polymer coatings after the polymerization process. For example, reactive sites can be added to the polymer structure during the polymerization process. Biomolecules can be incorporated at the reactive sites subsequent to the polymerization. The reactive sites can comprise bromoacetyl sites. The reactive sites can comprise azides. The reactive sites can comprise sites compatible with azide-alkyne Huisgen cycloaddition.

Biomolecules (e.g., oligonucleotides) can be incorporated into the polymer coatings in a controlled manner, with particular biomolecules located at particular regions of the polymer coatings. Biomolecules can be incorporated into the polymer coatings at random, with particular biomolecules randomly distributed throughout the polymer coatings.

In some instances a composition of the invention comprises a surface, a polyacrylamide coating covalently bound to said surface; and at least one oligonucleotide coupled to said polyacrylamide coating. In other instances, the surface includes at least 1, 10, 100, 10,000, 100,000, 1,000,000, 10,000,000, 100,000,000, or 1,000,000,000 oligonucleotides coupled to the polyacrylamide coating.

Modification of Physicochemical Characteristics of Polymer Coating

The polymer coatings described in this disclosure can have their physicochemical characteristics modulated. This modulation can be achieved by incorporating modified acrylamide monomers during the polymerization process.

In some cases, ethoxylated acrylamide monomers can be incorporated during the polymerization process. Ethoxylated acrylamide monomers can be incorporated by being present in the polymerization solution. The ethoxylated acrylamide monomers can comprise monomers of the form $\text{CH}_2=\text{CH}-\text{CO}-\text{NH}(\text{---CH}_2\text{---CH}_2\text{---O---})_n\text{H}$. The ethoxylated acrylamide monomers can comprise hydroxyethyl acrylamide monomers. The ethoxylated acrylamide monomers can comprise ethylene glycol acrylamide monomers. The ethoxylated acrylamide monomers can comprise hydroxyethylmethacrylate (HEMA). The ethoxylated acrylamide monomers can comprise N-(2-hydroxyethyl)acrylamide. The incorporation of ethoxylated acrylamide monomers can result in a more hydrophobic polyacrylamide surface coating.

In some cases, phosphorylcholine acrylamide monomers can be incorporated during the polymerization process. The phosphorylcholine acrylamide monomers can comprise monomers of the structure shown in FIG. 2. The phosphorylcholine acrylamide monomers can comprise other phosphorylcholine acrylamide monomers. Phosphorylcholine acrylamide monomers can be incorporated by being present in the polymerization solution.

In some cases, betaine acrylamide monomers can be incorporated during the polymerization process. The betaine acrylamide monomers can comprise monomers of the structure shown in FIG. 3. Betaine acrylamide monomers can be incorporated by being present in the polymerization solution.

The polymer coating can be of uniform thickness. The polymer coating can be of varying thickness over its area. The polymer coating can be, on average, at least 1 μm thick. The polymer coating can be at least 2 μm thick. The polymer coating can be at least 3 μm thick. The polymer coating can be at least 5 μm thick. The polymer coating can be at least 10 μm thick. The polymer coating can be at least 15 μm thick. The polymer coating can be at least 20 μm thick. The polymer coating can be at least 25 μm thick. The polymer coating can be at least 30 μm thick. The polymer coating can be at least 40 μm thick. The polymer coating can be at least 50 μm thick. The polymer coating can be at least 75 μm thick. The polymer coating can be at least 100 μm thick. The polymer coating can be at least 150 μm thick. The polymer coating can be at least 200 μm thick. The polymer coating can be at least 300 μm thick. The polymer coating can be at least 400 μm thick. The polymer coating can be at least 500 μm thick. The polymer coating can be between about 1 μm and about 10 μm thick. The polymer coating can be between about 5 μm and about 15 μm thick. The polymer coating can be between about 10 μm and about 20 μm thick. The polymer coating can be between about 30 μm and about 50 μm thick. The polymer coating can be between about 10 μm and about 50 μm thick. The polymer coating can be between about 10 μm and about 100 μm thick. The polymer coating can be between about 50 μm and about 100 μm thick. The polymer coating can be between about 50 μm and about 200 μm thick. The polymer coating can be between about 100 μm and about 300 μm thick. The polymer coating can be between about 100 μm and about 500 μm thick.

Reactions

The polymer coatings described in this disclosure can be used in performing reactions. The reactions performed can be enzymatic. The reagents for the reactions performed can comprise nucleic acids. The reactions can comprise digestion reactions. The reactions can comprise extension reactions such as primer extension, or overlap extension. The reactions can comprise amplification reactions, such as polymerase chain reaction (PCR) and variants thereof (such as multiplex PCR, nested PCR, reverse transcriptase PCR (RT-PCR), semi-quantitative PCR, quantitative PCR (qPCR) or real time PCR, touchdown PCR, or assembly PCR), nucleic acid sequence based amplification (NASBA) (see e.g., "Compton, J (1991). Nucleic acid sequence-based amplification. *Nature* 350 (6313): 91-2."), strand displacement assay (SDA) (see e.g., U.S. Pat. No. 5,712,124, "Strand displacement amplification"), and loop mediated isothermal amplification (LAMP) (see e.g., U.S. Pat. No. 6,410,278, "Process for synthesizing nucleic acid"). The reactions can comprise transcription reactions, such as in vitro transcription. The reactions can comprise sequencing reactions, such as BAC-based sequencing, pyrosequencing, sequencing by synthesis, or any method described in "Mardis, E. R. (2008). Next-generation DNA sequencing methods. *Annu. Rev. Genomics Hum. Genet.*, 9, 387-402."

The polymer coatings described in this disclosure can be robust. The robustness of the polymer coatings can be exhibited by the durability, the resistance to degradation, or the level of attachment of the coating after being subjected to certain conditions. The robustness of the polymer coatings can be exhibited by the number or percentage of biomolecules (e.g., oligonucleotides) molecules coupled to the polymer coating which remain coupled to the polymer coating after being subjected to certain conditions. Conditions can include but are not limited to duration of time, a temperature or set of temperatures, presence of chemicals (e.g., acids, bases, reducing agents, oxidizing agents), mechanical forces (e.g. stress, strain, vibrations, high pressures, vacuums), combinations of conditions, or repeated cycles of conditions or combinations of conditions (e.g. reaction cycles comprising temperatures and use of chemicals). Durations of time can comprise at least 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 20, 30, 40, or 50 minutes, at least 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22, or 23 hours, at least 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, or 13 days, or at least 2, 3, 4, 5, 6, 7, 8, 9, 10, 12, 14, 16, 18, 20, 22, 24, 26, 28, 30, 40, 50, or 60 weeks. Temperatures can comprise at least 0, 5, 10, 15, 20, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, or 100° C. Temperatures can comprise at most 0, 5, 10, 15, 20, 25, 30, 35, 40, 45, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, or 100° C. Chemicals can comprise strong acids, weak acids, strong bases, weak bases, strong oxidizers, weak oxidizers, strong reducers, weak reducers, enzymes, monomers, polymers, buffers, solvents, or other reagents. Cycles of conditions can comprise at least 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31, 32, 33, 34, 35, 36, 37, 38, 39, 40, 41, 42, 43, 44, 45, 46, 47, 48, 49, 50, 55, 60, 65, 70, 75, 80, 85, 90, 95, 100, 125, 150, 175, 200, 250, 300, 350, 400, 450, 500, 600, 700, 800, 900, 1000, 2000, 3000, 4000, 5000, 6000, 7000, 8000, 9000, or 10,000 cycles. In some embodiments, the polymer coatings herein are used to perform at least 10, 20, 30, 40, 50, 60, 70, 80, 90, 100, 200, 300, 400, 500, 600, 700, 800, 900, or 1000 cycles of conditions, and wherein at least 50, 60, 70, 80, 90, 91, 92,

93, 94, 95, 96, 97, 98, 99, 99.5 or 99.9% the polymer chains remain completely intact and bonded to said surface after the cycles.

In some embodiments, the polymer coatings herein are used as a solid support to perform sequencing by synthesis (SBS). In SBS, a target polynucleotide sequence can be determined by generating its complement using the polymerase reaction to extend a suitable primer, and characterizing the successive incorporation of bases that generate the complement. The target sequence is, typically, immobilized on a solid support. Each of the different bases A, T, G or C is then brought, by sequential addition, into contact with the target, and any incorporation events detected via a suitable label attached to the base. In contrast to the prior art methods, the present invention requires the presence of a polymerase enzyme that retains a 3' to 5' exonuclease function, which is induced to remove an incorporated labeled base after detection of incorporation. A corresponding non-labeled base can then be incorporated into the complementary strand to allow further sequence determinations to be made. Repeating the procedure allows the sequence of the complement to be identified, and thereby the target sequence also. In some embodiments, the polymer coatings herein are used to perform at least 10, 20, 30, 40, 50, 60, 70, 80, 90, 100, 200, 300, 400, 500, 600, 700, 800, 900, or 1000 cycles of sequencing by synthesis (SBS), for example as described by the methods of U.S. Pat. No. 6,833,246, and wherein at least 50, 60, 70, 80, 90, 91, 92, 93, 94, 95, 96, 97, 98, 99, 99.5 or 99.9% the polymer chains remain completely intact and bonded to said surface after the SBS. Prior to the SBS cycles, the polymer coating can have coupled to it at least 10, 20, 50, 100, 200, 500, 1,000, 2,000, 5,000, 10,000, 20,000, 50,000 or 100,000, 200,000, 500,000, 1,000,000, 2,000,000, 5,000,000, 10,000,000, 20,000,000, 100,000,000, 200,000,000, 500,000,000, or a billion nucleic acid molecules. Prior to the SBS cycles, the polymer coating can have nucleic acid molecules arranged on it at an areal density of at least about 10, 20, 50, 100, 200, 500, 1,000, 2,000, 5,000, 10,000, 20,000, 50,000, 100,000, 1,000,000, 1×10^7 , 5×10^7 , 1×10^8 , 5×10^8 , 1×10^9 , 5×10^9 , 1×10^{10} , 5×10^{10} , or 1×10^{11} molecules per square micrometer. In some cases, prior to the SBS cycles, the polymer coating has nucleic acid molecules arranged on it at an areal density of about 1×10^2 to about 1×10^6 per square micrometer. In some cases, prior to the SBS cycles, the polymer coating has nucleic acid molecules arranged on it at an areal density of about 5×10^2 to about 5×10^4 per square micrometer. In some cases, prior to the SBS cycles, the polymer coating has nucleic acid molecules arranged on it at an areal density of about 1×10^3 to about 1×10^4 per square micrometer.

In some embodiments, the polymer coatings herein are used to perform PCR on nucleic acid polymer chains bound to the coating. PCR, for example, can include multiple cycles, wherein each cycle includes a denaturation step, an annealing step, and an extension or elongation step. The denaturation step can comprise subjecting the nucleic acids to a temperature of at least about 85° C., 86° C., 87° C., 88° C., 89° C., 90° C., 91° C., 92° C., 93° C., 94° C., 95° C., 96° C., 97° C., or 98 OC. The denaturation step can comprise duration of at least about 15 seconds, 20 seconds, 25 seconds, 30 seconds, 35 seconds, 40 seconds, or 45 seconds. The annealing step can comprise subjecting the nucleic acids to a temperature of at least about 50° C., 51° C., 52° C., 53° C., 54° C., 55° C., 56° C., 57° C., 58° C., 59° C., 60° C., 61° C., 62° C., 63° C., 64° C., or 65 OC. The annealing step can comprise duration of at least about 15 seconds, 20 seconds, 25 seconds, 30 seconds, 35 seconds, 40 seconds, or 45

seconds. The extension or elongation step can comprise a temperature of at least about 70° C., 71° C., 72° C., 73° C., 74° C., 75° C., 76° C., 77° C., 78° C., 79° C., or 80° C. The extension or elongation step can comprise duration of at least about 30 seconds, 40 seconds, 50 seconds, 60 seconds, 70 seconds, 80 seconds, 90 seconds, 100 seconds, 110 seconds, or 120 seconds. The polymer coatings herein can be used to perform at least 10, 20, 30, 40, 50, 60, 70, 80, 90, or, 100 cycles of polymerase chain reaction (PCR), and wherein at least 50, 60, 70, 80, 90, 91, 92, 93, 94, 95, 96, 97, 98, 99, 99.5 or 99.9% the polymer chains remain completely intact and bonded to said surface after the final PCR cycle. Prior to the PCR cycles, the polymer coating can have coupled to it at least 10, 20, 50, 100, 200, 500, 1,000, 2,000, 5,000, 10,000, 20,000, 50,000 or 100,000, 200,000, 500,000, 1,000,000, 2,000,000, 5,000,000, 10,000,000, 20,000,000, 100,000,000, 200,000,000, 500,000,000, or a billion nucleic acid molecules. Prior to the PCR cycles, the polymer coating can have nucleic acid molecules arranged on it at a density of at least 10, 20, 50, 100, 200, 500, 1,000, 2,000, 5,000, 10,000, 20,000, 50,000, 100,000, 1,000,000, 1×10^7 , 5×10^7 , 1×10^8 , 5×10^8 , 1×10^9 , 5×10^9 , 1×10^{10} , 5×10^{10} , or 1×10^{11} molecules per square micrometer. In some cases, prior to the PCR cycles, the polymer coating has nucleic acid molecules arranged on it at an areal density of about 1×10^2 to about 1×10^6 per square micrometer. In some cases, prior to the PCR cycles, the polymer coating has nucleic acid molecules arranged on it at an areal density of about 5×10^2 to about 5×10^4 per square micrometer. In some cases, prior to the PCR cycles, the polymer coating has nucleic acid molecules arranged on it at an areal density of about 1×10^3 to about 1×10^4 per square micrometer.

Advantages

Use of initiator species, such as silanes, with multiple bonding groups can provide high thermal and hydrolytic stability (see, e.g., U.S. Pat. No. 6,262,216). Such stability can increase the durability of the coating through repeated cycles of reactions or other processing.

Use of surface coatings as described herein can provide a more enzymatically compatible or favorable environment than that provided by an uncoated surface. Surface coatings with modulated physicochemical characteristics as described herein can provide advantages to use for conducting enzymatic reactions on, near, or on molecules bound to the surfaces. The advantages can comprise a reduction in non-specific binding to the surface. The advantages can comprise an optimal environment for enzymes, such as polymerases. For example, neutral hydrophilic polymers and linking groups can provide favorable environments for enzymes.

EXAMPLES

Example 1—Production of a Flat Surface Array

Initiator silanes of the structure shown in FIG. 1 are bound to a flat silica substrate in the presence of EtOH, forming di-podal surface polymer initiation sites. A mixture of acrylamide and ethoxylated acrylamide, together with acrydite-modified oligonucleotides, undergoes atom-transfer radical polymerization (ATRP) on the substrate in the presence of CuBr, PMDETA, and H₂O. This forms a covalently-bonded, lightly-crosslinked polyacrylamide surface coating bound to the surface initiator sites, with thickness between about 50 nm and about 200 nm, with oligonucleotides incorporated into the structure (see FIG. 4).

11

Example 2—Use of a Flat Surface Array in Sequencing


A polyacrylamide coated substrate is prepared as described in Example 1. DNA to be sequenced is bound to the oligonucleotides incorporated into the polymer structure. Sequencing by synthesis reagents are added to the substrate and sequencing by synthesis is performed for 40 cycles. At least 90% of polymer chains remain intact and bonded to the surface.

Example 3—Use of a Flat Surface Array in DNA Amplification


A polyacrylamide coated substrate is prepared as described in Example 1. DNA to be amplified is bound to the oligonucleotides incorporated into the polymer structure. Polymerase chain reaction (PCR) reagents are added to the substrate and PCR is performed for 30 cycles. At least 90% of polymer chains remain intact and bonded to the surface.

Example 4—Synthesis of Azido-PEG4-N,N-Bis(3-(Trimethoxysilyl)Propyl)Carbamate

Azido-PEG4-alcohol (BroadPharm, 220 mg; 1.0 mmol) was dried by co-evaporating twice with 2 ml CH₃CN, then combined with diphosgene (200 mg; 1.0 mmol) in 1 ml of CH₂Cl₂ under N₂. After standing overnight at ambient temperature, the solvent was evaporated to obtain 280 mg of the product as a pale yellow oil, which was used without further purification. ¹H-NMR (CDCl₃): δ (ppm) 4.46 (2H, t J=2.8 Hz; CH₂OC(O)Cl); 3.79 (2H, t J=4.5 Hz; CH₂CH₂N₃); 3.68-3.70 (10H, m, CH₂OCH₂); 3.41 (2H, t J=5.2 Hz, CH₂N₃).




Bis(trimethoxysilylpropyl)amine (342 mg/320 uL; 1.0 mmol) and DIEA (136 mg/182 uL; 1.05 mmol) were combined in 1 ml dry ether under N₂ and cooled on ice to 0-4° C. The azido-PEG4 chloroformate (280 mg; 1.0 mmol) was dissolved in 1 ml dry ether and added dropwise via syringe, and then stirring was continued at ambient temperature overnight. Another 2 ml of dry ether was added, and the solution was quickly filtered and evaporated to yield the silane as a light yellow oil (~550 mg). ¹H-NMR (CD₃OD): δ (ppm) 4.20-4.24 (2H, br m, CH₂OC(O)N<); 3.67-3.74 (13H, m, CH₂OCH₂); 3.39 (2H, t J~5.0 Hz, CH₂N₃); 3.35 (21H, s, CH₃OSi); 3.22-3.28 (4H, br m, —CH₂NC(O)O—); 1.60-1.70 (4H, br m, C—CH₂—C); 0.55-0.65 (4H, br m, C—CH₂—Si).



12

Example 5—Synthesis of N-(3-(Bromoacetamido)propyl)methacrylamide

N-(3-aminopropyl)methacrylamide hydrochloride (Polysciences; 360 mg; 2.0 mmol) and N-(bromoacetoxy)succinimide (Broad Pharm; 570 mg; 2.4 mmol) were combined in 10 mL dry CH₂Cl₂ under N₂ and cooled to -10° C. with ice-MeOH. Diisopropylethylamine (Aldrich, 800 uL; 4.2 mmol) was then added dropwise while stirring. The solution was stirred for another 30 min cold, then for 3 h at rm temp. The solution was diluted with 40 ml ethyl acetate, and washed successively with 12 ml each of 1M HCl; 0.1M NaOH; and then brine. The organic phase was dried with MgSO₄ and evaporated to yield 220 mg (~40%) of 3:1 mixture of bromo-, and chloroacetylated products as an off-white solid. ¹H-NMR (acetone-d₆): δ (ppm) 7.70 (1H, br s, NH_a); 7.40 (1H, br s, NH_b); 5.71-5.73 (1H, br m, CH=C); 5.30-5.32 (1H, m, CH'=C); 4.08 (0.5H, s, CH₂Cl); 3.89 (1.5H, s, CH₂Br); 3.24-3.32 (4H, m, CH₂N); 1.91-1.93 (3H, br m, CH₃); 1.68 (2H, br qnt, J=6.4 Hz; H₂'CCH₂CH₂"). LC-MS (ESI): 5.7 min: 242, 243, 244 (10:1:3; M.Na⁺/chloro); 219, 220, 221 (10:1:3; M.H⁺/chloro); 134, 135, 136 (10:0.6:3; M—CH₂=C(Me)CONH/chloro); 126, 127 (10:1; M—Cl/BrCH₂CCONH⁻). 5.9 min: 286, 287, 288, 289 (10:1:10:1; M.Na⁻/bromo); 263, 265, 266 (10:10:1; M.H⁺/bromo); 178, 179, 180, 181 (10:0.6:10:0.6; M—CH₂=C(Me)CONH⁻/bromo); 126, 127 (10:1; M—Cl/BrCH₂CCONH⁻).




Example 6—Synthesis of N-(4-Azidobutyl)methacrylamide

4-Azido-1-butylamine (Synthonix; 1.1 g; 8.75 mmol) was combined with DIEA (1.22 g; 9.5 mmol) in 15 mL of dry ethyl acetate in a 50 mL flask equipped w/ stirbar & dropping funnel and flushed with dry N₂. The solution was cooled to 2° C. on an ice-waterbath, and a solution of methacryloyl chloride (0.96 g; 9.2 mmol) in 5 ml dry ether was added dropwise with stirring over 30 min. The ice bath was removed, another 15 ml of dry ethyl acetate was added, and stirring was continued at ambient temperature overnight. The solids were removed by filtration and the combined filtrates were washed twice w/ 10 ml water, once w/

13

brine, then dried (MgSO₄) evaporated in vacuo to obtain 1.50 g (93%) product as an orange liquid. ¹H-NMR (CDCl₃): δ (ppm) 5.92-5.83 (1H, br s, NH); 5.68 (1H, t J=0.8 Hz; =CH_a); 5.68 (1H, m, =CH_b); 3.45 (4H, br m, NCH₂); 1.97 (3H, t J=1.4 Hz, CH₃); 1.69-1.60 (4H, br m, C—CH₂—C). MS (ESI): 126.2 (M-CH₂N₃); 183.2 (M.H⁺); 205.2 (M.Na⁺). The product was used within 10 days, as decomposition with evolution of N₂ was noted after 2-3 weeks storage at 4° C. by NMR.



Example 7—Silanation of Flowcell Surfaces

For most experiments, the flowcells used were flat “capillary micro glass slides” made from Corning® 7740 borosilicate, low expansion, type I glass (p/n 63825-05, EM Sciences, Hatfield, Pa.). A short length of 0.5 mm ID heat-shrink PTFE tubing was sealed to both ends of the capillaries to provide leak-proof connection to manifolds, syringes, etc. For some experiments, “refurbished” Illumina MiSeq™ flowcells were employed. These were stripped of indigenous surface coatings with 200 mM sodium persulfate at 65° C. for 18 hr, followed by 1M KOH/65° C./6 hr, rinsing with deionized water and drying with a stream of nitrogen.

Prior to silanation, all capillary flowcell surfaces were cleaned by immersion in sulfuric-peroxide solution (Nanostrip, Cyantek Corp., Fremont Calif.) for 16-18 hr at 25° C., then rinsed thoroughly with deionized water and dried with a stream of nitrogen. The cleaned flowcells were stored under nitrogen and silanated within 48 hours. Silanation was performed by filling the flowcell with a freshly prepared 2% (wt/vol) solution of the appropriate silane in 95:5 ethanol-water, and incubating for 4-18 hours at room temperature. The flowcells were then rinsed thoroughly with ethanol and deionized water; dried with nitrogen, and stored at ambient temperature.

Example 8—Oligonucleotide Primer Immobilization by Surface-Initiated Acrylamide ATRP

Flowcells for SI-ATRP were silanated as described in Example 7, with 2-Bromo-2-methyl-N,N-bis-(3-trimethoxysilylpropyl)propionamide (see, e.g., US 2011/0143967).

Dry-down Primers: Equivalent amounts of 5'-acrydite modified primers FWD (4 uL, 1 mM) and REV (4 uL, 1 mM) were combined in a 0.9 mL conical-tip HPLC vial. The solutions were reduced to dryness on a Speed-Vac evaporator at ambient temperature (10-15 minutes). The vial containing dried primers was tightly closed with a septum-sealed screw cap and connected to a vacuum/N₂ manifold via an 18-gauge syringe needle. The vial was deoxygenated 5 cycles of alternating vacuum/nitrogen refill through a syringe needle.

Deoxygenate Flowcell: The flowcell to be used for SI-ATRP was deoxygenated by purging with dry nitrogen.

Deoxygenate Solvent: In another vial, a solvent mixture composed of 28% methanol in water (v:v) was deoxygenated by sparging continuously with nitrogen for 30 minutes,

14

Preparation of Catalyst/Acrylamide Solution: CuBr (6.8 mg, 47.4 umol) and CuBr₂ (3.9 mg, 17.5 umol) were weighed and placed in a 20 mL septum-capped vial containing a magnetic stirring bar. The vial was connected to a vacuum/nitrogen manifold and deoxygenated carefully with three cycles of evacuation-nitrogen back-fill. Then a portion of the deoxygenated solution (14.5 mL) was transferred to the vial containing the copper salts via gas-tight syringe. Finally, acrylamide (42.5 mg, 600 umol) and PMDETA (14 uL, 67.2 umol) were added, and the solution was stirred vigorously while sparging with nitrogen for another 15 minutes. It was occasionally necessary to sonicate the solution briefly to disperse the CuBr solid to obtain a light blue homogeneous solution.

Transfer Polymerization Solution to Flowcell: The dried-down primers were reconstituted in deoxygenated catalyst/acrylamide solution (20 uL), which was transferred via gas tight syringe. The resulting solution was transferred to the pre-purged flowcell from step 3, filling it completely. The ends of the flowcell were sealed with parafilm, and the flowcell was maintained at ambient temperature for 24-48 hours in an anaerobic environment.

Wash and Storage: The flowcell was flushed with 28% methanol-water, and 1×TE buffer (~1 mL/ea) and stored at 4° C.

Example 9—Oligonucleotide Primer Immobilization Via Solution-Initiated FRP Grafting of Acrylamide/Bromoacetyl-Acrylamide

Flowcell surfaces were silanated with 3-(acrylamido)propyltrimethoxysilane (Gelest, Inc).

Purge Flowcell: The flowcell to be used for FRP was deoxygenated by purging with dry nitrogen.

Solution Preparation and Polymerization: A solution of acrylamide (0.0713 g, 1 mmol) and N-(3-bromoacetamidopropyl)methacrylamide (6.4 mg, 0.024 mmol) in Milliq water (5 g) in a vial was capped with rubber septum-sealed cap. The solution was deoxygenated by sparging with nitrogen for 30 minutes. Polymerization was initiated by adding a solution of potassium persulfate (2.5 mg, 0.0093 mmol in degassed water 50 uL) and neat tetramethylenediamine (4.45 mg, 0.038 mmol). The resulting solution was transferred immediately into the flowcell, filling it completely. The ends of the flowcell were sealed with parafilm, and the flowcell was maintained at ambient temperature for 60-80 minutes in an anaerobic environment. Polymerization was terminated by purging the flowcell with 4-6 mL of water, followed by 1 mL of 6×SSPE to remove unbound polymer. The flowcell was stored in 6×SSPE at 4° C.

Primer Conjugation: A combined solution of FWD (2.5 uL, 1 mM) and REV (2.5 uL, 1 mM) 5'-phosphorothioate-modified primers was placed in a 0.9 mL conical-tip HPLC vial. The solution was reduced to dryness on a Speed-Vac evaporator at ambient temperature (10-15 minutes) and then redissolved in 6×SSPE (20 uL). The storage solution was removed from the flowcell and replaced with the primer solution via a gas-tight syringe. The ends of the flowcell were sealed tightly with parafilm, and the flowcell was maintained at 55° C. for 2 hours. The flowcell was allowed to cool to ambient temperature and then rinsed with Milliq water, 6×SSPE, and 1×TE (1 mL per rinse). The flowcell containing 1×TE was sealed with parafilm and stored at 4° C.

Example 10—Direct Immobilization of Primers on Silanated Flowcell Surface Using Click Chemistry

Flowcell surfaces were cleaned by immersion in sulfuric-peroxide solution (Nanostrip, Cyantek Corp., Fremont

15

Calif.) for 16-18 hr at 25° C., then rinsed thoroughly with deionized water and dried with a stream of nitrogen. Flowcells were stored under nitrogen and silanated within 48 hours with a freshly prepared 2% (wt/vol) solution of Azido-PEG4-N,N-bis(3-(trimethoxysilyl)propyl)carbamate in 95:5 ethanol-water for 18 hours. The flowcells were then rinsed thoroughly with ethanol and deionized water; and dried with nitrogen. A solution containing 100 uM each of the 5'-alkynyl-modified oligonucleotide primers FWD and REV, 5 mM CuI, and 10 mM tris-(3-hydroxypropyltriazolylmethyl)amine (THPTA) in 0.1M Tris buffer (pH 7.0) was added and maintained at 22° C. for 18 hours, after which the oligonucleotide solution was removed and the flowcell was rinsed with deionized water, dried & stored at 4° C.

Example 11—Immobilization Analysis by Hybridization

Successful primer attachment was confirmed with a 5'-CY3-labeled oligonucleotide hybridization target complementary to the FWD primer ("FWD"): the flowcell was filled with 250 nM target oligo in 6×SSPE buffer pH 7.4, incubated for 1 h at 55° C., cooling to 25° C., and then washed with 4-5 volumes 6×SSPE. Surface fluorescence was measured with a CCD-based imaging fluorescence microscope (LED bb excitation; >640 nm emission filter). The hybridization target solution was then removed and the flowcell was washed out with 20 volumes of formamide at 55° C., and stored at 4° C. in nuclease-free water.

Example 12—Solid Phase DNA Amplification and Cluster Generation

Prepared flowcells (e.g., those prepared in previous examples) were placed on a programmable thermo-fluidic station (purpose built CentiPD). An actively cooled Peltier thermoelectric module (Laird), NTC thermistor temperature sensors and a programmable PID Controller (Laird) provided thermal control. The range of achievable temperatures was 20-100° C. On the fluidic side, a 250 ul syringe pump (Cavro) pulled a programmed volume of reagent at a specified speed through the capillary flowcell. The appropriate reagent was selected via a 24-way selector valve (VICI) with sippers leading to each of the reagent tubes. The prepared reagents Eppendorf tubes were sitting in an aluminum cooling block placed in an ice bath (to maintain them at 4° C. during the protocol time period).

A solution of 10 mM dNTPs was prepared as follows: combine 300 μL of each dNTP stock solution (stock solution concentration: 100 mM) to make 25 mM stock, then add 1000 μL of 25 mM stock to 1500 μL of 10 mM Tris pH 8.0.

An HB1 solution was prepared in 1×(~10 mL aliquot) and 5× amounts, shown in Table 1:

TABLE 1

HB1 solution			
Reagent	Stock	Final	1 RXN
H2O			7400 ul
20X SSC	20X	5X	2500 ul
Tween-20	10%	0.1%	100 ul
Total			10 ml

16

A Wash Buffer (W2) solution was prepared in 5× and 1× amounts (~10 mL aliquot), as shown in Table 2:

TABLE 2

W2 solution				
Reagent	Stock	Final	1 RXN	5 RXNS
H2O			9750 ul	48750 ul
20X SSC	20X	0.3X	150 ul	750 ul
Tween-20	10%	0.1%	100 ul	500 ul
Total			10 ml	50000 ul

Labeled Primer (FP) solution was prepared at a concentration of 5 μM by adding 15 μL of 500 μM primer stock solution to 1485 μL of HB1 solution as shown in Table 3:

TABLE 3

FP solution					
Reagent	Stock	Final	1 RXN	16 RXNS	Cost
HB1			360 ul	5760 ul	\$0
5 uM Primer	5.0 uM	0.5 uM	40 ul	640 ul	\$0
Total			400 ul	6400 ul	\$0

An Amplification Premix (APM) solution was prepared as shown in Table 4:

TABLE 4

APM Buffer solution				
Reagent	Stock	Final	1 RXN	32 RXNS
H2O			687 ul	21984 ul
10X Thermopol	10X	1X	100 ul	3200 ul
5M Betaine	5M	1M	200 ul	6400 ul
DMSO	100%	1.3%	13 ul	416 ul
Total			1000 ul	32000 ul

An Amplification Mix (AM) was prepared as shown in Table 5:

TABLE 5

AM Buffer solution					
Reagent	Stock	Final	1 RXN	16 RXNS	Cost
H2O			1756 ul	28090 ul	\$ 0
10X Thermopol	10X	1X	280 ul	4480 ul	\$ 0
5M Betaine	5M	1M	560 ul	8960 ul	\$128
DMSO	100%	1.3%	36 ul	582 ul	\$ 0
10 mM dNTPs	10 mM	0.2 mM	56 ul	896 ul	\$ 0
Bst Lg. Fragment	8 U/ul	0.32 U/ul	112 ul	1792 ul	\$444
Total			2800 ul	44800 ul	\$573

17

An Linearization Mix (LM) solution was prepared as shown in Table 6:

TABLE 6

LM solution					
Reagent	Stock	Final	1 RXN	16 RXNS	Cost
H2O			356 ul	5696 ul	\$ 0
10X Thermopol	10X	1X	40 ul	640 ul	\$ 0
USER	1 U/ul	0.01 U/ul	4 ul	64 ul	\$83
Total			400 ul	6400 ul	\$83

A Library Dilution Buffer was prepared which comprises 10 mM Tris-Cl at pH 8.5 with 0.1% Tween-20.

A dilute library was prepared as follows: 1) Stock 2 N NaOH solution was diluted to 0.1 N NaOH solution, as shown in Table 7. 2) Stock 10 nM PhiX solution was diluted to 2 nM by adding 2 μ L of PhiX to 8 μ L of Library Dilution Buffer. 3) The sample was denatured by adding 10 μ L of 0.1 N NaOH to 10 μ L of 2 nM sample solution and incubating for 5 minutes at room temperature. 4) The denatured sample was diluted to 20 μ M by adding 980 μ L of pre-chilled HB1 solution to 20 μ L of sample. 5) The diluted sample was

18

further diluted to 7 μ M by adding 650 μ L of pre-chilled HB1 solution to 350 μ L of 20 μ M sample solution. 6) The diluted sample was saved on ice until later use.

TABLE 7

0.1N NaOH solution		
Reagent	1 RXN	4 RXNS
H2O	475 ul	1900 ul
2N NaOH	25 ul	100 ul
Total	500 ul	2000 ul

A reagent plate was loaded with solutions in 2 mL Eppendorf tubes, with reagent tubes matched to appropriate CentPD sippers, as follows: Reagent 1: 950 ul HB1; Reagent 2: 950 ul APM; Reagent 3: 1300 ul AM1; Reagent 4: 1100 ul FM (Formamide 100%); Reagent 5: 1300 ul AM2; Reagent 6: 1100 ul W2; Reagent 7: 350 ul LM; Reagent 8: 400 ul NAOH (0.1 N NaOH); Reagent 9: 400 ul FP.

A prepared flowcell, such as described in previous examples, was placed on a thermo-fluidic station and a clustering protocol was initiated and run on a CentPD as described in Table 9:

TABLE 9

CentPD clustering protocol									
	Repeats	Heat Step			Wait Time [s]	Chem	Flow Step		
		Temp [$^{\circ}$ C.]	Rate [$^{\circ}$ C./s]	Time [s]			Volume [μ L]	Rate [μ L/s]	Time [s]
Initial Prime		25			60	HB1	60	4	15
						W2	60	4	15
						NAOH	60	4	15
						APM	60	4	15
						AM1	60	4	15
						AM2	60	4	15
						FM	60	1	60
						HB1	120	1	120
TMP Introduction		90				Library	150	1	150
TMP Rampdown		40	0.05	1120	80	W2	20	1	20
TMP Buffer wash						W2	100	0.5	200
First Extension						W2	100	0.5	200
						AIR	3	0.5	6
						AM1	100	1	100
						AIR	3	0.5	6
						W2	40	1	40
FE Wait		40			90				
Amp-TempRamp									
Template Strip		25				NAOH	150	0.5	300
		60				W2	150	1	150
Amplification 1	16X					FM	28	8.5	8
						APM	28	1	28
						AM1	72	4	18
Amplification 2	16X					FM	28	3.5	8
						APM	28	1	28
						AM2	72	4	18
Amplification wash		25				W2	120	2	60
Linearization Start		38			300	HB1	95	4	23.75
Linearization Cycle	5X				300	LM	150	1	150
						LM	20	1	
Linearization Finish		25				W2	150	4	37.5

TABLE 9-continued

CentPD clustering protocol									
Flow Check	Repeats	Heat Step			Wait Time [s]	Chem	Flow Step		
		Temp [° C.]	Rate [° C./s]	Time [s]			Volume [μL]	Rate [μL/s]	Time [s]
Read 1		60			300	HB1	95	4	23.75
Preparation		40				NAOH	200	1	200
		25				W2	200	1	200
						FP	200	1	200
						W2	150	1	150
						HB1	150	1	150

1) All the reagents were primed (60 μL, 4 μL/s 25° C.), last of which were HB1 and W2 buffers (Illumina nomenclature). 2) 150 μL of template was introduced at 90° C. at a rate of 1 μL/s. The template was a PhiX DNA library (7 pM in HB1, denatured, insert size 450 bp). 3) After incubating for 30 seconds, the temperature was slowly reduced to 40° C. over 18 minutes at a rate of 0.05 deg/s. 4) The excess template was washed out with 200 μL of W2 at 0.5 μL/sec, also at 40° C. 5) First extension of the grafted primers was achieved by infusing 150 μL of amplification mix (AM1) at 1 μL/s, book ended with 3 μL air bubbles in order to prevent mixing of reagents that may occur in the line in transit to the flowcell. A 90 second incubation step allows plentiful time for full template replication by Bst enzyme. 6) The flowcell is cooled to 25° C., and the template is stripped with 150 μL of 0.1N NaOH pumped at rate of 0.5 μL/s, followed by 150 μL of buffer (W2). 7) The flowcell is heated to 60° C. in preparation for isothermal amplification. 8) 32 cycles of isothermal amplification are performed by repeating these 3 steps: (a) denaturation in 100% formamide (FM) 28 μL at 3.5 μL/s; (b) pre-amplification buffer without the enzyme (APM) to remove formamide & allow for re-hybridization, 28 μL at 1 μL/s; and (c) extension of the primer with amplification mix (AM), 72 μL at 4 μL/s. 9) The amplification reagents are washed out with 120 μL of W2 and 95 μL of HB1). 10) 150 μL linearization reagent (LM) is introduced at 1 μL/s, temp 25° C. (to cut half of the amplified strands). 11) The flowcell is heated to 38° C., and incubated for 5 min (USER treatment, cutting of dU via Uracil DNA Glycosylase). 12) Fresh 20 μL of the LM solution is moved into the flowcell and incubating for 5 min, repeated five times. 13) After linearization, the temperature is reduced to 25° C., and washed with 150 μL W2 and 95 μL HB1. 14) The flowcell is denatured again with 200 μL of 0.1N NaOH and washed with 200 μL of W2. 15) Cy3 5' labeled sequencing primer (FP) complimentary to the remaining strand is introduced 200 μL at 1 μL/s. 16) The temperature is raised to 60° C. and the solution is incubated for 5 min to allow for hybridization. 17) After reducing the temperature to 40° C., excess primer is washed away with 150 μL W2. 18) After further reducing the temperature to 25° C., the flowcell is further washed with 150 μL of W2.

Images of clustered colonies were taken on a custom epi-fluorescence microscope with an Alta U-4000 CCD camera (Apogee). Since the hybridized primers were labeled on the 5' end with Cy3 fluorophore, we used Cy3-4040C filter cube (Semrock) and a 532 nm LED as the excitation light source. The images were magnified 40× with an ELWD Nikon 0.6 NA objective, rendering a field of view 375×375 μm in size.

While preferred embodiments of the present invention have been shown and described herein, it will be obvious to

those skilled in the art that such embodiments are provided by way of example only. Numerous variations, changes, and substitutions will now occur to those skilled in the art without departing from the invention. It should be understood that various alternatives to the embodiments of the invention described herein can be employed in practicing the invention. It is intended that the following claims define the scope of the invention and that methods and structures within the scope of these claims and their equivalents be covered thereby.

What is claimed is:

1. A method for performing an enzymatic reaction, comprising:

- (a) providing a substrate comprising surface-bonded initiator species comprising a silane;
- (b) conducting surface initiated polymerization of a mixture of (i) first monomers comprising acrylamide and/or ethoxylated acrylamide, each of which has no biomolecule attached to, and (ii) second monomers comprising acrydite, each of which has a biomolecule attached to, wherein said surface initiated polymerization starting from said initiator species, and coupling a plurality of said biomolecules to a polymer brush coating during said surface initiated polymerization, thereby producing said polymer brush coating with said plurality of said biomolecules coupled to said polymer brush coating; and
- (c) performing one or more enzymatic reactions with said biomolecules on said substrate; wherein the biomolecules are selected from the group consisting of: oligonucleotides and polynucleotides, wherein the one enzymatic reaction is selected from the group consisting of: polymerase chain reaction, sequencing reaction, sequencing by synthesis reaction, ligation reaction, extension reaction, and transcription reaction.

2. The method of claim 1, further comprising applying heat to said substrate.

3. The method of claim 1, wherein said polymer brush coating coupled with said plurality of biomolecules exhibits robustness wherein at least 90% of said biomolecules are retained on said surface after 40 cycles of sequencing by synthesis reactions.

4. The method of claim 1, wherein the substrate comprises at least 1,000,000 different types of biomolecules, and wherein each biomolecule is an oligonucleotide.

5. The method of claim 4, wherein said enzymatic reaction is an extension reaction.


6. A method for making a modified surface, comprising:

- (a) providing a surface;
- (b) covalently bonding initiator species to said surface, wherein said initiator species comprises a silane; and

21

(c) conducting surface initiated polymerization of a mixture of (i) first monomers comprising acrylamide and/or ethoxylated acrylamide, each of which has no biomolecule attached to, and (ii) second monomers comprising acrydite, each of which has a biomolecule attached, wherein said surface initiated polymerization starting polymer from said initiator species, thereby producing a polymer brush coating comprising a plurality of polymer chains, each of which has said biomolecule attached.

7. The method of claim 6, wherein said initiator species comprises the molecule shown below:



8. The method of claim 6, wherein said second monomers are 5' acrydite modified oligonucleotides.

9. The method of claim 1, wherein said polymer brush coating coupled with said plurality of biomolecules exhibits robustness in said polymerase chain reactions and wherein said polymerase chain reactions comprise the following reaction conditions:

22

- (a) a denaturation step at a temperature of at least 85° C. for at least 15 seconds;
 (b) an annealing step at a temperature of at least 50° C. for at least 15 seconds; and
 (c) an extension step at a temperature of at least 70° C. for at least 30 seconds.

10. The method of claim 1, wherein said first monomers comprise acrylamide.

11. The method of claim 10, wherein said first monomers further comprise N-(2-hydroxyethyl)acrylamide.

12. The method of claim 1, wherein said surface-bonded initiator species comprises 2-bromo-2-methyl-N,N-bis-(3-trimethoxysilylpropyl)propionamide.

13. The method of claim 1, wherein said surface initiated polymerization comprises atom-transfer radical polymerization (ATRP).

14. The method of claim 1, wherein said second monomers are 5' acrydite modified oligonucleotides or polynucleotides.

15. The method of claim 1, wherein said first monomers comprise ethoxylated acrylamide.

16. The method of claim 6, wherein said first monomers comprise ethoxylated acrylamide.

17. The method of claim 1, wherein robustness of said polymer brush coating coupled with said plurality of biomolecules is exhibited in said polymerase chain reaction: at least 90% of said biomolecules are retained on said surface after 25 cycles of said polymerase chain reactions.

* * * * *