

US010385518B2

(12) **United States Patent**  
**Robinson**

(10) **Patent No.:** **US 10,385,518 B2**

(45) **Date of Patent:** **\*Aug. 20, 2019**

(54) **HELICALLY-PACKAGED EXPANSION JOINT SEAL SYSTEM WITH COILING, TEAR STRIPS OR SECONDARY PACKAGING**

(71) Applicant: **Schul International Co., LLC**, Pelham, NH (US)

(72) Inventor: **Steven R. Robinson**, Windham, NH (US)

(73) Assignee: **Schul International Co., LLC**, Pelham, NH (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **16/173,823**

(22) Filed: **Oct. 29, 2018**

(65) **Prior Publication Data**

US 2019/0194880 A1 Jun. 27, 2019

**Related U.S. Application Data**

(63) Continuation of application No. 15/854,152, filed on Dec. 26, 2017, now Pat. No. 10,227,734.

(51) **Int. Cl.**

|                   |           |
|-------------------|-----------|
| <b>E01C 11/10</b> | (2006.01) |
| <b>B29D 99/00</b> | (2010.01) |
| <b>B32B 5/32</b>  | (2006.01) |
| <b>E04B 1/68</b>  | (2006.01) |
| <b>B32B 5/18</b>  | (2006.01) |
| <b>E04C 2/284</b> | (2006.01) |
| <b>E04B 1/94</b>  | (2006.01) |
| <b>B32B 7/12</b>  | (2006.01) |

(52) **U.S. Cl.**

CPC ..... **E01C 11/10** (2013.01); **B29D 99/001** (2013.01); **B32B 5/18** (2013.01); **B32B 5/32** (2013.01); **E04B 1/6801** (2013.01); **E04B 1/6812** (2013.01); **B32B 7/12** (2013.01); **E04B 1/948** (2013.01); **E04C 2/284** (2013.01)

(58) **Field of Classification Search**

CPC ..... E01C 11/10; E04B 1/6812; E04C 2/284; E04C 11/106

See application file for complete search history.

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

|              |         |                 |
|--------------|---------|-----------------|
| 3,507,735 A  | 4/1970  | Chisholm        |
| 4,767,655 A  | 8/1988  | Tschudin-Mahrer |
| 4,887,368 A  | 12/1989 | Latzke          |
| 6,685,196 B1 | 2/2004  | Baerveldt       |
| 8,317,444 B1 | 11/2012 | Hensley         |
| 8,341,908 B1 | 1/2013  | Hensley et al.  |
| 8,365,495 B1 | 2/2013  | Witherspoon     |

(Continued)

**FOREIGN PATENT DOCUMENTS**

JP 2002061794 A 2/2002

**OTHER PUBLICATIONS**

Polyethylene Foam Material; UFP Technologies; accessed Jan 28, 2019 (from <https://web.archive.org/web/20120108003656/http://www.ufpt.com:80/materials/foam/polyethylene-foam.html>).

(Continued)


*Primary Examiner* — Patrick J Maestri

(74) *Attorney, Agent, or Firm* — Crain, Caton & James, P.C.

(57) **ABSTRACT**

A foam-based expansion joint seal system packaging which facilitates transport and reduces the need for internal splices.

**20 Claims, 3 Drawing Sheets**



(56)

**References Cited**

U.S. PATENT DOCUMENTS

8,739,495 B1 6/2014 Witherspoon  
 8,813,449 B1 8/2014 Hensley et al.  
 8,813,450 B1 8/2014 Hensley et al.  
 8,870,506 B2 10/2014 Hensley et al.  
 9,068,297 B2 6/2015 Hensley et al.  
 9,200,437 B1 12/2015 Hensley et al.  
 9,206,596 B1 12/2015 Robinson  
 9,322,163 B1 4/2016 Hensley  
 9,404,581 B1 8/2016 Robinson  
 9,528,262 B2 12/2016 Witherspoon  
 9,631,362 B2 4/2017 Hensley et al.  
 9,637,915 B1 5/2017 Hensley et al.  
 9,644,368 B1 5/2017 Witherspoon  
 9,670,666 B1 6/2017 Witherspoon et al.  
 9,689,157 B1 6/2017 Hensley et al.  
 9,689,158 B1 6/2017 Hensley et al.  
 9,732,853 B2 8/2017 Kethorn et al.  
 9,739,049 B1 8/2017 Robinson  
 9,739,050 B1 8/2017 Hensley et al.  
 9,745,738 B2 8/2017 Robinson  
 9,765,486 B1 9/2017 Robinson  
 9,803,357 B1 10/2017 Robinson  
 9,840,814 B2 12/2017 Robinson  
 9,850,662 B2 12/2017 Hensley  
 9,856,641 B2 1/2018 Robinson  
 9,951,515 B2 4/2018 Robinson  
 9,963,872 B2 5/2018 Hensley et al.  
 9,982,428 B2 5/2018 Robinson  
 9,982,429 B2 5/2018 Robinson  
 9,995,036 B1 6/2018 Robinson  
 10,000,921 B1 6/2018 Robinson  
 10,060,122 B2 8/2018 Robinson  
 10,066,386 B2 9/2018 Robinson  
 10,066,387 B2 9/2018 Hensley et al.

2008/0172967 A1 7/2008 Hilburn  
 2010/0304078 A1 12/2010 Stol et al.  
 2011/0266050 A1 11/2011 Su et al.  
 2014/0219719 A1 8/2014 Hensley et al.  
 2014/0360118 A1 12/2014 Hensley et al.  
 2015/0068139 A1 3/2015 Witherspoon  
 2017/0130450 A1 5/2017 Witherspoon  
 2017/0159817 A1 6/2017 Robinson  
 2017/0191256 A1 7/2017 Robinson  
 2017/0226733 A1 8/2017 Hensley et al.  
 2017/0241132 A1 8/2017 Witherspoon  
 2017/0254027 A1 9/2017 Robinson  
 2017/0268222 A1 9/2017 Witherspoon et al.  
 2017/0292262 A1 10/2017 Hensley et al.  
 2017/0298618 A1 10/2017 Hensley et al.  
 2017/0314213 A1 11/2017 Robinson  
 2017/0314258 A1 11/2017 Robinson  
 2017/0342665 A1 11/2017 Robinson  
 2017/0342708 A1 11/2017 Hensley et al.  
 2017/0370094 A1 12/2017 Robinson  
 2018/0002868 A1 1/2018 Robinson  
 2018/0016784 A1 1/2018 Hensley et al.  
 2018/0038095 A1 2/2018 Robinson  
 2018/0106001 A1 4/2018 Robinson  
 2018/0106032 A1 4/2018 Robinson  
 2018/0119366 A1 5/2018 Robinson  
 2018/0142465 A1 5/2018 Robinson  
 2018/0148922 A1 5/2018 Robinson  
 2018/0163394 A1 6/2018 Robinson  
 2018/0171564 A1 6/2018 Robinson  
 2018/0171625 A1 6/2018 Robinson  
 2018/0202148 A1 7/2018 Hensley et al.  
 2018/0238048 A1 8/2018 Robinson

OTHER PUBLICATIONS

European Search Report for EP18211160.9, dated May 21 2019, 6pgs.




FIG. 1




FIG. 2






FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7



**HELICALLY-PACKAGED EXPANSION JOINT  
SEAL SYSTEM WITH COILING, TEAR  
STRIPS OR SECONDARY PACKAGING**

CROSS-REFERENCE TO RELATED  
APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 15/854,152 for Helically-packaged expansion joint seal system, filed Dec. 26, 2017, which is incorporated herein by reference, the benefit of and priority to are hereby claimed.

STATEMENT REGARDING FEDERALLY  
SPONSORED RESEARCH OR DEVELOPMENT

Not Applicable.

BACKGROUND

Field

The present disclosure relates generally to packaging of systems for creating a durable seal between adjacent panels, including those which may be subject to seismic or temperature expansion and contraction and/or mechanical shear. More particularly, the present disclosure is directed to a design for packaging and shaping/forming such expansion joint seal systems which facilitates transport, reduces material damage, the need for internal splices and waste.

Description of the Related Art

Construction panels come in many different sizes and shapes and may be used for various purposes, including roadways, sidewalks, and pre-cast structures, particularly buildings. Use of precast concrete panels for interior and exterior walls, ceilings and floors, for example, has become more prevalent. As precast panels are often aligned in generally abutting relationship, forming a lateral gap or joint between adjacent panels to allow for independent movement, such in response to ambient temperature variations within standard operating ranges, building settling or shrinkage and seismic activity. Moreover, these joints are subject to damage over time. Most damage is from vandalism, wear, environmental factors and when the joint movement is greater, the seal may become inflexible, fragile or experience adhesive or cohesive failure. As a result, "long lasting" in the industry refers to a joint likely to be usable for a period greater than the typical lifespan of five (5) years. Various seals have been created in the field.

Various seal systems and configurations have been developed for imposition between these panels to provide seals which provide one or more of fire protection, waterproofing, sound and air insulation. This typically is accomplished with a seal created by imposition of multiple constituents in the joint, such as silicone application, backer bars, and compressible foams.

Foam-based expansion joint seal systems are typically shipped in sticks, which often is a six-to-ten foot straight segment, or in rolls wherein the external layer is adhered to a release tape to permit the wrapping around a reel. Providing the joint seal system in a stick permits the product, in particular joint seals having a final width greater than one inch, to be compressed at the factory, i.e. pre-compressed, laterally, so the installer on site may remove the packaging and install the expansion joint seal system before it expands

beyond the gap of the expansion joint. Higher compression ratios, coupled with slower release time, facilitate the installation and function of such precompressed, stick-based expansion joint seal systems. Alternatively, the expansion joint seal may be provided on a roll, where successive layers are wrapped around a center, permitting immediate compression during wrapping.

Each shipping system has shortcomings. With the stick, the compressed product is typically encased in a shrink wrap sleeve, which shrinks when heated. Unfortunately, this is applied to each stick, which is limited in length due to shipping sizes, typically to six to ten foot sections. As a result, during shipping, the stick may be subjected to bending forces, such as when loaded on a truck over other materials, which causes the shrink wrap to crack or fail along a seal, permitting the compressed product to expand through the resultant opening and rendering the product unusable. Because the packaging is sized for conventional shipment, the sticks are typically limited to not more than ten (10) feet. Even with the size limitation the sticks are too long for easy handling which can result in damage in transit or added delivery fees. As a result, the resulting sections must be joined with a splice to fit within the actual expansion joint. Moreover, because each stick is individually packaged, when the packaging is opened, the entire stick begins to expand. That portion which exceeds the required length is often lost as it is cut off because it expands to size greater than the intended gap, therefore is discarded. With the roll, because any compression is generally radially as each successive layer is deposited, compression is possible in only one direction, but difficult to control over time due to the varying radius of the material and the potential for localized areas of higher or lower compression.

SUMMARY

The present disclosure therefore meets the above needs and overcomes one or more deficiencies in the prior art by providing a packaging of systems for creating a durable seal between adjacent panels. In particular, the present disclosure provides a foam-based expansion joint seal system which can be of longer length, shipped conventionally, facilitates constant and equal compression throughout the system, and precludes loss of large segments of material.

The disclosure provides an expansion joint seal system which includes a longitudinal body of foam in compression; a water-resistant constituent, the water-resistant constituent adhered to the longitudinal body of foam on a first surface or contained within the longitudinal body of foam in compression; and a casing helically encircling the longitudinal body of foam in compression and the water-resistant constituent.

Additional aspects, advantages, and embodiments of the disclosure will become apparent to those skilled in the art from the following description of the various embodiments and related drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

So that the manner in which the described features, advantages, and objects of the disclosure, as well as others which will become apparent, are attained and can be understood in detail; more particular description of the disclosure briefly summarized above may be had by referring to the embodiments thereof that are illustrated in the drawings, which drawings form a part of this specification. It is to be noted, however, that the appended drawings illustrate only



typical preferred embodiments of the disclosure and are therefore not to be considered limiting of its scope as the disclosure may admit to other equally effective embodiments.

In the drawings:

FIG. 1 provides an end view of one embodiment of the present disclosure.

FIG. 2 provides a side view of one embodiment of the present disclosure.

FIG. 3 provides an end view of one embodiment of the present disclosure after imposition between substrates.

FIG. 4 provides an illustration of a coiled embodiment of the present disclosure.

FIG. 5 provides an illustration of one embodiment with internal tear strips.

FIG. 6 provides an illustration of a structure for processing one embodiment of the present disclosure.

FIG. 7 provides an illustration of an alternative structure for processing one embodiment of the present disclosure.

#### DETAILED DESCRIPTION

Referring to FIG. 1, the packaging 100 of the present invention is illustrated. An expansion joint seal system 102, composed of a longitudinal body of foam 104 in compression and a water-resistant constituent 106, is surrounded by a casing 108 helically encircling the compressed longitudinal body of foam 104, typically laterally compressed, and the water-resistant constituent 106. The water-resistant constituent 106 may be adhered to the compressed longitudinal body of foam 104 on a first surface or contained within the compressed longitudinal body of foam 104, such as the elastomer coating depicted in U.S. Pat. No. 9,745,738 for Expansion Joint for Longitudinal Load Transfer, issued to Schul International Company, LLC. Because the casing 108 helically encircles the compressed longitudinal body of foam 104 and can accommodate flexing by the overlapping casing 108, the compressed longitudinal body of foam 104 may be cut to length without fear of a shrink-wrap seam failing due to flexion.

The system is particularly beneficial in connection with foam-based expansion joint seal systems, which are often supplied pre-compressed. Pre-compression of such expansion joint seal systems is desirable as installation of the uncompressed expansion joint system can be problematic given the length, often in multiple meters, resulting in long sections above the expansion joint while working in sections on centimeter basis. As the expansion joint seal system may be compressed at installation between one-fifth to one-half the original width to a final density in excess of 300 kg/m<sup>3</sup>, such installation of uncompressed product can be difficult. It is therefore desirable in the industry to provide the expansion joint seal systems compressed to a size less than the nominal expansion joint size, so the expansion joint seal can be removed from the packaging and rapidly installed before the expansion joint seal system can be relaxed and thereby contact the adjacent substrate walls. The present disclosure maintains, and may provide, such precompression with additional benefits.

To facilitate removal of the casing 108, the casing may have a casing internal surface 110 which may have a low friction coefficient. The casing internal surface 110 may be a layer of the casing 108 or may be applied to the casing 108. A casing internal surface 110 having a low coefficient of friction may be particularly beneficial when the associated expansion joint seal system 102 and its compressed longi-

tudinal body of foam 104 includes an adhesive at expansion joint seal system first and second sidewalls 150, 152.

The casing 108 may be overlapped as little as 15% of its width, or as great as 85%, though more or less is possible. As the overlap approaches 15%, the casing 108 provides beneficial tensioning and resilience against external damage.

To maintain the casing 108 in position, the casing may include an external surface with clinginess, such as a polyvinyl chloride or low density polyethylene, or adhesive, preferably an external adhesive surface, such that the successive layering of the casing 108 provides a bond to the prior layer, and, where desired, to the expansion joint seal system 102 or any boards or other materials abutting the expansion joint seal system 102, which may also have adhesive surfaces. Such materials may be applied to only the exterior to-be-overlapped portion, such that the ultimate exposed surface has no such property while bonding to the successive overlap. The casing 108, for example, may overlap 50% of itself with each successive application, where the overlapped exterior surface has an adhesive to bond to the successive application and therefore further retard any propagation of a tear in the resultant packaging 100.

Because the longitudinal body of foam 104 provides elasticity and compressibility in the packaging 100, the casing 108 may be constructed of an inelastic material. Alternatively, the casing 108 may be constructed of a material which is elastic. Regardless of the material from which the casing 108 is constructed, the casing 108 is applied under tension to maintain, and to impart at the level desired, compression to the longitudinal body of foam 104. Moreover, because the casing 108 includes multiple layers of the casing 108 along the expansion joint seal system 102, the failure at any point of the casing 108 does not result in the expansion joint seal system 102 being permitted to expand significantly and reduces the potential for unusable material. This marks a substantial departure from the prior art, wherein the shrink wrap packaging would fail due to impact or flexing, often initially splitting along a seam, and then further failing as the now-permitted expansion of the expansion joint seal system 102 further split the packaging and rendered the product unusable due to the force needed to recompress to the necessary width. The casing 108 may be an inelastic paper of sufficient strength to resist tearing and may be coated externally with a water-resistant layer to ensure maintenance of the packaging 100 in case of precipitation. When desired, conventional bandings can be applied about the packaging 100.

The casing 108 may be formed of a material of sufficient durability to withstand exposure to any additive such as a fire retardant, a hydrophobic additive, or a hydrophilic additive, which may be associated with the expansion joint seal system 102, such as by a coating, infusion or impregnation. Such fire retardants, in amounts sufficient to obtain a desired fire endurance rating under any of the various tests, such as E-119, UL 2079, UL 84, DIN 4102, etc., may otherwise adversely react with the casing 108.

The interior surface of casing 108 may be selected to ensure other materials do not adhere, or may be impermeable to ensure no leakage of additives. Water and airflow resistant constituents 106, may be additives 132 introduced before foaming such as by mixing into the isocyanate or polyol, or after such by infusion and/or impregnation, or may, instead be a layer 134 subsequently applied externally, such as an elastomer or may be internal membranes, force compensating and/or recovery spring members, or other systems known in the art. Notably, such water-resistant



5

constituents **106** may have adhesive surfaces to which the casing **108** may apply pressure but to which the casing **108** should not adhere.

The casing **108** may further include compositions on some or all of its inner and outer surface which react when brought in contact, when the casing **108** is overlapped, and which may therefore provide a more durable chemical bond. The casing **108** may include a first chemically sensitive coating on a first surface and a second chemically sensitive coating on a second surface, where the first chemically sensitive coating is reactive to the second chemically sensitive coating. Likewise, the casing **108** may include heat reactive compositions on one or both surfaces or itself may be heat-reactive, such that the packaging **100** may be subjected to some degree of heating to increase the adhesion between layers of the casing **108**, to cause further constriction by shrinking, or to alter other properties, such as permeability or ductility. Similarly, the casing **108** may be an insulating material, precluding substantial heat transfer to the expansion joint system **102**. The casing **108** may therefore include cellulose, soy or carob oil derivatives.

Because the compression of the compressed longitudinal body of foam **104** of the expansion joint seal system **102** is maintained by, and may be provided by, the casing **108**, the packaging **100** permits the compression ratio of the compressed longitudinal body of foam **104** to be adjusted as needed, such as higher compression or lower compression, even in the same stick or coil. Similarly, because the compression around a transition, a change in direction of the material, varies according to the length of each successive section **114**, the tension maintained in the casing **108** during application may be reduced for those sections surrounding a transition. Beneficially, because the casing **108** is continually encapsulating, the expansion joint system **102** may include longitudinal bodies of foam **104** of different seal sizes, i.e., a continuation expansion joint **102** intended for use across a span which includes a section of narrower expansion joint width, avoiding the need for a field splice to accommodate the varying sizes. As a result, the casing **108** may be applied at varying radius, whether as a result of varying compression ratio upon application of the coating or due to the application of a common compression ratio as the expansion joint system **102** varies in dimension.

To ensure sufficient binding of the expansion joint seal system **102**, the casing **108** may be overlapped such that a successive section **114** overlaps a prior section **112** by a quarter, 25%, of its width **116**. Increased overlaps ensure the casing **108** remains tight against the compressed longitudinal body of foam **104** of the expansion joint seal system **102**, but consumes a substantially greater length of casing **108** and results in a thicker casing **108** which must be cut through prior to installation. The interior surface **110** of the casing **108** may include an adhesive edge **111**, or may adhere by virtue of an electrostatic charge, or by a high friction surface, preferably on the exterior of the casing **108**, or other systems known in the art to maintain the overlap.

The resulting packaging **100** permits dispatch of an expansion joint seal system **102** sized to, or above, the necessary length, avoiding the need for any field splice.

To aid cutting the expansion joint seal system **102** to the desired length, the casing **108** may include a distance indicator **146** at regular intervals, such as feet, yards, or meters. The presence of the distance indicator **146** outside the packaging **100** permits the packaging **100** to be cut to the needed length prior to cutting the casing **108** to open the packaging **100**. The use of the casing **108** and, where desired, the distance indicator **146**, permits a packaging **100**

6

where the compressed longitudinal body of foam **104** may have a length greater than ten feet.

Referring to FIG. 1 and to FIG. 2, an end view of the packaging **100**, consistent with pre-compressed foam-based expansion joint seals, the expansion joint seal system **102** may be positioned, while in—or prior to—compression against a board **118** or between a board **118** and a second board **120** prior to be encased within the casing **108**. The board **118** is positioned intermediate the compressed longitudinal body of foam **104** and the casing **108** at the interior surface **110** of the casing **108**. Preferably the board **118** has a height **224** equivalent to a height **226** of the compressed longitudinal body of foam **104**, the foam body height **226**. Alternatively, the board height **224** may be equivalent to the height **228** of the expansion joint seal system **102**, particularly where an external layer **134** of water-resistant constituent **106** is provided. Thus, the board **118** is positioned intermediate the compressed longitudinal body of foam **104** and the casing **108** in contact with the casing internal surface **110**. A second board **120** may be positioned intermediate the compressed longitudinal body of foam **104** and the casing internal surface **110**. Preferably the second board **120** also has a second board height **240** equivalent to the height **226** of the compressed longitudinal body of foam **104**. Use of one of more boards **118**, **120** permits the expansion joint seal system **102** to be laterally compressed so the expansion joint seal system width **222** is maintained in compression at a distance less than the width of the expansion joint into which the expansion joint seal system **102** is to be imposed after removal from the casing **108**. Beneficially, because the casing **108** is provided as a single, continuous helical wrap around the expansion joint seal system **102**, the boards **118** and **120** need to be of great length of even co-terminal. Shorter board **118**, **120** might be used and positioned so the ends are not co-terminal, reducing the potential for deflection at any single point. Such boards **118**, **120** may even be spliced when appropriate, particularly when the expansion joint seal system **102** includes a transition, such as that the product is in more than one plane. The boards **118**, **120** may be of wood, or plastic, or high density paper, any may be constructed from recyclable materials. The boards **118**, **120** may be positioned on any surface of the expansion joint system **102**, and may be of any size, any may only provide a longitudinal strut to control flexing prior to use.

Referring to FIGS. 2 and 3, while the first board **118** and the second board **120** are typically aligned in parallel planes, such that the distances between the tops **230**, **232** of the first board **118** and the second board **120** and bottoms **234**, **236** of each of the first board **118** and the second board **120** are equal, the first board **118** and the second board **120** may be skewed, such that the distance between the first board top **230** and the second board top **232** of the second board is greater than the distance between the first board bottom **234** and the second board bottom **236**, such as illustrated in FIG. 3. Such a skewed construction may be advantageous where the expansion joint seal system **102** incorporates a chambered base. To ensure the compression introduced into the longitudinal body of foam **104** is maintained along the length of a stick of the expansion joint seal system **102**, one or both of the board **118** and the second board **120** may have a board first end **142** and a second board first end **144** to which the casing **108** reaches.

Beneficially, because the casing **108** may be applied after the expansion joint seal system **102** is in lateral compression, maintaining compression of the expansion joint system **102** in other planes is possible. The expansion joint seal system **102** may be subjected to a longitudinal com-



pression in a section immediately subject to the helical encircling by the casing **108**, such that the longitudinal compression is retained by the successive layering of the casing **108**. Longitudinal compression may be desirable to ensure that, upon release in the expansion joint, the expansion joint seal system **102** is maintained in abutment with the end of the expansion joint and to ensure that any joint is maintained in position. Further, the expansion joint seal system **102** may be subjected to a vertical compression such that the expansion joint seal system height **228** is less than its operational height. Vertical compression may be desirable, particularly in connection with any surface cover over the expansion joint, such as a cover plate, to ensure the expansion joint seal system **102** abuts the cover plate after installation and, when desired, transfers any load from the cover plate to adjacent substrate. Further because the expansion joint seal system **102** is maintained in compression by the packaging **100**, the compressed longitudinal body of foam **104** may be provided with different shapes and profiles, such as chamfering at the lower sides, to facilitate compression and installation.

Unlike any packaging **100** known in the art, use of the casing **108** helically encircling the compressed longitudinal body of foam **104** permits the longitudinal body of foam **104** to itself be helically curved, such that the longitudinal body of foam **104** is bent or curved into a different plane, off a central axis **402**, and, while deflected or bent, helically bound with the casing **108**, such that each successive section **114** of casing **108** is bound and a constant radius is provided to result in the application of a coiling from a casing **108** provided at the constant radius about that central axis, as illustrated in FIG. 4. The packaging **100** may therefore be directed and coiled in any direction—laterally, vertically or in any combination thereof. Eliminating the conventional stick format permits the storage and shipping of expansion joint seal systems **102** of lengths substantially greater than available in a stick form, potentially eliminates the need for internal field splices, and permits conventional shipping. On the job site, the coil **400** of the packaging **100** can be released by cutting the casing **108**, unrolling the coil **400**, and opening the packaging **100** and inserting the expansion joint seal system **102** in the expansion joint. Cutting the packaging **100** to the appropriate length using the distance indicators **146** permits the packaging **100** to be maintained as the coil **400** until needed. Alternatively, the coil **400** may be constructed in a vertical plane, inducing the deflection and associated coiling in a plane perpendicular to the longitudinal and lateral axes.

Additional components may be incorporated into the expansion joint seal system **102** and included in the coil **400**. One such component may include one or more longitudinal flexible members bonded to the compressed longitudinal body of foam **104** at the longitudinal body of foam top **154** opposite the longitudinal body of foam bottom **156** and capable of transferring a load to the compressed longitudinal body of foam **104**, which would have sufficient flexibility in the horizontal plane to permit the coiling if desired. Another component may be one or more membranes, which may be permeable or impermeable, which may extend from one side of the compressed longitudinal body of foam **104** to the other, or some portion thereof, which may be in the horizontal plane and which may permit coiling as well. Such membranes may be used to provide an air barrier, vapor permeability, hydrostatic head resistance, electromagnetic frequency/radio frequency interference insulators, or other functions known for association with expansion joint seal systems. Another component may be an elastomeric gland,

wherein the compressed longitudinal body of foam **104** may surround the gland, be incorporated in it, or some combination thereof. The packaging **100** provides the potential for lengths far in excess of conventional lengths and, where the gland permits coiling of the expansion joint seal system, the expansion joint seal system **102** may be coiled. Another component may be a combination of one or more flexible members, one or more cover plates, and one or more ribs, where the flexible member is attached to the cover plate and to the rib, such that the ribs extends into the compressed longitudinal body of foam **104**. An increased number of cover plates, functional as a series of overlapping shields, may permit the expansion joint seal system **102** to be coiled vertically when packaged and facilitates constant and equal compression throughout the expansion joint seal system **102**. Beneficially, the compressed longitudinal body of foam **104** may be offset with respect to these additional components, or extend past the end of the compressed longitudinal body of foam **104**, such that the additional component provides a mating surface for another expansion joint seal system **100**, to serve as a splice when desired. While a splice is ideally avoided in a run of the expansion joint seal system **102** by the present invention, should a second expansion joint seal system intersect the first, such as in a T or angled joint, such additional components may provide the splice.

Referring to FIG. 5, to further aid in installation, internal tear strips **502** may be affixed to the casing **108** at regular intervals associated with the circumference of the expansion joint seal system **102** and any boards **118**, **120**, such that the tear strips are commonly positioned along the length of the packaging **100** and may tear the casing **108** for a desired distance, such as in two-foot sections. Other tools may be used to separate the casing, such as box knives, particularly those with depth control and automatic retracing systems.

The expansion joint seal system **102** may be compressed prior to or during the application of the casing **108**. For example, the expansion joint system **102** may be processed through one or more sets of rollers, such as depicted in FIG. 6, wherein each roller set **602**, **604** provides an increased compression during which any external layer **134** of water-resistant constituent **106** is applied by an applicator **608**, and after which the compressed longitudinal body of foam **104** is subsequently maintained by a final roller set **606** until the application of the casing **108**, which may be after the imposition of the board **118**, **120** about the expansion joint seal system **102**.

Alternatively, the boards **118**, **120** may be applied to the sides of the expansion joint seal system **102** prior to the imposition of compression, such as by the rollers **602**, **604** as previously described, or by a lateral press **702** as illustrated in FIG. 7. The boards **118**, **120** may facilitate the compression in both systems by resisting any problematic necking of the expansion joint seal system **102** when passing between rollers **620**, **604** or by providing a working surface for the application of force by a lateral press **702**. The roller system **610** depicted in FIG. 6 permits a longer run of the expansion joint seal system **102** as the board **118**, **120** limit the length which can be readily transported in packaging. The roller system **610** depicted in FIG. 6 facilitates the forming of the coil **400** at the final set of rollers **606**, such as by a guide offsetting the expansion joint seal system **102** after exit from the final set of rollers **606**, or by one roller **606a**, **606b** of the final set of rollers **606b** introducing a greater amount of compression on one side than the other.

Alternatively, the casing **108** may itself be applied to introduce the compression of the longitudinal body of foam **104** in the expansion joint seal system **102** during encircle-



ment. The casing **108** therefore provides a packaging **100** which may be provided without the structural support of boards **18**, **120**, which must be disposed after unpackaging. The casing **108** may be tensioned, such that once a first end of the casing **108** is affixed or bound to the expansion joint seal system **102**, the casing **108** under tension may be wrapped about the expansion joint seal system **102**, while the expansion joint seal system **102** is maintained in position, permitting the necessary amount of casing **108** to be released while the supply of the casing **108** revolves about the expansion joint seal system **102** or while the expansion joint seal system **102** is rotated about a central axis. Where the first board **118** and the second board **120** are used, the resultant compression would be limited to lateral compression. Where the expansion joint seal system **102** is directly encircled by the casing **108** with any board, the expansion joint seal system **102** may be compressed laterally and vertically (under compression between a longitudinal body of foam top and a longitudinal body of foam bottom). Where the rate of advance of the expansion joint seal system **102** is decreased immediately prior to the encirclement by the casing **108**, the expansion joint seal system **102** may also be compressed longitudinally. Alternatively, where the rate of advance of the expansion joint seal system **102** is increased, the opposite occurs.

Beneficially, the casing **108** may be used in connection with expansion joint seal systems **102** which incorporate other components beyond a longitudinal body of foam **104**, such as one or more membranes, such as disclosed in U.S. Pat. No. 9,803,357 and by U.S. Patent Application Publication 2017-0159817, both by Schul International Company, LLC, each of which teach a membrane extending to or beyond the sides of the foam, which may therefore be positioned against one or more of the external surfaces for packaging. The casing **108** may thus contact the winged membranes or extensions, which may serve as the bond breaker or support for the now-compressed expansion joint seal systems **102**, such that only the wrapping material is required reducing weight and waste.

A second layer of casing **108** may be applied about some or all of the expansion joint seal system **102** when encircled in the casing **108** to provide a second compression ratio in the applied area. When a second layer of casing **108** is used, the overlap may be reduced to less than 15% and may be entirely eliminated.

The foregoing disclosure and description is illustrative and explanatory thereof. Various changes in the details of the illustrated construction may be made within the scope of the appended claims departing from the spirit of the invention. The present invention should only be limited by the following claims and their legal equivalents.

I claim:

1. An expansion joint seal system, comprising:
  - a longitudinal body of foam in compression;
  - a water-resistant constituent, the water-resistant constituent adhered to the longitudinal body of foam on a first surface or contained within the longitudinal body of foam in compression; and
  - a casing in tension helically compressively encircling the longitudinal body of foam in compression and the water-resistant constituent,
  - the longitudinal body of foam in compression helically curved at a constant radius.
2. The expansion joint seal system of claim 1, further comprising:

the casing having an internal surface, the internal surface contacting the longitudinal body of foam, the internal surface having a low friction coefficient.

3. The expansion joint seal system of claim 1, wherein a successive section of the casing overlaps a prior section of the casing by 15%.

4. The expansion joint seal system of claim 1, further comprising:

a board intermediate the longitudinal body of foam in compression and the casing at a first side of the casing, the board having a board height, the longitudinal body of foam in compression having a foam body height, the board height being greater than or equal to the foam body height.

5. The expansion joint seal system of claim 4, further comprising:

a second board intermediate the longitudinal body of foam in compression and the casing at a second side of the casing, the second board having a second board height, the second board height being greater than or equal to the foam body height.

6. The expansion joint seal system of claim 5, wherein the board and the second board are in parallel planes.

7. The expansion joint seal system of claim 5, wherein the board and the second board are askew, and wherein the board has a first end adjacent a first end of the longitudinal body of foam in compression, and the second board has a first end adjacent the first end of the longitudinal body of foam in compression.

8. The expansion joint seal system of claim 1, wherein the casing is paper.

9. The expansion joint seal system of claim 1, wherein the casing is inelastic.

10. The expansion joint seal system of claim 1, wherein the longitudinal body of foam in compression has a length greater than ten feet.

11. The expansion joint seal of claim 1, wherein the casing bears a distance indicator at regular intervals.

12. The expansion joint seal of claim 1, wherein the longitudinal body of foam in compression is under compression laterally between a first sidewall and a second sidewall.

13. The expansion joint seal of claim 1 wherein the longitudinal body of foam in compression is under compression laterally between a first sidewall and a second sidewall and is under compression longitudinally.

14. The expansion joint seal of claim 1 wherein the longitudinal body of foam in compression is under compression laterally between a first sidewall and a second sidewall and the longitudinal body of foam in compression is under compression between a longitudinal body of foam top and a longitudinal body of foam bottom.

15. The expansion joint seal of claim 1 wherein the longitudinal body of foam in compression is under compression laterally between a first sidewall and a second sidewall, the longitudinal body of foam in compression is under compression longitudinally and the longitudinal body of foam in compression is under compression between a longitudinal body of foam top and a longitudinal body of foam bottom.

16. The expansion joint seal system of claim 1, wherein the casing includes an external adhesive surface.

17. The expansion joint seal system of claim 1, wherein the casing includes a heat sensitive coating.

18. The expansion joint seal system of claim 1, wherein the casing includes a first chemically sensitive coating on a first surface and a second chemically sensitive coating on a



second surface, the first chemically sensitive coating reactive to the second chemically sensitive coating bonding the first surface to the second surface.

**19.** An expansion joint seal system, comprising:  
 a longitudinal body of foam in compression; 5  
 a water-resistant constituent, the water-resistant constituent adhered to the longitudinal body of foam on a first surface or contained within the longitudinal body of foam in compression; and  
 a casing in tension helically compressively encircling the 10  
 longitudinal body of foam in compression and the water-resistant constituent, and  
 a plurality of internal tear strips, each of the plurality of internal tear strips affixed to the casing at regular intervals. 15

**20.** An expansion joint seal system, comprising:  
 a longitudinal body of foam in compression;  
 a water-resistant constituent, the water-resistant constituent adhered to the longitudinal body of foam on a first surface or contained within the longitudinal body of 20  
 foam in compression; and  
 a casing in tension helically compressively encircling the longitudinal body of foam in compression and the water-resistant constituent, and  
 a second casing in tension helically compressively encircling the casing. 25

\* \* \* \* \*