



US010388546B2

(12) **United States Patent**
Mohn et al.

(10) **Patent No.:** **US 10,388,546 B2**
(45) **Date of Patent:** ***Aug. 20, 2019**

(54) **APPARATUS FOR UV FLOWABLE DIELECTRIC**

(58) **Field of Classification Search**
None
See application file for complete search history.

(71) Applicant: **Lam Research Corporation**, Fremont, CA (US)

(56) **References Cited**

(72) Inventors: **Jonathan D. Mohn**, Saratoga, CA (US); **Nicholas Muga Ndiege**, Fremont, CA (US); **Patrick A. Van Cleemput**, San Jose, CA (US); **David Fang Wei Chen**, San Jose, CA (US); **Wenbo Liang**, Fremont, CA (US); **Shawn M. Hamilton**, Boulder Creek, CA (US)

U.S. PATENT DOCUMENTS

3,504,181 A 3/1970 Campbell et al.
3,704,219 A 11/1972 McDowell
(Continued)

(73) Assignee: **Lam Research Corporation**, Fremont, CA (US)

FOREIGN PATENT DOCUMENTS

CN 1655330 A 8/2005
CN 1722403 A 1/2006
(Continued)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 576 days.

This patent is subject to a terminal disclaimer.

OTHER PUBLICATIONS

U.S. Final Office Action, dated Jul. 29, 2016, issued in U.S. Appl. No. 14/519,712.

(Continued)

(21) Appl. No.: **14/942,703**

Primary Examiner — Karla A Moore
(74) *Attorney, Agent, or Firm* — Weaver Austin Villeneuve & Sampson LLP

(22) Filed: **Nov. 16, 2015**

(65) **Prior Publication Data**

US 2017/0137943 A1 May 18, 2017


(51) **Int. Cl.**
C23C 16/04 (2006.01)
C23C 16/44 (2006.01)
(Continued)

(57) **ABSTRACT**

Provided are methods and apparatus for ultraviolet (UV) assisted capillary condensation to form dielectric materials. In some embodiments, a UV driven reaction facilitates photo-polymerization of a liquid phase flowable material. Applications include high quality gap fill in high aspect ratio structures and por sealing of a porous solid dielectric film. According to various embodiments, single station and multi-station chambers configured for capillary condensation and UV exposure are provided.

(52) **U.S. Cl.**
CPC **H01L 21/67109** (2013.01); **C23C 16/045** (2013.01); **C23C 16/44** (2013.01); **C23C 16/56** (2013.01); **H01L 21/67103** (2013.01); **H01L 21/67115** (2013.01); **H01L 21/67225** (2013.01); **H01L 21/68764** (2013.01); **H01L 21/68771** (2013.01)

9 Claims, 14 Drawing Sheets



(51)	Int. Cl.								
	<i>C23C 16/56</i>	(2006.01)		6,072,227 A	6/2000	Yau et al.			
	<i>H01L 21/67</i>	(2006.01)		6,080,965 A	6/2000	Osawa			
	<i>H01L 21/687</i>	(2006.01)		6,114,224 A	9/2000	Ngo et al.			
				6,114,259 A	9/2000	Sukharev et al.			
				6,143,063 A	11/2000	Hayashi et al.			
				6,143,626 A	11/2000	Yabu et al.			
				6,207,535 B1	3/2001	Lee et al.			
				6,218,268 B1	4/2001	Xia et al.			
				6,232,248 B1	5/2001	Shinriki et al.			
				6,235,112 B1	5/2001	Satoh			
				6,235,146 B1	5/2001	Kadotani et al.			
				6,239,018 B1	5/2001	Liu et al.			
				6,242,366 B1	6/2001	Beekman et al.			
				6,242,717 B1	6/2001	Sanderson			
				6,244,575 B1	6/2001	Vaartstra et al.			
				6,251,759 B1	6/2001	Guo et al.			
				6,259,061 B1	7/2001	Osawa			
				6,284,050 B1	9/2001	Shi et al.			
				6,287,989 B1	9/2001	Dobson			
				6,288,493 B1	9/2001	Lee et al.			
				6,291,800 B1	9/2001	Shirakawa et al.			
				6,300,219 B1	10/2001	Doan et al.			
				6,309,933 B1	10/2001	Li et al.			
				6,323,123 B1	11/2001	Liu et al.			
				6,383,951 B1	5/2002	Li			
				6,394,797 B1	5/2002	Sugaya et al.			
				6,399,213 B2	6/2002	Shiokawa			
				6,413,583 B1	7/2002	Moghadam et al.			
				6,439,244 B1	8/2002	Wu			
				6,448,187 B2	9/2002	Yau et al.			
				6,467,491 B1	10/2002	Sugiura et al.			
				6,475,564 B1	11/2002	Carter et al.			
				6,475,854 B2	11/2002	Narwanker et al.			
				6,497,783 B1	12/2002	Suzuki et al.			
				6,519,036 B1	2/2003	Hickman			
				6,524,389 B1	2/2003	Katayama et al.			
				6,530,380 B1	3/2003	Zhou et al.			
				6,544,858 B1	4/2003	Beekman et al.			
				6,563,092 B1	5/2003	Shrinivasan et al.			
				6,568,346 B2	5/2003	Pu et al.			
				6,605,955 B1	8/2003	Costello et al.			
				6,613,695 B2	9/2003	Pomarede et al.			
				6,629,012 B1	9/2003	Riley et al.			
				6,635,586 B2	10/2003	Goo et al.			
				6,640,840 B1	11/2003	MacNeil			
				6,653,247 B2	11/2003	MacNeil			
				6,660,663 B1	12/2003	Cheung et al.			
				6,703,321 B2	3/2004	Geiger et al.			
				6,740,853 B1	5/2004	Johnson et al.			
				6,743,436 B1	6/2004	Lee			
				6,743,736 B2	6/2004	Mardian et al.			
				6,756,085 B2	6/2004	Waldfried et al.			
				6,787,463 B2	9/2004	Mardian et al.			
				6,790,737 B2	9/2004	Schneegans et al.			
				6,812,135 B2	11/2004	Li et al.			
				6,821,906 B2	11/2004	Wada et al.			
				6,828,162 B1	12/2004	Halliyal et al.			
				6,846,757 B2	1/2005	MacNeil			
				6,858,195 B2	2/2005	Aronowitz et al.			
				6,900,413 B2	5/2005	Ratliff et al.			
				6,902,947 B2	6/2005	Chinn et al.			
				6,972,262 B2	12/2005	Lee et al.			
				6,977,014 B1	12/2005	Stevens et al.			
				6,984,561 B2	1/2006	Herner et al.			
				6,995,056 B2	2/2006	Lee et al.			
				7,018,479 B2	3/2006	Goodwin			
				7,020,238 B1	3/2006	Kantonen et al.			
				7,025,831 B1	4/2006	Butterbaugh et al.			
				7,033,945 B2	4/2006	Byun et al.			
				7,056,560 B2	6/2006	Yim et al.			
				7,067,819 B2	6/2006	Janik			
				7,071,126 B2	7/2006	Johnston et al.			
				7,074,690 B1	7/2006	Gauri et al.			
				7,074,727 B2	7/2006	Hsu et al.			
				7,084,505 B2	8/2006	Hamada et al.			
				7,087,497 B2	8/2006	Yuan et al.			
				7,091,453 B2	8/2006	Murayama et al.			
				7,094,713 B1	8/2006	Niu et al.			
				7,097,712 B1	8/2006	Yamazaki et al.			
(56)	References Cited								
	U.S. PATENT DOCUMENTS								
	4,099,990 A	7/1978	Brown et al.						
	4,527,620 A	7/1985	Pedersen et al.						
	4,563,589 A	1/1986	Scheffer						
	4,654,226 A	3/1987	Jackson et al.						
	4,740,480 A	4/1988	Ooka						
	4,832,777 A	5/1989	Davis et al.						
	4,872,947 A	10/1989	Wang et al.						
	4,923,720 A	5/1990	Lee et al.						
	4,927,786 A	5/1990	Nishida						
	4,956,582 A	9/1990	Bourassa						
	5,005,519 A	4/1991	Egermeier et al.						
	5,049,739 A	9/1991	Okamoto						
	5,150,253 A	9/1992	Watanuki et al.						
	5,166,101 A	11/1992	Lee et al.						
	5,174,881 A	12/1992	Iwasaki et al.						
	5,178,682 A	1/1993	Tsukamoto et al.						
	5,195,045 A	3/1993	Keane et al.						
	5,240,746 A	8/1993	O'Connell Litteral						
	5,281,274 A	1/1994	Yoder						
	5,282,121 A	1/1994	Bornhorst et al.						
	5,288,684 A	2/1994	Yamazaki et al.						
	5,298,939 A	3/1994	Swanson et al.						
	5,314,538 A	5/1994	Maeda et al.						
	5,320,983 A	6/1994	Ouellet						
	5,354,715 A	10/1994	Wang et al.						
	5,382,311 A	1/1995	Ishikawa et al.						
	5,387,546 A	2/1995	Maeda et al.						
	5,407,524 A	4/1995	Patrick et al.						
	5,413,664 A	5/1995	Yagi et al.						
	5,426,076 A	6/1995	Moghadam et al.						
	5,462,603 A	10/1995	Murakami						
	5,516,721 A	5/1996	Galli et al.						
	5,518,959 A	5/1996	Jang et al.						
	5,525,157 A	6/1996	Hawkins et al.						
	5,534,731 A	7/1996	Cheung						
	5,552,927 A	9/1996	Wheatly et al.						
	5,556,549 A	9/1996	Patrick et al.						
	5,558,717 A	9/1996	Zhao et al.						
	5,667,592 A	9/1997	Boitnott et al.						
	5,674,783 A	10/1997	Jang et al.						
	5,747,381 A	5/1998	Wu et al.						
	5,753,886 A	5/1998	Iwamura et al.						
	5,775,808 A	7/1998	Pan						
	5,795,448 A	8/1998	Hurwitt et al.						
	5,796,074 A	8/1998	Edelstein et al.						
	5,807,785 A	9/1998	Ravi						
	5,833,290 A	11/1998	Curelop et al.						
	5,840,631 A	11/1998	Kubo et al.						
	5,858,880 A	1/1999	Dobson et al.						
	5,874,367 A	2/1999	Dobson						
	5,879,574 A	3/1999	Sivaramakrishnan et al.						
	5,899,751 A	5/1999	Chang et al.						
	5,902,127 A	5/1999	Park						
	5,903,428 A	5/1999	Grimard et al.						
	5,911,833 A	6/1999	Denison et al.						
	5,932,289 A	8/1999	Dobson et al.						
	5,958,510 A *	9/1999	Sivaramakrishnam ..	B05D 1/60					
				118/719					
	5,962,085 A	10/1999	Hayashi et al.						
	5,970,383 A	10/1999	Lee						
	5,990,013 A	11/1999	Berenguer et al.						
	5,994,678 A	11/1999	Zhao et al.						
	6,001,183 A	12/1999	Gurary et al.						
	6,013,581 A	1/2000	Wu et al.						
	6,015,503 A	1/2000	Butterbaugh et al.						
	6,035,101 A	3/2000	Sajoto et al.						
	6,044,329 A	3/2000	Kidd						
	6,054,379 A	4/2000	Yau et al.						
	6,060,384 A	5/2000	Chen et al.						

(56)

References Cited

U.S. PATENT DOCUMENTS

7,153,783 B2	12/2006	Lu et al.	8,846,536 B2	9/2014	Draeger et al.
7,160,813 B1	1/2007	Chen et al.	8,883,406 B2	11/2014	Lee et al.
7,169,256 B2	1/2007	Dhindsa et al.	8,889,233 B1	11/2014	Kelman et al.
7,176,144 B1	2/2007	Wang et al.	8,951,348 B1	2/2015	Shrinivasan et al.
7,211,525 B1	5/2007	Shanker et al.	8,980,769 B1	3/2015	Haverkamp et al.
7,214,630 B1	5/2007	Varadarajan et al.	9,028,765 B2	5/2015	Gytri et al.
7,235,137 B2	6/2007	Kitayama et al.	9,064,684 B1	6/2015	Mui et al.
7,238,604 B2	7/2007	Kloster et al.	9,073,100 B2	7/2015	Gytri et al.
7,244,672 B2	7/2007	Nguyen et al.	9,224,594 B2	12/2015	Kashefi et al.
7,256,111 B2	8/2007	Lopatin et al.	9,245,739 B2	1/2016	Ndiege et al.
7,264,676 B2	9/2007	Lai et al.	9,257,302 B1	2/2016	Wang et al.
7,271,112 B1	9/2007	Papasouliotis et al.	9,299,559 B2	3/2016	Draeger et al.
7,301,148 B2	11/2007	Johnson	9,384,959 B2	7/2016	Smargiassi et al.
7,304,302 B1	12/2007	Nunan et al.	9,719,169 B2*	8/2017	Mohn C23C 16/401
7,311,782 B2	12/2007	Strang et al.	9,847,222 B2	12/2017	Reilly et al.
7,327,948 B1	2/2008	Shrinivasan et al.	9,916,977 B2*	3/2018	Van Cleemput H01L 21/02348
7,332,445 B2	2/2008	Lukas et al.	10,049,921 B2	8/2018	Draeger et al.
7,365,000 B2	4/2008	Lee et al.	2001/0018267 A1	8/2001	Shinriki et al.
7,394,067 B1	7/2008	Soltz et al.	2001/0054381 A1	12/2001	Umotoy et al.
7,453,560 B2	11/2008	Miyake	2002/0006729 A1	1/2002	Geiger et al.
7,480,129 B2	1/2009	Brown et al.	2002/0007785 A1	1/2002	Gujer et al.
7,498,273 B2	3/2009	Mallick et al.	2002/0017242 A1	2/2002	Hamaguchi et al.
7,521,378 B2	4/2009	Fucsko et al.	2002/0050246 A1	5/2002	Parkhe
7,524,735 B1	4/2009	Gauri et al.	2002/0066726 A1	6/2002	Cole et al.
7,575,633 B2	8/2009	Romanin	2002/0076490 A1	6/2002	Chiang et al.
7,582,555 B1	9/2009	Lang et al.	2002/0098627 A1	7/2002	Pomarede et al.
7,585,704 B2	9/2009	Belyansky et al.	2002/0117109 A1	8/2002	Hazelton et al.
7,589,012 B1	9/2009	Seo et al.	2002/0134439 A1	9/2002	Kawasaki et al.
7,622,369 B1	11/2009	Lee et al.	2002/0148563 A1	10/2002	Carlson et al.
7,629,227 B1	12/2009	Wang et al.	2003/0007917 A1	1/2003	Ohmi et al.
7,638,780 B2	12/2009	Kilburn et al.	2003/0013280 A1	1/2003	Yamanaka
7,642,205 B2	1/2010	Timans	2003/0015669 A1	1/2003	Janos et al.
7,648,927 B2	1/2010	Singh et al.	2003/0040199 A1	2/2003	Agarwal
7,655,532 B1	2/2010	Chen et al.	2003/0066482 A1	4/2003	Pokharna et al.
7,670,436 B2	3/2010	Miller et al.	2003/0077887 A1	4/2003	Jang et al.
7,704,894 B1	4/2010	Henry et al.	2003/0121898 A1	7/2003	Kane et al.
7,727,906 B1	6/2010	Shanker et al.	2003/0124870 A1	7/2003	Macneil et al.
7,772,527 B2	8/2010	Choi	2003/0146416 A1	8/2003	Takei et al.
7,790,243 B2	9/2010	Radhakrishnan et al.	2003/0150560 A1	8/2003	Kinnard et al.
7,794,544 B2	9/2010	Nguyen et al.	2003/0159655 A1	8/2003	Lin et al.
7,804,130 B1	9/2010	Fung	2003/0194493 A1	10/2003	Chang et al.
7,825,044 B2	11/2010	Mallick et al.	2003/0194861 A1	10/2003	Mardian et al.
7,888,233 B1	2/2011	Gauri et al.	2003/0199603 A1	10/2003	Walker et al.
7,888,273 B1	2/2011	Wang et al.	2003/0200931 A1	10/2003	Goodwin
7,915,139 B1	3/2011	Lang et al.	2003/0207580 A1	11/2003	Li et al.
7,935,940 B1	5/2011	Smargiassi	2003/0210065 A1	11/2003	Lu et al.
7,941,039 B1	5/2011	Shrinivasan et al.	2004/0023513 A1	2/2004	Aoyama et al.
7,947,551 B1	5/2011	Syue et al.	2004/0025787 A1	2/2004	Selbrede et al.
7,960,297 B1	6/2011	Rivkin et al.	2004/0033639 A1	2/2004	Chinn et al.
7,993,937 B2	8/2011	Chen et al.	2004/0048455 A1	3/2004	Karasawa et al.
7,999,356 B2	8/2011	Nakasaki et al.	2004/0082163 A1	4/2004	Mori et al.
8,058,181 B1	11/2011	Chen et al.	2004/0096593 A1	5/2004	Lukas et al.
8,075,789 B1	12/2011	Littau et al.	2004/0152342 A1	8/2004	Li et al.
8,137,465 B1	3/2012	Shrinivasan et al.	2004/0169005 A1	9/2004	Kim et al.
8,178,159 B2	5/2012	Baikerikar et al.	2004/0221871 A1	11/2004	Fletcher et al.
8,187,951 B1	5/2012	Wang et al.	2004/0224496 A1	11/2004	Cui et al.
8,211,510 B1	7/2012	Varadarajan et al.	2004/0266214 A1	12/2004	Suguro et al.
8,246,778 B2	8/2012	Lu et al.	2005/0006916 A1	1/2005	Mantz
8,278,224 B1	10/2012	Mui et al.	2005/0016687 A1	1/2005	Shinriki et al.
8,282,768 B1	10/2012	Smargiassi et al.	2005/0020074 A1	1/2005	Kloster et al.
8,283,644 B2	10/2012	Smargiassi et al.	2005/0020093 A1	1/2005	Ahn et al.
8,398,816 B1	3/2013	Gytri et al.	2005/0026443 A1	2/2005	Goo et al.
8,454,750 B1	6/2013	Shrinivasan et al.	2005/0056369 A1	3/2005	Lai et al.
8,481,403 B1	7/2013	Gauri et al.	2005/0064698 A1	3/2005	Chang et al.
8,512,818 B1	8/2013	Varadarajan et al.	2005/0072716 A1	4/2005	Quiles et al.
8,518,210 B2	8/2013	Smargiassi et al.	2005/0085094 A1	4/2005	Yoo
8,557,712 B1	10/2013	Antonelli et al.	2005/0098553 A1	5/2005	Devine et al.
8,580,697 B1	11/2013	Lang et al.	2005/0109276 A1	5/2005	Iyer et al.
8,608,035 B2	12/2013	Lee et al.	2005/0112282 A1	5/2005	Gordon
8,629,068 B1	1/2014	Shrinivasan et al.	2005/0136684 A1	6/2005	Mukai et al.
8,664,287 B2	3/2014	Shukla	2005/0150453 A1	7/2005	Simmons et al.
8,685,867 B1	4/2014	Danek et al.	2005/0181566 A1	8/2005	Machida et al.
8,728,958 B2	5/2014	Ashtiani et al.	2005/0190248 A1	9/2005	Konno et al.
8,734,663 B2	5/2014	Smargiassi et al.	2005/0191863 A1	9/2005	Olmer et al.
8,809,161 B2	8/2014	Gauri et al.	2005/0196929 A1	9/2005	Yuan et al.
			2005/0212179 A1	9/2005	Honda et al.
			2005/0229849 A1	10/2005	Silvetti et al.
			2005/0255712 A1	11/2005	Kato et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

2005/0258542 A1 11/2005 Fuller et al.
 2005/0260864 A1 11/2005 Huang et al.
 2005/0263719 A1 12/2005 Ohdaira et al.
 2005/0264218 A1 12/2005 Dhindsa et al.
 2006/0014384 A1 1/2006 Lee et al.
 2006/0021568 A1 2/2006 Matsumoto
 2006/0024912 A1 2/2006 Lee
 2006/0074153 A1 4/2006 Boisseau et al.
 2006/0105106 A1 5/2006 Balseanu et al.
 2006/0172531 A1 8/2006 Lin et al.
 2006/0172552 A1 8/2006 Ajmera et al.
 2006/0183345 A1 8/2006 Nguyen et al.
 2006/0216839 A1 9/2006 Shemesh et al.
 2006/0216946 A1 9/2006 Usami et al.
 2006/0223290 A1 10/2006 Belyansky et al.
 2006/0269693 A1 11/2006 Balseanu et al.
 2006/0270217 A1 11/2006 Balseanu et al.
 2006/0279217 A1 12/2006 Peuchert et al.
 2007/0034159 A1 2/2007 Komino et al.
 2007/0054505 A1 3/2007 Antonelli et al.
 2007/0134821 A1 6/2007 Thakur
 2007/0161230 A1 7/2007 Chen et al.
 2007/0196011 A1 8/2007 Cox et al.
 2007/0218204 A1 9/2007 Garg et al.
 2007/0224777 A1 9/2007 Hamelin
 2007/0235660 A1* 10/2007 Hudson H01J 37/32082
 250/423 P
 2007/0256785 A1 11/2007 Pamarthy et al.
 2007/0258186 A1 11/2007 Matyushkin et al.
 2007/0277734 A1 12/2007 Lubomirsky et al.
 2007/0281495 A1 12/2007 Mallick et al.
 2007/0289534 A1* 12/2007 Lubomirsky C23C 16/452
 118/723 R
 2007/0296035 A1 12/2007 George et al.
 2007/0298585 A1 12/2007 Lubomirsky et al.
 2008/0020591 A1 1/2008 Balseanu et al.
 2008/0053615 A1 3/2008 Sago et al.
 2008/0054466 A1 3/2008 Nasu et al.
 2008/0066682 A1 3/2008 Yamashita
 2008/0081434 A1 4/2008 Nam et al.
 2008/0089001 A1 4/2008 Parkhe et al.
 2008/0132087 A1 6/2008 Xia et al.
 2008/0199977 A1 8/2008 Weigel et al.
 2008/0274626 A1 11/2008 Glowacki et al.
 2008/0286697 A1 11/2008 Verhaverbeke et al.
 2008/0295872 A1 12/2008 Riker et al.
 2008/0318439 A1 12/2008 Ito et al.
 2009/0020847 A1 1/2009 Byun et al.
 2009/0053895 A1 2/2009 Oshima et al.
 2009/0059406 A1 3/2009 Powers et al.
 2009/0061647 A1 3/2009 Mallick et al.
 2009/0104789 A1 4/2009 Mallick et al.
 2009/0104790 A1 4/2009 Liang
 2009/0159566 A1 6/2009 Brillhart et al.
 2009/0159587 A1 6/2009 Shimanuki et al.
 2009/0190908 A1 7/2009 Shibagaki
 2009/0215282 A1 8/2009 Moore et al.
 2009/0298257 A1 12/2009 Lee et al.
 2009/0321936 A1 12/2009 Kojima et al.
 2010/0000684 A1 1/2010 Choi
 2010/0055904 A1 3/2010 Chen et al.
 2010/0109155 A1 5/2010 Liu et al.
 2010/0167533 A1 7/2010 Lim et al.
 2010/0267231 A1 10/2010 Van Schravendijk et al.
 2011/0020955 A1 1/2011 DeYoung
 2011/0070665 A1 3/2011 Chen et al.
 2011/0081782 A1 4/2011 Liang et al.
 2011/0151678 A1 6/2011 Ashtiani et al.
 2011/0262870 A1 10/2011 Lee et al.
 2012/0091097 A1 4/2012 Chen et al.
 2012/0149213 A1 6/2012 Nittala et al.
 2012/0161021 A1 6/2012 Smargiassi et al.
 2012/0161405 A1 6/2012 Mohn et al.
 2012/0164328 A1 6/2012 Kojima et al.
 2012/0213940 A1 8/2012 Mallick

2013/0122718 A1 5/2013 Kato et al.
 2013/0160946 A1 6/2013 Smargiassi et al.
 2013/0230987 A1 9/2013 Draeger et al.
 2013/0284087 A1 10/2013 Gytri et al.
 2013/0298940 A1 11/2013 Smargiassi et al.
 2014/0004717 A1 1/2014 Chan et al.
 2014/0017904 A1 1/2014 Gauri et al.
 2014/0065557 A1 3/2014 Lee et al.
 2014/0080324 A1 3/2014 Shrinivasan et al.
 2014/0106083 A1 4/2014 Wu et al.
 2014/0150647 A1 6/2014 Ahn et al.
 2014/0230861 A1 8/2014 Smargiassi et al.
 2014/0302689 A1 10/2014 Ashtiani et al.
 2014/0329027 A1* 11/2014 Liang C23C 16/401
 427/551
 2015/0004806 A1 1/2015 Ndiege et al.
 2015/0044882 A1 2/2015 Draeger et al.
 2015/0056108 A1 2/2015 Gytri et al.
 2015/0114292 A1 4/2015 Haverkamp et al.
 2015/0118862 A1 4/2015 Reilly et al.
 2015/0118863 A1 4/2015 Rathod et al.
 2015/0255285 A1 9/2015 Gytri et al.
 2016/0056071 A1 2/2016 Draeger et al.
 2016/0284574 A1 9/2016 Smargiassi et al.
 2017/0140931 A1 5/2017 Van Cleemput et al.

FOREIGN PATENT DOCUMENTS

CN 1815709 A 8/2006
 CN 101079391 A 11/2007
 CN 102089861 A 6/2011
 CN 102420164 A 4/2012
 EP 1 063 692 A1 12/2000
 EP 0 819 780 B1 2/2004
 JP 63307740 12/1988
 JP 01-107519 4/1989
 JP 05-031735 2/1993
 JP 05-138658 6/1993
 JP 62-229833 10/1997
 JP 11-214364 8/1999
 JP 2001-104776 4/2001
 JP 2001-148382 5/2001
 JP 2007-194582 8/2007
 JP 2010-153859 7/2010
 KR 2000-0043888 7/2000
 KR 10-2006-0005476 A 1/2006
 KR 10-2007-0104591 A 10/2007
 KR 10-2009-0040867 A 4/2009
 KR 10-2010-0079154 7/2010
 TW 380286 1/2000
 TW 2004/00589 A 1/2004
 WO WO 99/22043 A1 5/1999
 WO WO 02/40740 A1 5/2002
 WO WO 03/021642 3/2003
 WO WO 2004/105103 A1 12/2004
 WO WO 2006/104583 10/2006
 WO WO 2006/127463 11/2006
 WO WO 2007/140376 12/2007
 WO WO 2007/140424 12/2007
 WO WO 2011/072143 6/2011

OTHER PUBLICATIONS

U.S. Office Action, dated May 4, 2017, issued in U.S. Appl. No. 14/519,712.
 U.S. Office Action, dated May 6, 2016, issued in U.S. Appl. No. 14/942,704.
 U.S. Final Office Action, dated Oct. 19, 2016, issued in U.S. Appl. No. 14/942,704.
 U.S. Notice of Allowance, dated Oct. 30, 2017, issued in U.S. Appl. No. 14/942,704.
 U.S. Office Action, dated Jul. 29, 2016, issued in U.S. Appl. No. 13/329,078.
 U.S. Notice of Allowance, dated Mar. 22, 2017, issued in U.S. Appl. No. 13/329,078.
 Korean Office Action dated Dec. 27, 2015 issued in KR 10-2009-0124466.

(56)

References Cited

OTHER PUBLICATIONS

Korean Office Action dated Jul. 12, 2016 issued in KR 10-2009-0124466.

Taiwan Office Action and Search Report dated Nov. 16, 2016 issued in TW 102107721.

Weast, (1975) "CRC Handbook of Chemistry and Physics," 56th edition, CRC Press, Cleveland, Ohio, excerpts from F-95 & F-119, 4 pages.

U.S. Office Action, dated Jan. 20, 2016, issued in U.S. Appl. No. 14/519,400.

U.S. Office Action, dated Jan. 21, 2016, issued in U.S. Appl. No. 14/519,712.

U.S. Office Action, dated Dec. 30, 2015, issued in U.S. Appl. No. 14/464,071.

U.S. Notice of Allowance, dated Sep. 10, 2015, issued in U.S. Appl. No. 13/461,287.

U.S. Notice of Allowance [Corrected Notice of Allowability], dated Oct. 22, 2015, issued in U.S. Appl. No. 13/461,287.

U.S. Notice of Allowance [Corrected Notice of Allowability], dated Jan. 11, 2016, issued in U.S. Appl. No. 13/461,287.

U.S. Office Action, dated Oct. 22, 2015, issued in U.S. Appl. No. 13/313,735.

U.S. Notice of Allowance, dated Oct. 23, 2015, issued in U.S. Appl. No. 14/466,222.

Taiwan Office Action dated Dec. 10, 2015 issued in TW 099143081.

Chinese Second Office Action and Search Report dated Sep. 14, 2015 issued in CN 201110424193.X.

Chinese Second Office Action and Search Report dated Aug. 25, 2015 issued in CN 201110442926.2.

Taiwan Office Action dated Nov. 20, 2015 issued in TW 100147521.

U.S. Appl. No. 14/464,071, filed Aug. 20, 2014, entitled "Flowable Dielectric for Selective Ultra Low-K Pore Sealing."

U.S. Appl. No. 14/942,704, filed Nov. 16, 2015, entitled "Low K Dielectric Deposition via UV Driven Photopolymerization."

U.S. Appl. No. 13/461,287, filed May 1, 2012, entitled "CVD Flowable Gap Fill".

U.S. Appl. No. 12/986,070, filed Jan. 6, 2011, entitled "Density Gradient-Free Gap Fill".

U.S. Office Action, dated Mar. 25, 2015, issued in U.S. Appl. No. 14/464,196.

U.S. Notice of Allowance, dated Sep. 14, 2015, issued in U.S. Appl. No. 14/464,196.

U.S. Office Action, dated Aug. 23, 2005, issued in U.S. Appl. No. 10/810,066.

U.S. Notice of Allowance and Fee Due, dated Feb. 15, 2006, issued in U.S. Appl. No. 10/810,066.

U.S. Office Action, dated Jun. 27, 2008, issued in U.S. Appl. No. 11/447,594.

U.S. Notice of Allowance and Fee Due, dated Dec. 11, 2008, issued in U.S. Appl. No. 11/447,594.

U.S. Office Action, dated May 24, 2010, issued in U.S. Appl. No. 12/411,243.

U.S. Final Office Action, dated Sep. 13, 2010, issued in U.S. Appl. No. 12/411,243.

U.S. Notice of Allowance, dated Oct. 6, 2010, issued in U.S. Appl. No. 12/411,243.

U.S. Office Action, dated May 18, 2012, issued in U.S. Appl. No. 12/984,524.

U.S. Final Office Action, dated Sep. 14, 2012, issued in U.S. Appl. No. 12/984,524.

U.S. Notice of Allowance, dated Mar. 7, 2013, issued in U.S. Appl. No. 12/984,524.

U.S. Office Action, dated Dec. 16, 2013, issued in U.S. Appl. No. 13/935,398.

U.S. Notice of Allowance, dated Apr. 11, 2014, issued in U.S. Appl. No. 13/935,398.

U.S. Office Action, dated Oct. 26, 2007, issued in U.S. Appl. No. 11/323,812.

U.S. Final Office Action, dated Apr. 9, 2008, issued in U.S. Appl. No. 11/323,812.

U.S. Office Action, dated Oct. 9, 2008, issued in U.S. Appl. No. 11/323,812.

U.S. Notice of Allowance and Fee Due, dated Apr. 23, 2009, issued in U.S. Appl. No. 11/323,812.

U.S. Notice of Allowance, dated Nov. 18, 2010, issued in U.S. Appl. No. 12/508,461.

U.S. Notice of Allowance, dated Aug. 6, 2012, issued in U.S. Appl. No. 13/031,077.

U.S. Notice of Allowance, dated Jul. 8, 2013, issued in U.S. Appl. No. 13/031,077.

U.S. Office Action, dated Nov. 4, 2008, issued in U.S. Appl. No. 11/925,514.

U.S. Final Office Action, dated Jun. 17, 2009, issued in U.S. Appl. No. 11/925,514.

U.S. Notice of Allowance, dated Jul. 29, 2009, issued in U.S. Appl. No. 11/925,514.

U.S. Office Action, dated Apr. 26, 2011, issued in U.S. Appl. No. 12/625,468.

U.S. Final Office Action, dated Oct. 14, 2011, issued in U.S. Appl. No. 12/625,468.

U.S. Notice of Allowance, dated Jan. 31, 2012, issued in U.S. Appl. No. 12/625,468.

U.S. Office Action, dated Aug. 15, 2013, issued in U.S. Appl. No. 13/461,287.

U.S. Office Action, dated Feb. 28, 2014, issued in U.S. Appl. No. 13/461,287.

U.S. Final Office Action, dated Aug. 26, 2014, issued in U.S. Appl. No. 13/461,287.

U.S. Notice of Allowance, dated Apr. 20, 2015, issued in U.S. Appl. No. 13/461,287.

U.S. Office Action, dated Nov. 12, 2008, issued in U.S. Appl. No. 11/834,581.

U.S. Final Office Action, dated Aug. 6, 2009, issued in U.S. Appl. No. 11/834,581.

U.S. Office Action dated Dec. 18, 2009, issued in U.S. Appl. No. 11/834,581.

U.S. Final Office Action, dated Apr. 22, 2010, issued in U.S. Appl. No. 11/834,581.

U.S. Notice of Allowance, dated Oct. 7, 2010, issued in U.S. Appl. No. 11/834,581.

U.S. Office Action, dated Nov. 25, 2011, issued in U.S. Appl. No. 12/986,070.

U.S. Final Office Action, dated Jun. 25, 2012, issued in U.S. Appl. No. 12/986,070.

U.S. Office Action, dated Feb. 26, 2010, issued in U.S. Appl. No. 12/334,726.

U.S. Final Office Action, dated Oct. 26, 2010, issued in U.S. Appl. No. 12/334,726.

U.S. Office Action, dated Sep. 16, 2011, issued in U.S. Appl. No. 12/334,726.

U.S. Final Office Action, dated Mar. 30, 2012, issued in U.S. Appl. No. 12/334,726.

U.S. Final Office Action, dated Oct. 23, 2012, issued in U.S. Appl. No. 12/334,726.

U.S. Notice of Allowance dated Jun. 10, 2013, issued in U.S. Appl. No. 12/334,726.

U.S. Notice of Allowance, dated May 29, 2012, issued in U.S. Appl. No. 12/566,085.

U.S. Notice of Allowance, dated Jun. 21, 2012, issued in U.S. Appl. No. 12/566,085.

U.S. Office Action, dated Jun. 21, 2013, issued in U.S. Appl. No. 13/607,511.

U.S. Final Office Action, dated Dec. 11, 2013, issued in U.S. Appl. No. 13/607,511.

U.S. Office Action, dated Jul. 25, 2014, issued in U.S. Appl. No. 13/607,511.

U.S. Notice of Allowance, dated Jan. 23, 2015, issued in U.S. Appl. No. 13/607,511.

U.S. Office Action, dated Dec. 21, 2012, issued in U.S. Appl. No. 12/964,110.

U.S. Final Office Action, dated Sep. 12, 2013, issued in U.S. Appl. No. 12/694,110.

(56)

References Cited

OTHER PUBLICATIONS

- U.S. Notice of Allowance, dated Dec. 27, 2013, issued in U.S. Appl. No. 12/964,110.
- U.S. Notice of Allowance, dated Apr. 23, 2014, issued in U.S. Appl. No. 12/964,110.
- U.S. Office Action, dated Dec. 6, 2012, issued in U.S. Appl. No. 13/315,123.
- U.S. Office Action, dated Jul. 15, 2013, issued in U.S. Appl. No. 13/315,123.
- U.S. Notice of Allowance, dated Nov. 8, 2013, issued in U.S. Appl. No. 13/315,123.
- U.S. Office Action, dated Nov. 8, 2013, issued in U.S. Appl. No. 13/313,735.
- U.S. Final Office Action, dated Jul. 29, 2014, issued in U.S. Appl. No. 13/313,735.
- U.S. Office Action, dated Oct. 10, 2014, issued in U.S. Appl. No. 13/313,735.
- U.S. Office Action, dated Apr. 20, 2015, issued in U.S. Appl. No. 13/313,735.
- U.S. Office Action, dated Sep. 12, 2013, issued in U.S. Appl. No. 13/493,936.
- U.S. Final Office Action, dated Feb. 3, 2014, issued in U.S. Appl. No. 13/493,936.
- U.S. Notice of Allowance, dated May 22, 2014, issued in U.S. Appl. No. 13/493,936.
- U.S. Office Action, dated Dec. 9, 2014, issued in U.S. Appl. No. 14/466,222.
- U.S. Final Office Action, dated Jul. 14, 2015, issued in U.S. Appl. No. 14/466,222.
- Japanese Office Action dated Sep. 17, 2013 issued in JP2009-282737.
- Japanese Office Action dated Jun. 3, 2014 issued in JP2009-282737.
- PCT International Search Report and Written Opinion dated Aug. 10, 2011 issued in PCT/US2010/059721.
- PCT International Preliminary Report on Patentability and Written Opinion dated Jun. 21, 2012 issued in PCT/US2010/059721.
- Chinese First Office Action dated Feb. 8, 2014 issued in CN 2010-80055670.3.
- Chinese Second Office Action dated Dec. 15, 2014 issued in CN 2010-80055670.3.
- Chinese Third Office Action and Search Report dated Jun. 23, 2015 issued in CN 2010-80055670.3.
- Taiwan Office Action [no translation] dated Jun. 12, 2015 issued in TW 099143081.
- Chinese First Office Action and Search Report dated Dec. 18, 2014 issued in CN 201110424193.X.
- Chinese First Office Action and Search Report dated Jan. 6, 2015 issued in CN 201110442926.2.
- Bekiari, V. et al. (1998) "Characterization of Photoluminescence from a Material Made by Interaction of (3-Aminopropyl)triethoxysilane with Acetic Acid," *Langmuir*, 14(13):3459-3461.
- Brankova et al. (2003) "Photoluminescence from Sol-Gel Organic/Inorganic Hybrid Gels Obtained through Carboxylic Acid Solvolysis," *Chem. Mater.*, 15(9):1855-1859.
- Chung, Sung-Woong et al. (Mar. 2004) "Flowable Oxide CVD Process for Shallow Trench Isolation in Silicon Semiconductor," *Journal of Semiconductor Technology and Science*, 4(1):45-51.
- Chung, Sung-Woong, et al. (2002) "Novel Shallow Trench Isolation Process Using Flowable Oxide CVD for sub-100nm DRAM," *IEEE, IEDM*, pp. 233-236.
- Fessenden et al. (1961) "The Chemistry of Silicon-Nitrogen Compounds," *Chem. Rev.* 61(4):361-388.
- Hatanaka, M., et al. (1991) "H₂O-TEOS Plasma-CVD Realizing Dielectrics Having a Smooth Surface," *IEEE, VMIC Conference*, pp. 435-441.
- Kessler et al. (2006) "New insight in the role of modifying ligands in the sol-gel processing of metal alkoxide precursors: A possibility to approach new classes of materials," *J. Sol-Gel Sci. Techn.* 40(2-3):163-179.
- Matsuura, M., et al. (1994) "Novel Self-Planarizing CVD Oxide for Interlayer Dielectric Applications," *IEEE*, pp. 117-120.
- Nakano, M., et al. (1989) "Digital CVD of SiO₂," *Extended Abstracts of the 21st Conference on Solid State Devices and Materials*, Tokyo, pp. 49-52.
- Noguchi, S. et al. (1987) "Liquid Phase Oxidation Employing O Atoms Produced by Microwave Discharge and Si(CH₃)₄," *Extended Abstracts of the 19th Conference on Solid State Devices and Materials*, Tokyo, pp. 451-454.
- Sakaue, H., et al. (1990) "Digital Chemical Vapor Deposition of SiO₂ Using a Repetitive Reaction of Triethylsilane /Hydrogen and Oxidation," *Department of Electrical Engineering, Hiroshima University*, pp. L 124-L 127.
- Stathatos et al. (Jul. 19, 2003) "Study of Acetic Acid-Catalyzed Nanocomposite Organic/Inorganic Ureasil Sol-Gel Ionic Conductors," *Langmuir*, 19:(18):7587-7591.
- U.S. Final Office Action, dated Jul. 29, 2016, issued in U.S. Appl. No. 14/519,400.
- U.S. Office Action, dated Mar. 27, 2017, issued in U.S. Appl. No. 14/519,400.
- U.S. Notice of Allowance, dated Aug. 15, 2017, issued in U.S. Appl. No. 14/519,400.
- U.S. Final Office Action, dated Sep. 2, 2016, issued in U.S. Appl. No. 14/464,071.
- U.S. Office Action, dated May 11, 2017, issued in U.S. Appl. No. 14/464,071.
- U.S. Final Office Action, dated Jan. 26, 2018, issued in U.S. Appl. No. 14/464,071.
- U.S. Notice of Allowance dated Apr. 12, 2018, issued in U.S. Appl. No. 14/464,071.
- U.S. Office Action, dated Jun. 24, 2016, issued in U.S. Appl. No. 14/249,272.
- U.S. Final Office Action, dated Feb. 19, 2016, issued in U.S. Appl. No. 13/313,735.
- Chinese Fourth Office Action dated Mar. 14, 2016 issued in CN 2010-80055670.3.
- Korean Office Action dated Nov. 1, 2016 issued in KR 10-2012-7013775.
- Taiwan Office Action dated Apr. 20, 2016 issued in TW 100145389.
- Taiwan First Office Action dated Apr. 3, 2018 issued in TW 105136948.
- Taiwan Second Office Action [Decision of Refusal] dated Mar. 9, 2018 issued in TW 102107721.
- Chinese Second Office Action dated Aug. 14, 2018 issued in CN 201510516169.7.
- Chinese First Office Action dated Dec. 13, 2017 issued in CN 20170801752910.
- Korean First Office Action dated Dec. 18, 2017 issued in KR 10-2011-0131725.
- Taiwan First Office Action dated Jul. 3, 2018 issued in TW 103136878.
- Taiwan First Office Action dated May 25, 2018 issued in TW 103136882.

* cited by examiner




Figure 1




Figure 2A




Figure 2B




Figure 2C




Figure 2D




Figure 3




Figure 4A




Figure 4B




Figure 5




Figure 6




Figure 7




Figure 8




Figure 9




Figure 10




Figure 11A




Figure 11B




Figure 12A




Figure 12B

1

APPARATUS FOR UV FLOWABLE
DIELECTRIC

BACKGROUND

It is often necessary in semiconductor processing to fill high aspect ratio gaps with insulating material. This is the case for shallow trench isolation (STI), inter-metal dielectric (IMD) layers, inter-layer dielectric (ILD) layers, pre-metal dielectric (PMD) layers, passivation layers, etc. As device geometries shrink and thermal budgets are reduced, void-free filling of narrow width, high aspect ratio (AR) features (e.g., AR>6:1) becomes increasingly difficult due to limitations of existing deposition processes.

SUMMARY

One aspect of the disclosure may be implemented in an apparatus including a multi-station chamber including chamber walls and a first station and a second station at least partially within the chamber walls; the first station having a first substrate support and a showerhead located above the first substrate support; a gas distribution system configured to deliver reactants to the first station via the showerhead; the second station having a second substrate support and an ultraviolet light configured to illuminate a UV exposure area on the second substrate support; and a mechanism to transfer a substrate from the first station to the second station.

In some embodiments, the apparatus may further include a heating system and cooling system, wherein the heating system is configured to heat an inner surface of the chamber walls and the cooling system is configured to cool the first substrate support. In some embodiments, the ultraviolet light is located above the second substrate support.

In some embodiments, the apparatus may further include a controller having machine readable instructions to: distribute a gas comprising a dielectric precursor to the first station while a substrate is present in the first station; maintain the first substrate support at a temperature between -20° C. and 100° C. while the dielectric precursor is in the first station; after distributing the gas to the first station, transfer the substrate to the second station; and expose the substrate to UV radiation. The instructions may further include instructions for maintaining the second substrate support at a temperature of between -20° C. and 100° C. while the substrate is in the second station.

Another aspect of the disclosure may be implemented in an apparatus including a chamber including a substrate support; an ultraviolet radiation source; a showerhead configured to distribute a reactant to the chamber; and a controller comprising machine readable instructions for introducing a dielectric precursor the chamber via the showerhead at a support temperature of between about -20° C. and 100° C. to thereby form a flowable film; and exposing the flowable film to UV radiation.

In some embodiments, the chamber is a single-station chamber. In some embodiments, the chamber is a multi-station chamber. In some embodiments, the ultraviolet radiation source is embedded within or mounted to the showerhead. In some embodiments, the apparatus has a plurality of ultraviolet radiation sources evenly distributed across the showerhead. In some embodiments, the ultraviolet radiation source is part of a second chamber connected to the chamber. The substrate support may be rotatable.

2

These and other aspects of the disclosure are described further below.

BRIEF DESCRIPTION OF DRAWINGS

FIG. 1 is a flow diagram illustrating an example of a process for forming a flowable dielectric film.

FIGS. 2A-2D show examples of schematic cross-sectional illustrations of substrates including gaps that may be filled with a flowable dielectric film.

FIG. 3 is a schematic illustration of a graph showing an example of a critical dimension-partial pressure deposition curve.

FIGS. 4A and 4B are flow diagrams illustrating examples of processes for forming a flowable dielectric film.

FIG. 5 is a schematic illustration of pore sealing according to certain implementations.

FIG. 6 is an example of a reaction mechanism that may be employed in certain implementations.

FIG. 7 shows an image 701 of uniform densified flowable film formed with in-situ UV exposure.

FIG. 8 shows Fourier transform infrared spectroscopy (FTIR) spectra for films deposited from TVTMCTS with no oxidant employed and in-situ UV exposure during the deposition.

FIGS. 9, 10, 11A, 11B, 12A, and 12B are schematic illustrations of apparatus suitable to practice the methods described herein.

DETAILED DESCRIPTION OF THE
INVENTION

Introduction

Aspects of the present invention relate to forming flowable dielectric films on substrates and related apparatuses. Some embodiments include filling high aspect ratio gaps with insulating material. Some embodiments include filling small pores with insulating material. For ease of discussion, the description below refers chiefly to flowable silicon oxide films, however the processes described herein may also be used with other types of flowable dielectric films. For example, the dielectric film may be primarily silicon nitride, with Si—N and N—H bonds, primarily silicon oxynitrides, primarily silicon carbide, or primarily silicon oxycarbide films.

It is often necessary in semiconductor processing to fill high aspect ratio gaps with insulating material. This is the case for shallow trench isolation (STI), inter-metal dielectric (IMD) layers, inter-layer dielectric (ILD) layers, pre-metal dielectric (PMD) layers, passivation layers, etc. As device geometries shrink and thermal budgets are reduced, void-free filling of narrow width, high aspect ratio (AR) features becomes increasingly difficult due to limitations of existing deposition processes. In certain embodiments, the methods pertain to filling high aspect (AR) ratio (typically at least 6:1, for example 7:1 or higher), narrow width (e.g., sub-50 nm) gaps. In certain embodiments, the methods pertain to filling low AR gaps (e.g., wide trenches). Also in certain embodiments, gaps of varying AR may be on the substrate, with the embodiments directed at filling low and high AR gaps.

In a particular example, a PMD layer is provided between the device level and the first layer of metal in the interconnect level of a partially fabricated integrated circuit. The methods described herein include dielectric deposition in which gaps, (e.g., the gaps between gate conductor stacks)

are filled with dielectric material. In another example, the methods are used for shallow trench isolation processes in which trenches are formed in semiconductor substrates to isolate devices. The methods described herein include dielectric deposition in these trenches. The methods can also be used for back end of line (BEOL) applications, in addition to front end of line (FEOL) applications. These can include filling gaps at an interconnect level.

Still further, in certain embodiments, the methods pertain to pore sealing of porous dielectric films using flowable dielectric material. For example, the methods can involve pore sealing of a porous ultra low-k (ULK) film in BEOL processing of semiconductor devices.

The methods described herein can be used for any type of flowable dielectric process including undoped silica glass (USG), low-k, and ultra-low k ULK flowable oxide.

The term "semiconductor device" as used herein refers to any device formed on a semiconductor substrate or any device possessing a semiconductor material. In many cases, a semiconductor device participates in electronic logic or memory, or in energy conversion. The term "semiconductor device" subsumes partially fabricated devices (such as partially fabricated integrated circuits) as well as completed devices available for sale or installed in particular apparatus. In short, a semiconductor device may exist at any state of manufacture that employs a method of the subject matter disclosed herein or possesses a structure of this subject matter disclosed herein.

Vapor-phase reactants are introduced to a deposition chamber to deposit the flowable dielectric films. As-deposited, the flowable dielectric films generally have flow characteristics that can provide consistent fill of at least the opening of a pore. The term "as-deposited flowable dielectric film" refers to a flowable dielectric film prior to any post-deposition treatments, densification, cure or anneal. An as-deposited flowable dielectric film may be characterized as a soft jelly-like film, a gel, a sol, or a flowable film. In some embodiments, the as-deposited film is a solid, non-liquid film that is liquid and flowable only during the deposition process; as soon as the deposition process stops, it is a solid film.

FIG. 1 is a process flow diagram illustrating one example of a process for forming a flowable dielectric film. The process can be used in the fabrication of semiconductor devices, displays, LEDs, photovoltaic panels and the like. As noted above, in semiconductor device fabrication, the process can be used for BEOL applications and FEOL applications. In some embodiments, the processes may be used for applications in which high aspect ratio gaps are filled with insulating material. Examples include shallow trench isolation (STI), formation of inter-metal dielectric (IMD) layers, inter-layer dielectric (ILD) layers, pre-metal dielectric (PMD) layers, and passivation layers, and filling gaps at the interconnect level. In some embodiments, the process can be used for pore-sealing. Further examples include formation of sacrificial layers for air gap formation or lift-off layers.

First, a substrate including a gap is provided to a deposition chamber (block 101). Examples of substrates include semiconductor substrates, such as silicon, silicon-on-insulator (SOI), gallium arsenide and the like, as well as glass and plastic substrates. The substrate includes at least one and typically more than one gap to be filled, with the one or more gaps being trenches, holes, vias, pores, or other unfilled features on the substrate.

FIGS. 2A-2D show examples of schematic cross-sectional illustrations of substrates 201 including gaps 203.

Turning first to FIG. 2A, a gap 203 can be defined by sidewalls 205 and a bottom 207. It may be formed by various techniques, depending on the particular integration process, including patterning and etching blanket (i.e., planar) layers on a substrate or by building structures having gaps there-between on a substrate. In certain embodiments a top of the gap 203 can be defined as the level of planar surface 209. Specific examples of gaps are provided in FIGS. 2B and 2C. In FIG. 2B, a gap 203 is shown between two gate structures 202 on a substrate 201. The substrate 201 may be a semiconductor substrate and may contain n-doped and p-doped regions (not shown). The gate structures 202 include gates 204 and silicon nitride or silicon oxy-nitride layer 211. In certain embodiments, the gap 203 is re-entrant, i.e., the sidewalls taper inwardly as they extend up from the bottom 207 of the gap; gap 203 in FIG. 2B is an example of a re-entrant gap.

FIG. 2C shows another example of gap to be filled. In this example, gap 203 is a trench formed in silicon substrate 201. The sidewalls and bottom of the gap are defined by liner layer 216, e.g., a silicon nitride or silicon oxynitride layer. The structure also includes pad silicon oxide layer 215 and pad silicon nitride layer 213. FIG. 2C is an example of a gap that may be filled during a STI process. In certain cases, liner layer 216 is not present. In certain embodiments, the sidewalls of silicon substrate 201 are oxidized.

FIGS. 2B and 2C provide examples of gaps that may be filled with dielectric material in a semiconductor fabrication process. The processes described herein may be used to fill any gap that requires dielectric fill. In certain embodiments, the gap critical dimension is the order of about 1-50 nm, in some cases between about 2-30 nm or 4-20 nm, e.g. 13 nm. Critical dimension refers to the width of the gap opening at its narrowest point. In certain embodiments, the aspect ratio of the gap is between 3:1 and 60:1. According to various embodiments, the critical dimension of the gap is 32 nm or below and/or the aspect ratio is at least about 6:1.

As indicated above, a gap may be defined by a bottom surface and sidewalls. The term sidewall or sidewalls may be used interchangeably to refer to the sidewall or sidewalls of a gap of any shape, including a round hole, a long narrow trench, etc. In some embodiments, the processes described herein may be used to form flowable films on planar surfaces in addition to or instead of in gaps.

Also in some embodiments, the gap may be a pore. FIG. 2D shows an example of a structure including an embedded metal line 251 in a first dielectric layer 253. An etched porous dielectric layer 255 overlies the first dielectric layer 253 and, optionally an etch stop layer 261 such as a silicon carbide, silicon oxycarbide, silicon nitride, or silicon oxynitride etch stop layer. The etched porous dielectric layer 255 is etched in previous processing to define a recess 257 and expose the metal line 251. An exposed surface 262 of the etched porous dielectric layer 255 includes the surface of the recess 257.

The etched porous dielectric layer 255 is a porous dielectric having connected porosity. An enlarged schematic view of a cross-section of a portion of the etched porous dielectric layer 255 is depicted. The etched second dielectric layer includes gaps 203 that are connected (in or out of the plane of the cross-section) pores and thus exposed at the surface 212 to the ambient conditions.

A portion 265 of the etched porous dielectric layer 255 includes sealant material 266 deposited by a flowable dielectric deposition process. An enlarged schematic view of a cross-section of a portion of the sealed etched porous dielectric layer 255 is depicted. Gaps 203 that were previ-

ously open to the ambient are sealed with the sealant material **216** deposited from the flowable dielectric deposition process. Depending on whether or not the field regions of the etched porous dielectric layer **255** are capped or not with another material (e.g., such an etch stop or hard mask layer), pores open to the field region (not shown) may also be sealed in addition to the pores open to the recess **257**. Subsequent operations may involve optionally cleaning or treating the surface of the metal line **251**, depositing a barrier layer, and filling the recess **257** with a conductive material. If the pores are not sealed, any of these operations may result in precursor and/or metal penetration into the gaps **203**, which can result in lower break down voltage and failure.

The porous dielectric film may be for example, a ULK film, having a dielectric constant of 2.4 or less. Examples of ULK films include carbon doped oxide (CDO) films, zeolite films, and polymer films.

The porosity of a dielectric film may be connected, and may include pores that are introduced by removal of a porogen from a dielectric matrix and/or pores that are inherent to the dielectric matrix. For example, a CDO matrix may have porosity due the incorporation of methyl or other organic groups. The porous dielectric film may include mesoporosity and/or microporosity. Mesoporosity generally refers to pore sizes of 2 nm-50 nm and microporosity to pore sizes less than 2 nm. In dielectrics having connected porosity, the size of at least some of the connected pores may be on a continuum with micropores having sizes on the order of Angstroms to nanometers, connected to mesopores having sizes on the order of nanometers to tens of nanometers. Although the methods may also be used to seal unconnected pores and provided smooth deposition surfaces, particular use may be found in sealing connected pores that left unsealed provide a diffusion pathway through a film. Porosity characteristics at the exposed surface may depend on the etch process as well as on the particular film and method of deposition.

Returning to FIG. 1, the deposition surface may be or include one or multiple materials. For example, sidewall and bottom surfaces that define a gap may be one material or include multiple materials. Referring to FIG. 2C, for example, if a liner layer **216** is present, it may be the only deposition surface. However, if the liner layer **216** is not present, the deposition surface can include the silicon substrate **201**, the pad silicon oxide layer **215** and the pad silicon nitride layer **213**. Examples of gap surface materials, including sidewall and/or bottom materials, include silicon nitrides, silicon oxides, silicon carbides, silicon oxynitrides, silicon oxycarbides, silicides, silicon germanium, as well as bare silicon or other semiconductor material. Particular examples include SiN, SiO₂, SiC, SiON, NiSi, and polysilicon. Further examples of gap materials used in BEOL processing include copper, tantalum, tantalum nitride, titanium, titanium nitride, ruthenium and cobalt. In certain embodiments, prior to flowable dielectric deposition, the gap is provided with a liner, barrier or other type of conformal layer formed in the gap, such that the deposition surfaces include the conformal layer. In some embodiments, the deposition surfaces of a substrate are exposed to a treatment. Examples of pre-deposition treatments are provided further below.

Returning to FIG. 1, a process gas including a dielectric precursor is flowed into the deposition chamber (block **103**). As described below, the process gas may include an optional co-reactant. A flowable dielectric film is deposited into the gap (block **105**).

In some embodiments, the flowable dielectric film is selectively deposited in the gap. Selective deposition refers to a process that preferentially deposits in a location without or prior to depositing in other locations. In block **105**, the flowable dielectric material preferentially deposits inside the gaps rather than outside the gaps. In the context of pore sealing, the dielectric preferentially deposits in at least the opening of the pores of the porous dielectric material than outside the pores of the porous dielectric material, for example, on the discontinuous external surface of the porous dielectric and on the exposed metal surfaces in FIG. 2D. As such, deposition of flowable dielectric material on other exposed surfaces such as on the field regions may be non-existent or substantially non-existent, with one of ordinary skill in the art understanding that there may be some small areas of film nucleating on these surfaces.

According to various implementations, block **105** may involve a mechanism that deposits preferentially in the smallest features, be it a via hole, trench, or the small openings of pores in the porous dielectric, without or prior to forming a continuous film outside of these features.

In some implementations, block **105** exploits a thermodynamic effect in which a flowable dielectric material remains selectively condensed in the gaps, as the smallest spaces available for formation of the flowable dielectric material. As such the flowable dielectric material is selectively deposited in these gaps. In some pore sealing applications, the smallest space available is the openings to the pores such that flowable dielectric material is deposited in the openings but does not completely fill the pores. (In some implementations, the thermodynamic effect can be exploited to evaporate flowable dielectric material deposited outside the pores, while the flowable material in the pores remains condensed.)

Depositing a flowable oxide film, for example, can involve exposing the substrate to gaseous reactants including a dielectric precursor such that a condensed flowable film forms in the gap. The deposition generally occurs in non-plasma conditions, though in certain embodiments, plasma-enhanced conditions may be employed. In other embodiments, reactive species from a downstream plasma may be present even though the substrate is not directly exposed to a plasma.

The dielectric precursor is a silicon-containing compound. In some implementations, the dielectric precursor is a compound that undergoes photo-induced polymerization and may be a cyclic siloxane, a cyclic silazane, or a linear or cyclic silicon-containing compound that includes unsaturated hydrocarbon groups.

An oxidant such as a peroxide, ozone, oxygen, water, etc. may be optionally flowed. In some embodiments, the oxidant is a non-hydroxyl-forming oxidant such as ozone or oxygen.

In some implementations, a SiCOH film is formed, using for example a dielectric precursor including one or more Si—C bonds. In some implementations, the flowable dielectric film is a silicon and nitrogen-containing film, such as silicon nitride or silicon oxynitride deposited by introducing vapor phase reactants to a deposition chamber at conditions such that they react to form a flowable film. The nitrogen incorporated in the film may come from one or more sources, such as a silicon and nitrogen-containing precursor, a nitrogen precursor (for example, ammonia (NH₃) or hydrazine (N₂H₄)), or a nitrogen-containing gas (for example N₂, NH₃, NO, NO₂, or N₂O).

Further discussion of deposition chemistries is provided below.

The process gases may be introduced into the reactor simultaneously, or one or more component gases may be introduced prior to the others. U.S. Pat. No. 8,278,224, incorporated by reference herein, provides a description of reactant gas sequences that may be used in accordance with certain embodiments.

Block **105** may involve a capillary condensation mechanism in which the flowable dielectric material preferentially deposits in the smallest features. Due to capillary condensation, flowable process reactants can condense the smallest features even if their partial pressure is below the saturated vapor pressure. This is due to an increased number of van der Waals interactions between vapor phase molecules inside the confined space of capillaries (i.e., the gaps). In pore sealing applications, this allows pore sealing without continuous film deposition on surfaces and bottom up gap fill.

In some implementations, block **105** involves providing a precursor in a vapor phase at a partial pressure below its saturation pressure. The preference for liquid to remain condensed in the small spaces (i.e., capillary condensation) at pressures below the saturation pressure allows for selective deposition in gaps. In some embodiments, the partial pressure may be gradually increased until it approaches the point the material begins to condense as a liquid in the gaps, or the precursor may be introduced at this pressure.

Reaction conditions are set to appropriately control the reactant partial pressures relative to their saturated vapor pressures, generally at relatively low temperatures, e.g., -20°C . to 100°C . The capillary condensation in the gaps may be self-limiting, stopping when the gaps are filled or when the pore or other gap openings are sealed.

Pressure and temperature may be varied to adjust deposition time; high pressure and low temperature are generally favorable for quick deposition. High temperature and low pressure will result in slower deposition time. Thus, increasing temperature may involve increasing pressure. In one embodiment, the temperature is about 5°C . and the pressure about 10 Torr. Exposure time depends on reaction conditions as well as pore or other gap size. Deposition rates are from about 100 angstroms/min to 1 micrometer/min according to various embodiments. The substrate is exposed to the reactants under these conditions for a period long enough to deposit a flowable film in the pores or other gaps. In certain embodiments, deposition time is 0.1-5 seconds.

The amount of condensation is controlled by the reactants' partial pressures relative to their saturated vapor pressures (which are constant for a given deposition temperature). The dependence of fill rate on critical dimension can be tuned by varying the partial pressures. In this manner, selectivity can be tuned, improving the capability to deposit in just the pores, other gaps, or as otherwise desired. This is illustrated qualitatively in FIG. 3, which shows a partial pressure-critical dimension deposition curve. At low enough partial pressure of the dielectric precursor, there is no condensation or deposition in features of any size. As the partial pressure is increased, the dielectric precursor condenses in small features, with deposition occurring in increasingly larger feature sizes as the partial pressure is increased. So, for example, to prevent deposition in a 20 nm etched trench of a ULK film while allowing deposition in the pores of the ULK film, the partial pressure of the dielectric precursor is maintained within the cross-hatched portion of the curve.

Returning to FIG. 1, at block **107**, the substrate is exposed to UV radiation. As a result, photo-induced polymerization and densification occurs in some embodiments. According

to various embodiments, UV exposure may be in-situ or ex-situ with respect to the deposition chamber. FIGS. 4A and 4B show operations in examples of in-situ and ex-situ processes. First, in FIG. 4A, an optional pre-treatment may be performed to activate the substrate and improve wettability (block **401**). Examples of pre-treatments are given below. If performed, the pre-treatment may be in the same or a different station or chamber as the subsequent deposition. Next, a dielectric precursor is condensed to yield a liquid dielectric film (block **403**). As discussed above, block **403** can involve capillary condensation to preferentially deposit in a pore or other gap. The substrate including the deposited dielectric film is then transferred to a UV station (block **405**). The transfer may be under vacuum, for example, with the deposition chamber and UV station connected via a vacuum transfer chamber. The UV station may be in a single station or multi-station UV module. As described below, in some embodiments, the UV station may take place in the same module as the deposition, for example, with deposition taking place at one or more stations of a multi-station module and UV exposure taking place at one or more other stations of the multi-station module. UV exposure is then performed, yielding a dense solid dielectric film (block **407**).

In some embodiments, blocks **403** to blocks **407** may be repeated to build up a film of a desired thickness. For example, UV exposure may be performed after each 500 nanometers of flowable dielectric film is deposited.

In various embodiments, dielectric precursors having relatively high boiling points are used such that the substrate can be maintained at a temperature below the boiling point during the process. This allows a dielectric precursor to be condensed and then transferred to the UV station. Temperature during UV exposure should also be kept significantly below the boiling point of the precursor or a condensed product thereof. In some embodiments, the substrate temperature during UV exposure may be at least 25°C . less than the boiling point of a precursor. Boiling points for examples of various precursors are given below.

In FIG. 4B, block **401** is performed as described above. Next, the dielectric precursor is condensed with simultaneous UV exposure to yield a dense solid dielectric film (block **406**). UV exposure may be performed after dielectric deposition in-situ in the deposition chamber, in some embodiments.

The UV exposure in FIGS. 4A and 4B is distinct from a post-deposition UV cure operation that may be performed as an alternative to a thermal anneal, for example, to densify sol gel deposited films or remove reaction by products. Such UV cure operations typically take place at much higher temperatures.

Deposition Chemistries and Reaction Mechanisms Dielectric Precursor

The dielectric precursor is a silicon-containing compound capable of undergoing photo-induced polymerization. Examples of such compounds include cyclic siloxanes, cyclic silazanes, and linear or cyclic silicon-containing precursors containing vinyl or other unsaturated hydrocarbon groups.

Examples of cyclic siloxanes include octamethylcyclotetrasiloxane (OMCTS), tetravinyltetramethylcyclotetrasiloxane (TVMCTS), tetramethylcyclotetrasiloxane (TMCTS), pentamethylcyclopentasiloxane, and hexamethylcyclotrisiloxane. In some embodiments, cyclic siloxanes can be used in the methods described herein for catalyst-free deposition processes. In some embodiments,

cyclic silazanes can be used in the methods described herein for catalyst-free deposition processes.

In some embodiments, dielectric precursors having relatively high boiling points are employed. For example, TMCTS has a boiling point of 135° C., TVTMCTS has a boiling point of 224° C., and OMCTS has a boiling point of 175° C. In some embodiments, dielectric precursors having boiling points of at least 100° C., at least 125° C., at least 150° C., at least 175° C., or at least 200° C. are employed. Boiling points are given at atmospheric pressure.

In pore-sealing applications, the size of the precursor may be tailored to the pore size of the porous dielectric film: it should be small enough that it fits in a pore, but large enough that it does not penetrate too deeply within the porous dielectric. This is illustrated in FIG. 5, in which relatively large cyclic molecules **501** (e.g., van der Waals radius of 1.2 nm) fit within the pores of the porous dielectric **500** to seal the pores, but do not penetrate deeply within the pores. By contrast, smaller linear molecules **503** (e.g., van der Waals radius of 0.5 nm) penetrate the porous dielectric, which can lead to an undesirable increase in dielectric constant. In some embodiments, the van der Waals radius of the molecule is targeted to be about the same as the average pore size. As an example, the average pore size of a CVD ULK film may be 1.0±0.5 nm. A cyclical molecule having a van der Waals radius of at least 0.8 nm may be used. In some embodiments, it may have a van der Waals radius of at least 1.0 nm or 1.2 nm.

According to various embodiments, the as-deposited film is a silicon oxide film or a silicon nitride film, including carbon-containing silicon oxide or silicon nitride films. According to various embodiments, Si—C or Si—N containing dielectric precursors may be used, either as a main dielectric precursor or a dopant precursor, to introduce carbon or nitrogen into the film. Examples of such films include carbon doped silicon oxides and silicon oxynitrides. In some embodiments, the silicon nitride film, including primarily Si—N bonds with N—H bonds.

Co-Reactant

For silicon oxide deposition, an oxidant may be employed in some embodiments. In some other embodiments, oxygen may be supplied solely by a cyclic siloxane precursor, for example, such that the deposition is a single reactant deposition, with no co-reactant. However, an oxidant may be supplied depending on the oxygen content of the particular precursor employed.

If employed, examples of suitable oxidants include, but are not limited to, ozone (O₃), peroxides including hydrogen peroxide (H₂O₂), oxygen (O₂), water (H₂O), alcohols such as methanol, ethanol, and isopropanol, nitric oxide (NO), nitrous dioxide (NO₂), nitrous oxide (N₂O), carbon monoxide (CO) and carbon dioxide (CO₂). In certain embodiments, a remote plasma generator may supply activated oxidant species.

For silicon nitride deposition, a nitrogen co-reactant may be employed in some embodiments. In some other embodiments, nitrogen may be supplied solely by a cyclic silazane precursor, for example, such that the deposition is a single reactant deposition, with no co-reactant. If employed, examples of suitable nitrogen co-reactants include, but are not limited to, ammonia (NH₃), hydrazine (N₂H₄), nitrogen (N₂), NO, NO₂, and N₂O.

Dopant

One or more dopant precursors, e.g., a carbon-, nitrogen-, fluorine-, phosphorous- and/or boron-containing gas, may be supplied. Sometimes, though not necessarily, an inert carrier gas is present. In certain embodiments, the gases are

introduced using a liquid injection system. In certain embodiments, carbon-doped silicon precursors are used, either in addition to another precursor (e.g., as a dopant) or alone. Carbon-doped precursors can include at least one Si—C bond. In certain embodiments, aminosilane precursors are used.

Catalyst

In some embodiments, the deposition may be a catalyst-free deposition that does not employ any one of the below-described catalysts. However, a catalyst may be employed in certain embodiments. In certain embodiments, a proton donor catalyst is employed. Examples of proton donor catalysts include 1) acids including nitric, hydrofluoric, phosphoric, sulfuric, hydrochloric and bromic acids; 2) carboxylic acid derivatives including R—COOH and R—C(=O)X where R is substituted or unsubstituted alkyl, aryl, acetyl or phenol and X is a halide, as well as R—COOC—R carboxylic anhydrides; 3) Si_xX_yH_z where x=1-2, y=1-3, z=1-3 and X is a halide; 4) R_xSi—X_y, where x=1-3 and y=1-3; R is alkyl, alkoxy, alkoxyalkane, aryl, acetyl or phenol; and X is a halide; and 5) ammonia and derivatives including ammonium hydroxide, hydrazine, hydroxylamine, and R—NH₂ where R is substituted or unsubstituted alkyl, aryl, acetyl, or phenol.

In addition to the examples of catalysts given above, halogen-containing compounds which may be used include halogenated molecules, including halogenated organic molecules, such as dichlorosilane (SiCl₂H₂), trichlorosilane (SiCl₃H), methylchlorosilane (SiCH₃ClH₂), chlorotriethoxysilane, chlorotrimethoxysilane, chloromethyldiethoxysilane, chloromethyldimethoxysilane, vinyltrichlorosilane, diethoxydichlorosilane, and hexachlorodisiloxane. Acids which may be used may be mineral acids such as hydrochloric acid (HCl), sulfuric acid (H₂SO₄), and phosphoric acid (H₃PO₄); organic acids such as formic acid (HCOOH), acetic acid (CH₃COOH), and trifluoroacetic acid (CF₃COOH). Bases which may be used include ammonia (NH₃) or ammonium hydroxide (NH₄OH), phosphine (PH₃); and other nitrogen- or phosphorus-containing organic compounds. Additional examples of catalysts are chlorodiethoxysilane, methanesulfonic acid (CH₃SO₃H), trifluoromethanesulfonic acid (“triflic”, CF₃SO₃H), chlorodimethoxysilane, pyridine, acetyl chloride, chloroacetic acid (CH₂ClCO₂H), dichloroacetic acid (CHCl₂CO₂H), trichloroacetic acid (CCl₂CO₂H), oxalic acid (HO₂CCO₂H), benzoic acid (C₆H₅CO₂H), and triethylamine.

Examples of other catalysts include hydrochloric acid (HCl), hydrofluoric acid (HF), acetic acid, trifluoroacetic acid, formic acid, dichlorosilane, trichlorosilane, methyltrichlorosilane, ethyltrichlorosilane, trimethoxychlorosilane, and triethoxychlorosilane.

In addition to the catalysts described above, in some implementations, catalysts formulated for BEOL processing applications may be used. Such catalysts are disclosed in U.S. patent application Ser. No. 14/464,196 titled “LOW-K OXIDE DEPOSITION BY HYDROLYSIS AND CONDENSATION”, Aug. 20, 2014 and incorporated herein by reference.

In some implementations, halogen-free acid catalysts may be employed, with examples including 1) acids including nitric, phosphoric, sulfuric acids; and 2) carboxylic acid derivatives including R—COOH where R is substituted or unsubstituted alkyl, aryl, acetyl or phenol, as well as R—COOC—R carboxylic anhydrides.

Also in some implementations, self-catalyzing silane dielectric precursors including aminosilanes, may be used. Aminosilanes that may be used include, but are not limited

11

to, the following: (1) $H_x-Si-(NR)_y$, where $x=0-3$, $x+y=4$ and R is an organic hydride group. Further examples of self-catalyzed dielectric precursors are provided in U.S. patent application Ser. No. 14/464,196, incorporated herein by reference.

Surfactants

Surfactants may be used to relieve surface tension and increase wetting of reactants on the substrate surface. They may also increase the miscibility of the dielectric precursor with the other reactants, especially when condensed in the liquid phase. Examples of surfactants include solvents, alcohols, ethylene glycol and polyethylene glycol. Difference surfactants may be used for carbon-doped silicon precursors because the carbon-containing moiety often makes the precursor more hydrophobic.

Solvents may be non-polar or polar and protic or aprotic. The solvent may be matched to the choice of dielectric precursor to improve the miscibility in the oxidant. Non-polar solvents include alkanes and alkenes; polar aprotic solvents include acetones and acetates; and polar protic solvents include alcohols and carboxylic compounds.

Examples of solvents that may be introduced include alcohols, e.g., isopropyl alcohol, ethanol and methanol, or other compounds, such as ethers, carbonyls, nitriles, miscible with the reactants. Solvents are optional and in certain embodiments may be introduced separately or with the oxidant or another process gas. Examples of solvents include, but not limited to, methanol, ethanol, isopropanol, acetone, diethylether, acetonitrile, dimethylformamide, and dimethyl sulfoxide, tetrahydrofuran (THF), dichloromethane, hexane, benzene, toluene, isoheptane and diethylether. The solvent may be introduced prior to the other reactants in certain embodiments, either by puffing or normal delivery. In some embodiments, the solvent may be introduced by puffing it into the reactor to promote hydrolysis, especially in cases where the precursor and the oxidant have low miscibility.

Carrier Gases

Sometimes, though not necessarily, an inert carrier gas is present. For example, helium and/or argon, may be introduced into the chamber with one of the compounds described above.

Any of the process gases (silicon-containing precursor, oxidant or other co-reactant, solvent, catalyst, etc.) either alone or in combination with one or more other reactants, may be introduced prior to the remaining reactants. Also in certain embodiments, one or more reactants may continue to flow into the reaction chamber after the remaining reactant flows have been shut off.

Reaction Mechanisms

It has been found that when using certain dielectric precursors, excellent fill may be achieved using the processes described with reference to FIGS. 4A and 4B, even in the absence of a catalyst. In particular, cyclic siloxanes have been found to provide excellent fill even in the absence of a catalyst. It is believed that cyclic silazanes would show similar results.


Without being bound by a particular theory, it is believed that a reaction may transpire by one or more of the following reaction mechanisms.

In some embodiments, the reaction may proceed by a radical-chain mechanism. The radical initiation mechanism is possibly (but not limited to) an adsorbate based radical which adds across oxidizable neighbors such as unsaturated hydrocarbon bonds (such as terminal vinyl, hydrides, or halides) on a siloxane ring that constitute the condensed precursor. Radical propagation progresses to generate a

12

polymer film out of the condensed liquid and release H radicals that recombine to release H_2 gas or terminal hydride on reactor surfaces. The final product is a dense low-k oxide film devoid of unsaturated hydrocarbons.

In some embodiments, ring opening and polymerization may include photo dissociation of small amounts of water:



The ring opening and polymerization reactions may proceed as shown in the example of FIG. 6 for a generic cyclic siloxane ring 601. (R represents organic groups and M represents any positively charged moiety (e.g., H^+ or NH_4^+) in the mechanism shown in FIG. 6). A hydroxyl anion generated by the photodissociation attacks a silicon atom of the siloxane ring, which results in the ring opening. Polymerization may then proceed by a SiO^- attack on another siloxane ring, resulting in opening that ring and polymerizing.

The above-described mechanisms are distinct from sol gel deposition reactions where a precursor and an oxidizer are introduced and condensed onto a substrate where they are allowed to react via hydrolysis and polycondensation to form an oxide film with water and alcohol as byproducts. Advantages to certain described embodiments include reduced or eliminated reliance on post deposition film processing such as thermal or UV cure for film densification and removal of reaction byproducts, excess reactants and adsorbed residual hydroxyl groups to attain the desired physical and electrical properties. As noted above, in some embodiments, the described methods allow flowable dielectric deposition without a catalyst and with a halide-free chemistry. By contrast, hydrolysis and polycondensation depositions typically include use of catalysts that could oxidize metallic components of integrated structures. Halide anions that constitute the catalyst also may be retained in the deposited material and leach out of the low-k layer into other parts of the integrated structure leading to corrosion during integration/further processing/longer times. Residual halide anions can also lead to mobile charges in the dielectric layer, degrading its insulating electrical properties. While organic acid catalysts may address some issues associated with halide catalysts, their use is limited by relatively lower deposition rates and a need for long queue times. Moreover, photosensitivity of uncured films derived from organic acid catalyzed deposition also poses significant post deposition processing challenges. Basic catalysts that are molecularly grafted as part of the precursor or incorporated as an additive result in significantly porous films. Embodiments of the methods described herein can avoid these issues associated with halide, organic acid and base catalysts.

There is typically a presence of pores and voids within material deposited in small dimensions via hydrolysis-polycondensation deposition. These pores and voids are generated upon removal of byproducts and unreacted material. Embodiments of the methods that do not rely on hydrolysis and polycondensation may not have these voids. The generated by products generated are H radicals and H_2 gas, which are easily expunged without leaving voids and pores behind. In particular, single reactant systems (no co-reactant) generate significantly fewer byproducts with no unreacted material left behind at the end of deposition.

According to various embodiments, the films may be deposited at thicknesses of several microns, while still maintaining excellent quality. By contrast, sol gel derived films typically exhibit low hardness and modulus and with tensile stresses that limit maximum thicknesses to about 1

micron before film begins to crack. By contrast, the methods herein may be used to deposit films up to 2 microns before cracking has been observed.

A radical chain reaction mechanism also has a significantly more rapid rate of deposition than a hydrolysis-polycondensation reaction.

Reaction Conditions

Reaction conditions can be such that the dielectric precursor, or a vapor phase product of a reaction thereof, condenses on the substrate surface to form a flowable film. Chamber pressure may be between about 1 and 200 Torr, in certain embodiments, it is between 10 and 75 Torr. In a particular embodiment, chamber pressure is about 10 Torr.

Substrate temperature is between about -20°C . and 100°C . in certain embodiments. In certain embodiments, temperature is between about -20°C . and 30°C ., e.g., between -10°C . and 10°C . Pressure and temperature may be varied to adjust deposition time; high pressure and low temperature are generally favorable for quick deposition. High temperature and low pressure will result in slower deposition time. Thus, increasing temperature may involve increasing pressure. In one embodiment, the temperature is about 5°C . and the pressure about 10 Torr. Exposure time depends on reaction conditions as well as pore or other gap size. Deposition rates are from about 100 angstroms/min to 1 micrometer/min according to various embodiments. The substrate is exposed to the reactants under these conditions for a period long enough to deposit a flowable film in the pores or other gaps. In certain embodiments, deposition time is 0.1-5 seconds.

As described above, the amount of condensation may be controlled by the reactants' partial pressures relative to their saturated vapor pressures (which are constant for a given deposition temperature).

Substrate temperature throughout the deposition and simultaneous or subsequent UV exposure is maintained at a level below the boiling point of the dielectric precursors and reaction products thereof. Pressure throughout the deposition and simultaneous or subsequent UV exposure may be sub-atmospheric.

Example UV intensities include 50 W to 500 W of 253.7 nm UV from a broadband (190 nm to 290 nm) source.

Pre-Treatment

According to various embodiments, a pretreatment operation involves exposure to a plasma containing oxygen, nitrogen, helium or some combination of these. The plasma may be downstream or in-situ, generated by a remote plasma generator, such as an Astron® remote plasma source, an inductively-coupled plasma generator or a capacitively-coupled plasma generator. Examples of pre-treatment gases include O_2 , O_3 , H_2O , NO , NO_2 , N_2O , H_2 , N_2 , He , Ar , and combinations thereof, either alone or in combination with other compounds. Examples of chemistries include O_2 , O_2/N_2 , O_2/He , O_2/Ar , O_2/H_2 and H_2/He . The particular process conditions may vary depending on the implementation. In alternate embodiments, the pretreatment operation involves exposing the substrate to O_2 , O_2/N_2 , O_2/He , O_2/Ar or other pretreatment chemistries, in a non-plasma environment. The particular process conditions may vary depending on the implementation. In these embodiments, the substrate may be exposed to the pretreatment chemistry in the presence energy from another energy source, including a thermal energy source, a ultra-violet source, a microwave source, etc. In certain embodiments, in addition to or instead of the pretreatment operations described above, a substrate is pretreated with exposure to a catalyst, surfactant, or adhesion-promoting chemical. The pre-treatment operation, if per-

formed, may occur in the deposition chamber or may occur in another chamber prior to transfer of the substrate to the deposition chamber. Once in the deposition chamber, and after the optional pre-treatment operation, process gases are introduced.

Surface treatments to create hydrophilic surfaces that can be wet and nucleate evenly during deposition are described in U.S. patent application Ser. No. 14/519,400, titled "Treatment For Flowable Dielectric Deposition On Substrate Surfaces," incorporated by reference herein. As described therein, the surface treatments may involve exposure to a remote plasma.

EXPERIMENTAL

FIG. 7 shows an image 701 of uniform densified flowable film formed with in-situ UV exposure as described with reference to FIG. 4A. TVTMCTS was the dielectric precursor, with no oxidant employed. Chamber pressure was 25 Torr and substrate temperature was 25°C . A 12 KW UV source at 35% power (4.2 KW) was used to irradiate the chamber interior during deposition. Notably the film is of uniform density (indicated by the uniform shade of the fill in the image) and there is no line bending observed. This indicates that the flowability of the film is maintained without line bending. The results shown in image 701 are substantially better than those deposited using triethoxysilane (TES) as shown in images 703, 705 and 707, regardless of the cure. The flowable oxide in image 703 was exposed to a UV Cure at 250°C .; the flowable oxide in image 705 was exposed to a thermal cure at 545°C . for 10 minutes, and the flowable oxide in image 707 was exposed to a thermal cure at 545°C . for 10 minutes followed by a UV cure. In each case, there is a density gradient (visible by the graded, non-uniform shade in the images) indicated in the circled portion.

FIG. 8 shows Fourier transform infrared spectroscopy (FTIR) spectra for films deposited from TVTMCTS with no oxidant employed and in-situ UV exposure during the deposition. The spectra show that the deposited films retain $\text{Si}-\text{CH}_3$ groups. Cage and network oxide phases are observed. Residual vinyl groups are observed in thicker films.

Apparatus

The methods of the present invention may be performed on a wide-range of modules. The methods may be implemented on any apparatus equipped for deposition of dielectric film, including HDP-CVD reactors, PECVD reactors, sub-atmospheric CVD reactors, any chamber equipped for CVD reactions, and chambers used for PDL (pulsed deposition layers).

Such an apparatus may take many different forms. Generally, the apparatus will include one or more modules, with each module including a chamber or reactor (sometimes including multiple stations) that house one or more wafers and are suitable for wafer processing. Each chamber may house one or more wafers for processing. The one or more chambers maintain the wafer in a defined position or positions (with or without motion within that position, e.g. rotation, vibration, or other agitation). While in process, each wafer is held in place by a pedestal, wafer chuck and/or other wafer holding apparatus. For certain operations in which the wafer is to be heated, the apparatus may include a heater such as a heating plate. Examples of suitable reactors are the Sequel™ reactor, the Vector™, the Speed™ reactor, and the Gamma™ reactor all available from Lam Research of Fremont, Calif.

As discussed above, according to various embodiments, the surface treatment may take place in the same or different module as the flowable dielectric deposition. FIG. 9 shows an example tool configuration **960** including wafer transfer system **995** and loadlocks **990**, flowable deposition module **970**, and UV module **980**. Additional modules, such as a pre-deposition treatment module, and/or one or more additional deposition modules **970** or UV modules **980** may also be included at **975**.

Modules that may be used for pre-treatment include SPEED or SPEED Max, NOVA Reactive Preclean Module (RPM), Altus ExtremeFill (EFx) Module, Vector Extreme Pre-treatment Module (for plasma, ultra-violet or infra-red pre-treatment), and Vector or Vector Extreme modules. A SOLA module may be used for UV exposure. All of the tools are available from Lam Research, Fremont Calif. These modules may be attached to the same backbone as the flowable deposition module. Also, any of these modules may be on different backbones. A controller may be connected to any or all of the components of a tool; its placement and connectivity may vary based on the particular implementation.

In certain embodiments, a controller **922** is employed to control process conditions during deposition and/or pre or post-treatment. Further description of a controller is provided below.

FIG. 10 shows an example of a deposition chamber for flowable dielectric deposition. A deposition chamber **1000** (also referred to as a reactor, or reactor chamber) includes chamber housing **1002**, top plate **1004**, skirt **1006**, showerhead **1008**, pedestal column **1024**, and seal **1026** provide a sealed volume for flowable dielectric deposition. Wafer **1010** is supported by chuck **1012** and insulating ring **1014**. Chuck **1012** includes RF electrode **1016** and resistive heater element **1018**. Chuck **1012** and insulating ring **1014** are supported by pedestal **1020**, which includes platen **1022** and pedestal column **1024**. Pedestal column **1024** passes through seal **1026** to interface with a pedestal drive (not shown). Pedestal column **1024** includes platen coolant line **1028** and pedestal purge line **1030**. Showerhead **1008** includes co-reactant-plenum **1032** and precursor-plenum **1034**, which are fed by co-reactant-gas line **1036** and precursor-gas line **1038**, respectively. Co-reactant-gas line **1036** and precursor-gas line **1038** may be heated prior to reaching showerhead **1008** in zone **1040**. While a dual-flow plenum is described herein, a single-flow plenum may be used to direct gas into the chamber. For example, reactants may be supplied to the showerhead and may mix within a single plenum before introduction into the reactor. **1020'** and **1020** refer to the pedestal, but in a lowered (**1020**) and raised (**1020'**) position.

The chamber is equipped with, or connected to, gas delivery system for delivering reactants to reactor chamber **1000**. A gas delivery system may supply chamber **1010** with one or more co-reactants, such as oxidants, including water, oxygen, ozone, peroxides, alcohols, etc. which may be supplied alone or mixed with an inert carrier gas. The gas delivery system may also supply chamber with one or more dielectric precursors, for example triethoxysilane (TES), which may be supplied alone or mixed with an inert carrier gas. The gas delivery system is also configured to deliver one or more treatment reagents, for plasma treatment as described herein reactor cleaning. For example, for plasma processing, hydrogen, argon, nitrogen, oxygen or other gas may be delivered.

Deposition chamber **1000** serves as a sealed environment within which flowable dielectric deposition may occur. In many embodiments, deposition chamber **1000** features a

radially symmetric interior. Reducing or eliminating departures from a radially symmetric interior helps ensure that flow of the reactants occurs in a radially balanced manner over wafer **1010**. Disturbances to the reactant flows caused by radial asymmetries may cause more or less deposition on some areas of wafer **1010** than on other areas, which may produce unwanted variations in wafer uniformity.

Deposition chamber **1000** includes several main components. Structurally, deposition chamber **1000** may include a chamber housing **1002** and a top plate **1004**. Top plate **1004** is configured to attach to chamber housing **1002** and provide a seal interface between chamber housing **1002** and a gas distribution manifold/showerhead, electrode, or other module equipment. Different top plates **1004** may be used with the same chamber housing **1002** depending on the particular equipment needs of a process.

Chamber housing **1002** and top plate **1004** may be machined from an aluminum, such as 6061-T6, although other materials may also be used, including other grades of aluminum, aluminum oxide, and other, non-aluminum materials. The use of aluminum allows for easy machining and handling and makes available the elevated heat conduction properties of aluminum.

Top plate **1004** may be equipped with a resistive heating blanket to maintain top plate **1004** at a desired temperature. For example, top plate **1004** may be equipped with a resistive heating blanket configured to maintain top plate **1004** at a temperature of between -20° C. and 100° C. Alternative heating sources may be used in addition to or as an alternative to a resistive heating blanket, such as circulating heated liquid through top plate **1004** or supplying top plate **1004** with a resistive heater cartridge.

Chamber housing **1002** may be equipped with resistive heater cartridges configured to maintain chamber housing **1002** at a desired temperature. Other temperature control systems may also be used, such as circulating heated fluids through bores in the chamber walls.

The chamber interior walls may be temperature-controlled during flowable dielectric to a temperature between -20° C. and 100° C. In some implementations, top plate **1004** may not include heating elements and may instead rely on thermal conduction of heat from chamber resistive heater cartridges to maintain a desired temperature. Various embodiments may be configured to temperature-control the chamber interior walls and other surfaces on which deposition is undesired, such as the pedestal, skirt, and showerhead, to a temperature approximately 10° C. to 40° C. higher than the target deposition process temperature. In some implementations, these components may be held at temperatures above this range.

Through actively heating and maintaining deposition chamber **1000** temperature during processing, the interior reactor walls may be kept at an elevated temperature with respect to the temperature at which wafer **1010** is maintained. Elevating the interior reactor wall temperature with respect to the wafer temperature may minimize condensation of the reactants on the interior walls of deposition chamber **1000** during flowable film deposition. If condensation of the reactants occurs on the interior walls of deposition chamber **1000**, the condensate may form a deposition layer on the interior walls, which is undesirable.

In addition to, or alternatively to, heating chamber housing **1002** and/or top plate **1004**, a hydrophobic coating may be applied to some or all of the wetted surfaces of deposition chamber **1000** and other components with wetted surfaces, such as pedestal **1020**, insulating ring **1014**, or platen **1022**, to prevent condensation. Such a hydrophobic coating may

be resistant to process chemistry and processing temperature ranges, e.g., a processing temperature range of -20°C . to 100°C . Some silicone-based and fluorocarbon-based hydrophobic coatings, such as polyethylene, may not be compatible with an oxidizing, e.g., plasma, environment and may not be suitable for use. Nano-technology based coatings with super-hydrophobic properties may be used; such coatings may be ultra-thin and may also possess oleophobic properties in addition to hydrophobic properties, which may allow such a coating to prevent condensation as well as deposition of many reactants, used in flowable film deposition. One example of a suitable super-hydrophobic coating is titanium dioxide (TiO_2).

Various thermal breaks may separate various components of the chamber **1000**. As used herein, a thermal break refers to a physical separation, i.e., gap, between parts which is sufficiently large enough to substantially prevent conductive heat transfer between the parts via any gases trapped within the thermal break yet which is also sufficiently small enough to prevent substantial convective heat transfer between the parts via the gases. Parts or portions of parts which are either in direct contact, or which are separated by a gap but which are still sufficiently close enough together to experience significant conductive heat transfer across the gap via any gases trapped within the gap, may be referred to as being in "thermal contact" with each other. Thermal breaks are described more fully in U.S. patent application Ser. No. 13/329,078, incorporated by reference herein.

Deposition chamber **1000** may also include one or more UV sources, which may be used for in situ UV exposure. This is discussed further below with respect to FIG. **12**.

FIGS. **11A** and **11B** show an example of a UV chamber for UV exposure of flowable dielectric material. Chamber **1101** includes multiple stations **1103**, **1105**, **1107** and **1109**, each of which can accommodate a substrate. Station **1103** includes transfer pins **1119**. FIG. **11B** is a side view of the chamber showing stations **1103** and **1105** and substrates **1113** and **1115** located above pedestals **1123** and **1125**. There are gaps **1104** between the substrates and the pedestals. A substrate may be supported above a pedestal by an attachment, such as a pin, or floated on gas. Parabolic or planar cold mirrors **1153** and **1155** are located above UV flood lamp sets **1133** and **1135**. UV light from lamp sets **1133** and **1135** passes through windows **1143** and **1145**. Substrates **1103** and **1105** are then exposed to the radiation. In alternative embodiments, a substrate may be supported by the pedestals **1123** and **1125**. The lamps may or may not be equipped with cold mirrors. In some embodiments, the substrate temperature may be maintained by use of a conductive gas such as helium or a mixture of helium and argon at a sufficiently high pressure, typically between 50 and 760 Torr.

In operation, a substrate may be sequentially exposed to each UV light source, with multiple substrates exposed to a UV light source in parallel. Alternatively, each substrate may be exposed to only one or subset of the UV light sources.

In some cases, different stations irradiate the wafer at different wavelengths or wavelength ranges. The example above uses a UV flood lamp, which generates radiation in a broad spectrum. Optical components may be used in the radiation source to modulate the part of the broad spectrum that reaches the wafer. For example, reflectors, filters, or combination of both reflectors and filters may be used to subtract a part of the spectrum from the radiation. One such filter is a bandpass filter.

Optical bandpass filters are designed to transmit a specific waveband. They are composed of many thin layers of

dielectric materials, which have differing refractive indices to produce constructive and destructive interference in the transmitted light. In this way optical bandpass filters can be designed to transmit a specific waveband only. The range limitations are usually dependent upon the interference filters lens, and the composition of the thin-film filter material. Incident light is passed through two coated reflecting surfaces. The distance between the reflective coatings determines which wavelengths will destructively interfere and which wavelengths will be allowed to pass through the coated surfaces. In situations where the reflected beams are in phase, the light will pass through the two reflective surfaces. However, if the wavelengths are out of phase, destructive interference will block most of the reflections, allowing almost nothing to transmit through. In this way, interference filters are able to attenuate the intensity of transmitted light at wavelengths that are higher or lower than the desired range.

Another filter that can attenuate the wavelengths of the radiation reaching the wafer is the window **343**, typically made of quartz. By changing the level of metal impurities and water content, the quartz window can be made to block radiations of undesired wavelengths. High-purity Silica Quartz with very little metal impurity is more transparent deeper into the ultraviolet. As an example, quartz with a thickness of 1 cm will have a transmittance of about 50% at a wavelength of 170 nm, which drops to only a few percent at 160 nm. Increasing levels of impurities in the quartz cause transmission of UV at lower wavelengths to be reduced. Electrically fused quartz has a greater presence of metallic impurities, limiting its UV transmittance wavelength to around 200 nm. Synthetic silica, on the other hand, has much greater purity and will transfer down to 170 nm. For infrared radiation, the transmittance through quartz is determined by the water content. More water in the quartz means that infrared radiation is more likely absorbed. The water content in the quartz may be controlled through the manufacturing process. Thus, the spectrum of radiation transmission through the quartz window may be controlled to cutoff or reduce UV transmission at shorter wavelengths and/or to reduce infrared transmission at longer wavelengths.

Another type of filter is UV cut-off filters. These filters do not allow UV transmission below a set value, e.g. 280 nm. These filters work by absorbing wavelengths below the cut-off value. This may be helpful to optimize the desired cure effect.

Radiation wavelength can also be controlled by modifying the properties of the light generator. UV flood lamps can generate a broad spectrum of radiation, from UV to infrared, but other light generators may be used to emit a smaller spectrum or to increase the intensity of a narrower spectrum. Other light generators may be mercury-vapor lamps, doped mercury-vapor lamps, electrode lamps, excimer lamps, excimer lasers, pulsed Xenon lamps, doped Xenon lamps. Lasers such as excimer lasers can emit radiation of a single wavelength. When dopants are added to mercury-vapor and to Xenon lamps, radiation in a narrow wavelength band may be made more intense. Common dopants are iron, nickel, cobalt, tin, zinc, indium, gallium, thallium, antimony, bismuth, or combinations of these. For example, mercury vapor lamps doped with indium emits strongly in the visible spectrum and around 450 nm; iron, at 360 nm; and gallium, at 320 nm. Radiation wavelengths can also be controlled by changing the fill pressure of the lamps. For example, high-pressure mercury vapor lamps can be made to emit wave-

lengths of 250 to 440 nm, particularly 310 to 350 nm more intensely. Low-pressure mercury vapor lamps emit at shorter wavelengths.

In addition to changing light generator properties and the use of filters, reflectors that preferentially deliver one or more segments of the lamps spectral output may be used. A common reflector is a cold mirror that allows infrared radiation to pass but reflects other light. Other reflectors that preferentially reflect light of a spectral band may be used. Therefore a wafer may be exposed to radiation of different wavelengths at different stations. Of course, the radiation wavelengths may be the same in some stations.

In FIG. 11B, pedestals 1123 and 1125 are stationary. Indexer 1111 lifts and moves each substrate from one pedestal to another between each exposure period. Indexer 1111 is an indexer plate 1121 attached to a motion mechanism 1131 that has rotational and axial motion. Upward axial motion is imparted to indexer plate 1121 to pick up substrates from each pedestal. The rotational motion serves to advance the substrates from one station to another. The motion mechanism then imparts downward axial motion to the plate to put the substrates down on the stations.

Pedestals 1123 and 1125 may be electrically heated and maintained at a desired process temperature. As noted above, the substrate temperature is maintained at below the boiling point of the dielectric precursors in some embodiments. As such, pedestals 1123 and 1125 may also be equipped with cooling lines. Each pedestal may have its own heating or cooling system. In an alternate embodiment, a large heater block may be used to support the wafers instead of individual pedestals. A thermally conductive gas, such as helium, is used to cause good thermal coupling between the pedestal and the wafer. In some embodiments, cast pedestals with coaxial heat exchangers may be used. These are described in U.S. Pat. No. 7,327,948, incorporated by reference herein.

FIGS. 11A and 11B show only an example of a suitable apparatus and other apparatuses may be used. For example, in another embodiment that uses flood lamps, the substrate support may be a carousel. Unlike with the stationary pedestal substrate supports, the substrates do not move relative to the carousel. After a substrate is loaded onto the carousel, the carousel rotates, if necessary, to expose the wafer to light from a UV lamp set. The carousel is stationary during the exposure period. After the exposure period, the carousel may be rotated advance each substrate for exposure to the next set of lamps. Heating and cooling elements may be embedded within the rotating carousel. Alternatively the carousel may be in contact with a heat transfer plate or hold the substrates so that they are suspended above a heat transfer plate.

In certain embodiments, the substrates are exposed to UV radiation from focused, rather than, flood lamps. Unlike the flood lamp embodiments wherein the substrates are stationary during exposure (as in FIGS. 11A and 11B), there is relative movement between the wafers and the light sources during exposure to the focused lights as the substrates are scanned.

FIGS. 11A and 11B show an example of multi-station UV exposure tool that may be connected under vacuum to a flowable dielectric deposition tool to permit transfer between a flowable dielectric deposition tool and UV exposure tool under controlled pressure and temperature. An example of a multi-station UV exposure tool is the SOLA station UV exposure tools may be employed.

In certain embodiments, a multi-station tool may be employed in which dielectric deposition occurs at a first station or subset of stations and UV exposure at a second station or subset of stations. A schematic example of such an apparatus is provided in FIG. 12A, which a multi-station chamber 1200 including a deposition station 1202 configured for cold condensation of a dielectric precursor or product thereof and UV station 1204 configured for UV exposure. One or more deposition stations 1202 may be configured as in the example of FIG. 10. One or more UV exposure stations 1204 may be configured as station 1103 in the example of FIG. 11B.

One or more of the apparatuses depicted in FIGS. 9-12A may be used in to perform ex-situ UV exposure as discussed above with respect to FIG. 4A. To perform in-situ UV exposure, a UV exposure tool as shown in FIGS. 11A and 11B may be employed, with deposition gases inlet to the chamber, e.g., through side or top gas inlets. In alternate embodiments, a deposition chamber such as that shown in FIG. 10 may be equipped with one or more UV sources. A schematic example of such a chamber is shown in FIG. 12B. Chamber 1201 includes a showerhead 1203; similar to showerhead 1008 in the example of FIG. 10, showerhead 1203 has one or more plenums 1205 for introducing reactant gases to form a flowable film. Further, UV sources 1207 are embedded within or mounted on the showerhead to provide UV radiation. Each UV source 1207 may be separated from the interior of the chamber 1201 by a window 1209. Examples of windows are described above with reference to FIGS. 11A and 11B. The showerhead 1203 may be designed such that the UV sources 1207 and gas openings are in a regular pattern such that gas delivery and UV irradiation are fairly uniform across a substrate in the chamber. For example, the UV sources and/or the showerhead holes may be in a hexagonal pattern. FIG. 12 also shows a purge gas 1211, e.g., Ar, that may be employed to keep the windows 1209 clean. A pedestal 1213 is configured to support a substrate. In some embodiments, the pedestal 1213, or a support thereon, is rotatable such that a substrate can be rotated if necessary during deposition to promote deposition and UV exposure uniformity.

As indicated above with respect to FIG. 9, in certain embodiments, a controller 922 is employed to control process conditions during deposition and/or pre or post-treatment. Such a controller may be used to control operations in any of the apparatuses depicted in FIGS. 9-12B.

The controller 922 will typically include one or more memory devices and one or more processors. The processor may include a CPU or computer, analog and/or digital input/output connections, stepper motor controller boards, etc. Typically there will be a user interface associated with controller 922. The user interface may include a display screen, graphical software displays of the apparatus and/or process conditions, and user input devices such as pointing devices, keyboards, touch screens, microphones, etc.

In certain embodiments, the controller 922 may also control all of the activities during the process, including gas flow rate, chamber pressure, generator process parameters. The controller 922 executes system control software including sets of instructions for controlling the timing, mixture of gases, chamber pressure, pedestal (and substrate) temperature, UV power, and other parameters of a particular process. The controller 922 may also control concentration of various process gases in the chamber by regulating valves, liquid delivery controllers and MFCs in the delivery system as well as flow restriction valves and the exhaust line. The controller 922 executes system control software including sets of

instructions for controlling the timing, flow rates of gases and liquids, chamber pressure, substrate temperature, UV power, and other parameters of a particular process. Other computer programs stored on memory devices associated with the controller may be employed in some embodiments. In certain embodiments, the controller 922 controls the transfer of a substrate into and out of various components of the apparatuses.

The computer program code for controlling the processes in a process sequence can be written in any conventional computer readable programming language: for example, assembly language, C, C++, Pascal, Fortran or others. Compiled object code or script is executed by the processor to perform the tasks identified in the program. The system software may be designed or configured in many different ways. For example, various chamber component subroutines or control objects may be written to control operation of the chamber components necessary to carry out the described processes. Examples of programs or sections of programs for this purpose include process gas control code and pressure control code.

In some implementations, the controller 922 is part of a system, which may be part of the above-described examples. Such systems can include semiconductor processing equipment, including a processing tool or tools, chamber or chambers, a platform or platforms for processing, and/or specific processing components (a wafer pedestal, a gas flow system, etc.). These systems may be integrated with electronics for controlling their operation before, during, and after processing of a semiconductor wafer or substrate. The electronics may be referred to as the “controller,” which may control various components or subparts of the system or systems. The controller 922, depending on the processing requirements and/or the type of system, may be programmed to control any of the processes disclosed herein, including the delivery of processing gases, temperature settings (e.g., heating and/or cooling), pressure settings, vacuum settings, power settings, radio frequency (RF) generator settings, RF matching circuit settings, frequency settings, flow rate settings, fluid delivery settings, UV power and duty cycle settings, positional and operation settings, wafer transfers into and out of a tool and other transfer tools and/or load locks connected to or interfaced with a specific system.

Broadly speaking, the controller 922 may be defined as electronics having various integrated circuits, logic, memory, and/or software that receive instructions, issue instructions, control operation, enable cleaning operations, enable endpoint measurements, and the like. The integrated circuits may include chips in the form of firmware that store program instructions, digital signal processors (DSPs), chips defined as application specific integrated circuits (ASICs), and/or one or more microprocessors, or microcontrollers that execute program instructions (e.g., software). Program instructions may be instructions communicated to the controller 922 in the form of various individual settings (or program files), defining operational parameters for carrying out a particular process on or for a semiconductor wafer or to a system. The operational parameters may, in some embodiments, be part of a recipe defined by process engineers to accomplish one or more processing steps during the fabrication of one or more layers, materials, metals, oxides, silicon, silicon dioxide, surfaces, circuits, and/or dies of a wafer.

The controller 922, in some implementations, may be a part of or coupled to a computer that is integrated with, coupled to the system, otherwise networked to the system, or a combination thereof. For example, the controller 922 may

be in the “cloud” or all or a part of a fab host computer system, which can allow for remote access of the wafer processing. The computer may enable remote access to the system to monitor current progress of fabrication operations, examine a history of past fabrication operations, examine trends or performance metrics from a plurality of fabrication operations, to change parameters of current processing, to set processing steps to follow a current processing, or to start a new process. In some examples, a remote computer (e.g. a server) can provide process recipes to a system over a network, which may include a local network or the Internet. The remote computer may include a user interface that enables entry or programming of parameters and/or settings, which are then communicated to the system from the remote computer. In some examples, the controller 922 receives instructions in the form of data, which specify parameters for each of the processing steps to be performed during one or more operations. It should be understood that the parameters may be specific to the type of process to be performed and the type of tool that the controller 922 is configured to interface with or control. Thus as described above, the controller 922 may be distributed, such as by comprising one or more discrete controllers that are networked together and working towards a common purpose, such as the processes and controls described herein. An example of a distributed controller for such purposes would be one or more integrated circuits on a chamber in communication with one or more integrated circuits located remotely (such as at the platform level or as part of a remote computer) that combine to control a process on the chamber.

Without limitation, example systems may include a plasma etch chamber or module, a deposition chamber or module, a spin-rinse chamber or module, a metal plating chamber or module, a clean chamber or module, a bevel edge etch chamber or module, a physical vapor deposition (PVD) chamber or module, a chemical vapor deposition (CVD) chamber or module, an atomic layer deposition (ALD) chamber or module, an atomic layer etch (ALE) chamber or module, an ion implantation chamber or module, a track chamber or module, a UV exposure chamber or module, and any other semiconductor processing systems that may be associated or used in the fabrication and/or manufacturing of semiconductor wafers.

As noted above, depending on the process step or steps to be performed by the tool, the controller 922 might communicate with one or more of other tool circuits or modules, other tool components, cluster tools, other tool interfaces, adjacent tools, neighboring tools, tools located throughout a factory, a main computer, another controller, or tools used in material transport that bring containers of wafers to and from tool locations and/or load ports in a semiconductor manufacturing factory.

The controller parameters relate to process conditions such as, for example, timing of each operation, pressure inside the chamber, substrate temperature, and process gas flow rates. These parameters are provided to the user in the form of a recipe, and may be entered utilizing the user interface. Signals for monitoring the process may be provided by analog and/or digital input connections of the controller 922. The signals for controlling the process are output on the analog and digital output connections of the apparatus.

The disclosed methods and apparatuses may also be implemented in systems including lithography and/or patterning hardware for semiconductor fabrication. Further, the disclosed methods may be implemented in a process with lithography and/or patterning processes preceding or fol-

lowing the disclosed methods. The apparatus/process described hereinabove may be used in conjunction with lithographic patterning tools or processes, for example, for the fabrication or manufacture of semiconductor devices, displays, LEDs, photovoltaic panels and the like. Typically, though not necessarily, such tools/processes will be used or includes together in a common fabrication facility. Lithographic patterning of a film typically comprises some or all of the following steps, each step enabled with a number of possible tools: (1) application of photoresist on a workpiece, i.e., substrate, using a spin-on or spray-on tool; (2) curing of photoresist using a hot plate or furnace or UV curing tool; (3) exposing the photoresist to visible or UV or x-ray light with a tool such as a wafer stepper; (4) developing the resist so as to selectively remove resist and thereby pattern it using a tool such as a wet bench; (5) transferring the resist pattern into an underlying film or workpiece by using a dry or plasma-assisted etching tool; and (6) removing the resist using a tool such as an RF or microwave plasma resist stripper.

Although the foregoing invention has been described in some detail for purposes of clarity of understanding, it will be apparent that certain changes and modifications may be practiced within the scope of the appended claims. It should be noted that there are many alternative ways of implementing the processes, systems and apparatus of the present invention. Accordingly, the present embodiments are to be considered as illustrative and not restrictive, and the invention is not to be limited to the details given herein.

The invention claimed is:

1. An apparatus comprising:

- a chamber including chamber walls and a substrate support;
- a showerhead having channels configured to distribute reactants to the chamber;
- an ultraviolet radiation source embedded within or mounted to the showerhead;

a heating system configured to heat an inner surface of the chamber walls;
 a cooling system configured to cool the substrate support;
 and
 a controller comprising machine readable instructions for concurrently performing:
 introducing a vapor phase cyclic silicon precursor to the chamber via the showerhead at a substrate support temperature less than the boiling point of the cyclic silicon precursor to thereby form a flowable film on a substrate supported by the substrate support;
 powering the ultraviolet radiation source to expose the flowable film to UV radiation; and
 maintaining the substrate support at a temperature less than the boiling point of the cyclical silicon precursor during the exposure.

2. The apparatus of claim 1, wherein the chamber is a single-station chamber.

3. The apparatus of claim 1, wherein the chamber is a multi-station chamber.

4. The apparatus of claim 1, further comprising a plurality of ultraviolet radiation sources evenly distributed across the showerhead.

5. The apparatus of claim 1, wherein the substrate support is rotatable.

6. The apparatus of claim 5, further comprising instructions for rotating the substrate support while exposing the chamber to UV radiation.

7. The apparatus of claim 1, wherein the cyclic silicon precursor is a cyclic silazane or cyclic siloxane.

8. The apparatus of claim 1, wherein the cyclic silicon precursor is octamethylcyclotetrasiloxane, tetravinyltetramethylcyclotetrasiloxane, tetramethylcyclotetrasiloxane, pentamethylcyclopentasiloxane, or hexamethylcyclotrisiloxane.

9. The apparatus of claim 1, wherein the instructions further comprise instructions for heating the chamber walls.

* * * * *