



(12) **United States Patent**
Monna et al.

(10) **Patent No.:** **US 10,428,717 B2**
(45) **Date of Patent:** **Oct. 1, 2019**

(54) **METHOD FOR DIAGNOSING DEGRADATION IN CATALYST**

11/002; F01N 11/007; F01N 2550/02; F01N 2560/02; F01N 2560/026; F01N 2560/06; F01N 2900/0416; Y02T 10/47

(71) Applicant: **NGK INSULATORS, LTD.**, Nagoya-shi, Aichi (JP)

See application file for complete search history.

(72) Inventors: **Kosuke Monna**, Aichi (JP); **Taku Okamoto**, Nagoya (JP); **Noriko Hirata**, Nagoya (JP)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,290,530 A * 3/1994 Muramatsu B01D 53/945 423/213.2

5,296,196 A 3/1994 Takeshima

(Continued)

FOREIGN PATENT DOCUMENTS

EP 1154131 B1 2/2005

JP 2876793 B2 3/1999

(Continued)

Primary Examiner — Audrey K Bradley

(74) *Attorney, Agent, or Firm* — Mattingly & Malur, PC

(73) Assignee: **NGK Insulators, Ltd.**, Nagoya (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 36 days.

(21) Appl. No.: **15/640,683**

(22) Filed: **Jul. 3, 2017**

(65) **Prior Publication Data**

US 2018/0010506 A1 Jan. 11, 2018

(30) **Foreign Application Priority Data**

Jul. 5, 2016 (JP) 2016-132955

(51) **Int. Cl.**

F01N 3/10 (2006.01)

F01N 11/00 (2006.01)

(52) **U.S. Cl.**

CPC **F01N 11/002** (2013.01); **F01N 3/10** (2013.01); **F01N 3/103** (2013.01); **F01N 11/00** (2013.01); **F01N 11/007** (2013.01); **F01N 2550/02** (2013.01); **F01N 2560/02** (2013.01); **F01N 2560/026** (2013.01); **F01N 2560/06** (2013.01); **F01N 2900/0416** (2013.01); **Y02T 10/47** (2013.01)


(58) **Field of Classification Search**

CPC . F01N 3/10; F01N 3/103; F01N 11/00; F01N

(57) **ABSTRACT**

Provided is a method for diagnosing whether an oxidation catalyst has degraded, based on an output value from one diagnostic sensor with higher accuracy. When a ratio of nitrogen monoxide that is oxidized by a catalyst and discharged downstream of the catalyst as nitrogen dioxide, with respect to nitrogen monoxide contained in an exhaust gas supplied upstream of the catalyst in an exhaust path is defined as a NO conversion rate, a diagnostic sensor configured to output an electromotive force corresponding to the NO conversion rate as a diagnostic output is provided downstream of the catalyst in the exhaust path, and whether the catalyst has degraded beyond an acceptable limit is diagnosed by comparing the diagnostic output with a threshold value predetermined depending on a temperature of the catalyst.

5 Claims, 6 Drawing Sheets



1000

(56)

References Cited

U.S. PATENT DOCUMENTS


9,551,260 B2 1/2017 Kakimoto
2010/0161242 A1* 6/2010 Wang G01N 27/4074
702/24
2014/0060007 A1* 3/2014 Bedford F01N 3/206
60/274
2014/0060012 A1* 3/2014 Kakimoto F01N 11/00
60/277
2016/0356199 A1 12/2016 Kakimoto

FOREIGN PATENT DOCUMENTS

JP 2001-263048 A 9/2001
JP 2005-240716 A 9/2005
JP 2010-156243 A 7/2010
JP 2012-036860 A 2/2012
JP 2014-62541 A 4/2014

* cited by examiner

FIG. 1



1000 ↗

FIG. 2A




FIG. 2B




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 4A




FIG. 4B




FIG. 5




FIG. 6





FIG. 7



METHOD FOR DIAGNOSING DEGRADATION IN CATALYST

BACKGROUND OF THE INVENTION

Field of the Invention

The present invention relates to a method for diagnosing a degree of degradation in a catalyst that oxidizes a predetermined gas component such as nitrogen monoxide.

Description of the Background Art

Conventionally, for on-board diagnostics (OBD) of an exhaust gas cleaning system for vehicles, that is, the function of diagnosing whether a catalyst acts normally or not in the system, a large number of patent applications have been filed mainly by auto companies. Most of these patent applications relate to techniques using an exhaust gas temperature sensor, an oxygen sensor, a wide-range oxygen concentration sensor (λ sensor), a NO_x sensor, or a PM sensor, and are targeted for three-way catalysts, oxidation catalysts, NO_x storage catalysts, NO_x selective reduction catalysts, and diesel particulate filters (DPFs) (for example, see Japanese Patent Application Laid-Open Nos. 2001-263048, 2005-240716, 2012-036860, 2014-62541, and 2010-156243, and Japanese Patent No. 2876793).

Among these, for the OBDs targeted for diesel oxidation catalysts (DOCs), a variety of techniques using various existing sensors such as a temperature sensor, an O_2 sensor, a λ sensor, a NO_x sensor, and a pH sensor individually or in combination are known at present (for example, see Japanese Patent Application Laid-Open Nos. 2001-263048, 2005-240716, 2012-036860, 2014-62541, and 2010-156243). Specifically, diagnosing techniques using, as indicators, the heat of reaction of a hydrocarbon and oxygen on a catalyst, change in temperature of an oxidation catalyst, an oxygen storage capacity (OSC), a NO/NO_2 ratio, and an NO_2 ratio in NO_x , for example are known.

The techniques disclosed by Japanese Patent Application Laid-Open Nos. 2001-263048, 2005-240716, 2012-036860, 2014-62541, and 2010-156243 all relate to indirect evaluation of an oxidation ability of a diesel oxidation catalyst. Here, there are problems with poor diagnosis accuracy. Furthermore, using a plurality of sensors complicates the system, thus causing a problem with increased cost.

For example, disclosed in Japanese Patent Application Laid-Open No. 2001-263048 is a technique involving the use of a relationship that when the ability of converting (oxidizing or combusting) an unburned hydrocarbon in an oxidation catalyst decreases, exothermic energy will also decrease. In outline, a temperature difference ΔT is measured, which occurs at the time of fuel injection in exhaust gas temperature sensors disposed forward and backward (upstream and downstream) of an oxidation catalyst in an exhaust path, and the degree of degradation in the ability of converting (oxidizing or combusting) an unburned hydrocarbon in the oxidation catalyst is diagnosed indirectly from a measurement value.

In this method, however, a cause of error may be excessively large due to changes in the temperature and the flow rate of an exhaust gas when the gas sensors are practically used, and fuel consumption may inevitably degrade because a large amount of fuel injection is required for accelerating heat generation.

Disclosed in Japanese Patent Application Laid-Open No. 2005-240716 is a technique involving the use of a fact that when the ability of converting an unburned hydrocarbon in an oxidation catalyst decreases, the amount of oxygen consumed during the combustion of oxygen changes. In

outline, on the basis of a difference $\Delta\lambda$ between output values λ_F and λ_R of two wide-range oxygen concentration sensors (λ sensors) disposed forward and backward of an oxidation catalyst in an exhaust path, or a difference between output values (electromotive force values) of two oxygen sensors, an amount of oxygen consumed in an oxidation catalyst is measured, and the degree of degradation in the ability of converting an unburned hydrocarbon on the oxidation catalyst is diagnosed indirectly from a change in the measured value.

However, the concentration of oxygen in a diesel exhaust that is an excessive O_2 atmosphere is approximately 10% (=100000 ppm), whereas the amount (concentration) of hydrocarbon that is converted (oxidized or combusted) by an oxidation catalyst is normally on the order of several hundreds of ppm, and the amount (concentration) of oxygen consumed when such a trace amount of hydrocarbon is burned is no more than several hundreds of ppm. This means that the diagnosis of the degradation in an oxidation catalyst with an air-fuel ratio sensor or oxygen sensor requires an accurate calculation of $\Delta\lambda$ or a difference in electromotive force corresponding to a ppm-order change in the amount of oxygen consumed, but the air-fuel sensors and oxygen sensors originally cannot achieve such accuracy in measurements.

Even when an unburned hydrocarbon with a concentration of several thousands to several tens of thousands of ppm is produced by an intentional fuel injection, in principle, the sensors disposed forward and backward of an oxidation catalyst do not have any difference in output.

Disclosed in Japanese Patent Application Laid-Open No. 2012-036860 is a technique for determining a degree of degradation in an oxidation catalyst that oxidizes NO to NO_2 , using an NO_2 value obtained based on a ratio of NO_x values measured upstream and downstream of the oxidation catalyst in an exhaust path. More specifically, the techniques disclosed by Japanese Patent Application Laid-Open No. 2012-036860 are broadly distinguished into two, in one of which the upstream NO_x value is obtained based on a predetermined map and the other of which the upstream NO_x value is obtained by a NO_x sensor. In both of the techniques, the downstream NO_x value is measured by the NO_x sensor.

However, in both of the techniques, there is a problem with low diagnosis accuracy, since the degree of degradation in the oxidation catalyst is determined based on a ratio of the two NO_x values. Particularly in the former technique, since an estimated value is used as a NO_x value for the exhaust immediately after a discharge of an engine or factors except for an engine speed and an engine load are not taken into account in setting of such an estimated value, it is conceivable that the accuracy of estimation will degrade remarkably depending on usage condition.

Disclosed in Japanese Patent Application Laid-Open No. 2014-62541 is a technique in which a NO_2 ratio (NO_2 concentration/ NO concentration) is obtained using a multi-gas sensor including both a NO_x detection part and a NO_2 detection part and a degree of degradation in an oxidation catalyst is determined based on the NO_2 ratio.

However, there is a problem that such a multi-gas sensor has a complicated structure due to including a plurality of sensing electrodes and therefore it is expensive.

Disclosed in Japanese Patent Application Laid-Open No. 2010-156243 is a technique for determining a NO_2 ratio in NO_x , based on a NO_2 concentration in the exhaust that is measured by a NO_x sensor and on pH of a condensate liquid obtained by condensing the exhaust, and for diagnosing degradation in a catalyst based on the NO_2 ratio. However,

since this technique requires a condensation apparatus for obtaining the condensate liquid and a pH sensor besides the NO_x sensor, the overall system becomes complicated, which causes a problem with high cost.

SUMMARY

The present invention relates to a method for diagnosing a degree of degradation in a catalyst that oxidizes a predetermined gas component such as nitrogen monoxide.

According to the present invention, the method for diagnosing a degree of degradation in a catalyst that oxidizes a gas component contained in an exhaust gas discharged from an internal combustion engine, the catalyst being provided in an exhaust path of the internal combustion engine, the method includes: a) providing a diagnostic sensor downstream of the catalyst in the exhaust path, the diagnostic sensor being configured to output an electromotive force corresponding to a NO conversion rate as a diagnostic output; and b) diagnosing whether the catalyst has degraded beyond an acceptable limit by comparing the diagnostic output with a threshold value predetermined depending on a temperature of the catalyst, wherein the NO conversion rate is defined as a ratio of nitrogen monoxide that is oxidized by the catalyst and discharged downstream of the catalyst as nitrogen dioxide, with respect to nitrogen monoxide contained in the exhaust gas supplied upstream of the catalyst in the exhaust path.

According to the present invention, whether the oxidation catalyst has degraded can be diagnosed in real time based on a diagnostic output from one diagnostic sensor.

Preferably, the diagnostic output from the diagnostic sensor increases as a concentration of the nitrogen monoxide in the exhaust gas increases and as a concentration of the nitrogen dioxide decreases.

Accordingly, whether the oxidation catalyst has degraded can be diagnosed based on a diagnostic output from one diagnostic sensor in real time and with superior accuracy.

Thus, the object of the present invention is to provide a method for diagnosing whether the oxidation catalyst has degraded, based on an output value from one diagnostic sensor with higher accuracy.

These and other objects, features, aspects and advantages of the present invention will become more apparent from the following detailed description of the present invention when taken in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 schematically illustrates a configuration of a diesel engine system 1000 including an oxidation catalyst diagnosis system DS1;

FIGS. 2A and 2B are schematic sectional views of an example configuration of a diagnostic sensor 100;

FIGS. 3A to 3C exemplify the situation of progress of degradation in an oxidation catalyst 600;

FIGS. 4A and 4B exemplify the dependence of a diagnostic sensor output from the diagnostic sensor 100 on NO and NO₂ concentrations;

FIG. 5 exemplifies a relationship between a NO conversion rate and the diagnostic sensor output;

FIG. 6 exemplifies a threshold map indicating a relationship between a temperature of the oxidation catalyst 600 and the diagnostic sensor output; and

FIG. 7 illustrates an example procedure of a degradation diagnosis.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Overview of System

FIG. 1 schematically illustrates a configuration of a diesel engine system (hereinafter also merely referred to as an engine system) 1000 including an oxidation catalyst diagnosis system DS1 according to an embodiment of the present invention.

The oxidation catalyst diagnosis system DS1 mainly includes a zirconia sensor for diagnosing degradation in a catalyst (hereinafter also merely referred to as a diagnostic sensor) 100, and an electronic controller 200 that is a controller for controlling an operation of the entire engine system 1000.

The engine system 1000 mainly includes, in addition to the oxidation catalyst diagnosis system DS1, an engine main body 300 that is a diesel engine of one type of internal combustion engine, a plurality of fuel injection valves 301 that inject a fuel into the engine main body 300, a fuel injection instruction part 400 for instructing the fuel injection valves 301 to inject a fuel, an exhaust pipe 500 forming an exhaust path that externally discharges an exhaust gas (engine exhaust) G generated in the engine main body 300, and an oxidation catalyst 600 such as platinum or palladium that is provided at some midpoint of the exhaust pipe 500 and oxidizes a predetermined gas component (for example, nitrogen monoxide (NO)) in the exhaust gas G. In the present embodiment, in a relative meaning, the position closer to the engine main body 300 that is one side of the exhaust pipe 500 is referred to an upstream side, and the position closer to an exhaust port 510 that is opposite the engine main body 300 is referred to as a downstream side. Furthermore, the engine system 1000 may include one or a plurality of purification devices 700 at some midpoint of the exhaust pipe 500, in addition to the oxidation catalyst 600.

The engine system 1000 is typically mounted in a vehicle, and in such a case, the fuel injection instruction part 400 is an accelerator pedal.

In the engine system 1000, the electronic controller 200 issues a fuel injection instruction signal sg1 to the fuel injection valves 301. The fuel injection instruction signal sg1 is usually issued in response to a fuel injection request signal sg2 for demanding an injection of a predetermined amount of fuel, which is provided from the fuel injection instruction part 400 to the electronic controller 200 during the operation (action) of the engine system 1000 (e.g., an accelerator pedal is depressed so that an optimum fuel injection reflecting a large number of parameters, such as the position of an accelerator, an amount of oxygen intake, an engine speed, and torque is demanded). In addition to this, the fuel injection instruction signal sg1 may be issued for the oxidation catalyst diagnosis system DS1 to operate.

A monitor signal sg3 for monitoring various situations inside the engine main body 300 is provided from the engine main body 300 to the electronic controller 200.

In the engine system 1000, the exhaust gas G discharged from the engine main body 300 that is a diesel engine is a gas in an excessive oxygen (O₂) atmosphere having an oxygen concentration of approximately 10%, in addition to including, for example, carbon dioxide (CO₂), soot (graphite), NO_x (nitrogen oxide, mainly NO), and a hydrocarbon (HC), and contains NO the most except for CO₂ and O₂. Furthermore, a ratio of HC to NO_x ranges approximately from HC:NO_x=1:1.8 (approximately under 200 C.^o) to 1:10 (approximately under 400 C.^o), depending on a temperature. NO_x may be included in a larger ratio than these cases,

depending on an operating state of the engine system **1000**. In the specification, carbon monoxide (CO) is treated as a kind of HC, in addition to typical hydrocarbon gases (gases classified as hydrocarbons in terms of chemical formula) such as C₂H₄, C₃H₆, and n-C₈.

The oxidation catalyst diagnosis system DS1 is targeted for a diagnosis of a degree of degradation in the oxidation catalyst **600** (more specifically, a degree of degradation in the oxidation ability of the oxidation catalyst **600**). The oxidation catalyst **600** is provided to oxidize a gas component to be processed (for example, NO and HC) that is a predetermined gas component in the exhaust gas G that has flowed from the upstream side to prevent the gas component to be processed from flowing out through the exhaust port **510** at the end of the exhaust pipe **500**, but its oxidation ability degrades with time. The occurrence of such degradation is not preferable because it increases an amount of the gas component to be processed that is not captured by the oxidation catalyst **600** but flows downstream.

The oxidation catalyst diagnosis system DS1 according to the present embodiment diagnoses a degree of degradation in the oxidation ability of the oxidation catalyst **600** based on a degree of oxidation of NO by the oxidation catalyst **600**, with attention given to NO that is one of the gas components to be processed and has a higher abundance ratio in the exhaust gas G.

In the present embodiment, a ratio of NO that is oxidized by the oxidation catalyst **600** and discharged downstream as nitrogen dioxide (NO₂) with respect to NO contained in the exhaust gas G and supplied upstream to the oxidation catalyst **600** is referred to as a NO conversion rate. The NO conversion rate can be obtained as a ratio of a difference between a NO concentration (N1) in the exhaust gas G that exists upstream of the oxidation catalyst **600** and a NO concentration (N2) in the exhaust gas G that exists downstream of the oxidation catalyst **600**, with respect to the NO concentration (N1). Thus, the following equation holds:

$$\text{NO Conversion Rate (\%)} = 100 \times (N1 - N2) / N1.$$

Degradation in the oxidation ability of the oxidation catalyst **600** also means decrease in the NO conversion rate.

In the diagnosis of degradation, a diagnostic sensor **100** that yields an output corresponding to an abundance ratio of NO to NO₂ obtained by oxidizing NO is used. The diagnostic sensor **100** is disposed downstream of the oxidation catalyst **600** in the exhaust pipe **500**, with one of its ends inserted into the exhaust pipe **500**.

The output from the diagnostic sensor **100** is given to the electronic controller **200** as a diagnosis detection signal sg11. In the oxidation catalyst diagnosis system DS1, the electronic controller **200** is configured to diagnose whether the oxidation catalyst **600** has degraded or not on the basis of the diagnosis detection signal sg11 issued from the diagnostic sensor **100**. An example configuration of the diagnostic sensor **100** and details of the diagnosis of degradation will be described later.

Alternatively, the oxidation catalyst diagnosis system DS1 may include a temperature sensor **110** that is disposed upstream of the oxidation catalyst **600** and detects a temperature (exhaust temperature) of the exhaust gas G in the relevant portion. The temperature sensor **110** may be a conventionally known sensor as one used to measure an exhaust temperature in a common engine system. The temperature sensor **110** is also disposed with one of its ends inserted into the exhaust pipe **500**, similarly as the diagnostic sensor **100**. The temperature sensor **110** intended for a use

other than the diagnosis of degradation in the oxidation catalyst **600** may be used for this diagnosis of degradation.

When the oxidation catalyst diagnosis system DS1 includes the temperature sensor **110**, the electronic controller **200** obtains an exhaust temperature detection signal sg12 issued from the temperature sensor **110** to identify an exhaust temperature. Such an exhaust temperature is regarded as a temperature of the oxidation catalyst **600** at that point of time.

The electronic controller **200** includes storage (not shown) such as memory or HDD, and the storage stores a program for controlling the operations of the engine system **1000** and the oxidation catalyst diagnosis system DS1, and also stores threshold information used to diagnose a degree of degradation in the oxidation catalyst **600** which will be described below.

Example Configuration of Diagnostic Sensor

FIGS. 2A and 2B are schematic sectional views of an example configuration of the diagnostic sensor **100** used in the present embodiment. FIG. 2A is a vertical sectional view of a sensor element **101**, which is a main component of the diagnostic sensor **100**, taken along the longitudinal direction of the sensor element **101**. FIG. 2B is a view including a cross-section of the sensor element **101** perpendicular to the longitudinal direction of the sensor element **101** at a position A-A' of FIG. 2A.

The diagnostic sensor **100** used in the present embodiment is a generally called mixed-potential type gas sensor. Generally speaking, the diagnostic sensor **100** determines a concentration of a gas component in a measurement gas, using a potential difference that occurs between a sensing electrode **10**, which is provided on the surface of the sensor element **101** mainly made of zirconia (ZrO₂) ceramics that is an oxygen-ion conductive solid electrolyte, and a reference electrode **20**, which is provided inside the sensor element **101**, due to a difference in the concentration of the gas component between portions near the electrodes on the basis of the principle of mixed potential.

The sensor element **101** mainly includes a reference gas introduction layer **30**, a reference gas introduction space **40**, and a surface protective layer **50** in addition to the sensing electrode **10** and the reference electrode **20** described above.

In the present embodiment, the sensor element **101** has a structure in which six layers, namely, a first solid electrolyte layer **1**, a second solid electrolyte layer **2**, a third solid electrolyte layer **3**, a fourth solid electrolyte layer **4**, a fifth solid electrolyte layer **5**, and a sixth solid electrolyte layer **6**, each formed of an oxygen-ion conductive solid electrolyte, are laminated in the stated order from the bottom side of FIGS. 2A and 2B. The sensor element **101** additionally includes other components mainly between these layers or on an outer surface of the element. The solid electrolytes constituting these six layers are fully airtight. Such a sensor element **101** is manufactured by, for example, laminating ceramic green sheets corresponding to the individual layers, which have been subjected to a predetermined process and printing of a circuit pattern, and further, by integrating the laminated layers through firing.

In the following description, for the sake of convenience, the surface located as the upper surface of the sixth solid electrolyte layer **6** in FIGS. 2A and 2B is referred to as a front surface Sa of the sensor element **101**, and the surface located as the lower surface of the first solid electrolyte layer **1** in FIGS. 2A and 2B is referred to as a rear surface Sb of the sensor element **101**. In the determination of the concentration of an unburned hydrocarbon gas in a measurement gas with the diagnostic sensor **100**, a predetermined range

starting from a distal end E1 being one end of the sensor element 101, which includes at least the sensing electrode 10, is disposed in a measurement gas atmosphere, and the other portion including a base end E2 opposite the distal end E1 is disposed so as not to be in contact with the measurement gas atmosphere.

The sensing electrode 10 is an electrode for sensing a measurement gas. The sensing electrode 10 is formed as a porous cermet electrode made of Pt containing a predetermined ratio of Au, namely, a Pt—Au alloy and zirconia. The sensing electrode 10 is provided in a substantially rectangular shape in plan view at a position closer to the distal end E1 that is one end in the longitudinal direction of the sensor element 101 on the front surface Sa.

The catalytic activity of the sensing electrode 10 against NO and NO₂ is disabled by preferably determining the composition of the Pt—Au alloy being its constituent material. That is, the decomposition reaction of NO and NO₂ is prevented or reduced in the sensing electrode 10. In the diagnostic sensor 100, accordingly, the potential of the sensing electrode 10 varies in accordance with the NO and NO₂ concentrations in the measurement gas.

The catalytic activity of the sensing electrode 10 is disabled by containing gold (Au) as a conductive component (noble metal component) of the sensing electrode 10, in addition to platinum (Pt) that is a main component. Specifically, the sensing electrode 10 is formed such that the ratio of Au (Au abundance ratio) in the sensing electrode 10 is 0.3 or more. In this specification, the Au abundance ratio means an area ratio of the portion covered with Au to the portion at which Pt is exposed in the surface of the noble metal particle of the sensing electrode 10. The Au abundance ratio is 1 when the area of the portion at which Pt is exposed is equal to the area of the portion covered with Au. In this specification, an Au abundance ratio is calculated from a peak intensity of a peak detected for Au and Pt, obtained using X-ray photoelectron spectroscopy (XPS), by a relative sensitivity coefficient method.

When the Au abundance ratio is 0.3 or more, in the sensing electrode 10, Au is enriched in the surface of the noble metal particle of the sensing electrode 10. More specifically, an Au-rich Pt—Au alloy is formed near the surface of a Pt-rich Pt—Au alloy particle. When such a state is achieved, the catalytic activity in the sensing electrode 10 is disabled preferably, and the dependence (sensitivity) of the potential of the sensing electrode 10 on the NO and NO₂ concentrations is enhanced.

It suffices that the volume ratio between a noble metal component and zirconia of the sensing electrode 10 is approximately from 5:5 to 8:2.

For the diagnostic sensor 100 to preferably exhibit its function, the porosity of the sensing electrode 10 is preferably 10% or more and 30% or less, and the thickness of the sensing electrode 10 is preferably 5 μm or more. In particular, the porosity is more preferably 15% or more and 25% or less, and the thickness is more preferably 25 μm or more and 45 μm or less.

The plane size of the sensing electrode 10 may be determined appropriately, and it suffices that, for example, the length in the longitudinal direction of the sensor element 101 is approximately 0.2 mm to 10 mm and the length perpendicular to the longitudinal direction is approximately 1 mm to 5 mm.

The reference electrode 20 is an electrode having a substantially rectangular shape in plan view, which is provided inside the sensor element 101 and serves as a reference in the determination of the concentration of the measure-

ment gas. The reference electrode 20 is provided as a porous cermet electrode of Pt and zirconia.

It suffices that the reference electrode 20 has a porosity of 10% or more and 30% or less and a thickness of 5 μm or more and 15 μm or less. The plane size of the reference electrode 20 may be smaller than that of the sensing electrode 10 as illustrated in FIGS. 2A and 2B, or may be equal to that of the sensing electrode 10.

The reference gas introduction layer 30 is a layer made of porous alumina, which is provided inside the sensor element 101 to cover the reference electrode 20. The reference gas introduction space 40 is an internal space provided on the base end E2 of the sensor element 101. Air (oxygen) serving as a reference gas is externally introduced into the reference gas introduction space 40.

The reference gas introduction space 40 and the reference gas introduction layer 30 are in communication with each other, and accordingly, in the use of the diagnostic sensor 100, the surrounding of the reference electrode 20 is always filled with air (oxygen) through the reference gas introduction space 40 and the reference gas introduction layer 30. During the use of the diagnostic sensor 100, thus, the reference electrode 20 always has a constant potential.

The reference gas introduction space 40 and the reference gas introduction layer 30 are provided so as not to come into contact with a measurement gas owing to their surrounding solid electrolytes. This prevents the reference electrode 20 from coming into contact with the measurement gas even if the sensing electrode 10 is exposed to the measurement gas.

In the case illustrated in FIG. 2A, the reference gas introduction space 40 is provided in such a manner that part of the fifth solid electrolyte layer 5 is in communication with the exterior on the base end E2 of the sensor element 101. The reference gas introduction layer 30 is provided so as to extend in the longitudinal direction of the sensor element 101 between the fifth solid electrolyte layer 5 and the sixth solid electrolyte layer 6. The reference electrode 20 is provided under the center of gravity of the sensing electrode 10 with reference to FIGS. 2A and 2B.

The surface protective layer 50 is a porous layer made of alumina, which is provided so as to cover at least the sensing electrode 10 on the front surface Sa of the sensor element 101. The surface protective layer 50 is provided as an electrode protective layer that prevents or reduces the degradation in the sensing electrode 10 due to continuous exposure to a measurement gas during the use of the diagnostic sensor 100. In the case illustrated in FIG. 2A, the surface protective layer 50 is provided so as to cover not only the sensing electrode 10 but also substantially the entire front surface Sa of the sensor element 101 except for a predetermined range starting from the distal end E1.

As illustrated in FIG. 2B, the diagnostic sensor 100 is equipped with a potentiometer 60 capable of measuring a potential difference between the sensing electrode 10 and the reference electrode 20. Although FIG. 2B simply illustrates wiring between the potentiometer 60 and each of the sensing electrode 10 and the reference electrode 20, in the actual sensor element 101, connection terminals (not shown) are provided correspondingly to the respective electrodes on the front surface Sa or the rear surface Sb on the base end E2 side, and wiring patterns (not shown), which connect the respective electrodes and their corresponding connection terminals, are formed on the front surface Sa and inside the element. The sensing electrode 10 and the reference electrode 20 are electrically connected with the potentiometer 60 through the wiring patterns and the connection terminals.

The sensor element **101** further includes a heater part **70**, which performs temperature control of heating the sensor element **101** and maintaining the temperature of the sensor element **101**, to enhance the oxygen ion conductivity of the solid electrolytes. The heater part **70** includes a heater electrode **71**, a heater **72**, a through hole **73**, a heater insulating layer **74**, and a pressure diffusion hole **75**.

The heater electrode **71** is an electrode formed while being in contact with the rear surface Sb of the sensor element **101** (in FIGS. **2A** and **2B**, the lower surface of the first solid electrolyte layer **1**). The heater part **70** can be powered externally through the heater electrode **71** connected with an external power supply (not shown).

The heater **72** is an electric resistor provided inside the sensor element **101**. The heater **72** is connected with the heater electrode **71** through the through hole **73** and generates heat by being powered externally via the heater electrode **71** to heat the solid electrolytes forming the sensor element **101** and maintain their temperatures.

In the case illustrated in FIGS. **2A** and **2B**, the heater **72** is buried while being vertically sandwiched between the second solid electrolyte layer **2** and the third solid electrolyte layer **3** so as to extend from the base end E2 to the position below the sensing electrode **10** near the distal end E1. This enables the adjustment of the entire sensor element **101** at a temperature at which the solid electrolytes are activated.

The heater insulating layer **74** is an insulating layer formed of an insulator such as alumina on the upper and lower surfaces of the heater **72**. The heater insulating layer **74** is formed for electrical insulation between the second solid electrolyte layer **2** and the heater **72** and for electrical insulation between the third solid electrolyte layer **3** and the heater **72**.

The pressure diffusion hole **75** is a part provided to penetrate the third solid electrolyte layer **3** and the fourth solid electrolyte layer **4** and to be in communication with the reference gas introduction space **40**, and is formed to mitigate an internal pressure rise associated with a temperature rise in the heater insulating layer **74**.

In the diagnosis of a degree of degradation in the oxidation catalyst **600** using the diagnostic sensor **100** having the above configuration, as described above, air (oxygen) is supplied to the reference gas introduction space **40**, with the sensor element **101** in only a predetermined range, which starts from the distal end E1 and includes at least the sensing electrode **10**, being disposed in the exhaust pipe **500** of the engine system **1000**, and with the sensor element **101** on the base end E2 being apart from the space. The heater **72** heats the sensor element **101** to an appropriate temperature from 300° C. to 800° C., preferably from 400° C. to 700° C., and more preferably from 400° C. to 600° C.

In such a state, a potential difference (electromotive force (EMF)) occurs between the sensing electrode **10** exposed to the measurement gas (exhaust gas G) and the reference electrode **20** disposed in the air atmosphere. According to the present embodiment, a difference in potential measured by the potentiometer **60** between the sensing electrode **10** and the reference electrode **20** is output as the diagnosis detection signal sg11. The potential difference may be referred to as a diagnostic sensor output.

As described above, while the potential of the reference electrode **20** disposed in the air atmosphere (with the concentration of oxygen maintained constant) is maintained constant, the potential of the sensing electrode **10** has a dependence on respective concentrations of NO and NO₂ in the measurement gas (exhaust gas G). Accordingly, the diagnostic sensor output varies according to the NO and

NO₂ concentrations. When a measurement gas contains both NO and NO₂, the diagnostic sensor output yields a value corresponding to an abundance ratio of NO to NO₂. The oxidation catalyst diagnosis system DS1 according to the present embodiment diagnoses the degradation in the oxidation catalyst **600** using the dependence of the diagnostic sensor output on the abundance ratio (component ratios) of NO to NO₂ in the exhaust gas G, which will be described later.

Degradation in Oxidation Catalyst and Output Behavior of Diagnostic Sensor

FIGS. **3A** to **3C** exemplify the situation of progress of degradation in the oxidation catalyst **600**. Specifically, FIGS. **3A** to **3C** illustrate respective component ratios of the exhaust gas G upstream and downstream of each of three oxidation catalysts **600** which differ in used times. FIGS. **3A**, **3B**, and **3C** illustrate evaluation results when the temperatures of the exhaust gas G are 400° C., 300° C., and 200° C., respectively. The operating conditions of the engine main body **300** are conditions on the temperatures that are listed in TABLE 1 to be described later.

More specifically, FIGS. **3A** to **3C** illustrate results of components of the exhaust gas G measured upstream and downstream of those three oxidation catalysts **600**, wherein a “NEW ITEM” indicates the one that has been first used, a “USED ITEM 1” indicates the one that has been continuously used, and a “USED ITEM 2” indicates the one that has been used longer than the “USED ITEM 1”. Here, those three oxidation catalysts **600** are of the same type (structure). Furthermore, the gas components illustrated in those figures are limited to NO, NO₂, and HC that are mainly relevant to the oxidation ability of the oxidation catalysts **600**. The reason why the degree of degradation in the oxidation catalyst **600** can be evaluated from a component ratio of the exhaust gas G at the downstream side but the oxidation catalyst **600** was also measured upstream is because the component ratios of the exhaust gas G before introduction to the oxidation catalysts **600** were checked.

First, as for the cases that the temperatures of the exhaust gas G are 400° C. and 300° C. shown in FIGS. **3A** and **3B**, the concentrations of the gas components measured upstream are almost the same among the “NEW ITEM”, the “USED ITEM 1”, and the “USED ITEM 2”. This means that the exhaust gas G reaches the oxidation catalyst **600** with an approximately equal component ratio since the engine main body **300** is operated under the same conditions. FIG. **3A** exhibits approximately HC:NO_x=1:10 when the temperature of the exhaust gas G is 400° C., whereas FIG. **3B** exhibits approximately HC:NO_x=1:5 when the temperature of the exhaust gas G is 300° C.

In contrast, at the downstream side of each catalyst, though the concentration of NO is smaller than those at the upstream side while NO₂, which is rarely present at the upstream side, is abundant, the concentration of NO increases and the concentration of NO₂ decreases in ascending order of the “NEW ITEM”, the “USED ITEM 1”, and the “USED ITEM 2”. This means increasing of a ratio of NO that is discharged downstream as it is to the total amount of NO introduced upstream to the oxidation catalyst **600**, that is, decreasing of the NO conversion rate. Such a tendency demonstrates that the degradation in the catalytic ability (oxidation ability) of the oxidation catalyst **600** proceeds as the oxidation catalyst **600** is used.

As seen from FIGS. **3A** and **3B**, even when the oxidation catalyst **600** is the “NEW ITEM”, it cannot oxidize all the NO supplied upstream thereof. The NO conversion rate

when the oxidation catalyst **600** is the “NEW ITEM” is approximately 55% at the maximum.

Both FIGS. **3A** and **3B** illustrate that the concentrations of HC at the downstream side are smaller than those at the upstream side and thus the ratios to the entire NO_x at the downstream side are much smaller than those at the upstream side. For example, the “USED ITEM 1” at the downstream side in FIG. **3A** exhibits approximately $\text{HC}:\text{NO}_x=1:42$. Furthermore, the concentrations of HC at the downstream side do not exhibit prominent change over time unlike NO. This means that the oxidation ability is sufficiently reserved for HC even when the oxidation ability for NO degrades and accordingly, in a state where degradation in the oxidation catalysts **600** against NO is troublesome, the component ratios of the exhaust gas G at the downstream side of the oxidation catalysts **600** are values almost reflecting the oxidation ability (in other words, the NO conversion rate) of NO in the oxidation catalysts **600**.

In the case that the temperature of the exhaust gas G is 200°C . shown in FIG. **3C**, although only the “NEW ITEM” exhibits a larger concentration of NO_2 at the downstream side than that at the upstream side, there is almost no difference in concentrations of NO to NO_2 between the downstream and upstream sides, as for the “USED ITEM 1” and the “USED ITEM 2”. The reason is considered that since the temperature of the oxidation catalyst **600** is insufficient for activation, the oxidation ability against NO degrades at a relatively earlier use stage. On the other hand, due to a higher concentration of HC at the upstream side, the concentrations of HC at the downstream side shown in FIG. **3C** are higher than those in FIGS. **3A** and **3B**, and increase in ascending order of the “NEW ITEM”, the “USED ITEM 1”, and the “USED ITEM 2”. Nonetheless, the ratio of HC at the downstream side to the total NO_x tends to be sufficiently smaller, similarly as the cases where the temperatures of the exhaust gas G are 400°C . and 300°C . Thus, this means that the component ratios of the exhaust gas G at the downstream side of the oxidation catalysts **600** are values almost reflecting the oxidation ability (in other words, the NO conversion rate) of NO even when the temperature of the exhaust gas G is 200°C ., though the influence of HC is larger.

In view of such situations of progress of the degradation in the oxidation catalyst **600**, the oxidation catalyst diagnosis system DS1 according to the present embodiment diagnoses a degree of the degradation in the oxidation catalyst **600**, based on a value of the diagnostic sensor output which is obtained from the diagnostic sensor **100** and depends on concentrations of NO and NO_2 , with disposition of the diagnostic sensor **100** downstream of the oxidation catalyst **600**.

FIGS. **4A** and **4B** exemplify the dependence of the diagnostic sensor output (EMF) from the diagnostic sensor **100** on the NO and NO_2 concentrations. The total 18 kinds of evaluation gases with the following compositions (volume ratios) were used.

NO or NO_2 : 0 ppm, 100 ppm, 300 ppm, 500 ppm, 700 ppm, or 1000 ppm;
 C_2H_4 : 0 ppm, 100 ppm, or 500 ppm;
 O_2 : 10%; and
 N_2 : the residue.

C_2H_4 is contained as HC. Furthermore, the temperature (catalyst temperature) of the gases was set to 300°C . In the sensor element **101**, the sensing electrode **10** whose Au abundance ratio is 0.3 or more was used.

The diagnostic sensor output from the diagnostic sensor **100** tends to increase as the NO concentration increases in

a range where HC is sufficiently less as illustrated in FIG. **4A**, and tends to increase as the NO_2 concentration decreases as illustrated in FIG. **4B**.

In other words, as seen from the dependence on the concentrations illustrated in FIGS. **4A** and **4B**, both of increase in NO and decrease in NO_2 contribute to increase in the diagnostic sensor output from the diagnostic sensor **100**, though the ratio of NO in the exhaust gas G at the downstream side increases and the ratio of NO_2 decreases as the degradation in the oxidation catalyst **600** progresses as illustrated in FIGS. **3A** to **3C**. This means that the diagnostic sensor output from the diagnostic sensor **100** has superior sensitivity to the progress of degradation in the oxidation ability of the oxidation catalyst **600**, particularly, to the progress of degradation in the oxidation ability against NO (in other words, decrease in the NO conversion rate).

In addition, although increase in the concentration of HC greatly influences the value of the diagnostic sensor output according to FIGS. **4A** and **4B**, the concentration of HC at the downstream side of the oxidation catalyst **600** is sufficiently lower than that of NO_x as illustrated in FIGS. **3A** to **3C**. An example ratio is approximately $\text{HC}:\text{NO}_x=1:6$ even in FIG. **3C** where the concentration of HC is relatively higher and the temperature of the exhaust gas G is 200°C . Thus, it is less necessary to consider the influence of the concentration of HC in diagnosing the degradation, and the diagnostic sensor output can be regarded as reflecting a degree of the degradation in the oxidation ability of the oxidation catalyst **600** against NO (in other words, a degree of decrease in the NO conversion rate).

FIG. **5** exemplifies a relationship between the NO conversion rate and the diagnostic sensor output. FIG. **5** confirms that the diagnostic sensor output has a tendency to increase as the NO conversion rate is lower, irrespective of a temperature of the oxidation catalyst **600**.

Thus, in the oxidation catalyst diagnosis system DS1 according to the present embodiment with disposition of the diagnostic sensor **100** downstream of the oxidation catalyst **600** as illustrated in FIG. **1**, the diagnostic sensor output from the diagnostic sensor **100** reflects a degree of the degradation in the oxidation ability of the oxidation catalyst **600**. Thus, it is possible, in principle, to compare the diagnostic sensor output with a predetermined threshold value and diagnose that the oxidation catalyst **600** is deteriorated beyond an acceptable limit (to an extent requiring replacement) if the diagnostic sensor output exceeds the threshold value.

More specifically, as seen from the differences between the “NEW ITEMS” in component ratio at the downstream side as illustrated in, for example, FIGS. **3A** to **3C**, the oxidation ability of the oxidation catalyst **600** differs depending on a temperature of the exhaust gas G, and thus, a threshold value serving as a reference for diagnosing whether the oxidation catalyst **600** has degraded needs to be changed according to the temperature of the exhaust gas G. Since, in effect, the temperature of the exhaust gas G reaching the oxidation catalyst **600** is regarded as the temperature of the oxidation catalyst **600**, the temperature of the exhaust gas G may be referred to as the temperature of the oxidation catalyst **600** in the following description. As described above when the oxidation catalyst diagnosis system DS1 includes the temperature sensor **110**, the temperature of the oxidation catalyst **600** is identified based on the exhaust temperature detection signal sg12 output by the temperature sensor **110**.

In view of such difference in oxidation ability depending on a temperature of the oxidation catalyst **600**, in the

oxidation catalyst diagnosis system DS1 according to the present embodiment, a relationship between the temperature of the oxidation catalyst **600** and a threshold value of the diagnostic sensor output for the temperature is predetermined and stored as threshold information in the storage of the electronic controller **200**. Then, for the degradation diagnosis, the temperature of the oxidation catalyst **600** is identified, and the degradation diagnosis is made using a threshold value for the identified temperature. The threshold information does not have any particular limitation on its format as long as it is compared with a value of the diagnostic sensor output that is given as the diagnosis detection signal **g11**.

FIG. 6 exemplifies a threshold map illustrated based on the threshold information and indicating the relationship between the temperature of the oxidation catalyst **600** (horizontal axis) and the diagnostic sensor output (vertical axis). More specifically, the threshold information to be the basis for the threshold map shown in FIG. 6 is intended to set a value of the diagnostic sensor output (EMF) when the NO conversion rate is 30% as a threshold value, and is obtained by operating the engine system **1000** incorporating the oxidation catalyst **600** whose NO conversion rate is 30%, under five operation conditions for achieving different temperatures (150° C., 200° C., 300° C., 400° C., and 500° C.) of the oxidation catalyst **600** which are listed in TABLE 1 below.

TABLE 1

ENGINE SPEED (rpm)	λ	AMOUNT OF AIR INTAKE (kg/h)	CATALYST TEMPERATURE (° C.)
1600	1.21	145	500
1600	1.58	131	400
1600	2.22	117	300
1600	4.02	103	200
1600	5.48	95	150

According to the threshold map in FIG. 6, the oxidation catalyst **600** is diagnosed as having degraded to an extent that the NO conversion rate falls under 30% (beyond an acceptable limit) when a value of the diagnostic sensor output is larger than a value on a boundary L, whereas the oxidation catalyst **600** is diagnosed as having no problem in using it even with slight degradation, and being normal when a value of the diagnostic sensor output is smaller than or equal to a value on the boundary L.

When an actual degradation diagnosis is made, it is preferred that a temperature of the oxidation catalyst **600** is identical to a temperature for which the threshold information has been defined. However, when a temperature of the oxidation catalyst **600** is another temperature, interpolation may be appropriately performed on the temperature based on the threshold information to identify a threshold value for the temperature. Alternatively, when a value of the diagnostic sensor output to be a threshold value is regarded almost constant with respect to the temperature of the oxidation catalyst **600** as in a range higher than or equal to 300° C. in the threshold map of FIG. 6, one threshold value may be set for the temperature range.

Example of Diagnosis Procedure

FIG. 7 illustrates an example procedure of a degradation diagnosis to be made in the present embodiment. The degradation diagnosis in the present embodiment starts first from checking by the electronic controller **200** whether

degradation diagnosing conditions hold, under the condition that the engine system **1000** is operating (step S1). The degradation diagnosing conditions includes the following three conditions:

The first condition: the temperature of the oxidation catalyst **600** falls within a predetermined temperature range (e.g., 300° C. to 400° C.);

The second condition: the engine main body **300** is in a predetermined operating state (operating conditions such as an engine speed, an amount of air, an amount of injection, injection timing, and EGR satisfy a predetermined condition range); and

The third condition: the NO_x concentration at the upstream side of the oxidation catalyst **600** falls within a predetermined range (e.g., 500 ppm±25 ppm).

Among these, the first condition may be judged based on a measurement value of the temperature sensor **110**. Alternatively, the first and second conditions may be set so that the temperature of the oxidation catalyst **600** when the second condition holds falls within a temperature range defined under the first condition, and the first condition may establish itself when the second condition holds.

Furthermore, the second condition may hold by operating the engine main body **300** under the conditions identical to those for obtaining the threshold information as indicated in, for example, TABLE 1.

Moreover, the third condition establishes itself when the second condition holds, because the NO_x concentration at the upstream side of the oxidation catalyst **600** is almost uniquely determined once an operating state of the engine main body **300** is fixed. In spite of this, a NO_x sensor may be provided upstream of the oxidation catalyst **600** to check whether the third condition holds, based on its measurement value. The NO_x sensor may be provided downstream of the oxidation catalyst **600** because the NO_x concentration does not change between the upstream side and the downstream side of the oxidation catalyst **600**.

While the degradation diagnosing conditions do not hold (No in step S1), the subsequent processes are suspended. If the degradation diagnosing conditions hold (Yes in step S1), the electronic controller **200** obtains from the diagnostic sensor **100** the diagnosis detection signal **sg11**, that is, the diagnostic sensor output (step S2). Furthermore, the electronic controller **200** calls a threshold value matching the held degradation diagnosing conditions (more specifically, matching the first condition) from the threshold information pre-stored in the storage (step S3).

Upon obtainment of the diagnostic sensor output and calling of the threshold value, the electronic controller **200** compares both of the values (step S4). If the diagnostic sensor output is larger than the threshold value (Yes in step S4), the oxidation catalyst **600** is diagnosed as having degraded (NG) to an unacceptable extent (for example, requiring replacement) (step S5). If the diagnostic sensor output is smaller than or equal to the threshold value (No in step S4), the oxidation catalyst **600** is diagnosed as not having degraded (OK) (step S6).

If the diagnosis is repeated after the end of the diagnosis irrespective of being diagnosed as NG or OK (Yes in step S7), the processes are repeated from the checking whether the degradation diagnosing conditions hold. If not, the diagnosis ends immediately (No in step S7).

As described above, according to the present embodiment, a degree of degradation in the oxidation ability of an oxidation catalyst that is provided at some midpoint of an exhaust pipe connected from an engine main body being a diesel engine in an engine system and that oxidizes a

15

predetermined gas component contained in an exhaust gas is diagnosed, based on an output value of a diagnostic sensor that is provided downstream of the oxidation catalyst and that yields an output corresponding to a NO conversion rate of the oxidation catalyst. Accordingly, without using any output value from a plurality of sensors, whether the oxidation catalyst has degraded can be diagnosed based on an output value from one sensor. Furthermore, since an output from the diagnostic sensor increases as NO increases and as NO₂ decreases, the diagnostic sensor has superior sensitivity to the degradation in the oxidation catalyst. Thus, according to the present embodiment, whether the oxidation catalyst has degraded can be diagnosed in real time and with superior accuracy.

While the invention has been shown and described in detail, the foregoing description is in all aspects illustrative and not restrictive. It is therefore understood that numerous modifications and variations can be devised without departing from the scope of the invention.

What is claimed is:

1. A method for diagnosing a degree of degradation in a catalyst that oxidizes a gas component contained in an exhaust gas discharged from an internal combustion engine, said catalyst being provided in an exhaust path of said internal combustion engine, said method comprising the steps of:

a) providing a diagnostic sensor disposed downstream of said catalyst in said exhaust path, said diagnostic sensor being connected to a controller having a storage and being configured to output an electromotive force corresponding to an NO conversion rate as a diagnostic output; and

b) diagnosing, by said controller, whether said catalyst has degraded beyond an acceptable limit by comparing said diagnostic output with a threshold value stored in said storage that is predetermined depending on a temperature of said catalyst,

wherein said NO conversion rate is defined as a ratio of nitrogen monoxide that is oxidized by said catalyst and discharged downstream of said catalyst as nitrogen dioxide, with respect to nitrogen monoxide contained in said exhaust gas supplied upstream of said catalyst in said exhaust path; and

c) checking, by said controller, whether degradation diagnosing conditions hold, before performing said diagnosing by said controller in said step (b),

wherein said degradation diagnosing conditions include the following first to third conditions:

16

said first condition: said temperature of said catalyst falls within a predetermined temperature range;

said second condition: said internal combustion engine is in a predetermined operating state; and

said third condition: a concentration of nitrogen oxide upstream of said catalyst in said exhaust path falls within a predetermined range,

said degree of degradation in said catalyst being diagnosed by said controller in said step (b) based on a value of said threshold value and said diagnostic output, after checking by said controller in said step (c) that said degradation diagnosing conditions hold,

said threshold value being defined based on an acceptable limit of said NO conversion rate, and said threshold value being determined for said predetermined temperature range defined under said first condition, and in said step (b):

said catalyst being diagnosed by said controller as not having degraded beyond said acceptable limit when said diagnostic output is smaller than or equal to said threshold value; and

said catalyst being diagnosed by said controller as having degraded beyond said acceptable limit when said diagnostic output is larger than said threshold value.

2. The method according to claim 1,

wherein said exhaust gas is a gas in an excessive oxygen atmosphere, and contains a hydrocarbon (HC) and nitrogen oxide (NO_x) in an abundance ratio of HC:NO_x=1:1.8 to 1:10.

3. The method according to claim 1,

wherein said diagnostic output from said diagnostic sensor increases as a concentration of said nitrogen monoxide in said exhaust gas increases and as a concentration of said nitrogen dioxide decreases.

4. The method according to claim 1,

wherein said diagnostic output from said diagnostic sensor increases as a concentration of said nitrogen monoxide in said exhaust gas increases and as a concentration of said nitrogen dioxide decreases.

5. The method according to claim 4,

wherein a mixed-potential type zirconia sensor is used in said diagnostic sensor, said zirconia sensor having a sensing electrode made of a Pt—Au alloy disabling a catalytic activity of said sensing electrode.

* * * * *