



US010444589B2

(12) **United States Patent**  
**Parker et al.**

(10) **Patent No.: US 10,444,589 B2**  
(45) **Date of Patent: Oct. 15, 2019**

(54) **SPACERS AND CONNECTORS FOR INSULATED GLASS UNITS**

(71) Applicant: **View, Inc.**, Milpitas, CA (US)

(72) Inventors: **Ronald M. Parker**, Olive Branch, MS (US); **Yashraj Bhatnagar**, Santa Clara, CA (US); **Trevor Frank**, San Jose, CA (US); **Travis D. Wilbur**, Capitola, CA (US); **Stephen C. Brown**, San Mateo, CA (US)

(73) Assignee: **View, Inc.**, Milpitas, CA (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **15/868,748**

(22) Filed: **Jan. 11, 2018**

(65) **Prior Publication Data**

US 2018/0196325 A1 Jul. 12, 2018

**Related U.S. Application Data**

(63) Continuation of application No. 15/219,832, filed on Jul. 26, 2016, now Pat. No. 9,910,336, which is a (Continued)

(51) **Int. Cl.**  
**G02F 1/163** (2006.01)  
**G02F 1/161** (2006.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **G02F 1/163** (2013.01); **B32B 17/10055** (2013.01); **B32B 17/10174** (2013.01);  
(Continued)

(58) **Field of Classification Search**  
CPC ..... G02F 1/163; G02F 1/155; G02F 1/153; E06B 2009/2464; E06B 9/24  
(Continued)

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

4,306,140 A 12/1981 Stromquist  
4,393,105 A 7/1983 Kreisman  
(Continued)

**FOREIGN PATENT DOCUMENTS**

CH 525376 A 7/1972  
CN 1380991 A 11/2002  
(Continued)

**OTHER PUBLICATIONS**

Preliminary Amendment filed Oct. 5, 2015 in U.S. Appl. No. 14/823,969.

(Continued)


*Primary Examiner* — Mohammed A Hasan

(74) *Attorney, Agent, or Firm* — Weaver Austin Villeneuve & Sampson LLP; Brian D. Griedel

(57) **ABSTRACT**

This disclosure describes insulated glass units (IGUs) that incorporate electrochromic devices. More specifically, this disclosure focuses on different configurations available for providing an electrical connection to the interior region of an IGU. In many cases, an IGU includes two panes separated by a spacer. The spacer defines an interior region of the IGU and an exterior region of the IGU. Often, the electrochromic device positioned on the pane does not extend past the spacer, and some electrical connection must be provided to supply power from the exterior of the IGU to the electrochromic device on the interior of the IGU. In some embodiments, the spacer includes one or more holes (e.g., channels, mouse holes, other holes, etc.) through which an electrical connection (e.g., wires, busbar leads, etc.) may pass to provide power to the electrochromic device.

**20 Claims, 15 Drawing Sheets**



Related U.S. Application Data							
continuation of application No. 14/196,895, filed on Mar. 4, 2014, now Pat. No. 9,442,339, which is a continuation-in-part of application No. 14/152,873, filed on Jan. 10, 2014, now Pat. No. 9,158,173, which is a continuation of application No. 13/312,057, filed on Dec. 6, 2011, now Pat. No. 8,711,465, said application No. 14/196,895 is a continuation-in-part of application No. 14/103,660, filed on Dec. 11, 2013, now Pat. No. 8,810,889, which is a continuation of application No. 13/326,168, filed on Dec. 14, 2011, now Pat. No. 8,643,933.			6,567,708	B1 *	5/2003	Bechtel .....	E06B 9/24 700/19
			6,795,226	B2	9/2004	Agrawal et al.	
(60) Provisional application No. 61/421,154, filed on Dec. 8, 2010, provisional application No. 61/435,914, filed on Jan. 25, 2011.			6,897,936	B1	5/2005	Li et al.	
			6,919,530	B2	7/2005	Borgeson et al.	
(51) <b>Int. Cl.</b>			7,002,720	B2	2/2006	Beteille et al.	
			7,033,655	B2	4/2006	Beteille et al.	
<i>B32B 17/10</i> (2006.01)			7,230,748	B2	6/2007	Giron et al.	
			7,362,491	B2	4/2008	Busick et al.	
<i>E06B 3/663</i> (2006.01)			7,531,101	B2	5/2009	Beteille	
			7,586,664	B2	9/2009	O'Shaughnessy et al.	
<i>G02F 1/153</i> (2006.01)			7,710,671	B1	5/2010	Kwak et al.	
			7,869,114	B2	1/2011	Valentin et al.	
<i>E06B 9/24</i> (2006.01)			7,894,119	B2	2/2011	Valentin et al.	
			7,929,194	B2	4/2011	Legois et al.	
<i>G02F 1/155</i> (2006.01)			7,941,982	B2	5/2011	Merica	
			8,035,882	B2	10/2011	Fanton et al.	
<i>H01R 13/22</i> (2006.01)			8,213,074	B1	7/2012	Shrivastava et al.	
			8,254,013	B2	8/2012	Mehtani et al.	
<i>H01R 13/62</i> (2006.01)			8,300,298	B2	10/2012	Wang et al.	
			8,432,603	B2	4/2013	Wang et al.	
(52) <b>U.S. Cl.</b>			8,643,933	B2	2/2014	Brown et al.	
			8,669,503	B2	3/2014	Johnson et al.	
CPC .... <i>B32B 17/10513</i> (2013.01); <i>E06B 3/66304</i> (2013.01); <i>E06B 3/66314</i> (2013.01); <i>E06B 3/66328</i> (2013.01); <i>E06B 3/66333</i> (2013.01); <i>E06B 3/66352</i> (2013.01); <i>E06B 9/24</i> (2013.01); <i>G02F 1/153</i> (2013.01); <i>G02F 1/155</i> (2013.01); <i>G02F 1/161</i> (2013.01); <i>H01R 13/22</i> (2013.01); <i>H01R 13/6205</i> (2013.01); <i>E06B 2003/6638</i> (2013.01); <i>E06B 2003/66385</i> (2013.01); <i>E06B 2009/247</i> (2013.01)			8,711,465	B2	4/2014	Bhatnagar et al.	
			8,800,221	B1	8/2014	Header	
(58) <b>Field of Classification Search</b>			8,810,889	B2	8/2014	Brown et al.	
			9,019,588	B2	4/2015	Brown et al.	
USPC ..... 359/265, 245, 237–239, 275 See application file for complete search history.			9,158,173	B2	10/2015	Bhatnagar et al.	
			9,360,280	B2	6/2016	White et al.	
(56) <b>References Cited</b>			9,442,339	B2	9/2016	Parker et al.	
			9,897,888	B2	2/2018	Bhatnagar et al.	
U.S. PATENT DOCUMENTS			9,910,336	B2	3/2018	Parker et al.	
			9,958,750	B2	5/2018	Parker et al.	
4,893,908 A 1/1990 Wolf et al.			10,139,696	B2	11/2018	Brown et al.	
			10,139,697	B2	11/2018	Wilbur et al.	
4,941,302 A 7/1990 Barry			2002/0075552	A1	6/2002	Poll et al.	
5,170,108 A 12/1992 Peterson et al.			2003/0041533	A1	3/2003	Trpkivski	
5,313,761 A 5/1994 Leopold			2003/0137712	A1	7/2003	Westfall et al.	
5,379,146 A 1/1995 Defendini			2003/0227663	A1	12/2003	Agrawal et al.	
5,384,653 A 1/1995 Benson et al.			2004/0047050	A1	3/2004	Bauer et al.	
5,657,149 A 8/1997 Buffat et al.			2005/0002081	A1	1/2005	Beteille et al.	
5,657,150 A 8/1997 Kallman et al.			2005/0166495	A1	8/2005	Cho et al.	
5,724,175 A 3/1998 Hichwa et al.			2006/0077511	A1	4/2006	Poll et al.	
5,877,936 A 3/1999 Nishitani et al.			2006/0132923	A1	6/2006	Hsiao et al.	
5,948,195 A 9/1999 Thomas			2006/0187608	A1	8/2006	Stark	
6,001,487 A 12/1999 Ladang et al.			2006/0283084	A1	12/2006	Johnson	
6,045,896 A 4/2000 Boire et al.			2007/0003726	A1	1/2007	Swannell	
6,055,088 A 4/2000 Fix et al.			2007/0020442	A1	1/2007	Giron et al.	
6,055,089 A 4/2000 Schulz et al.			2007/0022700	A1	2/2007	Gallagher	
6,068,720 A 5/2000 McHugh			2007/0067048	A1	3/2007	Bechtel et al.	
6,176,715 B1 1/2001 Buescher			2007/0103761	A1	5/2007	Giron et al.	
6,204,953 B1 3/2001 Zieba et al.			2007/0133078	A1	6/2007	Fanton et al.	
6,261,641 B1 7/2001 Zieba et al.			2007/0138949	A1	6/2007	Yoshida et al.	
6,337,758 B1 1/2002 Beteille et al.			2007/0248756	A1	10/2007	Krisko et al.	
6,369,935 B1 4/2002 Cardinal et al.			2009/0058295	A1	3/2009	Auday et al.	
6,407,847 B1 6/2002 Poll et al.			2009/0067031	A1	3/2009	Piroux et al.	
6,420,071 B1 7/2002 Lee et al.			2009/0097098	A1	4/2009	Piroux	
6,509,999 B1 1/2003 Shelepin et al.			2009/0110918	A1	4/2009	Jacquioid et al.	
6,529,308 B2 3/2003 Beteille et al.			2009/0114928	A1	5/2009	Messere et al.	
6,559,411 B2 5/2003 Borgeson et al.			2009/0130409	A1	5/2009	Reutler et al.	
			2009/0148642	A1	6/2009	Mauser et al.	
			2009/0174300	A1	7/2009	Jousse et al.	
			2009/0181203	A1	7/2009	Valentin et al.	
			2009/0251758	A1	10/2009	Valentin et al.	
			2009/0262411	A1	10/2009	Karmhag et al.	
			2009/0297806	A1	12/2009	Dawson-Elli et al.	
			2009/0323160	A1 *	12/2009	Egerton .....	G02F 1/13336 359/275
			2009/0323162	A1	12/2009	Fanton et al.	
			2010/0208326	A1	8/2010	Kwak et al.	
			2010/0243427	A1	9/2010	Kozlowski et al.	
			2010/0245973	A1	9/2010	Wang et al.	
			2011/0043885	A1	2/2011	Lamine et al.	
			2011/0048614	A1	3/2011	Veerasamy	
			2011/0051221	A1	3/2011	Veerasamy	
			2011/0059275	A1	3/2011	Stark	
			2011/0061319	A1	3/2011	Anderson et al.	
			2011/0094585	A1	4/2011	Debije et al.	
			2011/0148218	A1	6/2011	Rozbicki et al.	

(56)

## References Cited

## U.S. PATENT DOCUMENTS

2011/0211247 A1 9/2011 Kozlowski et al.  
2011/0216389 A1 9/2011 Piroux et al.  
2011/0249314 A1 10/2011 Wang et al.  
2011/0260961 A1 10/2011 Burdis  
2011/0261429 A1 10/2011 Sbar et al.  
2011/0266137 A1 11/2011 Wang et al.  
2011/0266138 A1 11/2011 Wang et al.  
2011/0267672 A1 11/2011 Sbar et al.  
2011/0267674 A1 11/2011 Wang et al.  
2011/0267675 A1 11/2011 Wang et al.  
2011/0292488 A1 12/2011 McCarthy et al.  
2011/0299149 A1 12/2011 Park et al.  
2012/0026573 A1 2/2012 Collins et al.  
2012/0033287 A1 2/2012 Friedman et al.  
2012/0062975 A1 3/2012 Mehtani et al.  
2012/0147449 A1 6/2012 Bhatnagar et al.  
2012/0194895 A1 8/2012 Podbelski et al.  
2012/0200908 A1 8/2012 Bergh et al.  
2012/0239209 A1 9/2012 Brown et al.  
2012/0268803 A1 10/2012 Greer et al.  
2012/0300280 A1 11/2012 Murphy et al.  
2012/0327499 A1 12/2012 Parker et al.  
2013/0157493 A1 6/2013 Brown  
2013/0241299 A1 9/2013 Snyder et al.  
2013/0278988 A1 10/2013 Jack et al.  
2013/0319756 A1 12/2013 Snyder et al.  
2014/0000191 A1 1/2014 Snyder et al.  
2014/0041933 A1 2/2014 Snyder et al.  
2014/0160550 A1 6/2014 Brown et al.  
2014/0170863 A1 6/2014 Brown  
2014/0192393 A1 7/2014 Bhatnagar et al.  
2014/0247475 A1 9/2014 Parker et al.  
2014/0340731 A1 11/2014 Strong et al.  
2014/0349497 A1 11/2014 Brown et al.  
2014/0355097 A1 12/2014 Brown et al.  
2015/0092260 A1 4/2015 Parker et al.  
2015/0118869 A1 4/2015 Brown et al.  
2015/0219975 A1 8/2015 Phillips et al.  
2015/0346575 A1 12/2015 Bhatnagar et al.  
2016/0089869 A1 3/2016 Parker et al.  
2016/0334689 A1 11/2016 Parker et al.  
2016/0363831 A1 12/2016 Ash et al.  
2018/0024408 A1 1/2018 Strong et al.  
2018/0157140 A1 6/2018 Bhatnagar et al.  
2019/0210346 A1 7/2019 Parker et al.

## FOREIGN PATENT DOCUMENTS

CN 1734325 A 2/2006  
CN 1779527 A 5/2006  
CN 1784631 A 6/2006  
CN 1822951 A 8/2006  
CN 1984549 A 6/2007  
CN 201228500 Y 4/2009  
CN 202108407 U 1/2012  
DE 3918913 A1 12/1989  
DE 19611245 A1 9/1997  
DE 102006042538 3/2008  
EP 2136409 12/2009  
EP 2348357 7/2011  
GB 1437198 5/1976  
JP 2000-257352 A 9/2000  
JP 2001-193364 7/2001  
JP 2008-542578 A 11/2008  
JP 2011-526378 A 10/2011  
TW 521118 2/2003  
TW M266467 6/2005  
TW I253182 4/2006  
TW 200731571 A 8/2007  
TW I291073 12/2007  
TW 201029838 A 8/2010  
TW 201215981 A 4/2012  
WO WO2002/008826 A1 1/2002  
WO WO2003/001290 A1 1/2003  
WO WO2005/076061 8/2005

WO WO2006/133298 A2 12/2006  
WO WO2006/133298 A3 12/2007  
WO WO2008/043951 4/2008  
WO WO2009/145876 12/2009  
WO WO2009/148861 12/2009  
WO WO2011/010067 1/2011  
WO WO2011/028253 3/2011  
WO WO2011/028254 3/2011  
WO WO2011/050291 4/2011  
WO WO2011/109688 9/2011  
WO WO2012/078634 A2 6/2012  
WO WO2012/102964 A1 8/2012  
WO WO2012/145155 10/2012  
WO WO2013/090264 6/2013  
WO WO2013/109881 7/2013  
WO WO2014/019780 2/2014  
WO WO2014/032023 2/2014  
WO WO2014/169253 10/2014  
WO WO2015/086459 6/2015  
WO WO2016/092278 A1 6/2016  
WO WO2016/092778 A1 6/2016  
WO WO2016/100075 A1 6/2016  
WO WO2016/121331 A1 8/2016  
WO WO2016/121332 A1 8/2016  
WO WO2016/121347 A1 8/2016

## OTHER PUBLICATIONS

Preliminary Amendment filed Jun. 17, 2016 in U.S. Appl. No. 14/782,772.  
Office Action dated Nov. 3, 2014 in U.S. Appl. No. 13/456,056.  
Final Office Action dated Jul. 16, 2015 in U.S. Appl. No. 13/456,056.  
Office Action dated Feb. 17, 2016 in U.S. Appl. No. 13/456,056.  
Final Office Action dated Sep. 21, 2016 in U.S. Appl. No. 13/456,056.  
Notice of Allowance dated Nov. 24, 2017 in U.S. Appl. No. 13/456,056.  
Office Action dated Oct. 6, 2014 in U.S. Appl. No. 13/968,258.  
Final Office Action dated Jun. 5, 2015 in U.S. Appl. No. 13/968,258.  
Office Action dated Jul. 11, 2013 in U.S. Appl. No. 13/312,057.  
Notice of Allowance dated Dec. 13, 2013 in U.S. Appl. No. 13/312,057.  
Office Action dated Jan. 30, 2015 in U.S. Appl. No. 14/152,873.  
Notice of Allowance dated May 19, 2015 in U.S. Appl. No. 14/152,873.  
Office Action dated May 25, 2016 in U.S. Appl. No. 14/823,969.  
Final Office Action dated Feb. 21, 2017 in U.S. Appl. No. 14/823,969.  
Notice of Allowance dated Sep. 13, 2017 for U.S. Appl. No. 14/823,969.  
Notice of Allowance dated Dec. 7, 2017 for U.S. Appl. No. 14/823,969.  
Office Action dated Mar. 31, 2015 in U.S. Appl. No. 14/196,895.  
Final Office Action dated Sep. 18, 2015 in U.S. Appl. No. 14/196,895.  
Notice of Allowance dated Apr. 21, 2016 in U.S. Appl. No. 14/196,895.  
Notice of Allowance dated Jul. 21, 2016 in U.S. Appl. No. 14/196,895.  
Office Action dated Jun. 29, 2017 for U.S. Appl. No. 15/219,832.  
Notice of Allowance dated Sep. 18, 2013 for U.S. Appl. No. 13/326,168.  
Notice of Allowance dated Jun. 13, 2014 for U.S. Appl. No. 14/103,660, and allowed claims.  
Notice of Allowance dated Oct. 9, 2014 for U.S. Appl. No. 14/325,290.  
Notice of Allowance dated Feb. 25, 2015 for U.S. Appl. No. 14/325,290.  
Office Action dated Feb. 4, 2015 for U.S. Appl. No. 14/591,851.  
Office Action dated Jul. 28, 2017 for U.S. Appl. No. 13/456,056.  
Notice of Allowance dated Oct. 16, 2017 for U.S. Appl. No. 15/219,832.  
Extended Supplementary European Search Report dated Feb. 16, 2016 for EP Application No. 13781444.8.  
Partial Supplementary European Search Report dated Dec. 7, 2015 for EP Application No. 13781444.8.  
EP Office Action dated Feb. 23, 2017 for EP Application No. 13781444.8.

(56)

**References Cited**

## OTHER PUBLICATIONS

CN Office Action dated Oct. 8, 2016 for CN Application No. 201380025955.6.  
 CN Office Action dated Jul. 4, 2017 in CN Application No. 201380025955.6.  
 RU Office Action dated Sep. 19, 2016 in RU Application No. 2014147152.  
 RU Search Report dated Jan. 19, 2017 in RU Application No. 2014147152.  
 TW Office Action dated Oct. 25, 2016 in TW Application No. 102114688.  
 International Preliminary Report on Patentability dated Jun. 11, 2014 for PCT/US2013/037644.  
 International Search Report and Written Opinion dated Aug. 12, 2013 for PCT/US2013/037644.  
 European Search Report dated Mar. 3, 2014 for EP Application No. 11846667.1.  
 EP Office Action dated Nov. 4, 2013 for EP Application No. 11846667.1.  
 CN Office Action dated Jun. 2, 2015 in CN Application No. 201180058960.8.  
 CN Office Action dated Mar. 14, 2016 in CN Application No. 201180058960.8.  
 CN Office Action dated Nov. 16, 2016 in CN Application No. 201180058960.8.  
 EP Office Action dated May 18, 2016 for EP Application No. 11846667.1.  
 TW Office Action dated Oct. 15, 2015 in TW Application No. 100145134.  
 TW Office Action dated Apr. 11, 2017 in TW Application No. 105129376.  
 International Search Report and Written Opinion dated Jul. 23, 2012, from PCT/US2011/063534.  
 International Preliminary Report on Patentability dated Jun. 20, 2013, from PCT/US2011/063534..  
 European Search Report dated Apr. 2, 2015 for EP Application No. 12858168.3.  
 CN Office Action dated Jun. 3, 2015 in CN Application No. 201280069715.1.  
 International Preliminary Report on Patentability dated Jun. 26, 2014 from PCT/US2012/068950.  
 International Search Report and Written Opinion dated Apr. 1, 2013 from PCT/US2012/068950.  
 International Search Report and Written Opinion dated May 18, 2015 from PCT/US2015/014479.  
 International Preliminary Report on Patentability dated Mar. 5, 2015 for PCT/US2013/056506.  
 International Search Report and Written Opinion dated Nov. 22, 2013 for PCT/US2013/056506.  
 Extended Supplementary European Search Report dated Oct. 11, 2016 for EP Application No. 14782906.3.  
 European Examination Report dated Jun. 9, 2017 for EP Application No. 14782906.3.

International Preliminary Report on Patentability dated Oct. 22, 2015 for PCT/US2014/033870.  
 International Search Report and Written Opinion dated Aug. 19, 2014 for PCT/US2014/033870.  
 International Search Report and Written Opinion dated Apr. 6, 2016 for PCT/US2015/064942.  
 International Preliminary Report on Patentability dated Jun. 29, 2017 for PCT/US2015/064942.  
 Ernst, Randi, "Gas Filling of IG Units" by FDR Design, Inc. (undated), 37 pages.  
 Armstrong, Dave, "Smart, energetic glass could take over" in *Earth Times*, [http://www.earthtimes.org/energy/smart-energetic-glass-take-over/2866/] Apr. 12, 2015.  
 "'Smart glass' changes colour and produces electricity", *ZeeNewsIndia.com* [http://zeenews.india.com/news/sci-tech/smart-glass-changes-colour-and-produces-electricity\_1577561.html] Apr. 12, 2015.  
 Burdis et al., "Electrochromic windows: Process and fabrication improvements for lower total costs," SAGE Electronics, Inc., Contract No. DE-FC26-03NT41952, Final Report, Technical Report of SciTech Connect, Mar. 31, 2009.  
 U.S. Appl. No. 15/535,681, filed Jun. 13, 2017, Strong, et al.  
 Preliminary Amendment filed Jun. 13, 2017 in U.S. Appl. No. 15/535,681.  
 Preliminary Amendment filed Apr. 16, 2018 in U.S. Appl. No. 15/866,379.  
 Office Action dated Feb. 7, 2019 in U.S. Appl. No. 15/866,379.  
 Notice of Allowance (corrected) dated Feb. 2, 2018 for U.S. Appl. No. 15/219,832.  
 US Office Action dated Dec. 21, 2018 for U.S. Appl. No. 14/782,772.  
 EP Summons to Attend Oral Proceedings dated Feb. 8, 2018 for EP Application No. 13781444.8.  
 EP Office Action dated Dec. 6, 2018 for EP Application No. 13781444.8.  
 Extended Supplementary European Search Report dated Apr. 17, 2019 for EP Application No. 19150851.4.  
 CN Office Action dated Mar. 26, 2018 in CN Application No. 201380025955.6.  
 CN Office Action dated Dec. 18, 2018 in CN Application No. 201380025955.6.  
 In Office Action dated Mar. 19, 2019 in IN Application No. 2564/KOLNP/2014.  
 TW Office Action dated Jun. 20, 2018 in TW Application No. TW 106119450.  
 European Search Report dated Nov. 7, 2018 for EP Application No. 18182249.5.  
 TW Office Action dated Jul. 13, 2018 in TW Application No. 107109673.  
 TW Decision of Rejection dated Nov. 19, 2018 in TW Application No. 107109673.  
 European Office Action dated Jan. 18, 2018 for EP Application No. 14782906.3.  
 U.S. Appl. No. 16/386,094, filed Apr. 16, 2016, Brown et al.  
 Preliminary Amended dated Apr. 17, 2019 in U.S. Appl. No. 16/386,094.

\* cited by examiner




Fig. 1A






Fig. 1B



*Fig. 1C*



**Fig. 2A**




Fig. 2B







Fig. 3A




*Fig. 3B*




*Fig. 4*




*Fig. 5A*




*Fig. 5B*



*Fig. 6*



*Fig. 7*







Fig. 9



**Fig. 10A**




Fig. 10B




Fig. 11A




Fig. 11B

## SPACERS AND CONNECTORS FOR INSULATED GLASS UNITS

### CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of and claims priority to U.S. application Ser. No. 15/219,832 filed Jul. 26, 2016, and titled "SPACERS AND CONNECTORS FOR INSULATED GLASS UNITS," which is a continuation of U.S. application Ser. No. 14/196,895 (issued as U.S. Pat. No. 9,442,339), filed Mar. 4, 2014, and titled "SPACERS AND CONNECTORS FOR INSULATED GLASS UNITS," which is a continuation-in-part of U.S. patent application Ser. No. 14/152,873 (issued as U.S. Pat. No. 9,158,173), filed Jan. 10, 2014, and titled "SPACERS FOR INSULATED GLASS UNITS," which is a continuation of U.S. patent application Ser. No. 13/312,057 (issued as U.S. Pat. No. 8,711,465), filed Dec. 6, 2011, and titled "SPACERS FOR INSULATED GLASS UNITS," which claims benefit of priority to U.S. Provisional Patent Application No. 61/421,154, filed Dec. 8, 2010, and titled "IMPROVED SEPARATORS FOR INSULATED GLASS UNITS," and to U.S. Provisional Patent Application No. 61/435,914, filed Jan. 25, 2011, and titled "IMPROVED SEPARATORS FOR INSULATED GLASS UNITS," each of which is herein incorporated by reference in its entirety and for all purposes. U.S. patent application Ser. No. 14/196,895 is also a continuation-in-part of U.S. patent application Ser. No. 14/103,660 (issued as U.S. Pat. No. 8,810,889), filed Dec. 11, 2013, and titled "CONNECTORS FOR SMART WINDOWS," which is a continuation of U.S. patent application Ser. No. 13/326,168 (issued as U.S. Pat. No. 8,643,933), filed Dec. 14, 2011, and titled "CONNECTORS FOR SMART WINDOWS." Each of the above-identified applications is herein incorporated by reference in its entirety and for all purposes.

### FIELD

The disclosed embodiments relate generally to spacers and insulated glass units containing them, and more particularly to insulated glass units including optically switchable devices.

### BACKGROUND

Various optically switchable devices are available for controlling tinting, reflectivity, etc. of window panes. Electrochromic devices are one example of optically switchable devices generally. Electrochromism is a phenomenon in which a material exhibits a reversible electrochemically-mediated change in an optical property when placed in a different electronic state, typically by being subjected to a voltage change. The optical property being manipulated is typically one or more of color, transmittance, absorbance, and reflectance. One well known electrochromic material is tungsten oxide ( $\text{WO}_3$ ). Tungsten oxide is a cathodic electrochromic material in which a coloration transition, transparent to blue, occurs by electrochemical reduction.

Electrochromic materials may be incorporated into, for example, windows for home, commercial, and other uses. The color, transmittance, absorbance, and/or reflectance of such windows may be changed by inducing a change in the electrochromic material, that is, electrochromic windows are windows that can be darkened or lightened electronically. A small voltage applied to an electrochromic (EC) device of the window will cause it to darken; reversing the voltage

causes it to lighten. This capability allows for control of the amount of light that passes through the window, and presents an enormous opportunity for electrochromic windows to be used not only for aesthetic purposes but also for energy-savings.

With energy conservation being foremost in modern energy policy, it is expected that growth of the EC window industry will be robust in the coming years. An important aspect of EC window engineering is how to integrate EC windows into new and existing (retrofit) applications. Of particular import is how to deliver power to the EC glazings through framing and related structures.

### SUMMARY

Insulated glass units (IGUs) incorporating electrochromic devices are disclosed herein. The disclosed IGUs include spacers that allow for an electrical connection to be passed through or under the spacer to provide power from an external power source to the electrochromic device in the IGU.

In one aspect of the disclosed embodiments, an IGU includes a first glass substrate; a second glass substrate oriented parallel to the first glass substrate; an electrochromic device positioned on the first or second glass substrate; two bus bars electrically connected to the electrochromic device; a spacer positioned between the first and second glass substrates proximate the periphery of the first and second glass substrates, where the spacer defines an interior region of the IGU located interior of the spacer and an exterior region of the IGU located outside of the spacer; and one or more wires passing through the spacer to provide electrical power from an external power source located in the exterior region to the bus bars and the electrochromic device in the interior region of the IGU.

In certain embodiments the spacer may be hollow. Where this is the case, the wires may enter the hollow spacer at a first location, pass within the hollow interior of the spacer for a distance, and exit the spacer at a second location. In these or other cases, the spacer may include one or more holes through which the one or more wires pass.

The spacer may include different parts, for example a conductive portion and an insulating or non-conductive portion. For example, the insulating or non-conductive portion may be a connector key that joins the ends of the conductive portion together. In this embodiment, the one or more wires passing through the spacer may traverse the spacer at the insulating or non-conductive connector key. The IGU may also include a controller coupled to the IGU and configured to drive an electrochromic transition of the electrochromic device of the IGU.

In a particular embodiment, the spacer is a track having interior recesses for two or more electrical connections on the interior of the track and exterior recesses for two or more electrical connections on the exterior of the track. The track may include one or more holes through the track for establishing a pass-through electrical connection between the two or more electrical connections on the exterior of the track and the two or more electrical connections on the interior of the track, where the electrical connections on the interior of the track provide power to the bus bars, and where the electrical connections on the exterior of the track provide power from an external power source.

In various implementations, the IGU includes a seal in a hole of the spacer through which the one or more wires pass. The wires passing through the spacer may be provided

## 3

together as a braided wire. Where the spacer is hollow, a dessicant may be provided in the hollow interior of the spacer.

In another aspect of the disclosed embodiments, an IGU includes a first glass substrate; a second glass substrate oriented parallel to the first glass substrate; an electrochromic device positioned on the first or second glass substrate; two bus bars electrically connected to the electrochromic device; a spacer positioned between the first and second glass substrates proximate the periphery of the first and second glass substrates, where the spacer defines an interior region of the IGU located interior of the spacer and an exterior region of the IGU located outside of the spacer; and one or more electrical connections passing through or under the spacer to provide electrical power from an external power source located in the exterior region to the bus bars and the electrochromic device in the interior region of the IGU.

In certain embodiments, the IGU further includes a channel in or under the spacer, through which the electrical connections pass from the interior region of the IGU to the exterior region of the IGU. For example, the spacer may include an indented portion such that the channel is defined on one side by the first or second glass substrate or a layer of material thereon, and on remaining sides by the indented portion of the spacer as the channel passes from the exterior region to the interior region of the IGU. The channel may have a height between about 0.1-1 mm, in certain cases. The electrical connections may be wires that pass under (or through) the spacer. In other cases, the electrical connections may be bus bar leads that pass under the spacer. A controller may be coupled to the IGU and configured to drive an electrochromic transition of the electrochromic device on the IGU.

These and other features and advantages will be described in further detail below, with reference to the associated drawings.

## BRIEF DESCRIPTION OF THE DRAWINGS

FIGS. 1A-1C show examples of schematic diagrams of electrochromic devices formed on windows.

FIG. 2A shows a cross-sectional schematic diagram of an electrochromic window integrated into an IGU.

FIG. 2B is an additional cross-sectional schematic of an electrochromic device.

FIG. 3A depicts an example of an electrochromic window fabrication process.

FIG. 3B depicts an example of a window assembly.

FIG. 4 shows examples of three modes of potential shorting to the spacer and consequent failure of an electrochromic device in an IGU.

FIG. 5A shows an example of a cross-section of an edge region of an IGU where the spacer of the IGU and the bus bar reside.

FIG. 5B shows cross-sections of other spacers in accord with embodiments described herein.

FIG. 6 shows two embodiments of connector keys.

FIG. 7 shows an example of a detailed cross-sectional view of a crimped connector key aligned on a glass sheet with an electrochromic device fabricated thereon.

FIGS. 8 and 9 show schematic diagrams of an insulated glass unit including an electrochromic pane and an associated wire assembly.

FIGS. 10A and 10B include schematic diagrams of an insulated glass unit (IGU) with a frame that may serve as

## 4

both as a secondary sealing element and an electrical connector for an electrochromic pane of the IGU.

FIGS. 11A and 11B show examples of IGUs with different wiring configurations.

## DETAILED DESCRIPTION

It should be understood that while the disclosed embodiments focus on electrochromic (EC) windows (also referred to as smart windows), the concepts disclosed herein may apply to other types of switchable optical devices, including liquid crystal devices, suspended particle devices, and the like. For example, a liquid crystal device or a suspended particle device, instead of an electrochromic device, could be incorporated in any of the disclosed embodiments.

An insulated glass unit (IGU) is part of the transparent component of a window. In the following description, an IGU may include two substantially transparent substrates, for example, two glass lites (also referred to as panes), where at least one lite includes an electrochromic device disposed thereon, and the lites have a spacer disposed between them. One or more of the lites may itself be a laminate structure of lites. An IGU is typically hermetically sealed, having an interior region that is isolated from an exterior region including the ambient environment. A window assembly may include an IGU, electrical connectors for coupling the one or more electrochromic devices of the IGU to a window controller, and a frame that supports the IGU and related wiring.

Disclosed herein are various embodiments in which electrochromic windows are incorporated in IGUs with spacers and connectors having improved configurations. An electrochromic window includes a transparent substrate (e.g., a glass sheet or lite) on which is provided a thin electrochromic device. Metal spacers conventionally employed in IGUs may not work well with electrochromic windows due to, e.g., shorting issues with the electrical components of the electrochromic device on one or more lites of the window unit. Specifically, the IGUs disclosed herein generally have measures for avoiding electrical shorting between a metal spacer and conductive components of the electrochromic window, such as bus bars.

For example, electrochromic devices on glass lites use conductive wires, bus bars, or other connections that pass over, under or through a spacer used to form an IGU, for electrical communication to the electrochromic device. Spacers are often chosen, or required, to be a metal, and for some IGUs, the glass lites may be compressed against the spacer. In some configurations, there are problematic issues created by compressing a metallic, conductive spacer against a conductor (e.g., the conductive wires, bus bars, or other connections) of the electrochromic device. Some conventional sealants may not suffice as insulators in such conditions.

In order to orient the reader to the embodiments of IGUs disclosed herein, a brief discussion of electrochromic devices, edge deletion, and IGUs is provided. This initial discussion of electrochromic devices, edge deletion, and IGUs is provided for context only, and the subsequently described embodiments of spacers are not limited to the specific features and fabrication processes of this initial discussion.

Particular examples of electrochromic devices formed on substrates are described with reference to FIGS. 1A-1C. FIG. 1A is a cross-sectional representation (along cut X-X as depicted in FIG. 1C) of an electrochromic lite, **100**, which is fabricated starting with a glass sheet, **105**. FIG. 1B shows

## 5

a different view from Y-Y as depicted in FIG. 1C; i.e., FIG. 1B shows a view of electrochromic lite **100** from the bottom edge and in the plane of the paper (e.g., 90 degrees from the cross-sectional view shown in FIG. 1A). FIG. 1C shows a top-down view of electrochromic lite **100**.

FIG. 1A shows an electrochromic lite after edge deletion (described below), laser scribing, and bus bar attachment. Glass sheet **105** has a diffusion barrier, **110**, and a first transparent conducting oxide (TCO) layer, **115**, on the diffusion barrier. First TCO layer **115** is the first of two

conductive layers that form the electrodes of the electrochromic device fabricated on the glass sheet. In some embodiments, the glass sheet as supplied may include the diffusion barrier layer as well as the first TCO layer. Thus, in some embodiments, an electrochromic stack, **120**, and then a second TCO layer, **125**, may be formed in the fabrication of electrochromic lite **100**. The electrochromic stack (also referred to as an electrochromic device) is typically a series of layers, e.g., an electrochromic layer, an electrolyte layer, and an ion storage layer; however, in some embodiments electrochromic stack **120** is an electrochromic layer and an ion storage layer with an interfacial region that acts as an electrolyte layer. Examples of electrochromic devices including such stacks are described in U.S. patent application Ser. No. 12/772,055, filed Apr. 30, 2010, titled "Electrochromic Devices," and naming Wang et. al as inventors; the application is incorporated by reference in its entirety herein. In some embodiments, electrochromic stack **120** and second TCO layer **125** are fabricated in an integrated deposition system where glass sheet **105** does not leave the integrated deposition system at any time during fabrication of the stack. In some embodiments, first TCO layer **115** is also formed using the integrated deposition system where glass sheet **105** does not leave the integrated deposition system during deposition of the stack/layers. In some embodiments, all of the layers (diffusion barrier **110**, first TCO layer **115**, electrochromic stack **120**, and the second TCO layer **125**) are deposited in the integrated deposition system where glass sheet **105** does not leave the integrated deposition system during deposition of the stack/layers.

After formation of the electrochromic device, edge deletion and laser scribing are performed. FIG. 1A depicts areas, **140**, where portions of the electrochromic device have been removed from a perimeter region surrounding the laser scribe trenches, **130**, **131**, **132**, and **133** (see also FIGS. 1B and 1C). The laser scribe trenches pass through the second TCO layer and the electrochromic stack, but not through the first TCO. The laser scribe trenches are made to isolate portions of the electrochromic device, **135**, **136**, **137**, and **138**, from the operable electrochromic device. The isolated portions of the electrochromic device are portions that were potentially damaged during edge deletion and/or fabrication. If the edge deletion produces a clean cut edge to the device stack, e.g., using lasers for the removal of material in the edge deletion, then these isolation trenches may not be needed.

In some embodiments, laser scribe trenches **130**, **132**, and **133** pass through the first TCO layer to aide in isolation of the device. Note that laser scribe trench **131** does not pass through the first TCO layer; otherwise, it would cut off bus bar **2**'s electrical communication with the first TCO layer and thus the electrochromic stack.

The laser or lasers used for the laser scribing are typically, but not necessarily, pulse-type lasers, for example, including diode-pumped solid state lasers. For example, the laser scribing can be performed using a suitable laser from IPG

## 6

Photonics (Oxford, Mass.), or from Ekspla (Vilnius, Lithuania). Scribing can also be performed mechanically, for example, with a diamond tipped scribe. One of ordinary skill in the art would appreciate that the laser scribing can be performed at different depths and/or performed in a single process whereby the laser cutting depth is varied, or not, during a continuous (or not) path around the perimeter of the electrochromic device. In some embodiments, the edge deletion is performed to the depth below the first TCO layer. In some embodiments, a second laser scribe is performed to isolate a portion of the first TCO layer near the edge of the glass sheet from that toward the interior, as depicted in FIGS. 1A-C, for example. In some embodiments, this scribe is at least along the edge of electrochromic lite **100** where bus bar **2** is applied to the first TCO layer and is between bus bar **2** and the edge of electrochromic lite **100**.

After laser scribing is complete, bus bars are attached. In FIGS. 1A-C, a non-penetrating bus bar **1** is applied to second TCO layer **125**. Non-penetrating bus bar **2** is applied to an area where the device was not deposited (for example, from a mask protecting first TCO layer **115** from device deposition), in contact with first TCO layer **115** or, as depicted in FIG. 1A, where edge deletion was used to remove material down to first TCO layer **115**. In this example, both bus bar **1** and bus bar **2** are non-penetrating bus bars. A penetrating bus bar is one that is typically pressed into and through the electrochromic stack to make contact with the TCO layer at the bottom of the stack. In some embodiments, a soldering step, where a contact is soldered to a bus bar, may serve to penetrate the electrochromic stack and establish electrical contact to a lower conducting layer. A non-penetrating bus bar is one that does not penetrate into the electrochromic stack layers, but rather makes electrical and physical contact on the surface of a conductive layer, for example, a TCO layer. Both types are suitable for use with the embodiments disclosed herein.

Edge deletion may be performed on a window where edge portions of an electrochromic device are removed prior to integration of the window into the IGU. The edge portions may include, for example, regions of "roll off" where layers of an electrochromic stack that are normally separated contact one another due to non-uniformity in the layers near the edge of the electrochromic device.

Further, edge deletion may be employed for removal of one or more electrochromic device layers that would otherwise extend to underneath the IGU. In some embodiments, isolation trenches are cut and the isolated portions of the electrochromic device on the perimeter of the electrochromic lites are removed by edge deletion. The process of performing edge deletion is, in some embodiments, a mechanical process such as a grinding or sandblasting process. An abrasive wheel may be employed for grinding. In some embodiments, edge deletion is done by laser, where a laser is used to ablate electrochromic material from the perimeter of the electrochromic lite. The process may remove all electrochromic device layers, including the underlying TCO layer, or it may remove all electrochromic device layers except the bottom TCO layer. The latter case is appropriate when the edge deletion is used to provide an exposed contact for a bus bar, which may be connected to the bottom TCO layer. In some embodiments, a laser scribe is used to isolate that portion of the bottom TCO layer that extends to the edge of the glass sheet from that which is connected to the bus bar (sometimes referred to as a bus bar pad or contact pad) in order to avoid having a conductive path to the electrochromic device from the edge of the glass sheet.

When edge deletion is employed, it can be performed before or after the electrochromic lites are cut from the glass sheet (assuming that lites are cut from a larger glass sheet as part of the fabrication process). In some embodiments, edge deletion is performed in some edge areas prior to cutting the electrochromic lites and again after they are cut. In some embodiments, all edge deletion is performed prior to cutting the electrochromic lites. In embodiments employing edge deletion prior to cutting the electrochromic lites, portions of the electrochromic device on the glass sheet can be removed in anticipation of where the cuts (and thus edges) of the newly formed electrochromic lites will be. In most fabrication processes, after edge deletion, bus bars are applied to the one or more electrochromic lites.

After the electrochromic devices with bus bars are fully assembled on the glass sheets, IGUs are manufactured using the one or more electrochromic lites (e.g., refer to FIG. 3A and the associated description). Typically, an IGU is formed by placing a primary sealing spacer, which may include a gasket or sealing material (e.g., PVB (polyvinyl butyral), PIB (polyisobutylene), or other suitable elastomer) and a rigid spacer around the perimeter of the glass sheet. The primary sealing spacer may also be referred to as a primary sealant. In the disclosed embodiments, the primary sealing spacer includes a metal spacer, or other rigid material spacer, and sealing material between the metal spacer and each glass lite. After the lites are joined to the primary sealing spacer, a secondary seal may be formed around the outer perimeter of the primary sealing spacer. The secondary seal may be, for example, a polymeric material that resists water and that adds structural support to the IGU. Typically, but not necessarily, a desiccant is included in the IGU frame or spacer during assembly to absorb any moisture and/or organic volatiles that may diffuse from the sealant materials. In some embodiments, the primary sealing spacer surrounds the bus bars and electrical leads to the bus bars extend through the seal. Typically, but not necessarily, the IGU is filled with inert gas such as argon. The completed IGU can be installed in, for example, a frame or curtain wall and connected to a source of electricity and a controller to operate the electrochromic window.

As described above, after the bus bars are connected, the electrochromic lite is integrated into an IGU as shown in FIG. 2A, which includes, for example, wiring for the bus bars and the like (wiring shown in FIG. 2B). In the embodiments described herein, both of the bus bars are inside the primary seal of the finished IGU. FIG. 2A shows a cross-sectional schematic diagram of the electrochromic window as described in relation to FIGS. 1A-C integrated into an IGU, 200. A spacer, 205, is used to separate electrochromic lite 201 from a second lite, 210. Second lite 210 in IGU 200 is a non-electrochromic lite, however, the embodiments disclosed herein are not so limited. For example, lite 210 can have an electrochromic device thereon and/or one or more coatings such as low-E coatings and the like. Lite 201 can also be laminated glass, for example with glass lite 201 laminated to a reinforcing pane via a layer of resin. Between spacer 205 and the first TCO layer of the electrochromic lite is a primary seal material, 215. This primary seal material is also between spacer 205 and second glass lite 210. Around the perimeter of spacer 205 is a secondary seal, 220. Bus bar wiring/leads traverse the seals for connection to controller. Secondary seal 220 may be much thicker than depicted. These seals aid in keeping moisture out of an interior space, 202, of the IGU. They also serve to prevent argon or other gas in the interior of the IGU from escaping.

The electrochromic window may be controlled to provide a desired optical window state. Details regarding voltages and algorithms used for driving an optical state transition for an electrochromic device may be found in U.S. patent application Ser. No. 13/049,623, titled "CONTROLLING TRANSITIONS IN OPTICALLY SWITCHABLE DEVICES," filed Mar. 16, 2011, which is herein incorporated by reference.

Along with voltage algorithms, there is associated wiring and connections for the electrochromic device being powered. FIG. 2B shows an example of a cross-sectional schematic of an electrochromic device, 250. Electrochromic device 250 includes a substrate, 255. The substrate may be transparent and may be made of, for example, glass. A first transparent conducting oxide (TCO) layer, 260, is on substrate 255, with first TCO layer 260 being the first of two conductive layers used to form the electrodes of electrochromic device 250. Electrochromic stack 265 may include (i) an electrochromic (EC) layer, (ii) an ion-conducting (IC) layer, and (iii) a counter electrode (CE) layer to form a stack in which the IC layer separates the EC layer and the CE layer. Electrochromic stack 265 is sandwiched between first TCO layer 260 and a second TCO layer, 270, TCO layer 270 being the second of two conductive layers used to form the electrodes of electrochromic device 250. First TCO layer 260 is in contact with a first bus bar, 280, and second TCO layer 270 is in contact with a second bus bar, 275. Wires, 281 and 282, are connected to bus bars 280 and 275, respectively, and form a wire assembly (not shown) which terminates in a connector, 285. Wires of another connector, 290, may be connected to a controller that is capable of effecting a transition of electrochromic device 250, e.g., from a first optical state to a second optical state. Connectors 285 and 290 may be coupled, such that the controller may drive the optical state transition for electrochromic device 250.

Further details regarding electrochromic devices may be found in U.S. patent application Ser. No. 12/645,111, titled "FABRICATION OF LOW DEFECTIVITY ELECTROCHROMIC DEVICES," filed Dec. 22, 2009. Further details regarding electrochromic devices may also be found in U.S. Pat. No. 8,432,603, filed Dec. 22, 2009, U.S. Pat. No. 8,300,298, filed Apr. 30, 2010, U.S. patent application Ser. No. 12/814,277 filed Jun. 11, 2010, and U.S. patent application Ser. No. 12/814,279 filed Jun. 11, 2010, each titled "ELECTROCHROMIC DEVICES;" each of the aforementioned are herein incorporated by reference.

In accordance with voltage algorithms and associated wiring and connections for powering an electrochromic device, there are also aspects of how the wired EC glazing is incorporated into an IGU and how the IGU is incorporated into, e.g., a frame. FIG. 3A shows examples of the operations for fabricating an insulated glass unit, 325, including an electrochromic pane, 305, and incorporating the insulated glass unit into a frame, 327. Electrochromic pane 305 has an electrochromic device (not shown, but for example on surface A) and bus bars, 310, which provide power to the electrochromic device. Electrochromic pane 305 is matched with another glass pane, 315. The electrochromic pane may include, for example, an electrochromic device similar to the electrochromic device shown in FIGS. 2A and 2B, as described above. In some embodiments, the electrochromic device is solid state and inorganic.

During fabrication of IGU 325, a separator, 320 is sandwiched in between and registered with glass panes 305 and 315. IGU 325 has an associated interior space defined by the faces of the glass panes in contact with separator 320 and the interior surfaces of the separator. Separator 320 may be a

sealing separator, that is, the separator may include a spacer and sealing material (primary seal) between the spacer and each glass pane where the glass panes contact the separator. A sealing separator together with the primary seal may seal, e.g., hermetically, the interior volume enclosed by glass panes **305** and **315** and separator **320** and protect the interior volume from moisture and the like. Once glass panes **305** and **315** are coupled to separator **320**, a secondary seal may be applied around the perimeter edges of IGU **325** in order to impart further sealing from the ambient environment, as well as further structural rigidity to IGU **325**. The secondary seal may be a silicone based sealant, for example.

IGU **325** may be wired to a window controller, **350**, via a wire assembly, **330**. Wire assembly **330** includes wires electrically coupled to bus bars **310** and may include other wires for sensors or for other components of IGU **325**. Insulated wires in a wire assembly may be braided and have an insulated cover over all of the wires, such that the multiple wires form a single cord or line. A wire assembly may also be referred to as a “pig-tail.” IGU **325** may be mounted in frame **327** to create a window assembly, **335**. Window assembly **335** is connected, via wire assembly **330**, to window controller, **350**. Window controller **350** may also be connected to one or more sensors in frame **327** with one or more communication lines, **345**. During fabrication of IGU **325**, care must be taken, e.g., due to the fact that glass panes may be fragile but also because wire assembly **330** extends beyond the IGU glass panes and may be damaged.

FIG. **3B** depicts an example of a window assembly, **335**, including frame **340**. The viewable area of the window assembly is indicated on the figure, inside the perimeter of frame **340** (using a heavy black line). As indicated by dotted lines, inside frame **340** is IGU **325** which includes two glass lites separated by sealing spacer **320**, shaded in gray.

In some embodiments, an edge bumper is employed to protect the edges of the glass after incorporation in the IGU. This protection allows the IGU to be safely transported from manufacturer to installation, for example. In some embodiments, the protective bumper is a U-channel cap which fits over the glass edges around the perimeter of the IGU. It may be made from an elastomeric or plastic material. In some embodiments, the edge bumper is a vinyl cap.

FIG. **4** is a facing or front view of an IGU, **400**, which includes electrochromic lite **305** as depicted in FIG. **3A**. Electrochromic lite **305** has bus bars **310** fabricated on an electrochromic device (not depicted). FIG. **4** shows the relative configurations of the spacer, the electrochromic lite, the wiring, and so forth. Spacer **320** surrounds bus bars **310** and overlays leads to the bus bars. In some embodiments, the bus bar leads may be a conductive ink. Wiring, **405**, connects to bus bars **310** via the bus bar leads. Wiring **405** further occupies at least a portion of the secondary seal area and then passes out of IGU **400**. In some embodiments, wiring **405** may be insulated (i.e., the wiring may have a conductive metal core covered with an insulating material, for example).

Because the spacer in a conventional IGU is made from a metal, such as a steel hollow bar or a stainless steel hollow bar, for example, it can possibly short out one or more features contained in an electrochromic device employed in an electrochromic window. Using IGU **325** (see FIG. **3A**) as an example, lite **315** is pressed together with electrochromic lite **305** with spacer **320** and a primary sealant material there between. With the bus bar leads extending under spacer **320**, there is a chance of shorting between the bus bar leads and the spacer.

In some embodiments, rather than bus bar leads traversing the area where the spacer presses against the primary sealant material, wires **405** may traverse the area. However, the compression used to assemble an IGU may compromise the integrity of insulation on wires **405**. In some embodiments, wires **405** may be thin, flat wires (e.g., braided wire cabling, ribbon cable, circuit-board type flat electrical connections) with insulation over the wires. In some embodiments, the wires run between the spacer and the lite, rather than leads as depicted in FIG. **4**. Even if thin, flat wires are used, there still may be issues with shorting.

FIG. **4** further shows examples of three modes of potential shorting of the electrochromic device to the spacer and consequent failure of the electrochromic device. Reference **X** illustrates a potential short between the bus bar and the spacer at a “crossover point,” e.g., the bus bar lead. The crossover point can be understood as the electrical connection between the bus bar of the electrochromic device and an external connection to the bus bar from outside the interior space of the IGU. Typically, the external connection provides power from a voltage or other power source to the bus bar. The bus bar provides power to one of the two sheet electrodes of the electrochromic device. In the above embodiments, the sheet electrodes are typically transparent conductive oxides (TCOs), such as indium tin oxide (ITO) or TEC (a fluorinated tin oxide conductive layer provided on glass lites marketed under the trademark TEC Glass™ by Pilkington). The contact between the bus bar lead and the spacer shown as reference **X** is a region where the bus bar lead (or a wire) extends across the spacer from the interior space of the IGU to the secondary seal area. The bus bar lead, which is an extension of the bus bar, is sometimes referred to as a “bus bar exit.” Whichever wiring configuration is used, there is a potential for shorting with a conductive spacer. As will be described in more detail below, one mode of addressing this potential problem of an electrical short between the spacer and the bus bar lead is by creating a small notch or “mouse hole” in the underside side of the spacer that contacts the lite in order to allow room for the bus bar lead (or wire) to pass between the lite and the spacer without contacting the spacer.

A second potential short or failure area depicted in FIG. **4** is illustrated by reference **Y**. In area **Y**, between the bus bar and the spacer, it is possible that the bus bar itself may contact the conductive spacer. Because the bus bar is a relatively long structure, oriented along one edge of the window, the bus bar could contact a corresponding point on the metal spacer anywhere along the length of the bus bar. Typically the bus bar is situated as close as possible to the spacer without touching it, in order to maximize viewable area of the window. Because of the tight tolerances employed in manufacturing an electrochromic device, it is possible that there will be some minor misalignment of the bus bar and/or the spacer resulting in contact in the area indicated by **Y**. The bus bar itself typically resides on an inactive area of the electrochromic device, for example, behind a laser scribe line, and the bus bar material used is often light in color. With this also in mind, the bus bar is typically placed very close to the edge of the window at the edge of the electrochromic device. As a consequence, it is typically placed very close to the spacer.

The third mode of potential shorting and failure is illustrated by reference **Z**. As shown, a contact can occur between the spacer and some amount of the transparent conductive electrode employed in the electrochromic device. While it is typical to remove some or all of the electrochromic device stack, for example, in an edge delete

## 11

process, it is not uncommon to have some small amount of an underlying conductive film such as ITO or TEC remain near the edge of the device on the window. As described above, the primary sealant, such as PIB or PVB, typically separates the metal spacer bar from the glass lite with the transparent conductive electrode. However, the primary sealant can deform under pressure and it is not uncommon for the sealant to be squeezed out of the seal area over time. As a consequence, there is a significant risk that the spacer will electrically contact some of the transparent conductive electrode and cause a short.

It should be understood that the design placement of the bus bar, the connectors/leads, the location of the conductive electrode layers, etc., are specified with very tight tolerances, e.g., on the order of about a few millimeters or less. It has been found in practice that the specification may not be met. Therefore, each of the three depicted modes of shorting failure represents a significant design challenge. The discussion herein describes certain embodiments that address one or more of these potential modes of failure. One of ordinary skill in the art would appreciate that, where useful, combinations of these embodiments are contemplated as individual embodiments herein. Certain embodiments are described in terms of an IGU; however, one embodiment is a spacer as described herein, or a sub-assembly of an IGU described herein.

FIG. 5A shows an example of a cross section, **500**, of an edge region of an IGU where the spacer of the IGU and the bus bar reside. As illustrated, a spacer, **510**, is sandwiched between two sheets of glass near the edge of the IGU. In a typical design, the glass interfaces directly with a primary seal material, **515**, (e.g., a thin elastomeric layer, such as PIB or PVB), which is in direct contact with spacer **510**. In some embodiments, spacer **510** may be metal spacer, such as a steel spacer or a stainless steel spacer, for example. This three-part interface (i.e., glass/primary seal material/spacer) exists on both a top piece of glass and a bottom piece of glass. Spacer **510** may have a hollow structure, as depicted in FIG. 5A. In some embodiments, the spacer may have a substantially rectangular cross section. At a minimum, spacers described herein have at least two surfaces, each substantially parallel to the lites of the IGU in which they are to be incorporated. The remaining cross section, e.g., surfaces of the spacer that face the interior space of the IGU and the exterior, secondary seal area, may have any number of contours, i.e., they need not be flat, but may be. In the example depicted in FIG. 5A, spacer **510** has two surfaces on each face that forms the primary seal, which are substantially parallel to the glass lites of the IGU (a raised surface on the left hand side of the spacer **510** and a depressed surface (notch **501**) on the right hand side of the spacer **510**). In some embodiments, the top and bottom outer corners of the spacer are beveled and/or rounded to produce a shallower angle in these areas. Rounding, beveling, or smoothing may be included to ensure there are no sharp edges that might enhance electrical shorting. An electrochromic device stack, **505**, is fabricated on the lower glass lite, as depicted. A bus bar, **520**, is located on electrochromic device stack **505** in order to make electrical contact with one of the electrodes of the device. In this example, bus bar **520** is between spacer **510** and the lower glass lite. This is accomplished by configuring one of the aforementioned surfaces below (see top surface of spacer **510**) or above (see bottom surface of spacer **510**) the other surface on the face of the spacer that forms the primary seal with the glass surface. This configuration of surfaces forms “notch” **501**;

## 12

see further description below. Primary seal material **515** serves as an insulating layer between bus bar **520** and spacer **510**.

There are two primary distinctions between a normal spacer design and spacer **510** shown in FIG. 5A. First, spacer **510** is relatively thicker (wider) in the direction parallel to the glass sheet (i.e., a larger footprint as would be typical from the view depicted in FIG. 3B, for example). A conventional metal spacer is approximately 6 millimeters in width. Spacer **510** is about two times to about two and one half times (about 2× to about 2.5×) that width. For example, spacer **510** may be about 10 millimeters to about 15 millimeters wide, about 13 millimeters to about 17 millimeters wide, or about 11 millimeters wide. This additional width may provide a greater margin of error in a sealing operation compared to a conventional spacer.

The second significant distinction of spacer **510** from a conventional spacer is in the use of recesses or notches **501** on the upper and lower inner corners of spacer **510**. In some embodiments, a spacer may include two notches, and in some embodiments, the spacer may include one notch. Two notches, e.g., as depicted in FIG. 5A, may be used for an IGU containing two electrochromic lites, or may be useful in fabricating IGUs with only one electrochromic light. When using a spacer with two notches in an IGU containing one electrochromic lite, there is no need for special placement of a single notch toward the electrochromic lite. In some embodiments, a recess or notch may extend from a corner of one side of the rectangular cross section of the spacer to a point along the one side of the rectangular cross section of the spacer. At least one notch provides an area for covering the bus bar formed on the glass surface and/or covering the bus bar formed on electrochromic device stack **505** formed on the glass surface. In some embodiments, the bus bar is about 2 millimeters to about 3 millimeters in width and about 0.01 millimeters to about 0.1 millimeter in height (thickness). The bus bar length depends on the window size. In some embodiments, a bus bar may have a length about the length of the electrochromic device. The added width, along with the “notched” profile of spacer **510** that accommodates the bus bar, creates a region of “encapsulation” whereby the bus bar is unlikely to contact the spacer at any point along the length of the bus bar, but is encapsulated in the primary sealant.

In some embodiments, the portion of the spacer’s face that does not include the notch (i.e., the outer portion of the spacer) is approximately the same width as a normal spacer employed in non-electrochromic IGU applications. As depicted in FIG. 5A, bus bar **520** is entirely covered by the spacer **510**. As a consequence, the bus bar is not visible to a user of the window.

In FIG. 5A, electrochromic device stack **505** extends underneath bus bar **520** and partially into the region formed by notch **501** in spacer **510**. As noted above, an electrochromic device stack typically includes a conductive electrode layer such as ITO or TEC. Electrochromic device stack **505** may be entirely removed from the edge of the glass surface by an edge deletion process, described above. However, the removal by edge deletion may not extend entirely up to the edge of the bus bar, as this would be unacceptable given normal process tolerances. Therefore, electrochromic device stack **505** may extend just slightly beyond bus bar **520**, e.g., while still residing in notch **501**.

Spacer **510**, which is wider than conventional spacers, as well as notches **501** in spacer **510**, provide additional space for primary seal material **515** (e.g., PIB). This feature, along with the notch or notches on the top and/or bottom inside

edges of the spacer, give spacer **510** various advantages that are particular to electrochromic devices incorporated in IGUs. For example, a wider primary seal area provides better containment of argon or other gas within the IGU interior as well as protection of the IGU from moisture and other gasses in the ambient environment. The sealing of the IGU secondary seal also may be improved and may provide better structural integrity than a conventional IGU design. Additionally, the IGU may color all the way to the edge defined by the interior perimeter of the spacer. With the bus bars hidden underneath the notch in the spacer, there will be no bright sight lines created either by the inactive area where the bus bar is placed or by the relatively lightly colored material used to fabricate the bus bar.

Still further, the disclosed embodiment will satisfy industry expectations for an IGU that contains a primary seal having a glass/primary seal material (e.g., PIB)/metal spacer construction. Additionally, because the electrochromic device may employ an edge deletion down to the level of the glass (or the diffusion barrier) and from the glass edge to an area where a notch of the bus bar will form a portion of the primary seal and thus provide more space between the bus bar and spacer, the likelihood of shorting between the electrochromic device electrode and the spacer is greatly reduced. FIG. **5B** shows cross-sections of other spacers, **540-575**, in accord with embodiments described herein, each spacer having at least one notch **501**.

As noted, embodiments described herein, including notched embodiments, may employ a channel or "mouse hole" under an edge of the spacer where a lead or a connector to the bus bar may run to allow connection to an outside power source (described further herein). One embodiment is the spacer as described in relation to FIGS. **5A** and **5B** including a channel on one or both faces of the spacer that form the primary seal with the lite or lites. As also noted, the bus bar lead is typically oriented substantially perpendicular to the line of the bus bar itself. It is typically made from the same material as the bus bar (e.g., silver, conductive ink, or other highly conductive material). The channel or mouse hole may be formed in a metal spacer, e.g., stainless steel, or be part of a connector key that joins two ends of a slotted, open, spacer. This is described in more detail below.

FIG. **6** shows two embodiments of connector keys. A connector key is typically used to join two ends of a spacer. As noted above, a spacer may be made from hollow metal rectangular pieces. One or more of these pieces are bent into an overall rectangular-shaped piece that forms the spacer. This rectangular-shaped spacer is sized and shaped to mate with the perimeter of the glass used to form an IGU. Two ends of the one or more pieces of tubular spacer material are joined by a connector key. For example, an end of the tubular spacer material may slide over a portion of a connector key, and the other end of the tubular spacer material may slide over another portion of the connector key. Alternatively, as depicted in FIG. **6**, the ends of the metal spacer slide into the connector key.

Each of the connector keys in FIG. **6** has been modified to accommodate a bus bar lead. In some embodiments, a metal spacer and a primary seal material form a barrier between an interior region of the window assembly and an exterior region of the window assembly. A lead or a wire passes from an electrode of an optically switchable device on the interior region of the window assembly, under a connector key, and to the exterior region of the window assembly. The connector key is not in electrical communication with the lead or the wire.

In embodiment **600**, a connector key, **605**, joins two ends, **620**, of the spacer. In some embodiments, the spacer may be a metal spacer, such as a steel spacer or a stainless steel spacer, for example. In some embodiments, the spacer may have a substantially rectangular cross section. In some embodiments, the spacer may be hollow. The two ends of the spacer, **607**, slide into the respective ends of connector key **605**. The connector key and spacer are configured so that when joined, the surfaces that are to come into contact with the glass are substantially co-planar. Connector key **605** has a middle section that is made from a metal, particularly a crimpable metal, such as steel or stainless steel, for example. The bottom portion of the middle region of connector key **605** is made from this crimpable metal and is in fact crimped to produce the channel **609** or mouse hole under which the bus bar lead passes. Of course, connector key **605** could be cast or machined to achieve the same result, but stamped or crimped metal is more economical.

In some embodiments, instead of a bus bar lead passing under channel **609**, wiring for an electrode may pass under channel **609**. For example, in some embodiments, the wire may be thinner than the thickness (i.e., height) of the channel. In some embodiments, when a thin wire is used, the thickness (i.e., height) of the channel may be reduced.

In embodiment **610**, a connector key, **615**, joins two ends, **620**, of the spacer. The two ends of the spacer, **617**, slide into the ends of connector key **615**. Connector key **615** is an electrically non-conductive or insulating material (e.g., a plastic). Connector key **615** may or may not have a channel or mouse hole cut into it. Typically, such a channel will be unnecessary because connector key **615** is a non-conductive or insulating material, thereby eliminating the possibility of a short between the connector key and the bus bar lead. Thus, the connector key and the lead will not be in electrical communication.

It should be noted that the connector key normally sits at a random location in the spacer. This is because the tubular metal pieces used to make the spacer typically come in standard or fixed lengths. These lengths may be used to construct a rectangular spacer of effectively arbitrary size, as dictated by the size of the window and the associated IGU. In accordance with the embodiments shown FIG. **6**, the spacer may be constructed in a manner in which the connector key lines up with at least one of the bus bar leads. In some embodiments, the spacer is designed so that two separate connector keys are specifically aligned to coincide with the position of the two bus bar leads at opposite sides of the electrochromic device. In some embodiments, one of the connector keys is forced into alignment on the spacer with the bus bar lead. In such embodiments, the opposite bus bar lead may pass through a channel created in the body of the tubular metal used to make the spacer. Such a channel may be created by, e.g., forming a dent or a crimp in the tubular metal piece at a location coinciding with the bus bar lead.

In some other embodiments, the spacer is constructed using conventional connector keys. The spacer may then be dented or crimped at the locations where the bus bar lead passes.

FIG. **7** shows an example of a detailed cross-sectional view of a crimped connector key aligned on a glass sheet with an electrochromic device fabricated thereon. Particularly, the detailed view, **700**, shows a channel (mouse hole), **705**, in the middle portion of a connector key, **710**, where a bus bar lead, **715**, on a glass lite, **720**, passes through the channel. Various sample dimensions are provided in FIG. **7**. It should be understood that these are only examples and that

15

many other dimensions may be appropriate. In some embodiments, bus bar lead **715** may have a height, **725**, of about 0.05 millimeters to about 0.1 millimeters. In some embodiments, channel **705** may have a height, **730**, of about 0.1 millimeters to about 1 millimeter. In some embodiments, channel **705** may have a width in connector key **710** of about 4.5 millimeters to about 10 millimeters. In some embodiments, a clearance, **735**, that may be desired on either side of bus bar **715** may be between about 1.5 and about 2.5 millimeters.

A crimping process that may be used to form a crimped metal connector key may have tolerances associated with the process. Therefore, the channel formed in a connector key may be specified to be somewhat larger than what is desired to account for the tolerances in the process.

In some embodiments, the channel for the bus bar lead is located as in the embodiment described with respect to FIGS. 6 and 7, but need only penetrate part way under the spacer because the bus bar resides midway underneath the spacer. In some embodiments, the bus bar lead channel resides on an outside edge of the spacer or on an outside edge of a corner of the spacer.

FIG. 8 is a schematic diagram of an insulated glass unit, **800**, including an electrochromic pane, **805**, and an associated wire assembly, **830**. IGU **800** includes electrochromic pane **805** which includes bus bars, **815**, which are in electrical communication with an EC device, **817** (for an exemplary cross-section see FIG. 2A). Electrochromic pane **805** is matched with another pane (not shown) and attached to the other pane with a separator, **820** (indicated by the dotted lines). The area of EC pane **805** outside of separator **820** is a secondary sealing area, while EC device lies within the perimeter of separator **820** (which forms the primary seal against the glass panes of the IGU). In the assembled IGU, the secondary sealing area is typically filled with a sealing compound to form a secondary seal. Wires, **822** and **823**, are connected to bus bars **815** and extend through IGU **800** from bus bars **815**, through or under spacer **820**, and within the secondary seal to a first connector, **825**. Wires **822** and **823** may be positioned such that they do not appear in the viewable region of the panes. For example, the wires may be enclosed in the sealing separator or the secondary seal as depicted. In some embodiments, and as depicted, first connector **825** may be housed substantially within the secondary seal. For example, first connector **825** may be surrounded by the secondary sealant on all sides except for the face of first connector **825** having two pads, **827**. The first connector may be housed substantially within the secondary seal in different manners. For example, in some embodiments, the first connector may be housed substantially within the secondary seal and be recessed relative to the edges of the glass panes. In some embodiments, the first connector may be housed substantially within the secondary seal and protrude beyond the edges of the glass panes. In other embodiments, first connector **825** may itself form part of the secondary seal, e.g., by sandwiching between the glass panes with sealant disposed between itself and the glass panes.

As noted above, first connector **825** includes two pads **827**. The two pads are exposed and provide electrical contact to wires **822** and **823**. In this example, first connector **825** further includes a ferromagnetic element, **829**. Wire assembly **830** includes a second connector, **835**, configured to mate with and provide electrical communication with pads **827**. Second connector **835** includes a surface having two pads, **840**, that provide electrical contact to wires, **845**, of the wire assembly. Second connector **835** further includes a

16

ferromagnetic element, **850**, configured to register and mate with ferromagnetic element **829** of the first connector.

Pads **840** of second connector **835** are configured or shaped for mechanical and electrical contact with pads **827** of first connector **825**. Further, at least one of ferromagnetic elements **829** or **850** of first connector **825** or second connector **835**, respectively, may be magnetized. With at least one of ferromagnetic elements **829** or **850** being magnetized, first connector **825** and second connector **835** may magnetically engage one another and provide electrical communication between their respective pads. When both ferromagnetic elements are magnetized, their polarity is opposite so as not to repel each other when registered. A distal end (not shown) of the wire assembly **830** may include terminals, sometimes provided in a plug or socket, that allow the wire assembly to be connected to a window controller. In one embodiment, a distal end of wire assembly **830** includes a floating connector.

In one embodiment, rather than a pad to pad contact (e.g., **827** to **840** as in FIG. 8) for the first and second connectors, a pad to spring-type pin configuration is used. That is, one connector has a pad electrical connection and the other connector has a corresponding spring-type pin, or “pogo pin”; the spring-type pin engages with the pad of the other connector in order to make the electrical connection. In one embodiment, where ferromagnetic elements are also included, the magnetic attraction between the ferromagnetic elements of the first and second connectors is sufficiently strong so as to at least partially compress the spring mechanism of the pogo pin so as to make a good electrical connection when engaged. In one embodiment, the pads and corresponding pogo pins are themselves the ferromagnetic elements.

In some embodiments, first connector **825**, second connector **835**, or the terminals or connector at the distal end of the wire assembly (e.g. a floating connector) may include a memory device and/or an integrated circuit device. The memory device and/or integrated circuit device may store information for identifying and/or controlling electrochromic pane **805** in IGU **800**. For example, the device may contain a voltage and current algorithm or voltage and current operating instructions for transitioning electrochromic pane **805** from a colored state to a bleached state or vice versa. The algorithm or operating instructions may be specified for the size, shape, and thickness of electrochromic pane **805**, for example. As another example, the device may contain information that identifies the shape or size of electrochromic pane **805** to a window controller such that electrochromic pane **805** may operate in an effective manner. As yet another example, the device may contain information specifying a maximum electric signal and a minimum electric signal that may be applied to electrochromic pane **805** by a window controller. Specifying maximum and minimum electric signals that may be applied to the electrochromic pane may help in preventing damage to the electrochromic pane.

In another example, the memory and/or integrated circuit device may contain cycling data for the EC device to which it is connected. In certain embodiments, the memory and/or integrated circuit device includes part of the control circuitry for the one or more EC devices of the IGU. In one embodiment, individually, the memory and/or integrated circuit device may contain information and/or logic to allow identification of the EC device architecture, glazing size, etc., as described above, e.g., during a testing or initial programming phase when in communication with a controller and/or programming device. In one embodiment, collectively, the

memory and/or integrated circuit device may include at least part of the controller function of the IGU for an external device intended as a control interface of the installed IGU.

Further, in embodiments in which first connector **825** includes the memory device and/or the integrated circuit device, damage to the electrochromic pane may be prevented because the device is part of IGU **800**. Having the maximum and minimum electric signals that may be applied to electrochromic pane **805** stored on a device included in first connector **825** means that this information will always be associated with IGU **800**. In one example, a wiring assembly as described herein includes five wires and associated contacts; two of the wires are for delivering power to the electrodes of an EC device, and the remaining three wires are for data communication to the memory and/or integrated circuit device.

Wire assembly **830** described with respect to FIG. **8** may be easily attachable to, and detachable from, IGU **800**. Wire assembly **830** also may aid in the fabrication and handling of an IGU because wire assembly **830** is not permanently attached to the IGU and will therefore not interfere with any fabrication processes. This may lower the manufacturing costs for an IGU. Further, as noted above, in some IGUs that include wire assemblies that are permanently attached to the IGU, if the wire assembly becomes damaged and/or separated from the IGU, the IGU may need to be disassembled to reconnect the wire assembly or the IGU may need to be replaced. With a detachable wire assembly, an IGU may be installed and then the wire assembly attached, possibly precluding any damage to the wire assembly. If a wire assembly is damaged, it can also be easily replaced because it is modular.

Additionally, the detachable wire assembly allows for the replacement or the upgrade of the wire assembly during the installed life of the associated IGU. For example, if the wire assembly includes a memory chip and/or a controller chip that becomes obsolete or otherwise needs replacing, a new version of the assembly with a new chip can be installed without interfering with the physical structure of the IGU to which it is to be associated. Further, different buildings may employ different controllers and/or connectors that each require their own special wire assembly connector (each of which, for example, may have a distinct mechanical connector design, electrical requirements, logic characteristics, etc.). Additionally, if a wire assembly wears out or becomes damaged during the installed life of the IGU, the wire assembly can be replaced without replacing the entire IGU.

In certain embodiments, each of the first and second connectors includes at least two ferromagnetic elements. In a specific embodiment, each of the first and second connectors includes two ferromagnetic elements. A “double” magnetic contact allows for more secure connections. Magnets such as neodymium based magnets, e.g., comprising  $\text{Nd}_2\text{Fe}_{14}\text{B}$ , are well suited for this purpose because of their relatively strong magnetic fields as compared to their size. As described above, the two ferromagnetic elements may be part of the electrical pads, or not. In one embodiment, the two ferromagnetic elements in each of the first and the second connectors are themselves magnets, where the poles of the magnets of each of the first and second connectors that are proximate when the connectors are registered, are opposite so that the respective magnets in each of the first and second connectors attract each other.

When installing an IGU in some framing systems, e.g., a window unit or curtain wall where multiple IGUs are to be installed in proximity, it is useful to have flexibility in where the electrical connection is made to each IGU. This is

especially true since typically the EC glazing of the IGUs is always placed on the outside of the installation, facing the external environment of the installation. Given this configuration, having the connectors in the same position within the secondary seal of the IGUs of the installation requires much more wiring to the controller. However, for example, if the electrical connectors in the IGUs (as described herein) can be positioned more proximate to each other, then less wiring is needed from the IGU to the framing system in which the IGUs are installed. Thus, in some embodiments, IGU **800** may include more than one first connector **825**, that is, redundant connectors are installed. For example, an IGU **800** might include not only a first connector **825** at the upper right hand side, but also another connector at the lower left hand side or at the lower right hand side or the upper left hand side or in the top or bottom portion of the IGU. In this example, the connectors are all within the secondary seal. The exact position on each edge is not critical; the key is having more than one connector that feeds the same EC device so that when installing the IGU, there is flexibility in where to attach the external connector to the IGU. When an IGU having multiple connectors is mounted in a frame holding 2, 4, 6, or more similar IGUs, for example, having multiple first connectors included within each IGU, allows for more convenient routing of the wires (e.g., wires **845** as in FIG. **8** associated with each wire assembly **830**) in the frame due to the flexibility of having multiple redundant first connectors to which the second connector may be coupled. In one embodiment, the IGU has two first connectors, in another embodiment three first connectors, in yet another embodiment four first connectors. In certain embodiments there may be five or six first connectors. Although the number of connectors may impact production costs, this factor may be more than compensated for by the higher degree of flexibility in installation, e.g., in an expensive and sophisticated curtain wall installation where volume to accommodate wiring is often limited and installing multiple first connectors during fabrication is relatively easy.

In some embodiments, the IGU **800**, may include two electrochromic panes. In these embodiments, the first connector may include four pads (or corresponding pad to pin contacts) to provide contacts to the bus bars of each of the electrochromic panes (i.e., each electrochromic pane would include at least two bus bars). Additional pads for control and communication with the electrochromic device and/or onboard controller may also be included, e.g., four pads for bus bar wiring and three additional pads for communication purposes. Likewise, second connector **835** would include four pads to provide electrical contact to wires of the wire assembly. In other embodiments, each EC pane may have its own first connector, or two or more redundant first connectors. Further description of an IGU that includes two or more electrochromic panes is given in U.S. Pat. No. 8,270,059, titled “MULTI-PANE ELECTROCHROMIC WINDOWS,” filed Aug. 5, 2010, which is herein incorporated by reference.

FIG. **9** shows a schematic diagram of an insulated glass unit including an electrochromic pane and an associated ribbon cable. The IGU **900** includes an electrochromic pane, **905**, having bus bars, **915**, which are in electrical communication with an EC device, **917** (for an exemplary cross-section see FIG. **2A**). Electrochromic pane **905** is matched with another pane (not shown) and attached to the other pane with a separator, **920** (indicated by the dotted lines). Outside of separator **920** is a secondary sealing area. Wires **922** and **923** are connected to bus bars **915** and extend through IGU **900** to a connector, **902**. Connector **902** is capable of being

19

connected to a ribbon cable, **905**. Ribbon cable **905** may be connected to a window controller, **910**. In some embodiments, the ribbon cable may be a cable with many conducting wires running parallel to each other on the same plane. The ends of the ribbon cable may include connectors for connecting to connector **902** and to window controller **910**.

In some embodiments, connector **902** may be similar to connector **825** of FIG. 8 (i.e., connector **902** may include one or more ferromagnetic elements) and ribbon cable **905** also may include one or more ferromagnetic elements for engaging connector **902** with ribbon cable **905**. Other mechanisms also may be used to engage connector **902** with ribbon cable **905**.

In some embodiments, connector **902** may include a memory device and/or an integrated circuit device. Ribbon cable **905** may include more wires or electrically conductive paths than the two paths needed to electrically connect to bus bars **915** of electrochromic pane **905** so that the window controller can communicate with the memory device and/or the integrated circuit device. In some embodiments, the ribbon cable may have electrically conductive paths for controlling more than one electrochromic pane, as described below. Ribbon cables have advantages including the capability of having multiple parallel wires for carrying power, communication signals etc., in a thin, flexible format.

In some embodiments, IGU **900** includes two or more electrochromic panes. Connector **902** may be capable of providing electrical contact to the bus bars of each of the electrochromic panes (i.e., each electrochromic pane would include at least two bus bars). Thus, in the example of an IGU having two electrochromic panes, the ribbon cable may include four conducting wires running parallel to each other on the same plane for powering the electrochromic panes.

As described above, where a connector is configured within an IGU may be important when considering where to attach wiring connectors to the IGU. Flexibility in attaching wiring assemblies to an IGU can significantly reduce wiring complexity and length, and thus save considerable time and money, both for fabricators and installers. One embodiment is an electrical connection system including a track, the track including two or more rails that provide electrical communication, via wiring and bus bars, to the electrodes of an EC device of the IGU. The track is, e.g., embedded in the secondary sealing area of the IGU. An associated connector engages the rails and thereby makes electrical connection to the rails. A non-limiting example of the track described above is described in relation to FIGS. 10A and 10B.

FIGS. 10A and 10B depict aspects of an insulated glass unit, **1000**, including a track, **1025**, and an associated connector, **1045**. In this example, track **1025** is also a spacer that may serve as both a secondary sealing element and an electrical connector for an electrochromic pane of the IGU, although the sealing function is not necessary. FIG. 10A is a schematic diagram of IGU **1000** including an electrochromic pane, **1010**. Electrochromic pane **1010** includes bus bars, **1015**. Electrochromic pane **1010** is matched with another pane (not shown) and together the panes sandwich a separator, **1020**, with a primary seal being formed between separator **1020** and the inside surfaces of the panes along with an adhesive. In this example, track **1025** is used to form a secondary seal, similar to the primary seal formed between the glass panes and separator **1020**, with an adhesive between the inner surfaces of the glass panes and track **1025**. Thus, in this example, the primary and secondary seals are formed in the same fashion. Track **1025** adds additional rigidity and strength to the IGU structure as well as a sealing function. In certain embodiments, the track is embedded in

20

a traditional secondary sealant without also serving as a sealing element itself; in these embodiments, the track needs to traverse the entire perimeter of the IGU. In some embodiments, the track serves as the spacer, configured where a conventional spacer would be, along with a primary sealant between track surfaces and interior surfaces of the panes. In these embodiments, there is only one spacer, the track, which serves as a wired spacer and primary sealing element.

Track **1025** also includes rails, in this example in the form of wires, **1030** and **1035**, which provide electrical communication to bus bars **1015** via wires, **1017**. That is, wires **1017** connect bus bars **1015** to wires **1030** and **1035** in track **1025**. Track **1025** is described further in relation to FIG. 10B. FIG. 10A, in the bottom portion, shows only track **1025**. Included is an expanded view of a corner portion of track **1025**, showing detail of a channel in which reside wires **1030** and **1035**. In this example, wires **1030** and **1035** run all the way around the channel of track **1025**. In other embodiments, wires **1030** and **1035** run only in a portion (e.g., one side, two sides, or three sides) of track **1025**. The rails of the track may be other than wires, so long as they are conductive material, although wires are convenient because they are common and easily configured in a track, e.g., track **1025** may be an extruded plastic material into which wires may be molded, or the wires may be inserted into the track after extrusion or molding.

FIG. 10B shows a cross-section D, as indicated in FIG. 10A, of track **1025** showing the details of wires **1030** and **1035** and finer detail of track **1025**. Track **1025** may be a non-conducting material, such as an extruded polymer, for example, that holds wires **1030** and **1035** in place. In one example, track **1025** is made of an extruded plastic channeled material. The channeled material is cut and formed, e.g., ultrasonically welded, to form a unitary body as depicted. As shown in FIG. 10B, wires **1030** and **1035** are located within recesses in track **1025** and, in this example, each wire is insulated on three sides. As mentioned, the wires may be inserted into the recesses after the track is fabricated. Track **1025** includes two slots or channels, **1040** and **1050**. Slot **1050** allows for electrical connection of an electrical connector, e.g., from a window controller to IGU **1000**. Wires **1017** from bus bars **1015** of the electrochromic pane **1010** may be housed in slot **1040**. Wires **1017** may pass through the material of track **1025**, e.g., passing from slot **1040** through an aperture and into slot **1050**, so that each of the wires **1017** may contact its respective wire **1030** or **1035**. The aperture through which wires **1017** pass may be sealed prior to fabrication of the IGU, or during fabrication of the IGU, e.g., using adhesive sealant residing in slot **1040**. In one example, a sealant is applied to the gap between the wire and the aperture. Slot **1040** also may allow for additional wires and/or interconnections to be made to the IGU.

In one example, track **1025** is assembled with wires **1017** being attached to rails **1030** and **1035** prior to being attached to bus bars **1015**. That is, one embodiment is a track including rails and wires connected to the rails, the wires passing through the track such that the track, once sandwiched between two panes of glass, optionally with an adhesive sealant, forms a hermetic seal. In one such embodiment, assembly of the IGU includes 1) attaching wires **1017** to the bus bars, and 2) then simultaneously forming the primary and the secondary seal using separator **1020** and track **1025**. Electrical connections may be made to electrochromic pane **1010** with connector **1045**. Connector **1045** may include a non-conducting body **1047** with two conducting tabs, **1055** and **1060**. In this example, each of the two conducting tabs **1055** and **1060** is connected to a single

## 21

incoming wire, **1075**. Each of the single wires may be coupled to a connector, as described herein, and ultimately connected to a window controller. In this example, to establish electrical connection, connector **1045** is inserted into slot **1050** and then twisted about 90 degrees so that each of the conducting tabs, **1055** and **1060**, makes contact with a wire, **1035** and **1030**, respectively. In some embodiments, to ensure that a correct wire is in contact with the correct tab, tabs **1055** and **1060** and the recesses housing wires **1030** and **1035** are asymmetrical. As shown in FIG. 10B, tab **1060** is thicker than tab **1055**. Further, the recess housing wire **1030** is smaller than the recess housing wire **1035**. Connector **1045** enters slot **1050** and then, by virtue of the configuration of the recesses and tabs, the connector can be turned only so that tab **1060** contacts wire **1030** and tab **1055** contacts wire **1035**. Varying tab thickness and recess size is one way to help to insure that the connector **1045** is in contact with the correct wires, but other mechanisms to achieve this are also possible. In embodiments where the track is the only spacer, e.g., configured as a conventional spacer, connector **1045** may or may not be configured to penetrate the secondary sealant in order to establish contact with the rails. Where the connector **1045** is not configured to penetrate the secondary sealant to contact the rails on track **1025**, portions of the track **1025** may be exposed along one or more sides of the IGU so that connector **1045** can establish contact directly, without having to penetrate the secondary sealant when inserted into the track. In the latter embodiment, secondary sealant is optionally applied to seal any open spaces remaining in the secondary seal, including those around installed connector **1045**.

One of ordinary skill in the art would appreciate that other configurations of track **1025** are possible. For example, in one embodiment, track **1025** is a linear track that is inserted along one side of the IGU in the secondary sealing area. Depending upon the need, one, two, three or four such linear tracks, each along an independent side of the IGU, are installed in the IGU. In another embodiment, track **1025** is U-shaped, so that when installed in the secondary sealing area of the IGU, it allows electrical connection via at least three sides of the IGU.

FIGS. 11A and 11B show examples of diagrams of an IGU with a two-part spacer. The IGU, **1100**, shown in FIG. 11A includes electrochromic lite, **305**, as depicted in FIG. 3A. Electrochromic lite **305** has bus bars, **310**, fabricated on an electrochromic device (not depicted). In some embodiments, a bus bar may have a length about the length of the electrochromic device. IGU **1100** includes a two-part spacer, including an interior electrically non-conductive or insulating portion or spacer, **1105**, and an exterior metal portion or spacer, **1110**. In some embodiments, non-conductive or insulating spacer **1105** and metal spacer **1110** may have substantially rectangular cross sections. Non-conductive or insulating spacer **1105** may be made from a polymeric material, a plastic material, or a foam material, for example. In some embodiments, the non-conductive or insulating spacer **1105** is a Triseal spacer available from Edgetech USA (of Cambridge, Ohio). Metal spacer **1110** may be made from steel or stainless steel, for example. Metal spacer **1110** may be a conventional spacer. One or more channels may be included in the non-conductive or insulating spacer **1105** and in the metal spacer **1110**, for example to house the electrical connection the bus bars **310**.

The non-conductive or insulating spacer **1105** may include a notch or recess, **1115**, to accommodate bus bar **310**. The notch may form a channel in a side of the non-conductive or insulating spacer. An electrochromic

## 22

device stack (not shown) is fabricated on glass lite **1130**. Bus bar **310** located on the electrochromic device stack makes electrical contact with one of the electrodes of the device. With non-conductive or insulating spacer **1105** situated on top of bus bar **310**, the risk of a short between bus bar **310** and metal spacer **1110** is reduced. An edge delete operation may still be performed on glass lite **1130** down to the glass so that metal spacer **1110** does not contact the conductive electrodes of the electrochromic device stack. The IGU primary seal is comprised of interfaces between glass lites **1130** and **1135** and primary seal material (e.g., PIB), **1140**, and between primary seal material **1140** and non-conductive or insulating spacer **1105** and metal spacer **1110**.

In some embodiments, metal spacer **1110** may have about the same width as a conventional spacer; i.e., about 6 millimeters wide. In some embodiments, metal spacer **1110** may have a smaller width than a conventional spacer. For example, metal spacer **1110** may be about 4 millimeters wide. Regardless of whether metal spacer **1110** has the same width or has a smaller width than a conventional spacer, the overall design of metal spacer **1110** may be similar in many regards to a conventional spacer.

A channel in one or more of the spacers may be used to house leads to the bus bars. In one embodiment, metal spacer **1110** includes a raised (i.e., less tall) portion compared to non-conductive or insulating spacer **1105**. The raised portion of metal spacer **1110** effectively forms the channel or mouse hole under which the bus bar leads passes to avoid electrical contact with metal spacer **1110**.

One advantage of the embodiments shown in FIGS. 11A and 11B is the incorporation of a relatively wide spacer including non-conductive or insulating spacer **1105** and metal spacer **1110**. The wide spacer provides additional area for the primary seal as compared to a conventional metal spacer. As explained above, this additional seal area, which includes primary seal material, can better protect the IGU interior from moisture and other ambient gasses, as well as prevent argon or other gas in the interior of the IGU from escaping.

In some embodiments, non-conductive or insulating spacer **1105** includes a desiccant. In conventional IGUs, a desiccant is provided in the interior of the metal spacer. Therefore, the metal spacer maintains its integrity in the IGU. For example, the metal spacer cannot include any holes to the outside environment which would permit direct contact with the desiccant when a desiccant is provided in the interior of the metal spacer. Typically, there are one or more holes used to introduce desiccant into the spacer, but these are sealed after the desiccant is introduced.

The metal spacer may include holes to accommodate the wiring to connect the electrochromic device bus bars with a power source. The wires can be fed through the interior of the metal spacer. These holes may be sealed around the wires to secure the desiccant's function in the metal spacer. FIG. 11A shows an example of a diagram of an IGU in which wiring for an electrochromic device is inside the metal spacer. As shown in FIG. 11A, IGU **1150** includes electrochromic lite **305** with bus bars **310** fabricated on an electrochromic device (not depicted). IGU **1150** includes a two-part spacer, including an interior non-conductive or insulating spacer **1105** and an exterior metal spacer **1110**. Wires **1155** are in electrical contact with leads from bus bars **310**. The wires are shown as being in the interior of metal spacer **1110** and exit from metal spacer **1110**, providing electrical communication from the interior of IGU **1150** to the exterior of IGU **1150**. FIG. 11B shows an alternative

23

embodiment, **1160**, where the wires run in the secondary seal area, external to both spacers.

In some embodiments, the non-conductive or insulating spacer and the metal spacer may form a barrier between an exterior region and an interior region of the IGU. The metal spacer may include two holes, with a wire in electrical contact or communication with an electrode of an electrochromic device passing through the first hole, though the hollow metal spacer, and out of the second hole. The wire may provide electrical communication from the exterior region of the IGU to the interior region of the IGU.

The manufacturing advantage of the embodiment shown in FIG. **11A** is that a spacer can be fabricated from the metal rectangular tubular portion in which the wires have already been fed. These metal rectangular tubular portions are normally provided as linear sections which are subsequently bent into the rectangular shape of the spacer. If the wiring is provided in the linear sections prior to bending, the difficulty of feeding a metal wire through bent portions of the metal rectangular tubes is avoided. During manufacturing, and after the wiring is connected to the bus bar through the metal portion of the spacer, the holes in the metal tubular portion through which the wires are fed can be plugged with a sealant, such as PIB, for example.

In some other embodiments, the entire spacer may be made from a material that is electrically non-conductive (i.e., electrically resistive or electrically insulating) and therefore does not exhibit any of the three modes of shorting illustrated in FIG. **4**. Examples of such materials that may be used for a spacer include plastic materials, polymeric material, foam materials, and hard rubber materials. As an example, a foam spacer similar to a Triseal spacer (Cambridge, Ohio), as mentioned above, may be used. When an electrically resistive spacer is used, it may be wider such that it occupies about 5 millimeters to about 10 millimeters of the outer edge of the IGU. This embodiment does not include a metal spacer, and the non-conductive material may be sufficiently rigid and strong to serve the role of a spacer. In some embodiments, the non-conductive spacer includes a desiccant and/or wiring, as described and illustrated in the context of FIGS. **11A** and **11B**.

In some embodiments, a metal spacer has an electrically non-conductive or insulating outer coating (i.e., an electrically resistive outer coating) but may otherwise be similar in design and structure to a conventional spacer. In some embodiments, the metal spacer may have a substantially rectangular cross section. In some embodiments, the non-conductive outer coating may be on at least one side of the substantially rectangular cross section of the metal spacer. In some embodiments, the non-conductive outer coating may be on all four sides of the substantially rectangular cross section of the metal spacer. In some embodiments, the metal spacer may include a channel configured to accommodate an electrode of an optically switchable device on one of the glass lites.

For example, one embodiment is metal spacer coated on one or more sides with an insulating (non-electrically conductive) coating. The insulating coating may be a paint or polymeric material such as polytetrafluoroethylene or similar material. The spacer is used along with a primary sealant material as described herein. The spacer may include a channel and/or a notch as described herein. In one embodiment, the spacer includes one or more connector keys as described herein. In one embodiment, the spacer is coated on all sides; in another embodiment, the spacer is coated on only the sides proximate the bus bar and/or bus bar lead.

24

Although the foregoing embodiments have been described in some detail to facilitate understanding, the described embodiments are to be considered illustrative and not limiting. It will be apparent to one of ordinary skill in the art that certain changes and modifications can be practiced within the scope of the appended claims.

What is claimed is:

**1.** A connector key for joining a pair of open ends of one or more spacers in an insulated glass unit (IGU), the connector key comprising:

two ends, each of which is configured to mate with a separate one of the pair of open ends of the one or more spacers;

surfaces for mating with lites of the IGU, the lites of the IGU being substantially parallel; and

a channel configured to accommodate an electrical connection, wherein the channel passes at least partially through the connector key, and wherein the channel has a width of between about 4.5-10 mm, the width being measured in a direction between the two ends of the connector key that mate with the pair of open ends of the one or more spacers.

**2.** The connector key of claim **1**, wherein the connector key has a substantially rectangular cross section.

**3.** The connector key of claim **1**, wherein the ends of the connector key are configured to slide over or into the pair of open ends of the one or more spacers.

**4.** The connector key of claim **1**, wherein the channel is positioned on one of the surfaces for mating with lites of the IGU.

**5.** The connector key of claim **1**, wherein the connector key comprises a metal portion, and wherein the channel comprises a crimped region of the metal portion of the connector key.

**6.** The connector key of claim **1** that comprises a material that is electrically non-conductive.

**7.** The connector key of claim **6**, wherein the connector key comprises a plastic.

**8.** The connector key of claim **1**, wherein the channel has a height between about 0.1-1 mm, the height being measured in a direction perpendicular to the lites of the IGU.

**9.** The connector key of claim **1**, wherein the channel passes all the way through the connector key.

**10.** The connector key of claim **1**, wherein the channel passes only partway through the connector key.

**11.** The connector key of claim **10**, wherein the channel is on one of the surfaces for mating with the lites of the IGU.

**12.** An insulated glass unit (IGU) comprising:

a first substantially transparent substrate having an electrochromic device disposed thereon;

a second substantially transparent substrate positioned substantially parallel to the first substantially transparent substrate;

one or more spacers positioned between the first and second substantially transparent substrates, each of the one or more spacers having surfaces that mate with the first and second substantially transparent substrates;

a connector key joining a pair of ends of the one or more spacers, the connector key comprising:

two ends, each of which mates with one of the ends of the one or more spacers,

surfaces for mating with the substantially transparent substrates, and

a channel configured to accommodate an electrical connection, wherein the channel passes at least partially through the connector key; and

## 25

a sealing material bonding the first and second substantially transparent substrates to the one or more spacers and to the connector key, thereby forming a sealed interior region between the first and second substantially transparent substrates and interior of the one or more spacers and connector key. 5

13. The IGU of claim 12, further comprising the electrical connection passing at least partially through the connector key.

14. The IGU of claim 13, wherein a single spacer and a single connector key are provided, wherein the electrical connection provides power to a first bus bar of the electrochromic device. 10

15. The IGU of claim 14, wherein the single spacer comprises a crimped portion configured to accommodate a second electrical connection, wherein the second electrical connection provides power to a second bus bar of the electrochromic device. 15

16. The IGU of claim 13, wherein the channel passes all the way through the connector key. 20

17. The IGU of claim 12, wherein two or more connector keys are provided to join ends of two or more spacers.

18. The IGU of claim 17, wherein the two or more connector keys include a first connector key and a second connector key, wherein a first electrical connection passes through the channel in the first connector key to provide 25

## 26

power to a first bus bar of the electrochromic device, and wherein a second electrical connection passes through the second connector key to provide power to a second bus bar of the electrochromic device.

19. The IGU of claim 12, wherein a bus bar of the electrochromic device is positioned at least partially under at least one spacer of the one or more spacers and at least partially under the connector key, and wherein the channel passes only partway through the connector key, the electrical connection providing power to the bus bar.

20. A connector key for joining a pair of open ends of one or more spacers in an insulated glass unit (IGU), the connector key comprising:

two ends, each of which is configured to mate with a separate one of the pair of open ends of the one or more spacers;

surfaces for mating with lites of the IGU, the lites of the IGU being substantially parallel; and

a channel configured to accommodate an electrical connection, wherein the channel passes at least partially through the connector key, wherein the channel has a height between about 0.1-1 mm, the height being measured in a direction perpendicular to the lites of the IGU.

\* \* \* \* \*