



US010658482B2

(12) **United States Patent**
Cheng et al.

(10) **Patent No.:** **US 10,658,482 B2**
(45) **Date of Patent:** **May 19, 2020**

(54) **PLATE DESIGN TO DECREASE NOISE IN SEMICONDUCTOR DEVICES**

(71) Applicant: **Taiwan Semiconductor Manufacturing Co., Ltd.**, Hsin-Chu (TW)

(72) Inventors: **Chih-Chang Cheng**, Hsinchu (TW); **Fu-Yu Chu**, Hsinchu (TW); **Ming-Ta Lei**, Hsin-Chu (TW); **Ruey-Hsin Liu**, Hsin-Chu (TW); **Shih-Fen Huang**, Jhubei (TW)

(73) Assignee: **Taiwan Semiconductor Manufacturing Co., Ltd.**, Hsin-Chu (TW)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 149 days.

(21) Appl. No.: **15/800,474**

(22) Filed: **Nov. 1, 2017**

(65) **Prior Publication Data**

US 2019/0131414 A1 May 2, 2019

(51) **Int. Cl.**

H01L 29/423 (2006.01)
H01L 29/78 (2006.01)
H01L 21/265 (2006.01)
H01L 21/28 (2006.01)
H01L 29/06 (2006.01)
H01L 29/08 (2006.01)
H01L 29/49 (2006.01)

(52) **U.S. Cl.**

CPC **H01L 29/4238** (2013.01); **H01L 21/26513** (2013.01); **H01L 21/28123** (2013.01); **H01L 29/0653** (2013.01); **H01L 29/0847** (2013.01); **H01L 29/78** (2013.01); **H01L 29/4916** (2013.01)

(58) **Field of Classification Search**

CPC combination set(s) only.
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,716,768 B2 5/2014 Lyu et al.
9,190,536 B1 11/2015 Chan et al.
10,164,033 B2 12/2018 Yeo et al.

(Continued)

OTHER PUBLICATIONS

U.S. Appl. No. 16/363,114, filed Mar. 25, 2019.

(Continued)



Primary Examiner — Timor Karimy

(74) *Attorney, Agent, or Firm* — Eschweiler & Potashnik, LLC

(57) **ABSTRACT**

A semiconductor device and method for forming the semiconductor device are provided. In some embodiments, a semiconductor substrate comprises a device region. An isolation structure extends laterally in a closed path to demarcate the device region. A first source/drain region and a second source/drain region are in the device region and laterally spaced. A sidewall of the first source/drain region directly contacts the isolation structure at a first isolation structure sidewall, and remaining sidewalls of the first source/drain region are spaced from the isolation structure. A selectively-conductive channel is in the device region, and extends laterally from the first source/drain region to the second source/drain region. A plate comprises a central portion and a first peripheral portion. The central portion overlies the selectively-conductive channel, and the first peripheral portion protrudes from the central portion towards the first isolation structure sidewall.

20 Claims, 24 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

2006/0192258 A1 8/2006 Tsuchiya et al.
2009/0224335 A1 9/2009 Chang
2010/0315115 A1 12/2010 Lee et al.
2012/0074498 A1 3/2012 Chuang
2013/0154023 A1 6/2013 Yoshida et al.
2013/0334614 A1 12/2013 Liaw
2014/0042506 A1 2/2014 Ramberg et al.
2015/0200249 A1 7/2015 Kundu
2017/0235795 A1 8/2017 Gilder
2017/0294356 A1 10/2017 Yeh et al.
2019/0088780 A1 3/2019 Choi et al.

OTHER PUBLICATIONS

Non-Final Office Action dated Jul. 10, 2018 for U.S. Appl. No. 15/688,018.

Notice of Allowance dated Nov. 3, 2017 for U.S. Appl. No. 15/257,291.

Non-Final Office Action dated Aug. 20, 2019 in connection with U.S. Appl. 15/688,018.

Final Office Action dated Jan. 30, 2019 for U.S. Appl. No. 15/688,018. Carmonai, M, Hubert, L. Lopezi, F. Julieni, J., Ogieri, D. Goguenheim, and L. Beauvisagei Study of gate contact over active area, 2014 29th Symposium on Microelectronics Technology and Devices (SBMicro), Aracaju, 2014, pp. 1-4. (Year: 2014).

Kwon, et al. "Effects of Shallow Trench Isolation on Low Frequency Noise Characteristics of Source-Follower Transistors in CMOS Image Sensors." Solid-State Electronics 119 (2016) 29-32, published Mar. 1, 2016.

Chan, et al. "STI Effect on Flicker Noise in 0.13- μ m RF NMOS." Proceeding of the 36th European IEEE Solid-State Device Research Conference, 2006. ESSDERC 2006. Published Feb. 12, 2007.

U.S. Appl. No. 15/257,291, filed Sep. 6, 2016.

U.S. Appl. No. 15/688,018, filed Aug. 28, 2017.

Non-Final Office Action dated Jun. 2, 2017 for U.S. Appl. No. 15/257,291.

Notice of Allowance dated Feb. 13, 2020 in connection with U.S. Appl. No. 15/688,018.

Notice of Allowance dated Mar. 9, 2020 in connection with U.S. Appl. No. 16/363,114.




Fig. 2B




Fig. 2C




Fig. 2A




Fig. 6B




Fig. 6C




Fig. 6D




Fig. 6A




Fig. 8A




Fig. 8B





Fig. 8C

Fig. 8D




Fig. 9A




Fig. 9B




Fig. 9C




Fig. 9D




Fig. 10A




Fig. 10B




Fig. 10C




Fig. 10D




Fig. 11A




Fig. 11B




Fig. 11C




Fig. 11D




Fig. 12A




Fig. 12B




Fig. 12C




Fig. 12D




Fig. 13A




Fig. 13B




Fig. 13C




Fig. 13D




Fig. 14A




Fig. 14B




Fig. 14C




Fig. 14D




Fig. 15A




Fig. 15B




Fig. 15C




Fig. 15D




Fig. 16A




Fig. 16B




Fig. 16C




Fig. 16D




Fig. 17A




Fig. 17B




Fig. 17C




Fig. 17D

1800




Fig. 18

PLATE DESIGN TO DECREASE NOISE IN SEMICONDUCTOR DEVICES

BACKGROUND

Semiconductor devices are electronic components that exploit electronic properties of semiconductor materials to affect electrons or their associated fields. A widely used type of semiconductor device is a field-effect transistor (FET). A FET comprises a pair of source/drain regions, a selectively-conductive channel, and a gate electrode. FETs are versatile devices that may be used for, among other things, switches, amplifiers, and memory. Examples of FETs include metal-oxide-semiconductor field-effect transistors (MOSFETs) and junction gate field-effect transistors (JFETs).

BRIEF DESCRIPTION OF THE DRAWINGS

Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

FIGS. 1A-1D illustrate various perspective views of some embodiments of a field-effect transistor (FET) with low flicker and random telegraph noise.

FIGS. 2A-2C and 3A-3C illustrate various views of various more detailed embodiments of the FET of FIGS. 1A-1C in which the FET is a metal-oxide-semiconductor FET (MOSFET).

FIGS. 4A-4D through 7A-7D illustrate various views of various more detailed embodiments of the FET of FIGS. 1A-1C in which the FET is a junction gate FET (JFET).

FIGS. 8A-8D through 17A-17D illustrate a series of views of some embodiments of a method for forming a FET with low flicker and random telegraph noise.

FIG. 18 illustrates a flowchart of some embodiments of the method of FIGS. 8A-8D through 17A-17D.

DETAILED DESCRIPTION

The present disclosure will now be described with reference to the drawings wherein like reference numerals are used to refer to like elements throughout, and wherein the illustrated structures are not necessarily drawn to scale. It will be appreciated that this detailed description and the corresponding figures do not limit the scope of the present disclosure in any way, and that the detailed description and figures merely provide a few examples to illustrate some ways in which the inventive concepts can manifest themselves.

The present disclosure provides many different embodiments, or examples, for implementing different features of this disclosure. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is

for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

Some field-effect transistors (FETs) comprise a semiconductor substrate and a shallow trench isolation (STI) structure. The STI structure is over and sunken into the semiconductor substrate to demarcate a device region of the semiconductor substrate. Further, the FET comprises a pair of source/drain regions, a selectively-conductive channel, a gate dielectric layer, and a gate electrode. The source/drain regions are laterally spaced, and are over and recessed into the device region of the semiconductor substrate. The selectively-conductive channel is in the device region of the semiconductor substrate and extends from one of the source/drain regions to another one of the source/drain regions. The gate dielectric layer overlies the selectively-conductive channel, and the gate electrode overlies the gate dielectric layer.

A challenge with the above FETs is flicker noise and random telegraph noise (RTN). One source of flicker and random telegraph noise is defect states at an interface between the gate dielectric layer and the device region of the semiconductor substrate. As current flows through the selectively-conductive channel, carriers are trapped and de-trapped by the defect states, thereby generating the flicker and random telegraph noise. The trapping and de-trapping occurs at a central portion of the selectively-conductive channel that interfaces with the gate dielectric layer. Further, the trapping and de-trapping occurs at a pair of STI corners at peripheral portions of the selectively-conductive channel. The STI corners are top cross-sectional corners of the semiconductor substrate that interface with the gate dielectric layer and the STI structure in the device region of the semiconductor substrate. Further, the STI corners are respectively on opposite sides of the selectively-conductive channel, and each extends laterally along a length of the selectively-conductive channel from one of the source/drain regions to another one of the source/drain regions. The STI corners have a high amount of defect states because the STI corners have high mechanical stress and are not defined by perfectly planar surfaces. Further, electric fields are strong at the STI corners because the STI corners have small radii of curvature. This, in turn, leads to high trapping and high de-trapping at the STI corners.

A partial solution to the challenge is to move the source/drain regions from the STI corners using a photoresist mask. For example, a photoresist mask may be formed on the device region of the semiconductor with a pair of source/drain openings that overlap the device region and that are spaced from the STI corners. Ion implantation may then be performed into the device region of semiconductor substrate, through the photoresist mask, to form the source/drain regions spaced from the STI corners. By spacing the source/drain regions from the STI corners, current flow along the STI corners is reduced, thereby reducing flicker and random telegraph noise generated at the STI corners. However, the

partial solution does not address flicker and random telegraph noise generated by current flow along the central portion of the selectively-conductive channel. Further, using the photoresist mask to move the source/drain regions leads to poor performance uniformity during bulk manufacture, and leads to challenges during silicide formation. For example, it may be challenging to prevent silicide from forming on the device region, directly between the source/drains and the STI corners.

In view of the foregoing, various embodiments of the present application are directed toward a FET comprising a plate design that reduces noise, as well as method for forming the FET. In some embodiments, the FET comprises a semiconductor substrate, an isolation structure, a first source/drain region, a second source/drain region, a selectively-conductive channel, and a plate. The semiconductor substrate comprises a device region. The isolation structure extends laterally in a closed path to demarcate the device region. The first source/drain region and the second source/drain region are in the device region and are laterally spaced. A sidewall of the first source/drain region directly contacts the isolation structure at a first isolation structure sidewall, and remaining sidewalls of the first source/drain region are spaced from the isolation structure. A sidewall of the second source/drain region directly contacts the isolation structure at a second isolation structure sidewall, and remaining sidewalls of the second source/drain region are spaced from the isolation structure. The selectively-conductive channel is in the device region, and extends laterally from the first source/drain region to the second source/drain region. The plate comprises a central portion and a first peripheral portion. The central portion overlies the selectively-conductive channel, and the first peripheral portion protrudes from the central portion towards the first isolation structure sidewall.

During formation of the FET, ion implantation may be performed into the semiconductor substrate with the plate in place, such that the plate serves as a mask and the source/drain regions are self-aligned to the plate. Therefore, the planar top layout of the plate facilitates formation of the source/drain regions with the remaining sidewalls spaced from the isolation structure. As a result of the spacing, the source/drain regions are spaced from defect states at STI corners extending from the first isolation structure sidewall to the second isolation structure sidewall. This reduces source-drain current floating along the STI corners, which reduces carriers becoming trapped and de-trapped by defect states at the STI corners. Accordingly, flicker and random telegraph noise is reduced.

In some embodiments, the plate further comprises doped regions varying the work function of the plate, thereby pushing source-drain current deeper into the device region of the semiconductor substrate. Accordingly, less current flows along the top surface of the device region of the semiconductor substrate, thereby reducing charge carriers becoming trapped and de-trapped by defect states at a top surface. This, in turn, reduces flicker and random telegraph noise generated by the defect states.

With reference to FIGS. 1A-1D, various perspective views 100A-100C of some embodiments of a FET with low flicker and random telegraph noise is provided. FIG. 1A is a deconstructed perspective view 100A of the FET, FIG. 1B is another deconstructed perspective view 100B of the FET, FIG. 1C is a constructed perspective view 100C of the FET, and FIG. 1D is a constructed perspective view 110D of an alternative embodiment of the FET. FIG. 1A is “deconstructed” in that a plate dielectric layer 102 (also called a

gate dielectric layer in MOSFETs) and a plate 104 (also called a gate in MOSFETs) are separated from a semiconductor substrate 106 and an isolation structure 108 on which the plate dielectric layer 102 and the plate 104 normally rest. FIG. 1B is “deconstructed” in the same manner as FIG. 1A, except the isolation structure 108 is further separated from the semiconductor substrate 106 on which the isolation structure 108 normally rests. The FET may be, for example, a metal-oxide-semiconductor field-effect transistor (MOSFET) or a junction gate field-effect transistor (JFET).

As illustrated, the isolation structure 108 is over and extends into the semiconductor substrate 106 to delineate a device region 112 of the semiconductor substrate 106. In some embodiments, the isolation structure 108 has a generally ring-shaped layout, and/or defines a device-region opening 108_o (see FIG. 1B) filled by the device region 112. A “generally” ring-shaped layout is similar to a ring-shaped layout, except it is not limited to circular inner and outer sidewalls. For example, a generally ring-shaped layout may be a square ring-shaped layout. The isolation structure 108 may be, for example, a STI region or a deep trench isolation (DTI) region. The semiconductor substrate 106 may be, for example, a bulk semiconductor substrate, such as a bulk silicon substrate of monocrystalline silicon.

A pair of source/drain regions 114 is over and in the device region 112, and the source/drain regions 114 are laterally spaced. Further, the source/drain regions 114 are respectively on a first end of the device region 112 and a second end of the device region 112 opposite the first end. A selectively-conductive channel 116 is defined by a bulk of the device region 112, laterally between the source/drain regions 114. Further, the selectively-conductive channel 116 extends from one of the source/drain regions 114 to another one of the source/drain regions 114, along a top surface of the device region 112. In some embodiments where the FET is a MOSFET, the source/drain regions 114 and the bulk of the device region 112 are doped regions of the semiconductor substrate 106 having opposite doping types. For example, the device region 112 may be p-type and the source/drain regions 114 may be n-type, or vice versa. In some embodiments where the FET is a JFET, the source/drain regions 114 have the same doping type as the bulk of the device region 112, and further have a higher doping concentration than the bulk of the device region 112. Further, the source/drain regions 114 are each spaced from and laterally between two isolation corners 106_c.

The isolation corners 106_c are top cross-sectional corners of the semiconductor substrate 106 that are in the device region 112 and that border the isolation structure 108. Further, the isolation corners 106_c are line shaped and extend laterally in parallel with the selectively-conductive channel 116, from the first end of the device region 112 to the second end of the device region 112. In some embodiments, the isolation corners 106_c have the same lengths or have substantially the same lengths. Further yet, the isolation corners 106_c are on opposite sides of the device region 112, such that the source/drain regions 114 are each directly between the isolation corners 106_c. In some embodiments, the isolation corners 106_c are each at a location at which a top surface edge of the device region 112 meets a sidewall surface edge of the device region 112, where the sidewall surface edge of the sidewall surface edge borders and/or adjoins the isolation structure 108. Further, in some embodiments, the isolation corners 106_c directly contact the plate dielectric layer 102.

By spacing the source/drain regions 114 from the isolation corners 106_c, the flicker and random telegraph noise of the

FET is reduced. Namely, the spacing increases the resistance from the source/drain regions **114** to the isolation corners **106c**, such that a low amount of source-drain current flows through the isolation corners **106c**. This, in turn, reduces carriers being trapped and de-trapped at the isolation corners **106c**, thereby resulting in low flicker and random telegraph noise. As noted above, the isolation corners **106c** have a high amount of defect states because the isolation corners **106c** have high mechanical stress and are not defined by perfectly planar surfaces. Further, as noted above, the isolation corners **106c** have small radiuses of curvature that promote high electric fields.

The plate dielectric layer **102** and the plate **104** are stacked, such that the plate **104** overlies the plate dielectric layer **102**. Further, the plate dielectric layer **102** and the plate **104** overlie the device region **112** of the semiconductor substrate **106**, as well as the isolation corners **106c**. The plate **104** and, in some embodiments, the plate dielectric layer **102** comprise peripheral plate portions **117p** that protrude from a central plate portion **117c**. The peripheral plate portions **117p** respectively cover the isolation corners **106c**, and extend laterally in parallel with the isolation corners **106c** and the selectively-conductive channel **116**. The central plate portion **117c** covers the selectively-conductive channel **116**, and extends laterally from one of the peripheral plate portions **117p** to another one of the peripheral plate portions **117p**.

In some embodiments, the plate dielectric layer **102** and the plate **104** completely cover the isolation corners **106c**. Further, in some embodiments, the plate dielectric layer **102** and the plate **104** have the same layout, and/or sidewalls of the plate dielectric layer **102** are aligned to sidewalls of the plate **104**. Further yet, in some embodiments, the plate dielectric layer **102** and/or the plate **104** each have an H-shaped top layout. Further yet, the plate dielectric layer **102** and/or the plate **104** have a width W that is substantially perpendicular to the isolation corners **106c**, and have a length L that is substantially parallel to the isolation corners **106c**. The plate dielectric layer **102** may be, for example, silicon dioxide, silicon nitride, a high κ dielectric, some other dielectric, or any combination of the foregoing. As used herein, a high κ dielectric layer is a dielectric with a dielectric constant κ greater than about 3.9, 5, 10, 15, or 20. The plate **104** may be, for example, doped polysilicon, metal, or some other conductive material.

In some embodiments, the plate **104** comprises a first doped region **104a**, a second doped region **104b**, and a third doped region **104c**. The first doped region **104a** and the third doped region **104c** have the same doping type and may, for example, also have the same doping type as the source/drain regions **114**. The first doped region **104a** and the third doped region **104c** may, for example, be n-type or p-type. The second doped region **104b** is disposed between the first doped region **104a** and the third doped region **104c** and comprises a second doping type opposite the first doping type. For example, in an n-channel MOSFET, the first doped region **104a** and the third doped region **104c** comprise n-type doped polysilicon and the second doped region **104b** comprises p-type doped polysilicon. As another example, in a p-channel MOSFET, the first doped region **104a** and the third doped region **104c** comprise p-type doped polysilicon and the second doped region **104b** comprises n-type doped polysilicon.

The second doped region **104b** is within the central plate portion **117c**, and extends laterally along the width W of the plate **104**. In some embodiments, the second doped region **104b** is limited to the central plate portion **117c**. For

example, the second doped region **104b** may extend laterally along the width W of the plate **104** from one of the peripheral plate portions **117p** to another one of the peripheral plate portions **117p**, and may be sandwiched between the peripheral plate portions **117p**. In other embodiments, the second doped region **104b** is in both the central plate portion **117c** and the peripheral plate portions **117p**. For example, the second doped region **104b** may extend laterally along the width W of the plate **104** from a sidewall of the plate **104** to another sidewall of the plate **104**. In some embodiments, the second doped region **104b** is spaced from sidewalls of the plate **104** overlying the selectively-conductive channel **116**, and/or has a planar top layout that is line shaped.

The first doped region **104a** and the third doped region **104c** are within the peripheral plate portions **117p**. In some embodiments, the first and third doped regions **104a**, **104c** are limited to the peripheral plate portions **117p**. In other embodiments, the first and third doped regions **104a**, **104c** are also in the central plate portion **117c**. For example, the first doped region **104a** and the third doped region **104c** may each have a U-shaped top layout spanning the peripheral plate portions **117p** and the central plate portion **117c**. In some embodiments, the first doped region **104a** and the third doped region **104c** are separated by the second doped region **104b**. As illustrated in FIG. 1D, in other embodiments, the first doped region **104a** and the third doped region **104c** directly abut in the peripheral plate portions **117p**, and/or collectively extend laterally in a closed path to completely enclose the second doped region **104b**.

By doping the first doped region **104a** and the third doped region **104c** with the same doping type as the source/drain regions **114** and the second doped region **104b** with a different doping type, the flicker and random telegraph noise of the FET may be kept low. Namely, the arrangement and doping types of the first, second, and third doped regions **104a**, **104b**, **104c** alters the work function of the plate **104** to drive source-drain current flow deeper into the semiconductor substrate **106**, thereby moving the current flow away from defect states at an interface between the device region **112** of the semiconductor substrate **106** and the plate dielectric layer **102**. This, in turn, reduces trapping and de-trapping of carriers at the defect states, which leads to low flicker and random telegraph noise.

A pair of lateral plate openings **118** is defined by the plate **104** and, in some embodiments, the plate dielectric layer **102**. The lateral plate openings **118** extend vertically through the plate **104**, from top to bottom, and extend laterally into sides of the plate **104**. The lateral plate openings **118** are each laterally between and spaced from the isolation corners **106c**. In some embodiments, the lateral plate openings **118** are at a width-wise center of the plate **104** (i.e., at a center of the width W of the plate **104**). Further, the lateral plate openings **118** are respectively on opposite sides of the plate **104** and respectively overlie the source/drain regions **114**. In some embodiments, the lateral plate openings **118** are laterally spaced along the length L of the plate **104**. Further, in some embodiments, the lateral plate openings **118** each have a side that is open, and three sides defined by the plate **104** and, in some embodiments, the plate dielectric layer **102**.

In some embodiments, by having the lateral plate openings **118** in the plate **104**, and the peripheral plate portions **117p** covering the isolation corners **106c**, the plate **104** may be employed as a mask to form the source/drain regions **114** spaced from the isolation corners **106c** in a planar top layout of the FET. This, in turn, allows a low cost, low complexity process for reducing flicker and random telegraph noise

since the same photomask used to pattern the plate **104** may also be used to reduce flicker noise.

With reference to FIGS. **2A-2C** and **3A-3C**, various views of various more detailed embodiments of the FET of FIGS. **1A-1C** are provided in which the FET is a MOSFET. Figures having a suffix of "A" (e.g., FIG. **2A**) are top layout views of some embodiments of the MOSFET. Figures having a suffix of "B" (e.g., FIG. **3B**) are cross-sectional views of some embodiments of the MOSFET, taken along line A-A' in the figures having a suffix of "A." Figures having a suffix of "C" (e.g., FIG. **2C**) are cross-sectional views of some embodiments of the MOSFET, taken along line B-B' in the figures having a suffix of "A."

As illustrated by the views **200A-200C** of FIGS. **2A-2C**, a plate **104** overlaps the isolation corners **106c** and is laterally between a pair of source/drain regions **114**. A spacer **202** extends laterally along a boundary of the plate **104** to surround the plate **104**. Further, the source/drain regions **114** are laterally spaced in a first direction, and are laterally spaced from the isolation corners **106c** in a second direction perpendicular to or substantially perpendicular to the first direction. In some embodiments, the source/drain regions **114** are spaced from each of the isolation corners **106c** by an amount *S* in the second direction (see FIG. **2B**). As noted above, the FET has reduced flicker and random telegraph noise due to this spacing. Further, in some embodiments, the plate **104** has a planar top layout that is H-shaped, and/or has at more than four sidewalls (e.g., 12 sidewalls). Further yet, in some embodiments, the plate **104** has a pair of peripheral plate portions **117p** and a central plate portion **117c**. The peripheral plate portions **117p** respectively cover the isolation corners **106c**, and the central plate portion **117c** bridges the peripheral plate portions **117p**.

A first doped region **104a**, a second doped region **104b**, and a third doped region **104c** are within the central plate portion **117c** and the peripheral plate portions **117p**. The second doped region **104b** is disposed between the first doped region **104a** and the third doped region **104c** and comprises a doping type opposite that of the first doped region **104a** and the third doped region **104c**. Further, the second doped region **104b** extends laterally along a width *W* of the plate **104** (see FIG. **2A**) from a first sidewall of the plate **104** to a second sidewall of the plate **104**. The first doped region **104a** and the third doped region **104c** are respectively on opposite sides of the second doped region **104b** and are laterally spaced by the second doped region **104b** along a length *L* of the plate **104** (see FIG. **2A**). Further, the first doped region **104a** and the third doped region **104c** each have a U-shaped planar top layout that wraps around a respective one of the source/drain regions **114** and that spaces the second doped region **104b** from the respective one of the source/drain regions **114**. Further yet, the first doped region **104a** and the third doped region **104c** have the same doping type and may, for example, also have the same doping type as the source/drain regions **114**. As noted above, the FET has reduced flicker and random telegraph noise due to the arrangement and doping types of the first, second, and third doped regions **104a**, **104b**, **104c** altering the work function of the plate **104** to drive current flow to a deeper portion of the semiconductor substrate **106**.

As illustrated by the views **300A-300C** of FIGS. **3A-3C**, a plate **302** overlaps the isolation corners **106c** and is laterally between a pair of source/drain regions **114**. The plate **302** is undoped or comprises a single doping type, such as, for example, n-type or p-type. In some embodiments where the FET is an n-channel MOSFET, the plate **302** comprises p-type doped polysilicon. In other embodiments,

where the FET is a p-channel MOSFET, the plate **302** comprises n-type doped polysilicon. Further, the plate **302** may, for example, be as the plate **104** of FIGS. **2A-2C** is described, except that the plate lacks the first, second, and third doped regions **104a**, **104b**, **104c**.

With reference to FIGS. **4A-4D** through **7A-7D**, various views of various more detailed embodiments of the FET of FIGS. **1A-1C** are provided in which the FET is a JFET. Figures having a suffix of "A" (e.g., FIG. **5A**) are top layout views of some embodiments of the JFET. Figures having a suffix of "B" (e.g., FIG. **6B**) are cross-sectional views of some embodiments of the JFET, taken along line A-A' in the figures having a suffix of "A." Figures having a suffix of "C" (e.g., FIG. **4C**) are cross-sectional views of some embodiments of the JFET, taken along line B-B' in the figures having a suffix of "A." Figures having a suffix of "D" (e.g., FIG. **5D**) are cross-sectional views of some embodiments of the JFET, taken along line C-C' in the figures having a suffix of "A."

As illustrated by the views **400A-400D** of FIGS. **4A-4D**, a plate **402** overlaps the isolation corners **106c** and is laterally between a pair of source/drain regions **114**. The plate **402** may be, for example, doped polysilicon, metal, or some other conductive material. The source/drain regions **114** are laterally spaced in a first direction, and are laterally spaced from and between the isolation corners **106c** in a second direction perpendicular to or substantially perpendicular to the first direction. As noted above, the FET has reduced flicker and random telegraph noise due to this spacing. In some embodiments, the source/drain regions **114** have the same doping type, but a higher doping concentration, than a bulk of the device region **112**. A gate region **404** is over and in the device region **112**, and is laterally between the source/drain regions **114**. Further, the gate region **404** is spaced from each of the source/drain regions **114** in the first direction. In other embodiments, the gate region **404** is not spaced from each of the source/drain regions **114** in the first direction. In some embodiments, a first side of the gate region **404** abuts the selectively-conductive channel **116** (See FIGS. **1A-1D** and FIG. **4C**), and a second side opposite the first side abuts the isolation structure **108** at one of the isolation corners **106c**. The gate region **404** has an opposite doping type as the source/drain regions **114** and, in some embodiments, has an opposite doping type as the bulk of the device region **112**. For example, the source/drain regions **114** may be n-type and the gate region **404** may be p-type, or vice versa.

The plate **402** comprises peripheral plate portions **117p** that respectively cover the isolation corners **106c**, and a central plate portion **117c** that bridges the peripheral plate portions **117p**. In some embodiments, the plate **402** has a concave polygonal layout comprising at least sixteen sides. Further, the plate **402** comprises a first doped region **104a**, a second doped region **104b**, and a third doped region **104c**. The second doped region **104b** is disposed within the central plate portion **117c**, and in some embodiments, the second doped region **104b** extends laterally along the width *W* of the plate **402**, into the peripheral plate portions **117p**, to sidewalls of the plate **402**. In some embodiments, the second doped region **104b** separates the first doped region **104a** and the third doped region **104c** from the gate region **404**. The second doped region **104b** may, for example, have the same doping type as the gate region **404**, and/or the first and third doped regions **104a**, **104c** may, for example, have an opposite doping type as the gate region **404**. As noted above, the FET has reduced flicker and random telegraph noise due to the arrangement

and doping types of the first, second, and third doped regions **104a**, **104b**, **104c** altering the work function of the plate **402** to drive current flow into a deeper portion of the selectively-conductive channel **116** (see, FIGS. **1A-1D** and FIG. **4C**).

A lateral gate opening **406** is defined by the plate **402** and, in some embodiments, the plate dielectric layer **102**. The lateral gate opening **406** extends vertically through the plate **402**, from top to bottom, and extends laterally into a side of the plate **402**. The lateral gate opening **406** is laterally spaced between the source/drain regions **114** and borders one of the isolation corners **106c**. In some embodiments, the lateral gate opening **406** is at a length-wise center of the plate **402** (i.e., at a center of the length *L* of the plate **402**). Further, the lateral gate opening **406** overlies the gate region **404**. In some embodiments, the lateral gate opening **406** has a side that is open, and three sides defined by the plate **402** and, in some embodiments, the plate dielectric layer **102**.

As illustrated by the views **500A-500D** of FIGS. **5A-5D**, a plate **502** overlaps the isolation corners **106c** and is laterally between a pair of source/drain regions **114**. The source/drain regions **114** are laterally spaced in a first direction, and the gate region **404** is laterally between and spaced from each source/drain region **114** in the first direction. The plate **502** is undoped or comprises a single doping type, such as, for example, n-type or p-type. In some embodiments, the plate **502** comprises doped polysilicon with the same doping type as the gate region **404**.

As illustrated by the views **600A-600D** of FIGS. **6A-6D**, a plate **602** overlaps the isolation corners **106c** and is laterally between a pair of source/drain regions **114**. The plate **402** may be, for example, doped polysilicon, metal, or some other conductive material. The source/drain regions **114** are laterally spaced in a first direction, and are laterally spaced between the isolation corners **106c** in a second direction perpendicular to or substantially perpendicular to the first direction. As noted above, the FET has reduced flicker and random telegraph noise due to the spacing between the isolation corners **106c** and the source/drain regions **114**. In some embodiments, the source/drain regions **114** have the same doping type, but a higher doping concentration, than a bulk of the device region **112**. A pair of gate regions **604** is over and in the device region **112**, and the gate regions **604** are laterally between a pair of source/drain regions **114**. Further, the gate regions **604** are each spaced from the source/drain region **114** in the first direction, and are laterally spaced from each other in the second direction. In some embodiments, each of the gate regions **604** has a first side abutting the selectively-conductive channel **116** (See FIGS. **1A-1C** and FIG. **6C**), and a second side opposite the first side abutting the isolation structure **108** at a respective one of the isolation corners **106c**. The gate regions **404** have the same doping type. Further, the gate regions **404** have an opposite doping type as the source/drain regions **114** and, in some embodiments, have an opposite doping type as the bulk of the device region **112**.

The plate **602** comprises peripheral plate portions **117p** that respectively cover the isolation corners **106c**, and a central plate portion **117c** that bridges the peripheral plate portions **117p**. In some embodiments, the plate **602** has a polygonal-shaped layout comprising at least twenty sides. Further, the plate **602** comprises a first doped region **104a**, a second doped region **104b**, and a third doped region **104c**. The second doped region **104b** is disposed within the central plate portion **117c** and extends laterally along the width *W* of the plate **602**, into the peripheral plate portions **117p**, to sidewalls of the plate **602**. In some embodiments, the second doped region **104b** separates the first doped region **104a** and

the third doped region **104c** from each of the gate regions **604**. The second doped region **104b** may, for example, have the same doping type as the gate regions **404**, and/or the first and third doped regions **104a**, **104c** may, for example, have an opposite doping type as the gate regions **404**. As noted above, the FET has reduced flicker and random telegraph noise due to the arrangement and doping types of the first, second, and third doped regions **104a**, **104b**, **104c** altering the work function of the plate **602** to drive current flow to a deeper portion of the selectively-conductive channel **116**.

A pair of lateral gate openings **606** is defined by the plate **602** and, in some embodiments, the plate dielectric layer **102** (See FIGS. **6B-6D**). The lateral gate openings **606** extend vertically through the plate **602**, from top to bottom, and extend laterally into sides of the plate **602**. The lateral gate openings **606** are each laterally spaced between the source/drain regions **114**. In some embodiments, the lateral gate openings **606** are at a length-wise center of the plate **602** (i.e., at a center of the length *L* of the plate **602**). Further, the lateral gate openings **606** are respectively on opposite sides of the plate **602** and respectively overlie the gate regions **604**. In some embodiments, the lateral gate openings **606** are laterally spaced along the width *W* of the plate **602**. Further, in some embodiments, the lateral gate openings **606** each have a side that is open, and three sides defined by the plate **602** and, in some embodiments, the plate dielectric layer **102**.

As illustrated by the views **700A-700D** of FIGS. **7A-7D**, a plate **702** overlaps the isolation corners **106c** and is laterally between a pair of source/drain regions **114**. The source/drain regions **114** are laterally spaced in a first direction, and the gate regions **604** are laterally spaced in a second direction orthogonal or substantially orthogonal to the first direction. Further, each of the gate regions **604** are laterally spaced from the source/drain regions **114** in the first direction. The plate **702** is undoped or comprises a single doping type, such as, for example, n-type or p-type. In some embodiments, the plate **702** comprises doped polysilicon with the same doping type as the gate regions **404**.

With reference to FIGS. **8A-8D** through **17A-17D**, a series of views **800A-800D** through **1700A-1700D** of some embodiments of a method for manufacturing a FET with reduced flicker and random telegraph noise is provided. Figures having a suffix of "A" (e.g., FIG. **8A**) are top views of the FET under manufacture. Figures having a suffix of "B" (e.g., FIG. **9B**) are cross-sectional views of the FET manufacture, taken along line A-A' in the figures having a suffix of "A". Figures having a suffix of "C" (e.g., FIG. **10C**) are cross-sectional views of the FET under manufacture, taken along line B-B' in the figures having a suffix of "A". Figures having a suffix of "D" (e.g., FIG. **11D**) are cross-sectional views of the FET under manufacture, taken along line C-C' in the figures having a suffix of "A". The FET may, for example, be the FET of FIGS. **4A-4D**.

As illustrated by the views **800A-800D** of FIGS. **8A-8D**, an isolation structure **108** is formed over the semiconductor substrate **106**, sunken into a top of the semiconductor substrate **106**. Further, the isolation structure **108** is formed demarcating a device region **112** of the semiconductor substrate **106**. In some embodiments, the device region **112** of the semiconductor substrate **106** has a polygonal layout, and/or the isolation structure **108** has a polygonal ring-shaped layout. The isolation structure **108** may be, for example, an STI or DTI region, and/or the semiconductor substrate **106** may be, for example, a bulk substrate of monocrystalline or polycrystalline silicon or some other type of semiconductor substrate.

11

In some embodiments, a process for forming the isolation structure **108** comprises performing an etch into the semiconductor substrate **106** to form a trench in the semiconductor substrate **106**, and subsequently filling the trench with a dielectric material. The trench may, for example, be formed with the desired layout of the isolation structure, and/or the dielectric material may be, for example, silicon dioxide.

As illustrated by the views **900A-900D** of FIGS. **9A-9D**, in some embodiments, a well **902** is formed in the device region **112** of the semiconductor substrate **106**. The well **902** is a region of the semiconductor substrate **106** having an n-type doping or a p-type doping. Further, in some embodiments, the well **902** has a doping type opposite that of adjoining regions of the semiconductor substrate **106**, or the adjoining regions of the semiconductor substrate **106** are intrinsic. The well **902** may, for example, be formed by ion implantation.

As illustrated by the views **1000A-1000D** of FIGS. **10A-10D**, a dielectric layer **1002** and a conductive layer **1004** are formed on the isolation structure **108** and the device region **112** of the semiconductor substrate **106**, such that the conductive layer **1004** overlies the dielectric layer **1002**. The dielectric layer **1002** may, for example, be silicon dioxide, a high κ dielectric, or some other dielectric, and/or the conductive layer **1004** may be, for example, doped polysilicon, metal, or some other conductive. In other embodiments, the conductive layer **1004** is polysilicon that undergoes a subsequent doping process by, for example, ion implantation.

In some embodiments, a process for forming the dielectric layer **1002** and the conductive layer **1004** comprises depositing or growing the dielectric layer **1002** on the isolation structure **108** and the device region **112** of the semiconductor substrate **106**, and subsequently depositing or growing the conductive layer **1004** on the dielectric layer **1002**. The dielectric layer **1002** may, for example, be deposited or grown by thermal oxidation, chemical or physical vapor deposition, sputtering, or some other deposition or growth process. The conductive layer **1004** may, for example, be deposited or grown by chemical or physical vapor deposition, sputtering, electrochemical plating, electroless plating, or some other deposition or growth process.

As illustrated by the views **1100A-1100D** of FIGS. **11A-11D**, the conductive layer **1004** (see FIGS. **10A-10D**) and the dielectric layer **1002** (see FIGS. **10A-10D**) are patterned respectively into a plate **402** and a plate dielectric layer **102**. The plate **402** and the plate dielectric layer **102** are stacked on the isolation structure **108** and the device region **112** of the semiconductor substrate **106**, such that plate **402** overlies the plate dielectric layer **102**. Further, the plate **402** and the plate dielectric layer **102** overlap a pair of isolation corners **106c** of the semiconductor substrate **106**. The isolation corners **106c** are top cross-sectional corners of the semiconductor substrate **106** that border the isolation structure **108** in the device region **112** and that adjoin the plate dielectric layer **102**. Further, the isolation corners **106c** are line shaped and extend laterally in parallel in a first direction from a first end of the device region **112** to a second end of the device region **112** opposite the first end. The plate **402** and the plate dielectric layer **102** define a pair of lateral plate openings **118** respectively on the first and second ends of the device region **112**. Further, the lateral plate openings **118** are each laterally spaced between the isolation corners **106c** in the second direction. Further, in some embodiments, the plate **402** and the plate dielectric layer **102** define a lateral gate opening **406** that is laterally spaced between the lateral plate openings **118** in the first direction and that borders one of the

12

isolation corners **106c**. In further embodiments, the lateral gate opening **406** is paired with another lateral gate opening on an opposite side of the plate **104**. See, for example, FIGS. **6A-6D**.

In some embodiments, the plate **402** and the plate dielectric layer **102** have a polygonal-shaped layout comprising sixteen sides. In other embodiments, the polygonal shaped-layout has more (or less) than sixteen sides. Further, in some embodiments, the plate **402** and the plate dielectric layer **102** have a plurality of peripheral plate portions **117p** and a central plate portion **117c**. The peripheral plate portions **117p** protrude from the central plate portion **117c**. In some embodiments, a first one of the peripheral plate portions **117p** extends laterally in the first direction, from the first end of the device region **112** to the second end of the device region **112**. A second one of the peripheral plate portions **117p** extends laterally in the first direction, from the first end of the device region **112** to a first side of the lateral gate opening **406**. A third one of the peripheral plate portions **117p** extends laterally in the first direction, from a second side of the lateral gate opening **406** opposite the first side to the second end of the device region **112**. Further, the peripheral plate portions **117p** respectively cover the isolation corners **106c**. The central plate portion **117c** is between the peripheral plate portions **117p**, and interconnects the peripheral plate portions **117p**.

In some embodiments, a process for patterning the conductive layer **1004** and the dielectric layer **1002** into the plate **402** and the plate dielectric layer **102** comprises forming a patterned photoresist layer (not shown) on the conductive layer **1004**. The patterned photoresist layer may, for example, be formed by a spin on process. The patterned photoresist layer may, for example, be patterned with a layout of the plate **402** and may, for example, be patterned using photolithography. Further, in some embodiments, the process comprises performing an etch into the conductive layer **1004** and the dielectric layer **1002** with the patterned photoresist layer in place, and subsequently stripping the patterned photoresist layer.

As illustrated by the views **1200A-1200D** of FIGS. **12A-12D**, in some embodiments, a pair of lightly-doped source/drain extensions **1202** is formed in the device region **112** of the semiconductor substrate **106**. The lightly-doped source/drain extensions **1202** are respectively on opposite sides of the device region **112** of the semiconductor substrate **106**, and respectively underlie the lateral plate openings **118** in the plate dielectric layer **102** and the plate **402**. Further, the lightly-doped source/drain extensions **1202** are laterally spaced from one another in a first direction, and are laterally spaced from the isolation corners **106c** in a second direction transverse (e.g., perpendicular or substantially perpendicular) to the first direction. In some embodiments (e.g., where the FET is a MOSFET), the lightly-doped source/drain extensions **1202** may, for example, be doped regions of the semiconductor substrate **106** with an opposite doping type as the well **902**. In other embodiments (e.g., where the FET is a JFET), the lightly-doped source/drain extensions **1202** may, for example, be doped regions of the semiconductor substrate **106** with the same doping type as the well **902**, but a different doping concentration as the well **902**. In yet other embodiments, the lightly-doped source/drain extension **1202** are not formed. In some embodiments, the lightly-doped source/drain extensions **1202** may, for example, be formed by ion implantation, and/or may, for example, be formed using the plate **402** as a mask.

In some embodiments, a lightly-doped gate extension **1204** is also formed in the device region **112** of the semi-

conductor substrate **106**. The lightly-doped gate extension **1204** underlies the lateral gate opening **406** in the plate dielectric layer **102** and the plate **402**, and further has a single sidewall adjoining the isolation structure **108** at one of the isolation corners **106c**. In some embodiments, the lightly-doped gate extension **1204** is paired with another lightly-doped gate extension **1204** on an opposite side of the plate **104** and underlying another lateral gate opening **606**. See, for example, FIGS. **6A-6D**. The lightly-doped gate extension **1204** may, for example, be a doped region of the semiconductor substrate **106** with a different doping type as the well **902**. In some embodiments, the lightly-doped gate extension **1204** is formed by ion implantation, and/or formed using the plate **402** as a mask. In some embodiments, when forming both the lightly-doped source/drain extensions **1202** and the lightly-doped gate extension **1204**, a photoresist mask is employed to cover the lightly-doped source/drain extensions **1202** while forming the lightly-doped gate extension **1204** by ion implantation process, or vice versa.

As illustrated by the views **1300A-1300D** of FIGS. **13A-13D**, a spacer **202** is formed on sidewalls of the plate **402** and the plate dielectric layer **102**. Further, in some embodiments, the spacer **202** is formed completely enclosing the plate **402** and the plate dielectric layer **102**. The spacer **202** may, for example, be silicon nitride, silicon dioxide, some other dielectric, or a combination of the foregoing.

In some embodiments, a process for forming the spacer **202** comprises depositing or growing a spacer layer covering and conformally lining the structure in FIGS. **12A-12D**. The spacer layer may, for example, be deposited or grown by chemical or physical vapor deposition, sputtering, or some other deposition or growth process. Further, in some embodiments, the process comprises performing an etch back into the spacer layer to remove horizontal segments of the spacer layer without removing vertical segments of the spacer layer. A remaining vertical segment corresponds to the spacer **202**.

As illustrated by the views **1400A-1400D** of FIGS. **14A-14D**, a pair of source/drain regions **114** is formed in the device region **112** of the semiconductor substrate **106**, and a first doped region **104a** and a third doped region **104c** are formed in the plate **402**. The source/drain regions **114** are formed laterally spaced from one another in a first direction, and laterally spaced from the isolation corners **106c** in a second direction transverse (e.g., perpendicular or substantially perpendicular) to the first direction. As noted above, the FET has reduced flicker and random telegraph noise due to the spacing between the isolation corners **106c** and the source/drain regions **114**. Further, the source/drain regions **114** are respectively on opposite sides of the device region **112** of the semiconductor substrate **106**, and respectively underlie the lateral plate openings **118** in the plate dielectric layer **102** and the plate **402**. The source/drain regions **114** respectively adjoin the lightly-doped source/drain extensions **1202**. In some embodiments (e.g., where the FET is a JFET), the source/drain regions **114** may, for example, be regions of the semiconductor substrate **106** with the same doping type as the well **902**. In other embodiments (e.g., where the FET is a MOFSET), the source/drain regions **114** may, for example, be regions of the semiconductor substrate **106** with an opposite doping type as the well **902**. Further, the source/drain regions **114** may, for example, have the same doping type (e.g., p-type or n-type) as the lightly-doped source/drain extensions **1202** and/or a higher doping concentration than the lightly-doped source/drain extensions **1202**.

The first doped region **104a** and the third doped region **104c** are formed laterally spaced from one another in a first direction by the second region **104b'**. The first doped region **104a** of the plate **402** wraps around one of the source/drain regions **114**, and the third doped region **104c** of the plate **402** wraps around another one of the source/drain regions **114**. Further, in some embodiments, the first doped region **104a** and the third doped region **104c** are each laterally spaced from the lateral gate opening **406** in the first direction. In some embodiments, the first doped region **104a** and the third doped region **104c** may, for example, be regions of the plate **402** with the same doping type as the source/drain regions **114**.

In some embodiments, a process for forming the source/drain regions **114**, the first doped region **104a**, and the third doped region **104c** comprises forming a patterned photoresist layer (not shown) on the structure in FIGS. **13A-13D** and subsequently performing an ion implantation process. The patterned photoresist layer may, for example, be formed by a spin on process. The patterned photoresist layer may, for example, be patterned with a layout covering structure surrounding the device region **112**, and further covering the exposed lightly-doped gate extension **1204** and the second region **104b'**. Further, in some embodiments, the process comprises performing an ion implantation into the plate **402** and the semiconductor substrate **106** with the patterned photoresist layer in place, and subsequently stripping the patterned photoresist.

As illustrated by the views **1500A-1500D** of FIGS. **15A-15D**, a gate region **404** is formed in the device region **112** of the semiconductor substrate **106**, and a second doped region **104b** is formed in the plate **104**. The gate region **404** is formed laterally between and spaced from the source/drain regions **114**. Further, the gate region **404** adjoins a single sidewall of the isolation structure **108** at one of the isolation corners **106c**, and underlies the lateral gate opening **406** in the plate dielectric layer **102** and the plate **402**. In some embodiments, the gate region **404** is paired with another gate region on an opposite side of the plate **104**. See, for example, FIGS. **6A-6D**. In some embodiments, the gate region **404** adjoins the lightly-doped gate extensions **1204**. The gate region **404** may, for example, be a region of the semiconductor substrate **106** with an opposite doping type as the source/drain regions **114** and/or the well **902**. Further, the gate region **404** may, for example, have the same doping type (e.g., p-type or n-type) as the lightly-doped gate extension **1204** and/or a higher doping concentration than the lightly-doped gate extension **1204**.

The second doped region **104b** is formed in the plate **402** between the first doped region **104a** and the third doped region **104c**, such that the second doped region **104b** is laterally spaced from the source/drain regions **114** by the first doped region **104a** and the third doped region **104c**. Further, in some embodiments, the second doped region **104b** wraps around the lateral gate opening **406**. In some embodiments, the second doped region **104b** is a region of the plate **402** with the same doping type as the gate region **404**. As noted above, the FET has reduced flicker and random telegraph noise due to the arrangement and doping types of the first, second, and third doped regions **104a**, **104b**, **104c** altering the work function of the plate **104** to drive current flow deeper into the selectively-conductive channel **116**.

In some embodiments, a process for forming the gate region **404** and the second doped region **104b** comprises forming a patterned photoresist layer (not shown) on the structure in FIGS. **14A-14D** and subsequently performing an

ion implantation process. The patterned photoresist layer may, for example, be formed by a spin on process. The patterned photoresist layer may, for example, be patterned with a layout covering the first doped region **104a**, the third doped region **104c**, and the source/drain regions **114**, such that a top surface of the plate **402** is partially exposed between the first doped region **104a** and the third doped region **104c**. Further, in some embodiments, the process comprises performing an ion implantation into the plate **402** and the semiconductor substrate **106** with the patterned photoresist layer in place, and subsequently stripping the patterned photo resist.

As illustrated by the views **1600A-1600D** of FIGS. **16A-16D**, in some embodiments, silicide layers **1602** are formed on the source/drain regions **114** and the gate region **404**. Further, in some embodiments, an additional silicide layer (not shown) is formed on the first doped region **104a**, the second doped region **104b**, and/or the third doped region **104c**. The silicide layers **1602** may, for example, be nickel silicide, titanium silicide, cobalt silicide, platinum silicide, tungsten silicide, or some other transition metal silicide.

In some embodiments, a process for forming the silicide layers **1602** comprises depositing a transition metal layer covering the structure of FIGS. **15A-15D**, and subsequently heating the transition metal layer so it reacts with exposed silicon to form the silicide layers **1602**. Further, in some embodiments, the process comprising removing unreacted material of the transition metal layer by an etch. The process may, for example, be a self-aligned process.

As illustrated by the views **1700A-1700D** of FIGS. **17A-17D**, an ILD layer **1702** is formed covering the structure of FIGS. **16A-16D**. The ILD layer **1702** may, for example, be formed with a planar top surface, and/or may, for example, be formed of oxide, nitride, a low κ dielectric, some other dielectric, or a combination of the foregoing.

In some embodiments, a process for forming the ILD layer **1702** comprises depositing or growing the ILD layer **1702** covering the structure of FIGS. **16A-16D**, and subsequently performing a planarization into the ILD layer **1702**. The depositing or growing may, for example, be formed by chemical or physical vapor deposition, sputtering, some other deposition or growth process, or a combination of the foregoing. The planarization may, for example, be performed by chemical mechanical polishing (CMP).

Also illustrated by the views **1700A-1700D** of FIGS. **17A-17D**, contact vias **1704** are formed extending through the ILD layer **1702** to the source/drain regions **114** and/or the silicide layers **1602**. The silicide layers **1602** facilitate ohmic contacts between the contact vias **1704** and the source/drain regions **114**. Further, the contact vias **1704** are formed extending through the ILD layer **1702** to the first, second, and/or third doped region **104a**, **104b**, **104c** and/or an additional silicide layer (not shown) on the first, second, and/or third doped region **104a**, **104b**, **104c**.

In some embodiments, a process for forming the contact vias **1704** comprises performing an etch into the ILD layer **1702** to form contact-via openings corresponding to the contact vias **1704**. The etch may be, for example, performed using photolithography. Further, in some embodiments, the process comprises filling the contact-via openings with a conductive material. The contact-via openings may, for example, be filled by depositing or growing a conductive layer covering the ILD layer **1702** and filling the contact-via openings, and subsequently performing a planarization into the ILD layer and the conductive layer. The planarization may, for example, be performed by CMP. The process may,

for example, be part of a single damascene like process or a dual damascene like process.

While not shown, additional dielectric layers and conductive features may be subsequently formed on the ILD layer **1702**. For example, one or more additional ILD layers, wires, inter-wire vias, and/or passivation layers may be formed on the ILD layer **1702**.

Further, although FIGS. **8A-8D** through **17A-17D** illustrate a process for forming the embodiment depicted in FIG. **4A-4D**, it is appreciated that a person of ordinary skill could implement the steps above (or substantially similar steps) to form the embodiments depicted in FIGS. **2A-2C**, FIGS. **3A-3D**, and FIGS. **5A-5D** through **7A-7D**.

With reference to FIG. **18**, a flowchart **1800** of some embodiments of the method for forming a FET with reduced flicker and random telegraph noise is provided. While the disclosed method and other methods illustrated and/or described herein may be illustrated and/or described herein as a series of acts or events, it will be appreciated that the illustrated ordering of such acts or events are not to be interpreted in a limiting sense. For example, some acts may occur in different orders and/or concurrently with other acts or events apart from those illustrated and/or described herein. Further, not all illustrated acts may be required to implement one or more aspects or embodiments of the description herein, and one or more of the acts depicted herein may be carried out in one or more separate acts and/or phases.

At **1802**, an isolation structure is formed in a semiconductor substrate. The isolation structure demarcates a device region of the semiconductor substrate. The device region has a first top corner and a second top corner that are line-shaped and that extend laterally in parallel from a first end of the device region to a second end of the device region. See, for example, FIGS. **8A-8D**.

At **1804**, in some embodiments, a well is formed in the device region. See, for example, FIGS. **9A-9D**.

At **1806**, a plate is formed overlying the device region and the first and second top corners of the device region, where a planar top layout of the plate defines a pair of lateral plate openings respectively on the first end of the device region and the second end of the device region, spaced from the first and second top corners, and further defines a lateral gate opening on a side of the device region, laterally spaced from and between the lateral plate openings. See, for example, FIGS. **10A-10D** and **11A-11D**.

At **1808**, in some embodiments, a pair of lightly-doped source/drain extensions is formed in the device region, respectively through the lateral plate openings. Further, in some embodiments, a lightly-doped gate extension is formed in the device region, through the lateral gate opening. See, for example, FIGS. **12A-12D**.

At **1810**, a spacer is formed lining sidewalls of the plate and enclosing the plate. See, for example, FIGS. **13A-13D**.

At **1812**, a pair of source/drain regions is formed in the device region, respectively through the lateral plate openings and respectively overlapping the lightly-doped source/drain extensions. Further, a first doped region and a third doped region are formed in the plate. See, for example, FIGS. **14A-14D**.

At **1814**, a gate region is formed in the device region, respectively through the lateral gate opening and respectively overlapping the lightly-doped gate extension. Further, a second doped region is formed in the plate between the first doped region and the third doped region. See, for example, FIGS. **15A-15D**.

At **1816**, in some embodiments, silicide layers are formed on the source/drain regions, the gate region, and the plate. See, for example, FIGS. **16A-16D**.

At **1818**, an ILD layer is formed covering the source/drain regions, the gate region, the isolation structure, the semiconductor substrate, and the plate. See, for example, FIGS. **17A-17D**.

At **1820**, contact vias are formed extending through the ILD layer to the silicide layers and the plate. See, for example, FIGS. **17A-17D**.

By spacing lateral plate openings from the first and second top corners, the source/drain regions and the lightly-doped source/drain extensions are also spaced from the first and second top corners. This, in turn, decreases source-drain current flowing along the first and second top corners, thereby reducing flicker and random telegraph noise. Further, by doping the plate, the work function of the plate can be manipulated to push source-drain current deep into the device region and away from a top surface of the device region. This may further reduce flicker and random telegraph noise by reducing current flow at the top surface, where there is a high concentration of defect states.

Thus, as can be appreciated from above, the present application relates to a plate design (and related method) to decrease flicker and random telegraph noise in semiconductor devices that is attributed to defects along STI corners and defects along the interface between the device region and the plate dielectric layer.

Accordingly, in some embodiments, the present application provides a semiconductor device. The semiconductor device includes a semiconductor substrate having a device region. An isolation structure extends laterally in a closed path to demarcate the device region. A first source/drain region and a second source/drain region are in the device region and laterally spaced. A sidewall of the first source/drain region directly contacts the isolation structure at a first isolation structure sidewall. The remaining sidewalls of the first source/drain region are spaced from the isolation structure. A selectively-conductive channel is in the device region and extends laterally from the first source/drain region to the second source/drain region. The semiconductor device further includes a plate having a central portion and a first peripheral portion. The central portion overlies the selectively-conductive channel, and the first peripheral portion protrudes from the central portion towards the first isolation structure sidewall.

In other embodiments, the present application provides a semiconductor device having a semiconductor substrate. A pair of source/drain regions is in the semiconductor substrate. The source/drain regions share a first doping type and are laterally spaced. A selectively-conductive channel is in the semiconductor substrate. The selectively-conductive channel extends laterally from one of the source/drain regions to another one of the source/drain regions. The semiconductor device further includes a polysilicon plate having a first doped region, a second doped region, and a third doped region. The second doped region overlies the selectively-conductive channel and is between the first doped region and the third doped region. The first and third doped regions respectively wrap around the source/drain regions and have the first doping type. The second doped region has a second doping type that is opposite the first doping type.

In yet other embodiments, the present application provides a method for manufacturing a semiconductor device. An isolation structure is formed in a semiconductor substrate. The isolation structure demarcates a device region of

the semiconductor substrate. A plate is formed overlying the device region of the semiconductor substrate. The plate wraps around a first portion of the device region and a second portion of the device region. The first and second portions of the device region are on opposite sides of the device region and are separated by the plate. Further, the first and second portions of the device region each have a single sidewall adjoining the isolation structure. A first doping process is performed to implant first dopants into the device region of the semiconductor substrate. The first doping process is performed with the plate in place and forms a pair of source/drain regions, where the source/drain regions are respectively in the first portion of the device region and the second portion of the device region.

The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

What is claimed is:

1. A semiconductor device comprising:

a semiconductor substrate comprising a device region; an isolation structure extending laterally in a closed path to demarcate the device region;

a first source/drain region and a second source/drain region in the device region and laterally spaced, wherein a sidewall of the first source/drain region directly contacts the isolation structure at a first isolation structure sidewall, and wherein remaining sidewalls of the first source/drain region are spaced from the isolation structure;

a selectively-conductive channel in the device region, wherein the selectively-conductive channel extends laterally from the first source/drain region to the second source/drain region; and

a plate comprising a central portion and a first peripheral portion, wherein the central portion overlies the selectively-conductive channel, and wherein the first peripheral portion protrudes from the central portion towards the first isolation structure sidewall.

2. The semiconductor device of claim **1**, wherein the plate wraps around the first source/drain region, along the remaining sidewalls of the first source/drain region.

3. The semiconductor device of claim **1**, wherein the plate comprises a second peripheral portion, wherein the second peripheral portion protrudes from the central portion towards the first isolation structure sidewall on an opposite side of the first source/drain region as the first peripheral portion, and wherein both the central portion and the first source/drain region are disposed between the first and second peripheral portions.

4. The semiconductor device of claim **3**, wherein:

a perimeter of the central portion is disposed within a perimeter of the device region;

the first peripheral portion directly overlies a first portion of the device region and a first portion of the isolation structure; and

19

the second peripheral portion directly overlies a second portion of the device region and a second portion of the isolation structure.

5. The semiconductor device of claim 4, wherein:

the first peripheral portion has a first area;

the second peripheral portion has a second area; and

the central portion has a third area that is greater than both the first area and the second area.

6. The semiconductor device of claim 1, further comprising:

a first gate region within the device region, wherein a first sidewall of the first gate region adjoins the isolation structure, wherein a second sidewall of the first gate region adjoins the selectively-conductive channel, and wherein remaining sidewalls of the first gate region and the second sidewall of the first gate region are completely spaced from the isolation structure.

7. The semiconductor device of claim 6, wherein the plate wraps around the first gate region, along the second sidewall of the first gate region and the remaining sidewalls of the first gate region.

8. The semiconductor device of claim 6, wherein the plate comprises a second peripheral portion and a third peripheral portion, wherein the second and third peripheral portions protrude from the central portion, wherein the first gate region is disposed directly between the second and third peripheral portions, and wherein the first source/drain region is disposed directly between the first and second peripheral portions.

9. The semiconductor device of claim 8, further comprising:

a second gate region within the device region, wherein a first sidewall of the second gate region adjoins the isolation structure, wherein a second sidewall of the second gate region adjoins the selectively-conductive channel, wherein remaining sidewalls of the second gate region and the second sidewall of the second gate region are completely spaced from the isolation structure, and wherein the first and second gate regions are on opposite sides of the selectively-conductive channel.

10. The semiconductor device of claim 9, wherein the plate comprises a fourth peripheral portion protruding from the central portion, wherein the first gate region is disposed directly between the second and third peripheral portions, wherein the second gate region is disposed directly between the first and fourth peripheral portions, wherein the first source/drain region is disposed directly between the first and second peripheral portions, and wherein the second source/drain region is disposed directly between the third and fourth peripheral portions.

11. The semiconductor device of claim 10, wherein a sidewall of the second source/drain region directly contacts the isolation structure at a second isolation structure sidewall, wherein the first and second isolation structure sidewalls are on opposite sides of the device region, and wherein remaining sidewalls of the second source/drain region are spaced from the isolation structure.

12. The semiconductor substrate of claim 1, wherein the plate has more than four sidewalls.

13. A semiconductor device comprising:

a semiconductor substrate;

a pair of source/drain regions in the semiconductor substrate, wherein the source/drain regions share a first doping type and are laterally spaced;

a selectively-conductive channel in the semiconductor substrate, wherein the selectively-conductive channel

20

extends laterally from one of the source/drain regions to another one of the source/drain regions; and

a polysilicon plate comprising a first doped region, a second doped region, and a third doped region, wherein the second doped region is between the first and third doped regions and overlies the selectively-conductive channel, wherein the first and third doped regions respectively wrap around the source/drain regions and comprise the first doping type, and wherein the second doped region comprises a second doping type opposite the first doping type.

14. The semiconductor device of claim 13, wherein the first doped region of the polysilicon plate is disposed between the one of the source/drain regions and the second doped region of the polysilicon plate, and wherein the third doped region of the polysilicon plate is disposed between the another one of the source/drain regions and the second doped region of the polysilicon plate.

15. The semiconductor device of claim 13, wherein the first and third doped regions each have a planar top layout that is U-shaped, and wherein the second doped region has a planar top layout that is line shaped.

16. The semiconductor device of claim 13, further comprising:

an isolation structure extending laterally in a closed path to demarcate a device region of the semiconductor substrate, wherein the device region comprises the source/drain regions and the selectively-conductive channel; and

wherein the source/drain regions adjoin the isolation structure at a first isolation structure sidewall and a second isolation structure sidewall, respectively, and wherein remaining sidewalls of both of the source/drain regions are spaced from the isolation structure.

17. The semiconductor device of claim 16, wherein the polysilicon plate comprises: a central portion, a first peripheral portion, and a second peripheral portion, wherein:

the central portion overlies the selectively-conductive channel;

the first peripheral portion protrudes from the central portion toward the first isolation structure sidewall on a first side of the one of the source/drain regions; and the second peripheral portion protrudes from the central portion toward the first isolation structure sidewall on a second side of the one of the source/drain regions opposite the first side of the one of the source/drain regions.

18. A semiconductor device comprising:

a semiconductor substrate comprising a device region; an isolation structure extending laterally in a closed path to demarcate the device region;

a first source/drain region and a second source/drain region disposed in the device region, wherein the first and second source/drain regions share a first doping type and are laterally spaced;

a selectively-conductive channel disposed in the device region and extending laterally from the first source/drain region to the second source/drain region;

a first gate region disposed in the device region, wherein the first gate region adjoins a first side of the selectively-conductive channel between the first and second source/drain regions; and

a polysilicon plate comprising a first doped region having the first doping type, a second doped region having a second doping type opposite the first doping type, and a third doped region having the first doping type, wherein the first doped region wraps around at least

three sides of the first source/drain region, wherein the third doped region wraps around at least three sides of the second source/drain region, and wherein the second doped region wraps around at least three sides of the first gate region.

5

19. The semiconductor device of claim **18**, wherein:

the first doped region overlies a first portion of the selectively-conductive channel;

the second doped region overlies a second portion of the selectively-conductive channel;

10

the third doped region overlies a third portion of the selectively-conductive channel; and

the second portion of the selectively-conductive channel is disposed between the first portion of the selectively-

conductive channel and the second portion of the selectively-conductive channel.

15

20. The semiconductor device of claim **18**, further comprising:

a second gate region disposed in the device region, wherein the second gate region adjoins a second side of

20

the selectively-conductive channel between the first and second source/drain regions, wherein the second

side of the selectively-conductive channel is opposite the first side of the selectively-conductive channel, and

wherein the second doped region wraps around at least three sides of the second gate region.

25

* * * * *