



US010704728B2

(12) **United States Patent**  
**Free et al.**

(10) **Patent No.:** **US 10,704,728 B2**  
(45) **Date of Patent:** **Jul. 7, 2020**

(54) **PIPE LINER AND METHOD OF MAKING SAME**

(71) Applicant: **INA ACQUISITION CORP.**,  
Wilmington, DE (US)

(72) Inventors: **Charles Free**, Hernando, MS (US);  
**Abu Abraham**, St. Louis, MO (US);  
**Yevgeny Eugene Zaltsman**, St. Louis,  
MO (US)

(73) Assignee: **INA Acquisition Corp.**, Wilmington,  
DE (US)

(\*) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 182 days.

(21) Appl. No.: **15/926,325**

(22) Filed: **Mar. 20, 2018**

(65) **Prior Publication Data**  
US 2019/0293223 A1 Sep. 26, 2019

(51) **Int. Cl.**  
**F16L 55/16** (2006.01)  
**F16L 55/165** (2006.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **F16L 55/1656** (2013.01); **B29C 63/0021**  
(2013.01); **B29C 65/5042** (2013.01); **B29C**  
**65/62** (2013.01); **B29C 66/7234** (2013.01);  
**B29C 67/0018** (2013.01); **B32B 1/08**  
(2013.01); **B32B 5/022** (2013.01); **B32B 5/26**  
(2013.01); **B32B 7/03** (2019.01); **B32B 7/08**  
(2013.01); **F16L 55/1651** (2013.01); **B29L**  
**2023/006** (2013.01); **B32B 2305/10** (2013.01);  
(Continued)

(58) **Field of Classification Search**  
CPC ..... F16L 55/1656; F16L 55/1651  
USPC ..... 138/97, 98; 405/150.1, 184.2  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,459,014 A 8/1969 Berning  
3,520,749 A 7/1970 Rubenstein  
(Continued)

FOREIGN PATENT DOCUMENTS

AU 8533298 A 2/1999  
DE 2753669 A1 10/1978  
(Continued)

OTHER PUBLICATIONS

Extended European Search Report, Application No. 19163265.2-  
1010, dated Aug. 9, 2019, pp. 9.

(Continued)


*Primary Examiner* — James F Hook

(74) *Attorney, Agent, or Firm* — Stinson LLP

(57) **ABSTRACT**

An eversion liner for lining a pipe includes an impermeable  
outer portion, inner and outer strength portions inside the  
impermeable outer portion, and a middle portion including  
at least one felt layer radially between the inner and outer  
strength portions. At least one of the inner and outer strength  
portions is formed from a unitary sheet of strength material  
that includes parallel chopped strands of fiber. The longitu-  
dinal edge margins of the sheet of strength material are  
positioned in overlapping engagement and joined together  
by joining structure. The parallel chopped fibers can be  
oriented transverse to the length of the liner. The joining  
structure can prevent reduction in a width of the overlapped  
edge margins as the liner expands during eversion.

**20 Claims, 3 Drawing Sheets**



(51)	<b>Int. Cl.</b>			5,911,246 A	6/1999	Kittson et al.	
	<i>B32B 7/03</i>	(2019.01)		5,919,327 A	7/1999	Smith	
	<i>B29C 63/00</i>	(2006.01)		5,931,198 A	8/1999	Raji et al.	
	<i>B29C 65/50</i>	(2006.01)		5,931,199 A	8/1999	Kittson et al.	
	<i>B29C 65/62</i>	(2006.01)		5,937,910 A	8/1999	Chandler	
	<i>B29C 65/00</i>	(2006.01)		5,971,030 A	10/1999	Maimets	
	<i>B29C 67/00</i>	(2017.01)		5,971,440 A	10/1999	Boatman	
	<i>B32B 1/08</i>	(2006.01)		5,975,878 A	11/1999	Wood et al.	
	<i>B32B 5/02</i>	(2006.01)		5,988,702 A	11/1999	Sas-Jaworsky	
	<i>B32B 5/26</i>	(2006.01)		6,019,136 A	2/2000	Walsh et al.	
	<i>B32B 7/08</i>	(2019.01)		6,027,783 A	2/2000	Wagener	
	<i>B29L 23/00</i>	(2006.01)		6,042,668 A	3/2000	Kamiyama et al.	
(52)	<b>U.S. Cl.</b>			6,044,867 A	4/2000	Tweedie et al.	
	CPC ... <i>B32B 2305/22</i> (2013.01); <i>B32B 2307/7265</i>			6,085,794 A	7/2000	Kamiyama et al.	
	(2013.01); <i>B32B 2597/00</i> (2013.01)			6,085,798 A	7/2000	Le Nouveau	
(56)	<b>References Cited</b>			6,103,046 A	8/2000	Smith	
	<b>U.S. PATENT DOCUMENTS</b>			6,146,491 A	11/2000	Wood et al.	
	4,009,063 A	2/1977	Wood	6,168,846 B1	1/2001	Molyneaux	
	4,671,840 A	6/1987	Renaud	6,170,531 B1	1/2001	Jung et al.	
	4,681,783 A *	7/1987	Hyodo ..... F16L 55/1656	6,196,271 B1	3/2001	Braun et al.	
			138/124	6,206,993 B1	3/2001	Kiest, Jr. et al.	
	4,836,715 A	6/1989	Wood	6,207,002 B1	3/2001	Odell et al.	
	4,976,290 A	12/1990	Gelin et al.	6,228,312 B1	5/2001	Boyce	
	5,010,440 A *	4/1991	Endo ..... B29C 53/382	6,254,709 B1 *	7/2001	Kamiyama ..... B29C 66/038	156/91
			138/97				
	5,049,003 A	9/1991	Barton	6,276,401 B1	8/2001	Wilson	
	5,077,107 A	12/1991	Kaneda et al.	6,296,066 B1	10/2001	Terry et al.	
	5,164,237 A	11/1992	Kaneda et al.	6,296,729 B1	10/2001	Kamiyama et al.	
	5,168,006 A	12/1992	Inoguchi et al.	6,349,748 B1	2/2002	Dodds et al.	
	5,186,987 A	2/1993	Imoto et al.	6,354,434 B1	3/2002	Ellyin et al.	
	5,205,886 A *	4/1993	White ..... B29C 63/34	6,360,780 B1	3/2002	Adolphs et al.	
			138/145	6,361,080 B1	3/2002	Walsh et al.	
	5,218,810 A	6/1993	Isley, Jr.	6,446,670 B1	9/2002	Woodward et al.	
	5,271,433 A	12/1993	Schwert et al.	6,488,323 B1	12/2002	Boulogny	
	D343,628 S	1/1994	Sciholtz	6,503,024 B2	1/2003	Rupiper	
	5,322,563 A	6/1994	van Bonn et al.	6,508,276 B2	1/2003	Rädlinger et al.	
	5,334,429 A	8/1994	Imoto et al.	6,510,781 B2	1/2003	Pecca et al.	
	D358,599 S	5/1995	Dietterich et al.	6,562,426 B1	5/2003	Kamiyama et al.	
	5,411,060 A *	5/1995	Chandler ..... B29C 63/34	6,572,306 B2	6/2003	Prusak	
			138/103	6,578,882 B2	6/2003	Toliver	
	5,423,630 A	6/1995	Imoto et al.	6,595,069 B2	7/2003	Frey et al.	
	5,443,880 A	8/1995	Wike	6,615,875 B2	9/2003	Adolphs et al.	
	5,501,248 A	3/1996	Kiest, Jr.	6,634,387 B1	10/2003	Glejbøl	
	5,503,695 A *	4/1996	Imoto ..... B29C 63/34	6,641,688 B1	11/2003	Gearhart	
			156/287	6,641,688 B1	11/2003	Gearhart	
	5,535,786 A	7/1996	Makela et al.	6,668,596 B1	12/2003	Wagener	
	5,549,856 A	8/1996	Yokoshima	6,679,966 B1	1/2004	Brandenburger	
	5,593,700 A	1/1997	Stilgenbauer	6,681,641 B2	1/2004	Baumuel	
	5,597,227 A	1/1997	Bergen et al.	6,698,519 B2	3/2004	Nguyen et al.	
	5,632,575 A	5/1997	Lorenzen et al.	6,708,729 B1	3/2004	Smith	
	5,634,672 A	6/1997	Stack et al.	6,732,763 B2	5/2004	Williamson et al.	
	5,649,398 A	7/1997	Isley, Jr. et al.	6,737,134 B2	5/2004	Friedrich et al.	
	5,653,555 A	8/1997	Catallo	6,739,355 B2	5/2004	Glejbøl	
	5,683,530 A	11/1997	Fawley et al.	6,769,484 B2	8/2004	Longmore	
	5,698,056 A *	12/1997	Kamiyama ..... B29C 65/5042	6,854,479 B2	2/2005	Harwood	
			138/98	6,863,137 B2	3/2005	Terry et al.	
	5,700,110 A	12/1997	Kamiyama et al.	6,869,667 B2	3/2005	Kawazu et al.	
	5,703,154 A	12/1997	Davis et al.	6,889,716 B2	5/2005	Lundberg et al.	
	5,720,575 A	2/1998	Henrie	6,889,718 B2	5/2005	Glejbøl	
	5,758,796 A	6/1998	Nishimura et al.	6,890,476 B2	5/2005	Wagener et al.	
	5,769,109 A	6/1998	Stanton et al.	6,923,217 B2	8/2005	Smith	
	5,778,936 A	7/1998	McAlpine	6,923,273 B2	8/2005	Terry et al.	
	5,798,013 A	8/1998	Brandenburger	6,932,116 B2	8/2005	Smith et al.	
	5,799,705 A	9/1998	Friedrich et al.	6,978,806 B2	12/2005	Glejbøl	
	5,836,357 A	11/1998	Kittson et al.	6,981,526 B2	1/2006	Glejbøl	
	5,855,729 A	1/1999	Kiest, Jr. et al.	7,000,645 B2	2/2006	Glejbøl	
	5,868,169 A	2/1999	Catallo	7,018,691 B2	3/2006	McNeil	
	5,873,357 A	2/1999	Lake	7,025,580 B2	4/2006	Heagy et al.	
	5,873,391 A	2/1999	Kittson et al.	7,069,955 B2	7/2006	Glejbøl	
	5,876,645 A *	3/1999	Johnson ..... F16L 55/1651	7,096,890 B2	8/2006	Woolstencroft et al.	
			138/141	7,100,632 B2	9/2006	Harwood	
	5,881,760 A	3/1999	Del Zotto	7,137,757 B1	11/2006	Cosban	
				7,153,395 B2	12/2006	Foster et al.	
				7,172,038 B2	2/2007	Terry et al.	
				7,178,588 B2	2/2007	Harper et al.	
				7,220,081 B1	5/2007	Gantt, Jr.	
				7,231,975 B2	6/2007	Lavaure et al.	
				7,231,984 B2	6/2007	Jensch	
				7,241,076 B1	7/2007	Cosban	
				7,261,788 B1	8/2007	Driver	



(56)

References Cited

U.S. PATENT DOCUMENTS

7,264,695 B2	9/2007	Foster et al.	9,188,269 B2	11/2015	Hairston et al.
7,302,973 B2	12/2007	Glejbøl et al.	9,194,513 B2	11/2015	Sierra
7,306,011 B2	12/2007	Kiest, Jr.	9,222,611 B2	12/2015	Colasanto
7,360,797 B2	4/2008	Posson	9,248,605 B2	2/2016	Quitter
D568,347 S	5/2008	Manera et al.	9,261,216 B2	2/2016	Stalcup, II et al.
7,472,722 B2	1/2009	Nadarajah et al.	9,261,221 B2	2/2016	Kiest, Jr.
7,478,650 B2	1/2009	Pleydon et al.	9,267,635 B2	2/2016	Kulkarni et al.
7,478,659 B2	1/2009	Jeon	9,278,308 B2	3/2016	Jamtvedt et al.
7,494,592 B2	2/2009	Deskins	9,316,339 B1	4/2016	Souza et al.
7,500,494 B2	3/2009	Robinson et al.	9,321,210 B2	4/2016	Toliver et al.
7,527,076 B2	5/2009	Lepola et al.	9,366,375 B2	6/2016	Kiest, Jr.
7,621,333 B2	11/2009	Marchal	D764,554 S	8/2016	Charles et al.
7,632,408 B1	12/2009	Everson	9,435,468 B2	9/2016	Graham
7,637,169 B2	12/2009	Shanahan et al.	9,453,597 B2	9/2016	Delaney et al.
7,666,047 B2	2/2010	Suzuki et al.	9,453,606 B2	9/2016	Catha et al.
7,690,092 B2	4/2010	Wagener	9,488,511 B2	11/2016	Barto
7,691,261 B2	4/2010	Deskins	9,551,441 B2	1/2017	Dowe et al.
7,708,033 B2	5/2010	Tanaka et al.	9,579,854 B2	2/2017	Klethy et al.
7,727,447 B2	6/2010	Song et al.	10,077,855 B2*	9/2018	Free ..... F16L 9/14
7,784,552 B2	8/2010	Brouse	2001/0010781 A1	8/2001	Prusak
7,786,223 B2	8/2010	Mullelr-Frischinger	2001/0039875 A1	11/2001	Pecca et al.
7,794,813 B2	9/2010	Nguyen et al.	2001/0043839 A1	11/2001	Prusak
7,858,189 B2	12/2010	Wagener et al.	2001/0046415 A1	11/2001	Rupiper
7,891,381 B2	2/2011	Anders et al.	2002/0004116 A1	1/2002	Friedrich et al.
7,896,032 B2	3/2011	Kiest, Jr.	2002/0007970 A1	1/2002	Terry et al.
7,926,578 B2	4/2011	Moffitt et al.	2002/0033554 A1	3/2002	Heagy et al.
7,938,146 B2	5/2011	Brooks et al.	2002/0036085 A1	3/2002	Bass et al.
7,942,167 B1	5/2011	Llewellyn	2002/0060454 A1	5/2002	Toliver
7,975,726 B2	7/2011	Kiest, Jr.	2002/0124898 A1	9/2002	Renaud et al.
7,976,920 B2	7/2011	Braad et al.	2002/0162733 A1	11/2002	Foster et al.
D643,445 S	8/2011	Harrison	2003/0034156 A1	2/2003	Gondouin
7,987,875 B2	8/2011	Rytter	2003/0047007 A1	3/2003	Baumael
7,997,115 B2	8/2011	Tidl et al.	2003/0066567 A1	4/2003	Manners
D646,700 S	10/2011	Takeuchi	2003/0075361 A1	4/2003	Terry et al.
8,047,238 B2	11/2011	Wiessner et al.	2003/0108682 A1	6/2003	Lehrman et al.
8,047,396 B2	11/2011	Jenkins et al.	2003/0113489 A1	6/2003	Smith
8,069,880 B2	12/2011	Friedrich et al.	2003/0121559 A1	7/2003	Glejbøl et al.
8,082,954 B2	12/2011	Rytter	2003/0138298 A1	7/2003	Mercier
8,110,103 B2	2/2012	Mormino et al.	2003/0141303 A1	7/2003	Grazziotin
8,114,057 B2	2/2012	Gerdts et al.	2003/0155124 A1	8/2003	Nguyen et al.
8,119,047 B2	2/2012	Moore et al.	2003/0164196 A1	9/2003	Glejbøl et al.
D658,689 S	5/2012	Li	2003/0178201 A1	9/2003	Gleim et al.
8,256,089 B2	9/2012	Pionetti	2003/0213119 A1	11/2003	Frey et al.
8,272,406 B2	9/2012	McKaigue et al.	2003/0217777 A1	11/2003	Williamson et al.
8,322,382 B2	12/2012	Slagsvold et al.	2003/0234056 A1*	12/2003	Woolstencroft ..... B29D 23/001 138/98
8,375,972 B2	2/2013	Kiest, Jr.	2003/0234057 A1	12/2003	Woolstencroft et al.
8,418,337 B2	4/2013	Salama	2004/0035471 A1	2/2004	Harwood
8,580,364 B2	11/2013	Quitter	2004/0040703 A1	3/2004	Longmore
8,590,575 B2	11/2013	D'Hulster	2004/0050442 A1	3/2004	Glejbøl et al.
D696,317 S	12/2013	Carper	2004/0079524 A1	4/2004	Bass et al.
8,596,917 B2	12/2013	Emmons et al.	2004/0089358 A1	5/2004	Burd et al.
8,609,557 B2	12/2013	Palinsky et al.	2004/0094209 A1	5/2004	Harwood
8,616,243 B2	12/2013	Kiest, Jr.	2004/0118468 A1	6/2004	Mestemacher
8,636,869 B2	1/2014	Wiessner et al.	2004/0129373 A1	7/2004	Nadarajah et al.
D700,224 S	2/2014	Kmoch et al.	2004/0134767 A1	7/2004	Foster et al.
8,647,456 B2	2/2014	Wagener et al.	2004/0144440 A1	7/2004	Lundberg et al.
8,678,043 B2	3/2014	Emmons et al.	2004/0144530 A1	7/2004	Bass et al.
8,697,215 B2	4/2014	Lahijani	2004/0149341 A1	8/2004	Driver
8,739,809 B2	6/2014	Kiest, Jr.	2004/0168960 A1	9/2004	Holtzapple et al.
8,740,259 B2	6/2014	Mazzaferro et al.	2004/0171136 A1	9/2004	Holtzapple et al.
8,801,329 B2	8/2014	Bateman et al.	2004/0182462 A1	9/2004	Glejbøl et al.
8,813,873 B2	8/2014	Beardmore et al.	2004/0194838 A1	10/2004	Glejbøl et al.
8,844,577 B2	9/2014	Kiest, Jr.	2004/0194967 A1	10/2004	Jaensch
8,857,860 B2	10/2014	Schwalbach et al.	2004/0221907 A1	11/2004	Glejbøl
8,869,839 B1	10/2014	D'Hulster	2004/0247810 A1	12/2004	McNeil
8,914,954 B2	12/2014	Klethi et al.	2004/0258479 A1	12/2004	Manners
8,940,113 B2	1/2015	Lindner et al.	2004/0258837 A1	12/2004	Robinson
8,978,708 B2	3/2015	Brandenburger et al.	2004/0261998 A1	12/2004	Lavaure et al.
9,004,163 B2	4/2015	Tverlid	2005/0028880 A1	2/2005	Smith
9,040,136 B2	5/2015	Procida	2005/0028881 A1	2/2005	Smith et al.
D733,198 S	6/2015	Chappel	2005/0051344 A1	3/2005	Goss
9,052,053 B2	6/2015	Kiest	2005/0115741 A1	6/2005	Terry et al.
9,074,718 B2	7/2015	Kiest, Jr.	2005/0161100 A1	7/2005	Pleydon et al.
9,074,720 B2	7/2015	D'Hulster	2005/0173919 A1	8/2005	Posson
9,163,770 B2	10/2015	Kiest, Jr. et al.	2005/0183785 A1	8/2005	Lundberg et al.
			2005/0247448 A1	11/2005	Harper et al.
			2005/0257846 A1	11/2005	Nordling, Jr.
			2005/0281970 A1	12/2005	LaMarca, II et al.



(56)

References Cited

U.S. PATENT DOCUMENTS

2006/0006124	A1	1/2006	Deskins	2012/0018080	A1	1/2012	Wiessner et al.
2006/0048833	A1	3/2006	Glejbøl et al.	2012/0048455	A1	3/2012	Rocher et al.
2006/0090804	A1	5/2006	Driver et al.	2012/0056414	A1	3/2012	Thomas et al.
2006/0118028	A1	6/2006	Schroeder	2012/0090721	A1	4/2012	Toliver et al.
2006/0124188	A1	6/2006	Catha et al.	2012/0111578	A1	5/2012	Tverlid
2006/0137757	A1	6/2006	McKeen et al.	2012/0145271	A1	6/2012	McKeller et al.
2006/0151042	A1	7/2006	Stringfellow et al.	2012/0175004	A1	7/2012	Kiest, Jr.
2006/0175053	A1	8/2006	Marchal	2012/0193908	A1	8/2012	Mazzaferro et al.
2006/0185750	A1	8/2006	Mestemacher	2012/0199233	A1	8/2012	Mizell et al.
2006/0219311	A1	10/2006	Kiest, Jr.	2012/0211114	A1	8/2012	Nilsson et al.
2006/0278290	A1*	12/2006	Warren ..... F16L 55/165 138/98	2012/0248766	A1	10/2012	Schwalbach et al.
2007/0018448	A1	1/2007	Nadarajah et al.	2012/0261015	A1	10/2012	Warren
2007/0029688	A1	2/2007	Delaney et al.	2012/0261016	A1	10/2012	Fuechtjohann et al.
2007/0036925	A1	2/2007	Braad	2012/0280488	A1	11/2012	Pionetti
2007/0074774	A1	4/2007	Chandler	2012/0285575	A1	11/2012	Catha et al.
2007/0114689	A1	5/2007	Driver et al.	2013/0019982	A1	1/2013	Kobayashi
2007/0119512	A1	5/2007	Rytter	2013/0019983	A1	1/2013	Kiest, Jr.
2007/0144784	A1	6/2007	Head et al.	2013/0033033	A1	2/2013	Eck
2007/0163665	A1	7/2007	Lepola et al.	2013/0061971	A1	3/2013	Chamberland
2007/0172616	A1	7/2007	Ehsani et al.	2013/0074972	A1	3/2013	Fuechtjohann et al.
2007/0180610	A1	8/2007	Mohr et al.	2013/0081732	A1	4/2013	Kiest, Jr.
2007/0267785	A1	11/2007	Bellamy et al.	2013/0112303	A1	5/2013	Kiest, Jr.
2008/0017263	A1	1/2008	Robinson et al.	2013/0126034	A1	5/2013	Sierra
2008/0053554	A1	3/2008	Salama	2013/0133775	A1	5/2013	Duncan et al.
2008/0060699	A1	3/2008	Mestemacher	2013/0213513	A1	8/2013	Kiest, Jr.
2008/0078463	A1	4/2008	Kiest	2013/0220465	A1	8/2013	D'Hulster
2008/0121359	A1	5/2008	Holtzapple et al.	2013/0263443	A1	10/2013	Delaney et al.
2008/0145579	A1	6/2008	Nguyen et al.	2013/0280477	A1	10/2013	Davis et al.
2008/0173396	A1	7/2008	Wiessner	2014/0027000	A1	1/2014	Kiest, Jr.
2008/0217063	A1	9/2008	Moore et al.	2014/0034175	A1	2/2014	Fyfe
2008/0277012	A1	11/2008	Anders et al.	2014/0050464	A1	2/2014	Lin
2008/0277013	A1	11/2008	Anders et al.	2014/0076447	A1	3/2014	Kiest, Jr.
2008/0283138	A1	11/2008	Rytter	2014/0085643	A1	3/2014	Kiest, Jr.
2009/0036582	A1	2/2009	Muller-Frischinger	2014/0116557	A1	5/2014	Bichler
2009/0056823	A1	3/2009	Kiest, Jr.	2014/0116566	A1	5/2014	Bader et al.
2009/0090508	A1	4/2009	Brouse	2014/0209128	A1	7/2014	Abdul-Ali
2009/0101345	A1	4/2009	Moffitt et al.	2014/0238525	A1	8/2014	Dyksterhouse
2009/0116927	A1	5/2009	Keenan et al.	2014/0251480	A1	9/2014	Kulkarni et al.
2009/0127180	A1	5/2009	Deskins	2014/0261832	A1	9/2014	Kiest, Jr. et al.
2009/0129853	A1	5/2009	Pionetti	2014/0261972	A1	9/2014	Colasanto
2009/0165927	A1	7/2009	Driver et al.	2014/0262267	A1	9/2014	Fustos et al.
2009/0166273	A1	7/2009	Mormino et al.	2014/0284914	A1	9/2014	Tsambarlis
2009/0188327	A1	7/2009	Shanahan et al.	2014/0290782	A1	10/2014	Dowe et al.
2009/0205733	A1	8/2009	Stringfellow et al.	2014/0326511	A1	11/2014	Beardmore et al.
2009/0250134	A1	10/2009	Slagsvold et al.	2014/0352955	A1	12/2014	Tubel et al.
2009/0250135	A1	10/2009	Friedrich et al.	2014/0356074	A1	12/2014	Bureau et al.
2009/0308475	A1	12/2009	Stringfellow et al.	2014/0360611	A1	12/2014	Kiest, Jr.
2009/0314409	A1	12/2009	Ehsani	2014/0373631	A1	12/2014	Davis et al.
2010/0038019	A1	2/2010	Da Silveira et al.	2015/0020908	A1	1/2015	Warren
2010/0062202	A1	3/2010	Procida	2015/0045527	A1	2/2015	Schleicher et al.
2010/0078118	A1	4/2010	Ehsani	2015/0107713	A1	4/2015	Manners
2010/0181325	A1	7/2010	Jenkins et al.	2015/0144480	A1	5/2015	Zhao et al.
2010/0212803	A1	8/2010	Carr et al.	2015/0151484	A1	6/2015	Sanders
2010/0243154	A1	9/2010	Wiessner et al.	2015/0211342	A1	7/2015	Shaw et al.
2010/0291903	A1	11/2010	McPherson	2015/0246501	A1	9/2015	Den Besten et al.
2010/0295198	A1	11/2010	Kiest, Jr.	2015/0252929	A1	9/2015	Jaspaert
2010/0300760	A1	12/2010	Beardmore et al.	2015/0330536	A1	11/2015	Jaspaert
2011/0030830	A1	2/2011	McKaigue et al.	2015/0330550	A1	11/2015	Hairston et al.
2011/0052325	A1	3/2011	Bateman et al.	2015/0369399	A1	12/2015	Fyfe
2011/0074147	A1	3/2011	Thomas et al.	2016/0010785	A1	1/2016	Arnold et al.
2011/0083766	A1	4/2011	Anders	2016/0018027	A1	1/2016	Douglass, III et al.
2011/0101686	A1	5/2011	Dalmolen et al.	2016/0033072	A1	2/2016	Mersmann et al.
2011/0135899	A1	6/2011	Meltzer et al.	2016/0053922	A1	2/2016	Ehsani
2011/0236138	A1	9/2011	Cosban	2016/0078743	A1	3/2016	Tanner
2011/0244125	A1	10/2011	Weisenberg et al.	2016/0091352	A1	3/2016	Barto
2011/0247755	A1	10/2011	Sanders	2016/0146380	A1	5/2016	Anelli et al.
2011/0259461	A1	10/2011	Kiest, Jr.	2016/0178108	A1	6/2016	Ehsani
2011/0277864	A1	11/2011	Kiest, Jr.	2016/0186897	A1	6/2016	Stalcup, II et al.
2011/0277868	A1	11/2011	Emmons et al.	2016/0223122	A1	8/2016	Kiest, Jr.
2011/0280665	A1	11/2011	Emmons et al.	2016/0245429	A1	8/2016	Zhu et al.
2012/0000563	A1	1/2012	Lahijani	2016/0258567	A1	9/2016	Hairston et al.
2012/0006439	A1	1/2012	Kiest, Jr.	2016/0334046	A1	11/2016	Kiest
2012/0007714	A1	1/2012	Mühlin	2016/0348828	A1	12/2016	Mathey et al.
2012/0012217	A1	1/2012	Hairston et al.	2016/0363389	A1	12/2016	Hemker et al.

(56)

**References Cited**

U.S. PATENT DOCUMENTS

2017/0043606 A1 2/2017 Meltzer et al.  
2017/0082220 A1 3/2017 Free et al.

FOREIGN PATENT DOCUMENTS

DE	4326503	A1	2/1995
DE	1403370	A1	8/1995
DE	19941669	A1	3/2001
EP	0228998	A1	7/1987
EP	0510784	A1	10/1992
EP	2390547	A2	11/2001
EP	2273171	A1	1/2011
EP	2722157	A1	4/2014
JP	H02219635		9/1990
JP	H0350280	A	3/1991
JP	H03292127	A	12/1991
JP	S5262379		5/1997
JP	2007518608	A	7/2007
KR	20060012367		2/2006
WO	WO9114896	A1	10/1991
WO	WO1993015131	A2	8/1993
WO	WO9919659	A1	4/1999
WO	WO0017557	A1	3/2000
WO	2002018834	A2	3/2002
WO	WO2005047755	A1	5/2005
WO	WO2005047756	A1	5/2005
WO	WO2005047757	A1	5/2005
WO	WO2006111580	A1	10/2006
WO	WO2012082949	A1	6/2012
WO	2012145422	A1	10/2012
WO	2013163736	A1	5/2013
WO	2014110544	A1	7/2014

OTHER PUBLICATIONS


Trenchless Technology, CIPP of Leaking High-Pressure Gas main, Oct. 2011, 4 pages.  
Trenchless Technology, Trenchless Lateral Repair Keeps Oregon Landscape Untouched, Apr. 2012, 2 pages.

VECTORPLY(R) Performance Composite Reinforcements, product sheet E-LTM 3610, VECTORPLY(R) Corporation, Rev. May 3, 2011.  
VECTORPLY(R) Performance Composite Reinforcements, product sheet E-TLX 2400, VECTORSPORTS(TM), VECTORPLY(R) Corporation, Rev. May 3, 2011.  
VECTORPLY(R) Performance Composite Reinforcements, product sheet E-BX 1200, VECTORPLY(R) Corporation, Rev. May 3, 2011.  
VECTORPLY(R) Performance Composite Reinforcements, product sheet E-QX 4800, LABORSAVER(TM), VECTORPLY(R) Corporation, Rev. May 3, 2011.  
VECTORPLY(R) Performance Composite Reinforcements, product sheet E-LM 3610, LABORSAVER(TM), VECTORPLY(R) Corporation, Rev. May 3, 2011.  
VECTORPLY(R) Performance Composite Reinforcements, product sheet E-TLX 2200, VECTORSPORTS(TM), VECTORPLY(R) Corporation, Rev. May 3, 2011.  
VECTORPLY(R) Performance Composite Reinforcements, product sheet E-BXM 1708, VECTORPLY(R) Corporation, Rev. May 3, 2011.  
VECTORPLY(R) Performance Composite Reinforcements, product sheet E-BX 1700, VECTORPLY(R) Corporation, Rev. May 3, 2011.  
VECTORPLY(R) Performance Composite Reinforcements, product sheet E-QXCFM 3510, VECTORFUSION(TM) Infusion Specific Reinforcements, VECTORPLY(R) Corporation, Rev. May 3, 2011.  
VECTORPLY(R) Performance Composite Reinforcements, product sheet E-BXCFM 1710, VECTORFUSION(TM), Infusion-Specific Reinforcements, VECTORPLY(R) Corporation, Rev. May 3, 2011.  
Rongxing Zhou, An Improved MWK Structure for Composite Reinforcement, Textile Research Journal, Published by Sage, Apr. 1, 2005.  
FYFE(R) an Aegion Company, Tyfo(R) Fibrwrap(R) Composite Systems, 3 pages, Copyright 2013 Fyfe Co., LLC (admitted prior art).  
Oxnera, Keith B and Allsup, Todd; Advances in Cured-in-Place Pipe Rehabilitation for Pressurized Piping Systems, © 1999 Insituform Technologies, Inc., 12 pages.  
BKP Berolina Polyester GmbH Co. KG Technical Data, Sep. 5, 2003, pp. 1-101.  
BKP Berolina Polyester GmbH Co. KG Technical Data, Sep. 5, 2003, pp. 102-202.

\* cited by examiner



FIG. 1









FIG. 3





**1****PIPE LINER AND METHOD OF MAKING  
SAME**

## FIELD

The present invention generally relates to a cured-in-place pipe liner and, more specifically, to cured-in-place pipe liner comprising strengthening fibers.

## BACKGROUND

Over time or because of a particular event or condition (e.g., seismic activity, exposure to excessive or uneven loads or moments, poor compaction, crown corrosion, corrosive soil, etc.), the structural integrity or capacity of force mains, other pipes, and like structures may diminish. For example, such items may crack, corrode, deteriorate, and the like. Damage to a pipe is particularly problematic when the pipe is used to carry a high pressure fluid because the pressurized fluid can impart significant forces, particularly in the hoop direction, on the pipe. Different methods of repairing or otherwise strengthening damaged pipes and other items are known. For example, reinforced fabric liners can be attached to one or more portions of a pipe interior. In cured-in-place pipe (CIPP) lining applications, liners are impregnated with a curable resin or epoxy, positioned along the interior surface of a host pipe, and allowed to cure, thereby forming a watertight barrier between the host pipe and the pipe interior. Various techniques for positioning a CIPP liner inside a host pipe (e.g., eversion, pull-in and inflate, etc.) and curing the liner (e.g., steam curing, ultraviolet light curing, etc.) are known. In addition, CIPP liners have been formed from various materials that have been constructed in many different ways. For example, it is known to form pressure-bearing liners from mats and fabrics that are laden with strengthening fibers such as glass fibers, etc.

## SUMMARY

In one aspect, an eversion liner for lining a pipe comprises an outer impermeable portion having an interior. The outer impermeable portion comprises a fluid-impermeable material. The fluid impermeable material is formed into a longitudinally extending tube. The liner comprises inner and outer strength portions. The outer strength portion is located in the interior of the outer impermeable portion. Each of the inner and outer strength portions has an interior. Each of the inner and outer portions is arranged to form a respective longitudinally extending tube and comprises strengthening fibers. At least one of the inner and outer strength portions comprises a unitary sheet of strength material. The sheet of strength material has a width and opposite first and second longitudinal edge margins spaced apart along the width. The sheet of strength material comprises chopped strands of fiber oriented generally parallel to one another and distributed along the sheet of strength material. The first and second longitudinal edge margins of the sheet of strength material are positioned in overlapping engagement. The at least one of the inner and outer strength portions comprises joining structure connecting the first and second longitudinal edge margins of the sheet of strength material together in overlapped relation to form a longitudinal overlap portion extending parallel to a length of the at least one of the inner and outer strength portions. A middle portion has an interior. The middle portion comprises felt. The felt is formed into a longitudinally extending tube. The middle portion is located

**2**

in the interior of the outer strength portion. The inner strength portion is located in the interior of the middle portion.

In another aspect, a method of manufacturing a liner for lining a pipe comprises forming a first strength tube comprising strengthening fibers. At least one felt tube is formed around the first strength tube. A second strength tube comprising strengthening fibers is formed around the at least one felt tube. An impermeable tube is formed around the second strength tube. At least one of the steps of forming the first strength tube and forming the second strength tube comprises: arranging a unitary sheet of strength material so that a width of the sheet extends in a hoop direction of the respective one of the first strength tube and the second strength tube. The sheet of strength material comprises chopped strands of fiber oriented generally parallel to one another and distributed along the sheet of strength material. First and second longitudinal edge margins of the sheet are joined together in overlapped relation to form a longitudinal overlap portion extending parallel to a length of the respective one of the first strength tube and the second strength tube.

Other objects and features will be in part apparent and in part pointed out hereinafter.

## BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a fragmentary perspective of a liner;  
FIG. 2 is a schematic cross section of the liner; and  
FIG. 3 is a schematic fragmentary top plan view of a sheet of material for forming a strength layer of the liner.  
Corresponding reference characters indicate corresponding parts throughout the drawings.

## DETAILED DESCRIPTION

Referring to FIG. 1, one embodiment of a liner for being cured in place inside a host pipe (not shown) is generally indicated at reference number **10**. The illustrated liner **10** is configured to be installed by eversion. It is understood that aspects of the disclosure could be adapted for use with liners that are installed by other methods without departing from the scope of the invention. The liner **10** has a first end and a second end spaced apart along a length *L* of the liner. As will be explained in further detail below, the liner **10** comprises an outer portion **12**, an outer strength portion **14** nested in the outer portion, a middle portion **16** nested in the outer strength portion, and an inner strength portion **18** nested in the middle portion. Each of the outer portion **12**, the outer strength portion **14**, the middle portion **16**, and the inner strength portions **18** comprises one or more flexible tubes in the illustrated embodiment. The tubes are nested in a concentric arrangement to form the liner **10**. Prior to installation, the inner strength portion **18** defines the interior of the liner **10**, but after the liner is everted into a host pipe, the outer portion **12** defines the liquid flow passage of the installed liner. Throughout this disclosure the terms “inner” and “outer” (as well as other similar terminology) are used in reference to the arrangement of the liner **10** prior to eversion and as shown in the drawings. As will be described in further detail below, the illustrated liner **10** is configured so that the discrete portions **12**, **14**, **18**, **16** are connected to one another so that liner can be reliably everted into a host pipe as a single unit. Furthermore, as discussed below, the strengthening portions **14**, **18** of the liner **10** are configured to provide the installed liner with standalone pressure-



bearing capacity and, moreover, do so substantially without creating wrinkles in the installed liner.

Referring to FIG. 2, the outer portion 12 has a length that extends from the first end to the second end of the liner 10 and comprises a coated felt that is formed into a tube that extends along the length of the outer portion. The outer portion 12 comprises an inner layer of felt 12A (e.g., non-woven threads that are needle-punched, matted, condensed, or otherwise pressed together) and a fluid-impermeable coating 12B. The coating 12B can be formed by a polymer that is applied to the felt 12A in fluidic form and then cured to permanently bond to the felt. Alternatively, the coating 12B can be formed from an impermeable polymer film that is permanently bonded to the felt 12A using an adhesive, heat, etc., such that there is a bond between the coating and the felt that is substantially continuous along substantially the entire surface area of the felt. The felt 12A comprises a resin-impregnable material such as polyester felt. The impermeable coating 12B can comprise a polymer, for example a polyolefin, such as polyethylene or polypropylene; a vinyl polymer, such as polyvinylchloride; or a polyurethane. Exemplary methods of forming a coated felt outer portion 12 are described in U.S. Pat. Nos. 7,857,932, 7,261,788, and 7,238,251, each of which is hereby incorporated by reference in its entirety.

To form the outer portion 12 to a desired length, multiple sheets of coated felt are arranged end-to-end and joined together at adjoining end margins. The sheet of coated felt is folded into a tube such that side margins of the sheet engage one another, the felt layer 12A defines the interior of the tube, and the impermeable coating 12B defines the exterior of the tube. The side margins are joined together at a seam 19 (e.g., a butt seam, an overlap seam, etc.) by joining structure such as stitching, an adhesive bond, a flame bond, etc. In the illustrated embodiment, the seam 19 extends lengthwise of the outer portion 12. A fluid-impermeable tape 20 is applied to the exterior surface of the outer portion 12 along the length of the seam 19. The tape 20 can be heat-bonded or chemically bonded to the exterior surface of the outer portion 12 in certain embodiments. The tape 20 seals the seam 19 so that the outer portion 12 provides a fluid-impermeable barrier.

The coating 12B on the outer portion 12 is preferably airtight and the tape 20 provides a fluid seal of the seam 19 so that the liner can be everted and expanded into contact with the pipe by fluid pressure. Suitably, the coated felt that forms the outer portion 12 is configured to stretch circumferentially when the liner 10 is expanded radially from a first diameter to a larger second diameter. When the liner 10 expands radially during installation, the coated felt stretches circumferentially while the seam 19 remains intact and sealed by the tape 20. After being everted into a host pipe, the coating 12B defines a substantially smooth, watertight surface, which extends continuously along the interior of the installed liner 10.

In the illustrated embodiment, each of the strength portions 14, 18 is formed from the same type of material and is assembled in the same general manner. It will be understood that, in other embodiments, the strength portions could have different configurations without departing from the scope of the invention. Each strength portion 14, 18 has a length extending from the first end to the second end of the liner 10 and comprises a multilayer composite material formed into a tube that extends along the length of the respective strength portion. The outer strength portion 14 extends longitudinally through the interior of the outer portion 12 and defines a longitudinal interior of its own. The middle portion 16

extends longitudinally through the interior of the outer strength portion 14, and the inner strength portion 18 extends longitudinally through the interior of the middle portion. Although the illustrated liner 10 includes an outer strength portion 14 concentrically arranged between an outer portion 12 and a middle portion 16 and an inner strength portion 18 nested inside the middle portion, other embodiments can include other numbers and arrangements of strength portions.

Referring to FIG. 3, each strength portion 14, 18 is formed from a sheet 30 of a multilayer composite fabric. FIG. 3 has been broken away to illustrate its constituent layers. It is understood that, in order to be of a desired total length, each strength portion 14, 18 could also be formed multiple sheets that are connected together in an end-to-end arrangement. Each sheet 30 has first and second end margins spaced apart along a length LS. In the assembled liner 10, the length LS of the sheet 30 extends along a length L of the liner. Each sheet 30 also has first and second side margins spaced apart along a width W. In the assembled liner 10, the width W of each sheet extends in the hoop direction (e.g., about the circumference) of the liner. To form each of the strength portions 14, 18, the respective sheet is folded into a tube such that the side margins engage one another and are joined together at a respective seam 52, 54 (FIG. 2) that is circumferentially offset from the other seam and from the seam 19 of the outer portion 12.

The multilayer sheet 30 comprises a first impregnation layer 32 formed from resin-impregnable material, a second impregnation layer 34 formed from resin-impregnable material, and a strength layer 36 that includes strengthening fibers received between the impregnation layers. In the illustrated embodiment, the strength layer 36 is also configured to be impregnated with resin or other curable polymer. Other strength portions can comprise other multilayer materials (e.g., a multilayer material comprising a single impregnation layer and one or more strength layers; two or more strength layers and impregnation layers; etc.) or a single-layer material.

In the illustrated embodiment, each of the impregnation layers 32, 34 is formed from a resin-impregnable felt, e.g., a polyester felt, which extends continuously along the length LS and width W of the sheet 30. In the illustrated embodiment, the non-woven fibers of the felt layers 32, 36 are needed to the strength layer 36 to secure the strength layer between the felt layers. Needling the felt layers 32, 34 to the strength layer 36 enables the composite fabric 30 to be handled as a unitary sheet of material when the liner 10 is assembled. The felt layers 32, 34 provide good resin-impregnation characteristics and also provide structure that is suitable for being handled by industrial sewing machines when forming the composite fabric 30 into the respective tube 14, 18. An exemplary material for the felt layers 32, 34 is polyester felt. Such felts are used by Aegion Corporation of St. Louis, Mo., in various cured-in-place pipe lining products such as, for example, InsituMain® pipe liners. Other types of felts or other resin-impregnable materials can be used to form the impregnation layer(s) of the strength portions without departing from the scope of the invention.

Suitably, the strength layer 36 comprises strengthening fibers, such as glass fibers, carbon fibers, etc. The strength layer 36 extends continuously along the length LS and width W of the fabric sheet 30. In the illustrated embodiment, the strength layer 36 is formed from first, second, and third sublayers 36i, 36ii, 36iii, and each of the sublayers extends along the length LS and width W of the fabric sheet 30. In the illustrated embodiment, the first sublayer 36i is a mat



formed from randomly oriented chopped fibers **42** distributed throughout the strength layer **36**. The second sublayer **36ii** is formed from continuous fibers **44** oriented generally parallel to the length LS and distributed throughout the strength layer **36**, and the third sublayer **36iii** is formed from long oriented chop material containing long fibers **46** oriented generally parallel to one another and transverse to the continuous fibers and distributed throughout the strength layer. In the illustrated embodiment the sublayer of long oriented chopped fibers **46** is sandwiched between the sublayers of random oriented fibers **42** and continuous fibers **46**; however, other arrangements of the sublayers are also possible without departing from the scope of the invention. The different types of fibers **42**, **44**, **46** are illustrated schematically in FIGS. **2** and **3**. It will be understood that the strength layers can have other configurations in other embodiments

The chopped fibers **42** are matted together in random orientations to form the sublayer **36i** of the strength layer **36**. The random oriented chopped fibers **42** are loosely held together in a mat such that they can shift relative to one another and allow the sublayer **36i** to stretch circumferentially as the liner **10** expands radially. The random oriented fibers **42** are configured to enhance the strength of the respective strength portion **14**, **18** in a non-directional manner (e.g., the random oriented fibers strengthen the liner **10** in a hoop direction and also in other directions). Moreover, as described in further detail below, the mat of random oriented fibers **42** provides a backing structure to which the bundles of fibers **44**, **46** are secured to form the strength layer **36**. Securing the bundles of fibers **44**, **46** to the sublayer **36i** of randomly oriented fibers **42** allows sheet material including the three sublayers **36i**, **36ii**, **36iii** of strengthening fibers to be handled independently during manufacturing before it is needled or otherwise secured to one or both of the felt layers **32**, **34**.

In the illustrated embodiment the continuous fibers **44** are arranged in bundles that extend continuously along the length LS of each sheet **30**. The bundles of continuous fibers **44** are spaced apart along the width W of the sheet **30**. When the sheet is formed into the respective one of the outer and inner strength portions **14**, **18**, the bundles of continuous fibers **44** are spaced apart about the circumference of the respective strength portion. The bundles of continuous fibers **44** can move along the width W of the sheet **30** and about the circumference of the respective strength portion **14**, **18** so that each strength portion can stretch circumferentially when the liner **10** expands radially. The illustrated continuous fibers **44** form a one-bundle-thick sublayer **36ii** of fibers, but in other embodiments the bundles of continuous fibers can be stacked to form a sublayer of continuous fibers that is more than one bundle in thickness. The continuous fibers **44** provide longitudinal reinforcement of the sheet **30** and thus provide longitudinal reinforcement of the liner **10**.

The long fibers **46** in the sublayer **36iii** of the illustrated strength layer **36** extend generally parallel to the width W of the sheet **30**. More specifically, the long fibers **46** are arranged in bundles extending generally parallel to the width of the sheet. The individual long fibers **46** thus extend generally parallel to the bundles of which they are a part. The bundles of long oriented chop fibers **46** are spaced apart from one another along the length LS of the sheet **30** to form the middle sublayer **36iii** of the strength layer **36**. The illustrated long fibers **46** form a one-bundle-thick sublayer **36iii** of fibers, but in other embodiments the bundles of chopped fibers can be stacked to form a sublayer that is more than one bundle in thickness. The illustrated bundles of long

fibers **46** are oriented generally perpendicular to the bundles of continuous fibers **44**. In each of the assembled strength portions **14**, **18**, the bundles of long fibers **46** are spaced apart along the length of the respective strength portion and extend in the hoop direction (about the circumference of the respective strength portion) to circumferentially reinforce the liner **10**. In the illustrated embodiment, each bundle of long fibers **46** extends about the entire circumference of the respective strength portion **14**, **18**. Each long fiber **46** has a length that is long in comparison to random oriented fibers **42**, but is less than the width W of the sheet **30** and the circumference of the respective strength portion **14**, **18**. The fibers **46** can all have the same length or have different lengths without departing from the scope of the invention. Although the chopped fibers **46** are arranged in bundles in the illustrated embodiment, circumferentially oriented chopped fibers can also be supported in the strength layer without being arranged in bundles in other embodiments.

Referring to FIG. **2**, because the bundles in each sublayer **36iii** are formed from long fibers **46** instead of continuous fibers, each of the strength portions **14**, **18** can stretch circumferentially when the liner **10** expands radially. In each strength layer **36**, the long fibers **46** are held together loosely so that they can move relative to one another within each respective bundle in directions parallel to their lengths, along the circumference of the liner **10**. Since the long fibers **46** can move relative to one another along their lengths, the middle sublayer **36iii** of the strength layer **36** of each strength portion **14**, **18** can be stretched circumferentially when the liner **10** expands radially. Since the felt layers **32**, **34** and inner and outer sublayers **36i**, **36ii** of the strength layer **36** are also formed from circumferentially stretchable material as explained above, each strength portion **14**, **18** is configured to stretch circumferentially as the diameter of the liner **10** increases when it is expanded during eversion.

In the illustrated embodiment stitching **50** loosely secures the bundled long fibers **46** and bundled continuous fibers **44** to the mat of random oriented fibers **42** to form the strength layer **36**. But in other embodiments, other ways of loosely securing the strengthening fibers can be used without departing from the scope of the invention. The stitching **50** is sufficiently loose to permit the long fibers **46** within each circumferential bundle to move relative to one another along the circumference of the strength layer **36** but is sufficiently strong to hold the fibers **42**, **44**, **46** of the strength layer together during manufacturing. The stitching **50** is also configured to allow the random oriented fibers **42** to shift and the bundles of continuous fibers **44** to move circumferentially of the liner **10** during installation. Thus, the stitching **50** is configured to maintain the general arrangement of the strengthening fibers **42**, **44**, **46** during installation while permitting the strengthening fibers to move as required to facilitate circumferential stretching of the strength layer **36** when the liner **10** is radially expanded.

In each strength portion **14**, **18**, the composite fabric sheet **30** is folded so that the side margins of the fabric sheet overlap one another at a respective seam **52**, **54**. Each seam thus comprises an overlap portion that extends generally along the length L of the liner **10**. In the illustrated embodiment, overlap stitching **56**, **58** secures the overlapping side margins of the respective sheet **30** together in each strength portion **14**, **18**. In other embodiments, the overlapped side margins could be secured together by other types of joining structure, e.g., a heat bond, an adhesive bond, etc.

Each overlap portion **52**, **54** has a width WO1, WO2. In certain embodiments each width WO1, WO2 is in an inclusive range of from about 1.5 inches (3.8 cm) to about 2.5



inches (6.46 cm). Widths in this range can be suitable for using an industrial sewing machine to stitch the overlap portion 52, 54. However, it will be understood that overlap portions of other widths can be used in other embodiments. The stitching 56, 58 allows the tube to expand circumferentially without breaking the respective seam 52, 54. Because the impregnation layers 32, 34 and strength layer 36 are configured to stretch circumferentially, when each strength layer 14, 18 expands from a first diameter to a larger second diameter during installation, the width WO1, WO2 of the respective longitudinal overlap portion 52, 54 does not decrease. Instead the width WO1, WO2 of the respective longitudinal overlap portion 52, 54 either stays the same or increases, increasing proportionally with the increase in circumference of the respective strength portion 14, 18. The stitching 56, 58 holds the longitudinal side margins of the sheet 30 together at each seam 52, 54 even after the diameter of the respective strength portion 14, 18 increases.

In one or more embodiments, each overlap portion 52, 54 is reinforced with a reinforcing strip 60, 62. The reinforcing strips 60, 62 can comprise any suitable reinforcing material. In certain embodiments, each reinforcing strip 60, 62 comprises a two-layer material comprising a felt layer and a fibrous layer that is needle punched or otherwise secured to the felt layer. In one embodiment, the reinforcing strip 60, 62 is attached to the outer felt layer 34 of the respective strength portion 14, 18 at locations on opposite sides of the overlap seam 52, 54, e.g., by flame bonds, adhesive bonds, stitching, etc. In certain embodiments, each reinforcing strip 60, 62 extends continuously along the length of the respective strength portion 14, 18. Each reinforcing strip 60, 62 can be bonded to the outer felt layer 34 of the respective strength portion 14, 18 on opposite sides of the seam 52, 54 continuously along, or at spaced apart locations along, the length of the respective strength portion.

The middle portion 16 has a length extending from the first end to the second end of the liner 10 and comprises felt formed into a tube having an interior. As explained above, the middle portion 16 extends longitudinally through the interior of the outer strength layer 14, and the inner strength layer 18 extends longitudinally through the interior of the middle portion. The middle portion 16 comprises one or more discrete felt layers 16A, 16B, each formed into a discrete felt tube. The felt tubes 16A, 16B are each configured to be impregnated with a curable polymer such as resin. In the illustrated embodiment, the middle portion 16 comprises two discrete felt tubes 16A, 16B that are arranged concentrically. It will be understood that the middle portion of other liners can have other numbers of felt tubes (for example zero or more felt tubes, e.g., a number of felt tubes in an inclusive range of from 1 to 5, etc.)

Each discrete felt layer 16A, 16B comprises a sheet of felt (or a plurality of sheets of felt arranged end-to-end) having first and second end margins spaced apart along a length that extends along the length of the middle portion 16 and first and second side margins spaced apart along a width that extends about a circumference of the middle portion. Each felt sheet 16A, 16B is folded into a tube such that the side margins of the sheet engage one another and are joined together at a respective seam 66, 68. In the illustrated embodiment, the side margins are joined together at a stitched butt seam, but the side margins can be joined together in other ways without departing from the scope of the invention. Suitably, each seam 66, 68 is configured to withstand circumferential stretching of the middle portion 16 as the liner 10 expands radially during installation. In one

or more embodiments, all of the seams 19, 52, 54, 66, 68 in the liner 10 are offset circumferentially from one another.

In the illustrated embodiment, the outer portion 12, the outer strength portion 14, each of the middle felt tubes 16A, 16B, and the inner strength portion 18 each comprises a respective tube of the liner 10. The individual tubes 12, 14, 16A, 16B, 18 included in the liner 10 are bonded together at bonds 70A-70D. In one or more embodiments, each of the bonds 70A-70D extends continuously or intermittently along the length L of the liner 10. The outer portion 12 of the liner is bonded to the outer felt layer 32 of the outer strength portion 14 at a bond 70A; the inner felt layer 34 of the outer strength portion is bonded to the outer felt tube 16A at a bond 70B, the outer felt tube is bonded to the inner felt tube 16B at a bond 70C; and the inner felt tube is bonded to the outer felt layer 32 of the inner strength layer 18 at a bond 70D. Because the opposing surfaces the tubes 12, 14, 16A, 16B, 18 are all formed of felt material, the bonds 70A-70D can comprise flame bonds. In other words, in the illustrated embodiment, each discrete tube 12, 14, 16A, 16B, 18 is flame bonded to an adjacent tube to form a unitary liner 10. It will be understood that other types of bonds (e.g., adhesive bonds, a mix of flame bonds and adhesive bonds, etc.) can also be used to secure together two or more tubes of a liner in other embodiments.

In an exemplary method of manufacturing the liner 10, the manufacturer folds a composite fabric sheet 30 into an inner strength tube 18 so that the longitudinal side margins overlap one another at an overlap seam 54. The manufacturer guides the inner strength tube 18 through a stitching machine to stitch the side margins together along the overlap seam 54. The manufacturer then bonds the reinforcing strip 62 to the overlap portion 54 using an adhesive bond, a flame bond, etc.

After forming the inner strength tube 18, the manufacturer wraps one or more sheets of felt 16A, 16B around it to form the middle portion 16. In one embodiment, the manufacturer guides each sheet of felt through a stitching machine to stitch together the longitudinal side margins at the seams 66, 68. Suitably, the manufacturer wraps each felt sheet so that the seams 66, 68 are circumferentially spaced from the seam 54 of the inner strength tube 18. Each felt tube 16A, 16B is also flame bonded to the tube that is received in its interior. For example, in the illustrated embodiment, the manufacturer flame bonds the felt tube 16B to the inner strength portion 18 at flame bond 70D and flame bonds the felt tube 16A to the other felt tube at flame bond 70C.

After the desired number of felt tubes is/are formed and flame bonded to the inner strength portion 18, the manufacturer wraps another composite fabric sheet 30 around the middle portion 16 to form the outer strength tube 14. The manufacturer folds the sheet 30 around the middle portion 16 so that the longitudinal side margins of the sheet overlap one another at an overlap seam 52. Suitably, the manufacturer wraps the composite fabric sheet 30 so that the overlap seam 52 is circumferentially spaced from the overlap seam 54 and each of the seams 66, 68. The manufacturer guides the outer strength tube 14 through a stitching machine to stitch together the longitudinal side margins of the composite fabric sheet 30 along the overlap seam 52. The manufacturer then bonds the reinforcing strip 60 to the overlap seam 52 using an adhesive bond, a flame bond, etc. The outer strength tube 14 is also flame bonded to the outer felt tube 16A at a flame bond 70B.

The manufacturer then wraps a sheet of coated felt around the outer strength tube 14 to form the outer tube 12. Specifically, the manufacturer folds the coated felt around



the outer strength tube **14** so that the longitudinal side margins engage one another and the coating **12B** defines the exterior of the tube. The manufacturer guides the coated felt tube **12** through a stitching machine to stitch together the side margins of the material at the seam **19**. The manufacturer then applies impermeable tape **20** along the seam **19** to seal the seam.

To install the liner **10** in a host pipe (not shown), the liner is initially impregnated with curable polymer such as resin. Various techniques for impregnating a liner with curable polymer are known or may become known, and any suitable technique can be used without departing from the scope of the invention. For example, a resin impregnation system is disclosed in U.S. Pat. No. 7,238,251, which is hereby incorporated by reference in its entirety. In one embodiment, the step of impregnating the liner **10** with resin is performed at a factory remote from the host pipe and the impregnated liner is transported to the site of the host pipe in a suitably climate controlled truck. In other embodiments, the crew could impregnate the liner **10** at the site of the host pipe without departing from the scope of the invention. Suitably, the step of impregnating the liner **10** with resin distributes resin throughout the felt layer **12A** of the outer tube **12**, each of the layers **32**, **34**, **36** of the outer strength tube **14**, each of the felt tubes **16A**, **16B**, and each of the layers **32**, **34**, **36** of the inner strength tube **18**, as well as through each of the reinforcing strips **60**, **62**.

After the liner **10** is impregnated with resin, the crew installs the liner inside the host pipe by everting the liner. In the eversion process, the liner **10** is turned inside out, advancing down the host pipe as more of the liner is everted. The eversion process presses the inner strength portion **18** against the interior surface of the host pipe and causes the coating **12B** of the outer portion **12** to become the interior surface of the lined pipe. Thus, after eversion is complete, the impermeable coating **12B** provides a resin barrier that prevents the resin in the liner **10** from escaping into the interior of the pipe. During the eversion process, the flame bonds **70A-70D** maintain secure connections among the discrete tubes **12**, **14**, **16A**, **16B**, **18** such that liner retains its structure and can be everted as a single unit. Various techniques for everting the liner **10** are known or may become known, and any suitable technique can be used without departing from the scope of the invention. For example, systems for everting a liner are disclosed in U.S. Pat. Nos. 9,453,597, 8,066,499, 7,866,968, and 7,766,048, each of which is hereby incorporated by reference in its entirety.

Prior to eversion, the liner **10** and each of the tubes **12**, **14**, **16A**, **16B**, **18** has a respective initial diameter. The eversion process stretches the liner **10** and each tube **12**, **14**, **16A**, **16B**, **18** from its initial diameter to a larger second diameter. As explained above, the arrangement of strengthening fibers **42**, **44**, **46** within each of the strength portions **14**, **18** allows the strength portion to stretch circumferentially without reducing the width **WO1**, **WO2** of the respective overlap portion **52**, **54**. The stretching of the liner **10** helps prevent wrinkles from forming as the liner is positioned in contact with the interior surface of the host pipe **10**. Thus, after eversion is complete, the impermeable coating **12B** forms a smooth surface along which liquid may flow with minimal drag. The continuous fibers **44** resist elongation of the liner **10**.

Once the liner **10** is positioned in continuous contact with the interior surface of the host pipe, the resin in the liner cures to form a cured-in-place liner along the interior surface of the host pipe. In certain embodiments, the resin cures in

ambient conditions. In other embodiments, the crew cures the resin by directing a suitable form of curing energy, such as heat, ultraviolet radiation, etc., toward the resin impregnated liner **10**. Various techniques for curing a resin-impregnated liner are known or may become known, and any suitable technique can be used without departing from the scope of the invention. For example, curing systems are disclosed in several of the U.S. Patents incorporated by reference above, as well as in U.S. Pat. No. 7,360,559, each of which is hereby incorporated by reference in its entirety.

The cured resin strongly binds each of the tubes **12**, **14**, **16A**, **16B**, **18** together after the installed liner **10** is put into service. Furthermore, the strength layers **36** (in particular, the circumferentially oriented fibers **46**) of the inner and outer strength tubes **14**, **18** circumferentially reinforce the host pipe to withstand internal loads (e.g., internal fluid pressures, etc.) and/or external loads (e.g., seismic loads, etc.). As can be seen therefore, the liner **10** can be installed by eversion and provide a new, high strength pipe inside a host pipe that defines a substantially smooth, watertight flow passage.

Having described the invention in detail, it will be apparent that modifications and variations are possible without departing from the scope of the invention defined in the appended claims.

As various changes could be made in the above constructions and methods without departing from the scope of the invention, it is intended that all matter contained in the above description and shown in the accompanying drawings shall be interpreted as illustrative and not in a limiting sense.

What is claimed is:

**1.** An eversion liner for lining a pipe, the liner comprising: an outer impermeable portion having an interior, the outer impermeable portion comprising a fluid-impermeable material, the fluid impermeable material being formed into a longitudinally extending tube;

inner and outer strength portions, the outer strength portion being located in the interior of the outer impermeable portion, each of the inner and outer strength portions having an interior, each of the inner and outer portions being arranged to form a respective longitudinally extending tube and comprising strengthening fibers, at least one of the inner and outer strength portions comprising a unitary sheet of strength material, the sheet of strength material having a width and opposite first and second longitudinal edge margins spaced apart along the width, the sheet of strength material comprising chopped strands of fiber gathered into bundles, the bundles being oriented generally parallel to one another and distributed along the sheet of strength material, each of the bundles extending in a direction from the first longitudinal edge margin to the second longitudinal edge margin of the sheet of strength material, the first and second longitudinal edge margins of the sheet of strength material being positioned adjacent one another and being attached to one another at a seam, the sheet of strength material being configured for being stretched radially from a first external diameter to a second external diameter larger than the first external diameter, the seam being constructed to hold the first longitudinal edge margin from moving in a circumferential direction relative to the second longitudinal edge margin as the liner tube is stretched radially from the first external diameter to the second external diameter; and

a middle portion having an interior, the middle portion comprising felt, the felt being formed into a longitudi-



## 11

nally extending tube, the middle portion being located in the interior of the outer strength portion, the inner strength portion being located in the interior of the middle portion.

2. An eversion liner as set forth in claim 1, wherein the chopped strands of fiber are arranged to strengthen the liner in a hoop direction of the liner.

3. An eversion liner as set forth in claim 1, wherein the chopped strands of fiber extend generally parallel to the width of the sheet of strength material.

4. An eversion liner as set forth in claim 1, wherein the sheet of strength material further comprises an inner felt layer and an outer felt layer, the chopped strands of fiber being sandwiched between the inner and outer felt layers.

5. An eversion liner as set forth in claim 4, wherein the inner and outer felt layers are needle punched to the chopped strands of fiber.

6. An eversion liner as set forth in claim 4, wherein one of the inner and outer felt layers is flame bonded to the middle portion.

7. An eversion liner as set forth in claim 1, wherein the sheet of strength material further comprises continuous strands of fiber distributed along the sheet of strength material, the continuous strands of fiber being oriented parallel to one another and transverse to the chopped strands of fiber.

8. An eversion liner as set forth in claim 1, wherein the sheet of strength material further comprises a mat of random oriented chopped fibers.

9. An eversion liner as set forth in claim 1, wherein the longitudinal edge margins of the sheet of strength material are positioned in overlapping engagement the longitudinal to form an overlap portion having a width, the eversion liner being configured to be everted into a host pipe such that the at least one of the inner and outer strength portions expands from a first diameter to a larger second diameter without decreasing the width of the longitudinal overlap portion.

10. An eversion liner as set forth in claim 9, wherein the longitudinal overlap portion of has a width of at least about 3.8 cm.

11. An eversion liner as set forth in claim 1, wherein the seam comprises stitching.

12. An eversion liner as set forth in claim 1, wherein the at least one of the inner and outer strength portions further comprises a reinforcing strip, the reinforcing strip extending along the longitudinal overlap portion and being attached to the sheet of strength material at locations adjacent each of the first and second longitudinal edge margins.

13. An eversion liner as set forth in claim 1, wherein the middle portion comprises a plurality of discrete felt layers.

14. An eversion liner as set forth in claim 1, wherein each of the discrete felt layers is flame bonded to an adjacent one of the other discrete felt layers.

## 12

15. An eversion liner as set forth in claim 1, wherein the middle portion comprises a number of discrete felt layers in an inclusive range of from 1 to 5 discrete felt layers.

16. An eversion liner as set forth in claim 1, wherein the fluid-impermeable material comprises coated felt.

17. An eversion liner as set forth in claim 1, wherein the at least one of the inner and outer strength portions includes each of the inner and outer strength portions.

18. A method of manufacturing a liner for lining a pipe, the method comprising:

forming a first strength tube comprising strengthening fibers;

forming at least one felt tube around the first strength tube;

forming a second strength tube comprising strengthening fibers around the at least one felt tube; and

forming an impermeable tube around the second strength tube;

wherein at least one of the steps of forming the first strength tube and forming the second strength tube comprises:

arranging a unitary sheet of strength material so that a width of the sheet extends in a hoop direction of the respective one of the first strength tube and the second strength tube, the sheet of strength material comprising chopped strands of fiber gathered into bundles, the bundles being oriented generally parallel to one another and distributed along the sheet of strength material, each of the bundles extending in a direction from the first longitudinal edge margin to the second longitudinal edge margin of the sheet of strength material; and

joining first and second longitudinal edge margins of the sheet together in overlapped relation to form a longitudinal overlap portion extending parallel to a length of the respective one of the first strength tube and the second strength tube at a seam, the seam being constructed to hold the first longitudinal edge margin from moving in a circumferential direction relative to the second longitudinal edge margin as the liner is stretched radially from the first external diameter to the second external diameter.

19. A method as set forth in claim 18, wherein the at least one of the steps of forming the first strength tube and forming the second strength tube further comprises needle punching the chopped strands of fiber between two layers of felt.

20. A method as set forth in claim 18, further comprising flame bonding the at least one felt tube to each of the first strength tube and the second strength tube.

\* \* \* \* \*