



US010825689B2

(12) **United States Patent**
Cheng

(10) **Patent No.:** **US 10,825,689 B2**

(45) **Date of Patent:** **Nov. 3, 2020**

(54) **METHOD OF FABRICATING SEMICONDUCTOR FINs BY ENHANCING OXIDATION OF SACRIFICIAL MANDRELS SIDEWALLS THROUGH ANGLED ION BEAM EXPOSURE**

(71) Applicant: **TESSERA, INC.**, San Jose, CA (US)

(72) Inventor: **Kanguo Cheng**, Schenectady, NY (US)

(73) Assignee: **Tessera, Inc.**, San Jose, CA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **16/040,093**

(22) Filed: **Jul. 19, 2018**

(65) **Prior Publication Data**

US 2018/0323073 A1 Nov. 8, 2018

Related U.S. Application Data

(63) Continuation of application No. 15/647,689, filed on Jul. 12, 2017, now Pat. No. 10,083,839, which is a (Continued)

(51) **Int. Cl.**
H01L 21/308 (2006.01)
H01L 27/12 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 21/3088** (2013.01); **H01L 21/0337** (2013.01); **H01L 21/26506** (2013.01);
(Continued)

(58) **Field of Classification Search**

CPC H01L 21/823431; H01L 21/823821; H01L 21/845; H01L 27/0886; H01L 27/0924; H01L 27/1211; H01L 27/10826; H01L 27/10879; H01L 29/41791; H01L 29/66795-66818; H01L 29/785-7856;

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,063,688 A * 5/2000 Doyle B82Y 10/00 257/E21.038
6,875,703 B1 * 4/2005 Furukawa H01L 21/0337 257/E21.038

(Continued)

OTHER PUBLICATIONS

List of IBM Patents or Patent Applications Treated as Related dated Jul. 19, 2018, 2 pages.


(Continued)

Primary Examiner — Younes Boulghassoul

(57) **ABSTRACT**

A method of fabricating semiconductor fins, including, patterning a film stack to produce one or more sacrificial mandrels having sidewalls, exposing the sidewall on one side of the one or more sacrificial mandrels to an ion beam to make the exposed sidewall more susceptible to oxidation, oxidizing the opposite sidewalls of the one or more sacrificial mandrels to form a plurality of oxide pillars, removing the one or more sacrificial mandrels, forming spacers on opposite sides of each of the plurality of oxide pillars to produce a spacer pattern, removing the plurality of oxide pillars, and transferring the spacer pattern to the substrate to produce a plurality of fins.

10 Claims, 10 Drawing Sheets



Related U.S. Application Data

continuation of application No. 15/077,538, filed on Mar. 22, 2016, now Pat. No. 9,852,917.

(51) **Int. Cl.**

H01L 21/8234 (2006.01)
H01L 21/033 (2006.01)
H01L 21/311 (2006.01)
H01L 21/321 (2006.01)
H01L 29/66 (2006.01)
H01L 21/8238 (2006.01)
H01L 27/092 (2006.01)
H01L 21/265 (2006.01)
H01L 21/426 (2006.01)
H01L 21/3065 (2006.01)
H01L 27/11 (2006.01)
H01L 29/78 (2006.01)
H01L 29/786 (2006.01)

(52) **U.S. Cl.**

CPC *H01L 21/3065* (2013.01); *H01L 21/3081* (2013.01); *H01L 21/3085* (2013.01); *H01L 21/3086* (2013.01); *H01L 21/31138* (2013.01); *H01L 21/32105* (2013.01); *H01L 21/426* (2013.01); *H01L 21/823468* (2013.01); *H01L 21/823821* (2013.01); *H01L 27/0924* (2013.01); *H01L 27/1211* (2013.01); *H01L 29/66* (2013.01); *H01L 29/66795* (2013.01); *H01L 29/66818* (2013.01); *H01L 29/786* (2013.01); *H01L 29/7851* (2013.01); *H01L 27/1104* (2013.01)

(58) **Field of Classification Search**

CPC ... H01L 2029/7857-7858; H01L 2924/13067; H01L 29/42384-42392; H01L 29/0673; H01L 21/26506-2652; H01L 21/26586; H01L 21/31155; H01L 21/32155; H01L 21/425-426; H01L 29/66803; H01L 21/02236-02238; H01L 21/02255; H01L 21/32105; H01L 21/308-3088; H01L 21/033-0338; H01L 21/823468; H01L 29/6656; H01L 29/6653

See application file for complete search history.

(56)

References Cited

U.S. PATENT DOCUMENTS

7,763,531 B2 * 7/2010 Abadeer G01R 31/2831
 257/E21.421
 8,455,364 B2 6/2013 Kanakasabapathy

8,603,893 B1 * 12/2013 Wei H01L 21/76229
 257/E21.546
 8,669,167 B1 3/2014 Chang et al.
 8,822,320 B2 * 9/2014 Cheng H01L 21/3086
 257/288
 8,889,561 B2 11/2014 Woo et al.
 8,975,129 B1 * 3/2015 Shieh H01L 21/3086
 438/199
 9,034,723 B1 * 5/2015 Shieh H01L 21/30604
 438/424
 9,105,510 B2 8/2015 Woo et al.
 9,564,446 B1 * 2/2017 Weybright H01L 21/823431
 2007/0065990 A1 * 3/2007 Degroote H01L 21/0337
 438/142
 2008/0023803 A1 * 1/2008 Shi H01L 29/045
 257/623
 2008/0032506 A1 * 2/2008 Lee H01L 21/0337
 438/703
 2009/0124097 A1 * 5/2009 Cheng H01L 21/3086
 438/792
 2010/0203732 A1 * 8/2010 Doris H01L 21/3086
 438/694
 2011/0021010 A1 * 1/2011 Cheng H01L 21/2236
 438/513
 2011/0108961 A1 * 5/2011 Cheng H01L 21/033
 257/623
 2011/0127582 A1 * 6/2011 Cheng H01L 21/0337
 257/213
 2012/0235247 A1 * 9/2012 Cai H01L 21/3086
 257/392
 2014/0159164 A1 * 6/2014 Woo H01L 21/3086
 257/401
 2014/0273363 A1 * 9/2014 Chiu H01L 21/3086
 438/165
 2014/0353765 A1 12/2014 Woo et al.
 2015/0041812 A1 * 2/2015 Cheng H01L 27/0886
 257/57
 2015/0170927 A1 6/2015 Cheng et al.
 2015/0170973 A1 * 6/2015 Kim H01L 21/823821
 438/702
 2015/0294976 A1 * 10/2015 Kim H01L 27/1116
 438/702
 2015/0311085 A1 10/2015 Kozarsky et al.
 2016/0005596 A1 * 1/2016 Behera H01L 21/02115
 438/703
 2016/0111286 A1 * 4/2016 Wen H01L 27/0924
 438/492
 2016/0314983 A1 * 10/2016 Han H01L 21/3086
 2017/0004973 A1 * 1/2017 Kim H01L 21/3086

OTHER PUBLICATIONS

Office Action with cited art in corresponding U.S. Appl. No. 15/482,245 dated Sep. 11, 2018.

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8





FIG. 9

FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17

1

**METHOD OF FABRICATING
SEMICONDUCTOR FINS BY ENHANCING
OXIDATION OF SACRIFICIAL MANDRELS
SIDEWALLS THROUGH ANGLED ION
BEAM EXPOSURE**

BACKGROUND

Technical Field

The present invention relates to the fabrication of fins having variable pitch using spacers, and more particularly to a double sidewall image transfer technique involving variable width columns.

Description of the Related Art

A Field Effect Transistor (FET) typically has a source, a channel, and a drain, where current flows from the source to the drain, and a gate that controls the flow of current through the channel. Field Effect Transistors (FETs) can have a variety of different structures, for example, FETs have been formed with the source, channel, and drain formed in the substrate material itself, where the current flows horizontally (i.e., in the plane of the substrate), and FinFETs have been formed with the channel extending outward from the substrate, but where the current also flows horizontally. The channel for the FinFET can be an upright slab of thin rectangular Si, commonly referred to as the fin with a gate on the fin, as compared to a MOSFET with a single planar gate. Depending on the doping of the source and drain, an n-FET or a p-FET may be formed.

Examples of FETs can include a metal-oxide-semiconductor field effect transistor (MOSFET) and an insulated-gate field-effect transistor (IGFET). Two FETs also may be coupled to form a complementary metal oxide semiconductor (CMOS), where a p-channel MOSFET and n-channel MOSFET are connected in series.

With ever decreasing device dimensions, forming the individual components and electrical contacts become more difficult. An approach is therefore needed that retains the positive aspects of traditional FET structures, while overcoming the scaling issues created by forming smaller device components.

SUMMARY

A method of fabricating semiconductor fins, including, patterning a film stack to produce one or more sacrificial mandrels having sidewalls, exposing the sidewall on one side of the one or more sacrificial mandrels to an ion beam to make the exposed sidewall more susceptible to oxidation, oxidizing the opposite sidewalls of the one or more sacrificial mandrels to form a plurality of oxide pillars, removing the one or more sacrificial mandrels, forming spacers on opposite sides of each of the plurality of oxide pillars to produce a spacer pattern, removing the plurality of oxide pillars, and transferring the spacer pattern to the substrate to produce a plurality of fins.

A method of fabricating semiconductor fins, including, forming a film stack on a substrate, where the film stack includes a nitride layer on the substrate, an oxide layer, a sacrificial mandrel layer, and a capping layer; patterning the capping layer and sacrificial mandrel layer to produce one or more sacrificial mandrels having sidewalls; exposing the sidewall on one side of the one or more sacrificial mandrels to an ion beam to make the exposed sidewall more suscep-

2

tible to oxidation; oxidizing the sidewalls of the one or more sacrificial mandrels to form a plurality of oxide pillars; removing the one or more sacrificial mandrels; forming spacers on opposite sides of each of the plurality of oxide pillars to produce a spacer pattern; removing the plurality of oxide pillars; and transferring the spacer pattern to the substrate by etching the oxide layer, nitride layer and substrate.

An intermediate FinFET structure, including, a semiconductor substrate, a nitride layer on the semiconductor substrate, an oxide layer on the nitride layer, a sacrificial mandrel on the nitride layer, wherein the sacrificial mandrel has a width in the range of about 20 nm to about 400 nm, and a first oxide pillar on a first side of the sacrificial mandrel and a second oxide pillar on the opposite side of the sacrificial mandrel, wherein the first oxide pillar has a width in the range of about 15 nm to about 60 nm, and the second oxide pillar has a width in the range of about 10 nm to about 30 nm.

These and other features and advantages will become apparent from the following detailed description of illustrative embodiments thereof, which is to be read in connection with the accompanying drawings.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

The disclosure will provide details in the following description of preferred embodiments with reference to the following figures wherein:

FIG. 1 is a cross-sectional side view of a film stack on a substrate in accordance with an exemplary embodiment;

FIG. 2 is a cross-sectional side view of a substrate and film stack in accordance with an exemplary embodiment;

FIG. 3 is a cross-sectional side view of a patterned and etched film stack **105** in accordance with an exemplary embodiment;

FIG. 4 is a cross-sectional side view of a substrate and film stack exposed to an ion beam in accordance with an exemplary embodiment;

FIG. 5 is a cross-sectional side view of a substrate and preferentially doped sacrificial mandrels in accordance with an exemplary embodiment;

FIG. 6 is a cross-sectional side view of a substrate, sacrificial mandrels, and oxide pillars in accordance with an exemplary embodiment;

FIG. 7 is a cross-sectional side view of a substrate, sacrificial mandrels, and oxide pillars in accordance with an exemplary embodiment;

FIG. 8 is a cross-sectional side view of a substrate and oxide pillars in accordance with an exemplary embodiment;

FIG. 9 is a cross-sectional side view of a substrate, oxide pillars, and spacers in accordance with an exemplary embodiment;

FIG. 10 is a cross-sectional side view of a substrate and free-standing vertical spacers in accordance with an exemplary embodiment;

FIG. 11 is a cross-sectional side view of a substrate, oxide columns, and nitride columns in accordance with an exemplary embodiment;

FIG. 12 is a cross-sectional side view of a substrate, oxide and nitride columns, and fins in accordance with an exemplary embodiment;

FIG. 13 is a cross-sectional side view of fins and trenches partially filled with a dielectric in accordance with an exemplary embodiment;

3

FIG. 14 is a top view of fins in a predetermined pattern in accordance with an exemplary embodiment;

FIG. 15 is a top view of a static random access memory (SRAM) cell in accordance with an exemplary embodiment;

FIG. 16 is a cross-sectional side view of a film stack on a substrate in accordance with an exemplary embodiment; and

FIG. 17 is a cross-sectional side view of a substrate, spacers, oxide and nitride columns, and fins in accordance with an exemplary embodiment.

DETAILED DESCRIPTION

Principles and embodiments of the present disclosure relate to methods of fabricating vertical fins for FinFET devices, and to approaches of forming more closely spaced fins having variable pitch. Sidewall image transfer (SIT) involves a sacrificial mandrel that is formed, and the formation of spacers adjacent to the mandrels, where the width (i.e., thickness) of the spacers is less than the width possible through direct lithographic techniques. Instead, the width of the spacer(s) is controlled through chemical processes, such as the rate of oxidation of the mandrel material, or conformal sidewall depositions by ALD/CVD, where the reaction rate and/or spatial resolution is finer than lithographic resolution.

Further FinFET scaling involves finer control over the pitch between fins. Reduction in the width (i.e., thickness) of the fins and the size of the gaps between such fins may be accomplished by performing sidewall image transfer twice, which will be referred to a double SIT patterning (SIT²). A fin pitch (the distance from a first side surface of a fin to the same side surface of a neighboring fin) below 40 nm may be achieved using SIT². In one or more embodiments of a SIT² process, the sidewall spacers remaining after a first SIT process can be used as the sacrificial mandrels of a second SIT process. Variable mandrels for the second SIT process may be formed through the first SIT process by implementation of variable oxidation rates on opposite sides of a first sacrificial mandrel. The oxidation rate of the sacrificial mandrel material may be influenced by the type and/or degree of doping.

In the formation of SRAM including n-doped and p-doped CMOS, achieving the fin spacing can involve the removal of dummy fins; however, in the dense fin patterns, completely removing a dummy fin without damaging adjacent fins can be extremely challenging.

In various embodiments, a dense fin pattern produced by the SIT² process may be fabricated with controlled gaps; thereby, avoiding the formation and removal of dummy fins. An SRAM may be formed without dummy fin removal.

It is to be understood that the present invention will be described in terms of a given illustrative architecture; however, other architectures, structures, substrate materials and process features and steps may be varied within the scope of the present invention.

It will also be understood that when an element such as a layer, region or substrate is referred to as being “on” or “over” another element, it can be directly on the other element or intervening elements may also be present. In contrast, when an element is referred to as being “directly on” or “directly over” another element, there are no intervening elements present. It will also be understood that when an element is referred to as being “connected” or “coupled” to another element, it can be directly connected or coupled to the other element or intervening elements may be present. In contrast, when an element is referred to as being

4

“directly connected” or “directly coupled” to another element, there are no intervening elements present.

The present embodiments may include a design for an integrated circuit chip, which may be created in a graphical computer programming language, and stored in a computer storage medium (such as a disk, tape, physical hard drive, or virtual hard drive such as in a storage access network). If the designer does not fabricate chips or the photolithographic masks used to fabricate chips, the designer may transmit the resulting design by physical means (e.g., by providing a copy of the storage medium storing the design) or electronically (e.g., through the Internet) to such entities, directly or indirectly. The stored design is then converted into the appropriate format (e.g., GDSII) for the fabrication of photolithographic masks, which typically include multiple copies of the chip design in question that are to be formed on a wafer. The photolithographic masks are utilized to define areas of the wafer (and/or the layers thereon) to be etched or otherwise processed.

Methods as described herein may be used in the fabrication of integrated circuit chips. The resulting integrated circuit chips can be distributed by the fabricator in raw wafer form (that is, as a single wafer that has multiple unpackaged chips), as a bare die, or in a packaged form. In the latter case the chip is mounted in a single chip package (such as a plastic carrier, with leads that are affixed to a motherboard or other higher level carrier) or in a multichip package (such as a ceramic carrier that has either or both surface interconnections or buried interconnections). In any case the chip is then integrated with other chips, discrete circuit elements, and/or other signal processing devices as part of either (a) an intermediate product, such as a motherboard, or (b) an end product. The end product can be any product that includes integrated circuit chips, ranging from toys and other low-end applications to advanced computer products having a display, a keyboard or other input device, and a central processor.

Reference in the specification to “one embodiment” or “an embodiment” of the present principles, as well as other variations thereof, means that a particular feature, structure, characteristic, and so forth described in connection with the embodiment is included in at least one embodiment of the present principles. Thus, the appearances of the phrase “in one embodiment” or “in an embodiment”, as well as any other variations, appearing in various places throughout the specification are not necessarily all referring to the same embodiment.

It is to be appreciated that the use of any of the following “/”, “and/or”, and “at least one of”, for example, in the cases of “A/B”, “A and/or B” and “at least one of A and B”, is intended to encompass the selection of the first listed option (A) only, or the selection of the second listed option (B) only, or the selection of both options (A and B). As a further example, in the cases of “A, B, and/or C” and “at least one of A, B, and C”, such phrasing is intended to encompass the selection of the first listed option (A) only, or the selection of the second listed option (B) only, or the selection of the third listed option (C) only, or the selection of the first and the second listed options (A and B) only, or the selection of the first and third listed options (A and C) only, or the selection of the second and third listed options (B and C) only, or the selection of all three options (A and B and C). This may be extended, as readily apparent by one of ordinary skill in this and related arts, for as many items listed.

Referring now to the drawings in which like numerals represent the same or similar elements and initially to FIG.

5

1, which is a cross-sectional side view of a film stack on a substrate in accordance with an exemplary embodiment.

In one or more embodiments, a film stack **105** including a plurality of layers on a substrate **110** may be used to form a plurality of mandrels on the substrate **110**. In various embodiments, the substrate **110** may be a semiconductor substrate, for example silicon, silicon germanium, germanium, and/or compound semiconductors, including, III-V compound semiconductors and II-VI compound semiconductors. In various embodiments, the film stack **105** may include a nitride layer **120**, an oxide layer **130**, a sacrificial mandrel layer **140**, and a capping layer **150**. In various embodiments, additional layers may be included, different layers may be substituted, and/or some layers may be eliminated depending on the processing steps, etching selectivity, use of etch stop layers, specific material selections, etc., as would be known in the art.

In one or more embodiments, the film stack **105** may be deposited using known deposition methods, including but not limited to chemical vapor deposition (CVD), physical vapor deposition, (PVD), and atomic layer deposition (ALD), as well as variations and modifications thereof (e.g., plasma enhanced, low pressure, metal organic, etc.).

In various embodiments, a nitride layer **120** may be formed on the substrate, where the nitride layer may be silicon nitride (e.g., Si_3N_4). An oxide layer **130** may be formed on the nitride layer **120**, where the oxide layer may be silicon oxide (e.g., SiO_2). A sacrificial mandrel layer **140** may be formed on the oxide layer **130**, where the sacrificial mandrel layer **140** may be an undoped amorphous silicon layer (α -Si) or a polycrystalline silicon layer. A capping layer **150** may be formed on the sacrificial mandrel layer **140**, where the capping layer **150** may be a nitride material, for example, silicon nitride (e.g., Si_3N_4). The different materials may act as etch stops for processing features in various layers.

In one or more embodiments, the various layers may be processed using known etching techniques, including but not limited to reactive ion etching (RIE), plasma etching, and wet chemical etching, as well as variations and modifications thereof (e.g., ashing, plasma oxidation, etc.).

FIG. 2 is a cross-sectional side view of a substrate and film stack in accordance with an exemplary embodiment.

In one or more embodiments, a resist **160** may be formed on the film stack **105**, where the resist **160** may be a photoresist formed on the exposed surface of the capping layer **150**. In various embodiments, the resist may be a positive or negative resist material that can be patterned and developed by exposure to electron beams and/or photons (e.g., e-beams, X-rays, UV light, visible light, etc.). The resist may include a polymeric material or hydrogen silsesquioxane (HSQ).

In various embodiments, the resist **160** may be patterned and developed to form openings exposing the underlying capping layer **150**, where the resist **160** protects portions of the film stack **105** during reactive ion etching (RIE) of the capping layer **150**.

FIG. 3 is a cross-sectional side view of a patterned and etched film stack **105** in accordance with an exemplary embodiment.

In one or more embodiments, the capping layer **150** and underlying sacrificial mandrel layer **140** may be patterned by etching the capping layer **150** and sacrificial mandrel layer **140** exposed by developing the resist. Portions of the capping layer **150** and underlying sacrificial mandrel layer **140** may be removed to expose the underlying oxide layer **130**, where the capping layer **150** and underlying sacrificial

6

mandrel layer **140** may be removed by RIE or plasma etching. The RIE may provide essentially vertical sidewalls exposing side surfaces of the capping layer **150** and underlying sacrificial mandrel layer **140** to produce one or more sacrificial mandrels **141** having sidewalls **143**, **144**.

In various embodiments, the sacrificial mandrels **141** may be patterned to have the same pitch, or may have a variable pitch depending on the resist patterning. The sacrificial mandrels **141** may have the same widths or different widths depending on the resist patterning. In various embodiments, the sacrificial mandrels **141** may have a width in the range of about 20 nm to about 400 nm, or in the range of about 40 nm to about 400 nm, or in the range of about 20 nm to about 100 nm, or in the range of about 40 nm to about 100 nm.

FIG. 4 is a cross-sectional side view of a substrate and film stack exposed to an ion beam in accordance with an exemplary embodiment.

In one or more embodiments, the sidewalls **143** of a sacrificial mandrels **141** may be exposed to an ion beam **170**, where the ion beam may chemically alter at least one exposed sidewall **143** on one side of the sacrificial mandrels **141** to make the exposed sidewall more susceptible to oxidation. The ion beam **170** may include chemical species that can alter the material of the sacrificial mandrels **141** to be more susceptible to oxidation. In various embodiments, the ion beam **170** may be a p-type dopant (e.g., boron), that makes silicon more susceptible to oxidation. In various embodiments, the ion beam **170** may be an n-type dopant (e.g., phosphorous and/or arsenic), that makes silicon more susceptible to oxidation.

In one or more embodiments, the ion bombardment of the sacrificial mandrels **141** is done at an angle, such that one sidewall **144** of the sacrificial mandrels **141** is shadowed by the mandrel **141** and capping layer **150**, while the other sidewall **143** is impinged by the ion beam **170**. The ion implantation energy, ion beam density, and chemical species and associated mass of the implanted ion may be selected to control the depth of implantation and subsequent dopant concentration in the sacrificial mandrel(s) **141**. The implantation profile may be controlled to obtain a surface implantation of the dopant to a predetermined depth. A subsequent oxidation process may convert at least the most heavily-doped portions of the sacrificial mandrel(s) **141** into an oxide pillar, where the oxidation may occur faster at the heavily-doped side than the less-doped or undoped side of the sacrificial mandrel(s) **141**. In various embodiments, the surface portions of the sacrificial mandrel(s) **141** may be converted into oxide pillars by thermal oxidation of the amorphous or polycrystalline silicon.

FIG. 5 is a cross-sectional side view of a substrate and preferentially doped sacrificial mandrels in accordance with an exemplary embodiment.

In one or more embodiments, a portion of the sacrificial mandrel(s) **141** is chemically modified by the ion implantation to form a doped portion **180** of sacrificial mandrel(s) **141**.

FIG. 6 is a cross-sectional side view of a substrate, sacrificial mandrels, and oxide pillars in accordance with an exemplary embodiment.

In one or more embodiments, the sacrificial mandrel(s) **141** is oxidized to form oxide pillars **190**, **195**, where the doped portion **180** of the sacrificial mandrel(s) **141** undergoes faster and/or deeper oxidation than the undoped portion of the sacrificial mandrel(s) **141**. In various embodiments, the entire sacrificial mandrel(s) **141** is exposed to an oxidizing environment to form oxide pillars **190**, **195**, where a wider (i.e., thicker) oxide pillar **190** is formed on the doped

side of the sacrificial mandrel **141**, and a narrower (i.e., thinner) oxide pillar **195** is formed on the undoped side of the sacrificial mandrel **141**. The oxide pillars **190**, **195** may be formed on opposite sides of the sacrificial mandrel **141**, where a portion of the mandrel material is used to form the oxide pillars. In various embodiments, the oxide pillars **190**, **195** may have a width in the range of about 10 nm to about 60, or in the range of about 15 nm to about 60 nm, or in the range of about 10 nm to about 30 nm, or in the range of about 15 nm to about 30 nm. In various embodiments, the wider oxide pillar **190** (which may also be referred to as a first oxide pillar) has a width in the range of about 15 nm to about 60 nm, and the narrower oxide pillar **195** (which may also be referred to as a second oxide pillar) may have a width in the range of about 10 nm to about 30 nm, where the width of the narrower oxide pillar **195** may be less than the width of the wider oxide pillar **190**.

A plurality of oxide pillars **190**, **195** may be formed from one or more sacrificial mandrel(s) **141**. In various embodiments, not all of the doped portion **180** may be used to form the wider oxide pillar **190**, a portion of the doped mandrel may remain after oxidation. The thicker oxide pillar **190** may extend laterally out from the capping layer **150** due to changes in material density and crystal structure from implantation and oxidation.

In one or more embodiments, an amorphous silicon sacrificial mandrel **141** may be oxidized to form silicon oxide (e.g., SiO₂) pillars **190**, **195**.

FIG. **7** is a cross-sectional side view of a substrate, sacrificial mandrels, and oxide pillars in accordance with an exemplary embodiment.

In one or more embodiments, the capping layer **150** may be removed to expose the top surfaces of the oxide pillars **190**, **195**, and the doped portion **180** and undoped portion of the sacrificial mandrels **141**. The capping layer **150** may be removed by etching, for example, RIE, dry chemical etching, or plasma etching, such that the capping layer material is selectively etched. In various embodiments, a nitride capping layer (e.g., SiN) may be selectively removed by a fluorine containing plasma etch or RIE. The oxide layer **130** may remain substantially unetched by the selective etching of the capping layer **150**.

FIG. **8** is a cross-sectional side view of a substrate and oxide pillars in accordance with an exemplary embodiment.

In one or more embodiments, subsequent to removal of the capping layer **150** and remaining portions of the sacrificial mandrels **141** may be removed, for example by etching, to leave free-standing oxide pillars **190**, **195**. The oxide layer **130** may remain substantially unetched by the selective etching of the sacrificial mandrels **141**.

In various embodiments, removal of the sacrificial mandrels **141** may form gaps having a predetermined width between the oxide pillars **190**, **195**. The gap between a wide oxide pillar **190** and a narrow oxide pillar **195** formed by oxidation of the same sacrificial mandrel **141** may be based on the original width of the sacrificial mandrel **141**, whereas the gap between a wide oxide pillar **190** and a narrow oxide pillar **195** of adjacent sacrificial mandrels **141** may be based on the pitch of the sacrificial mandrel **141**.

FIG. **9** is a cross-sectional side view of a substrate, oxide pillars, and spacers in accordance with an exemplary embodiment.

In one or more embodiments, spacers **200**, **205** may be formed at least on opposite sides of the oxide pillars **190**, **195**, where the spacers **200**, **205** may be formed by conformal deposition of the spacer material on the sidewalls of the oxide pillars **190**, **195**. The spacers **200**, **205** may be

conformally deposited, for example, by ALD, CVD, or a combination thereof. In various embodiments, the spacers **200**, **205** may be made of amorphous carbon. The amorphous carbon may be deposited by CVD.

In various embodiments, the spacers **200**, **205** may have a width (i.e., thickness) less than the width of the wider oxide pillar **190** and/or the narrower oxide pillar **195**. In various embodiments, the spacers **200**, **205** may have a width in the range of about 5 nm to about 20 nm, or in the range of about 5 nm to about 10 nm.

FIG. **10** is a cross-sectional side view of a substrate and free-standing vertical spacers in accordance with an exemplary embodiment.

In one or more embodiments, the oxide pillars **190**, **195** may be removed to leave free-standing vertical spacers **200**, **205**, where the spacers are spatially arranged to have controlled pitches and gaps. The gap, G_2 between a vertical spacer **200** and vertical spacer **205** may be controlled by the width of the wider oxide pillar **190**, whereas the pitch, P_2 , between vertical spacer **200** and vertical spacer **205** may be controlled by the width of the wider oxide pillar **190** and the thickness of vertical spacer **200**. The gap, G_1 , between a vertical spacer **200** and vertical spacer **205** may be controlled by the width of the narrower oxide pillar **195**, whereas the pitch, P_1 , between vertical spacer **200** and vertical spacer **205** may be controlled by the width of the narrower oxide pillar **195** and the thickness of vertical spacer **205**. The gap, G_3 , may be controlled by adjusting the thicknesses of vertical spacers **200** and vertical spacers **205** of adjacent oxide pillars **190**, **195**.

In various embodiments, the oxide pillars **190**, **195** and oxide layer **130** may be removed through the same etching processes to form oxide columns **131** beneath free-standing vertical spacers **200**, **210** and free-standing vertical spacers **205**, **215**. Portions of the nitride layer **120** underlying oxide layer **130** may be partially removed to form a nitride layer **120** with different thicknesses between different vertical spacers **200**, **205**, **210**, **215** such that the gaps between the spacers **200**, **205**, **210**, **215** have varying depths.

FIG. **11** is a cross-sectional side view of a substrate, oxide columns, and nitride columns in accordance with an exemplary embodiment.

In one or more embodiments, free-standing vertical spacers **200**, **205**, **210**, **215** may be removed, and the nitride layer **120** etched to the underlying substrate, to leave oxide columns **131** over nitride columns **121**. In various embodiments, the oxide columns **131** and nitride columns **121** form a mask for transferring the spacer pattern into the substrate **110** to form fins **115** from the substrate **110**. The fins may be made of a semiconductor material, for example, amorphous silicon.

FIG. **12** is a cross-sectional side view of a substrate, oxide and nitride columns, and fins in accordance with an exemplary embodiment.

In one or more embodiments, a portion of the substrate material exposed between the columns is removed to form fins **115** separated by trenches **118**. In various embodiments, the substrate material may be removed by RIE to form the vertical fins **115** for fabricating FinFETs. The sides of the fins **115** may have different heights due to differential etching resulting from different gap sizes between the adjacent columns. The fins **115** may have different pitches through control of the widths and patterning of the overlying columns **190**, **195**, spacers **200**, **205**, **210**, **215**, pillars **121**, **131**, and mandrels **141**. The trenches **118** may have varying depths.

In an embodiment, a silicon substrate may be etched to form silicon fins, where the substrate may be doped to form p-type fin channels or n-type fin channels.

FIG. 13 is a cross-sectional side view of fins and trenches partially filled with a dielectric in accordance with an exemplary embodiment.

In one or more embodiments, a dielectric material 220 may be formed in the trenches 118 between the fins 115 to electrically insulate at least a portion of the fins. The dielectric fill may provide shallow trench isolation between the fins. In various embodiments, the dielectric material 220 may have varying vertical lengths, where the varying length may be due to varying depths of the trenches 118.

In various embodiments, the oxide columns 131 and nitride columns may be removed before or after depositing the dielectric material in the trenches 118. Complete FinFETs may subsequently be formed from the fins 115. The FinFETs may be used to form CMOS transistors and subsequently SRAM.

FIG. 14 is a top view of fins in a predetermined pattern in accordance with an exemplary embodiment.

In various embodiments, the fins may be patterned to have a predetermined pitch, where the pitch may depend on the characteristics of the FinFET to be fabricated. By controlling the various widths of the fabricated components (mandrels, columns, spacers), an arrangement of fins 115 having pitches P_1 and P_2 may be formed, where P_1 and P_2 may be variable, such that $P_2 = N \times P_1$, where P_1 may be a minimum fin pitch, and 'N' is an integer.

FIG. 15 is a top view of a static random access memory (SRAM) cell in accordance with an exemplary embodiment.

In one or more embodiments, a plurality of fins 115 may be electrically connected to form an SRAM, where each SRAM may include a pair of Pull-Down transistors 510, a pair of Pull-Up transistors 520, and a pair of Pass Gate transistors 530. Each Pull-Down transistor 510 may be an n-type transistor having two fins 115. Each Pass Gate transistor 530 may be an n-type transistor having two fins 115. Each Pull-Up transistor 520 may be a p-type transistor having a single fin 115. Each pair of Pull-Down transistors 510 and Pull-Up transistors 520 may share a common gate. Such an SRAM cell may be referred to as a "221" cell.

FIG. 16 is a cross-sectional side view of a film stack on a substrate in accordance with an exemplary embodiment.

In one or more embodiments, a film stack 305 including a plurality of layers on a substrate 310 may be used to form a plurality of mandrels on the substrate 310. In various embodiments, the film stack 305 may include a substrate 310, a first nitride layer 320, a fin-forming layer 330, a second nitride layer 340, an oxide layer 350, a second sacrificial mandrel layer 360, and a capping layer 370.

In various embodiments, the film stack including the second nitride layer 340, the oxide layer 350, the sacrificial mandrel layer 360, and the capping layer 370 may be patterned, etched, and formed as discussed above, to form spacers, and the spacer pattern may be transferred to the fin-forming layer 330 to form fins instead of processing and transferring the pattern to the substrate 310.

FIG. 17 is a cross-sectional side view of a substrate, spacers, oxide and nitride columns, and fins in accordance with an exemplary embodiment.

In various embodiments, the sacrificial mandrel layer 360 may be patterned, ion implanted, and oxidized to form spacers 380, that can provide the pattern to be transferred to the second nitride layer 340 and the oxide layer 350 to mask and form the fins 335 in the fin-forming layer 330, where the

fin-forming layer 330 may be an amorphous silicon layer or a polycrystalline silicon layer.

Having described preferred embodiments of a system and method for fabrication of fins using variable spacers (which are intended to be illustrative and not limiting), it is noted that modifications and variations can be made by persons skilled in the art in light of the above teachings. It is therefore to be understood that changes may be made in the particular embodiments disclosed which are within the scope of the invention as outlined by the appended claims. Having thus described aspects of the invention, with the details and particularity required by the patent laws, what is claimed and desired protected by Letters Patent is set forth in the appended claims.

What is claimed is:

1. A method of fabricating semiconductor fins on a substrate, comprising:

patterning a film stack to produce two or more sacrificial mandrels having first and second sidewalls on opposing sides of each of the mandrels and a capping layer on a top surface of each of the two or more sacrificial mandrels;

exposing each of the first sidewalls of the two or more sacrificial mandrels to an ion beam at a first angle to the surface of the substrate to make the exposed first sidewalls of each of the two or more sacrificial mandrels more susceptible to oxidation, wherein the capping layer covers the top surface of each of the two or more sacrificial mandrels during the exposure to the ion beam;

oxidizing the first and second sidewalls of each of the two or more sacrificial mandrels to form a plurality of oxide pillars on opposing sides of each of the mandrels;

removing the two or more sacrificial mandrels; and forming spacers on opposite sides of each of the plurality of oxide pillars to produce a spacer pattern.

2. The method of claim 1, wherein the two or more sacrificial mandrels comprise amorphous silicon.

3. The method of claim 1, wherein the ion beam impinges the sidewall on one side of each of the two or more sacrificial mandrels at an angle that shadows the opposite sidewall of each of the two or more sacrificial mandrels, wherein the capping layer on the top surface of each of the two or more sacrificial mandrels shadows at least a portion of each of the underlying sacrificial mandrels from the ion beam.

4. The method of claim 1, wherein the oxide pillars formed by oxidizing the first sidewalls of each of the two or more sacrificial mandrels have different widths than the oxide pillars formed by oxidizing the second sidewalls of each of the two or more sacrificial mandrels.

5. The method of claim 4, which further comprises removing the plurality of oxide pillars; and

transferring the spacer pattern to the substrate to produce a plurality of fins, wherein the plurality of fins have a predefined pitch.

6. The method of claim 5, which further comprises forming trenches having varying depths between the plurality of fins.

7. The method of claim 1, wherein the spacer formation comprises conformal deposition on at least opposite sides of each of the plurality of oxide pillars.

8. The method of claim 7, wherein the spacers comprise amorphous carbon.

9. The method of claim 1, wherein the first sidewall of the two or more sacrificial mandrels is exposed to an ion beam comprising a p-type dopant.

10. The method of claim 9, wherein the p-type dopant comprises boron and the sacrificial mandrels comprise amorphous silicon.

* * * * *