



US010832921B2

(12) **United States Patent**
Balaraman et al.

(10) **Patent No.:** **US 10,832,921 B2**
(45) **Date of Patent:** **Nov. 10, 2020**

(54) **ELECTRONIC DEVICE WITH TOP SIDE PIN ARRAY AND MANUFACTURING METHOD THEREOF**

(71) Applicant: **Amkor Technology, Inc.**, Tempe, AZ (US)

(72) Inventors: **Devarajan Balaraman**, Apex, NC (US); **Daniel Richter**, Goldsboro, NC (US); **Greg Hames**, Raleigh, NC (US); **Dean Zehnder**, Hillsborough, NC (US); **Glenn Rinne**, Apex, NC (US)

(73) Assignee: **AMKOR TECHNOLOGY, INC.**, Tempe, AZ (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **16/424,046**

(22) Filed: **May 28, 2019**

(65) **Prior Publication Data**
US 2019/0279882 A1 Sep. 12, 2019

Related U.S. Application Data

(63) Continuation of application No. 15/725,938, filed on Oct. 5, 2017, now Pat. No. 10,304,697.

(51) **Int. Cl.**
H01L 21/48 (2006.01)
H01L 21/56 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC *H01L 21/4853* (2013.01); *H01L 21/56* (2013.01); *H01L 21/565* (2013.01); *H01L 21/6835* (2013.01); *H01L 23/3121* (2013.01); *H01L 23/49811* (2013.01); *H01L 23/3128* (2013.01); *H01L 2221/68345* (2013.01); *H01L 2221/68359* (2013.01); *H01L 2224/131* (2013.01); *H01L 2224/16227* (2013.01); *H01L*

2224/32225 (2013.01); *H01L 2224/48091* (2013.01); *H01L 2224/48137* (2013.01); *H01L 2224/73204* (2013.01); *H01L 2224/73265* (2013.01); *H01L 2224/81005* (2013.01); *H01L 2224/81203* (2013.01); *H01L 2224/81815* (2013.01); *H01L 2224/92125* (2013.01); *H01L 2224/97* (2013.01); *H01L 2924/1533* (2013.01); *H01L 2924/181* (2013.01); *H01L 2924/19041* (2013.01); *H01L 2924/19042* (2013.01);

(Continued)

(58) **Field of Classification Search**
CPC *H01L 21/48*; *H01L 21/56*; *H01L 23/498*; *H01L 23/31*; *H01L 21/683*; *H01L 21/4863*; *H01L 23/49811*; *H01L 23/3121*; *H01L 21/6835*; *H01L 21/565*; *H01L 23/3128*
USPC 257/737
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,447,264 A 9/1995 Koopman et al.
7,427,557 B2 9/2008 Rinne et al.
(Continued)

FOREIGN PATENT DOCUMENTS

JP 06-177208 A 6/1994


Primary Examiner — Alexander O Williams

(74) *Attorney, Agent, or Firm* — McAndrews, Held & Malloy, Ltd.

(57) **ABSTRACT**

An electronic device and a manufacturing method thereof. As non-limiting examples, various aspects of this disclosure provide an electronic device having a top side pin array, for example which may be utilized for three-dimensional stacking, and a method for manufacturing such an electronic device.

20 Claims, 10 Drawing Sheets



| | | |
|------|---|---|
| (51) | Int. Cl. <i>H01L 23/498</i> (2006.01) <i>H01L 23/31</i> (2006.01) <i>H01L 21/683</i> (2006.01) | 10,256,114 B2 * 4/2019 Huemoeller H01L 23/5385 10,276,543 B1 * 4/2019 Liao H01L 25/0657 10,283,474 B2 * 5/2019 Jeng H01L 24/20 10,304,697 B2 * 5/2019 Balaraman H01L 23/3121 10,304,805 B2 * 5/2019 Yoo H01L 25/0657 |
| (52) | U.S. Cl. CPC <i>H01L 2924/19043</i> (2013.01); <i>H01L 2924/19105</i> (2013.01) | 10,515,827 B2 * 12/2019 Jeng H01L 21/486 2005/0215045 A1 9/2005 Rinne et al. 2006/0205170 A1 9/2006 Rinne 2015/0145123 A1 5/2015 Ha 2015/0340332 A1 11/2015 Rinne et al. 2016/0056055 A1 2/2016 Ko et al. 2016/0084905 A1 * 3/2016 Gandhi G01R 1/07307 324/756.03 2017/0141083 A1 * 5/2017 Prabhu H01L 24/19 2017/0162535 A1 6/2017 Rinne 2017/0316989 A1 * 11/2017 Tsai H01L 22/32 2018/0174981 A1 * 6/2018 Lu H01L 23/13 2019/0006308 A1 * 1/2019 Appelt H01L 24/24 2019/0013273 A1 * 1/2019 Jeng H01L 21/76885 2019/0199018 A1 * 6/2019 Tsuchiya H01R 11/284 |
| (56) | References Cited U.S. PATENT DOCUMENTS 7,994,043 B1 8/2011 Mis et al. 9,159,695 B2 * 10/2015 Chuang H01L 24/81 9,502,360 B2 * 11/2016 Lin H01L 25/105 9,543,242 B1 * 1/2017 Kelly H01L 23/49816 9,786,622 B2 * 10/2017 Cheng H01L 24/13 9,984,960 B2 * 5/2018 Hwang H01L 23/49805 10,002,857 B2 * 6/2018 Solimando H01L 25/105 10,043,779 B2 * 8/2018 Prabhu H01L 24/19 | * cited by examiner |

100
↓




Figure 1




Figure 2A




Figure 2B-1




Figure 2B-2




Figure 2C




Figure 2D




Figure 2E




Figure 2F




Figure 2G




Figure 2H




Figure 2I-1




Figure 2I-2




Figure 3




Figure 4D




Figure 4E




Figure 4F-1




Figure 4F-2




Figure 4F-3




Figure 5A




Figure 5B




Figure 5C

1

ELECTRONIC DEVICE WITH TOP SIDE PIN ARRAY AND MANUFACTURING METHOD THEREOF

BACKGROUND

Present semiconductor packages and methods for forming semiconductor packages are inadequate, for example resulting in excess cost, decreased reliability, or package sizes that are too large. Further limitations and disadvantages of conventional and traditional approaches will become apparent to one of skill in the art, through comparison of such approaches with the present disclosure as set forth in the remainder of the present application with reference to the drawings.

BRIEF DESCRIPTION OF SEVERAL VIEWS OF THE DRAWINGS

FIG. 1 shows a flow diagram of an example method of making an electronic device, in accordance with various aspects of the present disclosure.

FIGS. 2A to 2I-2 show cross-sectional views illustrating an example electronic device and an example method of making an example electronic device, in accordance with various aspects of the present disclosure.

FIG. 3 shows a flow diagram of an example method of making an electronic device, in accordance with various aspects of the present disclosure.

FIGS. 4A to 4F-3 show cross-sectional views illustrating an example electronic device and an example method of making an example electronic device, in accordance with various aspects of the present disclosure.

FIGS. 5A to 5C show cross-sectional views illustrating an example electronic device and an example method of making an example electronic device, in accordance with various aspects of the present disclosure.

SUMMARY

Various aspects of this disclosure provide an electronic device and a manufacturing method thereof. As non-limiting examples, various aspects of this disclosure provide an electronic device having a top side pin array, for example which may be utilized for three-dimensional stacking, and a method for manufacturing such an electronic device.

DETAILED DESCRIPTION OF VARIOUS ASPECTS OF THE DISCLOSURE

The following discussion presents various aspects of the present disclosure by providing examples thereof. Such examples are non-limiting, and thus the scope of various aspects of the present disclosure should not necessarily be limited by any particular characteristics of the provided examples. In the following discussion, the phrases “for example,” “e.g.,” and “exemplary” are non-limiting and are generally synonymous with “by way of example and not limitation,” “for example and not limitation,” and the like.

As utilized herein, “and/or” means any one or more of the items in the list joined by “and/or”. As an example, “x and/or y” means any element of the three-element set $\{(x), (y), (x, y)\}$. In other words, “x and/or y” means “one or both of x and y.” As another example, “x, y, and/or z” means any element of the seven-element set $\{(x), (y), (z), (x, y), (x, z), (y, z), (x, y, z)\}$. In other words, “x, y and/or z” means “one or more of x, y, and z.”

2

The terminology used herein is for the purpose of describing particular examples only and is not intended to be limiting of the disclosure. As used herein, the singular forms are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “comprises,” “includes,” “comprising,” “including,” “has,” “have,” “having,” and the like when used in this specification, specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

It will be understood that, although the terms first, second, etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another element. Thus, for example, a first element, a first component or a first section discussed below could be termed a second element, a second component or a second section without departing from the teachings of the present disclosure. Similarly, various spatial terms, such as “top,” “upper,” “bottom,” “lower,” “lateral,” “side,” and the like, may be used in distinguishing one element from another element in a relative manner. It should be understood, however, that components may be oriented in different manners, for example a semiconductor device or package may be turned sideways so that its “top” surface is facing horizontally and its “side” surface is facing vertically, without departing from the teachings of the present disclosure.

Various aspects of the present disclosure provide an electronic device (e.g., a semiconductor device, etc.) and a manufacturing (or fabricating or making) method thereof, which can decrease the cost, increase the reliability, and/or increase the manufacturability of the electronic device.

Various aspects of the present disclosure also provide a method of manufacturing an electronic device (and an electronic device manufactured thereby) that includes receiving a substrate that comprises a plurality of pads. A plurality of solder members may be formed, where each solder member of the plurality of solder members is positioned on a respective pad of the plurality of pads. A pin template comprising a plurality of apertures may be provided, and positioned above the substrate, where each aperture of the plurality of apertures is aligned with a respective pad of the plurality of pads. A plurality of pins may be provided, where each pin of the plurality of pins is positioned in a respective aperture of the plurality of apertures. The pin template may be removed from the pins and the solder members reflowed.

Various aspects of the present disclosure additionally provide a method of manufacturing an electronic device (and an electronic device manufactured thereby) that includes receiving a substrate that comprises a plurality of pads. A pin template and a plurality of pins may be provided above the substrate, where the pin template comprises a plurality of apertures and each pin of the plurality of pins is positioned in a respective aperture of the plurality of apertures and aligned with a respective pad of the plurality of pads. Each pin of the plurality of pins may be attached to its respective pad.

Various aspects of the present disclosure further provide a method of manufacturing an electronic device (and an electronic device manufactured thereby) that includes providing a pin template comprising a plurality of apertures. The pin template may be positioned above a substrate, where the substrate comprises a plurality of pads. A plurality of pins may be provided, where each pin of the plurality of pins

is positioned in a respective aperture of the plurality of apertures and aligned with a respective pad of the plurality of pads. Each pin of the plurality of pins may be soldered to its respective pad.

The above and other aspects of the present disclosure will be described in or be apparent from the following description of various example implementations. Various aspects of the present disclosure will now be presented with reference to accompanying drawings, such that those skilled in the art may readily practice the various aspects.

FIG. 1 shows a flow diagram of an example method 100 of making an electronic device (e.g., a semiconductor package, etc.), in accordance with various aspects of the present disclosure. The example method 100 may, for example, share any or all characteristics with any other example method(s) discussed herein (e.g., the example method 300 of FIG. 3, of FIGS. 4A to 4F-3, of FIGS. 5A to 5C, etc.) or any portion thereof. FIGS. 2A to 2I-2 show cross-sectional views illustrating an example electronic device (e.g., a semiconductor package, etc.) and an example method of making an example electronic device, in accordance with various aspects of the present disclosure. FIGS. 2A to 2I-2 may, for example, illustrate an example electronic device at various blocks (or steps) of the method 100 of FIG. 1. FIG. 1 and FIGS. 2A to 2I-2 will now be discussed together. It should be noted that the order of the example blocks of the method 100 may vary without departing from the scope of this disclosure.

The example method 100 may begin executing at block 105. The method 100 may begin executing in response to any of a variety of causes or conditions, non-limiting examples of which are provided herein. For example, the method 100 may begin executing automatically in response to one or more signals received from one or more upstream and/or downstream manufacturing stations, in response to a signal from a central manufacturing line controller, upon arrival of components and/or manufacturing materials utilized during performance of the method 100, etc. Also for example, the method 100 may begin executing in response to an operator command to begin. Additionally for example, the method 100 may begin executing in response to receiving execution flow from any other method block (or step) discussed herein.

The example method 100 may, at block 110, comprise receiving, fabricating, and/or preparing a substrate. Block 110 may comprise receiving, fabricating, and/or preparing a substrate in any of a variety of manners, non-limiting examples of which are provided herein. Various example aspects of block 110 are presented in the example 200A shown at FIG. 2A.

The received, fabricated, and/or prepared substrate may comprise any of a variety of characteristics. For example, the received, fabricated, and/or prepared substrate may comprise a plurality of substrates in a wafer form (e.g., as or on a silicon or other semiconductor wafer, as or on a glass wafer or panel, as or on a metal wafer or panel, etc.). Though the examples illustrated and discussed herein generally show a single substrate for illustrative clarity, at any or all of the process steps shown herein, the substrate may be one of a plurality of connected substrates and the steps may be performed similarly on each of the plurality of connected substrates.

In the examples shown herein, the substrate may, for example, only include electrical routing circuitry (e.g., without active semiconductor components and/or passive components, etc.). Note, however, that the scope of this disclosure is not limited thereto. For example, the substrate may,

for example, include (or be) a semiconductor die that has active semiconductor circuitry. Also for example, the substrate may comprise passive electronic components (e.g., resistors, capacitors, inductors, integrated passive devices (IPDs), etc.) and/or active electronic components (e.g., transistors, logic circuits, semiconductor processing components, semiconductor memory components, etc.) and/or optical components, etc.

The example 200A of FIG. 2A shows a substrate 210 comprising a support layer 209 (or carrier). The support layer 209 may, for example, comprise any of a variety of materials (e.g., silicon or other semiconductor material, glass, metal, plastic, etc.). The support layer 209 may, for example, be temporary or sacrificial (e.g., a temporary carrier, etc.).

The example substrate also comprises a signal distribution structure 201 (or signal redistribution structure) on the support layer 209. The example signal distribution structure 201, comprises a plurality of dielectric layers 202 and a plurality of conductive layers 203. The signal distribution structure 201 may comprise any of a variety of characteristics. For example, the signal distribution structure may comprise back-end-of-line (BEOL) signal distribution layers from a die fabrication process, may also or alternatively comprise signal distribution layers formed in an electronic component packaging process (e.g., formed directly on a semiconductor die or die pads thereof, formed on one or more BEOL signal distribution layers, etc.).

The example conductive layers 203, for example, include conductive pads 205. As shown herein, such conductive pads 205 may, for example, be utilized for pin attachment, die attachment, etc.

The conductive pads 205 may comprise any of a variety of characteristics. The conductive pads 205 may, for example, be generally circular (or matching the top-down view shape of the pins discussed herein). In an example implementation, the conductive pads 205 may comprise one or more layers of various metals (e.g., a titanium layer, a titanium tungsten layer, a copper layer, a nickel layer, a gold layer, etc.). The conductive pads 205 may, for example, comprise die pads, pads of a signal redistribution structure or layer, under bump metallization layer(s), etc.

The conductive pads 205 may comprise any of a variety of physical configurations. For example, as generally shown herein, the conductive pads 205 may have a perimeter border (or lip) that is positioned above and/or over the top dielectric layer 202 of the signal distribution structure 201. The conductive pads 205 may also, for example, have an uppermost surface that is vertically lower than an uppermost surface of the top dielectric layer 202 of the signal distribution structure 201. For example, the top dielectric layer 202 of the signal distribution structure 201 may cover a perimeter portion of the conductive pads 205.

As non-limiting examples, the substrate 210 may utilize inorganic dielectric layers (and/or a combination of inorganic and organic dielectric layers) in the signal distribution structure 201 and a semiconductor material-based support layer 209. The substrate 210 may, for example, be produced utilizing Amkor Technology's Silicon-Less Integrated Module (SLIM™) technology. Also for example, the substrate 210 may, for example, include organic dielectric layers (and/or a combination of inorganic and organic dielectric layers) in the signal distribution structure 201 and a semiconductor material-based support layer 209. The substrate 210 may, for example, be produced utilizing Amkor Technology's Silicon Wafer Integrated Fan-out (SWIFT™) technology. Non-limiting examples of the substrate 210, and the

forming thereof, may be found in U.S. patent application Ser. No. 14/823,689, filed Aug. 11, 2015, and titled "SEMI-CONDUCTOR PACKAGE AND FABRICATING METHOD THEREOF," now U.S. Pat. No. 9,543,242; and U.S. patent application Ser. No. 15/707,646, filed Sep. 18, 2017, and titled "SEMICONDUCTOR PACKAGE AND FABRICATING METHOD THEREOF,"; each of which is hereby incorporated herein by reference in its entirety

Block 110 may, for example, comprise receiving the substrate from an upstream manufacturing process at a same facility or geographical location. Block 110 may also, for example, comprise receiving the substrate from a supplier (e.g., from a foundry, etc.) at a geographically remote site.

In general, block 110 may comprise receiving, fabricating, and/or preparing a substrate. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular type of substrate or by characteristics of any particular manner of receiving, fabricating, and/or preparing a substrate.

The example method 100 may, at block 115, comprise forming solder (or other attachment material). Block 115 may comprise forming solder in any of a variety of manners, non-limiting examples of which are provided herein. Various example aspects of block 115 are presented in the examples 200B-1 and 200B-2 shown at FIGS. 2B-1 and 2B-2, respectively.

As shown in the example 200B-1 of FIG. 2B-1, block 115 may comprise forming a respective solder member 215 on each of the conductive pads 205. For example, block 115 may comprising forming the solder members 215 by screen printing the solder members 215 (e.g., as a solder paste, etc.) onto the conductive pads 205 through a removable stencil applied to signal distribution structure 201, or otherwise forming the solder members 215. In the example 200B-1, the solder members 215 may comprise flux already integrated therein. For example, an additional fluxing step might not be utilized.

As shown in the example 200B-2 of FIG. 2B-2, block 115 may comprise forming the solder members 215 by plating the solder members 215 on the conductive pads 205 (or otherwise forming the solder members 215). Block 115 may then, for example, comprise forming a respective flux member 216 on each of the solder members 215.

Though various examples shown herein (e.g., with regard to FIGS. 2C and 2D, with regard to FIGS. 4C and 4D, etc.) are based on the example 200B-1 shown in FIG. 2B-1, the example 200B-2 shown in FIG. 2B-2 may be utilized as well.

Also note that although solder is utilized in the example implementations shown herein, other forms of attaching may be utilized without departing from the scope of this disclosure. For example, instead of solder, block 115 may print (or otherwise) apply a conductive adhesive. Also for example, direct solderless metal-to-metal (e.g., copper-to-copper, etc.) bonds may be utilized.

In general, block 115 may comprise forming solder (or other attachment material). Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of forming solder (or other attachment material) or by characteristics of any particular type of solder (or other attachment material).

The example method 100 may, at block 120, comprise positioning a pin template and pins. Block 120 may comprise positioning the pin template and pins in any of a variety of manners, non-limiting examples of which are provided herein. Various example aspects of block 120 are presented in the example 200C shown at FIG. 2C.

As shown in the example 200C shown in FIG. 2C, block 120 may for example position a pin template 221 (e.g., a metal foil stencil, etc.) over the substrate 210. The pin template 221 may, for example, comprise a plurality of apertures 222, each corresponding to a respective one of the conductive pads 205. Block 120 may, for example, comprise laterally positioning each of the apertures 222 directly over a respective one of the conductive pads 205 (e.g., over a respective solder member 215 and/or flux member 216 on a respective one of the conductive pads 205).

As shown in FIG. 2C, the pin template 221 may be offset from (or elevated off) the substrate 210 enough so that the pin template 221 does not touch the solder members 215 (and/or flux members 216 if present). The pin template 221 may, for example, have a thickness that is less than a height of the pins 220. In an example implementation, the thickness of the pin template 221 combined with the vertical distance between the bottom of the pin template 221 and the top sides of the solder members 215 (and/or flux members 216) may be less than or equal to the height of the pins 220. Such relative dimensions may, for example, limit occupancy of a single aperture 222 to a single pin 220.

A plurality of pins 220 may, for example, be placed on the pin template 221 (e.g., dumped, poured, scooped, blown, etc.). At the example 200C of FIG. 2C, some or all of the pins 220 might not be positioned in respective apertures. Note that although the example 200C illustrates a same number of pins 220 and apertures 222, the pins 220 may outnumber the apertures 222.

The pins 220 may comprise any of a variety of characteristics. For example, the pins 220 may be cylinder-shaped, for example with a circular cross-section and flat top and bottom surfaces. Also for example, the pins 220 may have an oval cross-section, polygonal cross-section, non-circular cross-section, etc. A non-limiting example of the pin 220 is shown in the example 200I-1 of FIG. 2I-1. Such example pin 220 is generally cylinder-shaped with curved (or smooth) transitions 223 between the lateral side and the top and/or bottom ends. The top and/or bottom ends may, for example, be beveled. The example pin 220 shown in FIG. 200I-1 has a diameter of 150 um and a longitudinal height of 300 um. The scope of this disclosure, however, is not limited to any particular dimensions. For example, the pin 220 may have a diameter in the range of 100 um to 250 um. Also for example, the pin 220 may have a height in the range of 50 um to 300 um in diameter. The pin 220 may, for example, have a height that is greater than its width (e.g., diameter, minor axis width, major axis width, etc.), but the scope of this disclosure is not limited thereto.

In various example implementations, the pin 220 will have a diameter that is less than the diameter of the conductive pad 205. For example, the diameter of the pin 220 may be in the range of 10% to 25% less than the diameter of the conductive pad 205. Also for example, the diameter of the pin 220 may be in the range of 25% to 50% less than the diameter of the conductive pad.

In various example implementations, the pin 220 may be substantially thicker than a wirebond wire, which may for example be on the order of 25 um in diameter (e.g., at least two times as thick, at least five times as thick, etc.). Such thickness may provide various benefits. For example, below a certain diameter or size, wires may stick to each other and substantially adversely impact the manufacturing process, and/or such wires may be relatively more susceptible to bending during handling. Also for example, such thickness

may provide structural stability not found in a typical wirebond wire, for example during handling and/or encapsulating.

Though the example pin **220** (and all pins herein, pins **420**, **520**, etc.) are shown with generally flat ends, the scope of this disclosure is not limited thereto. For example, the top and/or bottom ends of the pins may comprise grooves, notches, sawtooth patterns, asperities, etc. Such features may, for example, enhance solderability and/or adherability (e.g., by allowing for the venting of flux vapors or gases, by providing rough surfaces for adhesion, etc.). Also for example, the top and/or bottom ends of the pins may comprise convex or concave shapes, n-sided polygonal shapes, non-vertical sides, etc.

Returning to FIG. 2C, the apertures **222** may for example be generally shaped like the pins **220**. For example, the apertures **222** may be cylinder-shaped to match cylinder-shaped pins **220**, etc. In an example implementation, the diameter of the apertures **222** may be slightly larger than the diameter of the pins **220** and sized to enhance pin placement temporal efficiency while maintaining placement accuracy. For example, the diameter of the apertures **222** may be in the range of 10 um to 60 um larger (e.g., 40 um larger, 50 um larger, etc.) than the diameter of the pins **220**. Also for example, the diameter of the apertures **222** may in the range of 10% to 50% larger (e.g., 25% larger, 33% larger, etc.) than the diameter of the pins **420**. Also note that the apertures **222** (e.g., at the upper side of the template **221**, etc.) may have curved, sloped, or beveled openings to enhance the filling of the apertures **222** with the pins **220**.

The pins **220** may be formed in any of a variety of manners. For example, the pins **220** may, for example, be formed by cutting a wire into segments. The pins **220** may also, for example, be formed by plating, molding, printing, reflowing, depositing, etc.

In general, block **120** may comprise positioning a pin template and pins. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of positioning a pin template and pins or by characteristics of any particular type of pin template and pins.

The example method **100** may, at block **125**, comprise positioning pins in pin template apertures. Block **125** may comprise positioning pins in pin template apertures in any of a variety of manners, non-limiting examples of which are provided herein. Various example aspects of block **125** are presented in the example **200D** shown at FIG. 2D.

For example, block **125** may comprise vibrating the pin template **221** to jostle the pins **220** until each of the apertures **222** is filled with a respective pin **220**. In an example implementation, block **125** may comprise vibrating the pin template **221** in a lateral direction in any of a variety of motion patterns (e.g., in a plane parallel to a general plane of the substrate **210**). Note that in various implementations, there may also be a vertical component to the vibrating. The range of the vibration motion may, for example, be a portion of the diameter (or width) of a conductive pad **205** (or solder **215** and/or flux **216** thereof), for example 5-10% of the pad diameter, 1-20% of the pad diameter, etc.). Any of a variety of vibration frequencies may be utilized. For example, a vibration frequency in the range of 1 KHz to 5 KHz (e.g., 2 KHz, 3 KHz, etc.) may be utilized.

Also for example, block **125** may comprise sweeping or brushing the pins **220** over the apertures **222** (e.g., repeatedly) until the apertures **222** are each filled with a respective pin **220**. Such sweeping or brushing may, for example, be utilized exclusively or may be combined (e.g., serially or in parallel) with the vibration motion.

In an example implementation, as each pin **220** falls into (or is directly pick-and-placed into) its respective aperture **222**, the pin **220** may contact the top side of its respective solder member **215** (or flux member **216**). The pin **220** may thus be adhered to its respective solder member **215** (or flux member **216**), which may for example be tacky (or sticky). The pin **220** may also, for example, sink into the top side of its respective solder member **215** (or flux member **216**).

In general, block **125** may comprise positioning pins in pin template apertures. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of positioning pins in pin template apertures.

Note that in various example implementations, for example in which block **120** positions the pin template with all of the pins already in place prior to the positioning, block **125** may be skipped, and block **120** may comprise placing the template and pins such that the pins are placed in contact with the solder (or flux), for example lowering the template such that the pins **220** each contact their respective solder members **215** (or flux members **216** if present).

The example method **100** may, at block **130**, comprise removing the pin template and reflowing the solder. Block **130** may comprise removing the pin template and reflowing the solder in any of a variety of manners, non-limiting examples of which are provided herein. Various example aspects of block **130** are presented in the example **200E** shown at FIG. 2E.

For example, block **130** may comprise, before reflowing the solder members **215** (or after such reflowing, in alternative implementations), lifting the pin template **221** upward. As the pin template **221** is lifted upward, the pins **220**, which may be adhered to the solder members **215** (or flux members **216** if present), stay in place.

Note that before removal of the pin template **221**, excess pins **220** (if any) may be removed from the top side of the pin template **221**, removed laterally from an area of the pin template **221** having the apertures **222**, etc. Such removal may, for example, be performed by sweeping or brushing, blowing, dumping, vacuuming, etc.

After removal of the pin template **221** (or prior to such removal in alternative implementations), block **130** may comprise reflowing the solder members **215** (e.g., utilizing mass reflow, etc.). It should be noted that other forms of pin attachment, instead of solder, may be utilized without departing from the scope of this disclosure. For example, a conductive adhesive may be applied and cured instead of applying and reflowing solder. Also for example, solderless direct metal-to-metal (e.g., copper-to-copper, etc.) bonding may be utilized to attach the pins **220** to the conductive pads **205**.

After the reflowing (or otherwise attaching), each of the pins **220** is fixedly solder-attached to a respective one of the conductive pads **205**. Non-limiting examples of such soldered pins are provided in the examples **200I-1** and **200I-2** shown at FIGS. 2I-1 and 2I-2, respectively. Referring to the example **200I-1**, the reflowed solder **215'** may form a fillet that rises up at least a portion of the lateral side of the pin **220**. As shown in FIG. 2I-1, there may be a layer of the reflowed solder **215'** that is positioned directly between the pin **220** and the conductive pad **205**, separating the pin **220** and the pad **205** from direct contact with each other. In alternative implementations, however, the bottom side of the pin **220** may directly contact the top side of the conductive pad **205**. The reflowed solder **215'** may, for example, cover the entire top side of the pad **205**, but need not.

Referring to the example **200I-2**, a smaller amount of solder (relative to the example **200I-1**) may be utilized. Utilizing a smaller amount of solder may, for example, reduce electromigration between the solder and the pin metal (e.g., copper, etc.) over time, resulting in a solder joint with enhanced conductivity performance and increased longevity. In the example **200I-2**, a space **208** (or volume, or indentation) directly between the perimeter of the bottom end of the pin **220** and the conductive pad **205** may be free of solder. As with the example **200I-1** shown at FIG. **2I-1**, there may be a layer of the reflowed solder **215'** that is positioned directly between the pin **220** and the conductive pad **205**, separating the pin **220** and the pad **205** from direct contact with each other. In alternative implementations, however, the bottom side of the pin **220** may directly contact the top side of the conductive pad **205**. The reflowed solder **215'** may cover the entire conductive pad **205**, but need not. The outer perimeter of the reflowed solder **215'** may, for example, extend laterally outside the lateral perimeter of the pin **220**, but need not.

In general, block **130** may comprise removing the pin template and reflowing the solder. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of removing a pin template and/or by characteristics of any particular manner of reflowing solder.

The example method **100** may, at block **135**, comprise mounting electronic components to the substrate. Block **135** may comprise mounting electronic components to the substrate in any of a variety of manners, non-limiting examples of which are provided herein. Various example aspects of block **135** are presented in the example **200F** shown at FIG. **2F**, which presents a different cross-section of the device of FIGS. **2A-2E**.

For example, block **135** may comprise mounting a semiconductor die **235** to die-mounting pads of the signal distribution structure **201** of the substrate **210**. The semiconductor die **235** (or other component(s)) may be mounted to the signal distribution structure **201** in any of a variety of manners. For example, conductive bumps **236** (e.g., pillars or posts, C4 bumps, conductive balls, etc.) may be connected to respective die mounting pads **237** utilizing respective solder joints **238** (e.g., mass reflowed joints, thermocompression bonded joints, laser-reflow joints, etc.), utilizing conductive adhesive, utilizing solderless direct metal-to-metal bonds, etc.

Though only a single semiconductor die **235** is shown in FIG. **2F**, the scope of this disclosure is not limited thereto. For example, one or more semiconductor dies and/or one or more passive electronic components (e.g., resistors, capacitors, inductors, etc.) may be mounted to the signal distribution structure **201**.

The mounted electronic component(s) may comprise any of a variety of dimensional characteristics. For example, a mounted electronic component may have a thickness that is entirely within the height of the pins **220**. Also for example, a mounted electronic component may have a top-side height above the substrate **210** that is less than or equal to the height of a top-side of the pins **220**. For example, in an example implementation, a pin **220** may be 300 μm tall, and the semiconductor die **235** may be 250 μm tall. Note that the scope of this disclosure should not be limited such example dimensions.

As shown in FIG. **2F**, a mounted electronic component **235** may be positioned directly laterally between a plurality of the pins **220**. A mounted electronic component **235** may also, for example, be laterally surrounded by the pins **220**.

Block **135** may comprise attaching the electronic component(s) **235** to the signal distribution structure **201** in any of a variety of manners. For example, block **135** may comprise utilizing reflow attachment, thermocompression bonding (e.g., with or without pre-applied non-conductive paste), adhesive bonding, solderless direct metal-to-metal bonding, etc. For example, block **135** may comprise performing a second reflow different from the reflow performed at block **130**. In an example implementation, in addition to forming solder **215** (and/or flux **216**) for the pins **220**, block **115** may comprise forming solder on die pads and/or other electronic component pads of the signal distribution structure **201**. In an example implementation, the pins **220** and the electronic component(s) **235** may all be attached utilizing a single reflow attachment (e.g., holding the pins **220** in place until the electronic component(s) **235** is also placed).

In general, block **135** may comprise mounting electronic components to the substrate. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of mounting electronic components to the substrate or by characteristics of any particular type of electronic component.

The example method **100** may, at block **140**, compose encapsulating and thinning. Block **140** may comprise performing the encapsulating and thinning in any of a variety of manners, non-limiting examples of which are provided herein. Various example aspects of block **140** are presented in the example **200G** shown at FIG. **2G**.

For example, block **140** may comprise forming an encapsulating material **240** utilizing a molding process (e.g., injection molding, compression molding, etc.) and a molding material. Also for example, block **140** may comprise spray-coating, spin-coating, otherwise depositing the encapsulating material **240**, etc.

Block **140** may, for example, comprise originally forming (e.g., prior to any thinning process being performed) the encapsulating material **240** to cover top ends of the pins **220** and/or of any or all of the electronic components **235**. Also for example, block **140** may comprise originally forming the encapsulating material **240** to a height that exposes the top ends of the pins **220** and/or of any or all of the electronic components(s).

As illustrated in FIG. **2G**, block **140** may, for example, comprise thinning (or originally forming) the encapsulating material **240** to expose the top end surfaces of the pins **220**. For example, the top surfaces of the pins **220** and the top surface of the encapsulating material **240** may be coplanar.

Though the top side of the example electronic component **235** (e.g., semiconductor die, etc.) is shown covered by the encapsulating material **240**, as with the pins **220**, the top sides of any one or more electronic components may also be exposed from the encapsulant. For example, the top surfaces of the pins **220**, the top surfaces of any or all electronic components **235**, and the top surface of the encapsulating material **240** may be coplanar.

Note that during the thinning, block **140** may also comprise thinning the pins **220** and/or the electronic component(s) **235**. For example, top ends of the pins **220** (as originally formed) may be ground or abraded off, bulk semiconductor material from the backside of a semiconductor die **235** may be ground or abraded off, etc. For example, in an implementation as shown in the example **200I-1** of FIG. **2I-1**, the curved (or smooth) transition **223** may be ground or abraded off, resulting in a pin **220** with a curved (or smooth) transition **223** at the bottom end and a sharp transition between the lateral side and the top end.

11

Note that in an example implementation in which block **140** comprises originally forming the encapsulating material **240** having the desired final thickness and in which the top sides of any pins **220** or component(s) **235** are originally formed and mounted with the desired final height, a thinning operation may be omitted.

As shown in FIG. 2G, the encapsulating material **240** may laterally surround the pins **220** and the electronic component(s) **235**. The encapsulating material **240** may also underfill the electronic component(s) **235**, though the electronic component(s) **235** may alternatively be underfilled utilizing a material separate from the encapsulating material **240**.

In general, block **140** may comprise encapsulating and thinning. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of encapsulating and/or thinning.

The example method **100** may, at block **145**, comprise performing further processing. Block **145** may comprise performing further processing in any of a variety of manners, non-limiting examples of which are provided herein. Various example aspects of block **145** are presented in the example **200H** shown at FIG. 2H.

For example, block **145** may comprise forming a top-side signal distribution structure **245** (or redistribution structure) over the pins **220**, encapsulating material **240**, and/or electronic component(s) **235**. Block **145** may comprise forming such a top-side signal distribution structure **245** in any of a variety of manners, many of which were discussed herein with regard to the signal distribution structure **201**. For example, top-side signal distribution structure **245** can be built layer by layer (dielectric and conductive layers) atop the device of example **200G**, or can be placed there instead as a pre-built unit. Block **145** may also, for example, comprise forming top side pads on (or connected to) the top ends of the pins. Such top side pads may, for example, comprise underbump metallization layers, etc.

Also for example, block **145** may comprise removing the support layer **209** (or carrier) from the substrate **210**, leaving the signal distribution structure **201** exposed. For example, bottom side conductive pads may be exposed at the bottom side of the signal distribution structure **201**. Block **145** may comprise removing the carrier in any of a variety of manners. For example, block **145** may comprise removing the support layer **209** (or carrier) by grinding, etching, peeling, sheering, melting, planarizing, etc.

Block **145** may then, for example, comprise building additional layers of signal distribution structure on the bottom side of the signal distribution structure **201**. Block **145** may also, for example, comprise forming interconnection structures **246** (e.g., conductive balls or bumps, conductive pillars or posts, etc.) on the bottom side of the signal distribution structure **201** (or on the bottom side of any additional signal distribution structure, any underbump metallization, etc., that may have been formed on the bottom of the original signal distribution structure **201**).

As discussed herein, any or all of the process steps discussed to this point may be performed on a single substrate or may be performed on a plurality of connected substrates (e.g., on a substrate wafer, on a substrate panel, on a die wafer, etc.). In such a scenario, block **145** may comprise performing a singulating (or cutting, or severing, etc.) operation, in which individual electronic devices (or packages) are separated from other connected electronic devices (or packages). For example, referring to FIG. 2H, block **145** may comprise singulating the example **200H** electronic device by cutting along singulation streets of a wafer or panel. Such cutting may, for example, result in

12

lateral sides of the signal distribution structure **201**, the encapsulating material **240**, and/or the top-side signal distribution structure **245** being coplanar.

In general, block **145** may comprise performing further processing. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of performing further processing.

The example method **100** may, at block **190**, comprise continuing the method **100**. Such continuing may comprise any of a variety of characteristics, non-limiting examples of which are provided herein.

For example, block **190** may comprise returning execution flow of the example method **100** to any block thereof. Also for example, block **190** may comprise directing execution flow of the example method **100** to any other method block (or step) discussed herein (e.g., with regard to the example method **300** of FIG. 3, FIGS. 4A to 4F-3, FIGS. 5A-5C, etc.).

As discussed herein with regard to the pins **220**, such pins **220** may comprise any of a variety of shapes and sizes. Additional example shapes of such pins **220** are shown at FIGS. 4F-1 to 4F-3. For example, the pins **220** might comprise a shape and/or dimensions that do not allow the pins **220** to slide completely through the apertures **222** of the pin template **221**. An example implementation that applies to pins having such shapes will be discussed next. Note, however, that the example implementation may also be utilized in a scenario in which the pins **220** are able to slide completely through the apertures **222** of the pin template.

Turning now to FIG. 3, such figure shows a flow diagram of an example method **300** of making an electronic device (e.g., a semiconductor package, etc.), in accordance with various aspects of the present disclosure. The example method **300** may, for example, share any or all characteristics with any other example method(s) discussed herein (e.g., the example method **100** of FIG. 1, of FIGS. 2A to 2I-2, of FIGS. 5A-5C, etc.) or any portion thereof. FIGS. 4A to 4F-3 show cross-sectional views illustrating an example electronic device (e.g., a semiconductor package, etc.) and an example method of making an example electronic device, in accordance with various aspects of the present disclosure. FIGS. 4A to 4F-3 may, for example, illustrate an example electronic device at various blocks (or steps) of the method **300** of FIG. 3. FIG. 3 and FIGS. 4A to 4F-3 will now be discussed together. It should be noted that the order of the example blocks of the method **300** may vary without departing from the scope of this disclosure.

The example method **300** may begin executing at block **305**. The method **300** may begin executing in response to any of a variety of causes or conditions, non-limiting examples of which are provided herein. For example, the method **300** may begin executing automatically in response to one or more signals received from one or more upstream and/or downstream manufacturing stations, in response to a signal from a central manufacturing line controller, upon arrival of components and/or manufacturing materials utilized during performance of the method **300**, etc. Also for example, the method **300** may begin executing in response to an operator command to begin. Additionally for example, the method **300** may begin executing in response to receiving execution flow from any other method block (or step) discussed herein.

The example method **300** may, at block **310**, comprise receiving, fabricating, and/or preparing a substrate. Block **310** may comprise receiving, fabricating, and/or preparing a substrate in any of a variety of manners, non-limiting examples of which are provided herein. For example, block

310 may share any or all characteristics with block 110 of the example method 100 shown in FIG. 1 and discussed herein. Various example aspects of block 310 are presented in the example 200A shown at FIG. 2A.

The example method 300 may, at block 315, comprise forming solder (or other attachment material). Block 315 may comprise forming solder in any of a variety of manners, non-limiting examples of which are provided herein. For example, block 315 may share any or all characteristics with block 115 of the example method 100 shown in FIG. 1 and discussed herein. Various example aspects of block 315 are presented in the examples 200B-1 and 200B-2 shown at FIGS. 2B-1 and 2B-2, respectively.

The example method 300 may, at block 317, comprise providing a pin template and pins. Block 317 may comprise providing the pin template and pins in any of a variety of manners, non-limiting examples of which are provided herein. Block 317 may, for example, share any or all characteristics with blocks 120 and 125 of the example method 100 shown in FIG. 1 and discussed herein. Various example aspects of block 317 are also shown in the example 400A shown at FIG. 4A.

As shown in the example 400A shown in FIG. 4A, block 317 may for example provide a pin template 421. The pin template 421 may, for example, share any or all characteristics with the pin template 221 of FIGS. 2A to 2I-2 discussed herein. The pin template 421 (e.g., a metal foil stencil, stainless steel stencil, electroform nickel stencil, etc.) may, for example, comprise a plurality of apertures 422, each corresponding to a respective one of the pins 420.

The pin template 421 may, for example, have a thickness that is less (or equal to) than a height of the pins 420, less than (or equal to) a height of the main body of the pins 420, etc.

In the example implementation 400A shown in FIG. 4A, an adhesive layer 424 (e.g., an adhesive tape or film, etc.) is adhered to a bottom side of the pin template 421. The adhesive layer 424 may, for example, be utilized to temporarily hold the pins 420 (e.g., when the pins 420 are positioned at block 318) until the pins 420 are released at block 323. Note that other manners of holding the pins 420 in place may also be utilized (e.g., vacuum pressure, electromagnetic force, mechanical holders, gravity, etc.).

A plurality pins 420 may, for example, be placed on the pin template 421 (e.g., dumped, poured, scooped, blown, etc.). At the example 400A of FIG. 4A, some or all of the pins 420 might not be positioned in respective apertures. Note that although the example 400A illustrates a same number of pins 420 and apertures 422, the pins 420 may outnumber the apertures 422.

The pins 420 may comprise any of a variety of characteristics. For example, the pins 420 may share any or all characteristics with the pins 220 discussed herein with regard to FIGS. 2A to 2I-2. For example, the pins 420 may have a cylinder-shaped main body and a head (e.g., like a head of a nail). Also example, the pins 420 (e.g., entire pins, main bodies of pins, heads of pins, etc.) may be cylinder-shaped, for example with a circular cross-section and flat top and bottom surfaces. Also for example, the pins 420 (e.g., entire pins, main bodies of pins, heads of pins, etc.) may have an oval cross-section, polygonal cross-section, non-circular cross-section, etc. A non-limiting example, of the pin 420 is shown in the example 400E-1 of FIG. 4F-1. Such example pin 420 has a main body portion 420a that is generally cylinder-shaped with curved (or smooth) transitions 423 between the lateral side and at least one of the top and/or bottom ends. Such example pin 420 also has a head

portion 420b that is generally cylinder-shaped with curved (or smooth) transitions 423 between the lateral side and at least one of the top and/or bottom ends. Note that any of such transitions 423 may be sharp (or comprise a surface discontinuity or sharp corner). The head portion 420b of the example pin 420 of FIG. 4F-1 has a diameter that is greater than the diameter of the main body portion 420a.

The top and/or bottom ends may, for example, be beveled. For example, as shown in the example 400E-3 of FIG. 4F-3, an end of the main body portion 420a opposite the head portion 420b may have a bevel 423'. Any of the ends of the main body portion 420a and/or the head portion 420b may have such a bevel.

The example pin 420 shown in FIG. 400E-1 has main body portion 420a with a diameter of 180 um and a longitudinal height of 210 um, and a head portion 420b with a diameter of 200 um and a longitudinal height of 50 um. The scope of this disclosure, however, is not limited to any particular dimensions.

Returning to FIG. 4A, the apertures 422 may for example be generally shaped like the pins 420 (e.g., like the main body portion 420a of the pin 420). For example, the apertures 422 may be cylinder-shaped to match cylinder-shaped main body portions 420a of the pins, etc. In an example implementation, the diameter of the apertures 422 may be slightly larger than the diameter of the main body portions 420a of the pins 420 and sized to enhance pin placement temporal efficiency while maintaining placement accuracy. For example, the diameter of the apertures 422 may be in the range of 10 um larger (e.g., 40 um larger, 50 um larger, etc.) than the diameter of the pins 420. Also for example, the diameter of the apertures 422 may in the range of 10% to 50% larger (e.g., 25% larger, 33% larger, etc.) than the diameter of the main body portions 420a of the pins 420. Additionally for example, the diameter of the apertures 422 may be smaller than the diameter of the head portions 420b of the pins 420, for example to inhibit the head portions 420b from sliding through the apertures 422 while allowing the main body portions 420a to slide through the apertures 422. Also note that the apertures 422 (e.g., at the upper side of the template 421 as oriented in FIG. 4A, etc.) may have curved, sloped, or beveled openings to enhance the filling of the apertures 422 with the pins 420.

The pins 220 may be formed in any of a variety of manners. For example, the pins 220 may, for example, be formed by cutting a wire into segments and stamping (or compressing) a head portion into each segment. The pins 220 may also, for example, be formed by plating, molding, printing, reflowing, depositing, etc.

In general, block 317 may comprise providing a pin template and pins. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of providing a pin template and pins or by characteristics of any particular type of pin template and pins.

The example method 300 may, at block 318, comprise positioning pins in pin template apertures. Block 318 may comprise positioning pins in pin template apertures in any of a variety of manners, non-limiting examples of which are provided herein. For example, block 318 may share any or all characteristics with block 125 of the example method 100 shown at FIG. 1 and discussed herein. Various example aspects of block 318 are presented in the example 200D shown at FIG. 2D. Various example aspects of block 318 are also presented in the example 400B shown at FIG. 4B.

For example, block 318 may comprise vibrating the pin template 421 to jostle the pins 420 until each of the apertures 422 is filled with a respective pin 420 (e.g., a main body

portion **420a** of a respective pin **420**, etc.). In an example implementation, block **318** may comprise vibrating the pin template **421** in a lateral direction in any of a variety of motion patterns (e.g., in a plane parallel to a general plane of the template **421**). Note that in various implementations, there may also be a vertical component to the vibrating. The range of the vibration motion may, for example, be a portion of the diameter (or width) of a conductive pad **205** (or solder **215** and/or flux **216** thereof), for example 5-10% of the pad diameter, 1-20% of the pad diameter, etc.). Any of a variety of vibration frequencies may be utilized. For example, a vibration frequency in the range of 1 KHz to 5 KHz (e.g., 2 KHz, 3 KHz, etc.) may be utilized.

Also for example, block **318** may comprise sweeping or brushing the pins **420** over the apertures **422** (e.g., repeatedly) until the apertures **422** are each filled with a respective pin **420** (or main body portion **420a** thereof). Such sweeping or brushing may, for example, be utilized exclusively or may be combined (e.g., serially or in parallel) with the vibration motion.

In an example implementation, as each pin **420** falls into (or is directly pick-and-placed into) its respective aperture **422**, pin **420** may contact the top side of the adhesive layer **424**. The pin **420** may thus be adhered to the adhesive layer **424** and held in place in its respective aperture **422** of the pin template **421**. Note, however, in an example implementation in which the substrate **410** is mated to the pins **420** by positioning the substrate **410** above the pin template **421**, the adhesive layer **424** may be skipped (e.g., utilizing gravity to hold the pins **420** in their respective apertures **422**, etc.).

In general, block **318** may comprise positioning pins in pin template apertures. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of positioning pins in pin template apertures.

Note that in various example implementations, for example in which block **317** provides the pin template with all of the pins already in place, block **318** may be skipped.

The example method **300** may, at block **320**, comprise positioning the pin template and pins (e.g., the pins positioned at block **318**). Block **320** may comprise positioning the pin template and pins in any of a variety of manners, non-limiting examples of which are provided herein. Block **320** may, for example, share any or all characteristics with block **120** and/or block **125** of the example method **100** shown at FIG. 1 and discussed herein. Various example aspects of block **320** are presented in the example **200C** shown at FIG. 2C. Various example aspects of block **320** are also presented in the example **400C** shown at FIG. 4C and discussed herein.

As shown in the example **400C** shown in FIG. 4C, block **320** may for example comprise positioning a pin template **421** (e.g., a metal foil stencil, etc.), for example including a plurality of pins **420** positioned in respective apertures **422**, adjacent to (e.g., over, under, etc.) the substrate **410**. The substrate **410** may share any or all characteristics of the substrate **210** of FIGS. 2A to 2I-2, discussed herein. For example, the substrate **410** may comprise a support layer **409** (or carrier) that shares any or all characteristics of the support layer **409** (or carrier), and a signal distribution structure **401** that shares any or all characteristics of the signal distribution structure **201**. Also for example, the substrate **410** may comprise conductive pads **405** that share any or all characteristics with the conductive pads **205** of FIGS. 2A to 2I-2, solder members **415** that share any or all characteristics with the solder members **215** of FIGS. 2B-1

to 2I-2, and/or flux members (not shown) that share any or all characteristics with the flux members **216** of FIG. 2B-2.

Each of the apertures **422** of the pin template **421** may, for example, correspond to a respective pin **421** and correspond to a respective one of the conductive pads **405** of the substrate **410**. Block **320** may, for example, comprise laterally positioning each of the apertures **422** (or respective pin **420** thereof) directly adjacent (e.g., directly over, directly under, etc.) a respective conductive pad **405** of the substrate **410** (e.g., over a respective solder member **415** and/or flux member). As shown in the example **400C** of FIG. 4C, an end surface of a head portion **420b** of each pin **420** contacts and is adhered to a respective solder member **415** (and/or flux member if present) of a respective conductive pad **405**. At the same time an end surface of a main body portion **420a** of each pin **420** is adhered to the adhesive layer **424**.

As shown in FIG. 4C, the pin template **421** may be elevated (or offset) from the substrate **410** enough so that the pin template **421** does not touch the solder members **415** (and/or flux members if present). Such height or offset may, for example be controlled at the edges of the stencil, by offset members connected to the bottom of the stencil, by tie members connected to the top of the stencil, etc. The pin template **421** may, for example, have a thickness that is less than a height of the pins **420**. In an example implementation, the thickness of the pin template **421** may, for example, be less than or equal to a longitudinal length of a main body portion **420a** of a pin **420**.

It should be understood that although in FIG. 4C, the pin template **421** is positioned over the substrate **410**, in another example implementation, the substrate **410** may be positioned over the pin template (e.g., generally inverting the diagram shown in FIG. 4C). As mentioned herein, in such an example implementation, the adhesive layer **424** may be skipped, but need not be.

In general, block **320** may comprise positioning the pin template and pins. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of positioning a pin template and pins or by characteristics of any particular type of pin template and pins.

The example method **300** may, at block **323**, comprise releasing the pins from the pin template. Block **323** may comprise releasing the pins from the pin template in any of a variety of manners, non-limiting examples of which are provided herein. Block **323** may, for example, share any or all characteristics with block **130** of the example method **100** shown at FIG. 1 and discussed herein. Various example aspects of block **323** are presented in the example **200E** shown at FIG. 2E. Various example aspects of block **323** are also presented in the example **400D** shown at FIG. 4D and discussed herein.

For example, as shown at FIG. 4D, block **323** may comprise peeling (or otherwise removing) the adhesive layer **424** (e.g., an adhesive tape or film, etc.) from the top side of the pin template **421** and from the top ends of the pins **420** (as oriented in FIG. 4D). Block **323** may also, for example, comprise utilizing chemical means to remove the adhesive layer **424**, applying temperature to release the adhesive layer **424**, applying light energy to release the adhesive layer **424**, etc. Removing the adhesive layer **424** may, for example, remove a mechanical coupling between the pins **420** and the pin template **421**.

As discussed herein, other manners of holding the pins **420** in place in the pin template **421** may be utilized (e.g., vacuum pressure, electromagnetic force, mechanical holders, gravity, etc.). In such implementations, block **323** may for example comprise releasing vacuum pressure (and/or

reversing such vacuum), removing any electromagnetic force or mechanical holder keeping the pins 420 in place, etc.

In general, block 323 may comprise releasing the pins from the pin template. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of releasing a pin from a pin template.

The example method 300 may, at block 330, comprise removing the pin template and reflowing the solder. Block 330 may comprise removing the pin template and reflowing the solder in any of a variety of manners, non-limiting examples of which are provided herein. For example, block 330 may share any or all characteristics with block 130 of the example method 100 shown at FIG. 1 and discussed herein. Various example aspects of block 330 are presented in the example 200E shown at FIG. 2E. Various example aspects of block 330 are also presented in the example 400E shown at FIG. 4E.

For example, block 330 may comprise, before reflowing the solder members 415 (or after such reflowing, in alternative implementations), lifting the pin template 421 upward. As the pin template 421 is lifted upward, the pins 420, which may be adhered to the solder members 415 (or flux members if present) stay in place.

After removal of the pin template 421 (or prior to such removal in alternative implementations), block 330 may comprise reflowing the solder members 415 (e.g., utilizing mass reflow, etc.). It should be noted that other forms of pin attachment, instead of solder, may be utilized without departing from the scope of this disclosure. For example, a conductive adhesive may be applied and cured instead of applying and reflowing solder. Also for example, solderless direct metal-to-metal (e.g., copper-to-copper, etc.) bonding may be utilized to attach the pins to the conductive pads.

After the reflowing, each of the pins 421 is fixedly solder-attached to a respective one of the conductive pads 405. Non-limiting examples of such soldered pins are provided in the examples 400E-1, 400E-2, and 400E-3 shown at FIGS. 4F-1, 4F-2, and 4F-3, respectively. Referring to the example 400E-1, the reflowed solder 415' may form a fillet that rises up at least a portion of the lateral side of the pin 420 (e.g., at least a portion of the lateral side of the head portion 420b of the pin 420, etc.). As shown in FIG. 4F-1, there may be a layer of the reflowed solder 415' that is positioned directly between the pin 420 (e.g., a head portion 420b of the pin 420, etc.) and the conductive pad 405, separating the pin 420 and the pad 405 from direct contact with each other. In alternative implementations, however, the bottom side of the pin 420 (e.g., a bottom side of a head portion 420b of the pin 420, etc.) may directly contact the top side of the conductive pad 405. The reflowed solder 415' may cover the entire pad 405, but need not.

Referring to the example 400E-2, a smaller amount of solder (relative to the example 400E-1) may be utilized. Utilizing a smaller amount of solder may, for example, reduce electromigration between the solder and the pin metal (e.g., copper, etc.) over time, resulting in a solder joint with enhanced conductivity performance and increased longevity. In the example 400E-2, a space 408 (or volume or indentation) directly between the perimeter of the bottom end of the pin 420 (e.g., a bottom end of the head portion 420b of the pin 420, etc.) and the conductive pad 405 may be free of solder. As with the example 400E-1 shown at FIG. 4F-1, there may be a layer of the reflowed solder 415' that is positioned directly between the pin 420 (e.g., a head

contact with each other. In alternative implementations, however, the bottom side of the pin 420 (e.g., the bottom side of a head portion 420b of the pin 420, etc.) may directly contact the top side of the conductive pad 405. The reflowed solder 415' may cover the entire conductive pad 405, but need not. The outer perimeter of the reflowed solder 415' may, for example, extend laterally outside the lateral perimeter of the pin 420 (e.g., laterally outside a lateral perimeter of a head portion 420b of the pin 420, etc.), but need not.

In general, block 330 may comprise removing the pin template and reflowing the solder. Accordingly, the scope of this disclosure should not be limited by characteristics of any particular manner of removing a pin template and/or by characteristics of any particular manner of reflowing solder.

The example method 300 may, at block 335, comprise mounting electronic components to the substrate. Block 335 may comprise mounting electronic components to the substrate in any of a variety of manners, non-limiting examples of which are provided herein. For example, block 335 may share any or all characteristics with block 135 of the example method 100 shown in FIG. 1 and discussed herein. Various example aspects of block 335 are presented in the example 200F shown at FIG. 2F (e.g., with the attached pins 420 of FIG. 4E, etc.).

The example method 300 may, at block 340, compose encapsulating and thinning. Block 340 may comprise performing the encapsulating and thinning in any of a variety of manners, non-limiting examples of which are provided herein. For example, block 340 may share any or all characteristics with block 140 of the example method 100 shown in FIG. 1 and discussed herein. Various example aspects of block 340 are presented in the example 200G shown at FIG. 2G (e.g., with the attached pins 420 of FIG. 4E, etc.).

The example method 300 may, at block 345, comprise performing further processing. Block 345 may comprise performing further processing in any of a variety of manners, non-limiting examples of which are provided herein. For example, block 345 may share any or all characteristics with block 145 of the example method 100 shown in FIG. 1 and discussed herein. Various example aspects of block 345 are presented in the example 200H shown at FIG. 2H (e.g., with the attached pins 420 of FIG. 4E, etc.).

The example method 300 may, at block 390, comprise continuing the method 300. Such continuing may comprise any of a variety of characteristics, non-limiting examples of which are provided herein.

For example, block 390 may comprise returning execution flow of the example method 300 to any block thereof. Also for example, block 390 may comprise directing execution flow of the example method 300 to any other method block (or step) discussed herein (e.g., with regard to the example method 100 of FIG. 1, FIGS. 2A to 2I-2, FIGS. 5A-5C, etc.).

As discussed herein, for example in either of the example methods 100 and 300 discussed herein, the substrate on which the pins are mounted may comprise an active semiconductor die (or wafer thereof), and the pins may be mounted to pads on the active surface of such die (or wafer thereof). Also for example, the pins may be mounted to a signal distribution layer that has been formed over the active surface of the die. Note that in various other implementations, for example incorporating through silicon via or other signal routing technology, the pins may be mounted to the backsides of various types of semiconductor dies.

In such an example, a semiconductor die having the pins attached thereto may then be coupled to another substrate (e.g., a motherboard, a laminate substrate, a printed circuit

board (PCB), a package substrate, another package, another die, etc.). FIGS. 5A to 5C provides examples 500A, 500B, and 500C of such operations. The example methods and structures shown in FIGS. 5A to 5C may, for example, share any or all characteristics with the example methods and structures shown in FIG. 1, FIGS. 2A to 2I-2, FIG. 3, FIGS. 4A to 4F-3, etc.

The example 500A of FIG. 5A may, for example, share any or all characteristics with the examples 200E and 400E of FIGS. 2 and 4, and discussed herein. In this example, the support layer 509 (or carrier) may include bulk semiconductor material, at least some of which may be permanent material of the completed electronic device. The example 500A also includes the signal distribution structure 501, conductive pads 505, solder members 515, and pins 520, many examples of which have been provided herein.

The example 500B of FIG. 5B shows providing a substrate 590 on which the example 500A will be mounted. The example substrate 590 comprises a base 599, a signal distribution structure 598 including various dielectric and conductive layers, and conductive pads 575. The example substrate 590 may, for example, share any or all characteristics with any other substrate discussed herein (e.g., substrate 210, etc.). The example substrate 590 may, for example, comprise a package substrate, a motherboard, a laminate substrate, a printed circuit board (PCB), a coreless substrate, another package, another die, etc.).

The example 500B also includes solder members 585 formed on the conductive pads 575. Note that as discussed herein, flux members may be added. The solder members 585 may comprise any of a variety of characteristics. For example, the solder members 585 may share any or all characteristics with any of the solder members discussed herein (e.g., solder member 215, etc.) Also note that, as discussed herein, any of a variety of forms of attachment may be utilized (e.g., conductive epoxy, solderless metal-to-metal bonds, etc.).

The example 500C of FIG. 5C shows the example 500A (as shown in FIG. 5A) coupled to the substrate 590 (of the example 500B shown in FIG. 5B), for example, by positioning the pins 530 in contact with the solder members 585 and performing a reflow process. Note that any of a variety of other operations may be performed (e.g., underfilling between the substrates 510 and 590, molding, forming additional signal distribution structures, forming interconnection structures, singulating, etc.).

In summary, various aspects of this disclosure provide an electronic device and a manufacturing method thereof. As non-limiting examples, various aspects of this disclosure provide an electronic device having a top side pin array, for example which may be utilized for three-dimensional stacking, and a method for manufacturing such an electronic device. While the foregoing has been described with reference to certain aspects and examples, it will be understood by those skilled in the art that various changes may be made and equivalents may be substituted without departing from the scope of the disclosure. In addition, many modifications may be made to adapt a particular situation or material to the teachings of the disclosure without departing from its scope. Therefore, it is intended that the disclosure not be limited to the particular example(s) disclosed, but that the disclosure will include all examples falling within the scope of the appended claims.

What is claimed is:

1. An electronic device comprising:
 - a lower redistribution structure comprising an upper surface and a lower surface, the upper surface comprising a conductive portion and a die-attach pad;
 - a semiconductor die attached and electrically coupled to the die-attach pad;
 - an upper redistribution structure comprising an upper surface and a lower surface, the lower surface comprising a conductive portion; and
 - a non-plated pin comprising:
 - a lower end attached to the conductive portion of the lower redistribution structure via a solder member; and
 - an upper end attached to the conductive portion of the upper redistribution structure.
2. The electronic device of claim 1, wherein the solder member comprises a portion directly positioned between the lower end of the pin and the conductive portion of the lower redistribution structure.
3. The electronic device of claim 2, wherein:
 - a width of an upper surface of the solder member is smaller than a width of the pin and leaves a space that is free of solder; and
 - the space is directly between a perimeter of the lower end of the pin and the conductive portion of the lower redistribution structure.
4. The electronic device of claim 1, wherein the solder member comprises a fillet that rises up a portion of a lateral side of the pin.
5. The electronic device of claim 1, wherein the pin comprises:
 - a lateral side between the upper end and the lower end of the pin; and
 - a rounded edge that directly joins the lower end of the pin to the lateral side of the pin, the rounded edge providing a curved transition between the lateral side of the pin and the lower end of the pin.
6. The electronic device of claim 1, wherein:
 - the pin comprises a cylinder-shaped main body and a head at the lower end of the pin;
 - the main body has a body diameter; and
 - the head has a head diameter that is greater than the body diameter.
7. The electronic device of claim 1, wherein:
 - the pin comprises a cylinder-shaped main body and a head at the upper end of the pin;
 - the main body has a body diameter; and
 - the head has a head diameter that is greater than the body diameter.
8. The electronic device of claim 1, wherein the upper end of the pin is beveled.
9. The electronic device of claim 1, wherein the lower end of the pin is beveled.
10. The electronic device of claim 1, further comprising encapsulating material that encapsulates and directly contacts a lateral side of the pin;
 - wherein the upper end of the pin is coplanar with an upper surface of the encapsulating material.
11. The electronic device of claim 1, wherein:
 - the upper redistribution structure comprises a dielectric layer having a lower surface; and
 - the lower surface of the conductive portion of the upper redistribution structure, the lower surface of the dielectric layer, and the lower surface of the upper redistribution structure are coplanar.
12. The electronic device of claim 11, further comprising encapsulating material that encapsulates and directly contacts a lateral side of the pin, wherein:

21

the encapsulating material comprises an upper surface that is coplanar with the lower surface of the upper redistribution structure.

13. The electronic device of claim 1, wherein a diameter of the pin is greater than a diameter of the conductive portion of the upper redistribution structure.

14. An electronic device comprising:

a lower redistribution structure comprising an upper surface and a lower surface, the upper surface comprising a conductive portion and a die-attach pad;

a semiconductor die attached and electrically coupled to the die-attach pad;

a pin comprising a lower end and an upper end, the lower end attached to the conductive portion of the lower redistribution structure via a conductive adhesive;

encapsulating material that encapsulates and directly contacts:

a lateral side of the pin; and

a lateral side of the semiconductor die; and

an upper redistribution structure comprising a conductive layer and a dielectric layer built on an upper surface of the encapsulating material such that:

a conductive portion of conductive layer is attached to an upper end of the pin; and

a lower surface of the dielectric layer, a lower surface of the upper redistribution structure, and a lower surface of the conductive layer are coplanar.

15. The electronic device of claim 14, wherein:

the pin comprises a main body and a head at an end of the pin, the end selected from the upper end and the lower end of the pin;

the main body has a body diameter;

22

the head has a head diameter that is greater than the body diameter; and

an end of the pin, that is opposite the head, is beveled.

16. The electronic device of claim 14, wherein a diameter of the pin is greater than a diameter of the conductive portion of the upper redistribution structure.

17. An electronic device comprising:

a lower redistribution structure comprising an upper surface and a lower surface, the upper surface comprising a conductive portion and a die-attach pad;

a semiconductor die attached and electrically coupled to the die-attach pad;

an upper redistribution structure comprising an upper surface and a lower surface, the lower surface comprising a conductive portion; and

a pin attached to:

the conductive portion of the lower redistribution structure via a solder member; and

the conductive portion of the upper redistribution structure;

wherein the pin comprises a first end, a second end, a main body that extends from the first end to the second end, and a head at the first end; and

wherein the head of the pin has a greater diameter than the main body of the first pin.

18. The electronic device of claim 17, wherein the second end of the pin is beveled.

19. The electronic device of claim 17, further comprising encapsulating material that encapsulates and directly contacts:

a lateral side of the pin; and

a surface of the semiconductor die.

20. The electronic device of claim 17, wherein a diameter of the pin is greater than a diameter of the conductive portion of the upper redistribution structure.

* * * * *