



US010861948B2

(12) **United States Patent**
Edwards et al.

(10) **Patent No.:** **US 10,861,948 B2**
(45) **Date of Patent:** **Dec. 8, 2020**

(54) **DRIFT REGION IMPLANT SELF-ALIGNED TO FIELD RELIEF OXIDE WITH SIDEWALL DIELECTRIC**

(56) **References Cited**

(71) Applicant: **TEXAS INSTRUMENTS INCORPORATED**, Dallas, TX (US)

U.S. PATENT DOCUMENTS

5,428,241 A 6/1995 Terashima
5,517,046 A 5/1996 Hsing et al.
(Continued)

(72) Inventors: **Henry Litzmann Edwards**, Garland, TX (US); **Binghua Hu**, Plano, TX (US); **James Robert Todd**, Plano, TX (US)

FOREIGN PATENT DOCUMENTS

JP H0955502 A 2/1997
JP 2011204998 A 10/2011

(73) Assignee: **TEXAS INSTRUMENTS INCORPORATED**, Dallas, TX (US)

OTHER PUBLICATIONS

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

Chahar Suman, et al: "The impact of gate and channel length of a Si LDMOS transistor on its on resistance and breakdown voltage", 2015 International Conference on Electrical, Electronics, Signals, Communication and Optimization (EESCO), IEEE, Jan. 24, 2015, pp. 1-4, XP033200347, DOI: 10.1109/EESCO.2015.7253874 ISBN: 978-1-4799-7676-8.

(21) Appl. No.: **16/683,517**

(22) Filed: **Nov. 14, 2019**

Primary Examiner — Feifei Yeung Lopez

(65) **Prior Publication Data**

US 2020/0083336 A1 Mar. 12, 2020

(74) *Attorney, Agent, or Firm* — Michael A. Davis, Jr.; Charles A. Brill; Frank D. Cimino

Related U.S. Application Data

(63) Continuation of application No. 15/406,891, filed on Jan. 16, 2017, now Pat. No. 10,497,787, which is a (Continued)

(57) **ABSTRACT**


(51) **Int. Cl.**
H01L 29/40 (2006.01)
H01L 29/78 (2006.01)
(Continued)

An integrated circuit which includes a field-plated FET is formed by forming a first opening in a layer of oxide mask, exposing an area for a drift region. Dopants are implanted into the substrate under the first opening. Subsequently, dielectric sidewalls are formed along a lateral boundary of the first opening. A field relief oxide is formed by thermal oxidation in the area of the first opening exposed by the dielectric sidewalls. The implanted dopants are diffused into the substrate to form the drift region, extending laterally past the layer of field relief oxide. The dielectric sidewalls and layer of oxide mask are removed after the layer of field relief oxide is formed. A gate is formed over a body of the field-plated FET and over the adjacent drift region. A field plate is formed immediately over the field relief oxide adjacent to the gate.

(52) **U.S. Cl.**
CPC **H01L 29/408** (2013.01); **H01L 21/02238** (2013.01); **H01L 21/02255** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 29/402; H01L 29/1095; H01L 29/42368; H01L 29/66681; H01L 29/7816
See application file for complete search history.

11 Claims, 16 Drawing Sheets



Related U.S. Application Data

continuation of application No. 15/003,776, filed on Jan. 21, 2016, now Pat. No. 9,583,612.

H01L 29/7835 (2013.01); *H01L 29/063* (2013.01); *H01L 29/1083* (2013.01)

(51) **Int. Cl.**

H01L 21/32 (2006.01)
H01L 21/8234 (2006.01)
H01L 27/088 (2006.01)
H01L 29/08 (2006.01)
H01L 29/66 (2006.01)
H01L 21/02 (2006.01)
H01L 21/266 (2006.01)
H01L 27/06 (2006.01)
H01L 29/10 (2006.01)
H01L 29/423 (2006.01)
H01L 21/265 (2006.01)
H01L 21/324 (2006.01)
H01L 21/762 (2006.01)
H01L 29/06 (2006.01)
H01L 29/167 (2006.01)
H01L 21/225 (2006.01)

(52) **U.S. Cl.**

CPC *H01L 21/2253* (2013.01); *H01L 21/266* (2013.01); *H01L 21/26513* (2013.01); *H01L 21/32* (2013.01); *H01L 21/324* (2013.01); *H01L 21/76202* (2013.01); *H01L 21/76224* (2013.01); *H01L 21/823418* (2013.01); *H01L 21/823462* (2013.01); *H01L 27/0617* (2013.01); *H01L 27/088* (2013.01); *H01L 29/0653* (2013.01); *H01L 29/0847* (2013.01); *H01L 29/1095* (2013.01); *H01L 29/167* (2013.01); *H01L 29/402* (2013.01); *H01L 29/42368* (2013.01); *H01L 29/66659* (2013.01); *H01L 29/66681* (2013.01); *H01L 29/7816* (2013.01); *H01L 29/7823* (2013.01);

(56)

References Cited

U.S. PATENT DOCUMENTS

5,622,878 A	4/1997	Beasom	
6,255,154 B1	7/2001	Akaishi et al.	
6,392,274 B1	5/2002	Tung	
6,483,149 B1	11/2002	Mosher et al.	
2002/0048912 A1	4/2002	Kikuchi et al.	
2005/0199968 A1	9/2005	Matsui et al.	
2006/0157781 A1*	7/2006	Takimoto	<i>H01L 29/0873</i> 257/335
2007/0063271 A1*	3/2007	Takimoto	<i>H01L 29/42368</i> 257/330
2008/0315308 A1	12/2008	Huang et al.	
2010/0102386 A1	4/2010	You	
2010/0102388 A1	4/2010	Levin et al.	
2010/0301411 A1	12/2010	Takeda et al.	
2010/0314683 A1*	12/2010	Yanagi	<i>H01L 27/0635</i> 257/339
2011/0241114 A1	10/2011	Su et al.	
2012/0037988 A1	2/2012	Hao	
2013/0037883 A1	2/2013	Huang et al.	
2013/0087828 A1	4/2013	Koshimizu et al.	
2014/0021560 A1	1/2014	Su et al.	
2014/0048880 A1	2/2014	Tsuchiko	
2014/0264581 A1	9/2014	Chan et al.	
2015/0085408 A1	3/2015	Ellis-Monaghan et al.	
2015/0137192 A1	5/2015	Han	
2015/0295081 A1*	10/2015	Matsuda	<i>H01L 29/7816</i> 257/339
2016/0087039 A1*	3/2016	Ko	<i>H01L 29/7816</i> 257/339
2016/0190269 A1*	6/2016	Brown	<i>H01L 29/66659</i> 438/286
2016/0254346 A1	9/2016	Zhang et al.	

* cited by examiner




FIG. 1




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 2G




FIG. 2H




FIG. 2I




FIG. 2J




FIG. 2K




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 3E




FIG. 3F

1

DRIFT REGION IMPLANT SELF-ALIGNED TO FIELD RELIEF OXIDE WITH SIDEWALL DIELECTRIC

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 15/406,891, which is a continuation of U.S. patent application Ser. No. 15/003,776 filed Jan. 21, 2016, issued as U.S. Pat. No. 9,583,612, the content of which is herein incorporated by reference in its entirety.

FIELD

This disclosure relates to the field of integrated circuits. More particularly, this disclosure relates to field effect transistors in integrated circuits.

BACKGROUND

Some integrated circuits contain field effect transistors (FETs) with drift regions to enable higher voltage operation. As these integrated circuits are scaled to the next generation of products, there is a desire to increase the switching frequency of these FETs to reduce the sizes of the external passive components such as inductors while maintaining a low power dissipation in these FETs. This requires simultaneously reducing the switching parasitics and the on-state specific resistances (the area-normalized on-state resistances) of the FETs.

To enable operation at elevated drain voltage, the FETs employ drift regions that deplete under high drain voltage conditions, allowing the FETs to block the voltage while supporting conduction during the on-state. A higher voltage FET tends to be formed with the gate extending over field oxide in order to act as a field plate for the drift region. Unfortunately, field oxide in advanced fabrication nodes such as the 250 nanometer node and beyond is commonly formed by shallow trench isolation (STI) processes, and is generally too thick for optimal use as a field relief oxide under a gate extension field plate in such a FET.

SUMMARY

The following presents a simplified summary in order to provide a basic understanding of one or more aspects of the disclosure. This summary is not an extensive overview of the disclosure, and is neither intended to identify key or critical elements of the disclosure, nor to delineate the scope thereof. Rather, the primary purpose of the summary is to present some concepts of the disclosure in a simplified form as a prelude to a more detailed description that is presented later.

An integrated circuit which includes a field-plated FET is formed by forming a layer of oxide mask over a top surface of a substrate of the integrated circuit, covering an area for the field-plated FET. A first opening is formed in the layer of oxide mask, exposing an area for a drift region of the field-plated FET. Dopants are implanted into the substrate under the first opening. Subsequently, dielectric sidewalls are formed on the layer of oxide mask along a lateral boundary of the first opening. A layer of field relief oxide is formed at the top surface of the substrate in the area of the first opening which is exposed by the dielectric sidewalls. The implanted dopants are diffused into the substrate to form the drift region, extending laterally past the layer of field

2

relief oxide. The dielectric sidewalls and layer of oxide mask are removed after the layer of field relief oxide is formed. A gate of the field-plated FET is formed over a body of the field-plated FET, extending over the adjacent drift region. A field plate is formed immediately over the field relief oxide adjacent to the gate.

DESCRIPTION OF THE VIEWS OF THE DRAWING

FIG. 1 is a cross section of an example integrated circuit including a field-plated FET.

FIG. 2A through FIG. 2K are cross sections of the integrated circuit of FIG. 1, depicting successive stages of an example method of formation.

FIG. 3A through FIG. 3F are cross sections of another example integrated circuit containing a field-plated FET, depicted in successive stages of an example method of formation.

DETAILED DESCRIPTION

The present disclosure is described with reference to the attached figures. The figures are not drawn to scale and they are provided merely to illustrate the disclosure. Several aspects of the disclosure are described below with reference to example applications for illustration. It should be understood that numerous specific details, relationships, and methods are set forth to provide an understanding of the disclosure. One skilled in the relevant art, however, will readily recognize that the disclosure can be practiced without one or more of the specific details or with other methods. In other instances, well-known structures or operations are not shown in detail to avoid obscuring the disclosure. The present disclosure is not limited by the illustrated ordering of acts or events, as some acts may occur in different orders and/or concurrently with other acts or events. Furthermore, not all illustrated acts or events are required to implement a methodology in accordance with the present disclosure.

FIG. 1 is a cross section of an example integrated circuit including a field-plated FET. In the instant example, an n-channel field-plated FET will be disclosed. An analogous p-channel field-plated FET may be described with appropriate changes in polarities of dopants. The integrated circuit **100** includes a substrate **102**, possibly with a heavily doped n-type buried layer **104** and a p-type layer **106** over the n-type buried layer **104**. The p-type layer **106** extends to a top surface **108** of the substrate **102**. The integrated circuit **100** includes the n-channel field-plated FET **110**. The integrated circuit **100** may also optionally include a planar FET **112**. Components of the integrated circuit **100**, such as the field-plated FET **110** and the planar FET **112** may be laterally separated by field oxide **114**. The field oxide **114** may have an STI structure as depicted in FIG. 1, or may have a localized oxidation of silicon (LOCOS) structure.

The field-plated FET **110** includes an n-type drift region **116** disposed in the substrate **102**. The drift region **116** extends from an n-type drain contact region **118** to a p-type body **120** of the field-plated FET **110**. An average dopant density of the drift region **116** may be, for example, $1 \times 10^{16} \text{ cm}^{-3}$ to $1 \times 10^{16} \text{ cm}^{-3}$. The drift region **116** may have a heavier-doped top portion and a lighter doped bottom portion, to provide desired values of breakdown voltage and specific resistance for the field-plated FET **110**. A layer of field relief oxide **122** is disposed over the drift region **116**. The field relief oxide **122** has a tapered profile at lateral edges of the field relief oxide **122**, commonly referred to as

a bird's beak. The field relief oxide **122** is thinner than the field oxide **114**. The drift region **116** extends past the field relief oxide **122** by a lateral distance **124** adjacent to the body **120**. The lateral distance **124** may be, for example, 100 nanometers to 200 nanometers, which may advantageously provide desired low values of specific resistance and gate-drain capacitance of the field-plated FET **110**. A gate dielectric layer **126** of the field-plated FET **110** is disposed at the top surface **108** of the substrate **102**, extending from the field relief oxide **122** to an n-type source **128** of the field-plated FET **110** abutting the body **120** opposite from the drift region **116**. The gate dielectric layer **126** is disposed over a portion of the drift region **116** which extends past the field relief oxide **122**, and over a portion of the body **120** between the drift region **116** and the source **128**. The field relief oxide **122** is at least twice as thick as the gate dielectric layer **126**. The field-plated FET **110** includes a gate **130** disposed over the gate dielectric layer **126**, extending from the source **128**, over the portion of the body **120** between the drift region **116** and the source **128**, and over the portion of the drift region **116** which extends past the field relief oxide **122**. In the instant example, the gate **130** extends partway over the field relief oxide **122** to provide a field plate **132** over a portion of the drift region **116**. In an alternate version of the instant example, the field plate may be provided by a separate structural element from the gate **130**. The thickness of the field relief oxide **122** may be selected to provide a desired maximum value of electric field in the drift region **116** during operation of the field-plated FET **110**.

The field-plated FET **110** may possibly include an optional charge adjustment region **134** disposed in the substrate immediately under the field relief oxide **122**. The charge adjustment region **134** is substantially aligned with the field relief oxide **122**. In one version of the instant example, dopants in the charge adjustment region **134** may be n-type, such as phosphorus and/or arsenic, so that a net dopant density in the charge adjustment region **134** is higher than in the drift region **116** below the charge adjustment region **134**. In this version of the instant example, the charge adjustment region **134** may be considered to be a part of the drift region **116**. In another version of the instant example, dopants in the charge adjustment region **134** may be p-type, such as boron, gallium and/or indium, which compensate, but do not counter-dope, the n-type dopants of the drift region **116**, so that a net dopant density in the charge adjustment region **134** is lower than in the drift region **116** below the charge adjustment region **134**, but remains n-type. In this version of the instant example, the charge adjustment region **134** may also be considered to be a part of the drift region **116**. In a further version of the instant example, the dopants in the charge adjustment region **134** may be p-type, which counter-dope the n-type dopants of the drift region **116**, so that a net dopant density in the charge adjustment region **134** is converted to p-type. In this version of the instant example, the charge adjustment region **134** may be considered to be separate from the drift region **116**. Dopant polarity and density in the charge adjustment region **134** may be selected to provide desired values of breakdown voltage and specific resistance for the field-plated FET **110**.

The field-plated FET **110** may also include a p-type body contact region **136** disposed in the substrate **102** in the body **120**. Gate sidewall spacers **138** may be disposed on side surfaces of the gate **130**. Metal silicide **140** may be disposed on the drain contact region **118** and the source **128** and body contact region **136**. The field-plated FET **110** may have a drain-centered configuration in which the drain contact region **118** is surrounded by the field relief oxide **122**, which

is surrounded by the body **120** and source **128**. Other configurations of the field-plated FET **110** are within the scope of the instant example.

The planar FET **112** includes an n-type drift region **142** disposed in the substrate **102**. The drift region **142** extends from an n-type drain contact region **144** to a p-type body **146** of the planar FET **112**. The planar FET **112** is free of a layer of field relief oxide similar to the field relief oxide **122** of the field-plated FET **110**. The planar FET **112** is also free of charge adjustment regions similar to the charge adjustment region **134** of the field-plated FET **110**. The drift region **142** of the planar FET **112** has a similar distribution and species of dopants as the drift region **116** of the field-plated FET **110**, as a result of being formed concurrently.

A gate dielectric layer **148** of the planar FET **112** is disposed at the top surface **108** of the substrate **102**, extending from the drain contact region **144** to an n-type source **150** of the planar FET **112** abutting the body **146** opposite from the drift region **142**. The gate dielectric layer **148** is disposed over a portion of the drift region **142** between the drain contact region **144** and the body **146**, and over a portion of the body **146** between the drift region **142** and the source **150**. The planar FET **112** includes a gate **152** disposed over the gate dielectric layer **148**, extending from the source **150** to a position proximate to the drain contact region **144**.

The planar FET **112** may also include a p-type body contact region **154** disposed in the substrate **102** in the body **146**. Gate sidewall spacers **156** may be disposed on side surfaces of the gate **152**. The metal silicide **140**, if present on the field-plated FET **110** may be disposed on the drain contact region **144** and the source **150** and body contact region **154**. The planar FET **112** may have a drain-centered configuration or other configuration.

FIG. 2A through FIG. 2K are cross sections of the integrated circuit of FIG. 1, depicting successive stages of an example method of formation. Referring to FIG. 2A, the substrate **102** may be formed by starting with a p-type silicon wafer, possibly with an epitaxial layer on a top surface, and forming the n-type buried layer **104** by implanting n-type dopants such as antimony at a dose of 1×10^{15} cm^{-2} to 1×10^{16} cm^{-2} . A thermal drive process heats the wafer to activate and diffuse the implanted n-type dopants. The p-type layer **106** is formed on the wafer by an epitaxial process with in-situ p-type doping. The epitaxially formed material may be, for example 4 microns to 6 microns thick, advantageously enabled by the relatively shallow drift region **116** of FIG. 1, which is made possible by the self-aligned nature of the field relief oxide **122** of FIG. 1 relative to the drift region **116**. The n-type dopants diffuse partway into the epitaxially grown material, so that the n-type buried layer **104** overlaps a boundary between the original silicon wafer and the epitaxially grown material. An average bulk resistivity of the p-type layer **106** may be, for example, 1 ohm-cm to 10 ohm-cm. An optional p-type buried layer may be formed in the p-type layer **106** by implanting boron at an energy, for example, of 2 mega-electron volts (MeV) to 3 MeV.

The field oxide **114** is formed at the top surface **108** of the substrate **102**, for example by an STI process or a LOCOS process. An example STI process includes forming a chemical mechanical polish (CMP) stop layer of silicon nitride and a layer of STI pad oxide over the substrate **102**. Isolation trenches are etched through the CMP stop layer and the STI pad oxide and into the substrate **102**. The isolation trenches are filled with silicon dioxide using a plasma enhanced chemical vapor deposition (PECVD) process using tetra-

ethyl orthosilicate (TEOS), a high density plasma (HDP) process, a high aspect ratio process (HARP) using TEOS and ozone, an atmospheric chemical vapor deposition (AP-CVD) process using silane, or a sub-atmospheric chemical vapor deposition (SACVD) process using dichlorosilane. Excess silicon dioxide is removed from over the CMP stop layer by an oxide CMP process. The CMP stop layer is subsequently removed, leaving the field oxide **114**. An example LOCOS process includes forming a silicon nitride mask layer over a layer of LOCOS pad oxide over the substrate **102**. The silicon nitride mask layer is removed in areas for the field oxide **114**, exposing the LOCOS pad oxide. Silicon dioxide is formed in the areas exposed by the silicon nitride mask layer by thermal oxidation, to form the field oxide **114**. The silicon nitride mask layer is subsequently removed, leaving the field oxide **114** in place.

A layer of pad oxide **158** is formed at the top surface **108** of the substrate **102**. The pad oxide **158** may be, for example, 5 nanometers to 25 nanometers thick, and may be formed by thermal oxidation or by any of several chemical vapor deposition (CVD) processes. A layer of oxide mask **160** is formed over the layer of pad oxide **158**. The layer of oxide mask **160** may include, for example, silicon nitride, formed by a low pressure chemical vapor deposition (LPCVD) process using dichlorosilane and ammonia. Alternatively, silicon nitride in the layer of oxide mask **160** may be formed by decomposition of bis(tertiary-butyl-amino) silane (BT-BAS). Other processes to form the layer of oxide mask **160** are within the scope of the instant example. The layer of oxide mask **160** may be, for example, around 1 to 2 times the thickness of the field relief oxide **122** of FIG. 1.

An etch mask **162** is formed over the layer of oxide mask **160** which exposes an area for the field relief oxide **122** of FIG. 1 in the area for the field-plated FET **110**, and exposes an area for implanting the drift region **142** of FIG. 1 in the area for the planar FET **112**. The etch mask **162** may include photoresist formed by a photolithographic process, and may include hard mask material such as amorphous carbon, and may include an anti-reflection layer such as an organic bottom anti-reflection coat (BARC). The exposed area for the field relief oxide **122** in the area for the field-plated FET **110** has lateral dimensions that are sufficiently wide so that after etching the layer of oxide mask **160**, a central portion of the etched area remains clear after formation of dielectric sidewalls. The exposed area for implanting the drift region **142** in the area for the planar FET **112** has a width sufficiently narrow so that after etching the layer of oxide mask **160**, the exposed area for implanting the drift region **142** remains blocked by the dielectric material used to form the dielectric sidewalls.

Referring to FIG. 2B, the layer of oxide mask **160** is removed in the areas exposed by the etch mask **162**, exposing the layer of pad oxide **158**. A portion of the pad oxide **158** may also be removed in the areas exposed by the etch mask **162**. Removing the layer of oxide mask **160** in the area for the field-plated FET **110** forms a first opening **164** in the layer of oxide mask **160**. Removing the layer of oxide mask **160** in the area for the planar FET **112** forms a second opening **166** in the layer of oxide mask **160**. Lateral dimensions **168** of the first opening **164** are sufficiently wide so that a central portion of the first opening **164** remains clear after formation of dielectric sidewalls. For example, in a version of the instant example in which the dielectric sidewalls are formed by deposition of a conformal layer that is 80 nanometers to 100 nanometers thick, the lateral dimensions **168** are greater than about 350 nanometers. A width **170** of the second opening **166** is sufficiently narrow so that

the second opening **166** remains blocked by the dielectric material used to form the dielectric sidewalls. To attain a desired amount of dielectric material in the second opening, the width **170** of the second opening **166** may be less than 2.5 times a thickness of a subsequently formed dielectric layer to form dielectric sidewalls in the first opening **164**. For example, in the version of the instant example disclosed above in which the dielectric sidewalls are formed by deposition of a conformal layer that is about 80 nanometers thick, the width **170** is less than about 200 nanometers. The layer of oxide mask **160** may be removed by a wet etch, for example an aqueous solution of phosphoric acid, which undercuts the etch mask **162** as depicted in FIG. 2B. Alternatively, the layer of oxide mask **160** may be removed by a plasma etch using fluorine radicals, which may produce less undercut. The etch mask **162** may optionally be removed after etching the layer of oxide mask **160**, or may be left in place to provide additional stopping material in a subsequent ion implant step.

Referring to FIG. 2C, n-type dopants **172** are implanted into the substrate **102** in the areas exposed by removing the layer of oxide mask **160**, including the first opening **164** in the area for the field-plated FET **110** and the second opening **166** in the area for the planar FET **112**, advantageously self-aligning the subsequently-formed drift region **116** of FIG. 1 to the subsequently-formed field relief oxide **122** of FIG. 1. The n-type dopants **172** may include, for example, phosphorus **174** which may be implanted at a dose of 1×10^{12} cm^{-2} to 4×10^{12} cm^{-2} at an energy of 150 kilo-electron volts (keV) to 225 keV, and arsenic **176** which may be implanted at a dose of 2×10^{12} cm^{-2} to 6×10^{12} cm^{-2} at an energy of 100 keV to 150 keV. The implanted phosphorus **174** forms a first phosphorus implanted region **178** under the first opening **164** and a second phosphorus implanted region **180** under the second opening **166**. Similarly, the implanted arsenic **176** forms a first arsenic implanted region **182** under the first opening **164** and a second arsenic implanted region **184** under the second opening **166**. The first phosphorus implanted region **178** and the second phosphorus implanted region **180** are advantageously deeper than the first arsenic implanted region **182** and the second arsenic implanted region **184**, to provide graded junctions in the drift region **116** of FIG. 1 in the field-plated FET **110** and the drift region **142** of FIG. 1 in the planar FET **112**. Optionally, the phosphorus dopants **174** of the n-type dopants **172** may also include a deep dose of phosphorus which forms a first deep compensating implanted region **186** in the substrate **102** below the first phosphorus implanted region **178** and forms a second deep compensating implanted region **188** in the substrate **102** below the second phosphorus implanted region **180**. The deep dose of phosphorus is intended to compensate the p-type layer **106** so as to reduce the net dopant density without counter-doping the p-type layer **106** to n-type. Any remaining portion of the etch mask **162** is removed after the n-type dopants **172** are implanted.

Referring to FIG. 2D, an optional thermal drive operation may be performed which activates and diffuses the implanted n-type dopants **172** of FIG. 2C. For example, the thermal drive operation may include a ramped furnace anneal at about 900° C. to 1050° C. for 30 minutes to 60 minutes. The phosphorus dopants in the first phosphorus implanted region **178** of FIG. 2C form a first phosphorus diffused region **190** under the first opening **164**, and the phosphorus dopants in the second phosphorus implanted region **180** of FIG. 2C form a second phosphorus diffused region **192** under the second opening **166**. Similarly, the arsenic dopants in the first arsenic implanted region **182** of

FIG. 2C form a first arsenic diffused region **194** under the first opening **164**, and the arsenic dopants in the second arsenic implanted region **184** of FIG. 2C form a second arsenic diffused region **196** under the second opening **166**. The first phosphorus diffused region **190** and the second phosphorus diffused region **192** are advantageously deeper than the first arsenic diffused region **194** and the second arsenic diffused region **196**. If the first deep compensating implanted region **186** and the second deep compensating implanted region **188** are formed as described in reference to FIG. 2C, the optional thermal driver operation diffuses and activates the phosphorus dopants in the first deep compensating implanted region **186** of FIG. 2C to form a first compensated region **198** in the substrate **102** under and around the first phosphorus diffused region **190**, and diffuses and activates the phosphorus dopants in the second deep compensating implanted region **188** of FIG. 2C to form a second compensated region **200** in the substrate **102** under and around the second phosphorus diffused region **192**. In lieu of the optional thermal drive operation, the implanted n-type dopants **172** may be activated and diffused during a subsequent thermal oxidation operation to form the field relief oxide **122** of FIG. 1.

Referring to FIG. 2E, a conformal dielectric layer **202** is formed over the layer of oxide mask **160** and in the first opening **164** in the area for the field-plated FET **110** and in the second opening **166** in the area for the planar FET **112**. The conformal dielectric layer **202** may comprise a single layer of dielectric material, or may comprise two or more sub-layers. The conformal dielectric layer **202** may include silicon nitride, silicon dioxide and/or other dielectric material. In the version of the instant example depicted in FIG. 2E, the conformal dielectric layer **202** may include a thin layer of silicon dioxide **204** formed on the layer of oxide mask **160** and on the pad oxide **158**, and a layer of silicon nitride **206** formed on the thin layer of silicon dioxide **204**. A thickness of the conformal dielectric layer **202** is selected to provide a desired width of subsequently-formed dielectric sidewalls in the first opening **164** on lateral edges of the layer of oxide mask **160**, and to block the second opening **166**. For example, the thickness of the conformal dielectric layer **202** may be 80 nanometers to 100 nanometers to provide dielectric sidewalls that are 75 nanometers to 90 nanometers wide. The conformal dielectric layer **202** in a center of the second opening **166** is thicker than the conformal dielectric layer **202** in a center of the first opening **164**, as a result of the limited width **170** of the second opening **166**. Silicon nitride in the conformal dielectric layer **202** may be formed by an LPCVD process or decomposition of BTBAS. Silicon dioxide in the conformal dielectric layer **202** may be formed by decomposition of TEOS.

Referring to FIG. 2F, an anisotropic etch process is performed which removes the conformal dielectric layer **202** from a central portion of the first opening **164**, leaving dielectric material of the conformal dielectric layer **202** to form dielectric sidewalls **208** in the first opening **164** on lateral edges of the layer of oxide mask **160**. A width of the dielectric sidewalls **208** may be, for example, 50 percent to 90 percent of the thickness of the conformal dielectric layer **202** as formed in the center of the first opening **164**. The anisotropic etch does not remove all of the dielectric material of the conformal dielectric layer **202** from the second opening **166** so that a continuous portion of the dielectric material covers the pad oxide **158** in the second opening **166**.

Referring to FIG. 2G, an optional charge adjustment implant operation may be performed which implants charge

adjustment dopants **210** are implanted into the substrate **102**, using the dielectric sidewalls **208** and the layer of oxide mask **160** as an implant mask. The implanted charge adjustment dopants **210** form a charge adjustment implanted region **212** in the substrate **102** immediately under the first opening **164**; lateral extents of the charge adjustment implanted region **212** are defined by the dielectric sidewalls **208**, advantageously self-aligning the subsequently-formed charge adjustment region **134** of FIG. 1 to the subsequently-formed field relief oxide **122** of FIG. 1. The dielectric material of the conformal dielectric layer **202** remaining in the second opening **166** blocks the charge adjustment dopants **210** from the substrate **102** below the second opening **166**. In one version of the instant example, the charge adjustment dopants **210** may be n-type dopants such as phosphorus and/or arsenic. In another version of the instant example, the charge adjustment dopants **210** may be p-type dopants, such as boron, gallium and/or indium. A dose of the charge adjustment dopants **210** may be, for example, 1×10^{10} cm^{-2} to 1×10^{12} cm^{-2} . The charge adjustment dopants **210** may be implanted at an energy sufficient to place a peak of the implanted dopants 25 nanometers to 100 nanometers into the substrate **102** below the pad oxide **158**.

Referring to FIG. 2H, the field relief oxide **122** is formed by thermal oxidation in the first opening **164** in the area for the field-plated FET **110**. Properties of the dielectric sidewalls **208** and the layer of oxide mask **160** affect a length and shape of the tapered profile, that is, the bird's beak, at lateral edges of the field relief oxide **122**. Thermal oxide does not form in the second opening **166** in the area for the planar FET **112**, because the dielectric material of the conformal dielectric layer **202** remaining in the second opening **166** blocks an oxidizing ambient of the thermal oxidation process. An example furnace thermal oxidation process may include ramping a temperature of the furnace to about 1000° C. in a time period of 45 minutes to 90 minutes with an ambient of 2 percent to 10 percent oxygen, maintaining the temperature of the furnace at about 1000° C. for a time period of 10 minutes to 20 minutes while increasing the oxygen in the ambient to 80 percent to 95 percent oxygen, maintaining the temperature of the furnace at about 1000° C. for a time period of 60 minutes to 120 minutes while maintaining the oxygen in the ambient at 80 percent to 95 percent oxygen and adding hydrogen chloride gas to the ambient, maintaining the temperature of the furnace at about 1000° C. for a time period of 30 minutes to 90 minutes while maintaining the oxygen in the ambient at 80 percent to 95 percent oxygen with no hydrogen chloride, and ramping the temperature of the furnace down in a nitrogen ambient. The temperature profile of the thermal oxidation process diffuses and activates the implanted dopants in the charge adjustment implanted region **212** of FIG. 2G to form the charge adjustment region **134**. The temperature profile of the thermal oxidation process also further diffuses the n-type dopants of the first phosphorus diffused region **190**, the second phosphorus diffused region **192**, the first arsenic diffused region **194** and the second arsenic diffused region **196**, and the first compensated region **198** and the second compensated region **200**, if present. A majority of the n-type dopants in the first arsenic diffused region **194** are arsenic, and a majority of the n-type dopants in the first phosphorus diffused region **190** are phosphorus. Similarly, a majority of the n-type dopants in the second arsenic diffused region **196** are arsenic, and a majority of the n-type dopants in the second phosphorus diffused region **192** are phosphorus. The first phosphorus diffused region **190** and the first arsenic diffused region **194** provide the drift region **116** of the field-plated FET **110**.

Similarly, the second phosphorus diffused region **192** and the second arsenic diffused region **196** provide the drift region **142** of the planar FET **112**. The first compensated region **198** and the second compensated region **200** are p-type, with a lower net dopant density than the underlying p-type layer **106**. The first compensated region **198** and the second compensated region **200** advantageously provide reduced drain junction capacitances for the field-plated FET **110** and the planar FET **112**, respectively. The layer of oxide mask **160**, the dielectric sidewalls **208** and the dielectric material of the conformal dielectric layer **202** remaining in the second opening **166** are subsequently removed. Silicon nitride may be removed by an aqueous solution of phosphoric acid. Silicon dioxide may be removed by an aqueous solution of buffered dilute hydrofluoric acid.

Referring to FIG. **2I**, the p-type body **120** of the field-plated FET **110** and the p-type body **146** of the planar FET **112** are formed, possibly concurrently. The body **120** and the body **146** may be formed by implanting p-type dopants such as boron at one or more energies, to provide a desired distribution of the p-type dopants. An example implant operation may include a first implant of boron at a dose of $1 \times 10^{14} \text{ cm}^{-2}$ to $3 \times 10^{14} \text{ cm}^{-2}$ at an energy of 80 keV to 150 keV, and a second implant of boron at a dose of $1 \times 10^{13} \text{ cm}^{-2}$ to $3 \times 10^{13} \text{ cm}^{-2}$ at an energy of 30 keV to 450 keV. A subsequent anneal process, such as a rapid thermal anneal at 1000° C . for 30 seconds, activates and diffuses the implanted boron.

A layer of gate dielectric material **214** is formed on exposed semiconductor material at the top surface **108** of the substrate **102**, including in the areas for the field-plated FET **110** and the planar FET **112**. The layer of gate dielectric material **214** may include silicon dioxide, formed by thermal oxidation, and/or hafnium oxide or zirconium oxide, formed by CVD processes, and may include nitrogen atoms introduced by exposure to a nitrogen-containing plasma. A thickness of the layer of gate dielectric material **214** reflects operating voltages of the field-plated FET **110** and the planar FET **112**. A layer of gate material **216** is formed over the layer of gate dielectric material **214** and the field relief oxide **122**. The layer of gate material **216** may include, for example, polycrystalline silicon, referred to herein as polysilicon, possibly doped with n-type dopants. Other gate materials, such as titanium nitride, in the layer of gate material **216** are within the scope of the instant example. Polysilicon in the layer of gate material **216** may be, for example, 300 nanometers to 800 nanometers thick.

A gate mask **218** is formed over the layer of gate material **216** to cover areas for the gate **130** of FIG. **1** of the field-plated FET **110** and the gate **152** of FIG. **1** of the planar FET **112**. In the instant example, the gate mask **218** extends partway over the field relief oxide **122** to cover an area for the field plate **132** of FIG. **1**. The gate mask **218** may include photoresist formed by a photolithographic process. The gate mask **218** may also include a layer of hard mask material such as silicon nitride and/or amorphous carbon. Further, the gate mask **218** may include a layer of anti-reflection material, such as a layer of BARC.

Referring to FIG. **2J**, a gate etch process is performed which removes the layer of gate material **216** of FIG. **2I** where exposed by the gate mask **218**, to form the gate **130** of the field-plated FET **110** and to form the gate **152** of the planar FET **112**. The gate etch process may be, for example, a reactive ion etch (RIE) process using fluorine radicals. The gate mask **218** may be eroded by the gate etch process. After the gates **130** and **152** are formed, the remaining gate mask **218** is removed.

Referring to FIG. **2K**, the layer of gate dielectric material **214** of FIG. **2J** provides the gate dielectric layer **126** of the field-plated FET **110** and the gate dielectric layer **148** of the planar FET **112**. The gate sidewall spacers **138** may be formed on side surfaces of the gate **130** of the field-plated FET **110** by forming a conformal layer of sidewall material, possibly comprising more than one sub-layer of silicon nitride and/or silicon dioxide, over the gate **130** and the top surface **108** of the substrate **102**. Subsequently, an anisotropic etch such as an RIE process removes the layer of sidewall material from top surfaces of the gate **130** and the substrate **102**, leaving the gate sidewall spacers **138** in place. The gate sidewall spacers **156** on the gate **152** of the planar FET **112** may be formed similarly to, and possibly concurrently with, the gate sidewall spacers **138** of the field-plated FET **110**.

The n-type source **128** and n-type drain contact region **118** of the field-plated FET **110** may be formed by implanting n-type dopants such as phosphorus and arsenic, for example at a dose of $1 \times 10^{14} \text{ cm}^{-2}$ to $5 \times 10^{15} \text{ cm}^{-2}$ into the substrate **102** adjacent to the gate **130** and the field relief oxide **122**, followed by an anneal operation, such as a spike anneal or a flash anneal, to activate the implanted dopants. An n-type drain extension portion of the source **128** which extends partway under the gate **130** may be formed prior to forming the gate sidewall spacers **138** by implanting n-type dopants into the substrate adjacent to the gate **130**. The n-type source **150** and n-type drain contact region **144** of the planar FET **112** may be formed similarly to, and possibly concurrently with, the source **128** and drain contact region **118** of the field-plated FET **110**.

The p-type body contact region **136** in the body **120** of the field-plated FET **110** may be formed by implanting p-type dopants such as boron, for example at a dose of $1 \times 10^{14} \text{ cm}^{-2}$ to $5 \times 10^{15} \text{ cm}^{-2}$ into the substrate **102**, followed by an anneal operation, such as a spike anneal or a flash anneal, to activate the implanted dopants. The p-type body contact region **136** in the body **146** of the planar FET **112** may be formed similarly to, and possibly concurrently with, the body contact region **136** in the body **120** of the field-plated FET **110**.

Forming the drift region **116** to be self-aligned with the field relief oxide **122** may provide a desired low value of the lateral distance **124** the gate **130** overlaps the drift region **116**, advantageously providing a low gate-drain capacitance. Further, the self-aligned configuration may provide the lateral distance **124** to be controllable from device to device without undesired variability due to unavoidable photolithographic alignment variations, sometimes referred to as alignment errors.

FIG. **3A** through FIG. **3F** are cross sections of another example integrated circuit **300** containing a field-plated FET, depicted in successive stages of an example method of formation. In the instant example, an n-channel field-plated FET will be disclosed. An analogous p-channel field-plated FET may be described with appropriate changes in polarities of dopants. Referring to FIG. **3A**, the integrated circuit **300** includes a substrate **302** with a p-type layer **306** extending to a top surface **308** of the substrate **302**. The p-type layer **306** may be an epitaxial layer on a semiconductor wafer, or may be a top portion of a bulk silicon wafer. The integrated circuit **300** includes the n-channel field-plated FET **310**, which in the instant example has a symmetric drain-centered configuration. The integrated circuit **300** may also optionally include a planar FET, not shown in FIG. **3A** through FIG. **3F**. In the instant example, the integrated circuit **300** includes field oxide **314** around an area for the field-plated FET **310**. The field oxide **314** is formed by an STI process, as

described in reference to FIG. 2A. The STI process uses a layer of STI pad oxide 420 over the top surface 308 of the substrate 302, and a CMP stop layer 422 of silicon nitride over the layer of STI pad oxide 420. In the instant example, the layer of STI pad oxide 420 and the CMP stop layer 422 are not removed after forming the field oxide 314, and are used to form the field-plated FET 310.

The layer of STI pad oxide 420 and the CMP stop layer 422 extend across the area for the field-plated FET 310. An etch mask 362 is formed over the CMP stop layer 422 which exposes areas for a subsequently-formed field relief oxide in the area for the field-plated FET 310. The etch mask 362 may be formed as described in reference to FIG. 2A. The exposed areas for the field relief oxide have lateral dimensions that are sufficiently wide so that after etching the CMP stop layer 422, central portions of the etched areas remains clear after formation of dielectric sidewalls.

Referring to FIG. 3B, the CMP stop layer 422 is removed in the areas exposed by the etch mask 362, exposing the layer of STI pad oxide 420, forming openings 364 in the CMP stop layer 422. Lateral dimensions 368 of the openings 364 are sufficiently wide so that central portions of the openings 364 remain clear after formation of dielectric sidewalls. The CMP stop layer 422 may be removed by a plasma etch using fluorine radicals, which may produce very little undercut, as depicted in FIG. 3B. Alternatively, the CMP stop layer 422 may be removed by a wet etch, as described in reference to FIG. 2B.

N-type dopants 372 are implanted into the substrate 302 in the areas exposed by removing the CMP stop layer 422, including the openings 364 in the area for the field-plated FET 310, advantageously self-aligning a subsequently-formed drift region to the subsequently-formed field relief oxide. The n-type dopants 372 may include, for example, phosphorus and arsenic as described in reference to FIG. 2C. The implanted n-type dopants 372 form drift implanted regions 424 under the openings 364. Any remaining portion of the etch mask 362 is removed after the n-type dopants 372 are implanted.

Referring to FIG. 3C, dielectric sidewalls 408 are formed in the openings 364 on lateral edges of the CMP stop layer 422, for example as described in reference to FIG. 2E and FIG. 2F. Additional sidewalls 426 may be formed over the field oxide 314 on lateral edges of the CMP stop layer 422, concurrently with the dielectric sidewalls 408 in the openings 364. Central portions of the openings 364 are clear after forming the dielectric sidewalls 408.

Referring to FIG. 3D, the field relief oxide 322 is formed by thermal oxidation in the openings 364 in the area for the field-plated FET 310. Properties of the dielectric sidewalls 408 and the CMP stop layer 422 affect a length and shape of lateral edges of the field relief oxide 322. The field relief oxide 322 may be formed by a furnace thermal oxidation process as described in reference to FIG. 2H. The temperature profile of the thermal oxidation process diffuses and activates the implanted n-type dopants in the drift implanted region 424 of FIG. 3C to form a drift region 316 of the field-plated FET 310. The CMP stop layer 422, the dielectric sidewalls 408 and the additional sidewalls 426 are subsequently removed.

Referring to FIG. 3E, an n-type well 428 may optionally be formed in the substrate 302 under the drift region 316 centrally located with respect to the field relief oxide 322. The n-type well 428 may advantageously reduce a drain resistance of the field-plated FET 310 and spread current flow through a central portion of the drain of the field-plated FET 310, providing improved reliability. The n-type well

428 may be formed concurrently with other n-type wells under p-channel metal oxide semiconductor (PMOS) transistors in logic circuits of the integrated circuit 300. A p-type body 320 of the field-plated FET 310 is formed in the substrate 302 abutting the drift region 316. The body 320 may be formed by implanting p-type dopants such as boron, for example as described in reference to FIG. 2I. A subsequent anneal process activates and diffuses the implanted boron.

The layer of STI pad oxide 420 of FIG. 3D is removed. A gate dielectric layer 326 is formed at the top surface 308 of the substrate 302 adjacent to the field relief oxide 322. The gate dielectric layer 326 may be formed, for example, as described in reference to FIG. 2I. A gate 330 of the field-plated FET 310 is formed over the gate dielectric layer 326, extending from proximate the field relief oxide 322 to partway overlapping the body 320. The gate 330 extends over a portion of the drift region between the field relief oxide 322 and the body 320. The gate 330 may be formed as described in reference to FIG. 2I and FIG. 2J.

Gate sidewall spacers 338 are formed on side surfaces of the gate 330, for example as described in reference to FIG. 2K. In the instant example, a gate cap 430 of dielectric material is formed over a top surface of the gate 330. The gate cap 430 and the gate sidewall spacers 338 electrically isolate the top surface and lateral surfaces of the gate 330. The gate cap 430 may be formed, for example, by forming a dielectric layer over a layer of gate material prior to forming a gate mask and performing a gate etch.

Referring to FIG. 3F, an n-type drain contact region 318 is formed in the substrate 302 in the drift region 316 between two opposing portions of the field relief oxide 322. An n-type source 328 is formed in the substrate 302 adjacent to the gate 330 opposite from the drain contact region 318. The drain contact region 318 and the source 328 may be formed as described in reference to FIG. 2K, and may be formed concurrently. An n-type drain extension portion of the source 328 which extends partway under the gate 330 may be formed prior to forming the gate sidewall spacers 338.

In the instant example, a field plate 432 is formed immediately over a portion of the field relief oxide 322, extending to the gate 330. The field plate 432 is electrically isolated from the gate 330. The field plate 432 may be formed by forming a layer of conductive material, such as polysilicon or titanium nitride, over the gate 330 and field relief oxide 322, forming an etch mask over the layer of conductive material to cover an area for the field plate 432, and performing an etch process to define the field plate 432. The integrated circuit 300 may be configured to apply separate bias voltages to the gate 330 and the field plate 432. Forming the field plate 432 to be electrically isolated and separately biasable from the gate 330 may advantageously enable reduction of an electric field in the drift region 316 during operation of the field-plated FET 310 compared to an analogous field-plated FET with a gate overlapping field relief oxide to provide a field plate.

The drift region 316 extends past the field relief oxide 322 a first lateral distance 434 on a first side of the field-plated FET 310, and extends past the field relief oxide 322 a second lateral distance 436 on a second side opposite from the first side. As a result of the drift region 316 being formed in a self-aligned manner with the field relief oxide 322, the first lateral distance 434 is substantially equal to the second lateral distance 436, which may advantageously provide for uniform current distribution through the field-plated FET 310. Forming the drift region 316 to be self-aligned with the field relief oxide 322 may also advantageously provide a

13

desired narrow range of values for the first lateral distance **434** and the second lateral distance **436** which is controllable from device to device without undesired variability due to unavoidable photolithographic alignment variations, sometimes referred to as alignment errors.

While various embodiments of the present disclosure have been described above, it should be understood that they have been presented by way of example only and not limitation. Numerous changes to the disclosed embodiments can be made in accordance with the disclosure herein without departing from the spirit or scope of the disclosure. Thus, the breadth and scope of the present disclosure should not be limited by any of the above described embodiments. Rather, the scope of the disclosure should be defined in accordance with the following claims and their equivalents.

What is claimed is:

1. An integrated circuit, comprising:

a semiconductor substrate layer having a first conductivity type;

a drain contact and a source both having a second conductivity type;

a field relief oxide layer between the drain contact and the source;

a gate oxide layer between the field relief oxide layer and the source;

a drift region under the field relief oxide layer, the drift region including:

a first region doped with a first dopant and having the second conductivity type;

a second region doped with a second dopant of the second conductivity type and having the second conductivity type, the second region being located between the first region and the field relief oxide layer;

a third region doped with the first dopant of the second conductivity type, the third region located between the first region and the semiconductor substrate layer and having the first conductivity type; and

14

a fourth region doped with the second dopant, the fourth region located between the second region and the field relief oxide layer, the fourth region being further doped with additional dopant of the first conductivity type or additional dopant of the second conductivity type.

2. The integrated circuit of claim **1**, wherein the field relief oxide layer has a thickness at least twice that of the gate oxide layer.

3. The integrated circuit of claim **1**, wherein the field relief oxide layer is a LOCOS oxide layer.

4. The integrated circuit of claim **1**, wherein the fourth region has the first conductivity type.

5. The integrated circuit of claim **1**, wherein the fourth region is further doped with additional dopant of the first conductivity type and has the second conductivity type.

6. The integrated circuit of claim **1**, further comprising a body region having the first conductivity type and extending from the drift region under the gate oxide layer to the source, the body region having a higher dopant concentration than the semiconductor substrate layer.

7. The integrated circuit of claim **6**, wherein the source extends under the gate oxide layer toward the drift region, and a portion of the body region is located between the source and the drift region at the gate oxide.

8. The integrated circuit of claim **6**, wherein a distance between the field relief oxide and the body region at the gate oxide is no greater than 100 nm.

9. The integrated circuit of claim **1**, further comprising a polysilicon layer over the field relief oxide layer and the gate oxide layer.

10. The integrated circuit of claim **1**, wherein the first conductivity type is p-type and the second conductivity type is n-type.

11. The integrated circuit of claim **1**, wherein the first dopant of the second conductivity type includes phosphorous and the second dopant of the second conductivity type includes arsenic.

* * * * *