

US010879459B2

(12) **United States Patent**  
**Liu et al.**

(10) **Patent No.:** **US 10,879,459 B2**  
(45) **Date of Patent:** **\*Dec. 29, 2020**

(54) **PHASE CHANGE MEMORY CELL WITH CONstriction STRUCTURE**

(71) Applicant: **Micron Technology, Inc.**, Boise, ID (US)

(72) Inventors: **Jun Liu**, Boise, ID (US); **Michael P. Violette**, Boise, ID (US)

(73) Assignee: **Micron Technology, Inc.**, Boise, ID (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **15/850,570**

(22) Filed: **Dec. 21, 2017**

(65) **Prior Publication Data**

US 2018/0138398 A1 May 17, 2018

**Related U.S. Application Data**

(60) Division of application No. 15/063,238, filed on Mar. 7, 2016, now Pat. No. 10,008,664, which is a (Continued)

(51) **Int. Cl.**  
**H01L 45/00** (2006.01)

(52) **U.S. Cl.**  
CPC ..... **H01L 45/06** (2013.01); **H01L 45/1233** (2013.01); **H01L 45/1246** (2013.01); (Continued)

(58) **Field of Classification Search**  
CPC ... H01L 45/144; H01L 45/06; H01L 45/1608; H01L 45/1675; H01L 45/1683; (Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,789,758 A \* 8/1998 Reinberg ..... G11C 11/56 257/3

6,908,812 B2 6/2005 Lowrey (Continued)

FOREIGN PATENT DOCUMENTS

CN 1967894 5/2007  
CN 1967895 5/2007

(Continued)

OTHER PUBLICATIONS

“Chinese Application Serial No. 200980117105.2 Response filed May 5, 2015 to Office Action dated Feb. 3, 2015”, W/ English Claims, 19 pgs.

(Continued)



*Primary Examiner* — Michael M Trinh

(74) *Attorney, Agent, or Firm* — Schwegman Lundberg & Woessner, P.A.

(57) **ABSTRACT**

Some embodiments include methods of forming memory cells. Such methods can include forming a first electrode, a second electrode, and a memory element directly contacting the first and second electrodes. Forming the memory element can include forming a programmable portion of the memory element isolated from the first electrode by a first portion of the memory element and isolated from the second electrode by a second portion of the memory element. Other embodiments are described.

**16 Claims, 24 Drawing Sheets**



**Related U.S. Application Data**

continuation of application No. 14/458,804, filed on Aug. 13, 2014, now Pat. No. 9,281,478, which is a division of application No. 12/950,827, filed on Nov. 19, 2010, now Pat. No. 8,809,108, which is a division of application No. 12/049,056, filed on Mar. 14, 2008, now Pat. No. 7,852,658.

(52) **U.S. Cl.**  
 CPC ..... *H01L 45/1253* (2013.01); *H01L 45/143* (2013.01); *H01L 45/144* (2013.01); *H01L 45/148* (2013.01); *H01L 45/1608* (2013.01); *H01L 45/1675* (2013.01); *H01L 45/1683* (2013.01)

(58) **Field of Classification Search**  
 CPC ..... H01L 45/1246; H01L 45/1253; H01L 45/1233; H01L 45/148; H01L 45/143  
 See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,927,410	B2	8/2005	Chen	
7,012,273	B2	3/2006	Chen	
7,045,383	B2	5/2006	Maimon et al.	
7,057,923	B2	6/2006	Furkay et al.	
7,351,613	B2	4/2008	Chen et al.	
7,615,770	B2	11/2009	Philipp et al.	
7,772,583	B2	8/2010	Liu	
7,852,658	B2*	12/2010	Liu	H01L 45/06 365/148
8,809,108	B2	8/2014	Liu et al.	
9,281,478	B2	3/2016	Liu et al.	
10,008,664	B2	6/2018	Liu et al.	
2004/0109351	A1	6/2004	Morimoto et al.	
2006/0115909	A1	6/2006	Happ	
2006/0157683	A1	7/2006	Scheuerlein	
2006/0226409	A1	10/2006	Burr et al.	
2006/0261321	A1*	11/2006	Happ	G11C 13/0004 257/1
2006/0286743	A1	12/2006	Lung et al.	
2007/0096248	A1	5/2007	Philipp et al.	
2007/0097739	A1*	5/2007	Happ	H01L 45/06 365/163
2007/0155117	A1	7/2007	Wicker	
2007/0155172	A1	7/2007	Lai et al.	
2007/0158632	A1	7/2007	Ho	
2007/0187663	A1	8/2007	Karpov	
2007/0215852	A1	9/2007	Lung	
2007/0215987	A1	9/2007	Schwerin	
2007/0221905	A1	9/2007	Liu	
2007/0235709	A1	10/2007	Kostylev et al.	
2007/0236988	A1	10/2007	Chen	
2007/0236989	A1	10/2007	Lung	
2007/0238031	A1	10/2007	Lee et al.	
2007/0241371	A1	10/2007	Lai et al.	
2007/0241385	A1	10/2007	Chang	
2007/0243659	A1	10/2007	Shin et al.	
2008/0006811	A1	1/2008	Philipp et al.	
2008/0019170	A1	1/2008	Happ et al.	
2008/0019257	A1	1/2008	Philipp et al.	
2008/0043520	A1*	2/2008	Chen	G11C 11/5678 365/163
2008/0121862	A1	5/2008	Liu	
2009/0231911	A1	9/2009	Liu et al.	
2011/0065235	A1	3/2011	Liu et al.	
2014/0346425	A1	11/2014	Liu et al.	
2016/0190438	A1	6/2016	Liu et al.	
2018/0138399	A1	5/2018	Liu et al.	

FOREIGN PATENT DOCUMENTS

CN	101026223	A	8/2007
CN	101110467	A	1/2008
EP	1845567		10/2007
JP	02674028		11/1997
JP	2007149900		6/2007
KR	20070080604	A	8/2007
KR	20080005886	A	1/2008
SG	164769		2/2013
TW	200807411	A	2/2008
TW	1463642	B	12/2014
WO	WO-2007072308		6/2007
WO	WO-2007099595		9/2007
WO	WO-09114177	A2	9/2009
WO	WO-09114177	A3	12/2009

OTHER PUBLICATIONS

“Chinese Application Serial No. 200980117105.2 Response filed May 19, 2015 to Office Action dated May 18, 2015”, w/English Translation, 9 pgs.

“Chinese Application Serial No. 200980117105.2, Office Action dated Jan. 16, 2013”, W/ English Translation, 5 pgs.

“Chinese Application Serial No. 200980117105.2, Office Action dated Jan. 17, 2014”, W/ English Translation, 20 pgs.

“Chinese Application Serial No. 200980117105.2, Office Action dated Feb. 3, 2015”, W/ English Translation, 16 pgs.

“Chinese Application Serial No. 200980117105.2, Office Action dated Feb. 22, 2012”, W/ English Translation, 10 pgs.

“Chinese Application Serial No. 200980117105.2, Office Action dated Jul. 14, 2014”, W/ English Translation, 18 pgs.

“Chinese Application Serial No. 200980117105.2, Office Action dated Jul. 16, 2013”, W/ English Translation, 15 pgs.

“Chinese Application Serial No. 200980117105.2, Response filed Mar. 26, 2013 to Office Action dated Jan. 16, 2013”, W/ English Claims, 77 pgs.

“Chinese Application Serial No. 200980117105.2, Response filed Mar. 28, 2014 to Office Action dated Jan. 17, 2014”, W/ English Claims, 14 pgs.

“Chinese Application Serial No. 200980117105.2, Response filed Sep. 25, 2013 to Office Action dated Jul. 16, 2013”, W/ English Claims, 14 pgs.

“Chinese Application Serial No. 200930117105.2, Response filed Dec. 1, 2014 to Office Action dated Jul. 14, 2014”, W/ English Claims, 17 pgs.

“Chinese Application Serial No. 200980117105.2, Response filed Sep. 5, 2012 to Office Action dated Feb. 22, 2012”, W/ English Claims, 12 pgs.

“International Application Serial No. PCT/US2009/001599, International Preliminary Report on Patentability dated Sep. 14, 2010”, 6 pgs.

“International Application Serial No. PCT/US2009/001599, International Search Report dated Sep. 29, 2009”, 3 pgs.

“International Application Serial No. PCT/US2009/001599, Written Opinion dated Sep. 29, 2009”, 4 pgs.

“Korean Application Serial No. 10-2010-7022867 Response filed Mar. 19, 2015 to Office Action dated Dec. 31, 2014”, W/ English Claims, 21 pgs.

“Korean Application Serial No. 10-2010-7022867, Non Final Office Action dated Dec. 31, 2014”, W/ English Translation, 10 pgs.

“Taiwanese Application Serial No. 098108309, Office Action dated Feb. 21, 2014”, W/ English Translation, 15 pgs.

“Taiwanese Application Serial No. 098108309, Response filed Aug. 20, 2014 to Office Action dated Feb. 21, 2014”, W/ English Claims, 49 pgs.

Atwood, Greg, et al., “Current Status of Chalcogenide Phase Change Memory”, Device Research Conference Digest (Intel Corporation), vol. 1, (2005), 29-33.

Breitwisch, M., et al., “Novel Lithography-Independent Pore Phase Change Memory”, 2007 Symposium on LLSI Technology Digest of Technical Papers, (Jun. 12-14, 2007), 100-101.

(56)

**References Cited**

OTHER PUBLICATIONS

Burcin, Laura, et al., "A 4-Mbit Non-Volatile Chalcogenide Random Access Memory", Aerospace, 2005 IEEE Conference (version 2), updated Dec. 9, 2004, (Mar. 5-12, 2005), 1-8.

Happ, T D, et al., "Novel One-Mask Self-Heating Pillar Phase Change Memory", Symposium on VLSI Technology, 2006. Digest of Technical Papers, (2006), 120-121.

Muller, Gerhard, et al., "Emerging Non-Volatile Memory Technologies", Infineon Technol, Solid-State Circuits Conference, (Sep. 16-13, 2003), 37-44.

\* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5

FIG. 6

FIG. 7

FIG. 8




FIG. 9




FIG. 11

FIG. 10






FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18

FIG. 19

FIG. 20

FIG. 21




FIG. 22




FIG. 23




FIG. 24




FIG. 25




FIG. 26




FIG. 27




FIG. 28




FIG. 29




FIG. 30




FIG. 31






FIG. 32




FIG. 33

3400 ↘




FIG. 34




FIG. 35




FIG. 36




FIG. 37

3800 ↘




FIG. 38




FIG. 39




FIG. 40




FIG. 41

4200 ↘




FIG. 42




FIG. 43

4400 ↘




FIG. 44




FIG. 45




FIG. 46




FIG. 47




FIG. 48




FIG. 49






FIG. 50






FIG. 51






FIG. 54




FIG. 55




FIG. 56

## PHASE CHANGE MEMORY CELL WITH CONSTRICTION STRUCTURE

### PRIORITY APPLICATION

This application is a divisional of U.S. application Ser. No. 15/063,238, filed Mar. 7, 2016, which is a continuation of U.S. application Ser. No. 14/458,804, filed Aug. 13, 2014, now issued as U.S. Pat. No. 9,281,478, which is a divisional of U.S. application Ser. No. 12/950,827, filed Nov. 19, 2010, now issued as U.S. Pat. No. 8,809,108, which is a divisional of U.S. application Ser. No. 12/049,056, filed Mar. 14, 2008, now issued as U.S. Pat. No. 7,852,658, all of which are incorporated herein by reference in their entirety.

### BACKGROUND

Computers and other electronic products, e.g., digital televisions, digital cameras, and cellular phones, often have a memory device to store data and other information. Some conventional memory devices may store information based on the amount of charges on a storage node of a memory cell. The storage node usually includes semiconductor material such as silicon. Different values of the charge on the storage node may represent different values (e.g., binary values “0” and “1”) of a bit of information stored in the memory cell.

Other conventional memory device (e.g., phase change memory devices) may store information based on a resistance state of a memory element of the memory cell. The memory element may have a material that can change between different phases (e.g., crystalline and amorphous phases) when programmed. Different phases of the material may cause the memory cell to have different resistance states with different resistance values. The different resistance states of the memory element may represent different values of the information stored in the memory.

Some conventional phase change memory devices may apply an electrical current during programming of the memory cell to cause the memory element to heat to some temperature to change the phase of the material of the memory element. The heat from the memory element may transfer to other features such as electrodes that are coupled to the memory element. In some cases, the heat transfer to the electrodes may affect the programming operation and performance of the device.

### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 shows a block diagram of a memory device having a memory array with phase change memory cells according to an embodiment of the invention.

FIG. 2 through FIG. 4 show schematic diagrams of examples of different memory cells having different access components and memory elements according to various embodiments of the invention.

FIG. 5 shows a partial cross-section of a memory cell having a memory element with a constriction structure according to various embodiments of the invention.

FIG. 6 through FIG. 8 show the memory element of FIG. 5 with various possible resistance states corresponding various resistance values.

FIG. 9 shows a three-dimensional (3D) view of the memory element and electrodes of FIG. 5.

FIG. 10 is a graph of temperature versus time for the material at a programmable portion of the memory element

of FIG. 5 during an example programming operation to reset the memory element according to various embodiments of the invention.

FIG. 11 is a graph of temperature versus time during an example programming operation to set the memory element 5 555 of one of FIG. 6 through FIG. 8.

FIG. 12 through FIG. 22 show a partial cross-section of memory cells with memory elements having constriction structures according to various embodiments of the invention. 10

FIG. 23 through FIG. 56 show various processes of forming memory cells with memory elements having constriction structures according to various embodiments of the invention. 15

### DETAILED DESCRIPTION

FIG. 1 shows a block diagram of a memory device 101 having a memory array 102 with phase change memory cells 100 according to an embodiment of the invention. Memory cells 100 may be arranged in rows and columns along with lines 104 (e.g., wordlines having signals WL0 through WLn) and lines 106 (e.g., bit lines having signals BL0 through BLn). Memory device 101 may use lines 104 and lines 106 to transfer information to and from memory cells 100. Row decoder 107 and column decoder 108 may decode address signals AO through AX on lines 109 (e.g., address lines) to determine which memory cells 100 are to be accessed. A sense amplifier circuit 110 may operate to determine the value of information read from memory cells 100 and provide the information in the form of signals to lines 106. Sense amplifier circuit 110 may also use the signals on lines 106 to determine the value of information to be written to memory cells 100. Memory device 101 may include circuitry 112 to transfer information between memory array 102 and lines (e.g., data lines) 105. Signals DQ0 through DQn on lines 105 may represent information read from or written into memory cells 100. Lines 105 may include nodes within memory device 101 or pins (or solder balls) on a package where memory device 101 may reside. Other devices external to memory device 101 (e.g., a memory controller or a processor) may communicate with memory device 101 through lines 105, 109, and 120.

Memory device 101 may perform memory operations such as a read operation to read information from memory cells 100 and a programming operation (sometimes referred to as write operation) to program (e.g., write) information into memory cells 100. A memory control unit 118 may control the memory operations based on control signals on lines 120. Examples of the control signals on lines 120 may include one or more clock signals and other signals to indicate which operation, e.g., a programming or read operation, that memory device 101 may perform. Other devices external to memory device 101 (e.g., a memory controller or a processor) may control the values of the control signals on lines 120. Specific values of a combination of the signals on lines may produce a command (e.g., programming or read command) that may cause memory device 101 to perform a corresponding memory operation (e.g., programming or read operation). 60

Each of memory cells 100 may be programmed to store information representing a value of a single bit (binary bit) or a value of multiple bits such as two, three, four, or other number of bits. For example, each of memory cells 100 may be programmed to store information representing a binary value “0” or “1” of a single bit. In another example, each of memory cells 100 may be programmed to store information 65

representing a value of multiple bits, such as one of four possible values “00”, “01”, “10”, and “11” of two bits.

Memory device **101** may receive a supply voltage, including supply voltage signals  $V_{cc}$  and  $V_{ss}$ , on lines **130** and **132**, respectively. Supply voltage signal  $V_{ss}$  may operate at a ground potential (e.g., having a value of approximately zero volts). Supply voltage signal  $V_{cc}$  may include an external voltage supplied to memory device **101** from an external power source such as a battery or an alternating current to direct current (AC-DC) converter circuitry.

Circuitry **112** of memory device **101** may include a select circuit **115** and an I/O (input/output) circuit **116**. Select circuit **115** may respond to signals SEL1 through SELn to select the signals on lines **106** and **113** that may represent the information read from or programmed into memory cells **100**. Column decoder **108** may selectively activate the SEL1 through SELn signals based on the AO through AX address signals on lines **109**. Select circuit **115** may select the signals on lines **106** and **113** to provide communication between memory array **102** and I/O circuit **116** during read and programming operations.

One skilled in the art may recognize that memory device **101** may include other components, which are not shown to help focus on the embodiments described herein.

Memory device **101** may include a phase change memory device such that each of memory cells **100** may include a material in which at least a portion of the material may be programmed by causing the portion to change between different phases (e.g., crystalline and amorphous phases) to change the resistance state of the memory cell. The value of the information stored in the memory cell may depend on which resistance state the memory cell has. Different resistance states may correspond to different values of information stored in each of memory cells **100**.

Each of memory cells **100** may include a memory cell with a memory element having a constriction structure such as those of memory cells described below with reference to FIG. 2 through FIG. 56.

FIG. 2 through FIG. 4 show schematic diagrams of examples of different memory cells **200**, **300**, and **400** having different access components **211**, **311**, and **411** and memory elements **222**, **333**, and **444** according to various embodiments of the invention. Each of memory cells **100** of FIG. 1 may include one of memory cells **200**, **300**, and **400** of FIG. 2 through FIG. 4. In FIG. 2 through FIG. 4, a line labeled WL and a line labeled BL may correspond to one of lines **104** and one of lines **106** of FIG. 1. In FIG. 4, labels WL and BL may be swapped. Access components **211**, **311**, and **411** of FIG. 2 through FIG. 4 may include metal-oxide-semiconductor field-effect transistor (MOSFET), bipolar junction transistor (BJT), and diode, respectively, to access memory elements **222**, **333**, and **444**. FIG. 2 through FIG. 4 show MOSFET, BJT, and diode as example access components. Other types of access components may be used.

As shown in FIG. 2 through FIG. 4, each of memory elements **222**, **333**, and **444** may couple between two electrodes, such as electrodes **251** and **252** (FIG. 2), electrodes **351** and **352** (FIG. 3), or electrodes **451** and **452** (FIG. 4). FIG. 2 through FIG. 4 schematically show electrodes **251**, **252**, **351**, **352**, **451**, and **452** as dots. Structurally, each of these electrodes may include a conductive material. In FIG. 2 through FIG. 4, access components **211**, **311**, and **411** may enable signals (e.g., voltage or current) to be transferred to and from memory elements **222**, **333**, and **444** via electrodes **251**, **252**, **351**, **352**, **451**, and **452** during programming and read operations.

For example, in a programming operation, signals on line WL may turn on access components **211**, **311**, and **411** to apply signals (e.g., signals from line BL in FIG. 2, FIG. 3, or FIG. 4) to memory cells **200**, **300**, and **400** to create a current flowing through memory elements **222**, **333**, and **444**. The current may cause at least a portion of the material of memory elements **222**, **333**, and **444** to heat up and then cool down, thereby changing the phase of the material, such as from a crystalline phase (or crystalline state) to an amorphous phase (or amorphous state) and vice versa. Different phases may cause memory elements **222**, **333**, and **444** to have different resistance states with different resistance values corresponding to different values of the information that is being stored in memory elements **222**, **333**, and **444** by the programming operation.

In a read operation, signals on line WL may turn on access components **211**, **311**, and **411** to apply signals (e.g., signals from line BL in FIG. 2, FIG. 3, or FIG. 4) to memory cells **200**, **300**, and **400** to create a current flowing through memory elements **222**, **333**, and **444** and then to line BL (FIG. 2 through FIG. 4). In each of memory cells **200**, **300**, and **400**, the signals on line BL may have different values, depending on the resistance value of the memory element of the memory cell. Based on the signals on line BL, other circuitry of the memory device (e.g., circuit such as I/O circuit **116** of FIG. 1) may determine the value of information stored in memory elements **222**, **333**, and **444**. For example, the other circuitry may use the signal on line BL and measure the resistance value of memory elements **222**, **333**, and **444** to determine the value of information.

The current used during a read operation may have a different value (e.g., amplitude or transition time value) from the current used during a programming operation. For example, in a programming operation, the value of the signal (e.g., signal from line BL in FIG. 2, FIG. 3, or FIG. 4) that creates a current flowing through the memory element may be sufficient to cause the material of at least a portion of the memory element to change between different phases to alter the resistance value of the memory element based on the value of the information to be stored in memory elements **222**, **333**, and **444**. In a read operation, the value of the signal (e.g., signal from line BL in FIG. 2, FIG. 3, or FIG. 4) that creates a current flowing through the memory element may be sufficient to create the current but insufficient to cause any portion of the memory element to change between different phases so that the value of the information stored in the memory element may remain unchanged in the read operation.

Each of memory cells **100**, **200**, **300**, and **400** of FIG. 1 through FIG. 4 may include a memory element with a constriction structure described below with reference to FIG. 5 through FIG. 56.

FIG. 5 shows a partial cross-section of a memory cell **500** having a memory element **555** with a constriction structure according to various embodiments of the invention. Memory cell **500** may correspond to memory cell **100**, **200**, **300**, or **400** (FIG. 1 through FIG. 4). As shown on FIG. 5 memory cell **500** may include memory element **555** and electrodes **551** and **552**. For clarity, FIG. 5 shows memory element **555** with cross-section lines (shading lines) and electrodes **551** and **552** without cross-section lines. Memory cell **500** may include insulation material surrounding memory element **555** and electrodes **551** and **552**. FIG. 5 omits the insulation material for clarity. Memory cell **500** may also include other components, such as an access component that may be similar to or identical to access component **211**, **311**, or **411**

(FIG. 2 through FIG. 4). However, FIG. 5 omits the other components to help focus on the embodiments discussed herein.

Each of electrodes **551** and **552** may include a conductive material and act as an electrode to transfer signals to and from memory element **555**. Electrodes **551** and **552** may correspond to electrodes **251** and **252** (FIG. 2), electrodes **351** and **352** (FIG. 3), or electrodes **451** and **452** (FIG. 4), which are schematically shown as dots in FIG. 2 through FIG. 4. Electrodes **551** and **552** may include material that may exhibit a relatively low resistivity (e.g., relative to memory element **555**) and withstand a relatively high temperature operation without interacting with the material of memory element **555**. Example material of electrodes **551** and **552** may include refractory metal nitride, carbides and borides such as TiN, ZrN, HfN, VN, NbN, TaN, TiC, ZrC, HfC, VC, NbC, TaC, TiB<sub>2</sub>, ZrB<sub>2</sub>, HfB<sub>2</sub>, VB<sub>2</sub>, NbB<sub>2</sub>, TaB<sub>2</sub>, Cr<sub>3</sub>C<sub>2</sub>, M<sub>2</sub>C, WC, CrB<sub>2</sub>, Mo<sub>2</sub>B<sub>5</sub>, W<sub>2</sub>B<sub>5</sub>, compounds such as TiAlN, TiSiN, TiW, TaSiN, TiCN, SiC, B<sub>4</sub>C, WSix, MoSi<sub>2</sub>, metal alloys such as NiCr, and elemental materials such as doped silicon, carbon, platinum, niobium, tungsten, molybdenum. In some cases, electrode **551**, **552**, or both may include multiple layers of different materials with different resistivity. In these cases, the layer with a higher resistivity may directly contact memory element **555** to promote localized heating for memory element **555** (e.g., during programming operations).

In FIG. 5, memory element **555** may include a portion **501** directly contacting electrode **551**, a portion **502** directly contacting electrode **552**, and a portion **503** between portions **501** and **502**. FIG. 5 shows portion **503** being located at a general area indicated by a broken circle to indicate that portion **503** may include a part of portion **501**, a part of portion **502**, or both. As shown in FIG. 5, portion **503** may indirectly contact electrodes **551** and **552** such that it may be isolated from electrode **551** by portion **501** and isolated from electrode **552** by portion **502**. Memory element **555** may be programmed to one of multiple possible resistance states to store information representing a value of a single bit or multiple bits. The value of the information may be based on which resistance state memory element **555** may have (e.g., the resistance state that has been programmed into memory element **555**). Different resistance states of memory element **555** may represent different values of information.

Portion **503** of memory element **555** may be referred to as a programmable portion (or programmable volume), as explained in more details with reference to FIG. 6 through FIG. 11 below, because the resistance state at which memory element **555** is programmed may depend mainly on the characteristics, such as the phase of the material of portion **503**. Memory element **555** may include the same material or different materials for portions **501**, **502**, and **503**. The material may be configured to change between multiple phases, e.g., between crystalline and amorphous phases. Memory element **555** may include a phase change material or multiple phase change materials. Some phase change materials may include chalcogenide materials with various combinations of germanium, antimony, tellurium, and other similar materials. Examples of phase change materials may include binary combinations such as germanium telluride (GeTe), indium selenide (InSe), antimony telluride (SbTe), gallium antimonide (GaSb), indium antimonide (InSb), arsenic telluride (AsTe), aluminum telluride (AlTe); ternary combinations such as germanium antimony telluride (GeSbTe, e.g., Ge<sub>2</sub>Sb<sub>5</sub>Te<sub>5</sub>), tellurium germanium arsenide (TeGeAs), indium antimony telluride (InSbTe), tellurium tin selenide (TeSnSe), germanium selenium gallide (GeSeGa),

bismuth selenium antimonide (BiSeSb), gallium selenium telluride (GaSeTe), tin antimony telluride (SnSbTe), indium antimony germanide (InSbGe); and quaternary combinations such as tellurium germanium antimony sulfide (TeGeSbS), tellurium germanium tin oxide (TeGeSnO), and alloys of tellurium germanium tin gold (TeGeSnAu), palladium tellurium germanium tin (PdTeGeSn), indium selenium titanium cobalt (InSeTiCo), germanium antimony tellurium palladium (GeSbTePd), germanium antimony tellurium cobalt (GeSbTeCo), antimony tellurium bismuth selenium (SbTeBiSe), silver indium antimony tellurium (AgInSbTe), germanium antimony selenium tellurium (GeSbSeTe), germanium tin antimony tellurium (GeSnSbTe), germanium tellurium tin nickel (GeTeSnNi), germanium tellurium tin palladium (GeTeSnPd), and germanium tellurium tin platinum (GeTeSnPt), among others. Some material compositions in this description list only the component elements. The relative amount of each component element in each of these material compositions is not limited to a particular value.

FIG. 5 shows an example where memory element **555** may have a resistance state **533** where the material at portions **501**, **502**, and **503** (material of memory element **555**) has the same crystalline phase **513**. Resistance state **533** may correspond to a resistance value of memory element **555**. With resistance state **533** of FIG. 5, memory element **555** may store information to represent a specific value of single or multiple bits. Memory element **555** may be programmed to have a resistance state different from resistance state **533** of FIG. 5 to store information representing one or more other values of a single or multiple bits.

FIG. 6 through FIG. 8 show memory element **555** of FIG. 5 with various other possible resistance states **633**, **733**, and **833** corresponding to various resistance values. A programming operation may cause memory element **555** of FIG. 5 to have one of resistance states **533**, **633**, **733**, and **833**. FIG. 5 through FIG. 8 show four examples where memory element **555** may have four resistance states **533**, **633**, **733**, and **833**, corresponding to information representing four possible combinations of two bits (e.g., “00”, “01”, “10”, or “11”). Memory element **555**, however, may be configured to be programmed to have a different number (e.g., eight, sixteen, or other number) of resistance states corresponding to information representing a value of more than two bits (three, four, or other number).

As shown in FIG. 5 through FIG. 8, memory element **555** may have a constriction structure such that the dimension at portion **503** (e.g., a cross-section of portion **503**, as shown in details in FIG. 9) may be narrower than that of each of portions **501** and **502**. Because of the constriction structure of memory element **555**, the material at portions **501**, **502**, and **503** may behave differently when memory element **555** is programmed. For example, during a programming operation, the material at portions **501** and **502** may remain at the same crystalline phase **513** (FIG. 5 through FIG. 8) while the material at portion **503** may change from a crystalline phase **513** (FIG. 5) to an amorphous phase (FIG. 6 through FIG. 8).

In FIG. 6 through FIG. 8, each of amorphous regions **613**, **713**, and **813** may represent a region that the material at portion **503** may change from crystalline phase **513** to an amorphous phase during a programming operation. Thus, each of amorphous regions **613**, **713**, and **813** of portion **503** may also be referred to as a region of portion **503** that has “amorphized” (changed from a crystalline phase to an amorphous phase) during a programming operation.

Amorphous regions **613**, **713**, and **813** may have different sizes, e.g., different volumes with different thicknesses **614**,

714, and 814. As mentioned above, the resistance state at which memory element 555 is programmed may depend mainly on the characteristics of portion 503. In FIG. 6 through FIG. 8, the characteristics of portion 503 may include the size of amorphous region 613, 713, or 813 (region that has amorphized) during a programming operation. Thus, the resistance state (e.g., resistance states 633, 733, or 833) at which memory element 555 is programmed may depend on the size of the amorphous region 613, 713, or 813.

During a programming operation, based on a value of information to be stored in memory element 555, the value (e.g., amplitude, pulse width, rise time, fall time, or a combination of these parameters) of a signal that is used to program memory element 555 may be appropriately controlled to control the size of the material at portion 503 that may amorphize (e.g., the size of amorphous region 613, 713, or 813) so that memory element 555 may have an appropriate resistance state to store information with the intended value. As shown in FIG. 6 through FIG. 8, amorphous region 613 may have a smaller size than that of each of amorphous region 713 or 813. Different values of the signal used to program memory element 555 may cause portion 503 to have different sizes. For example, during programming, a first amount of current may be used to obtain amorphized region 613 (FIG. 6) so that memory element 555 may have resistance state 633 (FIG. 6) to store information with a first value. A second amount of current greater than the first amount of current may be used to obtain resistance state 733 (FIG. 7) so that memory element 555 may have resistance state 733 to store information with a second value. A third amount of current greater than the second amount of current may be used to obtain resistance state 833 (FIG. 8) so that memory element 555 may have resistance state 833 to store information with a third value. The constriction structure of memory element 555 may allow easier control of the value of the signal used during a programming operation to obtain various thicknesses (e.g., thickness 614, 714, and 814) for the various amorphized regions (e.g., amorphized region 613, 713, or 813) corresponding to various resistance states of memory element 555. Thus, relatively precise resistance states of memory element 555 may be achieved, thereby the reliability values of information (e.g., values of multiple bits) corresponding to the resistance states may be improved. Further, as shown in FIG. 6 through FIG. 8, since portion 503 is located between portions 501 and 502, the amorphized region 613, 713, or 813 of portion 503 may fully block a current path that may flow between portions 501 and 502. Therefore, an occurrence of a current leakage path between portions 501 and 502 may be reduced, thereby device reliability during programming or reading (or both) of memory element 555 may be improved.

FIG. 9 shows a 3-D view of memory element 555 and electrodes 551 and 552 of memory cell 500 of FIG. 5. As shown in FIG. 9, memory element 555 has a constriction structure such that portion 501 may have a cone-like shape with a larger part (or base) having a cross-section area (areas with shading lines) 901 and tapered part (or tip) 913 having a cross-section area 903. Cross-section area 901 may include an area of portion 901 that directly contacts electrode 551. Portion 502 may have a cross-section area 902, which may include an area of portion 902 that directly contacts electrode 552. Portion 503 may include at least a part of the tapered part 913. As shown in FIG. 9, cross-section area 903 may be smaller than each of cross-section areas 901 and 902.

During a programming operation, a signal used to program memory element 555 may cause a current  $I_A$  (sym-

bolically shown in FIG. 9 as an arrow labeled " $I_A$ ") to flow between electrodes 551 and 552 (e.g., from electrode 551 to electrode 552) through memory element 555. Since cross-section area 903 may be smaller than each of cross-section areas 901 and 902, the current density at cross-section area 903 may be higher than the current density at each of cross-section areas 901 and 902. Different current densities may cause the material at portions 501, 502, and 503 to behave differently during the programming operation, resulting in memory element 555 having an amorphous region 913 with a thickness 914. Thickness 914 in FIG. 9 may represent one of thicknesses 614, 714, and 814 of FIG. 6 through FIG. 8. A cross-section of amorphous region 913 (taken in a direction perpendicular to both electrodes 551 and 552 or parallel to the direction of current  $I_A$ ) is shown in FIG. 6 through FIG. 8 as one of amorphous regions 613, 713, and 813 of FIG. 6 through FIG. 8. The behavior of the material at portions 501, 502 and 503 of FIG. 5 and FIG. 9 during a programming operation is described below with reference to FIG. 10 and FIG. 11.

FIG. 10 is a graph of temperature versus time for the material at portion 503 during an example programming operation to reset memory element 555 of FIG. 5 according to various embodiments of the invention. The following description refers to FIG. 5 through FIG. 10. In FIG. 10, an arrow 1001 symbolically shows the material at portion 503 changing from a crystalline phase to an amorphous phase. As shown in FIG. 9, since portion 503 may have a smaller cross-section area (e.g., cross-section area 903) than that of each of portions 501 and 502, the material at portion 503 may change from a crystalline phase to an amorphous phase while the material at portions 501 and 502 may remain at the same crystalline phase. Thus, the graph of FIG. 10 concentrates on the temperature versus time for the material at portion 503.

At time T0, portions 501, 502, and 503 of memory element 555 may have the same crystalline phase (e.g., crystalline phase 513 of FIG. 5) such that memory element 555 may have a resistance state such as resistance state 533 (FIG. 5).

From time T0 to time T3 in FIG. 10, a signal (e.g., signal similar to or identical to the signal from line BL of FIG. 2, FIG. 3, or FIG. 4) may be applied to memory element 555 to program it. A current (e.g., current  $I_A$  of FIG. 9) may flow through memory element 555 and cause the material at portion 503 to self-heat. Between times T0 and T1, the value of the signal may be controlled such that the temperature of the material at portion 503 may rise, exceed its crystallization (or glass transition) temperature  $T_c$ , and then reach or exceed its melting point temperature  $T_m$ . At time T1, the material at portion 503 may melt and become liquid.

Between times T1 and T3, the value of the signal may be controlled (e.g., decreased or deactivated) to allow the material at portion 503 to cool, e.g., allowed to rapidly cool between times T1 and T2. Then, the material at portion 503 may enter the amorphous phase (e.g., between time T2 and T3), resulting in memory element 555 having an amorphous region such as one of amorphous regions 613, 713, and 813 (FIG. 6 through FIG. 8).

As shown in FIG. 9, each of portions 501 and 502 may have a cross-section area (e.g., cross-section area 901 or 902) that is greater than that of portion 503. Therefore, the current density at each of portions 501 and 502 may be less than that of portion 503. Thus, during a programming operation between time T0 and T3 of FIG. 10, while the material at portion 503 may heat, melt, cool, and become "amorphized", the material at portions 501 and 502 may also

heat but may remain at the crystalline phase because the current density at portions **501** and **502** may be insufficient to cause the material at portions **501** and **502** to reach the melting point temperature  $T_m$ . As a result, during a programming operation, the material at portions **501** and **502** may remain at a crystalline phase (e.g., crystalline phase **513** of FIG. 5 through FIG. 8).

As shown in FIG. 9, portion **503** may indirectly contact electrodes **551** and **552** (or isolated from electrodes **551** and **552** by portions **501** and **502**), the heat sink effect of electrodes **551** and **552** on portion **503** may be relatively low because portions **501** and **502** may prevent or reduce the heat from portion **503** from being transferred (or “sink”) to electrodes **551** and **552**. Thus, the majority of heat that portion **503** generates between times  $T_0$  and  $T_1$  in FIG. 10 may stay mainly at portion **503** and allow it to quickly reach the melting point temperature. Therefore, programming time may be reduced, a relatively lower amount of current may be used, and power may be saved. Moreover, since portion **503** indirectly contacts electrodes **551** and **552**, these electrodes may stay at a relatively lower temperature in comparison with the case where electrode **551** or **552**, or both, directly contacts portion **503**, thereby device reliability may be improved. Further, the smaller cross-section **903** (FIG. 9) of portion **503** relative to cross-section areas **901** and **902** of portions **501** and **502** may also lower current and power used during a programming operation.

The activities performed from time  $T_0$  to time  $T_3$  in FIG. 10 may be referred to as reset activities to “reset” memory element **555** (e.g., to change a material of at least a portion of memory element **555** from a crystalline phase to an amorphous phase). After the reset activities (e.g., after time  $T_3$ ), memory element **555** may have a resistance state (e.g., one of resistance states **633**, **733**, and **833** of FIG. 6 through FIG. 8) that is different from its resistance state before time  $T_0$  (resistance state **533** of FIG. 5). Thus, the information stored in memory element **555** after time  $T_3$  may have a value that is different from the value it has before time  $T_0$ .

The reset activities described above with reference to FIG. 10 may be reversed by other activities (e.g., “set” activities) such that the resistance state with an amorphous region (e.g., resistance states **633**, **733**, or **833** of FIG. 6 through FIG. 8) of memory element **555** may be changed back to a resistance state without an amorphous region (e.g., resistance state **533** of FIG. 5).

FIG. 11 is a graph of temperature versus time during an example programming operation to set memory element **555** of one of FIG. 6 through FIG. 8. The following description refers to FIG. 5 through FIG. 11. In FIG. 11, an arrow **1101** symbolically shows the material at portion **503** changing from an amorphous phase a crystalline phase.

At time  $T_4$ , the material at each of portions **501** and **502** of memory element **555** (FIG. 6 through FIG. 8) may have a crystalline phase and the material at portion **503** may have an amorphous phase such that memory element **555** may have a resistance state such as one of resistance states **633**, **733**, and **833** (FIG. 6 through FIG. 8).

In FIG. 11, from time  $T_4$  to time  $T_7$ , a signal (e.g., signal similar to or identical to the signal from line BL of FIG. 2, FIG. 3, or FIG. 4) may be applied to memory element **555** to program it. A current (e.g., current  $I_A$  of FIG. 9) may flow through memory element **555** and cause the material at portions **501**, **502**, and **503** to heat. Between times  $T_4$  and  $T_5$ , the value of the signal may be controlled such that the temperature of the material at portion **503** may rise, exceed its crystallization temperature  $T_c$ , but stay below the melting point temperature  $T_m$ . For example, the signal may be

controlled such that its amplitude between times  $T_4$  and  $T_6$  in FIG. 11 may be less than that of the signal used between times  $T_0$  and  $T_1$  in FIG. 10.

Between times  $T_5$  and  $T_6$  in FIG. 11, the value of the signal may be controlled such that the temperature of the material at portions **501**, **502**, and **503** may be kept constant (or substantially constant). Under this heating condition, the material of portion **503** (having an amorphous phase at time  $T_4$ ) may “re-crystalline”, i.e., leave the amorphous phase and enter the crystalline phase. Thus, between time  $T_5$  and  $T_6$  (or from time  $T_6$  and after), an amorphous region of portion **503**, such as one of the amorphous regions **613**, **713**, and **813** of FIG. 6 through FIG. 8, may re-crystallize, resulting in memory element **555** with portions **501**, **502**, and **503** having the same crystalline phase such as crystalline phase **513** of FIG. 5.

The activities performed from time  $T_4$  to time  $T_7$  in FIG. 11 may be referred to as set activities to “set” memory element **555** (e.g., to change a material of memory element **555** to the same phase such as a crystalline phase). After the set activities (e.g., after time  $T_7$ ), memory element **555** may have a resistance state (resistance state **533** of FIG. 5) that is different from its resistance state before time  $T_4$  (e.g., one of resistance states **633**, **733**, and **833** of FIG. 6 through FIG. 8). Thus, the information stored in memory element **555** after time  $T_6$  may have a value that is different from the value it has before time  $T_4$ .

The terms “reset” and “set” in this description are used only for convenience to help distinguishing the activities during a programming operation such as a programming operation described above with reference to FIG. 10 and FIG. 11. The terms “reset” and “set” may be exchanged such that activities associated with the description of FIG. 10 may be referred to as “set” (instead of “reset”) and the activities associated with the description of FIG. 11 may be referred to as “reset” (instead of “set”).

The description above with reference to FIG. 5 through FIG. 11 refers to memory cell, such as memory cell **500**, including its structure, material, and operations. FIG. 12 through FIG. 22 show various other memory cells.

FIG. 12 and FIG. 13 show a partial cross-section of a memory cell **1200** with a memory element **1222** having a constriction structure and an intermediate material **1220** between portions of memory element **1222** according to various embodiments of the invention. Memory cell **1200** may include structure, material, and operations (e.g., programming operations) similar to or identical to that of memory cell **500** (FIG. 5 through FIG. 11) except for intermediate material **1220** of FIG. 12. As shown in FIG. 12, memory element **1222** may include a portion **1201** directly contacting electrode **1251**, a portion **1202** directly contacting electrode **1252**, and a portion **1203** (e.g., programmable portion) indirectly contacting electrodes **1251** and **1252** such that portion **1203** may be isolated from electrode **1251** by portion **1201** and isolated from electrode **1252** by intermediate material **1220** and portion **1202**. When memory element **1222** is programmed, the material at portion **1203** may amorphize to provide amorphous region **1313** (FIG. 13) with a thickness **1314** while the material at portions **1201** and **1202** may remain at a crystalline phase.

Intermediate material **1220** may include an electrically conductive material and may have a resistance value lower than that of portions **1201**, **1202**, and **1203**. Intermediate material **1220** may include material similar to or identical to those of electrodes **551** and **552** of FIG. 5, or other conductive material. The lower resistance of intermediate material **1220** may reduce the current density at portion **1202** during



## 11

a programming operation to prevent amorphous region **1313** (FIG. **13**) from extending into portion **1202**. Thus, improved control of the size of the amorphous region **1313** may be achieved and configuring memory element **1333** for multiple bits per memory cell based on the size of the amorphous region **1313** may be obtained.

FIG. **14** and FIG. **15** show a partial cross-section of a memory cell **1400** with a memory element **1444** having a constriction structure and an intermediate material **1420** between portions of element **1444** according to various embodiments of the invention. Memory cell **1400** may include structure, material, and operations (e.g., programming operations) similar to or identical to that of memory cell **1200** of FIG. **12** and FIG. **13** except for intermediate material **1420** of FIG. **14**. As shown in FIG. **14**, memory element **1444** may include a portion **1401** directly contacting electrode **1451**, a portion **1402** directly contacting electrode **1452**, and a portion (e.g., programmable portion) **1403** indirectly contacting electrodes **1451** and **1452** such that portion **1403** may be isolated from electrode **1451** by portion **1401** and isolated from electrode **1452** by intermediate material **1420** and portion **1402**. When memory element **1444** is programmed, the material at portion **1403** may amorphize to provide amorphous region **1513** (FIG. **15**) with a thickness **1514** while the material at portions **1401** and **1402** may remain at a crystalline phase.

Intermediate material **1420** may include a part of a mask that has been used during the formation of portion **1401** in which the part of the mask may remain in memory element **1444** as intermediate material **1420** as shown in FIG. **14**. Intermediate material **1420** may include material similar to or identical to those of electrodes **551** and **552** of FIG. **5**, or other conductive material. In FIG. **14**, since intermediate material **1420** may be a part of the mask, an additional process step (e.g., step to remove the mask) may be skipped, thereby the process of forming memory element **1444** may be simplified.

FIG. **16** and FIG. **17** show a partial cross-section of a memory cell **1600** with a memory element **1666** having a constriction structure and an intermediate material **1620** between portions of element **1666** according to various embodiments of the invention. Memory cell **1600** may include structure, material, and operations (e.g., programming operations) similar to or identical to that of memory cells **1400** of FIG. **14** and FIG. **15** except for intermediate material **1620** of FIG. **16**. Memory element **1666** may include a portion **1601** directly contacting electrode **1651**, a portion **1602** directly contacting electrode **1652**, and a portion (e.g., programmable portion) **1603** indirectly contacting electrodes **1651** and **1652** such that portion **1603** may be isolated from first electrode **1651** by portion **1601** and isolated from electrode **1652** by intermediate material **1620** and portion **1602**. Intermediate material **1620** may include sub-materials **1621** and **1622**. When memory element **1666** is programmed, the material at portion **1603** may amorphize to provide amorphous region **1713** (FIG. **17**) with a thickness **1714** while the material at portions **1601** and **1602** may remain at a crystalline phase.

Sub-materials **1621** and **1622** may include an electrically conductive material and may have a resistance value lower than that of portions **1601**, **1602**, and **1603**. Both sub-materials **1621** and **1622** may include the same material, in which the material may be material similar to or identical to those of electrodes **551** and **552** of FIG. **5**, or other conductive material. Sub-materials **1621** and **1622** may include materials different from each other. The inclusion of sub-materials **1621** and **1622** may provide memory element **1666**

## 12

with benefits similar to or identical to both of memory element **1222** of FIG. **12** and memory element **1444** of FIG. **14**.

FIG. **18** through FIG. **21** show a partial cross-section of a memory cell **1800** with a memory element **1888** having a constriction structure according to various embodiments of the invention. Memory cell **1800** may also include electrodes **1851** and **1852** to transfer signals to and from memory element **1888**. Electrodes **1851** and **1852** and memory element **1888** may include material similar to or identical to those of electrodes **551** and **552**, and memory element **555** of FIG. **5**. Memory cell **1800** may include insulation material surrounding memory element **1888** and electrodes **1851** and **1852**. As shown in FIG. **18**, memory element **1888** may include a portion **1801** directly contacting electrode **1851**, a portion **1802** directly contacting electrode **1852**, and a portion **1803** between portions **1801** and **1802**. FIG. **18** shows portion **1803** being located at a general area indicated by a broken circle to indicate that portion **1803** may include a part of portion **1801**, a part of portion **1802**, or both. As shown in FIG. **18**, portion **1803** may indirectly contact electrodes **1851** and **1852** such that it may be isolated from electrode **1851** by portion **1801** and isolated from electrode **1852** by portion **1802**. Portion **1803** of FIG. **18** may be referred to as a programmable portion (or programmable volume) of memory element **1888**.

FIG. **18** shows an example where memory element **1888** may have a resistance state **1833** where the material at portions **1801**, **1802**, and **1803** (material of memory element **1888**) has the same crystalline phase **1813**. Memory element **1888** may be programmed to have other resistance states such as resistance states **1933**, **2033**, and **2133** (FIG. **19** through FIG. **21**). A programming operation similar to or identical to those described above with reference to FIG. **5** through FIG. **11** may cause memory element **1888** of FIG. **18** to have one of resistance states **1833**, **1933**, **2033**, and **2133** corresponding to information representing a value of two bits. Memory element **1888** may be configured to be programmed to have other number (e.g., eight, sixteen, or other number) of resistance states corresponding to information representing a value of more than two bits (three, four, or other number).

As shown in FIG. **18** through FIG. **21**, memory element **1888** may have a constriction structure such that the dimension at portion **1803** (e.g., a cross-section of portion **1803**, as shown in details in FIG. **22**) may be narrower than that of each of portions **1801** and **1802**. Because of the constriction structure of memory element **1888**, the material at portions **1801** and **1802** may behave differently when memory element **1888** is programmed. For example, during a programming operation, the material at portions **1801** and **1802** may remain at the same crystalline phase **1813** (FIG. **18** through FIG. **22**) while the material at portion **1803** may change from crystalline phase **1813** (FIG. **18**) to an amorphous phase to provide amorphous region **1913** with a thickness **1914** (FIG. **19**), amorphous region **2013** with a thickness **2014** (FIG. **20**), or amorphous region **2113** with a thickness **2114** (FIG. **21**).

FIG. **22** shows a 3-dimensional view of memory element **1888** and electrodes **1851** and **1852** of FIG. **18**. As shown in FIG. **22**, memory element **1888** has a constriction structure such that portion **1801** may have a tapered part **2261**, and portion **1802** may have a tapered part **2262**. Portion **1803** may include at least one of tapered parts **2261** and **2262**. Memory element **1888** may have unequal cross-section areas (areas with shading lines) **2201**, **2202**, and **2203**. Cross-section area **2201** may include an area of portion **1801**

that may directly contact electrode **1851**. Cross-section area **2202** may include an area of portion **1802** that may directly contact electrode **1852**. Cross-section area **2203** may include an area of portion **1803**. As shown in FIG. **22**, cross-section area **2203** may be smaller than each of cross-section areas **2201** and **2202**. During a programming operation, a signal used to program memory element **1888** may cause a current  $I_s$  (symbolically shown in FIG. **22** as an arrow labeled “ $I_B$ ”) to flow between electrodes **1851** and **1852** (e.g., from electrode **1851** to electrode **1852**) through memory element **1888**. Since cross-section area **2203** may be smaller than each of cross-section areas **2201** and **2202**, the current density at cross-section areas **2203** may be higher than the current density at each of cross-section areas **2201** and **2202**. Different current densities may cause the material at portions **1801**, **1802**, and **1803** to behave differently during the programming operation, resulting in memory element **1888** having an amorphous region **2213** with a thickness **2214**. Thickness **2214** of FIG. **22** may represent one of thicknesses **1914**, **2014**, and **2114** of FIG. **19** through FIG. **21**. A cross-section of amorphous region **2213** (taken in direction perpendicular to both electrodes **1851** and **1852**) is shown in FIG. **19** through FIG. **21** as one of amorphous regions **1913**, **2013**, and **2113** of FIG. **19** through FIG. **21**.

Memory cells **500**, **1200**, **1400**, **1600**, and **1800** of FIG. **5** through FIG. **22**, may be formed by processes similar to or identical those described below with reference to FIG. **23** through FIG. **56**.

FIG. **23** through FIG. **34** show various processes of forming a memory cell with a memory element having a constriction structure according to various embodiments of the invention. FIG. **34** shows memory cell **3400** after completion of various processes described with reference to FIG. **23** through FIG. **34**. FIG. **23** through FIG. **33** show parts of memory cell **3400** (FIG. **34**) while it is being formed. For clarity, FIG. **23** through FIG. **56** show some components (e.g., memory elements) with cross-section lines and some other components without cross-section lines. Further, to help focus on the embodiments described herein, FIG. **23** through FIG. **56** omit the formation of additional components, such as access components, that may be formed to access the memory cells (e.g., memory cells **3400**, **3800**, **4200**, **4400**, **4900**, **5100**, **5200**, **5300**, and **5600**) described herein. The access components for these memory cells may be similar to or identical to access components **211**, **311**, and **411**, which are schematically shown in FIG. **2** through FIG. **4**.

FIG. **23** shows a substrate **2310** and a conductive material **2351** formed on substrate **2310**. Substrate **2310** may include other circuit elements, which may form at least a part of one or more access components that may couple to conductive material **2351**. Forming conductive material **2351** may include depositing a conductive material on substrate **2310**. The material of conductive material **2351** may include conductive material similar to or identical to those of electrode **551** or **552** of FIG. **5**.

In FIG. **24**, an electrode **2451** and insulators **2411** and **2412** may be formed through technique known in the art. Forming electrode **2451** may include removing a part of conductive material **2351**. Forming electrode **2451** may include patterning conductive material **2351** (e.g., using a mask to pattern). Forming insulators **2411** and **2412** may include depositing an insulation material (e.g., dielectric material such as silicon oxide or other insulation material) over substrate **2310** and electrode **2451** and then planarizing, e.g., through chemical mechanical polishing (CMP), the insulation material to form insulators **2411** and **2412**. Insu-

lators **2411** and **2412**, and electrode **2451** may also be formed by an alternative technique. For example, the alternative technique may include depositing an insulation material over substrate **2310** and forming via in the insulation material, thereby forming insulators such as insulators **2411** and **2412**. Then, a conductive material may be deposited into the via followed by a process, e.g., CMP, to planarize the conductive material to form electrode **2451**.

In FIG. **25** a material **2501**, a mask **2511**, and a photoresist **2512** may be formed on and/or over electrode **2451** and insulators **2411** and **2412**. As used herein, the term “on” used with respect to two or more materials, one “on” the other, means at least some contact between the materials, while “over” means the materials are in close proximity, but possibly with one or more additional intervening materials such that contact is possible but not required. Neither “on” nor “over” implies any directionality as used herein unless stated as such. In FIG. **25**, material **2501** may include conductive material similar to or identical to those of portion **501** of memory cell **500** of FIG. **5**, such as the material (e.g., chalcogenide-based material) that may be configured to change between different phases. In FIG. **25**, forming mask **2511** may include depositing materials known in the art on material **2501**. Mask **2511** may include material such as silicon oxide, silicon nitride, amorphous carbon, or transparent carbon, or other material similar to or identical to that of electrodes **551** and **552** of FIG. **5**, such as titanium nitride. Mask **2511** and photoresist **2512** may be used to remove (e.g., etch) a part of material **2501** as described below with reference to FIG. **27**.

In FIG. **26**, a remaining part of mask **2511** and a remaining part of photoresist **2512** are formed after some part of mask **2511** and some part of photoresist **2512** of FIG. **25** are removed, e.g., by patterning mask **2511** and photoresist **2512** of FIG. **25**, using techniques such as photolithography and etch. In FIG. **26**, the remaining part of mask **2511** and the remaining part of photoresist **2512** may be used as a masking structure for removing some part of material **2501** by techniques such as etching, as represented by arrows **2610**.

In FIG. **27**, a portion **2701** is formed. Portion **2701** is a remaining portion of material **2501** of FIG. **26** after some part of material **2501** is removed. As shown in FIG. **27**, portion **2701** may have cone-like shape with a larger part **2711** (or base) and a tapered part **2713**.

In FIG. **28**, insulators **2811** and **2812** may be formed. Insulators **2811** and **2812** may be formed before or after the remaining part of mask **2511** and the remaining part of photoresist **2512** of FIG. **27** are removed. Forming insulators **2811** and **2812** may include depositing insulation material on and/or over other components shown in FIG. **27** (including the remaining part of mask **2511** and the remaining part of photoresist **2512** if the remaining parts have not been removed) and then planarizing (e.g., including CMP planarization) the insulation material to form insulators **2811** and **2812**.

In FIG. **29**, a material **2902**, a mask **2911**, and a photoresist **2912** may be formed. Forming material **2902** may include depositing a material on and/or over portion **2701** and insulators **2811** and **2812**. Material **2902** may include a conductive material similar to or identical to those of portion **2701** (FIG. **29**) or portion **502** of memory cell **500** of FIG. **5**, such as the material (e.g., chalcogenide-based material) that may be configured to change between different phases. In FIG. **29**, forming mask **2911** and photoresist **2912** may include depositing a material (e.g., silicon oxide, silicon nitride, amorphous carbon, or transparent carbon, or other) on and/or over material **2902** and depositing a photoresist

material over mask **2911**. Mask **2911** and photoresist **2912** may be used to remove a part of material **2902** as described below with reference to FIG. **31**.

In FIG. **30**, a remaining part of mask **2911** and a remaining part of photoresist **2912** are formed after some part of mask **2911** and photoresist **2912** (FIG. **29**) is removed, e.g., by patterning mask **2911** and photoresist **2912** using techniques such as photolithography and etch. In FIG. **30**, the remaining part of mask **2911** and the remaining part of photoresist **2912** may be used as a masking structure for removing some part of material **2902** by techniques such as etching, as represented by arrows **3010**.

In FIG. **31**, a portion **3102** is formed. Portion **3102** is a remaining portion of material **2902** of FIG. **30** after some part of material **2902** is removed.

In FIG. **32**, insulators **3211** and **3212** may be formed. Insulators **3211** and **3212** may include material such as silicon oxide or other insulation material. Insulators **3211** and **3212** may be formed before or after the remaining part of mask **2911** (FIG. **31**) and the remaining part of photoresist **2912** (FIG. **31**) are removed. In FIG. **32**, forming insulators **3211** and **3212** may include depositing insulation material over portion **3102** and insulators **2811** and **2812**, and then planarizing (e.g., including CMP planarization) the insulation material to form insulators **3211** and **3212**.

In FIG. **33**, a conductive material **3352** may be formed on portion **3102** and insulators **3211** and **3212**. Forming conductive material **3352** may include depositing a conductive material on portion **3102** and insulators **3211** and **3212**. Conductive material **3352** may include a material similar to or identical to those of electrode **551** or **552** of FIG. **5**.

In FIG. **34**, an electrode **3452** and insulators **3411** and **3412** may be formed. Forming electrode **3452** may include removing (e.g., patterning) a part of conductive material **3352**. Forming insulators **3411** and **3412** may include depositing an insulation material (e.g., silicon oxide or other insulation material) on electrode **3452** and insulators **3211** and **3212**, and then planarizing (e.g., including CMP planarization) the insulation material to form insulators **3411** and **3412**. Electrode **3452** and portion **3102** of FIG. **34** may also be formed by an alternative technique. As described above, portion **3102** of FIG. **34** is formed from material **2902** of FIG. **29**. The alternative technique may include sequentially depositing a conductive material (e.g., conductive material **3352**) on material **2902** of FIG. **29** before mask **2911** and photoresist **2912** are formed, and then forming mask **2911** and photoresist **2912** over both the conductive material and material **2902**. Thus, the alternative technique may use the same mask **2911** and photoresist **2912** (FIG. **29**) to pattern both the conductive material (to produce electrode **3452** of FIG. **34**) and material **2902** (to produce portion **3102** of FIG. **34**). In the alternative technique, insulators **3211**, **3212**, **3411**, and **3412** (FIG. **34**) may be formed after electrode **3452** and portion **3102** are formed, e.g., by depositing an insulation material over electrode **3452** and insulators **2811** and **2812** (FIG. **34**), and then planarizing (e.g., including CMP planarization) the insulation material.

As shown in FIG. **34**, memory cell **3400** may include a memory element **3444** having portion **2701**, portion **3102**, and a portion **3403**. Portion **3403** may include at least a part of portion **2701** or portion **3102**, or both. Portion **3403** may correspond to portion **503** of FIG. **5** and may be referred to as a programmable portion of memory element **3444** of FIG. **34**. Memory cell **3400** may correspond to memory cell **500** of FIG. **5**. Thus, processes similar to or identical to those described above with reference to FIG. **23** through FIG. **34** may be used to form memory cell **500** of FIG. **5**.

FIG. **35** through FIG. **38** show various processes of forming a memory cell with a memory element having a constriction structure and an intermediate material according to various embodiments of the invention. FIG. **38** shows memory cell **3800** after various processes described with reference to FIG. **35** through FIG. **38**. FIG. **35** through FIG. **37** show parts of memory cell **3800** of FIG. **38** while it is being formed.

The processes described with reference to FIG. **35** through FIG. **38** may include processes similar to or identical to those described above with reference to FIG. **28** through FIG. **34**, except for the processes of forming an intermediate material **3520** shown in FIG. **35** through FIG. **48**. Thus, for simplicity, similar or identical processes and components in FIG. **28** through FIG. **38** are given the same reference numbers.

FIG. **35** shows intermediate material **3520** formed over portion **2701**, insulators **2811** and **2812**, electrode **2451**, insulators **2411** and **2412**, and substrate **2310**. Forming intermediate material **3520** may include depositing a material on portion **2701** and insulators **2811** and **2812**. Intermediate material **3520** may be similar to or identical to that of intermediate material **1220** of FIG. **13**, or other conductive material.

In FIG. **36**, material **2902**, mask **2911**, and photoresist **2912** may be formed on and/or over intermediate material **3520** using processes similar to or identical to those described above with reference to FIG. **29** and FIG. **30**.

In FIG. **37**, a part of material **2902** and a part of **3520** have been removed, leaving portion **3102** and a remaining part of intermediate material **3520**.

In FIG. **38**, insulators **3211** and **3212**, electrode **3452**, and insulators **3411** and **3412** may be formed using processes similar to or identical to those described above with reference to FIG. **34**. Further, electrode **3452**, portion **3102**, and intermediate material **3520** of FIG. **38** may be formed at the same time using the same patterning process. For example, in FIG. **36**, a conductive material may be sequentially deposited on material **2902** (over material **2902**) of FIG. **36** before mask **2911** and photoresist **2912** are formed. Then, mask **2911** and photoresist **2912** may be used to form electrode **3452**, portion **3102**, and intermediate material **3520** of FIG. **38** in the same patterning process.

As shown in FIG. **38**, memory cell **3800** may include a memory element **3888** having portion **2701**, portion **3102**, and a portion **3803**. Portion **3803** may include at least a part of portion **2701** or **3102**, or both. Portion **3803** may correspond to portion **1203** of FIG. **12** and may be referred to as a programmable portion of memory element **3888** of FIG. **38**. Memory cell **3800** may correspond to memory cell **1200** of FIG. **12**. Thus, processes similar to or identical to those described above with reference to FIG. **35** through FIG. **38** may be used to form memory cell **1200** of FIG. **12**.

FIG. **39** through FIG. **42** show various processes of forming a memory cell with a memory element having a constriction structure with an intermediate material according to various embodiments of the invention. FIG. **42** shows memory cell **4200** after various processes described with reference to FIG. **39** through FIG. **42**. Thus, FIG. **39** through FIG. **42** only shows some part of memory cell **4200** of FIG. **42**.

The processes described with reference to FIG. **39** through FIG. **42** may include processes that are similar to or identical to those described above with reference to FIG. **23** through FIG. **38**, except for the processes of leaving a part of mask **2511** (FIG. **40** through FIG. **42**) in memory cell **4200** (FIG. **42**) after memory cell **4200** is formed. For

simplicity, similar or identical processes and components in FIG. 28 through FIG. 42 are given the same reference numbers.

FIG. 39 shows components similar to or identical to those of FIG. 26 such as mask 2511, photoresist 2512, material 2501, electrode 2451, insulators 2411 and 2412, and substrate 2310. Mask 2511 and photoresist 2512 may be used as a masking structure for removing some part of material 2501 by techniques such as etching, as represented by arrows 3910.

In FIG. 40, portion 2701 is formed after some part of material 2501 (FIG. 39) is removed. FIG. 40 also shows a part of mask 2511 on and/or over portion 2701. As described above with reference to FIG. 39, mask 2511 and photoresist 2512 may be used as the masking structure for removing some part of material 2501. The removal (e.g. etching) of some part of material 2501 may be controlled such that the entire photoresist 2512 and some part of mask 2511 may also be removed (e.g. during the etching), leaving the part of mask 2511 on portion 2701. This part of mask 2511 in FIG. 40 may remain in memory cell 4200 (FIG. 42) and may be similar to or identical to that of intermediate material 1420 of FIG. 14. Thus, mask 2511 of FIG. 39 may include material similar to or identical to that of intermediate material 1420 of FIG. 14, or other conductive material.

In FIG. 41, insulators 4111 and 4112 may be formed. Forming insulators 4111 and 4112 may include depositing insulation material on and/or over other components shown in FIG. 41, including over the part of mask 2511, and then planarizing (e.g., including CMP planarization) the insulation material to form insulators 4111 and 4112.

FIG. 42 shows memory cell 4200 with components formed after the components shown in FIG. 41 are formed. Processes similar to or identical to those described above with reference to FIG. 29 through FIG. 34 may be used to form additional components of memory cell 4200 of FIG. 42. As shown in FIG. 42, memory cell 4200 may include a memory element 4222 and a remaining portion of a mask such as mask 2511. In FIG. 42, memory element 4222 may include a portion 2701, a portion 3102, and a portion 4203. Portion 4203 may include at least a part of portion 2701 or portion 3102, or both. Portion 4203 may correspond to portion 1403 of FIG. 14 and may be referred to as a programmable portion of memory element 4222 of FIG. 42. Memory cell 4200 may correspond to memory cell 1400 of FIG. 14. Thus, processes similar to or identical to those described above with reference to FIG. 35 through FIG. 42 may be used to form memory cell 1400 of FIG. 14.

FIG. 43 and FIG. 44 show various processes of forming a memory cell with a memory element having a constriction structure according to various embodiments of the invention. The processes described with reference to FIG. 43 and FIG. 44 may include processes that are similar to or identical to those described above with reference to FIG. 23 through FIG. 42, except for the processes of forming intermediate material 4322 shown in FIG. 43. Thus, for simplicity, similar or identical processes and components in FIG. 28 through FIG. 44 are given the same reference numbers.

FIG. 43 shows an intermediate material 4321 and an intermediate material 4322, insulators 4111, 4112, 2411, 2412, an electrode 2451, and a substrate 2310. Intermediate material 4321 may be similar to or identical to the part of mask 2511 of FIG. 41. Thus, intermediate material 4321 of FIG. 43 may be formed by processes similar to or identical to those described above with reference to FIG. 29 through FIG. 42 (e.g., intermediate material 4321 may include a remaining part of a mask such as mask 2511 of FIG. 39). In

FIG. 43, forming intermediate material 4322 may include depositing a conductive material other components of FIG. 43. In an alternative way, both intermediate materials 4321 and 4322 may be formed at the same time in one deposition step. For example, in FIG. 27, after portion 2701 may be formed, insulators 2811 and 2812 may be formed while mask 2511 or photoresist 2512, or both, may remain over portion 2701. Then, a process such as a planarization process may be performed to planarize insulators 2811 and 2812. The planarization process may stop at mask 2511. After the planarization process, mask 2511 may be removed, leaving an opening above portion 2701 (e.g., the opening occupied by intermediate material 4321 in FIG. 43). A conductive material (e.g., material to form both intermediate materials 4321 and 4322 of FIG. 43) may be deposited in one step over portion 2701 and insulators 4111 and 4112 to fill the opening and also cover insulators 4111 and 4112. Thus, in FIG. 43, intermediate materials 4321 and 4322 may be formed at the same time in one deposition step. Both intermediate materials 4321 and 4322 may include the same material in which the material may be similar to or identical to that of sub-materials 1621 and 1622 of FIG. 16, or other conductive material. Intermediate materials 4321 and 4322 may also include materials different from each other. A part of intermediate material 4322 may be removed (e.g., by patterning) to obtain a remaining part of intermediate material 4322, as shown in FIG. 44.

FIG. 44 shows memory cell 4400 with components formed after the components shown in FIG. 43 are formed. Processes similar to or identical to those described above with reference to FIG. 29 through FIG. 42 may be used to form additional components of memory cell 4400 of FIG. 44. As shown in FIG. 44, memory cell 4400 may include a memory element 4444 having portion 2701, portion 3102, and a portion 4403. Portion 4403 may include at least a part of portion 2701 or portion 3102, or both. Portion 4403 may correspond to portion 1603 of FIG. 16 and may be referred to as a programmable portion of memory element 4444 of FIG. 44. Memory cell 4400 may correspond to memory cell 1600 of FIG. 16. Thus, processes similar to or identical to those described above with reference to FIGS. 43 and 44 may be used to form memory cell 1600 of FIG. 16.

FIG. 45 through FIG. 49 show various processes of forming a memory cell with a memory element having a constriction structure according to various embodiments of the invention. FIG. 49 shows memory cell 4900 after completion of various processes described with reference to FIG. 45 through FIG. 49. FIG. 45 through FIG. 48 show parts of memory cell 4900 (FIG. 49) while it is being formed.

FIG. 45 shows electrode 2451 and insulators 2411 and 2412 formed over substrate 2310. The processes of forming the components shown in FIG. 45 may be similar to or identical to those described above with reference to FIG. 23 and FIG. 24.

In FIG. 46, a portion 4601, insulators, 4605, 4611, 4612, and 4621, 4622 may be formed. Portion 4601 may include a conductive material similar to or identical to those of portion 501 of memory cell 500 of FIG. 5, such as the material (e.g., chalcogenide-based material) that may be configured to change between different phases. Insulator 4605 of FIG. 46 may include insulation material such as silicon nitride. Insulators 4611 and 4612 may include insulation material such as silicon oxide. Insulators 4621 and 4622 may include insulation material such as silicon nitride or aluminum oxide. Insulators 4621 and 4622 may serve as additional protection layers (e.g., oxygen or hydrogen bar-

rier layers) that may encapsulate portion **4601** and insulator **4605** to protect portion **4601** from inadvertently being altered thermally, chemically, or both, (e.g., oxidized) during fabrication processes. In some cases, insulators **4621** and **4622** may be omitted. In FIG. **46**, forming portion **4601** and insulator **4605** may include depositing a conductive material (to form portion **4601**) over electrode **2451** and insulators **2411** and **2412**, depositing an insulation material (to form insulator **4605**) over the conductive material, and then removing (e.g., by patterning) a part of each of the conductive and insulation materials to form portion **4601** and insulator **4605**. Insulators **4611**, **4612**, **4621**, and **4622** may be formed after portion **4601** and insulator **4605** are formed.

In FIG. **47**, opening **4705** may be formed in insulator **4605** to expose a part (e.g., a part of a surface area) of portion **4601**. Forming opening **4705** may include removing (e.g., by etching) a part of insulator **4605** to form opening **4705** (e.g., via) with a tapered part **4713** having a slope as shown in FIG. **47**.

In FIG. **48**, portion **4802** may be formed. Portion **4802** may include conductive material similar to or identical to those of portion **4601** of or portion **501** of memory cell **500** of FIG. **5**, such as the material (e.g., chalcogenide-based material) that may be configured to change between different phases. In FIG. **48**, forming portion **4802** may include depositing a conductive material over insulator **4605** including filling opening **4705** with the conductive material to cover the exposed part of portion **4601**, and then removing a part of the conductive material, e.g., by CMP process, to obtain a remaining part of the conductive material, which corresponds to portion **4802** of FIG. **48**. As shown in FIG. **48**, since opening **4705** of FIG. **47** includes a tapered part (e.g., tapered part **4713** in FIG. **47**), portion **4802** may also include a tapered part that may conform to the tapered part of opening **4705**.

In FIG. **49**, an electrode **4952** and insulators **4911** and **4912** may be formed. Electrode **4952** may include conductive material similar to or identical to those of electrode **551** or **552** of FIG. **5**. Insulators **4911** and **4912** may include material similar to or identical to that of insulators of **4611** and **4612**. Forming electrode **4952** may include depositing a conductive material over other components of FIG. **49**, and then removing (e.g., patterning) a part of the conductive material to obtain electrode **4952**. Forming insulators **4911** and **4912** may include depositing an insulation material on electrode **4952** and insulators **4611** and **4612**, and planarizing (e.g., including CMP planarization) the insulation material to form insulators **4911** and **4912**.

As shown in FIG. **49**, memory cell **4900** may include a memory element **4999** having portion **4802**, portion **4601**, and a portion **4903**. Portion **4903** may include at least a part of portion **4802** or portion **4601**, or both. Portion **4903** may be referred to as a programmable portion of memory element **4999** of FIG. **49**.

FIG. **50** and FIG. **51** show various processes of forming a memory cell with a memory element having a constriction structure according to various embodiments of the invention. The processes described with reference to FIG. **50** and FIG. **51** may include processes that are similar to or identical to those described above with reference to FIG. **45** through FIG. **49**, except for the processes of forming materials **5002** and **5052** (FIG. **50**) and portion **5102** and electrode **5152** (FIG. **51**). Thus, for simplicity, similar or identical processes and components in FIG. **45** and FIG. **51** are given the same reference numbers.

FIG. **50** shows material **5002** and material **5052** formed over the other components of FIG. **50**. Material **5002** may

include a conductive material similar to or identical to those of portion **4601**. Material **5052** may include a conductive material similar to or identical to that of electrode **4952** of FIG. **49**. In FIG. **50**, forming materials **5002** and **5052** may include depositing a first conductive material (to form portion **5102** of FIG. **51**) over other components of FIG. **49** and depositing a second conductive material (to form electrode **5152**) over the first conductive material.

In FIG. **51**, portion **5102**, electrode **5152**, and insulators **5111**, **5112**, **5121**, and **5122** may be formed. Forming portion **5102** and electrode **5152** may include removing (e.g., patterning in situ) a part of each of the materials **5002** and **5052** (FIG. **50**) in one removing step to obtain a remaining part of each of materials **5002** and **5052**, which may correspond to portion **5102** and electrode **5152** of FIG. **51**. Insulators **5111**, **5112**, **5121**, and **5122** may be formed after portion **5102** and electrode **5152** are formed. Insulators **5111** and **5112** may include insulation material such as silicon oxide. Insulators **5121** and **5122** may include insulation material such as silicon nitride or aluminum oxide. Insulators **5121** and **5122** may serve as additional insulations that may encapsulate portion **5102** and electrode **5152** to protect portion **5102** from inadvertently being oxidized during fabrication processes. In some cases, insulators **5121** and **5122** may be omitted.

As shown in FIG. **51**, memory cell **5100** may include a memory element **5155** having portion **4601**, portion **5102**, and a portion **5103**. Portion **5103** may include at least a part of portion **4601** or portion **5102**, or both. Portion **5103** may be referred to as a programmable portion of memory element **5155** of FIG. **51**.

FIG. **52** shows a memory cell **5200**. Forming memory cell **5200** may include processes similar to or identical to at least some of the processes described above with reference to FIG. **45** through FIG. **48**, except for the processes of forming an intermediate material **5220** in memory element **5222** of FIG. **52**. Forming intermediate material **5220** may include depositing a material between portion **4601** and insulator **4605** (e.g., during processes described above with reference to FIG. **46**). Intermediate material **5220** in FIG. **52** may include material similar to or identical to those of intermediate material **1220** of FIG. **12**, or other conductive material.

FIG. **53** shows a memory cell **5300**. Forming memory cell **5300** may include processes similar to or identical to at least some of the processes described above with reference to FIG. **50** and FIG. **51**, except for the processes of forming an intermediate material **5320** of memory element **5333** of FIG. **53**. Forming intermediate material **5320** may include depositing a material between portion **4601** and insulator **4605** (e.g., during processes described above with reference to FIG. **46**). Intermediate material **5320** in FIG. **53** may include material similar to or identical to those of intermediate material **1220** of FIG. **12**.

FIG. **54** through FIG. **56** show various processes of forming a memory cell with a memory element having a constriction structure according to various embodiments of the invention. The processes described with reference to FIG. **54** through FIG. **56** may include processes that are similar to or identical to at least some of the processes described above with reference to FIG. **28** through FIG. **34**, except for the processes of forming memory element **5555** in FIG. **55**. Thus, for simplicity, similar or identical processes and components in FIG. **28** through FIG. **34** and FIG. **54** through FIG. **56** are given the same reference numbers.

FIG. **54** shows a mask **5411** and a photoresist **5412**, material **5401**, electrode **2451**, insulators **2411** and **2412**, and substrate **2310**. Material **5401** may include a material

similar to or identical to that of material **2501** of FIG. **26**. The components of FIG. **54** may be similar to or identical to those of FIG. **26** such as mask **2511**, photoresist **2512**, material **2501**, electrode **2451**, insulators **2411** and **2412**, and substrate **2310**.

FIG. **55** shows a memory element **5555**, which may be formed by a process that may include removing a part of material **5401** of FIG. **54** (memory element **5555** is a portion of material **5401** of FIG. **54**). For example, at least some part of material **5401** of FIG. **54** may be removed by etching (e.g., using isotropic etching in directions **5510**) to form memory element **5555** with portions **5501**, **5502**, and **5503**. Thus, portions **5501**, **5502**, and **5503** may be formed by one material removing step that may include removing a first amount of the material of material **5401** to form portion **5503**, removing a second amount of the material of material **5401** to form portion **5501**, and removing a third amount of the material of material **5401** to form portion **5502**. The first amount of material may be more than each of the second and third amounts of the material such that each of first and second portions **5501** and **5502** may have a tapered part. For example, as shown in FIG. **55**, portion **5501** may include a tapered part **5561**, portion **5502** may include a tapered part **5562**, and portion **5503** may include at least one of tapered part **5561** and **5562**.

FIG. **56** shows memory cell **5600** with components formed after the components shown in FIG. **55** are formed. Processes similar to or identical to those described above with reference to FIG. **32** through FIG. **34** may be used to form additional components of memory cell **5600** of FIG. **56** such as electrode **5652** and insulators **5611** and **5612**. Electrode **5652** may also be formed by an alternative technique. For example, in the alternative technique, mask **5411** (FIG. **54** and FIG. **55**) may include a conductive mask such that electrode **5652** (FIG. **56**) may be a remainder part of mask **5411** after memory element **5555** is formed. Further, in FIG. **56**, insulation materials (e.g., materials similar to or identical to those of insulators **4621** and **4622** of FIG. **46**) may be formed in areas **5621** and **5622** to encapsulate memory element **5555** to protect it. In FIG. **56**, portion **5503** may correspond to portion **1803** of FIG. **18** and may be referred to as a programmable portion of memory element **5555** of FIG. **56**. Memory cell **5600** may correspond to memory cell **1800** of FIG. **18**. Thus, processes similar to or identical to those described above with reference to FIGS. **54** and **56** may be used to form memory cell **1800** of FIG. **18**.

One skilled in art may recognize that the various processes of forming memory cells **3400**, **3800**, **4200**, **4400**, **4900**, **5100**, **5200**, **5300**, and **5600** described above with reference to FIG. **23** through FIG. **56** may include other processes of forming other components such as access components similar to or identical to access components **211**, **311**, and **411** shown in FIG. **2** through FIG. **4**. The description herein omits the description of the processes of forming other components of the memory cells to help focus on the embodiments described herein.

The illustrations of apparatus (e.g., memory device **101** and memory cells **200**, **300**, **400**, **500**, **1200**, **1400**, **1600**, **1800**, **3400**, **3800**, **4200**, **4400**, **4900**, **5100**, **5200**, **5300**, and **5600**) are intended to provide a general understanding of the structure of various embodiments and are not intended to provide a complete description of all the components and features of apparatus that might make use of the structures described herein.

Any of the components described above can be implemented in a number of ways, including simulation via

software. Thus, apparatus (e.g., memory device **101** and memory cells **200**, **300**, **400**, **500**, **1200**, **1400**, **1600**, **1800**, **3400**, **3800**, **4200**, **4400**, **4900**, **5100**, **5200**, **5300**, and **5600**) described above may all be characterized as “modules” (or “module”) herein. Such modules may include hardware circuitry, single and/or multi-processor circuits, memory circuits, software program modules and objects and/or firmware, and combinations thereof, as desired by the architect of the apparatus (e.g., memory device **101** and memory cells **200**, **300**, **400**, **500**, **1200**, **1400**, **1600**, **1800**, **3400**, **3800**, **4200**, **4400**, **4900**, **5100**, **5200**, **5300**, and **5600**) and as appropriate for particular implementations of various embodiments. For example, such modules may be included in a system operation simulation package, such as a software electrical signal simulation package, a power usage and distribution simulation package, a capacitance-inductance simulation package, a power/heat dissipation simulation package, a signal transmission-reception simulation package, and/or a combination of software and hardware used to operate or simulate the operation of various potential embodiments.

The apparatus of various embodiments may include or be included in electronic circuitry used in high-speed computers, communication and signal processing circuitry, memory modules, portable memory storage devices (e.g., thumb drives), single or multi-processor modules, single or multiple embedded processors, multi-core processors, data switches, and application-specific modules including multi-layer, multi-chip modules. Such apparatus may further be included as sub-components within a variety of electronic systems, such as televisions, cellular telephones, personal computers (e.g., laptop computers, desktop computers, handheld computers, tablet computers, etc.), workstations, radios, video players, audio players (e.g., MP3 (Motion Picture Experts Group, Audio Layer 3) players), vehicles, medical devices (e.g., heart monitor, blood pressure monitor, etc.), set top boxes, and others.

One or more embodiments described herein include apparatus and methods having a memory cell with a first electrode and a second electrode, and a memory element directly contacting the first and second contacts. The memory element may include a programmable portion having a material configured to change between multiple phases. The programmable portion may be isolated from the first electrode by a first portion of the memory element and isolated from the second electrode by a second portion of the memory element. Other embodiments including additional apparatus and methods are described above with reference to FIG. **1** through FIG. **56**.

The above description and the drawings illustrate some embodiments of the invention to enable those skilled in the art to practice the embodiments of the invention. Other embodiments may incorporate structural, logical, electrical, process, and other changes. In the drawings, like features or like numerals describe substantially similar features throughout the several views. Examples merely typify possible variations. Portions and features of some embodiments may be included in, or substituted for, those of others. Many other embodiments will be apparent to those of skill in the art upon reading and understanding the above description. Therefore, the scope of various embodiments of the invention is determined by the appended claims, along with the full range of equivalents to which such claims are entitled.

The Abstract is provided to comply with 37 C.F.R. § 1.72(b) requiring an abstract that will allow the reader to quickly ascertain the nature and gist of the technical disclo-

sure. The Abstract is submitted with the understanding that it will not be used to interpret or limit the scope or meaning of the claims.

What is claimed is:

1. A device comprising:
  - a first electrode and a second electrode; and
  - a memory element including a material configured to change between different phases and to pass a current between the first and second electrodes, the memory element including:
    - a first portion coupled to the first electrode and having a first cross-section area configured to allow the current to pass through;
    - a second portion coupled to the second electrode and having a second cross-section area and configured to allow the current to pass through; and
    - a third portion coupled between the first and second portions and having a third cross-section area configured to allow the current to pass through, wherein the third cross-section area is smaller than each of the first and second cross-section areas, a part of the second portion and a part of the third portion form a programmable portion of the memory element, each of the part of the third portion and the part of the second portion is included in the material configured to change between multiple phases, the third portion includes a tapered part between the first portion and the second portion, and the programmable portion includes the tapered part wherein the memory element includes an intermediate material between the first and second portions, the intermediate material having a resistance value lower than a resistance value of each of the first, second, and third portions.
2. The device of claim 1, wherein the first, second, and third portions include an identical material.
3. A device comprising:
  - a first electrode and a second electrode; and
  - a memory element including a material configured to change between different phases and to pass a current between the first and second electrodes, the memory element including:
    - a first portion coupled to the first electrode and having a first cross-section area configured to allow the current to pass through;
    - a second portion coupled to the second electrode and having a second cross-section area and configured to allow the current to pass through; and
    - a third portion coupled between the first and second portions and having a third cross-section area configured to allow the current to pass through, wherein the third cross-section area is smaller than each of the first and second cross-section areas, a part of the second portion and a part of the third portion form a programmable portion of the memory element, each of the part of the third portion and the part of the second portion is included in the material configured to change between multiple phases, the third portion includes a tapered part between the first portion and the second portion, and the programmable portion includes the tapered part wherein the memory element includes an intermediate material between the first and second portions, the intermediate material including one of TiN, ZrN, HfN, VN, NbN, TaN, TiC, ZrC, HfC, VC, NbC, TaC, TiB<sub>2</sub>, ZrB<sub>2</sub>, HfB<sub>2</sub>, VB<sub>2</sub>, NbB<sub>2</sub>, TaB<sub>2</sub>, Cr<sub>3</sub>C<sub>2</sub>, Mo<sub>2</sub>C, WC, CrB<sub>2</sub>, Mo<sub>2</sub>B<sub>5</sub>, W<sub>2</sub>B<sub>5</sub>, TiAlN, TiSiN, TiW, TaSiN, TiCN, SiC, B<sub>4</sub>C, WSix, MoSi<sub>2</sub>, NiCr, doped silicon, carbon, platinum, niobium, tungsten, and molybdenum.
  - 4. The device of claim 3, wherein the material includes a compound of germanium, antimony, and tellurium.

5. A device comprising:
  - a first electrode and a second electrode; and
  - a memory element including a programmable portion configured to change between different phases to represent a value of information stored in the memory element, the memory element including:
    - a first portion coupled to the first electrode and having a first cross-section area configured to allow the current to pass through;
    - a second portion coupled to the second electrode and having a second cross-section area and configured to allow the current to pass through, wherein the programmable portion is between the first and second portions, the programmable portion includes a part of the first portion and a part of the second portion, the part of the first portion directly contacts the part of the second portion, each of the part of the first portion and the part of the second portion includes a material configured to change between multiple phases, the first portion includes a tapered part, the tapered part is included in the part of the first portion, and the programmable portion includes the tapered part, wherein,
      - the first portion includes a first width adjacent the part of the second portion, the first width extending in a direction perpendicular to a direction between the first and second electrodes, and a second width adjacent the first electrode, the second width extending in the direction perpendicular to the direction between the first and second electrodes, and the first width is less than the second width; and
      - the second portion includes a third width adjacent the part of the first portion, the third width extending in the direction perpendicular to the direction between the first and second electrodes; and a fourth width adjacent the second electrode, the fourth width extending in the direction perpendicular to the direction between the first and second electrodes, and the third width is equal to the fourth width.
  - 6. The device of claim 5, wherein the first portion directly contacts the first electrode.
  - 7. The device of claim 6, wherein the second portion directly contacts the second electrode.
  - 8. The device of claim 5, wherein the first and second portions include an identical material.
  - 9. The device of claim 8, wherein the material includes a chalcogenide material.
  - 10. The device of claim 5, wherein the programmable portion is configured to change between a crystalline phase and an amorphous phase, and wherein the programmable portion in the amorphous phase has a first thickness corresponding to a first value of information stored in the memory element, and a second thickness corresponding to a second value of information stored in the memory element.
  - 11. The device of claim 10, wherein the programmable portion in the amorphous phase has a third thickness corresponding to a third first value of information stored in the memory element.
  - 12. The device of claim 5, wherein the programmable portion is configured to store information representing a single bit.
  - 13. The device of claim 5, wherein the programmable portion is configured to store information representing multiple bits.

25

14. A method comprising:  
forming a first electrode;  
forming a memory element over the first electrode;  
forming a second electrode over the memory element, the  
memory element formed to include a material config- 5  
ured to change between different phases and to pass a  
current between the first and second electrodes,  
wherein forming the memory element includes:  
forming a first portion of the memory element over the 10  
first electrode, the first portion having a first cross-  
section area configured to allow the current to pass  
through;  
forming a second portion of the memory element over  
the first portion, the second portion having a second 15  
cross-section area and configured to allow the cur-  
rent to pass through, wherein the second portion is  
formed after the first portion is formed; and  
the memory element is formed such that a part of the 20  
second portion and a part of the first portion form a  
programmable portion of the memory element, each  
of the part of the first portion and the part of the  
second portion is included in the material configured  
to change between multiple phases, the first portion  
includes a tapered part between the first portion and

26

the second portion, and the programmable portion  
includes the tapered part, and the memory element is  
formed such that,  
the first portion includes a first width adjacent the part  
of the second portion, the first width extending in a  
direction perpendicular to a direction between the  
first and second electrodes, and a second width  
adjacent the first electrode, the second width extend-  
ing in the direction perpendicular to the direction  
between the first and second electrodes, and the first  
width is less than the second width; and  
the second portion includes a third width adjacent the  
part of the first portion, the third width extending in  
the direction perpendicular to the direction between  
the first and second electrodes; and a fourth width  
adjacent the second electrode, the fourth width  
extending in the direction perpendicular to the direc-  
tion between the first and second electrodes, and the  
third width is equal to the fourth width.

15. The method of claim 14, wherein the first and second  
portions are formed to have a same material.

16. The method of claim 14, wherein the first and second  
portions are formed from a chalcogenide material.

\* \* \* \* \*