

US010950511B2

(12) **United States Patent**
Boone et al.

(10) **Patent No.:** **US 10,950,511 B2**
(45) **Date of Patent:** **Mar. 16, 2021**

(54) **DIE CARRIER PACKAGE AND METHOD OF FORMING SAME**

(71) Applicant: **Medtronic, Inc.**, Minneapolis, MN (US)

(72) Inventors: **Mark R. Boone**, Gilbert, AZ (US);
Mark E. Henschel, Phoenix, AZ (US)

(73) Assignee: **Medtronic, Inc.**, Minneapolis, MN (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **16/175,314**

(22) Filed: **Oct. 30, 2018**

(65) **Prior Publication Data**

US 2020/0135597 A1 Apr. 30, 2020

(51) **Int. Cl.**
H01L 23/12 (2006.01)
H01L 21/48 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 23/12** (2013.01); **H01L 21/4846** (2013.01); **H01L 21/4853** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 23/12; H01L 23/3121; H01L 23/49816; H01L 23/49838; H01L 23/49866; H01L 23/5386; H01L 21/48; H01L 21/52; H01L 21/56; H01L 21/4846; H01L 21/4853; H01L 23/00; H01L 23/31; H01L 23/538; H01L 25/07; H01L 25/071; H01L 25/072; H01L 25/073; H01L

25/074; H01L 25/075; H01L 25/0753; H01L 25/0756; H01L 25/041; H01L 25/042; H01L 25/043; H01L 25/046; H01L 25/047; H01L 25/048; H01L 25/065; H01L 25/16;

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,266,794 A 11/1993 Olbright et al.
6,174,749 B1 1/2001 Yuen et al.

(Continued)

FOREIGN PATENT DOCUMENTS

TW 201037793 A 10/2010
WO 2017171813 A1 10/2017

OTHER PUBLICATIONS

U.S. Appl. No. 15/477,904, filed Apr. 3, 2017, Boone.
(Continued)


Primary Examiner — Chuong A Luu

(74) *Attorney, Agent, or Firm* — Muetting Raasch Group

(57) **ABSTRACT**

Various embodiments of a die carrier package and a method of forming such package are disclosed. The package includes one or more dies disposed within a cavity of a carrier substrate, where a first die contact of one or more of the dies is electrically connected to a first die pad disposed on a recessed surface of the cavity, and a second die contact of one or more of the dies is electrically connected to a second die pad also disposed on the recessed surface. The first and second die pads are electrically connected to first and second package contacts respectively. The first and second package contacts are disposed on a first major surface of the carrier substrate adjacent the cavity.

15 Claims, 7 Drawing Sheets



- (51) **Int. Cl.**
H01L 21/52 (2006.01)
H01L 21/56 (2006.01)
H01L 23/31 (2006.01)
H01L 23/498 (2006.01)
H01L 23/538 (2006.01)
H01L 23/00 (2006.01)
H01L 31/12 (2006.01)
A61B 5/00 (2006.01)
A61N 1/375 (2006.01)
H01L 31/0203 (2014.01)
H01L 33/48 (2010.01)
- (52) **U.S. Cl.**
 CPC *H01L 21/52* (2013.01); *H01L 21/56* (2013.01); *H01L 23/3121* (2013.01); *H01L 23/49816* (2013.01); *H01L 23/49838* (2013.01); *H01L 23/49866* (2013.01); *H01L 23/5386* (2013.01); *H01L 24/48* (2013.01); *H01L 24/85* (2013.01); *H01L 31/125* (2013.01); *A61B 5/686* (2013.01); *A61N 1/375* (2013.01); *H01L 31/0203* (2013.01); *H01L 33/483* (2013.01); *H01L 2224/48248* (2013.01)
- (58) **Field of Classification Search**
 CPC *H01L 25/0652*; *H01L 25/0655*; *H01L 25/0657*; *H01L 31/0203*; *H01L 2225/06503*; *H01L 2225/06506*; *H01L 2225/0651*; *H01L 2225/06555*
 USPC 257/82
 See application file for complete search history.

- (56) **References Cited**
- U.S. PATENT DOCUMENTS
- | | | | |
|--------------|------|---------|--|
| 6,259,121 | B1 | 7/2001 | Lemoff et al. |
| 6,636,544 | B2 | 10/2003 | Baillargeon et al. |
| 6,953,702 | B2 | 10/2005 | Miller et al. |
| 8,313,962 | B2 | 11/2012 | Lott et al. |
| 8,664,756 | B2 | 3/2014 | Boone et al. |
| 8,743,923 | B2 | 6/2014 | Geske et al. |
| 9,057,853 | B2 | 6/2015 | Lau et al. |
| 9,065,254 | B2 | 6/2015 | Geske et al. |
| 2003/0116859 | A1 * | 6/2003 | Hashimoto H01L 23/49575
257/777 |
| 2005/0046035 | A1 * | 3/2005 | Egawa H01L 25/0657
257/777 |
| 2017/0272081 | A1 * | 9/2017 | Chiang H03L 1/02 |
| 2018/0012853 | A1 | 1/2018 | Lin et al. |
| 2018/0279924 | A1 | 10/2018 | Kuhn |

OTHER PUBLICATIONS

- Hunt et al., "Synergy between 2.5/3D Development and Hybrid 3D Wafer Level Fanout," *ASE Group Kaohsiung*, 10 pages.
 Lin et al., "Advanced 3D eWLB-PoP (embedded Wafer Level Ball Grid Array Package on Package) Technology," *2016 IEEE 66th Electronic Components and Technology Conference*, Singapore, 6 pages.
 (PCT/US2019/058000) PCT Notification of Transmittal of the International Search Report and the Written Opinion of the International Searching Authority, dated Jan. 21, 2020, 12 pages.

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10



FIG. 11A



FIG. 11B




FIG. 11C




FIG. 11D




FIG. 11E




FIG. 11F




FIG. 11G




FIG. 11H




FIG. 11I




FIG. 11J




FIG. 11K




FIG. 11L




FIG. 12

DIE CARRIER PACKAGE AND METHOD OF FORMING SAME

TECHNICAL FIELD

This disclosure generally relates to die carrier packages and methods of forming such packages.

BACKGROUND

IMDs for monitoring a physiological condition and/or delivering a therapy can include one or more physiological sensors. Such sensors can provide one or more signals related to one or more physiological conditions of a patient state. Examples of such IMDs include heart monitors, pacemakers, implantable cardioverter defibrillators (ICDs), myostimulators, neurological stimulators, drug delivery devices, insulin pumps, glucose monitors, etc.

Optical sensors may be employed in IMDs as physiological sensors configured to detect changes in light modulation by, for example, a body fluid or tissue measurement volume due to a change in a physiological condition in the body fluid or tissue. Such optical sensors can be used, for example, to detect changes in metabolite levels in the blood, such as oxygen saturation levels or glucose levels, or changes in tissue perfusion. A typical optical sensor can include one or more light sources and one or more detectors that are adapted to detect light emitted by the light sources and modulated by, e.g., body fluid or tissue measurement volume.

Monitoring such physiological conditions provides useful diagnostic measures that can be used in managing therapies for treating a medical condition. For example, a decrease in blood oxygen saturation or tissue perfusion may be associated with insufficient cardiac output or respiratory function. Thus, monitoring such conditions may allow an implantable medical device to respond to a decrease in oxygen saturation or tissue perfusion, for example, by delivering electrical stimulation therapies to the heart to restore normal hemodynamic function.

SUMMARY

The techniques of this disclosure generally relate to a die carrier package and a method of forming such package. The package can include one or more dies disposed within a cavity of a carrier substrate, where a first die contact of one or more of the dies is electrically connected to a first die pad disposed on a recessed surface of the cavity, and a second die contact of one or more of the dies is electrically connected to a second die pad also disposed on the recessed surface. The first and second die pads are electrically connected to first and second package contacts respectively. The first and second package contacts are disposed on a first major surface of the carrier substrate adjacent the cavity. In one or more embodiments, the first and second package contacts and an active surface of the die are disposed such that the package can be electrically connected to a major surface of a substrate so that the active surface of the die faces the major surface and the first and second package contacts are in contact with the same major surface. In embodiments where the die is adapted to emit electromagnetic radiation from its active surface, such radiation will be emitted in a direction away from the first major surface of the carrier substrate.

In one example, aspects of this disclosure relate to a die carrier package. The package includes a carrier substrate

having a first major surface, a second major surface, and a cavity disposed in the first major surface. The cavity includes a recessed surface. The package further includes a first package contact disposed on the first major surface of the carrier substrate adjacent the cavity and electrically connected to a first die pad disposed on the recessed surface via a first conductor, a second package contact disposed on the first major surface of the carrier substrate adjacent the cavity and electrically connected to a second die pad disposed on the recessed surface via a second conductor, and a die disposed within the cavity of the carrier substrate and having a first die contact disposed on an active surface of the die and a second die contact disposed on a major surface of the die that faces the recessed surface and that is opposed to the active surface. The first die contact is electrically connected to the first die pad and the second die contact is electrically connected to the second die pad.

In another example, aspects of this disclosure relate to a method of forming a die carrier package. The method includes forming a cavity in a first major surface of a carrier substrate, where the cavity includes a recessed surface; forming a patterned conductive layer on the recessed surface of the cavity and the first major surface of the carrier substrate, where the first patterned conductive layer includes first and second package contacts disposed on the first major surface of the carrier substrate adjacent the cavity and first and second die pads disposed on the recessed surface of the recessed surface, and where the first package contact is electrically connected to the first die pad by a first conductor and the second package contact is electrically connected to the second die pad by a second conductor; and disposing a die within the cavity. The method further includes electrically connecting a first die contact of the die to the first die pad of the patterned conductive layer, where the first die contact is disposed on an active surface of the die; and electrically connecting a second die contact of the die to the second die pad of the patterned conductive layer, where the second die contact is disposed on a major surface of the die that faces the recessed surface and is opposed to the active surface. The first and second conductors of the patterned conductive layer extend between the recessed surface of the cavity and the first major surface of the carrier substrate adjacent the cavity.

In another example, aspects of this disclosure relate to a hermetically-sealed system. The system includes a housing having an inner surface and an outer surface, a device substrate hermetically sealed to the housing and having a first major surface and a second major surface, and a die carrier package disposed on the first major surface of the substrate and having a die that has an active surface facing the device substrate. The die is adapted to emit light through the first and second major surfaces of the device substrate. Further, the die is disposed within a cavity of a carrier substrate of the package. The die also includes a first die contact disposed on the active surface of the die and a second die contact disposed on a major surface of the die that faces a recessed surface of the cavity of the die carrier package and that is opposed to the active surface. The first die contact is electrically connected to a first package contact disposed on a first major surface of the carrier substrate of the package adjacent the cavity and the second die contact is electrically connected to a second package contact disposed on the first major surface of the carrier substrate of the package adjacent the cavity. Further, the first and second package contacts are disposed between the first major surface of the carrier substrate and the first and second major surface of the device substrate. The system also

includes a detector disposed on the first major surface of the substrate and has a detecting surface. The detector is adapted to detect at least a portion of the light emitted by the die.

All headings provided herein are for the convenience of the reader and should not be used to limit the meaning of any text that follows the heading, unless so specified.

The terms “comprises” and variations thereof do not have a limiting meaning where these terms appear in the description and claims. Such terms will be understood to imply the inclusion of a stated step or element or group of steps or elements but not the exclusion of any other step or element or group of steps or elements.

In this application, terms such as “a,” “an,” and “the” are not intended to refer to only a singular entity but include the general class of which a specific example may be used for illustration. The terms “a,” “an,” and “the” are used interchangeably with the term “at least one.” The phrases “at least one of” and “comprises at least one of” followed by a list refers to any one of the items in the list and any combination of two or more items in the list.

The phrases “at least one of” and “comprises at least one of” followed by a list refers to any one of the items in the list and any combination of two or more items in the list.

As used herein, the term “or” is generally employed in its usual sense including “and/or” unless the content clearly dictates otherwise.

The term “and/or” means one or all of the listed elements or a combination of any two or more of the listed elements.

As used herein in connection with a measured quantity, the term “about” refers to that variation in the measured quantity as would be expected by the skilled artisan making the measurement and exercising a level of care commensurate with the objective of the measurement and the precision of the measuring equipment used. Herein, “up to” a number (e.g., up to 50) includes the number (e.g., 50).

Also herein, the recitations of numerical ranges by endpoints include all numbers subsumed within that range as well as the endpoints (e.g., 1 to 5 includes 1, 1.5, 2, 2.75, 3, 3.80, 4, 5, etc.).

The details of one or more aspects of the disclosure are set forth in the accompanying drawings and the description below. Other features, objects, and advantages of the techniques described in this disclosure will be apparent from the description and drawings, and from the claims.

BRIEF DESCRIPTION OF DRAWINGS

FIG. 1 is a schematic plan view of one embodiment of a die carrier package.

FIG. 2 is a schematic cross-section view of the die carrier package of FIG. 1.

FIG. 3 is a schematic perspective view of another embodiment of a die carrier package.

FIG. 4 is a schematic cross-section view of the die carrier package of FIG. 3.

FIG. 5 is a schematic cross-section view of the die carrier package of FIG. 3.

FIG. 6 is a schematic perspective view of one embodiment of hermetically-sealed system that includes the integrated circuit package of FIG. 3.

FIG. 7 is a schematic exploded view of the hermetically-sealed system of FIG. 6.

FIG. 8 is a schematic bottom plan view of a substrate of the hermetically-sealed system of FIG. 6.

FIG. 9 is a schematic top plan view of the substrate of the hermetically-sealed system of FIG. 6.

FIG. 10 is a schematic cross-section view of the substrate of the hermetically-sealed system of FIG. 6.

FIGS. 11A-L are various schematic cross-section views of one embodiment of a method of forming an integrated circuit package, where FIG. 11A is a schematic cross-section view of disposing an insulative layer on a carrier substrate wafer; FIG. 11B is a schematic cross-section view of disposing a mask on the insulative layer; FIG. 11C is a schematic cross-section view of patterning the insulative layer; FIG. 11D is a schematic cross-section view of forming a cavity in a first major surface of the carrier substrate wafer; FIG. 11E is a schematic cross-section view of removing the insulative layer; FIG. 11F is a schematic cross-section view of disposing a second insulative layer on the carrier substrate wafer; FIG. 11G is a schematic cross-section view of disposing conductive material on the carrier substrate wafer; FIG. 11H is a schematic cross-section view of patterning the conductive material to form a patterned conductive layer; FIG. 11I is a schematic cross-section view of disposing solder bumps on at least one of first and second package contacts; FIG. 11J is a schematic cross-section view of disposing a die within each cavity of the carrier substrate wafer and electrically connecting a first die contact of the die to a first die pad of the patterned conductive layer and a second die contact of the die to the second die pad of the patterned conductive layer; FIG. 11K is a schematic cross-section view of disposing an encapsulating material in each cavity of the carrier substrate wafer; and FIG. 11L is a schematic cross-section view of singulating the carrier substrate wafer to provide two or more die carrier packages.

FIG. 12 is a schematic cross-section view of another embodiment of a die carrier package.

DETAILED DESCRIPTION

In general, the present disclosure provides various embodiments of a die carrier package and a method of forming such package. The package can include one or more dies disposed within a cavity of a carrier substrate, where a first die contact of one or more of the dies is electrically connected to a first die pad disposed on a recessed surface of the cavity, and a second die contact of one or more of the dies is electrically connected to a second die pad also disposed on the recessed surface. The first and second die pads are electrically connected to first and second package contacts respectively. The first and second package contacts are disposed on a first major surface of the carrier substrate adjacent the cavity. In one or more embodiments, the first and second package contacts and an active surface of the die are disposed such that the package can be electrically connected to a major surface of a substrate such that the active surface of the die faces the major surface and the first and second package contacts are in contact with the same major surface. In embodiments where the die is adapted to emit electromagnetic radiation from its active surface, such radiation will be emitted in a direction away from the first major surface of the carrier substrate.

Various die carrier packages that include, e.g., one or more electromagnetic radiation emitting dies and that are mountable onto a substrate such that the electromagnetic radiation is emitted through the substrate can be challenging to manufacture. Some of these packages are required to translate a wire-bondable die into a surface-mount, solderable package while also orienting an active surface of the die towards the substrate upon which the package is mounted. In such configurations, solder pads or solder bumps of the package can be disposed on a side of the package that also

includes wire bond pads and other bare die components of the die. This is in contrast to typical die stacks, where the solder pads or bumps are disposed on a side of the package opposite from the wire bond pads and bare die components of the packaged die such as for a typical die stack that includes a ball grid array or most lead-frame-based packages.

Various embodiments of die carrier packages described herein can provide one or more advantages over these typical packages. For example, one or more embodiments described herein can provide a size-efficient surface-mount package that includes one or more dies (e.g., one or more electromagnetic radiation-emitting dies). In one or more embodiments, one or more of these dies can be mounted in a “marsupial” or “dead bug” configuration (i.e., on the same side of the carrier substrate as the package contacts). This configuration allows for the active surface of one or more of the dies to face the substrate upon which the package is disposed. In one or more embodiments, the die carrier package can be manufactured in an array format such that it is compatible with high-volume assembly processes and standard processing equipment. Further, disposal of the one or more dies in a cavity of the package allows for encapsulation of such dies.

FIGS. 1-2 are various views of one embodiment of a die carrier package 10. The package 10 includes a carrier substrate 12 that has a first major surface 14, a second major surface 16, and a cavity 18 disposed in the first major surface. The cavity 18 includes a recessed surface 20. The package 10 also includes a first package contact 22 disposed on the first major surface 14 of the carrier substrate 12 adjacent the cavity 18. As used herein, the phrase “adjacent the cavity” means that an element or component is disposed on the first major surface 14 of the carrier substrate 12 and next to but outside of the cavity 18. The first package contact 22 is electrically connected to a first die pad 24 disposed on the recessed surface 20 via a first conductor 26. The package 10 also includes a second package contact 28 disposed on the first major surface 14 of the carrier substrate 12 adjacent the cavity 18. The second package contact 28 is electrically connected to a second die pad 30 disposed on the recessed surface 20 via a second conductor 32. Further, the package 10 includes a die 34 disposed within the cavity 18 of the carrier substrate 12. The die 34 includes a first die contact 36 disposed on an active surface 38 of the die and a second die contact 40 disposed on a major surface 42 of the die that faces the recessed surface 20 and that is opposed to the active surface. The first die contact 36 is electrically connected to the first die pad 24 and the second die contact 40 is electrically connected to the second die pad 30.

The carrier substrate 12 can include any suitable material or materials, e.g., metallic, polymeric, inorganic, etc. In one or more embodiments, the carrier substrate 12 can include silicon. Further, the carrier substrate 12 can have any suitable dimensions and take any suitable shape or shapes.

The first and second major surfaces 14, 16 of the carrier substrate 12 can take any suitable shape or shapes. Disposed in the first major surface 14 is the cavity 18. The cavity 18 can take any suitable shape or shapes and have any suitable dimensions. Further, the cavity 18 can have any suitable depth 2 from the first major surface 14 of the carrier substrate 12 as measured in a direction orthogonal to the recessed surface 20 of the cavity as shown in FIG. 2. In one or more embodiments, the cavity 20 can have a depth 2 of at least 350 μm and no greater than 500 μm . In one or more embodiments, the cavity depth 2 is great than a height 4 of the die 34 as measured in the direction orthogonal to the

recessed surface 20 as shown in FIG. 2. The height 4 of the die 34 includes a thickness of the second die pad 30 as measured in the direction orthogonal to the recessed surface 20. The die 34 can have any suitable height 4. In one or more embodiments, the die 34 has a height 4 of at least 100 μm and no greater than 200 μm . In one or more embodiments, the cavity depth 2 is equal to the height 4 of the die 34. Further, in one or more embodiments, the cavity depth 2 is less than the height 4 of the die 34.

The recessed surface 20 of the cavity 18 can have any suitable dimensions and take any suitable shape or shapes. In one or more embodiments, the recessed surface 20 can be parallel to the first major surface 14 of the carrier substrate 12. The cavity 18 can also include one or more side walls 40. In one or more embodiments, each sidewall 40 connects the recessed surface 20 of the cavity 18 to the first major surface 14 of the carrier substrate 12. Further, the cavity 18 can include any suitable number of sidewalls 40. As shown in FIG. 1, the cavity 18 includes two side walls 40. In one or more embodiments, the cavity 18 can include four sidewalls 40 as shown, e.g., in FIG. 3 for die carrier package 100. In the embodiment illustrated in FIGS. 1-2, the sidewalls 40 include planar portions that form an angle with the direction orthogonal to the recessed surface 20.

In one or more embodiments, a dielectric layer (not shown) can be disposed on a portion or portions of the recessed surface 20 between the first and second die pads 24, 30 and the carrier substrate. Further, a dielectric layer can also be disposed between the first and second conductors 26, 32 and the carrier substrate 12. Any suitable dielectric layer or layers can be utilized to electrically isolate one or more of the first and second die pads 24, 30 and the first and second conductors 26, 32 from the carrier substrate 12, e.g., silicon oxide, silicon nitride, tetraethyl orthosilicate (TEOS), benzocyclobutene (BCB), polyimide, etc.

The cavity 18 can be formed using any suitable technique or techniques. In one or more embodiments, the cavity 18 can be formed, e.g., by at least one of chemical etching, drilling, polishing, mechanical routing or grinding, plasma etching, molding, etc.

Disposed on the first major surface 14 of the carrier substrate 12 adjacent the cavity 20 is the first package contact 22. The first package contact 22 can include any suitable electrical contact or pad, e.g., one or more of a die pad contact, solder bump, solder ball, gold ball bump, etc. The first package contact 22 can take any suitable shape or shapes and have any suitable dimensions. The first package contact 22 can also include any suitable conductive material or materials. Further, in one or more embodiments, one or more solder bumps (e.g., solder bumps 148 of die carrier package 100 of FIGS. 3-5) can be disposed on and electrically connected to the first package contact 22.

The first package contact 22 can be electrically connected to the first die pad 24 disposed on the recessed surface 20 of the cavity 18 using any suitable technique or techniques. In one or more embodiments, the first conductor 26 electrically connects the first package contact 22 to the first die pad 24. The first conductor 26 can include any suitable conductive material or materials and be disposed in any suitable location. In one or more embodiments, one or more portions of the first conductor 26 can be disposed on at least one of the recessed surface 20 of the cavity 18, the sidewall 40, and the first major surface 14 of the carrier substrate 12. The first conductor 26 can take any suitable shape or shapes and have any suitable dimensions.

The first die pad 24 can be disposed in any suitable location on or in the recessed surface 20 of the cavity 18.

Further, the first die pad **24** can include any suitable conductive material or materials. The first die pad **24** can take any suitable shape or shapes and have any suitable dimensions. Further, the first die pad **24** can be disposed on or in the recessed surface **20** using any suitable technique or techniques, e.g., photolithography, chemical vapor deposition, plasma vapor deposition, sputtering, plating, conductive ink jetting, etc.

The second package contact **28** is also disposed on the first major surface **14** of the carrier substrate **12** adjacent the cavity **18**. All of the design considerations and possibilities regarding the first package contact **22** apply equally to the second package contact **28**. The second package contact **28** is electrically connected to the second die pad **30** that is disposed on the recessed surface **20** of the cavity **18**. Any suitable technique or techniques can be utilized to electrically connect the second package contact **28** to the second die pad **30**. In one or more embodiments, the second conductor **32** electrically connects the second package contact **28** and the second die pad **30**. The second die pad **30** can include any suitable die pad or contact, e.g., first die pad **24**. Further, the second conductor **32** can include any suitable conductor or conductors, e.g., conductor **26**.

In general, the first and second package contacts **22**, **28** can be utilized to electrically connect the package **10** to any suitable device or system. For example, in one or more embodiments, the first and second package contacts **22**, **28** can electrically connect the package **10** to a patterned conductive layer of a system as is further described herein. Any suitable technique or techniques can be utilized to electrically connect the first and second package contacts **22**, **28** to another device or system. Although depicted as include first and second package contacts **22**, **28**, the package **10** can include any suitable number of package contacts.

Disposed within the cavity **18** of the carrier substrate **12** is the die **34**. The die **34** can include any suitable die or device, e.g., at least one of a capacitor, resistor, passive integrated capacitor system, logic circuit, analog circuit, diode, MOSFET, insulated-gate bipolar transistor, thyristor, etc. In one or more embodiments, the die **34** can be a light emitting die. For example, the die **34** can include any electrical circuit component(s) capable of emitting light in response to an applied voltage or current, including, for example, light emitting diodes (LEDs), laser diodes, vertical cavity surface emitting lasers (VCSELs), organic LEDs printed directly on the surface, nano-emitters, etc. Further, the die **34** can be a cluster of one or more components that emit one or more discrete wavelengths or broadband emitters spanning a large range of wavelengths.

Although depicted as including one die **34**, the package **10** can include any suitable number of dies as is further described herein. In one or more embodiments, the die **34** is adapted to emit electromagnetic radiation from its active surface **38**. Although depicted as having one active surface **38**, the die **34** can include two or more active surfaces.

In one or more embodiments, the die **34** can be a packaged light source. In one or more embodiments, the die **34** can include a flip-chip type package. In one or more embodiments, the die **34** can be a bare semiconductor die.

The die **34** can be adapted to emit light of any suitable wavelength or wavelengths. In one or more embodiments, the die **34** can emit at least one of infrared, near-infrared, visible, and UV light. In one or more embodiments, the die **34** can emit visible light having a wavelength of at least 350 nm and no greater than 950 nm. The die **34** can emit any suitable bandwidth of electromagnetic radiation. In one or more embodiments, the die **34** can emit electromagnetic

radiation in a narrow band, e.g., the die is adapted to emit light having an emission bandwidth of no greater than 20 nm, 15 nm, 10 nm, or 5 nm full-width at half-maximum (FWHM). In one or more embodiments, a narrow band emitting active die can be paired with a broadband detector (e.g., detector **216** of FIG. **8**) that is sensitive to most or all of the wavelengths emitted by the die. In one or more embodiments, a narrow-band emitting active die can be paired with a narrow-band detector. Further, in one or more embodiments, a narrow band emitting active die can be paired with two or more broadband detectors. For example, silicon detectors can be sensitive in the visible to near-infrared wavelength ranges (e.g., up to about 1000 nm), but gallium arsenide can be sensitive to longer infrared wavelengths (e.g., greater than 1000 nm). In one or more embodiments, a broadband emitting active die can be utilized with two or more narrow band detectors.

In one or more embodiments, the die **34** can include a broadband emitter that utilizes re-emission of phosphorous materials or combination of broadband FWHM LEDs, e.g., a 680 nm LED with greater than a 50 nm FWHM that spans into the 720 nm wavelength. In such embodiments, a single LED can provide emission at both 680 nm and 720 nm, paired with a detector that can discriminate between these two wavelengths. Similarly, a second broadband FWHM die can be used at 800 nm that also spans 760 nm. In such embodiments, two broadband FWHM dies can span four wavelengths, e.g., 680, 720, 760, and 800 nm.

In one or more embodiments, the die **34** can be adapted to emit electromagnetic radiation in one or more pulses having any suitable pulse width and periodicity. Further, in one or more embodiments, the die **34** may be pulsed in a sequential manner.

Further, the die **34** can have any suitable cone angle of emission. As used herein, the term "cone angle" refers to solid angle relative to a normal to the active surface **38** of the die. In one or more embodiments, the die **34** can have a cone angle of no greater than 90 degrees, 80 degrees, 70 degrees, 60 degrees, 50 degrees, 40 degrees, 30 degrees, 20 degrees, 10 degrees, or 5 degrees.

The die **34** includes at least one first die contact **36** disposed on the active surface **38** of the die. The first die contact **36** can include any suitable contact or pad that can provide an electrical connection to the die **34**. In one or more embodiments, the first die contact **36** can include a conductive pillar (or a solder bump with a barrier metal disposed over a die pad) that can be disposed on the active surface **38** of the die **34** using any suitable technique or techniques, e.g., electroplating, etching, photo etching, solder printing, solder jetting, ball drop, etc. Any suitable solder bumps can be disposed on the first die contact **36**. The first die contact **36** can have any suitable dimensions and can be disposed in any suitable arrangement or array on the active surface **38** of the die **34**. Further, the first die contact **36** can include any suitable conductive material or materials.

The die **34** also includes a second die contact **40** disposed on the major surface **42** of the die that faces the recessed surface **20**. Although illustrated as including one second die contact **40**, the die **34** can include any suitable number of die contacts disposed on the major surface **42**. The second die contact **40** can include any suitable contact or conductive pad described herein regarding first die contact **36**. Further, the second die contact **40** can have any suitable dimensions and be disposed in any suitable arrangement or array on the major surface **42** of the die **34**. Further, the second die contact **40** can take any suitable shape or shapes.

As mentioned herein, the die **34** is adapted to emit electromagnetic radiation from any portion or portions of its active surface **38**. In one or more embodiments, the die **34** can include one or more apertures **44** through which electromagnetic radiation is emitted. The aperture **44** can be formed using any suitable technique or techniques. In one or more embodiments, a masking layer or layers can be disposed on the active surface **38** of the die **34**, and the aperture **44** can be formed in the masking layer (not shown) using any suitable technique or techniques. The masking layer can include any suitable number of layers. Further, the masking layer can include any suitable material or materials, e.g., polymeric, metallic, inorganic materials, and combinations thereof.

The first die contact **36** of the die **34** can be electrically connected to the first die pad **24** using any suitable technique or techniques. In the embodiment illustrated in FIGS. 1-2, the first die contact **36** can be wire-bonded to the first die pad **24** by a wire **46** that is disposed within the cavity **18**. In one or more embodiments, the die **34** and the wire **46** are disposed below a plane defined by the first major surface **14** of the carrier substrate **12**. In one or more embodiments, the die **34** can include a flip-chip die that includes first and second die contacts **36**, **40** disposed on the major surface **42** with no contacts disposed on the active surface **38**.

Further, the second die contact **40** is electrically connected to the second die pad **30** using any suitable technique or techniques, e.g., thermocompression bonding, eutectic bonding, sintering, etc. In one or more embodiments, the second die contact **40** is disposed on the second die pad **30**. In one or more embodiments, a conductive adhesive or solder can be disposed between the second die contact **40** and the second die pad **30** such that the die **34** remains disposed on the second die contact.

As mentioned herein, the first and second package contacts **22**, **28**, the first and second conductors, **26**, **32**, and the first and second die pads **24**, **30** can each include any suitable conductive material or materials. In one or more embodiments, at least one of the first and second package contacts **22**, **28**, the first and second conductors, **26**, **32**, and the first and second die pads **24**, **30**, can include one or more metal layers. For example, in one or more embodiments, at least one of the first and second package contacts **22**, **28**, the first and second conductors, **26**, **32**, and the first and second die pads **24**, **30**, and can include a first metal layer and a second metal layer disposed on the first metal layer such that the second metal layer is electrically connected to the first metal layer. The first metal layer can include any suitable conductive material or materials, e.g., aluminum (Al), titanium (Ti), nickel-vanadium (NiV), etc. Further, the second metal layer can include any suitable conductive material or materials, e.g., the same materials described herein regarding the first metal layer. In one or more embodiments, the first metal layer includes the same material or materials as the material or materials of the second metal layer. In one or more embodiments, the second metal layer includes a material or materials that are different from the materials utilized to form the first metal layer.

Although not shown, the package **10** can include an encapsulant disposed in the cavity **18** over one or more portions of the die **34**. In one or more embodiments, this encapsulant can completely encapsulate the die **34**. In one or more embodiments, the encapsulant can also encapsulate the wire **46** that is utilized to electrically connect the first die contact **36** to the first die pad **24**. Any suitable encapsulant or encapsulants can be utilized, e.g., a thermosetting epoxy resin that includes inorganic filler particles, an (reflowable)

epoxy film that is laminated to the die in wafer form to fill the cavities level to the surface of the wafer **34** or over the top of the cavity, silicone (e.g., an optically-clear encapsulant that is typically used in electronics assembly), etc.

The various embodiments of die carrier packages described herein can include any suitable number of dies disposed in any suitable relationship on a carrier substrate. For example, FIGS. 3-5 are various views of another embodiment of a die carrier package **100**. All of the design considerations and possibilities regarding the die carrier package **10** of FIGS. 1-2 apply equally to the die carrier package **100** of FIGS. 3-5.

One difference between package **100** of FIGS. 3-5 and package **10** of FIGS. 1-2 is that the package **100** includes two or more dies (collectively referred to as dies **134**) disposed within cavity **118** of carrier substrate **112**. The package **100** can include any suitable number of dies **134**, e.g., 1, 2, 3, 4, 5, 6, or more dies disposed on the carrier substrate **112**. In general, the number of active dies and corresponding emission wavelengths utilized in the packages described herein can be selected according to the requirements of a particular application and will depend on the physiological condition or conditions being monitored.

As shown in FIGS. 3-5, the package **100** includes five dies **134** disposed within the cavity **118**. Each die **134** includes a first die contact **136** (FIG. 5) disposed on an active surface **138** of the die and a second die contact **140** disposed on a major surface **142** of the die that faces a recessed surface **120** of the cavity and that is opposed to its active surface. Each first die contact **136** of each die **134** is electrically connected to a common first die pad **124**, and each second die contact **140** is electrically connected to a second die pad **140** using any suitable technique or techniques. As shown in FIG. 5, the first die contact **136** of each die **134** is wire bonded to the first die pad **124** by a wire **146**. As is also shown in FIG. 5, each second die contact **140** is electrically connected to the second die pad **130** by being disposed on the second die pad.

The first die pad **124** can be electrically connected to a first package contact **122** using any suitable technique or techniques. In the embodiment illustrated in FIGS. 3-5, the first die pad **124** is electrically connected to the first package contact **122** by conductor **126**. Further, each second die pad **130** can be electrically connected to a second package contact **128** using any suitable technique or techniques. In one or more embodiments, each second die pad **130** is electrically connected to a second package contact **128** by a conductor **132**. Further, one or more of the second package contacts **128** can include solder bumps **148** that are electrically connected to the second package contact using any suitable technique or techniques. Solder bumps **148** can be utilized to electrically connect the die carrier package **100** to any suitable device or system as is further described herein.

As mentioned herein, the die carrier package **100** of FIGS. 3-5 includes two or more dies **134** disposed in any suitable arrangement on the carrier substrate **112**. Specifically, the package **100** includes five dies **134A-E** disposed within the cavity **118** of the carrier substrate **112**. As shown in FIG. 5, first die **134A** is disposed within the cavity **118** of the carrier substrate **112** and includes a first die contact **136** disposed on an active surface **138** of the die and a second die contact **140** disposed on a major surface **142** of the die that faces the recessed surface and that is opposed to the active surface. The first die contact **136** is electrically connected to the first die pad **124** by wire **146**, and the second die contact **140** is electrically connected to the second die pad **130**. Similarly, second, third, fourth, and fifth dies **134B-E** are electrically connected to the first die pad **124** and respective second die

pads **130** using any suitable technique or techniques. Each of the second die pads for the respective second, third, fourth, and fifth dies **134B-E** are electrically connected to second package contacts **128** using any suitable technique or techniques.

Each of the active dies **134** are adapted to emit electromagnetic radiation from one or more surfaces of each die. For example, in one or more embodiments, active die **134A** can be adapted to emit electromagnetic radiation that includes a first wavelength or wavelength band, active die **134B** can be adapted to emit electromagnetic radiation that includes a second wavelength or wavelength band, third active die **134C** can be adapted to emit electromagnetic radiation that includes a third wavelength or wavelength band, fourth active die **134D** can be adapted to emit electromagnetic radiation that includes a fourth wavelength or wavelength band, and fifth active die **134E** can be adapted to emit electromagnetic radiation from a top surface **122** that includes a fifth wavelength or wavelength band.

Another difference between the package **100** of FIGS. **3-5** and package **10** of FIGS. **1-2** is that the cavity **118** includes four sidewalls **140** that each connect the recessed surface **120** of the cavity to the first major surface **114** of the carrier substrate **112**. The sidewalls **140** can take any suitable shape or shapes and have any suitable dimensions. Further, such sidewalls **140** can be formed using any suitable technique or techniques. In one or more embodiments, a metal layer or layers can be disposed on one or more portions of the sidewalls **140** to provide reflective structures. Although illustrated as including for sidewalls **140**, the cavity **118** of the package **100** can include any suitable number of sidewalls.

In one or more embodiments, the dimensions of the cavity, the die, and the die contacts can be selected such that the first die contact of the die is disposed above the cavity and can be electrically connected directly to one or more conductors on a substrate without the need for a first die pad and first package contact. For example, FIG. **12** is a schematic cross-section view of another embodiment of a die carrier package **400**. All of the design considerations and possibilities regarding the die carrier package **10** of FIGS. **1-2** and the die carrier package **100** of FIGS. **3-5** apply equally to the die carrier package **400** of FIG. **12**. One difference between package **400** and package **10** is that a height **404** of die **434**, a depth **402** of cavity **418**, and dimensions of first die contacts **436** are selected such that the first die contacts are disposed above a plane **406** defined by a first major surface **414** of carrier substrate **412**. As a result, the first die contacts **436** and package contacts **428** (which are electrically connected to second die contact **440** via a second die pad (not shown)) can be directly connected to one or more conductors disposed on a substrate (e.g., conductors **226** disposed on a first major surface **210** of substrate **204** of FIG. **10**). Unlike first die contacts **36** of die **34** of FIG. **1**, the first die contacts **436** of die **434** are not electrically connected to a first die pad that is in turn electrically connected to one or more package contacts.

The various embodiments of integrated circuit packages described herein can be utilized in any suitable device or system. For example, FIGS. **6-10** are various schematic views of one embodiment of a hermetically-sealed system **200**. The system **200** includes a housing **202** and a substrate **204**. The housing **202** includes an inner surface **206** and an outer surface **208**. The substrate **204** can be a non-conductive substrate and includes a first major surface **210** and a second major surface **212**. The system **200** can also include one or more electronic devices **214** disposed within the

housing **202**. For example, the electronic devices **214** can include the integrated circuit package **10** of FIGS. **1-2** or integrated circuit package **100** of FIGS. **3-5**. Although depicted as including integrated circuit package **100**, the system **200** can include any suitable integrated circuit package. In one or more embodiments, the integrated circuit package **100** can be disposed on the first major surface **210** of the substrate **204**. The integrated circuit package **100** can be adapted to emit electromagnetic radiation through the first and second major surfaces **210**, **212** of the substrate **204**.

The electronic devices **214** can further include a detector **216** (FIG. **8**). In one or more embodiments, the detector **216** can be disposed on the first major surface **210** of the substrate **204**. The detector **216** can be adapted to detect the electromagnetic radiation emitted by the integrated circuit package **100** that is transmitted through the substrate **204** and reflected by an object or objects back through the substrate. Together, the integrated circuit package **100** and the detector **216** can, in one or more embodiments, provide an optical sensor.

The package **200** also includes a power source **218** that is disposed at least partially within the housing **202**. In one or more embodiments, the power source **218** can be disposed within a cavity **220** of the housing **202**. The power source **218** can include any suitable power source or sources as is further described herein. Further, the power source can be electrically connected to the electronic devices **214** using any suitable technique or techniques. For example, in one or more embodiments, the power source **218** can include one or more power sources contacts **234**, **236** that can be electrically connected to one or more device contacts **236** when the substrate **204** is sealed to the housing **202** using any suitable technique or techniques.

The substrate **204** can be sealed to the housing **202** using any suitable techniques or techniques. In one or more embodiments, the substrate **204** can be hermetically sealed to the housing **202**. In one or more embodiments, the substrate **204** can be hermetically sealed to the housing **202** by a laser bond.

The housing **202** can include any suitable material or materials, e.g., metallic, polymeric, ceramic, or inorganic materials. In one or more embodiments, the housing **202** can include at least one of glass, quartz, silica, sapphire, silicon carbide, titanium, and diamond. In one or more embodiments, the housing **202** can include at least one of copper, silver, titanium, niobium, zirconium, tantalum, stainless steel, platinum, and iridium. The housing **202** can include the same material or combination of materials as the substrate **204**. In one or more embodiments, the housing **202** can include one or more materials that are different from the material or materials of the substrate **204**. Further, in one or more embodiments, the housing **202** can include biocompatible materials such that the system **200** can be implanted within a patient's body. For example, one or more coatings or layers can be disposed on the outer surface **208** of the housing **202** that provide biocompatibility. In one or more embodiments, the housing **202** can be electrically conductive to provide a ground electrode for the system **200** as is known in the art. In one or more embodiments, the housing **202** can be nonconductive.

Further, the housing **202** can take any suitable shape or shapes and can have any suitable dimensions. In one or more embodiments, the housing **202** takes a shape that forms the cavity **220** that can accommodate the power source **218** (including active material and power source electronics) and one or more electronic devices **214** as is further described herein.

Sealed to the housing **202** is the substrate **204**. In one or more embodiments, the substrate **204** can be a non-conductive or insulative substrate such that the electronic devices **214** (including integrated circuit package **100** and detector **216**), optional external electrodes **222**, **224** and any conductors or other devices disposed on the substrate can be electrically isolated if desired. The substrate **204** can include any suitable material or materials. In one or more embodiments, the substrate **204** can include at least one of glass, quartz, silica, sapphire, silicon carbide, diamond, and gallium nitride. As with the housing **202**, the substrate **204** can include a biocompatible material. For example, the substrate **204** can include one or more coatings or layers that can provide biocompatibility.

In one or more embodiments, the substrate **204** can be a transparent substrate. As used herein, the phrase “transparent substrate” refers to a substrate that can transmit a given percentage of electromagnetic radiation incident thereon during use of laser bonding techniques described herein to preferentially heat only an outer surface of the substrate (e.g., first major surface **210** or second major surface **212** of substrate **204**), and not an inner bulk of the substrate, and thereby create a bond that has a relatively greater strength than the bulk strength of the substrate. Further, the transparent substrate **204** can transmit light emitted by the integrated circuit package **100** having any suitable wavelength or combinations of wavelengths. The substrate **204** can be substantially transparent at a desired wavelength or range of wavelengths. As used herein, the phrase “substantially transparent” means that the substrate **204** transmits greater than 50% of light incident on the substrate for a selected wavelength or range of wavelengths, assuming no reflection at the air-substrate boundaries. In one or more embodiments, the substrate **204** can be substantially transmissive to light having a wavelength of at least 200 nm. In one or more embodiments, the substrate **30** can be substantially transmissive to light having a wavelength of greater than 10,000 nm. In one or more embodiments, the substrate **204** can be substantially transmissive to light having a wavelength in a range of 200 nm to 10,000 nm. In one or more embodiments, the substrate **204** can be substantially transmissive to at least one of UV light, visible light, and IR light.

In one or more embodiments, at least a portion of the substrate **204** can be transparent such that the detector **216** disposed on the first major surface **210** of the substrate can detect one or more external signals, e.g., from a patient, when the system **200** is disposed within the patient. In one or more embodiments, the at least a portion of the substrate **204** can be sufficiently transparent to enable transmission of all, or a sufficient magnitude, of the electromagnetic radiation that is incident on the substrate for reception by the detector **216** such that the received electromagnetic radiation can be processed to detect the external signal. In one or more embodiments, the substrate **204** can be opaque, and a through-hole can be formed through the substrate and filled with a transparent hermetic material such as glass to provide a transparent portion of the substrate.

The substrate **204** can include any suitable dimensions, e.g., thicknesses. Further, the substrate **204** can take any suitable shape or combinations of shapes. In one or more embodiments, the substrate **204** can take a shape or combination of shapes that is complementary to a shape of the housing **202** such that the substrate can be sealed to the housing and provide a low-profile shape for the system **200**. Further, the substrate **204** can be a single, unitary substrate or multiple substrates joined together.

Disposed on the first major surface **210** of the substrate **204** are the electronic devices **214**. Although depicted as being disposed on the first major surface **210**, one or more electronic devices **214** can be disposed on the second major surface **212**, or one or more electronic devices can be disposed on both the first and second major surfaces. In one or more embodiments, one or more electronic devices **214** can be disposed within the housing **204** and not connected to the substrate **202**. The electronic devices **214** can include any suitable circuit or component, e.g., capacitors, transistors, integrated circuits, including controllers and multiplexers, sensors, light sources, detectors, accelerometers, signal processors, etc.

Further, any suitable technique or techniques can be utilized to dispose one or more electronic devices **214** on the substrate **204** and/or within the cavity **220** of the housing **202**. In one or more embodiments, one or more electronic devices **214** can be formed on the first major surface **210** of the substrate **204**. In one or more embodiments, one or more devices **214** can be formed separately and then connected to the first major surface **210**. Any suitable technique or techniques can be utilized to connect the electronic devices **214** to the substrate **204**, e.g., a bond can be formed between the electronic device and the first major surface **210** of the substrate. The electronic devices **214** can include one or more integrated circuit packages **10** each having any suitable number of active dies.

Although depicted as including a single integrated circuit package **100**, the system **200** can include any suitable number of integrated circuit packages. The integrated circuit package **100** can be disposed in any suitable location within the housing **202** of the system **200**. In one or more embodiments, the integrated circuit package **100** is disposed adjacent the first major surface **210** of the substrate **204**. As used herein, the term “adjacent” means that an element or component is disposed closer to the first major surface **210** of the substrate **204** than to the power source **218** disposed within the housing **202**. In one or more embodiments, the integrated circuit package **100** can be disposed on the first major surface **210** of the substrate **204** as shown in FIG. **10** using any suitable technique or techniques. In such embodiments, one or more first and second package contacts **122**, **128** of the package **100** can be electrically connected to one or more conductors **226** (FIG. **8**) disposed on the first major surface **210** of the substrate **204** using any suitable technique or techniques, e.g., bump bonding, solder reflow, conventional wire bonding, laser ribbon bonding, conductive epoxy bonding, etc.

The integrated circuit package **100** can be electrically connected to one or more electronic devices **214** disposed on one or both of the first major surface **210** and second major surface **212** of the substrate **204** or within the housing **202** using any suitable technique or techniques. For example, the integrated circuit package **100** can be electrically connected to the conductor **226** (FIG. **8**) that is disposed on or within the substrate **204**. The conductor **226** can electrically connect the integrated circuit package **100** to a controller **228** of the electronic devices **214**. In one or more embodiments, a patterned conductive layer (not shown) can be disposed on the first major surface **210** of the substrate **204**. In such embodiments, the first and second package contacts **122**, **128** of the integrated circuit package **100** can be electrically connected to the patterned conductive layer disposed on the first major surface **210** of the substrate **204** using any suitable technique or techniques.

The system **200** also includes the detector **216**. The detector **216** includes a detecting surface **230** (FIG. **10**). The

detector **216** can include any suitable detector that is adapted to detect electromagnetic radiation emitted by the integrated circuit package **10**, e.g., one or more photodiodes, photoreistors or light dependent resistors, phototransistors, photo-voltaic cells, charge-coupled devices, avalanche detectors, etc. In one or more embodiments, the integrated circuit package **100** can also be utilized as a detector. Although depicted as including a single detector **216**, the system **200** can include any suitable number of detectors. For example, the system **200** can include a second detector (not shown) disposed on the first major surface **210** of the substrate **204**. In one or more embodiments, the detector **216** can be adapted to detected electromagnetic radiation emitted, e.g., by the first die **134A** of the integrated circuit package **100** and the second detector can be adapted to detected electromagnetic radiation emitted, e.g., by the second die **134B** of the integrated circuit package.

The detector **216** can be adapted to detect any desired wavelength or wavelengths of electromagnetic radiation. In one or more embodiments, the detector **216** can detect one or more of infrared, near-infrared, visible, and UV light. In one or more embodiments, the detector **216** can detect visible light having a wavelength of at least 350 nm and no greater than 950 nm.

The detector **216** can be disposed in any suitable location within the housing **202** of the system **200** or outside of the housing (e.g., on the second major surface **212** of the substrate **204**). In one or more embodiments, the detector **216** is disposed adjacent the first major surface **210** of the substrate **204**. In one or more embodiments, the detector **216** can be disposed on the first major surface **210** of the substrate **204** using any suitable technique or techniques as shown in FIG. **10**. In such embodiments, the detecting surface **230** can be connected to the first major surface **210** of the substrate **204** using any suitable technique. For example, in one or more embodiments, the detecting surface **230** can be disposed on the first major surface **210** of the substrate **204** using an optical coupling layer. Any suitable coupling layer can be utilized. In one or more embodiments, the optical coupling layer can include an optical adhesive. In one or more embodiments, the detector **216** can be electrically connected to an electrode disposed on a carrier. The detector **216** can also be wired bonded from the integrated circuit package **100** to a second electrode on the carrier. The carrier can be designed such that the two electrodes are in a single plane. the carrier can then be bump-bonded to one or more conductors (e.g., conductor **232**) disposed on the substrate **204**.

The detector **216** can be electrically connected to one or more of the other electronic devices **214** disposed on one or both of the first major surface **210** and second major surface **212** of the substrate **204** or within the housing **202** using any suitable technique or techniques. For example, the detector **216** can be electrically connected to the conductor **232** that is disposed on or within the substrate **204**. In one or more embodiments, the conductor **232** can electrically connect the detector **218** to the controller **228** of the electronic devices **214**. Any suitable technique or techniques can be utilized to electrically connect the detector **218** to the conductor **232**.

The various embodiments of systems described herein can be utilized to determine one or more physiological conditions. Any suitable physiological condition can be determined, e.g., heart rate, arterial blood oxygen level (SpO₂), blood flow, fluid volume (e.g., edema), tissue oxygen saturation (StO₂), perfusion index (PI), Total Hemoglobin/Hematocrit, Tissue Hemoglobin Concentration Index (THI), venous oxygen saturation (SvO₂), ambient light level within

a patient, respiration rate, optically interrogated biochemical sensors (e.g., fluorescent or other coatings and materials in contact with tissue), pulse wave velocity (e.g., pulse transit time), etc.

Further, the various embodiments of integrated circuit packages described herein can be manufactured using any suitable technique or techniques. For example, FIGS. **11A-L** are various cross-section views of one method **300** of forming integrated circuit package **100**. Although described in reference to integrated circuit package **100** of FIGS. **3-5**, the method **300** can be utilized to form any suitable integrated circuit package.

As shown in FIG. **11A**, an insulative layer **302** can be disposed on a carrier substrate wafer **304** using any suitable technique or techniques. The insulative layer **302** can include any suitable material or materials, e.g., silicon dioxide, organic dielectric materials, etc. A photoresist layer **306** can be disposed on the insulative layer **302** using any suitable technique or techniques as shown in FIG. **11B**. The photoresist layer **306** can include any suitable material or materials. Further, the photoresist layer **306** can be patterned in any suitable pattern using any suitable technique or techniques.

As shown in FIG. **11C**, the insulative layer **302** can be etched through the patterned photoresist layer **306** using any suitable technique or techniques. Following etching of the thermal insulative layer **302**, the carrier substrate wafer **304** can be etched using any suitable technique or techniques to form cavities **118** in the carrier substrate wafer as shown in FIG. **11D**. In one or more embodiments, a cavity depth of each of the cavities **118** can be of sufficient dimensions to contain the die **134** and wires **146** without extending through a plane of a major surface **305** of the carrier substrate wafer **304**. In FIG. **11E**, the thermal insulative layer **302** is removed from the carrier substrate wafer **304** using any suitable technique or techniques.

A second insulative layer **308** can be disposed on one or more portions of the carrier substrate wafer **304** as shown in FIG. **11F** using any suitable technique or techniques. A metal layer **310** can be disposed on one or more portions of the second insulative layer **308** using any suitable technique or techniques as shown in FIG. **11G**. In one or more embodiments, the metal layer **310** can be sputtered onto the second insulative layer **308**. Any suitable conductive material or materials can be utilized for conductive material **310**, e.g., aluminum, silver, copper, gold, etc.

The metal layer **310** can be patterned as shown in FIG. **11H** to provide a patterned conductive layer **312** on the recessed surface **118** of each cavity **118** and the major surface **305** of the carrier substrate wafer **304** using any suitable technique or techniques. Although not shown for clarity, one or more portions of the second insulative layer **308** can remain disposed between the patterned conductive layer **312** and the carrier substrate wafer **304**. The patterned conductive layer **312** includes first and second package contacts **122**, **128** disposed on the first major surface **114** of each carrier substrate **112** adjacent the cavity **118** and first and second die pads **124**, **130** (FIG. **5**) disposed on the recessed surface **120** of the cavity. As is further shown in FIG. **5**, the first package contact **122** is electrically connected to the first die pad **124** by the first conductor **126**, and the second package contact **128** is electrically connected to the second die pad **130** by the second conductor **132**.

In one or more embodiments, the conductive material **310** that is utilized to form the patterned conductive layer **312** can include two or more metal layers. For example, in one or more embodiments, the conductive material **310** can

include a first metal layer of titanium, a second metal layer of nickel vanadium, and a third metal layer of gold. In one or more embodiments, the patterned conductive layer **312** can be formed by disposing a first metal layer on at least a portion of the recessed surface **120** of each cavity **118** and the first major surface **114** of each carrier substrate **112**. At least a portion of the first metal layer can be patterned using any suitable technique or techniques. A dielectric layer can be disposed on the first metal layer, and a second metal layer can then be disposed on the dielectric layer and the patterned first metal layer, and at least a portion of the second metal layer can be patterned such that the patterned portion of the first metal layer is registered with the patterned portion of the second metal layer.

In one or more embodiments, one or more solder bumps **148** can be disposed on one or both of the first and second package contacts **122**, **128** of each carrier substrate **112** using any suitable technique or techniques as shown in FIG. **11I**. Any suitable solder bumps **148** can be utilized. In one or more embodiments, the solder bumps **148** are adapted to electrically connect the individual die carrier packages **100** to a device or system as is further described herein.

As shown in FIG. **11J**, one or more dies **134** can be disposed within each cavity **118** that have been formed in the die carrier substrate **304** using any suitable technique or techniques, e.g., pick and place, etc. Further, any suitable technique or techniques can be utilized to attach the dies **134** to the said second die pad **130** of each cavity **118**. Further, in one or more embodiments, the first die contact **136** (FIG. **5**) of each die **134** can be electrically connected to the first die pad **124** using any suitable technique or techniques, e.g., by wire **146** as shown in FIG. **11J**. The second die contact **140** (FIG. **5**) can be electrically connected to the second die pad **130** of each cavity **118** using any suitable technique or techniques.

As shown in FIG. **11K**, each cavity **118** can be at least partially filled with an encapsulant **314** using any suitable technique or techniques. Further, any suitable encapsulant can be utilized to encapsulate one or more dies **134** disposed in each cavity **118** of the die carrier substrate wafer **304**, e.g., a UV curable epoxy, etc. In one or more embodiments, the encapsulant **314** can be planarized using any suitable technique or techniques. Further, shown in FIG. **11L**, the carrier substrate wafer **304** can be singulated using any suitable technique or techniques to provide individual die carrier packages **100**.

It should be understood that various aspects disclosed herein may be combined in different combinations than the combinations specifically presented in the description and accompanying drawings. It should also be understood that, depending on the example, certain acts or events of any of the processes or methods described herein may be performed in a different sequence, may be added, merged, or left out altogether (e.g., all described acts or events may not be necessary to carry out the techniques). In addition, while certain aspects of this disclosure are described as being performed by a single module or unit for purposes of clarity, it should be understood that the techniques of this disclosure may be performed by a combination of units or modules associated with, for example, a medical device.

In one or more examples, the described techniques may be implemented in hardware, software, firmware, or any combination thereof. If implemented in software, the functions may be stored as one or more instructions or code on a computer-readable medium and executed by a hardware-based processing unit. Computer-readable media may include computer-readable storage media, which corre-

sponds to a tangible medium such as data storage media (e.g., RAM, ROM, EEPROM, flash memory, or any other medium that can be used to store desired program code in the form of instructions or data structures and that can be accessed by a computer).

Instructions may be executed by one or more processors, such as one or more digital signal processors (DSPs), general purpose microprocessors, application specific integrated circuits (ASICs), field programmable logic arrays (FPGAs), or other equivalent integrated or discrete logic circuitry. Accordingly, the term "processor" as used herein may refer to any of the foregoing structure or any other physical structure suitable for implementation of the described techniques. Also, the techniques could be fully implemented in one or more circuits or logic elements.

All references and publications cited herein are expressly incorporated herein by reference in their entirety into this disclosure, except to the extent they may directly contradict this disclosure. Illustrative embodiments of this disclosure are discussed and reference has been made to possible variations within the scope of this disclosure. These and other variations and modifications in the disclosure will be apparent to those skilled in the art without departing from the scope of the disclosure, and it should be understood that this disclosure is not limited to the illustrative embodiments set forth herein. Accordingly, the disclosure is to be limited only by the claims provided below.

What is claimed is:

1. A die carrier package, comprising:

a carrier substrate comprising a first major surface, a second major surface, and a cavity disposed in the first major surface, wherein the cavity comprises a recessed surface;

a first package contact disposed on the first major surface of the carrier substrate adjacent the cavity and electrically connected to a first die pad disposed on the recessed surface via a first conductor;

a second package contact disposed on the first major surface of the carrier substrate adjacent the cavity and electrically connected to a second die pad disposed on the recessed surface via a second conductor; and

a die disposed within the cavity of the carrier substrate, and comprising a first die contact disposed on an active surface of the die and a second die contact disposed on a major surface of the die that faces the recessed surface and that is opposed to the active surface, wherein the first die contact is electrically connected to the first die pad and the second die contact is electrically connected to the second die pad, wherein the die is adapted to emit electromagnetic radiation from its active surface.

2. The package of claim 1, wherein the second die contact is disposed on the second die pad.

3. The package of claim 1, wherein the first die contact is wire-bonded to the first die pad by a wire that is disposed within the cavity, wherein the die and the wire are disposed below a plane defined by the first major surface of the carrier substrate.

4. The package of claim 1, wherein the die has a height measured in a direction orthogonal to the recessed surface and the cavity has a depth from the first major surface of the carrier substrate measured in a direction orthogonal to the recessed surface, wherein the cavity depth is greater than the height of the die.

5. The package of claim 1, further comprising solder bumps disposed on and electrically connected to each of the first and second package contacts.

19

6. The package of claim 1, further comprising a dielectric layer disposed on a portion of the recessed surface between the first and second die pads and the carrier substrate.

7. The package of claim 6, wherein the dielectric layer is further disposed between the first and second conductors and the carrier substrate. 5

8. The package of claim 1, wherein the cavity further comprises a sidewall that connects the recessed surface of the cavity to the first major surface of the carrier substrate.

9. The package of claim 1, wherein at least one of the first and second conductors, the first and second die pads, and the first and second package contacts comprises first and second metal layers. 10

10. The package of claim 9, wherein the first metal layer comprises at least one of Al, Cu, Ag, and Au. 15

11. The package of claim 10, wherein the second metal layer comprises at least one of Ti, NiV, and Au.

12. The package of claim 1, further comprising an encapsulant disposed in the cavity over the die.

13. The package of claim 1, further comprising a second die disposed within the cavity of the carrier substrate and comprising a first die contact disposed on an active surface of the second die and a second die contact disposed on a major surface of the second die that faces the recessed surface and that is opposed to the active surface, wherein the first die contact is electrically connected to the first die pad and the second die contact is electrically connected to a third die pad disposed on the recessed surface, wherein the third die pad is electrically connected to a third package contact disposed on the first major surface of the carrier substrate adjacent the cavity, wherein the third package contact is electrically connected to the third die pad by a third conductor. 20 25 30

14. A hermetically-sealed system, comprising:

a housing comprising an inner surface and an outer surface; 35

20

a device substrate hermetically sealed to the housing and comprising a first major surface and a second major surface;

a die carrier package disposed on the first major surface of the device substrate and comprising a die that comprises an active surface facing the device substrate, wherein the die is adapted to emit light through the first and second major surfaces of the device substrate, wherein the die is disposed within a cavity of a carrier substrate of the package, wherein the die further comprises a first die contact disposed on the active surface of the die and a second die contact disposed on a major surface of the die that faces a recessed surface of the cavity of the die carrier package and that is opposed to the active surface, wherein the first die contact is electrically connected to a first package contact disposed on a first major surface of the carrier substrate of the package adjacent the cavity and the second die contact is electrically connected to a second package contact disposed on the first major surface of the carrier substrate of the package adjacent the cavity, wherein the first and second package contacts are disposed between the first major surface of the carrier substrate and the first and second major surfaces of the device substrate; and

a detector disposed on the first major surface of the device substrate and comprising a detecting surface, wherein the detector is adapted to detect at least a portion of the light emitted by the die.

15. The system of claim 14, wherein the first and second package contacts are electrically connected to a patterned conductive layer disposed on the first major surface of the device substrate.

* * * * *