

US010991909B2

(12) **United States Patent**
Kim et al.

(10) **Patent No.:** **US 10,991,909 B2**
(45) **Date of Patent:** **Apr. 27, 2021**

(54) **ORGANIC LIGHT EMITTING DISPLAY DEVICE AND METHOD OF MANUFACTURING THE SAME**

(58) **Field of Classification Search**
None
See application file for complete search history.

(71) Applicant: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si (KR)

(56) **References Cited**

(72) Inventors: **Seol Kim**, Seongnam-si (KR); **Eunah Kim**, Seoul (KR); **Sungchan Jo**, Seoul (KR)

U.S. PATENT DOCUMENTS

9,520,577 B2 12/2016 Sato et al.
9,818,807 B2 11/2017 Park
(Continued)

(73) Assignee: **SAMSUNG DISPLAY CO., LTD.**,
Yongin-si (KR)

FOREIGN PATENT DOCUMENTS

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 24 days.

KR 1020160037496 4/2016
KR 1020160087982 7/2016
(Continued)

(21) Appl. No.: **16/246,865**

Primary Examiner — Michelle Mandala
(74) *Attorney, Agent, or Firm* — F. Chau & Associates, LLC

(22) Filed: **Jan. 14, 2019**

(65) **Prior Publication Data**

US 2019/0229289 A1 Jul. 25, 2019

(30) **Foreign Application Priority Data**

Jan. 23, 2018 (KR) 10-2018-0008287

(51) **Int. Cl.**

H01L 51/52 (2006.01)
H01L 27/32 (2006.01)

(Continued)


(52) **U.S. Cl.**

CPC **H01L 51/5253** (2013.01); **H01L 27/3244** (2013.01); **H01L 51/0097** (2013.01); **H01L 51/5256** (2013.01); **H01L 51/56** (2013.01); **H01L 2227/323** (2013.01); **H01L 2251/301** (2013.01); **H01L 2251/5338** (2013.01); **H01L 2251/558** (2013.01)

(57) **ABSTRACT**

An organic light emitting display device includes: a thin film transistor disposed in a display area of a substrate; an insulating layer disposed on the thin film transistor; an organic light emitting element disposed on the insulating layer and connected to the thin film transistor; and an encapsulation layer covering the organic light emitting element. The encapsulation layer includes: a first inorganic layer extending from the organic light emitting element to a non-display area; an organic layer disposed on the first inorganic layer; a second inorganic layer extending from the organic layer to the non-display area; and an organic pattern layer disposed between the first inorganic layer and the second inorganic layer and spaced apart from the organic layer in the non-display area. At least a part of the first inorganic layer and at least a part of the second inorganic layer may contact each other in the non-display area.

17 Claims, 7 Drawing Sheets



- (51) **Int. Cl.**
H01L 51/00 (2006.01)
H01L 51/56 (2006.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

9,911,943	B2	3/2018	Han	
10,326,110	B2 *	6/2019	Kwon	H01L 51/5256
2010/0156779	A1 *	6/2010	Park	G02F 1/167 345/107
2016/0064690	A1 *	3/2016	Kook	H01L 51/5256 257/40
2016/0079564	A1 *	3/2016	Shim	H01L 27/3246 257/40
2017/0040347	A1	2/2017	Seo et al.	
2017/0062534	A1	3/2017	Jiang et al.	
2017/0098798	A1	4/2017	Park et al.	
2018/0090714	A1	3/2018	Kim et al.	

FOREIGN PATENT DOCUMENTS

KR	101661809	9/2016	
KR	1020160150255	12/2016	
KR	1020170017057	2/2017	
KR	1020170026085	3/2017	
KR	1020170041339	4/2017	

* cited by examiner

FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6





FIG. 8



**ORGANIC LIGHT EMITTING DISPLAY
DEVICE AND METHOD OF
MANUFACTURING THE SAME**

CROSS-REFERENCE TO RELATED
APPLICATION

This application claims priority under 35 U.S.C. § 119 to Korean Patent Application No. 10-2018-0008287, filed on Jan. 23, 2018, in the Korean Intellectual Property Office (KIPO), the disclosure of which is incorporated by reference herein in its entirety.

TECHNICAL FIELD

Exemplary embodiments of the present invention relate to an organic light emitting display device, and a method of manufacturing the same.

DISCUSSION OF RELATED ART

Display device is an apparatus capable of providing a user with visual information such as an image or a text. Currently, display devices are being manufactured into various forms in order to generate various types of images and texts.

Organic light emitting diode (OLED) display devices are self-light-emitting type display devices which electrically excite an organic compound to emit light. Since such OLED display devices may be driven at a low voltage, are easy to be slimmed down, have a wide viewing angle, and are quick in response, thus capable of solving issues of Liquid-crystal-display (LCD) devices, they are garnering a lot of attention as next generation display devices.

In recent times, a thin film encapsulation layer including an organic layer and an inorganic layer has been used as a means for sealing an organic light emitting element to achieve slimness and/or flexibility of the OLED display devices. The thin film encapsulation layer has a multilayer thin film structure in which organic layers and inorganic layers are alternately laminated. When the organic layer is exposed through an end portion of the thin film encapsulation layer, the exposed portion may become an infiltration path for moisture and oxygen. The penetration of external moisture and oxygen to the OLED display device may be delayed or blocked, when the end portion of the thin film encapsulation layer is sealed with an inorganic layer. However, when such inorganic layers contact each other in at least a part of the sealing layer, there is a possibility that stress is concentrated at the interface between the inorganic layers and cracks are generated.

SUMMARY

Exemplary embodiments of the present invention may be directed to an organic light emitting display device partially modified in terms of the shape of an encapsulation layer to absorb stress caused by an external impact, to suppress crack generation by imparting flexibility, and realizing a robust structure of the encapsulation layer, and to a method of manufacturing the organic light emitting display device.

According to an exemplary embodiment of the present invention, an organic light emitting display device includes: a substrate including a display area and a non-display area; a thin film transistor disposed on the substrate in the display area; an insulating layer disposed on the thin film transistor; an organic light emitting element disposed on the insulating layer and connected to the thin film transistor; and an

encapsulation layer covering the organic light emitting element. The encapsulation layer includes: a first inorganic layer disposed on the organic light emitting element and extending from the organic light emitting element to the non-display area; an organic layer disposed on the first inorganic layer; a second inorganic layer disposed on the organic layer and extending from the organic layer to the non-display area; and an organic pattern layer disposed between the first inorganic layer and the second inorganic layer so as to be spaced apart from the organic layer in the non-display area. At least a part of the first inorganic layer and at least a part of the second inorganic layer may contact each other in the non-display area.

At least a part of the organic pattern layer may overlap the insulating layer in a plan view.

The organic pattern layer may include a material substantially the same as a material which the organic layer includes.

The organic layer may include at least one kind of organic material selected from: acrylic resins, methacrylic resins, isoprene resins, vinyl resins, epoxy resins, urethane resins, cellulose resins, phenylene resins, and imide resins.

The organic pattern layer may have a width of about 10 μm or more and a thickness of about 0.1 μm or more.

The first inorganic layer and the second inorganic layer may have a substantially equal area in a plan view, and an area of the organic layer may be less than an area of the first inorganic layer and an area of the second inorganic layer.

The first inorganic layer and the second inorganic layer may each independently include at least one kind of inorganic material selected from: silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, aluminum oxynitride, titanium oxide, titanium nitride, tantalum oxide, tantalum nitride, hafnium oxide, hafnium nitride, zirconium oxide, zirconium nitride, cerium oxide, cerium nitride, tin oxide, tin nitride, and magnesium oxide.

The organic light emitting display device may further include a dam portion disposed in the non-display area of the substrate.

The insulating layer may include a side portion inclined in a direction toward the dam portion.

The organic pattern layer may be disposed between the dam portion and the inclined side portion of the insulating layer.

The organic pattern layer may be disposed at an area in which at least a part of the non-display area where the first inorganic layer and the second inorganic layer contact each other and at least a part of the inclined side portion of the insulating layer and the organic pattern layer overlap each other in a plan view.

The dam portion may be provided in plural and the plurality of dam portions may have different heights.

The organic light emitting display device may further include a pixel defining layer disposed between the insulating layer and the encapsulation layer, the pixel defining layer defining a pixel area of the organic light emitting element. The dam portion may include a material substantially the same as a material which at least one of the insulating layer and the pixel defining layer includes.

The dam portion may include a first layer including a material substantially the same as a material which the insulating layer includes; and a second layer on the first layer, the second layer including a material substantially the same as a material which the pixel defining layer includes.

According to an exemplary embodiment of the present invention, a method of manufacturing the organic light emitting display device includes: forming a thin film tran-

3

sistor in a display area of a substrate, the substrate including the display area and a non-display area; forming an insulating layer on the thin film transistor; forming an organic light emitting element on the insulating layer and connecting the organic light emitting element with the thin film transistor; and forming an encapsulation layer covering the organic light emitting element. The forming of the encapsulation layer includes: forming a first inorganic layer to cover the organic light emitting element and to extend from the organic light emitting element to the non-display area; forming an organic layer on the first inorganic layer; removing a part of the organic layer and leaving a part of the organic layer in the non-display area to form an organic pattern layer spaced apart from the organic layer; and forming a second inorganic layer to cover the organic layer and to extend from the organic layer to the non-display area.

The first inorganic layer and the second inorganic layer may have a substantially equal area in a plan view, and an area of the organic layer may be less than an area of the first inorganic layer and an area of the second inorganic layer.

The organic layer may be formed by one of an inkjet method, a slit coating method, a screen printing method, an evaporation method, and a chemical vapor deposition method.

The forming of the organic pattern layer may include forming the organic pattern layer by an ashing process using a cleaning mask.

The method may further include etching the insulating layer formed in the non-display area of the substrate to form a dam portion.

The organic pattern layer may be disposed between the dam portion and one side portion of the insulating layer.

According to an exemplary embodiment of the present invention, an organic light emitting display device includes: a thin film transistor disposed on a substrate in a display area, the substrate including the display area and a non-display area; an insulating layer disposed on the thin film transistor, the insulating layer including an inclined side portion in the non-display area; an organic light emitting element disposed on the insulating layer and connected to the thin film transistor; and an encapsulation layer covering the organic light emitting element. The encapsulation layer includes: a first inorganic layer disposed on the organic light emitting element and extending from the organic light emitting element to the non-display area; an organic layer disposed on the first inorganic layer to cover a part of the first inorganic layer; an organic pattern layer disposed on the first inorganic layer, spaced apart from the organic layer, and overlapping at least a part of the inclined side portion of the insulating layer in a plan view; and a second inorganic layer disposed on the organic layer, extending from the organic layer to the non-display area, covering the organic pattern layer, and contacting the first inorganic layer in the non-display area where the organic layer and the organic pattern layer are not disposed on the first inorganic layer.

The organic pattern layer may include a material substantially the same as a material which the organic layer includes.

The first inorganic layer and the second inorganic layer may have a substantially equal area in the plan view.

BRIEF DESCRIPTION OF THE DRAWINGS

A more complete appreciation of the present invention will become more apparent by describing in detail exemplary embodiments thereof with reference to the accompanying drawings, in which:

4

FIG. 1 is a cross-sectional view illustrating an organic light emitting display device according to an exemplary embodiment of the present invention;

FIG. 2 is a cross-sectional view illustrating an organic light emitting display device according to an exemplary embodiment of the present invention;

FIG. 3 is a scanning electron microscopy (SEM) photograph showing a cross-sectional structure of an organic light emitting display device including a conventional encapsulation layer;

FIG. 4 is an SEM photograph showing a cross-sectional structure of an organic light emitting display device including an organic pattern layer according to an exemplary embodiment of the present invention; and

FIGS. 5, 6, 7 and 8 are cross-sectional views schematically showing a method of manufacturing the organic light emitting display device of FIG. 1 according to an exemplary embodiment of the present invention.

Since the drawings in FIGS. 1-2 and 5-8 are intended for illustrative purposes, the elements in the drawings are not necessarily drawn to scale. For example, some of the elements may be enlarged or exaggerated for clarity purpose.

DETAILED DESCRIPTION OF THE EMBODIMENTS

Exemplary embodiments will now be described more fully hereinafter with reference to the accompanying drawings. Although the present invention may be modified in various manners and have several embodiments, exemplary embodiments are illustrated in the accompanying drawings and will be mainly described in the specification. However, the scope of the present invention is not limited to the exemplary embodiments and should be construed as including all the changes, equivalents and substitutions included in the spirit and scope of the present invention.

When a layer, area, or plate is referred to as being “on” another layer, area, or plate, it may be directly on the other layer, area, or plate, or intervening layers, areas, or plates may be present therebetween. Conversely, when a layer, area, or plate is referred to as being “directly on” another layer, area, or plate, intervening layers, areas, or plates may be absent therebetween. Further, when a layer, area, or plate is referred to as being “below” another layer, area, or plate, it may be directly below the other layer, area, or plate, or intervening layers, areas, or plates may be present therebetween. Conversely, when a layer, area, or plate is referred to as being “directly below” another layer, area, or plate, intervening layers, areas, or plates may be absent therebetween.

The spatially relative terms “below”, “beneath”, “lower”, “above”, “upper” or the like, may be used herein for ease of description to describe the relations between one element or component and another element or component as illustrated in the drawings. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation, in addition to the orientation depicted in the drawings. For example, in the case where a device illustrated in the drawing is turned over, the device positioned “below” or “beneath” another device may be placed “above” another device. Accordingly, the illustrative term “below” may include both the lower and upper positions. The device may also be oriented in the other direction and thus the spatially relative terms may be interpreted differently depending on the orientations.

Throughout the specification, when an element is referred to as being viewed “in a plan view”, the element is viewed

from the above, and when an element is referred to as being viewed “on a cross-sectional view”, a cross-sectional surface of the element that is cut vertically is viewed from the lateral side.

Throughout the specification, when an element is referred to as being “connected” to another element, the element is “directly connected” to the other element, or “electrically connected” to the other element with one or more intervening elements interposed therebetween. It will be further understood that the terms “comprises”, “comprising”, “includes” and/or “including” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components and/or groups, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components and/or groups thereof.

It will be understood that, although the terms “first”, “second”, “third” or the like may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another element. Thus, “a first element” discussed below could be termed “a second element” or “a third element” and “a second element” and “a third element” may be termed likewise without departing from the teachings herein.

“About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” may mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% or 5% of the stated value.

Unless otherwise defined, all terms used herein (including technical and scientific terms) have the same meaning as commonly understood by those skilled in the art to which the present invention pertains. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an ideal or excessively formal sense unless clearly defined in the present specification.

Some of the parts which are not associated with the description may not be provided in order to specifically describe exemplary embodiments of the present invention and like reference numerals refer to like elements throughout the specification.

Hereinafter, an exemplary embodiment of the present invention will be described with reference to FIG. 1.

FIG. 1 is a cross-sectional view illustrating an organic light emitting display device (hereinafter, “organic light emitting diode (OLED) display device” by way of example) **10** according to an exemplary embodiment of the present invention.

Referring to FIG. 1, an OLED display device **10** according to an exemplary embodiment of the present invention includes a substrate **101**, a display unit **100** in a display area DA of the substrate **101**, and an encapsulation layer **300** across the display area DA and a non-display area NDA for sealing the display unit **100**.

The substrate **101** may include various materials. For example, the substrate **101** may include a transparent glass material including silicon oxide (SiO_2) as a main component. However, the present invention is not limited thereto. For example, in an exemplary embodiment of the present invention, the substrate **101** may include a transparent

plastic material and have flexibility. Such a plastic material may include an insulating organic material selected from one of, for example, polyethersulphone (PES), polyacrylate (PAR), polyetherimide (PEI), polyethylene naphthalate (PEN), polyethylene terephthalate (PET), polyphenylene sulfide (PPS), polyallylate, polyimide (PI), polycarbonate (PC), cellulose triacetate (TAC), and cellulose acetate propionate (CAP).

In the case of a bottom emission type where images are displayed toward the substrate **101**, it is necessary that the substrate **101** is formed of a transparent material. However, in the case of a top emission type where images are displayed in a direction opposite to the substrate **101**, it is not necessary that the substrate **101** includes a transparent material, and the substrate **101** may be either opaque or reflective and may include a metal material. In an exemplary embodiment of the present invention, the substrate **101** may include metals known in the art, and may include at least one of, for example, iron (Fe), chromium (Cr), manganese (Mn), nickel (Ni), titanium (Ti), molybdenum (Mo), stainless steel (SUS), Invar alloys, Inconel alloys, and Kovar alloys.

The substrate **101** may include a display area DA in which light is emitted by the display unit **100** to realize images to be recognized by users, and a non-display area NDA which corresponds to the remaining part other than the display area DA. An organic light emitting element (hereinafter, “organic light emitting diode (OLED)” by way of example) **100b** may be disposed in the display area DA, and a power wiring **220** for supplying power to the OLED **100b** may be disposed in the non-display area NDA. In addition, a power supplier or a pad unit for applying electric signals from a signal generator to the display area DA may be disposed in the non-display area NDA.

The display unit **100** will be described in more detail. A buffer layer **102** may be disposed on the substrate **101**. The buffer layer **102** may provide a planar surface on top of the substrate **101** and may block foreign matter or moisture penetrating through the substrate **101**. For example, the buffer layer **102** may include an inorganic material such as, for example, silicon oxide (SiO_2), silicon nitride (Si_3N_4), silicon oxynitride (SiON), aluminum oxide (Al_2O_3), aluminum nitride (AlN), titanium oxide (TiO_2), or titanium nitride (TiN), or an organic material such as, for example, polyimide, polyester, or acrylic polymers, and may have a multi-layer structure including the above-described materials. The buffer layer **102** is formed in the display area DA and may extend to the non-display area NDA.

A thin film transistor **100a** and the OLED **100b** electrically connected to the thin film transistor **100a** may be disposed in the display area DA over the buffer layer **102** on the substrate **101**.

The thin film transistor **100a** may include an active layer **103**, a gate electrode **105**, a source electrode **107**, and a drain electrode **108**. Hereinafter, the thin film transistor **100a** of a top gate type in which the active layer **103**, the gate electrode **105**, the source electrode **107**, and the drain electrode **108** are sequentially disposed will be described. However, the present invention is not limited thereto. For example, in an exemplary embodiment of the present invention, various types of thin film transistors **100a** such as a bottom gate type may be employed.

The active layer **103** is disposed on the buffer layer **102**. The active layer **103** may include a semiconductor material known in the art, for example, amorphous silicon or polycrystalline silicon. In an exemplary embodiment of the present invention, the active layer **103** may include an organic semiconductor material or the like. Alternatively, in

an exemplary embodiment of the present invention, the active layer **103** may include an oxide semiconductor material, and thus may include an oxide of a material selected from group **12**, **13**, or **14** metal elements such as, for example, zinc (Zn), indium (In), gallium (Ga), tin (Sn), cadmium (Cd), germanium (Ge), or combinations thereof. The oxide semiconductor materials have high mobility, and thus may be suitable for OLED application. In addition, since the oxide semiconductor materials usually have wide-bandgaps, they can also be transparent.

A gate insulating layer **104** is disposed on the active layer **103**, serves to insulate the active layer **103** from the gate electrode **105**, and may have a single-layer structure or a multilayer structure, with each layer including at least one inorganic material of, for example, silicon oxide (SiO_2) and silicon nitride (Si_3N_4). The gate insulating layer **104** may not only be disposed in the display area DA but also may extend to a part of the non-display area NDA.

The gate electrode **105** is disposed on the gate insulating layer **104**, and may be connected to a gate line for applying an on/off signal to the thin film transistor **100a**. The gate electrode **105** may include a low resistive metal material known in the art. In consideration of close contactness to an adjacent layer, surface flatness of a layer to be laminated thereon, and processability, the gate electrode **105** may have a single-layer structure or a multilayer structure, with each layer including at least one of, for example, aluminum (Al), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), lithium (Li), calcium (Ca), molybdenum (Mo), titanium (Ti), tungsten (W), copper (Cu), and the like.

An insulating interlayer **106** is disposed on the gate electrode **105**, and insulates the gate electrode **105** from the source electrode **107** and the drain electrode **108**. The insulating interlayer **106** may not only be disposed in the display area DA but also extend to a part of the non-display area NDA. The insulating interlayer **106** may have a single-layer structure or a multilayer structure, with each layer including an inorganic material. For example, the inorganic material may be metal oxide or metal nitride such as, for example, silicon oxide (SiO_2), silicon nitride (Si_3N_4), silicon oxynitride (SiON), aluminum oxide (Al_2O_3), titanium oxide (TiO_2), tantalum oxide (Ta_2O_5), hafnium oxide (HfO_2), zirconium oxide (ZrO_2), or the like.

The source electrode **107** and the drain electrode **108** are disposed on the insulating interlayer **106**. Each of the source electrode **107** and the drain electrode **108** may have a single-layer structure or a multilayer structure, with each layer including a metal known in the art. The metal may include at least one of, for example, aluminum (Al), platinum (Pt), palladium (Pd), silver (Ag), magnesium (Mg), gold (Au), nickel (Ni), neodymium (Nd), iridium (Ir), chromium (Cr), lithium (Li), calcium (Ca), molybdenum (Mo), titanium (Ti), tungsten (W), copper (Cu), and the like. The source electrode **107** and the drain electrode **108** are each disposed to contact an area of the active layer **103**. For example, the insulating interlayer **106** and the gate insulating layer **104** are formed to expose a source area and a drain area of the active layer **103** through openings, and the source electrode **107** and the drain electrode **108** are formed to fill the openings to contact the source area and the drain area of the active layer **103**, respectively.

The thin film transistor **100a** is electrically connected to the OLED **100b** to drive the OLED **100b** and is covered with and protected by an insulating layer **109**. The insulating layer **109** may include an inclined side portion in the non-display area NDA.

The insulating layer **109** eliminates a step (i.e., a height difference) caused by the thin film transistor **100a** and planarizes an upper surface above the thin film transistor **100a** so as to substantially prevent defects from occurring in the OLED **100b** due to unevenness therebelow. The insulating layer **109** may have a single-layer structure or a multilayer structure including an inorganic insulating layer, an organic insulating layer, or both of the inorganic insulating layer and the organic insulating layer that are known in the art. Examples of a material forming the inorganic insulating layer may include but is not limited to: SiO_2 , Si_3N_4 , SiON , Al_2O_3 , TiO_2 , Ta_2O_5 , HfO_2 , ZrO_2 , barium strontium titanate (BST), lead zirconate titanate (PZT) or a mixture thereof. The organic insulating layer may include a common polymer known in the art, and examples of a material forming the organic insulating layer may include but is not limited to: polymethylmethacrylate (PMMA), polystyrene (PS), polymer derivatives having a phenolic group, acrylic polymers, imide polymers, arylether polymers, amide polymers, fluorine polymers, p-xylene polymers, vinyl alcohol polymers, or blends thereof. In addition, the insulating layer **109** may be formed as a composite laminate including an inorganic insulating layer and an organic insulating layer.

On the insulating layer **109**, the OLED **100b** is disposed. The OLED **100b** is electrically connected to the thin film transistor **100a**, and includes a first electrode **110**, a second electrode **113** opposing the first electrode **110**, and an intermediate layer **112** interposed between the first electrode **110** and the second electrode **113**.

The first electrode **110** is disposed on the insulating layer **109** and may be electrically connected to the thin film transistor **100a**, specifically to the drain electrode **108**, through a contact hole defined in the insulating layer **109**. The first electrode **110** may have various shapes, for example, may be patterned into an island shape. The first electrode **110** may be a reflective electrode, and may include a reflective layer including, for example, Ag, Mg, Al, Pt, Pd, Au, Ni, Nd, Ir, Cr or a compound thereof, and a transparent or translucent electrode layer disposed on the reflective layer. The transparent or translucent electrode layer may include at least one of, for example, indium tin oxide (ITO), indium zinc oxide (IZO), zinc oxide (ZnO), indium oxide (In_2O_3), indium gallium oxide (IGO), and aluminum zinc oxide (AZO).

The second electrode **113** which is disposed to oppose the first electrode **110** may be a transparent or translucent electrode. For example, the second electrode **113** may include a metal thin film that has a low work function and includes, for example, Li, Ca, lithium fluoride (LiF)/Ca, LiF/Al, Al, Ag, Mg, or compounds thereof. In addition, an auxiliary electrode layer or a bus electrode that includes a transparent electrode forming material such as, for example, ITO, IZO, ZnO, or In_2O_3 may be further provided on the metal thin film. Accordingly, the second electrode **113** may transmit the light emitted from the organic light emitting layer included in the intermediate layer **112**. That is, the light emitted from the organic light emitting layer may be emitted directly toward the second electrode **113** or may be directed toward the second electrode **113** after being reflected by the first electrode **110** which is formed as a reflective electrode.

The display unit **100** is not limited to the top emission type. For example, in an exemplary embodiment of the present invention, the display unit **100** may be a bottom emission type in which light emitted from the organic light emitting layer is emitted toward the substrate **101**. In such a case, the first electrode **110** may be a transparent or trans-

lucent electrode, and the second electrode **113** may be a reflective electrode. In addition, in an exemplary embodiment of the present invention, the display unit **100** may be a double-sided emission type that emits light toward both top and bottom directions.

In an exemplary embodiment of the present invention, a pixel defining layer **119** including an insulating material may be disposed on the first electrode **110** and between the insulating layer **109** and the encapsulation layer **300**. The pixel defining layer **119** exposes a predetermined area of the first electrode **110**, and the intermediate layer **112** including an organic light emitting layer is disposed in the exposed area. That is, the pixel defining layer **119** defines a pixel area of the OLED. The pixel defining layer **119** may include at least one organic insulating material of, for example, polyimide, polyamide, an acrylic resin, benzocyclobutene, and a phenol resin, and may be formed by spin coating.

The organic light emitting layer included in the intermediate layer **112** may include a low molecular weight organic material or a high molecular weight organic material. In addition to the organic light emitting layer, the intermediate layer **112** may further include functional layers known in the art, e.g., a hole transport layer (HTL), a hole injection layer (HIL), an electron transport layer (ETL), and an electron injection layer (EIL) in a selected manner.

Although only one OLED is illustrated in FIG. 1, the display unit **100** may include a plurality of OLEDs **100b**. Each OLED **100b** may form one pixel, and a red, green, blue, or white color may be realized in each pixel. In addition, a color conversion layer or a color filter for converting the emitted light into a predetermined color may be further provided.

The encapsulation layer **300** seals the display unit **100** to substantially prevent the display unit **100** from being deteriorated. For example, the encapsulation layer **300** may protect the display unit **100** from external oxygen and moisture. The encapsulation layer **300** may have a multilayer thin film structure in which inorganic layers and organic layers are alternately stacked.

In an exemplary embodiment of the present invention, the encapsulation layer **300** includes a first inorganic layer **310** disposed on the OLED **100b** and extending from the OLED **100b** to the non-display area NDA, an organic layer **320** disposed on the first inorganic layer **310**, a second inorganic layer **330** disposed on the organic layer **320** and extending from the organic layer **320** to the non-display area NDA, and an organic pattern layer **340** spaced apart from the organic layer **320** in the non-display area NDA and disposed between the first inorganic layer **310** and the second inorganic layer **330**.

The first inorganic layer **310** may seal the OLED **100b** and may extend to cover a portion of the non-display area NDA, thereby securely preventing permeation of oxygen or moisture into the OLED **100b**. The first inorganic layer **310** may have a single-layer structure or a multilayer structure, with each layer including: metal oxide or metal nitride known in the art. For example, the first inorganic layer **310** may include at least one kind of inorganic material selected from: silicon oxide (SiO_2), silicon nitride (Si_3N_4), silicon oxynitride (SiON), aluminum oxide (Al_2O_3), aluminum nitride (AlN), aluminum oxynitride (AlON), titanium oxide (TiO_2), titanium nitride (TiN), tantalum oxide (Ta_2O_5), tantalum nitride (TaN), hafnium oxide (HfO_2), hafnium nitride (HfN), zirconium oxide (ZrO_2), zirconium nitride (ZrN), cerium oxide (CeO_2), cerium nitride (CeN), tin oxide (SnO_2), tin nitride (Sn_3N_4), and magnesium oxide (MgO).

The organic layer **320** covers a part of the first inorganic layer **310** and alleviates the internal stress of the first inorganic layer **310** or fills microcracks and pinholes of the first inorganic layer **310**, thereby enhancing effects of preventing permeation of moisture or oxygen. The organic layer **320** may have a single-layer structure or a multilayer structure, with each layer including a polymer known in the art. For example, the organic layer **320** may include at least one kind of organic material selected from: acrylic resins, methacrylic resins, isoprene resins, vinyl resins, epoxy resins, urethane resins, cellulose resins, phenylene resins, and imide resins. Moreover, the organic layer **320** may include small organic molecules which may be crosslinked afterwards. The organic layer **320** is disposed so as to cover a part of the first inorganic layer **310**, and thus an area of the organic layer **320** may be less than an area of the first inorganic layer **310** and an area of the second inorganic layer **330** to be described. The part of the first inorganic layer **310** covered by the organic layer **320** may include major portion in the display area DA and may also include some portion in the non-display area NDA.

The second inorganic layer **330** may be disposed on the organic layer **320** and may extend from the organic layer **320** to cover a part of the non-display area NDA, thereby securely preventing permeation of oxygen and moisture. The second inorganic layer **330** may have an area substantially equal to an area of the first inorganic layer **310** in a plan view. The second inorganic layer **330** may have a single-layer structure or a multilayer structure, with each layer including: metal oxide or metal nitride known in the art. For example, the second inorganic layer **330** may include at least one kind of inorganic material selected from: SiO_2 , Si_3N_4 , SiON , Al_2O_3 , AlN , AlON , TiO_2 , TiN , Ta_2O_5 , TaN , HfO_2 , HfN , ZrO_2 , ZrN , CeO_2 , CeN , SnO_2 , Sn_3N_4 , and MgO . The component of the second inorganic layer **330** may be substantially the same as or different from the component of the first inorganic layer **310**.

In an exemplary embodiment of the present invention, since the first inorganic layer **310** and the second inorganic layer **330** have a substantially equal area and the organic layer **320** interposed therebetween has an area less than the area of the first inorganic layer **310** and the area of the second inorganic layer **330**, there exists an area in the non-display area NDA where at least a portion of the first inorganic layer **310** and at least a portion of the second inorganic layer **330** contact each other. In such a non-display area NDA where the first and second inorganic layers **310** and **330** contact each other, peeling is likely to occur at an interface between the first and second inorganic layers **310** and **330**, and there is a high possibility that stress is concentrated at the interface and cracks are generated. In particular, when an impact caused by an external force is applied to an area of the non-display area NDA where the first and second inorganic layers **310** and **330** contact each other acts as a weak point, cracks may easily occur at this weak point as illustrated in FIG. 3, thereby inevitably resulting in defective products.

According to an exemplary embodiment of the present invention, the organic pattern layer **340** that is spaced apart from the organic layer **320** is additionally formed between the first inorganic layer **310** and the second inorganic layer **330** which contact each other in the non-display area NDA. For example, the first inorganic layer **310** and the second inorganic layer **330** may contact each other in the non-display area NDA where the organic layer **320** and the organic pattern layer **340** are not disposed between the first inorganic layer **310** and the second inorganic layer **330**. The

11

organic pattern layer **340** absorbs the stress between the inorganic layers **310** and **330** and imparts flexibility. Accordingly, the organic pattern layer **340** may serve to realize a robust sealing structure by mitigating impact due to external force and suppressing crack occurrence. FIG. 4 is an SEM photograph showing a cross-sectional structure of an organic light emitting display device **10** including an organic pattern layer **340** according to an exemplary embodiment of the present invention. As illustrated in FIG. 4, crack does not occur at the weak point where the first and second inorganic layers **310** and **330** contact each other in contrast to that illustrated in FIG. 3. This is due to the formation of the organic pattern layer **340** overlapping the inclined side portion (e.g., an edge) of the insulating layer **109**, and will be discussed further below.

In such an exemplary embodiment described above, it is necessary to dispose the organic pattern layer **340** at a specific position where cracks are likely to occur relative to other areas, in consideration of the structure of the encapsulation layer **300** and the process efficiency of the OLED display device **10**. According to an exemplary embodiment of the present invention, the organic pattern layer **340** may be disposed apart from the organic layer **320** and between the first inorganic layer **310** and the second inorganic layer **330** that contact each other in the non-display area NDA. According to an exemplary embodiment of the present invention, the organic pattern layer **340** may be disposed at an area in which at least a portion of the non-display area NDA where the first inorganic layer **310** directly contacts the second inorganic layer **330**, and at least a portion of an inclined side portion (e.g., an edge) of the insulating layer **109** and the organic pattern layer **340** overlap each other in a plan view. At least a portion of the organic pattern layer **340** may overlap the insulating layer **109** of the display unit **100** in a plan view. The organic pattern layer **340** disposed at the above-describe position may absorb the stress between the inorganic layers **310** and **330** that contact each other and may impart flexibility to suppress cracking. In addition, the organic pattern layer **340** may also be disposed at positions other than the one described above to prevent cracking by identifying the weak points such as the stress concentrated areas in the structure and applying the organic pattern layers **340** to the weak point areas to release the stress.

The organic pattern layer **340** may be formed by allowing a part of the organic layer **320**, that is supposed to be removed during a process of manufacturing the organic layer **320**, to remain, for example, on the first inorganic layer **310**. Accordingly, the organic pattern layer **340** may be disposed apart from the organic layer **320**, but may include a material substantially the same as a material included in the organic layer **320**. For example, the organic pattern layer **340** may include at least one kind of organic material selected from: acrylic resins, methacrylic resins, isoprene resins, vinyl resins, epoxy resins, urethane resins, cellulose resins, phenylene resins, and imide resins. In addition, in consideration of the structure of the encapsulation layer and the effect of impact mitigation, the organic pattern layer **340** may have a width of about 10 μm or more and a thickness of about 0.1 μm or more. For example, to substantially prevent an overlap with a monomer jetting line, the organic pattern layer **340** may have a width in a range from about 10 μm to about 100 μm . In addition, not to affect the profile of the second inorganic layer **330**, the organic pattern layer **340** may have a thickness in a range from about 0.1 μm to about 0.6 μm .

FIG. 1 exemplifies an embodiment in which the first inorganic layer **310**, the organic layer **320**, and the second

12

inorganic layer **330** are sequentially stacked as an encapsulation layer, and the organic pattern layer **340** is disposed between the first inorganic layer **310** and the second inorganic layer **330** that contact each other in the non-display area NDA. However, the present invention is not limited thereto. For example, the stack structure of the inorganic layers and the organic layers and the number of layers in the encapsulation layer are not particularly limited, as long as there is the organic pattern layer **340** between the inorganic layers that contact each other in the non-display area NDA. That is, the encapsulation layer **300** may further include a plurality of inorganic layers and a plurality of organic layers that are alternately disposed, and the number of times of lamination of the inorganic layers and the organic layers is not particularly limited as well. For example, in an exemplary embodiment of the present invention, the encapsulation layer **300** may further include additional organic layer(s), organic pattern layer(s), and inorganic layer(s), other than the organic layer **320**, the organic pattern layer **340**, the first inorganic layer **310** and the second inorganic layer **330** shown in FIG. 1.

FIG. 2 is a cross-sectional view illustrating an organic light emitting display device according to an exemplary embodiment of the present invention. In FIG. 2, the same reference numerals as those in FIG. 1 denote the same members.

In the following description of FIG. 2, the redundant descriptions described hereinabove with reference to FIG. 1 will not be provided, and only differences will be described.

Referring to FIG. 2, an OLED display device **11** according to the present exemplary embodiment may further include a dam portion **120** disposed in the non-display area NDA of the substrate **101**, as compared with FIG. 1.

The dam portion **120** disposed outside the display area DA may substantially prevent an organic material for forming the organic layer **320** from flowing toward an edge of the substrate **101** when forming the organic layer **320** of the encapsulation layer **300**, and accordingly, formation of an edge tail of the organic layer **320** may be substantially prevented. The dam portion **120** may surround the display area DA and have a predetermined height to enclose the display area DA.

The dam portion **120** may include a material substantially the same as a material included in at least one of the insulating layer **109** and the pixel defining layer **119**. The dam portion **120** may include a plurality of layers. In an exemplary embodiment of the present invention, the dam portion **120** may include a first layer **121** which includes a material substantially the same as a material included in the insulating layer **109**, and a second layer **122** which is on the first layer **121** and includes a material substantially the same as a material included in the pixel defining layer **119**. However, the present invention is not limited thereto. For example, in an exemplary embodiment of the present invention, the dam portion **120** may include one layer. Alternatively, in an exemplary embodiment of the present invention, the dam portion **120** may include three or more layers. For process simplification, in an exemplary embodiment of the present invention, the first layer **121** of the dam portion **120** and the insulating layer **109** may be formed by an identical process, and/or the second layer **122** of the dam portion **120** and the pixel defining layer **119** may be formed by an identical process.

The dam portion **120** may be formed in plural. In an exemplary embodiment of the present invention, the plurality of dam portions **120** may have different heights. Within the plurality of dam portions **120**, a height of one dam

portion **120** near an outer portion of the substrate **101** may be greater than a height of another dam portion **120** near an inner portion of the substrate **101**. That is, the height of the dam portion **120** may increase toward the outer portion of the substrate **101**.

In the OLED display device **11** illustrated in FIG. **2**, the first inorganic layer **310** and the second inorganic layer **330** may extend to the outside of the substrate **101** so as to cover the dam portion **120**. Accordingly, the penetration of external moisture and oxygen to the OLED display device **11** may be delayed or blocked. In addition, since the dam portion **120** substantially blocks an organic material from flowing toward an edge of the substrate **101** when forming the organic layer **320**, the organic layer **320** is to be disposed inside the dam portion **120** in the display area DA and the non-display area NDA. In addition, the organic pattern layer **340** may be disposed between the dam portion **120** and an inclined side portion (edge) of the insulating layer **109**. The inclined side portion of the insulating layer **109** is inclined in a direction toward the dam portion **120**. At least a portion of the organic pattern layer **340** may overlap the insulating layer **109** of the display unit **100** in a plan view. The first and second inorganic layers **310** and **330** may cover an outside surface of the dam portion **120** and may contact each other outside the dam portion **120** in the non-display area NDA. In addition, the first and second inorganic layers **310** and **330** may contact each other inside the dam portion **120** where the organic layer **320** and the organic pattern layer **340** are not disposed.

The dam portion **120** may be disposed so as to contact at least a part of the power wiring **220**. For example, the dam portion **120** may be disposed so as to overlap and contact at least an outer edge of the power wiring **220**. The dam portion **120** that includes a material substantially the same as a material included in at least one of the insulating layer **109** and the pixel defining layer **119** may have a good bonding strength with metal. Accordingly, when the dam portion **120** is disposed to contact the power wiring **220** that includes a metal material, the dam portion **120** may be stably constructed with excellent bonding strength with the power wiring **220**.

Although FIG. **2** illustrates an example in which the dam portion **120** is disposed to overlap an outer edge of the power wiring **220**, however, the present invention is not limited thereto. For example, in an exemplary embodiment of the present invention, the dam portion **120** may be disposed only on the power wiring **220**, or may be disposed so as to cover the power wiring **220**. Here, the power wiring **220** may be connected to the second electrode **113** via a wiring **116** for supplying power to the OLED **100b**.

FIGS. **5**, **6**, **7** and **8** are cross-sectional views schematically showing a method of manufacturing the organic light emitting display device of FIG. **1** according an exemplary embodiment of the present invention.

Referring to FIG. **5**, the display unit **100** is formed on the substrate **101**, and the first inorganic layer **310** which is over the display unit **100** and extends from the display unit **100** to cover a portion of the non-display area NDA is formed.

The display unit **100** may employ various OLED displays known in the art, in addition to the configuration exemplified in FIG. **1**, and thus a specific method of manufacturing the display unit **100** will be omitted.

The first inorganic layer **310** may include an inorganic material such as metal oxide, metal nitride, or the like that are known in the art. Such a first inorganic layer **310** may be

deposited by a method such as, for example, sputtering, atomic layer deposition (ALD), or chemical vapor deposition (CVD).

After the first inorganic layer **310** is formed, the organic layer **320** is formed as illustrated in FIG. **6**.

The organic layer **320** may include any organic material known in the art, e.g., monomers and/or polymers, without limitation. Such an organic layer may be formed through various process methods known in the art and may be formed by one of, for example, an inkjet method, a slit coating method, a screen printing method, an evaporation method, and a chemical vapor deposition (CVD) method.

After the organic layer **320** is formed, a part of the organic layer **320** is removed as illustrated in FIG. **7**. More specifically, the tail of the organic layer **320** is removed, and a part of the organic layer **320** is left in the non-display area NDA to form the organic pattern layer **340** that is spaced apart from the organic layer **320**.

The organic pattern layer **340** may be formed by an ashing process using a cleaning mask. The cleaning mask may be formed through a photolithographic process. The ashing process is a dry etch process in which a gas such as oxygen (O_2), nitrous oxide (N_2O) or ammonia (NH_3) is accelerated in a plasma state to remove carbon-based organic substances remaining at the bottom to be cleaned. It is preferable that the organic pattern layer **340** is formed by an oxygen (O_2) ashing process. For example, after disposing a cleaning mask on the organic layer **320** in a chamber, the ashing process is performed using the cleaning mask. In particular, according to an exemplary embodiment of the present invention, the pattern of the organic layer **320** to be removed may be freely controlled by partially modifying the design of the cleaning mask applied to the ashing process, and thus the organic pattern layer **340** on one side portion (edge) of the insulating layer **109** remains and the tail of the organic layer **320** other than the one side portion is removed in the non-display area NDA.

Any cleaning mask that is commonly used in the ashing process may be used without limitation, except that the design is partially modified. In addition, the conditions of the ashing process are not particularly limited. For example, conditions such as the internal pressure of the chamber, the oxygen flow rate, or the applied power may be appropriately adjusted within the range known in the art.

Next, the second inorganic layer **330** is formed to cover the organic layer **320** and further extends to cover a part of the non-display area NDA, as illustrated in FIG. **8**.

The second inorganic layer **330** may be formed by, for example, sputtering, atomic layer deposition (ALD), chemical vapor deposition (CVD), or the like. The second inorganic layer **330** may include an inorganic material such as metal oxide or metal nitride that are known in the art. For example, the second inorganic layer **330** may include a material substantially the same as or different from a material included in the first inorganic layer **310** described above.

The method according to an exemplary embodiment of the present invention may further include forming the dam portion **120** disposed in the non-display area NDA of the substrate **101**. Since the dam portion **120** may have the configuration exemplified in FIG. **2**, a specific manufacturing method thereof will be omitted. For example, the dam portion **120** may be formed in a process substantially the same as a process in which at least one of the insulating layer **109** and the pixel defining layer **119** is formed with a material substantially the same as a material included in the at least one of the insulating layer **109** and the pixel defining layer **119**. The dam portion **120** and at least one of the

15

insulating layer **109** and the pixel defining layer **119** may be formed of a photosensitive material through a photolithographic process. Accordingly, the dam portion **120** and at least one of the insulating layer **109** and the pixel defining layer **119** may be substantially formed simultaneously through an exposure process using a halftone mask by adjusting an exposure amount. However, the present invention is not limited thereto. For example, at least one of a preliminary insulating layer and a pixel defining layer may be formed on the substrate **101** through spin coating process, an etch mask may be formed on at least one of the preliminary insulating layer and the preliminary pixel defining layer through an photolithographic process, and an etching process may be carried out through the etch mask to etch at least one of the preliminary insulating layer and the preliminary pixel defining layer to form the dam portion **120** and the at least one of the insulating layer **109** and the pixel defining layer **119** simultaneously.

The OLED display device according to an exemplary embodiment of the present invention includes a separate organic pattern layer that may absorb stress and impart flexibility between inorganic layers that directly contact each other in the non-display area NDA, and thus may suppress cracking and achieve a robust structure of an encapsulation layer. Such OLED display devices may be applied not only to flat panel display (FPD) devices but also to any display devices such as, for example, curved display devices, foldable display devices and flexible display devices in the field of the present invention.

As set forth hereinabove, the OLED display device according to an exemplary embodiment of the present invention includes a separate organic pattern layer that may absorb stress and impart flexibility between the first inorganic layer and the second inorganic layer. Accordingly, the impact caused by an external force may be mitigated and the crack generation may be suppressed, and thereby a robust encapsulation structure may be realized.

The OLED display device according to an exemplary embodiment of the present invention may form the organic layer and the organic pattern layer substantially simultaneously without using a separate manufacturing process. Accordingly, the manufacturing cost of the OLED display device may be low.

While the present invention has been illustrated and described with reference to the exemplary embodiments thereof, it will be apparent to those of ordinary skill in the art that various changes in form and detail may be made therein without departing from the spirit and scope of the present invention as defined by the appended claims.

What is claimed is:

1. An organic light emitting display device comprising:
 - a substrate comprising a display area and a non-display area;
 - a thin film transistor disposed on the substrate in the display area;
 - an insulating layer disposed on the thin film transistor;
 - an organic light emitting element disposed on the insulating layer and connected to the thin film transistor; and
 - an encapsulation layer covering the organic light emitting element,
 wherein the encapsulation layer comprises:
 - a first inorganic layer disposed on the organic light emitting element and extending from the organic light emitting element to the non-display area;
 - an organic layer disposed on the first inorganic layer;
 - a second inorganic layer disposed on the organic layer and extending from the organic layer to the non-display area; and

16

an organic pattern layer disposed between the first inorganic layer and the second inorganic layer so as to be spaced apart from the organic layer in the non-display area,

wherein at least a part of the first inorganic layer and at least a part of the second inorganic layer contact each other in the non-display area, and

a thickness of the organic pattern layer is smaller than a thickness of the organic layer.

2. The organic light emitting display device of claim 1, wherein at least a part of the organic pattern layer overlaps the insulating layer in a plan view.

3. The organic light emitting display device of claim 1, wherein the organic pattern layer comprises a material the same as a material which the organic layer comprises.

4. The organic light emitting display device of claim 1, wherein the organic layer comprises at least one kind of organic material selected from: acrylic resins, methacrylic resins, isoprene resins, vinyl resins, epoxy resins, urethane resins, cellulose resins, phenylene resins, and imide resins.

5. The organic light emitting display device of claim 1, wherein the organic pattern layer has a width of about 10 μm or more and the thickness of about 0.1 μm or more.

6. The organic light emitting display device of claim 1, wherein the first inorganic layer and the second inorganic layer have a equal area in a plan view, and

an area of the organic layer is less than an area of the first inorganic layer and an area of the second inorganic layer.

7. The organic light emitting display device of claim 1, wherein the first inorganic layer and the second inorganic layer each independently comprises at least one kind of inorganic material selected from: silicon oxide, silicon nitride, silicon oxynitride, aluminum oxide, aluminum nitride, aluminum oxynitride, titanium oxide, titanium nitride, tantalum oxide, tantalum nitride, hafnium oxide, hafnium nitride, zirconium oxide, zirconium nitride, cerium oxide, cerium nitride, tin oxide, tin nitride, and magnesium oxide.

8. The organic light emitting display device of claim 1, further comprising a dam portion disposed in the non-display area of the substrate.

9. The organic light emitting display device of claim 8, wherein the insulating layer comprises a side portion inclined in a direction toward the dam portion.

10. The organic light emitting display device of claim 9, wherein the organic pattern layer is disposed between the dam portion and the inclined side portion of the insulating layer.

11. The organic light emitting display device of claim 9, wherein the organic pattern layer is disposed at an area in which at least a part of the non-display area where the first inorganic layer and the second inorganic layer contact each other and at least a part of the inclined side portion of the insulating layer and the organic pattern layer overlap each other in a plan view.

12. The organic light emitting display device of claim 8, wherein the dam portion is provided in plural and the plurality of dam portions have different heights.

13. The organic light emitting display device of claim 8, further comprising a pixel defining layer disposed between the insulating layer and the encapsulation layer, the pixel defining layer defining a pixel area of the organic light emitting element,

wherein the dam portion comprises a material the same as a material which at least one of the insulating layer and the pixel defining layer comprises.

14. The organic light emitting display device of claim 13, wherein the dam portion comprises:

17

a first layer comprising a material the same as a material which the insulating layer comprises; and
 a second layer on the first layer, the second layer comprising a material the same as a material which the pixel defining layer comprises.

15. An organic light emitting display device comprising:
 a thin film transistor disposed on a substrate in a display area, the substrate comprising the display area and a non-display area;
 an insulating layer disposed on the thin film transistor, the insulating layer comprising an inclined side portion in the non-display area;
 an organic light emitting element disposed on the insulating layer and connected to the thin film transistor; and
 an encapsulation layer covering the organic light emitting element,
 wherein the encapsulation layer comprises:
 a first inorganic layer disposed on the organic light emitting element and extending from the organic light emitting element to the non-display area;

18

an organic layer disposed on the first inorganic layer to cover a part of the first inorganic layer;
 an organic pattern layer disposed on the first inorganic layer, spaced apart from the organic layer, and overlapping at least a part of the inclined side portion of the insulating layer in a plan view; and
 a second inorganic layer disposed on the organic layer, extending from the organic layer to the non-display area, covering the organic pattern layer, and contacting the first inorganic layer in the non-display area where the organic layer and the organic pattern layer are not disposed on the first inorganic layer.

16. The organic light emitting display device of claim 15, wherein the organic pattern layer comprises a material the same as a material which the organic layer comprises.

17. The organic light emitting display device of claim 15, wherein the first inorganic layer and the second inorganic layer have an equal area in the plan view.

* * * * *