



US011038121B2

(12) **United States Patent**  
**Xia**

(10) **Patent No.:** **US 11,038,121 B2**  
(45) **Date of Patent:** **Jun. 15, 2021**

(54) **9 MEMBERED RING CARBAZOLE COMPOUNDS**

H01L 51/0073; H01L 51/0074; H01L 51/5012; H01L 51/5016; H01L 51/5056; H01L 51/5072; H01L 51/5096

(71) Applicant: **BEIJING SUMMER SPROUT TECHNOLOGY CO., LTD.**, Beijing (CN)

See application file for complete search history.

(72) Inventor: **Chuanjun Xia**, Lawrenceville, NJ (US)

(56) **References Cited**

(73) Assignee: **BEIJING SUMMER SPROUT TECHNOLOGY CO., LTD.**, Beijing (CN)

U.S. PATENT DOCUMENTS

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 104 days.

5,703,436	A	12/1997	Forrest et al.
5,707,745	A	1/1998	Forrest et al.
5,844,363	A	12/1998	Gu et al.
6,097,147	A	8/2000	Baldo et al.
6,303,238	B1	10/2001	Thompson et al.
7,279,704	B2	10/2007	Walters et al.
7,968,146	B2	6/2011	Wagner et al.
2003/0230980	A1	12/2003	Forrest et al.
2004/0174116	A1	9/2004	Lu et al.
2015/0349273	A1	12/2015	Hung et al.
2016/0163998	A1	6/2016	Saito et al.
2016/0359122	A1	12/2016	Boudreault et al.
2017/0018721	A1	1/2017	Tsang et al.
2018/0331301	A1	11/2018	Parham et al.

(21) Appl. No.: **16/378,559**

(22) Filed: **Apr. 8, 2019**

(65) **Prior Publication Data**

US 2019/0312214 A1 Oct. 10, 2019

FOREIGN PATENT DOCUMENTS

CN 111269239 A \* 6/2020

**Related U.S. Application Data**

(60) Provisional application No. 62/655,219, filed on Apr. 9, 2018.

(51) **Int. Cl.**

<b>H01L 51/00</b>	(2006.01)
<b>C07D 487/04</b>	(2006.01)
<b>C07D 495/04</b>	(2006.01)
<b>H01L 51/50</b>	(2006.01)

(52) **U.S. Cl.**

CPC ..... **H01L 51/0072** (2013.01); **C07D 487/04** (2013.01); **C07D 495/04** (2013.01); **H01L 51/006** (2013.01); **H01L 51/0061** (2013.01); **H01L 51/0067** (2013.01); **H01L 51/0073** (2013.01); **H01L 51/0074** (2013.01); **H01L 51/5016** (2013.01); **H01L 51/5056** (2013.01); **H01L 51/5072** (2013.01); **H01L 51/5096** (2013.01)

(58) **Field of Classification Search**

CPC .. **C07D 487/04**; **C07D 487/06**; **C07D 495/04**; **C07D 495/16**; **H01L 51/006**; **H01L 51/0061**; **H01L 51/0067**; **H01L 51/0072**;

OTHER PUBLICATIONS

Google Patents translation for CN 111269239 A (publication date Jun. 2020). (Year: 2020).\*  
C.W. Tang et al. "Organic electroluminescent diodes", Appl. Phys. Lett. 51, 913 (1987); doi: 10.1063/1.98799.  
Hiroki Uoyama et al. "Highly efficient organic light-emitting diodes from delayed fluorescence", Nature, vol. 492, Dec. 13, 2012. doi:10.1038/nature11687, 234.

\* cited by examiner

Primary Examiner — Dawn L Garrett

(74) Attorney, Agent, or Firm — Alston & Bird LLP

(57) **ABSTRACT**

Novel 9 membered ring carbazole compounds are disclosed, which can be used as host materials etc. in an electroluminescent device. Compared with the existing host materials etc., these novel compounds can effectively modulate the charge transporting properties in the above materials and give OLEDs better performance. Also disclosed are an electroluminescent device and a formulation.

**17 Claims, 2 Drawing Sheets**




Figure 1




Figure 2




Figure 3

## 9 MEMBERED RING CARBAZOLE COMPOUNDS

This application claims the benefit of U.S. Provisional Application No. 62/655,219, filed Apr. 9, 2018, the entire content of which is incorporated herein by reference.

### FIELD OF THE INVENTION

The present invention relates to compounds for organic electronic devices, such as organic light emitting devices. More specifically, the present invention relates to 9 membered ring carbazole compounds, an organic electroluminescent device and a formulation comprising the compounds.

### BACKGROUND ART

An organic electronic device is preferably selected from the group consisting of organic light-emitting diodes (OLEDs), organic field-effect transistors (O-FETs), organic light-emitting transistors (OLETs), organic photovoltaic devices (OPVs), dye-sensitized solar cells (DSSCs), organic optical detectors, organic photoreceptors, organic field-quench devices (OFQDs), light-emitting electrochemical cells (LECs), organic laser diodes and organic plasmon emitting devices.

In 1987, Tang and Van Slyke of Eastman Kodak reported a bilayer organic electroluminescent device, which comprises an arylamine hole transporting layer and a tris-8-hydroxyquinolato-aluminum layer as the electron and emitting layer (Applied Physics Letters, 1987, 51 (12): 913-915). Once a bias is applied to the device, green light was emitted from the device. This invention laid the foundation for the development of modern organic light-emitting diodes (OLEDs). State-of-the-art OLEDs may comprise multiple layers such as charge injection and transporting layers, charge and exciton blocking layers, and one or multiple emissive layers between the cathode and anode. Since OLED is a self-emitting solid state device, it offers tremendous potential for display and lighting applications. In addition, the inherent properties of organic materials, such as their flexibility, may make them well suited for particular applications such as fabrication on flexible substrates.

OLED can be categorized as three different types according to its emitting mechanism. The OLED invented by Tang and van Slyke is a fluorescent OLED. It only utilizes singlet emission. The triplets generated in the device are wasted through nonradiative decay channels. Therefore, the internal quantum efficiency (IQE) of a fluorescent OLED is only 25%. This limitation hindered the commercialization of OLED. In 1997, Forrest and Thompson reported phosphorescent OLED, which uses triplet emission from heavy metal containing complexes as the emitter. As a result, both singlet and triplets can be harvested, achieving 100% IQE. The discovery and development of phosphorescent OLED contributed directly to the commercialization of active-matrix OLED (AMOLED) due to its high efficiency. Recently, Adachi achieved high efficiency through thermally activated delayed fluorescence (TADF) of organic compounds. These emitters have small singlet-triplet gap that makes the transition from triplet back to singlet possible. In the TADF device, the triplet excitons can go through reverse intersystem crossing to generate singlet excitons, resulting in high IQE.

OLEDs can also be classified as small molecule and polymer OLEDs according to the forms of the materials used. Small molecule refers to any organic or organometallic material that is not a polymer. The molecular weight of a small molecule can be large as long as it has well defined

structure. Dendrimers with well-defined structures are considered as small molecules. Polymer OLEDs include conjugated polymers and non-conjugated polymers with pendant emitting groups. Small molecule OLED can become a polymer OLED if post polymerization occurred during the fabrication process.

There are various methods for OLED fabrication. Small molecule OLEDs are generally fabricated by vacuum thermal evaporation. Polymer OLEDs are fabricated by solution process, such as spin-coating, ink-jet printing, and nozzle printing. Small molecule OLEDs can also be fabricated by solution process if the materials can be dissolved or dispersed in solvents.

The emitting color of an OLED can be achieved by emitter structural design. An OLED may comprise one emitting layer or a plurality of emitting layers to achieve desired spectrum. In the case of green, yellow, and red OLEDs, phosphorescent emitters have successfully reached commercialization. Blue phosphorescent emitters still suffer from non-saturated blue color, short device lifetime, and high operating voltage. Commercial full-color OLED displays normally adopt a hybrid strategy, using fluorescent blue and phosphorescent yellow, or red and green. At present, efficiency roll-off of phosphorescent OLEDs at high brightness remains a problem. In addition, it is desirable to have more saturated emitting color, higher efficiency, and longer device lifetime.


Host materials play a key role in the OLED device, such as the hole and electron transporting balance and the effective dispersion of light-emitting materials. The charge-transfer performance of the host materials often directly affects the driving voltage and efficiency of the OLED device. The 9 membered ring carbazole compounds herein are capable of effectively regulating their charge transporting properties, especially for electrons. The present invention provides a series of novel 9 membered ring carbazole compounds. These compounds can effectively modulate the charge transporting properties in the host materials and give OLEDs better performance.

### SUMMARY OF THE INVENTION

The present invention aims to provide a new series of 9 membered ring carbazole compounds to solve at least part of the above problems. The compounds can be used as host materials, charge transporting materials, charge blocking materials and emitters in an organic electroluminescent device. Compared to existing materials, the novel compounds can effectively modulate the charge transporting properties in the above materials and give OLEDs better performance.

According to an embodiment of the present invention, a compound having Formula 1 is disclosed:

Formula 1



wherein


$X_1$  to  $X_{19}$  are each independently selected from N or CR;

Wherein R are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring.

According to another embodiment, an electroluminescent device is disclosed, which comprises:

- an anode,
- a cathode,
- and an organic layer, disposed between the anode and the cathode, comprising a compound of Formula 1:



wherein

$X_1$  to  $X_{19}$  are each independently selected from N or CR;

Wherein R are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic

acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring.

According to yet another embodiment, a formulation comprising a compound of Formula 1 is also disclosed.

The novel 9 membered ring carbazole compounds disclosed in the present invention can be used as host materials, charge transporting materials, charge blocking materials or emitters in an electroluminescent device. Compared to existing materials, the novel compounds can effectively modulate the charge transporting properties in the above materials and give OLEDs better performance.

#### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 schematically shows an organic light emitting device that can incorporate the compound or the formulation disclosed herein.

FIG. 2 schematically shows another organic light emitting device that can incorporate the compound or the formulation disclosed herein.

FIG. 3 shows the Formula 1 of the compound disclosed herein.

#### DETAILED DESCRIPTION

OLEDs can be fabricated on various types of substrates such as glass, plastic, and metal foil. FIG. 1 schematically shows the organic light emitting device **100** without limitation. The figures are not necessarily drawn to scale. Some of the layer in the figure can also be omitted as needed. Device **100** may include a substrate **101**, an anode **110**, a hole injection layer **120**, a hole transport layer **130**, an electron blocking layer **140**, an emissive layer **150**, a hole blocking layer **160**, an electron transport layer **170**, an electron injection layer **180** and a cathode **190**. Device **100** may be fabricated by depositing the layers described in order. The properties and functions of these various layers, as well as example materials, are described in more detail in U.S. Pat. No. 7,279,704 at cols. 6-10, which are incorporated by reference in its entirety.

More examples for each of these layers are available. For example, a flexible and transparent substrate-anode combination is disclosed in U.S. Pat. No. 5,844,363, which is incorporated by reference in its entirety. An example of a p-doped hole transport layer is m-MTDATA doped with F4-TCNQ at a molar ratio of 50:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. Examples of host materials are disclosed in U.S. Pat. No. 6,303,238 to Thompson et al., which is incorporated by reference in its entirety. An example of an n-doped electron transport layer is BPhen doped with Li at a molar ratio of 1:1, as disclosed in U.S. Patent Application Publication No. 2003/0230980, which is incorporated by reference in its entirety. U.S. Pat. Nos. 5,703,436 and 5,707,745, which are incorporated by reference in their entireties, disclose examples of cathodes including compound cathodes having a thin layer of metal such as Mg:Ag with an overlying transparent, electrically-conductive, sputter-deposited ITO layer. The theory and use of blocking layers is described in more detail in U.S. Pat. No. 6,097,147 and U.S. Patent Application Publication No. 2003/0230980, which are incorporated by reference in their entireties. Examples of injection layers are provided in U.S. Patent Application Publication No. 2004/0174116, which is

incorporated by reference in its entirety. A description of protective layers may be found in U.S. Patent Application Publication No. 2004/0174116, which is incorporated by reference in its entirety.

The layered structure described above is provided by way of non-limiting example. Functional OLEDs may be achieved by combining the various layers described in different ways, or layers may be omitted entirely. It may also include other layers not specifically described. Within each layer, a single material or a mixture of multiple materials can be used to achieve optimum performance. Any functional layer may include several sublayers. For example, the emissive layer may have a two layers of different emitting materials to achieve desired emission spectrum.

In one embodiment, an OLED may be described as having an “organic layer” disposed between a cathode and an anode. This organic layer may comprise a single layer or multiple layers.

An OLED can be encapsulated by a barrier layer to protect it from harmful species from the environment such as moisture and oxygen. FIG. 2 schematically shows the organic light emitting device 200 without limitation. FIG. 2 differs from FIG. 1 in that the organic light emitting device 200 include a barrier layer 102, which is above the cathode 190. Any material that can provide the barrier function can be used as the barrier layer such as glass and organic-inorganic hybrid layers. The barrier layer should be placed directly or indirectly outside of the OLED device. Multi-layer thin film encapsulation was described in U.S. Pat. No. 7,968,146, which is herein incorporated by reference in its entirety.

Devices fabricated in accordance with embodiments of the invention can be incorporated into a wide variety of consumer products that have one or more of the electronic component modules (or units) incorporated therein. Some examples of such consumer products include flat panel displays, monitors, medical monitors, televisions, billboards, lights for interior or exterior illumination and/or signaling, heads-up displays, fully or partially transparent displays, flexible displays, smart phones, tablets, phablets, wearable devices, smart watches, laptop computers, digital cameras, camcorders, viewfinders, micro-displays, 3-D displays, vehicles displays, and vehicle tail lights.

The materials and structures described herein may be used in other organic electronic devices listed above.

As used herein, “top” means furthest away from the substrate, while “bottom” means closest to the substrate. Where a first layer is described as “disposed over” a second layer, the first layer is disposed further away from substrate. There may be other layers between the first and second layer, unless it is specified that the first layer is “in contact with” the second layer. For example, a cathode may be described as “disposed over” an anode, even though there are various organic layers in between.

As used herein, “solution processible” means capable of being dissolved, dispersed, or transported in and/or deposited from a liquid medium, either in solution or suspension form.

A ligand may be referred to as “photoactive” when it is believed that the ligand directly contributes to the photoactive properties of an emissive material. A ligand may be referred to as “ancillary” when it is believed that the ligand does not contribute to the photoactive properties of an emissive material, although an ancillary ligand may alter the properties of a photoactive ligand.

It is believed that the internal quantum efficiency (IQE) of fluorescent OLEDs can exceed the 25% spin statistics limit

through delayed fluorescence. As used herein, there are two types of delayed fluorescence, i.e. P-type delayed fluorescence and E-type delayed fluorescence. P-type delayed fluorescence is generated from triplet-triplet annihilation (TTA).

On the other hand, E-type delayed fluorescence does not rely on the collision of two triplets, but rather on the transition between the triplet states and the singlet excited states. Compounds that are capable of generating E-type delayed fluorescence are required to have very small singlet-triplet gaps to convert between energy states. Thermal energy can activate the transition from the triplet state back to the singlet state. This type of delayed fluorescence is also known as thermally activated delayed fluorescence (TADF). A distinctive feature of TADF is that the delayed component increases as temperature rises. If the reverse intersystem crossing rate is fast enough to minimize the non-radiative decay from the triplet state, the fraction of back populated singlet excited states can potentially reach 75%. The total singlet fraction can be 100%, far exceeding 25% of the spin statistics limit for electrically generated excitons.

E-type delayed fluorescence characteristics can be found in an exciplex system or in a single compound. Without being bound by theory, it is believed that E-type delayed fluorescence requires the luminescent material to have a small singlet-triplet energy gap ( $\Delta E_{S-T}$ ). Organic, non-metal containing, donor-acceptor luminescent materials may be able to achieve this. The emission in these materials is often characterized as a donor-acceptor charge-transfer (CT) type emission. The spatial separation of the HOMO and LUMO in these donor-acceptor type compounds often results in small  $\Delta E_{S-T}$ . These states may involve CT states. Often, donor-acceptor luminescent materials are constructed by connecting an electron donor moiety such as amino- or carbazole-derivatives and an electron acceptor moiety such as N-containing six-membered aromatic rings.

#### Definition of Terms of Substituents

halogen or halide—as used herein includes fluorine, chlorine, bromine, and iodine.

Alkyl—contemplates both straight and branched chain alkyl groups. Examples of the alkyl group include methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, n-nonyl group, n-decyl group, n-undecyl group, n-dodecyl group, n-tridecyl group, n-tetradecyl group, n-pentadecyl group, n-hexadecyl group, n-heptadecyl group, n-octadecyl group, neopentyl group, 1-methylpentyl group, 2-methylpentyl group, 1-pentylhexyl group, 1-butylpentyl group, 1-heptyloctyl group, 3-methylpentyl group. Additionally, the alkyl group may be optionally substituted. The carbons in the alkyl chain can be replaced by other hetero atoms. Of the above, preferred are methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, and neopentyl group.

Cycloalkyl—as used herein contemplates cyclic alkyl groups. Preferred cycloalkyl groups are those containing 4 to 10 ring carbon atoms and includes cyclobutyl, cyclopentyl, cyclohexyl, 4-methylcyclohexyl, 4,4-dimethylcyclohexyl, 1-adamantyl, 2-adamantyl, 1-norbornyl, 2-norbornyl and the like. Additionally, the cycloalkyl group may be optionally substituted. The carbons in the ring can be replaced by other hetero atoms.

Alkenyl—as used herein contemplates both straight and branched chain alkene groups. Preferred alkenyl groups are those containing two to fifteen carbon atoms. Examples of the alkenyl group include vinyl group, allyl group, 1-butenyl group, 2-butenyl group, 3-butenyl group, 1,3-butadienyl group, 1-methylvinyl group, styryl group, 2,2-diphenylvinyl group, 1,2-diphenylvinyl group, 1-methylallyl group, 1,1-dimethylallyl group, 2-methylallyl group, 1-phenylallyl group, 2-phenylallyl group, 3-phenylallyl group, 3,3-diphenylallyl group, 1,2-dimethylallyl group, 1-phenyl 1-butenyl group, and 3-phenyl-1-butenyl group. Additionally, the alkenyl group may be optionally substituted.

Alkynyl—as used herein contemplates both straight and branched chain alkyne groups. Preferred alkynyl groups are those containing two to fifteen carbon atoms. Additionally, the alkynyl group may be optionally substituted.

Aryl or aromatic group—as used herein contemplates noncondensed and condensed systems. Preferred aryl groups are those containing six to sixty carbon atoms, preferably six to fifty carbon atoms, more preferably six to thirty carbon atoms, more preferably six to twenty carbon atoms, more preferably six to twelve carbon atoms. Examples of the aryl group include phenyl, biphenyl, terphenyl, triphenylene, tetraphenylene, naphthalene, anthracene, phenalene, phenanthrene, fluorene, pyrene, chrysene, perylene, and azulene, preferably phenyl, biphenyl, terphenyl, triphenylene, fluorene, and naphthalene. Additionally, the aryl group may be optionally substituted. Examples of the noncondensed aryl group include phenyl group, biphenyl-2-yl group, biphenyl-3-yl group, biphenyl-4-yl group, p-terphenyl-4-yl group, p-terphenyl-3-yl group, p-terphenyl-2-yl group, m-terphenyl-4-yl group, m-terphenyl-3-yl group, m-terphenyl-2-yl group, o-tolyl group, m-tolyl group, p-tolyl group, p-t-butylphenyl group, p-(2-phenylpropyl) phenyl group, 4'-methylbiphenyl group, 4"-t-butyl p-terphenyl-4-yl group, o-cumenyl group, m-cumenyl group, p-cumenyl group, 2,3-xylyl group, 3,4-xylyl group, 2,5-xylyl group, mesityl group, and m-quarterphenyl group.

Heterocyclic group or heterocycle—as used herein contemplates aromatic and non-aromatic cyclic groups. Heteroaromatic also means heteroaryl. Preferred non-aromatic heterocyclic groups are those containing 3 to 7 ring atoms which includes at least one hetero atom such as nitrogen, oxygen, and sulfur. The heterocyclic group can also be an aromatic heterocyclic group having at least one heteroatom selected from nitrogen atom, oxygen atom, sulfur atom, and selenium atom.

Heteroaryl—as used herein contemplates noncondensed and condensed hetero-aromatic groups that may include from one to five heteroatoms. Preferred heteroaryl groups are those containing three to fifty carbon atoms, preferably three to thirty carbon atoms, more preferably three to twenty carbon atoms, more preferably three to twelve carbon atoms. Suitable heteroaryl groups include dibenzothiophene, dibenzofuran, dibenzoselenophene, furan, thiophene, benzofuran, benzothiophene, benzoselenophene, carbazole, indolocarbazole, pyridylindole, pyrrolodipyridine, pyrazole, imidazole, triazole, oxazole, thiazole, oxadiazole, oxatriazole, dioxazole, thiadiazole, pyridine, pyridazine, pyrimidine, pyrazine, triazine, oxazine, oxathiazine, oxadiazine, indole, benzimidazole, indazole, indoxazine, benzoxazole, benzisoxazole, benzothiazole, quinoline, isoquinoline, cinnoline, quinazoline, quinoxaline, naphthyridine, phthalazine, pteridine, xanthene, acridine, phenazine, phenothiazine, phenoxazine, benzofuropyridine, furodipyridine, benzothienopyridine, thienodipyridine, benzoselenophenopyridine, and selenophenodipyridine, preferably dibenzothiophene, dibenzo-

furan, dibenzoselenophene, carbazole, indolocarbazole, imidazole, pyridine, triazine, benzimidazole, 1,2-azaborine, 1,3-azaborine, 1,4-azaborine, borazine, and aza-analogs thereof. Additionally, the heteroaryl group may be optionally substituted.

Alkoxy—it is represented by —O-Alkyl. Examples and preferred examples thereof are the same as those described above. Examples of the alkoxy group having 1 to 20 carbon atoms, preferably 1 to 6 carbon atoms include methoxy group, ethoxy group, propoxy group, butoxy group, pentyloxy group, and hexyloxy group. The alkoxy group having 3 or more carbon atoms may be linear, cyclic or branched.

Aryloxy—it is represented by —O-Aryl or —O-heteroaryl. Examples and preferred examples thereof are the same as those described above. Examples of the aryloxy group having 6 to 40 carbon atoms include phenoxy group and biphenyloxy group.

Arylalkyl—as used herein contemplates an alkyl group that has an aryl substituent. Additionally, the arylalkyl group may be optionally substituted. Examples of the arylalkyl group include benzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group, 2-phenylisopropyl group, phenyl-t-butyl group, alpha-naphthylmethyl group, 1-alpha-naphthylethyl group, 2-alpha-naphthylethyl group, 1-alpha-naphthylisopropyl group, 2-alpha-naphthylisopropyl group, beta-naphthylmethyl group, 1-beta-naphthylethyl group, 2-beta-naphthylethyl group, 1-beta-naphthylisopropyl group, 2-beta-naphthylisopropyl group, p-methylbenzyl group, m-methylbenzyl group, o-methylbenzyl group, p-chlorobenzyl group, m-chlorobenzyl group, o-chlorobenzyl group, p-bromobenzyl group, m-bromobenzyl group, o-bromobenzyl group, p-iodobenzyl group, m-iodobenzyl group, o-iodobenzyl group, p-hydroxybenzyl group, m-hydroxybenzyl group, o-hydroxybenzyl group, p-aminobenzyl group, m-aminobenzyl group, o-aminobenzyl group, p-nitrobenzyl group, m-nitrobenzyl group, o-nitrobenzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-hydroxy-2-phenylisopropyl group, and 1-chloro-2-phenylisopropyl group. Of the above, preferred are benzyl group, p-cyanobenzyl group, m-cyanobenzyl group, o-cyanobenzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenylisopropyl group, and 2-phenylisopropyl group.

The term “aza” in azadibenzofuran, aza-dibenzothiophene, etc. means that one or more of the C—H groups in the respective aromatic fragment are replaced by a nitrogen atom. For example, azatriphenylene encompasses dibenzo[f,h]quinoxaline, dibenzo[f,h]quinoline and other analogues with two or more nitrogens in the ring system. One of ordinary skill in the art can readily envision other nitrogen analogs of the aza-derivatives described above, and all such analogs are intended to be encompassed by the terms as set forth herein.

The alkyl, cycloalkyl, alkenyl, alkynyl, aralkyl, heterocyclic group, aryl, and heteroaryl may be unsubstituted or may be substituted with one or more substituents selected from the group consisting of deuterium, halogen, alkyl, cycloalkyl, arylalkyl, alkoxy, aryloxy, amino, cyclic amino, silyl, alkenyl, cycloalkenyl, heteroalkenyl, alkynyl, aryl, heteroaryl, an acyl group, a carbonyl group, a carboxylic acid group, an ether group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof.

It is to be understood that when a molecular fragment is described as being a substituent or otherwise attached to another moiety, its name may be written as if it were a fragment (e.g. phenyl, phenylene, naphthyl, dibenzofuryl) or as if it were the whole molecule (e.g. benzene, naphthalene,


9

dibenzofuran). As used herein, these different ways of designating a substituent or attached fragment are considered to be equivalent.


In the compounds mentioned in this disclosure, the hydrogen atoms can be partially or fully replaced by deuterium. Other atoms such as carbon and nitrogen, can also be replaced by their other stable isotopes. The replacement by other stable isotopes in the compounds may be preferred due to its enhancements of device efficiency and stability.

In the compounds mentioned in this disclosure, multi substitutions refer to a range that includes a double substitution, up to the maximum available substitutions. When some substituent of the compound mentioned in this disclosure represent multi substitutions (including double substitution, triple substitution, tetra substitution, and etc.), it refers that the substituent can exist at multiple substitutable positions, and the substituents existing at the multiple substitutable positions can have the same structures or different structures.

In the compounds mentioned in this disclosure, the expression that adjacent substitutions can be optionally joined to form a ring is intended to be taken to mean that two radicals are linked to each other by a chemical bond. This is illustrated by the following scheme:




Furthermore, the expression that adjacent substitutions can be optionally joined to form a ring is also intended to be taken to mean that in the case where one of the two radicals represents hydrogen, the second radical is bonded at a position to which the hydrogen atom was bonded, with formation of a ring. This is illustrated by the following scheme:




10

By analogy, it should also be understood that, in the case that both radicals represent hydrogen atoms, ring formation takes place by a single bond instead of the two hydrogen atoms.

Furthermore, the expression that adjacent substitutions can be optionally joined to form a ring is also intended to be taken to mean that in the case where one of the two radicals represents hydrogen, the second radical is bonded at a position to which the hydrogen atom was bonded, with formation of a fused ring. The fused ring can include a hetero atom. This is illustrated by the following scheme:



According to an embodiment of the present invention, a compound having a Formula 1 is disclosed:



Formula 1

wherein

$X_1$  to  $X_{19}$  are each independently selected from the group consisting of CR, and N;

Wherein R are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile




## 11

group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring.

According to one embodiment of the present invention, wherein  $X_1$  to  $X_{19}$  are each independent CR.

According to one embodiment of the present invention, wherein the compound has a Formula 2 structure:



Wherein

$R_1$ ,  $R_3$ ,  $R_4$ , and  $R_5$  independently represent mono, di, tri, tetra substitution, or no substitution;

$R_2$  independently represent mono, di, tri substitution, or no substitution;


$R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ , and  $R_5$  are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring.

According to one embodiment of the present invention, wherein the compound has a structure of anyone of Formula 3-6:


## 12

Formula 3




Formula 2


Formula 4



Formula 5



Formula 6




Wherein

$R_1$ ,  $R_3$ ,  $R_4$ ,  $R_5$ ,  $R_6$ , and  $R_7$  independently represent mono, di, tri, tetra substitution, or no substitution;


$R_2$  independently represent mono, di, tri substitution, or no substitution;




15



Formula 7



Formula 8



Formula 9

Wherein

$R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ , and  $R_5$  independently represent mono, multi substitution, or no substitution; said multi substitution refer to a range that includes di substitution, up to the maximum available substitutions of the formula;

$Z$  are each independently selected from the group consisting of O, S, Se,  $NR'$ ,  $CR''R'''$  and  $SiR''''R'''''$ ;

$R'$ ,  $R''$ ,  $R'''$ ,  $R''''$ ,  $R'''''$ ,  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ , and  $R_5$  are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a


16

nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring;


In this embodiment, with the different positions of  $Z$ , the maximum available substitutions for the substituents of the ring attached to  $Z$  are changed. Taking the Formula 9 in this embodiment as an example, the ring where  $R_2$  is located and the ring where  $R_3$  is located are connected through  $Z$ . In this case,  $R_2$  may represent mono, di substitution, or no substitution, and  $R_3$  may represent mono, di, tri substitution, or no substitution. Formulas 7 and 8 are analogously.

According to one embodiment of the present invention, wherein  $R_1$ , and  $R_2$  in Formula 2, Formula 7, Formula 8, and Formula 9 are each independently selected from the group consisting of:




17

-continued




18

-continued




65 According to one embodiment of the present invention, wherein  $R_1$ ,  $R_2$ ,  $R_6$ , and  $R_7$  in Formula 3-6 are each independently selected from the group consisting of:

19




20

-continued




21

-continued




According to one embodiment of the present invention, wherein the compound is selected from the group consisting of:



Compound 1

22

-continued



Compound 2

Compound 3


Compound 4

Compound 5


23

-continued


Compound 6




Compound 7



Compound 8




Compound 9




24

-continued


Compound 10




Compound 11



Compound 12




Compound 13




25

-continued


Compound 14




Compound 15



Compound 16




Compound 17




26

-continued


Compound 18




Compound 19




Compound 20



Compound 21



Compound 22







27

-continued


Compound 23




Compound 24



Compound 25




Compound 26




28

-continued


Compound 27




Compound 28



Compound 29




Compound 30




29

-continued


Compound 31




Compound 32



Compound 33



Compound 34



30

-continued

Compound 35

5

10

15

20

25

30

35

40


45

50


55

60


65




Compound 36




Compound 37



Compound 38




Compound 39



31


-continued

Compound 40



5

Compound 41




10

15

20

25

Compound 42




30

35

40

45

Compound 43



50


55

60

32

-continued

Compound 44



5


10

15

20

25

Compound 45




30

35

40

45

Compound 46



50

55


60

65

33

-continued

Compound 47




5

10

15

Compound 48




25

30

35

Compound 49




40

45

50

Compound 50



55


60

65


34

-continued


Compound 51




Compound 52



Compound 53




Compound 54




35

-continued


Compound 55




Compound 56



Compound 57



Compound 58



36

-continued

Compound 59

5

10

15

20

25

30

35

40


45

50


55

60


65




Compound 60



Compound 61




Compound 62



37

-continued




Compound 63

5

38

-continued




Compound 68

10

15

Compound 64




20

Compound 69


25

Compound 65



30



Compound 70



35

40


Compound 66




45

50

Compound 67



Compound 71




55

60

65


Compound 72




39

-continued


Compound 73




Compound 74



Compound 75



Compound 76



40

-continued

Compound 77

5

10

15

20

25

30

35

40


45

50


55

60


65




Compound 78



Compound 79




Compound 80




41

-continued


Compound 81




Compound 82



Compound 83



Compound 84



42


-continued

Compound 85

5

10

15




20

25

30

35




Compound 86

40

45

50




Compound 87

55

60

65




Compound 88



43

-continued

Compound 89




5

10

15


Compound 90



25

30

Compound 91




40

45

50

Compound 92



55


60

65

44

-continued

Compound 93



5

10

15

Compound 94

20

25

30

Compound 95

35

40

45


50

Compound 96

55

60


65



45

-continued

Compound 97



5


10

15

46


-continued

Compound 101



15

Compound 98




20

25


30

Compound 102



30

Compound 99




35

40

45

50


Compound 103



40

45

Compound 100




55

60

65


Compound 104



47

-continued


Compound 105



5

10


Compound 106



15

20


Compound 107



25

30


Compound 108



35

40

Compound 109



45

50

55


60

65


48

-continued


Compound 110




Compound 111



Compound 112




Compound 113



49

-continued

Compound 114



5


10

15

50

-continued

Compound 118



20

25

30

35

40

45


50

55


60

65


Compound 119




Compound 120




Compound 121




Compound 122




Compound 115



Compound 116




Compound 117



51

-continued

Compound 123



5


10

15

20

25


Compound 124



20

25

Compound 125




35

40

45

Compound 126



50

55


60

65

52

-continued

Compound 127



5


10

15

20

25

Compound 128




30

35

40

45

Compound 129



50

55


60

65


53

-continued


Compound 130




Compound 131



Compound 132




Compound 133




54

-continued


Compound 134




Compound 135



Compound 136




Compound 137




55

-continued


Compound 138




Compound 139



Compound 140




Compound 141




56

-continued


Compound 142




Compound 143



Compound 144




Compound 145



57

-continued

Compound 146




5

10

15


Compound 147



20

25

Compound 148




30

35

40


Compound 149



45

50

Compound 150



55


60

65


58

-continued


Compound 151




Compound 152




Compound 153



Compound 154



Compound 155







59

-continued


Compound 156




Compound 157



Compound 158




Compound 159




60

-continued


Compound 160




Compound 161



Compound 162




Compound 163



61

-continued

Compound 164




5

10

15

62

Compound 167




20

25

30

35

Compound 168




40


45

50

Compound 165



Compound 166




55


60

65

Compound 169




Compound 170



63

-continued

Compound 171




5

10

15

Compound 172




20

25

30

Compound 173




35

40

45

Compound 174



50

55


60

65

64

-continued

Compound 175




5

10

15

Compound 176




20

25

30

Compound 177




35

40

45

Compound 178



50

55


60

65


65

-continued


Compound 179




Compound 180



Compound 181




Compound 182




66

-continued


Compound 183




Compound 184



Compound 185




Compound 186



67

-continued


Compound 187



5

10

Compound 188




15

20

25


Compound 189



30

35

Compound 190




40

45

50

55

Compound 191




60

65

68

-continued


Compound 192



5

10

Compound 193




15

20

25


Compound 194



30

35

Compound 195




40

45

50

55

Compound 196




60

65

69

-continued

Compound 197



5


10

15

70

-continued

Compound 201




20

25

30

Compound 202




35

40

45


Compound 203



50

55


Compound 204




60

65


Compound 205




Compound 198



Compound 199




Compound 200




71

-continued


Compound 206




Compound 207




Compound 208



Compound 209








Compound 210



72

-continued

Compound 211



Compound 212


Compound 213



73

-continued


Compound 214



74


-continued

Compound 217




20

Compound 218




Compound 215




40

Compound 219




Compound 216



55

Compound 220






75

-continued

Compound 221




5

10

15


Compound 222



20

25

Compound 223




35

40

45

50

Compound 224



55


60

65

76

-continued

Compound 225




5

10

15

Compound 226




20

25

30

35

Compound 227




40

45

50

Compound 228



55


60

65

77

-continued


Compound 229




78

-continued


Compound 233




Compound 234




Compound 235




Compound 236




Compound 237




Compound 230



Compound 231




Compound 232



79

-continued

Compound 238




5

10

15


Compound 239



20

25


Compound 240



30

35

Compound 241




40

45

50

Compound 242



55


60

65

80

-continued

Compound 243




5

10

15

Compound 244




20

25

30

35

Compound 245




40

45

50

Compound 246



55


60

65


81

-continued


Compound 247




Compound 248



Compound 249



Compound 250




82

-continued

Compound 251

5




10

15

Compound 252

20




25

30

Compound 253

35




40

45

50

Compound 254

55




60

65

83

-continued

Compound 255




5

10

15

Compound 256

20




25

30

35

Compound 257


40



45

50

Compound 258



55


60

65


84

-continued


Compound 259




Compound 260



Compound 261



Compound 262




85

86


-continued

Compound 263



5

Compound 267




10

15

Compound 268


Compound 264



20


25

30



Compound 269


Compound 265




35

40

45



Compound 266




50

55

60

65


Compound 270



87


-continued

Compound 271




5

Compound 272




15

Compound 273




25

Compound 274



40

Compound 275



55


60

65

88


-continued

Compound 276




5

Compound 277




15

Compound 278



30


Compound 279



40

45

Compound 280



55


60

65

89

-continued

Compound 281




5

10

15

Compound 282




20

25

30

Compound 283




35

40

45

50

Compound 284



55


60

65

90

-continued

Compound 285




5

10

15

Compound 286




20

25

30

Compound 287




40

45

50

Compound 288



55

60


65



91

-continued

Compound 289




5

10

15


Compound 290



20

25


Compound 291



35

40


Compound 292



45

50

Compound 293



55


60

65

92

-continued

Compound 294




5

10

15

Compound 295




20

25

30

Compound 296




35

40

45

50

Compound 297



55


60

65


93

-continued


Compound 298




Compound 299



Compound 300




Compound 301




94

-continued


Compound 302




Compound 303



Compound 304




Compound 305



95

-continued

Compound 306




5

96

-continued

Compound 310




10

15

Compound 311


Compound 307



20


25

30



Compound 312

Compound 308




35

40


45

50



Compound 313


Compound 309



55

60


65




97

-continued


Compound 314




Compound 315



Compound 316




Compound 317




98

-continued


Compound 318




Compound 319




Compound 320



Compound 321




Compound 322



99


-continued

Compound 323




5

Compound 324




15

Compound 325




20

Compound 326



35

Compound 327



50

55


60

65

100


-continued

Compound 328




10

Compound 329



25

Compound 330




30

35

40

45

Compound 331



55


60

65


101

-continued


Compound 332




Compound 333



Compound 334



Compound 335



102

-continued

Compound 336

5

10

15

20

25

30

35

40


45

50


55

60


65




Compound 337



Compound 338




Compound 339




103

-continued


Compound 340




Compound 341



Compound 342




Compound 343




104

-continued


Compound 344




Compound 345



Compound 346




Compound 347



105

-continued

Compound 348



5


10

15

106

-continued

Compound 352



20

25

30

35

40

45


50

55


60

65


Compound 349




Compound 350




Compound 351




Compound 353



Compound 354



Compound 355







107

-continued


Compound 356




Compound 357



Compound 358



Compound 359



108


-continued

Compound 360

5

10

15



20

25

30

35

40

45


50

55


60

65


Compound 361



Compound 362




Compound 363




109


-continued




Compound 365



Compound 366




Compound 367



110

-continued

Compound 368




20 According to another embodiment, an electroluminescent device is disclosed. The electroluminescent device comprises:

an anode,

a cathode,

25 and an organic layer, disposed between the anode and the cathode, comprising a compound of Formula 1:

Formula 1



Wherein

X<sub>1</sub> to X<sub>19</sub> are each independently selected from the group consisting of CR, and N;

45 Wherein R are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

65 Any adjacent substitution can be optionally joined to form a ring.

111


According to one embodiment of the present invention, wherein the organic layer is a charge transporting layer.

According to one embodiment of the present invention, wherein the organic layer is a charge blocking layer.

According to one embodiment of the present invention, wherein the organic layer is an emissive layer and the compound is a host.

According to one embodiment of the present invention, wherein the organic layer further comprises a phosphorescent emitter.

According to one embodiment of the present invention, wherein the organic layer further comprises a phosphorescent emitter and the phosphorescent emitter is a metal complex having at least one ligand comprising the any following structures:



Wherein

$R_a$ ,  $R_b$ , and  $R_c$  can represent mono, di, tri, or tetra substitution or no substitution;

$X_b$  is independently selected from the group consisting of O, S, Se,  $NR_{N1}$ , and  $CR_{C1}R_{C2}$ ;

$R_a$ ,  $R_b$ ,  $R_c$ ,  $R_{N1}$ ,  $R_{C1}$  and  $R_{C2}$  are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl

112

group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring.

According to one embodiment of the present invention, wherein the organic layer is the emissive layer and the compound of Formula 1 is the thermally delayed fluorescent dopant.

According to yet another embodiment, a formulation comprising a compound having Formula 1 is also disclosed. The specific structures of the compounds are described in any of the above embodiments.

Combination with Other Materials

The materials described herein as useful for a particular layer in an organic light emitting device may be used in combination with a wide variety of other materials present in the device. The combinations of these materials are described in more detail in U.S. Pat. App. No. 20160359122 at paragraphs 0132-0161, which are incorporated by reference in its entirety. The materials described or referred to the disclosure are non-limiting examples of materials that may be useful in combination with the compounds disclosed herein, and one of skill in the art can readily consult the literature to identify other materials that may be useful in combination.


The materials described herein as useful for a particular layer in an organic light emitting device may be used in combination with a variety of other materials present in the device. For example, host materials disclosed herein may be used in combination with a wide variety of emissive dopants, hosts, transport layers, blocking layers, injection layers, electrodes and other layers that may be present. The combination of these materials is described in detail in paragraphs 0080-0101 of U.S. Pat. App. No. 20150349273, which are incorporated by reference in its entirety. The materials described or referred to the disclosure are non-limiting examples of materials that may be useful in combination with the compounds disclosed herein, and one of skill in the art can readily consult the literature to identify other materials that may be useful in combination.

It is understood that the various embodiments described herein are by way of example only, and are not intended to limit the scope of the invention. The present invention as claimed may therefore include variations from the particular examples and preferred embodiments described herein, as will be apparent to one of skill in the art. Many of the materials and structures described herein may be substituted with other materials and structures without deviating from the spirit of the invention. It is understood that various theories as to why the invention works are not intended to be limiting.

## 113

What is claimed is:

1. A compound comprising Formula 1:




wherein

$X_1$  to  $X_{19}$  are each independently selected from CR, or N; R are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring.

2. The compound of claim 1, wherein  $X_1$  to  $X_{19}$  are each independent CR.

3. The compound of claim 1, wherein the compound comprises a Formula 2 structure:



Wherein

$R_1$ ,  $R_3$ ,  $R_4$ , and  $R_5$  independently represent mono, di, tri, tetra substitution, or no substitution;

## 114


$R_2$  independently represent mono, di, tri substitution, or no substitution;

$R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ , and  $R_5$  are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring.


4. The compound of claim 1, wherein the compound comprises a structure of any one of Formula 3-6:

Formula 3



Formula 2


Formula 4




115

-continued

Formula 5



Formula 6



Wherein

$R_1$ ,  $R_3$ ,  $R_4$ ,  $R_5$ ,  $R_6$ , and  $R_7$  independently represent mono, di, tri, tetra substitution, or no substitution;

$R_2$  independently represent mono, di, tri substitution, or no substitution;

$X$ , are each independently selected from the group consisting of O, S, Se,  $NR'$ ,  $CR''R'''$  and  $SiR''''R'''''$ ;

$Y$  are each independently selected from the group consisting of O, S,  $NR'$ ,  $CR''R'''$  and  $SiR''''R'''''$ ;


$R'$ ,  $R''$ ,  $R'''$ ,  $R''''$ ,  $R'''''$ ,  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ ,  $R_5$ ,  $R_6$ , and  $R_7$  are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring;


116

L is selected from the group consisting of:


5




10




15




20




25




30




35



40




45



50




55



60






65



117


-continued




Single bond.

5. The compound of claim 1, wherein the compound comprises a structure of any one of Formula 7-9:

Formula 7




Formula 8



118

-continued

Formula 9



Wherein

$R_1$  independently represent mono, di, tri, tetra substitution, or no substitution;


$R_2$ ,  $R_3$ ,  $R_4$ , and  $R_5$  independently represent mono, multi substitution, or no substitution; said multi substitution refer to a range that includes di substitution, up to the maximum available substitutions of the formula;

$Z$  are each independently selected from the group consisting of O, S,  $NR'$ ,  $CR''R'''$  and  $SiR''''R'''''$ ;

$R'$ ,  $R''$ ,  $R'''$ ,  $R''''$ ,  $R'''''$ ,  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ , and  $R_5$  are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;


Any adjacent substitution can be optionally joined to form a ring.

6. The compound of claim 3, wherein  $R_1$ , and  $R_2$  are each independently selected from the group consisting of:




119

-continued




120

-continued




121

-continued




7. The compound of claim 4, wherein R<sub>1</sub>, R<sub>2</sub>, R<sub>6</sub>, and R<sub>7</sub> are each independently selected from the group consisting of:



122







-continued







123

-continued










124

-continued












25 **8.** The compound of claim 5, wherein R<sub>1</sub> and R<sub>2</sub> are each independently selected from the group consisting of:









125

-continued



126

-continued



5

10

15

20

25

30

35

40

45

50


55

60

65


127

-continued




9. The compound of claim 1, wherein the compound is selected from the group consisting of:


Compound 1



Compound 2



Compound 3



128


-continued

Compound 4

5

10

15




20

25

30

35

Compound 5




40

45

50

Compound 6




Compound 7

55

60


65



129

-continued

Compound 8




5

10

15

Compound 9




20

25

30

Compound 10




35

40

45

Compound 11



50

55


60

65


130

-continued


Compound 12




Compound 13



Compound 14




Compound 15




131

-continued


Compound 16




Compound 17




Compound 18



Compound 19




Compound 20




132

-continued


Compound 21




Compound 22




Compound 23



Compound 24




Compound 25



133

-continued

Compound 26




5

10

15

Compound 27




20

25

30

Compound 28




35

40

45

50

Compound 29



55


60

65


134

-continued


Compound 30




Compound 31



Compound 32




Compound 33



135

-continued


Compound 34



5

10


Compound 35



15

20


Compound 36



25

30


Compound 37



35


40

Compound 38



50

Compound 39



55


60

65


136

-continued


Compound 40




Compound 41



Compound 42




Compound 43



137

-continued


Compound 44




138

-continued


Compound 47




Compound 48




Compound 49



Compound 46



Compound 50







139

-continued


Compound 51




Compound 52




Compound 53



Compound 54



Compound 55




140

-continued

Compound 56

5



10

15

20

Compound 57

25

30

35

40

45




50

Compound 59

55

60


65



141

-continued

Compound 60




5

10

15


Compound 61



20

25


Compound 62



35

40


Compound 63



45

50

Compound 64



55


60

65


142

-continued


Compound 65




Compound 66




Compound 67



Compound 68




Compound 69




143

-continued


Compound 70




Compound 71




Compound 72



Compound 73



Compound 74



144

-continued

Compound 75

5

10

15

20

25

30

35

40


45

50


55

60


65



Compound 76




Compound 77



145

-continued

Compound 78




5

10

15

Compound 79




20

25

30

Compound 80




35

40

45

50

Compound 81



55


60

65


146

-continued


Compound 82




Compound 83



Compound 84




Compound 85



147

-continued




Compound 86

5


10

15


Compound 87



Compound 88




Compound 89




148

-continued


Compound 90




Compound 91



Compound 92




Compound 93



149

-continued

Compound 94




5

10

15

Compound 95




20

25

30

Compound 96




35

40

45

50

Compound 97



55


60

65


150

-continued


Compound 98




Compound 99



Compound 100




Compound 101




151

-continued


Compound 102




Compound 103




Compound 104



Compound 105




Compound 106




152

-continued


Compound 107




Compound 108




Compound 109



Compound 110




Compound 111



153

-continued

Compound 112



5


10

15

154

-continued

Compound 116




20

25

30

35

Compound 113




40

45

50

Compound 114




55


60

65


Compound 115




Compound 117



Compound 118



Compound 119






155

-continued

Compound 120




5

10

156

-continued


Compound 125



15

Compound 126


Compound 121



20


25

30



Compound 127

Compound 122




35

40

45

50


Compound 123



55


Compound 128

Compound 124



60


65



157

-continued


Compound 129




158

-continued


Compound 132




Compound 130




Compound 133




Compound 134



Compound 131




Compound 135



**159**

-continued

Compound 136




5

10

15

Compound 137




20

25

30

Compound 138




35

40

45

50

Compound 139



55


60

65


**160**

-continued


Compound 140




Compound 141



Compound 142




Compound 143



161

-continued


Compound 144



5

10

Compound 145




15

20

25

Compound 146




30

35

40

Compound 147




45

50

55

Compound 148




60

65


162

-continued


Compound 149




Compound 150




Compound 151



Compound 152




Compound 153




163

-continued


Compound 154




Compound 155




Compound 156



Compound 157



Compound 158




164

-continued

Compound 159

5



10

15

Compound 160

20

25

30

Compound 161

35

40

45


Compound 162

50

55

60


65




165

-continued


Compound 163




Compound 164



Compound 165




Compound 166




166

-continued


Compound 167




Compound 168



Compound 169




Compound 170



167

-continued

Compound 171




5

10

15

20

Compound 172




25

30

35

Compound 173




40

45

50

Compound 174



55


60

65

168

-continued

Compound 175




5

10

15

20

Compound 176




25

30

35

Compound 177




40

45

50

Compound 178



55


60

65

169

-continued

Compound 179



5


10

15

170

-continued

Compound 183




20

25

30

35

Compound 180




40

45

50

Compound 181




55


60

65


Compound 182




Compound 184



Compound 185



Compound 186






171

-continued

Compound 187




5

10

172

-continued

Compound 192




15

20

25

Compound 188




30

35

40

Compound 189




45


50

55

Compound 190




Compound 191




60

65


Compound 193




Compound 194



Compound 195




Compound 196



173

-continued

Compound 197



5


10

15

174

-continued

Compound 201




20

25

30

Compound 202



35


40

45


50

55


Compound 203




Compound 204




Compound 205




Compound 198



Compound 199




Compound 200



175

-continued

Compound 206




5

10

15


Compound 207



20

25

Compound 208




35

40

45


Compound 209



50

55

Compound 210




60

65

176

-continued

Compound 211




5

10

15

20

Compound 212




30

35

40

45

Compound 213



50

55


60

65

177

-continued


Compound 214




178

-continued


Compound 217




Compound 215




Compound 218




Compound 219



Compound 216




Compound 220



179

-continued

Compound 221



5


10

15

180

-continued

Compound 225




20

25

30

35

Compound 222




40

45

50

Compound 223




55


60

65


Compound 224




Compound 226



Compound 227




Compound 228



181

-continued


Compound 229



5

10

Compound 230




15

20

25

Compound 231




30

35

40

Compound 232




45

50

55

Compound 233




60

65


182

-continued


Compound 234




Compound 235




Compound 236



Compound 237




Compound 238



**183**

-continued




Compound 239

5

**184**

-continued




Compound 244

10

15

Compound 240




20

25

Compound 245


Compound 241




30

35

40



Compound 242




45

50

Compound 246


Compound 243



55

60


65



185

-continued

Compound 247




5

10

15

20

Compound 248




25

30

35

Compound 249




40

45

50

Compound 250



55


60

65


186

-continued


Compound 251




Compound 252



Compound 253



Compound 254






187

-continued

Compound 255



5


10

15

188


-continued

Compound 259



20

Compound 256




25

30


35

Compound 260



40


Compound 257



45


50

Compound 261



55


Compound 258



60

65


Compound 262



189

-continued

Compound 263



5


10

15

190

-continued

Compound 267




20

25

30

Compound 268




35

40

45

50

Compound 269




55


60

65


Compound 270




Compound 264



Compound 265




Compound 266




191

-continued


Compound 271




Compound 272




Compound 273



Compound 274




Compound 275




192

-continued


Compound 276




Compound 277



Compound 278




Compound 279



193

-continued

Compound 280




5

10

15

Compound 281




20

25

30

Compound 282




35

40

45

Compound 283



50

55


60

65

194

-continued

Compound 284




5

10

15

Compound 285




20

25

30

Compound 286




35

40

45

50

Compound 287



55


60

65

195

-continued

Compound 288



5


10

15

196

-continued

Compound 293




20

25

30

Compound 294




35

40

45


Compound 295




50

55


Compound 296




Compound 289




Compound 290



Compound 291



Compound 292




60

65


197

-continued


Compound 297



Compound 298




Compound 299




198

-continued


Compound 300




Compound 301



Compound 302




Compound 303



199

-continued

Compound 304




5

10

15

20

Compound 305




25

30

35

Compound 306




40

45

50

Compound 307



55


60

65

200

-continued

Compound 308




5

10

15

20

Compound 309




25

30

35

Compound 310




40

45

50

Compound 311



55


60

65


201

-continued


Compound 312




Compound 313



Compound 314




Compound 315




202

-continued


Compound 316




Compound 317




Compound 318



Compound 319




Compound 320





203

-continued




Compound 321

5

10


15

Compound 322




Compound 323

30




Compound 325

40



Compound 326


45



50

204

-continued



Compound 327

5

10

15

20

25

30

35

40


45

50


55

60


65



Compound 328



Compound 329




Compound 330

205

-continued

Compound 330




5

10

15

Compound 331




20

25

30

Compound 332




35

40

45

50

Compound 333



55


60

65


206

-continued


Compound 334




Compound 335



Compound 336




Compound 337




207

-continued


Compound 338




Compound 339



Compound 340




Compound 341



208


-continued

Compound 342



10


Compound 343



25

30


Compound 344



45

50

Compound 345




65


209

-continued


Compound 346




Compound 347



Compound 348




Compound 349




210

-continued


Compound 350




Compound 351



Compound 352




Compound 353



211

-continued

Compound 354



5

10


15

20

212

-continued

Compound 358




25


30

35


Compound 359




Compound 355




Compound 360




Compound 356



Compound 361



Compound 357



55


60

65

213

-continued

Compound 362



5


10

15

214

-continued


Compound 366



20

25

Compound 363




30

35

40


45

Compound 367



45

Compound 364




50

55


60

65

Compound 365



Compound 368




215

10. An electroluminescent device comprises:

an anode,

a cathode,

and an organic layer, disposed between the anode and the cathode, comprising a compound of Formula 1:



Formula 1

Wherein

$X_1$  to  $X_{19}$  are each independently selected from the group consisting of CR, and N;

Wherein R are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring.

11. The device of claim 10, wherein the organic layer is a charge transporting layer.


12. The device of claim 10, wherein the organic layer is a charge blocking layer.

13. The device of claim 10, wherein the organic layer is an emissive layer and the compound is a host.

14. The device of claim 10, wherein the organic layer further comprises a phosphorescent emitter.

15. The device of claim 14, wherein the phosphorescent emitter is a metal complex having at least one ligand comprising any of the following structures:

216



Wherein

$R_a$ ,  $R_b$ , and  $R_c$  can represent mono, multi substitution, or no substitution; said multi substitution refer to a range that includes di substitution, up to the maximum available substitutions of the formula;

$X_b$  is independently selected from the group consisting of O, S, Se,  $NR_{M1}$ , and  $CR_{C1}R_{C2}$ ;

$R_a$ ,  $R_b$ ,  $R_c$ ,  $R_{M1}$ ,  $R_{C1}$  and  $R_{C2}$  are each independently selected from the group consisting of hydrogen, deuterium, halogen, a substituted or unsubstituted alkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted cycloalkyl group having 3 to 20 ring carbon atoms, a substituted or unsubstituted heteroalkyl group having 1 to 20 carbon atoms, a substituted or unsubstituted arylalkyl group having 7 to 30 carbon atoms, a substituted or unsubstituted alkoxy group having 1 to 20 carbon atoms, a substituted or unsubstituted aryloxy group having 6 to 30 carbon atoms, a substituted or unsubstituted alkenyl group having 2 to 20 carbon atoms, a substituted or unsubstituted aryl group having 6 to 50 carbon atoms, a substituted or unsubstituted heteroaryl group having 3 to 50 carbon atoms, a substituted or unsubstituted alkylsilyl group having 3 to 20 carbon atoms, a substituted or unsubstituted arylsilyl group having 6 to 20 carbon atoms, a substituted or unsubstituted amino group having 0 to 20 carbon atoms, an acyl group, a carbonyl group, a

**217**

carboxylic acid group, an ester group, a nitrile group, an isonitrile group, a sulfanyl group, a sulfinyl group, a sulfonyl group, a phosphino group, and combinations thereof;

Any adjacent substitution can be optionally joined to form a ring. 5

**16.** The device of claim **10**, wherein the organic layer is an emissive layer and the compound of Formula 1 is a thermally delayed fluorescent dopant.

**17.** A formulation comprising the compound of claim **1**. 10

\* \* \* \* \*

**218**