



US011045909B2

(12) **United States Patent**  
**Wood et al.**

(10) **Patent No.:** **US 11,045,909 B2**  
(45) **Date of Patent:** **Jun. 29, 2021**

(54) **THICK, LONG SEAM WELDING SYSTEM AND METHOD FOR DISTORTION CONTROL AND NON POST WELD HEAT TREATMENT OF PIPELINE HOT TAP FITTINGS**

(58) **Field of Classification Search**  
CPC ..... B23K 9/0253; B23K 31/027  
See application file for complete search history.

(71) Applicant: **TDW Delaware, Inc.**, Wilmington, DE (US)

(56) **References Cited**

U.S. PATENT DOCUMENTS

(72) Inventors: **Paul Wood**, Depew, OK (US); **Chris Vrolyk**, Edmonton (CA); **Tran Mah-Paulson**, Edmonton (CA); **Mike Armstrong**, Wagoner, OK (US)

4,089,455 A \* 5/1978 Fellers ..... B23K 31/027  
138/97  
2005/0150550 A1\* 7/2005 Maichel ..... F16K 27/0218  
137/320

(73) Assignee: **TDW Delaware, Inc.**, Wilmington, DE (US)

FOREIGN PATENT DOCUMENTS

CN 102672360 A \* 9/2012 ..... B23K 31/02  
DE 19944972 A1 4/2001

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 486 days.

(Continued)

(21) Appl. No.: **15/939,996**

OTHER PUBLICATIONS

(22) Filed: **Mar. 29, 2018**

Translation of CN-102672360-A (Year: 2012).\*

(65) **Prior Publication Data**

US 2018/0281117 A1 Oct. 4, 2018

(Continued)

**Related U.S. Application Data**

(60) Provisional application No. 62/478,950, filed on Mar. 30, 2017, provisional application No. 62/556,050, filed on Sep. 8, 2017.

*Primary Examiner* — Erin E McGrath

(74) *Attorney, Agent, or Firm* — GableGotwals

(51) **Int. Cl.**  
**B23K 31/02** (2006.01)  
**F16L 55/18** (2006.01)


(Continued)

(57) **ABSTRACT**

A method for limiting fitting distortion when welding a fitting to an in-service pipeline—where the fitting includes a thick, longitudinally extending, seam located between fitting halves—involves welding, on each side of the fitting, a middle third section of the seam in a pyramid-like fashion using an inward progression starting from an end of the middle third section along a profile of a seam bevel, and welding outer third sections of the seam using an outward progression from an end adjacent to the middle third section along a profile of the seam bevel. The welding of each of the three sections per side includes a temper bead welding technique of at least two layers to provide stress relief in lieu of traditional post weld heat treatment.

(52) **U.S. Cl.**  
CPC ..... **B23K 31/027** (2013.01); **B23K 9/0253** (2013.01); **B23K 31/003** (2013.01);  
(Continued)

**13 Claims, 3 Drawing Sheets**



- |      |                    |           |    |                |         |       |           |
|------|--------------------|-----------|----|----------------|---------|-------|-----------|
| (51) | <b>Int. Cl.</b>    |           | JP | 2013146753 A * | 8/2013  | ..... | B23K 9/04 |
|      | <i>F16L 41/04</i>  | (2006.01) | RU | 2566798 C2     | 10/2015 |       |           |
|      | <i>B23K 37/04</i>  | (2006.01) | WO | 2016050866 A1  | 4/2016  |       |           |
|      | <i>F16L 41/06</i>  | (2006.01) |    |                |         |       |           |
|      | <i>B23K 31/00</i>  | (2006.01) |    |                |         |       |           |
|      | <i>B23K 9/025</i>  | (2006.01) |    |                |         |       |           |
|      | <i>B23K 33/00</i>  | (2006.01) |    |                |         |       |           |
|      | <i>B23K 101/06</i> | (2006.01) |    |                |         |       |           |
|      | <i>B23K 101/10</i> | (2006.01) |    |                |         |       |           |
|      | <i>B23K 103/04</i> | (2006.01) |    |                |         |       |           |
|      | <i>B23K 103/02</i> | (2006.01) |    |                |         |       |           |
|      | <i>B23K 9/035</i>  | (2006.01) |    |                |         |       |           |

OTHER PUBLICATIONS

Translation of JP-2007021530-A (Year: 2007).\*

Translation of JP-2013146753-A (Year: 2013).\*

ASME B31.8-2003 (p. 13) (Year: 2004).\*

Jaske et al, "Pipeline Repair Manual", "Catalog No. L52047", Aug. 8, 2006, pp. 15-21, Publisher Pipeline Research Council International.

Guangming et al, "Influence of the welding sequence on residual stress and distortion of fillet welded structures", "SP-002783047", Dec. 29, 2015, pp. 30-55, vol. 46, Publisher: Elsevier; Marine Structures 2015.

Mizuno et al, "Appropriate Welding Conditions of Terper Bead Weld REpair for SQV2A Pressure Vessel Steel", "XP-002783045", Oct. 6, 2004.

Welding Technology Institute of Australia, "Temper Bead Welding", Mar. 1, 2006, Publisher: XP-002783046.

Tsai et al, "Welding Distortion of a Thin-Plate Panel Structure", "XP-002783048", May 1, 1999, pp. 156-165, Publisher: Welding Research Supplement.

Alekseev et al, "Welding in industrial construction, Manual for technical schools, 4th edition", , p. 116, Publisher: Stroyizdat, 1944, Published in: Moscow, RU.

- (52) **U.S. Cl.**  
 CPC ..... *B23K 33/006* (2013.01); *B23K 37/04* (2013.01); *F16L 41/04* (2013.01); *F16L 41/06* (2013.01); *F16L 55/18* (2013.01); *B23K 9/035* (2013.01); *B23K 2101/06* (2018.08); *B23K 2101/10* (2018.08); *B23K 2103/02* (2018.08); *B23K 2103/04* (2018.08)

(56) **References Cited**

FOREIGN PATENT DOCUMENTS

- |    |                |        |       |            |
|----|----------------|--------|-------|------------|
| JP | 57134277 A *   | 2/1981 | ..... | B23K 9/23  |
| JP | 2007021530 A * | 2/2007 | ..... | B23K 31/00 |

\* cited by examiner




FIG. 1A




FIG. 1B




FIG. 1C




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 3






FIG. 2D

1

**THICK, LONG SEAM WELDING SYSTEM  
AND METHOD FOR DISTORTION  
CONTROL AND NON POST WELD HEAT  
TREATMENT OF PIPELINE HOT TAP  
FITTINGS**

CROSS-REFERENCE TO PENDING  
APPLICATIONS

This application claims priority to U.S. Provisional Patent Application No. 64/478,950, filed Mar. 30, 2017, and 62/556,050, filed Sep. 8, 2017, each of which is incorporated herein by reference.

BACKGROUND

This disclosure relates to welding of fittings that are installed on in-service pipelines. More specifically, the disclosure relates to welding performed on long seams of pipeline hot tap fittings.

In-service welding of thick section fittings (1¼ inches [32 mm] or more) long seam groove butt joints in carbon steel plate (e.g. ASTM A537 Class 1) is challenging because traditional stress relief via post weld heat treatment is not practical on in-service pipelines and the weld thickness results in high levels of stress often resulting in distortion and deformation of the fitting which can compromise the intended functionality of the fitting. Additionally, there is accelerated cooling caused by the thickness of the fitting and the pipeline product. Therefore, there is a desire to control distortion and deformation and provide local stress relief for applications where thick fittings are required to meet design conditions and post weld heat treatment is not practical. See ASME B31.8-2016, Ch. VIII, 825 (requiring stress relief in welds in all carbon steels when nominal wall thickness exceeds 1¼ inches [32 mm]).

Prior art approaches begin welding at one end of the joint and progress to the other end—typically left to right depending on the required orientation of the fitting's flange tee—and stack weld beads from the bottom up.

SUMMARY

In embodiments of a method for controlling fitting bore distortion when welding a seam located between two sleeve halves of a fitting located on a carrier pipe, the seam being at least 1¼ inches (32 mm) thick. The method includes dividing the seam on each side of the carrier pipe into a left outer third section, a middle third section, and a right outer third section and then, on each side of the carrier pipe, welding the middle third section of the fitting in a pyramid shaped manner completely to the weld cap. Once the middle sections are welded, the left and right third sections on either side of the fitting are then welded using an outward progression from an end adjacent to the middle section along the profile of the seam bevel.

The welding of each third section includes temper bead welding of the first layers (until sufficient weld metal is deposited such that additional weld beads will no longer affect the heat affected zone of the fitting) in the longitudinal seam bevel. The temper bead welding is controlled in a particular way such that stress relief and grain refinement is achieved without the need for traditional post weld heat treatment.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A is front elevation view of a hot tap or plugging fitting as it would be arranged about a section of pipe and

2

presenting a thick, long seam on each side of the fitting in need of welding. In some embodiments, the fitting is a T. D. Williamson (Tulsa, Okla.) STOPPLE® fitting or its equivalent.

FIG. 1B is a side elevation view of the fitting of FIG. 1A. FIG. 1C is a side elevation detail view of the thick, long seam of FIG. 1B.

FIG. 2A is an embodiment of a weld made according to this disclosure.

FIG. 2B is a side elevation view of the thick, long seam prior to welding.

FIG. 2C is an embodiment of a welding system and method of this disclosure.

FIG. 2D is an embodiment of the completed pyramid-shaped middle third (center) section.

FIG. 3 is a schematic illustrating four inside diameter measurement dimensions, with ØA being a diameter in an axial flow or X direction and ØB being a diameter in a direction perpendicular to the axial flow or a Y direction). ØC and ØD are diameters at ±45° relative to the axial flow in the X-Y plane.

ELEMENTS AND NUMBERING USED IN THE  
DRAWINGS AND DETAILED DESCRIPTION

- 10 Fitting
- 11 Upper sleeve half
- 13 Lower sleeve half
- 15 Gap
- 17 Root gap
- 19 Bevel
- 20 Long seam
- 21 First side of pipe or fitting
- 23 Second side of pipe or fitting
- 25 Outer edge
- 30 Long seam weld
- 31 Center third section
- 33 End
- 35 Center
- 37 Outer third section
- 39 End
- 47 First weld layer
- 49 Second weld layer
- 50 Backing strip
- 60 Bore
- L Length
- P Carrier pipe
- S Weld bead placement overlap
- T Thickness

Definitions

For the purpose of this disclosure, a thick, long seam is a seam requiring welding located between the upper and lower sleeve halves of a fitting after final fit-up on a carrier pipe, with the sleeve halves comprised of carbon steel plate at least 1¼ inches (32 mm) thick. In embodiments, the fitting may be a hot tap fitting and the material is carbon steel such as ASTM A537 Class 1 plate that is at least 1¼ inches (32 mm) thick.

In-service piping is piping containing a service fluid at any pressure or flow rate, including zero pressure and flow rate.

DETAILED DESCRIPTION

In embodiments of a thick, long seam welding system and method for non-post weld heat treatment and distortion



control, the long (longitudinally extending) seam **20** located between opposing upper and lower sleeve halves **11**, **13** of a fitting **10** for use about a carrier pipe is welded using a tempered head, controlled deposition on each side **21**, **23** of the seam **20**, with a middle (center) third **31** of the seam **20** welded first in an inward progression (from ends **33** to center **35**) and the two outer thirds **37A** & **B** of the seam **20** welded in an outward progression (from end **33** to end **39**). The weld extends an entire length **L** of the seam **20**. The thickness **T** of the seam **20** is at least 1¼ inches (32 mm).

Two welders may be used, one on each side **21**, **23** of the carrier pipe **P**, or four welders may be used, two on each side **21**, **23**. When two welders are on each side **21**, **23**, the outer third sections may be welded at the same time, with one welder welding the left outer third and another welder welding the right outer third.

Referring to FIG. 2B, prior to welding and final fit-up location, a backing strip **50** is placed along the length **L** of the seam **20** against the carrier pipe **P**. The backing strip **50** may be a flat bar ⅛ inch by ¼ inches (3.2 mm×32 mm). The sleeves **11**, **13** each have a bevel **19** that may present a seam **20** having an included angle of about 60°±15°. The root gap **17** should be as tight as practicable while ensuring sufficient gap remains to facilitate full penetration welding. In some embodiments, the root gap **17** is in a range of ⅜ inch to ½ inch (2.4 mm to 12.7 mm). In other embodiments, the root gap **17** is approximately ⅛ inch (3.2 mm).

Next, the fitting **10** is intermittently tack welded in the weld root's long seam **20** butt joint over the total length of the seam **20** in order to ensure the fitting's final correct welding position. The middle center section **31**, measuring about one-third of the total length **L** of the long seam **20**, is tack welded first to increase the fitting's stiffness. Because the backing strip **50** isolates the seam weld **30** from the carrier pipe **P**, in-service welding standards like those applied to the end circumferential welds do not apply to the long seam weld **30**.

A first weld layer **47** is then laid down, starting with the middle third section **31**, using an inward progression (from end **33** to center **35**), and following the profile of the bevel **19**. See FIGS. 2A & 2D. A second (tempered bead) layer **49** with dimension **S** is then laid down on top of the first **47**, again using the inward progression. Bead overlap may be in a range of 25% to 75%. Note both the first layer **47** and second layer **49** require the need for overlap, but only the second layer **49** requires the need to follow weld bead placement "S".

This sequencing continues in the middle third section **31** as the weld layers build in a pyramid fashion one on the other toward the outer edge **25** of the seam **20** and until the gap **15** between the sleeve halves **11**, **13** is filled. Temper bead welding is utilized for a minimum of two layers until

after about a ⅜-inch (4.8 mm) weld deposit is achieved after which large diameter welding electrodes (e.g. ¼", ⅜" or ⅝") are used to aid in minimizing stress and ultimately distortion. Care must be used when depositing large diameter weld passes over the temper bead layers so as not to compromise the integrity of the temper bead layers particularly the beneficial effects of grain refinement and stress relief.

Once the middle section **31** pyramid-like weld is complete, welding may begin on the two outer third sections **37**. The same sequencing as that used in the middle section **31** takes place, with an outward progression being used (from middle section end **33** to outer section end **39**) as the profile of the bevel **19** is followed. Circumferential welding may then occur at ends **39**.

In some embodiments, the method includes dividing the seam **20** on each side **21**, **23** of the carrier pipe **P** into a left outer third section **33**, a middle third section **31**, and a right outer third section **35** and, for each side **21**, **23**, welding the middle third section **31** using an inward progression from an end **33** of the middle third section **31** along a profile of a seam bevel **19**, and welding the left outer third section **33**, the right outer third section **35**, or the left and right outer third sections **33**, **35** using an outward progression from an end **33** adjacent to the middle section **31** along a profile of the seam bevel **19**. The welding of each section **31**, **33**, **35** includes a temper bead welding of at least a first layer **47** of surface bead placement by a second layer **49** of surface bead placement.

Compared to prior art methods, for a same size long seam **20** this method typically requires more time. However, no post weld heat treatment is required. Additionally, resulting distortion and deformation are dramatically reduced compared to prior art methods which helps maintain the integrity and ultimately desired functionality of the fitting. For example, prior art methods may result in distortion which increases the risk of cutting into the inside diameter of a fitting's bore **60** during the carrier pipe hole tapping operation. It can also compromise the seal interface around the completion plug's O-ring diameter  $\text{ØA-D}$  located in the bore **60** (when applicable). See FIG. 3. Typically, the tolerance is about ⅛ inch (0.125 inch or 3.2 mm) or ⅜ inch per side (0.0625 inch or 1.6 mm), with negative distortion in the axial flow direction and positive distortion in the perpendicular direction (as a general rule). Typical distortion results using the new system and method are shown in Tables 1-2 below.

Although the system and method have been described with reference to particular means, materials and embodiments, the system and method are not intended to be limited to those particulars; rather, to extend to all functionally equivalent embodiments and methods such as are within the scope of the appended claims.

TABLE 1

Example Results of Welding Technique Applied to 36-inch (91 cm) STOPPLE ® Fitting					
Dim. @O-ring	Start	Final After		Dia. Diff. as %	
	Dim (in.)	Welding 2nd Circ	Fillet Dim	Dia. diff	Per/side Diff
A Dim.	35.1300	35.1150	-0.0150	-0.0075	-12.0
B Dim.	35.1300	35.1490	0.0090	0.0045	7.2
A Dim.	35.1250	35.1150	-0.0100	-0.0050	-8.0
B Dim.	35.1250	35.1490	0.0150	0.0070	11.2



TABLE 2

Example Results of Welding Technique Applied to 42-inch (107 cm) STOPPLE® Fitting									
Dim. @O-ring	Start Dim (in.)	After Long- seam Welds	Dia. diff Start	Per/ side Diff Start	Dia. Diff. as % of Total Toler- ance (1/8")	After 2nd Circ Weld and Cooled	Dia. diff Start	Per/ side Diff Start	Dia. Diff. as % of Total Toler- ance (1/8")
A Dim.	40.9982	40.968	-0.0302	-0.0151	-24.16	40.986	0.0122	-0.0061	-9.76
B Dim.	40.9965	41.030	0.0335	0.01675	26.80	41.0054	0.0089	0.00445	7.12
C Dim.	40.9962	40.993	-0.0032	-0.0016	-2.56	40.9995	0.0033	0.00165	2.64
D Dim.	40.9962	40.9974	0.0012	0.0006	0.96	40.9987	0.0025	0.00125	2.00

What is claimed:

1. A method for controlling fitting bore distortion when welding a seam located between two sleeve halves of a fitting located on an in-service carrier pipe where the seam after welding must remain in its as-welded condition, the seam being at least 1¼ inches (32 mm) thick, the method comprising:

first welding a middle third section of the seam in multiple weld layers using only an inward progression starting from an end of the middle third section along a profile of a seam bevel, each weld layer having a different length than that of an adjacent weld layer, the weld layers decreasing in length from a root gap of the seam to an upper end of the seam; and,

after welding the middle third section, welding a left and a right outer third section of the seam using only an outward progression from an end adjacent to the middle third section along a profile of the seam bevel;

wherein the welding of each of the three sections includes a controlled temper bead welding technique applied only to a first two weld layers using a first diameter size welding electrode; and

wherein at least one second diameter size welding electrode having a diameter larger than that of the first diameter size welding electrode is used on remaining weld layers.

2. The method of claim 1 wherein the fitting is a hot-tap fitting.

3. The method of claim 1, wherein after the welding of the three sections the fitting bore distortion in an axial direction of the in-carrier service pipe, in a direction perpendicular to the axial direction, and in a direction at 45° to the axial direction, is no greater than 1/8".

4. The method of claim 1, wherein after the welding of the three sections the fitting bore distortion in an axial direction of the in-carrier service pipe, in a direction perpendicular to the axial direction, and in a direction at 45° to the axial direction, is in a range of -12% to +12% of a total tolerance.

5. A method for controlling fitting bore distortion when welding a seam located between two sleeve halves of a fitting located on an in-service carrier pipe where the seam after welding must remain in its as-welded condition, the seam being at least 1¼ inches (32 mm) thick, the method comprising:

welding a middle third section of the seam in multiple weld layers beginning along a profile of a seam bevel, each weld layer being made in only one welding direction and having a different length than that of an adjacent weld layer, the weld layers decreasing in

length from a root gap of the seam to an upper end of the seam; and, after welding the middle third section of the seam,

welding a left and a right outer third section of the seam beginning along a profile of the seam bevel, each of the left and right outer third sections being welded, respectively, in only one welding direction;

wherein the welding of each of the three sections includes a controlled temper bead welding technique of only a first two weld layers of the multiple weld layers; and wherein the only one welding direction used in each section is selected from the group consisting of (i) an outward progression and (ii) an inward progression.

6. The method of claim 5 further comprising the welding direction of the middle third section being an inward progression starting from an end of the middle third section.

7. The method of claim 5, wherein after the welding of the three sections the fitting bore distortion in an axial direction of the in-carrier service pipe, in a direction perpendicular to the axial direction, and in a direction at 45° to the axial direction, is no greater than 1/8".

8. The method of claim 5, wherein after the welding of the three sections the fitting bore distortion in an axial direction of the in-carrier service pipe, in a direction perpendicular to the axial direction, and in a direction at 45° to the axial direction, is in a range of -12% to +12% of a total tolerance.

9. A fitting located on an in-service carrier pipe, the fitting comprising:

a seam on one side of the in-service-carrier pipe and another seam on an opposite side of the in-service carrier pipe, each seam being at least 1¼ inches (32 mm) thick and including a middle third section and a left and a right outer third section,

the middle third section of the seam including a weld extending from a root gap of the seam to an upper end of the seam and containing multiple weld layers welded using an inward progression starting from an end of the middle third section along a profile of a seam bevel, each weld layer having a different length than that of an adjacent weld layer, the weld layers decreasing in length from the root gap of the seam to the upper end of the seam; and

the left and right outer third sections of the seam being in an unwelded state from the root gap of the seam to the upper end of the seam;

wherein only a first two weld layers of the middle-third section includes a controlled temper bead; and

wherein no post-weld heat treatment is applied to the welded seam; and



wherein a total distortion of the fitting bore in an axial direction of the in-carrier service pipe, in a direction perpendicular to the axial direction, and in a direction at 45° to the axial direction, is no greater than 1/8".

10. The fitting of claim 9, wherein a bead overlap of the first two weld layers is in a range of 25% to 75%. 5

11. The fitting of claim 9, wherein the first two weld layers result in a weld deposit of about 3/16".

12. The fitting of claim 9, further comprising, the left and right outer third sections transitioning between the unwelded state and a welded state, wherein only a first two weld layers of each outer third section include a controlled temper bead, and wherein the welded seam of each outer third section is welded in a single welding direction. 10

13. The fitting of claim 9 wherein the fitting is a hot-tap fitting. 15

\* \* \* \* \*