



US011205633B2

(12) **United States Patent**  
**Bajwa et al.**

(10) **Patent No.:** **US 11,205,633 B2**  
(45) **Date of Patent:** **Dec. 21, 2021**

(54) **METHODS OF BONDING OF SEMICONDUCTOR ELEMENTS TO SUBSTRATES, AND RELATED BONDING SYSTEMS**

(71) Applicant: **Kulicke and Soffa Industries, Inc.**,  
Fort Washington, PA (US)

(72) Inventors: **Adeel Ahmad Bajwa**, Blue Bell, PA  
(US); **Thomas J. Colosimo, Jr.**, West  
Chester, PA (US)

(73) Assignee: **Kulicke and Soffa Industries, Inc.**,  
Fort Washington, PA (US)

(\* ) Notice: Subject to any disclaimer, the term of this  
patent is extended or adjusted under 35  
U.S.C. 154(b) by 0 days.

(21) Appl. No.: **16/736,416**

(22) Filed: **Jan. 7, 2020**

(65) **Prior Publication Data**

US 2021/0098414 A1 Apr. 1, 2021

**Related U.S. Application Data**

(60) Provisional application No. 62/907,562, filed on Sep.  
28, 2019, provisional application No. 62/790,259,  
filed on Jan. 9, 2019.

(51) **Int. Cl.**  
**H01L 21/44** (2006.01)  
**H01L 23/00** (2006.01)

(52) **U.S. Cl.**  
CPC ..... **H01L 24/75** (2013.01); **H01L 24/81**  
(2013.01); **H01L 2224/75102** (2013.01);  
(Continued)

(58) **Field of Classification Search**  
CPC ..... H01L 24/75; H01L 24/81; H01L  
2224/81203; H01L 2224/81205; H01L  
2224/81801; H01L 2224/75102  
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,332,424 B2 2/2008 Bélanger et al.  
7,648,901 B2\* 1/2010 Tu ..... B23K 1/008  
438/613

(Continued)

FOREIGN PATENT DOCUMENTS

JP 2013-251404 12/2013  
KR 10-2013-0083400 7/2013  
WO WO2012166911 A2 12/2012

OTHER PUBLICATIONS

International Search Report dated Apr. 29, 2020 for International  
Patent Application No. PCT/US2020/012690.


*Primary Examiner* — Vu A Vu

(74) *Attorney, Agent, or Firm* — Christopher M Spletzer,  
Sr.

(57) **ABSTRACT**

A bonding system for bonding a semiconductor element to a substrate is provided. The bonding system includes a substrate oxide reduction chamber configured to receive a substrate. The substrate includes a plurality of first electrically conductive structures. The substrate oxide reduction chamber is configured to receive a reducing gas to contact each of the plurality of first electrically conductive structures. The bonding system also includes a substrate oxide prevention chamber for receiving the substrate after the reducing gas contacts the plurality of first electrically conductive structures. The substrate oxide prevention chamber has an inert environment when receiving the substrate. The bonding system also includes a reducing gas delivery system for providing a reducing gas environment during bonding of a semiconductor element to the substrate.

**18 Claims, 25 Drawing Sheets**



(52) **U.S. Cl.**  
CPC ..... H01L 2224/81203 (2013.01); H01L  
2224/81205 (2013.01); H01L 2224/81801  
(2013.01)

(58) **Field of Classification Search**  
USPC ..... 438/455  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,864,011	B2 *	10/2014	Abe	.....	H01L 24/81 228/42
9,282,650	B2	3/2016	Dhavaleswarapu et al.		
9,418,961	B2	8/2016	Yu et al.		
2002/0130164	A1	9/2002	Matsuki et al.		
2008/0188070	A1	8/2008	Johnson et al.		
2009/0313816	A1	12/2009	Cavazza		
2010/0084438	A1	4/2010	Biggs et al.		
2010/0089978	A1	4/2010	Hughlett et al.		
2011/0045653	A1	2/2011	Ohno et al.		
2012/0104076	A1	5/2012	Suga et al.		
2013/0181040	A1	7/2013	Watanabe et al.		
2015/0048523	A1	2/2015	Suga et al.		
2017/0271145	A1	9/2017	Dietze et al.		
2019/0252349	A1	8/2019	Bajwa		

\* cited by examiner






FIG. 1A




FIG. 1B






FIG. 2A




FIG. 2B






FIG. 2C




FIG. 2D








FIG. 2F







FIG. 2G








FIG. 3B




FIG. 4






FIG. 5




FIG. 6






FIG. 7




FIG. 8






FIG. 9




FIG. 10A






FIG. 10B




FIG. 10C






FIG. 10D




FIG. 11A






FIG. 11B




FIG. 110






FIG. 11D

**1****METHODS OF BONDING OF  
SEMICONDUCTOR ELEMENTS TO  
SUBSTRATES, AND RELATED BONDING  
SYSTEMS****CROSS-REFERENCE TO RELATED  
APPLICATIONS**

This application claims the benefit of U.S. Provisional Application No. 62/790,259, filed Jan. 9, 2019, and of U.S. Provisional Application No. 62/907,562, filed Sep. 28, 2019, the contents of both of which are incorporated herein by reference.

**FIELD**

The invention relates to bonding systems and processes (such as flip chip, thermocompression, and thermosonic bonding systems and processes), and more particularly, to improved systems and methods for bonding a semiconductor element to a substrate.

**BACKGROUND**

Traditional semiconductor packaging typically involves die attach processes and wire bonding processes. Advanced semiconductor packaging technologies (e.g., flip chip bonding, thermocompression bonding, etc.) continue to gain traction in the industry. For example, in thermocompression bonding (i.e., TCB), heat and/or pressure (and sometimes ultrasonic energy) are used to form a plurality of interconnections between (i) electrically conductive structures on a semiconductor element and (ii) electrically conductive structures on a substrate.

In certain flip chip bonding or thermocompression bonding applications, the electrically conductive structures of the semiconductor element and/or the substrate may include copper structures (e.g., copper pillars) or other material(s) that is subject to oxidation and/or other contamination. In such applications, it is desirable to provide an environment suitable for bonding. Conventionally, such an environment may be provided by using a reducing gas at the bonding area to reduce potential oxidation and/or contamination of the electrically conductive structures of the semiconductor element or the substrate to which it will be bonded.

Thus, it would be desirable to provide improved methods of bonding semiconductor elements to a substrate with the use of a reducing gas.

**SUMMARY**

According to an exemplary embodiment of the invention, a bonding system for bonding a semiconductor element to a substrate is provided. The bonding system includes a substrate oxide reduction chamber configured to receive a substrate. The substrate includes a plurality of first electrically conductive structures. The substrate oxide reduction chamber is configured to receive a reducing gas to contact each of the plurality of first electrically conductive structures. The bonding system also includes a substrate oxide prevention chamber for receiving the substrate after the reducing gas contacts the plurality of first electrically conductive structures. The substrate oxide prevention chamber has an inert environment when receiving the substrate. The bonding system also includes a reducing gas delivery system for providing a reducing gas environment during bonding of a semiconductor element to the substrate. The semiconduc-

**2**

tor element includes a plurality of second electrically conductive structures. The plurality of first electrically conductive structures are configured to be bonded with corresponding ones of the plurality of second electrically conductive structures.

According to another exemplary embodiment of the invention, a method of bonding a semiconductor element to a substrate is provided. The method includes the steps of: moving a substrate into a substrate oxide reduction chamber, the substrate including a plurality of first electrically conductive structures, the substrate oxide reduction chamber configured to receive a reducing gas to contact each of the plurality of first electrically conductive structures; moving the substrate into a substrate oxide prevention chamber after the reducing gas contacts the plurality of first electrically conductive structures, the substrate oxide prevention chamber having an inert environment when receiving the substrate; and providing a reducing gas environment during bonding of a semiconductor element to the substrate, the semiconductor element including a plurality of second electrically conductive structures, the plurality of first electrically conductive structures being configured to be bonded with corresponding ones of the plurality of second electrically conductive structures.

According to yet another exemplary embodiment of the invention, a method of bonding a semiconductor element to a substrate is provided. The method includes the steps of: (a) carrying a semiconductor element with a bonding tool of a bonding machine, the semiconductor element including a plurality of first electrically conductive structures; (b) supporting a substrate with a support structure of the bonding machine, the substrate including a plurality of second electrically conductive structures; (c) providing a reducing gas in contact with each of the plurality of first electrically conductive structures and the plurality of second electrically conductive structures; and (d) bonding the corresponding ones of the plurality of first electrically conductive structures to the respective ones of the plurality of second electrically conductive structures after step (c). At least one of the plurality of first electrically conductive structures and the plurality of second electrically conductive structures includes a solder material.

**BRIEF DESCRIPTION OF THE DRAWINGS**

The invention is best understood from the following detailed description when read in connection with the accompanying drawings. It is emphasized that, according to common practice, the various features of the drawings are not to scale. On the contrary, the dimensions of the various features are arbitrarily expanded or reduced for clarity.

FIG. 1A is a block diagram illustration of a bonding system for bonding a semiconductor element to a substrate in accordance with an exemplary embodiment of the invention;

FIG. 1B is a block diagram illustration of a bonding system for bonding a semiconductor element to a substrate in accordance with an exemplary embodiment of the invention;

FIGS. 2A-2G are a series of block diagram illustrations of the bonding system of FIG. 1A, illustrating a method of bonding a semiconductor element to a substrate in accordance with an exemplary embodiment of the invention;

FIGS. 3A-3B are a series of block diagram illustrations of the bonding system of FIG. 1A, illustrating a method of bonding a semiconductor element to a substrate in accor-



dance with an exemplary embodiment of the invention, while preparing another substrate for bonding;

FIG. 4 is a block diagram illustration of a bonding system for bonding a semiconductor element, having conductive structures including a solder material, to a substrate in accordance with an exemplary embodiment of the invention;

FIG. 5 is a block diagram illustration of a bonding system for bonding a semiconductor element to a substrate, having conductive structures including a solder material, in accordance with an exemplary embodiment of the invention;

FIG. 6 is a block diagram illustration of a bonding system for bonding a semiconductor element, having conductive structures including a solder material, to a substrate, having conductive structures including a solder material, in accordance with an exemplary embodiment of the invention;

FIG. 7 is a block diagram illustration of a bonding system for bonding a semiconductor element, having conductive structures formed of a solder material, to a substrate in accordance with an exemplary embodiment of the invention;

FIG. 8 is a block diagram illustration of a bonding system for bonding a semiconductor element to a substrate, having conductive structures formed of a solder material, in accordance with an exemplary embodiment of the invention;

FIG. 9 is a block diagram illustration of a bonding system for bonding a semiconductor element, having conductive structures formed of a solder material, to a substrate, having conductive structures formed of a solder material, in accordance with an exemplary embodiment of the invention;

FIGS. 10A-10D are a series of block diagram illustrations of the bonding system of FIG. 4, illustrating a method of bonding a semiconductor element to a substrate in accordance with an exemplary embodiment of the invention; and

FIGS. 11A-11D are a series of block diagram illustrations of another bonding system, illustrating a method of bonding a semiconductor element to a substrate in accordance with an exemplary embodiment of the invention.

#### DETAILED DESCRIPTION

As used herein, the term “semiconductor element” is intended to refer to any structure including (or configured to include at a later step) a semiconductor chip or die. Exemplary semiconductor elements include a bare semiconductor die, a semiconductor die on a substrate (e.g., a leadframe, a PCB, a carrier, a semiconductor chip, a semiconductor wafer, a BGA substrate, a semiconductor element, etc.), a packaged semiconductor device, a flip chip semiconductor device, a die embedded in a substrate, a stack of semiconductor die, amongst others. Further, the semiconductor element may include an element configured to be bonded or otherwise included in a semiconductor package (e.g., a spacer to be bonded in a stacked die configuration, a substrate, etc.).

As used herein, the term “substrate” is intended to refer to any structure to which a semiconductor element may be bonded. Exemplary substrates include, for example, a leadframe, a PCB, a carrier, a module, a semiconductor chip, a semiconductor wafer, a BGA substrate, another semiconductor element, etc.

In accordance with certain exemplary embodiments of the invention, a fluxless bonding system is provided using reducing gas/gases. The bonding system may be, for example, a flip chip bonding system, a thermocompression bonding system, a thermosonic bonding system, etc.

Aspects of the invention relate to a novel fluxless chip-to-substrate or chip-to-wafer system that avoids oxidation of metal and solder pads during bonding (e.g., during thermocompression bonding).

Exemplary systems include a “substrate oxide reduction chamber” (also referred to as a substrate cleaning compartment), a “substrate oxide prevention chamber” (also referred to as a substrate protection compartment), and a “reducing gas delivery system” (e.g., a localized chip and substrate oxide reduction bond head shroud, or other reducing gas delivery system) to eliminate the use of a fluxing process.

FIG. 1A illustrates exemplary bonding system 300. Bonding system 300 includes: a substrate source 300a (e.g., a wafer handler or other source) for providing a substrate(s) 104 (such as a wafer, a printed circuit board, etc.) on a support structure 300a1; and a processing system 300b. Substrate 104 is configured to be transferred to processing system 300b (e.g., including a tunnel 302, but may be a different type of structure). Tunnel 302 (or other structure, as desired) includes a substrate oxide reduction chamber 302a, a substrate oxide prevention chamber 302b, and a bonding location 302c (which is part of substrate oxide prevention chamber 302b). A reducing gas delivery system 308 is also included in processing system 300b.

In the example shown in FIG. 1A, because tunnel 302 includes both substrate oxide reduction chamber 302a and a substrate oxide prevention chamber 302b, at least a portion of substrate oxide reduction chamber 302a has a common boundary with substrate oxide prevention chamber 302b. Substrate oxide reduction chamber 302a is closed using entry door 302a1 (which closes opening 302a1a) and exit door 302a2 (which closes opening 302a2a). Another reducing gas delivery system 302d (which may be interconnected with reducing gas delivery system 308 to use a common source of reducing gas) is provided to provide a reducing gas (e.g., formic acid vapor) in substrate oxide reduction chamber 302a. After processing (e.g., removal of oxides from conductive structures of substrate 104) in substrate oxide reduction chamber 302a, a substrate transfer system (which may be part of a material handling system including support structure 102) is used to transfer substrate 104 through exit door 302a2 to substrate oxide prevention chamber 302b. Substrate oxide prevention chamber 302b includes an inert environment 306 (e.g., through a nitrogen supply, not shown for simplicity). A material handling system (e.g., including support structure 102) is used to move substrate 104 within substrate oxide prevention chamber 302b to a bonding location 302c. While at bonding location 302c, a reducing gas 130 is provided by reducing gas delivery system 308.

FIG. 1A also illustrates bond head assembly 106, including heater 108, and bonding tool 110. FIG. 1A also illustrates main exhaust 304 which pulls exhaust gases (e.g., gases such as reducing gas vapors) through piping 304a and 114b1 (where piping 114b1 is coupled, directly or indirectly, to center channel 114b described below). Bond head assembly 106 carries a bond head manifold 114 for receiving and distributing fluids (e.g., gases, vapors, etc.) as desired in the given application. Details of an exemplary bond head assembly 106, including exemplary bond head manifold 114, are described below in connection with FIGS. 4-9, and FIGS. 10A-10D.

In connection with a bonding operation, semiconductor element 112 is bonded to substrate 104 using bonding tool 110. During the bonding operation, corresponding ones of electrically conductive structures of semiconductor element 112 are bonded (e.g., using heat, force, ultrasonic energy, etc.) to respective ones of electrically conductive structures



of substrate **104**. Bond head manifold **114** provides a reducing gas **130** (e.g., where the reducing gas is a saturated vapor gas) in the area of semiconductor element **112** and substrate **104** in connection with a bonding operation. After reducing gas **130** is distributed in the area of semiconductor element **112** and substrate **104**, reducing gas **130** contacts surfaces of each of electrically conductive structures of semiconductor element **112** and substrate **104**.

FIG. 1B illustrates exemplary bonding system **400**, which is similar in many respect to bonding system **300** of FIG. 1A (where like elements have the same reference numerals, or a numeral beginning with a “4” instead of a “3”). Bonding system **400** includes a substrate source **400a** (e.g., a wafer handler or other source) for providing a substrate(s) **104** (such as a wafer, a printed circuit board, etc.) on a support structure **400a1**. Substrate **104** is configured to be transferred to processing system **400b** (e.g., including a tunnel **402**, but may be a different type of structure). Tunnel **402** (or other structure, as desired) includes a substrate oxide reduction chamber **402a**, a substrate oxide prevention chamber **402b**, and a bonding location **402c** (which is part of substrate oxide prevention chamber **402b**).

In the example shown in FIG. 1B, because tunnel **402** includes both substrate oxide reduction chamber **402a** and a substrate oxide prevention chamber **402b**, at least a portion of substrate oxide reduction chamber **402a** has a common boundary with substrate oxide prevention chamber **402b**. A reducing gas delivery system **408** is also included in processing system **400b**. Substrate oxide reduction chamber **402a** is closed using entry door **402a1** (which closes opening **402a1a**) and exit door **402a2** (which closes opening **402a2a**). Another reducing gas delivery system **402d** (which may be interconnected with reducing gas delivery system **408** to use a common source of reducing gas) is provided to provide a reducing gas (e.g., formic acid vapor) in substrate oxide reduction chamber **402a**. After processing (e.g., removal of oxides from conductive structures of substrate **104**) in substrate oxide reduction chamber **402a**, a substrate transfer system (which may be part of a material handling system including support structure **102**) is used to transfer substrate **104** through opening **402a2a** to substrate oxide prevention chamber **402b**. Substrate oxide prevention chamber **402b** includes an inert environment **406** (e.g., through a nitrogen supply, not shown for simplicity). A material handling system (e.g., including support structure **102**) is used to move substrate **104** within substrate oxide prevention chamber **402b** to a bonding location **402c**. While at bonding location **402c**, a reducing gas **130** is provided by reducing gas delivery system **408**.

FIG. 1B also illustrates bond head assembly **106**, including heater **108**, and bonding tool **110**. FIG. 1B also illustrates main exhaust **404** which pulls exhaust gases (e.g., gases such as reducing gas vapors) through piping **404a** and **404b**. A manifold **214** is provided for receiving and distributing fluids (e.g., gases, vapors, etc.) as desired in the given application. Details of an exemplary bond head assembly **106**, and an exemplary manifold **214**, are described below in connection with FIGS. 11A-11D).

In connection with a bonding operation, semiconductor element **112** is bonded to substrate **104** using bonding tool **110**. During the bonding operation, corresponding ones of electrically conductive structures of semiconductor element **112** are bonded (e.g., using heat, force, ultrasonic energy, etc.) to respective ones of electrically conductive structures of substrate **104**. Manifold **214** provides a reducing gas **130** (e.g., where the reducing gas is a saturated vapor gas) in the area of semiconductor element **112** and substrate **104** in

connection with a bonding operation. After reducing gas **130** is distributed in the area of semiconductor element **112** and substrate **104**, reducing gas **130** contacts surfaces of each of electrically conductive structures of semiconductor element **112** and substrate **104**.

FIG. 2A-2G illustrate a method of bonding a semiconductor element **112** to a substrate **104** in connection with an exemplary embodiment of the invention, using bonding system **300** shown in FIG. 1A. FIG. 2A illustrates a substrate **104** in substrate source **300a**, with entry door **302a1** in an open position. Substrate oxide reduction chamber **302a** and substrate oxide prevention chamber **302b** have an inert environment **306** (e.g., a nitrogen environment). At FIG. 2B, substrate **104** has been moved into substrate oxide reduction chamber **302a** through opening **302a1a** using a substrate handling system (e.g., a material handling system including support structure **102**). At FIG. 2C, entry door **302a1** is closed, and a reducing gas **130** (e.g., formic acid vapor) is provided in substrate oxide reduction chamber **302a** via reducing gas delivery system **302d**. Reducing gas **130** removes residual oxide from the metal and solder pads (i.e., conductive structures) on substrate **104**. At FIG. 2D, exit door **302a2** is opened, and substrate **104** is transferred from substrate oxide reduction chamber **302a** to substrate oxide prevention chamber **302b** as shown in FIG. 2E. Substrate oxide prevention chamber **302b** includes an inert environment **306** (e.g., a nitrogen environment). In FIG. 2F, substrate **104** has been moved (e.g., using a material handling system including support structure **102**) to bonding location **302c**. At bonding location **302c**, a reducing gas **130** is directed from bond head manifold **114** toward semiconductor element **112** and substrate **104**. This reducing gas **130** is provided during bonding of semiconductor element **112** to substrate **104** to reduce/remove oxides on semiconductor element **112** as well as any remaining residual oxides on substrate **104**. At FIG. 2G, semiconductor element **112** has been bonded to substrate **104** using bond head assembly **106**.

Although FIGS. 2A-2G illustrate bonding system **300**, it is contemplated that a substantially similar process could be applied to bonding system **400** shown in FIG. 1B, or other bonding systems within the scope of the invention.

While the exemplary process of FIGS. 2A-2G illustrates a single substrate **104**, it is contemplated that a plurality of substrates **104** may be involved in system **300** (or bonding system **400** of FIG. 1B) (or another bonding system within the scope of the invention). Thus, FIGS. 3A-3B illustrate multiple substrates **104**. In FIG. 3A, a first substrate **104** (already having been processed using substrate oxide reduction chamber **302a**) is being moved to bonding location **302c** of substrate oxide prevention chamber **302b**. In FIG. 3B, while that substrate **104** is at bonding location **302c**, another substrate **104** is in substrate oxide reduction chamber **302a** (e.g., for cleaning of conductive structures on the another substrate **104**).

Exemplary aspects of the invention provides an opportunity to rework a substrate **104** (e.g., to transfer the substrate back to substrate oxide reduction chamber **302a**). For example, such an approach might be useful in situations where prolonged substrate exposures to heating is unavoidable, for example, bonding of small dies (e.g. 0.1-1 mm edge size) to a large area (e.g. 200-300 mm diameter substrate).

The invention may provide a number of benefits such as, for example: fluxless bonding (e.g., no fluxing of the semiconductor element or the substrate is required prior to or during bonding); reduction of oxides (e.g., metal oxides such as Cu and Sn oxides formed on pads/bumps) on both the semiconductor element and the substrate, as well as



prevention of oxide formation during long heat exposures; a low consumption of nitrogen gas (or other gas providing the inert environment in the substrate oxide prevention chamber); and a pre-cleaning chamber, an inert gas chamber, and an in-situ oxide cleaning bond head are all provided in the same bonding system.

While it is not explicitly shown in FIG. 1, FIGS. 2A-2G, and FIGS. 3A-3B, it is understood that a bonding operation may include bonding a semiconductor element **112** (or a plurality of elements) to a portion of the bond sites (bonding areas) of substrate **104** in the tunnel (e.g., tunnel **302/402**). For example, that portion of the bond sites of substrate **104** may be exposed by an opening in the tunnel **302/402**, where the bonding tool may be lowered through opening **302e/402e** to complete the bonding operation. By only exposing a portion of substrate **104** at a time, the environment within tunnel **302/402** is better maintained.

In connection with bonding (e.g., thermocompression bonding) of a semiconductor element **112** (including electrically conductive structures) to a substrate **104** (including electrically conductive structures), heat may be provided through bonding tool **110** (e.g., from a heater of bond head assembly **106**). A reducing gas may also be provided for cleaning oxides and/or other contaminants on the surface of the electrically conductive structures (of semiconductor element **112** and/or substrate **104**).

In specific examples of such methods, a semiconductor element **112** (e.g., a semiconductor chip) is transferred from a source (e.g., a semiconductor wafer) to bonding tool **110** of a thermocompression bonding machine or a flip chip bonding machine. With semiconductor element **112** carried by bonding tool **110** (e.g., using vacuum), bond head assembly **106** (carrying bonding tool **110**) is moved to a desired bonding position. The semiconductor element **112** is bonded to the bonding position of substrate **104** (e.g., while heating the semiconductor element **112** and/or the substrate **104**) (e.g., where the bonding occurs in the presence of a reducing gas). The respective conductive structures of the semiconductor element **112**, and/or the substrate **104** may include a solder material (e.g., the conductive structures may include a solder material at a contact surface, the conductive structures may be formed of a solder material, etc.), or the conductive structures may be formed of another conductive material (e.g., copper).

Throughout the various drawings (including FIGS. 4-9, FIGS. 10A-10D, and FIGS. 11A-11D), like reference numerals refer to the like elements, except where explained herein.

Referring now to FIG. 4, a bonding machine **100** (e.g., a flip chip bonding machine, a thermocompression bonding machine, etc.) is provided. Bonding machine **100** includes a support structure **102** for supporting a substrate **104** during a bonding operation (where substrate **104** includes a plurality of electrically conductive structures **104a**). Support structure **102** may include any appropriate structure for the specific application. In FIGS. 4-9 and FIGS. 10A-10D, support structure **102** includes top plate **102a** (configured to directly support substrate **104**), chuck **102c**, and heater **102b** disposed therebetween. In applications where heat for heating substrate **104** is desirable in connection with the bonding operation, a heater such as heater **102b** may be utilized.

FIG. 4 also illustrates bond head assembly **106**, which may be configured to move along (and about) a plurality of axes of bonding machine **100** such as, for example, the x-axis, y-axis, z-axis, theta (rotative) axis, etc. Bond head assembly **106** includes heater **108** and bonding tool **110**. That is, in certain bonding machines (e.g., thermocompres-

sion bonding machines) it may be desirable to heat the bonding tool. Thus, while FIG. 4 illustrates a separate heater **108** for heating bonding tool **110** (for heating semiconductor element **112** including a plurality of electrically conductive structures **112a**), it will be appreciated that heater **108** and bonding tool **110** may be integrated into a single element (e.g., a heated bonding tool).

In connection with a bonding operation, semiconductor element **112** is bonded to substrate **104** using bonding tool **110**. During the bonding operation, corresponding ones of electrically conductive structures **112a** are bonded (e.g., using heat, force, ultrasonic energy, etc.) to respective ones of electrically conductive structures **104a**. In FIG. 4, electrically conductive structures **112a** include a solder material **112a1** at a contact portion of each electrically conductive structure **112a** (e.g., a portion configured to contact the electrically conductive structures **104a** of substrate **104**).

In certain bonding applications (e.g., flip chip and/or thermocompression bonding with copper conductive structures), it is desirable to provide an environment suitable for bonding. Conventionally, such an environment may be provided by using a reducing gas at the bonding area to reduce potential contamination of the electrically conductive structures of the semiconductor element or the substrate to which it will be bonded.

In FIG. 4, bond head assembly **106** carries a bond head manifold **114** for receiving and distributing fluids (e.g., gases, vapors, etc.) as desired in the given application. In FIG. 4, while bond head manifold **114** is illustrated in a cross sectional view, the actual bond head manifold **114** surrounds bonding tool **110** (e.g., bond head manifold **114** surrounds bonding tool **110** in a coaxial configuration). Of course, bond head manifold **114** may have different configurations from that shown in FIG. 4. Further, it is understood that certain details of bond head manifold **114** (e.g., interconnection with piping **120**, structural details for distributing a reducing gas within bond head manifold **114**, structural details for distributing a shielding gas within bond head manifold **114**, structural details for drawing a vacuum through a center channel of bond head manifold **114**, etc.) are omitted for simplicity.

Bond head manifold **114** includes three channels **114a**, **114b**, **114c** having different functions. Outer channel **114a** receives a shielding gas (e.g., nitrogen gas) from shielding gas supply **118**. That is, a shielding gas is provided from shielding gas supply **118** (e.g., a nitrogen supply), through piping **120** (where piping **120** may include hard piping, flexible tubing, a combination of both, or any other structure adapted to carry the fluids described herein), to outer channel **114a** of bond head manifold **114**. From outer channel **114a** of bond head manifold **114**, the shielding gas **128** is provided as a shield from the outside environment (e.g., see FIGS. 10B-10C).

Inner channel **114c** receives a reducing gas **130** (e.g., see FIGS. 10B-10C) (e.g., where the reducing gas is a saturated vapor gas) via piping **120**, and provides reducing gas **130** in the area of semiconductor element **112** and substrate **104** in connection with a bonding operation. Reducing gas **130** is provided by a vapor generation system **122**, but initiates as reducing gas **126**. In the example shown in FIG. 4, vapor generation system **122** is a bubbler type system including an acid fluid **124** (e.g., formic acid, acetic acid, etc.) in vessel **122a** of the bubbler type system. A carrier gas (e.g., nitrogen) is provided (via piping **120**) into acid fluid **124** in vessel **122a**, where the carrier gas acts as a carrier for the acid fluid **124**. Collectively, the carrier gas (e.g., nitrogen) and acid fluid **124** are transported as reducing gas **126**. Within piping



120, additional carrier gas (e.g., nitrogen) may be added to reducing gas 126 (e.g., to vary the concentration of the reducing gas, as desired) via piping section 120a, thereby providing reducing gas 130 in the area of semiconductor element 112 and substrate 104 in connection with the bonding operation. After reducing gas 130 is distributed in the area of semiconductor element 112 and substrate 104, reducing gas 130 contacts surfaces of each of electrically conductive structures 104a and electrically conductive structures 112a (e.g., see FIG. 10B). The surfaces of electrically conductive structures 104a/112a may then include a reaction product (e.g., where the reaction product is provided as a result of (i) a surface oxide on electrically conductive structures 104a/112a, and (ii) reducing gas from reducing gas 130 (and possibly heat provided by heater 108 and transferred to electrically conductive structures 104a via contact with electrically conductive structures 112a, if desired). This reaction product is desirably removed from the bonding area (i.e., the area where electrically conductive structures 112a of semiconductor element 112 are bonded to corresponding electrically conductive structures 104a of substrate 104) using vacuum provided through center channel 114b of bond head manifold 114 via exit piping 116.

Thus, FIG. 4 illustrates: (i) various elements of bonding machine 100; (ii) a path of carrier gas from carrier gas supply 118 to outer channel 114a of bond head manifold 114; (iii) a path of reducing gas 126 (which may receive additional carrier gas from piping 120) from vapor generation system 122 to inner channel 114c of bond head manifold 114, where it is released to the bonding area as reducing gas 130; and (iv) a path of gas (which may carry away a reaction product from surfaces of electrically conductive structures 104a/112a) drawn by vacuum through center channel 114b of bond head manifold 114. The aforementioned paths are illustrated in FIG. 4 through various arrows even though gas is not flowing in FIG. 4 (see FIGS. 10A-10D for an exemplary operation).

FIG. 5 again illustrates bonding machine 100 as shown in FIG. 4; however, in FIG. 5 electrically conductive structures 112a do not include a solder material 112a1 as shown in FIG. 4. Rather, in FIG. 5, electrically conductive structures 104a include a solder material 104a1 at a contact portion of each electrically conductive structure 104a (e.g., a portion configured to contact the electrically conductive structures 112a of semiconductor element 112).

FIG. 6 again illustrates bonding machine 100 as shown in FIGS. 4-5; however, in FIG. 6 electrically conductive structures 112a include a solder material 112a1 as shown in FIG. 4, and electrically conductive structures 104a include a solder material 104a1 as shown in FIG. 5.

FIG. 7 again illustrates bonding machine 100 as shown in FIG. 4; however, in FIG. 7 electrically conductive structures 112a (shown in FIG. 4) are replaced by electrically conductive structures 112a2 which are formed of a solder material. That is, unlike FIG. 4, where electrically conductive structures 112a includes a solder material 112a1 at a contact portion, in FIG. 7, electrically conductive structures 112a2 are fully formed of a solder material.

FIG. 8 again illustrates bonding machine 100 as shown in FIG. 5; however, in FIG. 8 electrically conductive structures 104a (shown in FIG. 5) are replaced by electrically conductive structures 104a2 which are formed of a solder material. That is, unlike FIG. 5, where electrically conductive structures 104a includes a solder material 104a1 at a contact portion, in FIG. 8, electrically conductive structures 104a2 are fully formed of a solder material.

FIG. 9 again illustrates bonding machine 100 as shown in FIGS. 4-8; however, in FIG. 9 electrically conductive structures 112a (shown in FIGS. 4 and 6, including a solder material 112a1) are replaced by electrically conductive structures 112a2 (fully formed of a solder material) as shown in FIG. 7. Further, in FIG. 9, electrically conductive structures 104a (shown in FIG. 5, including a solder material 104a1) are replaced by electrically conductive structures 104a2 (fully formed of a solder material) as shown in FIG. 8.

Thus, according to certain aspects of the invention the electrically conductive structures of the semiconductor element being bonded, or the substrate configured to receive the semiconductor element during bonded, may include a solder material. The solder material may be included in a number of different configurations. For example, the solder material may be included at a contact portion of the electrically conductive structures (e.g., see FIGS. 4-6). In another non-limiting example, the entire electrically conductive structures may be formed of the solder material (e.g., see FIGS. 7-9).

FIGS. 10A-10D and FIGS. 11A-11D are block diagrams illustrating methods of bonding a semiconductor element to a substrate. In each of FIGS. 10A-10D and FIGS. 11A-11D: (i) the semiconductor element 112 (with electrically conductive structures 112a including solder material 112a1 at a contact portion) is shown as in FIG. 4; and (ii) the substrate 104 (with electrically conductive structures 104a not including a solder material) is shown as in FIG. 4. However, it is understood that the methods shown and described with respect to FIGS. 10A-10D and FIGS. 11A-11D are equally applicable to the semiconductor elements and substrates of each of FIGS. 4-9, and are applicable to the semiconductor elements and substrates of any other embodiment within the scope of the invention.

Prior to the processes shown and described in connection with FIGS. 10A-10D and FIGS. 11A-11D, semiconductor element 112 and/or substrate 104 may be "cleaned". For example, the electrically conductive structures 112a, 104a of one or both of semiconductor element 112 and substrate 104 may be cleaned using a solution such as hydrochloric acid or acetic acid. Such a cleaning step may be performed, for example, by dipping at least a portion of semiconductor element 112 and/or substrate 104 into such a solution.

Referring now to FIG. 10A, semiconductor element 112 (carried by bond head 106) is positioned above substrate 104. As shown in FIG. 10B, vapor generation system 122 has been activated to produce reducing gas 130 at the bonding area. More specifically, FIG. 10B illustrates reducing gas 130 being provided at the bonding area, as well as shielding gas 128 being provided, and vacuum being drawn through center channel 114b of bond head manifold 114 via exit piping 116. Thus, the flow of reducing gas 130 reach desired portions of semiconductor element 112 and substrate 104 (e.g., electrically conductive structures 104a and electrically conductive structures 112a) for: removing contaminants from the electrically conductive structures 104a and electrically conductive structures 112a; and/or shielding electrically conductive structures 104a and electrically conductive structures 112a from further potential contamination.

Also shown in FIG. 10B, respective ones of electrically conductive structures 112a (of semiconductor element 112) are aligned with ones of electrically conductive structures 104a (of substrate 104). At FIG. 10C, the process proceeds to a bonding step (e.g., a thermocompression bonding step), for example, through the lowering of bond head 106. That is,



## 11

electrically conductive structures **112a** are bonded to corresponding electrically conductive structures **104a**. This may be through a thermocompression bonding process (e.g., including heat and/or bond force, where the bond force may be a higher bond force such as 50-300 N), and may also include ultrasonic energy transfer (e.g., from an ultrasonic transducer included in bond head assembly **106**). At FIG. **10D**, the bonding process has been completed. That is, semiconductor element **112** has been bonded to substrate **104**, such that corresponding electrically conductive structures **112a**, **104a** are now bonded to one another with deformed solder material **112a1** provided therebetween.

Although FIGS. **10A-10D** (and FIGS. **4-9**) illustrate manifold **114**, integrated with the bond head, for: delivering the reducing gas; delivering the shielding gas; and providing vacuum—the invention is not limited thereto. For example, instead of such functions being provided through integration of a manifold with the bond head assembly, such functions may be provided through integration with a support structure for supporting the substrate. Further, such functions may be split between the bond head assembly and the support structure (and possibly other structures of the bonding machine). FIGS. **11A-11D** are a series of block diagrams of a bonding machine **100"**, with certain similar elements and functions to that illustrated and described with respect to FIG. **4** and FIGS. **10A-10D**, except that the manifold functions (delivering the reducing gas; delivering the shielding gas; and providing vacuum) are integrated into a support structure **202**.

FIG. **11A** illustrates bonding machine **100"** (e.g., a flip chip bonding machine, a thermocompression bonding machine, etc.). Bonding machine **100"** includes a support structure **202** for supporting a substrate **104** during a bonding operation (where substrate **104** includes a plurality of electrically conductive structures **104a**). Support structure **202** may include any appropriate structure for the specific application. In FIGS. **11A-11D**, support structure **202** includes top plate **202a** (configured to directly support substrate **104**), chuck **202c**, and heater **202b** disposed therebetween. In applications where heat for heating substrate **104** is desirable in connection with the bonding operation, a heater such as heater **202b** may be utilized.

FIG. **11A** also illustrates bond head assembly **106** (including heater **108** and bonding tool **110**), which may be configured to move along (and about) a plurality of axes of bonding machine **100"** such as, for example, the x-axis, y-axis, z-axis, theta (rotative) axis, etc. In FIG. **11A**, bond head assembly **106** carries a plate **107** for partially containing at least one of shielding gas **128** and reducing gas **130** (see description below).

As opposed to a bond head manifold **114** carried by bond head assembly **106** (as in FIGS. **10A-10D**), FIGS. **11A-11D** illustrate a manifold **214** carried by, and/or integrated with, support structure **202**. Manifold **214** is configured for receiving and distributing fluids (e.g., gases, vapors, etc.) as desired in the given application. In FIG. **11A**, while manifold **214** is illustrated in a cross sectional view, the actual manifold **214** at least partially surrounds substrate **104**. Of course, manifold **214** may have different configurations from that shown in FIG. **11A**. Further, it is understood that certain details of manifold **214** (e.g., interconnection with piping **120**, structural details for distributing reducing gas **130** within manifold **214**, structural details for distributing shielding gas **128** within manifold **214**, structural details for drawing a vacuum through a center channel of manifold **214**, etc.) are omitted for simplicity.

## 12

Manifold **214** includes three channels **214a**, **214b**, **214c** having different functions. Outer channel **214a** receives shielding gas **128** (e.g., nitrogen gas) from shielding gas supply **118** via piping **120**. From outer channel **214a** of manifold **214**, shielding gas **128** is provided as a shield from the outside environment (e.g., see FIGS. **11B-11C**). Inner channel **214c** receives a reducing gas **130** (e.g., see FIGS. **11B-11C**) (e.g., where the reducing gas is a saturated vapor gas) via piping **120**, and provides reducing gas **130** in the area of semiconductor element **112** and substrate **104** in connection with a bonding operation. Reducing gas **130** is provided by a vapor generation system **122**, but initiates as reducing gas **126** (e.g., see description above with respect to FIG. **4**). After reducing gas **130** is distributed in the area of semiconductor element **112** and substrate **104**, reducing gas **130** contacts surfaces of each of electrically conductive structures **104a** and electrically conductive structures **112a**. The surfaces of electrically conductive structures **104a/112a** may then include a reaction product (e.g., where the reaction product is provided as a result of: (i) a surface oxide on electrically conductive structures **104a/112a**, and (ii) reducing gas from reducing gas **130** (and possibly heat provided by heater **108**, if desired). This reaction product is desirably removed from the bonding area (i.e., the area where electrically conductive structures **112a** of semiconductor element **112** are bonded to corresponding electrically conductive structures **104a** of substrate **104**) using vacuum provided through center channel **214b** of manifold **214** via exit piping **216**.

Thus, FIG. **11A** illustrates: (i) various elements of bonding machine **100"**; (ii) a path of carrier gas from carrier gas supply **118** to outer channel **214a** of manifold **214**; (iii) a path of reducing gas **126** (which may receive additional carrier gas from piping **120a**) from vapor generation system **122** to inner channel **214c** of manifold **214**, where it is released to the bonding area as reducing gas **130**; and (iv) a path of gas (which may carry away a reaction product from surfaces of electrically conductive structures **104a/112a**) drawn by vacuum through center channel **214b** of manifold **214**. The aforementioned paths are illustrated in FIG. **11A** through various arrows even though gas is not flowing in FIG. **11A**.

Referring now to FIG. **11A**, semiconductor element **112** (carried by bond head **106**) is positioned above substrate **104**. As shown in FIG. **11B**, vapor generation system **122** has been activated to produce reducing gas **130** at the bonding area. More specifically, FIG. **11B** illustrates reducing gas **130** being provided at the bonding area, as well as shielding gas **128** being provided, and vacuum being drawn through center channel **214b** of manifold **214** via exit piping **116**. Thus, the flow of reducing gas **130** reach desired portions of semiconductor element **112** and substrate **104** (e.g., electrically conductive structures **104a** and electrically conductive structures **112a**) for: removing contaminants from the electrically conductive structures **104a** and electrically conductive structures **112a**; and/or shielding electrically conductive structures **104a** and electrically conductive structures **112a** from further potential contamination.

Also shown in FIG. **11B**, respective ones of electrically conductive structures **112a** (of semiconductor element **112**) are aligned with ones of electrically conductive structures **104a** (of substrate **104**). At FIG. **11C**, the process proceeds to a bonding step (e.g., a thermocompression bonding step), for example, through the lowering of bond head **106**. That is, electrically conductive structures **112a** are bonded to corresponding electrically conductive structures **104a**. This may be through a thermocompression bonding process (e.g.,



## 13

including heat and/or bond force, where the bond force may be a higher bond force such as 50-300 N), and may also include ultrasonic energy transfer (e.g., from an ultrasonic transducer included in bond head assembly **106**). At FIG. **11D**, the bonding process has been completed. That is, semiconductor element **112** has been bonded to substrate **104**, such that corresponding electrically conductive structures **112a**, **104a** are now bonded to one another with deformed solder material **112a2** provided therebetween.

Although the invention has been illustrated primarily with respect to one of manifolds **114**, **214** for directing (i) the flow of reducing gas **130**, (ii) the flow of shielding gas **128**, and (iii) the pull of the vacuum, it is understood that the structure used to direct the flow patterns may be different from that illustrated. That is, the configuration of the structure used to provide and direct fluids **130**, **128** (and to draw vacuum) may vary considerably from that shown.

The invention described herein in connection with FIGS. **4-9**, FIGS. **10A-10D**, and FIGS. **11A-11D** may provide a number of benefits such as, for example: fluxless bonding (e.g., no fluxing of the semiconductor element or the substrate is required prior to or during bonding); reduction of oxides on both the semiconductor element and the substrate; among others.

It will be appreciated by those skilled in the art that certain elements of bonding machine **100** (see FIGS. **4-9** and FIGS. **10A-10D**), and/or bonding machine **100'** (see FIGS. **11A-11D**) may be integrated into the systems of FIG. **1**, FIGS. **2A-2G**, and FIGS. **3A-3B**, to replace at least a portion of the elements of the bondhead compartments (e.g., the bond head, the shroud, certain piping, etc.).

Although the invention has been described and illustrated with respect to the exemplary embodiments thereof, it should be understood by those skilled in the art that the foregoing and various other changes, omissions and additions may be made therein and thereto, without parting from the spirit and scope of the present invention. Rather, various modifications may be made in the details within the scope and range of equivalents of the claims and without departing from the invention.

What is claimed:

**1.** A bonding system for bonding a semiconductor element to a substrate, the bonding system comprising:  
 a substrate oxide reduction chamber configured to receive a substrate, the substrate including a plurality of first electrically conductive structures, the substrate oxide reduction chamber configured to receive a reducing gas to contact each of the plurality of first electrically conductive structures;  
 a substrate oxide prevention chamber for receiving the substrate after the reducing gas contacts the plurality of first electrically conductive structures, the substrate oxide prevention chamber having an inert environment when receiving the substrate; and  
 a reducing gas delivery system for providing a reducing gas environment during bonding of a semiconductor element to the substrate, the semiconductor element including a plurality of second electrically conductive structures, the plurality of first electrically conductive structures being configured to be bonded with corresponding ones of the plurality of second electrically conductive structures, wherein the substrate oxide prevention chamber includes a bonding location for receiving the substrate during bonding of the semiconductor element to the substrate.

## 14

**2.** The bonding system of claim **1** further comprising a substrate transfer system for transferring the substrate from the substrate oxide reduction chamber to the substrate oxide prevention chamber.

**3.** The bonding system of claim **1** wherein the substrate oxide prevention chamber is provided with nitrogen to create the inert environment.

**4.** The bonding system of claim **1** further comprising a material handling system for moving the substrate within the substrate oxide prevention chamber.

**5.** The bonding system of claim **1** further comprising a bond head including a bonding tool for bonding the semiconductor element to the substrate, wherein the reducing gas delivery system is integrated with the bond head.

**6.** The bonding system of claim **1** further comprising a substrate support structure, the substrate support structure supporting the substrate during bonding of the semiconductor element to the substrate, wherein the reducing gas delivery system is integrated with the substrate support structure.

**7.** The bonding system of claim **1** wherein the semiconductor element is a semiconductor die.

**8.** The bonding system of claim **7** wherein the substrate is a semiconductor wafer.

**9.** The bonding system of claim **1** wherein the substrate is returned to the substrate oxide reduction chamber after being received by the substrate oxide prevention chamber.

**10.** The bonding system of claim **1** wherein at least a portion of the substrate oxide reduction chamber has a common boundary with the substrate oxide prevention chamber.

**11.** The bonding system of claim **1** wherein the substrate oxide reduction chamber is configured to receive another substrate after the substrate is moved to the substrate oxide prevention chamber.

**12.** A bonding system for bonding a semiconductor element to a substrate, the bonding system comprising:

a substrate oxide reduction chamber configured to receive a substrate, the substrate including a plurality of first electrically conductive structures, the substrate oxide reduction chamber configured to receive a reducing gas to contact each of the plurality of first electrically conductive structures;

a substrate oxide prevention chamber for receiving the substrate after the reducing gas contacts the plurality of first electrically conductive structures, the substrate oxide prevention chamber having an inert environment when receiving the substrate;

a reducing gas delivery system for providing a reducing gas environment during bonding of a semiconductor element to the substrate, the semiconductor element including a plurality of second electrically conductive structures, the plurality of first electrically conductive structures being configured to be bonded with corresponding ones of the plurality of second electrically conductive structures; and

a bond head including a bonding tool for bonding the semiconductor element to the substrate, the reducing gas delivery system being integrated with the bond head.

**13.** The bonding system of claim **12** further comprising a substrate transfer system for transferring the substrate from the substrate oxide reduction chamber to the substrate oxide prevention chamber.

**14.** The bonding system of claim **12** further comprising a material handling system for moving the substrate within the substrate oxide prevention chamber.

**15**

**15.** The bonding system of claim **12** wherein the substrate oxide prevention chamber is provided with nitrogen to create the inert environment.

**16.** A bonding system for bonding a semiconductor element to a substrate, the bonding system comprising:

a substrate oxide reduction chamber configured to receive a substrate, the substrate including a plurality of first electrically conductive structures, the substrate oxide reduction chamber configured to receive a reducing gas to contact each of the plurality of first electrically conductive structures;

a substrate oxide prevention chamber for receiving the substrate after the reducing gas contacts the plurality of first electrically conductive structures, the substrate oxide prevention chamber having an inert environment when receiving the substrate;

a reducing gas delivery system for providing a reducing gas environment during bonding of a semiconductor element to the substrate, the semiconductor element

**16**

including a plurality of second electrically conductive structures, the plurality of first electrically conductive structures being configured to be bonded with corresponding ones of the plurality of second electrically conductive structures; and

a substrate support structure, the substrate support structure supporting the substrate during bonding of the semiconductor element to the substrate, wherein the reducing gas delivery system is integrated with the substrate support structure.

**17.** The bonding system of claim **16** further comprising a substrate transfer system for transferring the substrate from the substrate oxide reduction chamber to the substrate oxide prevention chamber.

**18.** The bonding system of claim **16** further comprising a material handling system for moving the substrate within the substrate oxide prevention chamber.

\* \* \* \* \*