

US011243348B2

(12) **United States Patent**
Brown et al.

(10) **Patent No.:** **US 11,243,348 B2**
(45) **Date of Patent:** **Feb. 8, 2022**

(54) **HIGH-DENSITY OPTICAL FIBER RIBBON WITH CLADDING-STRENGTHENED GLASS OPTICAL FIBERS IN A COMMON PROTECTIVE COATING AND FIBER RIBBON INTERCONNECTS EMPLOYING SAME**

(52) **U.S. Cl.**
CPC **G02B 6/02395** (2013.01); **C03C 25/1068** (2018.01); **G02B 6/03694** (2013.01)

(58) **Field of Classification Search**
CPC G02B 6/02395; G02B 6/03694; C03C 25/1068
See application file for complete search history.

(71) Applicant: **CORNING INCORPORATED**,
Corning, NY (US)

(56) **References Cited**

(72) Inventors: **Philip Simon Brown**, Big Flats, NY (US); **Matthew Ryan Drake**, Painted Post, NY (US); **Richard Michael Fiacco**, Corning, NY (US); **Mandakini Kanungo**, Painted Post, NY (US); **Ming-Jun Li**, Horseheads, NY (US); **Jeffery Scott Stone**, Addison, NY (US); **Qi Wu**, Painted Post, NY (US); **Haitao Zhang**, Ithaca, NY (US)

U.S. PATENT DOCUMENTS

5,140,665 A 8/1992 Backer et al.
5,868,734 A * 2/1999 Soufiane G02B 6/02 606/15

(Continued)

FOREIGN PATENT DOCUMENTS

WO 2015013224 A1 1/2015
WO 2016164513 A1 10/2016
WO 2018081076 A1 5/2018

OTHER PUBLICATIONS

Scott R. Bickham, "Multimode and single-mode fibers for data center and high-performance computing applications," Proc. SPIE 9753, Optical Interconnects XVI, 97530R (Mar. 15, 2016); doi: 10.1117/12.2217882 (Year: 2016).*

(Continued)

Primary Examiner — Peter Radkowski

(74) *Attorney, Agent, or Firm* — Kevin L. Bray

(73) Assignee: **Corning Incorporated**, Corning, NY (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **16/685,065**

(22) Filed: **Nov. 15, 2019**

(65) **Prior Publication Data**

US 2020/0192023 A1 Jun. 18, 2020

Related U.S. Application Data



(60) Provisional application No. 62/778,631, filed on Dec. 12, 2018.

(51) **Int. Cl.**
G02B 6/02 (2006.01)
C03C 25/1065 (2018.01)
G02B 6/036 (2006.01)

(57) **ABSTRACT**

A high-density optical fiber ribbon is formed by two or more cladding-strengthened glass optical fibers each having an outer surface and that do not individually include a protective polymer coating. A common protective coating substantially surrounds the outer surfaces of the two or more cladding-strengthened glass optical fibers so that the common protective coating is common to the two or more cladding-strengthened glass optical fibers. A fiber ribbon cable is formed by adding a cover assembly to the fiber ribbon. A fiber ribbon interconnect is formed adding one or

(Continued)



more optical connectors to the fiber ribbon or fiber ribbon cable. Optical data transmission systems that employ the fiber ribbon to optically connect to a photonic device are also disclosed. Methods of forming the cladding-strengthened glass optical fibers and the high-density optical fiber ribbons are also disclosed.

19 Claims, 21 Drawing Sheets

(56)

References Cited

U.S. PATENT DOCUMENTS

| | | | | |
|-------------------|---------|----------------|-------|-------------------------|
| 6,577,802 B1 * | 6/2003 | Chien | | C03C 25/1065 385/128 |
| 8,488,932 B2 * | 7/2013 | Bennett | | C03B 37/027 385/128 |
| 9,346,709 B2 * | 5/2016 | Gross | | C03C 17/28 |
| 9,939,599 B2 * | 4/2018 | Blazer | | G02B 6/4404 |
| 10,155,689 B2 * | 12/2018 | Gross | | C03C 4/18 |
| 2008/0149363 A1 * | 6/2008 | Han | | C08K 3/04 174/102 SC |
| 2011/0211797 A1 * | 9/2011 | Bennett | | G02B 6/03694 385/127 |
| 2011/0217011 A1 | 9/2011 | Bennett et al. | | |
| 2015/0093084 A1 | 4/2015 | Cooke et al. | | |
| 2017/0031121 A1 * | 2/2017 | blazer | | G02B 6/4434 |
| 2018/0031761 A1 * | 2/2018 | Bookbinder | | G02B 6/03616 |
| 2020/0192040 A1 * | 6/2020 | Li | | G02B 6/4403 |

OTHER PUBLICATIONS

Scott R. Bickham, Radawan Ripumaree, Julie A. Chalk, Mark T. Paap, William C. Hurley, Randy L. McClure, "Multimode fiber for high-density optical interconnects," Proc. SPIE 10109, Optical Interconnects XVII, 101090S (Feb. 20, 2017); doi: 10.1117/12.2255505 (Year: 2017).*

Drzal et al., Exfoliated Graphite Nanoplatelet Vinyl Ester Nanocomposites, <https://www.researchgate.net/publication/237121849>, 2014 (Year: 2014).*

Bickham et al., Multimode fiber for high-density optical interconnects, Proc. SPIE 10109, Optical Interconnects XVII, 101090S, Feb. 20, 2017; doi: 10.1117/12.2255505 (Year: 2017).*

Kalaitzidou et al., Multifunctional polypropylene composites produced by incorporation of exfoliated graphite nanoplatelets, Carbon 45 (2007) 1446-1452 (Year: 2007).*

International Search Report and Written Opinion of the European International Searching Authority; PCT/US2019/064114; dated Feb. 26, 2020; 13 Pgs.

Estep et al; "The Effect of Carbon Overcoating on the Mechanical Behavior of Large Flaws," SPIE vol. 1791, pp. 18-24, 1992.

Vethanayagam et al; "Mechanical Performance and Reliability of Corning Titan SMF CPC5 Fiber After Exposure to a Variety of Environments," Proc. SPIE, vol. 1366, pp. 343-350, 1991.

Wolfe; "Titan SMF Single-Mode Optical Fiber"; Broadband '90 Proceedings; 1990; 6 Pages.

* cited by examiner




FIG. 1




FIG. 2A




FIG. 2B




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 4A




FIG. 4B





FIG. 4C






FIG. 4D









FIG. 4E








FIG. 6




FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 9




FIG. 10A




FIG. 10B






FIG. 10C






FIG. 11C




FIG. 11D




FIG. 11E




FIG. 11F

1

**HIGH-DENSITY OPTICAL FIBER RIBBON
WITH CLADDING-STRENGTHENED GLASS
OPTICAL FIBERS IN A COMMON
PROTECTIVE COATING AND FIBER
RIBBON INTERCONNECTS EMPLOYING
SAME**

This application claims the benefit of priority to U.S. Provisional Application Ser. No. 62/778631 filed on Dec. 12, 2018, the content of which is relied upon and incorporated herein by reference in its entirety.

FIELD

The present disclosure relates to optical fiber ribbons, and in particular to a high-density optical fiber ribbon with cladding-strengthened glass optical fibers in a common protective coating and fiber ribbon interconnects employing same.

BACKGROUND

The push for higher data rates in digital communications has driven the integration of optics with electronics. In particular, the use of silicon photonics for electro-optical transceivers has resulted in very dense optical circuitry concentrating many separate optical signal lines in the form of optical waveguides (e.g., channel waveguides) into one silicon photonics chip. For many optical signal transmission applications, the optical signals generated on the silicon photonics chips need to be coupled from the optical waveguides into optical fibers. Likewise, optical signals generated at a remote location (e.g., a telecommunications device) need to be coupled from optical fibers to the optical waveguides to be detected by the silicon photonics chip.

Optical fiber ribbons and multicore optical fibers are two approaches to increase the fiber density to achieve the parallel connectivity required for the optical circuitry of silicon photonics chips. Unfortunately, using conventional optical fibers in a fiber ribbon does not result in a sufficiently high fiber density due to their relatively large size (as defined by the core, cladding and protective coating) as compared to the size of the optical waveguides of the silicon photonics chips. Likewise, the use of multicore optical fibers is problematic due to manufacturing shortcomings (e.g., maintaining concentricity of the hard protective coating), the high connectivity costs, and the lack of component ecosystems.

SUMMARY

A high-density fiber ribbon is formed by two or more cladding-strengthened glass optical fibers each having an outer surface and each not individually including a protective polymer coating. A protective polymer coating substantially surrounds the outer surfaces of the two or more cladding-strengthened glass optical fibers so that the protective polymer coating is common to the two or more cladding-strengthened glass optical fibers. A fiber ribbon cable is formed by adding a cover assembly to the fiber ribbon. A fiber ribbon interconnect is formed by adding one or more optical connectors to the fiber ribbon or fiber ribbon cable. Optical data transmission systems that employ the fiber ribbon to optically connect to a photonic device are also disclosed.

Present day optical transceivers used on silicon photonics chips of photonic devices operate at a speed of 100 Gb/s based on 4 lanes at 25 Gb/s per lane. The roadmap for

2

electrical lane speed has been defined for the next generation, and the existing 25 Gb/s lane speed will increase to 56 GBaut/s in the PAM4 signaling protocol which amounts to 112 Gb/s per lane (PAM stands for “pulse amplitude modulation”). The 400 Gb/s Ethernet speed will therefore continue to follow the 4-lane architecture. The optics to support 4 electrical lanes are currently based on either PSM4 (parallel single mode 4 fibers) or the CWDM4 signaling protocol (i.e., 4 wavelength coarse wavelength division multiplexing). The transceiver optical interface is typically an 8 fiber MPO for PSM-4, and a duplex LC for CWDM4.

The pro and cons of the PSM4 versus CWDM4 signaling protocols has been an ongoing debate. The PSM4 transceiver that employs a standard ribbon fiber is currently the lower cost solution, even though the connectivity cost is considerably higher than CWDM4 due to the use of a manual push-on pull-off (MPO) connector. The PSM4 protocol consumes more chip space for coupling to fibers. On the other hand, the CWDM4 transceivers suffer from the excess insertion loss of the WDM multiplexer and demultiplexer, which typically exceeds 4 decibels (dB). As the transceiver speed increases, the link budget will be challenged to accommodate the high insertion loss of WDM components. Moreover, CWDM transceivers require multiple laser sources and consume more power than PSM4 transceivers. As mega data centers increasingly focus on energy efficiency, parallel single mode remains an appealing solution if the connectivity density can be improved.

The fiber ribbons, cables and assemblies disclosed herein substantially enhance the density of parallel fiber connectivity with photonic devices that include silicon photonics chips (e.g., transceiver chips that support optical waveguides) without resorting to the use of multicore fibers. The conventional approach to improving the fiber density in an optical fiber-based connection has been to reduce the thickness of the protective coating(s) of the optical fibers. A 200 μm diameter fiber, for instance, is designed to reduce the protective coating thickness from 250 μm while using the same glass cladding diameter of 125 μm . The improvement in fiber density has been appreciable for high-fiber-count cables when protective coating thickness is reduced. For transceiver chip coupling, however, the density improvement is incremental at best.

In an example, the high-density fiber ribbons disclosed herein comprise a closely packed array of single-mode fibers in one or more rows, with each fiber having a strengthened cladding and a single common protective coating that directly encapsulates all the fibers, with the exception of the fiber ends as well as the fiber end sections in some examples. Each fiber is made entirely of glass and does not have an individual non-glass protective coating, other than perhaps a thin hermetic seal coating. The lack of individual protective coatings allows for maximizing the fiber density in a fiber ribbon configuration without compromising the optical transmission properties of the fibers.

The fiber cladding is made of silica and includes an inner cladding and an outer cladding. The outer cladding is compositionally distinct from the inner cladding and has higher mechanical strength, greater abrasion resistance, and/or greater fatigue resistance than the inner cladding. The outer cladding is referred to herein as a “strengthened cladding” or a “strengthened outer cladding” and a fiber having the outer cladding is referred to herein as a “cladding-strengthened fiber” or a “cladding-strengthened optical fiber” or a “cladding-strengthened glass optical fiber”. The outer cladding is strengthened by doping silica glass. In one aspect, a strengthened outer cladding is made by doping

silica glass with titanium dioxide (TiO₂). Doping of silica glass to form a strengthened outer cladding improves the scratch and fatigue resistance of the fiber and permits handling and installation of the fiber (e.g. in a ribbon) without damage. The strengthened outer cladding is sufficiently robust to obviate the need for an individual protective coating for each fiber in a ribbon. The overall fiber diameter is accordingly reduced and a higher packing density of fibers in a ribbon is achieved.

The common protective coating can be based on an ultraviolet (UV) curable acrylate, a thermoplastic, or other adhesives. The collectively coated fiber array can include indicia (i.e., features, shapes, markings, etc.) to identify the polarity of the fiber ribbon. The pitch of the fiber array of the fiber ribbon can be transitioned from a relatively high fiber density (e.g., substantially equal to the fiber diameter) at one end to up to 250 μm at the other end. In an example, this can be accomplished using a fan-out structure configured to minimize bending. The different fiber densities can be exploited for mass fusion splicing or termination by MPO ferrules for subsequent termination by an MPO connector. The fiber ribbon can be made compatible to standard 127 μm pitch grooves of a grooved substrate, enabling a simple assembly process for high-density connector assemblies, such as fiber array units (FAUs).

The fiber array can be collectively coated into a relatively small form factor. With a standard outer cladding diameter of 125 μm, the high-density fiber array can utilize existing fiber termination equipment and connectivity components. Higher fiber densities can be achieved by reducing the outer cladding diameter to 80 μm or even lower. Without protective coatings on the individual fibers, the tightly packed fiber array has inherent geometric precision due to the high manufacturing tolerance and consistency of the fiber outer cladding diameter associated with the fiber drawing process.

The present disclosure extends to:
An optical fiber ribbon, comprising:

a plurality of cladding-strengthened glass optical fibers, each of the cladding-strengthened glass optical fibers having an outer surface, the outer surface comprising glass or an inorganic material; and

a common protective coating directly contacting the outer surface of at least two of plurality of cladding-strengthened glass optical fibers.

The present disclosure extends to:
An optical fiber ribbon, comprising:

a plurality of glass optical fibers surrounded by a common protective coating, each of the glass optical fibers having a centerline, the centerlines of adjacent glass optical fibers being separated by less than 150 microns.

The present disclosure extends to:

A method of forming a cladding-strengthened glass optical fiber, comprising:

forming a glass preform having a preform core, an inner preform cladding and an outer preform cladding, the outer preform cladding comprising titania-doped silica; and

drawing the glass preform into a cladding-strengthened glass optical fiber, the cladding-strengthened glass optical fiber having an outer cladding, the outer cladding comprising the titania-doped silica and having a glass outer surface; and

adding a hermetic sealing layer to the glass outer surface.

The present disclosure extends to:

A method of forming an optical fiber ribbon, comprising:

forming a glass preform having a preform core, an inner preform cladding and an outer preform cladding, the outer preform cladding comprising titania-doped silica;

drawing the glass preform into a cladding-strengthened glass optical fiber, the cladding-strengthened glass optical fiber having an outer cladding, the outer cladding comprising the a titania-doped silica and having a glass outer surface;

arranging a plurality of the cladding-strengthened glass optical fibers in a row; and

coating the row of the plurality of the cladding-strengthened glass optical fibers with a common protective coating, the common protective coating directly contacting the outer surface of at least two of the plurality of cladding-strengthened glass optical fibers.

Additional features and advantages are set forth in the Detailed Description that follows, and in part will be apparent to those skilled in the art from the description or recognized by practicing the embodiments as described in the written description and claims hereof, as well as the appended drawings. It is to be understood that both the foregoing general description and the following Detailed Description are merely exemplary, and are intended to provide an overview or framework to understand the nature and character of the claims.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings are included to provide a further understanding, and are incorporated in and constitute a part of this specification. The drawings illustrate one or more embodiment(s), and together with the Detailed Description explain the principles and operation of the various embodiments. As such, the disclosure will become more fully understood from the following Detailed Description, taken in conjunction with the accompanying Figures, in which:

FIG. 1 is a front elevated view of an example cladding-strengthened glass optical fiber as disclosed herein.

FIG. 2A is a cross-sectional view of the cladding-strengthened glass optical fiber of FIG. 1.

FIG. 2B is similar to FIG. 2A, but shows an embodiment of the cladding-strengthened glass optical fiber that includes a hermetic sealing layer.

FIG. 3A is a schematic diagram of an optical fiber drawing system used to form the cladding-strengthened glass optical fibers disclosed herein.

FIGS. 3B and 3C are close-up views of the glass outer surface of the cladding-strengthened glass optical fiber and illustrate how the outer surface can be readily functionalized using a fluorinated silane.

FIG. 3D is a plot of the contact angle θ (°) versus measurement position P (mm) for a bare fiber (10B) and for a fiber (10) having a silane-based hermetic sealing layer.

FIG. 4A is a top-down view of an example fiber ribbon that employs the cladding-strengthened glass optical fibers embedded in a common protective coating.

FIG. 4B is a cross-sectional view of the fiber ribbon of FIG. 4A.

FIG. 4C is similar to FIG. 4B and shows two rows of the cladding-strengthened glass optical fibers within the common protective coating.

FIG. 4D is a close-up cross-sectional view of a portion of the fiber ribbon of FIGS. 4A and 4B, illustrating an example where the common protective coating comprises two different materials that define a primary (inner) layer and a secondary (outer) layer.

FIG. 4E is similar to FIG. 4B and shows an example where the common protective coating is thicker on one side

5

of the cladding-strengthened glass optical fibers than the other as an indication of the polarity of the fiber ribbon.

FIG. 5A is a top down view of an example fiber ribbon cable formed using the fiber ribbon.

FIGS. 5B through 5D are cross-sectional views of the fiber ribbon cable of FIG. 5A, wherein the fiber ribbon cable comprises the fiber ribbon and a cover assembly that surrounds the outside of the fiber ribbon.

FIG. 6 is an elevated view of an example fiber ribbon interconnect that comprises the fiber ribbon cable connectorized at its opposite ends with optical fiber connectors.

FIG. 7A is an exploded front elevated view of an example method of forming a high-density connector assembly that can be used directly as a high-density optical fiber connector or that can be used to form a high-density optical fiber connector.

FIG. 7B is a front elevated view of the assembled high-density connector assembly.

FIG. 7C is a cross-sectional view of the high-density connector assembly of FIG. 7B, illustrating an example of the cladding-strengthened glass optical fibers extracted from the protective coating of the fiber ribbon, and the fiber ribbon extracted from the cover assembly.

FIG. 7D is an elevated view illustrating how the high-density connector assembly of FIG. 7B can be used to form a high-density optical fiber connector by adding additional components in the form of a connector housing and alignment features.

FIG. 8A is a top-down view of an example fan-out fiber ribbon.

FIGS. 8B and 8C are x-y cross-sectional views of the fan-out fiber ribbon of FIG. 8A taken at the lines B-B and C-C respectively, and illustrating how the fiber pitch (density) can be made different at the opposite ends of the fan-out fiber ribbon using a fan-out region.

FIG. 9 is a top-down view of an example fiber ribbon interconnect that comprises the fan-out fiber ribbon of FIG. 8A with a high-density optical fiber connector operably attached to the high-density (narrow) end and a conventional (e.g., MPO) connector attached to the standard-density (wide) end.

FIG. 10A is an elevated view of an example furcated fiber ribbon.

FIGS. 10A and 10B are cross-sectional views of each of the furcations of the furcated fiber ribbon.

FIG. 10C is similar to FIG. 10A and shows an example interconnect that employs the furcated fiber ribbon.

FIG. 11A is a schematic diagram of an optical data transmission system that employs the fiber ribbon as disclosed herein.

FIG. 11B is a close-up view of one end of the fiber ribbon connectorized with a high-density optical fiber connector, which is in position to operably engage a photonics chip of a photonics device.

FIG. 11C is similar to FIG. 11B and shows the high-density optical fiber connector operably engaged with the photonics chip of the photonics device so that the cladding-strengthened glass optical fibers are in optical communication with optical waveguides supported by the photonics chip.

FIG. 11D is a side view of a connectorized end of an example fiber ribbon interconnect, wherein the connectorized end includes a standard connector, and illustrating an example of how the fiber ribbon interconnect can be optically connected to a standard optical fiber cable using an adapter.

6

FIG. 11E is a top-down view of an example of an optical data transmission system wherein a fiber ribbon interconnect terminated by two high-density optical connectors is used to optically connect two different photonic devices.

FIG. 11F is similar to FIG. 11E and shows an example of an optical data transmission system wherein the fiber ribbon interconnect utilizes a bifurcated fiber ribbon to provide high-density optical interconnections between one photonic device at one end of the fiber ribbon interconnect and two photonic devices at the other end of the fiber ribbon interconnect.

DETAILED DESCRIPTION

Reference is now made in detail to various embodiments of the disclosure, examples of which are illustrated in the accompanying drawings. Whenever possible, the same or like reference numbers and symbols are used throughout the drawings to refer to the same or like parts. The drawings are not necessarily to scale, and one skilled in the art will recognize where the drawings have been simplified to illustrate the key aspects of the disclosure.

The claims as set forth below are incorporated into and constitute part of this Detailed Description.

Cartesian coordinates are shown in some of the Figures for the sake of reference and are not intended to be limiting as to direction or orientation.

The expression “comprises” as used herein includes the term “consists of” as a special case, so that for example the expression “A comprises B and C” is understood to include the case of “A consists of B and C.”

Relative terms like top, bottom, side, horizontal, vertical, etc. are used for convenience and ease of explanation and are not intended to be limiting as to direction or orientation.

The acronym MPO as used herein stands for multifiber push on and is used to describe a type of optical fiber connector known in the art and that is standard in the art.

The term “elastic modulus” as used herein refers to Young’s modulus.

The terms “optical fiber” and “glass optical fiber” as used herein refer to a glass fiber configured to operate as a waveguide.

Fiber with Strengthened Cladding

FIG. 1 is a front elevated view of an example cladding-strengthened glass optical fiber (“fiber”) 10 as disclosed herein. FIG. 2A is a cross-sectional view of the fiber 10 of FIG. 1. The fiber 10 has a centerline AC, a core 16 centered on the centerline and having a diameter D1, and a cladding 20 surrounding the core and having a diameter D2 and a thickness TH2. The core 16 and cladding 20 are both made of glass and can have the configuration (i.e., refractive index profile, dimensions, etc.) of a conventional optical fiber. The refractive index profile of the fiber 10 can be that for a standard single mode fiber, a bend-insensitive single mode fiber, a few-mode fiber, or a multimode fiber.

An example diameter D1 of the core 16 for a single mode fiber is in the range from about 5 microns to about 10 microns, with about 8 microns being typical value for telecommunications wavelengths of 1310 nm and 1550 nm. An example diameter D2 of the cladding 20 is in the range from about 30 μm to about 250 μm , depending on the desired overall fiber diameter DF, which in an example can be in the range from 50 μm to 200 μm .

The fiber 10 also includes an additional cladding 30 that surrounds the cladding 20, so that the cladding 20 can be considered an inner cladding and the cladding 30 considered an outer cladding of a two-part cladding region 40. The outer

cladding **30** has a diameter **D3** and a thickness **TH3**. An example range on the thickness **TH3** is between 1 μm and 20 μm .

The outer cladding **30** comprises silica (SiO_2) doped with titanium dioxide (TiO_2 , which is also called “titania”). An example of such a fiber **10** is the Corning® Titan® single-mode optical fiber, available from Corning, Inc., Corning, N.Y. The outer cladding **30** strengthens the fiber **10** and in particular provides abrasion and/or fatigue resistance to the fiber **10**. That is, outer cladding **30** has a higher strength parameter **S** and/or a higher dynamic fatigue parameter **nd** than inner cladding **20**. A fiber with a strengthened outer cladding **30** is referred to herein as a “cladding-strengthened fiber”, or a “cladding-strengthened optical fiber”, or a “cladding-strengthened glass fiber”, or a “cladding-strengthened glass optical fiber”. The outer cladding **30** need not be stripped off during splicing or termination. The outer cladding **30** has an outer surface **32**, which defines the outer surface of the cladding region **40**. The outer surface **32** is a glass surface.

The outer cladding **30** has an amount of compressive stress **SC** that strengthens the outer surface **32** of the outer cladding layer in a manner similar to chemically strengthened glasses. In an example, the amount of compressive stress **SC** is in the range from 30 MPa to 100 MPa. In addition, the formation of microcrystals due to doping of the SiO_2 with titania can stop defects such as scratches from propagating through the fiber **10**, resulting in further fatigue resistance. In an example, the doping concentration of titania in the SiO_2 of the outer cladding **30** is in the range from 5 wt % to 25 wt %. The outer cladding **30** contributes to the overall refractive index profile of the fiber **10**, but is also designed to avoid excess loss of the guided light from the core **16**. Because the titania dopant in silica glass increases the refractive index, it can cause tunneling loss of guided light traveling in the core **16** to the titania doped outer cladding **30**. To avoid this excess loss, the starting position (inner radius) of outer cladding **30** needs to be sufficiently away from the core. Preferably, the spacing (radial distance) between the core **16** and the outer cladding **30** (i.e., the thickness **TH2** of the inner cladding **20** as shown in FIG. 2A) is greater than 25 μm and more preferably greater than 30 μm .

The fiber **10** also has an outer surface **70**. In the example of FIG. 2A, fiber **10** is bare fiber **10B** and outer surface **70** is the same as the outer surface **32** of the outer cladding **30**. FIG. 2B is similar to FIG. 2A and illustrates an example sealed fiber **10H** that includes a hermetic sealing layer **50** on the outer surface **32** of the outer cladding **30**. In an example, the hermetic sealing layer **50** comprises or consists essentially of carbon. In one example, the hermetic sealing layer **50** has a thickness **TH5** < 100 nm and so does not contribute substantially to the overall size (diameter **DF**) of the sealed fiber **10H**. In an example, the hermetic sealing layer is made of an inorganic material, e.g., is not made of an organic polymer such as acrylate. The hermetic sealing layer **50** is designed to prevent moisture and other adverse materials in the environment from entering and possibly damaging the fiber. The hermetic sealing layer **50** is thus substantially different in chemical composition from a protective coating used on conventional individual optical fibers or the common protective coating for fibers in an array or bundle. Protective coatings for individual optical fibers and fiber arrays or bundles are organic polymers. The organic polymers are formed by polymerizing organic monomers, usually acrylate or methacrylate monomers. Thermoplastic organic polymers are also used as protective coatings for

individual optical fibers and fiber arrays or bundles. The hermetic sealing layer **50** is not an organic polymer and has a thickness well below the thickness used for the protective coatings of individual optical fibers or fiber arrays or bundles. In an example discussed below, the hermetic sealing layer comprises a self-assembled monolayer (SAM), such as formed using a silane compound. Example hermetic sealing layers **50** are discussed in greater detail below. In the discussions below, the fiber **10** can be a fiber such as sealed fiber **10H** in FIG. 2B or a bare fiber **10B** such as in FIG. 2A, unless the particular type of fiber is specified.

A given length of fiber **10** has opposite end sections **60** each with an end face **62**, as shown in FIG. 1. The fiber **10** has the aforementioned outer surface **70**, which can be defined by the cladding region **40** as in bare fiber **10B** of FIG. 2A or the hermetic sealing layer **50** as in sealed fiber **10H** of FIG. 2B, depending on the configuration of the fiber.

In the discussion and in the drawings, reference to fiber **10** refers to either bare fiber **10B** or the sealed fiber **10H**, unless otherwise noted.

Fabricating the Fiber

The fiber **10** can be made by drawing a fiber from a preform using standard optical fiber fabrication drawing techniques. FIG. 3A is a schematic diagram of an example optical fiber drawing system (“drawing system”) **100**. The drawing system **100** may comprise a draw furnace **102** for heating the preform to the glass melt temperature, non-contact measurement sensors **104A** and **104B** for measuring the size of the drawn fiber as it exits the draw furnace for size (diameter) control, a cooling station **106** to cool the drawn fiber, a tensioner **120** with a surface **122** to pull (draw) the fiber, guide wheels **130** with respective surfaces **132** to guide the drawn fiber, and a fiber take-up spool (“spool”) **150** to store the drawn fiber.

The drawing system **100** also includes a preform holder **160** located adjacent the top side of the draw furnace **102** and that holds a glass preform **10P** used to form the fiber **10**. With reference to the close-up inset of FIG. 3A that shows a cross-sectional view of the glass preform **10P**, the preform has a preform core **16P**, an inner preform cladding **20P** and a outer preform cladding **30P**. The glass preform **10P** has generally the same relative configuration and dimensional proportions in the radial direction as bare fiber **10B** but is much larger, e.g., 25 \times to 100 \times larger.

The preform core **16P** can be made by doping silica with an index-increasing dopant such germanium oxide. The inner preform cladding **20P** and outer preform cladding **30P** start out as pure silica (SiO_2). The preform outer cladding **30P** is then doped with titania to strengthen it. The glass preform **10P** and in particular preform core **16P** and the inner preform and outer preform cladding layers **20P** and **30P** may be produced in a single-step process or multi-step process. Suitable methods or processes include: the double crucible method, rod-in-tube procedures, and doped deposited silica processes, also commonly referred to as chemical vapor deposition (CVD). A variety of CVD processes are known and are suitable for producing the core and cladding layers used in the optical fibers of the present invention. They include outside vapor deposition process (OVD) process, vapor axial deposition (VAD) process, modified CVD (MCVD), and plasma-enhanced CVD (PECVD).

After the glass preform **10P** is formed, it is operably supported in the preform holder **160** relative to the draw furnace as shown in FIG. 3A. The glass preform **10P** is then heated by the draw furnace **102** and drawn into fiber **10** using the drawing system **100**. The drawing process is similar to a conventional fiber draw process, except that no

polymer coatings are added to the fiber **10**, i.e. the fiber is a bare glass fiber **10B** with a strengthened outer cladding **30** or a sealed glass fiber **10H** with a strengthened outer cladding **30** and a hermetic sealing layer **50** as discussed above. Note in particular that the doped outer preform cladding **30P** defines the chemically strengthened (doped) outer cladding **30** when the preform **10P** is drawn to form the fiber **10**.

In the fabrication process, the fiber drawn from glass preform **10P** exits the draw furnace **102**, with tension applied by the tensioner **120**. The dimensions (e.g., the diameter) of the fiber are measured by the non-contact sensors **104A** and **104B** and the measured dimensions are used to control the draw process. The fiber can then pass through the cooling mechanism **106**, which can be filled with a gas that facilitates cooling at a rate slower than air at ambient temperatures. At this point, the fiber **10** is a bare fiber **10B**.

The fiber **10** passes from the tensioner **120** to the guide wheels **130**, then through the guide wheels to the spool **150**, where the fiber **10** is taken up and stored. It is noted that a bare glass fiber without a protective coating that lacks outer cladding **30** cannot be collected on a take-up spool as a practical matter due to the high break rate due to surface damage to the fiber. The strengthened outer cladding **30** of fiber **10** makes possible collecting this glass fiber on the spool **150** without breaks. Also, in an example, the tensioner surface **122** and the guide wheel surfaces **132** preferably comprise either a polymer material such as a fluoropolymer (e.g., polytetrafluoroethylene or PTFE), or a plastic material or a rubber material, to protect the fiber **10** from surface damage.

The configuration of the glass preform **10P** and the various drawing parameters (draw speed, temperature, tension, cooling rate, etc.) dictate the final form of the fiber **10**.

Embodiments of the Hermetic Sealing Layer

In the example sealed fiber **10H** of FIG. **2B** that includes the hermetic sealing layer **50** (i.e., the coated fiber), the drawing system **100** can include an applicator device **170** that applies a hermetic sealing layer material **50M** to the drawn bare fiber **10B** as the bare fiber **10B** passes by the applicator device **170**. The applicator device **170** can also be one that is off-line, i.e., in another location besides in the drawing system **100** and employed after the bare fiber **10B** is collected on the spool **150**, with the fiber distributed from the spool for application of the hermetic sealing layer material **50M** to bare fiber **10B** by the applicator device **170** for form hermetic sealing layer **50**.

In an example, the hermetic sealing layer material **50M** comprises an inorganic material, such as an inorganic hydrophobic material. Hermetic sealing layer materials that include silicon are regarded herein as inorganic materials even if carbon or an organic fragment is bonded to silicon. Organosilanes, for example, are regarded as inorganic materials for purposes of the present disclosure.

In another example, the hermetic sealing layer material **50M** comprises a self-assembled monolayer (SAM). In an example, the SAM is formed using a silane, preferably an organosilane, which can be applied in liquid form onto the bare fiber **10B** using the applicator device **170**. The SAM hermetic sealing layer material **50M** that defines an example hermetic sealing layer **50** produces a hydrophobic outer surface **70** for the sealed fiber **10H** that shields the outer cladding **30** from moisture, thereby slowing down the development of glass fatigue and reduce fiber breaks. Because the SAM layer is thin (e.g., <10 nm), it does not need to be removed when making the fiber ribbon (introduced and discussed below), and does not affect fiber positioning (e.g.,

the fiber ribbon pitch). In some embodiments, the SAM layer covers or is uniformly distributed over the entirety of the outer surface **32** of the outer cladding **30**. In other embodiments, the SAM layer does not cover or is not uniformly distributed over the entirety of the outer surface **32** of the outer cladding **30**. For example, gaps may exist in the SAM layer and portions of the outer surface **32** of the outer cladding **30** may be exposed.

One example of a silane in liquid form comprises octadecyldimethyl trimethoxysilylpropyl ammonium chloride (60 wt % in MeOH), acetic acid (0.05 wt %) and deionized water (18 Mohm, 0.2 micron filtered). In an example, the proportions by weight of the three ingredients can be 16.7:1:19823.4. The deposited layer of the silane liquid as the hermetic sealing layer material **50M** produces on the outer surface **32** of the outer cladding **30** a hermetic sealing layer **50** with a hydrophobic fiber outer surface **70** that can inhibit moisture from getting into the glass material of the fiber.

FIGS. **3B** and **3C** are close-up views of the outer surface **32** of the sealed fiber **10H** and illustrate how the outer surface can be functionalized using a fluorinated silane **80** as hermetic sealing material **50M**. The fluorinated silane **80** includes a silane core **82** and fluorinated chain **84** attached thereto. The fluorinated silane **80** can be introduced to the outer surface **32** (FIG. **3B**) so that the silane core **82** bonds to silanol groups **86** on the outer surface **32**, thereby forming the thin silane-based SAM hermetic sealing layer **50** (FIG. **3C**).

In an example, a solution of perfluoropolyether-functionalized silane **80** was used as the hermetic sealing layer material **50M** to create a hydrophobic hermetic sealing layer **50**. The silane-based hermetic sealing layer material **50M** was prepared as a solution by adding 0.12 vol % perfluoropolyether-functionalized silane to a fluorinated solvent. Perfluoropolyether-functionalized silanes include Fomblin®-based silanes (available from Solvay), Demnum-based silanes (available from Daikin Industries), and Krytox™-based silanes (available from Chemours). A typical structure of perfluoropolyether-functionalized silanes is $\text{Si}(\text{OCH}_3)_3\text{C}_3\text{H}_6\text{O}(\text{CF}_2)_x(\text{OCF}_2\text{CF}_2)_y\text{CF}_3$. Fluorinated solvents include $\text{C}_4\text{F}_9\text{OC}_2\text{H}_5$ (e.g. Novec 7200), $\text{C}_5\text{H}_2\text{F}_{10}$ (e.g. HFC-4310mee), $\text{C}_3\text{HCl}_2\text{F}_5$ (e.g. HCFC-225-ca/cb). Non-fluorinated solvents such as chloroform or toluene can also be used. A silane-based hermetic sealing layer material **50M** can be applied to the bare fiber **10B** by using an applicator device **170** that includes a die containing the liquid hermetic sealing layer material **50M**. After passing through the die, a thin layer of the hermetic sealing layer material **50M** is coated on the outer surface **32**. Some hermetic sealing layer materials **50M** can be dried in air at the ambient temperature. Some hermetic sealing layer materials **50M** require curing. The curing can be done by heating for heat-curable materials or by UV light for UV-curable materials.

In another example, the hermetic sealing layer material **50M** comprises carbon to define a carbon-based hermetic sealing layer **50**. The carbon can be deposited on the outer surface **32** of the outer cladding **30** by the applicator device **170** in the form of an atmospheric chemical vapor deposition chamber in which a hydrocarbon gas, such as methane, acetylene, ethylene, propane, etc. undergoes pyrolysis and a heterogeneous reaction on the outer surface **32**. Carbon is strongly bonded to silica with Si—C bond. The carbon layer has typically a randomly oriented graphite platelet structure or amorphous cross-linked graphite structure. Forms of carbon with graphite structures are regarded herein as inorganic materials.

The wettability of example sealed fibers **10H** with the hermetic sealing layer **50** was evaluated by using dynamic contact angle measurement using a tensiometer (K100C-MK2, Kruss GmbH, Germany). The contact angle θ is a quantitative measure of wettability of the outer surface **70** of the fiber **10H** by a liquid. Generally, if the contact angle θ is less than 90° the surface is said to be hydrophilic. On the other hand, if the contact angle θ is greater than 90° , the surface is said to be hydrophobic.

FIG. **3D** is a plot of the contact angle θ ($^\circ$) versus measurement position P (mm) for a bare fiber **10B** (i.e., no hermetic sealing layer **50**; see FIG. **2A**) and for a sealed fiber **10H** (see FIG. **2B**) having a silane-based hermetic sealing layer **50** as described above. The plot includes the advancing contact angle measured as the sample fiber **10** is immersed in the liquid (+ P direction) and the receding contact angle measured as the sample fiber emerges from liquid ($-P$ direction). Table 1 below lists the advancing, receding and the contact angle hysteresis (difference between the advancing and receding contact angle). The contact angle hysteresis is a measure of surface heterogeneity and surface roughness.

TABLE 1

| Sample | Water contact angle θ ($^\circ$) | | |
|----------------------|---|-----------------|-----------------|
| | Advancing | Receding | Hysteresis |
| Bare fiber | 29.3 ± 18.2 | 63.0 ± 7.0 | 33.7 ± 25.2 |
| Coated fiber | 131.4 ± 5.0 | 114.9 ± 5.6 | 16.6 ± 10.6 |
| Control (flat glass) | 118.4 ± 0.3 | 95.8 ± 3.1 | 22.6 ± 3.3 |

Contact angles θ of the bare fibers **10B** were in the range of 29 - 63° indicating the hydrophilic nature of the bare fibers **10B**. In contrast, contact angles θ measured on the sealed fiber **10H** were in the range of 115 - 131° , indicating that the hermetic sealing layer **50** is hydrophobic. In addition, the contact angle hysteresis of the sealed fibers **10H** is lower than that for the bare fibers **10B**, suggesting good uniformity of the hermetic sealing layer **50** on the outer surface **70**.

In the case of a silane-based hermetic sealing layer **50**, the thickness TH **5** of this layer need not exceed 10 nm. The thickness of a hermetic sealing layer **50** made in the form of a SAM from a silane-based hermetic sealing material **50m** is less than or equal to 10 nm, or less than or equal to 8 nm, or less than or equal to 6 nm, or in the range from 3 nm- 10 nm, or in the range from 4 nm- 8 nm. These ranges for the thickness TH **5** are suitable if the main purpose of the hermetic sealing layer **50** is to provide hydrophobicity. In other embodiments, the hermetic sealing layer **50** is also used to improve the mechanical properties of the fiber and the thickness TH **5** of the hermetic sealing layer **50** is preferably greater than 10 nm. In an example, the hermetic sealing layer material **50** can comprise a fluorosilicone and/or a perfluoroelastomer and the layer thickness TH **5** can be in the range from 10 nm- 10 microns, or in the range from 50 nm- 5 microns, or in the range from 100 nm- 3 microns. One example of the fluorosilicone comprises a polysiloxane backbone with fluorinated pendent groups (e.g. trifluoropropyl groups). Such fluorosilicones can be moisture cured or catalyst-cured (e.g. platinum-cured) with a hydride cross-linker at room temperature and the cure can be accelerated by applying heat. The fluorosilicones, in addition to providing hydrophobicity, can also provide shock and vibration absorption and increased durability, thereby increasing the mechanical properties of the fibers.

In another example, the hermetic sealing layer material **50M** comprises a perfluoroelastomer (FKM). A type of FKM

suitable for use as the hermetic sealing layer material **50M** is known as VITON®, which is a registered trademark of The Chemours Company of Wilmington, Delaware. In an example, the FKM can be cured by peroxide and can also be grafted with silicones using amino-functionalized polydimethyl siloxane. These silicone-grafted FKMs can provide the flexibility of the silicones along with the durability and tensile strength of the FKMs.

Fiber Ribbon

FIG. **4A** is a top-down view of an example optical fiber ribbon (“fiber ribbon”) **200** that employs an array **8** of the fibers **10** disclosed herein. FIG. **4B** is an x-y cross-sectional view of the example fiber ribbon **200** as taken along the line A-A in FIG. **4A**. The example fiber ribbon **200** of FIG. **4A** has a substantially constant x-y cross-sectional shape in the z-direction. The array **8** of fibers **10** are arranged in a row i.e., with their centerlines AC substantially residing on reference line R1 that runs in the x-direction (see the close-up inset of FIG. **4B**). The fiber ribbon **200** has a first end section **201** with a first end **202** and a second end section **203** with a second end **204**.

While the fiber ribbon **200** can generally comprise two or more fibers **10** in the fiber array **8**, in some preferred embodiments, the fiber ribbon **200** comprises multiples of 8 fibers, e.g., 8 , 16 , 24 , etc.

The fibers **10** reside within a common protective coating **210**, i.e., the common protective coating **210** generally surrounds the outer surfaces **70** of the fibers **10**. The cross-sectional view of FIG. **4B** shows the fibers **10** encapsulated within the common protective coating **210**. In some examples, one or both end sections **60** of one or more of the fibers **10** are exposed, as explained below. The common protective coating **210** has an outer surface **221** with a top side **222**, a bottom side **224** and edges **226**. In an example, the common protective coating **210** has an oval, rectangular (with sharp or rounded corners), or similar elongate shape, with a long dimension LX in the x-direction and a short dimension LY in the y-direction. Note that in an embodiment where the outer surfaces **70** of the fibers **10** are in contact with each other to maximize the fiber density, the common protective coating **210** may not be contact the entire outer surface **70** of each fiber **10** at the location where adjacent fibers are in contact. In other embodiments where the fibers **10** are spaced apart from each other, the common protective coating **210** surrounds the entire outer surface **70** of each fiber over at least a portion of the length of the fiber ribbon **200**.

As discussed above, typical optical fibers, in an array or individually, each have an individual protective coating. In contrast, the fibers **10** in array **8** do not each include individual protective coatings. Instead, the common protective coating **210** is common to fibers **10** in array **8** of fiber ribbon **200**. As used herein, a coating is said to be “common” if it is applied to a plurality of fibers **10** of an array **8** and if it makes direct contact with an outer surface **70** of at least some of the plurality of fibers **10** of the array **8**. The common protective coating **210** may be applied simultaneously to the plurality of fibers **10** of the array **8**. If the plurality of fibers **10** includes two or more bare fibers **10B**, a coating is common if it makes direct contact with outer surface **32** of at least two of the fibers in the plurality. If the plurality of fibers includes two or more hermetic sealed fibers **10H**, a coating is common if it makes direct contact with outer surface **70** of at least two of the fibers in the plurality.

In an example, the common protective coating **210** is made of a non-glass material, and further in the example is made of a polymer such as those used as protective primary

or secondary coatings for individual optical fibers. The polymer is preferably an organic polymer. Such polymers include acrylates, methacrylates, and polyamides. Other non-glass materials known in the art for coating glass optical fibers can also be used for the common protective coating **210**, including thermoplastics and adhesives. In an example, the material used for the common protective coating **210** is curable by exposure to ultraviolet (UV) light (i.e., is UV curable). An example thermoplastic has a melt temperature in the range of 160° C. to 260° C., a melt viscosity in the range of 100 centipoise (cP) to 10,000 cP, and an operating temperature from -40° C. to 100° C., noting that telecommunications standards involve testing telecommunications components (including fibers) over a temperature range from -40° C. to 85° C.

In an experiment, an example fiber **10** having an outer cladding **30** with a thickness of 2 μm was formed using the above-described drawing process using the drawing system **100** and wound around the take-up spool **150**. Then eight fibers **10** were bundled together to form a fiber array **8**. The fiber array **8** was then coated using a thermoplastic split die coating drawing process to form a common protective coating **210** around the eight fibers **10**. The polymer used to form the common protective coating **210** was polyamide (Henkel PA652, also known as MACROMELT OM 652, available from Henkel Corporation, Rocky Hill, Conn.), which was heated to 190° C. as the fiber array **8** passed through. The polyamide coating solidified when cooled down to less than 120° C. to form the (solid) common protective coating **210**. With reference to FIG. 4B, the resulting fiber ribbon **200** had a dimension LY in the y-direction 0.21 mm and a dimension LX in the x-direction of 1.1 mm. The fiber ribbon **200** was measured for bending loss and exhibiting the preferential bending properties as expected.

FIG. 4C is similar to FIG. 4B and shows an example embodiment wherein the fibers **10** are arranged in two arrays **8** in the form of rows defined by respective reference lines R1 and R2 that run in the x-direction. More than two rows of fibers **10** can also be implemented, and the discussion below focuses on a single-row embodiment of the fiber ribbon **200** for ease of illustration and explanation.

The fibers **10** define a fiber pitch PR for the fiber ribbon **200**, which defines the fiber density for the fiber ribbon i.e., the number of fibers per unit length along the given row of fibers. As discussed below, the fiber pitch PR for the fiber ribbon **200** can be constant with length along the fiber ribbon, or can change, depending on the particular fiber ribbon configuration. The fiber pitch PR can be in the range from the fiber diameter DF to 250 microns, wherein the greatest fiber density is about 2× of the greatest fiber density of a conventional fiber ribbon. This factor increases to 4× for two-dimensional arrays **8** (i.e., two rows) of fibers **10**.

In one embodiment, fiber density is expressed as the separation between adjacent glass optical fibers in a fiber ribbon. Each of the fibers in a ribbon has a centerline and fiber density is expressed in terms of the separation between centerlines of adjacent glass optical fibers in the fiber ribbon. The separation of centerlines of adjacent glass optical fibers is less than 150 microns, or less than 125 microns, or less than 100 microns, or less than 80 microns, or less than 60 microns, or in the range from 40 microns-150 microns, or in the range from 60 microns-125 microns, or in the range from 75 microns-110 microns.

The fiber density of the fiber ribbon **200** is greater than that of a conventional fiber ribbon mainly because conventional optical fibers include individual protective coatings

applied during the fiber drawing process. Such protective coatings typically have an outer diameter of about 240 microns, which approximately doubles the diameter of the fiber relative to the cladding-strengthened fibers disclosed herein. Without the protective coating, a conventional optical fiber has very high chance of breaking when wound onto the take-up spool because a conventional optical fiber lacks a strengthened outer cladding **32** as described herein, which makes the ribbon fabrication process with high fiber density as disclosed herein impractical to implement. The local stress imparted to a bare glass conventional fiber also present long-term reliability risks that are mitigated through inclusion of the strengthened outer cladding **32**.

In one example, the common protective coating **210** is made of a single polymer material. In another example illustrated in the close-up cross-sectional view of FIG. 4D, the common protective coating **210** includes multiple polymer materials, which in one aspect are layered to define a primary (inner) layer **212** and a secondary (outer) layer **214** in the case of two different polymer materials. In an example, the secondary layer **214** has a higher elastic modulus than the primary layer **212**, with the elastic modulus of the entire common protective coating **210** being an effective elastic modulus that is substantially an average of the respective elastic moduli of the primary and secondary layers. This configuration provides a relatively soft, cushioning layer closest to the fibers **10** that protects the fibers from mechanical loads while also providing a harder, abrasion-resistant layer on the outermost surface **221** of the fiber ribbon. An example of a dual-layer common protective coating **210** that can be effectively utilized to form the fiber ribbon **200** is the Corning° CPC° protective coating, available from Corning, Inc., Corning, N.Y. In an example, the effective elastic modulus of a protective coating with one or a plurality of layers is in the range from 10 MPa-1000 MPa, or in the range from 20 MPa-800 MPa, or in the range from 50 MPa-600 MPa.

The common protective coating **210** may be deposited over the fibers **10** using techniques known in the art such as by disposing a curable coating composition on the fibers **10** and then curing the curable coating composition using, for example, ultraviolet (UV) light, heat, or by other means known in the art. In this embodiment, the common protective coating **210** is a cured product of the curable coating composition.

The fiber ribbon **200** may optionally include indicia **230**, such as geometrical features, markings, colorings, etc. to identify the polarity of the fiber ribbon. For instance, with reference to FIG. 4E, the common protective coating **210** may be made asymmetric relative to the reference line R1, e.g., the thickness of the common protective coating **210** may be different between the reference line R1 and the top surface **222** as compared to the thickness between the reference line R1 and the bottom surface **224**. In other example, the top/bottom sides or left/right sides of the common protective coating **210** can be formed by polymers having different colors.

Fiber Ribbon Cable

FIG. 5A is a top-down view similar to FIG. 4A and shows an example of a fiber ribbon cable **300** formed using the fiber ribbon **200**. The fiber ribbon cable **300** has first and second end sections **301** and **303** that respectively include first and second ends **302** and **304**. The first and second ends **202** and **204** of the fiber ribbon are shown as coinciding with the first and second ends **302** and **304** of the fiber ribbon cable, but this need not be the case.

FIGS. 5B through 5D are cross-sectional views of examples of the fiber ribbon cable 300 of FIG. 5A. The fiber ribbon cable 300 includes the fiber ribbon 200 and a cover assembly 310 that surrounds the outer surface 221 of the common protective coating 210 of the fiber ribbon. In an example, one or more fiber ribbons 200 can be loosely arranged within the cover assembly 310, i.e., the fiber ribbon cable 300 can be a loose-buffered cable. In another embodiment, the fiber ribbon cable 300 can be a tight-buffered cable.

In the example cover assembly 310 of the fiber ribbon cable of FIG. 5B, the fiber ribbon 200 is surrounded by a strength layer 314 (e.g., aramid yarn), and an outer jacket 320 that surrounds the strength layer. The example configuration of FIG. 5C comprises a binder layer 312 that surrounds the fiber ribbon 200, with the strength layer 314 surrounding the binder layer 312 and the outer jacket 320 surrounding the strength layer.

FIG. 5D shows an example where the outer jacket 320 is provided directly to the outer surface 221 of the common protective coating 210 of the fiber ribbon 200.

Various other configurations for the cover assembly 310 as known in the art can also be effectively employed. For example, multiple fiber ribbons 200 can be supported within the cover assembly 310.

Fiber Ribbon Interconnect

The fiber ribbon 200 is compatible with existing fiber processing tools and termination components. In one example, a fiber ribbon interconnect is formed by terminating the first and second ends of the fiber ribbon 200 with respective optical fiber connectors (“connectors”). In another example, the fiber ribbon interconnect is formed by connectorizing the fiber ribbon at only one end. In another example, a fiber ribbon interconnect includes the cover assembly that forms a fiber ribbon cable 300. Most of the example fiber ribbon interconnects discussed below are formed from a fiber ribbon cable 300, but the fiber ribbon interconnect as disclosed herein need not include the cover assembly 310. Furthermore, as noted above, the fiber ribbon interconnect disclosed herein can include only one connectorized end.

Connectorizing the fiber ribbon 200 with connectors to form a fiber ribbon interconnect typically requires extracting the fibers 10 from the common protective coating 210. This process can be done mechanically, though it may be relatively difficult as compared to conventional fiber ribbons. Thus, other stripping approaches, such as chemical stripping and thermal stripping, can be used. An example chemical stripping approach includes using hot sulfuric acid. An example thermal stripping process includes the use of a hot nitrogen jet.

FIG. 6 is an elevated view of an example fiber ribbon interconnect 400 that includes the fiber ribbon cable 300 terminated at the first and second ends 402 and 404 by respective optical fiber connectors (“connectors”) 450. In an example, the connectors 450 can be the same or substantially the same connector. In an example, the one or both of the connectors 450 can be high-density connectors, denoted 450H. The term “high density” generally means a fiber density that is greater than a conventional optical fiber connector, such as an MPO connector, which typically has a fiber density (pitch) of 250 crows. In the discussion below, some connectors 450 can be standard-density connectors, and these are denoted 450S.

High-Density Connector Assembly

FIG. 7A is an exploded front elevated view of an example method of forming a high-density connector assembly

(“connector assembly”) 452 that can be used directly as the high-density connector 450H or that can be used to form the high-density connector 450H (e.g., by adding further connector components, as discussed below).

The connector assembly 452 includes a grooved substrate 460 having a front-end section 461 with a front end 462, a back-end section 463 with a back end 464, and a central axis A2 that runs in the z-direction. The front-end section 461 has a planar top surface 472 while the back-end section 463 has a planar top surface 474 that is lower than the top surface 472 of the front section. The front-end section 461 includes an array 480 of grooves 482 formed in the planar top surface 472 and that run parallel to the central axis A2. In an example, the grooved substrate 460 comprises a glass or glass-based material. In an example, the grooves 482 are V-grooves, but other cross-sectional shapes for the grooves can also be effectively employed.

FIG. 7A shows the end sections 60 of the array 8 of fibers 10 of the fiber ribbon 200 extracted from the common protective coating 210. The grooves 482 of the front-end section 461 of the V-groove support substrate 460 are sized to accommodate the end sections 60 of the fibers 10 while the back-end section 463 accommodates the fiber ribbon 200, which in an example has been removed from the cover assembly 310 of a fiber ribbon cable 300 (e.g., a portion of the cover assembly has been stripped away). In an example, the fiber pitch P1 at the first end 202 of the fiber ribbon 200 is 125 μm and is closely matched to the pitch PV of standard 127 μm grooves 482.

Once the end sections 60 of the fibers 10 are supported in the grooves 482, then with reference to FIGS. 7B and 7C, an adhesive 490 is applied to the fiber ribbon 200 at the back-end section 463. A cover 500 having a front end 502, a back end 504, a top surface 512 and a bottom surface 514 is then placed over the top of the array 480 of grooves 482 to secure the end sections 60 of the fibers 10 in the front-end section 461 of the grooved support substrate 460. The cover 500 is held in place by the adhesive 490 contacting the back end 504 of the cover. The adhesive 490 can also be added to the grooves 482. The cover 500 can be used to press the end sections 60 of the fibers 10 into their respective grooves 482. In an example, the cover 500 is a thin planar sheet made of a glass or a glass-based material.

FIG. 7B shows the resulting connector assembly 452, with the end faces 62 of the fibers 10 residing substantially at the front end 462 of the grooved substrate 460. The connector assembly 452 supports the fibers at a pitch P1 (wherein P1=PV), which can be the same as or different than the fiber pitch PR of the fiber ribbon 200. The fiber end faces 62 are typically polished once assembly of the connector assembly 452 is completed.

FIG. 7C is a y-z cross-sectional view of the connector assembly 452 as attached to the end section 201 of the fiber ribbon 200, which is shown as incorporated into a cover assembly to form a fiber ribbon cable 300. In this case, a portion of the cover assembly 310 is stripped away to expose the first-end section 201 of the fiber ribbon 200. In an example, the front end 462 of the grooved substrate, the front end 502 of the cover 500 and the end face 62 of the fiber 10 define a tilt angle θ relative to a vertical plane VP to reduce reflection losses. In an example, the tilt angle θ can be up to about 8 degrees.

FIG. 7D is similar to FIG. 7B and illustrates an example high-density connector 450H formed by at least partially enclosing the connector assembly 452 within a connector housing 454 having a front end 456 and a back end 457. In an example, the high-density connector 450 includes at least

one alignment feature **458**, which is shown by way of example as alignment pins that extend from the front end **456** of the connector housing to define a plug type connector. The at least one alignment feature **458** can also comprise alignment holes sized to receive alignment pins, thereby defining a receptacle type connector.

The front end **462** of the grooved substrate **460** is shown residing at or proximate to the front end **456** of the connector housing **450** while the fiber ribbon **200** extends from the back end **457** of the connector housing. In another example, the connector assembly **452** can extend from the front end **456** of the connector housing **454**.

Fan-Out Fiber Ribbon

FIG. **8A** is a top-down view of an example fiber ribbon **200** similar to that shown in FIG. **4A**, except that the fiber pitch PR is not constant along the length of the fiber ribbon. FIGS. **8B** and **8C** are cross-sectional views of the fiber ribbon **200** as taken along the lines B-B and C-C respectively, and show two different fiber pitches PR1 and PR2 as a function of the z-position, and in particular at the front-end section **201** and the back-end section **203**. In an example, the change in the fiber pitch PR occurs over a fan-out region **250** of length LF, with the fiber pitch PR1 in the front-end section **201** being substantially constant and the fiber pitch PR2 in the back-end section **203** being substantially constant. The length LF is called the transition length, and the fiber ribbon **200** with the fan-out region **250** is called a fan-out fiber ribbon. In an example, the fiber pitch PR1 at the first end **202** of the fiber ribbon **200** is in the range from 80 microns to 125 microns (which can also be the range of the diameter DF of the fiber **10**) while the fiber pitch PR2 at the second end **204** is greater, such as that for a standard connector, e.g., 250 microns.

The transition length LF of the fan-out region **250** can be designed to minimize the bending stress on the fibers **10**. As can be seen in FIG. **8A**, the outermost fibers **10** experience the greatest amount of bending, i.e., the tightest bend radius. In an example, the shape of the fiber transition in the fan-out region **250** is designed to maximize the bend radius along the fiber's path. In one example, the fiber path is a half period of a cosine function, which is also known in the art of waveguide design as an "S-bend." For example, for an 8-fiber fan out, the outermost fiber **10** has an x position as a function of axial position z as given by $x = \{3.5 \cdot (\text{PR}2 - \text{PR}1) / 2\} \cdot \cos\{\pi z / \text{LF}\}$. In an example the transition length LF is about 10 mm, so that the minimum bend radius, which occurs at both ends of the transition, is at least 46 mm. The corresponding maximum tensile stress in the fiber **10** at this bend radius is about 14 kpsi, which is well within the capability of the fiber.

Reliability research of example fibers **10** showed a significantly increased fatigue resistance factor as compared to conventional fibers, even though the tensile strength of the fiber was on par or even slightly less than conventional fiber. As a result, while conventional fiber can one operate in the 20%~30% of proof tested stress level, examples of the fiber **10** are fatigue resistant and can operate at about 80% of proof test stress level.

FIG. **9** is a top-down view of an example fiber ribbon assembly **400** that includes the fan-out fiber ribbon **200** of FIG. **8A** with a high-density connector **450H** operably attached to the first (narrow) end **202** of the fan-out fiber ribbon and a standard-density connector **450S** attached to the second (wide) end of the fan-out fiber ribbon. In an example, the standard-density connector **450S** comprises an MPO connector that supports the fibers **10** at a standard pitch P2 of 250 microns. In an example, the fiber ribbon assembly

400 can include the cover assembly **310**, only a portion of which is shown in dashed-line outline in FIG. **9** for ease of illustration.

Furcated Fiber Ribbon

FIG. **10A** is similar to FIG. **8A** and illustrates an example embodiment of a furcated fiber ribbon **200** wherein the fiber ribbon is bifurcated at a furcation location **209** into two sub-sections (bifurcations) **200A** and **200B** having respective second ends **204A** and **204B** and each containing a sub-set of the total set (array) of fibers **10**. This furcated configuration for the fiber ribbon **200** is useful for example when making optical connections to transmitters and receivers that reside on separate silicon-photonics chips. In other embodiments, there can be two or more furcations (**200A**, **200B**, **200C**, etc.), with the bifurcation embodiment shown by way of example. Also in an example the furcations need not have the same number of fibers **10** and need not have the same length. The furcation location **209** can also be selected for convenience based on the given connection application.

FIG. **10B** shows cross-sectional views of the example sub-sections **200A** and **200B** of the furcated fiber ribbon **200**, wherein each sub-section includes four of the eight total fibers **10**. In the example furcated fiber ribbon **200** of FIG. **10B**, the first end section **201** of the furcated fiber ribbon **200** is unfurcated (see also FIG. **8B**) and is terminated by a single connector **450** (e.g., high-density connector **450H**) while the second end section **203** now comprises two end sections **203A** and **203B** with respective ends **204A** and **204B** each terminated by a connector **450** (e.g., high-density connectors **450H**), as shown in FIG. **10C**, to define an example fiber ribbon interconnect **400**. In an example, the furcated fiber ribbon **200** can be incorporated into a furcated cover assembly **310** to form a furcated fiber ribbon cable **300**.

Optical Data Transmission System

FIG. **11A** is a schematic diagram of an example optical data transmission system **700**. The optical data transmission system **700** comprises a photonic device **710** having a circuit board **720** having a top surface **722** and that operably supports a photonics chip **730**, e.g., a silicon-photonics chip. The photonics chip **730** has a front end **732**. The example optical data transmission system **700** also includes a telecommunications device **800** having a connector receptacle **810**. The optical data transmission system **700** also includes an example fiber ribbon interconnect **400** with a high-density connector **450H** and a standard-density connector **450S**.

FIG. **11B** is a top-down view of an example photonic device **710**. FIG. **11B** also shows the high-density connector **450H** at the first end **402** of the fiber ribbon interconnect **400** in position to operably engage the photonic device. The photonics chip **730** operably supports an array of optical waveguides **740**. Eight optical waveguides **740** that terminate at the front end **732** of the photonics chip **730** are shown by way of example. In an example, the optical waveguides **740** comprise channel waveguides.

The photonics chip **730** may be fabricated from any material capable of having optical waveguides **740** disposed thereon or therein. As non-limiting examples, the photonics chip **730** may be fabricated from a glass-based material (e.g., glass, glass-ceramic, and fused silica) or a semiconductor material (e.g., silicon). The optical waveguides **740** may be configured as any known or yet-to-be-developed optical waveguides. Non-limiting example optical waveguides **740** include thin-film deposition, photolithographic masking and etching processes, laser written waveguides, ion-exchanged waveguides, optical waveguides, among others. It will be understood that the optical waveguides **740** may be suitably

configured for the operations of the photonics chip **730** and are merely schematically depicted in a straight-line configuration.

The optical waveguides **740** are operably connected to respective active photonic elements **750**, which in an example can comprise an optical transceiver, an optical light source (e.g., a vertical-cavity surface-emitting laser or VCSEL) or an optical detector. In an example, the photonics chip **730** can comprise a first sub-chip that includes the optical waveguides **740** and a second sub-chip that includes the active photonic elements **750**.

In an example, the photonics chip **730** is configured to generate and/or receive optical data signals using the active photonic elements **750** and the optical waveguides **740**. The optical waveguides **740** terminate the front end **732** of the photonics chip **730**. The front end **732** of the photonics chip **730** can include one or more alignment features **734**, which are shown by way of example as alignment holes. In an example, the front **732** and the one or more alignment features **734** define an optical connector **760**, which is shown by way of example as receptacle type of optical connector that complements the plug type of high-density connector **450H** of the fiber ribbon interconnect **400** and that allows for mating and de-mating of the photonic device **710** with the fiber ribbon interconnect to establish optical communication between the optical waveguides of the photonics chip **730** and the fibers **10** of the fiber ribbon interconnect.

Also shown in FIG. 11B is the connector high-density connector **450** having one or more alignment features **458** that are complementary to the one or more alignment features **734** of the photonic device **710**. The example alignment features **458** are shown in the form of alignment pins sized and configured to closely engage the alignment holes **734** when the high-density connector **450** is operably engaged with the photonic device **730**, as shown in FIG. 11C. The photonic device **710** is shown as having additional alignment features **734** that help guide the second connector into position relative to the photonics chip **730**. The optical waveguides **740** have a pitch that matches that of the fibers **10** supported by the connector **450** so that when the high-density connector **450** is operably engaged with the photonic device **730**, the fibers **10** are in optical communication with respective optical waveguides **740**. The optical waveguides **740** have a high waveguide density, i.e., greater than that associated with standard connectors used in standard optical fiber cables.

At the other end of the ribbon interconnect **200**, the standard-density connector **450S** is operably engaged with the connector receptacle **610** of the telecommunications device **600**. The telecommunications device **600** can be a wide variety of standard telecommunication devices known in the art, such as a server, a fiber optic cable, an electronics panel in a data center, etc. The standard-density connector **450S** has the aforementioned standard fiber density associated with industry standard telecommunication systems and devices.

With reference to FIG. 11D, in the example where the telecommunications device **800** is a fiber optic cable **840** terminated by a standard-density connector **450S**, the connector receptacle **810** can be defined by a connector adapter **880** having two connector receptacles and used to operably connect optical fiber cables as is known in the art. Thus, in an example, the ribbon interconnect **400** disclosed herein can be used to optically connect a photonic device **710** having a high waveguide density to a remote telecommunications device **800** having a standard fiber density.

In another example of the optical data transmission system **700** illustrated in FIG. 11E, the ribbon interconnect **400** can be used to establish optical data communication between one photonic device **710** and another photonic device.

FIG. 11F is similar to FIG. 11E and shows an example of an optical data transmission system **700** wherein the fiber ribbon interconnect **500** utilizes a bifurcated fiber ribbon **200** to provide high-density optical interconnections between one photonic device **710** at the first end **402** of the fiber ribbon interconnect **400** and two photonic devices **710** at the second ends **404** of the fiber ribbon interconnect.

Aspect 1 of the description is:

An optical fiber ribbon, comprising:

a plurality of cladding-strengthened glass optical fibers, each of the cladding-strengthened glass optical fibers having an outer surface, the outer surface comprising glass or an inorganic material; and

a common protective coating directly contacting the outer surface of at least two of plurality of cladding-strengthened glass optical fibers.

Aspect 2 of the description is:

The optical fiber ribbon according to Aspect 1, wherein each of the cladding-strengthened glass optical fibers comprises a core, an inner cladding surrounding the core and an outer cladding surrounding the inner cladding, the outer cladding comprising the outer surface, the outer cladding further comprising silica (SiO₂) doped with an amount of titania (TiO₂).

Aspect 3 of the description is:

The optical fiber ribbon according to Aspect 2, wherein the amount of titania is in the range from 5 wt % to 25 wt %.

Aspect 4 of the description is:

The optical fiber ribbon according to Aspect 2 or 3, wherein the outer cladding has a thickness in the range between 2 μm and 20 μm.

Aspect 5 of the description is:

The optical fiber ribbon according to any of Aspects 2-4, wherein the outer cladding has an amount of compressive stress in the range from 30 MPa to 100 MPa.

Aspect 6 of the description is:

The optical fiber ribbon according to any of Aspects 1-5, wherein the outer surface comprises a hermetic sealing layer, the hermetic sealing layer comprising the inorganic material.

Aspect 7 of the description is:

The optical fiber according to Aspect 6, wherein the hermetic sealing layer comprises a self-assembled monolayer (SAM).

Aspect 8 of the description is:

The optical fiber according to Aspect 7, wherein the SAM comprises a silane.

Aspect 9 of the description is:

The optical fiber according to Aspect 6, wherein the hermetic sealing layer comprises a carbon, the carbon having a randomly oriented graphite platelet structure or an amorphous graphite structure.

Aspect 10 of the description is:

The optical fiber according to any of Aspects 6-9, wherein the hermetic sealing layer has a thickness of less than 10 nanometers.

Aspect 11 of the description is:

The optical fiber according to any of Aspects 6-9, wherein the hermetic sealing layer has a thickness in the range from 10 nm-10 microns.

21

Aspect 12 of the description is:
The optical fiber ribbon according to any of Aspects 1-11, wherein each cladding-strengthened glass optical fiber has an outer diameter DF in the range from 60 μm to 250 μm .

Aspect 13 of the description is:
The optical fiber ribbon according to any of Aspects 1-12, further comprising three or more of the cladding-strengthened glass optical fibers arranged in a row.

Aspect 14 of the description is:
The optical fiber ribbon according to Aspect 13, wherein each of the cladding strengthened glass optical fibers has an outer diameter DF, and wherein the three or more cladding-strengthened glass optical fibers are closely arranged to define a fiber pitch substantially equal to the outer diameter.

Aspect 15 of the description is:
The optical fiber ribbon according to any of Aspects 1-14, further comprising two or more rows of two or more of the cladding-strengthened glass optical fibers.

Aspect 16 of the description is:
The optical fiber ribbon according to any of Aspects 1-15, wherein the common protective coating comprises at least two different materials disposed in at least two layers.

Aspect 17 of the description is:
The optical fiber ribbon according to Aspect 16, wherein the at least two layers comprise a primary layer with a first elastic modulus and immediately surrounding the cladding-strengthened optical fibers and a secondary layer with a second elastic modulus immediately surrounding the primary layer, wherein the primary elastic modulus is less than the secondary elastic modulus.

Aspect 18 of the description is:
The optical fiber ribbon according to Aspect 17, wherein the common protective coating has an effective elastic modulus that is larger than the first elastic modulus but less than the second elastic modulus.

Aspect 19 of the description is:
The optical fiber ribbon according to Aspect 18, wherein the effective elastic modulus is in the range from 10 MPa to 1000 MPa.

Aspect 20 of the description is:
The optical fiber ribbon according to any of Aspects 1-19, wherein two or more cladding-strengthened glass optical fibers are disposed within the common protective cladding in a row defined by a reference line, and wherein the common protective coating is asymmetric about the reference line.

Aspect 21 of the description is:
The optical fiber ribbon according to any of Aspects 1-20, wherein the common protective coating comprises a polymer.

Aspect 22 of the description is:
The optical fiber ribbon according to Aspect 21, wherein the polymer is a cured product of a curable coating composition.

Aspect 23 of the description is:
The optical fiber ribbon according to any of Aspects 1-22, wherein the common protective coating comprises a thermoplastic polymer having a melt temperature in the range of 160° C. to 260° C. and a melt viscosity in the range of 100 cP to 10,000 cP.

Aspect 24 of the description is:
The optical fiber ribbon according to any of Aspects 1-23, wherein the common protective coating has a thickness in the range from 10 μm to 100 μm .

22

Aspect 25 of the description is:
The optical fiber ribbon according to any of Aspects 1-24, further comprising a fan-out region.

Aspect 26 of the description is:
5 The optical fiber ribbon according to Aspect 25, further comprising first and second end sections separated by the fan-out region, wherein the first end section has a first fiber pitch $PR_1 \leq 100 \mu\text{m}$ and the second section has a second fiber pitch PR_2 of 250 μm or 125 μm .

Aspect 27 of the description is:
10 The optical fiber ribbon according to Aspect 25, wherein the fan-out region has an S-bend configuration and comprises a transition length LF in the range from 5 mm to 50 mm.

Aspect 28 of the description is:
15 The optical fiber ribbon according to any of Aspects 1-27, further comprising at least one furcation that forms at least first and second furcation sections.

Aspect 29 of the description is:
20 A fiber ribbon cable, comprising:
the optical fiber ribbon according to any of Aspects 1-28;
and
a cover assembly surrounding at least a portion of the optical fiber ribbon.

Aspect 30 of the description is:
25 The fiber ribbon cable according to Aspect 29, wherein the cover assembly comprises a strength layer and an outer jacket surrounding the strength layer.

Aspect 31 of the description is:
30 An optical fiber ribbon, comprising:
a plurality of glass optical fibers surrounded by a common protective coating, each of the glass optical fibers having a centerline, the centerlines of adjacent glass optical fibers being separated by less than 150 microns.

Aspect 32 of the description is:
35 The optical fiber ribbon according to Aspect 31, wherein the centerlines of adjacent glass optical fibers are separated by less than 125 microns.

Aspect 33 of the description is:
40 The optical fiber ribbon according to Aspect 31, wherein the centerlines of adjacent glass optical fibers are separated by less than 100 microns.

Aspect 34 of the description is:
45 The optical fiber ribbon according to Aspect 31, wherein the centerlines of adjacent glass optical fibers are separated by less than 80 microns.

Aspect 35 of the description is:
The optical fiber ribbon according to Aspect 31, wherein the centerlines of adjacent glass optical fibers are separated
50 by less than 60 microns.

Aspect 36 of the description is:
The optical fiber ribbon according to any of Aspects 31-35, wherein the plurality of glass optical fibers comprises a plurality of cladding-strengthened glass optical fibers, the cladding-strengthened optical fibers comprising an outer surface, the outer surface comprising glass or an inorganic material, the common protective coating directly contacting the outer surface of at least two of the plurality of cladding-strengthened glass optical fibers.

Aspect 37 of the description is:
60 The optical fiber ribbon according to Aspect 36, wherein each of the cladding-strengthened glass optical fibers comprises a core, an inner cladding surrounding the core and an outer cladding surrounding the inner cladding, the outer cladding comprising the outer surface, the outer cladding further comprising silica (SiO_2) doped with an amount of titania (TiO_2).

23

Aspect 38 of the description is:
A method of forming a cladding-strengthened glass optical fiber, comprising:

forming a glass preform having a preform core, an inner preform cladding and an outer preform cladding, the outer preform cladding comprising titania-doped silica; and

drawing the glass preform into a cladding-strengthened glass optical fiber, the cladding-strengthened glass optical fiber having an outer cladding, the outer cladding comprising the a titania-doped silica and having a glass outer surface; and

adding a hermetic sealing layer to the glass outer surface.

Aspect 39 of the description is:

The method according to Aspect 38, wherein the hermetic sealing layer comprises a self-assembled monolayer (SAM).

Aspect 40 of the description is:

The method according to Aspect 39, wherein the SAM comprises a silane.

Aspect 41 of the description is:

The method according to Aspect 40, wherein the SAM is added by dispensing a silane liquid onto the glass outer surface.

Aspect 42 of the description is:

The method according to Aspect 41, wherein the silane liquid comprises perfluoropolyether-functionalized silane.

Aspect 43 of the description is:

The method according to Aspect 41, wherein the silane liquid comprises octadecyldimethyl trimethoxysilylpropyl ammonium chloride.

Aspect 44 of the description is:

The method according to any of Aspects 39-43, further comprising functionalizing the glass outer surface using a fluorinated silane.

Aspect 45 of the description is:

The method according to Aspect 38, wherein the hermetic sealing layer comprises carbon having a randomly oriented graphite platelets structure or an amorphous graphite structure.

Aspect 46 of the description is:

The method according to any of Aspects 38-45, wherein the hermetic sealing layer comprises an inorganic material having a thickness of less than 100 nm.

Aspect 47 of the description is:

The method according to any of Aspects 38-46, wherein the titania-doped silica comprises titania in the range from 5 wt % to 25 wt %.

Aspect 48 of the description is:

The method according to any of Aspects 38-47, wherein the outer cladding has a thickness in the range of 2 μm to 20 μm .

Aspect 49 of the description is:

The method according to any of Aspects 38-48, wherein the drawing further comprises:

tensioning the cladding-strengthened glass optical fiber with a tensioner having a tensioner surface;

passing the cladding-strengthened glass optical fiber from the tensioner to a spool through one or more guide wheels each having a surface and winding the cladding-strengthened glass optical fiber around the spool; and

wherein the tensioner surface and the one or more guide wheel surfaces comprise either a plastic material, a polymer material or a rubber material.

24

Aspect 50 of the description is:

The method according to any of Aspects 38-49, further comprising:

arranging a plurality of the cladding-strengthened glass optical fibers in a row;

coating the row of the plurality of the cladding-strengthened glass optical fibers with a common protective coating to define a fiber ribbon, wherein the common protective coating directly contacts the glass outer surface of each of the plurality of cladding-strengthened glass optical fibers.

Aspect 51 of the description is:

The method according to Aspect 50, wherein the coating comprises flowing a thermoelastic polymer over the row of the plurality of the cladding-strengthened glass optical fibers and then cooling the thermoplastic polymer.

Aspect 52 of the description is:

The method according to Aspect 50, wherein the coating comprises applying a curable coating composition to the glass outer surface of each of the plurality of cladding-strengthened glass optical fibers and curing the curable coating composition.

Aspect 53 of the description is:

A method of forming an optical fiber ribbon, comprising:
forming a glass preform having a preform core, an inner preform cladding and an outer preform cladding, the outer preform cladding comprising titania-doped silica;

drawing the glass preform into a cladding-strengthened glass optical fiber, the cladding-strengthened glass optical fiber having an outer cladding, the outer cladding comprising the a titania-doped silica and having a glass outer surface;

arranging a plurality of the cladding-strengthened glass optical fibers in a row; and

coating the row of the plurality of the cladding-strengthened glass optical fibers with a common protective coating, the common protective coating directly contacting the outer surface of at least two of the plurality of cladding-strengthened glass optical fibers.

Aspect 54 of the description is:

The method according to Aspect 53, wherein the common protective coating comprises at least two different materials disposed in at least two layers.

Aspect 55 of the description is:

The method according to Aspect 54, wherein the at least two layers comprise a primary layer with a first elastic modulus and immediately surrounding the cladding-strengthened glass optical fibers and a secondary layer with a second elastic modulus and immediately surrounding the primary layer, wherein the primary elastic modulus is less than the secondary elastic modulus.

Aspect 56 of the description is:

The method according to Aspect 53, wherein the common protective coating is formed by curing a curable coating composition with ultraviolet light.

Aspect 57 of the description is:

The method according to any of Aspects 53-56, further comprising providing a hermetic sealing layer to the glass outer surface of each of the cladding-strengthened glass optical fibers, the hermetic sealing material comprising an inorganic material.

Aspect 58 of the description is:

The method according to Aspect 57, wherein the hermetic sealing layer comprises a self-assembled monolayer (SAM).

Aspect 59 of the description is:

The method according to Aspect 58, wherein the SAM comprises a silane.

25

Aspect 60 of the description is:
The method according to Aspect 58, wherein the SAM is added by dispensing a silane liquid onto the glass outer surface of each of the cladding-strengthened glass optical fibers.

Aspect 61 of the description is:
The method according to Aspect 60, wherein the silane liquid comprises perfluoropolyether-functionalized silane.

Aspect 62 of the description is:
The method according to Aspect 60, wherein the silane liquid comprises octadecyldimethyl trimethoxysilylpropyl ammonium chloride.

Aspect 63 of the description is:
The method according to any of Aspects 58-62, further comprising functionalizing the glass outer surface using a fluorinated silane.

Aspect 64 of the description is:
The method according to Aspect 57, wherein the hermetic sealing layer comprises carbon having a randomly oriented graphite platelets structure or an amorphous graphite structure.

Aspect 65 of the description is:
The method according to any of Aspects 57-64, wherein the hermetic sealing layer has a thickness of less than 100 nm.

It will be apparent to those skilled in the art that various modifications to the preferred embodiments of the disclosure as described herein can be made without departing from the spirit or scope of the disclosure as defined in the appended claims. Thus, the disclosure covers the modifications and variations provided they come within the scope of the appended claims and the equivalents thereto.

What is claimed is:

1. An optical fiber ribbon, comprising:
a plurality of cladding-strengthened glass optical fibers, each of the cladding-strengthened glass optical fibers comprising a core surrounded by a cladding, the cladding comprising silica (SiO₂) doped with an amount of titania (TiO₂), each of the cladding-strengthened glass optical fibers having an outer surface, the outer surface comprising glass or an inorganic material; and
a common protective coating directly contacting the outer surface of at least two of the plurality of cladding-strengthened glass optical fibers, the common protective coating surrounding the at least two of the plurality of cladding-strengthened glass optical fibers.
2. The optical fiber ribbon according to claim 1, wherein the cladding comprises an inner cladding surrounding the core and an outer cladding surrounding the inner cladding, the outer cladding comprising the outer surface, the outer cladding further comprising the silica (SiO₂) doped with an amount of titania (TiO₂).
3. The optical fiber ribbon according to claim 2, wherein the amount of titania is in the range from 5 wt % to 25 wt %.
4. The optical fiber ribbon according to claim 2, wherein the outer cladding has a thickness in the range between 2 μm and 20 μm.
5. The optical fiber ribbon according to claim 1, wherein the outer surface comprises a hermetic sealing layer, the hermetic sealing layer comprising the inorganic material.
6. The optical fiber according to claim 5, wherein the hermetic sealing layer comprises a self-assembled monolayer (SAM), the self-assembled monolayer (SAM) comprising a silane.
7. The optical fiber according to claim 5, wherein the hermetic sealing layer comprises a carbon, the carbon hav-

26

ing a randomly oriented graphite platelet structure or an amorphous graphite structure.

8. The optical fiber according to claim 5, wherein the hermetic sealing layer has a thickness of less than 10 nanometers.

9. The optical fiber according to claim 5, wherein the hermetic sealing layer has a thickness in the range from 10 nm-10 microns.

10. The optical fiber ribbon according to claim 1, wherein each cladding-strengthened glass optical fiber has an outer diameter DF in the range from 60 μm to 250 μm.

11. The optical fiber ribbon according to claim 1, wherein the common protective coating comprises at least two different materials disposed in at least two layers.

12. The optical fiber ribbon according to claim 1, wherein the common protective coating comprises a polymer, the polymer being a cured product of a curable coating composition.

13. The optical fiber ribbon according to claim 1, wherein the common protective coating comprises a thermoplastic polymer having a melt temperature in the range of 160° C. to 260° C. and a melt viscosity in the range of 100 cP to 10,000 cP.

14. A fiber ribbon cable, comprising:

the optical fiber ribbon according to claim 1; and
a cover assembly surrounding at least a portion of the optical fiber ribbon.

15. An optical fiber ribbon, comprising:

a plurality of cladding-strengthened glass optical fibers, each of the cladding-strengthened glass optical fibers comprising a core surrounded by a cladding, the cladding comprising silica (SiO₂) doped with an amount of titania (TiO₂), each of the cladding-strengthened glass optical fibers having a glass outer surface and a centerline, the outer surface comprising glass or an inorganic material, the centerlines of adjacent cladding-strengthened glass optical fibers being separated by less than 150 microns; and

the plurality of cladding-strengthened glass optical fibers residing within a common protective coating that contacts each of the glass outer surface of at least two of the plurality of cladding-strengthened glass optical fibers, the common protective coating surrounding the at least two of the plurality of cladding-strengthened glass optical fibers.

16. The optical fiber ribbon according to claim 15, wherein the centerlines of adjacent glass optical fibers are separated by less than 80 microns.

17. The optical fiber ribbon according to claim 15,

wherein the cladding comprises an inner cladding surrounding the core and an outer cladding surrounding the inner cladding, the outer cladding comprising the outer surface, the outer cladding further comprising the silica (SiO₂) doped with an amount of titania (TiO₂).

18. The optical fiber ribbon according to claim 1, wherein the common protective coating surrounds each of the at least two cladding-strengthened glass optical fibers.

19. The optical fiber ribbon according to claim 15, wherein the common protective coating surrounds each of the at least two cladding-strengthened glass optical fibers.

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION


PATENT NO. : 11,243,348 B2
APPLICATION NO. : 16/685065
DATED : February 8, 2022
INVENTOR(S) : Philip Simon Brown et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

In the Claims

In Column 26, Line 45, in Claim 15, delete "surface" and insert -- surfaces --.

Signed and Sealed this
Twenty-fourth Day of May, 2022

Katherine Kelly Vidal
Director of the United States Patent and Trademark Office