



(12) **United States Patent**
Lin et al.

(10) **Patent No.: US 11,264,292 B2**
(45) **Date of Patent: Mar. 1, 2022**

(54) **CELL-LIKE FLOATING-GATE TEST STRUCTURE**

(71) Applicant: **Taiwan Semiconductor Manufacturing Co., Ltd.**, Hsin-Chu (TW)

(72) Inventors: **Meng-Han Lin**, Hsinchu (TW);
Chih-Ren Hsieh, Changhua (TW);
Ya-Chen Kao, Fuxing Township (TW);
Chen-Chin Liu, Hsinchu (TW);
Chih-Pin Huang, Hsinchu (TW)

(73) Assignee: **Taiwan Semiconductor Manufacturing Company, Ltd.**, Hsinchu (TW)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **16/682,210**

(22) Filed: **Nov. 13, 2019**

(65) **Prior Publication Data**
US 2020/0083126 A1 Mar. 12, 2020

Related U.S. Application Data

(63) Continuation of application No. 15/962,177, filed on Apr. 25, 2018, now Pat. No. 10,535,574.
(Continued)

(51) **Int. Cl.**
H01L 27/11529 (2017.01)
H01L 27/11524 (2017.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 22/34** (2013.01); **H01L 27/11524** (2013.01); **H01L 27/11526** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 22/34; H01L 27/11526; H01L 29/42328; H01L 27/11529;
(Continued)

(56) **References Cited**
U.S. PATENT DOCUMENTS
5,864,501 A 1/1999 Lee
10,026,742 B2 7/2018 Kim et al.
(Continued)
FOREIGN PATENT DOCUMENTS


TW	200516727 A	5/2005
TW	200843040 A	11/2008

OTHER PUBLICATIONS
Ex Parte Quayle Office Action dated Aug. 16, 2019 in connection with U.S. Appl. No. 15/962,177.
(Continued)

Primary Examiner — Hoang-Quan Ho
(74) *Attorney, Agent, or Firm* — Eschweiler & Potashnik, LLC

(57) **ABSTRACT**
Various embodiments of the present application are directed to an integrated circuit (IC) comprising a floating gate test device with a cell-like top layout, as well as a method for forming the IC. In some embodiments, the IC comprises a semiconductor substrate and the floating gate test device. The floating gate test device is on the semiconductor substrate, and comprises a floating gate electrode and a control gate electrode overlying the floating gate electrode. The floating gate electrode and the control gate electrode partially define an array of islands, and further partially define a plurality of bridges interconnecting the islands. The islands and the bridges define the cell-like top layout and may, for example, prevent process-induced damage to the floating gate test device.

20 Claims, 40 Drawing Sheets



Related U.S. Application Data

- (60) Provisional application No. 62/560,967, filed on Sep. 20, 2017.
- (51) **Int. Cl.**
H01L 27/11526 (2017.01)
H01L 29/423 (2006.01)
H01L 27/11519 (2017.01)
H01L 21/66 (2006.01)
- (52) **U.S. Cl.**
CPC .. *H01L 27/11529* (2013.01); *H01L 29/42328* (2013.01); *H01L 27/11519* (2013.01)
- (58) **Field of Classification Search**
CPC H01L 27/11524; H01L 27/11519; H01L 22/32; H01L 27/11521; H01L 27/0207; H01L 21/76838; H01L 21/76829; H01L

29/42324; H01L 29/66825; H01L 29/7841; H01L 22/30

See application file for complete search history.

(56)

References Cited

U.S. PATENT DOCUMENTS

2006/0079052	A1	4/2006	Kanamori
2007/0026612	A1	2/2007	Lee
2009/0184364	A1	7/2009	Terada
2009/0283764	A1	11/2009	Kim et al.
2017/0110201	A1*	4/2017	Lien H01L 21/76877
2017/0110202	A1*	4/2017	Wu H01L 21/76877

OTHER PUBLICATIONS

Notice of Allowance dated Oct. 8, 2019 in connection with U.S. Appl. No. 15/962,177.

* cited by examiner




Fig. 1A




Fig. 1B




Fig. 2A




Fig. 2B




Fig. 2C




Fig. 2D




Fig. 2E




Fig. 2F




Fig. 3A




Fig. 3B




Fig. 3C




Fig. 3D




Fig. 3E




Fig. 3F




Fig. 3G




Fig. 3H




Fig. 4A




Fig. 4B




Fig. 4C




Fig. 4D




Fig. 5A




Fig. 5B




Fig. 6A




Fig. 6B




Fig. 7A




Fig. 7B




Fig. 8A




Fig. 8B




Fig. 9A




Fig. 9B




Fig. 10A




Fig. 10B




Fig. 11A




Fig. 11B




Fig. 12A




Fig. 12B




Fig. 13A




Fig. 13B




Fig. 14A




Fig. 14B




Fig. 15A




Fig. 15B




Fig. 16A




Fig. 16B




Fig. 17A




Fig. 17B




Fig. 18A




Fig. 18B




Fig. 19A




Fig. 19B




Fig. 20A




Fig. 20B




Fig. 21A




Fig. 21B




Fig. 22A




Fig. 22B




Fig. 23A




Fig. 23B




Fig. 24A




Fig. 24B




Fig. 25A




Fig. 25B




Fig. 26A




Fig. 26B




Fig. 27A





Fig. 27B

**Fig. 28**




Fig. 29A




Fig. 29B




Fig. 30A




Fig. 30B




Fig. 31A




Fig. 31B




Fig. 32A




Fig. 32B




Fig. 33A




Fig. 33B




Fig. 34A




Fig. 34B




Fig. 35A




Fig. 35B




Fig. 36A




Fig. 36B




Fig. 37A




Fig. 37B




Fig. 38A




Fig. 38B




Fig. 39A




Fig. 39B




Fig. 40A




Fig. 40B




Fig. 41A




Fig. 41B

CELL-LIKE FLOATING-GATE TEST STRUCTURE

REFERENCE TO RELATED APPLICATIONS

This Application is a Continuation of U.S. application Ser. No. 15/962,177, filed on Apr. 25, 2018, which claims the benefit of U.S. Provisional Application No. 62/560,967, filed on Sep. 20, 2017. The contents of the above-referenced Patent Applications are hereby incorporated by reference in their entirety.

BACKGROUND

The integrated circuit (IC) manufacturing industry has experienced exponential growth over the last few decades. As ICs have evolved, functional density (i.e., the number of interconnected devices per chip area) has generally increased while geometry size (i.e., the smallest component that can be created) has decreased. Some advancements in the evolution of ICs include embedded memory technology. Embedded memory technology is the integration of memory devices with logic devices on the same semiconductor chip, such that the memory devices support operation of the logic devices. Embedded memory finds application in, among other things, smart cards and automotive devices.

BRIEF DESCRIPTION OF THE DRAWINGS

Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

FIGS. 1A and 1B illustrate top layout views of various embodiments of an integrated circuit (IC) comprising a floating gate test device with a cell-like top layout.

FIGS. 2A-2F illustrate various top layout views of some more detailed embodiments of the IC of FIG. 1A in which the IC comprises a memory cell array.

FIGS. 3A-3H illustrate various top layout views of some more detailed embodiments of the IC of FIG. 1B in which the IC comprises a memory cell array.

FIGS. 4A-4D illustrate various cross-sectional views of some embodiments of the IC of FIGS. 2A and 2B and/or the IC of FIGS. 3A and 3B.

FIGS. 5A and 5B through FIGS. 27A and 27B illustrate a series of cross-sectional views of some embodiments a method for forming an IC comprising a floating gate test device with a cell-like top layout.

FIG. 28 illustrates a flowchart of some embodiments of the method of FIGS. 5A and 5B through FIGS. 27A and 27B.

FIGS. 29A and 29B through FIGS. 41A and 41B illustrate a series of cross-sectional views of some alternative embodiments of the method of FIGS. 5A and 5B through FIGS. 27A and 27B in which the method has a gate replacement process.

DETAILED DESCRIPTION

The present disclosure provides many different embodiments, or examples, for implementing different features of this disclosure. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are

not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper,” and the like, may be used herein for ease of description to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device or apparatus in use or operation in addition to the orientation depicted in the figures. The device or apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly. Even more, the terms “first,” “second,” “third,” “fourth,” and the like are merely generic identifiers and, as such, may be interchanged in various embodiments. For example, while an element (e.g., an opening) may be referred to as a “first” element in some embodiments, the element may be referred to as a “second” element in other embodiments.

According to a method for manufacturing an integrated circuit (IC) with embedded memory technology, a memory cell structure and a floating gate test device structure are formed on a semiconductor memory region of a semiconductor substrate. The floating gate test device structure comprises a floating gate dielectric layer and a floating gate electrode overlying the floating gate dielectric layer. The floating gate test device may, for example, be employed to test the quality of the floating gate dielectric layer since the quality of the floating gate dielectric layer is representative of the life span of the memory cell structure. A hard mask layer is formed covering the semiconductor substrate, and a planarization is performed into a top surface of the hard mask layer to flatten the top surface. The hard mask layer is patterned to remove the hard mask layer from a semiconductor logic region of the semiconductor substrate, and to define a memory hard mask covering the memory cell structure and the floating gate test device structure, but not the semiconductor logic region. Residual material remaining from formation of the memory cell structure and the floating gate test device structure is removed from the semiconductor logic region with the memory hard mask in place. Logic device layers are then deposited and patterned on the of the semiconductor logic region to form a logic device structure on the of the semiconductor logic region.

A challenge with the method is a height of the memory cell structure and a height of the floating gate test device structure exceed a height of the logic device structure, thereby precluding application of the method in future process nodes. A solution is to reduce the heights respectively of the floating gate test device structure and memory cell structure before forming the memory hard mask. An etch-back layer is deposited covering the memory cell structure and the floating gate test device structure, and a non-selective etch back is subsequently performed to reduce the heights respectively of the memory cell structure and the floating gate test device structure. The non-selective etch back etches the etch-back layer, the memory cell structure,

and the floating gate test device structure until the heights respectively of the memory cell structure and the floating gate test device structure are sufficiently reduced.

While the non-selective etch back is effective at reducing the height of the memory cell structure, the non-selective etch back is ineffective at reducing the height of the floating gate test device structure. The floating gate test device structure has a bulk floating gate top layout covering a large area of the semiconductor substrate compared to a bulk floating gate top layout of the memory cell structure. A bulk top layout may, for example, be a top layout that has a single area, instead of multiple smaller areas, and that has a single boundary extending in a closed path. The bulk floating gate top layouts respectively propagate to a top of the floating gate test device structure and a top of the memory cell structure, such that the floating gate test device structure has a bulk, large-area top layout and the top of the memory cell structure has a bulk, small-area top layout. The difference in area between the bulk, large-area top layout and the bulk, small-area top layout causes etch-back material of the etch-back layer to more readily accumulate on the floating gate test device structure than on the memory cell structure during deposition of the etch-back layer, whereby the etch-back layer is thicker on the floating gate test device structure than on the memory cell structure. Because there is more etch-back material to etch through on the floating gate test device structure, the floating gate test device structure is minimally etched during the non-selective etch back compared to the memory cell structure. Further, a height of the floating gate test device structure exceeds that of the memory cell structure upon completion of the non-selective etch back.

Because the height of the floating gate test device structure exceeds that of the memory cell structure, and the top surface of the memory hard mask is flat or substantially flat, a first thickness of the memory hard mask on the floating gate test device structure is less than a second thickness of the memory hard mask on the memory cell structure. As a result, the floating gate test device structure has less protection and may be destroyed or severely damaged while forming the logic device structure. For example, removing the residual material on the semiconductor logic region may partially remove the memory hard mask. Due to the reduced thickness of the memory hard mask on the floating gate test device structure, the removal may also uncover the floating gate test device structure, but not the memory cell structure, and form an opening extending through the floating gate test device structure. The opening may extend to the floating gate electrode and the semiconductor memory region, and facilitate electrical shorting between the semiconductor memory region and the floating gate electrode during subsequent back-end-of-line (BEOL) processing.

In view of the foregoing, various embodiments of the present application provide a method for forming an IC comprising a floating gate test device structure with a cell-like top layout. In some embodiments, a floating gate test device structure is formed on a semiconductor substrate. The floating gate test device structure comprises a first floating gate electrode and a first control gate electrode overlying the first floating gate electrode. The first floating gate electrode and the first control gate electrode partially define an array of islands, and further partially define a plurality of bridges. The bridges interconnect the islands. A memory cell structure is formed on the semiconductor substrate, and comprises a second floating gate electrode and a second control gate electrode overlying the second floating gate electrode. An etch-back layer is formed covering the

floating gate test device structure and the memory cell structure. The etch-back layer has a first thickness directly over the first control gate electrode, and further has a second thickness directly over the second control gate electrode. The first and second thicknesses are the same or substantially the same.

By forming the first floating gate electrode comprising the islands and the bridges, the floating gate electrode has a cell-like top layout. The cell-like top layout is a top layout having multiple small areas that are interconnected, instead of one large area, and is similar to a top layout of an array of memory cells. The cell-like top layout may prevent etch-back material of the etch-back layer from more readily accumulating atop the floating gate test device structure compared to the memory cell structure. This may, in turn, prevent the floating gate test device structure from being destroyed or damaged while forming a logic device structure, and/or may prevent electrical shorting between the semiconductor substrate and the first floating gate electrode during BEOL processing. The method may be performed at low cost, without extra reticles or photomasks, and without effecting the reliability and performance of the floating gate test device structure. Further, the method may be compatible with future process nodes, such as, for example, 28 nanometer process nodes, 20 nanometer process nodes, 16 nanometer process nodes, and smaller process nodes.

With reference to FIG. 1A, a top layout view **100A** of some embodiments of an IC comprising a floating gate test device **102** with a cell-like top layout is provided. The floating gate test device **102** is on a semiconductor memory region **104m** and comprises a gate stack **106**. As seen hereafter, the gate stack **106** is defined by multiple gate electrodes (e.g., a floating gate electrode and a control gate electrode) stacked along an axis extending into and out of the page. The gate stack **106** comprises a plurality of islands **106i** and a plurality of bridges **106b**. For illustrative purposes, the hashing is varied between the islands **106i** and the bridges **106b**. However, it is to be understood that the islands **106i** may be integrated and/or continuous with the bridges **106b**.

The islands **106i** are arranged in one or more rows and one or more columns to define an island array. In some embodiments, the islands **106i** are arranged in a single row and multiple columns, or multiple rows and a single column. For example, the islands **106i** may be arranged in three columns and one row. Further, in some embodiments, the islands **106i** share a common top layout. For example, the islands **106i** may have a rectangular top layout, a square top layout, a triangular top layout, or some other suitable top layout(s). As used herein, a term (e.g., top layout) with a suffix of "(s)" may, for example, be singular or plural. The bridges **106b** are arranged between the islands **106i** to interconnect the islands **106i**, and each of the bridges **106b** extends from direct contact with a corresponding first island of the islands **106i** to a corresponding second island of the islands **106i** that neighbors the corresponding first island. In some embodiments, the bridges **106b** comprise a bridge for each pair of neighboring islands in the island array, and the bridge extends from direct contact with a first island of the pair to a second island of the pair. Further, in some embodiments, the bridges **106b** share a common top layout, and/or the common top layout of the bridges **106b** is smaller than the common top layout of the islands **106i**. For example, the bridges **106b** may have a rectangular top layout, a square top layout, a triangular top layout, or some other suitable top layout(s). The common top layout of the bridges **106b** may,

5

for example, be smaller than the common top layout of the islands **106i** in terms of area, width, length, or some other suitable parameter(s).

In some embodiments, a plurality of test-device select gate electrodes **108** border the gate stack **106**. The test-device select gate electrodes **108** may be or comprise, for example, metal, doped polysilicon, or some other suitable conductor(s). In some embodiments, the test-device select gate electrodes **108** comprise a plurality of recessed select gate electrodes **108r** arranged completely or substantially completely within recesses defined by the gate stack **106**. For ease of illustration, only some of the recessed select gate electrodes **108r** are labeled **108r**. The recessed select gate electrodes **108r** may, for example, have a u-shaped top layout or some other suitable top layout(s). Further, in some embodiments, the test-device select gate electrodes **108** comprise a plurality of peripheral select gate electrodes **108p** arranged to the sides of the gate stack **106**, and arranged completely or substantially completely outside recesses defined by the gate stack **106**. For ease of illustration, only one of the peripheral select gate electrodes **108p** is labeled **108p**. The peripheral select gate electrodes **108p** may, for example, have a line-shaped top layout or some other suitable top layout(s).

By forming the floating gate test device **102** comprising the islands **106i** and the bridges **106b**, the floating gate test device **102** has a cell-like top layout made up of multiple small areas that are interconnected instead of one large area. As seen hereafter, this may prevent the floating gate test device **102** from becoming destroyed or damaged while forming a logic device of the IC, and/or may prevent electrical shorting between the semiconductor memory region **104m** and a floating gate electrode (not shown) of the gate stack **106**. Further, as seen hereafter, the floating gate test device **102** may be formed with the cell-like top layout at low cost, without extra reticles or photomasks, and without effecting the reliability and performance of the floating gate test device **102**. Further yet, as seen hereafter, the floating gate test device **102** is compatible with future process nodes, such as, for example, 28 nanometer process nodes, 20 nanometer process nodes, 16 nanometer process nodes, and smaller process nodes.

With reference to FIG. 1B, a top layout view **100B** of some other embodiments of an IC comprising a floating gate test device **102** with a cell-like top layout is provided. FIG. 1B is a variant of FIG. 1A in which the islands **106i** are arranged in a plurality of rows and a plurality of columns. For example, the islands **106i** may be arranged in three rows and three columns. Further, in some embodiments, the test-device select gate electrodes **108** comprise one or more enclosed select gate electrodes **108e** completely enclosed by the gate stack **106**. For ease of illustration, only some of the enclosed select gate electrodes **108e** are labeled **108e**. The enclosed select gate electrodes **108e** may, for example, have a ring-shaped-like top layout or some other suitable top layout(s). As used herein, a ring-shaped-like top layout is a ring-shaped top layout that is not limited to circular boundaries or sidewalls.

With reference to FIG. 2A, a top layout view **200A** of some more detailed embodiments of the IC of FIG. 1A is provided. The floating gate test device **102** comprises a test-device control gate electrode **202** partially defining the gate stack **106**. The test-device control gate electrode **202** may be or comprise, for example, metal, doped polysilicon, some other suitable conductor(s), or any combination of the foregoing. Further, the test-device control gate electrode **202** includes a plurality of control gate islands **202i** and a

6

plurality of control gate bridges **202b**. For illustrative purposes, the hashing is varied between the control gate islands **202i** and the control gate bridges **202b**. However, it is to be understood that the control gate islands **202i** may be integrated and/or continuous with the control gate bridges **202b**.

The control gate islands **202i** partially define the islands **106i** of the gate stack **106**, respectively, and are arranged in one or more rows and one or more columns to define a control gate island array. In some embodiments, the control gate island array has a single row and multiple columns, or multiple rows and a single column. Further, in some embodiments, the control gate islands **202i** share a common top layout. For example, the control gate islands **202i** may share a rectangular top layout, a square top layout, or some other suitable top layout(s). The control gate bridges **202b** partially define the bridges **106b** of the gate stack **106**, respectively, and are arranged between the control gate islands **202i** to interconnect the control gate islands **202i**. Further, the control gate bridges **202b** comprise a control gate bridge for each pair of neighboring control gate islands in the control gate island array, and the control gate bridge extends from direct contact with a first island of the pair to a second island of the pair. In some embodiments, the control gate bridges **202b** share a common top layout. For example, the control gate bridges **202b** may share a rectangular top layout or some other suitable top layout(s).

In some embodiments, the floating gate test device **102** borders a memory cell array **204**. Further, in some embodiments, the memory cell array **204** rests on the semiconductor memory region **104m**, and/or the semiconductor memory region **104m** is continuous from the floating gate test device **102** to the memory cell array **204**. The memory cell array **204** comprises a plurality of memory cells **204c** arranged in a plurality of rows and a plurality of columns. For ease of illustration, only some of the memory cells **204c** are labeled **204c**. The memory cells **204c** comprise a plurality of memory control gate electrodes **208**, a plurality of memory select gate electrodes **210**, and a plurality of memory erase gate electrodes **212**. For ease of illustration, only some of the memory control gate electrodes **208** are labeled **208**, only some of the memory select gate electrodes **210** are labeled **210**, and only some of the memory erase gate electrodes **212** are labeled **212**. The memory control gate electrodes **208**, the memory select gate electrodes **210**, and the memory erase gate electrodes **212** may be or comprise, for example, metal, doped polysilicon, or some other suitable conductor(s).

Each of the memory cells **204c** includes a corresponding control gate electrode of the memory control gate electrodes **208**, a corresponding select gate electrode of the memory select gate electrodes **210**, and a corresponding erase gate electrode of the memory erase gate electrodes **212**. The corresponding select gate electrode borders a first sidewall of the corresponding control gate electrode. The corresponding erase gate electrode borders a second sidewall of the corresponding control gate electrode that is opposite the first sidewall. Further, in some embodiments, the memory cells **204c** are grouped into pairs, and the memory cells of each pair share the corresponding erase gate electrode.

In some embodiments, a plurality of inter-device lines **214** are electrically coupled to the memory cell array **204**. For ease of illustration, only some of the inter-device lines **214** are labeled **214**. The inter-device lines **214** are elongated in a common direction, and are each elongated in the common direction along a corresponding row or column of the memory cell array **204**. In some embodiments, the inter-device lines **214** have line-shaped top layouts or some other

suitable top layout(s) that is/are elongated. The inter-device lines **214** are conductive and may be or comprise, for example, metal, doped polysilicon, or some other suitable conductor(s). The inter-device lines **214** comprise a plurality of select gate inter-device lines **214s**, a plurality of erase gate inter-device lines **214e**, and a plurality of control gate inter-device lines **214c**. For ease of illustration, only one of the select gate inter-device lines **214s** is labeled **214s**, only one of the erase gate inter-device lines **214e** is labeled **214e**, and only one of the control gate inter-device lines **214c** is labeled **214c**.

The select gate inter-device lines **214s** are each integrated and continuous with select gate electrodes of the memory select gate electrodes **210** in the corresponding row or column of the memory cell array **204**. The erase gate inter-device lines **214e** are each integrated and continuous with erase gate electrodes of the memory erase gate electrodes **212** in the corresponding row or column of the memory cell array **204**. The control gate inter-device lines **214c** are each integrated and continuous with control gate electrodes of the memory control gate electrodes **208** in the corresponding row or column of the memory cell array **204**. Further, in some embodiments, at least one of the control gate inter-device lines **214c** extends beyond the memory cell array **204** to the floating gate test device **102**, and is integrated and continuous with the test-device control gate electrode **202**.

Note that the hashing is varied along the select gate inter-device lines **214s** merely to emphasize the memory select gate electrodes **210**. Further, the hashing is varied along the erase gate inter-device lines **214e** merely to emphasize the memory erase gate electrodes **212**. Further, the hashing is varied along the control gate inter-device lines **214c** merely to emphasize the memory control gate electrodes **208**. Therefore, the varied hashing should not be construed as limiting the composition of the select gate inter-device lines **214s**, the memory select gate electrodes **210**, the erase gate inter-device lines **214e**, the memory erase gate electrodes **212**, the control gate inter-device lines **214c**, and the memory control gate electrodes **208**.

With reference to FIG. 2B, another top layout view **200B** of some more detailed embodiments of the IC of FIG. 1A is provided. Whereas the top layout view **200A** of FIG. 2A illustrates a control gate layout of the IC, the top layout view **200B** of FIG. 2B illustrates a floating gate layout of the IC. As will be better seen hereafter, the control gate layout overlies the floating gate layout along an axis extending into and out of the page.

The floating gate test device **102** comprises a test-device floating gate electrode **216** partially defining the gate stack **106**. The test-device floating gate electrode **216** may be or comprise, for example, metal, doped polysilicon, some other suitable conductor(s), or any combination of the foregoing. Further, the test-device floating gate electrode **216** includes a plurality of floating gate islands **216i** and a plurality of floating gate bridges **216b**. For illustrative purposes, the hashing is varied between the floating gate islands **216i** and the floating gate bridges **216b**. However, it is to be understood that the floating gate islands **216i** may be continuous and/or integrated with the floating gate bridges **216b**.

The floating gate islands **216i** partially define the islands **106i** of the gate stack **106**, respectively, and are arranged in one or more rows and one or more columns to define a floating gate island array. In some embodiments, the floating gate island array has a single row and multiple columns, or multiple rows and a single column. Further, in some embodiments, the floating gate islands **216i** share a common top

layout. For example, the floating gate islands **216i** may share a rectangular top layout, a square top layout, or some other suitable top layout(s). The floating gate bridges **216b** partially define the bridges **106b** of the gate stack **106**, respectively, and are arranged between the floating gate islands **216i** to interconnect the floating gate islands **216i**. Further, the floating gate bridges **216b** comprise a floating gate bridge for each pair of neighboring floating gate islands in the floating gate island array, and the floating gate bridge extends from direct contact with a first island of the pair to a second island of the pair. In some embodiments, the floating gate bridges **216b** share a common top layout. For example, the floating gate bridges **216b** may share a rectangular top layout or some other suitable top layout(s). The floating gate bridges **216b** have a floating-gate-bridge width W_{fb} . In some embodiments, each of the floating gate bridges **216b** individually has the floating-gate-bridge width W_{fb} .

The memory cells **204c** comprise the plurality of memory select gate electrodes **210** and the plurality of memory erase gate electrodes **212**, and further comprise a plurality of memory floating gate electrodes **218**. For ease of illustration, only some of the memory cells **204c** are labeled **204**, only some of the memory floating gate electrodes **218** are labeled **218**, only some of the memory select gate electrodes **210** are labeled **210**, and only some of the memory erase gate electrodes **212** are labeled **212**. Each of the memory cells **204c** includes a corresponding floating gate electrode of the memory floating gate electrodes **218**, a corresponding select gate electrode of the memory select gate electrodes **210**, and a corresponding erase gate electrode of the memory erase gate electrodes **212**. The corresponding select gate electrode borders a first sidewall of the corresponding floating gate electrode. The corresponding erase gate electrode borders a second sidewall of the corresponding floating gate electrode that is opposite the first sidewall. The memory erase gate electrodes **212** have an erase-gate width W_{eg} . In some embodiments, each of the erase gate electrodes **212** individually has the erase-gate width W_{eg} . In some embodiments, the floating-gate-bridge width W_{fb} is greater than or equal to the erase-gate width W_{eg} .

With reference to FIGS. 2C and 2D, top layout views **200C**, **200D** of some alternative embodiments respectively of the top layout views **200A**, **200B** of FIGS. 2A and 2B are provided in which the control gate islands **202i** and the floating gate islands **216i** are square shaped (e.g., all four sides are the same length or approximately the same length). Other shapes and/or sizes are, however, amenable in other embodiments.

With reference to FIGS. 2E and 2F, top layout views **200E**, **200F** of some alternative embodiments respectively of the top layout views **200A**, **200B** of FIGS. 2A and 2B are provided in which an additional island **106i** and an additional bridge **106b** have been added to a single side of the gate stack **106**. In other embodiments, more islands and more bridges may be added to the single side of the gate stack **106** and/or to other sides of the gate stack **106**.

With reference to FIGS. 3A and 3B, various top layout views **300A**, **300B** of some more detailed embodiments of the IC of FIG. 1B is provided. The top layout views **300A**, **300B** of FIGS. 3A and 3B are variants respectively of FIGS. 2A and 2B in which the floating gate test device **102** employs the cell-like top layout of FIG. 1B. FIG. 3A illustrates a control gate layout of the IC, and FIG. 3B illustrates floating gate layout of the IC. The floating gate bridges **216b** have a floating-gate-bridge width W_{fb} (see FIG. 3B) and the memory erase gate electrodes **212** have an erase-gate width W_{eg} . In some embodiments, each of the

floating gate bridges **216b** individually has the floating-gate-bridge width W_{fb} , and/or each of the erase gate electrodes **212** individually has the erase-gate width W_{eg} . In some embodiments, the floating-gate-bridge width W_{fb} is greater than or equal to the erase-gate width W_{eg} .

With reference to FIGS. 3C and 3D, top layout views **300C**, **300D** of some alternative embodiments respectively of the top layout views **300A**, **300B** of FIGS. 3A and 3B are provided in which the control gate islands **202i** and the floating gate islands **216i** are square shaped (e.g., all four sides are the same length or approximately the same length). Other shapes and/or sizes are, however, amenable in other embodiments.

With reference to FIGS. 3E and 3F, top layout views **300E**, **300F** of some alternative embodiments respectively of the top layout views **300A**, **300B** of FIGS. 3A and 3B are provided in which there is one less row of islands **106i**. In other embodiments, there may be more or less rows of islands **106i** and/or more or less columns of islands **106i**.

With reference to FIGS. 3G and 3H, top layout views **300G**, **300H** of some alternative embodiments respectively of the top layout views **300A**, **300B** of FIGS. 3A and 3B are provided in which an additional island **106i** and an additional bridge **106b** have been added to a single side of the gate stack **106**. In other embodiments, more islands and more bridges may be added to the single side of the gate stack **106** and/or to other sides of the gate stack **106**.

With reference to FIG. 4A, a cross-sectional view **400A** of some embodiments of the IC of FIGS. 2A and 2B and/or the IC of FIGS. 3A and 3B is provided. The cross-sectional view **400A** may, for example, be taken along line A-A' in FIGS. 2A and 2B and/or along line A-A' in FIGS. 3A and 3B. Additionally, the cross-sectional view **400A** may, for example, be taken along line A-A' in FIG. 1A and/or FIG. 1B.

As illustrated, a semiconductor substrate **402** includes the semiconductor memory region **104m**, and an isolation structure **404** extends into a top surface of the semiconductor substrate **402** to demarcate a boundary of the semiconductor memory region **104m**. The semiconductor substrate **402** may be or comprise, for example, a bulk silicon substrate, a silicon-on-insulator (SOI) substrate, or some other suitable semiconductor substrate(s). The isolation structure **404** electrically isolates the semiconductor memory region **104m** from adjoining regions of the semiconductor substrate and may, for example, include a trench filled with dielectric material. In some embodiments, the isolation structure **404** is a shallow trench isolation (STI) region, a deep trench isolation (DTI) region, or some other suitable isolation structure(s).

The floating gate test device **102** overlies the semiconductor memory region **104m** and comprises the gate stack **106**. The gate stack **106** has a cell-like top layout and includes the plurality of islands **106i**. Examples of the cell-like top layout are shown in, for example, FIGS. 1A and 1B. While the islands **106i** are shown as being unconnected, the islands **106i** may, for example, be connected out of the cross-sectional view **400A** of FIG. 4A. The gate stack **106** is defined by a test-device floating gate dielectric layer **406**, the test-device floating gate electrode **216**, a test-device control gate dielectric layer **408**, the test-device control gate electrode **202**, and a test-device control gate hard mask **410** stacked upon one another.

The test-device floating gate electrode **216** overlies the test-device floating gate dielectric layer **406**, the test-device control gate dielectric layer **408** overlies the test-device floating gate electrode **216**, the test-device control gate

electrode **202** overlies the test-device control gate dielectric layer **408**, and the test-device control gate hard mask **410** overlies the test-device control gate electrode **202**. The test-device floating gate electrode **216** and the test-device control gate electrode **202** may be or comprise, for example, metal, doped polysilicon, or some other suitable conductive material(s). The test-device floating gate dielectric layer **406**, the test-device control gate dielectric layer **408**, and the test-device control gate hard mask **410** may be or comprise, for example, silicon oxide, silicon nitride, some other suitable dielectric(s), or any combination of the foregoing. Further, the test-device floating gate dielectric layer **406**, the test-device floating gate electrode **216**, the test-device control gate dielectric layer **408**, the test-device control gate electrode **202**, and the test-device control gate hard mask **410** have cell-like top layouts. In some embodiments, the test-device floating gate dielectric layer **406** and the test-device floating gate electrode **216** have the same or substantially the same cell-like top layout. Examples of this cell-like top layout are shown in, for example, FIGS. 2B and 3B with respect to the test-device floating gate electrode **216**. In some embodiments, the test-device control gate dielectric layer **408**, the test-device control gate electrode **202**, and the test-device control gate hard mask **410** have the same or substantially the same cell-like top layout. Examples of this cell-like top layout are shown in, for example, FIGS. 2A and 3A with respect to the test-device control gate electrode **202**.

While the test-device floating gate dielectric layer **406**, the test-device floating gate electrode **216**, the test-device control gate dielectric layer **408**, the test-device control gate electrode **202**, and the test-device control gate hard mask **410** are each shown as having multiple segments corresponding to the islands **106i**, the segments may, for example, be connected out of the cross-sectional view **400A** of FIG. 4A. Further, for ease of illustration, only one segment has been labeled for each of the test-device floating gate dielectric layer **406**, the test-device floating gate electrode **216**, the test-device control gate dielectric layer **408**, the test-device control gate electrode **202**, and the test-device control gate hard mask **410**.

A test-device control gate spacer **412** lines sidewalls of the test-device control gate electrode **202**, sidewalls of the test-device control gate dielectric layer **408**, and sidewalls of the test-device control gate hard mask **410**, and comprises a plurality of control gate spacer segments corresponding to the sidewalls. For ease of illustration, only some of the control gate spacer segments are labeled **412**. Further, the test-device control gate spacer **412** overlies the test-device floating gate electrode **216** and, in some embodiments, the isolation structure **404**. The test-device control gate spacer **412** may be or comprise, for example, silicon oxide, silicon nitride, some other suitable dielectric(s), or any combination of the foregoing.

A test-device floating gate spacer **414** lines sidewalls of the test-device floating gate electrode **216**, sidewalls of the test-device floating gate dielectric layer **406**, and sidewalls of the test-device control gate spacer **412**, and comprises a plurality of floating gate spacer segments corresponding to the sidewalls. For ease of illustration, only some of the floating gate spacers are labeled **414**. Further, the test-device floating gate spacer **414** overlies the semiconductor memory region **104m** and, in some embodiments, the isolation structure **404**. The test-device floating gate spacer **414** may be or comprise, for example, silicon oxide, silicon nitride, some other suitable dielectric(s), or any combination of the foregoing.

A plurality of test-device select gate electrodes **108** border sidewalls of the gate stack **106**, and a plurality of test-device select gate dielectric layers **416** space the test-device select gate electrodes **108** from the semiconductor memory region **104m**. For ease of illustration, only some of the test-device select gate electrodes **108** are labeled **108**, and only one of the test-device select gate dielectric layers **416** is labeled **416**. The test-device select gate electrodes **108** may be or comprise, for example, metal, doped polysilicon, or some other suitable conductive material(s). The test-device select gate dielectric layers **416** may be or comprise, for example, silicon oxide, some other suitable dielectric material(s), or any combination of the foregoing.

A BEOL interconnect structure **418** covers the floating gate test device **102** and comprises a plurality of interconnect dielectric layers covering the floating gate test device **102**. The interconnect dielectric layers comprise a pre-wire dielectric layer **420a**, a first ILD layer **420b** overlying the pre-wire dielectric layer **420a**, and a second ILD layer **420c** overlying the first ILD layer **420b**. The pre-wire dielectric layer **420a** and the first and second ILD layers **420b**, **420c** may be or comprise, for example, silicon oxide, silicon nitride, silicon oxynitride, a low κ dielectric, some other suitable dielectric(s), or any combination of the foregoing. As used herein, a low κ dielectric is a dielectric with a dielectric constant κ less than about 3.9, 3, 2, or 1. In some embodiments, a contact etch stop layer **422** covers and conforms to the floating gate test device **102**, between the floating gate test device **102** and the pre-wire dielectric layer **420a**. The contact etch stop layer **422** may be or comprise, for example, silicon nitride, silicon carbide, some other suitable dielectric(s), or any combination of the foregoing.

The BEOL interconnect structure **418** further comprises a wire **424** and a plurality of contact vias **426**. For ease of illustration, only some of the contact vias **426** are labeled **426**. The wire **424** covers and contacts the contact vias **426**, and further overlies the floating gate test device **102**. Further, the wire **424** is recessed into a top of the first ILD layer **420b** and is covered by the second ILD layer **420c**. The contact vias **426** respectively overlie the islands **106i** of the gate stack **106**. Further, the contact vias **426** extend from a top surface of the pre-wire dielectric layer **420a**, through the pre-wire dielectric layer **420a** and the test-device control gate electrode **202**, to contact with a top surface of the test-device floating gate electrode **216**. Note that the openings in the islands **106i** through which the contact vias **426** extend to the test-device floating gate electrode **216** are not shown in FIGS. 2A-2F and 3A-3H for ease of illustration. In some embodiments, the contact vias **426** are electrically insulated from the test-device control gate electrode **202** by dielectric liners (not shown) separating the contact vias **426** from sidewalls of the test-device control gate electrode **202**. The wire **424** and the contact vias **426** may be or comprise, for example, copper, aluminum, aluminum copper, tungsten, some other suitable conductor(s), or any combination of the foregoing.

The contact vias **426** have a contact-via width W_{cv} and the control gate islands **202i** have a control-gate-island width W_{ci} . In some embodiments, each of the contact vias **426** individually has the contact-via width W_{cv} , and/or each of the control gate islands **202i** individually has the control-gate-island width W_{ci} . In some embodiments, the control-gate-island width W_{ci} is three or more times greater than the contact-via width W_{cv} . Such embodiments may arise when top layouts of the control gate islands **202i** are square shaped, examples of which are shown in FIGS. 2C and 3C. If the control-gate-island width W_{ci} is less than three times

greater than the contact-via width W_{cv} , the reliability of the floating gate test device **102** is low and bulk manufacturing yields are low.

In some embodiments, a plurality of test-device source/drain regions **427** are in the semiconductor substrate **402**, and each of the test-device source/drain regions **427** is formed between two opposing gate electrodes of the test-device select gate electrodes **108**. In other embodiments, the test-device source/drain regions **427** are omitted. In some embodiments, the BEOL interconnect structure **418** defines a conductive path (not shown) electrically coupling the test-device source/drain regions **427** to the test-device floating gate electrode **216**. The test-device source/drain regions **427** may, for example, be n-type or p-type.

In some embodiments, a plurality of silicide pads **428** are on a top surface of the test-device floating gate electrode **216**, a top surface of the test-device source/drain regions **427**, top surfaces of the test-device select gate electrodes **108**, a top surface of some other structure, or any combination of the foregoing. For ease of illustration, only some of the silicide pads **428** are labeled **428**. The silicide pads **428** may be or comprise, for example, nickel silicide or some other suitable silicide(s).

With reference to FIG. 4B, another cross-sectional view **400B** of some embodiments of the IC of FIGS. 2A and 2B and/or the IC of FIGS. 3A and 3B is provided. The cross-sectional view **400B** of FIG. 4B may, for example, be taken along line B-B' in FIGS. 2A and 2B and/or along line B-B' in FIGS. 3A and 3B. Additionally, the cross-sectional view **400B** may, for example, be taken along line B-B' in FIG. 1A and/or FIG. 1B.

As illustrated, the gate stack **106** further comprises the plurality of bridges **106b** interconnecting the islands **106i**. The bridges **106b** comprise a bridge for each pair of neighboring islands, and the bridge extends from direct contact with a first island of the pair to a second island of the pair. While the islands **106i** and the bridges **106b** have similar layouts in the cross-sectional view **400B**, it is to be appreciated that the islands **106i** and the bridges **106b** have different top layouts. See, for example, FIGS. 1A and 1B.

With reference to FIG. 4C, another cross-sectional view **400C** of some embodiments of the IC of FIGS. 2A and 2C and/or the IC of FIGS. 3A and 3B is provided. The cross-sectional view **400C** of FIG. 4C may, for example, be taken along line C-C' in FIGS. 2A and 2B and/or along line C-C' in FIGS. 3A and 3B.

As illustrated, a pair of memory cells **204c** rests on the semiconductor memory region **104m**. The memory cells **204c** comprise a pair of individual memory source/drain regions **430i** and a common memory source/drain region **430c**. For ease of illustration, only one of the individual memory source/drain regions **430i** is labeled **430i**. The individual memory source/drain regions **430i** and the common memory source/drain region **430c** are in the semiconductor substrate **402**, along a top surface of the semiconductor substrate **402**. Further, the individual memory source/drain regions **430i** are spaced from the common memory source/drain region **430c** and are respectively on opposite sides of the common memory source/drain region **430c**.

A pair of selectively-conductive memory channels **432** is in the semiconductor substrate **402**. The selectively-conductive memory channels **432** extend along the top surface of the semiconductor substrate **402**, from the common memory source/drain region **430c** respectively to the individual memory source/drain regions **430i**. Further, the selectively-conductive memory channels **432** have an opposite doping type as the common memory source/drain region **430c** and

the individual memory source/drain regions **430i**. For example, the selectively-conductive memory channels **432** may be p-type, whereas the common memory source/drain region **430c** and the individual memory source/drain regions **430i** may be n-type, or vice versa.

A pair of memory floating gate dielectric layers **434**, a pair of memory floating gate electrodes **218**, a pair of memory control gate dielectric layers **436**, a pair of memory control gate electrodes **208**, and a pair of memory control gate hard masks **438** are stacked on the selectively-conductive memory channels **432**. The memory floating gate dielectric layers **434** respectively overlie the selectively-conductive memory channels **432** and may be or comprise, for example, silicon oxide, some other suitable dielectric(s), or any combination of the foregoing. The memory floating gate electrodes **218** respectively overlie the memory floating gate dielectric layers **434** and may be or comprise, for example, metal, doped polysilicon, or some other suitable conductor(s). The memory control gate dielectric layers **436** respectively overlie the memory floating gate electrodes **218** and may be or comprise, for example, silicon dioxide, silicon nitride, some other suitable dielectric(s), or any combination of the foregoing. The memory control gate electrodes **208** respectively overlie the memory control gate dielectric layers **436** and may be or comprise, for example, memory, doped polysilicon, or some other suitable conductor(s). The memory control gate hard masks **438** respectively overlie the memory control gate electrodes **208** and may be or comprise, for example, silicon nitride, silicon oxide, some other suitable dielectric(s), or any combination of the foregoing.

A memory control gate spacer **440** overlies the memory floating gate electrodes **218**, and comprises multiple control gate spacer segments respectively lining sidewalls of the memory control gate electrodes **208**, sidewalls of the memory control gate dielectric layers **436**, and sidewalls of the memory control gate hard masks **438**. For ease of illustration, only some of the control gate spacer segments are labeled **440**. The memory control gate spacer **440** may be or comprise, for example, silicon oxide, silicon nitride, some other suitable dielectric(s), or any combination of the foregoing.

A memory erase gate electrode **212** overlies the common memory source/drain region **430c**, between the memory control gate electrodes **208**. Further, the memory erase gate electrode **212** is electrically insulated from the memory floating gate electrodes **218** and the common memory source/drain region **430c** by a memory erase gate dielectric layer **442**. The memory erase gate dielectric layer **442** cups an underside of the memory erase gate electrode **212**, such that the memory erase gate dielectric layer **442** lines a bottom surface of the memory erase gate electrode **212** and sidewalls of the memory erase gate electrode **212**. The memory erase gate electrode **212** may be or comprise, for example, metal, doped polysilicon, or some other suitable conductive material(s). The memory erase gate dielectric layer **442** may be or comprise, for example, silicon oxide, some other suitable dielectric(s), or any combination of the foregoing.

A pair of memory select gate electrodes **210** is on the selectively-conductive memory channels **432**. For ease of illustration, only one of the memory select gate electrodes **210** is labeled **210**. The memory select gate electrodes **210** respectively overlie the selectively-conductive memory channels **432**, and respectively border the individual memory source/drain regions **430i**. Further, the memory select gate electrodes **210** are laterally spaced from the

common memory source/drain region **430c** by the memory floating gate electrodes **218**, and are laterally spaced from the memory floating gate electrodes **218** by a memory floating gate spacer **444**. The memory floating gate spacer **444** comprises multiple floating gate spacer segments respectively lining sidewalls of the memory control gate spacer **440**, sidewalls of the memory floating gate electrodes **218**, and sidewalls of the memory floating gate dielectric layers **434**. Further, the memory select gate electrodes **210** are vertically spaced from the selectively-conductive memory channels **432** by a pair of memory select gate dielectric layers **446**. The memory select gate electrodes **210** may be or comprise, for example, metal, doped polysilicon, or some other suitable conductor(s). The memory floating gate spacer **444** may be or comprise, for example, silicon oxide, silicon nitride, some other suitable dielectric(s), or any combination of the foregoing. The memory select gate dielectric layers **446** may be or comprise, for example, silicon oxide, some other suitable dielectric(s), or any combination of the foregoing.

A logic device **448** rests on a semiconductor logic region **104l** of the semiconductor substrate **402**, and may be, for example, a static random-access memory (SRAM) device, a core logic device, an input/output (I/O) device, or some other suitable logic device(s). While the semiconductor logic region **104l** is shown as being adjacent to the semiconductor memory region **104m**, this is merely for illustrative purposes. The semiconductor logic region **104l** may or may not be adjacent to the semiconductor memory region **104m**. Further, note that the logic device **448** is not shown in the top layout views **200A**, **200B** of FIGS. **2A** and **2B** and the top layout views **300A**, **300B** of FIGS. **3A** and **3B** for ease of illustration and because the top layout of the logic device **448** is beyond the scope of the present application.

In some embodiments, the logic device **448** comprises a pair of logic source/drain regions **450** and a selectively-conductive logic channel **452**. For ease of illustration, only one of the logic source/drain regions **450** is labeled **450**. The logic source/drain regions **450** and the selectively-conductive logic channel **452** are in the semiconductor substrate **402**, along a top surface of the semiconductor substrate **402**. The logic source/drain regions **450** are laterally spaced, and the selectively-conductive logic channel **452** extends from one of the logic source/drain regions **450** to another one of the logic source/drain regions **450**. Further, the selectively-conductive logic channel **452** has an opposite doping type as the logic source/drain regions **450**. For example, the selectively-conductive logic channels **452** may be p-type, whereas the logic source/drain regions **450** may be n-type, or vice versa.

A logic gate dielectric layer **456** and a logic gate electrode **458** are stacked on the selectively-conductive logic channel **452**. The logic gate dielectric layer **456** overlies the selectively-conductive logic channel **452**. The logic gate dielectric layers **456** may be or comprise, for example, silicon oxide, a high κ dielectric, some other suitable dielectric(s), or any combination of the foregoing. As used herein, a high κ dielectric is a dielectric with a dielectric constant κ greater than about 3.9, 5, 10, 15, or 20. The logic gate electrode **458** overlies the logic gate dielectric layer **456**, and may be or comprise, for example, metal, doped polysilicon, or some other suitable conductor(s).

The BEOL interconnect structure **418** covers the memory cells **204c** and the logic device **448** and comprises the pre-wire dielectric layer **420a** and the first and second ILD layers **420b**, **420c**. In some embodiments, the contact etch stop layer **422** covers and conforms to the memory cells

204c and the logic device **448** to separate the pre-wire dielectric layer **420a** from the memory cells **204c** and the logic device **448**. Further, the BEOL interconnect structure **418** comprises a plurality of additional wires **462** and a plurality of additional contact vias **464**. For ease of illustration, only some of the additional wires **462** are labeled **462**, and only some of the additional contact vias **464** are labeled **464**.

The additional contact vias **464** extend from a top surface of the pre-wire dielectric layer **420a**, through the pre-wire dielectric layer **420a**, respectively to the individual memory source/drain regions **430i**, the memory select gate electrodes **210**, the memory erase gate electrode **212**, the logic source/drain regions **450**, or any combination of the foregoing. The additional wires **462** overlie the pre-wire dielectric layer **420a** and are covered by the second ILD layer **420c**. Further, the additional wires **462** are recessed into a top of the first ILD layer **420b**, and respectively overlie and contact the additional contact vias **464**. In some embodiments, the additional wires **462** directly contact the additional contact vias **464**. The additional wires **462** and the additional contact vias **464** may be or comprise, for example, copper, aluminum copper, aluminum, tungsten, some other suitable conductor(s), or any combination of the foregoing.

In some embodiments, the silicide pads **428** are also on top surfaces of the memory select gate electrodes **210**, a top surface of the memory erase gate electrode **212**, a top surface of the individual memory source/drain regions **430i**, top surfaces of the logic source/drain regions **450**, a top surface of the logic gate electrode **458**, or any combination of the foregoing. For ease of illustration, only some of the silicide pads **428** are labeled **428**. In some embodiments, a logic gate hard mask (not shown) overlies the logic gate electrode **458**, whereby a top surface of the logic gate electrode **458** is free of silicide.

With reference to FIG. 4D, another cross-sectional view **400D** of some embodiments of the IC of FIGS. 2A and 2C and/or the IC of FIGS. 3A and 3B is provided. The cross-sectional view **400D** of FIG. 4D may, for example, be taken along line D-D' in FIGS. 2A and 2B and/or along line D-D' in FIGS. 3A and 3B.

As illustrated, a control gate inter-device line **214c** is integrated and continuous with a memory control gate electrode **208**. Further, the control gate inter-device line **214c** conforms to a memory floating gate electrode **218** that underlies the memory control gate electrode **208**. In some embodiments, the control gate inter-device line **214c** and the memory control gate electrode **208** collectively have an inverted U-shaped profile covering and straddling the memory floating gate electrode **218**. Note that the hashing is varied along the control gate inter-device lines **214c** merely to emphasize the memory control gate electrode **208**. The varied hashing should not be construed as limiting the composition of the control gate inter-device line **214c** and the memory control gate electrodes **208**.

The control gate inter-device line **214c** and the memory control gate electrode **208** are electrically insulated from the semiconductor substrate **402** and the memory floating gate electrode **218** by a memory control gate dielectric layer **436**. Further, control gate inter-device line **214c** and the memory control gate electrode **208** are covered and protected by a memory control gate hard mask **438**. The memory control gate dielectric layer **436** and the memory control gate hard mask **438** are laterally elongated in a common direction and may, for example, have a line-shaped top layout or some other suitable top layout(s).

While FIG. 4C illustrates a single pair of neighboring memory cells **204c** taken along, for example, line C-C' in FIGS. 2A and 2B and/or along line C-C' in FIGS. 3A and 3B, it is to be appreciated that FIG. 4C may, for example, be representative of each other pair of neighboring memory cells in FIGS. 2A and 2B and/or FIGS. 3A and 3B. Further, while FIG. 4D illustrates a single memory cells **204c** taken along, for example, line D-D' in FIGS. 2A and 2B and/or along line D-D' in FIGS. 3A and 3B, it is to be appreciated that FIG. 4D may, for example, be representative of each other memory cell in FIGS. 2A and 2B and/or FIGS. 3A and 3B.

In operation of the IC, each of the memory cells **204c** stores a variable amount of charge in a corresponding floating gate electrode of the memory floating gate electrodes **218**. When the corresponding floating gate electrode stores a low amount of charge, the corresponding floating gate electrode stores a first data state (e.g., a binary "1"). When the corresponding floating gate electrode stores a high amount of charge, the corresponding floating gate electrode stores a second data state (e.g., a binary "0").

The variable amount of charge screens an electric field produced by a corresponding control gate electrode of the memory control gate electrodes **208** across a corresponding selectively-conductive channel of the selectively-conductive memory channels **432**. This changes a threshold voltage of the corresponding control gate electrode between a low value and a high value. Therefore, the variable amount of charge can be read by biasing a corresponding select gate electrode of the memory select gate electrodes **210** with a voltage exceeding a threshold voltage of the corresponding select gate electrode, by further biasing the corresponding control gate electrode with a voltage between the low and high values, and by measuring a resistance of the corresponding selectively-conductive channel. Depending upon whether the corresponding selectively-conductive channel is in a high resistance state or a low resistance state, the memory cell is in the first data state or the second data state.

To change the variable amount of charge, program and erase operations are performed. Carriers (e.g., electrons) are added to the corresponding floating gate electrode during program operations, and carriers are removed from the corresponding floating gate electrode during erase operations. The program and erase operations may, for example, be performed by Fowler-Nordheim tunneling (FNT), hot carrier injection, or by some other suitable process(s) for moving charge into and/or out of the corresponding floating gate electrode. In some embodiments, the program operations are performed by hot carrier injection, and the erase operations are performed by FNT.

During program operations, carriers tunnel through a corresponding floating gate dielectric layer of the memory floating gate dielectric layers **434** to the corresponding floating gate electrode. This wears out the corresponding floating gate dielectric layer over time and causes the memory cell to eventually fail. Therefore, the quality of the corresponding floating gate dielectric layer is important to the lifespan of the memory cell, and testing of the corresponding floating gate dielectric layer is important for quality control.

The floating gate test device **102** (see, e.g., FIGS. 4A and 4B) may, for example, be used to measure the quality of the memory floating gate dielectric layers **434** and, hence, to estimate the lifespan of the memory cells **204c**. Namely, the floating gate test device **102** is configured to measure the quality of the test-device floating gate dielectric layer **406** (see, e.g., FIGS. 4A and 4B). Further, as seen hereafter, the

test-device floating gate dielectric layer **406** and the memory floating gate dielectric layers **434** are formed together by a common deposition process, whereby the test-device floating gate dielectric layer **406** has the same or substantially the same quality as the memory floating gate dielectric layers **434**. Accordingly, by measuring the quality of the test-device floating gate dielectric layer **406** using the floating gate test device **102**, the floating gate test device **102** also measures the quality of the memory floating gate dielectric layers **434**. This may, in turn, be used to estimate the lifespan of the memory cells **204c** and to ensure that the memory cells **204c** meet design specifications.

In some embodiments, the floating gate test device **102** may be used to determine the breakdown voltage of the test-device floating gate dielectric layer **406**. For example, a voltage from the test-device floating gate electrode **216** to the semiconductor memory region **104m** may be progressively increased until breakdown. Since the breakdown voltage is representative of the quality of the test-device floating gate dielectric layer **406**, the breakdown voltage may then be used to estimate the life span of the memory cells **204c**.

While FIGS. **4A-4D** are described with respect to FIGS. **2A, 2B, 3A, and 3B**, it is to be understood that FIGS. **4A-4D** are also applicable to FIGS. **2C-2F** and FIGS. **3C-3H**. As such, the cross-sectional views **400A-400D** of FIGS. **4A-4D** may be, and/or may be representative of, cross sections for the ICs in FIGS. **2C-2F** and FIGS. **3C-3H**.

With reference to FIGS. **5A** and **5B** through FIGS. **27A** and **27B**, a series of cross-sectional views **500A, 500B** through **2700A, 2700B** of some embodiments of a method for forming an IC comprising a floating gate test device with a cell-like top layout is provided. Figures with a suffix of "A" are taken along line A-A' in FIG. **1A, 1B, 2A, 2B, 3A, 3B**, or any combination of the foregoing, and/or may, for example, correspond to FIG. **4A**. Figures with a suffix of "B" are taken along line C-C' in FIG. **2A, 2B, 3A, 3B**, or any combination of the foregoing, and/or may, for example, correspond to FIG. **4C**.

As illustrated by the cross-sectional views **500A, 500B** of FIGS. **5A** and **5B**, an isolation structure **404** is formed in a top surface of a semiconductor substrate **402**. The isolation structure **404** separate a semiconductor memory region **104m** of the semiconductor substrate **402** and a semiconductor logic region **104l** of the semiconductor substrate **402**, and further demarcate a boundary of the semiconductor memory region **104m** and a boundary the semiconductor logic region **104l**. The boundary of the semiconductor memory region **104m** may, for example, be as shown in FIG. **2A** or **3A**. Note that the boundary of the semiconductor logic region **104l** is demarcated out of the cross-sectional views **500A, 500B** of FIGS. **5A** and **5B**. The semiconductor substrate **402** may be or comprise, for example, a bulk silicon substrate, a SOI substrate, or some other suitable semiconductor substrate(s). The isolation structure **404** may be or comprise, for example, a STI region, a DTI, or some other suitable isolation structure(s).

In some embodiments, a process for forming the isolation structure **404** comprises depositing a lower pad layer **502** covering the semiconductor substrate, and further depositing an upper pad layer **504** covering the lower pad layer **502**. The depositing of the lower and upper pad layers **502, 504** may, for example, be performed by chemical vapor deposition (CVD), physical vapor deposition (PVD), thermal oxidation, some other suitable deposition process(es), or any combination of the foregoing. As used herein, a term (e.g., process) with a suffix of "(es)" may, for example, be singular

or plural. The lower pad layer **502** is a different material than the upper pad layer **504** and may be or comprise, for example, silicon oxide or some other suitable dielectric(s). The upper pad layer **504** may be or comprise, for example, silicon nitride or some other suitable dielectric(s). The lower and upper pad layers **502, 504** and the semiconductor substrate **402** are patterned to define a trench with a top layout of the isolation structure **404**, and the trench is subsequently filled with a dielectric layer. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es). The trench may, for example, be filled by depositing the dielectric layer filling the trench and covering the upper pad layer **504**, and subsequently performing a planarization into the dielectric layer until the upper pad layer **504** is reached. The depositing of the dielectric layer may, for example, be performed by CVD, PVD, or some other suitable deposition process(es). The planarization may, for example, be performed by a chemical mechanical polish (CMP) or some other suitable planarization process(es).

As used herein, a photolithography/etching process may comprise, for example, depositing a photoresist layer on a substrate, and subsequently patterning the photoresist layer with a pattern. The depositing may, for example, be performed by spin on coating or some other suitable deposition process(es). The patterning may, for example, be performed by photolithography or some other suitable patterning processes. Further, the photolithography/etching process may comprise, for example, performing an etch into the substrate with the patterned photoresist in place to transfer the pattern to the substrate, and thereafter removing the patterned photoresist layer. The removal may, for example, be performed by plasma ashing or some other suitable removal process(es).

As illustrated by the cross-sectional views **600A, 600B** of FIGS. **6A** and **6B**, the upper pad layer **504** is patterned to remove the upper pad layer **504** from the semiconductor memory region **104m**, but not the semiconductor logic region **104l**. The patterning forms a pad opening **602** in place of the removed portion of the upper pad layer **504**, and may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es).

Also illustrated by the cross-sectional views **600A, 600B** of FIGS. **6A** and **6B**, the lower pad layer **502** is patterned to remove the lower pad layer **502** from the semiconductor memory region **104m**, but not the semiconductor logic region **104l**. The patterning expands the pad opening **602** to fill the space previously occupied by the removed portion of the lower pad layer **502**, and may, for example, be performed by an etching process or some other suitable patterning process(es). The etching process may, for example, comprise a wet etching process or some other suitable etching process(es), and/or may, for example, use a wet etchant comprising hydrofluoric acid (HF) or some other suitable chemical(s). Further, the etching process may, for example, be performed as part of a cleaning process or some other suitable process(es).

As illustrated by the cross-sectional views **700A, 700B** of FIGS. **7A** and **7B**, a floating gate dielectric layer **701** is formed on the semiconductor memory region **104m**, within the pad opening **602**. The floating gate dielectric layer **701** may be or comprise, for example, silicon oxide, some other suitable dielectric(s), or any combination of the foregoing. The floating gate dielectric layer **701** may, for example, be formed by thermal oxidation, CVD, PVD, sputtering, some other suitable deposition process(es), or any combination of the foregoing. In some embodiments in which the floating

gate dielectric layer **701** is formed by thermal oxidation, the floating gate dielectric layer **701** does not form on, or minimally forms on, the semiconductor logic region **104l** and the isolation structure **404** since oxide of the thermal oxidation more readily forms on exposed semiconductor material at the semiconductor memory region **104m** than on exposed material (e.g., silicon nitride) at the logic semiconductor region **102l** and exposed material (e.g., oxide) at the isolation structure **404**.

Also illustrated by the cross-sectional views **700A**, **700B** of FIGS. **7A** and **7B**, a floating gate electrode layer **702** is formed covering the isolation structure **404** and lining the pad opening **602** (see FIGS. **6A** and **6B**). The floating gate electrode layer **702** may, for example, be formed of metal, doped polysilicon, some other suitable conductor(s), or any combination of the foregoing. Further, the floating gate electrode layer **702** may, for example, be formed by CVD, PVD, electroless plating, electroplating, some other suitable deposition process(es), or some other suitable plating process(es).

As illustrated by the cross-sectional views **800A**, **800B** of FIGS. **8A** and **8B**, a planarization is performed into the floating gate electrode layer **702** until the isolation structure **404** is reached. The planarization removes the floating gate electrode layer **702** from the semiconductor logic region **104l** and patterns the floating gate electrode layer **702** with the same top layout as the semiconductor memory region **104m**. Examples of this top layout are shown in, for example, FIGS. **2A**, **2B**, **3A**, and **3B** with respect to the semiconductor memory region **104m**. The planarization may, for example, be performed by a CMP or some other suitable planarization process(es).

Further, although not visible within the cross-sectional views **800A**, **800B** of FIGS. **8A** and **8B**, the floating gate electrode layer **702** may, for example, be patterned to separate the floating gate electrode layer **702** into a plurality of discrete segments. See, for example, FIGS. **2B** and **3B** and note that the test-device and memory floating gate electrodes **216**, **218** are separated in a direction parallel to line D-D'. It's this separation that is the subject of the patterning. The discrete segments may include, for example, a test-device segment corresponding to a floating gate test device under manufacture. Further, the discrete segments may include, for example, a plurality of line-shaped segments having a common orientation and corresponding to rows or columns of a memory cell array under manufacture. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es).

As illustrated by the cross-sectional views **900A**, **900B** of FIGS. **9A** and **9B**, a control gate dielectric layer **902**, a control gate electrode layer **904**, and a control gate hard mask layer **906** are formed stacked on the floating gate electrode layer **702**, the upper pad layer **504**, and the isolation structure **404**. The control gate electrode layer **904** overlies the control gate dielectric layer **902**, and the control gate hard mask layer **906** overlies the control gate electrode layer **904**. The control gate electrode layer **904** may be or comprise, for example, metal, doped polysilicon, or some other suitable conductor(s), and/or may, for example, be formed by CVD, PVD, electroless plating, electroplating, or some other suitable deposition or plating process(es). The control gate dielectric layer **902** and the control gate hard mask layer **906** may be or comprise, for example, silicon oxide, silicon nitride, some other suitable dielectric(s), or any combination of the foregoing. Further, the control gate dielectric layer **902** and the control gate hard mask layer **906**

may, for example, be formed by CVD, PVD, or some other suitable deposition process(es).

As illustrated by the cross-sectional views **1000A**, **1000B** of FIGS. **10A** and **10B**, the control gate dielectric layer **902** (see FIGS. **9A** and **9B**), the control gate electrode layer **904** (see FIGS. **9A** and **9B**), and the control gate hard mask layer **906** (see FIGS. **9A** and **9B**) are patterned on the semiconductor memory region **104m**, but not the semiconductor logic region **104l**. The patterning defines a test-device control gate dielectric layer **408**, a test-device control gate electrode **202**, and a test-device control gate hard mask **410** stacked upon one another. See FIG. **10A**. Further, the patterning defines a pair of memory control gate dielectric layers **436**, a pair of memory control gate electrodes **208**, and a pair of memory control gate hard masks **438** stacked upon one another. See FIG. **10B**. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es).

The test-device control gate dielectric layer **408** overlies the floating gate electrode layer **702**, the test-device control gate electrode **202** overlies the test-device control gate dielectric layer **408**, and the test-device control gate hard mask **410** overlies the test-device control gate electrode **202**. Further, the test-device control gate dielectric layer **408**, the test-device control gate electrode **202**, and the test-device control gate hard mask **410** have cell-like top layouts. As discussed above, a cell-like top layout may be or comprise, for example, an array of islands and a plurality of bridges interconnecting the islands. In some embodiments, the test-device control gate dielectric layer **408**, the test-device control gate electrode **202**, and the test-device control gate hard mask **410** have the same or substantially the same cell-like top layout. Examples of this cell-like top layout are shown in, for example, FIGS. **2A** and **3A** with respect to the test-device control gate electrode **202**. While the test-device control gate dielectric layer **408**, the test-device control gate electrode **202**, and the test-device control gate hard mask **410** are each shown as having multiple separate segments, the separate segments may, for example, be connected out of the cross-sectional view **1000A** of FIG. **10A**.

The memory control gate dielectric layers **436** overlie the floating gate electrode layer **702** and are laterally spaced. The memory control gate electrodes **208** respectively overlie the memory control gate dielectric layers **436**, and the memory control gate hard masks **438** respectively overlie the memory control gate electrodes **208**. In some embodiments, the memory control gate dielectric layers **436**, the memory control gate electrodes **208**, and the memory control gate hard masks **438** have the same or substantially the same memory-cell top layout. Examples of this memory-cell top layout are shown in, for example, FIGS. **2A** and **3A** with respect to the memory control gate electrodes **208**.

As illustrated by the cross-sectional views **1100A**, **1100B** of FIGS. **11A** and **11B**, a test-device control gate spacer **412** (see FIG. **11A**) and a memory control gate spacer **440** (see FIG. **11B**) are formed. The test-device control gate spacer **412** comprises multiple segments respectively on sidewalls of the test-device control gate dielectric layer **408**, sidewalls of the test-device control gate electrode **202**, and sidewalls of the test-device control gate hard mask **410**. Similarly, the memory control gate spacer **440** comprises multiple segments respectively on sidewalls of the memory control gate dielectric layers **436**, sidewalls of the memory control gate electrodes **208**, and sidewalls of the memory control gate hard masks **438**. The test-device control gate spacer **412** and the memory control gate spacer **440** may be or comprise, for

example, silicon oxide, silicon nitride, silicon oxynitride, some other suitable dielectric(s), or any combination of the foregoing.

In some embodiments, a process for forming the test-device control gate spacer **412** and the memory control gate spacer **440** comprises depositing a spacer layer covering and lining the structure of FIGS. **10A** and **10B**, and subsequently performing an etch back into the spacer layer. The depositing may, for example, be performed conformally, and/or may, for example, be performed by CVD, PVD, or some other suitable deposition process(es). The etch back removes horizontal segments of the spacer layer, without removing vertical segments of the spacer layer, and the remaining vertical segments correspond to the test-device control gate spacer **412** and the memory control gate spacer **440**.

Also illustrated by the cross-sectional views **1100A**, **1100B** of FIGS. **11A** and **11B**, the floating gate electrode layer **702** (see FIGS. **10A** and **10B**) and the floating gate dielectric layer **701** (see FIGS. **10A** and **10B**) are patterned. The patterning defines a test-device floating gate electrode **216** and a test-device floating gate dielectric layer **406** stacked upon one another. See FIG. **11A**. Further, the patterning defines a pair of memory floating gate electrodes **218** and a pair of memory floating gate dielectric layers **434** stacked upon one another. See FIG. **11B**. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es).

The test-device floating gate electrode **216** underlies the test-device control gate dielectric layer **408**, and the test-device floating gate dielectric layer **406** underlies the test-device floating gate electrode **216**. Further, the test-device floating gate electrode **216** and the test-device floating gate dielectric layer **406** have cell-like top layouts. In some embodiments, the test-device floating gate electrode **216** and the test-device floating gate dielectric layer **406** have the same or substantially the same cell-like top layout. Examples of this cell-like top layout are shown in, for example, FIGS. **2B** and **3B** with respect to the test-device floating gate electrode **216**. While the test-device floating gate electrode **216** and the test-device floating gate dielectric layer **406** are each shown as having multiple separate segments, the separate segments may, for example, be connected out of the cross-sectional view **1100A** of FIG. **11A**.

The memory floating gate electrodes **218** respectively underlie the memory control gate dielectric layers **436**, and the memory floating gate dielectric layers **434** respectively underlie the memory floating gate electrodes **218**. In some embodiments, the memory floating gate electrodes **218** and the memory floating gate dielectric layers **434** have the same or substantially the same memory-cell top layout. Examples of this memory-cell top layout are shown in, for example, FIGS. **2B** and **3B** with respect to the memory floating gate electrodes **218**.

As illustrated by the cross-sectional views **1200A**, **1200B** of FIGS. **12A** and **12B**, a test-device floating gate spacer **414** (see FIG. **12A**) and a memory floating gate spacer **444** (see FIG. **11B**) are formed. The test-device floating gate spacer **414** comprises multiple segments respectively on sidewalls of test-device control gate spacer **412**, sidewalls of the test-device floating gate electrode **216**, and sidewalls of the test-device floating gate dielectric layer **406**. Similarly, the memory control gate spacer **440** comprises multiple segments respectively on sidewalls of the memory control gate spacer **440**, sidewalls of the memory floating gate electrodes **218**, and sidewalls of the memory floating gate dielectric

layers **434**. The test-device floating gate spacer **414** and the memory floating gate spacer **444** may be or comprise, for example, silicon oxide, silicon nitride, silicon oxynitride, some other suitable dielectric(s), or any combination of the foregoing.

In some embodiments, a process for forming the test-device floating gate spacer **414** and the memory floating gate spacer **444** comprises depositing a spacer layer covering and lining the structure of FIGS. **11A** and **11B**, and subsequently performing an etch back into the spacer layer. The depositing may, for example, be performed conformally, and/or may, for example, be performed by CVD, PVD, or some other suitable deposition process. The etch back removes horizontal segments of the spacer layer, without removing vertical segments of the spacer layer, and the remaining vertical segments correspond to the test-device floating gate spacer **414** and the memory floating gate spacer **444**.

Also illustrated by the cross-sectional views **1200A**, **1200B** of FIGS. **12A** and **12B**, a common memory source/drain region **430c** is formed in a top surface of the semiconductor substrate **402**, between the memory floating gate electrodes **218**. See FIG. **12B**. The common memory source/drain region **430c** is a doped region of the semiconductor substrate **402** and may, for example, have an opposite doping type as an adjoining region of the semiconductor substrate **402**. In some embodiments, a process for forming the common memory source/drain region **430c** comprises forming a photoresist layer covering the structure of FIGS. **11A** and **11B**. The photoresist layer is patterned to define an opening exposing the semiconductor substrate between the memory floating gate electrodes **218** using photolithography. A doping process is then performed with the patterned photoresist layer in place to form the common memory source/drain region **430c** through the opening. The doping process may be or comprise, for example, ion implantation or some other suitable doping process(es). The photoresist layer is then removed.

As illustrated by the cross-sectional views **1300A**, **1300B** of FIGS. **13A** and **13B**, segments of the memory floating gate spacer **444** that border the common memory source/drain region **430c** are removed. The removal may, for example, be performed by a photolithography/etching process or some other suitable etching process(es).

Also illustrated by the cross-sectional views **1300A**, **1300B** of FIGS. **13A** and **13B**, a memory erase gate dielectric layer **442** is formed covering the common memory source/drain region **430c**. See FIG. **13B**. Further, the memory erase gate dielectric layer **442** lines sidewalls of the memory floating gate electrodes **218** that face the common memory source/drain region **430c**, sidewalls of the memory floating gate dielectric layers **434** that face the common memory source/drain region **430c**, and sidewalls of the memory control gate spacer **440** that face the common memory source/drain region **430c**. The memory erase gate dielectric layer **442** may be or comprise, for example, silicon oxide or some other suitable dielectric(s).

In some embodiments, a process for forming the memory erase gate dielectric layer **442** comprises depositing a dielectric layer covering and lining the structure of FIGS. **12A** and **12B**. The dielectric layer may, for example, be deposited by thermal oxidation, CVD, PVD, or some other suitable deposition process(es). The dielectric layer is then patterned into the memory erase gate dielectric layer **442**. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es).

As illustrated by the cross-sectional views **1400A**, **1400B** of FIGS. **14A** and **14B**, a select gate dielectric layer **1402** is formed on the semiconductor substrate **402**, to the sides of the test-device floating gate electrode **216** and to the sides of the memory floating gate electrodes **218**. The select gate dielectric layer **1402** may be or comprise, for example, silicon oxide or some other suitable dielectric(s). Further, the select gate dielectric layer **1402** may be formed by, for example, thermal oxidation or some other suitable deposition process(es). In some embodiments, the select gate dielectric layer **1402** is formed by a deposition process that preferentially forms the select gate dielectric layer **1402** directly on semiconductor material of the semiconductor substrate **402** relative to surrounding dielectric material.

Also illustrated by the cross-sectional views **1400A**, **1400B** of FIGS. **14A** and **14B**, a gate electrode layer **1404** is formed covering and lining the structure of FIGS. **13A** and **13B** over the select gate dielectric layer **1402**. The gate electrode layer **1404** may be or comprise, for example, metal, doped polysilicon, or some other suitable conductor(s). The gate electrode layer **1404** may be formed by, for example, CVD, PVD, electroless plating, electroplating, or some other suitable deposition or plating process(es).

As illustrated by the cross-sectional views **1500A**, **1500B** of FIGS. **15A** and **15B**, the select gate dielectric layer **1402** (see FIGS. **14A** and **14B**) and the gate electrode layer **1404** (see FIGS. **14A** and **14B**) are patterned to define test-device select gate dielectric layers **416** and test-device select gate electrodes **108**. See FIG. **15A**. Further, the patterning defines memory select gate dielectric layers **446**, memory select gate electrodes **210**, and a memory erase gate electrode **212**. See FIG. **15B**. The test-device select gate electrodes **108** respectively overlie the test-device select gate dielectric layers **416** and border sidewalls of the test-device floating gate spacer **414**. The memory select gate electrodes **210** respectively overlie the memory select gate dielectric layers **446** and border sidewalls of the memory floating gate spacer **444**. The memory erase gate electrode **212** overlies the common memory source/drain region **430c**.

In some embodiments, a process for patterning the select gate dielectric layer **1402** and the gate electrode layer **1404** comprises performing a first etch into the gate electrode layer **1404** to etch back the gate electrode layer **1404**, and to remove horizontal segments of the gate electrode layer **1404** without removing vertical segments of the gate electrode layer **1404**. The remaining vertical segments correspond to the test-device select gate electrodes **108**, the memory select gate electrodes **210**, and the memory erase gate electrode **212**. Further, a second etch is performed into the select gate dielectric layer **1402** with the test-device select gate electrodes **108** and the memory select gate electrodes **210** in place to form the test-device select gate dielectric layers **416** and the memory select gate dielectric layers **446**. The second etch may, for example, stop on the semiconductor substrate **402**, and/or the test-device select gate electrodes **108** and the memory select gate electrodes **210** may serve as a mask for the first etch.

As illustrated by the cross-sectional views **1600A**, **1600B** of FIGS. **16A** and **16B**, an etch-back layer **1602** is formed covering the structure of FIGS. **15A** and **15B**. The etch-back layer **1602** may be, for example, a flowable material, an organic material, an anti-reflective coating (ARC), some other suitable material(s), or any combination of the foregoing. Further, the etch-back layer **1602** may, for example, be formed by spin on coating or some other suitable deposition process(es).

In some embodiments, the etch-back layer **1602** more readily deposits on a large flat area than a small flat area. Because the test-device control gate hard mask **410** has a cell-like top layout, a top of the test-device control gate hard mask **410** defines multiple small flat areas (e.g., corresponding to islands and/or corresponding to bridges) instead of a single large flat area. Examples of the cell-like top layout are shown with respect to the test-device control gate electrode **202** in FIGS. **2A** and **3A**. Further, the multiple small flat areas may, for example, be similar in size to small flat areas defined by tops of the memory control gate hard masks **438**. Therefore, the etch-back layer **1602** evenly or substantially evenly deposits on the test-device control gate hard mask **410** and the memory control gate hard masks **438**. Further, a first thickness T_1 of the etch-back layer **1602** directly over the test-device control gate hard mask **410** is the same or substantially the same as a second thickness T_2 of the etch-back layer **1602** directly over the memory control gate hard masks **438**. On the other hand, a top of the control gate hard mask layer **906** defines a large flat area on the semiconductor logic region **104/** that is large compared to the multiple small flat areas of the test-device control gate hard mask **410** and the small flat areas of the memory control gate hard masks **438**. Accordingly, a third thickness T_3 of the etch-back layer **1602** directly over the control gate hard mask layer **906** is substantially greater than the first and second thicknesses T_1 , T_2 .

As illustrated by the cross-sectional views **1700A**, **1700B** of FIGS. **17A** and **17B**, an etch back is performed into the etch-back layer **1602**, the test-device control gate hard mask **410**, and the memory control gate hard masks **438**. Further, the etch back is performed into the test-device control gate spacer **412**, the test-device floating gate spacer **414**, the memory control gate spacer **440**, the memory floating gate spacer **444**, and the memory erase gate dielectric layer **442**. The etch back may, for example, be a non-selective etch back or some other suitable etch back(s). A non-selective etch back may be, for example, an etch back that does not preferentially or more quickly remove one material over another. The etch back etches the etch-back layer **1602** until the test-device control gate hard mask **410** and the memory control gate hard masks **438** are reached. Thereafter, the etch back etches the etch-back layer **1602**, the test-device control gate hard mask **410**, and the memory control gate hard masks **438** in parallel to reduce a first height H_1 of the test-device control gate hard mask **410**, and to reduce a second height H_2 of the memory control gate hard masks **438**. In some embodiments, the first and second heights H_1 , H_2 are the same or substantially the same upon completion of the etch back. Because the third thickness T_3 of the etch-back layer **1602** exceeds the first and second thickness T_1 , T_2 of the etch-back layer **1602** (see FIGS. **16A** and **16B**), the etch back may not fully remove the etch-back layer **1602** from the semiconductor logic region **104/** before the etch back concludes, whereby the etch back may not reduce a third height H_3 of the control gate hard mask layer **906** directly on the semiconductor logic region **104/**.

As illustrated by the cross-sectional views **1800A**, **1800B** of FIGS. **18A** and **18B**, the etch-back layer **1602** (see FIGS. **17A** and **17B**) is removed. The removal may, for example, be performed by an etching process or some other suitable removal process(es).

Also illustrated by the cross-sectional views **1800A**, **1800B** of FIGS. **18A** and **18B**, a hard mask layer **1802** is formed covering the structure of FIGS. **17A** and **17B**, less the etch-back layer **1602**, and with a top surface **1802t** that is planar or substantially planar. In some embodiments, a

first thickness T_1 of the hard mask layer **1802** directly over the test-device control gate hard mask **410** is the same or substantially the same as a second thickness T_2 of the hard mask layer **1802** directly over the memory control gate hard masks **438**. Further, in some embodiments, a third thickness T_3 of the hard mask layer **1802** directly over the semiconductor logic region **104l** is substantially less than the first and second thicknesses T_1 , T_2 . As should be appreciated, this is caused by the increased thickness of the etch-back layer **1602** on the semiconductor logic region **104l** during the etch back of FIGS. **17A** and **17B**. The hard mask layer **1802** may be or comprise, for example, silicon oxide, silicon nitride, polysilicon, or some other suitable hard mask material(s).

In some embodiments, a process for forming the hard mask layer **1802** comprises depositing the hard mask layer **1802**, and subsequently performing a planarization into the top surface **1802t** of the hard mask layer **1802**. The depositing may, for example, be performed by CVD, PVD, or some other suitable deposition process(es). The planarization may, for example, be performed by a CMP or some other suitable planarization process(es).

As illustrated by the cross-sectional views **1900A**, **1900B** of FIGS. **19A** and **19B**, the hard mask layer **1802** (see FIGS. **18A** and **18B**) is patterned to remove the hard mask layer **1802** from the semiconductor logic region **104l**, and to define a memory hard mask **1902** covering the semiconductor memory region **104m**. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es).

Also illustrated by the cross-sectional views **1900A**, **1900B** of FIGS. **19A** and **19B**, lower pad layer **502** (see FIGS. **18A** and **18B**), the upper pad layer **504** (see FIGS. **18A** and **18B**), the control gate dielectric layer **902** (see FIGS. **18A** and **18B**), the control gate electrode layer **904** (see FIGS. **18A** and **18B**), and the control gate hard mask layer **906** (see FIGS. **18A** and **18B**) are removed from the semiconductor logic region **104l**. In some embodiments, a process for performing the removal comprises etching the lower pad layer **502**, the upper pad layer **504**, the control gate dielectric layer **902**, the control gate electrode layer **904**, and the control gate hard mask layer **906** with the memory hard mask **1902** in place until the semiconductor logic region **104l** is reached. During the etching, the memory hard mask **1902** serves as a mask and protects the structure on the semiconductor memory region **104m** from damage. Further, the memory hard mask **1902** is partially etched, such that a first thickness T_1 of the memory hard mask **1902** directly over the test-device control gate hard mask **410** and a second thickness T_2 of the memory hard mask **1902** directly over the memory control gate hard masks **438** are reduced.

Since the test-device control gate hard mask **410** has a cell-like top layout, the first thickness T_1 of the memory hard mask **1902** is large and the same or substantially the same as the second thickness T_2 of the memory hard mask **1902**. See the above discussion regarding FIGS. **16A** and **16B** through FIGS. **18A** and **18B** for an explanation as to why this is. As such, the memory hard mask **1902** is not completely removed from the test-device control gate hard mask **410**, and the first thickness T_1 is sufficient to protect the test-device control gate hard mask **410**, while etching the upper pad layer **504**, the control gate dielectric layer **902**, the control gate electrode layer **904**, and the control gate hard mask layer **906**. This may, in turn, prevent electrical shorting

between the semiconductor memory region **104m** and the test-device floating gate electrode **216** during subsequent BEOL processing.

As illustrated by the cross-sectional views **2000A**, **2000B** of FIGS. **20A** and **20B**, a logic gate dielectric layer **2002**, a logic gate electrode layer **2004**, and a logic gate hard mask layer **2006** are formed stacked on the semiconductor memory and logic regions **104m**, **104l**. The logic gate dielectric layer **2002** overlies the memory hard mask **1902** and the semiconductor logic region **104l**, the logic gate electrode layer **2004** overlies the logic gate dielectric layer **2002**, and the logic gate hard mask layer **2006** overlies the logic gate electrode layer **2004**. The logic gate electrode layer **2004** may be or comprise, for example, metal, doped polysilicon, some other suitable conductor(s), or some other suitable material, and/or may, for example, be formed by CVD, PVD, electroless plating, electroplating, or some other suitable deposition or plating process(es). The logic gate dielectric layer **2002** may be or comprise, for example, silicon oxide, silicon nitride, a high κ dielectric, some other suitable dielectric(s), or any combination of the foregoing. The logic gate hard mask layer **2006** may be or comprise, for example, silicon oxide, silicon nitride, some other suitable dielectric(s), or any combination of the foregoing. Further, the logic gate dielectric layer **2002** and the logic gate hard mask layer **2006** may, for example, be formed by CVD, PVD, or some other suitable deposition process(es).

As illustrated by the cross-sectional views **2100A**, **2100B** of FIGS. **21A** and **21B**, the logic gate dielectric layer **2002** (see FIGS. **20A** and **20B**), the logic gate electrode layer **2004** (see FIGS. **20A** and **20B**), and the logic gate hard mask layer **2006** (see FIGS. **20A** and **20B**) are patterned. The patterning removes the logic gate dielectric layer **2002**, the logic gate electrode layer **2004**, and the logic gate hard mask layer **2006** from the semiconductor memory region **104m**, and defines a logic gate dielectric layer **456**, a logic gate electrode **458**, and a logic gate hard mask **2102** stacked on the semiconductor logic region **104l**. The logic gate dielectric layer **456** overlies the semiconductor logic region **104l**, the logic gate electrode **458** overlies the logic gate dielectric layer **456**, and the logic gate hard mask **2102** overlies the logic gate electrode **458**. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es).

The memory hard mask **1902** protects the structure on the semiconductor memory region **104m** from damage during the patterning of the logic gate dielectric layer **2002**, the logic gate electrode layer **2004**, and the logic gate hard mask layer **2006**. Further, in some embodiments, the memory hard mask **1902** is partially removed, such that the first thickness T_1 of the memory hard mask **1902** directly over the test-device control gate hard mask **410** and the second thickness T_2 of the memory hard mask **1902** directly over the memory control gate hard masks **438** are reduced. Since the test-device control gate hard mask **410** has a cell-like top layout, the first thickness T_1 of the memory hard mask **1902** is large and the same or substantially the same as the second thickness T_2 of the memory hard mask **1902**. See the above discussion regarding FIGS. **16A** and **16B** through FIGS. **18A** and **18B** for an explanation as to why this is. As such, the memory hard mask **1902** is not completely removed from the test-device control gate hard mask **410**, and the first thickness T_1 is sufficient to protect the test-device control gate hard mask **410**, during the patterning.

As illustrated by the cross-sectional views **2200A**, **2200B** of FIGS. **22A** and **22B**, the memory hard mask **1902** (see

FIGS. 21A and 21B) is removed. The removal may be performed by an etching process or some other suitable removal process(es).

Also illustrated by the cross-sectional views 2200A, 2200B of FIGS. 22A and 22B, the test-device control gate hard mask 410, the test-device control gate electrode 202, and the test-device control gate dielectric layer 408 are patterned to define a plurality of contact openings 2202 exposing the test-device floating gate electrode 216. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es).

As illustrated by the cross-sectional views 2300A, 2300B of FIGS. 23A and 23B, a pair of individual memory source/drain regions 430i and a pair of logic source/drain regions 450 are formed in a top surface of the semiconductor substrate 402. See FIG. 23B. The individual memory source/drain regions 430i respectively border the memory select gate electrodes 210 and are spaced from the common memory source/drain region 430c respectively by the memory floating gate electrodes 218. Further, the individual memory source/drain regions 430i have the same doping type as the common memory source/drain region 430c. The logic source/drain regions 450 respectively border opposite sidewalls of the logic gate electrode 458 and have a common doping type. In some embodiments, a plurality of test-device source/drain regions 427 are also formed in a top surface of the semiconductor substrate 402. The test-device source/drain regions 427 are each between two opposing gate electrodes of the test-device select gate electrodes 108 and have a common doping type. In other embodiments, the test-device source/drain regions 427 are omitted. The individual memory source/drain regions 430i, the logic source/drain regions 450, and the test-device source/drain regions 427 may, for example, be formed by ion implantation or some other suitable doping process(es).

As illustrated by the cross-sectional views 2400A, 2400B of FIGS. 24A and 24B, the logic gate hard mask 2102 (see, e.g., FIG. 23B) is removed from the logic gate electrode 458. Such removal may, for example, be performed by an etching process or some other suitable removal process(es).

Also illustrated by the cross-sectional views 2400A, 2400B of FIGS. 24A and 24B, silicide pads 428 are formed on top surfaces of the test-device select gate electrodes 108, top surfaces of the test-device floating gate electrode 216 exposed through the contact openings 2202, top surfaces of the individual memory source/drain regions 430i, top surfaces of the memory select gate electrodes 210, a top surface of the memory erase gate electrode 212, top surfaces of the logic source/drain regions 450, and a top surface of the logic gate electrode 458. In some embodiments where the test-device source/drain regions 427 are present, the silicide pads 428 are also formed on top surfaces of the test-device source/drain regions 427, between the test-device select gate electrodes 108. For ease of illustration, only some of the silicide pads 428 are labeled 428. The silicide pads 428 may, for example, be nickel silicide or some other suitable silicide(s), and/or may, for example, be formed a silicide process or some other suitable process(es) for forming silicide.

As illustrated by the cross-sectional views 2500A, 2500B of FIGS. 25A and 25B, a contact etch stop layer 422 is formed covering and conforming to the structure of FIGS. 24A and 24B in some embodiments. The contact etch stop layer 422 may, for example, be silicon nitride, silicon oxynitride, silicon carbide, some other suitable dielectric(s), or any combination of the foregoing. Further, the contact etch stop layer 422 may, for example, be formed by con-

formal deposition, and/or may, for example, be formed by CVD, PVD, some other suitable deposition process(es), or any combination of the foregoing.

Also illustrated by the cross-sectional views 2500A, 2500B of FIGS. 25A and 25B, a pre-wire dielectric layer 420a is formed covering the contact etch stop layer 422 and with a top surface 420t that is planar or substantially planar. The pre-wire dielectric layer 420a may be or comprise, for example, silicon oxide, a low κ dielectric, some other suitable dielectric(s), or any combination of the foregoing. In some embodiments, a process for forming the pre-wire dielectric layer 420a comprises depositing the pre-wire dielectric layer 420a, and subsequently performing a planarization into the top surface 420t of the pre-wire dielectric layer 420a. The depositing may, for example, be performed by CVD, PVD, or some other suitable deposition process(es). The planarization may, for example, be performed by a CMP or some other suitable planarization process(es).

As illustrated by the cross-sectional views 2600A, 2600B of FIGS. 26A and 26B, contact vias 426 are formed extending from a top surface of the pre-wire dielectric layer 420a, through the pre-wire dielectric layer 420a, to contact with the test-device floating gate electrode 216. See FIG. 26A. Further, additional contact vias 464 are formed extending from the top surface of the pre-wire dielectric layer 420a, through the pre-wire dielectric layer 420a, to the individual memory source/drain regions 430i, the memory select gate electrodes 210, the memory erase gate electrode 212, and the logic source/drain regions 450. See FIG. 26B. The contact vias 426 and the additional contact vias 464 may be or comprise, for example, tungsten, aluminum copper, copper, aluminum, or some other suitable conductor(s).

In some embodiments, a process for forming the contact vias 426 and the additional contact vias 464 comprises forming a photoresist layer covering the pre-wire dielectric layer 420a. The photoresist layer is patterned with a layout of the contact vias 426 and the additional contact vias 464, and an etch is performed into the pre-wire dielectric layer 420a with the patterned photoresist layer in place to form contact openings corresponding to the contact vias 426 and the additional contact vias 464. The patterning may, for example, be performed by photolithography or some other suitable patterning process(es). A conductive layer is deposited covering the pre-wire dielectric layer 420a and filling the contact openings, and a planarization is performed into the conductive layer until the pre-wire dielectric layer 420a is reached. The conductive layer may, for example, be deposited by CVD, PVD, electroless plating, electroplating, or some other suitable deposition or plating process(es). The planarization may, for example, be performed by a CMP or some other suitable planarization process(es).

As illustrated by the cross-sectional views 2700A, 2700B of FIGS. 27A and 27B, a wire 424 is formed overlying and contacting the contact vias 426. See FIG. 27A. Further, a plurality of additional wires 462 are respectively formed overlying and contacting the additional contact vias 464. See FIG. 27B. For ease of illustration only some of the additional wires 462 are labeled 462. The wire 424 and the additional wires 462 may be or comprise, for example, aluminum copper, copper, aluminum, or some other suitable conductor(s).

In some embodiments, a process for forming the wire 424 and the additional wires 462 comprises depositing a first ILD layer 420b covering the pre-wire dielectric layer 420a, the contact vias 426, and the additional contact vias 464. The depositing of the first ILD layer 420b may, for example, be performed by CVD, PVD, or some other suitable deposition

process(es). The first ILD layer **420b** is planarized to flatten a top surface of the first ILD layer **420b**, and the first ILD layer **420b** is patterned to form a plurality of wire openings with a layout of the wire **424** and the additional wires **462**. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es). A conductive layer is formed covering the first ILD layer **420b** and filling wire openings, and another planarization is performed into the conductive layer to form the wire **424** and the additional wires **462** in the wire openings. The depositing of the conductive layer may, for example, be performed by CVD, PVD, electroless plating, electroplating, or some other suitable deposition or plating process(es). The planarizations of the first ILD layer **420b** and the conductive layer may, for example, be performed by a CMP or some other suitable planarization process.

Also illustrated by the cross-sectional views **2700A**, **2700B** of FIGS. **27A** and **27B**, a second ILD layer **420c** is formed covering the first ILD layer **420b**, the wire **424**, and the additional wires **462**. Further, the second ILD layer **420c** is formed with a top surface **420'** that is planar or substantially planar. The second ILD layer **420c** may be or comprise, for example, silicon oxide, a low κ dielectric, some other suitable dielectric(s), or any combination of the foregoing. In some embodiments, a process for forming the second ILD layer **420c** comprises depositing the second ILD layer **420c**, and subsequently performing a planarization into the top surface **420'** of the second ILD layer **420c**. The depositing may, for example, be performed by CVD, PVD, or some other suitable deposition process(es). The planarization may, for example, be performed by a CMP or some other suitable planarization process(es).

With reference to FIG. **28**, a flowchart **2800** of some embodiments of the method of FIGS. **5A** and **5B** through FIGS. **27A** and **27B** is provided. The method may, for example, be employed to form the ICs of any one of FIGS. **1A**, **1B**, **2A**, **2B**, **3A**, **3B**, and **4A-4D**.

At **2802**, a floating gate test device structure and a memory cell structure are formed on a semiconductor memory region of a semiconductor substrate. The floating gate test device structure has a cell-like top layout, examples of which are shown in FIGS. **2A**, **2B**, **3A**, and **3B**. Further, a multilayer film is formed on a semiconductor logic region of the semiconductor substrate. See, for example, FIGS. **5A** and **5B** through FIGS. **15A** and **15B**.

At **2804**, heights of the floating gate test device structure and the memory cell structure are reduced. See, for example, FIGS. **16A** and **16B** through FIGS. **17A** and **17B**.

At **2806**, a memory hard mask is formed covering the floating gate test device structure and the memory cell structure, but not a semiconductor logic region. See, for example, FIGS. **18A** and **18B** and FIGS. **19A** and **19B**.

At **2808**, the multilayer film is removed from the semiconductor logic region by an etching process, and the memory hard mask protects the floating gate test device structure and the memory cell structure during the removal. See, for example, FIGS. **19A** and **19B**.

At **2810**, a logic device structure is formed on the semiconductor logic region, and the memory hard mask protects the floating gate test device structure and the memory cell structure during the formation. See, for example, FIGS. **20A** and **20B** through FIGS. **21A** and **21B**.

At **2812**, contact openings are formed exposing a floating gate electrode of the floating gate test device structure. See, for example, FIGS. **22A** and **22B**.

At **2814**, source/drain regions are formed along sidewalls of the memory cell structure and the logic device structure. See, for example, FIGS. **23A** and **23B**.

At **2816**, silicide pads are formed on the source/drain regions, gate electrodes of the memory cell structure, and gate electrodes of the floating gate test device structure. See, for example, FIGS. **24A** and **24B**.

At **2818**, a BEOL interconnect structure is formed covering the logic device structure, the memory cell structure, and the floating gate test device structure. See, for example, FIGS. **25A** and **25B** through FIGS. **27A** and **27B**.

While the flowchart **2800** of FIG. **28** is illustrated and described herein as a series of acts or events, it will be appreciated that the illustrated ordering of such acts or events is not to be interpreted in a limiting sense. For example, some acts may occur in different orders and/or concurrently with other acts or events apart from those illustrated and/or described herein. Further, not all illustrated acts may be required to implement one or more aspects or embodiments of the description herein, and one or more of the acts depicted herein may be carried out in one or more separate acts and/or phases.

With reference to FIGS. **29A** and **29B** through FIGS. **41A** and **41B**, a series of cross-sectional views **2900A**, **2900B** through **4100A**, **4100B** of some alternative embodiments of the method of FIGS. **5A** and **5B** through FIGS. **27A** and **27B** is provided in which the method has a gate replacement process. Figures with a suffix of "A" are taken along line A-A' in FIG. **1A**, **1B**, **2A**, **2B**, **3A**, **3B**, or any combination of the foregoing. Figures with a suffix of "B" are taken along line C-C' in FIG. **2A**, **2B**, **3A**, **3B**, or any combination of the foregoing.

As illustrated by the cross-sectional views **2900A**, **2900B** of FIGS. **29A** and **29B**, a top surface portion of the semiconductor substrate **402** at the semiconductor memory region **104m** is recessed below a top surface portion of the semiconductor substrate **402** at the semiconductor logic region **104l** by a distance *D*. In some embodiments, a process for performing the recessing comprises forming a mask covering the semiconductor logic region **104l**, but not the semiconductor memory region **104m**, and subsequently performing oxidation with the mask in place. The oxidation consumes the top surface portion of the semiconductor substrate **402** at the semiconductor memory region **104m**, thereby recessing the top surface portion of the semiconductor substrate **402** at the semiconductor memory region **104m**. The mask and oxide formed by the oxidation are then removed by an etching process or some other suitable removal process(es). The mask may be or comprise, for example, silicon nitride or some other material(s) suitable for protecting the semiconductor logic region **104l** from oxidation.

As illustrated by the cross-sectional views **3000A**, **3000B** of FIGS. **30A** and **30B**, the acts at FIGS. **5A** and **5B** through FIGS. **13A** and **13B** are performed. By performing these acts, the following features are formed on the semiconductor substrate **402**. The test-device floating gate dielectric layer **406**, the test-device floating gate electrode **216**, the test-device control gate dielectric layer **408**, the test-device control gate electrode **202**, and the test-device control gate hard mask **410** are formed stacked on the semiconductor memory region **104m**. See FIG. **30A**. The memory floating gate dielectric layers **434**, the memory floating gate electrodes **218**, the memory control gate dielectric layers **436**, the memory control gate electrodes **208**, and the memory control gate hard masks **438** are formed stacked on the semiconductor memory region **104m**. See FIG. **30B**. The

isolation structure **404**, the common memory source/drain region **430c**, the test-device control gate spacer **412**, the test-device floating gate spacer **414**, the memory control gate spacer **440**, the memory erase gate dielectric layer **442**, and the memory floating gate spacer **444** are formed on the semiconductor memory region **104m**. The lower pad layer **502**, the upper pad layer **504**, the control gate dielectric layer **902**, the control gate electrode layer **904**, and the control gate hard mask layer **906** are formed on the semiconductor logic region **104l**.

Also illustrated by the cross-sectional views **3000A**, **3000B** of FIGS. **30A** and **30B**, the select gate dielectric layer **1402** is formed on the semiconductor substrate **402**, to the sides of the test-device floating gate electrode **216** and to the sides of the memory floating gate electrodes **218**. The select gate dielectric layer **1402** may be or comprise, for example, silicon oxide or some other suitable dielectric(s). Further, the select gate dielectric layer **1402** may be formed by, for example, thermal oxidation or some other suitable deposition process(es).

Also illustrated by the cross-sectional views **3000A**, **3000B** of FIGS. **30A** and **30B**, a gate electrode layer **3002** and an etch-back layer **3004** are formed stacked over the select gate dielectric layer **1402**, the test-device control gate hard mask **410**, the memory control gate hard masks **438**, and the control gate hard mask layer **906**. The gate electrode layer **1404** may be or comprise, for example, metal, doped polysilicon, or some other suitable conductor(s). The etch-back layer **3004** may be, for example, a flowable material, an organic material, an ARC, some other suitable material(s), or any combination of the foregoing.

In some embodiments, a process for forming the gate electrode layer **3002** comprising depositing the gate electrode layer **3002** and subsequently performing a planarization into a top surface of the gate electrode layer **3002**. The gate electrode layer **1404** may be deposited by, for example, CVD, PVD, electroless plating, electroplating, or some other suitable deposition or plating process(es). The gate electrode layer **1404** may, for example, be planarized by a CMP or some other suitable planarization process. In some embodiments, a process for forming the etch-back layer **3004** comprises depositing the etch-back layer **3004** by, for example, spin on coating or some other suitable deposition process(es).

As illustrated by the cross-sectional views **3100A**, **3100B** of FIGS. **31A** and **31B**, an etch back is performed into the etch-back layer **3004** and the gate electrode layer **3002**. The etch back etches the etch-back layer **3004** until the gate electrode layer **3002** is reached. Thereafter, the etch back etches the etch-back layer **3004** and the gate electrode layer **3002** in parallel until the etch-back layer **3004** is removed. Thereafter, the etch back continues until a top surface of the gate electrode layer **3002** is below a top surface of the test-device control gate hard mask **410** and/or top surfaces of the memory control gate hard masks **438**. In some embodiments, the etch back continues until the top surface of the gate electrode layer **3002** is about even with a top surface of the test-device control gate electrode **202** and/or top surface of the memory control gate electrodes **208**.

As illustrated by the cross-sectional views **3200A**, **3200B** of FIGS. **32A** and **32B**, a select gate hard mask layer **3202** is formed covering and lining the structure of FIGS. **31A** and **31B** over the gate electrode layer **3002**. The select gate hard mask layer **3202** may be or comprise, for example, silicon nitride, silicon oxynitride, silicon oxide, some other suitable dielectric(s), or any combination of the foregoing. The select gate hard mask layer **3202** may be formed by, for example,

CVD, PVD, electroless plating, electroplating, or some other suitable deposition or plating process(es).

As illustrated by the cross-sectional views **3300A**, **3300B** of FIGS. **33A** and **33B**, the select gate dielectric layer **1402** (see FIGS. **32A** and **32B**), the gate electrode layer **3002** (see FIGS. **32A** and **32B**), and the select gate hard mask layer **3202** (see FIGS. **32A** and **32B**) are patterned to define test-device select gate dielectric layers **416**, test-device select gate electrodes **108**, and test-device select gate hard masks **3302**. See FIG. **15A**. The patterning further defines memory select gate dielectric layers **446**, memory select gate electrodes **210**, memory select gate hard masks **3304**, a memory erase gate electrode **212**, and a memory erase gate hard mask **3306**. See FIG. **15B**. The patterning may, for example, be performed by a photolithography/etching process or some other suitable patterning process(es).

The test-device select gate electrodes **108** respectively overlie the test-device select gate dielectric layers **416** and border the test-device floating gate spacer **414**. Further, the test-device select gate hard masks **3302** respectively overlie the test-device select gate electrodes **108**. The memory select gate electrodes **210** respectively overlie the memory select gate dielectric layers **446** and border the memory floating gate spacer **444**. Further, the memory select gate hard masks **3304** respectively overlie the memory select gate electrodes **210**. The memory erase gate electrode **212** overlies the common memory source/drain region **430c**, and the memory erase gate hard mask **3306** overlies the memory erase gate electrode **212**.

As illustrated by the cross-sectional views **3400A**, **3400B** of FIGS. **34A** and **34B**, the acts at FIGS. **16A** and **16B** through FIGS. **24A** and **24B** are performed. By performing the acts at FIGS. **16A** and **16B** through FIGS. **24A** and **24B**, top surfaces of the various hard masks (e.g., the test-device select gate hard masks **3302**) are flattened. Further, by performing the acts at FIGS. **16A** and **16B** through FIGS. **24A** and **24B**, the following features are formed. Contact openings **2202** are formed in the test-device control gate hard mask **410**, the test-device control gate electrode **202**, and the test-device control gate dielectric layer **408**. The logic gate dielectric layer **456**, the logic gate electrode **458**, and the logic gate hard mask **2102** are formed stacked on the semiconductor logic region **104l**. The individual memory source/drain regions **430i**, the logic source/drain regions **450**, and the silicide pads **428** are formed. In some embodiments, the test-device source/drain regions **427** are formed. In other embodiments, the test-device source/drain regions **427** are omitted.

As illustrated by the cross-sectional views **3500A**, **3500B** of FIGS. **35A** and **35B**, the various hard masks are removed. The various hard masks include, for example, the logic gate hard mask **2102**, the test-device control gate hard mask **410**, and the test-device select gate hard masks **3302**. See, e.g., FIGS. **34A** and **34B**. In some embodiments, a process for performing the removal comprise forming an etch-back layer covering and conforming to the structure of FIGS. **34A** and **34B**. The etch-back layer may be, for example, a flowable material, an organic material, an ARC, some other suitable material(s), or any combination of the foregoing. An etch back is performed into the etch-back layer and the various hard masks. The etch back etches the etch-back layer until the various hard masks are reached. Thereafter, the etch back etches the etch-back layer and the various hard masks in parallel until the various hard masks are removed. With the various hard masks removed, the etch back layer is

removed. Removal of the etch back layer may, for example, be performed by an etching process or some other suitable removal process(es).

Also illustrated by the cross-sectional views **3500A**, **3500B** of FIGS. **35A** and **35B**, the contact etch stop layer **422** is formed covering and conforming to the structure of FIGS. **34A** and **34B**, less the various hard masks. The contact etch stop layer **422** may, for example, be silicon nitride, silicon oxynitride, silicon carbide, some other suitable dielectric(s), or any combination of the foregoing. Further, the contact etch stop layer **422** may, for example, be formed by conformal deposition, and/or may, for example, be formed by CVD, PVD, some other suitable deposition process(es), or any combination of the foregoing.

Also illustrated by the cross-sectional views **3500A**, **3500B** of FIGS. **35A** and **35B**, a first pre-wire dielectric layer **420a'** is formed covering the contact etch stop layer **422**. The first pre-wire dielectric layer **420a'** may be or comprise, for example, silicon oxide, a low κ dielectric, some other suitable dielectric(s), or any combination of the foregoing. The first pre-wire dielectric layer **420a'** may, for example, be formed by depositing the first pre-wire dielectric layer **420a'** by CVD, PVD, or some other suitable deposition process(es).

As illustrated by the cross-sectional views **3600A**, **3600B** of FIGS. **36A** and **36B**, a planarization is performed into the first pre-wire dielectric layer **420a'** and the contact etch stop layer **422** to expose the various gate electrodes. The various gate electrodes include, for example, the test-device control gate electrode **202**, the memory select gate electrodes **210**, and the logic gate electrode **258**. The planarization may, for example, be performed by a CMP and/or some other suitable planarization process.

As illustrated by the cross-sectional views **3700A**, **3700B** of FIGS. **37A** and **37B**, the logic gate electrode **458** (see FIG. **36B**) is removed, thereby defining a logic gate opening **3702** in place of the logic gate electrode **458**. The removal may, for example, be performed by a photolithography/etching process or some other removal process.

As illustrated by the cross-sectional views **3800A**, **3800B** of FIGS. **38A** and **38B**, a gate replacement layer **3802** is formed covering the structure of FIGS. **37A** and **37B** and filling the logic gate opening **3702** (see FIG. **37B**). The gate replacement layer **3802** may, for example, be or comprise metal or some other suitable conductive material, and may, for example, be formed by CVD, PVD, electroless plating, electroplating, some other suitable deposition or plating process(es), or any combination of the foregoing.

As illustrated by the cross-sectional views **3900A**, **3900B** of FIGS. **39A** and **39B**, a planarization is performed into a top of the gate replacement layer **3802** (see FIGS. **38A** and **38B**) until about even with a top surface of the first pre-wire dielectric layer **420a'**, thereby forming a replacement logic gate electrode **3902** on the semiconductor logic region **104**. The planarization may, for example, be performed by a CMP and/or some other suitable planarization process.

Also illustrated by the cross-sectional views **3900A**, **3900B** of FIGS. **39A** and **39B**, more of the silicide pads **428** are formed on top surfaces of the various gate electrodes. In some embodiments, the various gate electrodes include the test-device select gate electrodes **108**, the memory select and erase gate electrodes **210**, **212**, the replacement logic gate electrode **3902**, or any combination of the foregoing. In some embodiments, the silicide pads **428** are not formed on a top surface of the replacement logic gate electrode **3902**. In some embodiments, the silicide pads **428** are formed on top surfaces of the memory control gate electrodes **208**

and/or a top surface of the test-device control gate electrode **202**. The silicide pads **428** may, for example, be nickel silicide or some other suitable silicide(s), and/or may, for example, be formed a silicide process or some other suitable process(es) for forming silicide.

As illustrated by the cross-sectional views **4000A**, **4000B** of FIGS. **40A** and **40B**, a second pre-wire dielectric layer **420a''** is formed covering the first pre-wire dielectric layer **420a'** with a top surface that is planar or substantially planar. The second pre-wire dielectric layer **420a''** may be or comprise, for example, silicon oxide, a low κ dielectric, some other suitable dielectric(s), or any combination of the foregoing. In some embodiments, a process for forming the second pre-wire dielectric layer **420a''** comprises depositing the second pre-wire dielectric layer **420a''**, and subsequently performing a planarization into the top surface of the second pre-wire dielectric layer **420a''**. The depositing may, for example, be performed by CVD, PVD, or some other suitable deposition process(es). The planarization may, for example, be performed by a CMP or some other suitable planarization process(es).

Also illustrated by the cross-sectional views **4000A**, **4000B** of FIGS. **40A** and **40B**, the contact vias **426** are formed extending from a top surface of the second pre-wire dielectric layer **420a''**, through the first and second pre-wire dielectric layers **420a'**, **420a''**, to contact with the test-device floating gate electrode **216**. Further, the additional contact vias **464** are formed extending from the top surface of the second pre-wire dielectric layer **420a''**, through the first and second pre-wire dielectric layers **420a'**, **420a''**, to contact with the individual memory source/drain regions **430i**, the memory select gate electrodes **210**, the memory erase gate electrode **212**, the logic source/drain regions **450**, or any combination of the foregoing. The contact vias **426** and the additional contact vias **464** may be or comprise, for example, tungsten, aluminum copper, copper, aluminum, or some other suitable conductor(s), and/or may, for example, be formed as described with regard to FIGS. **26A** and **26B**.

As illustrated by the cross-sectional views **4100A**, **4100B** of FIGS. **41A** and **41B**, a wire **424** is formed overlying and contacting the contact vias **426**. Further, a plurality of additional wires **462** are respectively formed overlying and contacting the additional contact vias **464**. The wire **424** and the additional wires **462** are laterally surrounded by the first ILD layer **420b** and are covered by the second ILD layer **420c**. The wire **424**, the additional wires **462**, the first ILD layer **420b**, and the second ILD layer **420c** are formed as illustrated and described with regard to FIGS. **27A** and **27B**.

In some embodiments, the present application provides a method for forming an IC, the method including: forming a floating gate test device structure on a semiconductor substrate, wherein the floating gate test device structure includes a first floating gate electrode and a first control gate electrode overlying the first floating gate electrode, wherein the first floating gate electrode and the first control gate electrode partially define an array of islands, and further partially define a plurality of bridges interconnecting the islands; forming a memory cell structure on the semiconductor substrate, wherein the memory cell structure includes a second floating gate electrode and a second control gate electrode overlying the second floating gate electrode; and depositing an etch-back layer covering the floating gate test device structure and the memory cell structure, wherein the etch-back layer has a first thickness directly over the first control gate electrode and a second thickness directly over the second control gate electrode, and wherein the first and second thicknesses are the same or substantially the same. In

some embodiments, the method further includes: performing an etch into the etch-back layer, the floating gate test device structure, and the memory cell structure to uniformly or substantially uniformly decrease heights respectively of the floating gate test device structure and the memory cell structure; and removing the etch-back layer. In some embodiments, the method further includes: forming a memory hard mask covering the floating gate test device structure and the memory cell structure, but not a semiconductor logic region of the semiconductor substrate; and forming a logic device structure of the semiconductor logic region, wherein the forming of the logic device structure partially etches the memory hard mask, but not the memory cell structure and the floating gate test device structure. In some embodiments, the forming of the logic device structure includes: forming a plurality of logic device layers covering the memory hard mask and the semiconductor logic region; patterning the logic device layers to define the logic device structure on the semiconductor logic region; and removing the memory hard mask. In some embodiments, the forming of the memory hard mask includes: forming a hard mask layer covering the floating gate test device structure, the memory cell structure, and the semiconductor logic region; performing a planarization into a top surface of the hard mask layer to flatten the top surface of the hard mask layer; and patterning the hard mask layer to remove the hard mask layer from the semiconductor logic region, without removing the hard mask layer from the floating gate test device structure and the memory cell structure. In some embodiments, the forming of the floating gate test device structure includes: forming the first floating gate electrode including a floating gate array of floating gate islands, and further including a plurality of floating gate bridges, wherein the floating gate bridges interconnect the floating gate islands; and forming the first control gate electrode including a control gate array of control gate islands, and further including a plurality of control gate bridges, wherein the control gate islands respectively overlie the floating gate islands, and wherein the control gate bridges interconnect the control gate islands. In some embodiments, the method further includes: forming an ILD layer covering the floating gate test device structure and the memory cell structure; forming a plurality of contact vias extending through the ILD layer, wherein the contact vias respectively overlie the floating gate islands and respectively overlie the control gate islands, and wherein the contact vias extend respectively through the control gate islands and respectively to direct contact with the floating gate islands; and forming a conductive wire covering and directly contacting the contact vias.

In some embodiments, the present application provides an IC including: a semiconductor substrate; and a floating gate test device on the semiconductor substrate, wherein the floating gate test device includes a floating gate electrode and a control gate electrode overlying the floating gate electrode, wherein the floating gate electrode and the control gate electrode partially define an array of islands, and further partially define a plurality of bridges, and wherein the bridges interconnect the islands. In some embodiments, the array is limited to a single row or column. In some embodiments, the array includes a plurality of rows and a plurality of columns. In some embodiments, the plurality of bridges includes a bridge for each pair of neighboring islands in the array, wherein the bridge extends from direct contact with a first island of the pair to a second island of the pair. In some embodiments, the islands have substantially the same top layout, wherein the bridges have substantially the same top layout. In some embodiments, the floating gate electrode

includes a floating gate array of floating gate islands, wherein the floating gate electrode further includes a plurality of floating gate bridges, wherein the floating gate islands partially define the islands, respectively, wherein the floating gate bridges partially define the bridges, respectively, and wherein the floating gate bridges interconnect the floating gate islands. In some embodiments, the IC further includes a BEOL interconnect structure covering the semiconductor substrate and the floating gate test device, wherein the BEOL interconnect structure includes an ILD layer, a plurality of contact vias, and a wire, wherein the wire overlies the floating gate test device, and wherein the contact vias respectively overlie the islands and extend from direct contact with the wire, through the control gate electrode, to direct contact with the floating gate electrode. In some embodiments, the control gate electrode includes a control gate array of control gate islands, wherein the control gate electrode includes a plurality of control gate bridges interconnecting the control gate islands, wherein the control gate islands partially define the islands, respectively, and wherein the control gate bridges partially define the bridges, respectively, and wherein the control gate bridges interconnect the control gate islands. In some embodiments, the IC further includes a memory cell on the semiconductor substrate, wherein the memory cell includes a second floating gate electrode, a second control gate electrode, an erase gate electrode, and a select gate electrode, wherein the second control gate electrode overlies the second floating gate electrode, and wherein the erase gate electrode and the select gate electrode respectively border opposite sidewalls of the second control gate electrode. In some embodiments, the floating gate electrode is independent of the second floating gate electrode, and wherein the IC further includes an inter-device line extending continuously from direct contact with the control gate electrode to direct contact with the second control gate electrode.

In some embodiments, the present application another method for forming an IC, the method including: forming a floating gate layer covering a semiconductor substrate; patterning the floating gate layer to define a first floating gate region and a second floating gate region independent of the first floating gate region; forming a control gate layer covering the first and second floating gate regions; patterning the control gate layer to define a first control gate electrode and a second control gate electrode, wherein the first control gate electrode overlies the first floating gate region, wherein the first control gate electrode has a control gate array of control gate islands, and further has a plurality of control gate bridges interconnecting the control gate islands, and wherein the second control gate electrode overlies the second floating gate region and is connected to the first control gate electrode; and performing a first etch into the first and second floating gate regions with the first and second control gate electrodes in place to form a first floating gate electrode and a second floating gate electrode respectively underlying the first and second control gate electrodes. In some embodiments, the method further includes: forming a pad layer covering the semiconductor substrate; patterning the pad layer and the semiconductor substrate to define a trench demarcating a semiconductor device region of the semiconductor substrate, and extending in a closed path along a boundary of the semiconductor device region; filling the trench with a dielectric layer; performing a second etch to remove a portion of the pad layer from the semiconductor device region, and to form an opening in place of the removed portion of the pad layer; and forming the floating gate layer covering the dielectric layer

and filling the opening. In some embodiments, the patterning of the floating gate layer includes: performing a planarization into the floating gate layer until the dielectric layer is reached to localize the floating gate layer to the opening, wherein the floating gate layer has the same to layout as the semiconductor device region upon completion of the planarization; and performing a third etch into the floating gate layer to define the first and second floating gate regions.

The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

What is claimed is:

1. An integrated circuit (IC) comprising:
 - a substrate;
 - a gate array overlying the substrate and comprising a plurality of gate electrodes in a plurality of rows and a plurality of columns; and
 - a test-device control gate electrode overlying the substrate at a periphery of the gate array, wherein a top layout of the test-device control gate electrode has a periodic pattern that is configured to prevent material from preferentially accumulating atop the test-device control gate electrode compared to the gate electrodes during blanket deposition of the material atop the gate electrodes and the test-device control gate electrode.
2. The IC according to claim 1, wherein the test-device control gate electrode comprises a plurality of island-type regions and a plurality of bridge-type regions interconnecting the island-type regions.
3. The IC according to claim 1, wherein at least some of the gate electrodes are defined by different regions of a conductive line, and wherein the test-device control gate electrode directly contacts the conductive line at an end of the conductive line.
4. The IC according to claim 1, further comprising:
 - a test-device floating gate electrode underlying the test-device control gate electrode, wherein a top layout of the test-device floating gate electrode has a plurality of island-type regions and a plurality of bridge-type regions interconnecting the island-type regions.
5. The IC according to claim 4, further comprising:
 - a wire overlying the test-device control gate electrode; and
 - a plurality of vias extending from the wire, through the test-device control gate electrode, respectively to the island-type regions.
6. The IC according to claim 1, wherein the gate array partially defines a memory array comprising a plurality of memory cells in the plurality of rows and the plurality of columns.
7. An integrated circuit (IC) comprising:
 - a substrate; and
 - a test device overlying the substrate and comprising a floating gate electrode, a control gate electrode, and a first select gate electrode, wherein the control gate electrode overlies the floating gate electrode, wherein the control gate electrode and the floating gate elec-

trode border the first select gate electrode, and wherein the control gate electrode extends laterally and continuously in a closed path to surround the first select gate electrode.

8. The IC according to claim 7, wherein the first select gate electrode extends laterally in a closed path to surround and demarcate a cross-shaped region of the IC.

9. The IC according to claim 7, wherein the control gate electrode has a plurality of pad regions and a plurality of interconnect regions that alternate along the closed path of the control gate electrode, and wherein the pad regions have different top surface areas than the interconnect regions.

10. The IC according to claim 9, wherein the pad regions have larger top surface areas than the interconnect regions.

11. The IC according to claim 7, wherein the floating gate electrode has a plurality of pad regions and a plurality of interconnect regions that alternate across a width of the test device.

12. The IC according to claim 7, wherein the test device comprises a second select gate electrode bordering the control gate electrode and the floating gate electrode, wherein the second select gate electrode is on an opposite side of the control gate electrode as the first select gate electrode, wherein the second select gate electrode has a U-shaped top layout, and wherein the control gate electrode has a side recess within which the second select gate electrode is arranged.

13. The IC according to claim 7, further comprising:

- a memory array overlying the substrate and comprising a plurality of memory gate electrodes, wherein the control gate electrode and at least some of the memory gate electrodes are integrated into a common structure that is continuous throughout its entirety.

14. An integrated circuit (IC) comprising:

- a substrate;
- a floating gate electrode comprising a plurality of pad regions and a plurality of interconnect regions, wherein the floating gate electrode alternates between the pad regions and the interconnect regions along a first axis and is continuous along the first axis from a first pad region of the plurality of pad regions to a second pad region of the plurality of pad regions, wherein the floating gate electrode is discontinuous along a second axis from the first pad region to the second pad region, wherein the first and second axes extend in parallel and are laterally offset from each other in a direction transverse to the first and second axes, and wherein the first and second pad regions are on the first and second axes and are respectively on opposite sides of the floating gate electrode;
- a control gate electrode overlying the floating gate electrode;
- a wire overlying the control gate electrode; and
- a plurality of vias extending through the control gate electrode, from the wire respectively to the pad regions.

15. The IC according to claim 14, further comprising:

- an array of unit cells bordering the control and floating gate electrodes, wherein the array of unit cells is partially defined by a layer that defines the control gate electrode.

16. The IC according to claim 14, wherein the pad regions are in a plurality of rows and a plurality of columns, and wherein the IC further comprises:

- a select gate electrode bordering the control gate electrode, wherein the select gate electrode overlaps with the second axis, but not the first axis.

17. The IC according to claim 14, wherein the control gate electrode is continuous throughout its entirety and comprises a plurality of pad regions respectively overlying the pad regions of the floating gate electrode.

18. The IC according to claim 14, further comprising: 5
a trench isolation structure extending into a top of the substrate and comprising a dielectric material, wherein the control gate electrode overlies and straddles a top edge of the trench isolation structure.

19. The IC according to claim 14, further comprising: 10
a trench isolation structure extending into a top of the substrate and comprising a dielectric material, wherein a top edge of the trench isolation structure overlies the floating gate electrode, and wherein a bottom edge of the floating gate electrode underlies the trench isolation 15
structure.

20. The IC according to claim 2, wherein the plurality of island-type regions comprises a first island-type region, a second island-type region, and a third island-type region, wherein the first and second island-type regions overlap with 20
and border along a first axis, wherein the first and third island-type regions overlap with and border along a second axis orthogonal to the first axis, wherein the plurality of bridge-type regions comprises a first bridge-type region and 25
a second bridge-type region, wherein the first bridge-type region is elongated along the first axis and extends from direct contact with the first island-type region to direct contact with the second island-type region, and wherein the 30
second bridge-type region is elongated along the second axis and extends from direct contact with the first island-type region to direct contact with the third island-type region.

* * * * *