

US011342446B2

(12) **United States Patent**  
**Guillorn et al.**

(10) **Patent No.:** **US 11,342,446 B2**  
(45) **Date of Patent:** **\*May 24, 2022**

(54) **NANOSHEET FIELD EFFECT TRANSISTORS WITH PARTIAL INSIDE SPACERS**

(71) Applicant: **TESSERA, INC.**, San Jose, CA (US)

(72) Inventors: **Michael A. Guillorn**, Cold Springs, NY (US); **Terence B. Hook**, Jericho, VT (US); **Robert R. Robison**, Colchester, VT (US); **Reinaldo A. Vega**, Mahopac, NY (US); **Rajasekhar Venigalla**, Hopewell Junction, NY (US)

(73) Assignee: **Tessera, Inc.**, San Jose, CA (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 196 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **16/684,115**

(22) Filed: **Nov. 14, 2019**

(65) **Prior Publication Data**

US 2020/0098893 A1 Mar. 26, 2020

**Related U.S. Application Data**

(60) Continuation of application No. 15/797,648, filed on Oct. 30, 2017, now Pat. No. 10,559,670, which is a (Continued)

(51) **Int. Cl.**

**H01L 29/66** (2006.01)  
**H01L 21/28** (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC ..... **H01L 29/66553** (2013.01); **B82Y 10/00** (2013.01); **H01L 21/28088** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC ..... H01L 29/66553; H01L 29/42392; H01L 29/78696; H01L 29/775; H01L 29/66439;

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

7,354,839 B2 4/2008 Wei et al.  
8,741,701 B2 6/2014 Cheng et al.

(Continued)

FOREIGN PATENT DOCUMENTS

KR 102.0160019048 A 2/2016

OTHER PUBLICATIONS

List of IBM Patents or Patent Applications Treated as Related dated Nov. 14, 2019, 2 pages.

(Continued)


*Primary Examiner* — Khiem D Nguyen

(74) *Attorney, Agent, or Firm* — Lee & Hayes, P.C.

(57) **ABSTRACT**

A method of forming a nanosheet device, including forming a channel stack on a substrate, where the channel stack includes at least one nanosheet channel layer and at least one sacrificial release layer, forming a stack cover layer on at least a portion of the channel stack, forming a dummy gate on at least a portion of the stack cover layer, wherein at least a portion of the at least one nanosheet channel layer and at least one sacrificial release layer is exposed on opposite sides of the dummy gate, removing at least a portion of the at least one sacrificial release layer on each side of the dummy gate to form a sacrificial supporting rib, and forming an inner spacer layer on exposed portions of the at least one nanosheet channel layer and at least one sacrificial supporting rib.

**20 Claims, 16 Drawing Sheets**



**Related U.S. Application Data**

division of application No. 15/417,312, filed on Jan. 27, 2017, now Pat. No. 10,170,584.

- (51) **Int. Cl.**  
*H01L 29/06* (2006.01)  
*H01L 29/423* (2006.01)  
*H01L 29/49* (2006.01)  
*H01L 29/786* (2006.01)  
*B82Y 10/00* (2011.01)  
*H01L 29/775* (2006.01)  
*H01L 29/10* (2006.01)
- (52) **U.S. Cl.**  
 CPC .... *H01L 21/28194* (2013.01); *H01L 29/0653* (2013.01); *H01L 29/0673* (2013.01); *H01L 29/1054* (2013.01); *H01L 29/42376* (2013.01); *H01L 29/42392* (2013.01); *H01L 29/4966* (2013.01); *H01L 29/66439* (2013.01); *H01L 29/66545* (2013.01); *H01L 29/66742* (2013.01); *H01L 29/66772* (2013.01); *H01L 29/775* (2013.01); *H01L 29/78651* (2013.01); *H01L 29/78654* (2013.01); *H01L 29/78696* (2013.01)
- (58) **Field of Classification Search**  
 CPC ..... H01L 29/0847; H01L 29/66545; H01L 29/0673

USPC ..... 257/347  
 See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,766,353	B2	7/2014	Doris et al.	
9,287,357	B2	3/2016	Rodder et al.	
9,831,324	B1 *	11/2017	Chao .....	H01L 21/30604
9,881,998	B1 *	1/2018	Cheng .....	H01L 21/465
10,177,235	B2 *	1/2019	Balakrishnan .....	H01L 29/0673
10,559,670	B2 *	2/2020	Guillorn .....	H01L 29/4966
2014/0151639	A1 *	6/2014	Chang .....	H01L 27/1211 257/27
2015/0364546	A1	12/2015	Rodder et al.	
2015/0372111	A1 *	12/2015	Koh .....	H01L 29/66575 257/29
2016/0049427	A1	2/2016	Zang	
2016/0071729	A1	3/2016	Hatcher et al.	
2017/0250291	A1 *	8/2017	Lee .....	H01L 29/0665
2018/0308699	A1 *	10/2018	Yeung .....	H01L 29/7848
2018/0374930	A1 *	12/2018	Bergendahl .....	H01L 21/31111

OTHER PUBLICATIONS

Ist of IBM Patents or Patent Applications Treated as Related dated Oct. 30, 2017, 2 pages.

\* cited by examiner






FIG. 1






FIG. 2






FIG. 3






FIG. 4






FIG. 5






FIG. 6






FIG. 7






FIG. 8






FIG. 9






FIG. 10






FIG. 11






FIG. 12






FIG. 13










FIG. 15






FIG. 16



## NANOSHEET FIELD EFFECT TRANSISTORS WITH PARTIAL INSIDE SPACERS

### BACKGROUND

#### Technical Field

The present invention generally relates to formation of nanosheet field effect transistors (NSFETs) having a wrap-around gate, and more particularly to the fabrication of NSFETs utilizing sacrificial layers with an inside spacer occupying a space between the source/drains and the gate.

#### Description of the Related Art

A Field Effect Transistor (FET) typically has a source, a channel, and a drain, where current flows from the source to the drain, and a gate that controls the flow of current through the channel. Field Effect Transistors (FETs) can have a variety of different structures, for example, FETs have been fabricated with the source, channel, and drain formed in the substrate material itself, where the current flows horizontally (i.e., in the plane of the substrate), and finFETs have been formed with the channel extending outward from the substrate, but where the current also flows horizontally from a source to a drain. The channel for the finFET can be an upright slab of thin rectangular Si, commonly referred to as the fin with a gate on the fin, as compared to a MOSFET with a single gate in the plane of the substrate. Depending on the doping of the source and drain, an n-FET or a p-FET can be formed.

Examples of FETs can include a metal-oxide-semiconductor field effect transistor (MOSFET) and an insulated-gate field-effect transistor (IGFET). Two FETs also can be coupled to form a complementary metal oxide semiconductor (CMOS) device, where a p-channel MOSFET and n-channel MOSFET are coupled together.

With ever decreasing device dimensions, forming the individual components and electrical contacts becomes more difficult. An approach is therefore needed that retains the positive aspects of traditional FET structures, while overcoming the scaling issues created by forming smaller device components.

#### SUMMARY

In accordance with an embodiment of the present invention, a method is provided for forming a nanosheet device. The method includes the step of forming a channel stack on a substrate, where the channel stack includes at least one nanosheet channel layer and at least one sacrificial release layer. The method further includes the step of forming a stack cover layer on at least a portion of the channel stack. The method further includes the step of forming a dummy gate on at least a portion of the stack cover layer, wherein at least a portion of the at least one nanosheet channel layer and at least one sacrificial release layer is exposed on opposite sides of the dummy gate. The method further includes the steps of removing at least a portion of the at least one sacrificial release layer on each side of the dummy gate to form a sacrificial supporting rib, and forming an inner spacer layer on exposed portions of the at least one nanosheet channel layer and at least one sacrificial supporting rib.

In accordance with another embodiment of the present invention, a method is provided for forming a nanosheet device. The method includes the step of forming a channel stack on a substrate, where the channel stack includes at

least one nanosheet channel layer and at least one sacrificial release layer. The method further includes the step of forming a stack cover layer on at least a portion of the channel stack. The method further includes the step of forming a dummy gate on at least a portion of the stack cover layer, wherein at least a portion of the at least one nanosheet channel layer and at least one sacrificial release layer is exposed on opposite sides of the dummy gate. The method further includes the step of removing at least a portion of the at least one sacrificial release layer on each side of the dummy gate to form a sacrificial supporting rib. The method further includes the steps of forming an inner spacer layer on exposed portions of the at least one nanosheet channel layer and at least one sacrificial supporting rib, and removing the inner spacer layer, at least one nanosheet channel layer, and at least one sacrificial supporting rib from the opposite sides of the dummy gate to expose a portion of the substrate, wherein cavity fills remain under the dummy gate.

In accordance with yet another embodiment of the present invention, a nanosheet device is provided. The arrangement of the nanosheet device includes a gate structure on a substrate. The arrangement further includes a source/drain region on opposite sides of the gate structure. The arrangement further includes at least one nanosheet channel layer extending between the source/drain region on each of the opposite sides of the gate structure, wherein the at least one nanosheet channel layer is in physical and electrical contact with the source/drain region on each of the opposite sides of the gate structure. The arrangement further includes four cavity fills between the substrate and the at least one nanosheet channel layer, where one of the four cavity fills is located at each of the four corners of the at least one nanosheet channel layer.

These and other features and advantages will become apparent from the following detailed description of illustrative embodiments thereof, which is to be read in connection with the accompanying drawings.

#### BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

The disclosure will provide details in the following description of preferred embodiments with reference to the following figures wherein:

FIG. 1 is a cross-sectional perspective view of a channel layer stack including nanosheet channel layers and sacrificial release layers, in accordance with an embodiment of the present invention;

FIG. 2 is a cross-sectional perspective view of a channel layer stack including alternating nanosheet channel layers and sacrificial release layers on a single crystal wafer substrate, in accordance with an embodiment of the present invention;

FIG. 3 is a cross-sectional perspective view of a patterned channel stack having a length,  $L$ , and a width,  $W$ , on a substrate with adjacent isolation regions, in accordance with an embodiment of the present invention;

FIG. 4 is a cut-away perspective view of a patterned channel stack having a stack cover layer and a dummy gate with side spacers formed on the channel stack, in accordance with an embodiment of the present invention;

FIG. 5 is a cut-away perspective view of a patterned channel stack after removing a portion of the stack cover layer and a portion of each of the sacrificial release layers in the channel stack, in accordance with an embodiment of the present invention;



FIG. 6 is a cut-away perspective view of a patterned channel stack with a plurality of nanosheet channel layers, sacrificial supporting ribs between the nanosheet channel layers, and an inner spacer layer on the nanosheet channel layers and sacrificial supporting ribs, in accordance with an embodiment of the present invention;

FIG. 7 is a cut-away perspective view of a patterned channel stack with a plurality of nanosheet channel layers, sacrificial supporting ribs between the nanosheet channel layers and sacrificial supporting ribs, in accordance with an embodiment of the present invention;

FIG. 8 is a cut-away perspective view of the long axis of the patterned channel stack with a plurality of nanosheet channel layers and sidewalls of the wider portion of the sacrificial supporting ribs between the nanosheet channel layers with the inner spacer layer filling the cavities, in accordance with an embodiment of the present invention;

FIG. 9 is a cut-away perspective view of the long axis of the patterned channel stack after removing the portions of the channel stack extending out from either side of the dummy gate and sidewall spacer, in accordance with an embodiment of the present invention;

FIG. 10 is a cut-away perspective view of the long axis of the patterned channel stack after forming source/drain regions on either side of the channel stack and dummy gate, in accordance with an embodiment of the present invention;

FIG. 11 is a cut-away perspective view of the long axis of the patterned channel stack prior to removing the dummy gate, in accordance with an embodiment of the present invention;

FIG. 12 is a cut-away perspective view of the long axis of the patterned channel stack after removing the dummy gate, in accordance with an embodiment of the present invention;

FIG. 13 is a cut-away perspective view of the long axis of the channel stack after removing the remaining portions of the sacrificial supporting ribs, in accordance with an embodiment of the present invention;

FIG. 14 is a cut-away perspective view of the long axis of the channel stack with a gate dielectric layer formed on the exposed surfaces of the nanosheet channel layers, in accordance with an embodiment of the present invention;

FIG. 15 is a cross-sectional side view of the long axis of the nanosheet device **100** with source/drain regions on opposite ends of the nanosheet channel layer(s), and a gate structure on and around each of the one or more nanosheet channel layer(s), in accordance with an embodiment of the present invention; and

FIG. 16 is a cross-sectional view of a nanosheet device **100**, looking across the channel layers and inside the gate, with a gate structure formed around each of the nanosheet channel layers, in accordance with an embodiment of the present invention.

#### DETAILED DESCRIPTION

Principles and embodiments of the present disclosure relate generally to formation of nanosheet (NS) channels for a field effect transistor (FET) without significant lateral encroachment caused by an isotropic release etch. To mitigate the problem of lateral encroachment due to removal of the sacrificial release layers at the gate edge between the nanosheets, an inside spacer is utilized to protect the materials at the vulnerable positions.

Principles and embodiments of the present disclosure also relate generally to formation of a partial inside spacer prior to a release etch by removing a portion of the sacrificial

release layers and replacing the sacrificial material with a protective spacer material at the exposed face of the channel stack.

Principles and embodiments of the present disclosure also relate generally to avoiding creation of multiple epitaxial growth fronts created by alternating epitaxial growth surfaces in the channel stack. The present principles and embodiments can also be directed to developing nanosheet (NS) channel strain with the embedded source/drain epitaxial growth.

Exemplary applications/uses to which the present principles can be applied include, but are not limited to: formation of complementary metal oxide silicon (CMOS) field effect transistors (FETs) formed by coupled finFETs, and digital gate devices (e.g., NAND, NOR, XOR, etc.).

In various embodiments, the materials and layers can be deposited by physical vapor deposition (PVD), chemical vapor deposition (CVD), atomic layer deposition (ALD), molecular beam epitaxy (MBE), or any of the various modifications thereof, for example, plasma-enhanced chemical vapor deposition (PECVD), metal-organic chemical vapor deposition (MOCVD), low pressure chemical vapor deposition (LPCVD), electron-beam physical vapor deposition (EB-PVD), and plasma-enhanced atomic layer deposition (PEALD). The depositions can be epitaxial processes, and the deposited material can be crystalline. In various embodiments, formation of a layer can be by one or more deposition processes, where, for example, a conformal layer may be formed by a first process (e.g., ALD, PEALD, etc.) and a fill may be formed by a second process (e.g., CVD, electrodeposition, PVD, etc.).

It is to be understood that the present invention will be described in terms of a given illustrative architecture; however, other architectures, structures, substrate materials and process features and steps may be varied within the scope of the present invention.

Reference to source/drain projections, layers, regions, etc., is intended to indicate that the particular device feature can be implemented as a source or a drain except as expressly indicated otherwise. In addition, the role of source and drain for an active device can in some instances be reversed, so a previously indicated drain may instead be a source and vice versa. Reference to a source/drain is, therefore, intended to encompass the broadest reasonable scope of the term.

It should be noted that certain features may not be shown in all figures for the sake of clarity. This is not intended to be interpreted as a limitation of any particular embodiment, or illustration, or scope of the claims.

Referring now to the drawings in which like numerals represent the same or similar elements and initially to FIG. 1, a cross-sectional perspective view of a channel layer stack including nanosheet channel layers and sacrificial release layers is shown, in accordance with an embodiment of the present invention.

In one or more embodiments, a substrate **110** can be a semiconductor or an insulator with an active surface semiconductor layer. The substrate can be crystalline, semi-crystalline, microcrystalline, or amorphous. The substrate can be essentially (i.e., except for contaminants) a single element (e.g., silicon), primarily (i.e., with doping) of a single element, for example, silicon (Si) or germanium (Ge), or the substrate can include a compound, for example, Al<sub>2</sub>O<sub>3</sub>, SiO<sub>2</sub>, GaAs, SiC, or SiGe. The substrate can also have multiple material layers, for example, a semiconductor-on-insulator substrate (SeOI), a silicon-on-insulator substrate (SOI), germanium-on-insulator substrate (GeOI), or



silicon-germanium-on-insulator substrate (SGOI), where an active surface layer **125** of the substrate **110** can be on a substrate insulator layer **120** (e.g., buried oxide layer (BOX)). The substrate can also have other layers forming the substrate, including high-k oxides and/or nitrides. In one or more embodiments, the substrate **110** can be a silicon wafer. In various embodiments, the substrate can be a single crystal silicon (Si), silicon germanium (SiGe), or III-V semiconductor (e.g., GaAs) wafer, or have a single crystal silicon (Si), silicon germanium (SiGe), or III-V semiconductor (e.g., GaAs) surface/active layer.

In one or more embodiments, a sacrificial release layer **130** can be formed on the surface of an active surface layer **125** of an SeOI substrate **110**, where the active surface layer **125** is a semiconductor material. In one or more embodiments, a sacrificial release layer **130** can be formed on the surface of a semiconductor substrate **110**, where the surface of the substrate **110** is a semiconductor material. The sacrificial release layers **130** can provide a gap for subsequent formation of at least a portion of a gate structure between the substrate and a nanosheet channel layer.

In one or more embodiments, a plurality of sacrificial release layers **130** can be formed with alternating nanosheet channel layers **140** on a substrate **110**, where the substrate **110** can be a semiconductor-on-insulator (SeOI) substrate with an active semiconductor surface layer **125** or a semiconductor substrate (e.g., single crystal silicon wafer), as shown in FIG. 2.

In various embodiments, the sacrificial release layers **130** can have a top surface, a bottom surface, and a thickness there between, where the sacrificial release layers **130** can be epitaxially grown on a surface of a crystalline material. The sacrificial release layers **130** can be a different material than the substrate material and/or the material of a nanosheet channel layer **140**. The sacrificial release layers **130** can be heteroepitaxially deposited on an exposed crystalline surface, for example, on a crystalline nanosheet channel layer **140**.

In one or more embodiments, the sacrificial release layers **130** can have a thickness in the range of about 5 nm to about 20 nm, or in the range of about 10 nm to about 15 nm, or about 10 nm, although other thicknesses are also contemplated.

In one or more embodiments, a sacrificial release layer **130** can be made of a material that can be selectively etched compared to the material of the nanosheet channel layer **140** and/or substrate **110** material. In a non-limiting exemplary embodiment, the sacrificial release layer **130** can be silicon-germanium ( $\text{Si}_x\text{Ge}_{1-x}$ ), where the germanium concentration can be about 50 at. % to about 70 at. %, or about 60 at. % (atomic percent).

In various embodiments, the nanosheet channel layer **140** can have a top surface, a bottom surface, and a thickness there between, where the nanosheet channel layer **140** can be epitaxially grown on a surface of a crystalline material. The nanosheet channel layer **140** can be a different material than the substrate material and/or the material of a sacrificial release layer **130**. The nanosheet channel layer **140** can be heteroepitaxially deposited on an exposed crystalline surface, for example, on a crystalline sacrificial release layer **130**. Additional nanosheet channel layer(s) **140** and sacrificial release layer(s) **130** can be alternately formed to provide a channel layer stack having N sacrificial release layers **130** and N-1 nanosheet channel layer(s) **140**.

In one or more embodiments, the nanosheet channel layer **140** can have a thickness in the range of about 2 nm to about

10 nm, or in the range of about 3 nm to about 7 nm, or about 5 nm, although other thicknesses are also contemplated.

In one or more embodiments, a nanosheet channel layer **140** can be made of a material that can be selectively etched compared to the material of the sacrificial release layer **130**. In various embodiments, the nanosheet channel layer **140** can be the same material as the substrate **110**. In a non-limiting exemplary embodiment, the nanosheet channel layer **140** can be silicon.

FIG. 2 is a cross-sectional perspective view of a channel layer stack including alternating nanosheet channel layers and sacrificial release layers on a single crystal wafer substrate, in accordance with an embodiment of the present invention.

In one or more embodiments, a sacrificial release layer **130** can be formed on at least a portion of an exposed substrate surface, where the sacrificial release layer **130** can be epitaxially grown on a single crystal substrate **110** having a predetermined crystal orientation. The sacrificial release layer **130** can be a material that is different from the exposed substrate material, where the sacrificial release layer **130** can be heteroepitaxially grown on the substrate surface. The material of the sacrificial release layer **130** can be selected to reduce inherent strain in the epitaxially grown layer, and the thickness of the sacrificial release layer **130** can be kept below the critical thickness at which dislocations (e.g., threading dislocations) could appear.

In one or more embodiments, a nanosheet channel layer **140** can be formed on at least a portion of an exposed surface of a sacrificial release layer **130**, where the nanosheet channel layer **140** can be epitaxially grown on a single crystal sacrificial release layer **130** having a predetermined crystal orientation. The nanosheet channel layer **140** can be a material that is different from the sacrificial release layer **130** material, where the nanosheet channel layer **140** can be heteroepitaxially grown on the surface of the sacrificial release layer **130**. The material of the nanosheet channel layer **140** can be selected to reduce inherent strain in the epitaxially grown layer, and the thickness of the nanosheet channel layer **140** can be kept below the critical thickness at which dislocations could appear.

In one or more embodiments, N nanosheet channel layers **140** alternating with N or N+1 sacrificial release layers **130** can form a channel layer stack, where N can be a predetermined number of nanosheet channel layers **140**.

FIG. 3 is a cross-sectional perspective view of a patterned channel stack having a length, L, and a width, W, on a substrate with adjacent isolation regions, in accordance with an embodiment of the present invention.

In one or more embodiments, the channel layer stack can be masked and patterned to form one or more channel stacks **111** on the substrate **110**, where the process of masking and patterning can involve a sidewall image transfer process, self-aligned double patterning (SADP), or self-aligned quadruple patterning (SAQP) to provide a tight pitch between vertical fins, as would be known in the art.

In one or more embodiments, the patterned channel stack **111** can have a length, L, in the range of about 40 nm to about 1000 nm, or about 80 nm to about 500 nm, or about 120 nm to about 240 nm, although other lengths are contemplated.

In one or more embodiments, the patterned channel stack **111** can have a width, W, in the range of about 2 nm to about 100 nm, or about 10 nm to about 50 nm, or about 5 nm to about 40 nm, or about 20 nm to about 40 nm, although other widths are contemplated.



In one or more embodiments, isolation trenches can be formed in the substrate, where the isolation trenches can be adjacent to the channel stack **111**. The isolation trenches can be formed during the patterning process when the channel stack sidewalls are being cut, for example, by a directional reactive ion etch (RIE), where the isolation trenches can be self-aligned with the sidewalls of the channel stack **111**. The substrate **110** can be etched to form a self-aligned trench, where the depth of the trench can be predetermined to form an isolation region **150** between neighboring devices. In various embodiments, the isolation trench(es) can be filled with an insulating dielectric material, including, but not limited to, silicon oxide (SiO), or a low-k dielectric, as would be known in the art, to form an isolation region **150**. In various embodiments, the isolation region **150** can be a shallow trench isolation (STI) region.

FIG. **4** is a cut-away perspective view of a patterned channel stack having a stack cover layer and a dummy gate with side spacers formed on the channel stack, in accordance with an embodiment of the present invention.

In one or more embodiments, a stack cover layer **160** can be formed on at least a portion of the channel stack **111**. In various embodiments, the stack cover layer **160** can be formed on one or more channel stack(s) and at least a portion of the exposed surface of the substrate **110**. The stack cover layer **160** can be blanket deposited or conformally deposited on the channel stack, substrate **110**, and isolation regions **150**. The stack cover layer **160** can be removed from the isolation regions **150** and substrate surface by an etch-back using a selective, dry plasma etch (e.g., reactive ion etch (RIE)).

In various embodiments, the stack cover layer **160** can be an oxide, for example, silicon oxide (SiO), or a nitride, for example, silicon nitride (SiN). The stack cover layer **160** can be formed by deposition on the exposed surfaces of the channel stack, or grown (e.g., thermal oxide) on the channel stack. The stack cover layer **160** can be formed on the exposed sides of the sacrificial release layer(s) **130** and nanosheet channel layers **140**.

In one or more embodiments, the channel stack(s) **111** and stack cover layer **160** can be masked and patterned to provide open regions for formation of a dummy gate **170** on the stack cover layer **160** covering each of the one or more channel stacks. In various embodiments, three dummy gates **170** can be formed on each channel stack **111**, where a dummy gate **170** can be formed on each end of the channel stack and a dummy gate **170** can be formed on a central portion of the channel stack. The dummy gates on the endwalls of the channel stack(s) can protect the channel stacks during subsequent processes.

In one or more embodiments, a dummy gate **170** can be formed on a stack cover layer **160** over one or more channel stacks **111**, where the dummy gate **170** can be formed over three sides of the channel stack. In various embodiments, the dummy gate **170** can be a material that can be easily and selectively removed from the stack cover layer **160**, including, but not limited to, poly-silicon (p-Si), amorphous silicon (a-Si), amorphous carbon (a-C), silicon oxide (SiO), silicon nitride (SiN), silicon oxynitride (SiON), and combinations thereof. In various embodiments, the dummy gate **170** may include multiple material layers (e.g., a capping layer), where the dummy gate can be a dummy gate stack.

In one or more embodiments, a sidewall spacer **180** can be formed on each of the dummy gates. The sidewall spacer **180** can be conformally deposited on the dummy gates **170** and etched back to expose the top surface of the dummy gate **170**, the channel stack **111**, and the substrate surface. A cut

away of the sidewall spacer **180** revealing a portion of the dummy gate **170** is shown in FIG. **4**, where the sidewall spacer **180** can be completely around the dummy gate **170**.

In various embodiments, the sidewall spacer **180** can be a silicon nitride (SiN), a silicon carbonitride (SiCN), a silicon boronitride (SiBN), a silicon borocarbide (SiBC), a silicon boro carbonitride (SiBCN), a boron carbide (BC), a boron nitride (BN), a titanium nitride (TiN) or combinations thereof, where the dummy gate **170** and/or stack cover layer **160** can be selectively etched relative to the sidewall spacer **180**.

FIG. **5** is a cut-away perspective view of a patterned channel stack after removing a portion of the stack cover layer and a portion of each of the sacrificial release layers in the channel stack, in accordance with an embodiment of the present invention.

In one or more embodiments, the exposed portion of the stack cover layer **160** projecting out from the sidewall spacer **180** and dummy gate **170** can be removed to expose the sides of the sacrificial release layers **130** and nanosheet channel layers **140** in the gate stack **111**. The stack cover layer **160** can be removed by an isotropic etch that removes the stack cover layer from the top and sidewalls of the channel stack.

In one or more embodiments, a portion of the one or more sacrificial release layers **130** can be partially removed to form recesses **135** in the channel stack leaving a sacrificial supporting rib **131** between each of the nanosheet channel layers **140**. Each of the recesses **135** can extend into the area below the sidewall spacer **180** and dummy gate **170**.

In one or more embodiments, the one or more sacrificial release layers **130** can be partially removed using a timed isotropic etch, for example, a wet etch, where the wet etchant can enter into the recesses **135** being formed. In various embodiments, a cavity can be formed below the stack cover layer **160** and sidewall spacer **180**, where the isotropic etch removes sacrificial release layer material not otherwise exposed.

FIG. **6** is a cut-away perspective view of a patterned channel stack with a plurality of nanosheet channel layers, sacrificial supporting ribs between the nanosheet channel layers, and an inner spacer layer on the nanosheet channel layers and sacrificial supporting ribs, in accordance with an embodiment of the present invention.

In one or more embodiments, an inner spacer layer **190** can be formed on the one or more nanosheet channel layer(s) **140** and one or more sacrificial supporting rib(s) **131**, where the inner spacer layer **190** can fill the recesses **135** adjacent to the sacrificial supporting rib(s) **131**, and between overhanging nanosheet channel layer(s) **140**. The inner spacer layer **190** can fill the portion of recesses **135** below the stack cover layer **160**, sidewall spacer **180**, and dummy gate **170**. The inner spacer layer **190** can be formed on at least a portion of the substrate **110**.

In one or more embodiments, the inner spacer layer **190** can be formed by ALD, PEALD, CVD, PECVD, or combinations thereof, where the inner spacer layer **190** can be conformally deposited within the recesses **135** by ALD to fill the recesses **135**. The conformal deposition can fill the cavities formed adjacent to a portion of the stack cover layer **160** and/or covered by a nanosheet channel layer **140** with a cavity fill **193**. A CVD or PECVD deposition can be used to increase the thickness on the outer surfaces of the nanosheet channel layer(s) **140** and top sacrificial supporting rib **131**.

In various embodiments, the sacrificial supporting rib(s) **131** can have a wider portion **136** under the dummy gate **170**, where the etching process forming the recesses **135** did



not remove material of the sacrificial release layer **130**, and a narrower portion extending out from below the stack cover layer **160** and sidewall spacer **180**. At least a portion of the sacrificial supporting rib(s) **131** can be narrower than adjacent nanosheet channel layer(s) **140**. The sacrificial supporting rib(s) **131** can, thereby, form a cross-like shape, where the cavity fill **193** can be in each of the corners of the cross-like shaped sacrificial release layer on a nanosheet channel layer **140**. Four cavity fills **193** can be in between the substrate and the bottom-most nanosheet channel layer **140**, where one of the four cavity fills is located at each of the four corners of the at least one nano sheet channel layer.

FIG. **6** illustrates portions of the sidewall spacer **180** and stack cover layer **160** cut-away to show otherwise hidden portions of the dummy gate **170**, underlying wider portion **136** of sacrificial supporting rib **131**, and inner spacer layer **190** including cavity fill **193**. Dummy gate(s) (not shown) can cover the ends of the channel stack **111** to prevent etching and/or depositions on the end faces of the nanosheet channel layer(s) **140** and sacrificial supporting rib(s) **131**.

In one or more embodiments, the inner spacer layer **190** can be a silicon nitride (SiN), a silicon oxide (SiO), a high-k metal oxide, a low-K oxide or suitable combinations thereof. In various embodiments, the inner spacer layer **190** can be  $\text{Si}_3\text{N}_4$  or  $\text{SiO}_2$ .

In various embodiments, the high-K metal oxide can include, but is not limited to, transition metal oxides such as hafnium oxide (e.g.,  $\text{HfO}_2$ ), hafnium silicon oxide (e.g.,  $\text{HfSiO}_4$ ), hafnium silicon oxynitride ( $\text{Hf}_w\text{Si}_x\text{O}_y\text{N}_z$ ), lanthanum oxide (e.g.,  $\text{La}_2\text{O}_3$ ), lanthanum aluminum oxide (e.g.,  $\text{LaAlO}_3$ ), zirconium oxide (e.g.,  $\text{ZrO}_2$ ), zirconium silicon oxide (e.g.,  $\text{ZrSiO}_4$ ), zirconium silicon oxynitride ( $\text{Zr}_w\text{Si}_x\text{O}_y\text{N}_z$ ), tantalum oxide (e.g.,  $\text{TaO}_2$ ,  $\text{Ta}_2\text{O}_5$ ), titanium oxide (e.g.,  $\text{TiO}_2$ ), barium strontium titanium oxide (e.g.,  $\text{BaTiO}_3$ — $\text{SrTiO}_3$ ), barium titanium oxide (e.g.,  $\text{BaTiO}_3$ ), strontium titanium oxide (e.g.,  $\text{SrTiO}_3$ ), yttrium oxide (e.g.,  $\text{Y}_2\text{O}_3$ ), aluminum oxide (e.g.,  $\text{Al}_2\text{O}_3$ ), lead scandium tantalum oxide ( $\text{Pb}(\text{Sc}_x\text{Ta}_{1-x})\text{O}_3$ ), and lead zinc niobate (e.g.,  $\text{PbZn}_{1/3}\text{Nb}_{2/3}\text{O}_3$ ). The high-k material can further include dopants such as lanthanum and/or aluminum. The stoichiometry of the high-K compounds can vary.

In various embodiments, the dummy gate **170** can be adjacent to the stack cover layer **160** on the channel stack **111**, and covered by the sidewall spacer **180**. The dummy gate **170** can be in direct contact with the stack cover layer **160**.

FIG. **7** is a cut-away perspective view of a patterned channel stack with a plurality of nanosheet channel layers, sacrificial supporting ribs between the nanosheet channel layers, and an inner spacer layer on the nanosheet channel layers and sacrificial supporting ribs, in accordance with an embodiment of the present invention.

FIG. **7** illustrates the inner spacer layer **190** covering the channel stack **111** on three sides and extending along the exposed surface of the substrate **110** and isolation regions **150**. Portions of the sidewall spacer **180** are shown in front of the dummy gate **170** along the sides of the channel stack. The top portion of the dummy gate is removed to show a portion of the stack cover layer **160** and wider portion **136** of the uppermost sacrificial supporting rib **131**.

FIG. **8** is a cut-away perspective view of the long axis of the patterned channel stack with a plurality of nanosheet channel layers and sidewalls of the wider portion of the sacrificial supporting ribs between the nanosheet channel layers with the inner spacer layer filling the cavities, in accordance with an embodiment of the present invention.

FIG. **8** depicts a side view of the channel stack **111** with a portion of the dummy gate **170** cut away to show the arrangement of the nanosheet channel layers **140**, and cavity fills **193** positioned on either side of the wider portion **136** of the sacrificial supporting ribs **131**, where a cavity fill **193** is also on either side of the narrower portion of sacrificial supporting rib(s) **131** and below a portion of the sidewall spacer **180**. The inner spacer layer **190** covers the portions of the channel stack extending out from either side of the dummy gate **170** and sidewall spacer **180**.

FIG. **9** is a cut-away perspective view of the long axis of the patterned channel stack after removing the portions of the channel stack extending out from either side of the dummy gate and sidewall spacer, in accordance with an embodiment of the present invention.

In one or more embodiments, a portion of the inner spacer layer **190** can be removed from the patterned channel stack **111** to expose the sacrificial supporting ribs **131** and nanosheet channel layers **140** not covered by the stack cover layer **160** and/or sidewall spacer **180**. The inner spacer layer **190** can be removed by a non-selective anisotropic etch (e.g., a non-selective RIE), where the anisotropic etch can be a directional dry plasma etch, which can be a timed etch. In various embodiments, a portion of the inner spacer layer **190** can be selectively removed relative to the stack cover layer **160**, sacrificial supporting ribs **131** and nanosheet channel layers **140**.

In various embodiments, the portion of the inner spacer layer **190** within the section of the recesses **135** forming cavities under the stack cover layer **160** are not removed by the directional RIE, but form a rectangular cavity fill **193** at each corner of the nanosheet channel layers **140** in the channel stack. The rectangular cavity fill **193** do not extend across the narrower portion of the supporting ribs **131**. In various embodiments, a single RIE can be used for removing both the inner spacer layer **190** and for the source/drain recess etch.

In one or more embodiments, the portions of the sacrificial supporting ribs **131** and nanosheet channel layers **140** extending out from either side of the dummy gate **170** and sidewall spacer **180** can be removed by a directional dry plasma etch (e.g., reactive ion etch (RIE)), where the dummy gate **170** and sidewall spacer **180** can act as a mask for the etching. Removal of the sacrificial supporting ribs **131** and nanosheet channel layers **140** can expose a face of the rectangular or cubic cavity fills **193** beneath the dummy gate **170**, and the surface **115** of the substrate **110**. Removal of the portion of the nanosheet channel layer **140** from either side of the dummy gate **170** can leave a rectangular nanosheet channel layer **140** in the gate stack. Reference to a rectangular shape is intended to include a square as well.

FIG. **9** depicts a side view of the channel stack **111** with a portion of the dummy gate **170** cut away to show the arrangement of the nanosheet channel layers **140**, and cavity fills **193** after removal of portions of the sacrificial supporting ribs **131** and nanosheet channel layers **140**.

FIG. **10** is a cut-away perspective view of the long axis of the patterned channel stack after forming source/drain regions on either side of the channel stack and dummy gate, in accordance with an embodiment of the present invention.

In one or more embodiments, a source/drain region **200** can be formed on an exposed portion of the channel stack **111**, where the source/drain region **200** can be epitaxially grown on the exposed portion of the substrate surface **115** and/or exposed portions of the nanosheet channel layers **140** and sacrificial supporting ribs **131**. In various embodiments, the surface **115** of a single crystal substrate **110** exposed by



## 11

removal of portions of the channel stack **111** can provide a suitable surface for epitaxial growth of source/drain regions **200** on either side of the dummy gate **170**.

In various embodiments, the sidewall surfaces of the nanosheet channel layers **140** and sacrificial supporting ribs **131** can provide a crystalline surface for epitaxial growth of the source/drain regions **200**. The cavity fills **193** can allow the nanosheet channel layers **140** and sacrificial supporting ribs **131** to have crystal plane continuity along the sidewall, while preventing lateral encroachment. The stacked nanosheet channel layers **140** and sacrificial supporting ribs **131** can provide a continuous sidewall for epitaxial growth of the source/drain regions **200**, since the nanosheet channel layers **140** and sacrificial supporting ribs **131** have the same crystal structure, where alternating nanosheet channel layers and sacrificial release layers have been heteroepitaxially grown on each other. The source/drain regions **200** can, thereby, grow on the sidewall of the gate stack in conjunction with the upward growth from a crystalline surface of a substrate **110**. The source/drain regions **200** can still epitaxially grow on the sidewall of the gate stack alone if the substrate surface is an amorphous layer (e.g., buried oxide layer of an SOI).

In various embodiments, the sidewalls can have a different crystal face exposed than the surface of the substrate, such that epitaxial growth may occur at different rates on the two different surfaces. The substrate surface, for example, may be a (100) face, whereas the sidewalls may be (110). One of the surfaces may thereby provide the predominant growth surface for forming the source/drain regions **200**. In various embodiments, the nanosheet channel layers **140** and sacrificial supporting ribs **131** can provide the predominant growth surface for forming the source/drain regions **200**.

In various embodiments, the source/drain region(s) **200** can be silicon or silicon-germanium suitably doped to form an n-type or a p-type field effect transistor (NFET or PFET). The source/drain region(s) **200** can be in physical and electrical contact with each of the one or more nanosheet channel layer(s) **140** in the channel stack **111**.

In one or more embodiments, an interlayer dielectric (ILD) **210** can be formed on the source/drain region(s) **200**. The interlayer dielectric (ILD) **210** can be formed by a blanket deposition that covers the source/drain region(s) **200**, as well as portions of the dummy gate **170**, isolation regions **150**, and substrate surface **115**. The interlayer dielectric (ILD) **210** can extend above the top surface of the dummy gate **170**, and chemical-mechanical polishing (CMP) can be utilized to remove the excess material and provide a smooth, flat surface.

In various embodiments, the interlayer dielectric (ILD) **210** can be silicon oxide or a low-k dielectric, where the ILD can be formed by CVD, LPCVD, or spun on. In various embodiments, a low-k dielectric material can be a fluoride-doped silicon oxide (e.g., fluoride doped glass), a carbon-doped silicon oxide, a porous silicon oxide, a spin-on silicon based polymeric material (e.g., tetraethyl orthosilicate (TEOS), hydrogen silsesquioxane (HSQ) and methylsilsesquioxane (MSQ)), or combinations thereof.

FIG. **10** depicts a portion of the dummy gate **170** and sidewall spacer **180** cut-away to show the source/drain regions **200** on the substrate **110** and in contact with the channel stack **111**. The cavity fill(s) **193** are shown remaining in the corners of the channel stack adjacent to the wider portion **136** of the sacrificial supporting ribs **131**. The portion of the ILD **210** that would wrap around and cover the sidewalls of the source/drain regions **200** and be on the

## 12

isolation region **150** is also cut away to show the source/drain regions **200** on either side of the nano sheet channel layer(s) **140**.

FIG. **11** is a cut-away perspective view of the long axis of the patterned channel stack prior to removing the dummy gate, in accordance with an embodiment of the present invention.

FIG. **11** depicts the sidewall spacer **180** surrounding the dummy gate **170** except for a partial cut-away to show the dummy gate **170** extending to the isolation region **150** and substrate **110** around the sacrificial supporting ribs **131** and nanosheet channel layer(s) **140** of the channel stack **111**. A portion of the source/drain region **200** and ILD **210** is also cut away to show the dummy gate extending around three sides of the channel stack, and the cavity fill **193**, and end faces of the sacrificial supporting ribs **131** and nanosheet channel layer(s) **140**. The rectangular cavity fills **193** are located at either side of the sacrificial supporting ribs **131** on the corners of the nanosheet channel layer(s) **140**.

FIG. **12** is a cut-away perspective view of the long axis of the patterned channel stack after removing the dummy gate and stack cover layer, in accordance with an embodiment of the present invention.

In one or more embodiments, the dummy gate **170** and stack cover layer **160** can be removed to expose the underlying channel stack **111**. The dummy gate and stack cover layer can be selectively removed. The sidewall spacer **180** can remain around the channel stack to provide a defined opening **220** for formation of an active gate structure.

In one or more embodiments, the dummy gate **170** can be removed by an isotropic etch, for example, a wet etch, that is selective for the material of the dummy gate **170** relative to the sidewall spacer **180**, sacrificial supporting ribs **131**, and nanosheet channel layers **140**. Removal of the dummy gate **170** can expose the remaining portions of the sacrificial supporting ribs **131**. The top surface of the top-most sacrificial supporting ribs **131** may be exposed by removal of the dummy gate **170** and stack cover layer **160**.

FIG. **13** is a cut-away perspective view of the long axis of the channel stack after removing the remaining portions of the sacrificial supporting ribs, in accordance with an embodiment of the present invention.

In one or more embodiments, the remaining portions of the sacrificial supporting ribs **131** including the wider portion **136**, can be removed to release the nanosheet channel layers **140**, where the nanosheet channel layers **140** can be secured at the opposite end faces to the source/drain regions **200**. The cavity fills **193** can be between the substrate surface and the bottom-most nanosheet channel layer **140**, and between each of the nano sheet channel layers **140**, where there can be four cavity fills **193** with each cavity fill **193** positioned at one of the four corners of each nanosheet channel layer. At least two cavity fills can be adjacent to a source/drain region **200**.

In one or more embodiments, the sacrificial supporting ribs **131** can be removed using an isotropic etch, for example, a wet etch selective for the material of the sacrificial supporting ribs **131**. In various embodiments, the etchant can be introduced into the opening **220**, such that the etchant can access the sides of the channel stack **111** including the sidewalls of the wider portion **136** of sacrificial supporting ribs **131**.

FIG. **13** depicts the nanosheet channel layers **140** between the source/drain regions **200**. The dummy gate was previously removed, and the sidewall spacer **180** is not shown to provide a clear view of the remaining portion of the channel stack **111**. Only a portion of the stack cover layer **160** is



## 13

shown along the bottom edges of the portion of the sidewall spacer **180**. A portion of the ILD **210** is shown adjacent to the portion of the sidewall spacer **180**. A portion of the substrate surface **115** is visible below the lowest nanosheet channel layer **140**. The cavity fills **193** can be seen adjacent to the source/drain regions **200** and separating the nanosheet channel layers **140**.

FIG. **14** is a cut-away perspective view of the long axis of the channel stack with a gate dielectric layer formed on the exposed surfaces of the nanosheet channel layers, in accordance with an embodiment of the present invention.

In one or more embodiments, a gate dielectric layer **230** can be formed on the exposed surfaces of the nanosheet channel layer(s) **140**, where the gate dielectric layer **230** can be formed by a conformal deposition process, for example, ALD, CVD, or combinations thereof. In various embodiments, the precursors for the gate dielectric layer **230** can be selected based on the ability of entering the spaces formed between the nanosheet channel layer(s) **140** vacated by the sacrificial supporting ribs **131**. In one or more embodiments, the precursors for the gate dielectric layer **230** can be introduced into the opening **220**.

In one or more embodiments, the gate dielectric layer **230** can be formed on the exposed surfaces of the isolation regions **150** at the bottom of the opening **220** within the sidewall spacer **180**. The gate dielectric layer **230** can also be formed on the inside surfaces of the sidewall spacer **180**, stack cover layer **160**, and cavity fills **193**.

FIG. **14** depicts the gate dielectric layer **230** on the exposed surfaces of the nanosheet channel layer(s) **140**, where a portion of the sidewall spacer **180** is not shown to allow a clear view of the gate dielectric layer **230** and nanosheet channel layers **140**. A portion of the gate dielectric layer **230** is shown on the illustrated portion of the sidewall spacer **180**, whereas other components of the nanosheet device are not shown for the sake of clarity.

In one or more embodiments, the gate dielectric layer **230** can be an insulating dielectric layer, for example, a silicon oxide (SiO), silicon nitride (SiN), silicon oxynitride (SiON), a high-K dielectric, or a suitable combination of these materials.

In various embodiments, the gate dielectric layer **230** can be a high-K dielectric material that can include, but is not limited to, transition metal oxides such as hafnium oxide (e.g., HfO<sub>2</sub>), hafnium silicon oxide (e.g., HfSiO<sub>4</sub>), hafnium silicon oxynitride (Hf<sub>w</sub>Si<sub>x</sub>O<sub>y</sub>N<sub>z</sub>), lanthanum oxide (e.g., La<sub>2</sub>O<sub>3</sub>), lanthanum aluminum oxide (e.g., LaAlO<sub>3</sub>), zirconium oxide (e.g., ZrO<sub>2</sub>), zirconium silicon oxide (e.g., ZrSiO<sub>4</sub>), zirconium silicon oxynitride (Zr<sub>w</sub>Si<sub>x</sub>O<sub>y</sub>N<sub>z</sub>), tantalum oxide (e.g., TaO<sub>2</sub>, Ta<sub>2</sub>O<sub>5</sub>), titanium oxide (e.g., TiO<sub>2</sub>), barium strontium titanium oxide (e.g., BaTiO<sub>3</sub>—SrTiO<sub>3</sub>), barium titanium oxide (e.g., BaTiO<sub>3</sub>), strontium titanium oxide (e.g., SrTiO<sub>3</sub>), yttrium oxide (e.g., Y<sub>2</sub>O<sub>3</sub>), aluminum oxide (e.g., Al<sub>2</sub>O<sub>3</sub>), lead scandium tantalum oxide (Pb(Sc<sub>x</sub>Ta<sub>1-x</sub>)O<sub>3</sub>), and lead zinc niobate (e.g., PbZn<sub>1/3</sub>Nb<sub>2/3</sub>O<sub>3</sub>). The high-K material can further include dopants such as lanthanum and/or aluminum. The stoichiometry of the high-K compounds can vary.

In various embodiments, the gate dielectric layer **230** can have a thickness in the range of about 1 nm to about 5 nm, or can have a thickness in the range of about 1 nm to about 3 nm.

FIG. **15** is a cross-sectional side view of the long axis of the nanosheet device **100** with source/drain regions on opposite ends of the nanosheet channel layer(s), and a gate

## 14

structure on and around each of the one or more nanosheet channel layer(s), in accordance with an embodiment of the present invention.

In one or more embodiments, a work function layer **240** can be formed on the gate dielectric layer **230**, where the work function layer **240** and gate dielectric layer **230** can surround at least a portion of each of the one or more nanosheet channel layer(s) **140**. A work function layer **240** can be formed on the exposed portion(s) of the gate dielectric layer **230** between the nanosheet channel layer(s) **140**. The work function layer **240** can be formed on the gate dielectric layer **230** to adjust the electrical properties of the gate electrode. In various embodiments, the work function layer **240** can be optional. A portion of the work function layer can be formed on the gate dielectric layer **230** on the substrate surface **115** beneath the bottom nanosheet channel layer **140**.

In one or more embodiments, the work function layer **240** can fill in the spaces between the gate dielectric layer **230** and nanosheet channel layer(s) **140**. The work function layer **240** can be formed by a conformal deposition, for example, ALD.

In various embodiments, a work function layer **240** can be a conductive nitride, including but not limited to titanium nitride (TiN), titanium aluminum nitride (TiAlN), hafnium nitride (HfN), hafnium silicon nitride (HfSiN), tantalum nitride (TaN), tantalum silicon nitride (TaSiN), tungsten nitride (WN), molybdenum nitride (MoN), niobium nitride (NbN); a conductive carbide, including but not limited to titanium carbide (TiC), titanium aluminum carbide (TiAlC), tantalum carbide (TaC), hafnium carbide (HfC); or combinations thereof. The work function layer **240** can include multiple layers of work function materials, for example, a work function layer **240** can be a TiN/TiC stack.

In various embodiments, the work function layer **240** can have a thickness in the range of about 1 nm to about 11 nm, or can have a thickness in the range of about 1 nm to about 5 nm.

In one or more embodiments, a gate fill layer **250** can be formed on the gate dielectric layer **230** and/or work function layer **240** if present, where the gate fill layer **250** can fill in the space **220** between interlayer dielectric **240**. The gate fill layer **250**, gate dielectric layer **230**, and optionally the work function layer **240**, can form a gate structure on one or more nanosheet channel layer(s) **140**, where the gate fill layer **250** and work function layer **240** can form a conductive gate electrode.

In various embodiments, the gate fill layer **250** can be blanket deposited on the exposed surfaces of the gate dielectric layer **210** and/or work function layer **240** on the nanosheet channel layers **140**. The formed gate fill layer **250** can extend above the top surface of the interlayer dielectric **210**, where the gate fill layer material above the top surfaces of the interlayer dielectric **210** can be removed by a CMP to provide a flat, uniform surface.

In various embodiments, the gate fill layer **250** can be a conductive metal, where the metal can be tungsten (W), titanium (Ti), molybdenum (Mo), cobalt (Co), or a conductive carbon material (e.g., carbon nanotube, graphene, etc.), or any suitable combinations thereof.

In various embodiments, each of the four cavity fills **193** can be separated from the other cavity fills on the same layer by at least a portion of the gate structure, where the cavity fills **193** can reduce the amount of surface area directly between the gate structure and the source/drain regions **200**. At least a portion of the conductive gate electrode can be



separated from the adjacent portion of the source/drain regions **200** by only the gate dielectric layer **230**.

FIG. **16** is a cross-sectional view of a nanosheet device **100**, looking across the channel layers and inside the gate, with a gate structure formed around each of the nanosheet channel layers, in accordance with an embodiment of the present invention.

In one or more embodiments, the gate dielectric layer **230** and the work function layer **240** can wrap around each of the nano sheet channel layer(s) **140**, and the gate fill layer **250** can surround the nanosheet channel layer(s) **140** and work function layer **240**. The gate dielectric layer **230** can extend up the inside surface of the sidewall spacer **180**, and the interlayer dielectric (ILD) **210** can be on the outside surface of the sidewall spacer **180**.

In various embodiments, electrical contacts can be formed to the gate structure and source/drain regions **200**.

It will also be understood that when an element such as a layer, region or substrate is referred to as being “on” or “over” another element, it can be directly on the other element or intervening elements may also be present. In contrast, when an element is referred to as being “directly on” or “directly over” another element, there are no intervening elements present. It will also be understood that when an element is referred to as being “connected” or “coupled” to another element, it can be directly connected or coupled to the other element or intervening elements may be present. In contrast, when an element is referred to as being “directly connected” or “directly coupled” to another element, there are no intervening elements present.

It should be understood that use of descriptions such as top, bottom, left, right, vertical, horizontal, or the like, are intended to be in reference to the orientation(s) illustrated in the figures, and are intended to be descriptive and to distinguish aspects of depicted features without being limiting. Spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper,” and the like, may be used herein for ease of description to describe one element’s or feature’s relationship to another element(s) or feature(s) as illustrated in the FIGS. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the FIGS. For example, if the device in the FIGS. is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the term “below” can encompass both an orientation of above and below. The device may be otherwise oriented (rotated 90 degrees or at other orientations), and the spatially relative descriptors used herein may be interpreted accordingly. In addition, it will also be understood that when a layer is referred to as being “between” two layers, it can be the only layer between the two layers, or one or more intervening layers may also be present.

It will be understood that, although the terms first, second, etc. may be used herein to describe various elements, these elements should not be limited by these terms. These terms are only used to distinguish one element from another element. Reference to first, second, third, etc., feature is intended to distinguish features without necessarily implying a particular order unless otherwise so stated or indicated. Thus, a first element discussed herein could be termed a second element without departing from the scope of the present concept.

The present embodiments may include a design for an integrated circuit chip, which may be created in a graphical computer programming language, and stored in a computer

storage medium (such as a disk, tape, physical hard drive, or virtual hard drive such as in a storage access network). If the designer does not fabricate chips or the photolithographic masks used to fabricate chips, the designer may transmit the resulting design by physical means (e.g., by providing a copy of the storage medium storing the design) or electronically (e.g., through the Internet) to such entities, directly or indirectly. The stored design is then converted into the appropriate format (e.g., GDSII) for the fabrication of photolithographic masks, which typically include multiple copies of the chip design in question that are to be formed on a wafer. The photolithographic masks are utilized to define areas of the wafer (and/or the layers thereon) to be etched or otherwise processed.

Methods as described herein may be used in the fabrication of integrated circuit chips. The resulting integrated circuit chips can be distributed by the fabricator in raw wafer form (that is, as a single wafer that has multiple unpackaged chips), as a bare die, or in a packaged form. In the latter case the chip is mounted in a single chip package (such as a plastic carrier, with leads that are affixed to a motherboard or other higher level carrier) or in a multichip package (such as a ceramic carrier that has either or both surface interconnections or buried interconnections). In any case the chip is then integrated with other chips, discrete circuit elements, and/or other signal processing devices as part of either (a) an intermediate product, such as a motherboard, or (b) an end product. The end product can be any product that includes integrated circuit chips, ranging from toys and other low-end applications to advanced computer products having a display, a keyboard or other input device, and a central processor.

It should also be understood that material compounds will be described in terms of listed elements, e.g., SiGe. These compounds include different proportions of the elements within the compound, e.g., SiGe includes  $\text{Si}_x\text{Ge}_{1-x}$  where  $x$  is less than or equal to 1, etc. In addition, other elements can be included in the compound and still function in accordance with the present principles. The compounds with additional elements will be referred to herein as alloys.

Reference in the specification to “one embodiment” or “an embodiment” of the present invention, as well as other variations thereof, means that a particular feature, structure, characteristic, and so forth described in connection with the embodiment is included in at least one embodiment of the present invention. Thus, the appearances of the phrase “in one embodiment” or “in an embodiment”, as well as any other variations, appearing in various places throughout the specification are not necessarily all referring to the same embodiment.

It is to be appreciated that the use of any of the following “/”, “and/or”, and “at least one of”, for example, in the cases of “A/B”, “A and/or B” and “at least one of A and B”, is intended to encompass the selection of the first listed option (A) only, or the selection of the second listed option (B) only, or the selection of both options (A and B). As a further example, in the cases of “A, B, and/or C” and “at least one of A, B, and C”, such phrasing is intended to encompass the selection of the first listed option (A) only, or the selection of the second listed option (B) only, or the selection of the third listed option (C) only, or the selection of the first and the second listed options (A and B) only, or the selection of the first and third listed options (A and C) only, or the selection of the second and third listed options (B and C) only, or the selection of all three options (A and B and C).



This may be extended, as readily apparent by one of ordinary skill in this and related arts, for as many items listed.

Having described preferred embodiments of a device and method (which are intended to be illustrative and not limiting), it is noted that modifications and variations can be made by persons skilled in the art in light of the above teachings. It is therefore to be understood that changes may be made in the particular embodiments disclosed which are within the scope of the invention as outlined by the appended claims. Having thus described aspects of the invention, with the details and particularity required by the patent laws, what is claimed and desired protected by Letters Patent is set forth in the appended claims.

What is claimed is:

1. A nanosheet device comprising:
  - a patterned channel stack disposed over a substrate comprising a first contiguous channel formed from a bottommost nanosheet channel layer;
  - a gate structure disposed over the patterned channel stack, the gate structure extending in a first direction parallel to the substrate;
  - a first and a second source/drain regions disposed on opposite sides of the gate structure in a second direction, the second direction being (i) parallel to the substrate and (ii) orthogonal to the first direction;
  - a first cavity fill;
  - a second cavity fill;
  - a third cavity fill; and
  - a fourth cavity fill,
 wherein the first, second, third, and fourth cavity fills are (i) non-contiguous and (ii) each disposed under and contacting respective first, second, third, and fourth corners of the first contiguous channel.
2. The nanosheet device of claim 1, wherein the gate structure includes a gate dielectric layer wrapped around a portion of the first contiguous channel and on a surface of each of the first, second, third, and fourth cavity fills.
3. The nanosheet device of claim 2, wherein the gate structure includes a work function layer disposed on the gate dielectric layer wrapped around the portion of the first contiguous channel.
4. The nanosheet device of claim 1, wherein the first contiguous channel is silicon.
5. The nanosheet device of claim 1, wherein the first and second cavity fills contact the first source/drain region, and the third and fourth cavity fills contact the second source/drain region.
6. The nanosheet device of claim 1, wherein each of the first, second, third, and fourth cavity fills are adjacent a portion of the gate structure underlying the first contiguous channel.
7. The nanosheet device of claim 1, further comprising an interlayer dielectric on the first and second source/drain regions.
8. The nanosheet device of claim 1, further comprising:
  - a second contiguous channel within the patterned channel stack;
  - a fifth cavity fill;
  - a sixth cavity fill;
  - a seventh cavity fill; and
  - an eighth cavity fill,
 wherein the fifth, sixth, seventh, and eighth cavity fills are (i) non-contiguous and (ii) each disposed between and

contacting the first and second contiguous channels at respective first, second, third, and fourth corners of the first and second contiguous channels.

9. The nanosheet device of claim 8, wherein the eight cavity fills comprise a low-K oxide.

10. A nanosheet device comprising:

- a patterned channel stack disposed over a substrate comprising (i) a first contiguous channel formed from a first nanosheet channel layer and (ii) a second contiguous channel formed from a second nanosheet channel layer, wherein the first contiguous channel is above and adjacent to the second contiguous channel;

- a gate structure disposed over the patterned channel stack, the gate structure extending in a first direction parallel to the substrate;

- a first and a second source/drain regions disposed on opposite sides of the gate structure in a second direction, the second direction being (i) parallel to the substrate and (ii) orthogonal to the first direction;

- a first cavity fill;

- a second cavity fill;

- a third cavity fill; and

- a fourth cavity fill,

wherein the first, second, third, and fourth cavity fills are (i) non-contiguous, (ii) each disposed under and contacting respective first, second, third, and fourth corners of the first contiguous channel, and (iii) each disposed over and contacting respective first, second, third, and fourth corners of the second contiguous channel.

11. The nanosheet device of claim 10, wherein the first and second contiguous channels each have a thickness in a range of about 2 nm to about 10 nm.

12. The nanosheet device of claim 10, wherein the first and second contiguous channels each have a thickness in a range of about 3 nm to about 7 nm.

13. The nanosheet device of claim 10, wherein the first and second contiguous channels are silicon (Si).

14. The nanosheet device of claim 10, wherein the first, second, third, and fourth cavity fills each have a thickness in a range of about 5 nm to about 20 nm.

15. The nanosheet device of claim 10, wherein the first, second, third, and fourth cavity fills each have a thickness in a range of about 10 nm to about 15 nm.

16. The nanosheet device of claim 10, wherein the first and second cavity fills contact the first source/drain region, and the third and fourth cavity fills contact the second source/drain region.

17. The nanosheet device of claim 10, wherein the gate structure includes a work function layer disposed on a first gate dielectric layer wrapped around a portion of the first contiguous channel and on a second gate dielectric layer wrapped around a portion of the second contiguous channel.

18. The nanosheet device of claim 17, wherein the work function layer fills a space between opposing first and second gate dielectric layers.

19. The nanosheet device of claim 17, wherein the work function layer has a thickness in a range of about 1 nm to about 11 nm.

20. The nanosheet device of claim 17, wherein the work function layer has a thickness in a range of about 1 nm to about 5 nm.