



(10) **Patent No.:** US 11,462,802 B2  
(45) **Date of Patent:** Oct. 4, 2022

(52) **U.S. Cl.**  
CPC ..... ***H01M 50/403*** (2021.01); ***C08J 5/18***  
(2013.01); ***C08J 9/0038*** (2013.01); ***C08K 3/22***  
(2013.01);

(Continued)

(58) **Field of Classification Search**  
None  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,704,192 B2 3/2004 Pekala  
8,057,718 B2 11/2011 Lee et al.  
(Continued)

FOREIGN PATENT DOCUMENTS

CN	1565038	A	1/2005
CN	101466784	A	6/2009

(Continued)

Primary Examiner — Lisa S Park  
(74) Attorney, Agent, or Firm — The Webb Law Firm


(57) **ABSTRACT**

The present disclosure relates to a composition for manufacturing a secondary battery separator having excellent electrical conductivity and capable of minimizing occurrence of black scum on an electrode and a secondary battery thereof. The composition for manufacturing a secondary battery separator according to the present disclosure includes a polyethylene resin and an ionic liquid lubricant composition. The ionic liquid lubricant composition includes a pore-controlling agent, an ionic liquid, and paraffinic oil.

**8 Claims, 1 Drawing Sheet**

Dec. 21, 2016 (KR) ..... 10-2016-0175884

(51) **Int. Cl.**  
***H01M 50/403*** (2021.01)  
***H01M 50/409*** (2021.01)  
(Continued)



### Conservative Example 1

## Example 2

(51) **Int. Cl.**  
*H01M 50/40* (2021.01)  
*H01M 10/04* (2006.01)  
*C08K 3/22* (2006.01)  
*C08K 3/36* (2006.01)  
*C08L 91/00* (2006.01)  
*C08J 9/00* (2006.01)  
*C08K 5/42* (2006.01)  
*C08J 5/18* (2006.01)  
*C08K 5/19* (2006.01)  
*C08K 5/50* (2006.01)  
*H01M 50/446* (2021.01)

(52) **U.S. Cl.**  
CPC ..... *C08K 3/36* (2013.01); *C08K 5/19* (2013.01); *C08K 5/42* (2013.01); *C08K 5/50* (2013.01); *C08L 91/00* (2013.01); *H01M 10/04* (2013.01); *H01M 50/40* (2021.01); *H01M 50/409* (2021.01); *H01M 50/446* (2021.01); *C08J 2201/02* (2013.01); *C08J 2323/06* (2013.01); *C08K 2003/2227* (2013.01); *C08K 2003/2231* (2013.01); *C08K 2003/2241* (2013.01); *C08K 2201/005* (2013.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS


9,214,659	B2	12/2015	Horpel et al.	
9,418,019	B2	8/2016	Lepak et al.	
2004/0260001	A1 *	12/2004	Lin .....	C08L 23/20 524/474
2006/0100323	A1 *	5/2006	Schmidt .....	C08K 5/19 524/106
2006/0228540	A1 *	10/2006	Lee .....	C08J 5/18 428/317.9
2007/0116944	A1	5/2007	Lee et al.	
2008/0138700	A1	6/2008	Horpel et al.	
2012/0178658	A1	7/2012	Tredget	
2015/0037692	A1 *	2/2015	Park .....	H01M 50/1385 429/405
2016/0064712	A1	3/2016	Hoerpel et al.	
2019/0023819	A1 *	1/2019	Schmid .....	C08K 3/04

FOREIGN PATENT DOCUMENTS

JP	2013503957	A	2/2013
KR	20030035414	A	5/2003
KR	1020060106102	A	10/2006
KR	1020070012833	A	1/2007
KR	1020080020742	A	3/2008
KR	1020150079413	A	7/2015
KR	1020160109391	A	9/2016

\* cited by examiner





Comparative Example 1

Example 2



## 1

**COMPOSITION FOR MANUFACTURING  
SECONDARY BATTERY SEPARATOR AND  
SECONDARY BATTERY INCLUDING THE  
SAME**

**CROSS-REFERENCE TO RELATED  
APPLICATIONS**

This application is the United States national phase of International Application No. PCT/KR2017/014526 filed Dec. 12, 2017, and claims priority to Korean Patent Application No. 10-2016-0175884 filed Dec. 21, 2016, the disclosures of which are hereby incorporated by reference in their entirety.

**BACKGROUND**

**1. Technical Field**

The present disclosure relates to a composition for manufacturing a secondary battery separator and a secondary battery thereof, and more particularly, to a composition for manufacturing a secondary battery separator having excellent electrical conductivity and capable of minimizing occurrence of black scum on an electrode and a secondary battery thereof.

**2. Description of the Related Art**

A process oil used in manufacturing a lead-acid battery separator, which is one of secondary batteries, is extracted in an amount of about 85% in a manufacturing process and removed, and the remaining 15% of the oil remains as it is in a final product. The remaining oil adversely affects performance of the final battery. Accordingly, the process oil used in manufacturing the lead-acid battery separator has a great influence on not only performance of the separator but also performance and stability of the lead-acid battery.

In general, naphthene oil or aromatic oil is largely used as the process oil for a lead-acid battery. However, the naphthene oil or the aromatic oil has a problem in that black scum occurs according to charging and discharging at the electrode to thereby deteriorate the performance of the battery.

**SUMMARY**

It is an object of the present disclosure to provide a composition for manufacturing a secondary battery separator capable of improving electrical conductivity and workability while minimizing occurrence of black scum, and a secondary battery thereof.

Objects of the present disclosure are not limited to the above-described objects and other objects and advantages can be appreciated by those skilled in the art from the following descriptions. Further, it will be easily appreciated that the objects and advantages of the present disclosure can be practiced by means recited in the appended claims and a combination thereof.

In accordance with one aspect of the present disclosure, a composition for manufacturing a secondary battery separator includes: a polyethylene resin and an ionic liquid lubricant composition, wherein the ionic liquid lubricant composition includes a pore-controlling agent, an ionic liquid, and paraffinic oil.

## 2

**BRIEF DESCRIPTION OF DRAWINGS**

FIG. 1 is an image showing whether black scum occurs by charging single batteries using lubricant compositions according to Comparative Example 1 and Example 2.

**DETAILED DESCRIPTION**

The above objects, features and advantages will become apparent from the detailed description with reference to the accompanying drawings. Embodiments are described in sufficient detail to enable those skilled in the art in the art to easily practice the technical idea of the present disclosure. Detailed descriptions of well known functions or configurations may be omitted in order not to unnecessarily obscure the gist of the present disclosure. Hereinafter, embodiments of the present disclosure will be described in detail with reference to the accompanying drawings. Throughout the drawings, like reference numerals refer to like elements.

Hereinafter, a composition for manufacturing a secondary battery separator according to a preferred embodiment of the present disclosure and a secondary battery thereof will be described in detail with reference to the accompanying drawings.

**Composition for Manufacturing Secondary Battery Separator**

The composition for manufacturing a secondary battery separator according to an exemplary embodiment of the present disclosure includes a polyethylene resin and an ionic liquid lubricant composition, wherein the ionic liquid lubricant composition includes a pore-controlling agent, an ionic liquid, and paraffinic oil.

More specifically, the composition for manufacturing a secondary battery separator according to an exemplary embodiment of the present disclosure includes 15 to 30 wt % of the polyethylene resin, 30 to 50 wt % of the pore-controlling agent, 0.1 to 10 wt % of the ionic liquid, and 20 to 50 wt % of the paraffin oil.

That is, the composition for manufacturing a secondary battery separator according to an exemplary embodiment of the present disclosure may minimize occurrence of black scum on an electrode by adding paraffinic oil as a main component while securing excellent electrical conductivity and workability by adding an ionic liquid having excellent electrical conductivity and silica which is a pore-control agent for controlling pores.

Here, the polyethylene resin preferably has a weight average molecular weight (Mw) of 300,000 to 700,000. When the weight average molecular weight of the polyethylene resin is less than 300,000, it is not preferable since tensile strength and puncture strength are lowered. On the contrary, when the weight average molecular weight of the polyethylene resin is more than 700,000, high cost is required and there is a problem in kneading at the time of extrusion.

It is preferable to add the polyethylene resin at a content ratio of 15 to 30 wt %, based on the total weight of the composition for manufacturing a secondary battery separator. When the added content of the polyethylene resin is less than 15 wt %, it may be difficult to manufacture a gel sheet. On the contrary, when the added content of the polyethylene resin is more than 30 wt %, there may be a problem in that porosity may remarkably decrease.

Here, the paraffinic oil includes 60% or more of paraffinic hydrocarbon in order to minimize occurrence of black scum and to increase electrical conductivity and workability. Fur-



3

ther, the paraffinic oil is more preferably a base oil including 0.03 wt % or less of sulfur (S).

It is preferable to add the pore-controlling agent at a content ratio of 30 to 50 wt %, based on the total weight of the composition for manufacturing a secondary battery separator. When the added content of the pore-controlling agent is less than 30 wt %, it is difficult to form uniform pores since the content thereof is excessively small. On the contrary, when the added content of the pore-controlling agent is more than 50 wt %, the content thereof is excessively large, and thus, solubility to oil may be lowered, which may cause problems such as haze phenomenon, precipitation, etc.


As the pore-controlling agent, at least one selected from silica, titanium dioxide, alumina, and tin oxide may be used, and among them, silica is more preferably used.

The pore-controlling agent preferably has an average particle size of 100 nm to 30  $\mu\text{m}$ . When the average particle size of the pore-controlling agent is less than 100 nm, it may be difficult to manufacture uniform porous particles, and since the particle size and the pore size become similar, it may be difficult to maintain the porous structure of the separator for a long period of time. On the contrary, when the average particle size of the pore-controlling agent is more than 30  $\mu\text{m}$ , it is not preferred since the particle size is excessively large, it is difficult to maintain a uniform pore size, and performance and durability are easily deteriorated due to the formation of big pores.

The ionic liquid is added for the purpose of improving electrical conductivity. To this end, the ionic liquid is preferably added at a content ratio of 0.1 to 10 wt %, more preferably 0.1 to 5.0 wt %, based on the total weight of the composition for manufacturing a secondary battery separator. Here, it is confirmed through experiments that when the ionic liquid is added in an excessively large content or is added in an excessively small content which is out of the above-described range, an effect of improving the electric conductivity is insignificant.

In particular, the ionic liquid according to an exemplary embodiment of the present disclosure includes a cation including any one of tetra alkyl ammonium and tetra alkyl phosphonium, and an anion including any one of sulfonate and phosphate.

Preferably, the cation included in the ionic liquid according to the exemplary embodiment of the present disclosure may have a structure represented by Chemical Formula 1 below:





in Chemical Formula 1, A means any one element of nitrogen (N), phosphorus (P), and sulfur (S), and n has a range of  $1 \leq n \leq 20$ .

In Chemical Formula 1, R1, R2, R3, and R4 are each independently selected from hydrogen, (C1-C20)alkyl, (C6-C30) aryl, (C1-C20)alkoxy, (C3-C20)cycloalkyl, (C2-C7) alkenyl, (C1-C10)alkoxycarbonyl(C1-C20)alkyl, carbonyl (C1-C20)alkyl, (C3-C20)heterocycloalkyl, and (C4-C20) heteroaryl, or R1, R2, R3, and R4 are not simultaneously hydrogen, and the alkyl, aryl, alkoxy, cycloalkyl, alkenyl, alkoxycarbonylalkyl, carbonylalkyl, heterocycloalkyl, het-

4

eroaryl of the R1, R2, R3, and R4 may be further substituted with one or more selected from (C1-C20)alkyl, halogen, nitro, cyano, hydroxy, amino, (C6-C20)aryl, (C2-C7)alkenyl, (C3-C20)cycloalkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl.


Further, the cation included in the ionic liquid according to the exemplary embodiment of the present disclosure may have any one of a structure represented by Chemical Formula 2 and a structure represented by Chemical Formula 3:



Here, the specific cation represented by Chemical Formula 2 includes tetra alkyl phosphonium and the specific cation represented by Chemical Formula 3 includes tetra alkyl ammonium.

The specific cations having the structures of Chemical Formulas 2 and 3 according to the present disclosure are designed to have specific chain lengths and structures, and are particularly capable of combining with specific anions according to the present disclosure with excellent property. Accordingly, the ionic liquid according to the present disclosure has excellent physicochemical properties such as hydrophilicity/hydrophobicity, solubility, polarity, viscosity, and density, etc.

Meanwhile, the anion included in the ionic liquid according to the exemplary embodiment of the present disclosure may have a structure represented by Chemical Formula 4 below:




in Chemical Formula 4, R1 and R2 are each independently selected from hydrogen, (C1-C20)alkyl, (C6-C30)aryl, (C1-C20)alkoxy, (C3-C20)cycloalkyl, (C2-C7)alkenyl, (C1-C10)alkoxycarbonyl(C1-C20)alkyl, carbonyl(C1-C20)alkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl, or R1 and R2 are not simultaneously hydrogen, and the alkyl, aryl, alkoxy, cycloalkyl, alkenyl, alkoxycarbonylalkyl, carbonylalkyl, heterocycloalkyl, heteroaryl of the R1 and R2 may be further substituted with one or more selected from (C1-C20)alkyl, halogen, nitro, cyano, hydroxy, amino, (C6-C20)aryl, (C2-C7)alkenyl, (C3-C20)cycloalkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl.

Further, the anion included in the ionic liquid according to the exemplary embodiment of the present disclosure may have a structure represented by Chemical Formula 5 below:



5



[Chemical Formula 5]

in Chemical Formula 5, R1 and R2 are each independently selected from hydrogen, (C1-C20)alkyl, (C6-C30) aryl, (C1-C20)alkoxy, (C3-C20)cycloalkyl, (C2-C7)alkenyl, (C1-C10)alkoxycarbonyl(C1-C20)alkyl, carbonyl(C1-C20) alkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl, or R1 and R2 are not simultaneously hydrogen, and the alkyl, aryl, alkoxy, cycloalkyl, alkenyl, alkoxycarbonylal-  
kyl, carbonylalkyl, heterocycloalkyl, heteroaryl of the R1 and R2 may be further substituted with one or more selected from (C1-C20)alkyl, halogen, nitro, cyano, hydroxy, amino, (C6-C20)aryl, (C2-C7)alkenyl, (C3-C20)cycloalkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl.

The composition for manufacturing a secondary battery separator according to the exemplary embodiment of the present disclosure as described above may have excellent electrical conductivity and remarkably reduce occurrence of black scum on the electrode by applying the paraffinic oil having excellent evaporation loss and oxidation stability unlike the naphthene oil and the aromatic oil, as a base oil, and by adding the ionic liquid having excellent electrical conductivity and the silica which is a pore-controlling agent for controlling pores at an optimum content ratio.

Hereinafter, a method of manufacturing a polyethylene porous film for a secondary battery separator according to an exemplary embodiment of the present disclosure will be briefly described.

The method of manufacturing a polyethylene porous film for a secondary battery separator according to an exemplary embodiment of the present disclosure includes melting and kneading a composition for manufacturing a secondary

6

battery separator including a polyethylene resin and an ionic liquid lubricant composition, compressing the mixture, followed by cooling to form a gel composition.

Next, the gel composition is biaxially stretched, followed by heat setting to manufacture a polyethylene porous film.

Here, the polyethylene resin preferably has a weight average molecular weight (Mw) of 300,000 to 700,000. When the weight average molecular weight of the polyethylene resin is less than 300,000, it is not preferable since tensile strength and puncture strength are lowered. On the contrary, when the weight average molecular weight of the polyethylene resin is more than 700,000, high cost is required and there is a problem in kneading at the time of extrusion.

Here, it is preferable that the composition for manufacturing a secondary battery separator includes 15 to 30 wt % of the polyethylene resin, 30 to 50 wt % of the pore-controlling agent, 0.1 to 10 wt % of the ionic liquid, and 20 to 50 wt % of the paraffinic oil.

Example

Hereinafter, constitution and function of the present disclosure will be described in more detail through preferable exemplary embodiments of the present disclosure. It is to be noted that Examples to be described below are provided merely for specifically exemplifying the present disclosure, and accordingly, the present disclosure is not limited to the following Examples.

Descriptions which are not described in the specification can be sufficiently and technically deduced by a person skilled in the technical field, and accordingly, details thereof will be omitted.

1. Preparation of Composition for Manufacturing Secondary Battery Separator

Compositions for manufacturing secondary battery separators according to Examples 1 to 23 and Comparative Examples 1 to 24 were prepared with the compositions shown in Tables 1 to 3.

TABLE 1

(Unit: wt %)								
Classification	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7	Example 8
Polyethylene resin	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
Paraffinic oil	39.5	39.0	37.0	35.0	39.9	39.0	37.0	30.0
Silica	40.0	40.0	40.0	40.0	40.0	40.0	40.0	40.0
Ionic liquid (Chemical Formulas 1 + 4)	0.5	1.0	3.0	5.0	—	—	—	—
Ionic liquid (Chemical Formulas 1 + 5)	—	—	—	—	0.1	1.0	3.0	10.0

Classification	Example 9	Example 10	Example 11	Example 12	Example 13	Example 14	Example 15
Polyethylene resin	20.0	20.0	20.0	20.0	20.0	20.0	20.0
Paraffinic oil	39.5	39.0	37.0	35.0	39.9	38.0	35.0
Silica	40.0	40.0	40.0	40.0	40.0	40.0	40.0
Ionic liquid (Chemical Formulas 2 + 4)	0.5	1.0	3.0	5.0	—	—	—
Ionic liquid (Chemical Formulas 2 + 5)	—	—	—	—	0.1	2.0	5.0

TABLE 1-continued

(Unit: wt %)								
Classification	Example 16	Example 17	Example 18	Example 19	Example 20	Example 21	Example 22	Example 23
Polyethylene resin	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
Paraffinic oil	39.5	39.0	37.0	30.0	39.9	39.5	37.0	35.0
Silica	40.0	40.0	40.0	40.0	40.0	40.0	40.0	40.0
Ionic liquid (Chemical Formulas 3 + 4)	0.5	1.0	3.0	10.0	—	—	—	
Ionic liquid (Chemical Formulas 3 + 5)	—	—	—	—	0.1	0.5	3.0	5.0

TABLE 2

(Unit: wt %)								
Classification	Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4	Comparative Example 5	Comparative Example 6	Comparative Example 7	Comparative Example 8
Polyethylene resin	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
Naphthene oil	40.0	—	39.999	—	39.999	—	39.999	—
Aromatic oil	—	40.0	—	39.999	—	39.999	—	39.999
Silica	40.0	40.0	40.0	40.0	40.0	40.0	40.0	40.0
Ionic liquid (Chemical Formulas 1 + 4)	—	—	0.001	0.001	—	—	—	—
Ionic liquid (Chemical Formulas 1 + 5)	—	—	—	—	0.001	0.001	—	—
Ionic liquid (Chemical Formulas 2 + 4)					—	—	0.001	0.001

Classification	Comparative Example 9	Comparative Example 10	Comparative Example 11	Comparative Example 12	Comparative Example 13	Comparative Example 14	Comparative Example 15	Comparative Example 16
Polyethylene resin	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
Naphthene oil	39.999	—	39.999	—	28.0	—	28.0	—
Aromatic oil	—	39.999	—	39.999	—	25.0	—	25.0
Silica	40.0	40.0	40.0	40.0	40.0	40.0	40.0	40.0
Ionic liquid (Chemical Formulas 2 + 5)	0.001	0.001	—	—	—	—	—	—
Ionic liquid (Chemical Formulas 3 + 4)	—	—	0.001	0.001	—	—	—	—
Ionic liquid (Chemical Formulas 1 + 5)	—	—	—	—	12.0	15.0	—	—





Evaporation test	Evaporation loss (%)	0.8	0.9	0.9	0.8	0.9	0.9	0.9	0.8
	Color change	None	None	None	None	None	None	None	None
	Electrical resistance (mΩ · dm <sup>2</sup> ): ER	1.02	1.03	1.00	1.02	1.03	1.00	1.00	1.02
	Workability	Good	Good	Good	Good	Good	Good	Good	Good
	Charging of single battery (5 A, 100 Hr)	No scum	No scum	No scum	Scum occurred	No scum	No scum	No scum	Scum occurred
Classification		Example 9	Example 10	Example 11	Example 12	Example 13	Example 14	Example 15	Example 16
Evaporation test	Sulfuric acid color test	Good discoloration	Good discoloration	Good discoloration	Good discoloration	Good discoloration	Good discoloration	Good discoloration	Good discoloration
	Evaporation loss (%)	0.9	0.9	0.9	0.8	0.9	0.9	0.9	0.8
	Color change	None	None	None	None	None	None	None	None
	Electrical resistance (mΩ · dm <sup>2</sup> ): ER	1.03	1.03	1.00	1.02	1.03	1.03	1.00	1.02
	Workability	Good	Good	Good	Good	Good	Good	Good	Good
Charging of single battery(5 A, 100 Hr)		No scum	No scum	No scum	Scum occurred	No scum	No scum	No scum	Scum occurred
Classification		Example 17	Example 18	Example 19	Example 20	Example 21	Example 22	Example 23	
Evaporation test	Sulfuric acid color test	Good discoloration	Good discoloration	Good discoloration	Good discoloration	Good discoloration	Good discoloration	Good discoloration	Good discoloration
	Evaporation loss (%)	0.9	0.9	0.9	0.8	0.9	0.9	0.9	0.9
	Color change	None	None	None	None	None	None	None	None
	Electrical resistance (mΩ · dm <sup>2</sup> ): ER	1.03	1.00	1.00	1.02	1.03	1.03	1.03	1.00
	Workability	Good	Good	Good	Good	Good	Good	Good	Good
Charging of single battery (5 A, 100 Hr)		No scum	No scum	No scum	Scum occurred	No scum	No scum	No scum	No scum

Classification		Comparative Example 1	Comparative Example 2	Comparative Example 3	Comparative Example 4	Comparative Example 5	Comparative Example 6	Comparative Example 7	Comparative Example 8
Evaporation test	Sulfuric acid color test	Discoloration occurred	Discoloration occurred	Discoloration occurred	Discoloration occurred	Discoloration occurred	Discoloration occurred	Discoloration occurred	Discoloration occurred
	Evaporation loss (%)	1.8	1.7	1.5	1.8	1.7	1.5	1.8	1.8
	Color change	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
	Electrical resistance (mΩ · dm <sup>2</sup> ): ER	1.24	1.26	1.25	1.25	1.24	1.26	1.25	1.25

TABLE 5-continued

Workability Charging of single battery (5 A, 100 Hr)		Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred
Classification		Comparative Example 9	Comparative Example 10	Comparative Example 11	Comparative Example 12	Comparative Example 13	Comparative Example 14	Comparative Example 15	Comparative Example 16
Evaporation test	Sulfuric acid color test	Discolor- ation occurred	Discolor- ation occurred	Discolor- ation occurred	Discolor- ation occurred	Discolor- ation occurred	Discoloration occurred	Discoloration occurred	Discoloration occurred
	Evaporation loss (%)	1.7	1.5	1.8	1.8	1.7	1.5	1.8	1.8
	Color change	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
	Electrical resistance (mΩ · dm <sup>2</sup> ): ER	1.24	1.26	1.25	1.25	1.24	1.26	1.25	1.25
	Workability Charging of single battery (5 A, 100 Hr)	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred
Classification		Comparative Example 17	Comparative Example 18	Comparative Example 19	Comparative Example 20	Comparative Example 21	Comparative Example 22	Comparative Example 23	Comparative Example 24
Evaporation test	Sulfuric acid color test	Discolor- ation occurred	Discolor- ation occurred	Discolor- ation occurred	Good discoloration	Good discoloration	Good discoloration	Good discoloration	Good discoloration
	Evaporation loss (%)	1.7	1.5	1.8	1.9	0.9	0.9	0.9	0.9
	Color change	None	None	None	None	None	None	None	None
	Electrical resistance (mΩ · dm <sup>2</sup> ): ER	1.24	1.26	1.25	1.25	1.24	1.26	1.25	1.26
	Workability Charging of single battery (5 A, 100 Hr)	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred	Good Scum occurred

As shown in Tables 1 to 5, it was confirmed that as compared to Comparative Examples 1 to 20 using naphthene oil and aromatic oil, Examples 1 to 23 showed excellent evaporation loss and oxidation stability, and significantly reduced electric resistance to have excellent electrical conductivity.

Further, it was confirmed that in Comparative Examples 21 to 24 in which even though the paraffinic oil was used, the added content of the ionic liquid was out of the range suggested by the present disclosure, the evaporation loss and the oxidation stability were excellent, but the electric resistance was significantly high as 1.24 to 1.26 mΩ·dm<sup>2</sup>, and thus the electrical conductivity was not good.

Meanwhile, FIG. 1 is an image showing whether black scum occurs by charging the single batteries using the lubricant compositions according to Comparative Example 1 and Example 2.

As shown in FIG. 1, it could be confirmed that when the lubricant composition according to Comparative Example 1 was used, the black scum severely occurred. On the other hand, it could be confirmed that when the lubricant composition according to Example 1 was used, the black scum did not occur.

The composition for manufacturing a secondary battery separator according to the present disclosure and the secondary battery thereof may have excellent electrical conductivity and remarkably reduce the occurrence of black scum on the electrode by applying the paraffinic oil having excellent evaporation loss and oxidation stability unlike the naphthene oil and the aromatic oil, as a base oil, and further, by adding the ionic liquid having excellent electrical conductivity and the silica which is a pore-controlling agent for controlling pores at an optimum content ratio.

The present disclosure described above may be variously substituted, altered, and modified by those skilled in the art to which the present disclosure pertains without departing from the scope and spirit of the present disclosure. Therefore, the present disclosure is not limited to the above-mentioned exemplary embodiments and the accompanying drawings.


What is claimed is:

1. A composition for manufacturing a polyethylene porous film of a secondary battery separator including:  
15 to 30 wt % of a polyethylene resin, 30 to 50 wt % of a pore-controlling agent, 0.1 to 10 wt % of an ionic liquid, and 20 to 50 wt % of paraffinic oil, wherein the pore-controlling agent includes silica, and



## 15

wherein the polyethylene resin has a weight average molecular weight (M<sub>w</sub>) of 300,000 to 700,000,  
 wherein the ionic liquid includes a cation including any one of tetra alkyl ammonium and tetra alkyl phosphonium, and an anion including any one of sulfonate and phosphate,  
 wherein the anion has a structure represented by Chemical Formula 4:



in Chemical Formula 4, R1 and R2 are each independently selected from hydrogen, (C1-C20)alkyl, (C6-C30)aryl, (C1-C20)alkoxy, (C3-C20)cycloalkyl, (C2-C7)alkenyl, (C1-C10)alkoxycarbonyl(C1-C20)alkyl, carbonyl(C1-C20)alkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl, or

R1 and R2 are not simultaneously hydrogen, and the alkyl, aryl, alkoxy, cycloalkyl, alkenyl, alkoxycarbonylalkyl, carbonylalkyl, heterocycloalkyl, heteroaryl of the R1 and R2 are further substituted with one or more selected from (C1-C20)alkyl halogen, nitro, cyano, hydroxy, amino, (C6-C20)aryl, (C2-C7)alkenyl, (C3-C20)cycloalkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl.


2. The composition of claim 1, wherein the pore-controlling agent has an average particle size of 100 nm to 30 μm.

3. The composition of claim 1, wherein the paraffinic oil is a base oil including 0.03 wt % or less of sulfur (S).

4. The composition of claim 1, wherein the paraffinic oil includes 60% or more of paraffinic hydrocarbon.

5. The composition of claim 1, wherein the ionic liquid is added at a content of 0.1 to 5.0 wt %.

6. The composition of claim 1, wherein the cation has a structure represented by Chemical Formula 1 below:  
 [Chemical Formula 1]



in Chemical Formula 1, A is any one element of nitrogen (N), phosphorus (P), and sulfur (S), and

in Chemical Formula 1, 1 ≤ n ≤ 20,



wherein R1, R2, R3, and R4 are each independently selected from hydrogen, (C1-C20)alkyl, (C6-C30)aryl, (C1-C20)alkoxy, (C3-C20)cycloalkyl, (C2-C7)alkenyl, (C1-C10)alkoxycarbonyl(C1-C20)alkyl, carbonyl(C1-C20)alkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl, or

R1, R2, R3, and R4 are not simultaneously hydrogen, and the alkyl, aryl, alkoxy, cycloalkyl, alkenyl, alkoxycarbonylalkyl, carbonylalkyl, heterocycloalkyl, heteroaryl

## 16

of the R1, R2, R3, and R4 are further substituted with one or more selected from (C1-C20)alkyl, halogen, nitro, cyano, hydroxy, amino, (C6-C20)aryl, (C2-C7)alkenyl, (C3-C20)cycloalkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl.

7. The composition of claim 1, wherein the cation has any one of a structure represented by Chemical Formula 2 and a structure represented by Chemical Formula 3:




8. A composition for manufacturing a polyethylene porous film of a secondary battery separator including:

15 to 30 wt % of a polyethylene resin, 30 to 50 wt % of a pore-controlling agent, 0.1 to 10 wt % of an ionic liquid, and 20 to 50 wt % of paraffinic oil,

wherein the pore-controlling agent includes silica,

wherein the polyethylene resin has a weight average molecular weight (M<sub>w</sub>) of 300,000 to 700,000,

wherein the ionic liquid includes a cation including any one of tetra alkyl ammonium and tetra alkyl phosphonium, and an anion including any one of sulfonate and phosphate, wherein the anion has a structure represented by Chemical Formula 5:



in Chemical Formula 5, R1 and R2 are each independently selected from hydrogen, (C1-C20)alkyl, (C6-C30)aryl, (C1-C20)alkoxy, (C3-C20)cycloalkyl, (C2-C7)alkenyl, (C1-C10)alkoxycarbonyl(C1-C20)alkyl, carbonyl(C1-C20)alkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl, or

R1 and R2 are not simultaneously hydrogen, and the alkyl, aryl, alkoxy, cycloalkyl, alkenyl, alkoxycarbonylalkyl, carbonylalkyl, heterocycloalkyl, heteroaryl of the R1 and R2 are further substituted with one or more selected from (C1-C20)alkyl, halogen, nitro, cyano, hydroxy, amino, (C6-C20)aryl, (C2-C7)alkenyl, (C3-C20)cycloalkyl, (C3-C20)heterocycloalkyl, and (C4-C20)heteroaryl.

\* \* \* \* \*

UNITED STATES PATENT AND TRADEMARK OFFICE  
**CERTIFICATE OF CORRECTION**

PATENT NO. : 11,462,802 B2  
APPLICATION NO. : 16/470287  
DATED : October 4, 2022  
INVENTOR(S) : Hyeung-Jin Lee et al.


Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:


In the Specification

Column 15, Line 29, Claim 1, delete “(C1-C20)alkyl” and insert -- (C1-C20)alkyl, --

Column 15, Lines 45-50, Claim 6, delete “



”



and insert --

--

Signed and Sealed this  
Twenty-ninth Day of November, 2022

*Katherine Kelly Vidal*

Katherine Kelly Vidal  
Director of the United States Patent and Trademark Office



UNITED STATES PATENT AND TRADEMARK OFFICE  
**CERTIFICATE OF CORRECTION**

PATENT NO. : 11,462,802 B2  
APPLICATION NO. : 16/470287  
DATED : October 4, 2022  
INVENTOR(S) : Hyeung-Jin Lee et al.

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

On the Title Page

Under (71) Applicant:

Please add the second applicant name “SK ENMOVE CO., LTD.”; and

Under (73) Assignee:

Please add the second assignee name “SK ENMOVE CO., LTD., Seoul (KR)”.

Signed and Sealed this  
Fifteenth Day of July, 2025



Coke Morgan Stewart  
*Acting Director of the United States Patent and Trademark Office*