



US011476239B2

(12) **United States Patent**
Higginson et al.

(10) **Patent No.:** **US 11,476,239 B2**
(45) **Date of Patent:** ***Oct. 18, 2022**

(54) **LIGHT EMITTING STRUCTURE**

(71) Applicant: **Apple Inc.**, Cupertino, CA (US)

(72) Inventors: **John A. Higginson**, Santa Clara, CA (US); **Andreas Bibi**, Los Altos, CA (US); **Hsin-Hua Hu**, Los Altos, CA (US)

(73) Assignee: **Apple Inc.**, Cupertino, CA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 84 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **17/072,240**

(22) Filed: **Oct. 16, 2020**

(65) **Prior Publication Data**

US 2021/0050337 A1 Feb. 18, 2021

Related U.S. Application Data

(60) Continuation of application No. 16/688,646, filed on Nov. 19, 2019, now Pat. No. 10,833,058, which is a (Continued)

(51) **Int. Cl.**

H01L 25/16 (2006.01)
H01L 33/44 (2010.01)

(Continued)

(52) **U.S. Cl.**

CPC **H01L 25/167** (2013.01); **H01L 23/3171** (2013.01); **H01L 25/0753** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC H01L 25/167; H01L 23/3171; H01L 25/0753; H01L 25/50; H01L 27/1214; H01L 27/1248; H01L 27/1262; H01L 33/005; H01L 33/06; H01L 33/42; H01L 33/44; H01L 33/54; H01L 33/62;
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,592,358 A 1/1997 Shamouilian et al.
5,839,187 A 11/1998 Sato et al.
(Continued)

FOREIGN PATENT DOCUMENTS

JP 3406207 5/1999
WO 2011123285 10/2011

OTHER PUBLICATIONS

Asano, Kazutoshi, et al., "Fundamental Study of an Electrostatic Chuck for Silicon Wafer Handling" IEEE Transactions on Industry Applications, vol. 38, No. 3, May/Jun. 2002, pp. 840-845.
(Continued)


Primary Examiner — Victor A Mandala

(74) *Attorney, Agent, or Firm* — Aikin & Gallant, LLP

(57) **ABSTRACT**

A method and structure for receiving a micro device on a receiving substrate are disclosed. A micro device such as a micro LED device is punched-through a passivation layer covering a conductive layer on the receiving substrate, and the passivation layer is hardened. In an embodiment the micro LED device is punched-through a B-staged thermoset material. In an embodiment the micro LED device is punched-through a thermoplastic material.

15 Claims, 14 Drawing Sheets



Related U.S. Application Data

continuation of application No. 16/219,896, filed on Dec. 13, 2018, now Pat. No. 10,510,736, which is a continuation of application No. 15/911,693, filed on Mar. 5, 2018, now Pat. No. 10,192,858, which is a continuation of application No. 15/405,042, filed on Jan. 12, 2017, now Pat. No. 9,911,722, which is a continuation of application No. 15/008,372, filed on Jan. 27, 2016, now Pat. No. 9,589,944, which is a continuation of application No. 14/563,763, filed on Dec. 8, 2014, now Pat. No. 9,263,627, which is a division of application No. 13/562,184, filed on Jul. 30, 2012, now Pat. No. 8,933,433.

(51) **Int. Cl.**

H01L 23/31 (2006.01)
H01L 33/06 (2010.01)
H01L 33/00 (2010.01)
H01L 33/42 (2010.01)
H01L 33/62 (2010.01)
H01L 25/075 (2006.01)
H01L 27/12 (2006.01)
H01L 25/00 (2006.01)
H01L 33/54 (2010.01)
H01L 21/56 (2006.01)

(52) **U.S. Cl.**

CPC *H01L 25/50* (2013.01); *H01L 27/1214* (2013.01); *H01L 27/1248* (2013.01); *H01L 27/1262* (2013.01); *H01L 33/005* (2013.01); *H01L 33/06* (2013.01); *H01L 33/42* (2013.01); *H01L 33/44* (2013.01); *H01L 33/54* (2013.01); *H01L 33/62* (2013.01); *H01L 21/56* (2013.01); *H01L 2924/0002* (2013.01); *H01L 2933/005* (2013.01); *H01L 2933/0016* (2013.01); *H01L 2933/0025* (2013.01); *H01L 2933/0033* (2013.01); *H01L 2933/0066* (2013.01)

(58) **Field of Classification Search**

CPC H01L 21/56; H01L 2924/0002; H01L 2933/0016; H01L 2933/0025; H01L 2933/0033; H01L 2933/005; H01L 2933/0066

See application file for complete search history.

(56)

References Cited

U.S. PATENT DOCUMENTS

5,851,664 A 12/1998 Bennett et al.
 5,888,847 A 3/1999 Rosoker et al.
 5,903,428 A 5/1999 Grimard et al.
 5,996,218 A 12/1999 Shamouilian et al.
 6,071,795 A 6/2000 Cheung et al.
 6,335,263 B1 1/2002 Cheung et al.
 6,403,985 B1 6/2002 Fan et al.
 6,420,242 B1 7/2002 Cheung et al.
 6,521,511 B1 2/2003 Inoue et al.
 6,558,109 B2 5/2003 Gibbel
 6,613,610 B2 9/2003 Iwafuchi et al.
 6,629,553 B2 10/2003 Odashima et al.
 6,670,038 B2 12/2003 Sun et al.
 6,878,607 B2 4/2005 Inoue et al.
 7,015,055 B2 3/2006 Oohata et al.
 7,033,842 B2 4/2006 Haii et al.
 7,148,127 B2 12/2006 Oohata et al.
 7,199,397 B2 4/2007 Huang et al.
 7,208,337 B2 4/2007 Eisert et al.
 7,353,596 B2 4/2008 Shida et al.
 7,358,158 B2 4/2008 Aihara et al.
 7,472,472 B2 1/2009 Takanami

7,585,703 B2 9/2009 Matsumura et al.
 7,723,764 B2 5/2010 Oohata et al.
 7,795,629 B2 9/2010 Watanabe et al.
 7,797,820 B2 9/2010 Shida et al.
 7,838,410 B2 11/2010 Hirao et al.
 7,880,184 B2 2/2011 Iwafuchi et al.
 7,884,543 B2 2/2011 Doi
 7,888,690 B2 2/2011 Iwafuchi et al.
 7,906,787 B2 3/2011 Kang
 7,910,945 B2 3/2011 Donofrio et al.
 7,927,976 B2 4/2011 Menard
 7,928,465 B2 4/2011 Lee et al.
 7,972,875 B2 7/2011 Rogers et al.
 7,999,454 B2 8/2011 Winters et al.
 8,023,248 B2 9/2011 Yonekura et al.
 8,497,143 B2 7/2013 Han
 8,497,512 B2 7/2013 Nakamura et al.
 8,933,433 B2 1/2015 Higginson et al.
 9,263,627 B2 2/2016 Higginson et al.
 9,466,621 B2 10/2016 Chou
 9,589,944 B2 3/2017 Higginson et al.
 9,911,722 B2 3/2018 Higginson et al.
 10,192,858 B2 1/2019 Higginson et al.
 10,510,736 B2* 12/2019 Higginson H01L 27/1248
 11,107,721 B2* 8/2021 Or-Bach H01L 27/1108
 2001/0029088 A1 10/2001 Odajima et al.
 2002/0076848 A1 6/2002 Spooner et al.
 2003/0040142 A1 2/2003 Lin et al.
 2003/0177633 A1 9/2003 Haji et al.
 2004/0129946 A1* 7/2004 Nagai F21K 9/00
 257/E25.02
 2005/0017256 A1 1/2005 Slater et al.
 2005/0233546 A1 10/2005 Oohata et al.
 2006/0169993 A1 8/2006 Fan et al.
 2008/0163481 A1 7/2008 Shida et al.
 2009/0140282 A1 6/2009 Wu et al.
 2009/0230383 A1 9/2009 Meng et al.
 2009/0314991 A1 12/2009 Cho et al.
 2010/0188794 A1 7/2010 Park et al.
 2010/0219432 A1* 9/2010 Kim H01L 27/156
 257/E33.056
 2010/0248484 A1 9/2010 Bower et al.
 2011/0003410 A1 1/2011 Tsay et al.
 2011/0242083 A1 10/2011 Chiou
 2011/0284867 A1 11/2011 Tran et al.
 2012/0018746 A1 1/2012 Hsieh
 2012/0134065 A1 5/2012 Furuya et al.
 2012/0153312 A1 6/2012 Chou
 2012/0168776 A1 7/2012 Nakamura et al.
 2012/0326188 A1 12/2012 Han
 2013/0126081 A1 5/2013 Hu et al.
 2013/0126891 A1 5/2013 Bibl et al.
 2013/0187179 A1 7/2013 Tan et al.
 2013/0273695 A1 10/2013 Menard et al.
 2013/0285086 A1 10/2013 Hu et al.
 2013/0316529 A1 11/2013 Golda et al.
 2014/0159064 A1 6/2014 Sakariva et al.
 2017/0125391 A1 5/2017 Higginson et al.

OTHER PUBLICATIONS

Bower, C.A., et al., "Active-Matrix OLEO Display Backplanes Using Transfer-Printed Microscale Integrated Circuits", IEEE, 2010 Electronic Components and Technology Conference, pp. 1339-1343.
 "Characteristics of electrostatic Chuck(ESC)" Advanced Materials Research Group, New Technology Research Laboratory, 2000, pp. 51-53 accessed at http://www.socnb.com/report/ptech_e/2000p51_e.pdf.
 Guerre, Roland, et al., "Selective Transfer Technology for Microdevice Distribution" Journal of Microelectromechanical Systems, vol. 17, No. 1, Feb. 2008, pp. 157-165.
 Han, Min-Koo, "AM backplane for AMOLED" Proc. of ASID '06, 8-12, Oct., New Delhi, pp. 53-58.
 Harris, Jonathan H., "Sintered Aluminum Nitride Ceramics for High-Power Electronic Applications" Journal of the Minerals, Metals and Materials Society, vol. 50, No. 6, Jun. 1998, p. 56.

(56)

References Cited

OTHER PUBLICATIONS

Horwitz, Chris M., "Electrostatic Chucks: Frequently Asked Questions" ElectroGrip, 2006, 10 pgs, accessed at www.electrogrip.com.
 Hossick-Schott, Joachim, "Prospects for the ultimate energy density of oxide-based capacitor anodes" Medtronic Energy and Components Center, Proceedings of CARTS Europe, Barcelona, Spain, 2007, 10 pgs.

Lee, San Youl, et al., "Wafer-level fabrication of GAN-based vertical light-emitting diodes using a multi-functional bonding material system" *Semicond. Sci. Technol.* 24, 2009, 4 pgs.

"Major Research Thrust: Epitaxial Layer Transfer by Laser Lift-off" Purdue University, Heterogeneous Integration Research Group, accessed at https://engineering.purdue.edu/HetInt/project_epitaxial_layer_transfer_llo.htm, last updated Aug. 2003.

Mei, Zequn, et al., "Low Temperature Solders" *Hewlett-Packard Journal*, Article 10, Aug. 1996, pp. 1-10.

Mercado, Lei, L., et al., "A Mechanical Approach to Overcome RF MEMS Switch Stiction Problem" 2003 Electronic Components and Technology Conference, pp. 377-384.

Miskys, Claudio R., et al., "Freestanding GaN-substrates and devices" *phys. Stat. sol.* © 0, 6,2003, pp. 1627-1650.

"Principles of Electrostatic Chucks: 1—Techniques for High Performance Grip and Release" *ElectroGrip, Principles1 rev3* May 2006, 2 pgs, accessed at www.electrogrip.com.

Steigerwald, Daniel, et al., "III-V Nitride Semiconductors for High-Performance Blue and Green Light-Emitting Devices" article appears in *journal JOM* 49 (9) 1997, pp. 18-23. Article accessed Nov. 2, 2011 at <http://www.tms.org/pubs/journals/jom/9709/setigerwald-9709.html>, 12 pgs.

Widas, Robert, "Electrostatic Substrate Clamping for Next Generation Semiconductor Devices" Apr. 21, 1999, 4 pgs.

Furman, et al., "A High Concentration Photovoltaic Module Utilizing Micro-Transfer Printing and Surface Mount Technology" Photovoltaic Specialists Conference (PVSC), 2010 35th IEEE, 2010, pp. 000475-000480.

Hekmatshoar, et al., "A novel TFT-OLED integration for OLEO-independent pixel programming in amorphous-Si AMOLED pixels" *Journal of the SID* 16/1, 2008, pp. 183-188.

Sarma, et al., "Active Matrix OLEO Using 150oC. a-Si TFT Backplane Built on Flexible Plastic Substrate" Presented at SPIE Symp. on Aerospace/Defense Sensing, Orlando, FL, Apr. 2003, and to be published in *SPIE Proc.* vol. 5080, paper 24 (2003), 12 pages.

Tsujimura, et al., "4.3 Passive-Matrix OLEO Display" *OLEO Displays: Fundamentals and Applications*, 2012, pp. 91-109, John Wiley & Sons, Inc., Hoboken, New Jersey, USA.

Yoo, et al., "Flexible GaN LED on a Polyimide Substrate for Display Applications" *Quantum Sensing and Nanophotonic Devices IX*, edited by Manijeh Razeghi, et al., 2012, *Proc. of SPIE* vol. 8268, pp. 82681Y-1 to 82681Y-6.

Long, K., et al., "Active-Matrix Amorphous-Silicon TFT Arrays at 180 ° Con Clear Plastic and Glass Substrates for Organic Light-Emitting Displays," *IEEE Transactions on Electron Devices*, vol. 53, No. 8, Aug. 2006, pp. 1789-1796.

Seong, Ryu-Gi, et al., "Flexible AMOLED Backplane Technology Using Pentacene IFT's," *Proc. Int. Symp. Super-Functionality Organic Devices IPAP Conf. Series* 6, pp. 146-149.

* cited by examiner




FIG. 1A




FIG. 1B




FIG. 2




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D







FIG. 3E






FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14A




FIG. 14B




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22

LIGHT EMITTING STRUCTURE

RELATED APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 16/688,646, filed Nov. 19, 2019, which is a continuation of U.S. patent application Ser. No. 16/219,896, filed Dec. 13, 2018, now U.S. Pat. No. 10,510,736, which is a continuation of U.S. patent application Ser. No. 15/911,693, filed Mar. 5, 2018, now U.S. Pat. No. 10,192,858, which is a continuation of U.S. patent application Ser. No. 15/405,042, filed Jan. 12, 2017, now U.S. Pat. No. 9,911,722, which is a continuation of U.S. patent application Ser. No. 15/008,372, filed Jan. 27, 2016, now U.S. Pat. No. 9,589,944, which is a continuation of U.S. patent application Ser. No. 14/563,763, filed Dec. 8, 2014, now U.S. Pat. No. 9,263,627, which is a divisional application of U.S. patent application Ser. No. 13/562,184 filed Jul. 30, 2012, now U.S. Pat. No. 8,933,433, which is incorporated herein by reference.

BACKGROUND

Field

The present invention relates to micro devices. More particularly embodiments of the present invention relate to a method and structure for receiving a micro device on a receiving substrate.

Background Information

Integration and packaging issues are one of the main obstacles for the commercialization of micro devices such as radio frequency (RF) microelectromechanical systems (MEMS) microswitches, light-emitting diode (LED) display and lighting systems, MEMS, or quartz-based oscillators.

Traditional technologies for transferring of devices include transfer by wafer bonding from a transfer wafer to a receiving wafer. One such implementation is “direct printing” involving one bonding step of an array of devices from a transfer wafer to a receiving wafer, followed by removal of the transfer wafer. Another such implementation is “transfer printing” involving two bonding/de-bonding steps. In transfer printing a transfer wafer may pick up an array of devices from a donor wafer, and then bond the array of devices to a receiving wafer, followed by removal of the transfer wafer. Some printing process variations have been developed where a device can be selectively bonded and de-bonded during the transfer process. In both traditional and variations of the direct printing and transfer printing technologies, the transfer wafer is de-bonded from a device after bonding the device to the receiving wafer. In addition, the entire transfer wafer with the array of devices is involved in the transfer process.

Other technologies for transferring of devices include transfer printing with elastomeric stamps. In one such implementation an array of elastomeric stamps with posts matching the pitch of devices on a source wafer are brought into intimate contact with the surface of the devices on the source wafer and bonded with van der Waals interaction. The array of devices can then be picked up from the source wafer, transferred to a receiving substrate, and released onto the receiving substrate.

SUMMARY OF THE INVENTION

A method and structure for receiving a micro device on a receiving substrate are described. In an embodiment, a

structure includes a substrate, a conductive layer on the substrate, and a micro LED device on the conductive layer. The micro LED device includes a micro p-n diode, a metallization stack between the micro p-n diode and the conductive layer, and a quantum well layer within the micro p-n diode. A bonding layer may optionally be formed between the metallization stack and the conductive layer. For example, the bonding layer can be a material such as indium, gold, silver, molybdenum, tin, aluminum, silicon, and alloys thereof. A thermoplastic or thermoset passivation layer laterally surrounds the quantum well layer of the micro LED device. A second conductive layer is formed on a top surface of the micro LED device. For example, the two conductive layers can be electrodes such as anode or cathode, or anode or cathode lines. A barrier layer can be formed on the second conductive layer, and a cover can be formed over the micro LED device. The cover may be conformal to a topography of the micro LED device or be a rigid cover plate. A black matrix material can be formed around the micro LED device and underneath the cover.

In an embodiment, the receiving substrate is a lighting or display substrate, and the structure can be configured to emit light from a top surface, through the substrate and a bottom surface, or both. In an embodiment, the passivation layer is transparent in the visible wavelength range, e.g. 380 nm-750 nm. For example, benzocyclobutene (BCB) and epoxy are suitable transparent thermoset materials. The first and/or second conductive layer may also be formed of a transparent material such as indium-tin-oxide (ITO) and poly(3,4-ethylenedioxythiophene (PEDOT). The conductive layer(s) can also include nanoparticles such as silver, gold, ITO and indium-zinc-oxide (IZO). In an embodiment, one of the conductive layers is reflective to the visible wavelength range. For example, the second conductive layer may be reflective for a bottom emitting structure. Alternatively, or in addition, a layer reflective to the visible wavelength range can be formed over the micro LED device for a bottom emitting structure.

In an embodiment, the micro LED device is integrated into a pixel of a display substrate. For example, the micro LED device can be integrated into a subpixel of the pixel, where the conductive layer and second conductive layer are the anode and cathode, or vice-versa. A cover can be formed over the subpixel with a black matrix material around the micro LED device in the subpixel, and underneath the cover. In an embodiment, the micro LED device emits a primarily blue, red, or green light. An arrangement of red, blue, and green micro LED devices may be arranged in separate subpixels of an RGB pixel. In an embodiment, the micro LED device is integrated into an active matrix pixel display in which each subpixel includes working circuitry such as a switching transistor, driving transistor, and storage capacitor. For example, the switching and driving transistors can be thin film transistors. In an embodiment, the micro LED device is integrated into a passive matrix pixel display.

In an embodiment, a method of transferring a micro device to a receiving substrate includes picking up a micro device from a carrier substrate with a transfer head and placing the micro device on a conductive layer formed on the receiving substrate by punching the micro device through a passivation layer covering the conductive layer. The micro device may be picked up from the carrier substrate with a variety of manners, including applying a voltage to the transfer head to generate an electrostatic pick up pressure on the micro device. The micro device is then released from the transfer head and the passivation layer is hardened so that the hardened passivation layer laterally

surrounds the micro device. A variety of micro devices can be transferred in accordance with embodiments of the invention, such as, a diode, LED, transistor, integrated circuit (IC), or microelectromechanical system (MEMS). In an embodiment, the micro device is a micro LED device including a micro p-n diode, a metallization stack between the micro p-n diode and the conductive layer, and a quantum well layer within the micro p-n diode where the hardened passivation layer laterally surrounds the quantum well layer of the micro LED device.

In an embodiment, the micro device is punched through a B-staged thermoset passivation layer which is then hardened by curing the B-staged thermoset passivation layer, for example by the application of heat or ultraviolet (UV) energy. The B-staged thermoset passivation layer may first be formed by directly applying the B-staged thermoset passivation layer, or first applying an A-staged thermoset passivation layer on the receiving substrate and covering the conductive layer, followed by partially curing the A-staged thermoset passivation layer to form the B-staged thermoset passivation layer. The B-staged thermoset passivation layer may also be heated during punch-through, which may allow the B-staged thermoset passivation layer to soften or flow to aid in the punch-through. In an embodiment, the micro device is punched through a thermoplastic passivation layer heated above its glass transition temperature, followed by cooling below its glass transition temperature to harden the thermoplastic passivation layer. For example, the thermoplastic passivation layer is heated to a temperature above the glass transition temperature but below the melting temperature of the thermoplastic passivation layer.

In an embodiment, a second conductive layer may be formed over the micro device and passivation layer. For example, the second conductive layer can be formed by deposition and etching a material such as indium-tin-oxide (ITO) or indium-zinc-oxide (IZO). The second conductive layer can also be formed by ink jet printing a material such as poly(3,4-ethylenedioxythiophene) (PEDOT) or a material containing nanoparticles such as of silver, gold, ITO, and IZO nanoparticles. A barrier layer can be formed over the second conductive layer to protect against oxygen and moisture absorption, for example. Suitable deposition techniques include, but are not limited to, atomic layer deposition (ALD) and ion sputtering.

The A-staged thermoset passivation layer can be deposited using a variety of suitable techniques such as spin coating, screen printing, ink jet printing, dispensing and spray coating, followed by the selective removal of a portion to expose an electrode line, for example by laser scribing or photolithography. Alternatively, a patterned A-staged thermoset passivation layer can be selectively applied so that the opening exposing the electrode line is included.

In an embodiment, placing the micro device on the conductive layer includes placing the micro device on a bonding layer formed on the conductive layer. For example, the bonding layer may include a material such as indium, gold, silver, molybdenum, tin, aluminum, silicon, and alloys thereof. The method may additionally include heating the structure to diffuse the bonding layer into the metal stack, or heating the structure to diffuse the bonding into a second bonding layer formed on the metal stack. Heating can be from a backside of the receiving substrate or from the transfer head, for example.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A is a cross-sectional side view illustration of a receiving substrate in accordance with an embodiment of the invention.

FIG. 1B is a cross-sectional side view illustration of a receiving substrate in accordance with an embodiment of the invention.

FIG. 2 is a cross-sectional side view illustration of a patterned passivation layer on a receiving substrate in accordance with an embodiment of the invention.

FIGS. 3A-3C are cross-sectional side view illustrations of an array of transfer heads picking up an array of micro LED devices from a carrier substrate in accordance with an embodiment of the invention.

FIG. 3D is a cross-sectional side view illustration of a transfer head holding a micro LED device over a receiving substrate with a patterned passivation layer in accordance with an embodiment of the invention.

FIG. 3E is a cross-sectional side view illustration of an array of transfer heads holding an array micro LED devices over a receiving substrate with a patterned passivation layer in accordance with an embodiment of the invention.

FIG. 4A is a cross-sectional side view illustration of a micro LED device punched through a passivation layer on a receiving substrate in accordance with an embodiment of the invention.

FIG. 4B is a cross-sectional side view illustration of an array of micro LED devices punched through a passivation layer on a receiving substrate in accordance with an embodiment of the invention.

FIG. 5 is a cross-sectional side view illustration of a conductive layer and barrier layer formed over a micro LED device on a receiving substrate in accordance with an embodiment of the invention.

FIG. 6 is a cross-sectional side view illustration of a cathode line formed directly over a micro LED device on a receiving substrate in accordance with an embodiment of the invention.

FIG. 7 is a cross-sectional side view illustration of a cathode line on a receiving substrate in accordance with an embodiment of the invention.

FIG. 8 is a cross-sectional side view illustration of cover layer formed over a micro LED device on a receiving substrate in accordance with an embodiment of the invention.

FIG. 9 is a cross-sectional side view illustration of a reflective layer and cover layer formed over a micro LED device on a receiving substrate in accordance with an embodiment of the invention.

FIG. 10 is a cross-sectional side view illustration of a black matrix layer and cover layer formed over a micro LED device on a receiving substrate in accordance with an embodiment of the invention.

FIGS. 11-12 are cross-sectional side view illustrations of attaching a cover plate over a micro LED device on a receiving substrate in accordance with an embodiment of the invention.

FIGS. 13-14A are cross-sectional side view illustrations of attaching a cover plate and black matrix over a micro LED device on a receiving substrate in accordance with an embodiment of the invention.

FIG. 14B is a cross-sectional side view illustration of a cover plate and black matrix over an array of micro LED devices on a receiving substrate in accordance with an embodiment of the invention.

FIGS. 15-17 are schematic illustrations of passive matrix display layouts in accordance with embodiments of the invention.

FIG. 18 is a circuit diagram of a passive matrix display in accordance with an embodiment of the invention.

5

FIG. 19 is a schematic illustration of a subpixel in an active matrix display in accordance with embodiments of the invention.

FIG. 20 is a circuit diagram of a subpixel in an active matrix display in accordance with an embodiment of the invention.

FIG. 21 is a circuit diagram of an active matrix display in accordance with an embodiment of the invention.

FIG. 22 is a schematic illustration of a display device in accordance with an embodiment of the invention.

DETAILED DESCRIPTION OF THE INVENTION

Embodiments of the present invention describe a method and structure for receiving a micro device or an array of micro devices such as micro light emitting diode (LED) devices on a receiving substrate. For example, the receiving substrate may be, but is not limited to, a display substrate, a lighting substrate, a substrate with functional devices such as transistors or integrated circuits (ICs), or a substrate with metal redistribution lines. While embodiments of the present invention are described with specific regard to micro LED devices comprising p-n diodes, it is to be appreciated that embodiments of the invention are not so limited and that certain embodiments may also be applicable to other micro semiconductor devices which are designed in such a way so as to perform in a controlled fashion a predetermined electronic function (e.g. diode, transistor, integrated circuit) or photonic function (LED, laser).

In various embodiments, description is made with reference to figures. However, certain embodiments may be practiced without one or more of these specific details, or in combination with other known methods and configurations. In the following description, numerous specific details are set forth, such as specific configurations, dimensions and processes, etc., in order to provide a thorough understanding of the present invention. In other instances, well-known semiconductor processes and manufacturing techniques have not been described in particular detail in order to not unnecessarily obscure the present invention. Reference throughout this specification to "one embodiment," "an embodiment" or the like means that a particular feature, structure, configuration, or characteristic described in connection with the embodiment is included in at least one embodiment of the invention. Thus, the appearances of the phrase "in one embodiment," "in an embodiment" or the like in various places throughout this specification are not necessarily referring to the same embodiment of the invention. Furthermore, the particular features, structures, configurations, or characteristics may be combined in any suitable manner in one or more embodiments.

The terms "spanning," "over," "to," "between" and "on" as used herein may refer to a relative position of one layer with respect to other layers. One layer "spanning," "over" or "on" another layer or bonded "to" another layer may be directly in contact with the other layer or may have one or more intervening layers. One layer "between" layers may be directly in contact with the layers or may have one or more intervening layers.

The terms "micro" device, "micro" p-n diode or "micro" LED device as used herein may refer to the descriptive size of certain devices or structures in accordance with embodiments of the invention. As used herein, the terms "micro" devices or structures are meant to refer to the scale of 1 to 100 μm . However, it is to be appreciated that embodiments of the present invention are not necessarily so limited, and

6

that certain aspects of the embodiments may be applicable to larger, and possibly smaller size scales.

In one aspect, embodiments of the invention describe a manner for mass transfer of an array of pre-fabricated micro devices with an array of transfer heads. For example, the pre-fabricated micro devices may have a specific functionality such as, but not limited to, a LED for light-emission, silicon IC for logic and memory, and gallium arsenide (GaAs) circuits for radio frequency (RF) communications.

In some embodiments, arrays of micro LED devices which are poised for pick up are described as having a 10 μm by 10 μm pitch, or 5 μm by 5 μm pitch. At these densities a 6 inch substrate, for example, can accommodate approximately 165 million micro LED devices with a 10 μm by 10 μm pitch, or approximately 660 million micro LED devices with a 5 μm by 5 μm pitch. A transfer tool including an array of transfer heads matching an integer multiple of the pitch of the corresponding array of micro LED devices can be used to pick up and transfer the array of micro LED devices to a receiving substrate. In this manner, it is possible to integrate and assemble micro LED devices into heterogeneously integrated systems, including substrates of any size ranging from micro displays to large area displays, and at high transfer rates. For example, a 1 cm by 1 cm array of micro device transfer heads can pick up and transfer more than 100,000 micro devices, with larger arrays of micro device transfer heads being capable of transferring more micro devices.

In another aspect, embodiments of the invention describe a method and structure for receiving a micro device or an array of micro devices on a receiving substrate. In an embodiment, a micro device or array of micro devices is transferred from a carrier substrate to a receiving substrate with a transfer head, or an array of transfer heads, which may be operated in accordance with electrostatic principles. Without being limited to a particular theory, embodiments of the invention utilize transfer heads and head arrays which operate in accordance with principles of electrostatic grippers, using the attraction of opposite charges to pick up micro devices. In accordance with embodiments of the present invention, a pull-in voltage is applied to a transfer head in order to generate a grip pressure on a micro device and pick up the micro device. In an embodiment, a grip pressure of greater than 1 atmosphere is generated. For example, each transfer head may generate a grip pressure of 2 atmospheres or greater, or even 20 atmospheres or greater without shorting due to dielectric breakdown of the transfer heads.

In one embodiment, placing the micro device or array of micro devices on the receiving substrate is performed with a punch-through technique in which the micro devices are placed on the receiving substrate by punching through a B-staged thermoset passivation layer. A final curing operation is then performed which may be associated with some amount of shrinking of the thermoset passivation layer that further retains the transferred array of micro devices on the receiving substrate during subsequent handling and processing operations. The term B-staged is known in the art and refers to an intermediate stage in a thermosetting material in which the material initially softens when heated but may not entirely fuse or dissolve. A B-staged material will cure upon continued heating. The term A-staged is also known in the art and refers to an early stage in a thermosetting material in which the material is fusible and still soluble in certain liquids.

In one embodiment, placing the micro device or array of micro devices on the receiving substrate is performed with

a punch-through technique in which the micro devices are placed on the receiving substrate by punching through a thermoplastic passivation layer heated above the glass transition temperature (T_g) of the thermoplastic during punch-through. In an embodiment, the thermoplastic passivation layer is heated above the T_g and below the melting temperature (T_m) of the thermoplastic during punch-through. Following punch-through, the thermoplastic passivation layer is cooled, and may further retain the transferred array of micro devices on the receiving substrate during subsequent handling and processing operations.

Furthermore, where an active surface exists on a micro device, the passivation layer (thermoset or thermoplastic) can passivate the active surface. For example, where the micro device is a micro LED device, a quantum well layer may be exposed or contained near side surfaces of the micro LED device. In this manner, the passivation layer may laterally surround and insulate the quantum well layer as result of the punch-through operation.

In another aspect, embodiments of the invention describe a manner of combining the performance, efficiency, and reliability of wafer based electronics with the high yield, low cost, and mixed materials of thin film electronics to provide cost effect, energy efficient, high performance devices. In accordance with embodiments of the invention, micro arrays of semiconductor LED devices fabricated in accordance with wafer based processing can be transferred to existing and new thin film substrate technologies. Due to the small micro size and high efficiency of the micro LED devices significant power savings of 20 times or more can be realized compared to existing technologies. In an embodiment, a micro LED device is transferred to an active or passive matrix organic LED (OLED) backplane rather than forming a typical organic light emitting layer. In this manner, a finished display device can be fabricated that exhibits significant power savings, increased battery life, and reduced peak pixel current compared to traditional OLED display technologies.

FIG. 1A is a cross-sectional side view illustration of a receiving substrate in accordance with an embodiment of the invention. As illustrated, a first conductive layer **102** is formed on a substrate **100**. An electrode line **106** may also be optionally formed on substrate **100**. Substrate **100** may be a variety of substrates such as, but not limited to, a display substrate, a lighting substrate, a substrate with functional devices such as transistors or integrated circuits (ICs), or a substrate with metal redistribution lines. Depending upon the particular application, substrate **100** may be opaque, transparent, or semi-transparent to the visible wavelength (e.g. 380-750 nm wavelength), and substrate **100** may be rigid or flexible. For example, substrate **100** may be formed of glass or a polymer such as polyethylene terephthalate (PET), polyethylene naphthalate (PEN), polycarbonate (PC), polyethersulphone (PES), aromatic fluorine-containing polyarylates (PAR), polycyclic olefin (PCO), and polyimide (PI). Depending upon the particular application, either or both of conductive layer **102** and electrode line **106** may be opaque, transparent, or semi-transparent to the visible wavelength. Exemplary transparent conductive materials include amorphous silicon, transparent conductive oxides (TCO) such as indium-tin-oxide (ITO) and indium-zinc-oxide (IZO), carbon nanotube film, or a transparent conducting polymer such as poly(3,4-ethylenedioxythiophene) (PEDOT), polyaniline, polyacetylene, polypyrrole, and polythiophene. In an embodiment conductive layer **102** is approximately 100 nm-200 nm thick ITO. In an embodiment, the conductive layer **102** includes nanoparticles such

as silver, gold, aluminum, molybdenum, titanium, tungsten, ITO, and IZO. The conductive layer **102** or electrode line **106** may also be reflective to the visible wavelength. In an embodiment, a conductive layer **102** or electrode line **106** comprises a reflective metallic film such as aluminum, molybdenum, titanium, titanium-tungsten, silver, or gold, or alloys thereof.

In an embodiment, conductive layer **102** functions as an electrode or electrode line. In an embodiment, conductive layer **102** functions as an anode or anode line in the completed device, and electrode line **106** functions as a cathode line in the completed device. It is to be appreciated that conductive layer **102** or electrode line **106** are described as being related to the anode and cathode, respectively, in the following description, however, the application can be reversed in other embodiments with conductive layer **102** and electrode line **106** being related to the cathode and anode, respectively.

A bonding layer **104** may optionally be formed over the conductive layer **102** to facilitate bonding of the micro device as described in further detail below. In an embodiment, bonding layer **104** includes a material such as indium, gold, silver, molybdenum, tin, aluminum, silicon, or an alloy thereof and is approximately 0.1 μm to 0.5 μm thick. An electrode line **106** may also be optionally formed on substrate **100**. The electrode line **106** may be formed of the same or different material from conductive layer **102**. In an embodiment, electrode line **106** is a cathode line out the completed device.

FIG. 1B is a cross-sectional side view illustration of a receiving substrate in accordance with an embodiment of the invention. In the particular embodiment illustrated, the receiving substrate **100** may be an active matrix organic LED (AMOLED) backplane prior to the formation of the light emitting organic layer. For example, the AMOLED backplane can include a working circuitry **110**, such as a traditional 2T1C (two transistors, one capacitor) circuitry including a switching transistor, a driving transistor, and a storage capacitor. It is to be appreciated that the 2T1C circuitry is meant to be exemplary, and that other types of circuitry or modifications of the traditional 2T1C circuitry are contemplated in accordance with embodiments of the invention. For example, more complicated circuits can be used to compensate for current distribution to the driver transistor and the micro device, or for their instabilities. A passivation layer **108** may optionally be formed on the substrate **100** between the conductive layer **102** (e.g. anode) and electrode line out **106** (e.g. cathode line out). Passivation layer **108** may be formed of a variety of materials such as, but not limited to, silicon oxide (SiO_2), silicon nitride (SiN_x), poly(methyl methacrylate) (PMMA), benzocyclobutene (BCB), polyimide, and polyester.

It is to be appreciated that embodiments of the invention are compatible with a number of different substrates, and that the substrates described with regard to FIGS. 1A-1B are meant to be exemplary and not limiting. In interest of conciseness and to not obscure embodiments of the invention, the following description is made with reference to the embodiment of the substrate illustrated in FIG. 1.

FIG. 2 is a cross-sectional side view illustration of a patterned passivation layer **112** on a receiving substrate **100** in accordance with an embodiment of the invention. In the particular embodiment illustrated, the patterned passivation layer **112** is patterned to expose the electrode line **106** (e.g. a cathode line out).

In an embodiment, the patterned passivation layer **112** is a B-staged thermoset. The B-staged thermoset passivation

layer **112** may be formed by directly applying the B-staged thermoset passivation layer, or by first applying an A-staged thermoset passivation layer on the receiving substrate **100** and covering the conductive layer **102**, and optionally electrode line **106**, followed by driving off the solvents and partially curing the A-staged thermoset passivation layer to form the B-staged thermoset passivation layer. The A-staged or B-staged thermoset passivation layer may be formed by a variety of techniques including spin coating, screen printing, ink jet printing, dispensing, and spray coating, and may be formed of a variety of materials including, but not limited to benzocyclobutene (BCB) and epoxy. The rheology of the B-staged thermoset layer can be controlled by the amount of cross-linking in the B-staged thermoset to allow for punch-through of the micro device without excessive flow. An opening exposing the electrode line **106** may be formed during the A-stage application or B-stage application, such as with a screen printing or ink jet printing application, or alternatively when B-staged, where the opening may be formed by laser scribing or lithography. In an embodiment, a B-staged thermoset passivation layer is formed on the receiving substrate **100** with vacuum lamination.

In an embodiment, the patterned passivation layer **112** is a thermoplastic. The thermoplastic passivation layer **112** may be formed by a variety of techniques including spin coating, screen printing, ink jet printing, dispensing, and spray coating, and may be formed of a variety of materials in which the rheology of the thermoplastic between the T_g and T_m of the thermoplastic is sufficient to allow for punch-through of the micro device without excessive flow. An opening exposing the electrode line **106** may be formed during application of the patterned thermoplastic passivation layer, such as with a screen printing or ink jet printing application, or alternatively after application, where the opening may be formed by laser scribing or lithography. In an embodiment, a thermoplastic passivation layer is formed on the receiving substrate **100** with vacuum lamination.

FIGS. 3A-3C are cross-sectional side view illustrations of an array of transfer heads picking up an array of micro devices from a carrier substrate in accordance with an embodiment of the invention. Referring to FIG. 3A, an array of transfer heads **302** supported by a transfer head substrate **300** are positioned over an array of micro devices **400** supported on a carrier substrate **200**. A heater **306** and heat distribution plate **304** may optionally be attached to the transfer head substrate **300**. A heater **204** and heat distribution plate **202** may optionally be attached to the carrier substrate **200**. The array of micro devices **400** are contacted with the array of transfer heads **302**, as illustrated in FIG. 3B, and picked up from the carrier substrate **200** as illustrated in FIG. 3C.

In an embodiment, the array of micro devices **400** are picked up with an array of transfer heads **302** operating in accordance with electrostatic principles. In an embodiment, a bonding layer (illustrated in further detail in FIG. 3A) may be formed between the array of micro devices **400** and the carrier substrate **200**. In such an embodiment, heat may be applied to the bonding layer from either or both heaters **204**, **306** prior to or during pick up to create a phase change in the bonding layer. For example, the bonding layer may be heated above a liquidus temperature of the bonding layer to create a phase change from solid to liquid state. In an embodiment, the bonding layer has a liquidus temperature of 350°C . or below, or more specifically 200°C . or below.

FIG. 3D is a cross-sectional side view illustration of a transfer head **302** holding a micro LED device **400** over a receiving substrate **100** with a patterned passivation layer

112 in accordance with an embodiment of the invention. In the embodiment illustrated, the transfer head **302** is supported by a transfer head substrate **300**. As described above, a heater **306** and heat distribution plate **304** may optionally be attached to the transfer head substrate to apply heat to the transfer head **302**. A heater **152** and heat distribution plate **150** may also, or alternatively, optionally be used to transfer heat to the conductive layer **102** and optional bonding layer **104** on the receiving substrate **100** and/or optional bonding layer **410** on a micro device **400** described below.

Still referring to FIG. 3D, a close-up view of an exemplary micro LED device **400** is illustrated in accordance with an embodiment. It is to be appreciated, that the specific micro LED device **400** illustrated is exemplary and that embodiments of the invention are not limited. For example, embodiments of the invention may also be applicable to other micro LED devices such as, but not limited to, the micro LED devices in U.S. patent application Ser. No. 13/372,222, U.S. patent application Ser. No. 13/436,260, and U.S. patent application Ser. No. 13/458,932, all of which are incorporated herein by reference. Embodiments of the invention may also be applicable to other micro devices including, but not limited to, other micro semiconductor devices which are designed in such a way so as to perform in a controlled fashion a predetermined electronic function (e.g. diode, transistor, integrated circuit) or photonic function (LED, laser).

In the particular embodiment illustrated, the micro LED device **400** includes a micro p-n diode **450** and a metallization stack **420**. A bonding layer **410** may optionally be formed below the metallization stack **420**, with the metallization stack **420** between the micro p-n diode **450** and the bonding layer **410**. In an embodiment, the micro p-n diode **450** includes a top n-doped layer **414**, one or more quantum well layers **416**, and a lower p-doped layer **418**. The micro p-n diodes can be fabricated with straight sidewalls or tapered sidewalls. In certain embodiments, the micro p-n diodes **450** possess outwardly tapered sidewalls **453** (from top to bottom). In certain embodiments, the micro p-n diodes **450** possess inwardly tapered sidewall (from top to bottom). The metallization stack **420** may include one or more layers. For example, the metallization stack **420** may include an electrode layer and a barrier layer between the electrode layer and the optional bonding layer. The metallization stack **420** may be transparent to the visible wavelength range (e.g. 380 nm-750 nm) or opaque. The metallization stack **420** may optionally include a reflective layer, such as a silver layer. The micro p-n diode and metallization stack may each have a top surface, a bottom surface and sidewalls. In an embodiment, the bottom surface **451** of the micro p-n diode **450** is wider than the top surface **452** of the micro p-n diode, and the sidewalls **453** are tapered outwardly from top to bottom. The top surface of the micro p-n diode **450** may be wider than the bottom surface of the p-n diode, or approximately the same width. In an embodiment, the bottom surface **451** of the micro p-n diode **450** is wider than the top surface of the metallization stack **420**. The bottom surface of the micro p-n diode may also be approximately the same width as the top surface of the metallization stack.

A conformal dielectric barrier layer **460** may optionally be formed over the micro p-n diode **450** and other exposed surfaces. The conformal dielectric barrier layer **460** may be thinner than the micro p-n diode **450**, metallization stack **420** and the optional bonding layer **410** so that the conformal dielectric barrier layer **260** forms an outline of the topography it is formed on. In an embodiment, the micro p-n diode **450** is several microns thick, such as $3\ \mu\text{m}$ or $5\ \mu\text{m}$, the

metallization stack **420** is 0.1 μm -2 μm thick, and the optional bonding layer **410** is 0.1 μm -1 μm thick. In an embodiment, the conformal dielectric barrier layer **460** is approximately 50-600 angstroms thick aluminum oxide (Al_2O_3). The conformal dielectric barrier layer **460** may protect against charge arcing between adjacent micro p-n diodes during the pick up process, and thereby protect against adjacent micro p-n diodes from sticking together during the pick up process. The conformal dielectric barrier layer **460** may also protect the sidewalls **453**, quantum well layer **416** and bottom surface **451**, of the micro p-n diodes from contamination which could affect the integrity of the micro p-n diodes. For example, the conformal dielectric barrier layer **460** can function as a physical barrier to wicking of the bonding layer material **410** up the sidewalls and quantum layer **416** of the micro p-n diodes **450**. The conformal dielectric barrier layer **260** may also insulate the micro p-n diodes **450** once placed on the receiving substrate. In an embodiment, the conformal dielectric barrier layer **460** span sidewalls **453** of the micro p-n diode, and may cover the quantum well layer **416** in the micro p-n diode. The conformal dielectric barrier layer may also partially span the bottom surface **451** of the micro p-n diode, as well as span sidewalls of the metallization stack **420**. In some embodiments, the conformal dielectric barrier layer also spans sidewalls of a patterned bonding layer **410**. A contact opening may be formed in the conformal dielectric barrier layer **460** exposing the top surface **452** of the micro p-n diode. The contact opening **462** may have a smaller width than the top surface **452** of the micro p-n diode and the conformal dielectric barrier layer **460** forms a lip around the edges of the top surface **452** of the micro p-n diode. Alternatively the contact opening **462** may have a slightly larger width than the top surface of the micro p-n diode or approximately the same width as the top surface of the micro p-n diode. In an embodiment, a conformal dielectric barrier layer **260** is not present, and the passivation layer **112** is used to insulate the micro p-n diodes **450** once placed on the receiving substrate.

FIG. 3E is a cross-sectional side view illustration of an array of transfer heads holding an array micro LED devices **400** over a receiving substrate with a patterned passivation layer **112** in accordance with an embodiment of the invention. FIG. 3E is substantially similar to the structure illustrated in FIG. 3D with the primary difference being the illustration of the transfer of an array of micro devices as opposed to a single micro device within the array of micro devices.

FIG. 4A is a cross-sectional side view illustration of a micro LED device punched through a passivation layer on a receiving substrate in accordance with an embodiment of the invention. Punch-through may be accomplished by physically driving the micro LED device **400** through the passivation layer **112** with the transfer head **302** until contacting the conductive layer **102** or optional bonding layer **104** on the receiving substrate **100**. As illustrated, the micro LED device **400** may be punched-through the passivation layer **112** so that passivation layer **112** laterally surrounds the quantum well layer **416**. The passivation layer **112** may also be thinner than the height of the micro LED device **400** so that electrical contact can be made with the top surface **452** of the micro LED device.

Punch-through may also be aided by the application of heat through the transfer head **302** or receiving substrate **100**. In an embodiment where the passivation layer **112** is a UV curable or thermally curable B-staged thermoset, the application of heat can melt or soften the B-staged thermoset

passivation layer **112** to aid in the punch-through. Thus, the amount of applied pressure, heat, and amount of cross-linking in the B-staged thermoset can be controlled to achieve punch-through. Application of UV energy after punch-through can then be used to cure the thermoset passivation layer **112** where the thermoset passivation layer **112** is UV curable. In an embodiment where the passivation layer **112** is a thermally curable B-staged thermoset, continued application of heat after punch-through can then be used to cure the thermoset passivation layer **112**. In an embodiment, where the passivation layer **112** is a thermoplastic material the thermoplastic passivation layer **112** is heated above the Tg, and more specifically, above the Tg and below the Tm of the thermoplastic material during punch-through. Thus, the amount of pressure and heat applied to the thermoplastic material can be controlled to achieve punch-through.

In certain embodiments, the application of heat during punch-through can also result in reflowing of one or both of the optional bonding layers **410**, **104** or diffusion between layers to assist with bonding. In addition, reflowing of any of the bonding layers **410**, **104** can result in forming a new bonding layer with a higher melting temperature. In one embodiment, the application of heat not only aids with punch-through of layer **112**, the application of heat also causes at least partial reflow and solidification of the bonding layer(s) **410**, **104**. For example, the application of heat can lead to the formation of an alloy having a higher Tm than that of the reflowed or diffused layer(s).

In an embodiment, the punch-through and release of the micro devices on the receiving substrate is performed in ten seconds or less, or more particularly one second or less. Where heat is applied, it is possible to rapidly reflow either of the optional bonding layer(s) **410**, **104** to assist in bonding and to soften or initially melt the passivation layer **112**, which can be a thermal or UV curable B-staged thermoset, or a thermoplastic. Following the release of the array of micro devices from the array of transfer heads, the passivation layer **112** is hardened to secure the array of micro devices on the receiving substrate. Where the passivation layer **112** is a thermoplastic, hardening is effected by allowing the thermoplastic material to cool. Where the passivation layer **112** is a B-staged thermoset, the passivation layer can be final cured through the application of UV energy or heat for an order of minutes or hours to effect curing. In an embodiment, heat can be applied from below the receiving substrate **100** with heater **152** and/or heat distribution plate **150**. Heat can also be applied from above the receiving substrate **100**. UV energy can also be applied from above or below the receiving substrate. In an embodiment, the receiving substrate is transferred to a curing chamber to effect curing following the release of the array of micro devices.

FIG. 4B is a cross-sectional side view illustration of an array of micro LED devices punched through a passivation layer on a receiving substrate in accordance with an embodiment of the invention. FIG. 4B is substantially similar to the structure illustrated in FIG. 4A with the primary difference being the illustration of the transfer of an array of micro devices as opposed to a single micro device within the array of micro devices.

Referring now to FIG. 5, following hardening of the punched-through passivation layer **112** a second conductive layer **114** and optional barrier layer **116** may be formed over the micro LED device **400** and receiving substrate **100** in accordance with an embodiment of the invention. In an embodiment, the second conductive layer **114** is a transparent material such as amorphous silicon, transparent conduc-

tive oxides (TCO) such as indium-tin-oxide (ITO) and indium-zinc-oxide (IZO), carbon nanotube film, or a transparent conducting polymer such as poly(3,4-ethylenedioxythiophene) (PEDOT), polyaniline, polyacetylene, polypyrrole, and polythiophene. In an embodiment, the second 5 conductive layer **114** includes nanoparticles such as silver, gold, aluminum, molybdenum, titanium, tungsten, ITO, and indium-zinc-oxide (IZO). The second conductive layer **114** may also be reflective to the visible wavelength. In an embodiment, a reflective conductive layer **114** comprises a 10 metallic film such as aluminum, molybdenum, titanium, titanium-tungsten, silver, or gold, or alloys thereof. In an embodiment, an optional barrier layer **116** is formed over the second conductive layer **114**. For example, the optional barrier layer **116** can act as a barrier to oxygen or moisture 15 absorption by any underlying layers during subsequent processing. In an embodiment, barrier layer **116** is formed from an inorganic material (e.g. SiO_xN_y , SiN_x , Al_2O_3 , etc.) for oxygen and moisture protection. Barrier layer **116** may also be transparent or opaque to the visible wavelength, and may be rigid or flexible. In an embodiment, the barrier layer **116** is Al_2O_3 , and may be deposited by a variety of methods including atomic layer deposition (ALD).

Referring now to FIG. 6 and FIG. 7, alternative embodiments are illustrated for forming an electrode line **118** (e.g. a cathode line out) where one is not already formed. Similar to electrode line **106**, the electrode line **118** may function 20 may be associated with an anode or cathode. In an embodiment, electrode line **118** is a cathode line out. Electrode line **118** may be formed of any of the materials already described with regard to layers **102**, **106**, and **114**. FIG. 6 is an illustration of an embodiment in which an electrode line **118** is formed on conductive layer **114** directly over the micro LED device **400**. In another embodiment electrode line **118** is formed directly on the micro LED device **400**. FIG. 7 is 25 an illustration of an embodiment in which electrode line **118** is formed on a trace portion of second conductive layer **114**. In both embodiments, an opening may be formed in the optional barrier layer **116**, if present, in order to expose the second conductive layer **114** prior to formation of the electrode line **118**.

FIG. 8 is a cross-sectional side view illustration of cover layer **120** formed over the exemplary structure of FIG. 5 in accordance with an embodiment. In the particular embodiment illustrated the cover layer **120** is conformal to the 30 topography of the micro LED device **400** and overall structure over substrate **100**. Cover layer **120** may function to provide both chemical passivation and physical protection to the underlying structure. Cover layer **120** may also be flexible, and may be transparent. Cover layer **120** may be formed of a variety of materials such as, but not limited to, silicon oxide (SiO_2), silicon nitride (SiN_x), poly(methyl methacrylate) (PMMA), benzocyclobutene (BCB), polyimide, and polyester.

As described up to this point, the layers on which the micro LED device **400** are supported and covered by can be 35 transparent or opaque to the visible wavelength. Accordingly, the structure illustrated in FIG. 8 can emit light through either the top cover **120**, through the bottom substrate **100**, or both depending on the selection of materials and type of substrate.

FIG. 9 is a cross-sectional side view illustration an embodiment in which a reflective layer **122** is formed over the micro LED device **400** prior to formation of the top 40 cover **120** to produce a bottom emitting structure. For example, reflective layer **122** can be evaporated or sputtered metallic material such as aluminum. In this manner, light

emitting upward from the micro LED device **400** is reflected back through the bottom substrate **100**. In such an embodiment, the metallic stack **420** and/or optional bonding layers **410/104** may be substantially transparent to the visible 45 wavelength. Transparency can be controlled by the selection of materials and/or thickness of the layers.

FIG. 10 is a cross-sectional side view illustration of an embodiment in which a black matrix layer **124** is formed around a micro LED device prior to formation of the top 50 cover **120** in order to block light emission, and to separate light emission from the micro LED device **400** from one or more adjacent micro LED devices **400**. In such an embodiment, the structure illustrated in FIG. 10 can emit light through either the top cover **120**, through the bottom substrate **100**, or both depending on the selection of materials and type of substrate. Black matrix **124** can be formed from 55 a method that is appropriate based upon the material used. For example, black matrix **124** can be applied using ink jet printing, sputter and etching, spin coating with lift-off, or a printing method. Exemplary black matrix materials include carbon, metal films (e.g. nickel, aluminum, molybdenum, and alloys thereof), metal oxide films (e.g. chromium oxide), and metal nitride films (e.g. chromium nitride), organic resins, glass pastes, and resins or pastes including a black pigment or silver particles.

While cover **120** has been described as being conformal to the topography of the underlying structure, a separate cover plate can also be secured to the structure in combination with cover **120**, or in the alternative to cover **120** in accordance with embodiments of the invention. FIGS. 11-12 60 are cross-sectional side view illustrations of attaching a cover plate **126** over a micro LED device **400** on a receiving substrate **100** in accordance with an embodiment of the invention. As illustrated, cover plate **126** can be attached to the substrate **100** with an adhesive **128** and may surround a plurality of pixels on the substrate **100**. For example, adhesive **128** can be, but is not limited to, a frit glass seal or epoxy formed along the edge of the cover with a dispenser or screen printing. Cover **126** can be provided in place of or 65 in combination with cover **120**. In an embodiment, cover plate **126** is transparent glass or plastic.

FIGS. 13-14A are cross-sectional side view illustrations of attaching a cover plate **126** over a micro LED device **400** on a receiving substrate **100** in accordance with an embodiment of the invention. FIGS. 13-14A are similar to FIGS. 11-12 with one difference being that a black matrix **124** is attached to the cover plate **126** prior to attaching the cover plate **126** to the substrate **100**. FIG. 14B is a cross-sectional side view illustration of a cover plate **126** and black matrix 70 **124** over an array of micro LED devices **400** on a receiving substrate in accordance with an embodiment of the invention. As illustrated, cover plate **126** is attached to the substrate **100** with an adhesive **128** surrounding a plurality of pixels on the substrate. In the embodiment illustrated, the black matrix **124** is patterned on the cover plate **126** and includes a plurality of openings corresponding to locations directly above the locations of the micro LED devices **400** on substrate **100**.

FIGS. 15-17 are schematic illustrations of passive matrix display layouts in accordance with embodiments of the invention. As illustrated, a pixel can include an array of subpixels. In the particular embodiments illustrated, each pixel comprises three subpixels, one with a red emitting LED device **400R**, one with a blue emitting LED device 75 **400B**, and one with a green emitting LED device **400G**. For example, a red emitting LED device **400R** (e.g. 620-750 nm wavelength) can include a micro p-n diode layer formed of

15

a semiconductor material such as aluminum gallium arsenide (AlGaAs), gallium arsenide phosphide (GaAsP), aluminum gallium indium phosphide (AlGaInP), and gallium phosphide (GaP). For example, a green emitting LED device **400G** (e.g. 495-570 nm wavelength) can include a micro p-n diode layer formed of a semiconductor material such as indium gallium nitride (InGaN), gallium nitride (GaN), gallium phosphide (GaP), aluminum gallium indium phosphide (AlGaInP), and aluminum gallium phosphide (AlGaP). For example, a blue emitting LED device **400B** (e.g. 450-495 nm wavelength) can include a micro p-n diode layer formed of a semiconductor material such as gallium nitride (GaN), indium gallium nitride (InGaN), and zinc selenide (ZnSe).

While the following pixel and subpixel arrangements are described with regard to a red-green-blue (RGB) subpixel arrangement, it is to be appreciated that the RGB arrangement is exemplary and that embodiments are not so limited. Other subpixel arrangements such as BGR or red-green-blue-yellow (RGBY), red-green-blue-yellow-cyan (RGBYC) can be utilized, as well subpixel rendering configurations in accordance with embodiments of the invention.

Referring now to FIG. 15, in the embodiment illustrated the LED devices **400R**, **400G**, **400B** are placed on the first conductive layer **102** (e.g. anode line out). The LED devices are connected to the electrode line **106**, **118** (e.g. cathode line out) by second conductive layer **114**, for example as described above with regard to FIG. 5 or FIG. 7. Referring to FIG. 16, in the embodiment illustrated the LED devices **400R**, **400G**, **400B** are placed on an electrode trace **103** connected with the first conductive layer **102**. Similar to FIG. 15, the LED devices are connected to the electrode line **106**, **118** by second conductive layer **114**, for example as described above with regard to FIG. 5 or FIG. 7. Referring to FIG. 17, in the embodiment illustrated, the LED devices **400R**, **400G**, **400B** are placed on the first conductive layer **102**, and the electrode line **118** is formed over the LED devices, for example as described above with regard to FIG. 6.

A circuit diagram of a passive matrix display **1800** for any of the arrangements in FIGS. 15-17 is illustrated in FIG. 18 in accordance with an embodiment of the invention. As illustrated, the anode lines out **102** are oriented horizontally, the cathode lines out **106**, **118** are oriented vertically, and the LED devices are placed between the lines. The cathode lines out **106**, **118** function as data lines, and are driven by one or more data drivers. The anode lines out **102** function as scan lines, and are driven by one or more scan drivers.

FIG. 19 is a schematic illustration of a subpixel in an active matrix display in accordance with embodiments of the invention. More particularly, FIG. 19 illustrates an embodiment of a micro LED device **400** placed in an aperture **160** over the anode **102** (e.g. ITO layer) of an AMOLED backplane subpixel including working circuitry such as a traditional 2T1C (two transistors, one capacitor) circuitry including a switching transistor **T1**, a driving transistor **T2**, and a storage capacitor **Cs**. It is to be appreciated that the 2T1C circuitry is meant to be exemplary, and that other types of circuitry or modifications of the traditional 2T1C circuitry are contemplated in accordance with embodiments of the invention.

As illustrated, the micro LED device **400** may occupy less than the available space of the aperture **160** depending upon application. Table 1 below includes calculations of diagonal pixel size based upon pixel density, along with minimum subpixel size estimation with an RGB pixel layout in accor-

16

dance with embodiments of the invention. In these examples, minimum subpixel size is approximated as being one third of the diagonal pixel size. It is to be appreciated that this number represents a minimum estimation, and is dependent upon the subpixel arrangement and landscape of the working circuitry.

TABLE 1

Pixel Density (per inch)	Diagonal Pixel Size (μm)	Minimum Subpixel Size (μm)
500	51	17
300	85	28
200	127	42
100	254	85

Where a display has a pixel density of 100 pixels per diagonal inch (e.g. a computer monitor), this corresponds to a diagonal pixel size of 254 microns. With an RGB pixel layout, a subpixel illustrated in FIG. 19 is estimated to have a diagonal size of at least 85 microns. Where the display has a pixel density of 300 pixels per diagonal inch (e.g. a mobile phone, tablet) this corresponds to a diagonal pixel size of 85 microns. With an RGB pixel layout, a subpixel illustrated in FIG. 19 is estimated to have a diagonal size of at least 28 microns. Thus, as shown in Table 1 displays including substrates receiving micro LED devices in accordance with embodiments of the invention may be scalable down to pixel densities greater than the maximum resolution of a perfect human eye, which is estimated as being somewhere between 300 and 500 pixels per inch.

FIG. 20 is a circuit diagram of a subpixel with 2T1C circuitry in an active matrix display in accordance with an embodiment of the invention. In such an embodiment, the circuit includes a switching transistor **T1**, a driving transistor **T2**, a storage capacitor **Cs** and a micro LED device **400**. The transistors **T1**, **T2** can be any type of transistor such as a thin film transistor. For example, the switching transistor **T1** can be a n-type metal-oxide semiconductor (NMOS) transistor, and the driving transistor **T2** can be a p-type metal-oxide semiconductor (PMOS) transistor. The switching transistor **T1** has a gate electrode connected to a scan line V_{select} and a first source/drain electrode connected to a data line V_{data} . The driving transistor **T2** has a gate electrode connected to a second source/drain electrode of the switching transistor **T1** and a first source/drain electrode connected to a power source V_{dd} . The storage capacitor **Cs** is connected between the gate electrode of the driving transistor **T2** and the first source/drain electrode of the driving transistor **T2**. The micro LED device **400** has an anode electrode connected to a second source/drain electrode of the driving transistor **T2** and a cathode electrode connected to a ground V_{ss} .

In operation, a voltage level scan signal turns on the switching transistor **T1**, which enables the data signal to charge the storage capacitor **Cs**. The voltage potential that stores within the storage capacitor **Cs** determines the magnitude of the current flowing through the driving transistor **T2**, so that the micro LED device **400** can emit light based on the current. It is to be appreciated that the 2T1C circuitry is meant to be exemplary, and that other types of circuitry or modifications of the traditional 2T1C circuitry are contemplated in accordance with embodiments of the invention. For example, more complicated circuits can be used to compensate for current distribution to the driver transistor and the micro device, or for their instabilities.

FIG. 21 is a circuit diagram of a pixel in an active matrix display **2100** in accordance with an embodiment of the

17

invention. As illustrated, the scan lines V_{select} are oriented horizontally and are driven by one or more scan drivers, and data lines V_{data} are oriented vertically and are driven by one or more data drivers. The red, green, and blue light emitting micro LED devices are placed between the scan lines and data lines.

FIG. 22 illustrates a display system 2200 in accordance with an embodiment. The display system houses a processor 2210, data receiver 2220, a display 2230, and one or more display driver ICs 2240, which may be scan driver ICs and data driver ICs. The data receiver 2220 may be configured to receive data wirelessly or wired. Wireless may be implemented in any of a number of wireless standards or protocols including, but not limited to, Wi-Fi (IEEE 802.11 family), WiMAX (IEEE 802.16 family), IEEE 802.20, long term evolution (LTE), Ev-DO, HSPA+, HSDPA+, HSUPA+, EDGE, GSM, GPRS, CDMA, TDMA, DECT, Bluetooth, derivatives thereof, as well as any other wireless protocols that are designated as 3G, 4G, 5G, and beyond. The one or more display driver ICs 2240 may be physically and electrically coupled to the display 2230.

In some embodiments, the display 2230 includes one or more micro LED devices 400 that are formed in accordance with embodiments of the invention described above. For example, the display 2230 may include pixels or subpixels in which a micro LED device 400 is received by passivation layer 112 laterally surrounding the quantum well layer of the micro LED device.

Depending on its applications, the display system 2200 may include other components. These other components include, but are not limited to, memory, a touch-screen controller, and a battery. In various implementations, the display system 2200 may be a television, tablet, phone, laptop, computer monitor, kiosk, digital camera, handheld game console, media display, ebook display, or large area signage display.

In utilizing the various aspects of this invention, it would become apparent to one skilled in the art that combinations or variations of the above embodiments are possible for receiving a micro device. Although the present invention has been described in language specific to structural features and/or methodological acts, it is to be understood that the invention defined in the appended claims is not necessarily limited to the specific features or acts described. The specific features and acts disclosed are instead to be understood as particularly graceful implementations of the claimed invention useful for illustrating the present invention.

What is claimed is:

1. A display comprising:

a display substrate;

a plurality of bottom conductive lines on the display substrate;

18

a plurality of groups of LED devices connected to the plurality of bottom conductive lines, each group of LED devices connected to a corresponding bottom conductive line;

a plurality of electrode lines on the display substrate;

a passivation layer spanning across the display substrate and laterally surrounding each LED device in the plurality of groups of LED devices such that each LED device is embedded within the passivation layer; and

a plurality of openings in the passivation layer; and

a plurality of transparent top conductive layers directly over the passivation layer and in contact with the plurality of groups of LEDs, and in electrical contact with the plurality of electrode lines through the plurality of openings in the passivation layer.

2. The display of claim 1, wherein the plurality of transparent top conductive layers span within the plurality of openings to make electrical contact the plurality of electrode lines.

3. The display of claim 1, wherein each transparent top conductive layer is in electrical contact with more than one LED device of the plurality of groups of LED devices.

4. The display of claim 3, wherein each transparent top conductive layer is in electrical contact with an LED device from each group of LED devices.

5. The display of claim 3, wherein each group of LED devices comprises a pixel group.

6. The display of claim 1, wherein the passivation layer is a thermoset material.

7. The display of claim 1, wherein the passivation is transparent.

8. The display of claim 1, wherein the plurality of groups of LED devices is connected to the plurality of bottom conductive lines with a corresponding plurality of bonding layers.

9. The display of claim 8, wherein each bonding layer in the plurality of bonding layers an alloy bonding layer.

10. The display of claim 1, wherein the display substrate has a pixel density of greater than 300 pixels per inch.

11. The display of claim 1, wherein each LED device has a maximum width of 1 to 100 μm .

12. The display of claim 1, wherein each LED device has a maximum width of 1 to 10 μm .

13. The display of claim 1, wherein each LED device has a top doped layer, a lower doped layer, and a quantum well layer between the top doped layer and the lower doped layer.

14. The display of claim 1, wherein the plurality of groups of LED devices includes a first group of LED devices designed to emit a first color, and a second group of LED devices designed to emit a second color different from the first color.

15. The display of claim 1, wherein the plurality of transparent top conductive layers is formed of a transparent conductive oxide material.

* * * * *

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 11,476,239 B2
APPLICATION NO. : 17/072240
DATED : October 18, 2022
INVENTOR(S) : John A. Higginson, Andreas Bibl and Hsin-Hua Hu

Page 1 of 1

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

On the Title Page

Item [72], delete "Andreas Bibi" and insert in place there of --Andreas Bibl--

Signed and Sealed this
Twenty-seventh Day of February, 2024



Katherine Kelly Vidal
Director of the United States Patent and Trademark Office