



US011650270B2

(12) **United States Patent**
Uchida et al.

(10) **Patent No.:** **US 11,650,270 B2**
(45) **Date of Patent:** ***May 16, 2023**

(54) **MAGNETIC SENSOR**

(71) Applicant: **TDK Corporation**, Tokyo (JP)

(72) Inventors: **Keisuke Uchida**, Tokyo (JP); **Hiraku Hirabayashi**, Tokyo (JP)

(73) Assignee: **TDK Corporation**, Tokyo (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **17/536,689**

(22) Filed: **Nov. 29, 2021**

(65) **Prior Publication Data**

US 2022/0082641 A1 Mar. 17, 2022

Related U.S. Application Data

(63) Continuation of application No. 16/665,185, filed on Oct. 28, 2019, now Pat. No. 11,209,503, which is a continuation of application No. 15/825,289, filed on Nov. 29, 2017, now Pat. No. 10,557,896.

(30) **Foreign Application Priority Data**

Mar. 24, 2017 (JP) JP2017-058523

(51) **Int. Cl.**

G01R 33/09 (2006.01)
H01F 10/32 (2006.01)
H01F 3/00 (2006.01)
H01F 1/12 (2006.01)

(52) **U.S. Cl.**

CPC **G01R 33/09** (2013.01); **G01R 33/093** (2013.01); **H01F 1/12** (2013.01); **H01F 3/00** (2013.01); **H01F 10/3254** (2013.01); **H01F 10/3268** (2013.01)

(58) **Field of Classification Search**

CPC G01R 33/09; G01R 33/093; H01F 10/3268
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,761,009 A * 6/1998 Hughbanks G11B 5/11
360/323
5,923,504 A * 7/1999 Araki H01L 43/10
7,292,414 B1 11/2007 Mallery
9,047,884 B2 * 6/2015 McNeill G11B 5/398
(Continued)

FOREIGN PATENT DOCUMENTS

JP 2005-049185 A 2/2005
JP 2009-175120 A 8/2009
(Continued)


Primary Examiner — Alvaro E Fortich

(74) *Attorney, Agent, or Firm* — Posz Law Group, PLC

(57) **ABSTRACT**

The magnetic sensor can prevent an increase of a positional detection error of a subject/object even in the case of applying an external magnetic field with a magnetic field intensity exceeding a predetermined range. A magnetic sensor is equipped with a magnetoresistive effect element (MR element) **11** that can detect an external magnetic field and a soft magnetic body shield **12**. The soft magnetic body shield(s) **12** are/is positioned above and/or below the MR element **11** in a side view, and the size of the MR element **11** is physically included within a perimeter of the soft magnetic body shield **12**.

19 Claims, 21 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

9,196,270	B1	11/2015	Yang et al.	
11,209,503	B2 *	12/2021	Uchida	G01R 33/09
2002/0075608	A1	6/2002	Kawato	
2002/0171982	A1	11/2002	Lairson et al.	
2005/0116255	A1 *	6/2005	Kato	H01L 27/222 257/E27.005
2006/0202692	A1	9/2006	Tatschl et al.	
2007/0053114	A1	3/2007	Uesugi et al.	
2009/0201600	A1 *	8/2009	Komura	G11B 5/102 360/59
2009/0279213	A1 *	11/2009	Wu	G11B 5/3912 360/319
2010/0270866	A1 *	10/2010	Ide	G01R 33/098 307/91
2011/0175605	A1	7/2011	Kim et al.	
2012/0062224	A1	3/2012	Ide et al.	
2013/0028011	A1	1/2013	Kitagawa et al.	
2014/0197505	A1	7/2014	Zhou et al.	
2014/0225596	A1	8/2014	Nakamura et al.	
2014/0268418	A1	9/2014	McKinlay et al.	
2014/0293474	A1	10/2014	Yamane et al.	
2017/0343584	A1 *	11/2017	Abe	G01R 15/148

FOREIGN PATENT DOCUMENTS

JP	2011-007685	A	1/2011
JP	2013-210335	A	10/2013
JP	2015-064246	A	4/2015
JP	2016-524142	A	8/2016
JP	2016-535845	A	11/2016
WO	2009/084435	A1	7/2009
WO	2016/148022	A1	9/2016

* cited by examiner




FIG.1 A




FIG.1 B




FIG.1 C




FIG. 2 A




FIG. 2 B




FIG. 3 A




FIG. 3 B




FIG. 4




FIG. 5 A




FIG. 5 B




FIG. 5 C




FIG. 6




FIG. 7




FIG. 8 A




FIG. 8 B




FIG. 9 A




FIG. 9 B




FIG. 1 0




FIG. 1 1 A




FIG. 1 1 B




FIG. 1 2 A




FIG. 1 2 B




FIG. 1 3




FIG. 1 4




FIG. 1 5




FIG. 1 6




FIG. 1 7




FIG. 1 8




FIG. 1 9




FIG. 2 0




FIG. 2 1




FIG. 2 2




FIG. 2 3




FIG. 2 4




FIG. 2 5




FIG. 2 6




FIG. 2 7 A




FIG. 2 7 B




FIG. 2 8 A




FIG. 2 8 B




FIG. 2 9

1**MAGNETIC SENSOR**CROSS REFERENCE TO RELATED
APPLICATIONS

The present application is a continuation application of U.S. utility application Ser. No. 16/665,185 filed on Oct. 28, 2019 which is a continuation application of U.S. utility application Ser. No. 15/825,289 filed on Nov. 29, 2017, which is based on Japanese Patent Application No. 2017-058523 filed on Mar. 24, 2017, the contents of which are incorporated herein by reference.

TECHNICAL FIELD

The present invention relates to a magnetic sensor.

BACKGROUND TECHNOLOGY

Conventionally, a magnetic sensor is widely used for applications, such as detection of a rotational position of vehicle steering or the like or detection of the linear displacement of an object. The magnetic sensor is a sensor that can detect the rotational position or linear displacement of an object, by detecting the orientation and magnitude of a magnetic field that is generated from a magnet placed in an object to be detected. Recently, a magnetoresistive effect element (MR element), which is a multilayer body having a magnetization free layer and a magnetization pinned layer, where the resistance of the MR element varies in accordance with a change of the magnetization direction of the free layer according to an external magnetic field, has been widely used as a magnetic sensor. When the external magnetic field acts on the MR element, the magnetization direction of the magnetization free layer is changed, and the relative angle with the magnetization direction in the magnetization pinned layer is changed. The change of the magnetization direction appears as a change in the magnetic resistance of the MR element, enabling the detection of the intensity of the external magnetic field.

PRIOR ART

Patent Literature

[Patent Literature 1] Japanese Patent Application Laid-Open 2013-210335

[Patent Literature 2] Japanese Translation of PCT International Application Publication No. JP-T-2016-535845

SUMMARY OF THE INVENTION

Problem to be Solved by the Invention

The predetermined range of a magnetic field intensity for the external magnetic field to be detected is set in a magnetoresistive effect element (MR element) used for an application to detect the rotational position or linear displacement of an object or the like. When an external magnetic field with the magnetic field intensity within the range is applied to the MR element, the rotational position, the linear displacement or the like of the object is detected based upon the output of the MR element.

Meanwhile, another external magnetic field, such as the leakage field from a motor or geomagnetism, may be applied to an MR element other than the external magnetic field to be generated from a magnet, due to its use environment or

2

the effect of a usage or the like. Due to the effects of other external magnetic fields, when an external magnetic field with a magnetic field that exceeds the predetermined range is applied to the MR element, the error of position detection, such as a rotational position or a linear displacement in an object, becomes greater.

The present invention has been accomplished by taking such actual circumstances as mentioned above into consideration and has the objective of providing a magnetic sensor that can prevent increasing an error in the position detection of an object even when an external magnetic field with a magnetic field intensity that exceeds the predetermined range is applied.

Means for Solving the Problem

To solve the above problem, the present invention provides a magnetic sensor that is equipped with a magnetoresistive effect element (MR element), which can detect an external magnetic field, and a soft magnetic body shield, wherein the soft magnetic body shield(s) are positioned above and/or below the MR element(s) in a side view, and the size of the MR element is physically included within a perimeter of the soft magnetic body shield in a plan view (Invention 1).

According to the invention (Invention 1), because the soft magnetic body shield(s) has a perimeter which physically includes the size of the MR element(s) in a plan view, is positioned above and/or below the MR element in a side view, even if an external magnetic field with a magnetic field intensity that exceeds a predetermined range is applied, an increase error in the position detection of an object can be prevented.

In the invention (Invention 1) above, it is preferable that shape of the soft magnetic body shield in a plan view is nearly circular (Invention 2), and it is preferable that the shape of the soft magnetic body shield in a plan view is an N-sided polygon (N is 6 or greater even number) (Invention 3).

In the invention (Invention 1) above, it is preferable that the soft magnetic body shield be columnar (Invention 4), and that the soft magnetic body shield can be conical (Invention 5).

In the invention (Invention 1) above, the soft magnetic body shield can include a columnar portion, which is equipped with a first surface and a second surface, where the second surface faces the first surface, and a convexity, which protrudes from the first surface side of the columnar portion and can be positioned to allow the second surface to face the MR element (Invention 6). The soft magnetic body shield can include a columnar portion equipped with a first surface and a second surface, where the second surface faces the first surface, and a concave portion, which is formed on the first surface side of the columnar portion and can be positioned to allow the second surface to face the MR element (Invention 7).

In the invention (Invention 1) above, the soft magnetic body shield may have a through-hole that penetrates through the soft magnetic body shield in the thickness direction (Invention 8).

In the invention (Invention 1) above, it is preferable that the diameter φ_s of the soft magnetic body shield and the diameter φ_m of the MR element fulfill a relationship in the following formula (1) (Invention 9), and it is preferable that the thickness h of the soft magnetic body shield and the diameter φ_m of the MR element fulfill a relationship in the following formula (2) (Invention 10):

3

$$\varphi_s \geq 1.3 \varphi_m \quad (1)$$

$$h > 0.3 \varphi_m \quad (2)$$

In the invention (Invention 1) above, it is preferable that a harmonic component V_{3rd} , which is output in the case of applying an external magnetic field with a magnetic field intensity that exceeds 70 mT (Millitesla) to the MR element, and a harmonic component V_{3rd} , which is output in the case of applying an external magnetic field with 70 mT or less of a magnetic field intensity to the MR element, are nearly the same (Invention 11).

In the invention (Invention 1) above, the magnetic sensor has a plurality of the MR elements, and it is preferable that the soft magnetic body shields are placed in correspondence with the MR elements, respectively (Invention 12), and in this case, it is preferable that the diameter φ_s of each of the soft magnetic body shields be 2.00 to 2.75 times the diameter φ_m of the corresponding MR element (Invention 13).

Effect of the Invention

According to the present invention, even when an external magnetic field with a magnetic field intensity that exceeds a predetermined range is applied, it is possible to prevent an increase of error in position detection of an object.

BRIEF DESCRIPTION OF DRAWINGS

FIG. 1A is a schematic perspective view showing a magnetic sensor relating to the first embodiment of the present invention.

FIG. 1B is a schematic side view showing the magnetic sensor relating to the first embodiment of the present invention.

FIG. 1C is a schematic plan view showing the magnetic sensor relating to the first embodiment of the present invention.

FIG. 2A is cross-sectional view showing a schematic configuration of a magnetic sensor package including the magnetic sensor relating to the first embodiment of the present invention.

FIG. 2B is circuit diagram showing a schematic configuration of a detection circuit using the magnetic sensor relating to the first embodiment of the present invention.

FIG. 3A is a perspective view showing a schematic configuration of a magnetoresistive effect element (MR element) relating to the first embodiment of the present invention.

FIG. 3B is a cross-sectional view showing a schematic configuration of the MR element relating to the first embodiment of the present invention.

FIG. 4 is a characteristic chart showing characteristics where the attenuation effect of a magnetic field intensity to be applied to an MR element varies per diameter size of a soft magnetic body shield.

FIG. 5A is a schematic side view showing the variation of the magnetic sensor relating to the first embodiment of the present invention.

FIG. 5B is a schematic plan view showing another variation of the magnetic sensor relating to the first embodiment of the present invention.

FIG. 5C is a schematic side view showing another variation of the magnetic sensor relating to the first embodiment of the present invention.

4

FIG. 6 is a schematic plan view showing the magnetic sensor where a plurality of MR elements, where a soft magnetic body shield is arranged above, respectively, relating to the first embodiment of the present invention are arranged in an array manner.

FIG. 7 is a characteristic chart showing an attenuation of effect of the magnetic field intensity in the magnetic sensor shown in FIG. 6.

FIG. 8A is an entire schematic perspective view showing a magnetic sensor relating to the second embodiment of the present invention.

FIG. 8B is a schematic side view showing the magnetic sensor relating to the second embodiment of the present invention.

FIG. 9A is an entire schematic perspective view showing a magnetic sensor relating to the third embodiment of the present invention.

FIG. 9B is a schematic side view showing the magnetic sensor relating to the third embodiment of the present invention.

FIG. 10 is an entire schematic cross-sectional view showing a magnetic sensor relating to the fourth embodiment of the present invention.

FIG. 11A is an entire schematic perspective view showing a magnetic sensor relating to the fifth embodiment of the present invention.

FIG. 11B is a schematic side view showing the magnetic sensor relating to the fifth embodiment of the present invention.

FIG. 12A is an entire schematic perspective view showing a magnetic sensor relating to the sixth embodiment of the present invention.

FIG. 12B is a schematic cross-sectional view showing the magnetic sensor relating to the sixth embodiment of the present invention.

FIG. 13 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 1.

FIG. 14 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 2.

FIG. 15 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 3.

FIG. 16 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 4.

FIG. 17 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 5.

FIG. 18 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 6.

FIG. 19 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 7.

FIG. 20 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using soft magnetic body shields of Examples 8 and 9.

5

FIG. 21 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using soft magnetic body shields of Examples 10 and 11.

FIG. 22 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using soft magnetic body shields of Examples 12 and 13.

FIG. 23 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 14.

FIG. 24 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 15.

FIG. 25 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 16.

FIG. 26 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Example 17.

FIG. 27A is a schematic plan view of a nearly square column-shaped soft magnetic body shield used in Comparative Example 1.

FIG. 27B is a pattern chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Comparative Example 1.

FIG. 28A is a schematic plan view of a soft magnetic body shield having a substantially rectangular shape in plan view used in Comparative Example 2.

FIG. 28B is a pattern chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Comparative Example 2.

FIG. 29 is a characteristic chart showing an attenuation effect of a magnetic field intensity to be applied to the MR element in the case of using a soft magnetic body shield of Comparative Example 3.

MODE FOR CARRYING OUT THE INVENTION

Embodiments of the present invention are explained hereafter with reference to the drawings. Furthermore, the drawings are schematic or conceptual, and dimensions of each member, the ratio of size between members and the like are not always realistic, and even if the same members or the like are indicated, mutual dimensions and ratio(s) may be differently indicated in each drawing. Further, in the drawings attached to the present specification, to facilitate understanding, shape, scale reduction, horizontal and vertical dimensional ratios and the like of each part may be changed or exaggerated from the actual ones.

First Embodiment

FIG. 1A is a schematic perspective view showing a magnetic sensor 1 relating to a first embodiment of the present invention; FIG. 1B is a schematic side view showing the magnetic sensor 1 relating to the first embodiment of the present invention; and FIG. 1C is a schematic plan view showing the magnetic sensor 1 relating to the first embodiment of the present invention. The magnetic sensor 1 is used for detecting a rotation angle due to relative movement of a

6

rotor or the like and a linear displacement or the like of an object. For example, a magnet as a magnetic field generating part is placed in a rotating body, which is an object for detection of a rotation angle, and the magnetic field generating part generates the magnetic field to be detected. When the magnetic sensor 1 which is incorporated into a rotation angle sensor is used, the magnetic sensor 1 produces an angle detection value having a correspondence relationship with the angle between the direction of the magnetic field to be detected at a reference position and the reference direction.

The magnetic sensor 1 relating to the first embodiment is equipped with a magnetoresistive effect element (MR element) 11 and a soft magnetic body shield 12. As shown in FIG. 1B, the magnetic sensor 1 relating to the first embodiment is configured such that the soft magnetic body shield 12 is positioned above the MR element 11 in a side view, and the size of the MR element 11 becomes any size physically included within the perimeter of the soft magnetic body shield 12 in a plan view. Hereafter, each component in the magnetic sensor 1 relating to the first embodiment will be explained in detail.

FIG. 2A is cross-sectional view showing a schematic configuration of a magnetic sensor package 10 including the magnetic sensor relating 1 to the first embodiment; and FIG. 2B is circuit diagram showing a schematic configuration of a detection circuit using the magnetic sensor relating to the first embodiment. The magnetic sensor package 10 has a base 4, a magnetic sensor part 2 placed on the base 4, connection leads 6, wiring parts 5, such as a bonding wire, which electrically connect the magnetic sensor part 2 with the connection leads 6, and a sealing part 3 that integrally seals them. The sealing part 3 is composed by a resin material, such as epoxy resin. The magnetic sensor part 2 includes the magnetic sensor 1.

The magnetic sensor part 2 has magnetic detection element circuits 21 and 22 that output a detection signal in association with a change of the external magnetic field, as a magnetic field detection part, respectively. The magnetic detection element circuit 21 outputs a detection signal V_{OUT} having a corresponding relationship with the angle formed between the direction of the magnetic field to be detected and the first direction D1. The magnetic detection element circuit 22 outputs a detection signal V_{OUT} having a corresponding relationship with the angle formed between the direction of the magnetic field to be detected and the second direction D2.

An operational amplifier 221 is connected to the magnetic detection element circuit 21, amplifies the detection signal V_{OUT} and outputs a sensor signal S1. An operational amplifier 222 is connected to the magnetic detection element circuit 22, amplifies the detection signal V_{OUT} and outputs a sensor signal S2. An operation part 23 calculates an angle detection value having a corresponding relationship with an angle θ based upon the two signals S1 and S2. Furthermore, the operating part 23 includes an angle detection value calculation part, a correction processing part and a correction information retaining part, but a detailed explanation about these will be omitted.

The magnetic detection element circuit 21 has a Wheatstone bridge circuit including at least one pair of magnetic detection elements configured by two magnetic detection elements connected in series. As shown in FIG. 2B, in the present embodiment, the magnetic detection element circuit 21 has a Wheatstone bridge circuit C21, which includes a first pair of magnetic detection elements in which a first magnetic detection element MR1 and a second magnetic

detection element MR2 are connected in series, and a second pair of magnetic detection elements, in which a third magnetic detection element MR3 and a fourth magnetic detection element MR4 are connected in series.

As shown in FIG. 2B, the Wheatstone bridge circuit C21 includes the first pair of magnetic detection elements, the second pair of magnetic detection elements, a power port V21, where one terminal of the first magnetic detection element MR1 and one terminal of the third magnetic detection element MR3 are connected, a ground port G21, where one terminal of the second magnetic detection element MR2 and one terminal of the fourth magnetic detection element MR4 are connected, a first output port E211, and a second output port E212. The first output port E211 is connected between (at a midpoint of) the first magnetic detection element MR1 and the second magnetic detection element MR2 in the first pair of magnetic detection elements, and the second output port E212 is connected between (at the midpoint of) the third magnetic detection element MR3 and the fourth magnetic detection element MR4 in the second pair of magnetic detection elements. The power port V21 is connected to a first power supply source V_s that is capable of supplying an electric current to the magnetic detection element circuit 21, and the ground port G21 is connected to a ground (reference potential point) VG. Furthermore, the first power supply source V_s may be a constant-voltage power supply that is capable of supplying constant voltage or may be a constant-current power supply that is capable of supplying a constant current.

Similarly, the magnetic detection element circuit 22 also has a Wheatstone bridge circuit including at least one pair of magnetic detection elements configured by two magnetic detection elements connected in series. As shown in FIG. 2B, in the present embodiment, the magnetic detection element circuit 22 has the Wheatstone bridge circuit C21, which includes the first pair of magnetic detection elements, where the first magnetic detection element MR1 and the second magnetic detection element MR2 are connected in series, and the second pair of magnetic detection elements, where the third magnetic detection element MR3 and the fourth magnetic detection element MR4 are connected in series. Since the specific configuration of the magnetic detection element circuit 22 is similar to that of the magnetic detection element circuit 21, an explanation thereof is omitted.

In the first embodiment, when an external magnetic field with a magnetic field intensity that exceeds the predetermined range is applied, waveforms of the first signal S1 and the second signal S2 that are output from the magnetic detection element circuits 21 and 22, respectively, are distorted, and an ideal component, which is periodically changed to draw an ideal sine curve, and one or more error components, which are equivalent to one or more harmonics relative to the ideal component, are included. Because the signals S1 and S2 include one or more error components, respectively, an angle detection value θ_s shall include an error. In general, in the magnetic sensor, it has been known that the angle error will change in accordance with the intensity of the magnetic field to be detected, i.e., a magnetic field intensity dependency of the angle error exists. A third harmonic component V_{3rd1} relative to the ideal component is included in the signal S1 as the error component, and a third harmonic component V_{3rd2} relative to the ideal component is included in the signal S2 as the error component. The magnetic sensor 1 relating to the first embodiment is configured such that the third harmonic component will become roughly the same before and after the change of the

magnetic field intensity even if the magnetic field intensity of the detected magnetic field is changed.

As the first to fourth magnetic detection elements MR1 to MR4 included in the Wheatstone bridge circuit C21, for example, the MR element, such as an AMR element, a GMR element or a TMR element is exemplified, and the GMR element, the TMR element and the like with comparatively great output voltage are particularly preferable.

FIG. 3A is a perspective view showing a schematic configuration of the MR element 11 relating to the first embodiment; and FIG. 3B is a cross-sectional view showing a schematic configuration of the MR element relating to the first embodiment. The GMR elements and TMR elements as the first to fourth magnetic detection elements MR1 to MR4, as shown in FIG. 3A, have a plurality of lower-side lead electrodes 61, a plurality of MR multilayer bodies 50 and a plurality of upper-side lead electrodes 62, respectively. The lower-side lead electrodes 61 and the upper-side lead electrode 62, for example, are composed by one type of conductive material among Cu, Al, Au, Ta, Ti and the like or a composite membrane of two or more types of conductive materials, for example, and their thicknesses are around 0.3 μm to 2.0 μm , respectively.

The plurality of lower-side lead electrodes 61 are placed on a substrate (not shown). The plurality of lower-side lead electrodes 61 have a long and narrow nearly-rectangular shape, respectively, and are placed to have a predetermined gap between the two adjacent lower-side lead electrodes 61 in an electric series direction of the plurality of MR multilayer bodies 50 (see FIG. 6) that are arranged in an array manner. The MR multilayer bodies 50 are placed in the vicinity of both ends in the longitudinal direction of the lower-side lead electrode 61, respectively. In other words, two MR multilayer bodies 50 are placed on each of the plurality of lower-side lead electrodes 61, respectively.

The MR multilayer body 50 in the present embodiment, as shown in FIG. 3B, has a magnetization pinned layer 53 where its magnetization direction is pinned, a free layer 51 where its magnetization direction is changed according to the direction of the magnetic field to be applied, a nonmagnetic layer 52 that is arranged between the magnetization pinned layer 53 and the free layer 51, and an antiferromagnetic layer 54.

The MR multilayer body 50 has a structure where the free layer 51, the nonmagnetic layer 52, the magnetization pinned layer 53 and the antiferromagnetic layer 54 are laminated in respective order from the lower-side lead electrode 61 side. The free layer 51 is electrically connected to the lower-side lead electrode 61, and the antiferromagnetic layer 54 is electrically connected to the upper-side lead electrode 62. As a material to compose the free layer 51 and the magnetization pinned layer 53, for example, NiFe, CoFe, CoFeB, CoFeNi, Co_2MnSi , Co_2MnGe , FeOx (oxide of Fe) and the like are exemplary. The thicknesses of the free layer 51 and the magnetization pinned layer 53 are around 1 nm to 20 nm, respectively.

The nonmagnetic layer 52 is a spacer layer, and is an essential membrane for developing a tunnel magnetoresistance effect (TMR effect) or a giant magnetoresistive effect (GMR effect) to the MR multilayer body 50. As a material to compose the nonmagnetic layer 52, oxides, such as MgO, Mg—Al—O or Al—O, metallic materials, such as Cu, Au, Ag, Cr, Ag—Zn or Ni—Al, and the like are exemplary. Furthermore, the thickness of the nonmagnetic layer 52 is around 0.1 nm to 5 nm.

The antiferromagnetic layer 54 is composed by an antiferromagnetic material containing Mn and at least one type

of element to be selected from a group of, for example, Pt, Ru, Rh, Pd, Ni, Cu, Jr, Cr and Fe. The content of Mn in this antiferromagnetic material is, for example, around 35 to 95 atom %. The antiferromagnetic layer **54** composed by the antiferromagnetic material fulfills the role of pinning the magnetization direction of the magnetization pinned layer **53** by exchange coupling with the magnetization pinned layer **53**. Furthermore, without establishing the antiferromagnetic layer **54**, the magnetization pinned layer **53** may have a three-layer structure of a first magnetization pinned layer, a nonmagnetic intermediate layer and a second magnetization pinned layer. The first magnetization pinned layer and the second magnetization pinned layer can be antiferromagnetically coupled via the nonmagnetic intermediate layer.

The plurality of upper-side lead electrodes **62** are placed on the plurality of MR multilayer bodies **50**. Each upper-side lead electrode **62** has a long and narrow nearly-rectangular shape. The upper-side lead electrodes **62** are arranged to have a predetermined gap between two adjacent upper-side lead electrodes **62** in the electric series direction of the plurality of MR multilayer bodies **50** arranged in an array manner, and, to connect the plurality of MR multilayer bodies **50** in series, and electrically connect the antiferromagnetic layers **54** in the two adjacent MR multilayer bodies **50**. Furthermore, the MR multilayer body **50** may have a structure where the antiferromagnetic layer **54**, the magnetization pinned layer **53**, the nonmagnetic layer **52** and the free layer **51** are laminated in respective order from the lower-side lead electrode **61** side. Further, a cap layer (protective layer) may be placed between the free layer **51** and the lower-side lead electrode **61** or the upper-side lead electrode **62**. In the first embodiment, the soft magnetic body shield **12** is arranged above the upper-side lead electrode **62** where the MR multilayer body **50** is positioned.

In the MR multilayer body **50**, a resistance value varies according to an angle between the magnetization direction of the free layer **51** and that of the magnetization pinned layer **53**, and when this angle is 0° (these magnetization directions are in parallel with each other), the resistance value becomes minimum, and when this angle is 180° (the magnetization directions are antiparallel to each other), the resistance value becomes maximum.

As shown FIG. 1 and FIG. 1C, the MR element **11** has a nearly circular cylindrical shape, but the shape of the MR element **11** is not particularly limited and can be, for example, a hexagonal-column shape or the like to be described later. The size of the MR element **11** is not particularly limited, as well, but it can be appropriately set according to the size of an object to be detected, a positional relationship with an object to be detected or the like. Furthermore, in the explanation below, the diameter of the MR element **11** is set at φ_m .

The soft magnetic body shield **12** includes a soft magnetic material with small coercive force and high permeability and prevents the application of an external magnetic field with a magnetic field intensity that exceeds a predetermined range to the MR **11**, if this characteristic is utilized. As the soft magnetic material, for example, a permalloy or the like that consists primarily of iron oxide, and that is a compound of ferrite, nickel and iron showing soft magnetic properties, are exemplified.

As shown in FIG. 1A and FIG. 1C, the soft magnetic body shield **12** has nearly a circular cylindrical shape, and has an upper surface and a lower surface, the shapes of which in a plan view are nearly the same size and are nearly circular. The shape of the soft magnetic body shield **12** in the first

embodiment in the plan view should be nearly circular and is not limited to a true circle, but it is preferable to form the soft magnetic body shield **12** as a true circle to reduce unevenness of the distribution of the magnetic field intensity of the external magnetic field in the in-plane direction of the MR element **11**. Furthermore, "true circle" here means a circle where φ_b becomes 0.977 to 0.987 when lengths (diameters) of two straight lines that are mutually at right angles are defined as φ_a and φ_b , and φ_a is 1.

It is preferable that the diameter φ_s of the soft magnetic body shield **12** in the plan view be set to fulfill the following formula (1) in the relationship with a diameter φ_m of the MR element **11**:

$$\varphi_s \geq 1.3 \varphi_m \quad (1)$$

Because the soft magnetic body shield **12**, in which the diameter φ_s is 1.3 times of the diameter φ_m , is arranged above the MR element **11**, the magnetic sensor **1**, the size of which is such that the size of the MR element **11** can be physically included within the perimeter of the soft magnetic body shield **12** in a plan view, can be obtained. Furthermore, as shown in FIG. 1A and

FIG. 1B, the central axis of the soft magnetic body shield **12** and that of the MR element **11** are adjusted to be the same, and the soft magnetic body shield **12** is arranged above the MR element **11**. Furthermore, as long as the size of the MR element **11** is such that the MR element is physically included within the perimeter of the soft magnetic body shield **12**, the soft magnetic body shield **12** should be arranged above the MR element **11**, and for example, even when the central axes of both are deviated to a certain extent, these should be arranged to prevent the MR element **11** from straying from within the perimeter of the soft magnetic body shield **12** in a top view.

FIG. 4 is a characteristic chart, in the external magnetic field with 200 mT (Millitesla) of the magnetic field intensity, showing characteristics where the attenuation effect of the magnetic field intensity of an external magnetic field to be applied to the MR element **11** varies per diameter size of a soft magnetic body shield. In FIG. 4, the vertical axis indicates the magnetic field intensity and the horizontal axis indicates the position of the MR element **11**, and the attenuation effects of the magnetic field intensities of the external magnetic field are indicated with curves protruding downward in the chart. The shaded portion in the chart indicates a position domain of the MR element **11**. As described later, it is preferable that the magnetic field intensity of the external magnetic field to be applied to the MR element **11** be 20 to 80 mT. Consequently, as the attenuation effect of the magnetic field intensity by the soft magnetic body shield **12**, it is preferable that the external magnetic field with 200 mT of the magnetic field intensity be attenuated to the range of 20 to 80 mT as mentioned above.

Here, a curve indicating a change of the magnetic field intensity of the external magnetic field in the case of using the soft magnetic body shield **12** having a diameter φ_{s1} , which is 0.6 times of the diameter φ_m of the MR element **11**, is indicated with a thin line; a curve indicating a change of the magnetic field intensity of the external magnetic field in the case of using the soft magnetic body shield **12** having a diameter φ_{s2} , which is same as the diameter φ_m of the MR element **11**, is indicated with a thick line; a curve indicating a change of the magnetic field intensity of the external

11

magnetic field in the case of using the soft magnetic body shield **12** having a diameter φ_{s3} , which is 1.3 times of the diameter φ_m of the MR element **11**, is indicated with a two-dot chain line; a curve indicating a change of the magnetic field intensity of the external magnetic field in the case of using the soft magnetic body shield **12** having a diameter φ_{s4} , which is 1.6 times of the diameter φ_m of the MR element **11**, is indicated with a long dashed line; a curve indicating a change of the magnetic field intensity of the external magnetic field in the case of using the soft magnetic body shield **12** having a diameter φ_{s5} , which is 2.0 times of the diameter φ_m of the MR element **11**, is indicated with a dashed-dotted line; a curve indicating a change of the magnetic field intensity of the external magnetic field in the case of using the soft magnetic body shield **12** having a diameter φ_{s6} , which is 2.3 times of the diameter φ_m of the MR element **11**, is indicated with a broken line; and a curve indicating a change of the magnetic field intensity of the external magnetic field in the case of using the soft magnetic body shield **12** having a diameter φ_{s7} , which is 2.6 times the diameter φ_m of the MR element **11**, is indicated with a solid line.

As is clear from FIG. 4, it is preferable to use the soft magnetic body shield **12** with the diameter φ_{s5} to the diameter φ_{s7} where the magnetic field intensity of the external magnetic field is attenuated to the range of 20 to 80 mT as mentioned above. In other words, the diameter φ_s of the soft magnetic body shield **12** is preferably 1.3 times or greater than the diameter φ_m of the MR element **11**, and more preferably 2.0 times or greater, and is further preferably 2.0 to 2.75 times greater. If the diameter φ_s of the soft magnetic body shield **12** is less than 1.3 times of the φ_m of the MR element **11**, the flatness of the distribution of the magnetic field intensities of the external magnetic field in the in-plane direction of the MR element **11** is deteriorated, and it may become difficult to reduce error that is included in the detection angle by the magnetic sensor **1**.

If the diameter φ_s of the soft magnetic body shield **12** exceeds 2.75 times the diameter φ_m of the MR element **11**, when the plurality of the MR elements **11** are arranged in an array manner to be described later and the soft magnetic body shields **12** are arranged above the MR elements **11**, respectively, the shield effect by the soft magnetic body shields **12** is liable to be reduced.

It is preferable to set thickness h of the soft magnetic body shield **12** to a magnitude that satisfies the following formula in the relationship with the diameter φ_m of the MR element **11**:

$$h > 0.3 \varphi_m \quad (2)$$

If the thickness h of the soft magnetic body shield **12** is adjusted to exceed 0.3 times of the diameter φ_m of the MR element **11**, the attenuation effect of the magnetic field intensity of the external magnetic field can be further enhanced. Furthermore, the thickness h of the soft magnetic body shield **12** is not particularly limited, but even if this is increased, it is inferred that the excess thickness will not impair the performance of the magnetic sensor **1**.

As shown in FIG. 1A to FIG. 1C, in the magnetic sensor **1** of the first embodiment, the soft magnetic body shield **12** is arranged above the MR element **11**. In this case, the closer a distance d between the soft magnetic body shield **11** and the MR element **11** becomes, the higher the attenuation effect of the magnetic field intensity of the external magnetic

12

field becomes, and the greater the distance d between the soft magnetic body shield **11** and the MR element **11** becomes, the lower the attenuation effect of the magnetic field intensity of the external magnetic field becomes. Consequently, the distance d between the soft magnetic body shield **12** and the MR element **11** can be appropriately set, for example, within 0.1 μm to 1 μm .

In the magnetic sensor **1** relating to the first embodiment, the soft magnetic body shield **12** having the distance and the thickness as mentioned above is arranged above the MR element **11**. Consequently, the harmonic component V_{3rd} , which is included in the output signal from the MR element **11** in the case of applying the external magnetic field with the magnetic field intensity that exceeds 80 mT to the MR element **11**, is nearly the same as the harmonic component V_{3rd} , which is included in the output signal in the case of applying the external magnetic field with the magnetic field intensity that is 80 mT or less to the MR element **11**. Consequently, even if the external magnetic field with a magnetic field intensity that exceeds the detection range is applied to the MR element **11**, the MR element **11** can output a desired detection signal, making it possible to prevent the positional detection error of an object from increasing.

Furthermore, the upper limit of the detection range of the magnetic field intensity is set at 80 mT, because the MR element **11** in the first embodiment is explained as a TMR element. In other words, 80 mT is a common upper limit value for the detection range in the case of using a TMR element as the MR element **11**. Instead, a common upper limit value for the detection range in the case of using a GMR element as the MR element **11** is set at 70 mT. In this case, the magnetic sensor **1** is configured so that the harmonic component V_{3rd} , which is included in the output signal in the case of applying the external magnetic field with the magnetic field intensity that exceeds 70 mT to the MR element **11**, become nearly the same as the harmonic component V_{3rd} , which is included in the output signal in the case of applying the external magnetic field with the magnetic field intensity that is 70 mT or less to the MR element **11**.

FIG. 5A is a schematic side view showing the variation of the magnetic sensor **1** relating to the first embodiment, and FIG. 5B is a schematic plan view of the magnetic sensor **1** relating to the variation. In the magnetic sensor **1** shown in FIG. 5A and FIG. 5B, the soft magnetic body shield **12** is arranged below the MR element **11**. In this point, the magnetic sensor **1** shown in FIG. 5A and FIG. 5B is different from the magnetic sensor **1** shown in FIG. 1A to FIG. 1C. Even in the magnetic sensor **1** shown in FIG. 5A and FIG. 5B, the size of the MR element **11** is a size that is physically included within the perimeter of the soft magnetic body shield **12**, in a plan view.

FIG. 5C is a schematic side view showing a magnetic sensor **1** having a different configuration from the magnetic sensor **1** shown in FIG. 1A to FIG. 1C and FIG. 5A to FIG. 5B, as a variation of the magnetic sensor relating to the first embodiment. In the magnetic sensor **1** shown in FIG. 5C, soft magnetic body shields **12T** and **12B** are arranged above and below the MR element **11**, respectively. In this point, the magnetic sensor **1** shown in FIG. 5C is different from the magnetic sensor **1** shown in FIG. 1A to FIG. 1C and the magnetic sensor **1** shown in FIG. 5A to FIG. 5B. Even in the magnetic sensor **1** shown in FIG. 5C, the size of the MR element **11** is a size that is physically included within the perimeter of the soft magnetic body shields **12T** and **12B** in a plan view.

13

In other words, even in the variations shown in FIG. 5A to FIG. 5C, because the magnetic sensor 1 is configured such that the size of the MR element 11 is adjusted to a size that is physically included within the perimeter of the soft magnetic body shield 12 in a plan view, even if the external magnetic field with the magnetic field intensity that exceeds the detection range is applied to the MR element 11, it becomes possible to prevent an increase of an error in position detection an object as is similar to the magnetic sensor 1 shown in FIG. 1A to FIG. 1C.

FIG. 6 is a schematic plan view showing the magnetic sensor 1 where a plurality of MR elements 11, where the soft magnetic body shields are arranged above, respectively, are arranged in an array manner. In FIG. 6, the magnetic sensor 1 where the MR elements 11 indicated by a broken line are arranged in 7 lines×7 rows, and where the soft magnetic body shields 12 are arranged in 7 lines×7 rows above (at a viewer side in the drawing) by corresponding to the MR elements 11, respectively, is shown, but the configuration of the magnetic sensor 1 is not limited to the one mentioned above but a configuration where size, shape and the like of an object to be detected are considered can be appropriately set. Further, in FIG. 6, a gap between mutually-adjacent soft magnetic body shields 12 (MR elements 11) is indicated by the symbol D. Furthermore, to confirm the attenuation effect of the magnetic field intensity, as indicated by the broken line Bx in FIG. 6, the magnetic field intensity of the external magnetic field is set at 200 mT and the magnetic field intensity is measured along the seven MR elements 11 aligned in the X-axis direction; and as indicated with a broken line By in FIG. 6, the magnetic field intensity is measured along the seven MR elements 11 aligned in the Y-axis direction.

FIG. 7 is a characteristic chart showing one example of an attenuation effect of the magnetic field intensity in the magnetic sensor 1 shown in FIG. 6, and the attenuation effect of the magnetic field intensity in the three MR elements 11 surrounded with a broken line S in FIG. 6 is indicated with a curve MF_B . In FIG. 7, shield regions SR of the soft magnetic body shields 12 are indicated with shaded lines. The attenuation effect of the magnetic field intensity here is confirmed by drawing measurements of the magnetic field intensities in the X-axis direction for seven MR elements 11 aligned in a single horizontal row including three MR elements 11 onto a graph where the horizontal axis indicates positions of the MR elements 11 and the vertical axis indicates the magnetic field intensities. As shown in FIG. 7, it is preferable that the magnetic field intensities at positions P1, P2 and P3 of the three MR elements 11 are attenuated to 20 to 80 mT of the detection range, as the attenuation effect (external magnetic field intensity: 200 mT) of the magnetic field intensities in the case of setting the diameter φ_s of the soft magnetic body shield 12 to twice the diameter φ_m of the MR elements 11. Further, as shown in FIG. 7, it is preferable that the distribution of the magnetic field intensities is substantially flat at element portions (P1, P2 and P3) covered with the shield regions SR.

Second Embodiment

FIG. 8A is an entire schematic perspective view showing the magnetic sensor 1 relating to the second embodiment of the present invention, and FIG. 8B is a schematic side view showing the magnetic sensor 1 relating to the second embodiment of the present invention. Furthermore, the configuration that is nearly similar to that of the magnetic

14

sensor 1 in the first embodiment is marked with the same symbols and its detailed explanation is omitted.

As shown in FIG. 8A and FIG. 8B, the soft magnetic body shield 12 configuring the magnetic sensor 1 relating to the second embodiment has a hexagonal-column shape. Furthermore, the shape of the soft magnetic body shield 12 configuring the magnetic sensor 1 is not limited to the hexagonal-column shape, but any shape is acceptable as long as the shape is a polygonal column with N sides (N is 6 or greater even number) of its plan view shape, such as an octagonal pillar, a dodecagonal pillar or a hexadecagonal pillar. Further, it is preferable that the shape of the soft magnetic body shield 12 configuring the magnetic sensor 1 be a polygonal column with N sides with M-fold symmetrical shape (M is four or greater even number) that overlaps with itself when this is rotated by a predetermined angle around the central axis in the plan view. If the soft magnetic body shield 12 is a polygonal column with N sides (N is 6 or greater even number) including a hexagonal shape in the plan view, and is preferably columnar with a polygon with N sides with an M-fold symmetrical shape (M is four or greater even number) in the plan view, it becomes possible to reduce the unevenness in the distribution of the magnetic field intensities of the external magnetic field in the in-plane direction of the MR element 11.

Because the soft magnetic body shield 12 in the second embodiment is arranged above or below the MR element 11 as is similar to the first embodiment, even if the external magnetic field with the magnetic field intensity that exceeds the detection range (for example, 80 mT or greater) is applied to the MR element 11, the harmonic component V_{3rd} , which is included in the output signal from the MR element 11, becomes nearly the same as the harmonic component V_{3rd} , which is included in the output signal when the external magnetic field with 80 mT or less of the magnetic field intensity is applied to the MR element 11. Consequently, the MR element 11 can output a desired detection signal, and it becomes possible to prevent the positional detection error of an object from increasing.

Third Embodiment

FIG. 9A is an entire schematic perspective view showing the magnetic sensor 1 relating to the third embodiment of the present invention, and FIG. 9B is a schematic side view showing the magnetic sensor 1 relating to the third embodiment of the present invention. Furthermore, the configuration that is nearly similar to that of the magnetic sensor 1 in the first embodiment is marked with the same symbols and its detailed explanation is omitted.

As shown in FIG. 9A and FIG. 9B, the soft magnetic body shield 12 configuring the magnetic sensor 1 relating to the third embodiment has shape in which a conical portion 12p is positioned on a columnar portion 12c that is circular in a plan view. The shape of the soft magnetic body shield 12 is not limited to the shape above, but can be a shape having a convexity where at least a portion of the upper surface of the columnar portion 12c protrudes. As the shape of the soft magnetic body shield 12, for example, a shape can be appropriately set in which a small columnar portion (convexity), which has a smaller diameter and thickness than those of the columnar portion 12c, is positioned on the columnar portion 12c. Furthermore, the shape of the soft magnetic body shield 12, is not limited to the columnar portion 12c above, but a pillar portion, for example, in a polygon with N sides (N is 6 or greater even number), such as a hexagonal prism, and preferably a polygon with N sides

15

with an M-fold symmetrical shape (M is four or greater even number) and the like can be appropriately set. Further, the shape of the soft magnetic body shield **12** is not limited to the conical portion **12p**, but a convexity, for example, an N-sided pyramid (N is 6 or greater even number), such as a hexagonal pyramid, preferably an N-sided pyramid with an M-fold symmetrical shape (M is four or greater even number) in the plan view and the like can be appropriately set. In the magnetic sensor **1** relating to the third embodiment, from a viewpoint to enjoy the attenuation effect of the magnetic field intensity of the external magnetic field as is similar to the first embodiment, both the MR element **11** and the soft magnetic body shield **12** can be arranged to face the upper surface of the MR element **11** and the nearly-flat lower surface (the conical portion **12p**, a surface at the side facing the small columnar portion (convexity)) of the soft magnetic body shield **12**.

Because the soft magnetic body shield **12** relating to the third embodiment is arranged above the MR element **11**, even though the external magnetic field with the magnetic field intensity that exceeds a detection range (for example, exceeding 80 mT) is applied to the MR element **11**, the harmonic component V_{3rd} which is included in the output signal from the MR element **11**, becomes nearly the same as the harmonic component V_{3rd} which is included in the output signal in the case of applying the external magnetic field with 80 mT or less of the magnetic field intensity to the MR element **11**. Consequently, the MR element **11** can output a desired detection signal, making it possible to prevent an increase of an error in position detection of an object.

Fourth Embodiment

FIG. **10** is an entire schematic cross-sectional view showing the magnetic sensor **1** relating to the fourth embodiment of the present invention. Furthermore, the configuration that is nearly similar to that of the magnetic sensor **1** in the first embodiment is marked with the same symbols and its detailed explanation is omitted.

As shown in FIG. **10**, a mortar-shaped portion **12n** where its upper surface is indented toward the lower surface side to be mortar-shaped is formed in the soft magnetic body shield **12** configuring the magnetic sensor **1** relating to the fourth embodiment. Furthermore, the form where the upper surface of the soft magnetic body shield **12** is indented toward the lower surface side is not limited to being mortar-shaped, but another form where at least a portion of the upper surface of the soft magnetic body shield **12** is indented toward the lower surface (concave portion) is also acceptable. The form of the soft magnetic body shield **12** can be appropriately set as, for example, a form in which a portion of the upper surface of the soft magnetic body shield **12** is indented toward the lower portion side by a nearly-cylindrical spatial portion with a smaller diameter than the diameter φ_s of the soft magnetic body shield **12** and with a thickness that is thinner than that of the soft magnetic body shield **12**.

From a similar viewpoint to that of the third embodiment, the MR element **11** and the soft magnetic body shield **12** can be arranged to face the upper surface of the MR element **11** and the nearly-flat lower surface (mortar-shaped portion **12n**, a plane at the side of facing the concave portion) of the soft magnetic body shield **12**. Because the soft magnetic body shield **12** relating to the fourth embodiment is arranged above the MR element **11**, even if the external magnetic field with the magnetic field intensity that exceeds the detection range (for example, exceeding 80 mT) is applied to the MR

16

element **11**, the harmonic component V_{3rd} which is included in the output signal from the MR element **11**, becomes nearly the same as the harmonic component V_{3rd} which is included in the output signal in the case of applying the external magnetic field with 80 mT or less of the magnetic field intensity to the MR element **11**. Consequently, the MR element **11** can output the desired detection signal, and it becomes possible to prevent an increase of an error in position detection of an object.

Fifth Embodiment

FIG. **11A** is an entire schematic perspective view showing the magnetic sensor **1** relating to the fifth embodiment of the present invention; and FIG. **11B** is a schematic side view showing the magnetic sensor **1** relating to the fifth embodiment of the present invention. Furthermore, the configuration that is nearly similar to that of the magnetic sensor **1** in the first embodiment is marked with the same symbols and its detailed explanation is omitted.

As shown in FIG. **11A** and FIG. **11B**, the soft magnetic body shield **12** configuring the magnetic sensor **1** relating to the fifth embodiment has a nearly conical shape. Furthermore, the shape of the soft magnetic body shield **12** is not limited to the nearly-conical shape, but it should be an N-sided pyramid (N is 6 or greater even number), such as a hexagonal pyramid, an eight-sided pyramid, a twelve-sided pyramid or a sixteen-sided pyramid, and should preferably be an N-sided pyramid with M-fold symmetrical shape (M is four or greater even number). Here, as an example of the N-sided pyramid, the shape where N is 6 or greater of even number is according to the similar reason to the case of the hexagonal-column shape of soft magnetic body shield **12** in the second embodiment.

In the fifth embodiment, because the soft magnetic body shield **12** is nearly conical, a shieldable region (a region where a magnetic shield effect proves effective in a plan view) is narrower than an area of the soft magnetic body shield **12** in the plan view, one with a relatively larger size compared to, for example, the nearly columnar soft magnetic body shield **12** in the first embodiment can be set to secure the sufficient shieldable region. For example, as shown in FIG. **11B**, as the size of the soft magnetic body shield **12** relating to the fifth embodiment, it is preferable that the thickness from the bottom surface be $2\varphi_m$ or greater and the diameter φ_{sb} of the bottom surface be $2\varphi_m$ or greater. Further, even in the soft magnetic body shield **12** relating to the fifth embodiment, the MR element **11** and the soft magnetic body shield **12** can be arranged to face the upper surface of the MR element and the lower surface of the soft magnetic body shield **12** from the similar viewpoint of the third embodiment and fourth embodiment.

Because the soft magnetic body shield **12** relating to the fifth embodiment is arranged above the MR element **11**, even if the external magnetic field with the magnetic field intensity that exceeds the detection range (for example, exceeding 80 mT) is applied to the MR element **11**, the harmonic component V_{3rd} which is included in the output signal from the MR element **11**, becomes nearly the same as the harmonic component V_{3rd} which is included in the output signal when the external magnetic field with 80 mT or less of the magnetic field intensity is applied to the MR element **11**. Consequently, the MR element **11** can output the desired detection signal, making it possible to prevent an increase of an error in position detection of an object.

Sixth Embodiment

FIG. **12A** is an entire schematic perspective view showing the magnetic sensor **1** relating to the sixth embodiment of the

present invention; and FIG. 12B is a schematic cross-sectional view showing the magnetic sensor 1 relating to the sixth embodiment of the present invention. Furthermore, the configuration that is nearly similar to that of the magnetic sensor 1 in the first embodiment is marked with the same symbols and its detailed explanation is omitted.

As shown in FIG. 12A and FIG. 12B, the soft magnetic body shield 12 configuring the magnetic sensor 1 relating to the sixth embodiment has a nearly circular cylindrical shape similar to that of the first embodiment, but is different from the soft magnetic body shield 12 relating to the first embodiment because a through-hole 12h penetrates through the central axis in the thickness direction is formed. The depth h of the through-hole 12h is equivalent to the thickness of the soft magnetic body shield 12. In the Sixth Embodiment, a diameter Wh and the depth h of the through-hole 12h can be adjusted to reduce unevenness of the distribution of the magnetic field intensities of the external magnetic field in the in-plane direction of the MR element 11. The diameter Wh of the through-hole 12h can be appropriately set to 0.03 φ_m or less.

Because the soft magnetic body shield 12 relating to the sixth embodiment is arranged above or below the MR element 11 as similar to the first embodiment, even if the external magnetic field with the magnetic field intensity exceeding the detection range (for example, exceeding 80 mT) is applied to the MR element 11, the harmonic component V_{3rd} which is included in the output signal from the MR element 11, becomes nearly the same as the harmonic component V_{3rd} which is included in the output signal when the external magnetic field with 80 mT or less of the magnetic field intensity is applied to the MR element 11. Consequently, the MR element 11 can output the desired detection signal, making it possible to prevent an increase of an error in position detection of an object.

The embodiments explained above are described to facilitate the understanding of the present invention, but are not described to restrict the present invention. Therefore, elements disclosed in the embodiments above are a concept to include all their design changes and equivalents belonging to the technical scope of the present invention.

In the embodiments above, the MR elements, the TMR element and GMR element having a lamination film structure were exemplified, but the present invention shall not be limited to such modes, and for example, an AMR element having a single film structure of an antiferromagnetic material is also acceptable.

EXAMPLES

The present invention is explained in further detail hereafter by exemplifying examples and the like, but the present invention should be limited to such examples and the like at all.

Example 1

As the magnetic sensor 1 having the configurations shown in FIG. 1A to FIG. 1C, the magnetic sensor 1 was prepared where a plurality of the MR elements 11, where the soft magnetic body shields 12 were arranged above, were arranged in an array manner. In such magnetic sensor 1, the diameter of the nearly-cylindrical MR element 11 was set at φ_m , the diameter φ_s of the nearly-cylindrical soft magnetic body shield 12 was set at 2.0 φ_m and the thickness h was set at φ_m , and the soft magnetic body shields 12 were arranged immediately above the MR elements 11, the arrangement

interval between the MR element 11 and the soft magnetic body shield 12 was set at 0.075 φ_m , and the interval D between the two adjacent soft magnetic body shields 12 (the MR elements 11) was set at 3.3 φ_m . An attenuation effect was confirmed based upon a curve MF_{1X} that was obtained by measuring the magnetic field intensity along the MR elements 11 aligned in the X-axis direction and MF_{1Y} that was obtained by measuring the magnetic field intensity along the MR elements 11 aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor 1 in Example 1 (see FIG. 6). The results are shown in Table 1 and FIG. 13. Furthermore, in the characteristic charts shown in FIGS. 14 to 26, FIG. 27B, FIG. 28B and FIG. 29 to be explained hereafter, the vertical axis indicates a magnetic field intensity MF (unit: mT) and the horizontal axis indicates a position P (unit: μm) of the MR element 11, and the diameter φ_m of the MR element 11 is indicated with a width (two-way arrow) interposed with broken lines extending from the horizontal axis in the vertical direction. In Example 1, since the magnetic field intensities that were measured along the MR elements 11 aligned in the X-axis direction and those that were measured along the MR elements 11 aligned in the Y-axis direction are nearly the same, the curve MF_{1X} and the curve MF_{1Y} are depicted to be nearly overlapped (FIG. 13). Furthermore, a benchmark to assess the attenuation effect of the magnetic field intensity was shown as “○”, “△” and “x” as mentioned below.

[Benchmark to Assess Attenuation Effect]

○: The magnetic field intensity of the external magnetic field to be applied to the MR element 11 remains generally within 20 to 80 mT.

△: Even though the magnetic field intensity of the external magnetic field to be applied to the MR element 11 is partially off 20 to 80 mT, or the flatness of the magnetic field intensity distribution within the plane of the MR element 11 is decreased, the result has reached the standard without any problem in practical use.

x: Most of the magnetic field intensity of the external magnetic field to be applied to the MR element 11 is off 20 to 80 mT, or the flatness of the magnetic field intensity distribution within the plane of the MR element 11 is remarkably deteriorated.

Example 2

The magnetic sensor 1 having the similar configuration to Example 1, except for setting the diameter φ_s of the soft magnetic body shield 12 at 2.6 φ_m , was prepared. An attenuation effect was confirmed based upon a curve MF_{2X} that was obtained by measuring the magnetic field intensity along the MR elements 11 aligned in the X-axis direction and MF_{2Y} that was obtained by measuring the magnetic field intensity along the MR elements 11 aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor 1 in Example 2. The results are shown in Table 1 and FIG. 14. In Example 2, the magnetic field intensities that were measured along the MR elements 11 aligned in the X-axis direction and those that were measured along the MR elements 11 aligned in the Y-axis direction are nearly the same, and the curve MF_{2X} and the curve MF_{2Y} are depicted to be nearly overlapped (FIG. 14).

Example 3

The magnetic sensor 1 having the similar configuration to Example 1, except for setting the thickness h of the soft

19

magnetic body shield **12** at $1.6 \varphi_m$, was prepared. An attenuation effect was confirmed based upon a curve MF_{3X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{3Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 3. The results are shown in Table 1 and FIG. **15**. In Example 3, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{3X} and the curve MF_{3Y} are depicted to nearly overlap (FIG. **15**).

Example 4

The magnetic sensor **1** having the similar configuration to Example 1, except for setting the thickness h of the soft magnetic body shield **12** at $1.3 \varphi_m$, was prepared. An attenuation effect was confirmed based upon a curve MF_{4X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{4Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 4. The results are shown in Table 1 and FIG. **16**. In Example 4, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{4X} and the curve MF_{4Y} are depicted to nearly overlap (FIG. **16**).

Example 5

The magnetic sensor **1** having the similar configuration to Example 1, except for setting the thickness h of the soft magnetic body shield **12** at $0.8 \varphi_m$, was prepared. An attenuation effect was confirmed based upon a curve MF_{5X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{5Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 5. The results are shown in Table 1 and FIG. **17**. In Example 5, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{5X} and the curve MF_{5Y} are depicted to nearly overlap (FIG. **17**).

Example 6

The magnetic sensor **1** having the similar configuration to Example 1, except for setting the configuration shown in FIG. **8A** to FIG. **8B**, i.e., setting the shape of the soft magnetic body shield **12** to be a hexagonal prism, was prepared. An attenuation effect was confirmed based upon a curve MF_{6X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{6Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 6. The results are shown in Table 1 and FIG. **18**. In

20

Example 6, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{6X} and the curve MF_{6Y} are depicted to nearly overlap (FIG. **18**).

Example 7

The magnetic sensor **1** having the similar configuration to Example 1, except for having the configuration shown in FIG. **12A** to FIG. **12B**, i.e., forming the through-hole **12h** with $0.2 \varphi_m$ of diameter in the soft magnetic body shield **12**, was prepared. An attenuation effect was confirmed based upon a curve MF_{7X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{7Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 7. The results are shown in Table 1 and FIG. **19**. In Example 7, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{7X} and the curve MF_{7Y} are depicted to nearly overlap (FIG. **19**).

Example 8

The magnetic sensor **1** having the similar configuration to Example 1, except for having the configuration shown in FIG. **11A** to FIG. **11B**, i.e., setting the shape of the soft magnetic body shield **12** to be nearly conical with $2 \varphi_m$ of the diameter of the bottom surface, and setting the thickness h of the soft magnetic body shield **12** at $2.0 \varphi_m$, was prepared. An attenuation effect was confirmed based upon a curve MF_{8X} (thick line) that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{8Y} (thick line) that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 8. The results are shown in Table 1 and FIG. **20**. In Example 8, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{8X} and the curve MF_{8Y} are depicted to nearly overlap (FIG. **20**).

Example 9

The magnetic sensor **1** having the similar configuration to Example 8, except for setting the thickness h of the soft magnetic body shield **12** at φ_m , was prepared. An attenuation effect was confirmed based upon a curve MF_{9X} (thin line) that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{9Y} (thin line) that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 9. The results are shown in Table 1 and FIG. **20**. In Example 9, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11**

21

aligned in the Y-axis direction are nearly the same, the curve MF_{9X} and the curve MF_{9Y} are depicted to nearly overlap (FIG. 20).

Example 10

The magnetic sensor **1** having the similar configuration to Example 1, except for having the configuration shown in FIG. 9A to FIG. 9B, i.e., having the configuration of the soft magnetic body shield **12** where the columnar portion **12c** and the conical portion **12p** are laminated in respective order, and setting the thickness in the central axis at φ_m , was prepared. An attenuation effect was confirmed based upon a curve MF_{10X} (thin line) that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{10Y} (thin line) that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 10. The results are shown in Table 1 and FIG. 21. In Example 10, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{10X} and the curve MF_{10Y} are depicted to nearly overlap (FIG. 21).

Example 11

The magnetic sensor **1** having the similar configuration to Example 10, except for arranging the soft magnetic body shield **12** immediately below the MR element **11**, was prepared. The magnetic field intensities to be applied to the MR element in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 11 were obtained in the X-axis direction and the Y-axis direction within the plane of the magnetic sensor **1**, and an attenuation effect was confirmed based upon a curve MF_{10X} and a curve MF_{11Y} (thick lines). The results are shown in Table 1 and FIG. 21. In Example 11, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{10X} and the curve MF_{11Y} are depicted to nearly overlap (FIG. 21).

Example 12

The magnetic sensor **1** having the similar configuration to Example 1, except for having the configuration shown in FIG. 10, i.e., forming the mortar-shaped portion **12n** on the upper surface of the soft magnetic body shield **12** and setting the thickness in the central axis at $0.8\varphi_m$, was prepared. The magnetic field intensities to be applied to the MR element in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 12 were obtained in the X-axis direction and the Y-axis direction within the plane of the magnetic sensor **1**, and an attenuation effect was confirmed based upon a curve MF_{12X} and a curve MF_{12Y} (thin lines). The results are shown in Table 1 and FIG. 22. In Example 12, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{12X} and the curve MF_{12Y} are depicted to nearly overlap (FIG. 22).

22

Example 13

The magnetic sensor **1** having the similar configuration to Example 12, except for arranging the soft magnetic body shield **12** immediately below the MR element **11**, was prepared. The magnetic field intensities to be applied to the MR element in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 13 were obtained in the X-axis direction and the Y-axis direction within the plane of the magnetic sensor **1**, and an attenuation effect was confirmed based upon a curve MF_{13X} and a curve MF_{13Y} (thick lines). The results are shown in Table 1 and FIG. 22. In Example 13, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{13X} and the curve MF_{13Y} are depicted to nearly overlap (FIG. 22).

Example 14

The magnetic sensor **1** having the similar configuration to Example 1, except for having the configuration shown in FIG. 5A to FIG. 5B, i.e., arranging the soft magnetic body shield **12** immediately below the MR element **11**, was prepared. The magnetic field intensities to be applied to the MR element in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 14 were obtained in the X-axis direction and the Y-axis direction within the plane of the magnetic sensor **1**, and an attenuation effect was confirmed based upon a curve MF_{14X} and a curve MF_{14Y} . The results are shown in Table 1 and FIG. 23. In Example 14, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{14X} and the curve MF_{14Y} are depicted to nearly overlap (FIG. 23).

Example 15

The magnetic sensor **1** having the similar configuration to Example 1, except for having the configuration shown in FIG. 5C, i.e., arranging the two soft magnetic body shields **12** immediately above and immediately below the MR elements **11**, respectively, was prepared. An attenuation effect was confirmed based upon a curve MF_{15X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{15Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 15. The results are shown in Table 1 and FIG. 24. In Example 15, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{15X} and the curve MF_{15Y} are depicted to nearly overlap (FIG. 24).

Example 16

The magnetic sensor **1** having the similar configuration to Example 1, except for setting the interval D between the adjacent soft magnetic body shields **12** (MR elements **11**) at $2.6\varphi_m$, was prepared. An attenuation effect was confirmed based upon a curve MF_{16X} that was obtained by measuring

23

the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{16Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 16. The results are shown in Table 1 and FIG. 25. In Example 16, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{16X} and the curve MF_{16Y} are depicted to nearly overlap (FIG. 25).

Example 17

The magnetic sensor **1** having the similar configuration to Example 1, except for setting the interval D between the adjacent soft magnetic body shields **12** (MR elements **11**) at $4.0 \varphi_m$, was prepared. An attenuation effect was confirmed based upon a curve MF_{17X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{17Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Example 17. The results are shown in Table 1 and FIG. 26. In Example 17, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{17X} and the curve MF_{17Y} are depicted to nearly overlap (FIG. 26).

Comparative Example 1

The magnetic sensor **1** having the similar configuration to Example 1, except for setting the soft magnetic body shield **12** to be a nearly quadratic prism as shown in FIG. 27A, was prepared. An attenuation effect was confirmed based upon a curve MF_{C1X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{C1Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Comparative Example 1. The results are shown in Table 1 and FIG. 27B. In Comparative Example 1, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{C1X} and the curve MF_{C1Y} are depicted to nearly overlap (FIG. 27B).

Comparative Example 2

The magnetic sensor **1** having the similar configuration to Example 1, except for setting the soft magnetic body shield **12** to be nearly rectangular in a plan view as shown in FIG. 28A, was prepared. In Comparative Example 2, the magnetic sensor **1** where a plurality of the planar-view nearly-rectangular soft magnetic fields **12** that regarded the vertical direction of the drawing as a longitudinal direction were arranged in a direction that was orthogonal to that longitudinal direction was used. An attenuation effect was confirmed based upon a curve MF_{C2X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{C2Y} that was

24

obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Comparative Example 2. The results are shown in Table 1 and FIG. 28B. In Comparative Example 2, the magnetic field intensities measured along the MR elements **11** aligned in the X-axis direction are depicted as the MF_{C2X} , and the magnetic field intensities measured along the MR elements **11** aligned in the Y-axis direction are depicted as the MF_{C2Y} (FIG. 28B).

Comparative Example 3

The magnetic sensor **1** having the similar configuration to Example 1, except for setting the thickness h of the soft magnetic body shield **12** at $0.3 \varphi_m$, was prepared. An attenuation effect was confirmed based upon a curve MF_{C3X} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the X-axis direction and MF_{C3Y} that was obtained by measuring the magnetic field intensity along the MR elements **11** aligned in the Y-axis direction in the case of applying 200 mT of an external magnetic field to the magnetic sensor **1** in Comparative Example 3. The results are shown in Table 1 and FIG. 29. In Comparative Example 3, since the magnetic field intensities that were measured along the MR elements **11** aligned in the X-axis direction and those that were measured along the MR elements **11** aligned in the Y-axis direction are nearly the same, the curve MF_{C3X} and the curve MF_{C3Y} are depicted to be nearly overlapped (FIG. 29).

TABLE 1

	φ_s	h	D	Attenuation effect
Example 1	2.0 φ_m	φ_m	3.3 φ_m	○
Example 2	2.6 φ_m	φ_m	3.3 φ_m	○
Example 3	2.0 φ_m	1.6 φ_m	3.3 φ_m	○
Example 4	1.3 φ_m	φ_m	3.3 φ_m	△
Example 5	2.0 φ_m	0.8 φ_m	3.3 φ_m	△
Example 6	2.0 φ_m	φ_m	3.3 φ_m	○
Example 7	2.0 φ_m	φ_m	3.3 φ_m	○
Example 8	2.0 φ_m	2.0 φ_m	3.3 φ_m	△
Example 9	2.0 φ_m	φ_m	3.3 φ_m	△
Example 10	2.0 φ_m	φ_m	3.3 φ_m	○
Example 11	2.0 φ_m	φ_m	3.3 φ_m	△
Example 12	2.0 φ_m	0.8 φ_m	3.3 φ_m	○
Example 13	2.0 φ_m	0.8 φ_m	3.3 φ_m	△
Example 14	2.0 φ_m	φ_m	3.3 φ_m	○
Example 15	2.0 φ_m	φ_m	3.3 φ_m	○
Example 16	2.0 φ_m	φ_m	2.6 φ_m	△
Example 17	2.0 φ_m	φ_m	4.0 φ_m	○
Comparative Example 1	2.0 φ_m	φ_m	3.3 φ_m	x
Comparative Example 2	2.0 φ_m	φ_m	3.3 φ_m	x
Comparative Example 3	2.0 φ_m	0.3 φ_m	3.3 φ_m	x

55

As it is clear from the results in Table 1, FIGS. 13 to 26, FIG. 27B, FIG. 28B and FIG. 29, because the soft magnetic body shield(s) **12**, in which the diameter φ_s is 1.3 times or more than the diameter φ_m of the MR element **11** and the thickness h of which exceeds 0.3 times the diameter φ_m of the MR element **11**, is positioned above and/or below the MR element(s) and the size of the MR element **11** becomes the size to be physically included within the perimeter of the soft magnetic body shield **12** in a plan view, even if an external magnetic field that exceeds the detection range of the MR element **11** is applied, it has been confirmed that the external magnetic field, the magnetic field intensity of which

65

has been attenuated to that within 20 to 80 mT of the detection range, is applied to the MR element **11**. Further, according to the results above, compared to the soft magnetic body shield having a nearly-quadratic prism shape or nearly rectangular shape in a plan view, with the soft magnetic body shield having nearly cylindrical shape, a columnar shape where its shape in a plan view is N-sided polygon (N is 6 or greater even number), a shape in which a conical portion is positioned on a columnar portion, a shape in which a convexity of an N-sided pyramid (N is 6 or greater even number) on an N-sided prism (N is 6 or greater even number), a columnar shape in which an upper surface is sagged to be the mortar-shaped, a nearly-conical shape, or an N-sided pyramid shape (N is 6 or greater even number) or the like, it has been confirmed that the magnetic field intensity is attenuated to 20 to 80 mT of the detection range, and, the magnetic field intensity will not be substantially changed within the plane of the MR element **11**. Thus, it is inferred that a positional detection error, such as a rotational position or a linear displacement of an object, can be reduced if the magnetic sensor **1** that fulfills the requirements above is used.

DESCRIPTION OF SYMBOLS

- 1** . . . magnetic sensor
11 . . . magnetoresistive effect element (MR element)
12 . . . soft magnetic body shield
12c . . . columnar portion (prismatic portion)
12p . . . conical portion (convexity)
12n . . . mortar-shaped portion (concave portion)
12h . . . through-hole

What is claimed is:

1. A magnetic sensor comprising:
 - a plurality of magnetoresistive effect elements (MR elements), which can detect an external magnetic field, and
 - a plurality of soft magnetic body shields, wherein the plurality of MR elements are laminated on and/or under the plurality of soft magnetic body shields in a side view, respectively,
 - the size of each of the MR elements is physically included within a perimeter of each of the soft magnetic body shields in a plan view, and
 - the plurality of the MR elements is two-dimensionally arranged in an array.
2. The magnetic sensor according to claim **1**, wherein all intervals between adjacent MR elements are the same.
3. The magnetic sensor according to claim **1**, wherein a shape of each of the soft magnetic body shields in the plan view is nearly circular.
4. The magnetic sensor according to claim **1**, wherein a shape of each of the soft magnetic body shields in the plan view is an N-sided polygon (N is 6 or greater even number).
5. The magnetic sensor according to claim **1**, wherein each of the soft magnetic body shields is columnar.
6. The magnetic sensor according to claim **1**, wherein each of the soft magnetic body shields is conical.
7. The magnetic sensor according to claim **1**, wherein each of the soft magnetic body shields includes a first ridge line, and a second ridge line and a third ridge line that are inclined with respect to the first ridge line in the side view, the first ridge line is parallel to an arrangement direction of the plurality of MR elements, and the second ridge line and the third ridge line are non-parallel to each other.

8. The magnetic sensor according to claim **1**, wherein each of the soft magnetic body shields includes a columnar portion that comprises a first surface and a second surface, wherein the second surface faces the first surface, and a convexity, which protrudes from the first surface of the columnar portion and is positioned to allow the second surface to face each of the MR elements.

9. The magnetic sensor according to claim **1**, wherein each of the soft magnetic body shields includes a columnar portion that comprises a first surface and a second surface, wherein the second surface faces the first surface, and a convexity, which protrudes from the first surface of the columnar portion.

10. The magnetic sensor according to claim **1**, wherein each of the soft magnetic body shields includes a columnar portion that comprises a first surface and a second surface, wherein the second surface faces the first surface, and a concave portion, which is formed on the first surface of the columnar portion and is positioned to allow the second surface to face each of the MR elements.

11. The magnetic sensor according to claim **1**, wherein each of the soft magnetic body shields includes a columnar portion that comprises a first surface and a second surface, wherein the second surface faces the first surface, and a concave portion, which is formed on the first surface of the columnar portion.

12. The magnetic sensor according to claim **1**, wherein each of the soft magnetic body shields comprises a through-hole that penetrates through the soft magnetic body shield in a thickness direction.

13. The magnetic sensor according to claim **1**, wherein a diameter φ_s of each of the soft magnetic body shields and a diameter φ_m of each of the MR elements fulfill a relationship in a following formula (1):

$$\varphi_s \geq 1.3 \varphi_m. \quad (1)$$

14. The magnetic sensor according to claim **1**, wherein thickness h of each of the soft magnetic body shields and a diameter φ_m of each of the MR elements fulfill a relationship in a following formula (2):

$$h > 0.3 \varphi_m. \quad (2)$$

15. The magnetic sensor according to claim **1**, wherein a harmonic component V_{3rd} , which is output in the case of applying the external magnetic field with a magnetic field intensity that exceeds 70 mT (Millitesla) to each of the MR elements, and the harmonic component V_{3rd} , which is output in the case of applying the external magnetic field with 70 mT or less of a magnetic field intensity to each of the MR elements, are the same.

16. The magnetic sensor according to claim **1**, wherein a diameter φ_s of the soft magnetic body shield is 2.00 to 2.75 times a diameter φ_m of the corresponding MR element.

17. A magnetic sensor comprising:

- a plurality of magnetoresistive effect elements (MR elements), which can detect an external magnetic field, and
- a plurality of soft magnetic body shields, wherein the plurality of MR elements are laminated on and/or under the plurality of soft magnetic body shields in a side view, respectively,

27

the size of each of the MR elements is physically included within a perimeter of each of the soft magnetic body shields in a plan view,

the plurality of the MR elements is two-dimensionally arranged in an array,

each of the soft magnetic body shields includes a first ridge line, and a second ridge line and a third ridge line that are inclined with respect to the first ridge line in the side view,

the first ridge line is parallel to an arrangement direction of the plurality of MR elements,

the second ridge line and the third ridge line are non-parallel to each other.

18. A magnetic sensor comprising:

a plurality of magnetoresistive effect elements (MR elements), which can detect an external magnetic field, and

a plurality of soft magnetic body shields, wherein the plurality of MR elements are laminated on and/or under the plurality of soft magnetic body shields in a side view, respectively,

the size of each of the MR elements is physically included within a perimeter of each of the soft magnetic body shields in a plan view,

the plurality of the MR elements is two-dimensionally arranged in an array, and

28

each of the soft magnetic body shields includes a columnar portion that comprises a first surface and a second surface, wherein the second surface faces the first surface, and a convexity, which protrudes from the first surface of the columnar portion.

19. A magnetic sensor comprising:

a plurality of magnetoresistive effect elements (MR elements), which can detect an external magnetic field, and

a plurality of soft magnetic body shields, wherein the plurality of MR elements are laminated on and/or under the plurality of soft magnetic body shields in a side view, respectively,

the size of each of the MR elements is physically included within a perimeter of each of the soft magnetic body shields in a plan view,

the plurality of the MR elements is two-dimensionally arranged in an array, and

each of the soft magnetic body shields includes a columnar portion that comprises a first surface and a second surface, wherein the second surface faces the first surface, and a concave portion, which is formed on the first surface of the columnar portion.

* * * * *