



US011702580B2

(12) **United States Patent**
Dietl et al.

(10) **Patent No.:** **US 11,702,580 B2**
(45) **Date of Patent:** ***Jul. 18, 2023**

(54) **COOLANT FOR COOLING SYSTEMS IN ELECTRIC VEHICLES HAVING FUEL CELLS AND/OR BATTERIES CONTAINING AZOLE DERIVATIVES AND ADDITIONAL CORROSION PROTECTANTS**

(58) **Field of Classification Search**
CPC ... C09K 5/20; C09K 5/00; C09K 5/08; C09K 5/10

See application file for complete search history.

(71) Applicant: **BASF SE**, Ludwigshafen am Rhein (DE)

(56) **References Cited**

U.S. PATENT DOCUMENTS

(72) Inventors: **Harald Dietl**, Ludwigshafen (DE); **Roger Sieg**, Ludwigshafen (DE)

3,931,029	A	1/1976	Dutton et al.
4,704,220	A	11/1987	Goddard et al.
7,307,104	B2	12/2007	Qiu et al.
2003/0052302	A1	3/2003	Eaton et al.
2006/0219975	A1	10/2006	Wenderoth et al.
2009/0266519	A1	10/2009	Marinho et al.
2012/0064426	A1	3/2012	Sato et al.
2013/0092870	A1	4/2013	Ha et al.
2013/0284971	A1	10/2013	Dietl et al.
2014/0056756	A1	2/2014	Dietl et al.
2015/0203735	A1	7/2015	Dietl et al.
2016/0075930	A1	3/2016	Dietl et al.
2016/0257868	A1	9/2016	Yang et al.
2018/0291250	A1	10/2018	Yang et al.
2019/0225855	A1	7/2019	Yang et al.
2020/0040244	A1	2/2020	Yang et al.

(73) Assignee: **BASF SE**, Ludwigshafen am Rhein (DE)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **17/567,963**

(22) Filed: **Jan. 4, 2022**

(65) **Prior Publication Data**

US 2022/0127510 A1 Apr. 28, 2022

Related U.S. Application Data

(63) Continuation of application No. 16/461,696, filed as application No. PCT/EP2017/079162 on Nov. 14, 2017, now Pat. No. 11,248,155.

(30) **Foreign Application Priority Data**

Nov. 23, 2016 (EP) 16200197

(51) **Int. Cl.**

C09K 5/20	(2006.01)
H01M 10/613	(2014.01)
H01M 10/625	(2014.01)
H01M 10/6567	(2014.01)
H01M 8/04029	(2016.01)
H01M 8/04701	(2016.01)
C09K 5/08	(2006.01)
C09K 5/00	(2006.01)
C09K 5/10	(2006.01)

(52) **U.S. Cl.**

CPC **C09K 5/20** (2013.01); **C09K 5/00** (2013.01); **C09K 5/08** (2013.01); **C09K 5/10** (2013.01); **H01M 8/04029** (2013.01); **H01M 8/04701** (2013.01); **H01M 10/613** (2015.04); **H01M 10/625** (2015.04); **H01M 10/6567** (2015.04); **H01M 2220/20** (2013.01); **H01M 2250/20** (2013.01)

FOREIGN PATENT DOCUMENTS

DE	194 87 94	4/1971
DE	198 02 490	7/1999
DE	100 63 951	6/2002
DE	101 04 771	8/2002
EP	1 009 050	6/2000
EP	2 549 575	1/2013
EP	2 888 386	7/2015
KR	20150003377 A	1/2015
WO	00/02978	1/2000
WO	00/17951	3/2000
WO	00/50543	8/2000
WO	02/101848	12/2002
WO	2009/124979	10/2009
WO	2014/029654	2/2014

OTHER PUBLICATIONS

Extended European Search Report dated May 23, 2017 in Patent Application No. 16200197.8.
International Search Report dated Feb. 13, 2018 in PCT/EP2017/079162 filed Nov. 14, 2017.

Primary Examiner — Jane L Stanley

(74) *Attorney, Agent, or Firm* — Grüneberg and Myers PLLC

(57) **ABSTRACT**

Coolants based on alkylene glycols or derivatives thereof are useful for cooling systems in electric vehicles having fuel cells and/or batteries, preferably for motor vehicles, particularly preferably for passenger cars and commercial vehicles (known as light and heavy duty vehicles). The coolants contain additional corrosion inhibitors for improved corrosion protection in addition to specific azole derivatives.

19 Claims, No Drawings

**COOLANT FOR COOLING SYSTEMS IN
ELECTRIC VEHICLES HAVING FUEL
CELLS AND/OR BATTERIES CONTAINING
AZOLE DERIVATIVES AND ADDITIONAL
CORROSION PROTECTANTS**

CROSS-REFERENCE TO RELATED
APPLICATIONS

This application is a continuation of U.S. application Ser. No. 16/461,696, filed on May 16, 2019, which was the National Stage entry under § 371 of International Application No. PCT/EP2017/079162, filed on Nov. 14, 2017, and which claims the benefit of priority to European Application No. 16200197.8, filed on Nov. 23, 2016. The content of each of these applications is hereby incorporated by reference in its entirety.

The present invention relates to coolants for cooling systems in electric vehicles having fuel cells and/or batteries, preferably in motor vehicles, particularly preferably in passenger cars and commercial vehicles (known as light and heavy duty vehicles), based on alkylene glycols or derivatives thereof, which contain additional corrosion inhibitors in addition to specific azole derivatives for improved corrosion protection.

Fuel cells and/or batteries for mobile use, in particular in motor vehicles, have to be able to be operated even at low exterior temperatures of down to about -40°C . A freezing-protected coolant circuit is therefore indispensable.

The use of conventional cooler protection compositions used in internal combustion engines would not be possible in the case of fuel cells and/or batteries without complete electric insulation of the cooling channels, since these compositions have an undesirably high electrical conductivity because of the salts and ionizable compounds comprised therein as corrosion inhibitors, which would adversely affect the function of the fuel cell or battery.

DE-A 198 02 490 (1) describes fuel cells having a freezing-protected cooling circuit in which a paraffinic isomer mixture having a pour point of less than -40°C . is used as coolant. However, the combustibility of such a coolant is disadvantageous.

EP-A 1 009 050 (2) discloses a fuel cell system for automobiles, in which air is used as cooling medium. However, this has the disadvantage that air is, as is known, a poorer heat conductor than a liquid cooling medium.

WO 00/17951 (3) describes a cooling system for fuel cells, in which a pure monoethylene glycol/water mixture in a ratio of 1:1 without additives is used as coolant. Since no corrosion protection at all would be present in respect of the materials present in the cooling system because of a lack of corrosion inhibitors, the cooling circuit comprises an ion-exchange unit in order to maintain the purity of the coolant and ensure a low specific conductivity over a prolonged period of time, as a result of which short circuits and corrosion are prevented. As suitable ion exchangers, mention is made of anionic resins such as those of the strongly alkaline hydroxyl type and cationic resins such as those based on sulfonic acid groups and also other filtration units such as activated carbon filters.

The structure and the function of a fuel cell for automobiles, in particular a fuel cell having an electron-conducting electrolyte membrane ("PEM fuel cell", "polymer electrolyte membrane fuel cell") is described by way of example in (3), with aluminum being preferred as preferred metal component in the cooling circuit (cooler).

WO 02/101848 A2 describes antifreeze compositions for cooling systems in fuel cell drives and concentrates thereof which comprise particular azole derivatives.

The antifreeze compositions display good corrosion protection on aluminum samples, but no longer satisfy modern requirements in respect of corrosion of iron and nonferrous metals.

DE-A 100 63 951 (4) describes coolants for cooling systems in fuel cell drives, which comprise ortho-silicic esters as corrosion inhibitors.

US 2012/0064426 A1 discloses coolants for fuel cells which comprise an ion exchanger, which coolants comprise ethylene glycol or propylene glycol as antifreeze component and inhibitors, for example, inter alia, azoles, against aluminum corrosion and also polyoxyethylene alkyl ethers or polyoxyethylene fatty acid esters as surface-active agents.

Apart from aluminum corrosion, no further corrosion is examined and the polyoxyethylene alkyl ethers or polyoxyethylene fatty acid esters used are employed exclusively as surface-active agents.

A main problem in cooling systems in fuel cell drives is, compared to conventional coolants, maintenance of a low electrical conductivity of the coolant in order to ensure safe and malfunction-free function of the fuel cell and batteries connected thereto and to prevent short circuits and corrosion in the long term.

U.S. Pat. No. 3,931,029 discloses antifreeze compositions which comprise ethylene glycol or diethylene glycol as antifreeze component and alkoxyated higher fatty acids or fatty amines as antifoams and also inorganic compounds as further inhibitors.

These inorganic compounds in these compositions are preferably used as alkali metal salts or ammonium salts, so that the compositions comprise a significant proportion of ionic constituents, so that these compositions are not suitable for use in fuel cells because of their inherent conductivity.

WO 2014 029654 A1 discloses corrosion protection formulations which can contain further additives in addition to glycols and polyalkylene glycols as antifreeze components and alkylamine ethoxylates as surfactant component. When choosing such additives, no attention is paid to the conductivity and anionic and cationic surfactants are also disclosed, with borax for adjusting the pH and carboxylic acids in the form of their salts.

These compositions, too, thus comprise a significant proportion of ionic constituents and are not suitable for use in fuel cells because of their inherent conductivity.

The same applies to U.S. Pat. No. 4,704,220, in which compositions which comprise at least one emulsifier and at least one organic hydrophobicizing agent and can be used as concentrates after dilution with water as coolant are described. The organic hydrophobicizing agent bears salt-forming groups and the emulsifier can also be anionic or cationic compounds. Inorganic compounds are added in a targeted manner to the water with which the compositions are admixed in the examples.

These compositions, too, thus comprise a significant proportion of ionic constituents and are not suitable for use in fuel cells because of their inherent conductivity.

It was an object of the present invention to make the antifreeze compositions known from WO 02/101848 A2 more corrosion-stable relative to metals other than aluminum.


It has now been found that the duration of a low electrical conductivity in a cooling system based on alkylene glycol/water can be significantly lengthened by addition of small

amounts of azole derivatives even and particularly when it comprises, as per (3), an integrated ion exchanger. The good protection of aluminum and aluminum-comprising alloys against corrosion described in WO 02/101848 A2 is also offered for other metals, in particular iron materials, iron-comprising alloys and nonferrous metals, among these copper and brass in particular, by the use according to the invention of the compounds (V), (VI) and/or (VII). This covers in practice the advantage that the time intervals between two coolant changes for fuel cells can be extended further, which is of particular interest in the automobile sector.

Accordingly, we have found antifreeze concentrates for cooling systems in fuel cells and/or batteries, from which ready-to-use aqueous coolant compositions having a conductivity of not more than 50 $\mu\text{S}/\text{cm}$ result, based on alkylene glycols or derivatives thereof which comprise one or more five-membered heterocyclic compounds (azole derivatives) having 2 or 3 heteroatoms from the group consisting of nitrogen and sulfur and comprise no or at most one sulfur atom and can bear an aromatic or saturated six-membered fused-on ring, and additionally comprise at least one of the compounds (V), (VI) and/or (VII). Preference is here given to antifreeze concentrates which comprise a total of from 0.05 to 5% by weight, in particular from 0.075 to 2.5% by weight, especially from 0.1 to 1% by weight, of the azole derivatives mentioned. Preference is given here to antifreeze compositions which comprise a total of from 0.05 to 5% by weight, in particular from 0.1 to 1% by weight, especially from 0.2 to 0.5% by weight, of at least one of the compounds (V), (VI) and/or (VII).

These five-membered heterocyclic compounds (azole derivatives) usually contain two N atoms and no S atom, 3 N atoms and no S atom or one N atom and one S atom as heteroatoms.

Preferred groups of the specified azole derivatives are annellated imidazoles and annellated 1,2,3-triazoles of the general formula




where

the variable R is hydrogen or a $\text{C}_1\text{-C}_{10}$ -alkyl radical, in particular methyl or ethyl, and

the variable X is a nitrogen atom or the C—H group.

Typical and preferred examples of azole derivatives of the general formula (I) are benzimidazole ($\text{X}=\text{C}-\text{H}$, $\text{R}=\text{H}$), benzotriazoles ($\text{X}=\text{N}$, $\text{R}=\text{H}$) and toluotriazole (tolyltriazole) ($\text{X}=\text{N}$, $\text{R}=\text{CH}_3$). A typical example of an azole derivative of the general formula (II) is hydrogenated 1,2,3-tolotriazole (tolyltriazole) ($\text{X}=\text{N}$, $\text{R}=\text{CH}_3$).

A further preferred group of the specified azole derivatives is benzothiazoles of the general formula (III)




where

the variable R is as defined above and

the variable R' is hydrogen, a $\text{C}_1\text{-C}_{10}$ -alkyl radical, in particular methyl or ethyl, or in particular a mercapto group ($-\text{SH}$). A typical example of an azole derivative of the general formula (III) is 2-mercaptobenzothiazole.

Further suitable azole derivatives are non-annellated azole derivatives of the general formula (IV)



(IV)

where

the variables X and Y together are two nitrogen atoms or one nitrogen atom and a C—H group,

for example 1H-1,2,4-triazole ($\text{X}=\text{Y}=\text{N}$) or preferably imidazole ($\text{X}=\text{N}$, $\text{Y}=\text{C}-\text{H}$).


For the purposes of the present invention, benzimidazole, benzotriazole, toluotriazole, hydrogenated toluotriazole or mixtures thereof, in particular benzotriazole or toluotriazole, are very particularly preferred as azole derivatives.

The azole derivatives mentioned are commercially available or can be prepared by conventional methods. Hydrogenated benzotriazoles such as hydrogenated toluotriazole are likewise obtainable as described in DE-A 1 948 794 (5) and are also commercially available.

Apart from the azole derivatives mentioned, the antifreeze concentrates of the invention preferably additionally comprise ortho-silicic esters as are described in (4). Typical examples of such ortho-silicic esters are tetraalkoxysilanes, preferably tetramethoxysilane and tetraethoxysilane, and alkoxyalkylsilanes, preferably triethoxymethylsilane, diethoxydimethylsilane, ethoxytrimethylsilane, trimethoxymethylsilane, dimethoxydimethylsilane and methoxytrimethylsilane. Preference is given to tetraalkoxysilanes, particularly preferably tetramethoxysilane and tetraethoxysilane, with very particular preference being given to tetraethoxysilane. Preference is given here to antifreeze concentrates, in particular those having a total content of from 0.05 to 5% by weight of the azole derivative mentioned, from which ready-to-use aqueous coolant compositions having a silicon content of from 2 to 2000 ppm by weight of silicon, in particular from 25 to 500 ppm by weight of silicon, result.


According to the invention, the antifreeze compositions and antifreeze concentrates of the present invention comprise at least one compound selected from the group consisting of compounds of the formula (V), compounds of the formula (VI), compounds of the formula (VII) and mixtures thereof.

These are compounds of the general formula (V)




5

of the general formula (VI)



and also of the general formula (VII)



where

R^1 is an organic radical having from 7 to 21 carbon atoms, in particular an alkyl or alkenyl radical having from 7 to 21 carbon atoms, preferably from 9 to 19, particularly preferably from 11 to 19, very particularly preferably from 13 to 19, in particular from 15 to 19 and especially 17, carbon atoms,

R^2 is an organic radical having from 8 to 22 carbon atoms, in particular an alkyl or alkenyl radical having from 8 to 22 carbon atoms, preferably from 10 to 20, particularly preferably from 12 to 20, very particularly preferably from 14 to 20, in particular from 16 to 20 and especially 18, carbon atoms,

R^3 is an organic radical having from 6 to 10 carbon atoms, in particular an alkyl or alkenyl radical having from 6 to 10 carbon atoms, preferably from 7 to 9 and particularly preferably 8 carbon atoms,

n is a positive integer from 10 to 60, preferably from 12 to 50, particularly preferably from 15 to 40, very particularly preferably from 18 to 30 and in particular from 20 to 25, p and q are each, independently of one another, a positive integer from 1 to 40, preferably from 1 to 30, particularly preferably from 2 to 25, very particularly preferably from 3 to 20 and in particular from 5 to 15, and

each X_i for $i=1$ to n , 1 to p and 1 to q is selected independently from the group consisting of $-CH_2-CH_2-O-$, $-CH_2-CH(CH_3)-O-$, $-CH(CH_3)-CH_2-O-$, $-CH_2-C(CH_3)_2-O-$, $-C(CH_3)_2-CH_2-O-$, $-CH_2-CH(C_2H_5)-O-$, $-CH(C_2H_5)-CH_2-O-$, $-CH(CH_3)-CH(CH_3)-O-$, $-CH_2-CH_2-CH_2-O-$ and $-CH_2-CH_2-CH_2-CH_2-O-$, preferably selected from the group consisting of $-CH_2-CH_2-O-$, $-CH_2-CH(CH_3)-O-$ and $-CH(CH_3)-CH_2-O-$, with particular preference being given to $-CH_2-CH_2-O-$.

It should be noted that the compounds of the formulae (V), (VI) and (VII) are usually reaction mixtures having a distribution of the product composition which depends on the reaction conditions. Thus, the length of the chain $-[X_i]-$ is subject to a distribution about a statistical average, so that the values for n , p and q can be distributed about a statistical average. Thus, the value for n , p and q for each individual compound of the formula (V), (VI) or (VII) is a positive integer, but for the reaction mixture can on statistical average also have nonintegral values.

Among these, compounds of the formulae (V) and (VII) are preferred, and compounds of the formula (VII) are particularly preferred.

In a preferred embodiment of the present invention, the structural element R^1-COO- in formula (V) is derived from fatty acids or mixtures thereof, preferably from 2-ethylhexanoic acid, octanoic acid (caprylic acid), pelargonic

6

acid (nonanoic acid), 2-propylheptanoic acid, decanoic acid (capric acid), undecanoic acid, dodecanoic acid (lauric acid), tridecanoic acid, tetradecanoic acid (myristic acid), pentadecanoic acid, palmitic acid (hexadecanoic acid), palmitoleic acid [(9Z)-hexadec-9-enoic acid], margaric acid (heptadecanoic acid), stearic acid (octadecanoic acid), oleic acid [(9Z)-octadec-9-enoic acid], elaidic acid [(9E)-octadec-9-enoic acid], linoleic acid [(9Z,12Z)-octadeca-9,12-dienoic acid], linolenic acid [(9Z,12Z,15Z)-octadeca-9,12,15-trienoic acid], eleostearic acid [(9Z,11E,13E)-octadeca-9,11,13-trienoic acid], ricinoleic acid ((R)-12-hydroxy-(Z)-octadec-9-enoic acid), isoricinoleic acid [(S)-9-hydroxy-(2)-octadec-12-enoic acid], nonadecanoic acid, arachidic acid (eicosanoic acid), behenic acid (docosanoic acid) and erucic acid [(13Z)-docos-13-enoic acid].

Among these, the structural element R^1-COO- in formula (V) is preferably derived from decanoic acid (capric acid), dodecanoic acid (lauric acid), tetradecanoic acid (myristic acid), palmitic acid (hexadecanoic acid), palmitoleic acid [(9Z)-hexadec-9-enoic acid], stearic acid (octadecanoic acid), oleic acid [(9Z)-octadec-9-enoic acid] or arachidic acid (eicosanoic acid), particularly preferably from tetradecanoic acid (myristic acid), palmitic acid (hexadecanoic acid), palmitoleic acid [(9Z)-hexadec-9-enoic acid], stearic acid (octadecanoic acid), oleic acid [(9Z)-octadec-9-enoic acid], ricinoleic acid ((R)-12-hydroxy-(Z)-octadec-9-enoic acid), isoricinoleic acid [(5)-9-hydroxy-(2)-octadec-12-enoic acid] or arachidic acid (eicosanoic acid), very particularly preferably from palmitic acid (hexadecanoic acid), palmitoleic acid [(9Z)-hexadec-9-enoic acid], stearic acid (octadecanoic acid), oleic acid [(9Z)-octadec-9-enoic acid] or arachidic acid (eicosanoic acid) and in particular from stearic acid (octadecanoic acid).

Particular mention may be made of the twenty-fold, forty-fold and sixty-fold ethoxylated alkoxyates thereof.

In a further preferred embodiment, it is possible to employ fatty acid mixtures which are obtainable industrially from the work-up of natural, vegetable or animal fats and oils, particularly preferably from linseed oil, coconut oil, palm kernel oil, palm oil, soy oil, peanut oil, cocoa butter, shea butter, cottonseed oil, maize oil, sunflower oil, rapeseed oil or castor oil, very particularly preferably from linseed oil, palm oil, soy oil, peanut oil, cocoa butter, shea butter, cottonseed oil, maize oil, sunflower oil, rapeseed oil or castor oil.

Mixtures of saturated and unsaturated fatty acids can also be employed.

The compounds (V) are, for example, obtainable by reaction of the respective acids or esters, preferably the C_1-C_4 -alkyl esters or glycerides, having the structural element R^1-COO- in formula (V) with the respective alcohol $HO-[X_i]_n-H$ in an esterification or transesterification under known conditions.

The respective acids R^1-COOH or salts thereof are preferably, however, reacted with alkylene oxides to the desired average statistical degree of alkoxylation, preferably under basic conditions. This is particularly preferred when the structural unit X_i is derived from ethylene oxide or propylene oxide, preferably from ethylene oxide.

According to the invention, the compounds (V) reduce corrosion, in particular nonferrous metal corrosion, but can also perform other tasks in the coolant compositions of the invention, for example reducing foam formation (antifoams, defoamers). Among the compounds (V), preference is given to those which reduce both foam formation and corrosion, in particular nonferrous metal corrosion, with particular pref-

erence being given to those which do not significantly influence foam formation but reduce corrosion, in particular nonferrous metal corrosion.

In the compounds of the formula (VI), the structural element R^2-O- is preferably derived from fatty alcohols which are preferably obtainable by hydrogenation of fatty acids and esters, particularly preferably by hydrogenation of the abovementioned fatty acids. In a particular embodiment, the radical R^2 is thus a R^1-CH_2- radical. What has been said above with regard to the fatty acids also applies analogously to the fatty alcohols.

In a preferred embodiment, the fatty alcohols are octyl alcohol (capryl alcohol), nonyl alcohol (pelargonyl alcohol), decyl alcohol (capric alcohol), undecyl alcohol, dodecyl alcohol (lauryl alcohol), tridecyl alcohol, tetradecyl alcohol (myristyl alcohol), pentadecyl alcohol, hexadecyl alcohol (cetyl alcohol, palmityl alcohol), heptadecyl alcohol, octadecyl alcohol (stearyl alcohol), oleyl alcohol, elaidyl alcohol, linoleyl alcohol, linolenoyl alcohol, nonadecyl alcohol, eicosyl alcohol (arachyl alcohol) or mixtures thereof.

In a preferred embodiment, the compounds of the formula (VI) are alkoxyated castor oils, particularly preferably hydrogenated alkoxyated castor oils, very particularly preferably ethoxyated, propoxyated and/or butoxyated castor oils, in particular ethoxyated castor oils.

Further examples of alcohols having the structural element R^2-O- are n-octanol, 2-ethylhexanol, 2-propylheptanol, tridecanol isomer mixtures and heptadecanol isomer mixtures.

Particular mention may be made of the twenty-fold and forty-fold ethoxyated alkoxyates thereof.

A tridecanol isomer mixture as parent alcohol R^2-OH is a mixture of alcohols having 13 carbon atoms, particularly preferably a mixture obtainable by hydroformylation from a C_{12} -olefin mixture which is in turn obtainable by oligomerization of an olefin mixture comprising predominantly hydrocarbons having four carbon atoms.

On statistical average, this olefin mixture has from 11 to 13 carbon atoms, preferably from 11.1 to 12.9, particularly preferably from 11.2 to 12.8, very particularly preferably from 11.5 to 12.5 and in particular from 11.8 to 12.2.

In a very particularly preferred embodiment, this alcohol R^1-OH has an average degree of branching, measured as ISO index, of from 2.8 to 3.7.

In particular, this alcohol R^2-OH is obtained by a process as described in WO 00/02978 or WO 00/50543.

A heptadecanol isomer mixture as parent alcohol R^2-OH is a mixture of alcohols having 17 carbon atoms, particularly preferably a mixture which is obtainable by hydroformylation of a C_{16} -olefin mixture which in turn is obtainable by oligomerization of an olefin mixture which predominantly comprises hydrocarbons having four carbon atoms.

On statistical average, this olefin mixture has from 15 to 17 carbon atoms, preferably from 15.1 to 16.9, particularly preferably from 15.2 to 16.8, very particularly preferably from 15.5 to 16.5 and in particular from 15.8 to 16.2.

In a very particularly preferred embodiment, this alcohol R^1-OH has an average degree of branching, measured as ISO index, of from 2.8 to 3.7.

In particular, this alcohol R^1-OH is obtained by a process as described in WO 2009/124979 A1, there in particular page 5, line 4 to page 16, line 29, and also the examples of page 19, line 19 to page 21, line 25, which is hereby incorporated by reference into the present disclosure.

A C_{17} -alcohol mixture having particularly advantageous use properties can be prepared by this preferred process as product of the transition metal-catalyzed oligomerization of

olefins having from 2 to 6 carbon atoms. Here, a C_{16} -olefin mixture is firstly isolated by distillation from the product of the olefin oligomerization and only subsequently is this C_{16} -olefin mixture subjected to hydroformylation. This makes it possible to provide a more highly branched C_{17} -alcohol mixture having particularly advantageous use properties.

The compounds (VI) are preferably obtainable by reacting the corresponding alcohols R^2-OH with alkylene oxides to the desired average statistical degree of alkoxylation, preferably under basic conditions. This is particularly preferred when the structural unit X_i is derived from ethylene oxide or propylene oxide, preferably from ethylene oxide.

According to the invention, the compounds (VI) reduce corrosion, in particular nonferrous metal corrosion, but can also perform other tasks in the coolant compositions of the invention, for example reducing foam formation (antifoams, defoamers). Among the compounds (V), preference is given to those which reduce both foam formation and also corrosion, in particular nonferrous metal corrosion, with particular preference being given to those which do not significantly influence foam formation but reduce corrosion, in particular nonferrous metal corrosion.

In the compounds of the formula (VII), the structural element $R^3-N<$ is preferably derived from fatty amines which are preferably obtainable by hydrogenation and amination of fatty acids and esters, particularly preferably by hydrogenation and amination of the abovementioned fatty acids or amination of the abovementioned fatty alcohols. What has been said with regard to the fatty alcohols also applies analogously to the fatty amines.

As radicals R^3 , preference is given to alkyl radicals over alkenyl radicals.

In a preferred embodiment, the fatty amines are n-hexylamine, 2-methylpentylamine, n-heptylamine, 2-heptylamine, isoheptylamine, 1-methylhexylamine, n-octylamine, 2-ethylhexylamine, 2-aminooctane, 6-methyl-2-heptylamine, n-nonylamine, isononylamine, n-decylamine and 2-propylheptylamine or mixtures thereof.

Particular preference is given to n-hexylamine, n-octylamine, 2-ethylhexylamine and n-decylamine, with n-octylamine and 2-ethylhexylamine, in particular n-octylamine, being particularly preferred.

Particular mention may be made of two-fold, eight-fold, twenty-fold and forty-fold ethoxyated n-octylamine and also eight-fold, twenty-fold and forty-fold ethoxyated n-hexylamine.

In the alkoxyated amines of the general formula (VII), the degree of alkoxylation refers to the sum (p+q), i.e. to the average total number of alkoxylation units per molecule of amine.

The compounds (VII) are preferably obtainable by reacting the corresponding amines R^3-NH_2 with alkylene oxides to the desired average statistical degree of alkoxylation, preferably under basic conditions. This is particularly preferred when the structural unit X_i is derived from ethylene oxide or propylene oxide, preferably from ethylene oxide.

The compounds of the formulae (V) to (VII), preferably the compounds of the formulae (V) and (VII), particularly preferably the compounds of the formula (VII), are particularly suitable for reducing nonferrous metal corrosion in the use of coolant compositions in fuel cells and are accordingly added to the coolant compositions in a method according to the invention.

Ready-to-use aqueous coolant compositions which have a conductivity of not more than 50 $\mu S/cm$, preferably up to 40

$\mu\text{S}/\text{cm}$, particularly preferably up to 30 and in particular up to 20 $\mu\text{S}/\text{cm}$, and consist essentially of

(a) from 10 to 90% by weight of alkylene glycols or derivatives thereof,

(b) from 90 to 10% by weight of water,

(c) from 0.005 to 5% by weight, in particular from 0.0075 to 2.5% by weight, especially from 0.01 to 1% by weight, of the azole derivatives mentioned, and

(d) optionally at least one ortho-silicic ester and also

(e) from 0.05 to 5% by weight, in particular from 0.1 to 1% by weight, especially from 0.2 to 0.5% by weight, of at least one of the compounds (V), (VI) and/or (VII)

can be produced from the antifreeze concentrates of the invention by dilution with ion-free water. The sum of all components here is 100% by weight.

The present invention therefore also provides ready-to-use aqueous coolant compositions for cooling systems in fuel cells and/or batteries, which consist essentially of

(a) from 10 to 90% by weight of alkylene glycols or derivatives thereof,

(b) from 90 to 10% by weight of water,

(c) from 0.005 to 5% by weight, in particular from 0.0075 to 2.5% by weight, especially from 0.01 to 1% by weight, of the azole derivatives mentioned, and

(d) optionally at least one ortho-silicic ester and also

(e) from 0.05 to 5% by weight, in particular from 0.1 to 1% by weight, especially from 0.2 to 0.5% by weight, of at least one of the compounds (V), (VI) and/or (VII)

and are obtainable by dilution of the specified antifreeze concentrates with ion-free water. The sum of all components here is 100% by weight.

The ready-to-use aqueous coolant compositions of the invention have an initial electrical conductivity of not more than 50 $\mu\text{S}/\text{cm}$, in particular 25 $\mu\text{S}/\text{cm}$, preferably 10 $\mu\text{S}/\text{cm}$, especially 5 $\mu\text{S}/\text{cm}$. The conductivity is maintained at this low level over a long period of time during long-term operation of the fuel cell, in particular when a cooling system having an integrated ion exchanger is used in the fuel cell.

The pH of the ready-to-use aqueous coolant compositions of the invention decreases significantly more slowly over the period of operation than in the case of cooling liquids to which the azole derivatives mentioned have not been added. The pH is usually in the range from 4.5 to 7 in the case of fresh coolant compositions according to the invention and in long-term operation usually decreases to 3.5. The ion-free water used for dilution can be pure distilled or twice-distilled water or water which has been deionized, for example by ion exchange.

The preferred mixing ratio by weight of alkylene glycol or derivatives thereof to water in the ready-to-use aqueous coolant compositions is from 20:80 to 80:20, in particular from 25:75 to 75:25, preferably from 65:35 to 35:65, especially from 60:40 to 40:60. As alkylene glycol component or derivative thereof, it is possible to use, in particular, monoethylene glycol, diethylene glycol, triethylene glycol, tetra-

ethylene glycol and mixtures thereof, but also monopropylene glycol, dipropylene glycol and mixtures thereof, polyglycols, glycol ethers, for example monoethylene glycol monomethyl ether, diethylene glycol monomethyl ether, triethylene glycol monomethyl ether, tetraethylene glycol monomethyl ether, monoethylene glycol monoethyl ether, diethylene glycol monoethyl ether, triethylene glycol monoethyl ether, tetraethylene glycol monoethyl ether, monoethylene glycol mono-n-butyl ether, diethylene glycol mono-n-butyl ether, triethylene glycol mono-n-butyl ether and tetraethylene glycol mono-n-butyl ether, or glycerol, in each case either alone or as mixtures thereof. Particular preference is given to monoethylene glycol alone or mixtures of monoethylene glycol as main component, i.e. having a content in the mixture of more than 50% by weight, in particular more than 80% by weight, especially more than 95% by weight, with other alkylene glycols or derivatives of alkylene glycols.

The antifreeze concentrates of the invention themselves, from which the above-described ready-to-use aqueous coolant compositions result, can be produced by dissolving the azole derivatives mentioned in alkylene glycols or derivatives thereof, which can be used in water-free form or with a small content of water (up to about 10% by weight, in particular up to 5% by weight).

The present invention also provides for the use of at least one of the compounds (V), (VI) and/or (VII) for producing antifreeze concentrates for cooling systems in fuel cells and/or batteries, in particular in motor vehicles, particularly preferably in passenger cars and commercial vehicles, based on alkylene glycols or derivatives thereof.

The present invention further provides for the use of these antifreeze concentrates for producing ready-to-use aqueous coolant compositions having a conductivity of not more than 50 $\mu\text{S}/\text{cm}$ for cooling systems in fuel cells and/or batteries, in particular in motor vehicles, particularly preferably in passenger cars and commercial vehicles.

The coolant compositions of the invention can also be used in a fuel cell apparatus as described in DE-A 101 04 771 (6), in which the cooling medium is additionally electrochemically deionized in order to prevent corrosion.

EXAMPLES

The invention is illustrated in the following examples, but without it being restricted thereto.

The test solutions were tested in accordance with the test method ASTM D1384 with the modification that the aqueous dilution with ASTM water to 33% of volume, which is usual in accordance with ASTM D1384, is omitted. Instead, the test fluid (about 50% strength by volume solution with distilled water) was tested without further dilution since a battery coolant has to have a low electrical conductivity of about 20 $\mu\text{S}/\text{cm}$, but ASTM D1384 water has a high electrical conductivity (caused by the corrosion accelerators in the form of various cations and anions).

Compositions of the Test Fluids

Starting materials	Fluid 1	Fluid 2	Fluid 3	Fluid 4	Fluid 5	Fluid 6
Monoethylene glycol	50.0	50.0	50.0	50.0	50.0	50.0
Water	49.8	49.8	49.8	49.8	49.8	49.8
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1
To this were added						
Castor oil ethoxylate (hydrogenated) with 60 EO	0.25			0.2		

-continued

Starting materials	Fluid 1	Fluid 2	Fluid 3	Fluid 4	Fluid 5	Fluid 6
Caprylamine ethoxylate with 2 EO	0.03	0.03	0.047	0.042	0.038	0.037
Castor oil ethoxylate with 40 EO		0.2			0.2	
Castor oil ethoxylate with 20 EO		0.05				0.2

EO: Ethylene oxide units

The comparison of the base composition composed of monoethylene glycol, water, benzotriazole and tetraethoxysilane without further additives led to very severe corrosion on iron materials within a few hours, associated with an increase in the electrical conductivity to values of greater than 1000 $\mu\text{S}/\text{cm}$.

On the other hand, when the additives were present, the following physical data were obtained in accordance with ASTM D1384 (without aqueous dilution with ASTM water to 33% by volume):

	Fluid 1	Fluid 2	Fluid 3	Fluid 4	Fluid 5	Fluid 6
pH, before test	7.5	7.48	7.00	7.00	7.00	7.00
pH, after test	6.9	6.8	7.44	7.32	7.11	7.04
Alkali reserve of ml of HCl 0.1 mol/l before test	0.49	0.18	0.39	0.36	0.38	0.35
Alkali reserve of ml of HCl 0.1 mol/l after test	0.1	0.08	0.26	0.27	0.10	0.20
Conductivity in $\mu\text{S}/\text{cm}$ before test	n.b.	19.5	28.2	25.9	24.0	23.1
Conductivity in $\mu\text{S}/\text{cm}$ after test	23.5	24.5	30.8	29.2	27.0	27.1

The following degrees of corrosion were determined in accordance with ASTM D1384 (specific change in mass with corrosion blank mg/cm^2)

	Fluid 1	Fluid 2	Fluid 3	Fluid 4	Fluid 5	Fluid 6
Copper F—CU	-0.04	0.06	-0.03	-0.03	-0.10	-0.10
Soft solder L - PbSn30 BASF	-0.34	-0.19	-0.10	-0.20	-0.11	-0.11
Brass Ms - 63	-0.13	0.06	-0.10	-0.09	-0.17	-0.17
Steel H - II	-0.02	0.02	0.00	0.01	-0.01	-0.01
Grey cast iron GG - 25	-0.56	0.03	-0.33	0.02	0.01	0.01
Cast aluminum G - AlSi6Cu4	0.06	0.11	-0.06	0.05	0.05	0.04

Compositions of Further Test Fluids

Starting materials	Fluid 7	Fluid 8	Fluid 9	Fluid 10	Fluid 11	Fluid 12 (Comparison)	Fluid 13
Monoethylene glycol	50.0	50.0	50.0	50.0	50.0	50.0	50.0
Water	49.8	49.8	49.8	49.8	49.8	49.8	49.8
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
To this were added							
Compound 1*	0.25	—	—	0.2	—	—	—
Compound 2**	0.03	0.03	0.04	0.042	0.038	0.037	—

-continued

Starting materials	Fluid 7	Fluid 8	Fluid 9	Fluid 10	Fluid 11	Fluid 12	Fluid 13 (Comparison)
Compound 3***	—	0.2	—	—	0.2	—	—
Compound 4****	—	0.05	—	—	—	0.2	—

*Compound 1: commercial, on statistical average 60-fold ethoxylated octadecanoic acid

**Compound 2: commercial, double ethoxylated n-octylamine

***Compound 3: commercial, on statistical average 40-fold ethoxylated octadecanoic acid

****Compound 4: commercial, on statistical average 20-fold ethoxylated C₁₈-carboxylic acid, mixture of saturated and unsaturated carboxylic acids

When the additives were present the following physical data were obtained in accordance with ASTM 01384 (without aqueous dilution with ASTM water to 33% by volume):

	Fluid 7	Fluid 8	Fluid 9	Fluid 10	Fluid 11	Fluid 12	Fluid 13 (Comparison)
pH, before test	6.57	6.61	6.86	6.87	6.82	6.86	4.85
pH, after test	6.11	6.05	6.45	6.35	6.26	6.19	3.76
Alkali reserve of ml of HCl 0.1 mol/l before test	0.25	0.25	0.23	0.29	0.22	0.26	0
Alkali reserve of ml of HCl 0.1 mol/l after test	0	0.13	0.23	0.23	0.15	0.10	0
Conductivity in $\mu\text{S}/\text{cm}$ before test	21.5	22.0	27.8	26.2	22.9	22.9	0.8
Conductivity in $\mu\text{S}/\text{cm}$ after test	23.9	22.2	31.5	28.8	26.8	25.6	23.6

The following degrees of corrosion were determined in accordance with ASTM D1384 (specific change in mass without corrosion blank mg/cm^2)³⁰

	Fluid 7	Fluid 8	Fluid 9	Fluid 10	Fluid 11	Fluid 12	Fluid 13 (Comparison)
Copper F—CU	-0.05	-0.05	-0.05	-0.07	-0.06	-0.07	-0.06
Soft solder L - PbSn30 BASF	-0.18	-0.12	-0.12	-0.16	-0.14	-0.06	-0.49
Brass Ms - 63	-0.06	-0.09	-0.06	-0.10	-0.09	-0.09	-0.15
Steel H - II	+0.01	± 0.00	-0.01	-0.01	-0.02	± 0.00	-4.16
Grey cast iron GG - 25	-0.04	+0.03	-0.08	+0.02	+0.04	+0.05	-6.18
Cast aluminum G - AlSi6Cu4	+0.09	+0.06	+0.04	+0.11	+0.12	+0.05	+0.20

Compositions of further test fluids with toluotriazole as corrosion inhibitor

Starting materials	Fluid 14	Fluid 15	Fluid 16	Fluid 17	Fluid 18	Fluid 19	Fluid 20 (Comparison)
Monoethylene glycol	50.0	50.0	50.0	50.0	50.0	50.0	50.0
Water	49.8	49.8	49.8	49.8	49.8	49.8	49.8
Tolutriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
To this were added							
Compound 1	0.25	—	—	0.2	—	—	—
Compound 2	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 4	—	0.05	—	—	—	0.2	—

When the additives were present, the following physical data were obtained in accordance with ASTM 01384 (without aqueous dilution with ASTM water to 33% by volume):

	Fluid 14	Fluid 15	Fluid 16	Fluid 17	Fluid 18	Fluid 19	Fluid 20 (Comparison)
pH, before test	6.93	6.99	7.18	7.19	7.08	7.07	4.45
pH, after test	6.04	6.62	6.97	6.73	6.76	6.65	3.76
Alkali reserve of ml of HCl 0.1 mol/l before test	0.24	0.23	0.27	0.26	0.20	0.25	0
Alkali reserve of ml of HCl 0.1 mol/l after test	0.05	0.09	0.21	0.15	0.09	0.08	0
Conductivity in $\mu\text{S}/\text{cm}$ before test	17.8	19.0	23.5	23.0	20.8	20.2	0.8
Conductivity in $\mu\text{S}/\text{cm}$ after test	23.2	20.7	28.5	30.9	22.9	23.9	21.1

The following degrees of corrosion were determined in accordance with ASTM 01384 (specific change in mass without corrosion blank mg/cm^2)

	Fluid 14	Fluid 15	Fluid 16	Fluid 17	Fluid 18	Fluid 19	Fluid 20 (Comparison)
Copper F—CU	-0.07	-0.05	-0.07	-0.05	-0.07	-0.07	-0.04
Soft solder L - PbSn30 BASF	-0.29	-0.06	-0.09	-0.28	-0.11	-0.05	-0.22
Brass Ms - 63	-0.08	-0.09	-0.07	-0.09	-0.10	-0.12	-0.05
Steel H - II	-0.03	-0.01	-0.02	± 0.00	± 0.00	+0.02	-4.02
Grey cast iron GG - 25	-0.15	+0.03	-0.24	-0.93	+0.02	+0.04	-7.12
Cast aluminum G - AlSi6Cu4	+0.05	+0.09	+0.08	+0.08	+0.04	+0.05	+0.13

Further test fluids are listed in Tables 1 to 23.

TABLE 1

Starting materials	Fluid 31	Fluid 32	Fluid 33	Fluid 34	Fluid 35	Fluid 36	Fluid 37 (Comparison)
1,2-Propylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>							
Compound 2	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 2

Starting materials	Fluid 41	Fluid 42	Fluid 43	Fluid 44	Fluid 45	Fluid 46	Fluid 47
1,2-Propylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Triethoxymethylsilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>							
8-fold ethoxylated octylamine	0.3						
20-fold ethoxylated octylamine		0.3					
40-fold ethoxylated octylamine			0.3				
60-fold ethoxylated octylamine				0.3			

TABLE 2-continued

Starting materials	Fluid 41	Fluid 42	Fluid 43	Fluid 44	Fluid 45	Fluid 46	Fluid 47
8-fold ethoxylated hexylamine					0.3		
20-fold ethoxylated hexylamine						0.3	
40-fold ethoxylated hexylamine							0.3
Compound 4	0.25	0.25	0.25	0.25	0.25	0.25	0.25

TABLE 3

Starting materials	Fluid 51	Fluid 52	Fluid 53	Fluid 54	Fluid 55	Fluid 56	Fluid 57
1,2-Propylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Triethoxymethylsilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
To this were added							
8-fold ethoxylated octylamine	0.3						
20-fold ethoxylated octylamine		0.3					
40-fold ethoxylated octylamine			0.3				
60-fold ethoxylated octylamine				0.3			
8-fold ethoxylated hexylamine					0.3		
20-fold ethoxylated hexylamine						0.3	
40-fold ethoxylated hexylamine							0.3
Compound 3	0.25	0.25	0.25	0.25	0.25	0.25	0.25

TABLE 4

Starting materials	Fluid 61	Fluid 62	Fluid 63	Fluid 64	Fluid 65	Fluid 66	Fluid 67
1,2-Propylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Triethoxymethylsilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
To this were added							
8-fold ethoxylated octylamine	0.3						
20-fold ethoxylated octylamine		0.3					
40-fold ethoxylated octylamine			0.3				
60-fold ethoxylated octylamine				0.3			
8-fold ethoxylated hexylamine					0.3		
20-fold ethoxylated hexylamine						0.3	
40-fold ethoxylated hexylamine							0.3
Compound 1	0.25	0.25	0.25	0.25	0.25	0.25	0.25

TABLE 5

Starting materials	Fluid 71	Fluid 72	Fluid 73	Fluid 74	Fluid 75	Fluid 76
1,2-Propylene glycol	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100

TABLE 5-continued

Starting materials	Fluid 71	Fluid 72	Fluid 73	Fluid 74	Fluid 75	Fluid 76
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1
Diethoxydimethylsilane	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>						
Compound 2	0.03	0.03	0.04	0.042	0.038	0.037
Compound 4	—	0.05	—	—	—	0.2
Compound 3	—	0.2	—	—	0.2	—
Compound 1	0.25	—	—	0.2	—	—

TABLE 6

Starting materials	Fluid 81	Fluid 82	Fluid 83	Fluid 84	Fluid 85	Fluid 86
1,2-Propylene glycol	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1
Ethoxytrimethylsilane	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>						
Compound 2	0.03	0.03	0.04	0.042	0.038	0.037
Compound 4	—	0.05	—	—	—	0.2
Compound 3	—	0.2	—	—	0.2	—
Compound 1	0.25	—	—	0.2	—	—

TABLE 7

Starting materials	Fluid 91	Fluid 92	Fluid 93	Fluid 94	Fluid 95	Fluid 96
1,2-Propylene glycol	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1
Tetramethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>						
Compound 2	0.03	0.03	0.04	0.042	0.038	0.037
Compound 4	—	0.05	—	—	—	0.2
Compound 3	—	0.2	—	—	0.2	—
Compound 1	0.25	—	—	0.2	—	—

TABLE 8

Starting materials	Fluid 101	Fluid 102	Fluid 103	Fluid 104	Fluid 105	Fluid 106
1,2-Propylene glycol	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1
Dimethoxydimethylane	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>						
Compound 2	0.03	0.03	0.04	0.042	0.038	0.037
Compound 4	—	0.05	—	—	—	0.2
Compound 3	—	0.2	—	—	0.2	—
Compound 1	0.25	—	—	0.2	—	—

TABLE 9

Starting materials	Fluid 111	Fluid 112	Fluid 113	Fluid 114	Fluid 115	Fluid 116	Fluid 117	Fluid 118 (Comparison)
Diethylene glycol	50	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Triethoxymethylsilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>								
8-fold ethoxylated octylamine	0.3							
20-fold ethoxylated octylamine		0.3						

TABLE 9-continued

Starting materials	Fluid 111	Fluid 112	Fluid 113	Fluid 114	Fluid 115	Fluid 116	Fluid 117	Fluid 118 (Comparison)
40-fold ethoxylated octylamine			0.3					
60-fold ethoxylated octylamine				0.3				
8-fold ethoxylated hexylamine					0.3			
20-fold ethoxylated hexylamine						0.3		
40-fold ethoxylated hexylamine							0.3	
Compound 3	0.25	0.25	0.25	0.25	0.25	0.25	0.25	

TABLE 10

Starting materials	Fluid 121	Fluid 122	Fluid 123	Fluid 124	Fluid 125	Fluid 126	Fluid 127	Fluid 128 (Comparison)
Triethylene glycol	50	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Triethoxymethylsilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
To this were added								
8-fold ethoxylated octylamine	0.3							
20-fold ethoxylated octylamine		0.3						
40-fold ethoxylated octylamine			0.3					
60-fold ethoxylated octylamine				0.3				
8-fold ethoxylated hexylamine					0.3			
20-fold ethoxylated hexylamine						0.3		
40-fold ethoxylated hexylamine							0.3	
Compound 3	0.25	0.25	0.25	0.25	0.25	0.25	0.25	

TABLE 11

Starting materials	Fluid 131	Fluid 132	Fluid 133	Fluid 134	Fluid 135	Fluid 136
1,2-Propylene glycol	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100
Tolutriazole	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1
To this were added						
Compound 2	0.03	0.03	0.04	0.042	0.038	0.037
Compound 4	—	0.05	—	—	—	0.2
Compound 3	—	0.2	—	—	0.2	—
Compound 1	0.25	—	—	0.2	—	—

TABLE 12

Starting materials	Fluid 141	Fluid 142	Fluid 143	Fluid 144	Fluid 145	Fluid 146	Fluid 147
1,2-Propylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Tolutriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Triethoxymethylsilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
To this were added							
8-fold ethoxylated octylamine	0.3						
20-fold ethoxylated octylamine		0.3					

TABLE 12-continued

Starting materials	Fluid 141	Fluid 142	Fluid 143	Fluid 144	Fluid 145	Fluid 146	Fluid 147
40-fold ethoxylated octylamine			0.3				
60-fold ethoxylated octylamine				0.3			
8-fold ethoxylated hexylamine					0.3		
20-fold ethoxylated hexylamine						0.3	
40-fold ethoxylated hexylamine							0.3
Compound 3	0.25	0.25	0.25	0.25	0.25	0.25	0.25

TABLE 13

Starting materials	Fluid 151	Fluid 152	Fluid 153	Fluid 154	Fluid 155	Fluid 156	Fluid 157 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
To this were added							
8-fold ethoxylated octylamine	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 14

Starting materials	Fluid 161	Fluid 162	Fluid 163	Fluid 164	Fluid 165	Fluid 166	Fluid 167 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
To this were added							
20-fold ethoxylated octylamine	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 15

Starting materials	Fluid 171	Fluid 172	Fluid 173	Fluid 174	Fluid 175	Fluid 176	Fluid 177 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
To this were added							
40-fold ethoxylated octylamine	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 16

Starting materials	Fluid 181	Fluid 182	Fluid 183	Fluid 184	Fluid 185	Fluid 186	Fluid 187 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<hr/>							
60-fold ethoxylated octylamine	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 17

Starting materials	Fluid 191	Fluid 192	Fluid 193	Fluid 194	Fluid 195	Fluid 196	Fluid 197 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<hr/>							
8-fold ethoxylated hexylamine	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 18

Starting materials	Fluid 201	Fluid 202	Fluid 203	Fluid 204	Fluid 205	Fluid 206	Fluid 207 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<hr/>							
20-fold ethoxylated hexylamine	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 19

Starting materials	Fluid 211	Fluid 212	Fluid 213	Fluid 214	Fluid 215	Fluid 216	Fluid 217 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<hr/>							
40-fold ethoxylated hexylamine	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 20

Starting materials	Fluid 221	Fluid 222	Fluid 223	Fluid 224	Fluid 225	Fluid 226	Fluid 227 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>							
60-fold ethoxylated hexylamine	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 21

Starting materials	Fluid 231	Fluid 232	Fluid 233	Fluid 234	Fluid 235	Fluid 236	Fluid 237 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>							
20-fold ethoxylated n-octanol	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 22

Starting materials	Fluid 241	Fluid 242	Fluid 243	Fluid 244	Fluid 245	Fluid 246	Fluid 247 (Comparison)
Monoethylene glycol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tetraethoxysilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>							
40-fold ethoxylated n-octanol	0.03	0.03	0.04	0.042	0.038	0.037	—
Compound 4	—	0.05	—	—	—	0.2	—
Compound 3	—	0.2	—	—	0.2	—	—
Compound 1	0.25	—	—	0.2	—	—	—

TABLE 23


Starting materials	Fluid 251	Fluid 252	Fluid 253	Fluid 254	Fluid 255	Fluid 256	Fluid 257
Glycerol	50	50	50	50	50	50	50
Water	to 100	to 100	to 100	to 100	to 100	to 100	to 100
Benzotriazole	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Triethoxymethylsilane	0.1	0.1	0.1	0.1	0.1	0.1	0.1
<u>To this were added</u>							
8-fold ethoxylated octylamine	0.3						
20-fold ethoxylated octylamine		0.3					
40-fold ethoxylated octylamine			0.3				
60-fold ethoxylated octylamine				0.3			
8-fold ethoxylated hexylamine					0.3		

TABLE 23-continued

Starting materials	Fluid 251	Fluid 252	Fluid 253	Fluid 254	Fluid 255	Fluid 256	Fluid 257
20-fold ethoxylated hexylamine						0.3	
40-fold ethoxylated hexylamine							0.3
Compound 4	0.25	0.25	0.25	0.25	0.25	0.25	0.25

The invention claimed is:

1. A coolant composition having a conductivity of not more than 50 $\mu\text{S}/\text{cm}$, the coolant composition comprising:
 at least one alkylene glycol or derivative thereof;
 one or more five-membered heterocyclic compounds,
 which are azole derivatives, and which have 2 or 3
 heteroatoms selected from the group consisting of
 nitrogen and sulfur, and comprise no or at most one
 sulfur atom and can bear an aromatic or saturated
 six-membered fused-on ring;
 ion free water;
 at least one compound of formula (V)



wherein

R^1 is an organic radical having from 7 to 21 carbon atoms,
 n is a positive integer from 10 to 60, and

each X_i for $i=1$ to n is selected independently from the
 group consisting of $-\text{CH}_2-\text{CH}_2-\text{O}-$, $-\text{CH}_2-\text{CH}$
 $(\text{CH}_3)-\text{O}-$, $-\text{CH}(\text{CH}_3)-\text{CH}_2-\text{O}-$, $-\text{CH}_2-\text{C}$
 $(\text{CH}_3)_2-\text{O}-$, $-\text{C}(\text{CH}_3)_2-\text{CH}_2-\text{O}-$, $-\text{CH}_2-\text{CH}$
 $(\text{C}_2\text{H}_5)-\text{O}-$, $-\text{CH}(\text{C}_2\text{H}_5)-\text{CH}_2-\text{O}-$, $-\text{CH}$
 $(\text{CH}_3)-\text{CH}(\text{CH}_3)-\text{O}-$, $-\text{CH}_2-\text{CH}_2-\text{CH}_2-\text{O}-$,
 and $-\text{CH}_2-\text{CH}_2-\text{CH}_2-\text{CH}_2-\text{O}-$; and

optionally, at least one ortho-silicic ester.

2. The coolant composition according to claim 1, wherein
 the structural element $\text{R}^1-\text{COO}-$ in the formula (V) is
 derived from an acid selected from the group consisting of
 2-ethylhexanoic acid, octanoic acid (caprylic acid), pelar-
 gonic acid (nonanoic acid), 2-propylheptanoic acid,
 decanoic acid (capric acid), undecanoic acid, dodecanoic
 acid (lauric acid), tridecanoic acid, tetradecanoic acid
 (myristic acid), pentadecanoic acid, palmitic acid (hexade-
 canoic acid), palmitoleic acid [(9Z)-hexadec-9-enoic acid],
 margaric acid (heptadecanoic acid), stearic acid (octade-
 canoic acid), oleic acid [(9Z)-octadec-9-enoic acid], elaidic
 acid [(9E)-octadec-9-enoic acid], linoleic acid [(9Z,12Z)-
 octadeca-9,12-dienoic acid], linolenic acid [(9Z,12Z,15Z)-
 octadeca-9,12,15-trienoic acid], eleostearic acid [(9Z,11E,
 13E)-octadeca-9,11,13-trienoic acid], ricinoleic acid ((R)-
 12-hydroxy-(Z)-octadec-9-enoic acid), isoricinoleic acid
 [(S)-9-hydroxy-(Z)-octadec-12-enoic acid], nonadecanoic
 acid, arachidic acid (eicosanoic acid), behenic acid (doco-
 sanoic acid), and erucic acid [(13Z)-docos-13-enoic acid].

3. The coolant composition according to claim 1, wherein
 the structural element $\text{R}^1-\text{COO}-$ in the formula (V)
 originates from a fatty acid mixture originating from a
 work-up of linseed oil, coconut oil, palm kernel oil, palm oil,
 soy oil, peanut oil, cocoa butter, shea butter, cottonseed oil,
 maize oil, sunflower oil, rapeseed oil, or castor oil.

4. The coolant composition according to claim 1, wherein
 n is a positive integer from 12 to 50.

5. The coolant composition according to claim 1, wherein
 n is a positive integer from 15 to 40.

6. The coolant composition according to claim 1, wherein
 n is a positive integer from 18 to 30.

7. The coolant composition according to claim 1, wherein
 n is a positive integer from 20 to 25.

8. The coolant composition according claim 1, wherein X_i
 is $-\text{CH}_2-\text{CH}_2-\text{O}-$.

9. The coolant composition according claim 1, wherein X_i
 is selected from the group consisting of $-\text{CH}_2-\text{CH}_2-$
 $\text{O}-$, $-\text{CH}_2-\text{CH}(\text{CH}_3)-\text{O}-$, and $-\text{CH}(\text{CH}_3)-\text{CH}_2-$
 $\text{O}-$.

10. The coolant composition according to claim 1, com-
 prising benzimidazole, benzotriazole, tolutriazole, and/or
 hydrogenated tolutriazole as the azole derivatives.

11. The coolant composition according to claim 1, further
 comprising at least one ortho-silicic ester in such an amount
 that a silicon content in the coolant composition is from 2 to
 2000 ppm by weight when in a ready-to-use state.

12. The coolant composition according to claim 1,
 wherein the coolant composition consists essentially of:

(a) from 10 to 90% by weight of the at least one alkylene
 glycol or derivative thereof;

(b) from 90 to 10% by weight of the ion free water;

(c) from 0.005 to 5% by weight of the one or more azole
 derivatives;

(d) optionally, at least one ortho-silicic ester, and

(e) from 0.05 to 5% by weight of the at least one
 compound of formula (V), and

wherein a sum of all components (a) to (e) is 100% by
 weight.

13. The coolant composition according to claim 1, having
 a conductivity of not more than 30 $\mu\text{S}/\text{cm}$.


14. A method for producing a coolant composition having
 a conductivity of not more than 50 $\mu\text{S}/\text{cm}$, the method
 comprising:

admixing at least one antifreeze concentrate with water,
 wherein the antifreeze concentrate comprises:

at least one alkylene glycol or derivative thereof,

one or more five-membered heterocyclic compounds,
 which are azole derivatives, and which have 2 or 3
 heteroatoms selected from the group consisting of
 nitrogen and sulfur, and comprise no or at most one
 sulfur atom and can bear an aromatic or saturated
 six-membered fused-on ring,

at least one compound of formula (V):



31

wherein

R¹ is an organic radical having from 7 to 21 carbon atoms,
n is a positive integer from 10 to 60, and

each X_i for i=1 to n is selected independently from the
group consisting of —CH₂—CH₂—O—, —CH₂—CH
(CH₃)—O—, —CH(CH₃)—CH₂—O—, —CH₂—C
(CH₃)₂—O—, —C(CH₃)₂—CH₂—O—, —CH₂—CH
(C₂H₅)—O—, —CH(C₂H₅)—CH₂—O—, —CH
(CH₃)—CH(CH₃)—O—, —CH₂—CH₂—CH₂—O—,
and —CH₂—CH₂—CH₂—CH₂O—; and

optionally, at least one ortho-silicic ester.

15. A coolant composition produced according to the
method of claim 14, wherein the structural element
R¹—COO— in the formula (V) is derived from an acid
selected from the group consisting of 2-ethylhexanoic acid,
octanoic acid (caprylic acid), pelargonic acid (nonanoic
acid), 2-propylheptanoic acid, decanoic acid (capric acid),
undecanoic acid, dodecanoic acid (lauric acid), tridecanoic
acid, tetradecanoic acid (myristic acid), pentadecanoic acid,
palmitic acid (hexadecanoic acid), palmitoleic acid [(9Z)-
hexadec-9-enoic acid], margaric acid (heptadecanoic acid),
stearic acid (octadecanoic acid), oleic acid [(9Z)-octadec-9-
enoic acid], elaidic acid [(9E)-octadec-9-enoic acid], lino-
leic acid [(9Z,12Z)-octadeca-9,12-dienoic acid], linolenic
acid [(9Z,12Z,15Z)-octadeca-9,12,15-trienoic acid], eleoste-
aric acid [(9Z,11E,13E)-octadeca-9,11,13-trienoic acid],
ricinoleic acid ((R)-12-hydroxy-(Z)-octadec-9-enoic acid),
isoricinoleic acid [(S)-9-hydroxy-(Z)-octadec-12-enoic
acid], nonadecanoic acid, arachidic acid (eicosanoic acid),
behenic acid (docosanoic acid), and erucic acid [(13Z)-
docos-13-enoic acid].

16. A coolant composition produced according to the
method of claim 14, wherein the structural element
R¹—COO— in the formula (V) originates from a fatty acid
mixture originating from a work-up of linseed oil, coconut
oil, palm kernel oil, palm oil, soy oil, peanut oil, cocoa
butter, shea butter, cottonseed oil, maize oil, sunflower oil,
rapeseed oil, or castor oil.

17. A coolant composition produced according to the
method of claim 14, wherein the coolant composition con-
sists essentially of:

- from 10 to 90% by weight of the at least one alkylene glycol or derivative thereof;
- from 90 to 10% by weight of the ion free water;
- from 0.005 to 5% by weight of the one or more azole derivatives;
- optionally, at least one ortho-silicic ester, and
- from 0.05 to 5% by weight of the at least one compound of formula (V); and

wherein a sum of all components (a) to (e) is 100% by weight.

32


18. A method, comprising:

reducing nonferrous metal corrosion by operating a cooling system with a coolant composition having a conductivity of not more than 50 μS/cm in a fuel cell and/or battery, the coolant composition comprising at least one antifreeze concentrate comprising:

at least one alkylene glycol or derivative thereof,
one or more five-membered heterocyclic compounds,
which are azole derivatives, and which have 2 or 3 heteroatoms selected from the group consisting of nitrogen and sulfur, and comprise no or at most one sulfur atom and can bear an aromatic or saturated six-membered fused-on ring,

ion free water, and

at least one compound of formula (V):




wherein

R¹ is an organic radical having from 7 to 21 carbon atoms,
n is a positive integer from 10 to 60, and

each X_i for i=1 to n is selected independently from the
group consisting of —CH₂—CH₂—O—, —CH₂—CH
(CH₃)—O—, —CH(CH₃)—CH₂—O—, —CH₂—C
(CH₃)₂—O—, —C(CH₃)₂—CH₂—O—, —CH₂—CH
(C₂H₅)—O—, —CH(C₂H₅)—CH₂—O—, —CH
(CH₃)—CH(CH₃)—O—, —CH₂—CH₂—CH₂—O—,
and —CH₂—CH₂—CH₂—CH₂O—.

19. A method, comprising:

reducing foam formation in a coolant composition by
formulating a coolant composition with at least one
compound of formula (V);



wherein

R¹ is an organic radical having from 7 to 21 carbon atoms,
n is a positive integer from 10 to 60, and

each X_i for i=1 to n is selected independently from the
group consisting of —CH₂—CH₂—O—, —CH₂—CH
(CH₃)—O—, —CH(CH₃)—CH₂—O—, —CH₂—C
(CH₃)₂—O—, —C(CH₃)₂—CH₂—O—, —CH₂—CH
(C₂H₅)—O—, —CH(C₂H₅)—CH₂—O—, —CH
(CH₃)—CH(CH₃)—O—, —CH₂—CH₂—CH₂—O—,
and —CH₂—CH₂—CH₂—CH₂O—.

* * * * *