



US011837461B2

(12) **United States Patent**  
**Yamazaki et al.**

(10) **Patent No.:** **US 11,837,461 B2**  
(45) **Date of Patent:** **\*Dec. 5, 2023**

(54) **SEMICONDUCTOR DEVICE AND MANUFACTURING METHOD THEREOF**

(71) Applicant: **Semiconductor Energy Laboratory Co., Ltd.**, Atsugi (JP)

(72) Inventors: **Shunpei Yamazaki**, Tokyo (JP); **Jun Koyama**, Kanagawa (JP); **Hiroyuki Miyake**, Kanagawa (JP); **Kei Takahashi**, Kanagawa (JP); **Kouhei Toyotaka**, Kanagawa (JP); **Masashi Tsubuku**, Kanagawa (JP); **Kosei Noda**, Kanagawa (JP); **Hideaki Kuwabara**, Kanagawa (JP)

(73) Assignee: **Semiconductor Energy Laboratory Co., Ltd.**, Atsugi (JP)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 126 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **17/010,151**

(22) Filed: **Sep. 2, 2020**

(65) **Prior Publication Data**

US 2021/0143281 A1 May 13, 2021

**Related U.S. Application Data**

(60) Continuation of application No. 16/121,700, filed on Sep. 5, 2018, now Pat. No. 10,777,682, which is a (Continued)

(30) **Foreign Application Priority Data**

Oct. 16, 2009 (JP) ..... 2009-238885

(51) **Int. Cl.**

**H01L 29/786** (2006.01)

**H01L 27/12** (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC .. **H01L 29/78609** (2013.01); **G06K 19/07758** (2013.01); **H01L 21/8236** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC ..... H01L 27/1225; H01L 29/7869

See application file for complete search history.

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

5,079,606 A 1/1992 Yamamura et al.

5,731,856 A 3/1998 Kim et al.

(Continued)

**FOREIGN PATENT DOCUMENTS**

CN 101681927 A 3/2010

EP 0380122 A 8/1990

(Continued)

**OTHER PUBLICATIONS**

Fortunato.E et al., "Wide-Bandgap High-Mobility ZNO Thin-Film Transistors Produced at Room Temperature", Appl. Phys. Lett. (Applied Physics Letters) , Sep. 27, 2004, vol. 85, No. 13, pp. 2541-2543.

(Continued)

*Primary Examiner* — Chad M Dicke


*Assistant Examiner* — Valerie N Newton

(74) *Attorney, Agent, or Firm* — Fish & Richardson P.C.

(57) **ABSTRACT**

An object is to reduce leakage current and parasitic capacitance of a transistor used for an LSI, a CPU, or a memory. A semiconductor integrated circuit such as an LSI, a CPU, or a memory is manufactured using a thin film transistor in which a channel formation region is formed using an oxide semiconductor which becomes an intrinsic or substantially intrinsic semiconductor by removing impurities which serve as electron donors (donors) from the oxide semiconductor and has larger energy gap than that of a silicon semicon-

(Continued)



ductor. With use of a thin film transistor using a highly purified oxide semiconductor layer with sufficiently reduced hydrogen concentration, a semiconductor device with low power consumption due to leakage current can be realized.

**6 Claims, 18 Drawing Sheets**

**Related U.S. Application Data**

continuation of application No. 15/372,493, filed on Dec. 8, 2016, now Pat. No. 10,074,747, which is a division of application No. 13/799,246, filed on Mar. 13, 2013, now Pat. No. 9,666,678, which is a continuation of application No. 12/904,565, filed on Oct. 14, 2010, now Pat. No. 8,421,068.

(51) **Int. Cl.**

*H01L 29/26* (2006.01)  
*G06K 19/077* (2006.01)  
*H01L 21/8236* (2006.01)  
*H01L 23/66* (2006.01)  
*H01L 27/088* (2006.01)  
*H01L 29/24* (2006.01)  
*H01L 29/66* (2006.01)  
*G11C 7/00* (2006.01)  
*G11C 19/28* (2006.01)  
*H02M 3/07* (2006.01)

(52) **U.S. Cl.**

CPC ..... *H01L 23/66* (2013.01); *H01L 27/0883* (2013.01); *H01L 27/1225* (2013.01); *H01L 29/24* (2013.01); *H01L 29/26* (2013.01); *H01L 29/66969* (2013.01); *H01L 29/7869* (2013.01); *H01L 29/78696* (2013.01); *G11C 7/00* (2013.01); *G11C 19/28* (2013.01); *H01L 2223/6677* (2013.01); *H02M 3/07* (2013.01)

(56)

**References Cited**

U.S. PATENT DOCUMENTS

5,744,864 A 4/1998 Cillessen et al.  
 6,294,274 B1 9/2001 Kawazoe et al.  
 6,509,616 B2 1/2003 Yamazaki  
 6,563,174 B2 5/2003 Kawasaki et al.  
 6,727,522 B1 4/2004 Kawasaki et al.  
 6,765,231 B2 7/2004 Yamazaki  
 6,787,807 B2 9/2004 Yamazaki et al.  
 6,914,302 B2 7/2005 Ohtani et al.  
 6,956,235 B2 10/2005 Yamazaki et al.  
 7,049,190 B2 5/2006 Takeda et al.  
 7,061,014 B2 6/2006 Hosono et al.  
 7,064,346 B2 6/2006 Kawasaki et al.  
 7,105,868 B2 9/2006 Nause et al.  
 7,189,992 B2 3/2007 Wager, III et al.  
 7,208,798 B2 4/2007 Baba  
 7,211,825 B2 5/2007 Shih et al.  
 7,276,730 B2 10/2007 Yamazaki et al.  
 7,282,782 B2 10/2007 Hoffman et al.  
 7,297,977 B2 11/2007 Hoffman et al.  
 7,319,238 B2 1/2008 Yamazaki  
 7,323,356 B2 1/2008 Hosono et al.  
 7,339,187 B2 3/2008 Wager, III et al.  
 7,385,224 B2 6/2008 Ishii et al.  
 7,402,506 B2 7/2008 Levy et al.  
 7,411,209 B2 8/2008 Endo et al.  
 7,453,065 B2 11/2008 Saito et al.  
 7,453,087 B2 11/2008 Iwasaki  
 7,462,862 B2 12/2008 Hoffman et al.  
 7,468,304 B2 12/2008 Kaji et al.  
 7,501,293 B2 3/2009 Ito et al.

7,674,650 B2 3/2010 Akimoto et al.  
 7,687,807 B2 3/2010 Koo et al.  
 7,732,251 B2 6/2010 Hoffman et al.  
 7,732,330 B2 6/2010 Fujii  
 7,732,819 B2 6/2010 Akimoto et al.  
 7,791,074 B2 9/2010 Iwasaki  
 7,829,444 B2 11/2010 Yabuta et al.  
 7,851,279 B2 12/2010 Takano. et al.  
 7,888,207 B2 2/2011 Wager, III et al.  
 7,932,521 B2 4/2011 Akimoto et al.  
 8,003,981 B2 8/2011 Iwasaki et al.  
 8,022,469 B2 9/2011 Takano. et al.  
 8,101,501 B2 1/2012 Ohnuma et al.  
 8,143,678 B2 3/2012 Kim et al.  
 8,158,980 B2 4/2012 Yamazaki et al.  
 8,203,144 B2 6/2012 Hoffman et al.  
 8,212,248 B2 7/2012 Itagaki et al.  
 8,241,948 B2 8/2012 Fujii  
 8,304,298 B2 11/2012 Ofuji et al.  
 8,354,674 B2 1/2013 Kimura  
 8,384,076 B2 2/2013 Park et al.  
 8,421,068 B2 4/2013 Yamazaki et al.  
 8,461,583 B2 6/2013 Yano et al.  
 8,502,217 B2 8/2013 Sato et al.  
 8,513,661 B2 8/2013 Takahashi et al.  
 8,558,227 B2 10/2013 Fujii  
 8,558,323 B2 10/2013 Kim et al.  
 8,581,332 B2 11/2013 Takano. et al.  
 8,643,015 B2 2/2014 Yamazaki et al.  
 8,647,031 B2 2/2014 Hoffman et al.  
 8,723,175 B2 5/2014 Yano et al.  
 8,791,457 B2 7/2014 Yano et al.  
 9,184,173 B2 11/2015 Takano. et al.  
 9,666,678 B2 5/2017 Yamazaki et al.  
 10,074,747 B2 9/2018 Yamazaki et al.  
 10,777,682 B2\* 9/2020 Yamazaki ..... H01L 29/7869  
 2001/0046027 A1 11/2001 Tai et al.  
 2002/0038889 A1 4/2002 Yamazaki et al.  
 2002/0039813 A1 4/2002 Yamazaki  
 2002/0056838 A1 5/2002 Ogawa  
 2002/0132454 A1 9/2002 Ohtsu et al.  
 2002/0175376 A1 11/2002 Ohtani et al.  
 2003/0189401 A1 10/2003 Kido et al.  
 2003/0218222 A1 11/2003 Wager, III et al.  
 2004/0038446 A1 2/2004 Takeda et al.  
 2004/0127038 A1 7/2004 Carcia et al.  
 2005/0006702 A1 1/2005 Baba  
 2005/0017302 A1 1/2005 Hoffman  
 2005/0199959 A1 9/2005 Chiang et al.  
 2005/0199960 A1 9/2005 Hoffman et al.  
 2005/0284518 A1 12/2005 Yamada et al.  
 2006/0035452 A1 2/2006 Carcia et al.  
 2006/0043377 A1 3/2006 Hoffman et al.  
 2006/0091793 A1 5/2006 Baude et al.  
 2006/0108529 A1 5/2006 Saito et al.  
 2006/0108636 A1 5/2006 Sano et al.  
 2006/0110867 A1 5/2006 Yabuta et al.  
 2006/0113536 A1 6/2006 Kumomi et al.  
 2006/0113539 A1 6/2006 Sano et al.  
 2006/0113549 A1 6/2006 Den et al.  
 2006/0113565 A1 6/2006 Abe et al.  
 2006/0169973 A1 8/2006 Isa et al.  
 2006/0170111 A1 8/2006 Isa et al.  
 2006/0197092 A1 9/2006 Hoffman et al.  
 2006/0208977 A1 9/2006 Kimura  
 2006/0228974 A1 10/2006 Thelss et al.  
 2006/0231882 A1 10/2006 Kim et al.  
 2006/0238135 A1 10/2006 Kimura  
 2006/0244107 A1 11/2006 Sugihara et al.  
 2006/0284171 A1 12/2006 Levy et al.  
 2006/0284172 A1 12/2006 Ishii  
 2006/0292777 A1 12/2006 Dunbar  
 2007/0024187 A1 2/2007 Shin et al.  
 2007/0035340 A1\* 2/2007 Kimura ..... G09G 3/325  
 2007/0046191 A1 3/2007 Saito  
 2007/0052025 A1 3/2007 Yabuta  
 2007/0054507 A1 3/2007 Kaji et al.  
 2007/0090365 A1 4/2007 Hayashi et al.

(56)

## References Cited

## FOREIGN PATENT DOCUMENTS

U.S. PATENT DOCUMENTS			FOREIGN PATENT DOCUMENTS		
			EP	1737044 A	12/2006
			EP	1818900 A	8/2007
2007/0108446	A1	5/2007 Akimoto	EP	1950177 A	7/2008
2007/0152217	A1	7/2007 Lai et al.	EP	2120267 A	11/2009
2007/0172591	A1	7/2007 Seo et al.	EP	2226847 A	9/2010
2007/0187678	A1	8/2007 Hirao et al.	EP	2408011 A	1/2012
2007/0187688	A1	8/2007 Whight et al.	EP	2927965 A	10/2015
2007/0187760	A1	8/2007 Furuta et al.	JP	60-177676 A	9/1985
2007/0188089	A1	8/2007 Choi et al.	JP	60-198861 A	10/1985
2007/0194379	A1	8/2007 Hosono et al.	JP	63-210022 A	8/1988
2007/0228389	A1	10/2007 Hsu et al.	JP	63-210023 A	8/1988
2007/0252928	A1	11/2007 Ito et al.	JP	63-210024 A	8/1988
2007/0272922	A1	11/2007 Kim et al.	JP	63-215519 A	9/1988
2007/0272948	A1	11/2007 Koo et al.	JP	63-221677 A	9/1988
2007/0287296	A1	12/2007 Chang	JP	63-239117 A	10/1988
2008/0006877	A1	1/2008 Mardilovich et al.	JP	63-265818 A	11/1988
2008/0038882	A1	2/2008 Takechi et al.	JP	02-197176 A	8/1990
2008/0038929	A1	2/2008 Chang	JP	03-171775 A	7/1991
2008/0050595	A1	2/2008 Nakagawara et al.	JP	05-251705 A	9/1993
2008/0073653	A1	3/2008 Iwasaki	JP	08-264794 A	10/1996
2008/0083950	A1	4/2008 Pan et al.	JP	10-319869 A	12/1998
2008/0106191	A1	5/2008 Kawase	JP	11-505377	5/1999
2008/0108198	A1	5/2008 Wager, III et al.	JP	2000-044236 A	2/2000
2008/0128689	A1	6/2008 Lee et al.	JP	2000-150900 A	5/2000
2008/0129195	A1	6/2008 Ishizaki et al.	JP	2000-183356 A	6/2000
2008/0135844	A1	6/2008 Yamazaki	JP	2000-194014 A	7/2000
2008/0166834	A1	7/2008 Kim et al.	JP	2002-076356 A	3/2002
2008/0182358	A1	7/2008 Cowdery-Corvan et al.	JP	2002-083974 A	3/2002
2008/0191204	A1	8/2008 Kim et al.	JP	2002-111008 A	4/2002
2008/0224133	A1	9/2008 Park et al.	JP	2002-198537 A	7/2002
2008/0254569	A1	10/2008 Hoffman et al.	JP	2002-289859 A	10/2002
2008/0258139	A1	10/2008 Ito et al.	JP	2003-086000 A	3/2003
2008/0258140	A1	10/2008 Lee et al.	JP	2003-086808 A	3/2003
2008/0258141	A1	10/2008 Park et al.	JP	2003-234355 A	8/2003
2008/0258143	A1	10/2008 Kim et al.	JP	2003-243657 A	8/2003
2008/0296568	A1	12/2008 Ryu et al.	JP	2004-103957 A	4/2004
2009/0002590	A1	1/2009 Kimura	JP	2004-193248 A	7/2004
2009/0008638	A1	1/2009 Kang et al.	JP	2004-273614 A	9/2004
2009/0045397	A1	2/2009 Iwasaki	JP	2004-273732 A	9/2004
2009/0068773	A1	3/2009 Lai et al.	JP	2005-277323 A	10/2005
2009/0073325	A1	3/2009 Kuwabara et al.	JP	2006-120885 A	5/2006
2009/0090914	A1	4/2009 Yano et al.	JP	2006-165527 A	6/2006
2009/0114910	A1	5/2009 Chang	JP	2006-165528 A	6/2006
2009/0121225	A1	5/2009 Ishizaki et al.	JP	2006-165529 A	6/2006
2009/0134399	A1	5/2009 Sakakura et al.	JP	2006-165531 A	6/2006
2009/0152506	A1	6/2009 Umeda et al.	JP	2007-043113 A	2/2007
2009/0152541	A1	6/2009 Maekawa et al.	JP	2007-096055 A	4/2007
2009/0206332	A1	8/2009 Son et al.	JP	2007-096126 A	4/2007
2009/0230392	A1	9/2009 Takahara	JP	2007-103918 A	4/2007
2009/0236602	A1	9/2009 Kato	JP	2007-219517 A	8/2007
2009/0242992	A1	10/2009 Kim et al.	JP	2007-250983 A	9/2007
2009/0272980	A1	11/2009 Shim et al.	JP	2007-529119	10/2007
2009/0278122	A1	11/2009 Hosono et al.	JP	2007-535164	11/2007
2009/0278128	A1	11/2009 Seong et al.	JP	2007-318061 A	12/2007
2009/0280600	A1	11/2009 Hosono et al.	JP	2008-060419 A	3/2008
2010/0065844	A1	3/2010 Tokunaga	JP	2008-091896 A	4/2008
2010/0084651	A1	4/2010 Yamazaki et al.	JP	2008-199005 A	8/2008
2010/0085081	A1	4/2010 Ofuji et al.	JP	2008-205451 A	9/2008
2010/0092800	A1	4/2010 Itagaki et al.	JP	2008-244027 A	10/2008
2010/0109002	A1	5/2010 Itagaki et al.	JP	2008-270313 A	11/2008
2010/0193785	A1	8/2010 Kimura	JP	2009-004733 A	1/2009
2010/0219411	A1	9/2010 Hoffman et al.	JP	2009-016844 A	1/2009
2010/0244029	A1	9/2010 Yamazaki et al.	JP	2009-033141 A	2/2009
2010/0267198	A1	10/2010 Yabuta et al.	JP	2009-033145 A	2/2009
2010/0276685	A1	11/2010 Itagaki et al.	JP	2009-117717 A	5/2009
2010/0276689	A1	11/2010 Iwasaki	JP	2009-135520 A	6/2009
2010/0279462	A1	11/2010 Iwasaki	JP	2009-141002 A	6/2009
2011/0089414	A1	4/2011 Yamazaki et al.	JP	2009-176865 A	8/2009
2011/0101331	A1	5/2011 Yamazaki et al.	JP	2009-206508 A	9/2009
2011/0256684	A1	10/2011 Iwasaki et al.	JP	2009-278115 A	11/2009
2012/0208318	A1	8/2012 Hoffman et al.	KR	2007-0113737 A	11/2007
2013/0193435	A1	8/2013 Yamazaki et al.	KR	2008-0074888 A	8/2008
2013/0221348	A1	8/2013 Yano et al.	TW	200534369	10/2005
2019/0157314	A1	5/2019 Kimura	TW	200539293	12/2005
			TW	200931503	7/2009
			TW	I697055	6/2020
			WO	WO-2004/038757	5/2004

(56)

## References Cited

## FOREIGN PATENT DOCUMENTS

WO	WO-2004/114391	12/2004
WO	WO-2005/093850	10/2005
WO	WO-2005/106960	11/2005
WO	WO-2007/029844	3/2007
WO	WO-2007/058248	5/2007
WO	WO-2007/119386	10/2007
WO	WO-2008/099528	8/2008
WO	WO-2008/143304	11/2008
WO	WO-2009/004919	1/2009
WO	WO-2009/072532	6/2009
WO	WO-2009/081885	7/2009
WO	WO-2009/087943	7/2009
WO	WO-2009/093722	7/2009
WO	WO-2009/096608	8/2009
WO	WO-2011/046048	4/2011

## OTHER PUBLICATIONS

- Dembo.H et al., "RFCPUS on Glass and Plastic Substrates Fabricated by TFT Transfer Technology", IEDM 05: Technical Digest of International Electron Devices Meeting, Dec. 5, 2005, pp. 1067-1069.
- Ikeda.T et al., "Full-Functional System Liquid Crystal Display Using CG-Silicon Technology", SID Digest '04 : SID International Symposium Digest of Technical Papers, 2004, vol. 35, pp. 860-863.
- Nomura.K et al., "Room-Temperature Fabrication of Transparent Flexible Thin-Film Transistors Using Amorphous Oxide Semiconductors", Nature, Nov. 25, 2004, vol. 432, pp. 488-492.
- Park.J et al., "Improvements in the Device Characteristics of Amorphous Indium Gallium Zinc Oxide Thin-Film Transistors by Ar Plasma Treatment", Appl. Phys. Lett. (Applied Physics Letters), Jun. 26, 2007, vol. 90, No. 26, pp. 262106-1-262106-3.
- Takahashi.M et al., "Theoretical Analysis of IGZO Transparent Amorphous Oxide Semiconductor", IDW '08 : Proceedings of the 15th International Display Workshops, Dec. 3, 2008, pp. 1637-1640.
- Hayashi.R et al., "42.1: Invited Paper: Improved Amorphous In-Ga-Zn-O TFTs", SID Digest '08 : SID International Symposium Digest of Technical Papers, May 20, 2008, vol. 39, pp. 621-624.
- Prins.M et al., "A Ferroelectric Transparent Thin-Film Transistor", Appl. Phys. Lett. (Applied Physics Letters), Jun. 17, 1996, vol. 68, No. 25, pp. 3650-3652.
- Nakamura.M et al., "The phase relations in the In<sub>2</sub>O<sub>3</sub>-Ga<sub>2</sub>ZnO<sub>4</sub>-ZnO system at 1350° C", Journal of Solid State Chemistry, Aug. 1, 1991, vol. 93, No. 2, pp. 298-315.
- Kimizuka.N et al., "Syntheses and Single-Crystal Data of Homologous Compounds, In<sub>2</sub>O<sub>3</sub>(ZnO)<sub>m</sub> (m=3, 4, and 5), InGaO<sub>3</sub>(ZnO)<sub>3</sub>, and Ga<sub>2</sub>O<sub>3</sub>(ZnO)<sub>m</sub> (m=7, 8, 9, and 16) in the In<sub>2</sub>O<sub>3</sub>-ZnGa<sub>2</sub>O<sub>4</sub>-ZnO System", Journal of Solid State Chemistry, Apr. 1, 1995, vol. 116, No. 1, pp. 170-178.
- Nomura.K et al., "Thin-Film Transistor Fabricated in Single-Crystalline Transparent Oxide Semiconductor", Science, May 23, 2003, vol. 300, No. 5623, pp. 1269-1272.
- Masuda.S et al., "Transparent thin film transistors using ZnO as an active channel layer and their electrical properties", J. Appl. Phys. (Journal of Applied Physics), Feb. 1, 2003, vol. 93, No. 3, pp. 1624-1630.
- Asakuma.N et al., "Crystallization and Reduction of Sol-Gel-Derived Zinc Oxide Films by Irradiation With Ultraviolet Lamp", Journal of Sol-Gel Science and Technology, 2003, vol. 26, pp. 181-184.
- Osada. T et al., "15.2: Development of Driver-Integrated Panel using Amorphous In-Ga-Zn-Oxide TFT", SID Digest '09 : SID International Symposium Digest of Technical Papers, May 31, 2009, vol. 40, pp. 184-187.
- Nomura.K et al., "Carrier transport in transparent oxide semiconductor with intrinsic structural randomness probed using single-crystalline InGaO<sub>3</sub>(ZnO)<sub>5</sub> films", Appl. Phys. Lett. (Applied Physics Letters), Sep. 13, 2004, vol. 85, No. 11, pp. 1993-1995.
- Li.C et al., "Modulated Structures of Homologous Compounds InMO<sub>3</sub>(ZnO)<sub>m</sub> (M=In,Ga; m=Integer) Described by Four-Dimensional Superspace Group", Journal of Solid State Chemistry, 1998, vol. 139, pp. 347-355.
- Son.K et al., "42.4L: Late-News Paper: 4 Inch QVGA AMOLED Driven by the Threshold Voltage Controlled Amorphous Gizo (Ga<sub>2</sub>O<sub>3</sub>-In<sub>2</sub>O<sub>3</sub>-ZnO) TFT", SID Digest '08 : SID International Symposium Digest of Technical Papers, May 20, 2008, vol. 39, pp. 633-636.
- Lee.J et al., "World's Largest (15-Inch) XGA AMLCD Panel Using IGZO Oxide TFT", SID Digest '08 : SID International Symposium Digest of Technical Papers, May 20, 2008, vol. 39, pp. 625-628.
- Nowatari.H et al., "60.2: Intermediate Connector With Suppressed Voltage Loss for White Tandem Oleds", SID Digest '09 : SID International Symposium Digest of Technical Papers, May 31, 2009, vol. 40, pp. 899-902.
- Kanno.H et al., "White Stacked Electrophosphorescent Organic Light-Emitting Devices Employing MOO<sub>3</sub> as a Charge-Generation Layer", Adv. Mater. (Advanced Materials), 2006, vol. 18, No. 3, pp. 339-342.
- Tsuda.K et al., "Ultra Low Power Consumption Technologies for Mobile TFT-LCDs", IDW '02 : Proceedings of the 9th International Display Workshops, Dec. 4, 2002, pp. 295-298.
- Van de Walle.C, "Hydrogen as a Cause of Doping in Zinc Oxide", Phys. Rev. Lett. (Physical Review Letters), Jul. 31, 2000, vol. 85, No. 5, pp. 1012-1015.
- Fung.T et al., "2-D Numerical Simulation of High Performance Amorphous In-Ga-Zn-O TFTs for Flat Panel Displays", AM-FPD '08 Digest of Technical Papers, Jul. 2, 2008, pp. 251-252, The Japan Society of Applied Physics.
- Jeong.J et al., "3.1: Distinguished Paper: 12.1-Inch WXGA AMOLED Display Driven by Indium-Gallium-Zinc Oxide TFTs Array", SID Digest '08 : SID International Symposium Digest of Technical Papers, May 20, 2008, vol. 39, No. 1, pp. 1-4.
- Park.J et al., "High performance amorphous oxide thin film transistors with self-aligned top-gate structure", IEDM 09: Technical Digest of International Electron Devices Meeting, Dec. 7, 2009, pp. 191-194.
- Kurokawa. Y et al., "UHF RFCPUS on Flexible and Glass Substrates for Secure RFID Systems", Journal of Solid-State Circuits, 2008, vol. 43, No. 1, pp. 292-299.
- Ohara.H et al., "Amorphous In-Ga-Zn-Oxide TFTs with Suppressed Variation for 4.0 inch QVGA AMOLED Display", AM-FPD '09 Digest of Technical Papers, Jul. 1, 2009, pp. 227-230, The Japan Society of Applied Physics.
- Coates.D et al., "Optical Studies of the Amorphous Liquid-Cholesteric Liquid Crystal Transition:The "Blue Phase"", Physics Letters, Sep. 10, 1973, vol. 45A, No. 2, pp. 115-116.
- Cho.D et al., "21.2:Al and Sn-Doped Zinc Indium Oxide Thin Film Transistors for AMOLED Back-Plane", SID Digest '09 : SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 280-283.
- Lee.M et al., "15.4:Excellent Performance of Indium-Oxide-Based Thin-Film Transistors by DC Sputtering", SID Digest '09 : SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 191-193.
- Jin.D et al., "65.2:Distinguished Paper:World-Largest (6.5') Flexible Full Color Top Emission AMOLED Display on Plastic Film and Its Bending Properties", SID Digest '09 : SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 983-985.
- Sakata.J et al., "Development of 4.0-In. AMOLED Display With Driver Circuit Using Amorphous In-Ga-Zn-Oxide TFTs", IDW'09: Proceedings of the 16th International Display Workshops, 2009, pp. 689-692.
- Park.J et al., "Amorphous Indium-Gallium-Zinc Oxide TFTs and Their Application for Large Size AMOLED", AM-FPD '08 Digest of Technical Papers, Jul. 2, 2008, pp. 275-278.
- Park.S et al., "Challenge to Future Displays: Transparent AMOLED Driven By PEALD Grown ZnO TFT", IMID '07 DIGEST, 2007, pp. 1249-1252.
- Godo.H et al., "Temperature Dependence of Characteristics and Electronic Structure for Amorphous In-Ga-Zn-Oxide TFT", AM-FPD '09 Digest of Technical Papers, Jul. 1, 2009, pp. 41-44.

(56)

## References Cited

## OTHER PUBLICATIONS

- Osada.T et al., "Development of Driver-Integrated Panel Using Amorphous In-Ga-Zn-Oxide TFT", AM-FPD '09 Digest of Technical Papers, Jul. 1, 2009, pp. 33-36.
- Hirao.T et al., "Novel Top-Gate Zinc Oxide Thin-Film Transistors (ZnO TFTS) for AMLCDS", J. Soc. Inf. Display (Journal of the Society for Information Display), 2007, vol. 15, No. 1, pp. 17-22.
- Hosono.H, "68.3:Invited Paper: Transparent Amorphous Oxide Semiconductors for High Performance TFT", SID Digest '07 : SID International Symposium Digest of Technical Papers, 2007, vol. 38, pp. 1830-1833.
- Godou.H et al., "P-9:Numerical Analysis on Temperature Dependence of Characteristics of Amorphous In-Ga-Zn-Oxide TFT", SID Digest '09 : SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 1110-1112.
- Ohara.H et al., "21.3:4.0 In. QVGA AMOLED Display Using In-Ga-Zn-Oxide TFTS With a Novel Passivation Layer", SID Digest '09 : SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 284-287.
- Miyasaka.M, "SUFTLA Flexible Microelectronics on Their Way to Business", SID Digest '07 : SID International Symposium Digest of Technical Papers, 2007, vol. 38, pp. 1673-1676.
- Chern.H et al., "An Analytical Model for the Above-Threshold Characteristics of Polysilicon Thin-Film Transistors", IEEE Transactions on Electron Devices, Jul. 1, 1995, vol. 42, No. 7, pp. 1240-1246.
- Kikuchi.H et al., "39.1:Invited Paper:Optically Isotropic Nano-Structured Liquid Crystal Composites for Display Applications", SID Digest '09 : SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 578-581.
- Asaoka. Y et al., "29.1:Polarizer-FREE Reflective LCD Combined With Ultra Low-Power Driving Technology", SID Digest '09 : SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 395-398.
- Lee.H et al., "Current Status of, Challenges to, and Perspective View of AM-OLED", IDW '06 : Proceedings of the 13th International Display Workshops, Dec. 7, 2006, pp. 663-666.
- Kikuchi.H et al., "62.2:Invited Paper:Fast Electro-Optical Switching in Polymer-Stabilized Liquid Crystalline Blue Phases for Display Application", SID Digest '07 : SID International Symposium Digest of Technical Papers, 2007, vol. 38, pp. 1737-1740.
- Nakamura.M, "Synthesis of Homologous Compound with New Long-Period Structure", NIRIM Newsletter, Mar. 1, 1995, vol. 150, pp. 1-4.
- Kikuchi.H et al., "Polymer-Stabilized Liquid Crystal Blue Phases", Nature Materials, Sep. 2, 2002, vol. 1, pp. 64-68.
- Kimizuka.N et al., "Spinel, YBFE2O4, and YB2FE3O7 Types of Structures for Compounds in the IN2O3 and SC2O3-A2O3-BO Systems [A; Fe, Ga, or Al; B: Mg, Mn, Fe, Ni, Cu, or Zn] at Temperatures Over 1000° C", Journal of Solid State Chemistry, 1985, vol. 60, pp. 382-384.
- Kitzerow.H et al., "Observation of Blue Phases in Chiral Networks", Liquid Crystals, 1993, vol. 14, No. 3, pp. 911-916.
- Costello.M et al., "Electron Microscopy of a Cholesteric Liquid Crystal and Its Blue Phase", Phys. Rev. A (Physical Review. A), May 1, 1984, vol. 29, No. 5, pp. 2957-2959.
- Meiboom.S et al., "Theory of the Blue Phase of Cholesteric Liquid Crystals", Phys. Rev. Lett. (Physical Review Letters), May 4, 1981, vol. 46, No. 18, pp. 1216-1219.
- Park.S et al., "42.3: Transparent ZnO Thin Film Transistor for the Application of High Aperture Ratio Bottom Emission AM-OLED Display", SID Digest '08 : SID International Symposium Digest of Technical Papers, May 20, 2008, vol. 39, pp. 629-632.
- Orita.M et al., "Mechanism of Electrical Conductivity of Transparent InGaZnO4", Phys. Rev. B (Physical Review. B), Jan. 15, 2000, vol. 61, No. 3, pp. 1811-1816.
- Nomura.K et al., "Amorphous Oxide Semiconductors for High-Performance Flexible Thin-Film Transistors", Jpn. J. Appl. Phys. (Japanese Journal of Applied Physics), 2006, vol. 45, No. 5B, pp. 4303-4308.
- Janotti.A et al., "Native Point Defects in ZnO", Phys. Rev. B (Physical Review. B), Oct. 4, 2007, vol. 76, No. 16, pp. 165202-1-165202-22.
- Park.J et al., "Electronic Transport Properties of Amorphous Indium-Gallium-Zinc Oxide Semiconductor Upon Exposure to Water", Appl. Phys. Lett. (Applied Physics Letters) 2008, vol. 92, pp. 072104-1-072104-3.
- Hsieh.H et al., "P-29:Modeling of Amorphous Oxide Semiconductor Thin Film Transistors and Subgap Density of States", SID Digest '08 : SID International Symposium Digest of Technical Papers, May 20, 2008, vol. 39, pp. 1277-1280.
- Janotti.A et al., "Oxygen Vacancies in ZnO", Appl. Phys. Lett. (Applied Physics Letters), 2005, vol. 87, pp. 122102-1-122102-3.
- Oba.F et al., "Defect energetics in ZnO: A hybrid Hartree-Fock density functional study", Phys. Rev. B (Physical Review. B), 2008, vol. 77, pp. 245202-1-245202-6.
- Orita.M et al., "Amorphous transparent conductive oxide InGaO3(ZnO)m (m<4):a Zn4s conductor", Philosophical Magazine, 2001, vol. 81, No. 5, pp. 501-515.
- Hosono.H et al., "Working hypothesis to explore novel wide band gap electrically conducting amorphous oxides and examples", J. Non-Cryst. Solids (Journal of Non-Crystalline Solids), 1996, vol. 198-200, pp. 165-169.
- Mo.Y et al., "Amorphous Oxide TFT Backplanes for Large Size AMOLED Displays", IDW '08 : Proceedings of the 6th International Display Workshops, Dec. 3, 2008, pp. 581-584.
- Kim.S et al., "High-Performance oxide thin film transistors passivated by various gas plasmas", 214th ECS Meeting, 2008, No. 2317, ECS.
- Clark.S et al., "First Principles Methods Using CASTEP", Zeitschrift für Kristallographie, 2005, vol. 220, pp. 567-570.
- Lany.S et al., "Dopability, Intrinsic Conductivity, and Nonstoichiometry of Transparent Conducting Oxides", Phys. Rev. Lett. (Physical Review Letters), Jan. 26, 2007, vol. 98, pp. 045501-1-045501-4.
- Park.J et al., "Dry etching of ZnO films and plasma-induced damage to optical properties", J. Vac. Sci. Technol. B (Journal of Vacuum Science & Technology B), Mar. 1, 2003, vol. 21, No. 2, pp. 800-803.
- Oh.M et al., "Improving the Gate Stability of ZnO Thin-Film Transistors With Aluminum Oxide Dielectric Layers", J. Electrochem. Soc. (Journal of the Electrochemical Society), 2008, vol. 155, No. 12, pp. H1009-H1014.
- Ueno.K et al., "Field-Effect Transistor on SrTiO3 With Sputtered Al2O3 Gate Insulator", Appl. Phys. Lett. (Applied Physics Letters), Sep. 1, 2003, vol. 83, No. 9, pp. 1755-1757.
- International Search Report (Application No. PCT/JP2010/067495) dated Nov. 16, 2010.
- Written Opinion (Application No. PCT/JP2010/067495) dated Nov. 16, 2010.
- Fortunato.E et al., "High field-effect mobility zinc oxide thin film transistors produced at room temperature", J. Non-Cryst. Solids (Journal of Non-Crystalline Solids), 2004, vol. 338-340, pp. 806-809, Elsevier.
- Taiwanese Office Action (Application No. 099134424) dated Apr. 22, 2015.
- Korean Office Action (Application No. 2012-7012352) dated Dec. 12, 2016.
- Taiwanese Office Action (Application No. 106103969) dated Oct. 6, 2017.
- Taiwanese Office Action (Application No. 109118669) dated Jul. 12, 2021.
- Taiwanese Office Action (Application No. 111104286) dated Nov. 24, 2022.

\* cited by examiner

FIG. 1A




FIG. 1B




FIG. 2




FIG. 3






FIG. 4A




FIG. 4B




FIG. 5




FIG. 6




FIG. 7A




FIG. 7B




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 9




FIG. 10A




FIG. 10B




FIG. 10C




FIG. 11A




FIG. 11B






FIG. 12




FIG. 13




FIG. 14A




FIG. 14B




FIG. 15




FIG. 16A




FIG. 16B




FIG. 17




FIG. 18A




FIG. 18D




FIG. 18B




FIG. 18E





FIG. 18C



## SEMICONDUCTOR DEVICE AND MANUFACTURING METHOD THEREOF

### CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. application Ser. No. 16/121,700, filed Sep. 5, 2018, now allowed, which is a continuation of U.S. application Ser. No. 15/372,493, filed Dec. 8, 2016, now U.S. Pat. No. 10,074,747, which is a divisional of U.S. application Ser. No. 13/799,246, filed Mar. 13, 2013, now U.S. Pat. No. 9,666,678, which is a continuation of U.S. application Ser. No. 12/904,565, filed Oct. 14, 2010, now U.S. Pat. No. 8,421,068, which claims the benefit of a foreign priority application filed in Japan as Serial No. 2009-238885 on Oct. 16, 2009, all of which are incorporated by reference.

### TECHNICAL FIELD

The present invention relates to a semiconductor device including an integrated circuit which includes a thin film transistor (hereinafter, referred to as a TFT) and a manufacturing method thereof. For example, the present invention relates to an electronic device on which a semiconductor integrated circuit is mounted as a component.

In this specification, a "semiconductor device" generally refers to a device which can function by utilizing semiconductor characteristics; an electro-optical device, a semiconductor circuit, an electronic component, and an electronic device are all included in semiconductor devices.

### BACKGROUND ART

In recent years, semiconductor devices have been developed to be used as an LSI, a CPU, or a memory. A CPU is an aggregation of semiconductor elements each provided with an electrode which is a connection terminal, which includes a semiconductor integrated circuit (including at least a transistor and a memory) separated from a semiconductor wafer.

A semiconductor circuit (IC chip) of an LSI, a CPU, or a memory is mounted on a circuit board, for example, a printed wiring board, to be used as one of components of a variety of electronic devices.

In addition, a semiconductor device capable of transmitting and receiving data has been developed. Such a semiconductor device is called a wireless tag, an RFID tag, or the like. Those put into practical use include a semiconductor circuit (IC chip) formed using an antenna and a semiconductor substrate in many cases.

A silicon-based semiconductor material has been known as a semiconductor thin film which can be applied to a thin film transistor; however, an oxide semiconductor is attracting attention as another material. As a material of the oxide semiconductor, zinc oxide or a material including zinc oxide as its component is known. In addition, a thin film transistor including an amorphous oxide (oxide semiconductor) whose electron carrier concentration is lower than  $10^{18}/\text{cm}^3$  is disclosed (Patent Documents 1 to 3).

### REFERENCE

[Patent Document 1] Japanese Published Patent Application No. 2006-165527

[Patent Document 2] Japanese Published Patent Application No. 2006-165528

[Patent Document 3] Japanese Published Patent Application No. 2006-165529

### DISCLOSURE OF INVENTION

5

Power consumption of electronic devices in a standby period is regarded as important in addition to power consumption in an operating period. Specifically, as for portable electronic devices, to which power is supplied from battery, time of use is limited due to limited amount of electric power. Further, as for in-vehicle electronic devices, when leakage current in a standby period is large, lifetime of battery may be reduced. In the case of an electric vehicle, leakage current of the in-vehicle electronic device shortens the traveling distance per a certain amount of charging.

In order to reduce power consumption, reducing leakage current in a standby period in addition to power consumption in an operating period is effective. Although the amount of leakage current of each transistor is not large, several millions of transistors are provided in the LSI, and when the amount of leakage current of those transistors is added up, the resulting amount is by no means small. Such leakage current causes an increase in power consumption of the semiconductor device in a standby period. Although leakage current is caused by various factors, electric power can be saved in a driver circuit or the like which is used in electronic devices, if leakage current in a standby period can be reduced.

Therefore, an object of the present invention is to reduce leakage current of a transistor used for an LSI, a CPU, or a memory.

Reduction in parasitic capacitance is also effective for reduction in power consumption in an operating period; therefore, another object of the present invention is to reduce power consumption by reducing parasitic capacitance.

In addition, another object of the present invention is to shorten the channel length  $L$  of a transistor used in a semiconductor integrated circuit such as an LSI, a CPU, or a memory, so that operation speed of the circuit is increased, and further, power consumption is reduced.

A semiconductor integrated circuit such as an LSI, a CPU, or a memory is manufactured using a thin film transistor in which a channel formation region is formed using an oxide semiconductor which becomes an intrinsic or substantially intrinsic semiconductor by removing impurities which serve as electron donors (donors) from the oxide semiconductor and has larger energy gap than that of a silicon semiconductor.

A highly purified oxide semiconductor layer with sufficiently reduced hydrogen concentration, in which impurities such as hydrogen or OH group contained are removed so that the hydrogen concentration is lower than or equal to  $5 \times 10^{19}/\text{cm}^3$ , preferably lower than or equal to  $5 \times 10^{18}/\text{cm}^3$  or, more preferably lower than or equal to  $5 \times 10^{17}/\text{cm}^3$ , is used for a thin film transistor, whereby an off-current of the thin film transistor is reduced. Note that the concentration of hydrogen in the oxide semiconductor layer is measured by secondary ion mass spectrometry (SIMS).

It is preferable that when the gate voltage  $V_g$  is positive, a drain current  $I_d$  be sufficiently large, and when the gate voltage  $V_g$  is less than or equal to zero, the drain current  $I_d$  be zero. In a thin film transistor using the highly purified oxide semiconductor layer with sufficiently reduced hydrogen concentration, in the case where a drain voltage  $V_d$  is +1V or +10V, an off-current value can be smaller than  $1 \times 10^{-13}$  [A] while the gate voltage  $V_g$  is in the range of -5V to -20V.



By using the thin film transistor using the highly purified oxide semiconductor layer with sufficiently reduced hydrogen concentration, a semiconductor device whose power consumption due to leakage current is low can be realized.

The thin film transistor using the highly purified oxide semiconductor layer with sufficiently reduced hydrogen concentration can be formed over a glass substrate, and an LSI, a CPU, or a memory can be formed thereover. By using a large-area glass substrate, manufacturing cost can be reduced. Without being limited to a glass substrate, the thin film transistor using the oxide semiconductor layer with sufficiently reduced hydrogen concentration can be formed over a silicon substrate. A silicon substrate with high thermal conductivity is preferably used to dissipate heat from the semiconductor circuit. Alternatively, the thin film transistor using the oxide semiconductor layer with sufficiently reduced hydrogen concentration can be formed over a flexible substrate, for example, a plastic film, whereby a flexible wireless tag can be manufactured.

One of the structures of the invention disclosed in this specification is a semiconductor device provided with a semiconductor integrated circuit including a plurality of thin film transistors including; an oxide semiconductor layer over an insulating surface, whose hydrogen concentration measured by secondary ion mass spectrometry is lower than or equal to  $5 \times 10^{19}/\text{cm}^3$  and carrier concentration is lower than or equal to  $5 \times 10^{14}/\text{cm}^3$ , a source and drain electrode layers over the oxide semiconductor layer, a gate insulating layer over the oxide semiconductor layer and the source and drain electrode layers, and a gate electrode layer over the gate insulating layer.

With the above structure, at least one of the above problems can be resolved.

In addition, a conductive layer may be formed below the oxide semiconductor layer. Thus, another structure of the invention is a semiconductor device including a plurality of thin film transistors including; a conductive layer over an insulating surface, an insulating layer over the conductive layer, an oxide semiconductor layer over the insulating layer, whose hydrogen concentration measured by secondary ion mass spectrometry is lower than or equal to  $5 \times 10^{19}/\text{cm}^3$  and carrier concentration is lower than or equal to  $5 \times 10^{14}/\text{cm}^3$ , a source and drain electrode layers over the oxide semiconductor layer, a gate insulating layer over the oxide semiconductor layer and the source and drain electrode layers, and a gate electrode layer over the gate insulating layer, wherein the conductive layer overlaps with the oxide semiconductor layer with the insulating layer interposed therebetween.

In order to reduce parasitic capacitance, each of the above structures further include an insulating layer over and in contact with the source and drain electrode layers, so that the source and drain electrode layers overlap with part of the gate electrode layer with the gate insulating layer and the insulating layer interposed therebetween. By providing the insulating layer over and in contact with the source and drain electrode layers, parasitic capacitance between the gate electrode layer and the source electrode layer and between the gate electrode layer and the drain electrode layer can be reduced.

Further, in a wiring intersection portion, in order to reduce the parasitic capacitance, the gate insulating layer and the insulating layer are stacked between a gate wiring layer and a source wiring layer. An increase in the distance between the gate wiring layer and the source wiring layer can reduce power consumption due to parasitic capacitance, and can prevent short circuit between wirings.

Further, an EDMOS circuit can be formed by combining a plurality of thin film transistors using an oxide semiconductor layer with sufficiently reduced hydrogen concentration. Such an EDMOS circuit includes a first thin film transistor including a first oxide semiconductor layer and a second thin film transistor including a second oxide semiconductor layer over an insulating surface, wherein the hydrogen concentration of the first oxide semiconductor layer and the second semiconductor layer measured by secondary ion mass spectrometry is lower than or equal to  $5 \times 10^{19}/\text{cm}^3$  and the carrier concentration thereof is lower than or equal to  $5 \times 10^{14}/\text{cm}^3$ .

A resistor, a capacitor, an inductor, and the like can be formed over one substrate by using the oxide semiconductor layer with sufficiently reduced hydrogen concentration. For example, the resistor can be formed by sandwiching the oxide semiconductor layer with sufficiently reduced hydrogen concentration between upper and lower electrode layers. In each of the above structures, an oxide semiconductor layer which serves as a resistor is formed over the same substrate, between a first conductive layer and a second conductive layer overlapping with the first conductive layer.

In addition to an LSI, a CPU, or a memory, the thin film transistor using the oxide semiconductor layer with sufficiently reduced hydrogen concentration can be used for a power supply circuit, a transmitting and receiving circuit, an amplifier of an audio processing circuit, a driver circuit of a display portion, a controller, a converter of an audio processing circuit, or the like.

Alternatively, a plurality of semiconductor integrated circuits can be mounted on one package, which is a so-called MCP (Multi Chip Package), so that the semiconductor device is highly integrated.

In the case where the semiconductor integrated circuit is mounted on a circuit board, the semiconductor integrated circuit may be mounted in a face-up state or a flip-chip state (face-down state).

A thin film transistor using the oxide semiconductor layer with sufficiently reduced hydrogen concentration can extremely reduce leakage current, and a semiconductor device with low power consumption can be realized by using the thin film transistor for a semiconductor integrated circuit.

#### BRIEF DESCRIPTION OF DRAWINGS

FIGS. 1A and 1B are cross-sectional views illustrating one embodiment of the present invention.

FIG. 2 is an equivalent circuit diagram illustrating one embodiment of the present invention.

FIG. 3 is a cross-sectional view illustrating one embodiment of the present invention.

FIGS. 4A and 4B are respectively a cross-sectional view and a top view illustrating one embodiment of the present invention.

FIG. 5 is a block diagram illustrating one embodiment of the present invention.

FIG. 6 illustrates a block diagram.

FIGS. 7A and 7B are views each illustrating a semiconductor device.

FIGS. 8A to 8C are views illustrating a semiconductor device.

FIG. 9 is a view illustrating a semiconductor device.

FIGS. 10A to 10C are views illustrating a semiconductor device.

FIGS. 11A and 11B are equivalent circuit diagrams illustrating one embodiment of the present invention.

FIG. 12 is a diagram illustrating a band structure between a source and a drain of a MOS transistor using an oxide semiconductor.

FIG. 13 is a diagram illustrating a state in which a positive voltage is applied to the drain side in FIG. 12.

FIGS. 14A and 14B are energy band diagrams of a MOS structure of the MOS transistor using an oxide semiconductor, illustrating a case where a gate voltage is set positive and a case where the gate voltage is set negative, respectively.

FIG. 15 is a comparative diagram illustrating a band structure between a source and a drain of a silicon MOS transistor.

FIGS. 16A and 16B are equivalent circuit diagrams illustrating one embodiment of the present invention.

FIG. 17 is an equivalent circuit diagram illustrating one embodiment of the present invention.

FIGS. 18A to 18E are views, each illustrating an example of an electronic device.

#### BEST MODE FOR CARRYING OUT THE INVENTION

Hereinafter, embodiments of the present invention will be described in detail with reference to the accompanying drawings. However, the present invention is not limited to the description below, and it is easily understood by those skilled in the art that modes and details disclosed herein can be modified in various ways without departing from the spirit and the scope of the present invention. Therefore, the present invention is not construed as being limited to description of the embodiments.

##### Embodiment 1

This embodiment describes an example of a cross-sectional structure of a semiconductor integrated circuit.

In this embodiment, one embodiment of a semiconductor integrated circuit and a manufacturing method thereof is described with reference to FIGS. 1A and 1B, FIG. 2, FIG. 3, and FIGS. 4A and 4B.

An example of a cross-sectional structure of the semiconductor integrated circuit is illustrated in FIGS. 1A and 1B. A thin film transistor 440 illustrated in FIG. 1B is one of top-gate thin film transistors.

The thin film transistor 440 includes a first insulating layer 447a, a second insulating layer 443, a third insulating layer 447b, an oxide semiconductor layer 442, a first source electrode layer 445a, a second source electrode layer 448a, a first drain electrode layer 445b, a second drain electrode layer 448b, a gate insulating layer 444, and a gate electrode layer 441, over a substrate 430 having an insulating surface.

Part of the oxide semiconductor layer 442 which overlaps with the gate electrode layer 441 is a channel formation region, and a channel length L1 is determined by the distance between the lower edge portion of the first source electrode layer 445a and the lower edge portion of the first drain electrode layer 445b which are next to each other over the oxide semiconductor layer 442.

The thin film transistor 440 is described using a single-gate thin film transistor; however, a thin film transistor having a multi-gate structure in which a plurality of channel formation regions is included can also be used as needed.

A thin film transistor 470 with reduced parasitic capacitance can be formed over the same substrate and in the same steps as the thin film transistor 440.

Hereinafter, steps for manufacturing the thin film transistors 440 and 470 over the substrate 430 will be described below with reference to FIG. 1A.

Although there is no particular limitation on a substrate which can be used as the substrate 430 having an insulating surface, the substrate needs to have at least heat resistance high enough to withstand heat treatment to be performed later. As the substrate 430 having an insulating surface, a glass substrate formed of barium borosilicate glass, aluminoborosilicate glass, or the like can be used.

In the case where a glass substrate is used and the temperature at which the heat treatment is to be performed later is high, a glass substrate whose strain point is greater than or equal to 730° C. is preferably used. As a glass substrate, a glass material such as aluminosilicate glass, aluminoborosilicate glass, or barium borosilicate glass is used, for example. Note that by containing a larger amount of barium oxide (BaO) than that of boric oxide (B<sub>2</sub>O<sub>3</sub>), a glass substrate is heat-resistant and of more practical use. Therefore, a glass substrate containing a larger amount of BaO than that of B<sub>2</sub>O<sub>3</sub> is preferably used.

Note that instead of the above glass substrate, a substrate formed of an insulator such as a ceramic substrate, a quartz substrate, or a sapphire substrate may be used. Alternatively, a crystallized glass substrate or the like may be used. Alternatively, a semiconductor substrate including an insulating layer on its surface, a plastic substrate, or the like can be used as appropriate.

First, after a conductive film is formed over the substrate 430 having an insulating surface, electrode layers 479a, 479b and 479c are formed by a first photolithography step. The electrode layers 479a, 479b and 479c can be formed using an element selected from Al, Cr, Cu, Ta, Ti, Mo, and W, an alloy containing any of these elements, an alloy film containing a combination of any of these elements, or the like. In this embodiment, the electrode layers 479a, 479b and 479c have a stacked layer structure of a tungsten nitride layer and a tungsten layer.

Next, the first insulating layer 447a is formed to cover the electrode layers 479a, 479b and 479c. The first insulating layer 447a can be formed using a single-layer or stacked layers of a silicon oxide layer, a silicon nitride layer, a silicon oxynitride layer, and/or a silicon nitride oxide layer by a plasma CVD method, a sputtering method, or the like.

Next, a spacer insulating layer is formed over the first insulating layer 447a, and is selectively removed then by a second photolithography step to form the second insulating layer 443. The spacer insulating layer is formed using a single layer or stacked layers of a silicon oxide layer, a silicon nitride layer, a silicon oxynitride layer, and/or a silicon nitride oxide layer by a plasma CVD method, a sputtering method, or the like. The thickness of the spacer insulating layer is 500 nm to 2 μm, inclusive. In the same step, a fifth insulating layer 473 functioning as a spacer insulating layer is formed so as to overlap with the electrode layer 479c. In this manner, a stacked layer region with large thickness and a single layer region with small thickness are formed. In order to reduce parasitic capacitance, the fourth insulating layer functioning as a spacer insulating layer and the first insulating layer are stacked in the region with large thickness, and in order to form a storage capacitor and the like, the first insulating layer is provided in the region with small thickness.

Next, the third insulating layer 447b is formed to cover the first insulating layer 447a, the second insulating layer 443, and the fifth insulating layer 473. The third insulating layer 447b which is in contact with the oxide semiconductor

layer is preferably formed using an oxide insulating layer such as a silicon oxide layer, a silicon oxynitride layer, an aluminum oxide layer, or an aluminum oxynitride layer. As a method for forming the third insulating layer **447b**, a plasma CVD method, a sputtering method, or the like can be used; however, it is preferable that the third insulating layer **447b** be formed by a sputtering method, so that the third insulating layer **447b** does not contain a large amount of hydrogen.

In this embodiment, a silicon oxide layer is formed as the third insulating layer **447b** by a sputtering method. The substrate **430** is transferred to a treatment chamber, a sputtering gas including highly purified oxygen from which hydrogen and moisture are removed is introduced thereinto, and a silicon oxide layer is formed over the substrate **430** as the third insulating layer **447b** using a silicon target. The temperature of the substrate **430** may be room temperature, or the substrate **430** may be heated.

For example, a silicon oxide layer is formed by an RF sputtering method using quartz (preferably, synthetic quartz) in an atmosphere containing oxygen and argon (the flow rate of oxygen is 25 sccm, and the flow rate of argon is 25 sccm), under conditions where a substrate temperature is 108° C., the distance between the substrate and the target (T-S distance) is 60 mm, the pressure is 0.4 Pa, and a high-frequency power source is 1.5 kW. The thickness of the layer is 100 nm. Note that instead of quartz (preferably, synthetic quartz), a silicon target can be used as a target for deposition of the silicon oxide layer. As the sputtering gas, oxygen or a mixed gas of oxygen and argon is used.

In this case, it is preferable that the third insulating layer **447b** be formed while moisture remaining in the treatment chamber is removed. This is so that the third insulating layer **447b** does not contain hydrogen, hydroxyl, or moisture.

In order to remove moisture remaining in the treatment chamber, an adsorption type vacuum pump is preferably used. For example, a cryopump, an ion pump, or a titanium sublimation pump is preferably used. As an evacuation unit, a turbo pump provided with a cold trap may be used. In a treatment chamber which is evacuated using a cryopump, for example, hydrogen atoms, compounds including hydrogen atoms such as water (H<sub>2</sub>O), or the like are exhausted; thus, the concentration of impurities contained in the third insulating layer **447b** which is deposited in the treatment chamber can be reduced.

Examples of a sputtering method include an RF sputtering method in which a high-frequency power source is used for a sputtering power supply, a DC sputtering method in which a DC power source is used, and a pulsed DC sputtering method in which a bias is applied in a pulsed manner. An RF sputtering method is mainly used in the case where an insulating film is formed, and a DC sputtering method is mainly used in the case where a metal film is formed.

In addition, there is also a multi-source sputtering apparatus in which a plurality of targets of different materials can be set. With the multi-source sputtering apparatus, films of different materials can be formed to be stacked in the same chamber, or a film of plural kinds of materials can be formed by electric discharge at the same time in the same chamber.

In addition, there are a sputtering apparatus provided with a magnet system inside the chamber and used for a magnetron sputtering, and a sputtering apparatus used for an ECR sputtering in which plasma generated with the use of microwaves is used without using glow discharge.

Furthermore, as a deposition method using sputtering, there are also a reactive sputtering method in which a target substance and a sputtering gas component are chemically

reacted with each other during deposition to form a thin compound film thereof, and a bias sputtering in which a voltage is also applied to a substrate during deposition.

The third insulating layer **447b** can also have a stacked layer structure. For example, a nitride insulating layer such as a silicon nitride layer, a silicon nitride oxide layer, or an aluminum nitride layer, and the above-described oxide insulating layer may be stacked in this order from the substrate **430** side.

For example, a sputtering gas including high-purified nitrogen from which hydrogen and moisture are removed is introduced between the silicon oxide layer and the substrate to form a silicon nitride layer using a silicon target. In this case, it is preferable that the silicon nitride layer be formed while moisture remaining in the treatment chamber is removed, in a manner similar to that of the silicon oxide layer.

Also in the case of forming the silicon nitride layer, the substrate may be heated at the time of deposition.

In the case where the silicon nitride layer and the silicon oxide layer are stacked as the third insulating layer **447b**, the silicon nitride layer and the silicon oxide layer can be formed in one treatment chamber using the same silicon target. First, a sputtering gas including nitrogen is introduced into the treatment chamber, and the silicon nitride layer is formed using a silicon target provided in the treatment chamber. Then, the sputtering gas is switched to a sputtering gas including oxygen, and the silicon oxide layer is formed using the same silicon target. The silicon nitride layer and the silicon oxide layer can be formed in succession without being exposed to air, thereby preventing impurities such as hydrogen or moisture from being adsorbed onto a surface of the silicon nitride layer.

Then, an oxide semiconductor film is formed to a thickness of greater than or equal to 2 nm and less than or equal to 200 nm over the third insulating layer **447b**.

In addition, in order that hydrogen, hydroxyl, and moisture are contained as little as possible in the oxide semiconductor film, it is preferable that the substrate **430** over which the third insulating layer **447b** is formed be preheated in a preheating chamber of the sputtering apparatus, so that impurities such as hydrogen or moisture absorbed onto the substrate **430** are discharged and exhausted, as a pretreatment before deposition. Note that as an evacuation, a cryopump is preferably provided in the preheating chamber. Note also that this preheating treatment can be omitted in some cases.

Note that before the oxide semiconductor film is formed by a sputtering method, dust on a surface of the third insulating layer **447b** is preferably removed by reverse sputtering in which an argon gas is introduced and plasma is generated. The reverse sputtering is a method in which voltage is applied to a substrate side without applying voltage to a target side, using a high-frequency power source to generate plasma in the vicinity of the substrate side in an argon atmosphere, so that a surface is modified. Note that instead of an argon atmosphere, a nitrogen atmosphere, a helium atmosphere, an oxygen atmosphere, or the like may be used.

The oxide semiconductor film is formed by a sputtering method. Any of the following is used as the oxide semiconductor film: an In—Ga—Zn—O-based oxide semiconductor film, an In—Sn—Zn—O-based oxide semiconductor film, an In—Al—Zn—O-based oxide semiconductor film, a Sn—Ga—Zn—O-based oxide semiconductor film, an Al—Ga—Zn—O-based oxide semiconductor film, a Sn—Al—Zn—O-based oxide semiconductor film, an In—Zn—O-based

oxide semiconductor film, a Sn—Zn—O-based oxide semiconductor film, an Al—Zn—O-based oxide semiconductor film, an In—O-based oxide semiconductor film, a Sn—O-based oxide semiconductor film, and a Zn—O-based oxide semiconductor film. In this embodiment, the oxide semiconductor film is formed by a sputtering method with the use of a target for formation of an In—Ga—Zn—O-based oxide semiconductor film. The oxide semiconductor film can be formed by a sputtering method in a rare gas (typically, argon) atmosphere, an oxygen atmosphere, or a mixed atmosphere including a rare gas (typically, argon) and oxygen. In the case of using a sputtering method, a target including SiO<sub>2</sub> at 2 wt % to 10 wt % inclusive may be used for deposition.

As a target for forming the oxide semiconductor film by a sputtering method, a target of metal oxide which contains zinc oxide as its main component can be used. As another example of a target of metal oxide, an oxide semiconductor target for film formation including In, Ga, and Zn (composition ratio is In<sub>2</sub>O<sub>3</sub>:Ga<sub>2</sub>O<sub>3</sub>:ZnO=1:1:1 [molar ratio]) can be used. As an oxide semiconductor target for film formation including In, Ga, and Zn, a target having a composition ratio of In<sub>2</sub>O<sub>3</sub>:Ga<sub>2</sub>O<sub>3</sub>:ZnO=1:1:2 [molar ratio], or In<sub>2</sub>O<sub>3</sub>:Ga<sub>2</sub>O<sub>3</sub>:ZnO=1:1:4 [molar ratio] can also be used. The filling rate of the oxide semiconductor target for film formation is 90% to 100% inclusive, preferably, 95% to 99.9% inclusive. By using an oxide semiconductor target for film formation with high filling rate, the deposited oxide semiconductor film becomes a dense film.

The oxide semiconductor film is formed in the following manner: the substrate is held in the treatment chamber which is kept in a reduced pressure state, a sputtering gas from which hydrogen and moisture are removed is introduced into the treatment chamber while removing moisture remaining therein, and the oxide semiconductor film is formed over the substrate **430** using metal oxide as a target. In order to remove moisture remaining in the treatment chamber, an adsorption type vacuum pump is preferably used. For example, a cryopump, an ion pump, or a titanium sublimation pump is preferably used. As an evacuation unit, a turbo pump provided with a cold trap may be used. In a treatment chamber which is evacuated using a cryopump, for example, hydrogen atoms, compounds including hydrogen atoms such as water (H<sub>2</sub>O) (more preferably, compounds including carbon atoms as well), or the like are exhausted; therefore, the concentration of impurities contained in the oxide semiconductor film which is deposited in the treatment chamber can be reduced. The substrate may be heated when the oxide semiconductor film is formed.

As one example of deposition conditions, conditions where a substrate temperature is room temperature, the distance between the substrate and the target is 60 mm, the pressure is 0.4 Pa, and a direct-current (DC) power source is 0.5 kW, and the atmosphere is an atmosphere of oxygen and argon (the flow rate of oxygen is 15 sccm, and the flow rate of argon is 30 sccm), are applied. It is preferable that a pulsed direct-current (DC) power supply be used because powder substances (also referred to as particles or dust) can be reduced and the film thickness can be uniform. The thickness of the oxide semiconductor film is preferably 5 nm to 30 nm, inclusive. Note that the appropriate thickness varies depending on the oxide semiconductor material used for the oxide semiconductor film, and can be selected as appropriate according to the material.

Next, the oxide semiconductor film is processed into island-shaped oxide semiconductor layers **442** and **472** in a third photolithography step (see FIG. 1A). Further, a resist

mask for forming the island-shaped oxide semiconductor layers **442** and **472** may be formed using an ink jet method. Formation of the resist mask by an inkjet method needs no photomask; thus, manufacturing cost can be reduced.

Note that etching of the oxide semiconductor film here can be dry etching, wet etching, or both of dry etching and wet etching.

As the etching gas for dry etching, a gas containing chlorine (chlorine-based gas such as chlorine (Cl<sub>2</sub>), boron chloride (BCl<sub>3</sub>), silicon chloride (SiCl<sub>4</sub>), or carbon tetrachloride (CCl<sub>4</sub>)) is preferably used.

Alternatively, a gas containing fluorine (fluorine-based gas such as carbon tetrafluoride (CF<sub>4</sub>), sulfur fluoride (SF<sub>6</sub>), nitrogen fluoride (NF<sub>3</sub>), or trifluoromethane (CHF<sub>3</sub>)); hydrogen bromide (HBr); oxygen (O<sub>2</sub>); any of these gases to which a rare gas such as helium (He) or argon (Ar) is added; or the like can be used.

As the dry etching method, a parallel plate RIE (reactive ion etching) method or an ICP (inductively coupled plasma) etching method can be used. In order to etch the films into desired shapes, the etching condition (the amount of electric power applied to a coil-shaped electrode, the amount of electric power applied to an electrode on a substrate side, the temperature of the electrode on the substrate side, or the like) is adjusted as appropriate.

As an etchant used for wet etching, a mixed solution of phosphoric acid, acetic acid, and nitric acid, an ammonia peroxide mixture (31 wt % of hydrogen peroxide solution: 28 wt % of ammonia water:water=5:2:2), or the like can be used. In addition, ITO07N (produced by KANTO CHEMICAL CO., INC.) may also be used.

The etchant after the wet etching is removed together with the etched materials by cleaning. The waste liquid including the etchant and the material etched off may be purified and the material may be reused. When a material such as indium included in the oxide semiconductor layer is collected from the waste liquid after the etching and reused, the resources can be efficiently used and the cost can be reduced.

The etching conditions (such as an etchant, etching time, and temperature) are appropriately adjusted depending on the material so that the material can be etched into a desired shape.

In this embodiment, the oxide semiconductor film is processed into island-shaped oxide semiconductor layers **442** and **472**, by a wet etching method using a mixed solution of phosphoric acid, acetic acid, and nitric acid as an etchant.

In this embodiment, a first heat treatment is performed on the oxide semiconductor layers **442** and **472**. A temperature of the first heat treatment is 400° C. to 750° C. inclusive, preferably higher than or equal to 400° C. and lower than the strain point of the substrate. In this embodiment, the substrate is introduced into an electric furnace, which is one of heat treatment apparatuses, and heat treatment is performed at 450° C. on the oxide semiconductor layers for an hour in a nitrogen atmosphere. Then, the oxide semiconductor layers are not exposed to air, which prevents reincorporation of water and hydrogen into the oxide semiconductor layers, so that the oxide semiconductor layers are obtained. By this first heat treatment, dehydration or dehydrogenation can be performed on the oxide semiconductor layers **442** and **472**.

However, the apparatus for the first heat treatment is not limited to the electric furnace and may be provided with a device for heating an object to be processed using heat conduction or heat radiation from a heating element such as a resistance heating element. For example, an RTA (rapid thermal anneal) apparatus such as a GRTA (gas rapid ther-

mal anneal) apparatus, or an LRTA (lamp rapid thermal anneal) apparatus can be used. An LRTA apparatus is an apparatus for heating an object to be processed by radiation of light (an electromagnetic wave) emitted from a lamp such as a halogen lamp, a metal halide lamp, a xenon arc lamp, a carbon arc lamp, a high pressure sodium lamp, or a high pressure mercury lamp. A GRTA apparatus is an apparatus with which heat treatment is performed using a high-temperature gas. As the gas, an inert gas which does not react with a process object by heat treatment, such as nitrogen or a rare gas such as argon is used.

For example, as the first heat treatment, GRTA can be performed, in which the substrate is transferred and put in an inert gas heated to a high temperature of 650° C. to 700° C. to be heated for several minutes, and then, the substrate is transferred and taken out of the inert gas heated to a high temperature. By using GRTA, high-temperature heat treatment in a short time is possible.

Note that in the first heat treatment, it is preferable that water, hydrogen, and the like be not contained in the atmosphere of nitrogen or a rare gas such as helium, neon, or argon. It is preferable that the purity of nitrogen or the rare gas such as helium, neon, or argon which is introduced into a heat treatment apparatus be set to be 6N (99.9999%) or higher, preferably 7N (99.99999%) or higher (that is, the impurity concentration is 1 ppm or lower, preferably 0.1 ppm or lower).

Further, the oxide semiconductor layer may be crystallized to be a microcrystalline film or a polycrystalline film depending on a condition of the first heat treatment or a material of the oxide semiconductor layer. For instance, the oxide semiconductor layer may be crystallized to be a microcrystalline semiconductor film having a degree of crystallization of 90% or more, or 80% or more. Further, depending on the condition of the first heat treatment and the material of the oxide semiconductor layer, the oxide semiconductor layer may be an amorphous oxide semiconductor film containing no crystalline component. The oxide semiconductor layer may be an oxide semiconductor film in which microcrystalline portions (each crystal grain having a diameter of 1 nm to 20 nm inclusive (typically, 2 nm to 4 nm inclusive)) are included in an amorphous oxide semiconductor in some cases.

The first heat treatment for the oxide semiconductor layer can be performed before the oxide semiconductor film is processed into the island-shaped oxide semiconductor layers. In that case, the substrate is taken out from the heat apparatus after the first heat treatment, and then a photolithography step is performed.

The heat treatment having an effect of dehydration or dehydrogenation of the oxide semiconductor layers may be performed at any of the following timings: after the oxide semiconductor layers are formed; after a source electrode and a drain electrode are formed over the oxide semiconductor layer; and after a gate insulating layer is formed over the source electrode and the drain electrode.

However, when a highly purified oxide semiconductor layer can be obtained by sufficiently reducing hydrogen or moisture at the time of deposition, the first heat treatment is not necessarily performed. In the case where a highly purified oxide semiconductor layer is obtained by sufficiently reducing hydrogen or moisture at the time of deposition, the substrate is held in a treatment chamber kept in a reduced pressure state and the substrate is heated to a temperature of higher than or equal to room temperature and lower than 400° C. Then, a sputtering gas from which hydrogen and moisture are removed is introduced while

moisture remaining in the treatment chamber is removed, and an oxide semiconductor layer is formed over the substrate using metal oxide as a target. In a treatment chamber which is evacuated using a cryopump, for example, hydrogen atoms, compounds including hydrogen atoms such as water (H<sub>2</sub>O) (more preferably, compounds including carbon atoms in addition), or the like are exhausted; therefore, the concentration of impurities contained in the oxide semiconductor layer deposited in the treatment chamber can be reduced. By performing deposition by sputtering while removing moisture remaining in the treatment chamber using a cryopump, a substrate temperature when the oxide semiconductor layer is formed can be higher than or equal to room temperature and lower than 400° C.

Next, a resist mask is formed over the third insulating layer **447b** by a fourth photolithography step, and selective etching is performed so as to form an opening which reaches the electrode layer **479a**.

A conductive film is formed over the third insulating layer **447b** and the oxide semiconductor layers **442** and **472**. The conductive film may be formed by a sputtering method or a vacuum evaporation method. As a material of the conductive film, an element selected from Al, Cr, Cu, Ta, Ti, Mo, and W; an alloy containing any of these elements as a component; an alloy film containing any of these elements in combination; and the like can be given. Alternatively, one or more materials selected from manganese, magnesium, zirconium, beryllium, and thorium can be used. Further, the metal conductive film may have a single-layer structure or a stacked-layer structure of two or more layers. For example, a single-layer structure of an aluminum film including silicon, a two-layer structure in which a titanium film is stacked over an aluminum film, a three-layer structure in which a titanium film, an aluminum film, and a titanium film are stacked in this order, and the like can be given. Alternatively, a film, an alloy film, or a nitride film of a combination of Al and one or plurality of elements selected from the followings may be used: titanium (Ti), tantalum (Ta), tungsten (W), molybdenum (Mo), chromium (Cr), neodymium (Nd), and scandium (Sc). In this embodiment, a stacked film of a titanium film (with a thickness of 10 nm to 100 nm inclusive) and an aluminum film (with a thickness of 20 nm to 500 nm inclusive) is formed as the conductive film.

Next, an insulating film with a thickness of 200 nm to 2000 nm inclusive is formed over the conductive film by a plasma CVD method, a sputtering method, or the like, using a single layer or stacked layers of a silicon oxide layer, a silicon nitride layer, a silicon oxynitride layer, and/or a silicon nitride oxide layer.

A resist mask is formed over the insulating film by a fifth photolithography step, selective etching is performed to form the fourth insulating layer **446**, the first source electrode layer **445a**, the second source electrode layer **448a**, the first drain electrode layer **445b**, and the second drain electrode layer **448b**, and then the resist mask is removed. The fourth insulating layer **446** is provided in order to reduce parasitic capacitance between the gate electrode layer formed later and the source and drain electrode layers. Note that it is preferable that the end portions of the source electrode layers and the drain electrode layers be a tapered shape because coverage of the gate insulating layer stacked thereover is improved.

Note that when the conductive film is etched, each material and etching conditions are adjusted as appropriate so

that the oxide semiconductor layers **442** and **472** are not removed so as to expose the third insulating layer **447b** thereunder.

In this embodiment, a Ti film is used as the first source electrode layer **445a** and the first drain electrode layer **445b**,  
5 an aluminum film is used as the second source electrode layer **448a** and the second drain electrode layer **448b**, an In—Ga—Zn—O-based oxide is used as the oxide semiconductor layer **442**, and an ammonia hydrogen peroxide mixture (a mixed solution of ammonia water, water, and a  
10 hydrogen peroxide solution) is used as the etchant.

Note that in the fifth photolithography step, only part of the oxide semiconductor layer **442** may be etched so that an oxide semiconductor layer having a groove (a depression  
15 portion) is formed in some cases. The resist mask for forming the first source electrode layer **445a** and the first drain electrode layer **445b** may be formed by an ink jet method. Formation of the resist mask by an inkjet method needs no photomask; thus, manufacturing cost can be  
20 reduced.

In light exposure for formation of the resist mask in the fifth photolithography step, ultraviolet light, KrF laser light, or ArF laser light is used. A channel length L1 of the thin film transistor **440** formed later is determined by the distance  
25 between the lower edge portion of the source electrode layer and the lower edge portion of the drain electrode layer which are next to each other over the oxide semiconductor layer **442**. In the case of performing light exposure by which the channel length L1 is shorter than 25 nm, light exposure for forming the resist mask in the fifth photolithography step is  
30 performed using extreme ultraviolet light with extremely short wavelength of several nanometers to several tens of nanometers. In light exposure using extreme ultraviolet, resolution is high and depth of focus is large. Therefore, the channel length L1 of the thin film transistor **440** formed later  
35 can be 10 nm to 1000 nm inclusive, operation speed of the circuit can be increased, and power consumption can be reduced because an off-current value is extremely small.

Next, the gate insulating layer **444** is formed over the fourth insulating layer **446**, the oxide semiconductor layers  
40 **442** and **472**, the first source electrode layer **445a**, the second source electrode layer **448a**, the first drain electrode layer **445b**, and the second drain electrode layer **448b**.

The gate insulating layer **444** can be formed to have a single-layer structure or a stacked-layer structure of a silicon  
45 oxide layer, a silicon nitride layer, a silicon oxynitride layer, a silicon nitride oxide layer, or an aluminum oxide layer by a plasma CVD method, a sputtering method, or the like. Note that the gate insulating layer **444** is preferably formed by a sputtering method so that the gate insulating layer **444**  
50 does not contain a large amount of hydrogen. In the case where a silicon oxide film is formed by a sputtering method, a silicon target or a quartz target is used as a target, and an oxygen gas or a mixed gas of oxygen and argon is used as a sputtering gas.

The gate insulating layer **444** can have a structure in which a silicon oxide layer and a silicon nitride layer are stacked in this order from the side of the second source  
55 electrode layer **448a** and the second drain electrode layer **448b**. For example, a silicon oxide layer ( $\text{SiO}_x$ , ( $x>0$ )) with a thickness of 5 nm to 300 nm inclusive is formed as the first gate insulating layer, a silicon nitride layer ( $\text{SiO}_y$ , ( $y>0$ )) with a thickness of 50 nm to 200 nm inclusive is stacked as the second gate insulating layer over the first gate insulating  
60 layer by a sputtering method, to form a gate insulating layer with a thickness of 100 nm. In this embodiment, a silicon oxide layer with a thickness of 100 nm is formed by an RF

sputtering method in an atmosphere containing oxygen and argon (the flow rate of oxygen is 25 sccm, and the flow rate of argon is 25 sccm), under conditions where the pressure is 0.4 Pa, and a high-frequency power source is 1.5 kW.

Next, a resist mask is formed by a sixth photolithography step, selective etching is performed so as to remove part of the gate insulating layer **444** and the fourth insulating layer  
5 **446**, and an opening is formed to reach the source electrode layer or the drain electrode layer of the thin film transistor **470**.

Then, a conductive film is formed over the gate insulating layer **444** and the opening, and gate electrode layers **441** and  
10 **471** and wiring layers **474a** and **474b** are formed by a seventh photolithography step. Note that a resist mask may be formed by an inkjet method. Formation of the resist mask by an inkjet method needs no photomask; thus, manufacturing cost can be reduced.

The gate electrode layers **441** and **471** and the wiring layers **474a** and **474b** can be formed to have a single-layer or stacked-layer structure using a metal material such as molybdenum, titanium, chromium, tantalum, tungsten, alu-  
15 minium, copper, neodymium, or scandium, or an alloy material which contains any of these materials as its main component.

For example, as a two-layer structure of the gate electrode layers **441** and **471** and the wiring layers **474a** and **474b**, the following structures are preferable: a two-layer structure of  
20 an aluminum layer and a molybdenum layer stacked thereover, a two-layer structure of a copper layer and a molybdenum layer stacked thereover, a two-layer structure of a copper layer and a titanium nitride layer or a tantalum nitride layer stacked thereover, and a two-layer structure of a titanium nitride layer and a molybdenum layer. As a three-  
25 layer structure, a stack of a tungsten layer or a tungsten nitride layer, a layer of an alloy of aluminum and silicon or an alloy of aluminum and titanium, and a titanium nitride layer or a titanium layer is preferable. Note that a gate electrode layer can be formed using a conductive film having a light-transmitting property. As an example of a conductive film having a light-transmitting property, a trans-  
30 parent conductive oxide or the like can be given.

In this embodiment, a tungsten film with a thickness of 150 nm is formed as the gate insulating layers **441** and **471**  
35 and the wiring layers **474a** and **474b**.

Next, a second heat treatment (preferably at a temperature of 200° C. to 400° C. inclusive, for example, 250° C. to 300°  
40 C. inclusive) is performed in an inert gas atmosphere or an oxygen gas atmosphere. In this embodiment, the second heat treatment is performed at 250° C. in a nitrogen atmosphere for one hour. The second heat treatment may be performed after a protective insulating layer or a planarizing insulating layer is formed over the thin film transistors **440** and **470**.

Further, heat treatment may be performed at 100° C. to 200° C. inclusive for one hour to 30 hours inclusive in an air  
45 atmosphere. This heat treatment may be performed at a fixed heating temperature. Alternatively, the following change in the heating temperature may be conducted plural times repeatedly: the heating temperature is increased from a room temperature to a temperature of 100° C. to 200° C. inclusive  
50 and then decreased to a room temperature. Further, this heat treatment may be performed before formation of the insulating layer under a reduced pressure. Under the reduced pressure, the heat treatment time can be shortened.

Through the above steps, the thin film transistors **440** and **470** respectively including the oxide semiconductor layers

442 and 472 with a reduced concentration of hydrogen, moisture, hydride, and hydroxide can be formed (see FIG. 1B).

The thin film transistor 470 in which parasitic capacitance between the electrode layer 479c and a fourth drain electrode layer 478b is reduced by the fifth insulating layer 473 includes a third source electrode layer 475a, a fourth source electrode layer 478a, a third drain electrode layer 475b, and the fourth drain electrode layer 478b. Note that the electrode layer 479c overlapping with the fifth insulating layer 473 is a gate signal line, and describes a structure of a wiring intersection with the fourth drain electrode layer 478b. The third source electrode layer 475a is electrically connected to the electrode layer 479a. The fourth source electrode layer 478a is electrically connected to a wiring layer 474a. The thin film transistor 470 is a thin film transistor which has a channel length L2 longer than the channel length L1 of the thin film transistor 440 and a small off-current value.

In addition, a protective insulating layer or a planarizing insulating layer for planarization may be formed over the thin film transistors 440 and 470. For example, a protective insulating layer can be formed to have a single-layer or stacked-layer structure of a silicon oxide layer, a silicon nitride layer, a silicon oxynitride layer, a silicon nitride oxide layer, or an aluminum oxide layer.

The planarizing insulating layer can be formed using an organic material having heat resistance, such as polyimide, acrylic, benzocyclobutene, polyamide, or epoxy. Other than such organic materials, it is also possible to use a low-dielectric constant material (a low-k material), a siloxane-based resin, PSG (phosphosilicate glass), BPSG (borophosphosilicate glass), or the like. The planarizing insulating layer may be formed by stacking a plurality of insulating films formed using these materials.

Note that the siloxane-based resin corresponds to a resin including a Si—O—Si bond formed using a siloxane-based material as a starting material. The siloxane-based resin may include as a substituent an organic group (e.g., an alkyl group or an aryl group) or a fluoro group. In addition, the organic group may include a fluoro group.

There is no particular limitation on the method for forming the planarizing insulating layer. The planarizing insulating layer can be formed, depending on the material, by a method such as a sputtering method, an SOG method, a spin coating method, a dipping method, a spray coating method, or a droplet discharge method (e.g., an inkjet method, screen printing, or offset printing), or a tool such as a doctor knife, a roll coater, a curtain coater, or a knife coater, or the like.

The electrode layer 479b provided below the oxide semiconductor layer 472 of the thin film transistor 470 can function as a back gate. A potential of the back gate can be a fixed potential, e.g., 0V, or a ground potential, and may be determined as appropriate by a practitioner. In addition, by providing the gate electrodes above and below the oxide semiconductor layer, in a bias-temperature stress test (hereinafter, referred to as a BT test) for examining reliability of the thin film transistor, the amount of shift in threshold voltage of the thin film transistor between before and after the BT test can be reduced. That is, provision of the gate electrodes above and below the oxide semiconductor layer can improve the reliability.

Further, by controlling gate voltage applied to the electrode layer 479b, threshold voltage can be determined. Alternatively, when the threshold voltage is set positive, the thin film transistor can function as an enhancement type

transistor. Further alternatively, when the threshold voltage is set negative, the thin film transistor can function as a depletion type transistor.

For example, an inverter circuit including a combination of the enhancement type transistor and the depletion type transistor (hereinafter, such a circuit is referred to as an EDMOS circuit) can be used for a driver circuit. The driver circuit includes at least a logic circuit portion, and a switch portion or a buffer portion. The logic circuit portion has a circuit structure including the above EDMOS circuit. Further, a thin film transistor by which large on-state current can flow is preferably used for the switch portion or the buffer portion. A depletion type transistor or a thin film transistor including gate electrodes above and below an oxide semiconductor layer is used.

Thin film transistors having different structures can be formed over one substrate without greatly increasing the number of steps. For example, an EDMOS circuit using the thin film transistor including gate electrodes above and below the oxide semiconductor layer may be formed in an integrated circuit for high-speed driving, and a thin film transistor including a gate electrode above an oxide semiconductor layer can be formed in other regions.

Note that an n-channel TFT whose threshold voltage is positive is referred to as an enhancement type transistor, and an n-channel TFT whose threshold voltage is negative is referred to as a depletion type transistor, throughout this specification.

In the thin film transistor 470 and the thin film transistor 440, when a silicon nitride film is used for both the gate insulating layer 444 and the first insulating layer 447a, the oxide semiconductor layers 442 and 472 can be sandwiched between silicon nitride films, and the entry of hydrogen or moisture can be effectively blocked. With such a structure, the concentration of water or hydrogen included in the oxide semiconductor layers 442 and 472 can be reduced to the utmost, and reentry of water or hydrogen can be prevented.

## Embodiment 2

In Embodiment 1, the thin film transistor 470 including a wiring intersection and the thin film transistor 440 including the gate electrode layer 441 only above the oxide semiconductor layer 442 is described. Hereinafter, an example of forming an inverter circuit of an integrated circuit using two n-channel thin film transistors will be described. Note that since the manufacturing process of the thin film transistor is almost the same as that in Embodiment 1, only different points are described in detail.

An integrated circuit is formed using an inverter circuit, a capacitor, a resistor, and the like; therefore, a process of forming a capacitor and two kinds of resistors over one substrate in addition to the inverter circuit is also described.

When the inverter circuit is formed using two n-channel TFTs in combination, there are two kinds of inverter circuits: an inverter circuit having a combination of an enhancement type transistor and a depletion type transistor (referred to as an EDMOS circuit) and an inverter circuit having a combination of two enhancement type TFTs (hereinafter, referred to as an EEMOS circuit).

In this embodiment, an example of an EDMOS circuit is described. Further, an equivalent circuit of the EDMOS circuit is illustrated in FIG. 2. A cross-sectional structure of the inverter circuit is illustrated in FIG. 3.

The circuit connection illustrated in FIG. 3 corresponds to that illustrated in FIG. 2. An example in which the first thin film transistor 480 is an enhancement type n-channel tran-

sistor and the second thin film transistor **490** is a depletion type n-channel transistor is illustrated.

In FIG. 3, electrode layers **479d**, **479e**, **479f**, **479g**, and **479h** are provided over a substrate **430**. The electrode layers **479d**, **479e**, **479f**, **479g**, and **479h** can be formed by the same step and using the same material as the electrode layers **479a**, **479b**, and **479c** in Embodiment 1.

A voltage is applied to the electrode layer **479d** and the thin film transistor **480** functions as an enhancement type transistor whose threshold voltage is set positive. A voltage is also applied to the electrode layer **479e** and the thin film transistor **490** functions as a depletion type transistor whose threshold voltage is set negative.

The electrode layer **479f** is one electrode which forms the capacitor. The electrode layer **479g** is one electrode connected to a first resistor. The electrode layer **479h** is one electrode connected to a second resistor.

A first insulating layer **487a** and a third insulating layer **487b** are formed so as to cover the electrode layers **479d**, **479e**, **479f**, **479g**, and **479h**. Note that although not illustrated, in a region where parasitic capacitance is to be reduced, a second insulating layer serving as a spacer insulating layer is provided as described in Embodiment 1. In the capacitor portion, the first insulating layer **487a** overlapping with the electrode layer **479f** and the third insulating layer **487b** overlapping with the electrode layer **479f** each become a dielectric.

In this embodiment, unlike in Embodiment 1, the second oxide semiconductor layer **482b** has a thickness larger than that of the first oxide semiconductor layer **482a**. Deposition and patterning are each performed twice to make the second oxide semiconductor layer **482b** thick. With such a large thickness, the thin film transistor **490** can function as a depletion type transistor. Since a voltage by which the threshold voltage is set negative need not necessarily be applied to the electrode layer **479e**, the electrode layer **479e** can be omitted.

A third oxide semiconductor layer **432b** formed to have the same thickness as that of the first oxide semiconductor layer **482a** functions as a first resistor. An opening is formed in the first insulating layer **487a** and the third insulating layer **487b** which overlap with the electrode layer **479h**, and the third oxide semiconductor layer **432b** and the electrode layer **479h** are electrically connected to each other through the opening. A fourth oxide semiconductor layer **432a** formed to have the same thickness as that of the second oxide semiconductor layer **482b** functions as a second resistor, whose resistance value is different from that of the first resistor. An opening is formed in the first insulating layer **487a** and the third insulating layer **487b** which overlap with the electrode layer **479g**, and the fourth oxide semiconductor layer **432a** and the electrode layer **479g** are electrically connected to each other through the opening.

The thin film transistor **480** includes a first gate electrode layer **481** and the oxide semiconductor layer **482a** overlapping with the first gate electrode layer **481** with a gate insulating layer **492** interposed therebetween. A first source electrode layer **485b** which is in contact with part of the oxide semiconductor layer **482a** electrically connects to a first wiring **484b**. The first wiring **484b** is a power supply line to which a negative voltage VDL is applied (a negative power supply line). This power supply line may be a power supply line with a ground potential (a ground potential power supply line).

The first source electrode layer **485b** is formed using the same material as that of the first source electrode layer **445a** in Embodiment 1, and the second source electrode layer

**488b** which is formed over and in contact with the first source electrode layer **485b** is formed using the same material as that of the second source electrode layer **448a** in Embodiment 1. In Embodiment 1, an example in which the insulating layer is formed and then patterned using the same mask as that of the insulating film is described; however, in this embodiment, the insulating film is formed in a step after the conductive layer is patterned. Subsequently, the insulating film is selectively removed to form an insulating layer **486**, the conductive layer is selectively etched using the insulating layer **486** as a mask, and the first source electrode layer **485b**, the second source electrode layer **488b**, a first drain electrode layer **485a**, and a second drain electrode layer **488a** are formed. The insulating layer **486** is provided to reduce parasitic capacitance between a second gate electrode layer **491** and a fourth drain electrode layer **498b** which are formed later.

In the capacitor portion, a first capacitor electrode layer **433** is formed in the same step and using the same material as the first source electrode layer **485b**, and a second capacitor electrode layer **434** is formed in the same step and using the same material as the second source electrode layer **488b**. The first capacitor electrode layer **433** and the second capacitor electrode layer **434** overlap with the electrode layer **479f**.

A first electrode layer **477** is formed over and in contact with the third oxide semiconductor layer **432b** which is the first resistor, in the same step and using the same material as the first source electrode layer **485b**. A second electrode layer **438** is formed over the first electrode layer **477** in the same step and using the same material as the second source electrode layer **488b**.

The second thin film transistor **490** includes the second gate electrode layer **491** functioning as a second wiring and the second oxide semiconductor layer **482b** which overlaps with the second gate electrode layer **491** with the gate insulating layer **492** interposed therebetween. A third wiring **484a** is a power supply line (a positive power supply line) to which a positive voltage VDH is applied.

The second thin film transistor **490** further includes a third source electrode layer **495a** which is partly in contact with and overlapped with the second oxide semiconductor layer **482b** and a fourth source electrode layer **498a**. The second thin film transistor **490** includes a third drain electrode layer **495b** which is partly in contact with and overlapped with the second oxide semiconductor layer **482b** and the fourth drain electrode layer **498b**. Note that the third source electrode layer **495a** and the third drain electrode layer **495b** are formed in the same step and using the same material as the first source electrode layer **485b**. The fourth source electrode layer **498a** and the fourth drain electrode layer **498b** are formed in the same step and using the same material as the second source electrode layer **488b**.

An opening is formed in the insulating layer **486** to reach the second drain electrode layer **488a**. The second drain electrode layer **488a** electrically connects to the second gate electrode layer **491** functioning as a second wiring, whereby the first thin film transistor **480** and the second thin film transistor **490** are connected to form an EDMOS circuit.

A fourth wiring **431** which connects to the second capacitor electrode layer **434** through an opening in the gate insulating layer **492** in a region overlapping with the electrode layer **479f**, functions as a capacitor wiring.

A fifth wiring **435** is in contact with the fourth oxide semiconductor layer **432a** which functions as the second resistor, through an opening in the gate insulating layer **492** in a region overlapping with the electrode layer **479g**.



In this embodiment, an example in which an EDMOS circuit, a capacitor portion, a first resistor, and a second resistor are formed over one substrate is described; however, the thin film transistor in Embodiment 1 can also be formed over the same substrate, without particular limitation.

In this embodiment, a cross-sectional structure of a terminal portion of a wiring which can be formed over the same substrate is illustrated in FIGS. 4A and 4B. FIG. 4A is a cross-sectional view taken along line C1-C2 of FIG. 4B.

In FIG. 4A, a conductive layer 437 formed over a stack of the insulating layer 486 and the gate insulating layer 492 is a terminal electrode for connection which functions as an input terminal. In FIG. 4A, an electrode layer 479i which is formed of the same material as that of the electrode layers 479d, 479e, 479f, 479g, and 479h is provided below and overlaps with a first terminal electrode layer 439 which is electrically connected to the first source electrode layer 485b, with the first insulating layer 487a and the third insulating layer 487b interposed therebetween. The electrode layer 479i is not electrically connected to the first terminal electrode layer 439, and a capacitor as a countermeasure against noise or static electricity can be formed by setting the potential of the electrode layer 479i so as to be different from that of the first terminal electrode layer 439, for example, floating, GND, 0 V, or the like. The first terminal electrode layer 439, over which a second terminal electrode layer 489 is provided, is electrically connected to the conductive layer 437 with the insulating layer 486 and the gate insulating layer 492 interposed therebetween.

The first terminal electrode layer 439 can be formed using the same material and in the same step as the first source electrode layer 485b. The second terminal electrode layer 489 can be formed using the same material and in the same step as the second source electrode layer 488b. The conductive layer 437 can be formed using the same material and in the same step as the first gate electrode layer 481.

This embodiment can be freely combined with Embodiment 1.

#### Embodiment 3

In this embodiment, an example of manufacturing a CPU (central processing unit) using the EDMOS circuit described in Embodiment 2 will be described.

An example of a block diagram of a CPU is illustrated in FIG. 5. A CPU 1001 illustrated in FIG. 5 includes a timing control circuit 1002, an instruction decoder 1003, a register array 1004, an address logic and buffer circuit 1005, a data bus interface 1006, an ALU 1007, an instruction register 1008, and the like.

These circuits are manufactured using the thin film transistor, the inverter circuit, the resistor, the capacitor, and the like described in Embodiment 1 or Embodiment 2. The thin film transistors described in Embodiment 1 or Embodiment 2 each use an oxide semiconductor layer with sufficiently reduced hydrogen concentration, whereby the off-current of the thin film transistor can be extremely small. By using a thin film transistor including an oxide semiconductor layer with sufficiently reduced hydrogen concentration for at least part of the CPU 1001, power consumption can be reduced.

Now, each circuit will be briefly described. The timing control circuit 1002 receives an instruction from the external, converts the instruction into information for the internal, and sends the information to other blocks. In addition, the timing control circuit gives directions such as reading and writing of memory data to the external, according to internal operation. The instruction decoder 1003 serves to convert

instruction from the external into information for the internal. The register array 1004 is a volatile memory for temporarily storing data. The address logic and buffer circuit 1005 is a circuit for specifying the address of an external memory. The data bus interface 1006 is a circuit for taking data in and out of an external memory or a device such as a printer. The ALU 1007 is a circuit for performing an operation. The instruction register 1008 is a circuit for temporarily storing an instruction. The CPU includes combination of such circuits.

By using any of the thin film transistors described in Embodiments 1 and 2 for at least part of the CPU 1001, leakage current in a standby period is reduced; thus, power consumption of the driver circuit or the like used in electronic devices can be reduced.

This embodiment can be freely combined with any of Embodiments 1 and 2.

#### Embodiment 4

In this embodiment, an example of a usage mode of the semiconductor device described in the above embodiments will be described. Specifically, an application example of a semiconductor device that can input and output data without contact is described below with reference to drawings. The semiconductor device capable of wirelessly transmitting and receiving data is also called an RFID tag, an ID tag, an IC tag, an RF tag, a wireless tag, an electronic tag, or a wireless chip depending on the application.

One example of a top structure of a semiconductor device described in this embodiment is described with reference to FIG. 8A. The semiconductor device illustrated in FIG. 8A includes a semiconductor integrated circuit chip 400 having an antenna (also referred to as an on-chip antenna) and a supporting substrate 406 having an antenna 405 (also referred to as a booster antenna). The semiconductor integrated circuit chip 400 is provided over an insulating layer 410 (FIG. 8C) that is formed over the supporting substrate 406 and the antenna 405. The semiconductor integrated circuit chip 400 can be fixed to the supporting substrate 406 and the antenna 405 by using the insulating layer 410.

Note that a conductive shield is provided on a surface of the semiconductor integrated circuit chip 400 to prevent electrostatic breakdown of the semiconductor integrated circuit (e.g., malfunction of the circuit and damage to a semiconductor element) due to electrostatic discharge. When the conductive shield has high resistance and current cannot pass through the pattern of the antenna 405, the antenna 405 and the conductive shield provided on the surface of the semiconductor integrated circuit chip 400 may be provided in contact with each other.

As for a semiconductor integrated circuit provided in the semiconductor integrated circuit chip 400, elements such as a plurality of thin film transistors for constituting a memory portion or a logic portion are provided. As a thin film transistor for constituting a memory portion or a logic portion, a thin film transistor using a highly purified oxide semiconductor layer with sufficiently reduced hydrogen concentration is used. As a semiconductor element in a semiconductor device according to this embodiment, not only a field-effect transistor but also a memory element which uses a semiconductor layer can be employed; accordingly, a semiconductor device which can meet functions required for various applications can be manufactured and provided.

FIG. 7A is an enlarged view of the antenna and the semiconductor integrated circuit that are included in the

semiconductor integrated circuit chip **400** illustrated in FIG. **8A**. In FIG. **7A**, the antenna **101** is a rectangular loop antenna in which the number of windings is 1; however, an embodiment of the present invention is not limited to this structure. The shape of the loop antenna is not limited to a rectangle and may be a shape with curve, for example, a circle. In addition, the number of windings is not limited to 1 and may be plural. However, when the number of windings of the antenna **101** is 1, parasitic capacitance generated between the semiconductor integrated circuit **100** and the antenna **101** can be reduced.

In FIG. **8A** and FIG. **7A**, the antenna **101** is arranged so as to surround the periphery of the semiconductor integrated circuit **100**, and the antenna **101** is arranged in a region different from a region of the semiconductor integrated circuit **100**, except portions corresponding to power feeding points **408** indicated by a dashed line. However, this embodiment is not limited to this structure. As illustrated in FIG. **7B**, the antenna **101** may be arranged so as to at least partly overlap with the semiconductor integrated circuit **100** in addition to the portions corresponding to the power feeding points **408** indicated by the dashed line. Note that in the case where the antenna **101** is arranged in a region different from a region of the semiconductor circuit **100** as illustrated in FIG. **8A** and FIG. **7A**, parasitic capacitance generated between the semiconductor integrated circuit **100** and the antenna **101** can be reduced.

In FIG. **8A**, the antenna **405** can transmit and receive signals or supply power to/from the antenna **101** by electromagnetic induction mainly in a loop-like shaped portion surrounded by a dashed line **407**. In addition, the antenna **405** can send and receive a signal to/from an interrogator or supply power by using a radio wave mainly in a region other than a portion surrounded by the dashed line **407**. A radio wave used as a carrier (a carrier wave) between the interrogator and the semiconductor device preferably has a frequency of about 30 MHz to 5 GHz, and for example, may have a frequency band of 950 MHz or 2.45 GHz.

The antenna **405** is a rectangular loop antenna in which the number of windings is 1 in the portion surrounded by the dashed line **407**; however, an embodiment of the present invention is not limited to this structure. The shape of the loop antenna is not limited to a rectangle and may be a shape with curve, for example, a circle. In addition, the number of windings is not limited to 1 and may be plural.

For the semiconductor device described in this embodiment, an electromagnetic induction method, an electromagnetic coupling method, or a microwave method can be employed. In the case of a microwave method, the shapes of the antenna **101** and the antenna **405** may be determined as appropriate depending on the wavelength of an electromagnetic wave.

If a microwave method (e.g., UHF band (860 MHz band to 960 MHz band), or 2.45 GHz band) is used as the signal transmission method in the semiconductor device, the length, shape, or the like of the antenna may be determined as appropriate in consideration of the wavelength of an electromagnetic wave used for signal transmission. For example, each of the antennas can be formed into a linear shape (e.g., a dipole antenna) or a flat shape (e.g., a patch antenna or an antenna having a ribbon shape). Further, each of the antennas is not limited to a linear shape and may have a curved shape, a serpentine curved shape, or in a shape combining them in consideration of the wavelength of the electromagnetic wave.

An example in which the antenna **101** and the antenna **405** have coil shapes and an electromagnetic induction method or an electromagnetic coupling method is used is illustrated in FIG. **9**.

In FIG. **9**, the semiconductor integrated circuit chip **400** having the coiled antenna **101** is formed over the supporting substrate **406** provided with the coiled antenna **405** as a booster antenna. Note that the supporting substrate **406** is sandwiched between the antenna **405** which is a booster antenna, and a capacitor is formed.

Next, the structures and arrangements of the semiconductor integrated circuit chip **400** and the booster antenna will be described. FIG. **8B** is a perspective view of the semiconductor device illustrated in FIG. **8A**, in which the semiconductor integrated circuit chip **400** and the antenna **405** formed over the supporting substrate **406** are stacked. In addition, FIG. **8C** is a cross-sectional view along a dashed line X-Y of FIG. **8B**.

As the semiconductor integrated circuit chip **400** illustrated in FIG. **8C**, any of the semiconductor devices described in Embodiment 1 or Embodiment 2 can be used, and here, a chip obtained by cutting the semiconductor integrated circuit into individual chips is referred to as a semiconductor integrated circuit chip. Note that, although the semiconductor integrated circuit chip illustrated in FIG. **8C** is an example of using Embodiment 1, this embodiment is not limited to this structure and can be applied to another embodiment.

The semiconductor integrated circuit **100** illustrated in FIG. **8C** is sandwiched between a first insulator **112** and a second insulator **102**, and the side surface is also sealed. In this embodiment, the first insulator and the second insulator between which a plurality of semiconductor integrated circuits is sandwiched are attached, and then the semiconductor integrated circuits are individually divided into stacks. A conductive shield is formed each for the divided stacks, and the semiconductor integrated circuit chips **400** are formed. There is no particular limitation on a separation means as long as physical separation is possible, and separation is performed by laser beam irradiation in this embodiment.

In FIG. **8C**, the semiconductor integrated circuit **100** is closer to the antenna **405** than the antenna **101**; however an embodiment of the present invention is not limited to this structure. The antenna **101** may be closer to the antenna **405** than the semiconductor integrated circuit **100**. The semiconductor integrated circuit **100** and the antenna **101** may be directly attached to the first insulator **112** and the second insulator **102**, or may be attached by a bonding layer functioning as an adhesive.

Next, operation of the semiconductor device of this embodiment will be described. FIG. **6** is a block diagram illustrating an example of a structure of a semiconductor device of this embodiment. A semiconductor device **420** illustrated in FIG. **6** includes an antenna **422** as a booster antenna, a semiconductor integrated circuit **423**, and an antenna **424** as an on-chip antenna. When an electromagnetic wave is transmitted from an interrogator **421**, the antenna **422** receives the electromagnetic wave to generate alternate current, whereby a magnetic field is generated around the antenna **422**. Then, a loop portion of the antenna **422** is electromagnetically coupled to the loop antenna **424**, so that induced electromotive force is generated in the antenna **424**. The semiconductor integrated circuit **423** receives a signal or power from the interrogator **421** by using the induced electromotive force. On the other hand, current flows into the antenna **424** and induced electromotive force is generated in the antenna **422** in accordance with a signal

generated in the semiconductor integrated circuit **423**, whereby a signal can be sent to the interrogator **421** using a reflected wave of the radio wave that is sent from the interrogator **421**.

Note that the antenna **422** can be divided between the loop portion that is mainly electromagnetically coupled to the antenna **424** and a portion that mainly receives electromagnetic waves from the interrogator **421**. The shape of the antenna **422** in the portion in which an electric wave from the interrogator **421** is mainly received may be a shape in which an electric wave can be received. For example, the shape of a dipole antenna, a folded dipole antenna, a slot antenna, a meander line antenna, a microstrip antenna, or the like may be used.

Although FIGS. **8A** to **8C** illustrate the structure of the semiconductor integrated circuit having only one antenna, this embodiment of the disclosed invention is not limited to this structure. A semiconductor device may include two antennas, that is, an antenna for receiving power and an antenna for receiving a signal. With the two antennas, frequency of a radio wave for supplying power and frequency of a radio wave for transmitting a signal can be separately used.

In a semiconductor device of this embodiment, the on-chip antenna is used and a signal or power can be sent and received between the booster antenna and the on-chip antenna without contact; therefore, unlike the case where a semiconductor integrated circuit is connected to an external antenna, the semiconductor integrated circuit and the antenna are less likely to be disconnected due to external force, and generation of initial failure in the connection can also be suppressed. In addition, the booster antenna is used in this embodiment. Accordingly, unlike the case where only the on-chip antenna is used, the advantage of an external antenna can also be offered: that is, the area of the semiconductor integrated circuit does not significantly limit the size or shape of the on-chip antenna, the frequency band of radio waves capable of being received is not restricted, and the communication distance can be increased.

The semiconductor integrated circuit can be directly formed over a flexible substrate. Alternatively, the semiconductor integrated circuit may be transferred from a formation substrate (for example, a glass substrate) to another substrate (for example, a plastic substrate).

There is no particular limitation on the method of transferring the semiconductor integrated circuit from the formation substrate to another substrate, and a variety of methods can be used. For example, a separation layer may be formed between the formation substrate and the semiconductor integrated circuit.

For example, in the case where a metal oxide film is formed as the separation layer, the metal oxide film is weakened by crystallization, and an element layer including the semiconductor integrated circuit, which is a layer to be separated, can be separated from the formation substrate. After the metal oxide film is weakened by crystallization, part of the separation layer may be removed by etching with use of a halogen fluoride gas such as  $\text{NF}_3$ ,  $\text{BrF}_3$ , or  $\text{ClF}_3$ , and then separation may be performed in the weakened metal oxide film.

In addition, when a substrate having a light-transmitting property is used as the formation substrate and a film containing nitrogen, oxygen, hydrogen or the like (e.g., an amorphous silicon film containing hydrogen, an alloy film containing hydrogen, an alloy film containing oxygen or the like) is used as the separation layer, the separation layer is irradiated with laser light through the formation substrate,

and nitrogen, oxygen, or hydrogen contained in the separation layer is evaporated so that separation can occur between the formation substrate and the separation layer.

Alternatively, the layer to be separated may be separated from the formation substrate by removing the separation layer by etching.

Alternatively, a method of removing the formation substrate by mechanical grinding or a method of removing the formation substrate by etching using a halogen fluoride gas such as  $\text{NF}_3$ ,  $\text{BrF}_3$ ,  $\text{ClF}_3$  or the like or HF, or the like can be employed. In this case, the separation layer can be omitted.

Alternatively, laser irradiation, etching using a gas, a solution, or the like, or a sharp knife or a scalpel, can be used so as to form a groove to expose the separation layer. The groove can trigger separation of the layer to be separated from the formation substrate from the separation layer.

For example, as a separation method, mechanical force (a separation process with a human hand or with a gripper, a separation process by rotation of a roller, or the like) may be used. Alternatively, the layer to be separated may be separated from the separation layer in such a manner that a liquid is dropped into the groove to allow the liquid to be infiltrated into the interface between the separation layer and the layer to be separated. Alternatively, a method can be employed in which a fluoride gas such as  $\text{NF}_3$ ,  $\text{BrF}_3$ , or  $\text{ClF}_3$  is introduced into the groove, and the separation layer is removed by etching with the use of the fluoride gas so that the layer to be separated is separated from the formation substrate. The separation may be performed while pouring a liquid such as water.

As another separation method, if the separation layer is formed using tungsten, separation can be conducted while the separation layer is being etched by a mixed solution of ammonia water and hydrogen peroxide water.

A thin film transistor using a highly purified oxide semiconductor layer with sufficiently reduced hydrogen concentration has a small off-current, and can realize low power consumption. By the conductive shield covering the semiconductor integrated circuit, electrostatic breakdown of the semiconductor integrated circuit (malfunction of the circuit or damage of the semiconductor element) due to electrostatic discharge can be prevented. Furthermore, by using the pair of insulators holding the semiconductor integrated circuit therebetween, a resistant and highly-reliable semiconductor device having a reduced thickness and size can be provided.

#### Embodiment 5

This embodiment will describe examples of the application of a semiconductor device capable of wireless data communication, which includes the above-described non-volatile semiconductor memory device formed using the device in Embodiment. 4. According to its mode of use, a semiconductor device capable of inputting and outputting data contactlessly may also be referred to as an RFID tag, an ID tag, an IC tag, an IC chip, an RF tag, a wireless tag, an electronic tag, or a wireless chip.

A semiconductor device **800** has a function of communicating data without contact, and includes a high-frequency circuit **810**, a power supply circuit **820**, a reset circuit **830**, a clock generating circuit **840**, a data demodulating circuit **850**, a data modulating circuit **860**, a control circuit **870** which controls another circuit, a memory circuit **880**, and an antenna **890** (see FIG. **10A**). The high-frequency circuit **810** receives a signal from the antenna **890** and outputs a signal received from the data demodulating circuit **860** through the

antenna **890**. The power supply circuit **820** generates a power supply potential from the received signal. The reset circuit **830** generates a reset signal. The clock generating circuit **840** generates various clock signals based on the signal input from the antenna **890**. The data demodulating circuit **850** demodulates the received signal and outputs the signal to the control circuit **870**. The data modulating circuit **860** modulates a signal received from the control circuit **870**. Further, as the control circuit **870**, a code extracting circuit **910**, a code determining circuit **920**, a CRC determining circuit **930**, and an output unit circuit **940** are provided, for example. The control circuit **870** includes, for example, a code extracting circuit **910**, a code determining circuit **920**, a CRC determining circuit **930**, and an output unit circuit **940**. The code determining circuit **920** compares the extracted code with a reference code to determine the content of the instruction. The CRC determining circuit **930** detects a transmission error and the like based on the determined code.

Next, an example of an operation of the above-mentioned semiconductor device will be described. First, a radio signal is received by the antenna **890**. The radio signal is transmitted to the power supply circuit **820** via the high frequency circuit **810**, thereby generating a high power supply potential (hereinafter referred to as a VDD). The VDD is supplied to each circuit of the semiconductor device **800**. A signal transmitted to the data demodulating circuit **850** via the high frequency circuit **810** is demodulated (hereinafter referred to as a demodulated signal). Further, a signal and a demodulated signal passing through the reset circuit **830** and the clock generating circuit **840** via the high frequency circuit **810** are transmitted to the control circuit **870**. The signals transmitted to the control circuit **870** are analyzed by the code extracting circuit **910**, the code determining circuit **920**, the CRC determining circuit **930**, and the like. Then, based on the analyzed signals, information in the semiconductor device stored in the memory circuit **880** is output. The output data of the semiconductor device **800** is encoded via the output unit circuit **940**. In addition, the encoded data of the semiconductor device **800** passes through the data modulating circuit **860** to be transmitted as a radio signal via the antenna **890**. Note that a low power supply potential (hereinafter referred to as VSS) is common in the plurality of circuits included in the semiconductor device **800**, and GND can be used as VSS.

In this manner, the data of the semiconductor device **800** can be read by transmitting a signal from a communication device to the semiconductor device **800** and receiving a signal from the semiconductor device **800** by the communication device.

Moreover, in the semiconductor device **800**, power supply voltage may be supplied to each circuit by electromagnetic waves without mounting a power source (battery), or a power source (battery) may be mounted so that power supply voltage is supplied to each circuit by both electromagnetic waves and the power source (battery).

Next, an example of a mode of use of a semiconductor device capable of inputting and outputting data contactlessly will be described. A communication device **3200** is provided for a side surface of a mobile terminal which includes a display portion **3210**. A semiconductor device **3230** is provided for a side surface of an article **3220** (FIG. **10B**). When the communication device **3200** is put close to the semiconductor device **3230** on the article **3220**, information on the article **3220**, such as the raw material or the source of the product, inspection result in each production step, history of the distribution process, and explanation of the article is

displayed on the display portion **3210**. When a product **3260** is transferred by a conveyer belt, the product **3260** can be inspected using a communication device **3240** and a semiconductor device **3250** provided on the product **3260** (FIG. **10C**).

When the semiconductor device is used in a system in this manner, information can be obtained easily, and higher performance and higher added value are achieved.

As described above, a semiconductor device of the present invention, which has a very wide range of application, can be used in electronic devices in all kinds of fields.

#### Embodiment 6

The thin film transistors obtained in Embodiment 1 or Embodiment 2 are thin film transistors each using a highly purified oxide semiconductor. By forming a circuit using the thin film transistors, low power consumption can be realized and operation of a memory circuit can be stabilized.

In this embodiment, an example of a memory circuit which can be formed using the thin film transistor in Embodiment 1 is described.

FIG. **11A** illustrates an equivalent circuit diagram of an example of a memory circuit. The memory circuit illustrated in FIG. **11A** includes a row decoder, a writing circuit and a refresh circuit, a column decoder, and memory elements **1100** arranged in matrix. A signal line connected to the memory elements **1100** arranged in matrix is connected to the row decoder through the writing circuit and the refresh circuit, and a scan line connected to the memory elements **1100** arranged in matrix is connected to the column decoder. A bit signal is input to the row decoder. A read enable signal and a write enable signal (RE/WE), a data signal (data), and an output signal (OUT) are input to the writing circuit and the refresh circuit.

Each of the memory elements **1100** includes a capacitor element and a thin film transistor. One of a source and a drain of the thin film transistor is connected to the signal line, and the other of the source and the drain of the thin film transistor is connected to one electrode of the capacitor element, and the other electrode of the capacitor element is connected to the low potential side (preferably, a reference potential Vss).

FIG. **11B** illustrates a specific structural example of the refresh circuit provided in the writing circuit and the refresh circuit illustrated in FIG. **11A**.

The writing circuit and the refresh circuit illustrated in FIG. **11B** include an AND circuit and a sense amplifier. To one input of each of a first AND circuit **1101**, a second AND circuit **1102**, and a third AND circuit **1103**, a signal is input from the row decoder. A PRC signal is input to the other input of the first AND circuit **1101**, the write enable signal (WE) is input to the other input of the second AND circuit **1102**, and the read enable signal (RE) is input to the other input of the third AND circuit **1103**. The output of the first AND circuit **1101** controls on/off of a first switch **1104**, the output of the second AND circuit **1102** controls on/off of a second switch **1105**, and the output of the third AND circuit **1103** controls on/off of a third switch **1106**. A pre-charge signal line V<sub>prc</sub> is connected to the signal line through the first switch **1104**, and a data signal line data is connected to the signal line through the second switch **1105**.

The signal line connected through the first switch **1104** and the second switch **1105** are connected to the sense amplifier through the third switch **1106**. A signal is output to the output signal line (OUT) from the sense amplifier.

Note that the above AND circuit may have a general structure, and preferably has a simple structure.

A sense amplifier is a circuit having a function of amplifying input signals.

Note that as a signal here, an analog signal or a digital signal which uses voltage, current, resistance, frequency, or the like can be used, for example. For example, at least two potentials, that is, a first potential and a second potential are set, a high-level (also referred to as high potential or  $V_H$ ) potential is used as the first potential, and a low-level (also referred to as low potential or  $V_L$ ) potential is used as the second potential, whereby a binary digital signal can be set. Although  $V_H$  and  $V_L$  are preferably constant values,  $V_H$  and  $V_L$  may take a wide range of values, in consideration of influence of noise.

Note that here, terms with ordinal numbers, such as “first” and “second”, are used in order to avoid confusion among components, and the terms do not limit the components numerically.

Thus, a memory circuit can be manufactured using the thin film transistor described in Embodiment 1 and the capacitor described in Embodiment 2.

A refresh timing of the memory circuit is determined to a certain time interval in the design phase, based on the leakage current of the memory elements 1100 which is evaluated in advance. That is, the refresh timing is set in consideration of the temperature dependence of leakage current and fluctuation of the manufacturing process, after the chip is completed.

In the thin film transistors described in Embodiment 1 or Embodiment 2, an oxide semiconductor layer with sufficiently reduced hydrogen concentration is used, whereby the off-current of the thin film transistors can be made extremely small. Further, since temperature characteristics of the off-current hardly change within the temperature of from  $-30^\circ$  C. to  $120^\circ$  C., the extremely small value can be kept.

Therefore, when the thin film transistors described in Embodiment 1 or Embodiment 2 are used, refresh interval can be set long compared to a transistor using silicon, and power consumption in a standby period can be reduced.

In addition, since the off-current has little temperature dependence, the memory circuit in this embodiment is suitable for an in-vehicle electronic device. Since leakage current in a standby period is extremely small, when used for electric vehicles, traveling distance per a certain amount of charging hardly changes even when the standby period is long.

The thin film transistors described in Embodiment 1 or Embodiment 2 each use an oxide semiconductor which is intrinsic or substantially intrinsic, in which impurities which may become carrier donors (donors or acceptors) are reduced to an extremely small number.

FIG. 12 illustrates a band structure between the source and the drain of the thin film transistor described in Embodiment 1 or Embodiment 2. Fermi level of the highly purified oxide semiconductor is positioned in the center of the forbidden band in an ideal state. In an oxide semiconductor with sufficiently reduced hydrogen concentration, the number of minority carriers (holes in this case) is zero or extremely close to zero.

When work function is  $\phi_m$  and electron affinity of the oxide semiconductor is  $\chi$ , in the case where work function  $\phi_m$  is smaller than the electron affinity  $\chi$ , ohmic contact is formed with electrons.

Here, when  $\phi_m = \chi$ , Fermi level of an electrode metal and the level of the end of the conduction band of the oxide semiconductor correspond to each other at the bonding

surface. When it is assumed that the band gap is 3.05 eV, the electronic affinity is 4.3 eV, the state is an intrinsic state (the carrier concentration is approximately  $1 \times 10^{-7}/\text{cm}^3$ ), and titanium (Ti) whose work function is 4.3 eV is used as the source electrode and the drain electrode, barrier is not formed against electrons, as illustrated in FIG. 12.

A schematic view of the energy band structure is illustrated in FIG. 13. In a state where positive voltage ( $V_D > 0$ ) is applied to the drain, the dashed line illustrates a case where a voltage is not applied to a gate ( $V_G = 0$ ), and the solid line illustrates a case where positive voltage ( $V_G > 0$ ) is applied to the gate. In the case where a voltage is not applied to the gate, carriers (electrons) are not injected from the electrode to the oxide semiconductor side because of high potential barrier, and an off state where no current flows is shown. On the other hand, when positive voltage is applied to the gate, potential barrier is reduced, and an on state where current flows is shown.

Here, height of the barrier has influence on carrier mobility. When the drain voltage is increased, the height of the barrier ( $h_b$ ) becomes smaller and mobility increases. If the work function  $\phi_m$  of the source electrode is approximately the same as the electron affinity of the oxide semiconductor,  $h_b$  becomes further smaller, and higher mobility can be expected. Note that it is necessary that such an electrode material and the oxide semiconductor do not come into contact with each other to form an insulator.

In such a case, in a bottom-gate (inverted stagger) transistor, the barrier between the source and the drain becomes small, and a parasitic channel is more likely to be formed. Therefore, a top-gate transistor is preferably used in the case of increasing mobility.

FIG. 14A is an energy band diagram of a MOS structure when the gate voltage is set positive, which illustrates the case of a transistor using an oxide semiconductor. In this case, thermally excited carriers hardly exist in a highly purified oxide semiconductor, and carriers are not accumulated in the vicinity of the gate insulating film even when positive gate voltage is applied. However, carriers injected from the source side can be propagated as illustrated in FIG. 13.

FIG. 14B is an energy band diagram of a MOS structure when the gate voltage is set negative, which illustrates the case of a transistor using an oxide semiconductor. Since the oxide semiconductor has almost no minority carriers (holes), carriers are not accumulated in the vicinity of the gate insulating film. This means that the off-current is small.

Note that a band diagram of a transistor in the case of using a silicon semiconductor is illustrated in FIG. 15. The intrinsic carrier density of the silicon semiconductor is approximately  $1.45 \times 10^{10}/\text{cm}^3$  (300 K), and carriers exist even at room temperature. In practical use, a silicon wafer to which an impurity element such as phosphorus or boron is added is used; therefore, the silicon semiconductor actually has  $1 \times 10^{14}/\text{cm}^3$  or more carriers which contribute to conduction between the source and the drain. Further, since the band gap of the silicon semiconductor is 1.12 eV, the off-current of a transistor using a silicon semiconductor greatly fluctuates depending on temperature.

As described above, carriers which are thermally excited at a practical operation temperature can be eliminated so that a transistor can operate only by the carriers injected from the source side; not by simply using an oxide semiconductor with a wide band gap for the transistor, but by reducing impurities such as hydrogen which form donors as much as possible so that the carrier concentration is lower than or equal to  $1 \times 10^{14}/\text{cm}^3$ , preferably lower than or equal to

$1 \times 10^{12}/\text{cm}^3$ . Accordingly, the off-current is decreased to be less than  $1 \times 10^{-13}$  A and a transistor with extremely stable operation, whose off-current hardly changes depending on temperature, can be obtained.

## Embodiment 7

In this embodiment, an example of a shift register which can be formed using the thin film transistors in Embodiment 1 or Embodiment 2 is described.

FIG. 16A is an equivalent circuit diagram illustrating an example of a shift register. The shift register illustrated in FIG. 16A includes two clock signal lines and two stages of flip-flops each of which is electrically connected to either of these clock signal lines. Note that a clock signal line may be further provided, and a larger number of stages of flip-flops may be provided.

In the two clock signal lines, each clock signal is input as follows: when one clock signal line is switched to high level ( $V_H$ ), the other is switched to low level ( $V_L$ ).

In the shift register illustrated in FIG. 16A, an example of a shift register is illustrated, which includes flip-flops which are in order from a flip-flop in a first stage which is electrically connected to a first clock signal line CLK and a flip-flop in a second stage which is electrically connected to the second clock signal line CLKB, to a flip-flop in an (n-1)th stage and a flip-flop in an (n)th stage. However, the present invention is not limited thereto, and the shift register having at least a first flip-flop and a second flip-flop is acceptable.

The clock signal line CLK is a wiring to which a clock signal CK is input.

A clock signal line CLKB is a wiring to which a clock signal CKB is input.

The clock signal CK and the clock signal CKB can be generated using a NOT circuit (inverter circuit) for example.

A start signal SP and a start signal SPB are input to the first flip-flop, a clock signal CK is input thereto as a clock signal, and the first flip-flop outputs an output signal OUT depending on the state of the signal SP, the signal SPB, and the clock signal CK, which are input. Note that in this specification, the state of a signal refers to a potential, a current, or a frequency of the signal, for example.

The start signal SP and the start signal SPB can be generated using a NOT circuit (inverter circuit) for example.

Note that as a signal here, an analog signal or a digital signal which uses voltage, current, resistance, frequency, or the like can be used, for example. For example, at least two potentials, that is, a first potential and a second potential are set, using a high-level (also referred to as high potential or  $V_H$ ) potential as the first potential and a low-level (also referred to as low potential or  $V_L$ ) potential as the second potential, whereby a binary digital signal can be set. Although it is preferable that  $V_H$  and  $V_L$  be a constant value,  $V_H$  and  $V_L$  may take a wide range of values, in consideration of influence of noise.

Note that here, terms with ordinal numbers, such as "first" and "second", are used in order to avoid confusion among components, and the terms do not limit the components numerically.

The second flip-flop has the following function: the output signal OUT of the first flip-flop is input as a start signal SP, a clock signal CK2 is input as the clock signal, and the second flip-flop outputs a signal FF2out as an output signal, which is set depending on the state of the output signal FF1out and the clock signal CK2 which are input.

A start signal SP and a start signal SPB are input to the second flip-flop, a clock signal CK2 is input thereto as a clock signal, and the second flip-flop outputs an output signal OUTB depending on the state of the signal SP, the signal SPB, and the clock signal CK2, which are input.

FIG. 16B illustrates a specific structural example of the first flip-flop illustrated in FIG. 16A.

The start signal SP is input to one of a source or a drain of a first thin film transistor 1111 and one of a source or a drain of a fourth thin film transistor 1114.

The start signal SPB is input to one of a source or a drain of a second thin film transistor 1112 and one of a source or a drain of a third thin film transistor 1113.

The clock signal CLK is input to each gate of the first thin film transistor 1111, the second thin film transistor 1112, the third thin film transistor 1113, and the fourth thin film transistor 1114.

The other of the source and the drain of the first thin film transistor 1111 is connected to a gate of a fifth thin film transistor 1115 and one electrode of a first capacitor element 1119.

The other of the source and the drain of the second thin film transistor 1112 is connected to a gate of a sixth thin film transistor 1116 and one electrode of a second capacitor element 1120.

The other of the source and the drain of the third thin film transistor 1113 is connected to a gate of a seventh thin film transistor 1117 and one electrode of a third capacitor element 1121.

The other of the source and the drain of the fourth thin film transistor 1114 is connected to a gate of an eighth thin film transistor 1118 and one electrode of a fourth capacitor element 1122.

A drain of the fifth thin film transistor 1115 is connected to a high potential side (preferably, a power supply potential Vdd). A source of the fifth thin film transistor 1115 is connected to the other electrode of the first capacitor element 1119 and a drain of the sixth thin film transistor 1116, and outputs an output signal OUT. The other electrode of the second capacitor element 1120 and a source of the sixth thin film transistor 1116 are connected to a low potential side (preferably, a reference potential Vss).

A drain of the seventh thin film transistor 1117 is connected to a high potential side (preferably, a power supply potential Vdd). A source of the seventh thin film transistor 1117 is connected to the other electrode of the third capacitor element 1121 and a drain of the eighth thin film transistor 1118, and outputs an output signal OUTB. The other electrode of the fourth capacitor element 1122 and a source of the eighth thin film transistor 1118 are connected to a low potential side (preferably, a reference potential Vss).

The first capacitor element 1119, the second capacitor element 1120, the third capacitor element 1121, and the fourth capacitor element 1122 can be formed over the same substrate as the thin film transistor, using the capacitor described in Embodiment 2.

As described above, a flip-flop circuit can be manufactured using the thin film transistor which uses a highly purified oxide semiconductor layer as described in Embodiment 1 or Embodiment 2 and the capacitor described in Embodiment 2.

## Embodiment 8

In this embodiment, an example of a boosting circuit (a charge pump circuit) which can be formed using the thin film transistor in Embodiment 1 or Embodiment 2 is described.

FIG. 17 illustrates a specific structural example of a boosting circuit. The boosting circuit illustrated in FIG. 17 includes two clock signal lines, a plurality of transistors **1123** that are diode-connected in a forward direction, a plurality of capacitor elements **1124** whose one electrode is connected between a source and a drain of the plurality of transistors, and a storage capacitor element whose one electrode is connected to the last of the plurality of transistors and the other electrode is kept at a constant potential. The other electrode of the plurality of capacitor elements is electrically connected to either of the two clock signal lines.

Note that a clock signal line may be further provided.

A transistor and a capacitor element may be further provided in accordance with the potential desired to be output.

In the two clock signal lines, each clock signal is input as follows: when one clock signal line is switched to high level ( $V_H$ ), the other is switched to low level ( $V_L$ ).

Each of the clock signal CLK and the clock signal CLKB can be generated using a NOT circuit (inverter circuit) for example. A NOT circuit can be manufactured using the EDMOS circuit described in Embodiment 2.

By using the boosting circuit illustrated in FIG. 17, a potential input from  $V_{in}$  can be raised to  $V_{out}$ . For example, when a power supply potential  $V_{dd}$  is input from  $V_{in}$ , a potential higher than  $V_{dd}$  can be output from  $V_{out}$  and raised to a desired potential. Thus, a signal with a potential raised to a desired potential is input to a power supply line for example, and is used for each circuit mounted on the same substrate as the boosting circuit.

Note that here, a constant potential kept at the other electrode of the storage capacitor element may be a power supply potential  $V_{dd}$  or a reference potential  $V_{ss}$  for example.

As a signal here, an analog signal or a digital signal which uses voltage, current, resistance, frequency, or the like can be used, for example. For example, at least two potentials, that is, a first potential and a second potential are set, a high-level (also referred to as high potential or  $V_H$ ) potential is used as the first potential, and a low-level (also referred to as low potential or  $V_L$ ) potential is used as the second potential, whereby a binary digital signal can be set. Although it is preferable that  $V_H$  and  $V_L$  be a constant value,  $V_H$  and  $V_L$  can take a wide range of values, in consideration of influence of noise.

Note that here, terms with ordinal numbers, such as “first” and “second”, are used in order to avoid confusion among components, and the terms do not limit the components numerically.

As described above, a boosting circuit can be manufactured using the thin film transistor described in Embodiment 1 and the capacitor described in Embodiment 2.

#### Embodiment 9

In this embodiment, examples of an electronic device mounted with a semiconductor integrated circuit which can be obtained in any of Embodiments 1 to 8 are described with reference to FIGS. 18A to 18E. By using the method described in Embodiment 4, that is, a method of transferring a semiconductor integrated circuit from a formation substrate to another substrate, a semiconductor integrated circuit can be mounted on a plastic film or the like, so that electronic devices which are thinned or made flexible can be manufactured. Note that a semiconductor integrated circuit is mounted on a circuit board or the like and then incorporated inside the main body of electronic devices.

On a mother board, a semiconductor integrated circuit including the thin film transistor in Embodiment 1 or Embodiment 2 is mounted. A semiconductor integrated circuit is manufactured by mounting a logic circuit, a flash memory circuit, an SRAM circuit, a DRAM circuit described in Embodiment 6, and the like. Further, the CPU described in Embodiment 3 can be mounted as well. Note that the semiconductor integrated circuit can be mounted by a wire bonding method. In this case, integrated circuit films having various shapes can be mounted.

In addition, an FPC is attached to the circuit board, through which display devices or the like is connected thereto. The circuit board can form a driver and a controller of a display portion. The driver in the display portion includes the shift register described in Embodiment 7 or the EDMOS circuit described in Embodiment 2.

FIG. 18A illustrates a laptop personal computer manufactured by mounting at least a semiconductor integrated circuit as a component, which includes a main body **3001**, a housing **3002**, a display portion **3003**, a keyboard **3004**, and the like. The laptop personal computer includes the CPU described in Embodiment 3, the DRAM circuit described in Embodiment 6, or the like.

FIG. 18B is a portable information terminal (PDA) manufactured by mounting at least a semiconductor integrated circuit as a component, which includes a display portion **3023**, an external interface **3025**, an operation button **3024**, and the like in a main body **3021**. A stylus **3022** is included as an accessory for operation.

FIG. 18C is an electronic paper manufactured by mounting at least a semiconductor integrated circuit as a component. An electronic paper can be used for electronic appliances of a variety of fields as long as they can display data. For example, an electronic paper can be applied to an e-book reader (electronic book), a poster, an advertisement in a vehicle such as a train, displays of various cards such as a credit card, or the like. FIG. 18C illustrates an example of an electronic book reader. For example, the e-book reader **2700** includes two housings: a housing **2701** and a housing **2703**. The housing **2701** and the housing **2703** are combined with a hinge **2711** so that the e-book reader **2700** can be opened and closed with the hinge **2711** as an axis. With such a structure, the e-book reader **2700** can operate like a paper book.

A display portion **2705** and a display portion **2707** are incorporated in the housing **2701** and the housing **2703**, respectively. The display portion **2705** and the display portion **2707** may display one image or different images. In the case where the display portion **2705** and the display portion **2707** display different images, for example, a display portion on the right (the display portion **2705** in FIG. 18C) can display text and a display portion on the left (the display portion **2707** in FIG. 18C) can display graphics.

FIG. 18C illustrates an example in which the housing **2701** is provided with an operation portion and the like. For example, the housing **2701** is provided with a power switch **2721**, an operation key **2723**, a speaker **2725**, and the like. With the operation key **2723**, pages can be turned. Note that a keyboard, a pointing device, or the like may also be provided on the surface of the housing, on which the display portion is provided. Furthermore, an external connection terminal (an earphone terminal, a USB terminal, a terminal that can be connected to various cables such as an AC adapter and a USB cable, or the like), a recording medium insertion portion, and the like may be provided on the back

surface or the side surface of the housing. Moreover, the e-book reader 2700 may have a function of an electronic dictionary.

The e-book reader 2700 may have a configuration capable of wirelessly transmitting and receiving data. Through wire-

less communication, desired book data or the like can be purchased and downloaded from an electronic book server. FIG. 18D is a cellular phone manufactured by mounting at least a semiconductor integrated circuit as a component, which includes two housings: a housing 2800 and a housing 2801. The housing 2801 includes a display panel 2802, a speaker 2803, a microphone 2804, a pointing device 2806, a camera lens 2807, an external connection terminal 2808, and the like. The housing 2800 includes a solar battery cell 2810 for charging of the portable information terminal, an external memory slot 2811, and the like. Further, an antenna is incorporated in the housing 2801.

The display panel 2802 is provided with a touch panel. A plurality of operation keys 2805 which is displayed as images is illustrated by dashed lines in FIG. 18D. Note that the display panel 2802 is mounted with a booster circuit (the booster circuit described in Embodiment 8) for raising a voltage output from the solar battery cell 2810 to a voltage needed for each circuit.

Further, in addition to the above structure, a contactless IC chip, a small memory device, or the like described in Embodiment 4 or Embodiment 5 may be incorporated.

In the display panel 2802, the display direction can be appropriately changed depending on a usage pattern. Further, the display device is provided with the camera lens 2807 on the same surface as the display panel 2802, and thus it can be used as a video phone. The speaker 2803 and the microphone 2804 can be used for videophone calls, recording and playing sound, and the like as well as voice calls. Moreover, the housings 2800 and 2801 in a state where they are developed as illustrated in FIG. 18D can shift by sliding so that one is lapped over the other; therefore, the size of the cellular phone can be reduced, which makes the cellular phone suitable for being carried.

The external connection terminal 2808 can be connected to an AC adaptor and a variety of cables such as a USB cable, whereby charging and data communication with a personal computer or the like are possible. Furthermore, a large amount of data can be stored and moved by inserting a recording medium into the external memory slot 2811.

Further, in addition to the above functions, an infrared communication function, a television reception function, or the like may be provided.

FIG. 18E is a digital camera manufactured by mounting at least a semiconductor integrated circuit as a component, which includes a main body 3051, a display portion (A) 3057, an eyepiece 3053, operation switches 3054, a display portion (B) 3055, a battery 3056, and the like.

This embodiment can be freely combined with any one of Embodiments 1 to 8.

This application is based on Japanese Patent Application serial no. 2009-238885 filed with Japan Patent Office on Oct. 16, 2009, the entire contents of which are hereby incorporated by reference.

The invention claimed is:

1. A semiconductor device comprising:

a first transistor over a glass substrate, the first transistor comprising a first oxide semiconductor layer where a channel formation region is provided,

a second transistor over the glass substrate, the second transistor comprising a second oxide semiconductor layer where a channel formation region is provided,

wherein each of the first oxide semiconductor layer and the second oxide semiconductor layer comprises indium and zinc,

wherein a conductive layer is provided between the substrate and the first oxide semiconductor layer,

wherein a first insulating layer is provided between the conductive layer and the first oxide semiconductor layer,

wherein each of the first oxide semiconductor layer and the second oxide semiconductor layer are over and in direct contact with the first insulating layer,

wherein a channel length of the first transistor is longer than a channel length of the second transistor,

wherein no conductive layer is provided between the substrate and the second oxide semiconductor layer, and

wherein a size of crystal grains in each of the first oxide semiconductor layer and the second oxide semiconductor layer is greater than or equal to 1 nm and smaller than or equal to 20 nm.

2. The semiconductor device according to claim 1, wherein a hydrogen concentration in each of the first oxide semiconductor layer and the second oxide semiconductor layer is lower than or equal to  $5 \times 10^{19}/\text{cm}^3$ .

3. The semiconductor device according to claim 1, wherein an off-current of each of the first transistor and the second transistor is less than or equal to  $1 \times 10^{-13}$  A.

4. A semiconductor device comprising:

a first transistor over a glass substrate, the first transistor comprising a first oxide semiconductor layer where a channel formation region is provided,

a second transistor over the glass substrate, the second transistor comprising a second oxide semiconductor layer where a channel formation region is provided,

wherein the first transistor comprises a first conductive layer and a second conductive layer,

wherein each of the first conductive layer and a second conductive layer are over the first oxide semiconductor layer,

wherein the second transistor comprises a third conductive layer and a fourth conductive layer,

wherein each of the third conductive layer and the fourth conductive layer are over the second oxide semiconductor layer,

wherein each of the first oxide semiconductor layer and the second oxide semiconductor layer comprises indium and zinc,

wherein a conductive layer is provided between the substrate and the first oxide semiconductor layer,

wherein a first insulating layer is provided between the conductive layer and the first oxide semiconductor layer,

wherein each of the first oxide semiconductor layer and the second oxide semiconductor layer are over and in direct contact with the first insulating layer,

wherein a channel length of the first transistor is longer than a channel length of the second transistor, and

wherein a size of crystal grains in each of the first oxide semiconductor layer and the second oxide semiconductor layer is greater than or equal to 1 nm and smaller than or equal to 20 nm.

5. The semiconductor device according to claim 4, wherein a hydrogen concentration in each of the first oxide semiconductor layer and the second oxide semiconductor layer is lower than or equal to  $5 \times 10^{19}/\text{cm}^3$ .



6. The semiconductor device according to claim 4, wherein an off-current of each of the first transistor and the second transistor is less than or equal to  $1 \times 10^{-13}$  A.

\* \* \* \* \*