



US011880195B2

(12) **United States Patent**  
**Dippel et al.**

(10) **Patent No.:** **US 11,880,195 B2**  
(45) **Date of Patent:** **Jan. 23, 2024**

(54) **APPARATUS, SYSTEM AND METHOD OF FORMING POLYMER MICROSPHERES FOR USE IN ADDITIVE MANUFACTURING**

(71) Applicant: **JABIL INC.**, St. Petersburg, FL (US)

(72) Inventors: **Nicholas J. Dippel**, St. Petersburg, FL (US); **Thomas Gardner**, St. Petersburg, FL (US); **Daryn York**, St. Petersburg, FL (US)

(73) Assignee: **JABIL INC.**, St. Petersburg, FL (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **16/871,824**

(22) Filed: **May 11, 2020**

(65) **Prior Publication Data**  
US 2020/0338816 A1 Oct. 29, 2020

**Related U.S. Application Data**

(63) Continuation of application No. PCT/US2019/065035, filed on Dec. 6, 2019.  
(Continued)

(51) **Int. Cl.**  
**B01J 2/16** (2006.01)  
**G05B 23/02** (2006.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **G05B 23/0283** (2013.01); **B01J 2/16** (2013.01); **B29C 64/153** (2017.08);  
(Continued)

(58) **Field of Classification Search**  
CPC ..... B01J 2/16  
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,177,766 A \* 10/1939 Black ..... B01J 2/00  
423/279  
2,460,546 A \* 2/1949 Stephanoff ..... B01J 8/18  
524/904

(Continued)

FOREIGN PATENT DOCUMENTS

DE 10339545 A1 3/2005  
DE 202016106243 U1 11/2016

(Continued)

OTHER PUBLICATIONS

Machine translation of EP 0945173, retrieved from EPO database Oct. 7, 2022 (Year: 2022).\*


(Continued)

*Primary Examiner* — Timothy Kennedy  
(74) *Attorney, Agent, or Firm* — Riverside Law LLP

(57) **ABSTRACT**

The embodiments are and include at least an apparatus, system and method for forming print material particles for additive manufacturing (AM) printing. The apparatus, system and method include at least a melt chamber comprising a polymer melt; a vertical extruder that fluidically receives the polymer melt; an atomizer that atomizes the polymer melt from the vertical extruder and that distributes the atomized polymer melt; a fall chamber comprising a plurality of zones into which the atomized polymer melt is distributed; and a collector to receive the print material particles formed of the atomized polymer melt after falling through the plurality of zones.

**20 Claims, 8 Drawing Sheets**



**Related U.S. Application Data**

(60) Provisional application No. 62/776,287, filed on Dec. 6, 2018.

(51) **Int. Cl.**

**G06T 19/00** (2011.01)  
**G06F 8/65** (2018.01)  
**G05B 19/042** (2006.01)  
**B29C 64/307** (2017.01)  
**B29C 64/364** (2017.01)  
**B29C 64/153** (2017.01)  
**B29C 64/245** (2017.01)  
**B29C 64/295** (2017.01)  
**B29C 64/205** (2017.01)  
**B29C 64/25** (2017.01)  
**H04L 9/40** (2022.01)  
**H04W 4/38** (2018.01)  
**B33Y 30/00** (2015.01)

(52) **U.S. Cl.**

CPC ..... **B29C 64/205** (2017.08); **B29C 64/245** (2017.08); **B29C 64/25** (2017.08); **B29C 64/295** (2017.08); **B29C 64/307** (2017.08); **B29C 64/364** (2017.08); **G05B 19/0425** (2013.01); **G06F 8/65** (2013.01); **G06T 19/006** (2013.01); **H04L 63/107** (2013.01); **H04W 4/38** (2018.02); **B29K 2823/06** (2013.01); **B29K 2995/0094** (2013.01); **B33Y 30/00** (2014.12)

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,976,574 A \* 3/1961 Keutgen ..... B01J 2/16  
 428/402.21  
 3,166,613 A 1/1965 Wright et al.  
 3,298,058 A \* 1/1967 Summerville ..... B29B 9/06  
 425/8  
 3,446,877 A \* 5/1969 Endler ..... B01J 2/02  
 264/13  
 4,141,316 A \* 2/1979 Grun ..... A23C 9/16  
 426/453  
 5,782,010 A \* 7/1998 Boersen ..... B01J 8/44  
 34/577  
 6,013,216 A \* 1/2000 Watanabe ..... B01J 2/16  
 264/117  
 6,171,433 B1 1/2001 Otaigbe et al.  
 6,533,563 B1 \* 3/2003 Otaigbe ..... B01J 2/04  
 425/6  
 10,981,130 B2 4/2021 Dressler  
 2003/0116080 A1 6/2003 Huang  
 2004/0018109 A1 \* 1/2004 Blatter ..... C09D 5/03  
 419/32  
 2004/0166248 A1 \* 8/2004 Hu ..... B01J 2/006  
 427/213  
 2008/0155853 A1 \* 7/2008 Wang ..... F26B 5/065  
 34/286  
 2009/0091049 A1 \* 4/2009 Nielsen ..... B01J 2/16  
 425/7

2011/0159180 A1 \* 6/2011 Ledoux ..... B05C 9/12  
 118/712  
 2014/0096409 A1 \* 4/2014 Ohtsu ..... G03G 9/0819  
 34/582  
 2014/0163109 A1 6/2014 Gerber et al.  
 2014/0290435 A1 10/2014 Sekine et al.  
 2017/0008082 A1 1/2017 Chen  
 2018/0093294 A1 \* 4/2018 Sherman ..... A01C 1/06  
 2019/0374917 A1 \* 12/2019 Liu ..... B01J 2/006

FOREIGN PATENT DOCUMENTS

DE 202016106243 U1 12/2016  
 DE 102020103912 A1 8/2021  
 EP 0945173 A1 3/1999  
 GB 1234562 A \* 6/1971 ..... B01J 2/003  
 GB 2436195 A \* 9/2007 ..... B01J 2/02  
 WO WO-9400229 A1 \* 1/1994 ..... B01F 15/00837  
 WO 2020025312 A1 2/2020

OTHER PUBLICATIONS

OED definition of vane, retrieved Jun. 15, 2023 (Year: 2023).  
 International Search Report for PCT/US2019/065035, dated Apr. 21, 2020.  
 Written Opinion of the International Searching Authority for PCT/US2019/065035, dated Apr. 121, 2020.  
 International Preliminary Report on Patentability for PCT/US2019/065035, dated Jun. 8, 2021.  
 Fluid Flow and Particle Size in Gas Atomization for Fine Powders; Michael J. Naylor; Imperial College, London SW72AZ 1987; pp. 1-244.  
 Gas Atomization of Polymers; Jon Michael McAvoy; Iowa State University; Ames, Iowa; 1997; Retrospective Theses and Dissertations. 16992; pp. 1-107.  
 Crystallization Kinetics of Polymers; 2015-2022; Polymer Properties Database; Polymerdatabase.com; pp. 1-4.  
 How to Manipulate Droplet Jetting From Needle Type Jet Dispensers; Thanh Huy Plung & Kye-Si Kwon; www.nature.com/scientificreports; Scientific Reports; pp. 1-12.  
 Simulation and Experiment on Droplet Formation and Separation for Needle-Type Micro-Liquid Jetting Dispenser; Shizhou Lu, Guangyu Cao, Hai Zheng, Dongqi Li, Meiyang Shi and Jiahui Qi; Micromachines (MDPI); 2018; Licensee MDPI, Basel Switzerland; pp. 1-14.  
 Scientific Reports, NatureResearch, Thanh Huy Phung & Kye-Si Kwon; How to Manipulate Droplet Jetting from Needle Tuype Jet Dispensers; 2019; p. 1-12.  
 Micromachines; MDPI; Shizhou Lu, Guangyu Cao, Hai Zheng, Dongqi Li, Meiyang Shi and Jiahui Qi; Simulation and Experiment on Droplet Formation and Separation for Needle-Type Micro-Liquid Jetting Dispenser, 2018; pp. 1-14.  
 Polymer Chemistry (2nd edition) Paul C. Hiemenz, Timothy P. Lodge; (Figure 13.16, Figure 13.21, Figure 13.33, p. 554, p. 555, p. 557, p. 559, p. 560).  
 Gas Atomization of Polymers. I. Feasibility Studies and Process Development; Joshua U. Otaigbe and Jon M. McAvoy; Department of Materials Science and Engineering, and Center for Advanced Technology Development, 3053 Gilman Hall, Iowa State University, Ames, Iowa 50011; Jun. 17, 1997 and revised Nov. 11, 1997.

\* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6






FIG. 7




FIG. 8

1

## APPARATUS, SYSTEM AND METHOD OF FORMING POLYMER MICROSPHERES FOR USE IN ADDITIVE MANUFACTURING

### CROSS-REFERENCE TO RELATED APPLICATIONS

The present application claims the benefit of priority, as a continuation-in-part, to International Application No. PCT/US2019/065035, filed Dec. 6, 2019, which claims the benefit of priority to U.S. Provisional Application No. 62/776,287, filed Dec. 6, 2018, entitled: "Apparatus, System and Method of Forming Polymer Microspheres For Use In Additive Manufacturing," the entirety of each of which applications is incorporated herein by reference as if set forth in its respective entirety.

### BACKGROUND

#### Field of the Disclosure

The present disclosure relates to additive manufacturing, and, more specifically, to an apparatus, system and method of forming polymer microspheres for use in additive manufacturing.

#### Description of the Background

Three-dimensional (3D) printing is any of various processes in which material is joined or solidified under computer control to create a three-dimensional object. The 3D print material is "added" onto a base, such as in the form of added liquid molecules or layers of powder grain or melted feed material, and upon successive fusion of the print material to the base, the 3D object is formed. 3D printing is thus a subset of additive manufacturing (AM).

A 3D printed object may be of almost any shape or geometry, and typically the computer control that oversees the creation of the 3D object executes from a digital data model or similar additive manufacturing file (AMF) file. Usually this AMF is executed on a layer-by-layer basis, and may include control of other hardware used to form the layers, such as lasers or heat sources.

There are many different technologies that are used to execute the AMF. Exemplary technologies may include: fused deposition modeling (FDM); stereolithography (SLA); digital light processing (DLP); selective laser sintering (SLS); selective laser melting (SLM); inkjet print manufacturing (IPM); laminated object manufacturing (LOM); and electronic beam melting (EBM).

Some of the foregoing methods melt or soften the print material to produce the print layers. For example, in FDM, the 3D object is produced by extruding small beads or streams of material which harden to form layers. A filament of thermoplastic, wire, or other material is fed into an extrusion nozzle head, which typically heats the material and turns the flow on and off.

Other methods, such as laser or similar beam-based techniques, may or may not heat the print material, such as a print powder, for the purpose of fusing the powder granules into layers. For example, such methods melt the powder using a high-energy laser to create fully dense materials that may have mechanical properties similar to those of conventional manufacturing methods. Alternatively, SLS, for example, uses a laser to solidify and bond grains of plastic, ceramic, glass, metal or other materials into layers to produce the 3D object. The laser traces the pattern of each

2

layer slice into the bed of powder, the bed then lowers, and another layer is traced and bonded on top of the previous.

In contrast, other methods, such as IPM, may create the 3D object one layer at a time by spreading a layer of powder, and printing a binder in the cross-section of the 3D object. This binder may be printed using an inkjet-like process.

Currently, the known art typically produces powders for additive manufacturing using methods that are slow, inefficient, and which require significant effort. The foregoing notwithstanding, it is typical that such known processes produce print material that varies greatly in size and density, and which generally lack the sphericity needed for more refined print processes. Worse yet, such powder forming methods are not only exhaustive, expensive and inefficient, but are also often print material-specific. That is, the methods and materials used are varied in the known art in direct accordance with the desired composition of the print material to be produced.

### SUMMARY

The embodiments are and include at least an apparatus, system and method for forming print material particles for additive manufacturing (AM) printing. The apparatus, system and method may include at least a melt chamber comprising a polymer melt; a vertical extruder that fluidically receives the polymer melt; an atomizer that atomizes the polymer melt from the vertical extruder and that distributes the atomized polymer melt; a fall chamber comprising a plurality of zones into which the atomized polymer melt is distributed; and a collector to receive the print material particles formed of the atomized polymer melt after falling through the plurality of zones.

### BRIEF DESCRIPTION OF THE DRAWINGS

The disclosed non-limiting embodiments are discussed in relation to the drawings appended hereto and forming part hereof, wherein like numerals indicate like elements, and in which:

FIG. 1 is an illustration of an additive manufacturing printing system;

FIG. 2 illustrates an exemplary print material;

FIG. 3 illustrates print particle formation;

FIG. 4 illustrates aspects of the embodiments;

FIG. 5 illustrates aspects of the embodiments;

FIG. 6 shows a vessel that can be utilized for forming polymer microspheres;

FIG. 7 illustrates additive manufacturing printing; and

FIG. 8 illustrates an exemplary computing system.

### DETAILED DESCRIPTION

The figures and descriptions provided herein may have been simplified to illustrate aspects that are relevant for a clear understanding of the herein described apparatuses, systems, and methods, while eliminating, for the purpose of clarity, other aspects that may be found in typical similar devices, systems, and methods. Those of ordinary skill may thus recognize that other elements and/or operations may be desirable and/or necessary to implement the devices, systems, and methods described herein. But because such elements and operations are known in the art, and because they do not facilitate a better understanding of the present disclosure, for the sake of brevity a discussion of such elements and operations may not be provided herein. However, the present disclosure is deemed to nevertheless

include all such elements, variations, and modifications to the described aspects that would be known to those of ordinary skill in the art.

Embodiments are provided throughout so that this disclosure is sufficiently thorough and fully conveys the scope of the disclosed embodiments to those who are skilled in the art. Numerous specific details are set forth, such as examples of specific components, devices, and methods, to provide a thorough understanding of embodiments of the present disclosure. Nevertheless, it will be apparent to those skilled in the art that certain specific disclosed details need not be employed, and that embodiments may be embodied in different forms. As such, the embodiments should not be construed to limit the scope of the disclosure. As referenced above, in some embodiments, well-known processes, well-known device structures, and well-known technologies may not be described in detail.

The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. For example, as used herein, the singular forms “a”, “an” and “the” may be intended to include the plural forms as well, unless the context clearly indicates otherwise. The terms “comprises,” “comprising,” “including,” and “having,” are inclusive and therefore specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof. The steps, processes, and operations described herein are not to be construed as necessarily requiring their respective performance in the particular order discussed or illustrated, unless specifically identified as a preferred or required order of performance. It is also to be understood that additional or alternative steps may be employed, in place of or in conjunction with the disclosed aspects.

When an element or layer is referred to as being “on”, “engaged to”, “connected to” or “coupled to” another element or layer, it may be directly on, engaged, connected or coupled to the other element or layer, or intervening elements or layers may be present, unless clearly indicated otherwise. In contrast, when an element is referred to as being “directly on,” “directly engaged to”, “directly connected to” or “directly coupled to” another element or layer, there may be no intervening elements or layers present. Other words used to describe the relationship between elements should be interpreted in a like fashion (e.g., “between” versus “directly between,” “adjacent” versus “directly adjacent,” etc.). Further, as used herein the term “and/or” includes any and all combinations of one or more of the associated listed items.

Yet further, although the terms first, second, third, etc. may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms may be only used to distinguish one element, component, region, layer or section from another element, component, region, layer or section. Terms such as “first,” “second,” and other numerical terms when used herein do not imply a sequence or order unless clearly indicated by the context. Thus, a first element, component, region, layer or section discussed below could be termed a second element, component, region, layer or section without departing from the teachings of the embodiments.

The disclosed apparatus, system and method provide additive manufacturing materials, and enable the production of additively manufactured parts from those materials, hav-

ing properties presently unavailable in the known art. Further, embodiments include designs for specification that may match and/or correlate particular print materials, print material fillers, and printed output objects given one or more processes available to produce the printed output object.

Historically, the use of additive manufacturing (AM), such as 3D printing, to produce parts having varying densities, such as a low density foam part, has been challenging and required custom machines and customized matching of materials. Contrary to the known art, the embodiments include materials and processes by which material is produced to more readily be used in existing AM technologies to produce parts of variable densities for various industries.

The embodiments may allow for a part to be printed from the provided print materials, and then selectively cut, crushed, or otherwise processed to create a final part. The part produced using AM can be printed very rapidly using existing AM printing technologies. Further, the inherent elastomeric properties of certain parts are more controllable throughout the printed part in the disclosed embodiments, due to the print material formation, and can thus be further tailored during and after the printing, than the known art.

FIG. 1 illustrates a typical additive manufacturing (AM) system **10**. In the illustration, a print material **12** is fed into a print process **14**, such as the powder/pulverant-based AM processes discussed throughout, and the print process **14** outputs a printed 3D part **16**. In the embodiments, the print material **12** may have the particular characteristics discussed herein, which may allow for the use of the print material **12** in any one or more processes **14**, and which thereby result in any of various types of output parts **16** such as may have the characteristics discussed herein.

Additionally, computing system **1100** may execute one or more programs/algorithms **1190** to control one or more aspects of system **10**, as referenced throughout. By way of example, program **1190** may be the AMF referenced herein above, and the AMF **1190** may independently control at least process **14**. The AMF may additionally control the selection and/or distribution of print material **12**, compounds **12a**, and/or additives and fillers, and may further modify processes **14**, print materials **12**, and so on in order to achieve a user-desired print output **16**, as discussed further herein below.

More particularly, the embodiments may include specifically polymer-based print materials **12**. These materials **12** may include a TPU-based microsphere, for example, and may additionally include one or more additives **20**, such as may further enhance the operating characteristics and print operating windows discussed throughout the disclosure, and such as are discussed further herein below.

That is, the embodiments allow for the addition of additives, such as using unique screw extruders to melt the incoming material(s), sometimes from multiple material sources. That is, the use of an extruder allows not only homopolymers to be melt-atomized, but also allows for the same melt-atomization with any ones of a near infinite amount of additives (an “additive” being defined to include anything other than the polymer) introduced immediately prior to atomization. By way of non-limiting example, reinforcement and filler additives, such as fibers, may be added via a twin screw extruder, melt-mixed, atomized, and solidified, all with the resin/filler ratio maintained in the resulting particle (e.g., the additive may still be encapsulated/surrounded by polymer). As such, melting/mixing/atomization/particle collection in an additive-inclusive method may nevertheless all be performed by the single disclosed system.

As referenced, the disclosed print input materials **12** may be used in powder-based AM processes **14**, such as those in which the powder **120** including the material **12** may be spread, melted in a targeted manner, and/or allowed to or processed to solidify, thus forming successive layers that result in a three-dimensional output object/part **16** having the characteristics discussed herein as indicative of both the process **14** and the input print material **12**. Processes **14** may include, but are not limited to: Selective Laser Sintering (SLS), Selective Laser Melting (SLM), Selective Heat Sintering (SHS), High Speed Sintering (HSS), Multi Jet Fusion (MJF), Binder Jetting (BJ), Material Jetting (MJ), Laminated Object Manufacturing (LOM), and other AM technologies referenced herein, and/or AM technologies that utilize thermoplastic powders/pulverants as may be known to the skilled artisan. It will also be understood to the skilled artisan that other AM and similar processes **14** may be modified to employ the print materials **12** disclosed herein, including but not limited to injection molding, roto molding, vacuum molding, subtractive manufacturing, and so on.

As referenced above, and referring now specifically to FIG. 2, additives **130** may be included with material **12** in forming powder **120**. Additives **130** may provide desired characteristics to powder **120**, may enable or improve aspects of processes **14**, or may provide desired characteristics to output part **16** produced by exposure of the input print material **12** to process **14**. Moreover, additives **130** may enable the particular characteristics of input print material **12** discussed herein. Additives **130** may include, by way of non-limiting example, glass beads, glass fibers, carbon fibers, carbon black, metal oxides, copper metals, flame retardants, antioxidants, pigments, powder flow aids, inks, and so on. For example, ink additives **130** may allow for modification of print material **12** properties, such as may provide for different functional inks for use in multi-jet fusion AM printing.

More particularly, the disclosure includes AM “printed” output objects **16** that are printed from print material **12**. As referenced above with respect to FIG. 2, such a print material **12** may be formed of combined particles having combination chemical makeups in melt **1304** discussed below. The combination print material **12** may provide a variability in the density of the print material **12**, and hence in the AM printed output **16**.

Particles having a combination chemical makeup **12** may necessitate a solvent during particle formation, and the solvent may be, for example, a liquid or gas that serves as the medium for a chemical reaction. The solvent may be non-participatory with the reactants in a solution, wherein the solvent does not participate in the reaction; or participatory, wherein the solvent may be, for example an acid (proton), a base (removing protons), or a nucleophile (donating a lone pair of electrons), and may thereby contribute to the chemical reaction.

For different applications, the melt material **1304** may vary in accordance with the application in the disclosed embodiments. That is, the melt **1304** detailed below may have a combination chemical makeup, or may consist of solely polymer **1306**. For example, foam-centric applications may require formation of an elastomeric print material **12** having high elongation, substantial rebound, and adequate compression. Applicable elastomeric compounds in the disclosed processes may thus include: styrene block copolymers, thermoplastic olefins, elastomeric alloys, thermoplastic polyurethanes, thermoplastic copolyesters, thermoplastic polyamides, ethylene-vinyl acetate, ethylene propylene rubber, ethylene propylene diene rubber,

polyurethanes, silicones, polysulfides, elastolefins, high density polyethylene, low density polyethylene, linear low density polyethylene, polypropylene, polyolefin copolymers, polystyrene, polystyrene copolymers, polyacrylates, polymethacrylates, polyesters, polyvinylchloride, fluoropolymers, liquid crystal polymers, polyamides, poly-ether imides, polyphenylene sulfides, polysulfones, polyacetals, polycarbonates, polyphenylene oxides, polyurethanes, thermoplastic elastomers, epoxies, alkyds, melamines, phenolics, ureas, vinyl esters, liquid crystal polymers and/or combinations thereof.

The embodiments provide improved methods of producing polymer powders **120** using the aforementioned polymer melt **1304**. Particular polymer-centric powders **120** may necessitate the use, in melt **1304** rather than as powder additives **130**, of melt-processed reinforcements or other additives that do not generally allow for the use of the liquid or gas-based processes of the known art. The known art for producing polymer powders **120** for additive manufacturing (AM) systems generally consists of precipitation and/or compounding-grinding-polishing. That is, the known art necessitates a multi-step process to form powders **120** of particles **12** having combination chemical makeups, which is inefficient, and which leads to poor results, at least in that the greater the number of process steps that must be controlled, the great the number of process points at which errors can be introduced. The embodiments allow for the production of powders **120** having complex particles **12** in a single-step, single machine process, and are applicable to wide range of both neat and reinforced/modified polymers.

That is, aspects of the embodiments may provide an apparatus, system and method for mass production of high-quality spherical powders, and high aspect ratio microfibers, from molten polymers, such as for use as a print material in AM printing processes. The polymer melt is fed, such as from an extruder, into an atomizer for distribution of the atomized polymer melt into a fall chamber having a plurality of controlled zones.

For example, a high-pressure non-reactive gas, such as a nitrogen gas in the range of 7.6 MPa/1050 psi, may force the extruded polymer melt through an atomizer such that the molten polymer is forced into fine droplets that cool through the multiple zones to form spherical powder particles. Polyethylene-based powders, such as ranging in size from about 0.1  $\mu\text{m}$  to about 200  $\mu\text{m}$ , may thereby be efficiently produced in short cycle times by exerting control over several process variables, such as atomization temperature, the polymer melt stream size, the fall rate, and the process zones. By way of non-limiting example, a maximum weight fraction of the powder at 0-53  $\mu\text{m}$  may be produced, such as by atomizing a 3.175-mm melt stream size at, by way of example, a range of 205° C.

Such zones may be flow, heat, or collection zones, by way of example. More specifically, heat may be selectively controlled in the embodiments, such as in bands or zones. Each of a plurality of heat zones may hold material at a specific temperature as the material falls or otherwise passes through that zone. This control of the temperature axially along chamber may be indirect, such as using heater bands. Direct heating zones may be created by heating the gas inlet to the chamber at different points or stages of the chamber, such as through the use of gas pre-heating. This gas pre-heating may utilize the aforementioned heater bands to pre-heat the gas in an external containment chamber.

More particularly and as illustrated in FIG. 3, a process chamber **1300** in accordance with the embodiments may include, at an upper portion thereof, a vertical extruder or

other vessel **1302** that contains a polymer melt **1304**. By way of example, the polymer **1306** may enter the extruder or vessel **1302** as a pellet or other raw material state, and is then heated at least to its respective melt point to obtain a suitable viscosity of the melt **1304** for processing.

More specifically, the vessel **1302** containing the polymer **1306** may be heated, such as by heater **1310**, past the respective  $T_m$  of that polymer **1306**, after which a valve **1312** at the base of the vessel **1302** may be opened to allow the polymer melt **1304** to flow gravimetrically. Alternatively, the polymer **1306** may be melted in the vessel **1302**, and may be pressurized to flow, such as through the atomizer **1320** referenced below. In this case, the flow path for the atomized melt may be heated in order to maintain the polymer melt **1304** in a molten state. Yet further and alternatively, a single or twin screw extruder **1322** may be mounted vertically atop the atomizer **1320** discussed below, and the polymer melt **1304** may be heated and compounded with various additives, such as to be alloyed, reinforced, or otherwise modified to a specific formulation, and the melt **1304** may then exit through a die.

The melt **1304** may be extruded or otherwise passed to atomizer **1320** that atomizes the melt **1304a** into a given particle size. The atomizer **1320** may be or include at least one of a centrifugal, a spinning/chopping disc, or gas (which may include a gas source and pump)-driven atomizer that provides the atomization of the received melt **1304**, as will be apparent to the skilled artisan in light of the discussion herein.

Of note, the fall chamber **1330** discussed herein may lead to preferred atomization techniques, as will be apparent to the skilled artisan. By way of example, a centrifugal and/or a spinning/chopping disc or similar atomizer may produce strings of polymer material, and thus may necessitate a wider fall chamber **1330**, while such a design consideration for the fall chamber **1330** may not be relevant for gas-driven directed atomization.

The atomized polymer melt **1304a** may include, such as within the melt **1304** or added during the atomization process, the aforementioned reinforcements or additives. The atomized melt **1304a** may then “fall” through the powder processing fall chamber **1330**, as illustrated. As such, the atomized melt **1304a** may comprise a suitable molecular weight and melt viscosity to successfully crystallize in a controlled amount of time, i.e., to crystallize as the atomized melt “falls” through the fall chamber **1330** to the collection point **1336**. It will be appreciated that, although the “fall” of the atomized melt **1304a** may be dependent solely on gravity, other expedients or impediments to a gravity-based fall may be provided. By way of example, the chamber **1330** may be pressurized, may include one or more gas inlets or high pressure “blowers” or the like **1340**, such as to advance or retard the “fall” through the fall chamber **1330**.

The chamber **1330** is optimally sized and shaped so as to accommodate the full spray of the atomizer **1320**, such as subject to any spray controls placed on the atomizer **1320** for a given process. That is, the chamber **1330** is sized and shaped so as to allow for controlled cooling of the maximum spray area for the atomized melt **1304a** as the particles of the atomized melt **1304a** fall/travel through the fall chamber **1330**.

The fall chamber **1330** may comprise substantially uniform conditions through the fall zone, such as with respect to temperature and pressure, or may comprise a plurality of processing zones **1336**. By way of example, the chamber may comprise a series of heating or cooling zones **1340a**.

**1340b**, **1340c**, **1340d** . . . , such as may cool the melt in accordance with a given control algorithm to obtain a desired final particle size and sphericity for produced print particle **12** from the provided atomized polymer melt **1304**

a. To that end, the fall chamber **1330** may comprise numerous heating or cooling elements **1340 a**, **1340 b**. **1340 c** . . . along the vertical axis thereof, and/or may include a tuned gas flow as required to control the temperature of the fall chamber, and, more particularly, the melt **1304** a passing therethrough, at many points along the vertical axis of the fall chamber **1330**. For example, one of the zones may hold the melt point of a particular polymer to build the crystalline region, such as a hold temperature of between 50-300 degrees C., and more particularly 170-250 degrees C., and may then provide a series of controlled cooling zones to solidify the crystallized polymer into a dried powder particle **12**.

The foregoing optimizes the control of the crystallinity and of other properties, such as the sphericity, of the polymer melt **1304a** as it cools or is affirmatively cooled through the fall chamber **1330**. The tuning and control, such as using the control algorithm **1190** discussed herein, of the polymer crystallization kinetics and/or of other powder characteristics allows for optimization for peak performance of the print material **12** formed by the disclosed system and method in an AM print process **14**.

Thus, simply put, the chamber **1330** may provide a particular “fall” time, given the conditions in the chamber **1330**. This fall time may or may not be divided into a series of time horizons, such as wherein each horizon comprises a fall time and temperature, such that the atomized melt is modified during the fall in order to reach a desired physical state as a pulverant/powder particle **12** upon reaching the collection point **1336**.

As discussed, following the “fall” through the chamber **1330**, collection of powder **12** at collection point **1336** may occur, such as prior to or in conjunction with particle separation. For example, powder collection may occur into a collection chamber acting as collection point **1336**, which may be located at the base of the fall chamber **1330**, or which may be adjacent to the fall chamber **1330** such that the powder is blown, rolled, sucked, or similarly collected into the adjacent collection chamber **1336**.

Particle separation may separate the particles based on any known criteria, including, but not limited to, particle size, weight, sphericity, chemical makeup, or pursuant to other engineering design criteria. Further, particle separation may occur via any known methodology, such as the use of air classifiers, cyclones, or the like within or otherwise in fluidic communication with collection point/chamber **1336**.

By way of non-limiting example, an air classifier **1350**, which is commonly employed in industrial processes in which a volume of mixed materials with differing physical characteristics needs to be separated quickly and efficiently, may separate the powder **12** based on size, shape, or density, by way of non-limiting example. In such a case, the powder **12** may be injected for sorting from collection point **1336** into air classifier **1350**, which may comprise a column of rising air. In the air classifier **1350**, air drag on the powder **12** supplies an upward force, which counteracts the force of gravity and lifts the powder **12** to be sorted. And, due to the dependence of air drag on each particle’s size and shape, the powder particles **12** in the moving air column are sorted vertically and thereby separated.

Collection of only powder particles having the desired characteristics, such as the desired particle size range, provides for further optimization of the powder collected as a

print material **12** for use in a particular AM process **14**. Moreover, powder particles that fail to meet the separation characteristics, such as being too large or too small, may be collected for re-melt into melt **1304**, thus implementing a “zero waste” process in certain of the embodiments.

As discussed throughout, the chamber **1330/300** may be horizontal or vertical. A vertical chamber may have material dropped from the top thereof through the chamber, or pushed/pumped up from the bottom, as discussed. A horizontal chamber may have material entry from the sides, and may include an “air table” to increase residence time in the chamber.

Feed material entered into the chamber may be in a filament form, or, in some embodiments, may be fed from an extruder. The extruder may be any of various designs, may be horizontal or vertical in format to match the chamber design, and may operate at any temperature or other feed characteristics needed for each embodiment.

Controlled feedback loop of pressure at the atomizer feed nozzle (i.e., a pressure transducer) and the pressure that which, for example, the extruder extrudes, allows for substantial control of incoming molten polymer pressure and flow rate. By way of non-limiting example, a screw extruder allows for optimal mixing, throughput and control of final particle size and characteristics.

Of course, extrusion may be used with or instead of various delivery methods to the chamber. For example, to obtain molten polymer beads, a large number of nozzles of a targeted length and diameter may be used to force a polymer through the tube, the end/tip of which is designed to retain a particle until it is of sufficient mass that it overcomes the capillary forces and falls free of the tube.

Increased residence time in the chamber may be provided by a gas inlet/gas flow from the bottom of the chamber, and, in some cases, along the chamber walls. This may be particularly the case in the instance of a free-falling particle.

Further, rings/baffles/blades/steps/scoops (collectively “baffles”), i.e., a flow-directing or obstructing step, vane or panel, may be provided on the chamber walls to not only control residence and fall time, but also to selectively control temperature, such as in zones or bands, among other functions. For example, the baffle may additionally be used to capture material, such as to capture particles of a certain size/density, and/or to increase residence time of a particle in the chamber, such as by redirecting airflow.

More particularly, steel or other material may be used to form the baffle(s) that allow for a breakup in the gas flow path. This gas flow modification may help to control temperature, capture material, or increase residence time, as discussed throughout.

More particularly, and as illustrated in FIG. 4, a chamber **300** may include a polymer or blend **304** input by an atomizer nozzle **302**. The atomized spray **304** may be flow directed and/or suspended by both temperature controlled gas flow inlets **306** at the base of the chamber, and/or temperature controlled gas flow inlets **308** providing flow **310** from along the chamber sidewalls. Of note, gas inlets **306**, **308** may both control flow/suspension, and at least partially control temperature zones.

Chamber **300** may additionally include one or more baffles **312**, which may help to collect certain material and to control the flow direction and amount in the chamber. Material collection points **314** may collect material desired to be collected from the chamber, such as based on the settings of the flow volume, flow direction, temperature, and baffles, as discussed throughout.

A fritted, i.e., finely porous, mesh, filter or the like **330** may be used to atomize the incoming polymer from nozzle **302**. The fritted mesh may be used in conjunction with a high gas flow rate and high molten polymer pressure. Of course, in such cases, the skilled artisan will appreciate that care need be taken to reduce the stringing/oozing that may occur.

The embodiments may additionally provide advantageous atomization mechanisms **340** associated with nozzle **302** for spray **304**. By way of example, a rotating blade or blades may atomize the polymer. Of course, a single blade may not have the energy required to fully atomize a high molecular weight polymer. However the use of a multi blade design, which multiple blades may or may not counter rotate, and which may or may not have some significant distance between the multiple blades, may remedy any issues experienced in a single blade embodiment.

Additionally in regard to the atomization nozzle, the embodiments may make use of a gas flow in/from the center of the atomization nozzle, as distinct from gas flow provided only along angles at the sides of the chamber. For example, molten polymer may exit a ring design of the nozzle, with a gas flow provided in the center of the nozzle exit ring. This gas flow may be in addition to gas flow along the sides of the chamber.

Now also with reference to FIG. 5, crystallization of the particle to obtain particular characteristics requires controlled heating, cooling, and thus flow of the particle, i.e., control in the changes of particle temperature over time. Therefore, the value in increasing/controlling the particle residence time in the chamber **300** is the enhanced control over the rate of the liquid  $\square$  solid phase change that a molten polymer goes through. This increased residence time may be provided by a flow direction such that the particles from atomizer nozzle **302** are suspended in a suspension **404**.

If the polymer is given more time, or more controlled time, to orient its chains into the desired crystallinity, the material formed will perform better in powder bed fusion additive manufacturing processes, by way of non-limiting example. Moreover, by using either a free fall or gas suspension chamber system, or a combination thereof, the particle will necessarily reduce its surface area, i.e., it will become more spherical. That is, the orientation of the chamber **300** or atomizer **302** is not critical in the embodiments, so long as the requisite chamber time, temperature and flow for each particle are maintained.

Gas flow **306**, **308** may be generated anywhere in, on or along the chamber, such as in order to control the residence time, such as in suspension **404**, and classification/collection **314**, of the particles. For example, gas control **306** from the bottom of the chamber uses the differential density of melt and the solid polymer to actively classify material. By way of particular non-limiting example, using the combination of a fluidized bed and/or suspension and/or a gravitational air classifier, the particles remain in a suspension of gas until the density of the molten particle increases enough (i.e., until it has cooled sufficiently) to fall from the suspension as solid particle **406** to be collected **314**. However, finer particles **408** may be too light, and may thus be carried away for collection, such as by an alternative gas flow **308**. The gas inlets discussed herein may periodically pulse with more pressure/flow, thereby clearing the chamber of fine or solid desired particles, such as through an exit located above the suspension zone for collection for fine particles, or at the base of chamber for desired particles.

The aforementioned fluidized bed/suspension additionally may be used to increase residence time in the chamber.

## 11

For example, a designed counter flow, such as an upward suspension flow, may be provided throughout chamber. Accordingly, this suspension of particles may allow for the particles to be held at certain temperatures for a desired residence time, and then moved along through temperature bands at a controlled cooling rate throughout the chamber.

FIG. 6 shows a vessel **601** that can be utilized for forming polymer microspheres. Polymer pieces, such as pellets, are heated to a temperature that allows them to flow and be forced through an atomizer **602**. A polymer extruder may provide melted polymer to atomizer **602**. The polymer extruder may be a twin-screw extruder and may be controlled to achieve a set point pressure in the atomizer **602**.

When using a polymer extruder to feed the atomizer **602**, a homopolymer may be extruded into the atomizer **602**. A benefit of using a polymer extruder to feed the atomizer **602** is that this configuration allows additives to easily be added to the polymer or polymers that are being extruded. In this way, polymer(s) and additive(s) can be melted, mixed, atomized, and solidified in one system. This system could be used to produce polymer spheres with additives encapsulated inside of them. Additives may comprise reinforcements and fillers such as fibers. Additives may comprise carbon fibers, glass fibers, inorganic reinforcements such as talc, glass beads, pigments, flame retardants, antioxidants, heat stabilizers, nucleating agents, and/or impact modifiers.

Additives could be added at the extruder hopper or just prior to the atomization nozzle **602**. The atomizer may force polymer through small openings, thereby causing them to exit the atomizer as small particles. To atomize the polymer, a fritted mesh or filter could be used in conjunction with a high gas flow rate and high molten polymer pressure. When using a fritted mesh or filter, pressurized polymer may be pushed through a very fine mesh and atomized polymer may exit the fritted mesh or filter.

Rotating blades are another option for polymer atomization. One or more rotating blades may be used to atomize the polymer. When multiple rotating blades are used, the blades may be spaced at a fixed distance apart from each other. The blades may rotate in the same direction as the nearest blade(s) or they may counter-rotate. A rotating disc, such as those used in glass fiber manufacturing, may be used to atomize polymer.

Further, the atomizer may include adding a gas stream, such as nitrogen, either into the nozzle to mix with the polymer before the polymer exits the nozzle or the gas stream may be added separately and nearby the nozzle exit to create a zone of low pressure to pull small polymer droplets into the vessel. Gas flow may also be added in the center of a polymer stream that is exiting the nozzle so that a gas flow is present at a center of the polymer stream leaving the nozzle and a ring of polymer is present around the center gas flow leaving the nozzle.

To obtain molten polymer beads, a large number of tubular nozzles of a targeted length and diameter could be used. The end/tip of the tubes could be designed to retain a particle until the particle is of sufficient mass to overcome the capillary forces holding the particle to the tube. At this point, the particle would fall free of the tube. Tubes could be spaced apart to avoid collision.

The vessel may introduce a gas, such as nitrogen, tangentially into the vessel **601** to introduce a swirling flow around the perimeter of the vessel **601**. The swirling flow could act to classify the falling polymer pellets. Larger and/or heavier polymer droplets would be pulled further to the outer perimeter and smaller and/or lighter polymer droplets would tend to stay towards the center of the vessel

## 12

**101**, per Stokes Law, where  $V$ =settling velocity of the sphere, towards to outer perimeter (m/s),  $d$ =particle diameter (m),  $\rho_1$ =density of the particle ( $\text{kg}/\text{m}^3$ ),  $\rho_2$ =density of the medium ( $\text{kg}/\text{m}^3$ ),  $r$ =radial distance from the center of rotation (m),  $\omega$ =angular speed of rotation (revolutions per minute), and  $\eta$ =viscosity of the medium ( $\text{kg}/(\text{m}^*\text{s})$ ):

$$V = \frac{d^2(\rho_1 - \rho_2)r\omega^2}{18\eta}$$

The outward force acting on the polymer particles as they rotate about the center axis of the vessel is a function of the particle's mass, the particles tangential velocity, and the radial distance from the center of vessel. This relationship is shown in the equation below.

$$F_c = \frac{(mv^2)}{r}$$

As shown in FIG. 6, various collection trays **603a**, **603b**, and **603c** can be located at varying radial distances. Because there will be a distribution of particles, where heavier/larger particles are more concentrated at the outer perimeter of the vessel and lighter/smaller particles are more concentrated towards the center of the vessel, positioning collection trays **603a**, **603b**, and **603c** as shown in FIG. 6 would allow the collection of particles according to particle size/weight. Alternatively, the vessel **601** in FIG. 6 could be conically shaped and polymer particles could be removed at various heights. This conical arrangement is also expected to separate particles by mass and/or size. The topmost collection ports of the conical vessel would be more concentrated in heavier/larger polymer particles and the lowermost collection ports of the conical vessel would be more concentrated in lighter/smaller particles.

FIG. 6 also shows a separation device **604**. A vacuum would pull gas and particles through the separation device **604** to create a flow in the direction shown by arrows in FIG. 6. The separation device may be a cyclone. Clean gas, with a lower concentration of particles exits the separation device at **605** and solids particles exit the separation device **604** at **606**. Separation device **604** may include an air lock **607** and a collection vessel **608**. As shown in FIG. 6, a slip stream **609** of the gas being pulled through the bottom of the vessel may be directed to the top of the vessel to introduce a swirling, rotation flow inside of the vessel.

The time and temperature that polymer particles are exposed to will affect their material properties, specifically because the amount of crystallinity in the polymer particles will vary as a function of cooling time and cooling temperature(s). By controlling the time that it takes for liquid polymer to change phase into a solid, the polymer's crystallinity can be controlled. If a polymer is given more time to orient its chains, it will become more crystalline. A certain degree of polymer crystallinity is desirable when using polymer in a powder bed fusion additive manufacturing process. In order to control the crystallinity in the solidified polymer microspheres, the temperature and/or residence time of the polymer microspheres in the vessel may be controlled. Temperature control may be accomplished by controlling the gas temperature in slip stream **609** and/or temperature control may be accomplished by heating or cooling the vessel **601**. Vessel temperature control may be



## 13

accomplished by a heated and/or cooled jacketed vessel. Alternatively, electric heaters may be used to heat the vessel. Electric heaters may be located on the outer perimeter of the vessel **601** or immersed within the vessel **601**. Multiple heated and/or cooled sections may be used to provide zones of different temperature.

A flow of gas (not shown) may be used to increase the residence time that particles spend inside of the vessel. The gas that is used to increase residence time would flow in the opposite direction that microspheres are travelling. For example, if microspheres are falling from the top of the vessel, gas would flow in an upward direction to increase the amount of time that it takes for microspheres to travel from the atomizer to the bottom of the vessel. By using a free fall or gas suspension (or combination thereof), polymer particles will reduce their surface area and become more spherical.

Further, baffles (represented as **610a**, **610b**, and **610c** in FIG. 6, but may include any number of baffles) may be used to increase microsphere residence time in the vessel. Baffles may be attached to the perimeter sides of the vessel and may be straight or curved. Baffles may be slanted upward (from the vessel wall to the center of the vessel), downward (from the vessel wall to the center of the vessel), or horizontal (from the vessel wall to the center of the vessel). Baffles may be made of steel or another material. Baffles may comprise rings, blades, or scoops and may allow for a breakup in the gas flow path to control temperature, capture material, and/or to increase residence time.

Once the print particles **12** are created, they may be printed using an AM process **14**, as illustrated in FIG. 7. The AM printing process **14** may use a laser **504**, and thus may be, for example, a dry blend SLS print. In such an embodiment, the particles **12** may also be dry blended with additives **130**, and the blended powder **120** may then be printed to a form **16**, layer-by-layer, using an SLS printer as discussed above.

Similarly, wherein the AM printing process is a powder bed fusion process, a single thin layer, such as an approximately 0.1 mm thick layer, of compound print material **12** in powder **120**, such as may be created using the methodologies discussed above, may be spread over a build platform. The laser **504** may then fuse the first layer, or first cross section, of the model. Thereafter, a new layer of the compound print material **12** in powder **120** is spread across the previous layer, such as using a roller. Further layers or cross sections may then be added until the entire model is created. Loose, unfused powder print material may remain in position throughout, but may be removed during post processing, by way of non-limiting example.

Also in a manner similar to that of FIG. 7, binder jetting may use a “binder”, rather than or in addition to a laser **504**. In such an embodiment, the powder print material **12** may be spread over the build platform, such as using a roller. A print head may then deposit a binder adhesive on top of the powder where required. The build platform may then be lowered by the model’s layer thickness. Another layer of powder may then be spread over the previous layer, and the object is formed where the powder is bound to the liquid, layer-by-layer.

A multijet fusion methodology may operate in a manner similar to the powder bed fusion, but may employ heat lamps or similar technologies, rather than a laser. Likewise, in a directed energy deposition AM method, an axis arm with a nozzle may move around a fixed object, and the print material **12** may be deposited from the nozzle onto existing surfaces of the object. The material may be provided, by way

## 14

of example, in wire/filament or powder form, and may be melted for dispersal from the nozzle using a laser, electron beam or plasma arc.

Various other methodologies may provide a suitable format for the print particles **12** to enable or improve printing using AM technologies. For example, a sheet may be made from the powder print materials, or a filament may be provided. Moreover, additives may be provided in the print material to enable or improve printing and/or object formation. Additive materials may include, but are not limited to, hollow metal oxide beads or hollow polymeric spheres.

In each such embodiment, parameters of interest for the print material **12** may include parameters such as moisture level, heat of build chamber, heater power and temperature emitted, time of heat exposure, time between layers, feed rate, feed temperature, pressure and vacuum, gas flow rate, and the like. In short, the core print particle **12** or an aspect thereof may melt, such as upon exposure to a laser, and thus fuses to nearby particles during an AM process. As such, the print material **12** should be heated during the selected AM print process **14** past its respective melting point. Under such circumstances, the respective polymer chains may suitably bond with those of the particle next to each particle, to form output **16**. The selected AM print process **14** may allow that bond to cool, and thus the cooled particle chains form a solid layer in output **16**. Of course, each print material **12** may also be subjected to additives **130** as discussed throughout, such as may aid with melting or flow during melting, with impact resistance, or with heat stabilization, by way of example, dependent upon the AM process selected.

As such, an output part **16** processed as described herein may provide correlated characteristics that are indicative of, and/or correlated to, the input material **12**, and which occur pursuant to application of AM process **14**, as described herein throughout. Such correlated characteristics may be measured, by way of non-limiting example, by heat-flowing a sample of the input **12** and/or the output **16**, and then measuring thermal characteristics of the heat-flowed sample, such as  $T_m$ ,  $T_g$ ,  $T_{cryst}$ , heat of fusion, and the like. Likewise, infrared microscopy may allow for identification of the wavelengths of the corresponding chemical structures of the input material and/or the output object layers. Yet further, a thermogravimetric or similar analysis may be performed on a sample of the input material **12** or printed output **16**, and this analysis may further include measurement of the composition of decomposition gases as the sample degrades, by way of example.

Of course, in view of the aforementioned prospective correlation of characteristics between an input print material **12** and a printed output object **16**, the correlated characteristics of output object **16** may vary dependently not only in accordance with the input material **12**, but additionally based upon the process **14** employed to print the print material **12** into the output object **16**. Accordingly, one or more computing programs/algorithms **1190**, such as may comprise one or more AMF files; one or more input material **12** and/or additive **130** choices; one or more process **14** choices and/or one or more process characteristics choices; and/or one or more output **16** shape, size, and/or characteristic choices, may be executed by a computing system **1100**. This execution may occur, for example, pursuant to an instruction to a GUI, such as to provide a particular correlation as between an input material **12** and/or additives **130** and a specific output object characteristic, and/or to use a particular available input material **12**, using an available

process **14**, to target the ultimate production of a particular output object **16**. This is illustrated with particularity in FIG. **8**.

More particularly, FIG. **8** depicts an exemplary computing system **1100** for use in association with the herein described systems and methods. Computing system **1100** is capable of executing software, such as an operating system (OS) and/or one or more computing applications/algorithms **1190**, such as applications applying the algorithms discussed herein, and may execute such applications **1190** using data, such as materials and process-related data, which may be stored **1115** locally or remotely.

More particularly, the operation of an exemplary computing system **1100** is controlled primarily by computer readable instructions, such as instructions stored in a computer readable storage medium, such as hard disk drive (HDD) **1115**, optical disk (not shown) such as a CD or DVD, solid state drive (not shown) such as a USB “thumb drive,” or the like. Such instructions may be executed within central processing unit (CPU) **1110** to cause computing system **1100** to perform the operations discussed throughout. In many known computer servers, workstations, personal computers, and the like, CPU **1110** is implemented in an integrated circuit called a processor.

It is appreciated that, although exemplary computing system **1100** is shown to comprise a single CPU **1110**, such description is merely illustrative, as computing system **1100** may comprise a plurality of CPUs **1110**. Additionally, computing system **1100** may exploit the resources of remote CPUs (not shown), for example, through communications network **1170** or some other data communications means.

In operation, CPU **1110** fetches, decodes, and executes instructions from a computer readable storage medium, such as HDD **1115**. Such instructions may be included in software, such as an operating system (OS), executable programs such as the aforementioned correlation applications, and the like. Information, such as computer instructions and other computer readable data, is transferred between components of computing system **1100** via the system’s main data-transfer path. The main data-transfer path may use a system bus architecture **1105**, although other computer architectures (not shown) can be used, such as architectures using serializers and deserializers and crossbar switches to communicate data between devices over serial communication paths. System bus **1105** may include data lines for sending data, address lines for sending addresses, and control lines for sending interrupts and for operating the system bus. Some busses provide bus arbitration that regulates access to the bus by extension cards, controllers, and CPU **1110**.

Memory devices coupled to system bus **1105** may include random access memory (RAM) **1125** and/or read only memory (ROM) **1130**. Such memories include circuitry that allows information to be stored and retrieved. ROMs **1130** generally contain stored data that cannot be modified. Data stored in RAM **1125** can be read or changed by CPU **1110** or other hardware devices. Access to RAM **1125** and/or ROM **1130** may be controlled by memory controller **1120**. Memory controller **1120** may provide an address translation function that translates virtual addresses into physical addresses as instructions are executed. Memory controller **1120** may also provide a memory protection function that isolates processes within the system and isolates system processes from user processes. Thus, a program running in user mode may normally access only memory mapped by its own process virtual address space; in such instances, the

program cannot access memory within another process’ virtual address space unless memory sharing between the processes has been set up.

In addition, computing system **1100** may contain peripheral communications bus **1135**, which is responsible for communicating instructions from CPU **1110** to, and/or receiving data from, peripherals, such as peripherals **1140**, **1145**, and **1150**, which may include printers, keyboards, and/or the sensors discussed herein throughout. An example of a peripheral bus is the Peripheral Component Interconnect (PCI) bus.

Display **1160**, which is controlled by display controller **1155**, may be used to display visual output and/or other presentations generated by or at the request of computing system **1100**, such as in the form of a GUI, responsive to operation of the aforementioned computing program(s). Such visual output may include text, graphics, animated graphics, and/or video, for example. Display **1160** may be implemented with a CRT-based video display, an LCD or LED-based display, a gas plasma-based flat-panel display, a touch-panel display, or the like. Display controller **1155** includes electronic components required to generate a video signal that is sent to display **1160**.

Further, computing system **1100** may contain network adapter **1165** which may be used to couple computing system **1100** to external communication network **1170**, which may include or provide access to the Internet, an intranet, an extranet, or the like. Communications network **1170** may provide user access for computing system **1100** with means of communicating and transferring software and information electronically. Additionally, communications network **1170** may provide for distributed processing, which involves several computers and the sharing of workloads or cooperative efforts in performing a task. It is appreciated that the network connections shown are exemplary and other means of establishing communications links between computing system **1100** and remote users may be used.

Network adaptor **1165** may communicate to and from network **1170** using any available wired or wireless technologies. Such technologies may include, by way of non-limiting example, cellular, Wi-Fi, Bluetooth, infrared, or the like.

It is appreciated that exemplary computing system **1100** is merely illustrative of a computing environment in which the herein described systems and methods may operate, and does not limit the implementation of the herein described systems and methods in computing environments having differing components and configurations. That is to say, the inventive concepts described herein may be implemented in various computing environments using various components and configurations.

In the foregoing detailed description, it may be that various features are grouped together in individual embodiments for the purpose of brevity in the disclosure. This method of disclosure is not to be interpreted as reflecting an intention that any subsequently claimed embodiments require more features than are expressly recited.

Further, the descriptions of the disclosure are provided to enable any person skilled in the art to make or use the disclosed embodiments. Various modifications to the disclosure will be readily apparent to those skilled in the art, and the generic principles defined herein may be applied to other variations without departing from the spirit or scope of the disclosure. Thus, the disclosure is not intended to be limited to the examples and designs described herein, but rather is to be accorded the widest scope consistent with the principles and novel features disclosed herein.

What is claimed is:

1. An apparatus for forming print material particles for additive manufacturing (AM) printing, comprising:
  - a melt chamber comprising a polymer melt;
  - an atomizer that atomizes the polymer melt and that distributes the atomized polymer melt;
  - a fall chamber comprising a plurality of zones into which the atomized polymer melt is distributed;
  - one or more vane baffles suitable to control a flow of the distribution of the atomized polymer melt, including temporary suspension thereof in the fall chamber, after entry to the fall chamber, wherein each of the vane baffles is affixed to a wall of the fall chamber;
  - a series of heating and cooling elements selectively varied along a vertical axis of the fall chamber and along the walls thereof to provide the plurality of zones and which in conjunction with the one or more vane baffles, further control the flow of the distribution of, and that thereby provide a varied series of modification horizons to, the atomized polymer melt along the vertical axis as the atomized polymer melt falls along the vertical axis;
  - a first collector to receive the print material particles formed of the atomized polymer melt after falling through the plurality of zones; and
  - a second collector to receive discarded particles not suitable as the print material particles.
2. The apparatus of claim 1, wherein the atomizer comprises a high-pressure non-reactive gas jet.
3. The apparatus of claim 2, wherein the non-reactive gas comprises nitrogen gas.
4. The apparatus of claim 2, wherein the high pressure comprises a about 1050 psi.
5. The apparatus of claim 1, wherein the print material particles range in size from about 0.1  $\mu\text{m}$  to about 200  $\mu\text{m}$ .
6. The apparatus of claim 1, wherein the melt is polyethylene-based.

7. The apparatus of claim 1, wherein the collected print material particles comprise a powder having a size of about 0.1-200  $\mu\text{m}$ .
8. The apparatus of claim 1, wherein the polymer melt comprises about a 3.175-mm melt stream size.
9. The apparatus of claim 1, further comprising a feeder to the melt chamber, wherein the polymer in the feeder comprises pellets.
10. The apparatus of claim 1, wherein the melt chamber comprises a heater to form the polymer melt.
11. The apparatus of claim 1, further comprising at least two gas inlets, each to further control at least a flow and a temperature in each of the plurality of zones.
12. The apparatus of claim 1, wherein the plurality of zones comprise successive cooling zones.
13. The apparatus of claim 1, wherein the plurality of zones comprise alternating heating and cooling zones.
14. The apparatus of claim 1, wherein the polymer melt comprises non-polymer additives.
15. The apparatus of claim 14, wherein the additives comprise at least one of an alloy and a reinforcement.
16. The apparatus of claim 1, wherein the atomizer comprises one of a centrifugal, a chopping disc, and a gas atomization.
17. The apparatus of claim 1, further comprising a gas inlet.
18. The apparatus of claim 17, wherein the gas inlet is affixed to the wall of the fall chamber.
19. The apparatus of claim 17, wherein the gas inlet is affixed to a bottom of the fall chamber to retard the fall of the atomized polymer melt.
20. The apparatus of claim 1, wherein the atomizer comprises at least one of a twin-screw extruder, a fritted mesh, or a rotating body, wherein the rotating body includes at least one of a rotating blade or a rotating disc.

\* \* \* \* \*