



US 20010051433A1

(19) **United States**

(12) **Patent Application Publication**

Francis et al.

(10) **Pub. No.: US 2001/0051433 A1**

(43) **Pub. Date: Dec. 13, 2001**

(54) **USE OF CSOH IN A DIELECTRIC CMP SLURRY**

(*) Notice: This is a publication of a continued prosecution application (CPA) filed under 37 CFR 1.53(d).

(76) Inventors: **Alicia F. Francis**, Naperville, IL (US);
Brian L. Mueller, Aurora, IL (US);
James A. Dirksen, Oswego, IL (US);
Paul M. Feeney, Aurora, IL (US)

(21) Appl. No.: **09/428,965**

(22) Filed: **Nov. 4, 1999**

Publication Classification

(51) Int. Cl.⁷ **H01L 21/302; H01L 21/461**


(52) U.S. Cl. **438/691**

(57) **ABSTRACT**

Chemical mechanical polishing compositions including an abrasive and cesium hydroxide and methods for polishing dielectric layers associated with integrated circuits using cesium hydroxide containing polishing compositions

Correspondence Address:

**PHYLLIS T. TURNER-BRIM, ESQ., LAW
DEPARTMENT
CABOT MICROELECTRONICS
CORPORATION
870 NORTH COMMONS DRIVE
AURORA, IL 60504 (US)**






Figure 1




Figure 2




Figure 5




Figure 6

USE OF CSOH IN A DIELECTRIC CMP SLURRY

BACKGROUND OF THE INVENTION

[0001] (1) Field of the Invention

[0002] This invention concerns chemical mechanical polishing compositions including an abrasive and cesium hydroxide. This invention also concerns methods for polishing dielectric layers associated with integrated circuits using cesium hydroxide containing polishing compositions.

[0003] (2) Description of the Art

[0004] Integrated circuits are made up of millions of active devices formed in or on a silicon substrate. The active devices, which are initially isolated from one another, are interconnected to form functional circuits and components. The devices are interconnected through the use of multilevel interconnections. Interconnection structures normally have a first layer of metallization, an interconnection layer, a second level of metallization, and sometimes a third and subsequent level of metallization. Interlevel dielectrics (ILDs) such as doped and undoped silicon dioxide (SiO_2), or low-K dielectrics tantalum nitride are used to electrically isolate the different levels of metallization in a silicon substrate or well.

[0005] In typical semiconductor manufacturing processes, metallized vias, metallized layer and interlevel dielectric layers are built-up to create an integrated circuit. As the layers are being built-up, the excess materials are removed and the substrate surfaces are planarized by using chemical mechanical polishing (CMP) techniques. In a typical chemical mechanical polishing process, the substrate is placed in direct contact with a rotating polishing pad. A carrier applies pressure against the backside of the substrate. During the polishing process, the pad and table are rotated while a downward force is maintained against the substrate back. An abrasive and chemically reactive solution is applied to the pad during polishing. The slurry initiates the polishing process by chemically reacting with the film being polished. The polishing process is facilitated by the rotational movement of the pad relative to the substrate as slurry is provided to the wafer/pad interface. Polishing is continued in this manner until the desired film on the insulator is removed.

[0006] The polishing composition ingredients are an important factor in the success of the CMP step. By carefully selecting ingredients, the polishing composition can be tailored to provide effective polishing to the selected layer at desired polishing rates while minimizing surface imperfections, defects and corrosion and erosion of adjacent layers. During the manufacture of integrated circuits, dielectric layers, typically including silicon dioxide are applied to the circuit. Once applied, the dielectric layer is generally non-planar and must be polished using a polishing composition to give a planar dielectric surface. It is important that the chosen polishing composition be capable of producing a planarized dielectric surface with few defects. Furthermore, it is important that the polishing composition chosen be capable of polishing the dielectric layer efficiently and repeatedly. Current ILD slurries are typically stabilized abrasive slurries including about 10-30 wt % abrasives. The stabilizing ion is typically potassium or ammonia where slurries typically have a pH greater than 8. The shortcomings of potassium slurries are ionic contamination from the

potassium where the contaminating ions become mobile ions and will detrimentally impact device reliability by migrating to the gate area 20 and lowering the threshold voltage of the transistors. In addition, there is a level of defectivity that is characteristic of silica dispersed with potassium.

[0007] Ammonia slurries solve the mobile ion problem associated with potassium stabilized slurries. However, ammonia has a strong odor. In addition, ammonia slurries planarize less effectively, polish with a high level of defectivity and polish with low rates compared to potassium slurries.

[0008] As a result, there remains a need for improved polishing compositions that are capable of polishing dielectric layers efficiently to give polished dielectric layers that are essentially planar and that exhibit few defects.

SUMMARY OF THE INVENTION

[0009] In one embodiment, this invention is a chemical mechanical polishing composition comprising fumed silica and from about 0.01 to about 5.0 wt % of at least one Cs^+ basic salt.

[0010] In another embodiment, this invention is a chemical mechanical polishing composition comprising water, from about 1 to about 50 wt % fumed silica, and from about 0.1 to about 2.0 wt % CsOH . The polishing composition planarizes a silicon containing substrate with an open field efficiency of at least 50% and with an array field efficiency of at least 85 %.

[0011] In yet another embodiment, this invention is a chemical mechanical polishing composition capable of polishing integrated circuits having gate widths less than about 0.25 microns comprising from about 1 to about 50 wt % of a metal oxide abrasive and from about 0.01 to about 5.0 wt % Cs^+ basic salt.

[0012] In still another embodiment, this invention is a method for planarizing an insulating layer with a polishing composition of this invention. The polishing is achieved by preparing a polishing composition comprising water and CsOH . The polishing composition is then applied to a surface of the substrate being planarized or to the polishing pad. The polishing pad is brought into contact with the surface of the silicon containing substrate layer being planarized, and the pad is moved in relation to the silicon containing substrate surface being planarized. An abrasive is used in conjunction with the polishing composition to facilitate polishing. The abrasive may be associated with the polishing pad or the abrasive may be added to the polishing composition to give a chemical mechanical polishing slurry before the slurry is applied to the substrate or to the polishing pad.

DESCRIPTION OF THE FIGURES

[0013] FIG. 1 is a simplified side-cutaway view of a portion of a semiconductor wafer that suitable for planarizing using the compositions and methods of this invention;

[0014] FIG. 2 illustrates the wafer shown in FIG. 1 after polishing;

[0015] FIG. 3 is a simplified side-cutaway view of a portion of a semiconductor wafer suitable for shallow trench isolation planarization using the compositions and methods of this invention;

[0016] FIG. 4 is the wafer of FIG. 3 including defects that could result due to inefficient planarization;

[0017] FIG. 5 is a plot of polish time versus step height for CsOH (A & B), KOH, (C) and NH₄OH (D) slurries tested according to the method described in Example 2. The term "polish time" in the plot refers to the time, in seconds, that the substrate is being polished. The term "step height" in the plot refers to the distance from the high points on the topography to the low points during the fabrication of integrated circuits. As devices are built a surface topography is produced and perpetuated through subsequent thin-film depositions. Step height is usually measured in Angstroms; and

[0018] FIG. 6 is a plot of delta field versus step height for slurries tested according to the method of described in Example 2.

DESCRIPTION OF THE CURRENT EMBODIMENT

[0019] The present invention relates to chemical mechanical polishing compositions including an abrasive and at least one Cs⁺ basic salt such as cesium hydroxide. This invention also concerns methods for polishing dielectric layers associated with integrated circuits using Cs⁺ basic salt containing polishing compositions.

[0020] Basic cesium salt stabilized slurries show an unexpected performance enhancement as compared to ammonia and potassium hydroxide stabilized slurries. Cesium ions have lower mobility than potassium and sodium ions. Furthermore, cesium ion containing polishing compositions polish at higher rates than ammonia slurries and do not have a foul odor like ammonia stabilizes slurries. Also, cesium ion containing polishing compositions polish with lower defectivity as measured as light point defects, and most surprisingly, with improved planarization efficiency in comparison to potassium, sodium and ammonia stabilized slurries.

[0021] An important parameter to determine if a semiconductor wafer has been sufficiently planarized is the number of defects remaining in the treated wafer surface following planarization. One type of defect is known in the industry as a "pit" or an undesirable depression in the wafer surface. Another defect is known in the industry as a "dig" or "skid" and represents a series of undesirable coarse scratches that are close together. Another type of defect is a residual slurry particle that cannot be clean off the substrate. The number and type of defects can be determined using art-recognized techniques, including laser light scattering. In general, it is desired to minimize the number of defects.

[0022] The polishing compositions of this invention include at least one Cs⁺ basic salt. Examples of Cs⁺ basic salts include but are not limited to cesium formate, cesium acetate, cesium hydroxide, cesium carbonate, cesium bicarbonates, cesium fluoride, cesium chloride, cesium iodide, and mixtures thereof. A preferred Cs⁺ basic salt is cesium hydroxide (CsOH).

[0023] Basic cesium salts such as cesium hydroxide is an important ingredient of the polishing compositions of this invention because cesium acts as a silica stabilizer. Furthermore, the cesium ions do not penetrate into the dielectric layer to the same depth as ammonium or potassium ions

resulting in a dielectric layer with few contaminants and with uniform dielectric properties. The overall result is an unexpected improvement is ILD polishing efficiency, defectivity, and an improvement in dielectric layer purity.

[0024] The polishing compositions of this invention are aqueous compositions of from about 0.01 to about 5.0 wt % basic cesium salt. Preferably, the basic cesium salt will be present in aqueous polishing compositions of this invention in an amount ranging from about 0.1 to about 2.0 wt %.

[0025] For best results, the pH of the polishing composition of this invention should be greater than about 7.0 and preferably greater than about 9.0.

[0026] The polishing compositions of this invention may be combined with at least one abrasive prior to using the composition to polish a substrate layer such as an ILD layer. The abrasive may be added to the aqueous polishing composition to form an aqueous chemical mechanical polishing slurry. Alternatively, the abrasive may be incorporated into a polishing pad during or following the manufacture of the polishing pad. When the abrasive is associated with the polishing pad, the aqueous polishing composition may be applied to a substrate being polished or it may be applied directly to the polishing pad such that the abrasive in the polishing pad and the aqueous polishing composition work in unison to polish the substrate.

[0027] The abrasive used in conjunction with the chemical mechanical polishing compositions of this invention are typically metal oxide abrasives. Useful metal oxide abrasives may be selected from the group including alumina, titania, zirconia, germania, silica, ceria and mixtures thereof. The compositions of this invention are preferably used in conjunction with a fumed abrasive.

[0028] The fumed abrasive can be any suitable fumed (pyrogenic) metal oxide. Suitable fumed metal oxides include, for example, fumed alumina, fumed silica, fumed titania, fumed ceria, fumed zirconia, and fumed magnesia. Preferably, the fumed metal oxide of the composition of the present invention is fumed silica.

[0029] The fumed abrasive and preferably fumed silica may be combined with a second abrasive particles are selected from metal oxides including alumina, silica, titania, ceria, zirconia, and magnesia. Also suitable for use in the composition are colloidal abrasive particles (condensation-polymerized abrasives) prepared in accordance with U.S. Pat. No. 5,230,833 (Romberger et al.) and various commercially available products, such as the Akzo-Nobel Bindzil 50/80 product and the Nalco 1050, 2327, and 2329 products as well as other similar products. Preferably, the second abrasive useful in the compositions and methods of this invention is colloidal silica (condensation-polymerized silica) typically prepared by condensing Si(OH)₄ to form colloidal silica particles.

[0030] Chemical mechanical polishing slurries of this invention will generally include from about 1.0 to about 50.0 weight percent or more of at least one metal oxide abrasive. It is more preferred, however, that the chemical mechanical polishing slurries of this invention include from about 1.0 to about 30.0 weight percent metal oxide abrasive, and most preferably from about 5.0 to about 25.0 wt % metal oxide abrasive. When a mixture of abrasives are used, it is preferred that the abrasives used in the compositions of this

invention include from about 25 to about 60% fumed abrasive and from about 40 to about 75% colloidal abrasive with fumed silica and colloidal silica being preferred.

[0031] Other well known additives may be incorporated alone or in combination into the polishing composition of this invention. A non-inclusive list of optional additives includes inorganic acids, organic acids, surfactants, alkyl ammonium salts or hydroxides, and dispersing agents, additional abrasives, oxidizing agents, complexing agents, film forming agents and so forth.

[0032] Dielectric layers such as silicon dioxide, and tantalum nitride are polished with the above described compositions by subjecting the surface to mechanical rubbing (polishing) in the presence of the composition. The rubbing effects mechanical smoothing or wear of the surface which is aided by abrasives in the composition or in the polishing pad, and when present, promoted by the components added to the abrasive to give a chemical mechanical polishing slurry which chemically attacks and dissolves the components comprising the dielectric layer. Polishing may thus be achieved solely by a mechanical mechanism, or by a combination of chemical and mechanical mechanisms.

[0033] The mechanical rubbing or polishing is conveniently effected by contacting the dielectric layer with a polishing pad under a predetermined compressive force with relative motion between the pad and the surface. The resulting dynamic friction between the pad and the surface causes the desired wear and smoothing of the disk surface. The relative motion is preferably achieved through rotation of either or both the disk surface and the pad. Commercially available polishing pads that are used to polish glass or wafers in the electronics industry may be used. These pads are typically composed of a microporous polymer such as polyurethane foam, or sintered urethane resin optionally backed with a substrate such as felt, latex filled felt, dense polyurethane, or latex.

[0034] As mentioned above, the abrasive may be incorporated into the chemical mechanical polishing composition to form a chemical mechanical polishing slurry or it may be incorporated into the polishing pad. In either instance, the chemical mechanical composition or slurry may be applied to the substrate surface being polished, to the polishing pad, or to both during the polishing process.

[0035] We have surprisingly found that the basic cesium salt containing polishing compositions of this invention are able to polish insulating layers, and in particular silicon dioxide dielectric layers at high efficiencies. Specifically, the polishing compositions of this invention are capable of polishing silicon containing substrate layer, and in particular, a silicon dioxide dielectric layer with an open field efficiency of at least 50%. In addition, the polishing compositions of this invention are capable of polishing silicon containing substrate layers, and in particular silicon dioxide containing dielectric layers with an array field efficiency of at least 85%.

[0036] We have also learned that the polishing compositions of this invention including basic cesium salts are the first polishing compositions that are known to be able to polishing integrated circuit layers with device geometries below about 0.25 microns. The term device geometries refers to average gate width.

[0037] FIG. 1 is a simplified view of a representative semiconductor wafer suitable for use with the composition and process according to the invention. For the sake of clarity, well-known features such as doped regions, active devices, epitaxial layers, carrier and field oxide layers. Previously deposited interconnect and previously deposited dielectric films have been omitted. Base 10 represents a semiconductor material such as, but not limited to single crystal silicon, gallium arsenide, and other semiconductor materials known in the art. Base 10 can also represent previous levels of interconnects or gate level dielectric layers.

[0038] On the top surface of base 10 are numerous discrete metal interconnect blocks 20 (e.g., metal conductor blocks). Metal interconnect blocks 20 can be made, for example, from aluminum, copper, aluminum copper alloy, tungsten, polysilicon and the like. Metal interconnect blocks 20 are made by typical methods known in the art. An insulating layer 30 is applied over top of metal interconnect blocks 20 and exposed base portions 10'. Insulating layer 30 is typically a metal oxide such as silicon dioxide, BPSG (borophosphosilicate glass), PSG (phosphosilicate glass), or combinations thereof. The resulting insulating layer 30 often has a top surface 32 that has topography and is not as "planar" and/or "uniform" as desired.

[0039] Before an additional layer of circuitry can be applied via and patterned photolithography, it is usually necessary to polish top surface 32 of the insulating layer 30 to achieve the desired degree of planarity and/or uniformity. The particular degree of planarity required will depend on many factors, including the individual wafer and the application for which it is intended, as well as the nature of any subsequent processing steps to which the wafer may be subjected. For the sake of simplicity, throughout the remainder of this application this process will be referred to as "planarization" or "polishing".

[0040] FIG. 2 illustrates the wafer shown in FIG. 1 after polishing or planarization. As a result of planarization, the polished surface 34 of insulating layer 30 should be sufficiently planar such that when the subsequent photolithography process is used to create a new circuit design, the critical dimension features can be resolved. It should be noted that within a die metal block or device (array) density will vary. Typically, the insulating layer sparse regions 36 will polish at a greater rate than the denser regions 38. In FIGS. 1 and 2 the sparse regions 36 are located above isolated metal block 40 and the denser regions over the densely packed metal interconnect blocks 20, 20', and 20". This planar non-uniformity with the die is referred to as WIDNU (within die non-uniformity).

[0041] The magnitude of this type of non-uniformity that can be tolerated in state of the art devices has decreased dramatically as device features (i.e., gate width) shrink below about 0.25 microns. One method of minimizing non-uniformity is to develop slurries and processes that will remove topography, including insulating layers very efficiently but with minimal field loss i.e., loss of insulating layer in sparse regions. Thus a slurry and polishing process that polishes sparse regions slowly will allow the more stringent WIDNU tolerances to be achieved. Two factors drive these more stringent WIDNU tolerances. Both factors are related to smaller and faster computer chips. The first

factor is depth of focus considerations during the photolithography step. As the devices shrink to 0.25 micron and below the stepper apertures are smaller making the depths of focus tolerance shallower and making insulating layer thickness uniformly via a global planarity more important. In addition, what limits the performance speed in some state-of-art chips is RC time delays in the backend interconnects. To control RC time delays and to maintain attainable clock speeds constant across the die, improved uniformity of the dielectric insulating layers is required.

[0042] Shallow trench isolation is another process in which an insulating layer is planarized. Shallow Trench Isolation (STI) is a process step in IC manufacturing to isolate transistors and other devices in integrated circuits. STI has an advantage over other isolation schemes due to improved minimum isolation space, latchup and junction capacitance. **FIG. 3** is a simplified view of a representative semiconductor wafer suitable for use with the composition and process according to the invention for direct STI polishing. In direct STI polishing, density effects are also important. Trenches are etched in semiconductor base **80** which is usually single crystal silicon. A hard mask silicon nitride **60** is deposited on the silicon prior to the etching of the trenches. The trenches are then filled with silicon dioxide insulating layer **70**. Once again the buildup includes denser and sparse areas. Unlike interlayer dielectric polishing the goal in STI is to polish until the silicon nitride is fully exposed and only silicon oxide remains in the trenches. In **FIG. 4** potential detrimental effects of WIDNU are shown where instead of “stopping” on the silicon nitride **60** the silicon nitride is removed to expose bare silicon **62**. This catastrophic failure usually occurs by the wear of the corner of the isolated feature **64**. One method to reduce the density effects in STI polishing are to use a slurry that has a high selectivity to the field area. Topography is removed at a high rate leaving a “planar” surface with a high degree of WIDNU. Subsequent polishing breaks through to the silicon nitride **90** uniformly and minimizes silicon nitride thinning.

[0043] As shown in the Examples below, the compositions and methods of this invention are useful for achieving the stringent planarization specifications of present day IC wafers.

EXAMPLE 1

[0044] This Example evaluated the ability of polishing compositions including various hydroxide compositions to polish silicon containing substrates at high efficiencies and low defectivity.

[0045] The polishing slurry compositions are reported in Table 1, below. Each polishing composition included CAB-O-SPERSE® SC-E fumed silica manufactured by Cabot Corporation. The slurries were stabilized with CsOH or KOH by adding a sufficient amount of each base to each slurry to increase the slurry pH to 10.8. The polishing compositions were used to planarize a test wafer. The test wafers were test patterns of a MIT designed mask where aluminum lines were created on a silicon substrate. The wafers had approximately 9000 angstroms of step height. The patterns were a 250 micron line pitch with systematically varying densities ranging from 100 to 8% where 100% means 100% stack area and 25% means that the lines are thick enough that 25 % is stack area and 75 % is field area.

[0046] Field measurements were taken from two areas of each wafer—the open field and the array field—and the measurements were used in the efficiency calculations. Array field measurements were taken in close proximity to the stack area. Because wide open (or sparse) areas are typically more problematic in real polishing we also evaluated slurry polishing efficiency by measuring the field in the largest open field area or the 8% area and calculating the open field efficiency from the measurement.

[0047] Each wafer was planarized using an IPEC 472 polishing machine. The wafers were polished using a down force of 7.5 psi, a back pressure of 3 psi, a platen speed of 37 rpm, a carrier speed of 24 rpm, and a slurry flow rate of 220 ml/min. The wafers were polished for 60, 90, 120 and 150 seconds. Polishing data (step height, stack thickness, field thickness) was collected for each wafer at the fixed polishing intervals (60, 90, 120, and 150 seconds).

[0048] There are two ways to measure step height. Step height can be measured directly by a Tencor P20 profilometer or step height can be measured by Tencor Surfscan UV 1050 and calculated by the following equation.

$$\text{Step height} = \text{initial step height} - \Delta \text{stack (initial stack thickness - polished stack thickness)} + \Delta \text{field (initial field thickness - polished field thickness)}$$

[0049] A plot was created for each slurry showing step height vs. time. The curve is fit to the data by interpolating the data along the fitted polishing curve to determine the time at which 95% planarization is achieved (i.e. step height is reduced to 450 Å). Planarization efficiency (sp) is calculated at each of the polishing intervals using the following formula:

$$\epsilon_p = 1 - \frac{\Delta \text{ field thickness}}{\Delta \text{ stack thickness}}$$

[0050] The calculated planarization efficiency was then plotted vs. time, and a curve is fit to the data. Taking the efficiency curve and identifying the time at which 95% planarization is achieved, the efficiency at the time required to reach 95% planarization is calculated.

[0051] The procedure for calculating the open field efficiency and the array field efficiency are the same. For open field efficiency, the field thickness measurement is at the 8% density region. For array field efficiency, the field thickness measurement is at the 52% density region.

[0052] The polishing results, array field efficiencies and open field efficiencies are reported in Table 1, below.

TABLE 1

Slurry Composition	Open Field Loss (Å)	Improvement In Field Loss (%)	Open Field Efficiency	Array Field Efficiency
10 wt % Silica; CsOH	4351	19% Reduction	55.5%	88.0%
13 wt % Silica; CsOH	4831	10% Reduction	52.7%	84.0%
12.5 wt % Silica; KOH	5374		49.7%	81.1%

[0053] The polishing results indicate that polishing compositions with cesium hydroxide polish silicon containing substrates at a much higher open field and array field efficiency than polishing compositions including potassium hydroxide. Specifically, polishing compositions including cesium hydroxide polish silicon containing substrates with a lower field loss, an improved open field efficiency and an improved array field efficiency.

[0054] Open field and array field efficiencies are dependent upon polishing parameters, polishing machine, and other consumables and slurries. For purposes of this application, the term “open field efficiency” and “array field efficiency” refer to the polishing efficiencies determined using an IPEC 472 polishing machine operating at the polishing parameters described above and calculated as described above.

EXAMPLE 2

[0055] In this Example, the planarization rate of polishing slurries including CsOH, KOH, and NH₄OH were evaluated. Each slurry tested included 12 wt % of CAB-O-SPERSE® SC-E fumed silica manufactured by Cabot Corp. The slurries were stabilized with CsOH, KOH, or NH₄OH by adding a sufficient amount of each base to each slurry to increase the slurry pH to 10.8. Each slurry was used to polish a wafer described in Example 1 according to the method described in Example 1.

[0056] The planarization results are represented graphically in FIGS. 5 and 6. According to FIG. 5, the planarization rate of CsOH and KOH slurries are superior to slurries including NH₄OH. According to FIG. 6, slurries including CsOH planarize silicon substrates more efficiently than slurries including KOH or NH₄OH. The greater efficiency is seen in the delta field improvement over the same step height for CsOH slurries in comparison to KOH and NH₄OH slurries.

EXAMPLE 3

[0057] This Example evaluated the planarization rate of commercially available polishing slurries. Two slurries were tested. The first slurry D7000, a 10.5 wt % fumed silica dispersion stabilized with KOH. The second slurry was Klebsol 30N50, an 30 wt % ammonia stabilized colloidal silica manufactured by Clariant. Each slurry was used to polish a wafer described in Example 1 according to the polishing method described in Example 1.

[0058] The planarization results are reported in Table 2, below.

TABLE 2

Slurry Composition	Open Field Loss (Å)	Improvement In Field Loss (%)	Open Field Efficiency	Array Field Efficiency
D7000	5015	12.4% reduction	52.4%	82.7%
30N50	5726		47.6	81.4%

What we claimed is:

1. A chemical mechanical polishing composition comprising a fumed abrasive and from about 0.01 to about 5.0 wt % of at least one Cs+ basic salt.

2. The chemical mechanical polishing composition of claim 1 wherein the fumed abrasive is fumed alumina.

3. The chemical mechanical polishing composition of claim 1 wherein the fumed abrasive is from about 1 to about 50 wt % fumed silica.

4. The chemical mechanical polishing composition of claim 1 including a second abrasive.

5. The chemical mechanical polishing composition of claim 4 wherein the second abrasive is colloidal silica.

6. The chemical mechanical polishing composition of claim 1 wherein the polishing composition planarizes a silicon containing substrate with an open field efficiency of at least 50%.

7. The chemical mechanical polishing composition of claim 1 wherein the polishing composition planarizes a silicon containing substrate with an array field efficiency of at least 85%.

8. The chemical mechanical polishing composition of claim 1 including from about 1 to about 20 wt % fumed silica.

9. The chemical mechanical polishing composition of claim 1 wherein the Cs + basic salt is CsOH.

10. The chemical mechanical polishing composition of claim 9 wherein the Cs+ basic salt is CsOH.

11. A chemical mechanical polishing composition comprising from about 1 to about 25 wt % fumed silica and from about 0.1 to about 2.0 wt % CsOH.

12. A chemical mechanical polishing composition capable of polishing integrated circuits with gate widths less than about 0.25 microns comprising from about 1 to about 50 wt % of a metal oxide abrasive and from about 0.01 to about 5.0 wt % Cs+ basic salt.

13. The chemical mechanical polishing composition of claim 12 wherein the Cs+ basic salt is CsOH.

14. A method for planarizing a silicon containing substrate with a polishing pad comprising the steps of:

- (a) preparing a polishing composition comprising water and at least one Cs+ basic salt;
- (b) applying the polishing composition to a surface of the substrate being planarized;
- (c) bringing the polishing pad into contact with the surface of the silicon containing substrate being planarized, and
- (d) moving the pad in relation to the silicon containing substrate surface being planarized wherein an abrasive is used in conjunction with the polishing composition.

15. The method of claim 14 wherein the abrasive is added to the chemical mechanical polishing composition before the chemical mechanical polishing composition is applied to the surface of the substrate being planarized.

16. The method of claim 14 wherein the abrasive is incorporated into the polishing pad.

17. The method of claim 14 wherein the polishing composition polishes the silicon containing dielectric layer with an open field efficiency of at least 50%.

18. The method of claim 14 wherein the polishing composition polishes the silicon containing dielectric layer with an array field efficiency of at least 85 %.

19. The method of claim 14 wherein the substrate is wafer including integrated circuits having gate widths less than about 0.25 microns.

20. The method of claim 14 wherein the silicon containing substrate layer is silicon dioxide.

21. The method of claim 14 wherein the polishing composition Cs+ basic salt is CsOH.

22. The method of claim 21 wherein the polishing composition includes from about 0.01 to about 5.0 wt % CsOH.

23. The method of claim 14 wherein the abrasive is fumed silica.

24. A method for planarizing an silicon dioxide dielectric layer of a wafer including integrated circuits having at least one gate width less than 0.25 microns using a polishing pad comprising the steps of:

- (a) preparing a polishing composition comprising water and from about 0.1 to about 2.0 wt % CsOH;
- (b) applying the polishing composition to a surface of the substrate being planarized;

(c) bringing the polishing pad into contact with the surface of the silicon dioxide dielectric layer, and

(d) moving the pad in relation to the silicon dioxide dielectric layer wherein a fumed silica abrasive is used in conjunction with the polishing composition and wherein the polishing composition polishes the silicon containing dielectric layer with an open field efficiency of at least 50 % and an array field efficiency of at least 85 %.

25. The method of claim 24 wherein the fumed silica is added to the chemical mechanical polishing composition before the chemical mechanical polishing composition is applied to the surface of the substrate being planarized.

26. The method of claim 24 wherein the fumed silica is incorporated into the polishing pad.

* * * * *