



US 20040053115A1

(19) **United States**

(12) **Patent Application Publication**
Skinlo

(10) **Pub. No.: US 2004/0053115 A1**

(43) **Pub. Date: Mar. 18, 2004**

(54) **ELECTRIC STORAGE BATTERY
CONSTRUCTION AND METHOD OF
MANUFACTURE**

(52) **U.S. Cl.** **429/94; 429/186; 29/623.1;
429/211**

(75) **Inventor: David M. Skinlo, Valencia, CA (US)**

(57) **ABSTRACT**

Correspondence Address:

Quallion LLC
P.O. Box 923127
Sylmar, CA 91392-3127 (US)

(73) **Assignee: Quallion LLC, Sylmar, CA**

(21) **Appl. No.: 10/665,440**

(22) **Filed: Sep. 17, 2003**

Related U.S. Application Data


(62) **Division of application No. 10/167,688, filed on Jun. 12, 2002, now Pat. No. 6,670,071.**

(60) **Provisional application No. 60/348,665, filed on Jan. 15, 2002.**

Publication Classification

(51) **Int. Cl.⁷ H01M 6/10; H01M 10/04**

An electric storage battery and method of manufacture thereof characterized by a feedthrough pin which is internally directly physically and electrically connected to an inner end of a positive electrode substrate. A C-shaped mandrel extends around the pin and substrate end enabling the pin/mandrel to be used during the manufacturing process as an arbor to facilitate winding layers of a spiral jellyroll electrode assembly. The pin additionally extends from the battery case and in the final product constitutes one of the battery terminals with the battery case comprising the other terminal. Active material is removed from both sides of the outer end of the negative electrode in the jellyroll to allow room for adhesive tape to secure the jellyroll. The electrolyte is injected through the open end of the case after the endcap is welded to the negative electrode but before sealing the endcap to the case. The electrolyte is preferably injected through the C-shaped mandrel to facilitate and speed filling.






FIG. 1




FIG. 2




FIG. 3




FIG. 4









FIG. 5








FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15






FIG. 16






FIG. 19






FIG. 20






FIG. 23




FIG. 24

ELECTRIC STORAGE BATTERY CONSTRUCTION AND METHOD OF MANUFACTURE

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of U.S. Provisional Application No. 60/348,665, filed Jan. 15, 2002.

FIELD OF THE INVENTION

[0002] This invention relates generally to electric storage batteries and more particularly to a battery construction, and method of manufacture thereof, suitable for use in implantable medical devices.

BACKGROUND OF THE INVENTION

[0003] Rechargeable electric storage batteries are commercially available in a wide range of sizes for use in a variety of applications. As battery technology continues to improve, batteries find new applications which impose increasingly stringent specifications relating to physical size and performance. Thus, new technologies have yielded smaller and lighter weight batteries having longer storage lives and higher energy output capabilities enabling them to be used in an increasing range of applications, including medical applications, where, for example, the battery can be used in a medical device which is implanted in a patient's body. Such medical devices can be used to monitor and/or treat various medical conditions.

[0004] Batteries for implantable medical devices are subject to very demanding requirements, including long useful life, high power output, low self-discharge rates, compact size, high reliability over a long time period, compatibility with the patient's internal body chemistry, etc. Although various battery chemistries have been tried, lithium ion technology is generally accepted as the preferred chemistry for medical implant applications.

[0005] Such electric storage batteries are generally comprised of a tubular metal case enveloping an interior cavity which contains an electrode assembly surrounded by a suitable electrolyte. The electrode assembly generally comprises a plurality of positive electrode, negative electrode, and separator layers which are typically stacked and/or spirally wound to form a jellyroll. The positive electrode is generally formed of a metal substrate having positive active material coated on both faces of the substrate. Similarly, the negative electrode is formed of a metal substrate having negative active material coated on both faces of the substrate. In forming an electrode assembly, separator layers are interleaved between the positive and negative electrode layers to provide electrical isolation.

SUMMARY OF THE INVENTION

[0006] The present invention is directed to an electric storage battery incorporating one or more aspects described herein for enhancing battery reliability while minimizing battery size. In addition, the invention is directed to a method for efficiently manufacturing the battery at a relatively low cost.

[0007] In accordance with a first significant aspect of the invention, a feedthrough pin is provided which is directly physically and electrically connected to the inner end of an

electrode substrate (e.g., positive), as by welding. The pin is used during the manufacturing process as an arbor to facilitate winding the layers to form an electrode assembly jellyroll. Additionally, in the fully manufactured battery, the pin extends through a battery case endcap and functions as one of the battery terminals. The battery case itself generally functions as the other battery terminal.

[0008] More particularly, in accordance with an exemplary preferred embodiment, the inner end of the positive electrode substrate is spot welded to the feedthrough pin to form an electrical connection. The substrate, e.g., aluminum, can be very thin, e.g., 0.02 mm, making it difficult to form a strong mechanical connection to the pin, which is preferably constructed of a low electrical resistance, highly corrosion resistant material, e.g., platinum iridium, and can have a diameter on the order of 0.40 mm. In order to mechanically reinforce the pin and secure the pin/substrate connection, a slotted C-shaped mandrel is provided. The mandrel is formed of electrically conductive material, e.g., titanium-6Al4V, and is fitted around the pin, overlaying the pin/substrate connection. The mandrel is then preferably welded to both the pin and substrate. The mandrel slot defines a keyway for accommodating a drive key which can be driven to rotate the mandrel and pin to wind the electrode assembly layers to form the spiral jellyroll.

[0009] In accordance with a further significant aspect of the invention, the outer layer of the jellyroll is particularly configured to minimize the size, i.e., outer radius dimension, of the jellyroll. More particularly, in the exemplary preferred embodiment, the active material is removed from both faces of the negative electrode substrate adjacent its outer end. The thickness of each active material coat can be about 0.04 mm and the thickness of the negative substrate can be about 0.005 mm. By baring the outer end of the negative electrode substrate, it can be adhered directly, e.g., by an appropriate adhesive tape, to the next inner layer to close the jellyroll to while minimizing the roll outer radius dimension.

[0010] A battery case in accordance with the invention is comprised of a tubular case body having open first and second ends. The feedthrough pin preferably carries a first endcap physically secured to, but electrically insulated from, the pin. This first endcap is preferably secured to the case body, as by laser welding, to close the open first end and form a leak free seal. With the jellyroll mounted in the case and the first endcap sealed, the interior cavity can thereafter be filled with electrolyte from the open second end.

[0011] In accordance with a still further aspect of the invention, the jellyroll assembly is formed with a flexible electrically conductive tab extending from the negative electrode substrate for electrical connection to the battery case. In accordance with a preferred embodiment, the tab is welded to a second endcap which is in turn welded to the case. The tab is sufficiently flexible to enable the second endcap to close the case body second end after the interior cavity is filled with electrolyte via the open second end. In accordance with an exemplary preferred embodiment, the tab is welded to the inner face of the second endcap such that when the jellyroll is placed in the body, the tab locates the second endcap proximate to the body without obstructing the open second end. After electrolyte filling, the case body is sealed by bending the tab to position the second endcap across the body second end and then laser welding the endcap to the case body.

BRIEF DESCRIPTION OF THE FIGURES

[0012] FIG. 1 is a side view of a feedthrough pin subassembly in accordance with the invention;

[0013] FIG. 2 is a longitudinal sectional view through the subassembly of FIG. 1;

[0014] FIG. 3 is a plan view of a positive electrode strip utilized in the exemplary preferred electrode assembly in accordance with the invention;

[0015] FIG. 4 is a side view of the positive electrode strip of FIG. 3;

[0016] FIG. 5 is an enlarged sectional view of the area A of FIG. 4 showing the inner end of the positive electrode strip of FIGS. 3 and 4;

[0017] FIG. 6 is an isometric view showing the bared inner end of the positive electrode substrate spot welded to the feedthrough pin and configured to receive a C-shaped mandrel thereon;

[0018] FIG. 7 is an end view showing the C-shaped mandrel being crimped to the pin and electrode;

[0019] FIG. 8 is an end view showing the C-shaped mandrel mounted on the pin and capturing the positive electrode substrate therebetween;

[0020] FIG. 9 is an isometric view depicting a drive key accommodated in the slot of the C-shaped mandrel;

[0021] FIG. 10 is a plan view showing the drive key coupled to a drive motor for rotating the C-shaped mandrel;

[0022] FIG. 11 is a schematic end view depicting how rotation of the C-shaped mandrel and pin can wind positive electrode, negative electrode, and separator strips to form a spiral jellyroll electrode assembly;

[0023] FIG. 12 is a plan view of a negative electrode strip utilized in the exemplary preferred electrode assembly in accordance with the invention;

[0024] FIG. 13 is a side view of the negative electrode strip of FIG. 12;

[0025] FIG. 14 is an enlarged sectional view of the area A of FIG. 13 showing the inner end of the negative electrode strip of FIGS. 12 and 13;

[0026] FIG. 15 is an enlarged sectional view of the area B of FIG. 13 showing the outer end of the negative electrode strip of FIGS. 11 and 12;

[0027] FIG. 16 is an isometric view showing that the layers of a spirally wound electrode assembly, i.e., jellyroll;

[0028] FIG. 17 is a plan view of the negative electrode strip showing the attachment of a flexible electrically conductive tab to the bared outer end of the negative electrode substrate;

[0029] FIG. 18 is an enlarged sectional view showing how the outer turn of the negative electrode strip is taped to the next inner layer to close the jellyroll to minimize its outer radius dimension;

[0030] FIG. 19 is an isometric view depicting the jellyroll electrode assembly being inserted into a cylindrical battery case body;

[0031] FIG. 20 is an isometric view showing a battery case body with the negative electrode tab extending from the open case body;

[0032] FIG. 21 is an isometric view showing how the negative electrode tab is mechanically and electrically connected to an endcap for sealing the case body second end;

[0033] FIG. 22 is a side view showing how the negative electrode tab holds the second endcap proximate to the case body second end without obstructing the open second end;

[0034] FIG. 23 is a front view showing the weld position and the relationship between the various components; and

[0035] FIG. 24 is an enlarged sectional view of the second end of the battery case showing the endcap in sealed position.

DETAILED DESCRIPTION

[0036] Attention is initially directed to FIGS. 1 and 2 which illustrate a preferred feedthrough pin subassembly 10 utilized in accordance with the present invention. The subassembly 10 is comprised of an elongate pin 12, preferably formed of a solid electrically conductive material, having low electrical resistance and high corrosion resistance such as platinum iridium, preferably 90 Pt/10 Ir. The pin 12 extends through, and is hermetically sealed to a header 14. The header 14 is comprised of dielectric disks, e.g., ceramic, 16 and 18 which sandwich a glass hollow cylinder 20 therebetween. The glass hollow cylinder is hermetically sealed to the pin 12. The outer surface of the glass hollow cylinder 20 is sealed to the inner surface of an electrically conductive hollow member 22, e.g., titanium-6Al-4V. As will be seen hereinafter, the conductive hollow material 22 functions as a battery case endcap in the final product to be described hereinafter.

[0037] Attention is now directed to FIGS. 3, 4, and 5 which illustrate a preferred positive electrode strip 30 which is utilized in the fabrication of a preferred spirally wound jellyroll electrode assembly in accordance with the present invention. The positive electrode strip 30 is comprised of a metal substrate 32 formed, for example, of aluminum. Positive electrode active material 34, 36 is deposited, respectively on the upper and lower faces 38 and 40 of the substrate 32. Note in FIGS. 3, 4, and 5 that the right end of the substrate 32 is bare, i.e. devoid of positive active material on both the upper and lower faces 38, 40.

[0038] It is to be pointed out that exemplary dimensions are depicted in FIGS. 1-5 and other figures herein. These exemplary dimensions are provided primarily to convey an order of magnitude to the reader to facilitate an understanding of the text and drawings. Although the indicated dimensions accurately reflect one exemplary embodiment of the invention, it should be appreciated that the invention can be practiced utilizing components having significantly different dimensions.

[0039] FIG. 6 depicts an early process step for manufacturing a battery in accordance with the invention utilizing the pin subassembly 10 (FIGS. 1, 2) and the positive electrode strip 30 (FIGS. 3-5). A topside electrode insulator (not shown), which may comprise a thin disk of DuPont Kapton® polyimide film, is slipped onto the pin 12 adjacent the header 14. In accordance with the present invention, the

bare end of the electrode strip substrate **32** is electrically connected to the pin **12** preferably by resistance spot welding, shown at **44**. Alternatively, substrate **32** may be ultrasonically welded to the pin **12**. The thinness, e.g. point 0.02 mm of the substrate **32**, makes it very difficult to form a strong mechanical connection between the substrate and the pin **12**. Accordingly, in accordance with a significant aspect of the present invention, an elongate C-shaped mandrel **48** is provided to mechanically reinforce the pin **12** and secure the substrate **32** thereto.

[0040] The mandrel **48** preferably comprises an elongate titanium or titanium alloy such as Ti-6Al4V tube **50** having a longitudinal slot **52** extending along the length thereof. The arrow **54** in **FIG. 6** depicts how the mandrel **48** is slid over the pin **12** and substrate **32**, preferably overlaying the line of spot welds **44**. The mandrel **48**, pin **12**, and substrate **32** are then preferably welded together, such as by resistance spot welding or by ultrasonic welding. Alternatively, the mandrel **48** may be crimped onto the pin **12** at least partially closing the "C" to create a strong mechanical connection. In the case of forming only a mechanical connection and not necessarily a gas-tight electrical connection between the mandrel **48** and the pin and substrate, the mandrel material is preferably made of a material that will not lead to electrolysis. When used with electrolytes that tend to contain hydrofluoric acid, the mandrel is preferably made of 304, 314, or 316 stainless steels or aluminum or an alloy thereof chosen for its compatibility with the other materials. **FIG. 7** is an end view showing the step of crimping the mandrel **48** to the pin **12** and substrate **32**. Supporting die **126** is used to support the mandrel **48** and crimping dies **124** and **125** are used to deform the edges of the mandrel **48** to bring them closer together and mechanically connect the mandrel **48** to the pin **12** and substrate **32**. By crimping in the direction of arrows **127** and **128**, a strong connection is formed without damaging the thin electrode or disturbing the electrical connection between the pin and the electrode.

[0041] **FIG. 8** is an end view showing the slotted mandrel **48** on the pin **12** with the substrate **32** extending tangentially to the pin **12** and terminating adjacent the interior surface of the mandrel tube **50**. The tube **50** is preferably sufficiently long so as to extend beyond the free end of the pin **12**. As depicted in **FIG. 9**, this enables a drive key **56** to extend into the mandrel slot **52**.

[0042] **FIG. 10** schematically depicts a drive motor **60** for driving the drive key **56** extending into mandrel slot **52**. With the pin subassembly header **14** supported for rotation (not shown), energization of the motor **60** will orbit the key drive **56** to rotate the mandrel **48** and subassembly **10** around their common longitudinal axes. The rotation of the mandrel **48** and subassembly **10** is employed to form a jellyroll electrode assembly in accordance with the present invention.

[0043] More particularly, **FIG. 11** depicts how a jellyroll electrode assembly is formed in accordance with the present invention. The bare end of the substrate **32** of the positive electrode strip **30** is electrically connected to the pin **12** as previously described. The conductive mandrel **48** contains the pin **12** and bare substrate end, being welded to both as previously described. A strip of insulating separator material **64** extending from opposite directions is introduced between the mandrel **48** and positive electrode substrate **32**, as

shown. A negative electrode strip **70** is then introduced between the portions of the separator material extending outwardly from mandrel **48**.

[0044] The preferred exemplary negative electrode strip **70** is depicted in **FIGS. 12-15**. The negative electrode strip **70** is comprised of a substrate **72**, e.g. titanium, having negative active material formed on respective faces of the substrate. More particularly, note in **FIG. 14** that negative active material **74** is deposited on the substrate upper surface **76** and negative active material **78** is deposited on the substrate lower surface **80**. **FIG. 14** depicts the preferred configuration of the inner end **82** of the negative electrode strip **70** shown at the left of **FIGS. 12 and 13**. **FIG. 15** depicts the configuration of the outer end **83** of the negative electrode strip **70** shown at the right side of **FIGS. 12 and 13**.

[0045] Note in **FIG. 14** that one face of the substrate inner end **82** is bared. This configuration can also be noted in **FIG. 11** which shows how the negative substrate inner end **82** is inserted between turns of the separator strip **64**. After the strip **70** has been inserted as depicted in **FIG. 11**, the aforementioned drive motor **60** is energized to rotate pin **12** and mandrel **48**, via drive key **56**, in a counterclockwise direction, as viewed in **FIG. 11**. Rotation of pin **12** and mandrel **48** functions to wind positive electrode strip **30**, separator strip **64**, and negative electrode strip **70**, into the spiral jellyroll assembly **84**, depicted in **FIG. 16**. The assembly **84** is comprised of multiple layers of strip material so that a cross section through the assembly **84** would reveal a sequence of layers in the form pos/sep/neg/sep/pos/sep/neg/. . . , etc.

[0046] **FIG. 15** depicts a preferred configuration of the outer end **83** of the negative electrode strip **70**. Note that the outer end **88** of the substrate **72** is bared on both its top and bottom faces. Additionally, as shown in **FIG. 17**, a flexible metal tab **90** is welded crosswise to the substrate **72** so as to extend beyond edge **92**. More particularly, note that portion **94** of tab **90** is cantilevered beyond edge **92** of negative electrode strip **70**. This tab portion, as will be described hereinafter, is utilized to mechanically and electrically connect to an endcap for closing a battery case.

[0047] Attention is now called to **FIG. 18**, which illustrates a preferred technique for closing the jellyroll assembly **84**. That is, the bared end **88** of the negative electrode substrate **72** extending beyond the negative active material coat **78** is draped over the next inner layer of the jellyroll assembly **84**. The end **88** can then be secured to the next inner layer, e.g., by appropriate adhesive tape **96**. One such suitable adhesive tape is DuPont Kapton® polyimide tape. It is important to note that the outer end configuration **88** of the negative electrode strip **70** enables the outer radius dimension of the jellyroll assembly **84** to be minimized as shown in **FIG. 18**. More particularly, by baring the substrate **72** beyond the active material **78**, the tape **96** is able to secure the substrate end without adding any radial dimension to the jellyroll assembly. In other words, if the outer end of the substrate were not sufficiently bared, then the tape **96** would need to extend over the active material and thus add to the outer radius dimension of the jellyroll **84**. Furthermore, the bare substrate **72** is more flexible than the substrate coated with active material **78** and conforms more readily to the jellyroll assembly **84**, making it easier to adhere it to the

surface of the jellyroll. These space savings, although seemingly small, can be clinically important in certain medical applications. It should be noted that the electrode need only be bared at an end portion long enough to accommodate the tape **96**, as shown in **FIG. 18**. Because the uncoated substrate does not function as an electrode, it would waste space in the battery to bare any more than necessary to accommodate the tape. In a preferred embodiment, the length of uncoated substrate is between 1 and 8 mm, and more preferably about 2 mm.

[0048] **FIG. 19** depicts the completed jellyroll assembly **84** and shows the cantilevered tab portion **94** prior to insertion into a battery case body **100**. The case body **100** is depicted as comprising a cylindrical metal tube **101** having an open first end **104** and open second end **106**. Arrow **107** represents how the jellyroll assembly **84** is inserted into the cylindrical tube **101**. **FIG. 20** depicts the jellyroll assembly **84** within the tube **101** with the cantilevered negative electrode tab **94** extending from the case open second end **106**. The case open first end **104** is closed by the aforementioned header **14** of the pin subassembly **10** shown in **FIGS. 1 and 2**. More particularly, note that the metal hollow member **22** is configured to define a reduced diameter portion **108** and shoulder **110**. The reduced diameter portion **108** is dimensioned to fit into the open end **104** of the cylindrical tube **101** essentially contiguous with the tube's inner wall surface. The shoulder **110** of the hollow member **22** engages the end of the case tube **101**. This enables the surfaces of the reduced diameter portion **108** and shoulder **110** to be laser welded to the end of the case **100** to achieve a hermetic seal.

[0049] Attention is now directed to **FIGS. 21-24**, which depict the tab **94** extending from the second open end **106** of the case tube **101**. Note that the tab **94** extends longitudinally from the body close to the case tube adjacent to tube's inner wall surface. In accordance with a preferred embodiment of the invention, the tab **94** is welded at **110** to the inner face **112** of a circular second endcap **114**. In accordance with a preferred embodiment, the tab **94** is sufficiently long to locate the weld **110** beyond the center point of the circular endcap **114**. More particularly, note in **FIGS. 21-24** that by locating the weld **110** displaced from the center of the cap **114**, the tab **94** can conveniently support the endcap **114** in a vertical orientation as depicted in **FIG. 22** misaligned with respect to the open end **106**. This end cap position approximately perpendicular to the end **122** of the case **100** is a first bias position wherein the end cap advantageously tends to remain in that orientation with the case end open prior to filling. To further describe the relationship between the weld location and the various components, **FIG. 23** shows a front view with various dimensions. L represents the length from the weld **110** to the top of the case **100** as measured parallel to the edge of the case. R is the radius of the end cap **114**. For the preferred geometry, $L \leq 2R$. Weld **110** is preferably made above the center point **111** of the end cap **114**. Preferably, the end cap **114** overlaps the case **100** by approximately $R/2$. By configuring the tab **94** and weld **110** as indicated, the endcap **114** can be supported so that it does not obstruct the open end **106**, thereby facilitating electrolyte filling of the case interior cavity via open end **106**. A filling needle or nozzle can be placed through open end **106** to fill the case. This obviates the need for a separate electrolyte fill port, thereby reducing the number of components and number of seals to be made, thus reducing cost

and improving reliability. Furthermore, for small medical batteries, the end caps would be very small to have fill ports therein. In a preferred embodiment in which the case wall is very thin, for example, 0.002 inches, providing a fill port in the side wall of the case would be impractical. Even in the case of larger devices where space is less critical and the wall is more substantial, providing a fill port in the side of the case would mean the electrolyte would have a very long path length to wet the jellyroll. Note that while the case could be filled with electrolyte prior to welding tab **94** to endcap **114**, it would be difficult and messy to do so. Therefore, it is advantageous to configure the tab **94** and weld **110** as described to allow the weld to be made prior to filling.

[0050] Preferably before filling, a bottomside electrode insulator (not shown), which may comprise a thin disk of DuPont Kapton® polyimide film, is installed into the case between the rolled electrode assembly and the still open end of the battery case.

[0051] In a preferred filing method, there is a channel of air between the pin and the crimped or welded C-shaped mandrel, which is used as a conduit for quickly delivering the electrolyte to the far end of the battery and to the inside edges of the electrodes within the jellyroll. Filling from the far end of the battery prevents pockets of air from being trapped, which could form a barrier to further filling. This facilitates and speeds the filling process, ensuring that electrolyte wets the entire battery.

[0052] Thereafter, the flexible tab **94** can be bent to the configuration depicted in **FIG. 24**. Note that the endcap **114** is configured similarly to header hollow member **22** and includes a reduced diameter portion **118** and a shoulder **120**. The reduced diameter portion snugly fits against the inner surface of the wall of tube **101** with the endcap shoulder **120** bearing against the end **122** of the cylindrical case **100**. The relatively long length of the tab **94** extending beyond the center point of the endcap surface **112** minimizes any axial force which might be exerted by the tab portion **94** tending to longitudinally displace the endcap **114**. The end cap position covering the end **122** of the case **100** is a second bias position wherein the end cap advantageously tends to remain in that orientation prior to welding. With the endcap in place, it can then be readily welded to the case wall **101** to hermetically seal the battery. With tab **90** welded to negative substrate **72** and with the negative electrode strip **70** as the outermost layer of the jellyroll, the endcap **114** becomes negative. In turn, welding the endcap **114** to the case **100** renders the case negative.

[0053] From the foregoing, it should now be appreciated that an electric storage battery construction and method of manufacture have been described herein particularly suited for manufacturing very small, highly reliable batteries suitable for use in implantable medical devices. Although a particular preferred embodiment has been described herein and exemplary dimensions have been mentioned, it should be understood that many variations and modifications may occur to those skilled in the art falling within the spirit of the invention and the intended scope of the appended claims.

We claim:

1. An electric storage battery including:
 - a case comprising a peripheral wall defining an interior volume; and
 - an electrode assembly mounted in said interior volume, said electrode assembly including:
 - an electrically conductive elongate pin; and
 - first and second opposite polarity electrode strips wound together to form a spiral roll, each electrode strip having inner and outer ends, wherein said first electrode strip is electrically coupled to said pin at said inner end; and
 - a hollow elongate mandrel closely fitted around said pin for mechanically reinforcing said pin.
2. The battery of claim 1 wherein said pin extends exteriorly of said case peripheral wall to function as a first battery terminal.
3. The battery of claim 1 wherein said mandrel is electrically coupled to said pin.
4. The battery of claim 1 wherein said first electrode strip inner end is directly connected to said pin by at least one weld.
5. The battery of claim 1 wherein said pin consists of a PtIr alloy.
6. The battery of claim 1 further comprising a first end cap mounted on said pin, said first end cap including an electrical insulator; and wherein said pin extends through and is hermetically sealed to said end cap electrical insulator.
7. The battery of claim 1 wherein said mandrel defines an elongate slot; and wherein
 - said first electrode strip extends through said mandrel slot.
8. The battery of claim A1 wherein said mandrel is welded to said pin.
9. The battery of claim A1 wherein said mandrel comprises titanium or an alloy thereof.
10. An electric storage battery made by the steps of:
 - providing an electrically conductive elongate pin having inner and outer ends;
 - providing a first polarity electrode strip;
 - providing a second polarity electrode strip;
 - electrically connecting a first end of the first polarity electrode strip to the pin proximate to the pin inner end;
 - mounting a reinforcing mandrel on the pin; and
 - winding together the first polarity electrode strip and the second polarity electrode strip to form a spiral roll having at least a portion of the pin within the spiral roll.
11. The battery of claim 10 wherein said steps further include the step of mounting the spiral roll in a case with the pin outer end extending exteriorly of the case to form a first battery terminal.
13. The battery of claim 10 wherein said steps further include the step of electrically coupling the reinforcing mandrel to the pin.
14. The battery of claim 10 wherein said step of winding together the first polarity electrode strip and the second polarity electrode strip comprises rotating the pin.
15. The battery of claim 10 wherein said step of providing an electrically conductive elongate pin includes a step of:

forming an end cap including an insulating member on the pin hermetically sealed thereto and positioned proximate to but spaced from the pin outer end.

16. The battery of claim 3 wherein said steps further include a step of mounting a conductive member around the insulating member; and

electrically connecting the conductive member to the case.

17. The battery of claim 1 wherein said steps further include a step of welding the reinforcing mandrel to the pin.

18. The battery of claim 1 wherein the mandrel comprises a tube having a slot therein and wherein said winding step further includes the steps of:

inserting a drive key into the slot; and

orbiting the drive key to rotate the mandrel and pin.

19. The battery of claim 1 wherein the mounted mandrel comprises a channel and wherein said steps further include a step of injecting electrolyte through the channel.

20. A method of constructing an electric storage battery including:

providing an electrically conductive elongate pin having inner and outer ends;

providing a first polarity electrode strip;

providing a second polarity electrode strip;

electrically connecting a first end of said first polarity electrode strip to said pin proximate to said pin inner end;

mounting a reinforcing mandrel on the pin;

winding together said first polarity electrode strip and said second polarity electrode strip to form a spiral roll having at least a portion of the pin within the spiral roll.

21. The method of claim 20 and further including the step of:

mounting said spiral roll in a case with said pin outer end extending exteriorly of said case to form a first battery terminal.

22. The method of claim 20 and further including the step of:

electrically coupling the reinforcing mandrel to the pin.

23. The method of claim 20 wherein said step of winding together the first polarity electrode strip and the second polarity electrode strip comprises rotating the pin.

24. The method of claim 20 wherein said step of providing said electrically conductive elongate pin includes a step of:

forming an end cap including an insulating member on said pin hermetically sealed thereto and positioned proximate to but spaced from said pin outer end.

25. The method of claim 24 including the further step of mounting a conductive member around said insulating member; and

electrically connecting said conductive member to said case.

26. The method of claim 20 including a further step of welding the reinforcing mandrel to the pin.

27. The method of claim 20 said step of mounting a reinforcing mandrel comprises mounting a mandrel comprising a tube having a slot therein; and wherein said winding step further includes the steps of:

inserting a drive key into the slot; and

orbiting the drive key to rotate the mandrel and pin.

28. The method of claim 20 wherein the said step of mounting a reinforcing mandrel comprises providing a channel and wherein said steps further include a step of injecting electrolyte through the channel.

29. An electrode assembly including:

an electrically conductive, elongate pin;

an elongate reinforcing mandrel mounted on at least a portion of said pin; and

a spiral roll comprising first and second opposite polarity electrode strips and at least one separator strip separating said electrode strips mounted on said pin, wherein one of said electrode strips is electrically coupled to said pin.

30. The electrode assembly of claim 29 wherein said mandrel is C-shaped and defines a longitudinal slot; and wherein

an inner end of said first electrode strip extends through said mandrel slot and is electrically connected to said pin.

31. The electrode assembly of claim 29 wherein said pin comprises a portion extending beyond said spiral roll to form a battery terminal.

32. The electrode assembly of claim 29 wherein said mandrel is crimped onto said pin.

33. The electrode assembly of claim 29 wherein the mounted mandrel has a channel through which electrolyte can be injected.

34. An electrode assembly made by the steps of:

providing an electrically conductive, elongate pin;

providing a first polarity electrode strip;

providing a second polarity electrode strip;

electrically connecting a first end of the first polarity electrode strip to the pin;

mounting a reinforcing mandrel on the pin; and

winding together the first polarity electrode strip and the second polarity electrode strip to form a spiral roll having at least a portion of the pin and the mandrel interior to the spiral roll.

35. The assembly of claim 34 wherein said steps further include a step of crimping the reinforcing mandrel to the pin.

36. The assembly of claim 34 wherein said steps further include a step of welding the reinforcing mandrel to the pin.

37. The assembly of claim 34 wherein said step of winding together the first polarity electrode strip and the second polarity electrode strip comprises rotating the pin and the mandrel.

38. The assembly of claim 34 wherein said step of winding together the first polarity electrode strip and the second polarity electrode strip to form a spiral roll comprises leaving a portion of the pin extending beyond the spiral roll to form a battery terminal.

39. A method of constructing an electric storage battery including:

providing an electrically conductive, elongate pin;

providing a first polarity electrode strip;

providing a second polarity electrode strip;

electrically connecting a first end of said first polarity electrode strip to said pin;

mounting a reinforcing mandrel on said pin; and

winding together the first polarity electrode strip and the second polarity electrode strip to form a spiral roll.

40. The method of claim 39 including the further step of crimping the reinforcing mandrel to the pin.

41. The method of claim 39 including the further step of welding the reinforcing mandrel to the pin.

42. The method of claim 39 wherein said step of winding together the first polarity electrode strip and the second polarity electrode strip comprises rotating the pin and the mandrel.

42. The method of claim 39 wherein said step of winding together the first polarity electrode strip and the second polarity electrode strip to form a spiral roll comprises leaving a portion of the pin extending beyond the spiral roll to form a battery terminal.

43. An electric storage battery comprising:

an electrically conductive case sealed by first and second end caps;

an electrically conductive terminal pin extending through said first end cap and electrically insulated from said case;

an electrode assembly disposed within said case and comprising first and second opposite polarity electrodes separated by separators wherein said first electrode is electrically coupled to said pin;

a flexible conductive tab electrically coupled to said second electrode proximate a first location at the seal formed between said second end cap and said case;

wherein said second end cap has a center and wherein said second end cap has a width from said first location to a second location at the seal formed between said second end cap and said case measured along a line through said center; and

said tab electrically connected to said second end cap at a third location between said second location and said center of said second end cap.

44. The battery of claim 43 wherein said case has no separate fill hole.

45. The battery of claim 43 wherein said second end cap is welded to said tab flat against an inner face of said second end cap.

46. The battery of claim 43 wherein said second end cap is circular and wherein said width is a diameter.

47. An electric storage battery made by the steps of:

providing a case comprising a peripheral wall of electrically conductive material defining an interior volume and having first and second wall openings communicating with the interior volume;

providing an electrically conductive terminal pin extending through a first end cap and electrically insulated from the case

providing an electrode assembly comprising first and second opposite polarity electrodes

electrically connecting the first electrode to the pin;

forming a flexible conductive tab extending beyond a second edge of the electrode assembly and electrically connected to the second electrode;

mounting the electrode assembly in the interior volume with the pin extending out through the first wall opening and the tab extending out through the second wall opening;

mounting the first end cap to seal the first wall opening;

providing a second end cap of electrically conductive material; and

fastening the second end cap to the tab in a manner to provide an electrical connection therebetween.

48. The electric storage battery of claim 47 wherein said steps further include a further step of depositing electrolyte into the case through the second wall opening following said step of fastening the second end cap to the tab.

49. The electric storage battery of claim 47 wherein said step of fastening the second end cap to the tab includes welding the tab flat against an inner face of the second end cap.

50. The electric storage battery of claim 49 including the further step of mounting the end cap in the second wall opening to seal the second wall opening.

51. A method of constructing an electric storage battery including:

providing a case comprising a peripheral wall of electrically conductive material defining an interior volume and having first and second wall openings communicating with the interior volume;

providing an electrically conductive terminal pin extending through a first end cap and electrically insulated from the case

providing an electrode assembly comprising first and second opposite polarity electrodes wherein the first electrode is electrically connected to the pin;

forming a flexible conductive tab extending beyond a second edge of the electrode assembly and electrically connected to the second electrode;

mounting the electrode assembly in the interior volume with the pin extending out through the first wall opening and the tab extending out through the second wall opening;

mounting the first end cap to seal the first wall opening;

providing a second end cap of electrically conductive material; and

fastening the second end cap to the tab in a manner to provide a mechanical and electrical connection therebetween.

52. The method of claim 51 including a further step of depositing electrolyte into the case through the second wall opening after said step of fastening the second end cap to the tab.

53. The method of claim 51 wherein said step of fastening the second end cap to the tab includes welding the tab flat against an inner face of the second end cap.

54. The method of claim 53 including the further step of mounting the end cap in the second wall opening to seal the second wall opening.

55. An electric storage battery comprising:

an electrically conductive case hermetically sealed by first and second end caps, wherein said case has no separate fill holes and wherein said first and second end caps have no separate fill holes;

an electrically conductive terminal pin extending through said first end cap and electrically insulated from said case;

an electrode assembly disposed within said case and comprising first and second opposite polarity electrodes separated by separators wherein said first electrode is electrically coupled to said pin; and

a flexible conductive tab electrically coupled to said second electrode and to said second end cap.

56. An electric storage battery made by the steps of:

providing a case comprising a peripheral wall of electrically conductive material defining an interior volume and having first and second wall openings communicating with the interior volume;

providing an electrically conductive terminal pin extending through the first end cap and electrically insulated from the case;

providing an electrode assembly comprising first and second opposite polarity electrodes

electrically coupling the first electrode to the pin;

mounting the electrode assembly in the interior volume with the pin extending out through the first wall opening;

mounting the first end cap to seal the first wall opening;

providing a second end cap of electrically conductive material; and

electrically coupling the second electrode to the second end cap;

depositing electrolyte into the case through the second wall opening; and

mounting the end cap in the second wall opening to seal the second wall opening.

57. The electric storage battery of claim 56 wherein the step of electrically coupling the second electrode to the second end cap precedes the step of depositing electrolyte into the case through the second wall opening.

58. A method of constructing an electric storage battery including:

providing a case comprising a peripheral wall of electrically conductive material defining an interior volume and having first and second wall openings communicating with the interior volume;

providing an electrically conductive terminal pin extending through the first end cap and electrically insulated from the case;

providing an electrode assembly comprising first and second opposite polarity electrodes

electrically coupling the first electrode to the pin;

mounting the electrode assembly in the interior volume with the pin extending out through the first wall opening;

mounting the first end cap to seal the first wall opening; providing a second end cap of electrically conductive material; and

electrically coupling the second electrode to the second end cap;

depositing electrolyte into the case through the second wall opening; and

mounting the end cap in the second wall opening to seal the second wall opening.

59. The method of claim 58 wherein the step of electrically coupling the second electrode to the second end cap precedes the step of depositing electrolyte into the case through the second wall opening.

60. A hermetically sealable electric storage battery comprising:

a case having an open end;

a first electrically conductive terminal electrically insulated from said case;

an electrode assembly disposed within said case and comprising first and second opposite polarity electrodes separated by separators wherein said first electrode is electrically coupled to said first terminal;

a flexible conductive tab electrically coupled to said second electrode proximate a first location at said case open end;

said tab electrically connected to said end cap at a second location whereby said end cap has a first bias position tending to keep said case open end open and a second bias position tending to close said case open end.

61. The battery of claim 60 wherein said first bias position orients said end cap approximately perpendicular to said open end.

62. The battery of claim 60 wherein said second end cap is welded to said tab flat against an inner face of said second end cap.

63. The battery of claim 60 wherein:

said end cap is circular and has a radius R ;

the distance from said second location to said case open end is a length L ; and

$L \leq 2R$.

64. The battery of claim 63 wherein said second location is above the center of said end cap in said first bias position.

65. The battery of claim 63 wherein said end cap overlaps the case by approximately $R/2$ in said second bias position.

* * * * *