

US 20050275079A1

(19) **United States**(12) **Patent Application Publication**
Stark(10) **Pub. No.: US 2005/0275079 A1**(43) **Pub. Date: Dec. 15, 2005**(54) **WAFER-LEVEL HERMETIC MICRO-DEVICE
PACKAGES****Publication Classification**(76) **Inventor: David H. Stark, Evergreen, CO (US)**(51) **Int. Cl.⁷ H01L 33/00**(52) **U.S. Cl. 257/680; 257/434; 257/98**

Correspondence Address:
HOWISON & ARNOTT, L.L.P
P.O. BOX 741715
DALLAS, TX 75374-1715 (US)


(21) **Appl. No.: 11/140,593**(22) **Filed: May 27, 2005****Related U.S. Application Data**

(60) Division of application No. 10/713,475, filed on Nov. 14, 2003, which is a continuation-in-part of application No. 10/133,049, filed on Apr. 26, 2002, now Pat. No. 6,723,379, which is a continuation-in-part of application No. 10/104,315, filed on Mar. 22, 2002, now Pat. No. 6,627,814.

(60) Provisional application No. 60/426,522, filed on Nov. 15, 2002. Provisional application No. 60/442,922, filed on Jan. 27, 2003. Provisional application No. 60/442,941, filed on Jan. 27, 2003.

(57) **ABSTRACT**

A hermetically sealed micro-device package encapsulating a micro-device and including a transparent window allowing light to pass into and out of a cavity containing the micro-device comprises a semiconductor substrate having a micro-device operably disposed thereupon. The substrate has a first frame-attachment area formed thereupon having a plan that circumscribes the micro-device. A sheet of transparent material has a window aperture portion defined thereupon, the sheet having a second frame-attachment area formed thereupon having a plan that circumscribes the window aperture portion. A frame/spacer is positioned between, and hermetically bonded to, the semiconductor substrate and the transparent sheet, the frame/spacer including a continuous sidewall having a plan on one side substantially corresponding to, and substantially in register with, the plan of the first frame-attachment area, having a plan on the opposite side substantially corresponding to, and substantially in register with, the plan of the second frame-attachment area, and having a height that exceeds the height of the micro-device.






FIG. 1




FIG. 2




FIG. 3




FIG. 4a








FIG. 4b






FIG. 9




FIG. 10







FIG. 11






FIG. 13a




FIG. 13b




FIG. 13c






FIG. 14







FIG. 16b







FIG. 17a







FIG. 19b






FIG. 19c








FIG. 20a




FIG. 20c




FIG. 20b










FIG. 20d










FIG. 22













FIG. 23








FIG. 30







FIG. 31






FIG. 35




FIG. 36




FIG. 37




FIG. 38




FIG. 39




FIG. 40

WAFER-LEVEL HERMETIC MICRO-DEVICE PACKAGES

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a Divisional of U.S. patent application Ser. No. 10/713,475 filed Nov. 14, 2003, which is a Continuation-In-Part of U.S. patent application Ser. No. 10/133,049 filed Apr. 26, 2002, now U.S. Pat. No. 6,723,379, which is a Continuation-In-Part of U.S. patent application Ser. No. 10/104,315 filed Mar. 22, 2002, now U.S. Pat. No. 6,627,814.

TECHNICAL FIELD OF THE INVENTION

[0002] The current invention relates to packages for photonic devices, optical devices, micro-mechanical devices, micro-electromechanical systems (MEMS) devices or micro-optoelectromechanical systems (MOEMS) devices, and more particularly, to manufacturing hermetic packages having a transparent window at the wafer level or substrate level of device fabrication.

BACKGROUND OF THE INVENTION

[0003] Photonic, photovoltaic, optical and micro-mechanical devices are typically packaged such that the active elements (i.e., the emitters, receivers, micro-mirrors, etc.) are disposed within a sealed chamber to protect them from handling and other environmental hazards. In many cases, it is preferred that the chamber be hermetically sealed to prevent the influx, egress or exchange of gasses between the chamber and the environment. Of course, a window must be provided to allow light or other electromagnetic energy of the desired wavelength to enter and/or leave the package. In some cases, the window will be visibly transparent, e.g. if visible light is involved, but in other cases the window may be visibly opaque while still being "optically" transparent to electromagnetic energy of the desired wavelengths. In many cases, the window is given certain optical properties to enhance the performance of the device. For example, a glass window may be ground and polished to achieve certain curve or flatness specifications in order to disperse in a particular pattern and/or avoid distorting the light passing therethrough. In other cases, anti-reflective or anti-refractive coatings may be applied to the window to improve light transmission therethrough.

[0004] Hermetically sealed micro-device packages with windows have heretofore typically been produced using cover assemblies with metal frames and glass window panes. To achieve the required hermetic seal, the glass window pane (or other transparent window material) has heretofore been fused to its metallic frame by one of several methods. A first of these methods is heating it in a furnace at a temperature exceeding the window's glass transition temperature, T_G and/or the window's softening temperature T_S (typically at or above 900° C.). However, because the fusing temperature is above T_G or T_S , the original surface finish of the glass pane is typically ruined, making it necessary to finish or re-finish (e.g., grinding and polishing) both surfaces of the window pane after fusing in order to obtain the necessary optical characteristics. This polishing of the window panes requires additional process steps during manufacture of the cover assemblies, which steps tend to be

relatively time and labor intensive, thus adding significantly to the cost of the cover assembly, and hence to the cost of the overall package. In addition, the need to polish both sides of the glass after fusing requires the glass to project both above and below the attached frame. This restricts the design options for the cover assembly with respect to glass thickness, dimensions, etc., which can also result in increased material costs.

[0005] A second method to hermetically attach a transparent window to a frame is to solder the two items together using a separate preform made of a metal or metal-alloy solder material. The solder preform is placed between a pre-metallized window and a metal or metallized frame, and the soldering is performed in a furnace. During soldering, no significant pressure is applied, i.e., the parts are held together with only enough force to keep them in place. For this type of soldering, the most common solder preform material is eutectic gold-tin.

[0006] Eutectic gold-tin solder melts and solidifies at 280° C. Its CTE at 20° is 16 ppm/° C. These two characteristics cause three drawbacks to the reliability of the assembled window. First, the CTE of Mil-Spec kovar from 280° C. to ambient is approximately 5.15 +/-0.2 ppm/0 C., while most window glasses intended for sealing to kovar have higher average CTEs over the same temperature range. During cooling from the set point of 280° down to ambient, the glass is shrinking at a greater rate than the kovar frame it's attached to. The cooled glass will be in tension, which is why it is prone to cracking. To avoid cracking, the glass should have an identical or slightly lower average CTE than the kovar so as to be stress neutral or in slight compression after cooling. Using solders with lower liquidus/solidus temperatures puts the kovar at a higher average CTE, more closely matching the average CTE of the glass. However, this worsens the second drawback of metal-allow solder seals.

[0007] The second drawback to soldering the glass to the kovar frame is that the window assembly will delaminate at temperatures above the liquidus temperature of the employed solder. Using lower liquidus/solidus temperature solders, while reducing the CTE mismatch between the kovar and glass, further limits the applications for the window assembly. Most lead-free solders have higher liquidus/solidus temperatures than the 183° C. of eutectic Sn/Pb. Surface-Mount Technology (SMT) reflow ovens are profiled to heat Printed-Wiring Board (PWB) assemblies 15-20 degrees above the solder's liquidus/solidus temperature. So the SMT reflow-soldering attachment to a PWB of a MOEMS device whose window was manufactured using lower melting-point solder preforms might have the unfortunate effect of reflowing the window assembly's solder, causing window delamination.

[0008] The third drawback is that the solder, which is the intermediate layer between the glass and the kovar frame, has a CTE up to three times greater than the two materials it's joining. An intermediate joining material would ideally have a compensating CTE in-between the two materials it's bonding.

[0009] A third method to hermetically attach a glass window to a frame is to solder the two items together using a solder-glass material. Solder-glasses are special glasses with a particularly low softening point. They are used to join

glass to other glasses, ceramics, or metals without thermally damaging the materials to be joined. Soldering is carried out in the viscosity range η where η is the range from 10^4 to 10^6 dPa s (poise) for the solder-glass; this corresponds generally to a temperature range T (for the glass solder or solder-glass) within the range from 350° C. to 700° C.

[0010] Once a cover assembly with a hermetically sealed window is prepared, it is typically seam welded to the device base (i.e., substrate) in order to produce the finished hermetically sealed package. Seam welding uses a precisely applied AC current to produce localized temperatures of about 1,100° C. at the frame/base junction, thereby welding the metallic cover assembly to the package base and forming a hermetic seal. To prevent distortion of the glass window-pane or package, the metal frame of the cover assembly should be fabricated from metal or metal alloy having a CTE (i.e., coefficient of thermal expansion) that is similar to that of the transparent window material and to the CTE of the package base.

[0011] While the methods described above have heretofore produced useable window assemblies for hermetically sealed micro-device packages, the relatively high cost of these window assemblies is a significant obstacle to their widespread application. A need therefore exists, for package and component designs and assembly methods which reduce the labor costs associated with producing each package.

[0012] A need still further exists for package and component designs and assembly methods that will minimize the manufacturing cycle time required to produce a completed package.

[0013] A need still further exists for package and component designs and assembly methods that reduce the number of process steps required for the production of each package. It will be appreciated that reducing the number of process steps will reduce the overhead/floor space required in the production facility, the amount of capital equipment necessary for manufacturing, and handling costs associated with transferring the work pieces between various steps in the process. A reduction in the cost of labor may also result. Such reductions would, of course, further reduce the cost of producing these hermetic packages.

[0014] A need still further exists for package and component designs and assembly methods that will reduce the overall materials costs associated with each package, either by reducing the initial material cost, by reducing the amount of wastage or loss during production, or both.

SUMMARY OF THE INVENTION

[0015] The present invention disclosed and claimed herein comprises, in one aspect thereof, a hermetically sealed micro-device package encapsulating a micro-device. The package includes a transparent window allowing light to pass into and out of a cavity containing the micro-device. The micro-device package comprises a semiconductor substrate, a sheet of transparent material and a frame/spacer. The semiconductor substrate has a micro-device operably disposed thereupon, and also a first frame-attachment area is formed thereupon having a plan that circumscribes the micro-device. The sheet of transparent material has a window aperture portion defined thereupon, and also has a second frame-attachment area formed thereupon having a

plan that circumscribes the window aperture portion. The frame/spacer is positioned between, and hermetically bonded to, the semiconductor substrate and the transparent sheet. The frame/spacer includes a continuous sidewall having a plan on one side substantially corresponding to, and substantially in register with, the plan of the first frame-attachment area, a plan on the opposite side substantially corresponding to, and substantially in register with, the plan of the second frame-attachment area, and a height that exceeds the height of the micro-device.

BRIEF DESCRIPTION OF THE DRAWINGS

[0016] FIG. 1 is a perspective view of a hermetically sealed micro-device package;

[0017] FIG. 2 is a cross-sectional view of the micro-device package of FIG. 1;

[0018] FIG. 3 is an exploded view of a cover assembly manufactured in accordance with one embodiment of the current invention;

[0019] FIGS. 4a and 4b show transparent sheets having contoured sides, specifically:

[0020] FIG. 4a showing a sheet having both sides contoured;

[0021] FIG. 4b showing a sheet having one side contoured;

[0022] FIG. 5 shows an enlarged view of the sheet sealing area prior to metallization;

[0023] FIG. 6 shows an enlarged view of the sheet sealing area after metallization;

[0024] FIG. 7 shows a cross-sectional view through a pre-fabricated frame;

[0025] FIG. 8 illustrates placing the frame against the metallized sheet prior to bonding;

[0026] FIG. 9 is a block diagram of a process for manufacturing cover assemblies using prefabricated frames in accordance with one embodiment;

[0027] FIG. 10 is an exploded view of a cover assembly manufactured using a solder preform;

[0028] FIG. 11 is a partial perspective view of another embodiment utilizing solder applied by inkjet;

[0029] FIGS. 12a-c and FIGS. 13a-c illustrate a process of manufacturing cover assemblies in accordance with yet another embodiment of the invention, specifically:

[0030] FIG. 12a shows the initial transparent sheet;

[0031] FIG. 12b shows the transparent sheet after initial metallization;

[0032] FIG. 12c shows the transparent sheet after deposition of the integral frame/heat spreader;

[0033] FIG. 13a shows a partial cross-section of the sheet of FIG. 12a;

[0034] FIG. 13b shows a partial cross-section of the sheet of FIG. 12b;

[0035] FIG. 13c shows a partial cross-section of the sheet of FIG. 12c;

[0036] FIG. 14 is a block diagram of a process for manufacturing cover assemblies using cold gas dynamic spray technology in accordance with another embodiment;

[0037] FIGS. 15a-15b illustrate a multi-unit assembly manufactured in accordance with another embodiment; specifically:

[0038] FIG. 15a illustrates an exploded view of a the multi-unit assembly;

[0039] FIG. 15b is bottom view of the frame of FIG. 15a;

[0040] FIG. 16a illustrates compliant tooling formed in accordance with another embodiment;

[0041] FIG. 16b is a side view of a multi-unit assembly illustrating the method of separation;

[0042] FIGS. 17a and 17b illustrate the manufacture of multiple cover assemblies in accordance with yet another embodiment, specifically:

[0043] FIG. 17a shows the transparent sheet in its original state;

[0044] FIG. 17b illustrates the sheet after deposition of the multi-aperture frame/heat spreader;

[0045] FIGS. 18a-18c illustrate an assembly configuration suitable for use with electrical resistance heating; specifically:

[0046] FIG. 18a illustrates the configuration of the sheet;

[0047] FIG. 18b illustrates the configuration of the frame;

[0048] FIG. 18c illustrates the joined sheet and frame;

[0049] FIGS. 19a-19f illustrate multi-unit assembly configurations suitable for heating with electrical resistance heating;

[0050] FIG. 20a illustrates an exploded view of a window assembly including interlayers for diffusion bonding;

[0051] FIG. 20b illustrates the window assembly of FIG. 20a after diffusion bonding;

[0052] FIGS. 20c and 20d illustrate an additional embodiment of the invention having internal and external frames; specifically:

[0053] FIG. 20c illustrates an exploded view of a “sandwiched” window assembly before bonding;

[0054] FIG. 20d illustrates the completed assembly of FIG. 20c after bonding;

[0055] FIGS. 20e, 20f and 20g, illustrate fixtures for aligning and compressing the window assemblies during diffusion bonding; specifically:

[0056] FIG. 20e illustrates an empty fixture and clamps;

[0057] FIG. 20f illustrates the fixture of FIG. 20e with a window assembly positioned therein for bonding;

[0058] FIG. 20g illustrates an alternative fixture designed to produce more axial pressure on the window assembly;

[0059] FIGS. 21a-21b are cross-sectional views of wafer-level hermetic micro-device packages in accordance with other embodiments of the invention; specifically:

[0060] FIG. 21a shows a wafer-level hermetic micro-device packages having reverse-side electrical connections;

[0061] FIG. 21b shows a wafer-level hermetic micro-device package having same-side electrical connections;

[0062] FIG. 21c is an exploded view illustrating the method of assembly of the package of FIG. 21b;

[0063] FIG. 22 illustrates a semiconductor wafer having a multiple micro-devices formed thereupon suitable for multiple simultaneous wafer-level packaging;

[0064] FIG. 23 illustrates the semiconductor wafer of FIG. 22 after metallization of the wafer surface;

[0065] FIG. 24 illustrates a metallic frame for attachment between the wafer surface and the window sheet of a hermetic package;

[0066] FIGS. 25a-25d show enlarged views of the frame members of FIG. 24; specifically:

[0067] FIG. 25a is a top view of a portion of a double frame member prior to singulation;

[0068] FIG. 25b is an end view of the double frame member of FIG. 25a;

[0069] FIG. 25c is a top view of a portion of a single frame member from the perimeter of the frame, or after device singulation; and

[0070] FIG. 25d is an end view of the single frame member of FIG. 25c;

[0071] FIG. 26 illustrates a metallized window sheet for attachment to the frame of FIG. 24;

[0072] FIG. 27 shows a cross-sectional side view of a multiple-package assembly prior to singulation;

[0073] FIG. 28 illustrates one option for singulation of the multiple-package assembly of FIG. 27;

[0074] FIG. 29 illustrates another option for singulation of the multiple-package assembly of FIG. 27;

[0075] FIG. 30 illustrates a semiconductor wafer after metallization of the wafer surface in accordance with another embodiment having an electrode placement portion;

[0076] FIG. 31 illustrates a metallized window sheet in accordance with another embodiment having an electrode placement portion;

[0077] FIG. 32 is a cross-sectional side view of a multiple-package assembly prior to singulation in accordance with another embodiment having direct electrode access;

[0078] FIG. 33 is a top view of a micro-device with same-side pads;

[0079] FIG. 34 illustrates a semiconductor wafer having formed thereon a plurality of the micro-devices of FIG. 33;

[0080] FIG. 35 illustrates the semiconductor wafer of FIG. 34 after metallization of the wafer surface;

[0081] FIG. 36 illustrates a metallic frame for attachment to the wafer surface of FIG. 35;

[0082] FIG. 37 illustrates a metallized window sheet for attachment to the frame of FIG. 36;

[0083] FIG. 38 shows a top view a complete multiple-package assembly;

[0084] FIG. 39 illustrates a multi-package strip after column separation of the multiple-package assembly of FIG. 38; and

[0085] FIG. 40 illustrates a single packaged micro-device after singulation of the multiple-package strip of FIG. 39.

DETAILED DESCRIPTION OF THE INVENTION AND BEST MODE

[0086] Referring now to FIGS. 1 and 2, there is illustrated a typical hermetically sealed micro-device package for housing one or more micro-devices. For purposes of this application, the term “micro-device” includes photonic devices, photovoltaic devices, optical devices (i.e., including reflective, refractive and diffractive type devices), electro-optical and electro-optics devices (EO devices), light emitting devices (LEDs), liquid crystal displays (LCDs), liquid crystal on silicon (LCOS) technologies inch includes direct drive image light amplifiers (D-ILA), opto-mechanical devices, micro-optoelectromechanical systems (i.e., MOEMS) devices and micro-electromechanical systems (i.e., MEMS) devices. The package 102 comprises a base or substrate 104 which is hermetically sealed to a cover assembly 106 comprising a frame 108 and a transparent window 110. A micro-device 112 mounted on the base 104 is encapsulated within a cavity 114 when the cover assembly 106 is joined to the base 104. One or more electrical leads 116 may pass through the base 104 to carry power, ground, and signals to and from the micro-device 112 inside the package 102. It will be appreciated that the electrical leads 116 must also be hermetically sealed to maintain the integrity of the package 102. The window 110 is formed of an optically or electromagnetically transparent material. For purposes of this application, the term “transparent” refers to materials which allow the transmission of electromagnetic radiation having predetermined wavelengths, including, but not limited to, visible light, infrared light, ultraviolet light, microwaves, radio waves, or x-rays. The frame 108 is formed from a material, typically a metal alloy, which preferably has a CTE close to that of both the window 110 and the package base 104.

[0087] Referring now to FIG. 3, there is illustrated an exploded view of a cover assembly manufactured in accordance with one embodiment of the current invention. The cover assembly 300 includes a frame 302 and a sheet 304 of a transparent material. The frame 302 has a continuous sidewall 306 which defines a frame aperture 308 passing therethrough. The frame sidewall 306 includes a frame seal-ring area 310 (denoted by crosshatching) circumscribing the frame aperture 308. Since the frame 302 will eventually be welded to the package base 104 (from FIGS. 1 and 2,) it is usually formed of a weldable metal or alloy, preferably one having a CTE very close to that of the micro-device package base 104. In some embodiments, however, the cover assembly frame 304 may be formed of a non-metallic material such as ceramic or alumina. Regardless of whether the frame 302 is formed of a metallic or non-metallic material, the surface of the frame seal-ring area 310 is preferably metallic (e.g., metal plated if not solid metal) to facilitate the hermetic sealing of the sheet 304 to the frame. In a preferred embodiment, the frame is primarily

formed of an alloy having a nominal chemical composition of 54% iron (Fe), 29% nickel (Ni) and 17% cobalt (Co). Such alloys are also known by the designation ASTM F-15 alloy and by the trade name Kovar Alloy. As used in this application, the term “Kovar Alloy” will be understood to mean the alloy having the chemical composition just described. In embodiments where a Kovar Alloy frame 302 is used, it is preferred that the surface of the frame seal-ring area 310 have a surface layer of gold (Au) overlying a layer of nickel (Ni), or a layer of nickel without the overlying gold. The frame 302 also includes a base seal area 320 which is adapted for eventual joining, typically by welding, to the package base 104. The base seal area 320 frequently includes a layer of nickel overlaid by a layer of gold to facilitate seam welding to the package base. Although the gold over nickel surface layers are only required along the base seal-ring area 320, it will be appreciated that in many cases, for example, where solution bath plating is used to apply the surface materials, the gold over nickel layers may be applied to the entire surface of the frame 302. The sheet 304 can be any type of transparent material, for example, soft glass (e.g., soda-lime glass), hard glass (e.g. borosilicate glass), crystalline materials such as quartz and sapphire, or polymeric materials such as polycarbonate plastic. In addition to optically transparent materials, the sheet 304 may be visibly opaque but transparent to non-visible wavelengths of energy. As previously discussed, it is preferred that the material of the sheet 304 have a CTE that is similar to that of the frame 304 and of the package base 104 to which the cover assembly will eventually be attached. For many semiconductor photonic, photovoltaic, MEMS or MOEMS applications, a borosilicate glass is well suited for the material of the sheet 304. Examples of suitable glasses include Corning 7052, 7050, 7055, 7056, 7058, 7062, Kimble (Owens Corning) EN-1, and Kimble K650 and K704. Other suitable glasses include Abrisa soda-lime glass, Schott 8245 and Ohara Corporation S-LAM60.

[0088] The sheet 304 has a window portion 312 defined thereupon, i.e., this is the portion of the sheet 302 which must remain transparent to allow for the proper functioning of the encapsulated, i.e., packaged, micro-device 112. The window portion 312 of the sheet has top and bottom surfaces 314 and 316, respectively, that are optically finished in the preferred embodiment. The sheet 304 is preferably obtained with the top and bottom surfaces 314 and 316 of the window portion 312 in ready to use form, however, if necessary the material may be ground and polished or otherwise shaped to the desired surface contour and finish as a preliminary step of the manufacturing process. While in many cases the window portion 312 will have top and bottom surfaces of 314 and 316 that are optically flat and parallel to one another, it will be appreciated that in other embodiments at least one of the finished surfaces of the window portion will be contoured. A sheet seal-ring area 318 (denoted with cross-hatching) circumscribes the window portion 312 of the sheet 304, and provides a suitable surface for joining to the front seal-ring area 310.

[0089] Referring now to FIGS. 4a and 4b, there are illustrated transparent sheets having contoured sides. In FIG. 4a, transparent sheet 304' has both a curved top side 314' and a curved bottom side 316' producing a window portion 312 having a curved contour with a constant thickness. In FIG. 4b, sheet 304" has a top side 314" which is curved and a bottom side 316" which is flat, thereby result-

ing in a window portion **312** having a plano-convex lens arrangement. It will be appreciated that in similar fashion (not illustrated) the finished surfaces **314** and **316** of the window portion **312** can have the configuration of a refractive lens including a plano-convex lens as previously illustrated, a double convex lens, a plano-concave lens or a double concave lens. Other surface contours may give the finished surfaces of the window portion **312** the configuration of a Fresnel lens or of a diffraction grating, i.e., “a diffractive lens.”

[0090] In many applications, it is desirable that window portion **312** of the sheet **304** have enhanced optical or physical properties. To achieve these properties, surface treatments or coatings may be applied to the sheet **304** prior to or during the assembly process. For example, the sheet **304** may be treated with silicon oxynitride (SiOn) to provide a harder surface on the window material. Whether or not treated with SiOn, the sheet **304** may be coated with a scratch resistant/abrasion resistant material such as amorphous diamond-like carbon (DLC) such as that sold by Diamonex, Inc., under the name Diamond Shield®. Other coatings which may be applied in addition to, or instead of, the SiOn or diamond-like carbon include, but are not limited to, optical coatings, anti-reflective coatings, refractive coatings, achromatic coatings, optical filters, solar energy filters or reflectors, electromagnetic interference (EMI) and radio frequency (RF) filters of the type known for use on lenses, windows and other optical elements. It will be appreciated that the optical coatings and/or surface treatments can be applied either on the top surface **314** or the bottom surface **316**, or in combination on both surfaces, of the window portion **312**. It will be further appreciated, that the optical coatings and treatments just described are not illustrated in the figures due to their transparent nature.

[0091] In some applications, a visible aperture is formed around the window portion **312** of the sheet **304** by first depositing a layer of non-transparent material, e.g., chromium (Cr), sometimes coating the material over the entire surface of the sheet and then etching the non-transparent material from the desired aperture area. This procedure provides a sharply defined border to the window portion **312** which is desirable in some applications. This operation may be performed prior to or after the application of other treatments depending on the compatibility and processing economics.

[0092] The next step of the process of manufacturing the cover assembly **300** is to prepare the sheet seal-ring area **318** for metallization. The sheet seal-ring area **318** circumscribes the window portion **312** of the sheet **304**, and for single aperture covers is typically disposed about the perimeter of the bottom surface **316**. It will be appreciated, however, that in some embodiments the sheet seal-ring area **318** can be located in the interior portion of a sheet, for example where the sheet will be diced to form multiple cover assemblies (i.e., as described later herein). The sheet seal-ring area **318** generally has a configuration which closely matches the configuration of the frame seal-ring area **310** to which it will eventually be joined. Preparing the sheet seal-ring area **318** may involve a thorough cleaning to remove any greases, oils or other contaminants from the surface, and/or it may involve roughening the seal-ring area by chemical etching, laser ablating, mechanical grinding or sandblasting this area. This roughening increases the surface area of the sheet

seal-ring, thereby providing increased adhesion for the subsequently deposited metallization materials, if the sheet seal-ring is to be metallized prior to joining to the frame seal-ring area **310** or to other substrates or device package bases.

[0093] Referring now to **FIG. 5**, there is illustrated a portion of the sheet **304** which has been placed bottom side up to better illustrate the preparation of the sheet seal-ring area **318**. In this example the seal-ring area **318** has been given a roughened surface **501** to improve adhesion of the metallic layers to be applied. Chemical etching to roughen glass and similar transparent materials is well known. Alternatively, laser ablating, conventional mechanical grinding or sandblasting may be used. A grinding wheel with **325** grit is believed suitable for most glass materials, while a diamond grinding wheel may be used for sapphire and other hardened materials. The depth **502** to which the roughened surface **501** of the sheet seal-ring area **318** penetrates the sheet **304** is dependent on at least two factors: first, the desired mounting height of the bottom surface **316** of the window relative to the package bottom and/or the micro-device **112** mounted inside the package; and second, the required thickness of the frame **306** including all of the deposited metal layers (described below). It is believed that etching or grinding the sheet seal-ring area **318** to a depth of **502** within the range from about 0 inches to about 0.05 inches will provide a satisfactory adhesion for the metallized layers as well as providing an easily detectable “lip” for locating the sheet **304** in the proper position against the frame **306** during subsequent joining operations.

[0094] It will be appreciated that it may be necessary or desirable to protect the finished surfaces **314** and/or **316** in the window portion **312** of the sheet (e.g., the portions that will be optically active in the finished cover assembly) from damage during the roughening process. If so, the surfaces **314** and/or **316** may be covered with semiconductor-grade “tacky tape” or other known masking materials prior to roughening. The mask material must, of course, be removed in areas where the etching/grinding will take place. Sandblasting is probably the most economical method of selectively removing strips of tape or masking material in the regions that will be roughened. If sandblasting is used, it could simultaneously perform the tape removal operation and the roughening of the underlying sheet.

[0095] Referring now to **FIG. 6**, there is illustrated a view of the seal-ring area **318** of the sheet **304** after metallization. The next step of the manufacturing process may be to apply one or more metallic layers to the prepared sheet seal-ring area **318**. The current invention contemplates several options for accomplishing this metallization. A first option is to apply metal layers to the sheet seal-ring area **318** using conventional chemical vapor deposition (CVD) technology. CVD technology includes atmospheric pressure chemical vapor deposition (APCVD), low pressure chemical vapor deposition (LPCVD), plasma assisted (enhanced) chemical vapor deposition (PACVD, PECVD), photochemical vapor deposition (PCVD), laser chemical vapor deposition (LCVD), metal-organic chemical vapor deposition (MOCVD) and chemical beam epitaxy (CBE). A second option for metallizing the roughened seal-ring area **318** is using physical vapor deposition (PVD) technology. PVD technology includes sputtering, ion plasma assist, thermal evaporation, vacuum evaporation, and molecular beam epi-

taxy (MBE). A third option for metallizing the roughened sheet seal-ring area **318** is using solution bath plating technology (SBP). Solution bath plating includes electroplating, electroless plating and electrolytic plating technology. While solution bath plating cannot be used for depositing the initial metal layer onto a nonmetallic surface such as glass or plastic, it can be used for depositing subsequent layers of metal or metal alloy to the initial layer. Further, it is envisioned that in many cases, solution bath plating will be the most cost effective metal deposition technique. Since the use of chemical vapor deposition, physical vapor deposition and solution bath plating to deposit metals and metal alloys is well known, these techniques will not be further described herein.

[0096] A fourth option for metallizing the sheet seal-ring area **318** of the sheet **304** is so-called cold-gas dynamic spray technology, also known as “cold-spray”. This technology involves the spraying of powdered metals, alloys, or mixtures of metal and alloys onto an article using a jet of high velocity gas to form continuous metallic coating at temperatures well below the fusing temperatures of the powdered material. Details of the cold-gas dynamic spray deposition technology are disclosed in U.S. Pat. No. 5,302,414 to Alkhimov et al. It has been determined that aluminum provides good results when applied to glass using the cold-gas dynamic spray deposition. The aluminum layer adheres extremely well to the glass and may create a chemical bond in the form of aluminum silicate. However, other materials may also be applied as a first layer using cold-spray, including tin, zinc, silver and gold. Since the cold-gas dynamic spray technology can be used at low temperatures (e.g., near room temperature), it is suitable for metallizing materials having a relatively low melting point, such as polycarbonates or other plastics, as well as for metallizing conventional materials such as glass, alumina, and ceramics.

[0097] For the initial metallic layer deposited on the sheet **304**, it is believed that any of chromium, nickel, aluminum, tin, tin-bismuth alloy, gold, gold-tin alloy can be used, this list being given in what is believed to be the order of increasing adhesion to glass. Other materials might also be appropriate. Any of these materials can be applied to the sheet seal-ring area **318** using any of the CVD or PVD technologies (e.g., sputtering) previously described. After the initial layer **602** is deposited onto the sheet seal-ring area **318** of the nonmetallic sheet **304**, additional metal layers, e.g., second layer **604**, third layer **606** and fourth layer **608** (as applicable) can be added by any of the deposition methods previously described, including solution bath plating. It is believed that the application of the following rules will result in satisfactory thicknesses for the various metal layers. Rule No. 1: the minimum thickness, except for the aluminum or tin-based metals or alloys which will be bonded to the gold-plated Kovar alloy frame: 0.002 microns. Rule 2: the minimum thickness for aluminum or tin-based metals or alloys deposited onto the sheet or as the final layer, which will be bonded to the gold-plated Kovar alloy frame: 0.8 microns. Rule 3: the maximum thickness for aluminum or tin-based metals or alloys deposited onto the sheet or as the final layer, which will be bonded to the gold-plated Kovar alloy frame: 63.5 microns. Rule 4: the maximum thickness for metals, other than chromium, deposited onto the sheet as the first layer and which will have other metals or alloys deposited on top of them: 25 microns. Rule 5: the

maximum thickness for metals, other than chromium, deposited onto other metals or alloys as intermediate layers: 6.35 microns. Rule 6: the minimum thickness for metals or alloys deposited onto the sheet or as the final layer, which will act as the solder for attachment to the gold-plated Kovar alloy frame: 7.62 microns. Rule 7: the maximum thickness for metals or alloys deposited onto the sheet or as the final layer, which will act as the solder for attachment to the gold-plated Kovar alloy frame: 101.6 microns. Rule 8: the maximum thickness for chromium: 0.25 microns. Rule 9: the minimum thickness for gold-tin solder, applied via inkjet or supplied as a solder preform: 6 microns. Rule 10: the maximum thickness for gold-tin solder, applied via inkjet or supplied as a solder preform: 101.6 microns. Rule 11: The minimum thickness for immersion zinc: 0.889 microns. Note that the above rules apply to metals deposited using all deposition methods other than cold-gas dynamic spray deposition.

[0098] For cold spray applications, the following rules apply: Rule 1: the minimum practical thickness for any metal layer: 2.54 microns. Rule 2: the maximum practical thickness for the first layer, and all additional layers, but not including the final Kovar alloy layer: 127 microns. Rule 3: the maximum practical thickness for the final Kovar alloy layer: 12,700 microns, i.e., 0.5 inches.

[0099] By way of example, not to be considered limiting, the following metal combinations are believed suitable for seal-ring area **318** when bonding the prepared sheet **304** to a Kovar alloy-nickel-gold frame **302** (i.e., Kovar alloy core plated first with nickel and then with gold) using thermal compression (TC) bonding, or sonic, ultrasonic or thermosonic bonding.

[0100] The assembly sequence can also be to first bond the frame/spacer and window sheet together to form a hermetically sealed window unit, and later, to bond this window unit to the substrate. A third assembly sequence can also be to first bond the frame/spacer and substrate together and later, to bond this substrate/frame/spacer unit to the window. In some instances, an intermediate material, also referred to as an interlayer material, maybe employed between the substrate and the frame/spacer and/or between the frame/spacer and the window sheet. It will be understood that, while the examples described herein are believed suitable for metallizing the seal-ring surface of a sheet or lens prior to bonding in applications where metallization is used, in some other embodiments employing diffusion bonding (i.e., thermal compression bonding), metallization of the seal-ring area on the sheet or lens may be omitted altogether when joining the sheet/lens to the frame or another substrate of the device package base.

EXAMPLE 1

[0101]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.7	63.5

EXAMPLE 2

[0102]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Cu	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Sn or SnBi	CVD, PVD, SBP	0.7	63.5

EXAMPLE 3

[0103]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Sn or Sn—Bi	CVD, PVD, SBP	0.7	63.5

EXAMPLE 4

[0104]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Sn or Sn—Bi	CVD, PVD, SBP	0.7	63.5

EXAMPLE 5

[0105]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn (de-stressed)	CVD, PVD	0.002	25
2	Cu	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Sn or Sn—Bi	CVD, PVD, SBP	0.7	63.5

EXAMPLE 6

[0106]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn—Bi	CVD, PVD	0.7	63.5

EXAMPLE 7

[0107]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Ni	CVD, PVD, SBP	0.002	6.35
3	Sn or Sn—Bi	CVD, PVD, SBP	0.7	63.5

EXAMPLE 8

[0108]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Ni	CVD, PVD, SBP	0.002	6.35
3	Al	CVD, PVD, SBP	0.7	63.5

EXAMPLE 9

[0109]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Ni	CVD, PVD, SBP	0.002	6.35
3	Zn	CVD, PVD, SBP	0.002	6.35
4	Al	CVD, PVD, SBP	0.7	63.5

EXAMPLE 10

[0110]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.002	152.4
2	Sn or Sn—Bi	CVD, PVD, SBP	0.7	63.5

EXAMPLE 11

[0111]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.002	152.4
2	Al	CVD, PVD, SBP	0.7	63.5

EXAMPLE 12

[0112]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.002	152.4
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Al	CVD, PVD, SBP	0.7	63.5

EXAMPLE 13

[0113]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn	CVD, PVD	0.7	63.5

EXAMPLE 14

[0114]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15

EXAMPLE 15

[0115]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.002	152.4

EXAMPLE 16

[0116]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn—Bi	CVD, PVD	0.7	63.5

[0117] By way of further example, not to be considered limiting, the following metal combinations and thicknesses are preferred for seal-ring area **318** when bonding the prepared sheet **304** to a Kovar alloy-nickel-gold frame **302** using thermal compression (TC) bonding, or sonic, ultra-sonic or thermosonic bonding.

EXAMPLE 17

[0118]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	1	50.8

EXAMPLE 18

[0119]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Cu	CVD, PVD, SBP	0.25	2.54
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn or SnBi	CVD, PVD, SBP	1	50.8

EXAMPLE 19

[0120]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn or Sn—Bi	CVD, PVD, SBP	1	50.8

EXAMPLE 20

[0121]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Sn or Sn—Bi	CVD, PVD, SBP	1	50.8

EXAMPLE 21

[0122]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn (de-stressed)	CVD, PVD	0.1	2.54
2	Cu	CVD, PVD, SBP	0.25	2.54
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn or Sn—Bi	CVD, PVD, SBP	1	50.8

EXAMPLE 22

[0123]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn—Bi	CVD, PVD	1	50.8

EXAMPLE 23

[0124]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Ni	CVD, PVD, SBP	1	5.08
3	Sn or Sn—Bi	CVD, PVD, SBP	1	50.8

EXAMPLE 24

[0125]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Ni	CVD, PVD, SBP	1	5.08
3	Al	CVD, PVD, SBP	1	50.8

EXAMPLE 25

[0126]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Ni	CVD, PVD, SBP	1	5.08
3	Zn	CVD, PVD, SBP	0.3175	5.08
4	Al	CVD, PVD, SBP	1	50.8

EXAMPLE 26

[0127]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	5.08
2	Sn or Sn—Bi	CVD, PVD, SBP	1	50.8

EXAMPLE 27

[0128]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	5.08
2	Al	CVD, PVD, SBP	1	50.8

EXAMPLE 28

[0129]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	5.08
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Al	CVD, PVD, SBP	1	50.8

EXAMPLE 29

[0130]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn	CVD, PVD	1	50.8

EXAMPLE 30

[0131]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12

EXAMPLE 31

[0132]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	50.8

EXAMPLE 32

[0133]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn—Bi	CVD, PVD	1	50.8

[0134] As indicated above, the previous examples are believed suitable for application of, among other processes,

thermal compression bonding. TC bonding is a process of diffusion bonding in which two prepared surfaces are brought into intimate contact, and plastic deformation is induced by the combined effect of pressure and temperature, which in turn results in atom movement causing the development of a crystal lattice bridging the gap between facing surfaces and resulting in bonding. TC bonding can take place at significantly lower temperatures than many other forms of bonding such as braze soldering.

[0135] Referring now to **FIG. 7**, there is illustrated a cross-sectional view of the prefabricated frame **302** suitable for use in this embodiment. The illustrated frame **302** includes a Kovar alloy core **702**, or a core of different metal or alloy, overlaid with a first metallic layer **704** of nickel which, in turn, is overlaid by an outer layer **706** of gold. The use of Kovar alloy for the core **702** of the frame **302** may be preferred where hard glass, e.g., Corning 7056 or 7058, is used for the sheet **304** and where Kovar alloy or a similar material is used for the package base **104**, since these materials have a CTE for the temperature range 30° C. to 300° C. that is within the range from about $5.0 \cdot 10^{-6}/^{\circ}\text{K}$ to about $5.6 \cdot 10^{-6}/^{\circ}\text{K}$ (e.g. from about 5.0 to about 5.6 ppm/ $^{\circ}\text{K}$).

[0136] Referring still to **FIG. 7**, another step of the manufacturing process is the preparation of a prefabricated frame **302** for joining to the sheet **304**. As previously described, the frame **302** includes a continuous sidewall **306** which defines an aperture **308** therethrough. The sidewall **306** includes a frame seal-ring area **310** on its upper surface and a base seal-ring area **320** on its lower surface. The frame seal-ring area **310** is generally dimensioned to conform with the sheet seal-ring area **318** of the transparent sheet **304**, while the base seal-ring area **320** is generally dimensioned to conform against the corresponding seal area on the package base. The frame **302** may be manufactured using various conventional metal forming technologies, including stamping, casting, die casting, extrusion/parting, and machining. It is contemplated that stamping or die casting may be the most cost effective method for producing the frames **302**. However, fabricating the frame **302** using photo-chemical machining (PCM), also known as chemical etching, may, in some instances be the most economical method. In some instances, several sheets of photo-chemical machined (i.e., etched) metals and/or alloy might be bonded together to form the frame **302**. One of the bonding methods includes TC bonding, also known as diffusion bonding, the PCM'd layers together to create the frame **302**. Depending upon the degree of flatness required for the contemplated bonding procedure and the degree achieved by a particular frame manufacturing method, surface grinding, and possibly even lapping or polishing, may be required on the frame seal-ring area **310** or base seal-ring area **320**, to provide the final flatness necessary for a successful hermetic seal.

[0137] In this example, the base seal-ring area **320** is on the frame face opposite frame seal-ring area **310**, and may utilize the same layers of nickel **704** overlaid by gold **706** to facilitate eventual welding to the package base **104**. In some instances, the gold **706** will not be overlaid on the nickel **704**.

[0138] In some embodiments, the frame **302** will serve as a "heat sink" and/or "heat spreader" when the cover assembly **300** is eventually welded to the package base **104**. It is

contemplated that conventional high temperature welding processes (e.g., manual or automatic electrical resistance seam welding or laser welding) may be used for this operation. If the metallized glass sheet **304** were welded directly to the package base **104** using these welding processes, the concentrated heat could cause thermal stresses likely to crack the glass sheet or distort its optical properties. However, when a metal frame is attached to the transparent sheet, it acts as both a heat sink, absorbing some of the heat of welding, and as a heat spreader, distributing the heat over a wider area such that the thermal stress on the transparent sheet **304** is reduced to minimize the likelihood of cracking or optical distortion. Kovar alloy is especially useful in this heat sink and heat spreading role as explained by Kovar alloy's thermal conductivity, 0.0395, which is approximately fourteen times higher than the thermal conductivity of Corning 7052 glass, 0.0028.

[0139] Another important aspect of the frame **302** is that it should be formed from a material having a CTE that is similar to the CTE of the transparent sheet **304** and the CTE of the package base **104**. This matching of CTE between the frame **302**, transparent sheet **304** and package base **104** is beneficial to minimize stresses between these components after they are joined to one another so as to ensure the long term reliability of the hermetic seal therebetween under conditions of thermal cycling and/or thermal shock environments.

[0140] For window assemblies that will be attached to package bases formed of ceramic, alumina or Kovar alloy, Kovar alloy is preferred for use as the material for the frame **304**. Although Kovar alloy will be used for the frames in many of the embodiments discussed in detail herein, it will be understood that Kovar alloy is not necessarily suitable for use with all transparent sheet materials. Additionally, other frame materials besides Kovar alloy may be suitable for use with glass. Suitability is determined by the desire that the material of the transparent sheet **304**, the material of the frame **302** and the material of the package base **104** all have closely matching CTEs to insure maximum long-term reliability of the hermetic seals.

[0141] Referring now to **FIG. 8**, the next step of the manufacturing process is to position the frame **302** against the sheet **304** such that at least a portion of the frame seal-ring area **310** and a least a portion of the sheet seal-ring area **318** contact one another along a continuous junction region **804** that circumscribes the window portion **312**. Actually, in some cases a plasma-cleaning operation and/or a solvent or detergent cleaning operation is performed on the seal-ring areas and any other sealing surfaces just prior to joining the components to ensure maximum reliability of the joint. In **FIG. 8**, the sheet **304** moves from its original position (denoted in broken lines) until it is in contact with the frame **302**. It is, of course, first necessary to remove any remaining tacky tape or other masking materials left over from operations used to prepare the sheet seal-ring area **318** if they cannot withstand the elevated temperatures encountered in the joining process without degradation of the mask material and/or its adhesive, if an adhesive is used to attach the mask to the sheet. It will be appreciated that it is not necessary that the sheet seal-ring area **318** and the frame seal-ring area **310** have an exact correspondence with regard to their entire areas, rather, it is only necessary that there be some correspondence between the two seal-ring areas form-

ing a continuous junction region **804** which circumscribes the window portion **312**. In the embodiment illustrated in **FIG. 8**, the metallized layers **610** in the sheet seal-ring area **318** are much wider than the plated outer layer **706** of the frame seal-ring area **310**. Further, the window portion **312** of the sheet **304** extends partway through the frame aperture **308**, providing a means to center the sheet **304** on the frame **302**.

[0142] The next step of the manufacturing process is to heat the junction region **804** until a joint is formed between the frame **302** and the sheet **304** all along the junction region, whereby a hermetic seal circumscribing the window portion **312** is formed. It is necessary that during the step of heating the junction region **804**, the temperature of the window portion **312** of the sheet **304** remain below its glass transition temperature, T_G as well as below the softening temperature of the sheet **304**, to prevent damage to the finished surfaces **314** and **316**. The softening point for glass is defined as the temperature at which the glass has a viscosity of 107.6 dPa s or 107.6 poise (method of measurement: ISO 7884-3). The current invention contemplates several options for accomplishing this heating. A first option is to utilize thermal compression (TC) bonding, also known as diffusion bonding, including conventional hot press bonding as well as Hot Isostatic Press or Hot Isostatic Processing (HIP) diffusion bonding. As previously described, TC bonding, also known as diffusion bonding involves the application of high pressures to the materials being joined such that a reduced temperature is required to produce the necessary diffusion bond. Rules for determining the thickness and composition of the metallic layers **610** on the sheet **304** were previously provided, for TC bonding to, e.g., a Kovar alloy, nickel or gold frame such as illustrated in **FIG. 7**. The estimated process parameters for the TC bonding of a Kovar alloy/nickel/gold frame **302** to a metallized sheet **304** having aluminum as the final layer would be a temperature of approximately 380° C. at an applied pressure of approximately 95,500 psi (6713.65 kg/cm²). Under these conditions, the gold plating **706** on the Kovar alloy frame **302** will diffuse into/with the aluminum layer, e.g., layer **4** in Example 7. Since the 380° C. temperature necessary for TC bonding is below the approximately 500° C. to 900° C. T_G for hard glasses such as Corning 7056, the TC bonding process could be performed in a single or batch mode by fixturing the cover assembly components **302**, **304** together in compression and placing the compressed assemblies into a furnace (or oven, etc.) at approximately 380° C. The hermetic bond would be obtained without risking the finished surfaces **314** and **316** of the window portion **312**. Vacuum, sometimes with some small amounts of specific gasses included, or other atmospheres with negative or positive pressures might be needed inside the furnace to promote the TC bonding process.

[0143] Alternatively, employing resistance welding at the junction area **804** to add additional heat in addition to the TC bonding could allow preheating the window assemblies to less than 380° C. and possibly reduce the overall bonding process time. In another method, the TC bonding could be accomplished by fixturing the cover assembly components **302** and **304** using heated tooling that would heat the junction area **304** by conduction. In yet another alternative method, electrical resistance welding can be used to supply 100% of the heat required to achieve the necessary TC

bonding temperature, thereby eliminating the need for furnaces, ovens, etc. or specialized thermally conductive tooling.

[0144] After completion of TC bonding or other welding processes, the window assembly **300** is ready for final processing, for example, chamfering the edges of the cover assembly to smooth them and prevent chipping, scratching, marking, etc., during post-assembly, cleaning, marking or other operations. In some instances, the final processing may include the application of a variety of coatings to the window and/or to the frame.

[0145] Referring now to **FIG. 9**, there is illustrated a block diagram of the manufacturing process just described in accordance with one embodiment of the current invention. Block **902** represents the step of obtaining a sheet of transparent material, e.g., glass or other material, having finished top and bottom surfaces as previously described. The process then proceeds to block **904** as indicated by the arrow.

[0146] Block **904** represents the step of applying surface treatments to the sheet, e.g., scratch-resistant or anti-reflective coatings, as previously described. In addition to these permanent surface treatments, block **904** also represents the sub-steps of applying tape or other temporary masks to the surfaces of the sheet to protect them during the subsequent steps of the process. It will be appreciated that the steps represented by block **904** are optional and that one or more of these steps may not be present in every embodiment of the invention. The process then proceeds to block **906** as indicated by the arrow.

[0147] Block **906** represents the step of preparing the seal-ring area on the sheet to provide better adhesion for the metallic layers, if such metallic layers are used. This step usually involves roughening the seal-ring area using chemical etching, mechanical grinding, laser ablating or sandblasting as previously described. To the extent necessary, block **906** also represents the sub-steps of removing any masking material from the seal-ring area. Block **906** further represents the optional steps of cleaning the sheet (or at least the seal-ring area of the sheet) to remove any greases, oils or other contaminants from the surface of the sheet. As previously discussed, such cleaning steps may be performed regardless of whether the seal-ring area is to be metallized (i.e., to promote better adhesion of the metallic layers) or is to be left unmetallized (i.e., to promote better diffusion bonding of the unmetallized sheet). It will be appreciated that the steps represented by block **906** are optional and that some or all of these steps may not be present in every embodiment of the invention. The process then proceeds to block **908** as indicated by the arrow.

[0148] Block **908** represents the step of metallizing the seal-ring areas of the sheet. The step represented by block **908** is mandatory only when the desired bond of sheet **304** to frame **302** is a metal-to-metal bond since at least one metallic layer must be applied to the seal-ring area of the sheet. It is possible, for instance by use of diffusion bonding processes, to bond the sheet **304** to frame **302** without first metallizing sheet **304**. In most embodiments, block **908** will represent numerous sub-steps for applying successive metallic layers to the sheet, where the layers of each sub-step may be applied by processes including CVD, PVD, cold-spray or solution bath plating as previously described. Following the

steps represented by block **908**, the sheet is ready for joining to the frame. However, before the process can proceed to this joining step (i.e., block **916**), a suitable frame must first be prepared.

[0149] Block **910** represents the step of obtaining a pre-fabricated frame, preferably having a CTE that closely matches the CTE of the transparent sheet from block **902** and the CTE of the package base. In most cases where the base is alumina or Kovar alloy, a frame formed of Kovar alloy will be suitable. As previously described, the frame may be formed using, e.g., stamping, die-casting or other known metal-forming processes. The process then proceeds to block **912** as indicated by the arrow.

[0150] Block **912** represents the step of grinding, polishing and/or otherwise flattening the seal-ring areas of the frame as necessary to increase its flatness so that it will fit closely against the seal-ring areas of the transparent sheet. It will be appreciated that the steps represented by block **912** are optional and may not be necessary or present in every embodiment of the invention. The process then proceeds to block **914** as indicated by the arrow.

[0151] Block **914** represents the step of applying additional metallic layers to the seal-ring areas of the frame. These metallic layers are sometimes necessary to achieve compatible chemistry for bonding with the metallized seal-ring areas of the transparent sheet. In most embodiments, block **914** will represent numerous sub-steps for applying successive metallic layers to the frame. Block **914** further represents the optional steps of cleaning the frame (or at least the seal-ring area of the frame) to remove any greases, oils or other contaminants from the surface of the frame. As previously discussed, such cleaning steps may be performed regardless of whether the seal-ring area of the frame is to be metallized with additional metal layers or is to be used without additional metallization. Once the steps represented by block **914** are completed, the frame is ready for joining to the transparent sheet. Thus, the results of process block **908** and block **914** both proceed to block **916** as indicated by the arrows.

[0152] Block **916** represents the step of clamping the prepared frame together with the prepared transparent sheet so that their respective metallized seal-ring areas are in contact with one another under conditions producing a predetermined contact pressure at the junction region circumscribing the window portion. This predetermined contact pressure between the seal-ring surfaces allows thermal compression (TC) bonding of the metallized surfaces to occur at a lower temperature than would be required for conventional welding (including most soldering and brazing processes). The process then proceeds to block **918** as indicated by the arrow.

[0153] Block **918** represents the step of applying heat to the junction between the frame and the transparent sheet while maintaining the predetermined contact pressure until the temperature is sufficient to cause thermal compression bonding to occur. In some embodiments, block **918** will represent a single heating step, e.g., heating the fixtured assembly in a furnace. In other embodiments, block **918** will represent several sub-steps for applying heat to the junction area, for example, first preheating the fixtured assembly (e.g., in a furnace) to an intermediate temperature, and then using resistance welding techniques along the junction to

raise the temperature of the localized area of the metallic layers the rest of the way to the temperature where thermal compression bonding will occur. The thermal compression bonding creates a hermetic seal between the transparent sheet material and the frame. The process then proceeds to block **920** as indicated by the arrow.

[0154] In the illustrated example, metallized seal-ring areas are joined using diffusion bonding/thermal compression bonding in which the predetermined pressure is applied first (block **916**) and the heat is applied second (block **918**). It will be appreciated, however, that the use of diffusion bonding is not limited to these specific conditions. In some other embodiments, the sheet and/or frame may not be metallized prior to bonding. In still other embodiments, the heat may be applied first until the desired bonding temperature is reached, and the predetermined pressure may be applied thereafter until the diffusion bond is formed. In yet additional embodiments, the heat and pressure may be applied simultaneously until the diffusion bond is formed.

[0155] Block **920** represents the step of completing the window assembly. Block **920** may represent merely cooling the window assembly after thermal compression bonding, or it may represent additional finishing processes including chamfering the edges of the assembly to prevent chipping, cracking, etc., marking the assembly, coating the window and/or the frame with one or more materials, or other post-assembly procedures. The process of this embodiment has thus been described.

[0156] It will be appreciated that in alternative embodiments of the invention, conventional welding techniques (including soldering and/or brazing) may be used instead of thermal compression bonding to join the frame to the transparent sheet. In such alternative embodiments, the steps represented by blocks **916** and **918** of FIG. 9 would be replaced by the steps of fixturing the frame and transparent sheet together so that the metallized seal-ring areas are in contact with one another (but not necessarily producing a predetermined contact pressure along the junction) and then applying heat to the junction area using conventional means until the temperature is sufficient to cause the melting and diffusing of the metallic layers necessary to achieve the welded bond.

[0157] In an alternative embodiment, braze-soldering is used to join the frame **302** to the metallized sheet **304**. In this embodiment, a solder metal or solder alloy may be utilized as the final layer of the metallic layers **610** on the metallized sheet **304**, and clamping the sheet **304** to the frame **302** at a high predetermined contact pressure is not required. A solder metal or solder alloy preform may be utilized as a separate, intermediate item between the frame **302** and the sheet **304** instead of having a solder metal or solder alloy as the final layer of the metallic layers **610** on the metallized sheet **304**. Light to moderate clamping pressure can be used: 1) to insure alignment during the solder's molten phase; and 2) to promote even distribution of the molten solder all along the junction region between the respective seal-ring areas; thereby helping to insure a hermetic seal, however, this clamping pressure does not contribute to the bonding process itself as in TC bonding. In most other respects, however, this embodiment is substantially similar to that previously described.

[0158] The following examples, not to be considered limiting, are provided to illustrate the details of the metallic

layers **610** in the sheet seal-ring area **318** that are suitable for braze-soldering to a Kovar alloy/nickel/gold frame **302** such as that illustrated in **FIG. 7**.

EXAMPLE 33

[0159]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Cu	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Eutectic Au—Sn solder	CVD, PVD, SBP	1.27	127

EXAMPLE 34

[0160]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Cu	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Sn—Bi solder	CVD, PVD, SBP	1.27	152.4

EXAMPLE 35

[0161]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Eutectic Au—Sn solder	CVD, PVD, SBP	1.27	127

EXAMPLE 36

[0162]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Sn—Bi solder	CVD, PVD, SBP	1.27	152.4

EXAMPLE 37

[0163]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Eutectic Au—Sn solder	CVD, PVD, SBP	1.27	127

EXAMPLE 38

[0164]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Ni	CVD, PVD, SBP	0.002	6.35
3	Eutectic Au—Sn solder	CVD, PVD, SBP	1.27	127

EXAMPLE 39

[0165]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Sn—Bi solder	CVD, PVD, SBP	1.27	152.4

EXAMPLE 40

[0166]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Ni	CVD, PVD, SBP	0.002	6.35
3	Sn—Bi solder	CVD, PVD, SBP	1.27	152.4

EXAMPLE 41

[0167]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Sn—Bi solder	CVD, PVD, SBP	1.27	152.4

EXAMPLE 42

[0168]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	De-stressed Sn Solder	CVD, PVD	1.27	152.4

EXAMPLE 43

[0169]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn—Bi Solder	CVD, PVD	1.27	152.4

EXAMPLE 44

[0170]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Eutectic Au—Sn Solder	CVD, PVD	1.27	127

EXAMPLE 45

[0171]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.002	152.4
2	Eutectic Au—Sn Solder	CVD, PVD, SBP	1.27	127

EXAMPLE 46

[0172]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.002	152.4
2	Sn—Bi Solder	CVD, PVD, SBP	1.27	152.4

[0173] While numerous examples herein show the use of eutectic Au—Sn, other applications may utilize non-eutectic Au—Sn, or other eutectic or non-eutectic solders for attaching the window. This allows subsequent use of a higher melting temperature solder to attach the unit to a higher level assembly without melting the window bond.

[0174] By way of further examples, not to be considered limiting, the following combinations are preferred for the

metallic layers **610** in the sheet seal-ring area **318** for braze-soldering to a Kovar alloy/nickel/gold frame **302** such as that illustrated in **FIG. 7**.

EXAMPLE 47

[0175]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Cu	CVD, PVD, SBP	0.25	2.54
3	Ni	CVD, PVD, SBP	1	5.08
4	Eutectic Au—Sn solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 47a

[0176]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Cu	CVD, PVD, SBP	0.25	2.54
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn—Cu—Ag Solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 48

[0177]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Cu	CVD, PVD, SBP	0.25	2.54
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn—Bi solder	CVD, PVD, SBP	2.54	127

EXAMPLE 49

[0178]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Eutectic Au—Sn solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 49a

[0179]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn—Cu—Ag Solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 50

[0180]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn—Bi solder	CVD, PVD, SBP	2.54	127

EXAMPLE 51

[0181]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Eutectic Au—Sn solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 51a

[0182]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn—Cu—Ag Solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 52

[0183]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Ni	CVD, PVD, SBP	1	5.08
3	Eutectic Au—Sn solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 52a

[0184]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Ni	CVD, PVD, SBP	1	5.08
3	Sn—Cu—Ag Solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 53

[0185]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn—Bi solder	CVD, PVD, SBP	2.54	127

EXAMPLE 54

[0186]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Ni	CVD, PVD, SBP	1	5.08
3	Sn—Bi solder	CVD, PVD, SBP	2.54	127

EXAMPLE 55

[0187]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Sn—Bi solder	CVD, PVD, SBP	2.54	127

EXAMPLE 56

[0188]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	De-stressed Sn Solder	CVD, PVD	2.54	127

EXAMPLE 57

[0189]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn—Bi Solder	CVD, PVD	2.54	127

EXAMPLE 58

[0190]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Eutectic Au—Sn Solder	CVD, PVD	2.54	63.5

EXAMPLE 58a

[0191]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn—Cu—Ag Solder	CVD, PVD	2.54	63.5

EXAMPLE 59

[0192]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	5.08
2	Eutectic Au—Sn Solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 59a

[0193]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	5.08
2	Sn—Cu—Ag Solder	CVD, PVD, SBP	2.54	63.5

EXAMPLE 60

[0194]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	5.08
2	Sn—Bi Solder	CVD, PVD, SBP	2.54	127

[0195] Referring now to **FIG. 10**, there is illustrated yet another embodiment of the current invention. Note that in this embodiment, the cover assembly **300** is circular in configuration rather than rectangular. It will be appreciated that this is simply another possible configuration for a cover assembly manufactured in accordance with this invention, and that this embodiment is not limited to configurations of any particular shape. As in the embodiment previously described, this embodiment also uses braze-soldering to hermetically join the transparent sheet **304** to the frame **302**. However, in this embodiment, the solder for braze soldering is provided in the form of a separate solder preform **1000** having the shape of the sheet seal-ring area **318** or the frame seal-ring area **310**. Also in this embodiment, preform **1000** can be of materials other than solder for use as an innerlayer or interlayer material between the transparent sheet **304** and the frame **302**. When used as the innerlayer or interlayer for TC bonding, one or more elements of preform **1000** diffuses with one or more elements of sheet **304** and the frame **302**.

[0196] In this embodiment, when the preform solder **1000** is used for braze-soldering to hermetically join the transparent sheet **304** to the frame **302**, instead of positioning the frame and the sheet directly against one another, the frame **302** and the sheet **304** are instead positioned against opposite sides of the solder preform **1000** such that the solder preform is interposed between the frame seal-ring area **310** and the sheet seal-ring area **318** along a continuous junction region that circumscribes the window portion **312**. After the frame **302** and sheet **304** are positioned against the solder preform **1000**, the junction region is heated until the solder preform fuses forming a solder joint between the frame and sheet all along the junction region. The heating of the junction region may be performed by any of the procedures previously described, including heating or preheating in a furnace, oven, etc., either alone or in combination with other heating methods including resistance welding. It is required that during the step of heating the junction region, the temperature of the window portion **312** of the sheet **304** remain below the glass transition temperature T_G and the softening temperature such that the finished surfaces **314** and **316** on the sheet are not adversely affected.

[0197] The current embodiment using a solder preform **1000** can be used for joining a metallized sheet **304** to a Kovar alloy/nickel/gold frame such as that illustrated in **FIG. 7**. In accordance with a preferred embodiment, the solder preform **1000** is formed of a gold-tin (Au—Sn) alloy, and in a more preferred embodiment, the gold-tin alloy is the eutectic composition. One of the alternative alloys for preform **1000** is tin-copper-silver (Sn—Cu—Ag). The thickness of the gold-tin preform **1000** will probably be within the range from about 6 microns to about 101.2 microns. The

thickness of other alloys for preform **1000** will also probably be within the range of about 6 microns to about 101.2 microns.

[0198] The following examples, not to be considered limiting, are provided to illustrate the details of the metallic layers **610** and the sheet seal-ring area **318** that are suitable for braze-soldering to a Kovar alloy/nickel/gold frame in combination with a gold-tin solder preform or other suitable solder alloy preforms, including, but not limited to tin-copper-silver alloys.

EXAMPLE 61

[0199]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Cu	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Au	CVD, PVD, SBP	0.0508	0.508

EXAMPLE 62

[0200]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Cu	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Sn—Bi	CVD, PVD, SBP	0.635	12.7

EXAMPLE 63

[0201]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Au	CVD, PVD, SBP	0.0508	0.508

EXAMPLE 64

[0202]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.002	25
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Sn—Bi	CVD, PVD, SBP	0.635	12.7

EXAMPLE 65

[0203]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Au	CVD, PVD, SBP	0.0508	0.508

EXAMPLE 66

[0204]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Ni	CVD, PVD, SBP	0.002	6.35
3	Au	CVD, PVD, SBP	0.0508	0.508

EXAMPLE 67

[0205]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Zn	CVD, PVD, SBP	0.002	6.35
3	Ni	CVD, PVD, SBP	0.002	6.35
4	Sn—Bi	CVD, PVD, SBP	0.635	12.7

EXAMPLE 68

[0206]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Ni	CVD, PVD, SBP	0.002	6.35
3	Sn—Bi	CVD, PVD, SBP	0.635	12.7

EXAMPLE 69

[0207]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15
2	Sn—Bi	CVD, PVD, SBP	0.635	12.7

EXAMPLE 70

[0208]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.002	0.15

EXAMPLE 71

[0209]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	De-stressed Sn or Sn—Bi	CVD, PVD	0.635	12.7

EXAMPLE 72

[0210]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Au	CVD, PVD	0.0508	0.508

EXAMPLE 73

[0211]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.002	152.4
2	Au	CVD, PVD, SBP	0.0508	0.508

EXAMPLE 74

[0212]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.002	152.4
2	Sn—Bi	CVD, PVD, SBP	0.635	12.7

EXAMPLE 75

[0213]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.002	152.4
2	Sn (De-stressed after deposition)	CVD, PVD, SBP	0.635	12.7

[0214] By way of further examples, not to be considered limiting, the following combinations are preferred for the metallic layers **610** and the sheet seal-ring area **318** for braze-soldering to a Kovar alloy/nickel/gold frame in combination with a gold-tin soldered preform. In addition to having a frame of Kovar alloy/nickel/gold, materials other than kovar may be employed as the frame's base material and the overlying layer or layers may be nickel without the gold, or combinations of two or more metals including, but not limited to nickel and gold.

EXAMPLE 76

[0215]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Cu	CVD, PVD, SBP	0.25	2.54
3	Ni	CVD, PVD, SBP	1	5.08
4	Au	CVD, PVD, SBP	0.127	0.381

EXAMPLE 77

[0216]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Cu	CVD, PVD, SBP	0.25	2.54
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn—Bi	CVD, PVD, SBP	2.54	7.62

EXAMPLE 78

[0217]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Au	CVD, PVD, SBP	0.127	0.381

EXAMPLE 79

[0218]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	CVD, PVD	0.1	2.54
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn—Bi	CVD, PVD, SBP	2.54	7.62

EXAMPLE 80

[0219]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Au	CVD, PVD, SBP	0.127	0.381

EXAMPLE 81

[0220]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Ni	CVD, PVD, SBP	1	5.08
3	Au	CVD, PVD, SBP	0.127	0.381

EXAMPLE 82

[0221]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Zn	CVD, PVD, SBP	0.3175	5.08
3	Ni	CVD, PVD, SBP	1	5.08
4	Sn—Bi	CVD, PVD, SBP	2.54	7.62

EXAMPLE 83

[0222]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Ni	CVD, PVD, SBP	1	5.08
3	Sn—Bi	CVD, PVD, SBP	2.54	7.62

EXAMPLE 84

[0223]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12
2	Sn—Bi	CVD, PVD, SBP	2.54	7.62

EXAMPLE 85

[0224]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	CVD, PVD	0.05	0.12

EXAMPLE 86

[0225]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	De-stressed Sn or Sn—Bi	CVD, PVD	2.54	7.62

EXAMPLE 87

[0226]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Au	CVD, PVD	0.127	0.381

EXAMPLE 88

[0227]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	5.08
2	Au	CVD, PVD, SBP	0.127	0.381

EXAMPLE 89

[0228]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	5.08
2	Sn—Bi	CVD, PVD, SBP	2.54	7.62

EXAMPLE 90

[0229]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	CVD, PVD	0.1	5.08
2	Sn (De-stressed after deposition)	CVD, PVD, SBP	2.54	7.62

[0230] Referring now to **FIG. 11**, there is illustrated yet another embodiment of the current invention. This embodiment also uses soldering, however, in this embodiment the solder is applied via inkjet technology to either the metallized area **610** in the sheet seal-ring area **318** or the sheet seal-ring **310** of the frame assembly. **FIG. 11** shows a portion of the Kovar alloy/nickel/gold frame **302** (or other frame alloy and overlayer combination) and an inkjet dispensing head **1102** which is dispensing overlapping drops of solder **1104** onto the frame seal-ring area **310** as the dispensing head moves around the frame aperture **308** or the frame aperture is moved underneath the dispensing head, as indicated by arrow **1106**. Preferably, the inkjet dispensed solder is a gold-tin (Au—Sn) alloy, and more preferably it is the eutectic composition. The preferred thickness of the gold-tin solder applied by dispensing head **1102** in this embodiment is within the range from about 6 microns to about 101.2 microns. It will be appreciated that while the example illustrated in **FIG. 11** shows the dispensing head **1102** depositing the solder droplets **1104** onto the frame **302**, in other embodiments the inkjet deposited solder may be applied to the sheet seal-ring area **318**, either alone or in combination with applications on the frame seal-ring area **310**. In still other embodiments, the inkjet deposited solder may be used to create a discrete solder preform that would be employed as described in the previous examples herein. In still other

[0231] embodiments, the inkjet deposited material, which may or may not be solder, may be used to create an innerlayer or interlay preform that would be employed for use in TC bonding or HIP diffusion bonding as described in previous examples herein. Details of the metallic layers **610** in the sheet seal-ring area **318** that are suitable for a soldering to a Kovar alloy/nickel/gold frame **302** such as that illustrated in **FIG. 7** using inkjet supplied solder are substantially identical to those layers illustrated in previous Examples 21 through 32.

[0232] Referring now to **FIGS. 12a** through **12c** and **FIGS. 13a** through **13c**, there is illustrated yet another alternative method for manufacturing cover assemblies constituting another embodiment of the current invention. Whereas, in the previous embodiments a separate prefabricated metal frame was joined to the transparent sheet to act as a heat spreader/heat sink needed for subsequent welding, in this embodiment a cold gas dynamic spray deposition process is used to fabricate a metallic frame/heat spreader directly on the transparent sheet material. In other words, in this embodiment the frame is fabricated directly on the transparent sheet as an integral part, no subsequent joining operation is required. In addition, since cold gas dynamic spray deposition can be accomplished at near room temperature, this method is especially useful where the transparent sheet material and/or surface treatments thereto have a relatively low T_G , melting temperature, or other heat tolerance parameter.

[0233] Referring specifically to **FIG. 12a**, there is illustrated a sheet of transparent material **304** having a window portion **312** defined thereupon. The window portion **312** has finished top and bottom surfaces **314** and **316** (note that the **304** sheet appears bottom side up in **FIGS. 12a** through **12c**). A frame attachment area **1200** is defined on the sheet **304**, the frame attachment area circumscribing the window portion **312**. It will be appreciated in the embodiment

illustrated in **FIG. 12** that the frame attachment area **1200** need not follow the specific boundaries of the window area **312** (i.e., which in this case are circular) as long as the frame attachment area **1200** completely circumscribes the window portion.

[0234] It will be appreciated that, unless specifically noted otherwise, the initial steps of obtaining a transparent sheet having a window portion with finished top and bottom surfaces, preparing the seal-ring area of the sheet and metallizing the seal-ring area of the sheet are substantially identical to those described for the previous embodiments and will not be described in detail again.

[0235] Referring now also to **FIG. 13a**, there is illustrated a partial cross-sectional view to the edge of the sheet **304**. In this example, the step of preparing a frame attachment area **1200** on the sheet **304** comprises an optional step of roughening the frame attachment area by roughening and/or grinding the surface from its original level (shown in broken line) to produce a recessed area **1302**. After the frame attachment area **1200** has been prepared, metal layers are deposited into the frame attachment area of the sheet using cold gas dynamic spray deposition. In **FIG. 12b**, an initial metal layer **1202** has been applied into the frame attachment area **1200** using cold gas dynamic spray deposition.

[0236] Referring now also to **FIG. 13b**, the cold gas dynamic spray nozzle **1304** is shown depositing a stream of metal particles **1306** onto the frame attachment area **1200**. The initial layer **1202** has now been overlaid with a secondary layer **1204** and the spray nozzle **1304** is shown as it begins to deposit the final Kovar alloy layer **1206**. Layer **1206** need not be Kovar.

[0237] Referring now to **FIG. 12c**, the completed cover assembly **1210** is illustrated including the integral frame/heat spreader **1212**, which has been built up from layer **1206** to a predetermined height, denoted by reference numeral **1308**, above the finished surface of the sheet. In a preferred embodiment, the predetermined height **1308** of the built-up metal frame above the frame attachment area **1200** is within the range from about 5% to about 100% of the thickness denoted by reference numeral **1310** of the sheet **304** beneath the frame attachment area. In the embodiment shown, the step of depositing metal using cold gas dynamic spray included depositing a layer of Kovar alloy onto the sheet to fabricate the built-up frame/heat spreader **1212**. The use of cold gas dynamic spray deposition allows a tremendous range of thickness for this Kovar alloy layer, which thickness may be within the range from about 2.54 microns to about 12,700 microns. It will, of course, be appreciated that the frame/heat spreader **1212** may be fabricated through the deposition of materials other than Kovar alloy, depending upon the characteristics of the transparent sheet **304** and of the package base **104**, especially their respective CTEs.

[0238] The following examples, not to be considered limiting, are provided to illustrate the details of the metallic layers, denoted collectively by reference numeral **1207** for forming a frame/heat spreader compatible with hard glass transparent sheets and Kovar alloy or ceramic package bases. The deposition of materials other than Kovar alloy may be used as the final layer whenever Kovar Alloy is indicated as the final layer, depending upon the characteristics of the transparent sheet **304** and of the package base **104**, especially their respective CTEs.

EXAMPLE 91

[0239]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	cold gas spray	2.54	127
2	Cu	cold gas spray	2.54	127
3	Ni	cold gas spray	2.54	127
4	Kovar Alloy	cold gas spray	127	12,700

EXAMPLE 92

[0240]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	cold gas spray	2.54	127
2	Ni	cold gas spray	2.54	127
3	Kovar Alloy	cold gas spray	127	12,700

EXAMPLE 93

[0241]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	cold gas spray	2.54	127
2	Kovar Alloy	cold gas spray	127	12,700

EXAMPLE 94

[0242]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Kovar Alloy	cold gas spray	127	12,700

EXAMPLE 95

[0243]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Zn	cold gas spray	2.54	127
2	Ni	cold gas spray	2.54	127
3	Kovar alloy	cold gas spray	127	12,700

EXAMPLE 96

[0244]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Zn	cold gas spray	2.54	127
2	Kovar alloy	cold gas spray	127	12,700

EXAMPLE 97

[0245]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	cold gas spray	2.54	127
2	Ni	cold gas spray	2.54	127
3	Kovar alloy	cold gas spray	127	12,700

EXAMPLE 98

[0246]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	cold gas spray	2.54	127
2	Kovar alloy	cold gas spray	127	12,700

EXAMPLE 99

[0247]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	cold gas spray	2.54	127
2	Zn	cold gas spray	2.54	127
3	Ni	cold gas spray	2.54	127
4	Kovar Alloy	cold gas spray	127	12,700

EXAMPLE 100

[0248]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	cold gas spray	2.54	127
2	Kovar Alloy	cold gas spray	127	12,700

EXAMPLE 101

[0249]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn or Sn—Bi	cold gas spray	2.54	127
2	Zn	cold gas spray	2.54	127
3	Ni	cold gas spray	2.54	127
4	Kovar Alloy	cold gas spray	127	12,700

EXAMPLE 102

[0250]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn or Sn—Bi	cold gas spray	2.54	127
2	Ni	cold gas spray	2.54	127
3	Kovar Alloy	cold gas spray	127	12,700

[0251] By way of further examples, not to be considered limiting, the following combinations are preferred for the metallic layers **1207** for forming a frame/heat spreader compatible with hard glass transparent sheets and Kovar or other alloys or ceramic package bases. The deposition of materials other than Kovar alloy may be used as the final layer whenever Kovar Alloy is indicated as the final layer, depending upon the characteristics of the transparent sheet **304** and of the package base **104**, especially their respective CTEs.

EXAMPLE 103

[0252]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	cold gas spray	12.7	76.2
2	Cu	cold gas spray	12.7	76.2
3	Ni	cold gas spray	12.7	76.2
4	Kovar Alloy	cold gas spray	635	2,540

EXAMPLE 104

[0253]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	cold gas spray	12.7	76.2
2	Ni	cold gas spray	12.7	76.2
3	Kovar Alloy	cold gas spray	635	2,540

EXAMPLE 105

[0254]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	cold gas spray	12.7	76.2
2	Kovar Alloy	cold gas spray	635	2,540

EXAMPLE 106

[0255]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Kovar Alloy	cold gas spray	635	2,540

EXAMPLE 107

[0256]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Zn	cold gas spray	12.7	76.2
2	Ni	cold gas spray	12.7	76.2
3	Kovar alloy	cold gas spray	635	2,540

EXAMPLE 108

[0257]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Zn	cold gas spray	12.7	76.2
2	Kovar alloy	cold gas spray	635	2,540

EXAMPLE 109

[0258]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	cold gas spray	12.7	76.2
2	Ni	cold gas spray	12.7	76.2
3	Kovar alloy	cold gas spray	635	2,540

EXAMPLE 110

[0259]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Cr	cold gas spray	12.7	76.2
2	Kovar alloy	cold gas spray	635	2,540

EXAMPLE 111

[0260]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Al	cold gas spray	12.7	76.2
2	Zn	cold gas spray	12.7	76.2
3	Ni	cold gas spray	12.7	76.2
4	Kovar Alloy	cold gas spray	635	2,540

EXAMPLE 112

[0261]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Ni	cold gas spray	12.7	76.2
2	Kovar Alloy	cold gas spray	635	2,540

EXAMPLE 113

[0262]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn or Sn—Bi	cold gas spray	12.7	76.2
2	Zn	cold gas spray	12.7	76.2
3	Ni	cold gas spray	12.7	76.2
4	Kovar Alloy	cold gas spray	635	2,540

EXAMPLE 114

[0263]

Layers	Metal	Deposition	Min. (microns)	Max. (microns)
1	Sn or Sn—Bi	cold gas spray	12.7	76.2
2	Ni	cold gas spray	12.7	76.2
3	Kovar Alloy	cold gas spray	635	2,540

[0264] After the deposition of the metal layers using the cold gas dynamic spray deposition, it may be necessary to grind or shape the top surface of the built-up frame **1212** to a predetermined flatness before performing additional steps to ensure that a good contact will be made in later bonding. Another process which may be used, either alone or in combination with shaping the top surface of the built-up frame, is the depositing of additional metal layers onto the built-up frame/heat spreader **1212** using solution bath plating. The most common reason for such plated layers is to promote a good bonding when the frame/heat spreader is adjoined to the package base **104**. In a preferred embodiment, the additional metallic layers applied to the built-up frame **1212** include a layer of nickel directly over the cold gas dynamic spray deposited metal having a thickness within the range of about 0.002 microns to about 25 microns

and, in some instances, then solution bath plating a layer of gold over the nickel layer until the gold layer has a thickness within the range from about 0.0508 microns to about 0.508 microns.

[0265] Referring now to **FIG. 14**, there is illustrated a block diagram of the alternative embodiment utilizing cold gas dynamic spray deposition. It will be appreciated that, unless specifically noted otherwise, the initial steps of obtaining a transparent sheet having finished surfaces, applying surface treatments to the sheet, cleaning, roughening or otherwise preparing the frame attachment area of the sheet are substantially identical to those described for the previous embodiments and will not be described in detail again. For example, block **1402** of **FIG. 14** represents the step of obtaining a sheet of transparent material having finished surfaces and corresponds directly with block **902**, and with the description of suitable transparent materials. Similarly, except as noted, blocks **1404**, **1406** and **1408** of **FIG. 14** correspond directly with blocks **904**, **906** and **908**, respectively, of **FIG. 9** and with the previous descriptions of the steps and sub-steps provided herein. Thus, it will be understood that all of the options described for performing the various steps and sub-steps represented by the blocks **902-908** in the previous (i.e., prefabricated frame) embodiments are applicable to the blocks **1402-1408** in the current (i.e., cold spray) embodiment.

[0266] The next step of the process is to use cold gas dynamic spray deposition to deposit frame/heat spreader metal onto any previously deposited metal layers in the frame attachment area **1200**. This step is represented by block **1410**. As previously described in connection with **FIGS. 13b** and **13c**, the high velocity particles **1306** from the gas nozzle **1304** form a new layer on the previous metallic layers, and by directing the cold spray jet across the frame attachment area **1200** repeatedly, the new material can become a continuous metallic layer around the entire periphery of the frame attachment area, i.e., it will circumscribe the window portion **312** of the transparent sheet **304**. Where the material of the package base **104** (to which the cover assembly **1210** will eventually be joined) is Kovar alloy or appropriately metallized alumina, Kovar alloy is preferred for the material **1206** to be cold sprayed to form the integral frame. In other cases, a heat spreader material should be selected which has a CTE that is closely matched to the CTE of the package base **104**. Of course, that material must also be compatible with the cold gas dynamic spray process.

[0267] The cold spraying of the powdered heat spreader material is continued until the new layer **1206** reaches the thickness required to serve as a heat spreader/integral frame. This would represent the end of the process represented by block **1410**. For some applications, the built-up heat spreader/frame **1212** is now complete and ready for use. For other applications, however, performing further finishing operations on the heat spreader/frame **1212** may be desirable.

[0268] For example, it is known that significant residual stresses maybe encountered in metal structures deposited using cold-gas dynamic spray technology as a result of the mechanics of the spray process. These stresses may make the resulting structure prone to dimensional changes, cracking or other stress-related problems during later use. Annealing by controlled heating and cooling is known to reduce or

eliminate residual stresses. Thus, in some applications, the integral heat spreader/frame **1212** is annealed following its deposition on the sheet **304**. This optional step is represented by block **1411** in **FIG. 14**. In some embodiments, the annealing step **1411** may include the annealing of the totality of the sprayed-on metals and alloys constituting the heat spreader/frame **1212**. In other embodiments, however, the annealing step **1411** includes annealing only the outermost portions of the integral built-up heat spreader/frame **1212**, while the inner layers are left unannealed.

[0269] It will be appreciated that there are flatness requirements for the sealing surface at the “top” of the heat spreader (which is actually projecting from the bottom surface **316** of the sheet). If these flatness requirements are not met via the application of the heat spreader material by the cold spray process, it will be necessary to flatten the sealing surface at the next step of the process. This step is represented by block **1412** in **FIG. 14**. There are a number of options for achieving the required surface flatness. First, it is possible to remove surface material from the heat spreader to achieve the required flatness. This may be accomplished by conventional surface grinding, by other traditional mechanical means, or it may be accomplished by the laser removal of high spots. Where material removal is used, care must be taken to avoid damaging the finished window surfaces **314** and **316** during the material removal operations. Special fixturing and/or masking of the window portion **312** may be required. Alternatively, if the cold spray deposited heat spreader **1212** is ductile enough, the surface may be flattened using a press operation, i.e., pressing the frame against a flat pattern or by employing a rolling operation. This would reduce the handling precautions as compared to using a surface grinder or laser operations.

[0270] Finally, as previously described, in some embodiments additional metal layers are plated onto the integral frame/heat spreader **1212**. These optional plating operations, such as solution bath plating layers of nickel and gold onto a Kovar alloy frame, are represented by block **1414** in **FIG. 14**. In the embodiment shown in **FIG. 14**, the optional plating operation **1414** is performed after the optional flattening operation **1412**, which in turn is performed after the optional annealing operation **1411**. While such order is preferred, it will be appreciated that in other embodiments the order of the optional finishing steps **1411**, **1412** and **1414** may be rearranged. The primary considerations for the ordering of these finishing steps is whether later steps will damage the results of earlier steps. For example, it would be impractical to perform plating step **1414** before the flattening step **1412** if the flattening was to be carried out by grinding, while it might be acceptable if the flattening was to be carried out by pressing.

[0271] Referring now to **FIGS. 15a** and **15b**, there is illustrated a method for manufacturing multiple cover assemblies simultaneously in accordance with another embodiment of the current invention. Shown in **FIG. 15a** is an exploded view of a multi-unit assembly which can be subdivided after fabrication to produce individual cover assemblies. The multi-unit assembly **1500** includes a frame **1502** and a sheet **1504** of a transparent material. The frame **1502** has sidewalls **1506** defining a plurality of frame apertures **1508** therethrough. Each frame aperture **1508** is circumscribed by a continuous sidewall section having a frame seal-ring area **1510** (denoted by cross-hatching). Each

frame seal-ring area **1510** has a metallic surface, which may result from the inherent material of the frame **1502** or it may result from metal layers which have been applied to the surface of the frame. In some embodiments, the frame **1502** includes reduced cross-sectional thickness areas **1509** formed on the frame sidewalls **1506** between adjacent frame apertures **1508**. **FIG. 15b** shows the bottom side of the frame **1502**, to better illustrate the reduced cross-sectional thickness areas **1509** formed between each aperture **1508**. Also illustrated is the base seal-ring area **1520** (denoted by cross-hatching) which surrounds each aperture **1508** to allow joining to the package bases **104**.

[0272] Further regarding the multi-aperture frames illustrated in **FIGS. 15a** and **15b**, it will be understood that the frame **1502** can be attached as shown, with the open ends of the V-shaped notches facing away from the sheet, or alternatively, with the open ends of the V-shaped notches facing toward the sheet.

[0273] Except for the details just described, the multiple-aperture frame **1502** of this embodiment shares material, fabrication and design details with the single aperture frame **302** previously described. In this regard, a preferred embodiment of the frame **1502** is primarily formed of Kovar alloy or similar materials and more preferably, will have a Kovar alloy core with a surface layer of gold overlaying an intermediate layer of nickel as previously described.

[0274] The transparent sheet **1504** for the multi-unit assembly can be formed from any type of transparent material as previously discussed for sheet **304**. In this embodiment, however, the sheet **1504** has a plurality of window portions **1512** defined thereupon, with each window portion having finished top and bottom surface **1514** and **1516**, respectively. A plurality of sheet seal-ring areas **1518** are denoted by cross-hatching surrounding each window portion in **FIG. 15a**. With respect to the material of the sheet **1504**, with respect to the finished configuration of the top and bottom surfaces **1514** and **1516**, respectively, of each window portion **1512**, with respect to surface treatments, and/or coatings, the sheet **1504** is substantially identical to the single window portion sheet **304** previously discussed.

[0275] The next step of the process of manufacturing the multi-unit assembly **1500** is to prepare the sheet seal-ring areas **1518** for metallization. As noted earlier, each sheet seal-ring area **1518** circumscribes a window portion of the sheet **1504**. The sheet seal-ring areas **1518** typically have a configuration which closely matches the configuration of the frame seal-ring areas **1510** to which they will eventually be joined. It will be appreciated, however, that in some cases other considerations will affect the configuration of the frame grid, e.g., when electrical resistance heating is used to produce bonding, then the seal-ring areas **1518** must be connected to form the appropriate circuits. The steps of preparing the sheet seal-ring areas **1518** for metallization is substantially identical to the steps and options presented during discussion of preparing the frame seal-ring area **310** on the single aperture frame **302**. Thus, at a minimum, preparing the sheet seal-ring area **1518** typically involves a thorough (e.g., plasma, solvent or detergent) cleaning to remove any contaminants from the surfaces and typically also involves roughening the seal-ring area by chemical etching, laser ablating, mechanical grinding or sandblasting this area.

[0276] The step of metallizing the prepared sheet seal-ring areas **1510** of the sheet **1502** are substantially identical to the steps described for metallizing the frame seal-ring area **310** on the single aperture frame **302**. For example, the metal layers shown in Examples 1 through 120 can be used in connection with thermal compression bonding, for soldering where the solder material is plated onto the sheet as a final metallic layer, and can be used in connection with soldering in combination with a separate gold-tin or solder preform and also for soldering in connection with solders deposited or formed using inkjet technology.

[0277] The next step of the process is to position the frame **1502** against the sheet **1504** (it being understood that solder preforms or solder layers would be interposed between the frame and the sheet if braze soldering is used to join the frame **1502** to the sheet **1504**) such that each of the window portions **1512** overlays one of the frame apertures **1508**, and that for each such window portion/frame aperture combination, at least a portion of the associated frame seal-ring area **1510** and at least a portion of the associated sheet seal-ring area **1518** contact one another along a continuous junction region that circumscribes the associated window portion. This operation is generally analogous to the steps of positioning the frame against the sheet in the single aperture embodiment previously described. If diffusion bonding is used to join the frame **1502** to the sheet **1504**, an interlayer or innerlayer between the frame **1502** to the sheet **1504** may or may not be employed.

[0278] Referring now to **FIG. 16a**, there is illustrated the positioning of a multi-window sheet **1504** (in this case having window portions **1512** with contoured surfaces) against a multi-aperture frame **1502** using compliant tooling in accordance with another embodiment. The compliant tooling includes a compliant element **1650** and upper and lower support plates **1652**, **1654**, respectively. The support plates **1652** and **1654** receive compressive force, denoted by arrows **1656**, at discrete locations from tooling fixtures (not shown). The compliant member **1650** is positioned between one of the support plates and the cover assembly pre-fab (i.e., frame **1502** and sheet **1504**). The compliant member **1650** yields elastically when a force is applied, and therefore can conform to irregular surfaces (such as the sheet **1504**) while at the same time applying a distributed force against the irregular surface to insure that the required contact pressure is achieved all along the frame/sheet junction. Such compliant tooling can also be used to press a sheet or frame against the other member when the two members are not completely flat, taking advantage of the inherent flexibility (even if small) present in all materials. In the illustrated example, the compliant member **1650** is formed from a solid block of an elastomer material, e.g., rubber, however in other embodiments the compliant member may also be fabricated from discrete elements, e.g., springs. The compliant material must be able to withstand the elevated temperatures experienced during the bonding operation.

[0279] The next step of the process is heating all of the junction regions until a metal-to-metal joint is formed between the frame **1502** and the sheet **1504** all along each junction region, thus creating the multi-unit assembly **1500** having a hermetic frame/sheet seal circumscribing each window portion **1512**. If diffusion bonding is used to join the frame **1502** and the sheet **1504**, the bond could be between the outermost metal layer of the frame and the non-metal-

lized sheet **1504**. It will be appreciated that any of the heating technologies previously described for joining the single aperture frame **302** to the single sheet **304** are applicable to joining the multi-aperture frame **1502** to the corresponding multi-window sheet **1504**.

[0280] Referring now to **FIG. 16b**, the final step of the current process is to divide the multi-unit assembly **1500** along each junction region that is common between two window portions **1512** taking care to preserve and maintain the hermetic seal circumscribing each window portion. A plurality of individual cover assemblies are thereby produced. **FIG. 16b**, illustrates a side view of a multi-unit assembly **1500** following the hermetic bonding of the sheet **1504** to the frame **1502**. Where the frame **1502** includes reduced cross-sectional thickness areas **1509**, the step of dividing the multi-unit assembly may include scoring the frame along the back side of the reduced cross-sectional thickness area at the position indicated by arrow **1602**, preferably breaking through or substantially weakening the remaining frame material below area **1509**, and also simultaneously scoring the sheet **1504** along a line vertically adjacent to area **1509**, i.e., at the point indicated by arrow **1604**, followed by flexing the assembly **1500**, e.g., in the direction indicated by arrows **1606** such that a fracture will propagate away from the score along line **1608**, thereby separating the assembly into two pieces. This procedure can be repeated along each area of reduced cross-sectional thickness **1509** until the multi-unit assembly **1500** has been completely subdivided into single aperture cover assemblies that are substantially identical to those produced by the earlier method described herein. In other embodiments, instead of using the score-and-break method, the cover assemblies may be cut apart, preferably from the frame side along the path indicated by arrow **1602** (i.e., between the window portions **1512**), using mechanical cutting, dicing wheel, laser, water jet or other parting technology.

[0281] Referring now to **FIGS. 17a** and **17b**, there is illustrated yet another method for simultaneously manufacturing multiple cover assemblies. This method expands upon the cold gas dynamic spray technique used to build an integral frame/heat spreader directly upon the transparent sheet material as previously illustrated in connection with **FIGS. 12a** through **12c** and **FIGS. 13a** through **13c**. As shown in **FIG. 17a**, the process starts with a sheet of nonmetallic transparent material **1704** having a plurality of window portions **1712** defined thereupon, each window portion having finished top and bottom surfaces **1714** and **1716**, respectively. The properties and characteristics of the transparent sheet **1704** are substantially identical to those in the embodiments previously discussed. The next step of the process involves preparing a plurality of frame attachment areas **1720** (denoted by the path of the broken line surrounding each window portion **1712**), each frame attachment area **1720** circumscribing one of the window portions **1712**. As in previous embodiments, the step of preparing the frame attachment areas may comprise cleaning, roughening, grinding or otherwise modifying the frame attachment areas in preparation for metallization.

[0282] The next step in this process is metallizing the prepared frame attachment areas on the sheet, i.e., this metallization may be performed using a cold gas dynamic spray technology or where the layers are relatively thin, using a CVD, physical vapor deposition or other conven-

tional metal deposition techniques. It will be appreciated that the primary purpose of this step is to apply metal layers necessary to obtain good adhesion to the transparent sheet **1704** and/or to meet the metallurgical requirements for corrosion prevention, etc.

[0283] Referring now to **FIG. 17b**, the next step of the process is depositing metal onto the prepared/metallized frame attachment areas of the sheet **1704** using cold gas dynamic spray deposition techniques until a built-up metal frame **1722** is formed upon the sheet having a seal-ring area **1726** that is a predetermined vertical thickness above the frame attachment areas, thus creating a multi-unit assembly having an inherent hermetic seal between the frame **1722** and the sheet **1704** circumscribing each window portion **1712**. In some embodiments, reduced cross-sectional thickness areas **1724** are formed by selectively depositing the metal during the cold spray deposition. In other embodiments, the reduced cross-sectional area sections **1724** may be formed following deposition of the frame/heat spreader **1722** through the use of grinding, cutting or other mechanical techniques such as laser ablation and water jet. In addition, the reduced cross-sectional area sections **1724** may be formed following deposition of the frame/heat spreader **1722** through the use of photo-chemical machining (PCM).

[0284] The next step of the process which, while not required is strongly preferred, is to flatten, if necessary, the seal-ring area **1726** of the sprayed-on frame **1722** to meet the flatness requirements for joining it to the package base **104**. This flattening can be accomplished by mechanical means, e.g., grinding, lapping, polishing, etc., or by other techniques such as laser ablation.

[0285] The next step of the process, which, while not required, is strongly preferred, is to add additional metallic layers, e.g., a nickel layer and preferably also a gold layer, to the seal-ring area **1726** of the sprayed-on frame **1722** to facilitate welding the cover assembly to the package base **104**. These metallic layers are preferably added using a solution bath plating process, e.g., solution bath plating, although other techniques may be used.

[0286] The next step of the process is dividing the multi-unit assembly **1700** along each frame wall section common between two window portions **1712** while, at the same time, preserving and maintaining the hermetic seal circumscribing each window portion. After dividing the multi-unit **1700**, a plurality of single aperture cover assemblies **1728** (shown in broken line) will be produced, each one being substantially identical to the single aperture cover assemblies produced using the method described in **FIGS. 12a** through **12c** and **FIGS. 13a** through **13c**. All of the options, characteristics and techniques described for use in the single unit cover assembly produced using cold gas dynamic spray technology are applicable to this embodiment. It will be appreciated that certain operations for example, the flattening of the frame and the plating of the frame with additional metallic layers, maybe performed on the multi-unit assembly **1700**, prior to separation of the individual units, or on the individual units after separation.

[0287] As previously described, heating the junction region between the metallized seal-ring area of the transparent sheet and the seal-ring area of the frame is required for forming the hermetic seal therebetween. Also as previously described, this heating may be accomplished using a

furnace, oven, or various electrical heating techniques, including electrical resistance heating (ERH). Referring now to **FIGS. 18a-18c**, there is illustrated methods of utilizing electric resistance heating to manufacture multiple cover assemblies simultaneously.

[0288] Referring first to **FIG. 18a**, there is illustrated a transparent sheet **1804** having a plurality of seal-ring areas **1818** laid out in a rectangular arrangement around a plurality of window portions **1812**. These seal-ring areas **1818** have been first prepared, and then metallized with one or more metal or metal alloy layers, as previously described herein. The transparent sheet **1804** further includes an electrode portion **1830** which has been metallized, but does not circumscribe any window portions **1812**. This electrode portion is electrically connected to the metallized seal-ring areas **1818** of the sheet. One or more electrode pads **1832** may be provided on the electrode portion **1830** to receive electrical energy from electrodes during the subsequent ERH procedure.

[0289] Referring now to **FIG. 18b**, there is illustrated a frame **1802** having a plurality of sidewalls **1806** laid out in a rectangular arrangement around a plurality of frame apertures **1808**. The apertures **1808** are disposed so as to correspond with the positions of the window portions **1812** of the sheet **1804**, and the sidewalls **1806** are disposed so that frame seal-ring areas **1810** (located thereupon) correspond with the positions of the sheet seal-ring areas **1818** of the sheet. The frame is metallic or metallized in order to facilitate joining as previously described herein. The frame **1802** further includes an electrode portion **1834** that does not circumscribe any frame apertures **1808**. This frame electrode portion **1834** is positioned so as not to correspond to the position of the sheet electrode portion **1830**, and preferably is disposed on an opposing side of the sheet-window/frame-grid assembly (i.e., when the sheet is assembled against the frame). The frame electrode portion **1834** is electrically connected to the metallized frame seal-ring areas **1810**. One or more electrode pads **1836** may be provided on the electrode portion **1834** to receive electrical energy from electrodes during the subsequent ERH procedure.

[0290] Referring now to **FIG. 18c**, the sheet **1804** is shown positioned against the frame **1802** in preparation for heating to produce the hermetic seal therebetween. If applicable, solder or a solder preform has been positioned therebetween as previously described. It will be appreciated that when the transparent sheet **1804** is brought against the frame **1802**, the metallized seal-ring areas **1818** on the lower surface of the sheet will be in electrical contact with the metallized seal-ring areas **1810** on the upper surface of the frame. However, the sheet electrode portion **1830** and the frame electrode portion **1834** will not be in direct contact with one another, but instead will be electrically connected only through the metallized seal-ring areas **1818** and **1810** to which they are, respectively, electrically connected. When an electrical potential is applied from electrode pads **1832** to electrode pads **1836** (denoted by the "+" and "-" symbols adjacent to the electrodes), electrical current flows through the junction region of the entire sheet-window/frame-grid assembly. This current flow produces electrical resistance heating (ERH) due to the resistance inherent in the metallic layers. In some embodiments, this electrical resistance heating may be sufficient to supply the necessary heat, in and of itself, to result in TC bonding, soldering, or other hermetic

seal formation between the sheet **1804** and the frame **1802** in order to form a multi-unit assembly. In other embodiments, however, electrical resistance heating may be combined with other heating forms such as furnace or oven pre-heating in order to supply the necessary heat required for bonding to form the multi-unit assembly.

[0291] After bonding the sheet **1804** to the frame **1802** to form the multi-unit assembly, the sheet electrode portion **1830** and the frame electrode portion **1834** can be cut away and discarded, having served their function of providing electrical access for external electrodes (or other electrical supply members) to the metallized seal-ring areas of the sheet and frame, respectively. The removal of these “sacrificial” electrode portions **1830** and **1834** may occur before or during the “dicing” process step, i.e., the separating of the multi-unit assembly into individual cover assemblies. It will be appreciated that any of the technologies previously described herein for separating a multi-unit assembly into individual cover assemblies can be used for the dicing step of separating a multi-unit assembly fabricated using ERH heating.

[0292] Where ERH is to be used for manufacturing multiple cover assemblies simultaneously, the configuration of the sheet-window/frame-grid array and/or the placement of the electrodes portions within the sheet-window/frame-grid array may be selected to modify the flow of current through the junction region during heating. The primary type of modification is to even the flow of current through the various portions of the sheet-window/frame-grid during heating to produce more even temperatures, i.e., to avoid “hot spots” or “cold spots.”

[0293] Referring now to **FIGS. 19a-19f**, there are illustrated various sheet-window/frame-grid configurations adapted for producing more even temperatures during ERH. In each of **FIGS. 19a-19f**, there is shown a sheet-window/frame-grid array **1900** comprising a prepared, metallized transparent sheet **1904** overlying a prepared, metallic/metallized frame **1902**. The window portions of the sheet **1904** directly overlie the frame apertures of the frame **1902**, and the metallized seal-ring areas of the sheet directly overlie the seal-ring areas of the frame (it will be appreciated that metallized portions of the sheet **1904** and the frame **1902** appear coincident in these figures). Metallized electrode portions formed on the transparent sheet **1904** are denoted by reference letters A, B, C and D. These electrode portions A, B, C and D are electrically connected to the adjoining sheet seal-ring areas of the sheet, but are electrically insulated from one another by non-metallized areas **1906** of the sheet. An external electrode is applied to the top of the metallic/metallized frame (on the side opposite from the sheet) across the area denoted by reference letter E. For bonding or soldering, electrical power is applied at the electrodes, e.g., one line to electrodes A, B, C and D simultaneously, and the other line to electrode E, or alternatively, one line in sequence to each of electrode A, B, C and D, and the other line to electrode E. It will be appreciated that many other combinations of electrode powering are within the scope of the invention.

[0294] Referring to **FIG. 19f**, this embodiment illustrates a sheet-window/frame-grid **1900** having a “shingle” configuration, i.e., where the seal-ring areas between the window portions/frame apertures do not form continuous

straight lines across the assembly array. Shingle-arrangement frame assemblies are more labor-intensive to separate using scribe-and-break or cutting procedures. Separating such assemblies requires that each row first be separated from the overall grid, and then that individual cover assemblies be separated from the row by separate scribe-and-break or cutting operations. Nevertheless, use of shingle-arrangement assemblies may have benefits relating to heating using ERH techniques.

[0295] It will be understood that a metal frame such as **1802** or **1902**, which may contain one or more added layers on its exterior, including but not limited to metal or metal alloy layers, may be diffusion bonded to a non-metallized sheet using ERH techniques to apply heat to the frame. The amount of temperature rise throughout the thickness of the non-metallized sheet will depend on the intensity and duration of the application of the electrical power (voltage and amperage) to the frame, as well as other factors. An inner-layer or interlayer material may be employed between the frame and the sheet during the diffusion bonding process, as discussed previously.

[0296] It will further be appreciated that the terms “thermal compression bonding” (and its abbreviation “TC bonding”) and “diffusion bonding” are used interchangeably throughout this application. The term “diffusion bonding” is preferred by metallurgists while the term “thermal compression bonding” is preferred in many industries (e.g., semiconductor manufacturing) to avoid possible confusion with other types of “diffusion” processes used for creating semiconductor devices. Regardless of which term is used, as previously discussed, diffusion bonding refers to the family of bonding methods using heat, pressure, specific positive or negative pressure atmospheres and time alone to create a bond between mating surfaces at a temperature below the normal fusing temperature of either mating surface. In other words, neither mating surface is intentionally melted, and no melted filler material is added, nor any chemical adhesives used.

[0297] As previously described, diffusion bonding utilizes a combination of elevated heat and pressure to hermetically bond two surfaces together without first causing one or both of the adjoining surfaces to melt (as is the case with conventional soldering, brazing and welding processes). When making optical cover assemblies, wafer level assemblies or other temperature-sensitive articles, it is almost always required that the bonding temperatures remain below some upper limit. For example, in optical cover assemblies, the bonding temperature should be below the T_G and the softening temperature, T_S , of the sheet material so as not to affect the pre-existing optical characteristics of the sheet. As another example, in wafer level assemblies, the bonding temperature should be below the upper temperature limit for the embedded micro device and/or its operating atmosphere (i.e., the gas environment inside the sealed package). However, the specific temperature and pressure parameters required to produce a hermetic diffusion bond can vary widely depending upon the nature and composition of the two mating surfaces being joined. Therefore, it is possible that some combinations of transparent sheet material (e.g., glass) and frame material (e.g., metals or metallized non-metals), or some combinations of frame materials and substrate materials (e.g., silicon, alumina or metals), will have a diffusion bonding temperature that exceeds the T_G and/or

the T_s of the sheet material, or that exceeds some other temperature limit. In such cases, it might appear that diffusion bonding is unsuitable for use in hermetically joining the components together if the temperature limits are to be followed. In fact, however, it has been discovered that the use of “interlayers,” i.e., intermediate layers of specially selected material, placed between the sheet material and the frame, or between the frame material and the substrate material, can cause hermetic diffusion bonding to take place at a substantially lower temperature than if the same sheet material was bonded directly to the same frame material, or if the same frame material was bonded directly to the same substrate material. Note that the terms “interlayers” and “innerlayers” are used interchangeably throughout this application, as both terms may be encountered in the art for the same thing.

[0298] A properly matched interlayer improves the strength and hermeticity (i.e., gas tightness or vacuum tightness) of a diffusion bond. Further, it may promote the formation of compatible joints, produce a monolithic bond at lower bonding temperatures, reduce internal stresses within the bond zone, and prevent the formation of extremely stable oxides which interfere with diffusion, especially on the surface of Al, Ti and precipitation-hardened alloys. The interlayer is believed to diffuse into the parent material, thereby raising the melting point of the joint as a whole. Depending upon the materials to be joined by diffusion bonding, the interlayer material could be composed of a metal, a metal alloy, a glass material, a solder glass material including solder glass in tape or sheet form, or other materials. In the diffusion bonding of BT5-1 Ti alloy to Armco iron, an interlayer of molybdenum foil 0.3 mm thick has been used. Reliable glass-to-glass and glass-to-metal bonds are achieved with metal interlayers such as Al, Cu, Kovar, Niobium and Ti in the form of foil, usually not over 0.2 mm thick. The interlayers are typically formed into thin preforms shaped like the seal ring area of the mating surfaces to be joined.

[0299] It is important to distinguish the use of diffusion bonding interlayers from the use of conventional solder preforms and other processes previously disclosed. For purposes of this application, an interlayer is a material used between sealing surfaces to promote the diffusion bonding of the surfaces by allowing the respective mating surfaces to diffusion bond to the interlayer rather than directly to one another. For example, with the proper interlayer material, the diffusion bonding temperature for the joint between the sheet material and interlayer material, and for the joint between the interlayer material and the frame material, may be substantially below the diffusion bonding temperature of a joint formed directly between the sheet material and the frame material. Thus, use of the interlayer allows diffusion bonding of the sheet to the frame at a temperature which is substantially below the diffusion bonding temperature that would be necessary for bonding that sheet material and that frame material directly. The hermetic joint is still formed by the diffusion bonding process, i.e., none of the materials involved (the sheet material, the interlayer material nor the frame material) melts during the bonding process. This distinguishes diffusion bonding using interlayers from other processes such as the use of solder preforms in which the solder material actually melts to form the bond between the materials being joined. It is possible to use materials conventionally used for solders, for example, Au—Sn solder

preforms, as interlayers for diffusion bonding. However, when used as interlayers they are used for their diffusion bonding properties and not as conventional solders (in which they melt).

[0300] The use of interlayers in the production of window assemblies or other packaging may provide additional advantages over and above their use as promoting diffusion bonding. These advantages include interlayers which serve as activators for the mating surfaces. Sometimes the interlayer materials will have a higher ductility in comparison to the base materials. The interlayers may also compensate for stresses which arise when the seal involves materials having different coefficients of thermal expansion or other thermal expansion properties. The interlayers may also accelerate the mass transfer or chemical reaction between the layers. Finally, the interlayers may serve as buffers to prevent the formation of undesirable chemical or metallic phases in the joint between components.

[0301] Referring now to FIGS. 20a and 20b, there is illustrated a window cover assembly including interlayers to promote joining by diffusion bonding. In this embodiment, the window assembly 2050 includes a transparent glass sheet 2052, an interlayer 2054 and a metal or metal alloy base 2056. The base 2056 includes a built-up seal ring area 2058 and a flange 2060 which facilitates the subsequent electric resistance seam welding of the finished window assembly to a package base or other higher level portion of the final component. The interlayer 2054 in this embodiment takes the form of a metallic preform which has the configuration selected to match the seal ring area 2058 of the frame. To form the hermetic window assembly, the sheet 2052, interlayer 2054 and frame 2056 are placed in a fixture (i.e., tooling) or mechanical apparatus (not shown) which can provide the required predetermined bonding pressure between the seal ring areas of the respective components. In some cases, the fixture may serve only to align the components during bonding, while the elevated bonding pressure is applied from a mechanical apparatus such as a ram. In other cases, however, the fixture may be designed to constrain the expansion of the stacked components during heating (i.e., along the stacking axis), whereby the thermal expansion of the assembly components toward the fixture, and of the fixture itself toward the components, will “self-generate” some or all of the necessary bonding pressures between the components as the temperature increases.

[0302] Referring now to FIGS. 20e and 20f, an example of a “self-compressing” fixture assembly is shown. As best seen in FIG. 20e, the fixture 2085 includes an upper fixture member 2086 and a lower fixture member 2087 which together define a cavity 2088 for receiving the window assembly components to be bonded. Clamps 2089 are provided which constrain the outward movement of the fixture members 2086 and 2087 in the axial direction (denoted by arrow 2090). Generally, the CTE of the material forming the clamps 2089 will be lower than the CTE of the material forming the fixture members 2086 and 2087. FIG. 20f shows the components for the window assembly 2070 (FIGS. 20c and 20d) loaded into the cavity 2088 of the fixture 2085 in preparation for bonding. Note that while the fixture members 2086 and 2087 are in contact with the upper and lower surfaces of the window components, a small gap 2097 is left between the fixture members themselves to allow the members to expand axially toward one another

when heated (since they are constrained by the clamps). Also note that a small gap **2098** is generally left between the lateral sides of the window assembly components and the fixture members **2086** and **2087** to minimize the lateral force exerted on the components by the fixture members during heating. When the fixture **2085** is heated, the inner surfaces (i.e., facing the cavity **2088**) of the fixture members **2086** and **2087** will expand (due to thermal expansion) axially toward one another against the window components, and the window components will expand outward against the fixture. These thermal expansions can press the window components against one another with great force in the axial direction to facilitate diffusion bonding. It will be appreciated that thermal expansion of the fixture members **2086** and **2087** will also occur in the lateral direction (denoted by arrow **2091**). While this lateral expansion is not generally desired, in most cases it will not present an obstacle to the use of self-compressing fixtures.

[0303] Referring now to **FIG. 20g**, there is illustrated an alternative self-compressing fixture adapted to enhance thermal expansion (and hence compression) in the axial direction **2090** without causing excessive thermal expansion in the lateral direction **2091**. As with the previous example, alternative fixture **2092** includes an upper fixture member **2086** and a lower fixture member **2087** defining a cavity **2088** for receiving the window assembly components to be bonded, and clamps **2089** (only one of which is shown for purposes of illustration) which constrain the outward movement of the fixture members in the axial direction **2090**. Also as in the previous embodiment, a first small gap **2097** is present between the fixture members **2086** and **2087** themselves, and a second small gap **2098** is present between the lateral sides of the window components and the fixture members. Unlike the previous embodiment, however, each fixture member **2086** and **2087** of the alternative fixture **2092** comprises two sub-members, namely, first sub-members **2093** and **2094**, respectively, adapted to bear primarily axially against the window assembly components (not shown), and second sub-members **2095** and **2096**, respectively, adapted to hold and align the window assembly components in the cavity. By selecting a material for the first sub-members **2093** and **2094** having a high CTE, axial expansion (and hence compression) during heating will be correspondingly high. However, lateral expansion and relative lateral movement between the second sub-members **2095** and **2096** and the window components can be minimized by selecting a different material for the second sub-members, namely, a material having a lower CTE (i.e., lower than the CTE for the first sub-members). Preferably, the CTE of the second sub-members **2095** and **2096** will be close to the CTE for the adjacent window components.

[0304] Referring again to **FIGS. 20a** and **20b**, the assembled (but not yet bonded) components of the window assembly **2050** are then heated until the diffusion bonding pressure/temperature conditions are reached, and these conditions are maintained until a first diffusion bond is formed between the sheet **2052** and the interlayer **2054**, and a second diffusion bond is formed between the interlayer **2054** and the seal ring area **2058** of the frame **2056**. It will be understood that the first bond between the sheet and the interlayer may actually occur before, after or simultaneously with, the second bond between the interlayer and the frame. As previously explained, it will also be understood that the order of applying heat and pressure to form the diffusion

bond is not believed to be significant, i.e., in other words whether the predetermined pressure is applied, and then the heat is applied or whether the heat is applied and then the predetermined pressure is applied, or whether both heat and pressure are increased simultaneously is not believed to be significant, rather the diffusion bonding will occur when the preselected pressure and temperature are present in the bond region for a sufficient amount of time. After the diffusion bonds are formed, the sheet **2052** will be hermetically bonded to the frame **2056** to form a completed window assembly **2050** as shown in **FIG. 20b**.

[0305] In further embodiments of the current invention, it has been discovered that clean, i.e., unmetallized, glass windows may be directly bonded to frames of Kovar or other metallic materials using diffusion bonding. This is in addition to the diffusion bonding of metallized glass windows to Kovar frames as previously described. Optionally, the direct diffusion bonding of unmetallized glass windows to metallic frames may be enhanced through the use of certain compounds, e.g., molybdenum-manganese, on the frames. Whether the glass is metallized or unmetallized, the diffusion bonding is most commonly performed in a vacuum, however, it may be performed in various other atmospheres. The use of oxidizing atmospheres is typically not required, however, as any resulting oxides tend to be dispersed by pressures encountered in the bonding operation. In still other embodiments, of the invention, diffusion bonding can be used for joining frames made of Kovar and other metallic materials directly to sheets or wafers of semiconductor materials including silicon and gallium arsenide (GaAs).

[0306] Since successful diffusion bonding requires the mating surfaces being bonded to be brought into intimate contact with one another, the surface finish characteristics of the mating surfaces may be important parameters of the invention. It is believed that the following mating surface parameters will allow successful diffusion bonding between the mating surfaces of Kovar frames and thin sheet materials including, but not limited to, Kovar to metallized glass, Kovar to clean (i.e., unmetallized) glass, Kovar to metallized silicon, Kovar to clean (i.e., unmetallized) silicon, Kovar to metallized gallium arsenide (GaAs) and Kovar to clean (i.e., unmetallized) GaAs: Parallelism of sheet material (i.e., uniformity of thickness) within the range of \pm about 12.7 microns; Surface flatness (i.e., deviation in height per unit length when placed on ideal flat surface) within range from 5 mils/inch to about 10 mils/inch; Surface roughness not more than about 16 micro-inches (0.4064 microns). These surface parameters can also be used for diffusion bonding of Kovar directly to Kovar, e.g., to manufacture built-up metallic frames.

[0307] The temperature parameters for diffusion bonding between the mating surfaces of Kovar frames and the thin sheet materials described above are believed to be within the range from about 40% to about 70% of the absolute melting temperature, in degrees Kelvin, of the parent material having the lower melting temperature. When diffusion bonding is used for bonding optically finished glass or other transparent materials, the bonding temperature may be selected to be below the T_G and/or the softening temperature of the for the glass other transparent materials, thereby avoiding damage to the optical finish. Depending upon the bonding temperature selected, in some embodiments the application of optical and/or protective coatings to the transparent sheets (i.e.,

that become the windows) may be performed after the bonding of the sheets to the frames, rather than before bonding. In other embodiments, some of the optical and/or protective coatings may be applied to the glass sheets prior to bonding, while other coatings may be applied subsequent to bonding. With regard to pressure parameters, a pressure of 105.5 kg/cm² (500 psi) is believed suitable for diffusion bonding Kovar frames and the thin sheet materials previously described.

[0308] It will be noted that since the diffusion bonding occurs at high temperature, the CTE of the glass sheet should be matched to the CTE of the metallic frame. To the extent that the CTEs cannot be completely matched (e.g., due to non-linearities in the CTEs over the range of expected temperatures), then it is preferred that the CTE of the glass sheet be lower than the CTE of the metallic frame. This will result in the metallic frame shrinking more than the glass sheet as the combined window/frame assembly cools from its elevated bonding temperature (or from an elevated operational temperature) back to room temperature. The glass will therefore be subjected primarily to compression stress rather than tension, which reduces the tendency for cracking.

[0309] Referring now to **FIGS. 20c** and **20d**, there is illustrated an additional embodiment of the invention, a window assembly having internal and external frames. **FIG. 20c** illustrates the components of window assembly **2070** before assembly, while **FIG. 20d** illustrates the completed assembly. The window assembly **2070** includes separate frame members **2072** and **2074**, which are bonded (using diffusion bonding, soldering, brazing or other techniques disclosed herein) to the inner and outer surfaces **2076** and **2078**, respectively, of the transparent sheet **2080**. In other words, the transparent window material is “sandwiched” between a layer of frame material on the top of the window and a layer of frame material on the bottom of the window. Interlayers **2082** and **2084** may be provided for diffusion bonding as previously described, or alternatively, solder preforms (also shown as **2082** and **2084**) may be provided for bonding by soldering as previously described.

[0310] Typically, the same bonding technique will be used for bonding both the internal and external frames to the window, however, this is not required. Similarly, the internal and external bonds will typically be formed at the same time, however, this is not required. The internal frame **2072** must, however, be hermetically bonded to the window **2080** to produce a hermetic window assembly. A hermetic bond is not typically required for bonding the external frame **2074** to the window **2080**, however, it may be preferred for a number of reasons.

[0311] One benefit of window assemblies having the so-called “sandwiched” frame configuration is to equalize the stresses on the internal and external surfaces, **2076** and **2078**, respectively, of the transparent sheet **2080** that are caused by differential thermal expansion characteristics of the frames **2072** and **2074** and sheet (due to unequal CTE), e.g., during cooling after bonding, or during thermal cycling. Put another way, when a window assembly has a frame bonded to only one surface, uneven expansion and contraction between the frame and sheet may produce significant shear stresses within the sheet. These shear stresses may be strong enough to cause shear failure (e.g., cracking or flaking) within the transparent sheet even though the win-

dow-to-frame bond itself remains intact. When a frame is bonded to both the internal and external surfaces of the window, however, the shear stresses within the glass (or other transparent material) may be significantly reduced. This is particularly true if the same material or material having similar CTEs are used for both the internal and external frames. This stress-equalization through the thickness of the window increases the reliability and durability of the assembled window during subsequent thermal cycling and/or physical shock.

[0312] Sandwiched construction may be used in window assemblies or in WLP assemblies. Sandwiched construction with internal and external frames is especially advantageous where the sheet and frame materials have significantly different CTEs. In addition to the stress balancing features of sandwiched construction, use of an external frame on the sheet may have additional benefits, including: enhancing thermal spreading across the window; enhancing heat dissipation from the assembly; serving as an optical aperture; facilitating the aligning/fixturing or clamping of the device during bonding or assembly to higher level assemblies; and to display working symbolization.

[0313] Referring now to **FIGS. 21a** and **21b**, there are illustrated two examples of hermetically sealed wafer-level packages (also known as “WLPs”) for micro-devices in accordance with other embodiments of the invention. These embodiments are substantially similar to one another, except that wafer-level package **2002** (**FIG. 21a**) has reverse-side external electrical connections while wafer-level package **2024** (**FIG. 21b**) has same-side external electrical connections. The wafer-level packages, while similar in many respects to the discrete device packages previously disclosed herein, utilize the substrate of the micro-device itself, typically a semiconductor substrate, as a portion of the package’s hermetic envelope. Such wafer-level packaging provides a very economical method for hermetically encapsulating wafer-fabricated micro-devices, especially where high production volumes are involved. As will be described below, a single micro-device may be packaged using WLP technology, or multiple micro-devices on the original production wafer may be packaged simultaneously using WLP technology in accordance with various aspects of the current invention.

[0314] Referring now specifically to **FIG. 21a**, the wafer-level package **2002** encloses one or more micro-devices **2004**, e.g., a MEMS device or MOEMS device fabricated on a substrate **2006**. The substrate **2006** is typically a wafer of silicon (Si) or gallium arsenide (GaAs) upon which electronic circuitry **2008** associated with the micro-device **2004** is formed using known semiconductor fabrication methods. Electrical vias **2010** (shown in broken line) may be formed in the substrate **2006** using known methods to connect the circuitry **2008** to externally accessible connection pads **2012** disposed on the reverse side (i.e., with respect to the device) of the substrate. It will be appreciated that the path of vias **2010** shown in **FIG. 20** has been simplified for purposes of illustration. One end of a frame **2014** made of Kovar or other metallic material is hermetically bonded to the substrate **2006**, and a transparent window **2016** is, in turn, hermetically bonded to the other end of the frame to complete the hermetic envelope sealing the micro-device within the cavity **2018**. The frame-mating surfaces of the substrate **2006** may be prepared or metallized with one or more metal layers

2020 to facilitate bonding to the frame, and similarly the frame-mating surfaces of the window **2016** may be prepared or metallized with one or more metal layers **2022** for the same purpose.

[0315] Referring now specifically to **FIG. 21b**, the wafer-level package **2024** is substantially identical to the package **2002** previously described, except that in this case the vias **2026** are routed to external connection pads **2028** disposed on the same side of the substrate **2006**. Obviously, in such embodiments, the frame **2014** and window **2016** are dimensioned to leave uncovered a portion of the substrate's upper surface.

[0316] Referring now to **FIG. 21c**, there is shown an exploded view of a WLP2100 illustrating one possible method of manufacture. To package individual or multiple micro-devices using WLP methods, the following components are necessary: a substrate **2006** having a micro-device **2004** thereupon; a frame/spacer **2014** having a continuous sidewall **2015** and that is "taller" than the device to be encapsulated (to provide clearance); and a transparent sheet or window **2016**. Depending upon the bonding method to be used, solder preforms of a metal alloy or glass composition, or interlayers for diffusion bonding **2102** and **2103** may also be required. It will be appreciated that the top preform **2102** (between the window **2106** and the frame **2014**) may be a different material than the bottom preform **2103** (between the frame **2014** and the substrate **2006**).

[0317] Briefly, the steps for forming the package **2100** are as follows: A first frame-attachment area **2104** is prepared on the surface of the wafer substrate **2006** of the subject micro-device. This first frame-attachment area **2104** has a plan (i.e., configuration when viewed from above) that circumscribes the micro-device or micro-devices **2004** on the substrate **2006**. A second frame-attachment area **2106** is prepared on the surface of the window **2016**. The second frame-attachment area **2106** typically has a plan substantially corresponding to the plan of the first frame-attachment area **2104**. The execution order the previous two steps is immaterial. Next, the frame/spacer **2014** is positioned between the substrate **2006** and the window **2016**. The frame/spacer **2014** has a plan substantially corresponding to, and in register with, the plans of the first and second frame-attachment areas **2104** and **2106**, respectively. If applicable, the solder preforms **2102** and **2103** or diffusion bonding interlayers **2102** and **2103** are interposed at this time between the frame/spacer **2014** and the frame-attachment areas **2104** and/or **2106**. Finally, the substrate **2006**, frame/spacer **2014** and window **2016** are bonded together (facilitated by solder or glass preforms **2102** and **2103** or diffusion bonding interlayers **2102** and **2103**, if applicable) to form a hermetically sealed package encapsulating micro-device **2004** within, but allowing light to travel to and/or from the micro-device through the transparent aperture area **2108** of the window.

[0318] It will be understood that diffusion bonding of the package **2100** can be performed in a single (combined) step or in a number of sub-steps. For example, all five components (sheet **2016**, first interlayer **2102**, frame **2014**, second interlayer **2103** and substrate **2006**) could be stacked in a single fixture and simultaneously heated and pressed together to cause diffusion bonds to form at each of the sealing surfaces. Alternatively, the window sheet **2016**

maybe first diffusion bonded to the frame **2014** using first interlayer **2102** (making a first subassembly), and then this first subassembly may be subsequently diffusion bonded to the substrate **2006** using second interlayer **2103**. In another alternative, the frame **2014** could be diffusion bonded to the substrate **2006** using second interlayer **2103**, and then the transparent sheet **2016** may subsequently be bonded to the sub-assembly using first interlayer **2102**. The choice of which bonding sequence to be used would, of course, depend upon the exact materials to be used, the heat sensitivity of the transparent material in the sheet **2016**, the heat sensitivity of the micro device **2004** and, perhaps, other parameters such as the expansion characteristics of the frame **2014** and interlayer materials.

[0319] It will further be appreciated that the current invention is similar in several respects to the manufacturing of the "stand-alone" hermetic window assemblies previously described. The preparing of the frame-attachment areas **2106** of the window **2016** may be performed using the same techniques previously described for use in preparing the sheet seal-ring area **318**, including cleaning, roughening, and/or metallizing with one or more metallic layers as set forth in the earlier Examples 1-96.

[0320] While the transparent windowpane **2016** may be roughened (e.g., in preparing the frame-attachment area **2106**) to promote adhesion of the first metallic layer being deposited onto it (e.g., by CVD or PVD), the wafer substrate **2006** will not typically be roughened in the same manner. Instead, the initial metallic layer on the wafer substrate **2006** will typically be deposited using conventional wafer fabrication techniques. Where conventional methods of wafer fabrication include the requirement or option of etching a silicon or GaAs wafer to promote adhesion of a metal's deposition, then the same practice maybe followed in preparing the frame attachment area **2104** on the wafer substrate **2006** when building WLP devices.

[0321] Other wafer or substrate materials include, but are not limited to, glass, diamond and ceramic materials. Some ceramic wafers are known as alumina wafers. These alumina wafers or substrates may be multi-layer substrates, and maybe manufactured using Low-Temperature Co-Fired (LTCC) or High-Temperature Co-Fired (HTCC) materials and processes. LTCC and HTCC substrates often have internal and external electrical circuitry or interconnections. This circuitry is typically screen printed onto the ceramic or alumina material layer(s) prior to co-firing the layers together.

[0322] Also, any of the bonding techniques and parameters previously described for use on window assemblies may be used to hermetically bond the WLP components to one another, including diffusion bonding/TC bonding with or without the use of interlayers, soldering using a solder preform and soldering using inkjet-dispensed solders. The primary difference is that when making "stand-alone" window assemblies, only two primary components (namely, the transparent sheet/window **304** and frame **302**) are bonded together, while when making WLPs, three primary components (namely, the window **2016**, frame **2014** and substrate **2006**) are bonded together (sometimes simultaneously). Of course, when producing WLPs using soldering techniques, additional components may be required, for example one or more solder preforms **2102** or a quantity of inkjet-dispensed

solder. The solder preforms, diffused, may be attached to the top and/or bottom of the frame **2014** as one step in the manufacture of that item. This will simplify the alignment of the three major components of the WLP assembly. It will, of course, be appreciated that this pre-attachment of the solder preforms to the frame is also applicable to the “stand-alone” window assemblies previously described. One of the methods for attaching solder preforms to the window **2016**, frame **2014** and/or substrate **2006** is to tack the preform in place using a localized heat source.

[0323] Prior to soldering components together, cleaning the surfaces of the solder preforms and/or the metallized surfaces of the window **2016**, frame **2014** and/or substrate **2006** maybe necessary to remove surface oxides. It is desirable to avoid using fluxes during the soldering process to eliminate the need for post-soldering or defluxing. Several surface preparation technologies are available to prepare the metal and solder surfaces for fluxless soldering.

[0324] Several other processes may be used for preparing the surfaces of window assemblies or WLP components for soldering to avoid the need to remove fluxes after soldering. A first option is to use what is known in the trade as a no-clean flux. This type of flux is intended to be left in place after soldering. A second option is the use of gas plasma treatments for improving solderability without flux. For example, a non-toxic fluorine-containing gas may be introduced that reacts at the surface of the solder. This reaction forms a crust on the solder and dissolves upon remelt. The welds and joints formed are equal to or better than those formed when using flux. Such plasmas offer benefits including the removal by reduction of oxides and glass to promote improvements in solderability and wire bondability. Such treatments have been indicated on thick film copper, gold and palladium. Additional candidate gases for leaving a clean oxide-free surface include hydrogen and carbon monoxide plasma. Still further candidate gases include hydrogen, argon and freon gas combinations. One version of plasma treatment is known as Plasma-Assisted Dry Soldering (PADS). The PADS process converts tin oxide (present in fluxless solders when unstable reduced tin oxide reoxidizes upon exposure to air) to oxyfluorides that promote wetting. The conversion film breaks up when the solder melts and allows reflow. The film is understood to be stable for more than a week in air and for more than two weeks when the parts are stored in nitrogen.

[0325] As in the previously described methods for manufacture of individual and multiple window assemblies for hermetically packaging discrete micro-devices, the selection of compatible materials for the various components for the manufacture of WLPs is another aspect of the invention. For example, each of the primary components (e.g., window, frame/spacer and wafer substrate) of the WLP will preferably have closely matched CTEs to insure maximum long-term reliability of the hermetic seal. The frame/spacer **2014** may be formed of either a metallic material or of a non-metallic material. The best CTE match will be achieved by forming the frame/spacer **2014** from the same material as either the wafer substrate **2006** or the window **2016**. However, gallium arsenide (GaAs) and silicon (Si) (i.e., the materials typically used for the wafer substrate) and most glasses (i.e., the material that is typically used for the window) are relatively brittle, at least in comparison to most metals and metal alloys. These non-metallic materials are

therefore typically not as preferred for forming the frame/spacer **2014** as are metals or metal alloys, because the metals and metal alloys typically exhibit better resistance to cracking. In fact, the use of a metal or metal alloy for the frame/spacer **2014** is believed to provide additional resistance to accidental cracking or breaking of the wafer substrate **2006**, window **2016** and complete WLP **2002** after bonding. When a metallic frame/spacer **2014** is employed, it will preferably be plated with either gold alone, or with nickel and then gold, sometimes to facilitate diffusion bonding or soldering, but more often, to provide a surface on the frame/spacer that provides various kinds of protection between the frame/spacer and the atmosphere inside the package. If, however, a non-metallic frame/spacer **2014** is employed, then it might be metallized to facilitate diffusion bonding or soldering. The metal layers used on the frame/spacer **2014** may be the same as those used on the window-pane **304** for the manufacture of window assemblies, e.g., the final layer might be one of chromium, nickel, tin, tin-bismuth and gold.

[0326] In selecting compatible materials for the components of WLPs, it is recognized that silicon (Si) has a CTE ranging from about 2.6 PPM/° K at 293° K to about 4.1 PPM/° K at 1400° K. If it is assumed that the operating temperatures for micro-devices such as MEMS and MOEMS will be within the range from about -55° C. to about +125° C., and that the expected diffusion bonding or soldering temperatures will be within the range from about +250° C. to about +500° C., it may be interpolated that silicon wafers of the type used for WLP substrates will have a CTE within the range from about 2.3 PPM/° K to about 2.7 PPM/° K. One metallic material believed suitable for use in frame/spacers **2014** that will be bonded to silicon (Si) substrates is the alloy known as “Low Expansion 39 Alloy,” developed by Carpenter Specialty Alloys. Low Expansion 39 Alloy is understood to have a composition (weight percent; nominal analysis) as follows: about 0.05% C, about 0.40% Mn, about 0.25% Si, about 39.0% Ni, and the balance Fe. Low Expansion 39 Alloy has a CTE that is understood to range from about 2.3 PPM/° K over the interval of 25° C. to 93° C., to about 2.7 PPM/° K at 149° C., to about 3.2 PPM/° K at 260° C., and to about 5.8 PPM/° K at 371° C.

[0327] Similarly, it is recognized that gallium arsenide (GaAs) of the type used for WLP wafer substrates has a nominal CTE of about 5.8 PPM/° K. Based on material suppliers’ data, Kovar alloy is understood to have a CTE ranging from about 5.86 PPM/° K at 20° C. to about 5.12 PPM/° K at 250° C. Thus, Kovar alloy appears to be a good choice for frame/spacers **2014** that will be bonded to GaAs substrates. Another material believed suitable for frame/spacers **2014** that will be bonded to GaAs substrates is the alloy known as Silvar™, developed by Texas Instruments Inc.’s Metallurgical Materials Division, of Attleboro, Mass. It is understood that Silvar™ is a derivative of Kovar with CTE characteristics closely matched to GaAs devices.

[0328] With regard to the window/lens for WLPs, it is believed that all of the glasses previously described for use in the manufacture of individual and multiple window assemblies having Kovar frames, e.g., Corning 7052, 7050, 7055, 7056, 7058 and 7062, Kimble (Owens Corning) EN-1, Kimble K650 and K704, Abrisa soda-lime glass, Schott 8245 and Ohara Corporation S-LAM60, will be suitable for the window/lens **2016** of WLPs having a GaAs substrate

2006. Pyrex glasses and similar formulations are believed suitable for the window/lens **2016** of WLPs having silicon substrates **2006**. The properties of Pyrex, per the Corning website, are: softening point of about 821° C., annealing point of about 560° C., strain point of about 510° C., working point of about 1252° C., expansion (0-300° C.) of about $32.5 \times 10^{-7}/^{\circ}\text{C.}$, density of about 2.23 g/cm³, Knoop hardness of about 418 and refractive index (at 589.3 nm) of about 1.474.

[0329] Referring now to **FIG. 22**, there is illustrated a semiconductor wafer **2202** having a plurality of micro-devices **2204** formed thereupon. It will be appreciated that methods for the production of multiple micro-devices on a single semiconductor wafer are conventional. Heretofore, however, when the micro-devices **2204** are of the type which must be hermetically packaged prior to use, e.g., MEMS, MOEMS, opto-electronic or optical devices, it has been standard practice in the industry to first “individuate” or “singulate” the micro-devices, e.g., by cutting-apart, dicing (apart) or breaking-apart the wafer **2202** into sections having, typically, only a single micro-device on each, and then packaging the individuated micro-devices in separate packages. Now, in accordance with additional embodiments of the current invention, multiple micro-devices may be individually hermetically packaged, or hermetically packaged in multiples, in a WLP prior to individuation or singulation of the substrate wafer. This process is referred to as multiple simultaneous wafer-level packaging, or “MS-WLP.”

[0330] Referring now to **FIGS. 23 through 29**, there is illustrated one method for MS-WLP of micro-devices. Briefly, this method includes the steps of: a) preparing a first frame-attachment area on the surface of a semiconductor wafer substrate having a plurality of micro-devices, the first frame-attachment area having a plan circumscribing individual (or multiple) micro-devices on the substrate; b) preparing a second frame-attachment area on the surface of a window (i.e., a sheet of transparent material), the second frame-attachment area having a plan substantially corresponding to the plan of the first frame-attachment area; c) positioning a frame/spacer between the substrate and the window, the frame/spacer having a plan substantially corresponding to, and in register with the plans of the first and second frame-attachment areas, respectively; and d) hermetically bonding the substrate, frame/spacer and window together so as to encapsulate the micro-device. If applicable, solder preforms or other materials including, but not limited to, innerlayers of interlayers for diffusion bonding, are also positioned between the frame/spacer and the window and/or substrate before bonding.

[0331] Referring now specifically to **FIG. 23**, the frame-attachment area **2302** of semiconductor wafer **2202** has been prepared by depositing metallized layers onto the surface of the wafer substrate completely around (i.e., circumscribing) each micro-device **2204**. In the embodiment shown, the prepared frame-attachment area **2302** includes a rectangular grid consisting of double-width metallized rows **2304** and columns **2306** (interposed between the micro-devices **2204**) surrounded by single-width outer rows **2308** and columns **2310**. The composition and thickness of the metallized layers in frame-attachment area **2302** may be any of those previously described for use in preparing the sheet seal-ring area **318** as set forth in Examples 1-96.

[0332] Referring now to **FIG. 24**, there is illustrated a MS-WLP frame/spacer **2402** for attachment between the wafer **2202** and the window sheet **2602** of the MS-WLP assembly. It will be appreciated that in this embodiment, the MS-WLP frame/spacer **2402** has double-width row members **2404** and column members **2406** surrounded by single-width outer row members **2408** and column members **2410**, resulting in a plan which corresponds substantially with the plan of the frame-attachment area **2302** on the wafer substrate **2202**. As will be further described below, the purpose of the double-width row and column members **2404** and **2406** is to allow room for cutting the frame during singulation of the MS-WLP assembly after bonding. It will be appreciated that, in other embodiments, the MS-WLP frame/spacer may have a different configuration. In this embodiment, the MS-WLP frame/spacer **2402** is formed of a metal alloy having a CTE substantially matched to the CTE of wafer substrate, however, in other embodiments the frame/spacer may be formed of non-metallic materials as previously described. Also as previously described, the frame/spacer **2402** will preferably be plated or metallized to facilitate the bonding process.

[0333] Referring now to **FIGS. 25a-25d**, there are illustrated details of a preferred configuration for the frame/spacer **2402**. **FIG. 25a** shows an enlarged plan view of a portion of the double-width column member **2406** and **FIG. 25b** shows an end view of the same portion. It will be appreciated that the row members **2404** of the frame/spacer **2402** preferably have a similar configuration. The member **2406** is formed to have a “groove” **2502**, or reduced thickness area, running along the central portion of each member, i.e., between the adjacent micro-devices in the completed MS-WLP assembly. As will be further described below, the groove **2502** facilitates cutting apart of the MS-WLP assembly during singulation of the packaged micro-devices. After being cut apart along the groove **2502**, the frame member **2406** will be divided into two single-width members **2504**, each one having the configuration shown in **FIGS. 25c** and **25d**. During assembly, the grooved side **2505** of the frame member is preferably positioned against the wafer substrate **2202**, while the ungrooved side **2505** is positioned against the window sheet.

[0334] Referring now to **FIG. 26**, there is illustrated a MS-WLP window sheet **2600** for attachment to the MS-WLP frame/spacer **2402**. The window sheet **2600** is formed of glass or other transparent material having a CTE compatible with the other principal components of the assembly as previously described. At least the inner side (i.e., the side that will be inside the hermetic envelope) of the sheet **2600**, and preferably both sides, must be optically finished. Any desired optical or protective coatings are preferably present on at least the inner side, and preferably on both sides, of the sheet **2600** at this point. However, if the sheet **2600** is attached to only the frame/spacer **2402** in the first of two bonding operations, then the optical or protective coatings may be applied prior to the second, later bonding step of attaching the window assembly to the wafer. A frame-attachment area **2602** is prepared on the MS-WLP window sheet **2600** so as to circumscribe a plurality of window apertures **2603** that will ultimately be aligned with the micro-devices **2204** in the final MS-WLP assembly. In the embodiment shown, the prepared frame-attachment area **2602** takes the form of metallic layers deposited on the sheet **2600** in a rectangular grid consisting of double-width rows

2604 and columns **2606** surrounded by single-width outer rows **2608** and columns **2610**. This results in a plan for the frame-attachment area **2602** which corresponds substantially with the plan of the frame/spacer **2402**. The composition and thickness of the metallized layers **2604**, **2606**, **2608** and **2610** in the frame-attachment area **2602** may be any of those previously described for use in preparing the sheet seal-ring area **318** of the “stand-alone” windows set forth in Examples 1-96.

[0335] In some embodiments, the inner surface of the window sheet **2600** may be scribed, e.g., with a diamond stylus, through each portion of the frame-attachment area **2602** to facilitate breaking apart of the MS-WLP assembly during singulation. The scribing of the window sheet **2600** would obviously be performed prior to bonding or joining it to the frame/spacer **2402**. Where the frame/spacer **2402** includes grooved members such as those illustrated in FIGS. 25a-25b, then the scribe lines on the sheet **2600** will preferably be in register with the grooves **2502** of the frame members in the MS-WLP assembly.

[0336] Referring now to FIG. 27, there is illustrated a side view of a complete MS-WLP assembly **2700**. It will be appreciated that the proportions of some of the components shown in FIG. 27 (e.g., the thicknesses of the metallic layers) maybe exaggerated for purposes of illustration. The frame/spacer **2402** is positioned between the wafer substrate **2202** (with associated micro-devices **2204**) and the window sheet **2600**, with the plans of the frame-attachment areas **2302** and **2602** being substantially in register with the plan of the frame/spacer **2402** such that each micro-device or set of micro-devices **2204** is positioned beneath a window aperture area **2603** of the window sheet. Of course, if the assembly **2700** is bonded using solder technology, then solder preforms (not shown) having a plan substantially corresponding with the frame-attachment areas **2302** and **2602** are also positioned between the frame/spacer **2402** and the frame-attachment areas prior to bonding. Also, if interlayers or interlayers are used in conjunction with diffusion bonding, these interlayers (not shown) having a plan substantially corresponding with the frame-attachment areas **2302** and **2602** are also positioned between the frame/spacer **2402** and the frame-attachment areas prior to bonding. Any of the previously described bonding technologies may be used to effectuate the bond between the components. The MS-WLP assembly **2700** will look essentially the same before bonding and after bonding (except for incorporation into the bond area of any solder preforms).

[0337] After bonding, the MS-WLP assembly **2700** is cut apart, or singulated, to form a plurality of hermetically sealed packages containing one or more micro-devices each. There are several options carrying out the singulation procedure. However, since the window sheet **2600**, frame **2402** and wafer substrate **2202** are bonded together, simply scribing and breaking the window sheet (as was done for the multiple stand-alone window assemblies) is not practical. Instead, at least the window sheet **2600** or the wafer substrate **2202** must be cut. The remaining portion may then either be cut, or scribed and broken. It is believed that the best result will be obtained by cutting the wafer substrate **2202** using a wafer-dicing saw, and then either scribing-and-breaking the window sheet **2600**, or cutting the window sheet using a similar dicing saw.

[0338] Referring now to FIG. 28, there is illustrated one option for singulation of a MS-WLP assembly. The MS-WLP assembly **2800** shown in FIG. 28 is similar in most respects to the assembly **2700** shown in FIG. 27, however, in this case the window sheet **2600** was pre-scribed (as denoted by reference number **2802**) through the metallic layers **2406**, if employed (and also layers **2404** running perpendicular thereto, also if employed) of the interior frame-attachment areas. After bonding, the assembly **2800** is cut from the outer side of the wafer substrate **2202** (as indicated by arrow **2804**) completely through the substrate and into the groove **2502** of interior frame/spacer members **2606** (and also members **2604** running perpendicular thereto). The cut **2804** does not, however, continue through the window sheet **2600**. Instead, after the wafer substrate **2202** and frame **2402** are cut, the window sheet **2600** is broken by bending it along the pre-scribed lines **2802**. The assembly **2800** may be first broken into rows, then each row broken into an individual packages along the column lines, or vice versa. In one variation of this method, the window sheet **2600** is not pre-scribed, but instead is scribed through the kerf **2806** formed by cutting through the wafer substrate **2202** and frame **2402**. It will be appreciated that this scribing must be sufficiently forceful to cut through the remaining portion of the frame member **2406** and metallic layers **2606** under the groove **2502**. The assembly is then broken into individual packages along the scribe lines as before.

[0339] Referring now to FIG. 29, in another variation, a MS-WLP assembly **2900** is individuated by simply cutting completely through the wafer substrate **2202**, frame/spacer **2402** and window sheet **2600** between each micro-device **2204** as indicated by arrow **2902**. The result is a plurality of individually WLP micro-devices **2904**. The individuating cuts may be made from either the window side or the substrate side, however, it may be necessary to protect the outer surface of the window sheet (e.g., with masking tape, etc.) to protect it from damage during the sawing operation.

[0340] When electrical-resistance heating (“ERH”) is used to facilitate diffusion bonding or soldering of the components of a MS-WLP assembly, the electrical current is typically applied so that it flows through both the window/frame junction and the frame/substrate junction simultaneously. To facilitate this ERH heating, the configuration of the MS-WLP assembly may be modified to provide “sacrificial” metallized areas (i.e., areas that will be discarded later) on the window sheet and wafer substrate for placement of ERH electrodes. Preferably, the electrode placement areas on the substrate and window will be accessible from directions substantially perpendicular to the wafer.

[0341] Referring now to FIG. 30, there is illustrated a wafer **3000** similar in most respects to the wafer **2002** of FIG. 23, i.e., having a plurality of micro-devices **2204** formed thereon and a metallized frame-attachment area **3002** formed thereon so as to surround the micro-devices. In this case, however, the wafer **3000** further includes a metallized electrode placement pad **3004** positioned at one end of the wafer. The electrode placement pad **3004** is in electrical contact with the metallized layers **2304**, **2306**, **2308** and **2310** of the frame-attachment area **3002**.

[0342] Referring now to FIG. 31, there is illustrated window sheet **3100** similar in most respects to the sheet **2600** of FIG. 26, i.e., having a metallized frame-attachment

area **3102** formed thereon so as to surround the window aperture areas **2603** on the sheet. In this case, however, the sheet **3100** further includes a metallized electrode placement pad **3104** positioned at one end of the sheet. The electrode placement pad **3104** is in electrical contact with the metallized layers **2604**, **2606**, **2608** and **2610** of the frame-attachment area **3102**.

[0343] Referring now to **FIG. 32**, there is illustrated a MS-WLP assembly **3200** in accordance with another embodiment. The components of the assembly **3200** are positioned such that the wafer substrate **3000** and the window sheet **3100** are adjacent to the frame/spacer **2402**, but the respective metallized electrode placement pads **3004** and **3104** over hang on opposite sides of the assembly. This configuration provides unobstructed access to the pads **3004** and **3104** in a direction perpendicular to the wafer (as denoted by arrows **3202**), allowing easy attachment of electrodes for ERH procedures.

[0344] During bonding of WLP assemblies, there are two bonds that should typically occur simultaneously: the junction between the frame/spacer and the window sheet and the junction between the frame/spacer and the wafer substrate. As was described previously, however, the window may first be bonded only to the frame, and later, using ERH, the window/frame assembly can be attached to the substrate of the device. As was previously described in the process for the manufacturing of stand-alone window assemblies, the configuration of the metal frame and placement of ERH electrodes may be critical for even heating using ERH heating techniques. Similarly, for MS-WLP devices, the metallization patterns and ERH electrode placement locations on the wafer substrate and the window sheet may be important to achieving even heating. Therefore, the size/shape of the frame including possibly excess or sacrificial features, and the metallization patterns on both the window sheet and the wafer substrate should be concurrently designed, modeled (e.g., using software simulation) and prototyped to ensure even heating of the bonded surfaces/features.

[0345] It will be appreciated that the previous embodiment describes a method for manufacturing MS-WLP assemblies which is suited for micro-devices having opposite-side electrical connection pads. Referring now to **FIG. 33**, there is illustrated a micro-device having same-side electrical connections. The micro-device **3300** is disposed on one side of a semiconductor substrate **3302**. A plurality of vias **3304** run from the active areas of the micro-device, through the substrate, and to a plurality of connection pads **3306** located on the same side of the substrate. Obviously, the electrical connection pads **3306** must be accessible even after the micro-device **3300** has been sealed within its hermetic package. In the following embodiment, there is presented another method for manufacturing MS-WLP assemblies suited for use with such micro-devices with same-side connections.

[0346] Referring now to **FIG. 34**, there is illustrated a wafer **3402** having a plurality of micro-devices **3300** formed thereupon, each micro-device having one or more sets **3403** of associated same-side connection pads **3306**. In accordance with this embodiment, the multiple micro-devices **3300** are individually hermetically packaged in a WLP prior to individuation of the substrate wafer **3402**, however the

same-side electrical connection pads **3306** remain accessible. The steps of this embodiment are similar in many respects to those of the previous embodiment, except for the changes described below.

[0347] Referring now to **FIG. 35**, the frame-attachment area **3502** of the semiconductor wafer **3402** is first prepared, in this case by depositing metallized layers onto the surface of the wafer substrate circumscribing each micro-device **3300**. In the embodiment shown, the prepared frame-attachment area **3502** includes three “ladder-shaped” grids **3503**, each consisting of double-width metallized rows **3504** (i.e., the “rungs” of the ladder) and single-width columns **3506** (the “sides” of the ladder) connected by buss strips **3508** at each end. The composition and thickness of the metallized layers in frame-attachment area **3502** may be any of those previously described for use in preparing the sheet seal-ring area or frame attachment areas.

[0348] Referring now to **FIG. 36**, there is illustrated a MS-WLP frame/spacer **3602** for attachment between the wafer **3402** and the window sheet **3702** (**FIG. 37**) of the MS-WLP assembly. It will be appreciated that in this embodiment, the MS-WLP frame/spacer **3602** is configured into multiple ladder shaped portions **3603**, each portion having double-width rung members **3604** and single-width side members **3606** that are configured to have a plan substantially corresponding to the ladder-shaped plans **3503** of the frame-attachment area **3502** on the wafer substrate **3402**. The ladder-shaped portions **3603** are attached to, and held in relative position to one-another by, connecting members **3608** located at opposite ends of the frame/spacer **3602**. As in the previous embodiment, the double-width members **3604** allow room for cutting the frame **3602** between micro-devices during singulation of the MS-WLP assembly (i.e., after bonding). In a preferred embodiment, the double-width members may have a grooved cross-section (e.g., similar to that shown in **FIGS. 25a** and **25b**) to facilitate their cutting apart. It will be appreciated however, that in other embodiments the MS-WLP frame/spacer may have a different configuration. In this embodiment, the MS-WLP frame/spacer **3602** is formed of a metal alloy having a CTE substantially matched to the CTE of the wafer substrate, however, in other embodiments the frame/spacer may be formed of non-metallic materials as previously described. Also as previously described, the frame/spacer **3602** will preferably be plated or metallized to facilitate the subsequent bonding process.

[0349] Referring now to **FIG. 37**, there is illustrated a MS-WLP window sheet **3700** for attachment to the MS-WLP frame/spacer **3602**. The window sheet **3700** is formed of glass or other transparent material having a CTE compatible with the other principal components of the assembly as previously described. At least the inner side (i.e., the side that will be inside the hermetic envelope) of the sheet **3700** (and preferably both sides) is optically finished, and any desired optical or protective coatings are in place on the inner side. Either before or after any desired optical or protective coatings are in place on the inner side of sheet **3700** (and preferably both sides), a frame-attachment area **3702** is prepared on the MS-WLP window sheet **3700** so as to circumscribe a plurality of window apertures **3705** that will ultimately be aligned with the micro-devices **3300** in the final MS-WLP assembly. In the embodiment shown, the prepared frame-attachment area **3702** includes metallic lay-

ers deposited on the sheet **3700** in multiple ladder-shaped portions **3703**, each portion including double-width rung members **3704** and single-width side members **3706**. Each ladder portion **3703** has a plan which corresponds substantially with the plan of the ladder portions **3603** of the frame/spacer **3602**. The methods and procedures for preparation of the window sheet **3700**, including the composition and thickness of the metallized layers **3704** and **3706** in the frame-attachment area **3702**, may be any of those previously described for use in preparing the sheet seal-ring area **318** of the “stand-alone” window assemblies or the frame attachment areas **2602** of the window sheet **2600** of the MS-WLP.

[0350] In the embodiment illustrated in **FIG. 37**, the metallized layers of window sheet **3700** extend beyond the ladder-shaped portions **3703**, and included additional portions configured to facilitate electric resistance heating (ERH). These additional portions include electrode attachment portions **3708** and bridge portions **3710**, both of which are electrically connected to the metallized layers **3704** and **3706** of the ladder portions **3703**. The configuration, e.g., placement and thickness, of these electrode attachment portions **3708** and bridge portions **3710** are selected to manage the flow of ERH current through the interfaces between the metallized portions of the window sheet **3700** and the frame/spacer **3602**, and through the interface between the frame/spacer **3602** and the metallized portions of the substrate **3402**, thereby controlling the heating at these interfaces during ERH-facilitated bonding operations.

[0351] As in previous embodiments, the inner surface of the window sheet **3700** maybe scribed, e.g., with a laser or diamond stylus, through each portion of the frame-attachment area **3702** to facilitate breaking apart of the MS-WLP assembly during singulation. Where the frame/spacer **3602** includes grooved members such as those illustrated in **FIGS. 25a-25b**, then the scribe lines on the window sheet **3700** will preferably be in register with the grooves **2502** of the frame members in the MS-WLP assembly.

[0352] Referring now to **FIG. 38**, there is illustrated a top view of a complete MS-WLP assembly **3800** including the wafer substrate **3402**, frame/spacer **3602** and window sheet **3700** stacked on one another such that the ladder-shaped areas **3503**, **3603** and **3703** of each respective component are substantially in register with one another, and such that each of the micro-devices **3300** is positioned beneath a window aperture area **3705** of the window sheet. It will be appreciated that in this embodiment, the configurations of the wafer **3402** and window sheet **3700** are complementary to facilitate the placement of ERH electrodes. Specifically, the portions of the wafer **3402** having the metallized buss strips **3508** project past the edges of the sheet **3700** (when viewed from above), allowing one set of ERH electrodes to make contact from vertically above, while the portions of the sheet having the metallized contact portions **3708** project past the edge of the wafer (when viewed from below), allowing another set of ERH electrodes to make contact from vertically below.

[0353] Of course, if the assembly **3800** is to be bonded using solder technology, then solder preforms (not shown) having a plan substantially corresponding with the frame-attachment areas are also positioned between the frame/spacer **3602** and the frame-attachment areas of the window sheet **3700** and substrate **3402** prior to bonding. Any of the

previously described bonding technologies may be used to effectuate the bond between the components. If the assembly **3800** is to be bonded using diffusion bonding technology, then when using interlayer preforms (not shown), these preforms will have a plan substantially corresponding with the frame-attachment areas and are also positioned between the frame/spacer, **3602** and the frame-attachment areas of the window sheet **3700** and/or between the frame/spacer **3602** and substrate **3402** prior to bonding. The MS-WLP assembly **3800** will look essentially the same before bonding and after bonding (except for incorporation into the bond area of any solder preforms or interlayers for diffusion bonding).

[0354] After bonding, the window sheet **3700** of the assembly **3800** may be viewed as including primary strip portions **3802**, which overlie the plurality of encapsulated micro-devices **3300**, secondary strip portions **3804**, which are interposed between the primary strips and overlie rows of non-encapsulated contact pads **3403**, and end strip portions **3806**, which are disposed at each end of the window sheet and also overlie rows of non-encapsulated contact pads **3403**. During singulation of the assembly **3800**, the secondary and end strip portions **3804** and **3806**, respectively, of the window sheet are cut away and discarded, these parts being essentially “sacrificial.” Further during singulation, the substrate **3402** is divided along cut lines (denoted by arrows **3808**) between the columns of micro-devices **3300** and contact pads **3403** to form multi-unit strips. The separating of the window sheet may be performed using saws, lasers or other conventional means, while the dividing of the substrate may be performed using saws, lasers, or by snapping along a score line.

[0355] Referring now to **FIGS. 39 and 40**, singulation of the MS-WLP assembly **3800** is illustrated. Referring first to **FIG. 39**, there is illustrated a multi-unit strip **3900** which has been separated from the MS-WLP assembly **3800**. The multi-unit strip **3900** includes a plurality of micro-devices **3300** on a portion **3902** of the original wafer substrate **3402**, the micro-devices being encapsulated within adjacent hermetic envelopes having one or more micro-devices under each window portion **3705** of the original window sheet, but with their associated electrical contact pads **3403** being non-encapsulated. The multi-unit strip **3900** is further cut apart, or singulated, along cut lines **3904**, which in this embodiment corresponds to the center of the frame members **3604** separating the adjacent hermetic envelopes. The result is a plurality of discrete hermetically sealed WLP packages containing one or more micro-devices under each window portion **3705**. An example of an individual WLP package **4000** produced by this method is illustrated in **FIG. 40**.

[0356] During the singulation of multi-unit strips **3900**, at least the window sheet **3700** or the wafer substrate portion **3902** must be cut. The remaining portion may then either be cut, or scribed and broken. It is believed that the best result will be obtained by cutting the wafer substrate portion **3902** using a wafer-dicing saw, and then either scribing-and-breaking the window sheet **3700**, or cutting the window sheet using a similar dicing saw.

[0357] While the invention has been shown or described in a variety of its forms, it should be apparent to those skilled in the art that it is not limited to these embodiments, but is susceptible to various changes without departing from the scope of the invention.

1. A hermetically sealed micro-device package encapsulating a micro-device and including a transparent window allowing light to pass into and out of a cavity containing the micro device, comprising:

- a semiconductor substrate having a micro-device operably disposed thereupon, the substrate having a first frame-attachment area formed thereupon having a plan that circumscribes the micro-device;
- a sheet of transparent material having a window aperture portion defined thereupon, the sheet having a second frame-attachment area formed thereupon having a plan that circumscribes the window aperture portion; and
- a frame/spacer positioned between, and hermetically bonded to, the semiconductor substrate and the transparent sheet, the frame including a continuous sidewall having a plan on one side substantially corresponding to, and substantially in register with, the plan of the first frame-attachment area, having a plan on the opposite side substantially corresponding to, and substantially in register with, the plan of the second frame-attachment area, and having a height that exceeds the height of the micro-device.

2. A package in accordance with claim 1, wherein the semiconductor substrate is substantially formed of silicon (Si).

3. A package in accordance with claim 1, wherein the semiconductor substrate is substantially formed of gallium arsenide (GaAs).

4. A package in accordance with claim 1, wherein the frame is formed of a material having a CTE substantially matched to the CTE of the transparent sheet and to the CTE of the semiconductor substrate.

5. A package in accordance with claim 1, wherein at least one of the hermetic bond between the frame and the semiconductor substrate and the hermetic bond between the frame and the transparent sheet is formed by diffusion bonding.

6. A package in accordance with claim 5, wherein both the hermetic bond between the frame and the semiconductor substrate and the hermetic bond between the frame and the transparent sheet are formed by diffusion bonding.

7. A package in accordance with claim 6, wherein the hermetic diffusion bond between the frame and the semiconductor substrate and the hermetic diffusion bond between the frame and the transparent sheet are formed in accordance with the following steps:

- pressing the substrate and the sheet against the frame with sufficient force to produce a first predetermined contact pressure along a first junction region between the frame and the first frame-attachment area of the substrate and a second predetermined contact pressure along a second junction region between the frame and the second frame-attachment area of the sheet;

heating the first junction region to produce a first predetermined temperature along the first junction region;

heating the second junction region to produce a second predetermined temperature along the second junction region;

maintaining the first predetermined contact pressure and the first predetermined temperature until a diffusion

bond is formed between the frame and the substrate all along the first junction region; and

maintaining the second predetermined contact pressure and the second predetermined temperature until a diffusion bond is formed between the frame and sheet all along the second junction region.

8. A package in accordance with claim 5, wherein during bonding of the frame to the semiconductor substrate and during bonding of the frame to the transparent sheet, the temperature of the window aperture portion of the sheet remains below the glass transition temperature (T_G) of the transparent material.

9. A multi-package assembly including a plurality of hermetically sealed cavities hermetically separated from one another by frame sidewalls, each of the cavities containing a micro-device positioned below a transparent window aperture allowing light to pass into and out of the cavity, the assembly comprising:

- a unitary semiconductor substrate having a plurality of micro-devices operably disposed thereupon, the substrate having a first frame-attachment area formed thereupon having a plan that circumscribes each of the micro-devices;

- a unitary sheet of transparent material, the sheet having a second frame-attachment area from thereupon having a plan that circumscribes a plurality of transparent window aperture positions of the sheet;

- a frame including a plurality of sidewalls, the sidewalls collectively having a plan on one side of the frame that substantially corresponds to, and is substantially in register with, the plan of the first frame-attachment area, having a plan on the opposite side of the frame that substantially corresponds to, and is substantially in register with, the plan of the second frame-attachment area, and having a height that exceeds the height of the micro-devices as disposed on the substrate;

wherein the semiconductor substrate, frame and transparent sheet are hermetically bonded together along the first and second frame attachment areas to form a plurality of hermetically sealed cavities separated from one another by the frame sidewalls, each of the cavities containing a micro-device positioned below one of the window aperture portions of the sheet.

10. A multi-package assembly in accordance with claim 9, wherein the semiconductor substrate is substantially formed of silicon (Si).

11. A multi-package assembly in accordance with claim 9, wherein the semiconductor substrate is substantially formed of gallium arsenide (GaAs).

12. A multi-package assembly in accordance with claim 9, wherein at least one of the hermetic bond between the frame and the semiconductor substrate and the hermetic bond between the frame and the transparent sheet is formed by diffusion bonding.

13. A multi-package assembly in accordance with claim 12, wherein both the hermetic bond between the frame and the semiconductor substrate and the hermetic bond between the frame and the transparent sheet are formed by diffusion bonding.

14. A multi-package assembly in accordance with claim 13, wherein the hermetic diffusion bond between the frame and the semiconductor substrate and the hermetic diffusion

bond between the frame and the transparent sheet frame formed in accordance with the following steps:

pressing the substrate and the sheet against the frame with sufficient force to produce a first predetermined contact pressure along a first junction region between the frame and the first frame-attachment area of the substrate and a second predetermined contact pressure along a second junction region between the frame and the second frame-attachment area of the sheet;

heating the first junction region to produce a first predetermined temperature along the first junction region;

heating the second junction region to produce a second predetermined temperature along the second junction region;

maintaining the first predetermined contact pressure and the first predetermined temperature until a diffusion bond is formed between the frame and the substrate all along the first junction region; and

maintaining the second predetermined contact pressure and the second predetermined temperature until a dif-

fusion bond is formed between the frame and sheet all along the second junction region.

15. A multi-package assembly in accordance with claim 9, wherein cutting through selected sidewalls will divide the assembly into discrete sub-assemblies, each of the discrete sub-assemblies including at least one hermetically sealed package containing a micro-device positioned below a transparent window aperture.

16. A multi-package assembly in accordance with claim 15, wherein at least some of the sidewalls of the frame are grooved to a reduced thickness at locations between adjacent cavities, thereby facilitating subsequent cutting through of the grooved sidewalls to divide the assembly.

17. A hermetically sealed micro-device package encapsulating a micro-device and including a transparent window allowing light to pass into and out of a cavity containing the micro-device, the package being formed by dividing a multi-package assembly in accordance with claim 9 into smaller sub-assemblies.

* * * * *