



US 20070113736A1

(19) **United States**

(12) **Patent Application Publication**
Bandosz

(10) **Pub. No.: US 2007/0113736 A1**

(43) **Pub. Date: May 24, 2007**

(54) **CATALYTIC ADSORBENTS OBTAINED FROM MUNICIPAL SLUDGES, INDUSTRIAL SLUDGES, COMPOST AND TOBACCO WASTE AND PROCESS FOR THEIR PRODUCTION**

Publication Classification

(51) **Int. Cl.**
B01D 53/02 (2006.01)
(52) **U.S. Cl.** **95/136; 95/139**

(75) Inventor: **Teresa J. Bandosz**, Teaneck, NJ (US)

Correspondence Address:
DARBY & DARBY P.C.
P. O. BOX 5257
NEW YORK, NY 10150-5257 (US)

(57) **ABSTRACT**

Industrial waste derived adsorbents were obtained by pyrolysis of sewage sludge, metal sludge, waste oil sludge and tobacco waste in some combination. The materials were used as media to remove hydrogen sulfide at room temperature in the presence of moisture. The initial and exhausted adsorbents after the breakthrough tests were characterized using sorption of nitrogen, thermal analysis, XRD, ICP, and surface pH measurements. Mixing tobacco and sludges result in a strong synergy enhancing the catalytic properties of adsorbents. During pyrolysis new mineral phases are formed as a result of solid state reaction between the components of the sludges. High temperature of pyrolysis is beneficial for the adsorbents due to the enhanced activation of carbonaceous phase and chemical stabilization of inorganic phase. Samples obtained at low temperature are sensitive to water, which deactivates their catalytic centers.

(73) Assignee: **Research Foundation of the City University of New York**, New York, NY (US)

(21) Appl. No.: **11/530,298**

(22) Filed: **Sep. 8, 2006**

Related U.S. Application Data

(60) Provisional application No. 60/715,788, filed on Sep. 8, 2005. Provisional application No. 60/782,593, filed on Mar. 14, 2006. Provisional application No. 60/801,545, filed on May 17, 2006.




FIGURE 1 – PRIOR ART




FIGURE 2A




FIGURE 2B




FIGURE 3




FIGURE 4




FIGURE 5




Figure 6




FIGURE 7A





FIGURE 7B

FIGURE 8






FIGURE 9




FIGURE 10




FIGURE 11




FIGURE 12




FIGURE 13




FIGURE 14




FIGURE 15




FIGURE 16




FIGURE 17




FIGURE 18




FIGURE 19




FIGURE 20




FIGURE 21






FIGURE 22

FIGURES 23A AND 23B





FIGURES 24A AND 24B




FIGURE 25




FIGURE 26




FIGURE 27






FIGURE 28



FIGURES 29A AND 29B



FIGURES 30A AND 30B

**CATALYTIC ADSORBENTS OBTAINED FROM
MUNICIPAL SLUDGES, INDUSTRIAL SLUDGES,
COMPOST AND TOBACCO WASTE AND
PROCESS FOR THEIR PRODUCTION**

**CROSS-REFERENCE TO RELATED
APPLICATIONS**

[0001] The present application claims priority to U.S. Provisional Patent Application Nos. 60/715,788 filed Sep. 8, 2005; 60/782,593 filed Mar. 14, 2006; and 60/801,545 filed May 17, 2006. The entireties of the applications are incorporated herein by reference.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The invention relates to the formation of catalytic adsorbents formed from the pyrolysis of different types of sludges alone or in combination with composting materials. The sludges include municipal, industrial, waste oil and metal based sludges. The composting materials can include tobacco waste.

[0004] 2. Discussion of the Related Art

[0005] Growing concerns about the environment has resulted in the development of new environmentally friendly technologies, new materials, and new ways to reduce and minimize wastes. One of the wastes produced by contemporary society in abundant quantity is municipal sewage sludge, often referred to as biosolids. Biosolids are a mixture of exhausted biomass generated in the aerobic and anaerobic digestion of the organic constituents of municipal sewage along with inorganic materials such as sand and metal oxides. Other sludges include wastes from such industry as shipyards, foundry, or paper mills. It is estimated that about 10 million dry tons of sewage sludge is produced in the United States. Moreover, Sweden alone contributes 220,000 dry tons of sludge to the 8-10 million tons of dry sludge produced by European Union.

[0006] Various methods have been used to dispose of or utilize municipal sewage sludge, including incineration, landfilling, road surfacing, conversion to fertilizer, compression into building blocks, and carbonization. Since 1976, several patents have been issued on carbonization of sewage sludge and various applications of the final materials. Carbonization of sludge in the presence of chemical activating agents such as zinc chloride and sulfuric acid produces new sorbents, with patented applications in processes such as removal of organics in the final stages of water cleaning and removal of chlorinated organics. Industrial sludges after dewatering processes/drying are either used as landfills or disposed mainly as hazardous wastes.

[0007] Carbonization of sludge to remove pollutants either from gas or liquid phase, is based on the fact that typically activated carbons are chosen. This is owing to their large surface area and high volume of pores. Often, these characteristics of activated carbons are not potent enough to retain certain molecules, especially small ones, for which the dispersive interactions with the carbon surface are rather weak. In such cases, the carbon surface has to be modified to impose the specific interactions. These interactions include hydrogen bonding, complexation, acid/base reactions or redox processes. Fortunately, in the case of carbons,

various technologies leading to modified surfaces exist and are relatively easy to achieve. Examples are oxidations with various oxidants such as strong acids, ozone, or air, impregnation with catalytic metals or reducing/oxidizing compounds, heat treatment in the presence of heteroatom sources such as chlorine or nitrogen compounds, and others.

[0008] As a result of the treatments mentioned above, new functional groups/chemical species are introduced to the surface. They impose the specific and/or chemical interactions with the species to be removed. To have the removal process efficient, the chemical state of these species and their dispersion on the surface are important issues. Another important challenge is preservation of carbon porosity which is a crucial asset for the retention/storage of pollutants. Thus, the surface modifications can be done in such a way in which a minimal decrease in the surface area/pore occur.

[0009] Taking into account the above requirements, in some cases modifications of a carbon surface, besides being a challenge, can also be associated with high expenses, especially when noble or catalytic metals are involved. Industrial sludges, as those coming from shipyards or other heavy metal industries, are rich in catalytic transition metals. By pyrolysis of these materials, not only the volume of waste is reduced but those environmentally detrimental wastes can be recycled and converted into valuable products. These products, when used, can be safely disposed since the leaching of materials is significantly reduced by mineralization of those metals via high temperature solid state reactions.

[0010] The process of carbonization of sewage sludges has been studied in detail previously and it is described in the literature. Materials obtained as a result of the treatment have surface areas between 100 and 500 m²/g. Their performance as adsorbents of hydrogen sulfides, sulfur dioxide, basic or acidic dyes, phenol or mercury has been reported as comparable or better than that of activated carbons. In many processes the excellent sorption ability of these materials is linked to the catalytic action of metals present in various forms in the final products. Their chemical forms along with the location on the surface were reported as important factors governing the pollutant removal capacities. In some cases the wastes were mingled and, owing to the synergy between the components, more efficient adsorbents were obtained.

[0011] Adsorbents obtained by pyrolysis of sludge can be considered as complex pseudocomposite materials. However, the process of carbonization of biosolids has been studied in detail previously and it is described in the literature. It has been recently shown that by simple pyrolysis of municipal sewage sludge derived fertilizer, Terrene®, exceptionally good adsorbents for removal of sulfur containing gases can be obtained. The removal capacity is twice that of coconut shell based activated carbon. Although, it was attributed to the specific combination of inorganic oxides of such metals as iron, copper, zinc or calcium. The predominant influence of inorganic phase or combination of oxides, which are also quite commonly used as catalysts for hydrogen sulfide oxidation or sulfur dioxide adsorption, was ruled out on the basis of the performance of a pure inorganic phase in the removal of sulfur containing gases. The capacity of pure inorganic phase heated at 950° C. was negligible. The data also showed that the oxidation of hydrogen sulfide

occurs until all micropores (mainly about 6 Å in size), likely within carbonaceous deposit or on the carbon/oxide interface, are filled with the reaction products. The form of that carbonaceous deposit is important and that deposit may play a role in adsorption capacity.

[0012] The products of oxidation immobilized on the surface are stored there. Table 1 shows the capacity of sewage sludge derived materials as adsorbents of sulfur containing gases. For removal of a toxic gas containing reduced sulfur the capacity is much greater than that of activated carbons. It happens in spite of the fact that the carbon content is small (about 20%) and pore volume much smaller than that of carbons.

TABLE 1

H ₂ S and SO ₂ breakthrough capacities for sludge derived adsorbents (SC series) and activated carbon (S208). The number after SC refers to the temperature of heat treatment in Centigrade.		
Sample	H ₂ S breakthrough capacity [mg/g]	SO ₂ breakthrough capacity [mg/g]
SC-400	8.2	5.1
SC-600	14.9	9.5
SC-800	23.6	22.2
SC-950	82.6	29.8
S208	48.8	48.2

[0013] Since pore volume seems to be a limiting factor for the capacity of sewage sludge derived materials, an increase in the content of carbonaceous deposit and pore volume with maintaining the desired content of a catalytically active phase seems to be the desired direction of feature research. Recent studies showed that the pore volume active in the removal of such compounds as hydrogen sulfide does not need to be in pores similar in size to adsorbent molecule. Since the catalytic oxidation is the predominant mechanism of adsorption, the larger pores, (meso- and macropores) where the product of oxidation is stored were found to be beneficial.

[0014] Another important factor is the chemistry of a catalytic phase, its dispersion, location on the surface, compatibility with the carbon phase and the effects of both phases on the removal process (adsorption/catalytic oxidation/storage). It was found that excellent capacity of an expensive desulfurization catalyst, US Filter carbon Midas®, is linked to the presence of calcium and magnesium oxides dispersed within the microporous activated carbon. On this catalyst, hydrogen sulfide is oxidized on basic centers of alkali earth metal oxides and sulfur is formed. The fact that this carbon is able to retain up to 60 wt % sulfur is linked to a limited reactivity of MgO and CaO. On their surface, due to the basic pH and the presence of moisture, sulfur is formed and owing to the close proximity of the carbon phase, that sulfur migrates to the high-energy adsorption centers, small pores. In this way the catalytic centers are renewed and the adsorbents work until all small pores are filled by sulfur.

[0015] Sewage sludge based materials were also found as efficient adsorbents for removal of mercury from waste water and copper. Other common industrial pollutants which can be efficiently removed using those materials are basic and acidic dyes. In the case of these adsorbates the high

capacity is linked to surface chemical nature (acidic and basic sites) and relatively large pores which are similar in size to the molecules of organic dyes.

[0016] At high temperature, the organic matter vaporizes, dehydrogenation occurs and carbon can be deposited back on the surface of an inorganic support as carbon nanotubes or filaments. This may happen due to the presence of highly dispersed catalytically active metals. Since this process resembles the chemical vapor deposition (CVD), it is referred to as the self-imposed chemical vapor deposition (SICVD). The process of carbon nanotube growth on the catalysts containing nickel or cobalt is well-known and described in the literature. The nanotubes and carbon filaments grow on metal “seeds” and their effective size depends on the sizes of the seeds. Introduction of more carbon phase can increase the porosity leading to more space for storing of oxidation products and also can lead to the formation of greater quantity of novel carbon entities in the process of CVD. FIG. 1 shows an SEM image of carbon nanotubes grown on the surface of sewage sludge-derived materials.

[0017] The carbon and nitrogen content of the sludge plays a role in the formation and properties of the adsorbent. While municipal sewage sludge is a promising material to use as a base with other waste sludges, other carbon or nitrogen based wastes can also be used. Besides formation of new carbon entities in the presence of catalytic metals as a result of heat treatment the new spinel-like/mineral like active components can be formed. Recently, for some sewage sludges containing iron and calcium the catalytically important entities were identified as dicalcium ferrite (Ca₂Fe₂O₅).

SUMMARY OF THE INVENTION

Definitions

[0018] The term “adsorption” refers to the phenomenon wherein the surface of a solid accumulates a concentration of molecules from its gaseous or liquid environment.

[0019] The term “adsorbent” refers to a material that is able to adsorb gases or vapors under certain conditions.

[0020] The term “pyrolysis” refers to heat treatment (e.g., at a temperature over 400° C.) in inert atmosphere of materials having organic origin.

[0021] The term “chemical activation” refers to the treatment of organic precursors with certain chemicals during pyrolysis.

[0022] The term “activated carbon” refers to a carbonaceous material obtained by pyrolysis of organic precursors (e.g., coal, wood, peat, etc.) at elevated temperatures followed by their activation using various physical or chemical agents (e.g., at a temperature between about 600° C. and 1,000° C.).

[0023] The term “caustic-impregnated carbon” refers to activated carbons impregnated with KOH and NaOH in order to increase their pH and adsorption capacity for acidic gases.

[0024] The term “breakthrough capacity” refers to the amount of substance adsorbed on the sorbent surface until the substance is detected in effluent air at a certain concentration level.

[0025] The term “acidic gases” refers to gases that are able to transform into acids, or gases that are able to interact as acid (e.g., electron acceptors).

[0026] The term “specific surface area” refers to the surface area of adsorbent considered as an area where adsorption of various molecules could occur.

[0027] The term “pore volume” refers to the volume of pores in an adsorbent calculated as available for nitrogen molecules at its boiling point.

[0028] The term “oxidation” refers to the change in the chemical stage of a substance associated with an electron loss. The charge on the species becomes more positive.

[0029] The term “residence time” refers to the average time taken by reagent molecules to pass through a reactor.

[0030] The term “compost material” refers to the individual materials that are composted.

[0031] The term “compost” can refer to either a mixture that consists largely of decayed organic matter or the act of converting compost materials into compost.

[0032] Waste oil sludge, waste metal sludge (both from a shipyard, but the origin of the sludges can be from any heavy industry facilities where transition metals such as iron, zinc, copper, nickel, chromium are used) were mixed with municipal sewage sludge at different proportions then pyrolyzed in the nitrogen atmosphere at 650° C. and 950° C. for two different time periods (half an hour and an hour). Additional samples were pyrolyzed in the nitrogen atmosphere at a low temperature, e.g., about 600° C., 625° C., 650° C., 675° C., or 700° C. or less, and at a high temperature, e.g., about 900° C., 925° C., 950° C., or 975° C., 1,000° C., 1,100° C. or higher. As used herein, the term “industrial sludge” includes any sludge that is not domestic wastewater sludge. This includes wastewater sludge from manufacturing or processing of raw materials, intermediate products, final products or other activities that include pollutants from non-domestic wastewater sources. “Municipal” or “domestic” wastewater sludge can be generated at plants servicing the general population and may conform to the “10 State Standards.”

[0033] Combinations of compost/compost materials and municipal/industrial sludge, along with pyrolyzation in a nitrogen atmosphere, can lead to formation of new adsorbents. The new adsorbents can consist of an inorganic phase (70-95% and 80-98%) and a carbonaceous phase (5-30% and 10-30%). The inorganic phase can contain highly dispersed catalytic metals such as iron, nickel, copper, zinc, chromium, and calcium and magnesium oxides, alumina, silica, etc.

[0034] As a result of synergy, a ceramics/mineral-like phase is formed. This phase reacts with nitrogen gas when exposed to elevated temperatures. The specific surface areas are about 10 m²/g to about 200 m²/g. For example, the specific surface areas may be about 10 m²/g, 20 m²/g, 30 m²/g, 40 m²/g, 50 m²/g, 60 m²/g, 70 m²/g, 80 m²/g, 90 m²/g, 100 m²/g, 110 m²/g, 120 m²/g, 130 m²/g, 140 m²/g, 150 m²/g, 160 m²/g, 170 m²/g, 180 m²/g, 190 m²/g, 200 m²/g, or greater. The specific pore volumes are about 0.002 cm³/g to about 0.074 m²/g. For example, the specific pore volumes are about 0.002 cm³/g, 0.005 m²/g, 0.015 m²/g, 0.025 m²/g, 0.035 m²/g, 0.045 m²/g, 0.055 m²/g, 0.065 m²/g, 0.074

m²/g, or greater. An important aspect of the texture is a significant volume of mesopores reaching about 0.8 cm³/g. All materials have basic pH, e.g., a pH over 9. They are capable of adsorbing up to about 10, 15, 20, 25, or 30 wt % of hydrogen sulfide, mainly as elemental sulfur.

[0035] The discovered solid state reactions form ceramics/mineral like crystallographic phases. Spinel-like compounds can form when municipal/industrial sludge is pyrolyzed at 950° C., such as wurtzite (ZnS), ferroan (Ca₂(Mg, Fe)₅(SiAl)₈O₂₂(OH)₂), chalcocite (Cu_{1.96}S), spinel (MgAl₂O₄), and feroxyhite (FeO(OH)) were found. In waste oil-based materials besides metallic iron, bornite (Cu₅FeS₄), hibonite (CaAl₁₂O₁₉), zincite (ZnO), ankerite (Ca(Fe, Mg)(CO₃)₂) are present. In metal sludge based adsorbent aluminum, metallic iron, copper, zinc, pyrope (Mg₃Al₂(SiO₄)₃), perrohotite (Fe₇S₈), Chalcocopyrite (CuFeS₂), Triolite (FeS) and Fersilicite, (FeSi) exist. Mixing industrial sludges with compost or compost materials can result in synergy enhancing the catalytic properties which can be linked to formation of new entities such as sapphirine (Mg_{3.5}Al₉Si_{1.5}O₂₀), maghemite (Fe₂O₃), cohenite (Fe₃C), lawsonite (CaAl₂Si₂O₇(OH)2H₂O), smithsonite (ZnCO₃), sphalerite (ZnS), and hematite (Fe₂O₃).

[0036] The new entities can be formed during pyrolysis that react with nitrogen gas when exposed to elevated temperatures (200-600° C.). This can result in an increase in weight between 0-3%. Some of these entities can be nitrides. The specific surface areas and total pore volumes of the adsorbents are between 10-210 m²/g and 0.15-0.85 cm³/g, respectively. An important aspect of the texture can be a significant volume of mesopores reaching 0.8 cm³/g (between 0.14-0.77 cm³/g). All materials have basic pH between 7-12. They are capable to adsorb up to 30 wt % of hydrogen sulfide mainly as elemental sulfur. Exposure to hydrogen sulfide and deposition of sulfur results in an increase in the volume of mesopores up to 25% as a result of formation of new pore space in-between deposited sulfur in large pores. The important components besides alkaline earth metals and transition metals are iron oxides and hydroxyoxides (but not only) since they contribute to oxidation of hydrogen sulfide to elemental sulfur. The developed materials are also good adsorbents of cationic or ionic dyes and heavy metals (up to 80 mg/g copper and up to 130 mg/g dyes). The spinel-like phase formed during pyrolysis contributes to cation exchange, complexations and precipitation reactions. During these reactions only small quantity of calcium and zinc is released to the solution as a result of a cation exchange process.

[0037] The present invention uses the combination of compost and/or compost materials and municipal and/or industrial waste sludge to form adsorbents. Successful results used fertilizer and municipal sludge to create adsorbents, because they contain, in part, large amounts of carbon and nitrogen. Other wastes are available that are rich in carbon and nitrogen to use as a base material. One waste is compost and compost materials. Compost materials can be divided into two categories, “brown”—high in carbon, and “green”—high in nitrogen.

[0038] Brown compost materials can be fall leaves, spent plants, straw and hay, pine needles, small twigs and wood chips, sawdust and woodshavings, shredded newspaper, egg shells, corncobs, bread and grains, wood ashes, old potting

soil, food-soiled paper towels and napkins, dried flowers, brewery waste, hops, and pomace, food-soiled cardboard (recycle if clean, but compost if dirty), stale flour, cereal, spices, beans, nutshells, meat and fish scraps.

[0039] Green compost materials can be fruit and vegetable scraps, coffee grounds and filters, tea bags, fresh leaves, green plants, prunings and hedge trimmings, grass clippings, weeds, flower bouquets, seaweed, feathers, horse manure, manure and bedding from small pets such as hamsters and rabbits, cornstarch and other organic packing materials, and spoiled juice.

[0040] Additionally, over 70,000 tons of tobacco waste is generated every year during the production of cigarettes. In India alone, over 20 years ago, almost 100,000 tons of tobacco waste was generated, and more is generated every year. Tobacco waste is currently used as a compost material and fertilizer. Tobacco waste spans the entire cigarette making process from growing and harvesting to final production. The types of wastes generated during pre- and post-harvest practice of tobacco include suckers, stems, mid ribs, leaf waste and dust. For example, green trimmings are generated as the either the stalks and/or leaves are harvested and separated from their stalks for curing. After curing, certain varieties of tobacco are threshed (by separating the midrib of the leaf) generating particle waste and stalks can also be removed at this stage, depending on the type of tobacco. Stems are removed from the cured and aged tobacco and the leaves and stems are chopped and blended. Tobacco dust can be formed during the chopping and blending stages. Further dust can be generated as the chopped tobacco is formed into tobacco rods and finally wrapped into paper. Some chemical characteristics of tobacco waste are listed in Table 2.

TABLE 2

Some Chemical Characteristics of Tobacco												
O.M. %	pH (1/5)	EC(1/5) (µm/cm)	Ca (µg/g)	Mg (µg/g)	N (%)	K (%)	P (µg/g)	Na (µg/g)	Fe (µg/g)	Cu (µg/g)	Zn (µg/g)	Mn (µg/g)
41	5.80	10700	8050	9400	2.35	1.95	973	572	3150	84	90	279

[0041] The use of compost and/or compost material was determined from studies using combinations of municipal sewage sludge and industrial sludge and municipal sludge and waste paper. The waste paper is used for its high carbon content. The paper was ground fine and added to the sludge. Compost materials can be ground like the paper and tobacco dust is in particulate/powder form. Sawdust is another compost material that is already in particulate/powder form. Sawdust is a brown compost material that is high in carbon. Wood char/ash can also be used based on its carbon content.

[0042] The invention can combine the compost/compost materials with industrial sludge or with a mixture of municipal and industrial sludge. The compost/compost materials can be wetted as it is mixed, or may contain enough natural moisture to be mixed directly. The ratios of compost to sludge can range between 25% and 75%. Additionally, calcium hydroxide may be added to help influence the dissociation of hydrogen sulfide.

BRIEF DESCRIPTION OF THE FIGURES

[0043] The above and still further objects, features and advantages of the present invention will become apparent upon consideration of the following detailed description of a specific embodiment thereof, especially when taken in conjunction with the accompanying drawings wherein like reference numerals in the various figures are utilized to designate like components, and wherein:

[0044] FIG. 1 is a SEM image of the carbon nanotubes on the surface of sewage sludge-derived adsorbent of the prior art;

[0045] FIGS. 2A and 2B are graphs depicting the predicted and measured volume of meso- and micro-pores, respectively, for the adsorbents derived from mixtures of industrial and municipal sludges;

[0046] FIG. 3 is a graph depicting dependence of H₂S removal capacity on the volume of mesopores in industrial and municipal sludge-derived adsorbents;

[0047] FIG. 4 is a graph depicting a comparison of the predicted and measured H₂S breakthrough capacity for sewage and industrial sludge-based adsorbents;

[0048] FIG. 5 is a graph depicting DTG curves in nitrogen for selected adsorbents for initial and H₂S exposed samples (E);

[0049] FIG. 6 is a graph depicting DTG curves in nitrogen for selected adsorbents for initial and H₂S exposed samples (E);

[0050] FIGS. 7A and 7B illustrate X-ray diffraction patterns at 650° C. and 950° C., respectively;

[0051] FIG. 8 illustrates changes in pore size distribution after H₂S adsorption;

[0052] FIG. 9 illustrates DTG curves in nitrogen for initial and exhausted samples;

[0053] FIG. 10 shows X-ray diffraction patterns for samples obtained at 650° C.;

[0054] FIG. 11 illustrates a comparison of the measured and predicted mesopores volume for WOSS samples obtained at various conditions;

[0055] FIG. 12 illustrates a comparison of the measured and predicted H₂S breakthrough capacities for samples obtained at various conditions;

[0056] FIG. 13 illustrates the H₂S breakthrough capacity curves for adsorbents obtained at 650° C.;

[0057] FIG. 14 illustrates the H₂S breakthrough curves for adsorbents obtained at 950° C.;

[0058] FIG. 15 illustrates the dependence of the H₂S breakthrough capacity on the amount of preadsorbed water;

[0059] FIG. 16 illustrates a comparison of measured and calculated (assuming the physical mixture of components) H₂S breakthrough capacities;

[0060] FIG. 17 illustrates XRD patterns for tobacco derived samples;

[0061] FIG. 18 illustrates XRD patterns for metal and waste oil sludge derived adsorbents;

[0062] FIG. 19 illustrate a XRD diffraction pattern for composite tobacco/metal sludge based adsorbents;

[0063] FIG. 20 illustrates nitrogen adsorption isotherms for samples pyrolyzed at 650° C.;

[0064] FIG. 21 illustrates nitrogen adsorption isotherms for samples pyrolyzed at 950° C.;

[0065] FIG. 22 illustrates pore size distributions for single component samples;

[0066] FIGS. 23A and 23B illustrate pore size distributions for samples pyrolyzed at 650° C.;

[0067] FIGS. 24A and 24B illustrate pore size distributions for samples pyrolyzed at 950° C.;

[0068] FIG. 25 shows a comparison of the volume of micropores measured and calculated assuming physical mixture of the components;

[0069] FIG. 26 shows a comparison of the volume of mesopores measured and calculated assuming physical mixture of the components;

[0070] FIG. 27 illustrates the dependence of H₂S breakthrough capacity on the volume of pores (micropores and mesopores for samples pyrolyzed at two temperatures);

[0071] FIG. 28 illustrates DTG curves in nitrogen for single component samples;

[0072] FIGS. 29A and 29B illustrate DTG curves in nitrogen for samples pyrolyzed at 650° C.; and

[0073] FIGS. 30A and 30B illustrate DTG curves in nitrogen for samples pyrolyzed at 950° C.

DETAILED DESCRIPTION OF THE INVENTION

[0074] Industrial sludges such as waste oil sludge and metal sludge can be utilized using pyrolysis to produce new catalytic adsorbents. An important result of mixing is an enhancement in the properties of the above-mentioned sewage sludge-based adsorbents. Although only waste oil sludge can lead to adsorbents with an exceptional ability for desulfurization with 30 wt % removal capacity, the presence of sewage sludge is an economically feasible method of utilizing this abundant material.

[0075] Mixing the sludge and their pyrolysis resulted in the enhanced properties compared to the physical mixture of pyrolyzed single components. FIGS. 2A and 2B show the comparison of the volumes of pores measured and predicted for the physical mixture of waste oil sludge (WO), sewage sludge (SS) and metal sludge (MS). The generally observed trend indicates that mixing sludges results in the development of an additional pore volume. That pore volume,

especially mesopores, was identified as one of the factors governing the adsorption capacity. FIG. 3 shows the dependence of the H₂S removal capacity on the volume of mesopores. Since the analysis of materials pH and thermodesorption indicated elemental sulfur as an oxidation product, only mesopores can store such amount of sulfur as found from H₂S breakthrough capacity tests (up to 30 wt %).

[0076] Besides porosity, surface chemistry is also altered during pyrolysis of the sludge mixture as compared to the single components. FIG. 4 shows the comparison of the measured and predicted capacity based on the performance of the individual components assuming the physical mixture. The huge enhancement found, reaching 100%, is the result of changes in the composition and the surface distribution of an inorganic phase. The sludges studied contain iron, copper, nickel, zinc, calcium, chromium and other metals in significant quantities. Their high temperature reaction in the presence of carbon phase can lead to unique spinel/mineral-like components active in the oxidation reactions.

[0077] FIG. 5 illustrates an increase in the mass of the sample obtained by high temperature pyrolysis. FIG. 5 shows DTG curves in nitrogen for selected adsorbents for initial and H₂S exposed samples (E). The phenomenon was not observed for the samples pyrolyzed at low temperature. While not intending to be bound by theory, the increase may be a result of nitride formation. It was found the certain ceramic materials, when exposed to nitrogen in the presence of char, are able to form nitrides. Formation of these ceramics can be crucial for catalytic performance.

[0078] Although the best adsorbents are obtained at about 650° C., the synergy is the most predominant at about 950° C. when a mineral like/ceramic phase is formed. Moreover, an increase in the mass of samples under nitrogen at about 600° C. indicates that ceramic components of adsorbents form nitrides in the presence of carbon. FIG. 6 illustrates DTG curves in nitrogen for selected adsorbents for initial and H₂S exposed samples (E). Those ceramics must be active in the process of H₂S adsorbents since an increase in mass significantly decreased after exposure to hydrogen sulfide and water. The surface of adsorbents treated at about 950° C. has very low affinity to retain water (hydrophobic). Temperature has also an effect on the density of the final products, which varies from about 0.25 at 650° C. to about 0.50 at 950° C.

[0079] As mentioned above, unique compounds exist as crystallographic phases and they consist of metals such as calcium, magnesium, alumina, copper, iron, zinc and non-metals such as oxygen sulfur, carbon and silica. The level of mineralization increases with an increase in the pyrolysis temperature and time. Higher temperature results in formation of two component metal-nonmetal crystallographic compounds with metals at low oxidation states. FIGS. 7A and 7B show the changes in the X-ray diffraction pattern for samples obtained at different temperatures. FIG. 7A illustrates the X-ray diffraction pattern at 650° C. and FIG. 7B is at 950° C.

[0080] Advantages of the present invention include the fact that the sorbents obtained from industrial sludge have five times higher capacity for hydrogen sulfide removal than unmodified carbons. Their capacity is comparable to that of caustics impregnated carbon used worldwide as hydrogen

sulfide adsorbents in sewage treatment plants. Furthermore, the kinetics of the removal process are very fast and no heat is released. Moreover, during adsorption, H_2S reacts with inorganic matter and is oxidized to elemental sulfur. The product is environmentally inert. Importantly, the pH of the spent material is basic, so it can be safely discarded. Only small amounts of SO_2 are released. Another advantage of the invention is that, since the sorbents are obtained from waste sludge, the significant amount of industrial and municipal waste can be recycled and reused in sewage treatment plants. The sorbents can be also used in desulfurization of gaseous fuels (for fuel cell applications) and in hydrothermal vents. The sorbents find another environmental application in removal of mercury from waste water. Furthermore, there is the possibility of regeneration of spent materials using heating to about $300^\circ C$. to remove elemental sulfur.

EXAMPLE 1

[0081] The homogeneous mixtures of waste sludges were prepared as listed in Table 3 and dried at $120^\circ C$. The dried samples were then crushed and pyrolyzed in a horizontal furnace at $950^\circ C$. for 30 min. The temperature ramp was 10 degrees/minute. An inert atmosphere was provided by 10 ml/min. flow of nitrogen. The yields, ash content and densities of materials are listed in Table 3.

TABLE 3

Adsorbents' composition, yields, ash content and densities.						
Sample	Wet composition	Solid content	Dry composition	Yield (dry mass)	Ash content*	γ [g/cm ³]
WO	WO: 100%	23.6	WO: 100%	29	92	0.48
SS	SS: 100%	24.6	SS: 100%	45	80	0.46
MS	MS: 100%	23.4	MS: 100%	47	@	0.85
WOSS	WO: 50% SS: 50%	—	WO: 49% SS: 51%	34	@	0.46
WOMS	WO: 50% MS: 50%	—	WO: 50% MS: 50%	50	@	0.47
WOSSMS	WO: 40% SS: 40% MS 10%	—	WO: 46% SS: 31% MS 23%	41	@	0.46

*Determined as mass left at $950^\circ C$. after in TA run in air.

@ - not determined due to reaction with air during burning

[0082] The performance of materials as sorbents for hydrogen sulfide was evaluated using lab developed breakthrough tests. Adsorbent samples were packed into a column (length 60 mm, diameter 9 mm, bed volume 6 cm³) and pre-humidified with moist air (relative humidity 80% at $25^\circ C$.) for an hour. The amount of adsorbed water was estimated from the increase in the sample weight after pre-humidification (the sorbents were removed from the column and weighted). Moist air containing 0.3% (3,000 ppm) H_2S was then passed through the column of adsorbent at 1.4 L/min. The breakthrough of H_2S was monitored using an Interscan LD-17 H_2S continuous monitor system interfaced with a computer data acquisition program. The test was stopped at the breakthrough concentration of 350 ppm. The adsorption capacities of each sorbent in terms of grams of H_2S per gram of material were calculated by integration of the area above the breakthrough curves, and from the H_2S concentration in the inlet gas, flow rate, breakthrough time, and mass of sorbent. The obtained results are collected in Table 4.

TABLE 4

H ₂ S breakthrough capacities, adsorption of water and surface pH before and after H ₂ S adsorption					
Sample	Brth capacity [mg/g]	Bth capacity [mg/cm ³]	Water adsorbed [mg/g]	pH	pHE
WO	109	52	0	9.9	9.4
SS	45	21	26	10.9	10.0
MS	2.8	2.4	0	10.67	10.04
WOSS	108	50	11	10.8	9.1
WOMS	86	40	3	9.9	8.8
WOSSMS	121	56	4	10.5	9.4

E - after exposure to H₂S

[0083] Characterization of pore sizes and adsorption capacity of materials prepared was accomplished using physical sorption measurement. The equilibrium adsorption isotherms of N₂ were measured by volumetric techniques. From the isotherms, the pore size distribution (PSD) was evaluated using the Density Functional Theory (DFT). The surface area was calculated using BET approach and micropore volumes using Dubinin-Radushkevich equation (DR). The results are presented in Table 5. The symbol “Δ” represents the difference in the specific pore volume before and after deposition of sulfur. For all samples but MS an increase in the volume of mesopores was found as a result of deposition of elemental sulfur and formation of new pores within that deposit. The examples of PSDs are presented in FIG. 8.

TABLE 5

Parameters of porous structure							
Sample	S_{BET} [m ² /g]	V_{mic} [cm ³ /g]	ΔV_{mic} [cm ³ /g]	V_{mes} [cm ³ /g]	ΔV_{mes} [cm ³ /g]	V_t [cm ³ /g]	V_{mic}/V_t
WO	132	0.050		0.314		0.364	14
WO-E	96	0.034	-0.16	0.355	0.041	0.389	8
SS	141	0.058		0.151		0.209	28
SS-E	121	0.032	-0.26	0.190	0.039	0.222	17
MS	10	0.002		0.015		0.017	12
MS-E	4	0.001	-0.01	0.005	-0.010	0.006	17
WOSS	150	0.061		0.163		0.224	41
WOSS-E	89	0.030	-0.31	0.258	0.096	0.288	31
WOMS	70	0.022		0.144		0.166	13
WOMS-E	60	0.017	-0.05	0.154	0.010	0.171	11
WOSSMS	144	0.053		0.267		0.320	20
WOSSMS-E	59	0.022	-0.21	0.183	-0.085	0.205	11

WO—waste oil origin;
SS—sewage sludge origin;
MS—metal sludge origin;
E—after exposure to H₂S.

[0084] Thermal analysis was carried out to identify the oxidation products and to balance the amount of sulfur deposited on the surface and the results are below in Table 6. The peaks between $200-450^\circ C$., illustrated in FIG. 9, represent the removal of elemental sulfur.

TABLE 6

Weight losses in various temperature ranges and amount of sulfur adsorbed from H ₂ S breakthrough capacity test. Weight loss is corrected for amount adsorbed in H ₂ S breakthrough test (Bth. Cap.)										
Sample	20–150° C.	Δ	150–450° C.	Δ	450–700° C.	Δ	800–1000° C.	Δ	Total Δ	S Bth Capacity
WO	3.02		0.84		0.05		2.3			
WO-E	2.31	0	9.20	8.36	1.0	0.95	1.9	0.0	9.31	10.2
SS	2.40		1.15		0.12		4.96		6.22	
SS-E	3.45	1.0	1.15	0	0.03	0	2.7		6.8	4.23
WOSS	3.48		0.21		0.43		2.67			
WOSS-E	3.15	0	5.85	5.64	0.53	0.1	2.67	0	5.64	10.1
WOMS	0.58		+1.88		+0.80		2.64			
WOMS-E	0.81	0.23	2.56	4.44	+0.59	0.21	2.12	0	4.88	8.08
WOSSMS	1.77		0.06		0.55		2.83			
WOSSMS-E	3.30	1.53	2.34	2.28	0.58	0.03	4.11	1.28	5.12	11.4

E - after exposure to H₂S.

[0085] X-Ray fluorescence was used to evaluate the content of iron, and sulfur after exhaustion. The results are presented in Table 7. Although the total amount is not given the intensities of the peaks in arbitrary units are related to the amount of specific species.

TABLE 7

XRF results.		
Sample	Fe	S(E)
WO	139.6	2496.86
SS	8584.02	ND
MS	12844.08	ND
WOSS	7321.80	ND
WOMS	12574.54	732.85
WOSSMS	12173.98	1352.93

EXAMPLE 2

[0086] The homogeneous mixtures of waste sludges were prepared as listed in Table 8 and dried at 120° C. The dried samples were then crushed and pyrolyzed in a horizontal furnace at 650° C. for 30 min. The temperature ramp was 10 degrees/minute. An inert atmosphere was provided by 10 ml/min flow of nitrogen. The yields, ash content and densities of materials are listed in Table 8.

TABLE 8

Adsorbents' composition, yield, and densities					
Sample	Wet composition	Solid content	Dry composition	Yield (dry mass)	γ [g/cm ³]
WOLT	WO: 100%	23.6	WO: 100%	32	0.26
SSLT	SS: 100%	24.6	SS: 100%	47	0.52
MSLT	MS: 100%	23.4	MS: 100%		0.47
WOSSLT	WO: 50%	—	WO: 49%		0.36
	SS: 50%		SS: 51%		
WOMSLT	WO: 50%	—	WO: 50%	58	0.38
	MS: 50%		MS: 50%		

TABLE 8-continued

Adsorbents' composition, yield, and densities					
Sample	Wet composition	Solid content	Dry composition	Yield (dry mass)	γ [g/cm ³]
WOSSMSLT	WO: 40%	—	WO: 46%	46	0.38
	SS: 40%		SS: 31%		
	MS 10%		MS 23%		

*Determined as mass left at 950° C. after thermol analyses run in air.
LT—low temperature, 650° C.

[0087] The performance of materials as sorbents for hydrogen sulfide was evaluated using lab developed breakthrough tests. Adsorbent samples were packed into a column (length 60 mm, diameter 9 mm, bed volume 6 cm³) and pre-humidified with moist air (relative humidity 80% at 25° C.) for an hour. The amount of adsorbed water was estimated from the increase in the sample weight after pre-humidification (the sorbents were removed from the column and weighted). Moist air containing 0.3% (3,000 ppm) H₂S was then passed through the column of adsorbent at 1.4 L/min. The breakthrough of H₂S was monitored using an Interscan LD-17 H₂S continuous monitor system interfaced with a computer data acquisition program. The test was stopped at the breakthrough concentration of 350 ppm. The adsorption capacities of each sorbent in terms of grams of H₂S per gram of material were calculated by integration of the area above the breakthrough curves, and from the H₂S concentration in the inlet gas, flow rate, breakthrough time, and mass of sorbent. The obtained results are collected in Table 9.

TABLE 9

H ₂ S breakthrough capacities, adsorption of water and surface pH before and after H ₂ S adsorption					
Sample	Brth capacity [mg/g]	Bth capacity [mg/cm ³]	Water adsorbed [mg/g]	pH	pH-E
WOLT	315	82	48	9.3	9.3
SSLT	9	5	18	10.9	11.1
MSLT	79	37	0	7.8	7.1
WOSSLT	146	53	21	9.2	9.1

TABLE 9-continued

H ₂ S breakthrough capacities, adsorption of water and surface pH before and after H ₂ S adsorption					
Sample	Bth		Water adsorbed [mg/g]	pH	pH-E
	Brth capacity [mg/g]	capacity [mg/cm ³]			
WOMSLT	130	49	14	9.8	9.4
WOSSMSLT	73	33	20	9.7	9.2

LT—low temperature, 650° C.;

E - after exposure to H₂S.

[0088] Characterization of pore sizes and adsorption capacity of materials prepared was accomplished using physical sorption measurement. Equilibrium adsorption isotherms of N₂ will be measured by volumetric techniques. From the isotherms the pore size distribution was evaluated using the Density Functional Theory (DFT). The surface area was calculated using BET approach and micropore volumes using Dubinin-Radushkevich equation (DR). The results are presented in Table 10. The symbol “Δ” represents the difference in the specific pore volume before and after deposition of sulfur.

TABLE 10

Sample	Parameters of porous structure						
	S _{BET} [m ² / g]	V _{mic} [cm ³ / g]	ΔV _{mic} [cm ³ /g]	V _{mes} [cm ³ / g]	ΔV _{mes} [cm ³ /g]	V _t [cm ³ /g]	V _{mic} / V _t
WOLT	202	0.074		0.765		0.839	10
WOLT-E	83	0.032	-0.42	0.434	-0.321	0.517	6
SSLT	92	0.037		0.113		0.150	25
SSLT-E	79	0.029	-0.008	0.106	-0.007	0.135	27
MSLT	34	0.014		0.122		0.136	11
MSLT-E	25	0.011	-0.003	0.160	0.038	0.171	6
WOSSLT	154	0.058		0.459		0.517	12
WOSSLT-E	72	0.027	-0.031	0.281	-0.178	0.308	10
WOMSLT	92	0.036		0.270		0.306	12
WOMSLT-E	65	0.026	-0.010	0.265	-0.005	0.291	9
WOSSMSLT	110	0.042		0.372		0.415	10
WOSSMSLT-E	59	0.023	-0.011	0.250	-0.122	0.273	8

LT—low temperature, 650° C.;

E - after exposure to H₂S

Thermal analysis was carried out to identify the oxidation products and to balance the amount of sulfur deposited on the surface is listed in Tables 11A and 11B, noting two different temperature ranges.

[0089] Tables 11A and 11B—Weight losses [in %] in various temperature ranges and amount of sulfur adsorbed from H₂S breakthrough capacity test [in %]. Weight loss is corrected for amount adsorbed in H₂S breakthrough test (Bth. Cap.); (LT—low temperature, 650° C.; E—after exposure to H₂S).

TABLE 11A

Sample	20–150° C.		150–450° C.		450–700° C.		800–1000° C.		Total Δ	S brth capacity
	Δ		Δ		Δ		Δ			
WOLT		4.70		1.85		1.00		6.69		
WOLT-E	2.51	7.21	32.75	34.6	3.88	4.88	0.59	7.28	39.7	29.6
SSLT		1.86		0.59		0.97		9.18		
SSLT-E	1.48	3.34	0.81	1.40	0.96	1.93	0.35	9.53	3.6	8.4
WOSSLT		3.56		1.49		1.04		10.46		
WOSSLT-E	1.64	5.20	14.41	15.9	1.83	2.87	1.71	12.17	19.59	13.7

[0090]

TABLE 11B

Sample	20–150° C.		150–400° C.		400–650° C.		Δ150–650° C.		Total Δ	S brth capacity
	Δ		Δ		Δ		Δ			
WOLT		4.70		1.71		0.77				
WOLT-E	0.72	5.42	21.64	23.35	3.41	4.82	2.64	7.46	31.6	31
SSLT		1.86		0.46		0.68				
SSLT-E	1.22	3.08	0.57	1.03	1.48	1.95	0.80	2.75	1.38	0.9
MSLT		3.66		1.37		0.78				
MSLT-E	0.82	4.48	11.93	13.3	2.28	14.11	1.5	15.61	15.2	14.3
WOSSLT		1.01		0		2.49				
WOSSLT-E	0.15	1.16	6.62	6.62	2.13	8.75	0	8.75	7.14	7.7
WOMSLT		3.31		0		0.93				
WOMSLT-E	0	2.86	6.13	6.13	2.78	8.91	1.85	10.76	9.00	12.7
WOSSMSLT		1.52		0		3.23				
WOSSMSLT-E	3.13	4.65	8.2	8.2	3.16	11.36	0	11.36	9.20	12.0

EXAMPLE 3

[0091] The homogeneous mixtures of waste sludges were prepared as listed in Table 12 and dried at 120° C. The dried samples were then crushed and pyrolyzed in a horizontal furnace at 950° C. for 60 min. The temperature ramp was 10 deg/min. An inert atmosphere was provided by 10 ml/min flow of nitrogen. The yields and densities of the materials are listed in Table 12.

TABLE 12

Adsorbents' composition and their densities				
Sample	Wet composition	Solid content	Dry composition	γ [g/cm ³]
WO60	WO: 100%	23.6	WO: 100%	0.47
SS60	SS: 100%	24.6	SS: 100%	0.46
MS60	MS: 100%	23.4	MS: 100%	0.84
WOSS60	WO: 50%	—	WO: 49%	0.41
	SS: 50%		SS: 51%	
WOMS60	WO: 50%	—	WO: 50%	0.46
	MS: 50%		MS: 50%	
WOSSMS60	WO: 40%	—	WO: 46%	0.45
	SS: 40%		SS: 31%	
	MS 10%		MS 23%	

[0092] The performance of materials as sorbents for hydrogen sulfide was evaluated using lab developed breakthrough tests. Adsorbent samples were packed into a column (length 60 mm, diameter 9 mm, bed volume 6 cm³) and prehumidified with moist air (relative humidity 80% at 25° C.) for an hour. The amount of adsorbed water was estimated from the increase in the sample weight after pre-humidification (the sorbents were removed from the column and weighted). Moist air containing 0.3% (3,000 ppm) H₂S was then passed through the column of adsorbent at 1.4 L/min. The breakthrough of H₂S was monitored using an Interscan LD-17 H₂S continuous monitor system interfaced with a computer data acquisition program. The test was stopped at the breakthrough concentration of 350 ppm. The adsorption capacities of each sorbent in terms of grams of H₂S per gram of material were calculated by integration of the area above the breakthrough curves, and from the H₂S concentration in the inlet gas, flow rate, breakthrough time, and mass of sorbent. The obtained results are collected in Table 13.

TABLE 13

H ₂ S breakthrough capacities, adsorption of water and surface pH before and after H ₂ S adsorption (E - after exposure to H ₂ S)					
Sample	Brth capacity [mg/g]	Bth capacity [mg/cm ³]	Water adsorbed [mg/g]	pH	pH-E
WO60	61	29	11	10.7	10.2
SS60	78	36	26	10.5	9.3

TABLE 13-continued

H ₂ S breakthrough capacities, adsorption of water and surface pH before and after H ₂ S adsorption (E - after exposure to H ₂ S)					
Sample	Brth capacity [mg/g]	Bth capacity [mg/cm ³]	Water adsorbed [mg/g]	pH	pH-E
MS60	2	1.7	0	9.8	9.6
WOSS60	78	32	36	11.8	9.8
WOMS60					9.4
WOSSMS60	73	33	20	10.7	10.2

EXAMPLE 4

[0093] X-ray diffraction measurements were conducted on WO, SS, MS, WOSS and WOSSMS adsorbent samples using standard powder diffraction procedure. Adsorbents were ground with methanol in a small agate mortar. Grinding of the adsorbents by hand ensures particle sizes between 5-10 μ m, which prevents line broadening in diffraction peaks. The mixture was smear-mounted onto the zero-background quartz window of a Philips specimen holder and allow to air dry. Samples were analyzed by Cu K α radiation generated in a Phillips XRG 300 X-ray diffractometer. A quartz standard slide was run to check for instrument wander and to obtain accurate location of 2 θ peaks.

[0094] In the waste oil based sludge sample heated at 650° C. (WO650) only metallic copper was detected as a separate crystallographic phase. See, FIG. 10. In the case of SS650, quartz (SiO₂), cristobalite (SiO₂), truscottite (Ca₁₄Si₂₄)O₅₈(OH)₈2 H₂O, and metallic iron are present. After mixing two components and heating at 650° C., besides quartz, cristobalite and metallic iron and copper, anorthite (CaAl₂Si₂O₈) and diasporite (AlO(OH)) are detected.

[0095] Comparison of the diffraction patterns presented in FIG. 10 clearly shows the synergetic effect in the chemical composition of materials. New components formed having their origin on addition of silica (coming from sewage sludge), and iron and zinc from waste oil sludge. These results indicated formation of new phases with an increase in the pyrolysis temperature and time. FIG. 10 shows the changes in chemistry after pyrolysis for half an hour at 650° C. while FIGS. 7A and 7B compare the sample pyrolyzed at 950° C.

[0096] The examples of crystallographic phases found for samples pyrolyzed at various conditions are presented in Tables 14 and 15. The headings indicate the composition of the sample, the temperature it was pyrolyzed at and the duration of the pyrolysis. For example, SS650-0.5 is sewage sludge pyrolyzed at 650° C. for 30 minutes.

TABLE 14

Crystallographic phases identified based on XRD analysis					
SS650-0.5	WO650-0.5	WOSS650-0.5	SS950-0.5	WO950-0.5	WOSS950-0.5
Aluminum Al	Aluminum Al	Anorthite CaAl ₂ Si ₂ O ₈			

TABLE 14-continued

Crystallographic phases identified based on XRD analysis					
SS650-0.5	WO650-0.5	WOSS650-0.5	SS950-0.5	WO950-0.5	WOSS950-0.5
Iron, Fe		Iron, Fe		Iron, Fe	Bayerite Al(OH) ₃ Bornite Cu ₅ FeS ₄ Maghemite Fe ₂ O ₃ Cohenite Fe ₃ C Lawsonite CaAl ₂ Si ₂ O ₇ (OH) ₂ H ₂ O
		Diaspore AlO(OH)		Hibonite CaAl ₁₂ O ₁₉ Ankerite Ca(Fe,Mg)CO ₃) ₂ Vaterite CaCO ₃	
Calcite magnesium Sapphirine (Mg ₄ Al ₄)Al ₄ Si ₂ O ₂₀	Huntite Mg ₃ Ca(CO ₃) ₄ Sapphirine (Mg ₄ Al ₄)Al ₄ Si ₂ O ₂₀		Spinel MgAl ₂ O ₄	Zincite ZnO	Vaterite CaCO ₃ Sapphirine (Mg ₄ Al ₄)Al ₄ Si ₂ O ₂₀ Spinel MgAl ₂ O ₄ Zincite ZnO Wurtzite ZnS
	Barringerite Fe ₂ P		Wurtzite ZnS		
	Goethite FeO(OH) Almandine Fe ₃ Al ₂ (SiO ₄) ₃		Ferroxhite, goethite FeO(OH)	Lepidocrocite, FeO(OH)	Smithsonite ZnCO ₃
Quartz, Cristobalite SiO ₂			Quartz SiO ₂	Quartz SiO ₂	

[0097]

TABLE 15

Crystallographic phases identified based on XRD analysis			
MS650	MS950	WOSSMS650	WOSSMS950
Aluminum	Aluminum Al		
Iron, Fe	Iron, Fe Copper, Cu Zinc, Zn	Iron Fe Copper, Cu	Huntite Mg ₅ Ca(CO ₃) Hematite, Fe ₂ O ₃
	Fersilicite, FeSi		
Moissanite, SiC Margarite, CaAl(Si ₂ Al ₂)O ₁₀ (OH) ₂ Almandine Fe ₃ Al ₂ (SiO ₄) ₃		Sphalerite, ZnS	
	Pyrrhotite, Fe _{1-x} S Triillite, FeS Pyrope, Mg ₃ Al ₂ (SiO ₄) ₃	Pyrrhotite, Fe _{1-x} S Triillite, FeS	Pyrrhotite, Fe _{1-x} S Triillite, FeS Spinel MgAl ₂ O ₄
	Chalcopyrite CuFeS ₂ Pyrrhotite Fe ₇ S ₈		Sphalerite ZnS
		Zhanghengite, CuZn Quartz, SiO ₂	

TABLE 15-continued

Crystallographic phases identified based on XRD analysis			
MS650	MS950	WOSSMS650	WOSSMS950
Quartz, Cristobalite SiO ₂		Moganite, SiO ₂	

[0098] Thus, in sewage sludge origin materials obtained at 950° C. such spinel-like compounds as wurtzite (ZnS), ferroan (Ca₂(Mg,Fe)₅(SiAl)₈O₂₂(OH)₂), chalcocite (Cu_{1.96}S), spinel (MgAl₂O₄), and feroxyhite (FeO(OH)) were found. In waste oil-based materials besides metallic iron, bornite (Cu₅FeS₄), hibonite (CaAl₁₂O₁₉), zincite (ZnO), ankerite (Ca(Fe, Mg)(CO₃)₂) are present. In metal sludge based adsorbent aluminum, metallic iron, copper, zinc, pyrope (Mg₃Al₂(SiO₄)₃), perrotite (Fe₇S₈), Chalcocopyrite (CuFeS₂), Triolite (FeS) and Fersilicite, (FeSi) exist. Mixing sludges results in synergy enhancing the catalytic properties which is linked to formation of new entities such as sapphirine (Mg_{3.5}Al₉Si_{1.5}O₂₀), maghemite (Fe₂O₃), cohenite (Fe₃C), lawsonite (CaAl₂Si₂O₇(OH)2H₂O), smithsonite (ZnCO₃), sphalerite (ZnS), and hematite (Fe₂O₃).

[0099] The materials obtained at 650° C. differ significantly from those obtained at 950° C. In the latter, more double-component crystallographic phases (metal-non-metal) are present with metals at lower oxidation states. The samples pyrolyzed at 650° C. contain more aluminosilicates with calcium, magnesium and iron cations.

EXAMPLE 5

[0100] The performance of adsorbents obtained at 650° C. and 950° C. for 0.5 hour or 1 hour as H₂S removal media was compared. The results are presented in Tables 16-18.

TABLE 16

H ₂ S breakthrough capacities, amount of water pre-adsorbed, and pH values for the initial and exhausted adsorbents.					
Sample	H ₂ S Brth.	H ₂ S Brth.	Water adsorbed	pH	pH-E
	Cap.	Cap.			
	[mg/g]	[mg/cm ³]	[mg/g]		
WO650-0.5	315	82	48	9.3	9.3
WO950-0.5	109	52	0	9.9	9.4
WO950-1	62	29	11	10.7	10.2
SS650-0.5	9	5	18	10.9	11.1
SS950-0.5	42	21	26	10.9	10.0
SS950-1	78	36	26	10.5	9.3
WOSS950-0.5	146	53	21	9.2	9.1
WOSS950-0.5	108	50	11	10.8	9.1
WOSS950-1	78	32	36	11.8	9.4

[0101]

TABLE 17

Shift in the pH – ΔpH between initial and exhausted samples, amount of sulfur expected based on the H ₂ S breakthrough capacity – S _{BT} , weight loss between 150–400° C., ΔW, and selectivity for oxidation to elemental sulfur, S _{el}				
Sample	ΔpH	S _{BT} [%]	ΔW [%]	S _{el} [%]
WO650-0.5	0	30.8	22.52	73
WO950-0.5	0.5	10.7	6.04	56
WO950-1	0.5	6.1	4.39	72
SS650-0.5	0	0.8	0.15	19
SS950-0.5	0.9	4.1	2.02	47
SS950-1	0.8	7.7	4.32	56
WOSS650-0.5	0.1	14.2	11.91	83
WOSS950-0.5	1.7	10.6	4.58	42
WOSS950-1	2.4	7.7	6.32	82

[0102]

TABLE 18

Structural parameters calculated from nitrogen adsorption isotherms					
Sample	S _{BET} [m ² /g]	V _{mic} [cm ³ /g]	V _{mes} [cm ³ /g]	V _t [cm ³ /g]	V _{mes} /V _t
WO650-0.5	202	0.074	0.765	0.839	0.92
WO650-0.5E	83	0.032	0.434	0.517	0.84
WO950-0.5	132	0.050	0.314	0.364	0.86
WO950-0.5E	96	0.054	0.355	0.389	0.91
WO950-1	92	0.037	0.303	0.340	0.89
WO950-1E	64	0.024	0.275	0.299	0.92
SS650-0.5	92	0.037	0.113	0.150	0.75
SS650-0.5E	79	0.029	0.106	0.135	0.78
SS950-0.5	141	0.058	0.151	0.209	0.72
SS950-0.5E	121	0.032	0.190	0.222	0.85
SS950-1	125	0.049	0.138	0.187	0.74
SS950-1E	47	0.018	0.124	0.132	0.94
WOSS650-0.5	154	0.058	0.459	0.517	0.89
WOSS650-0.5E	72	0.027	0.281	0.308	0.91
WOSS950-0.5	150	0.061	0.163	0.224	0.73
WOSS950-0.5E	89	0.030	0.258	0.288	0.89
WOSS950-1	199	0.075	0.377	0.447	0.84
WOSS950-1E	79	0.031	0.269	0.300	0.90

[0103] The results demonstrate the possibility of obtaining the valuable desulfurization catalysts from mixture of waste oil sludge and sewage sludge. Up to 30 wt % hydrogen sulfide can be retained on their surface. The surface properties, such as porosity, selectivity, or catalytic activity can be modified by changing the pyrolysis conditions. The catalytic activity and hydrogen sulfide removal capacity are directly related to the new surface chemistry formed by solid-state reactions during pyrolysis. This chemistry can also be controlled to certain degree by varying the composition of the precursor mixture. As a result of the synergy

between the sludge components new chemistry and porosity is formed which enhances both the physicochemical properties of the materials and their performance. FIG. 11 shows the comparison of the predicted (based on the composition and yield of the individual components) and measured volume of mesopores while FIG. 12 compares the predicted and measured H₂S breakthrough capacities.

EXAMPLE 6

[0104] Equilibrium studies for adsorption of acid red and basic fuchsin were conducted in a series of 100 ml Erlenmeyer flasks at 293 K. Each flask was filled with 10 ml of dye solution with concentrations between 10-1000 mg/l. After equilibration, the samples were filtrated, analyzed for their dyes content and the equilibrium adsorption capacity was calculated. The equilibrium data was fitted to the so-called Langmuir-Freundlich single solute isotherm. The results are presented in Table 19. The variable q_m is the adsorption capacity per unit gram of adsorbent, K is the Langmuir-type equilibrium constant, and the exponential term n is the heterogeneity parameter of the site energy.

TABLE 19

Fitting parameters to Langmuir-Freundlich isotherm				
sample	q_m [mg dye/g]	K [l/mg]	n	R^2
<u>Acid Red1</u>				
SS	45.00	0.10	0.44	0.9706
WO	46.35	0.14	0.23	0.9757
WOSSO	71.19	0.17	0.75	0.9610
WOSS650	68.40	0.15	0.74	0.9325
WVA	71.42	0.029	0.76	0.9919
<u>Basic Fuchsin</u>				
SS	70.36	0.03	0.36	0.9969
WO	94.21	0.18	0.65	0.9851
WOSS	126.89	0.29	0.59	0.9929
WOSS650	105.94	0.15	0.57	0.9804

[0105] The adsorption capacity is much higher than that for commercial activated carbon and it is attributed to the high volume of mesopores and the presence of mineral-like structures, which can participate in ion exchange reactions and precipitation reactions.

EXAMPLE 7

[0106] To check the effect of water exposure on the porosity of samples, the materials were dispersed in water and shake in room temperature for 24 hours. After drying the surface area, pore volumes and the average pore sizes were determined. The results indicated an increase in the volume of mesopores as a result of the reaction of inorganic oxides/salts with water. The results are presented in Table 20. Δ is the average pore size.

TABLE 20

Structural parameters						
Sample	S_{BET} (m ² /g)	V_{mic} (cm ³ /g)	V_{mes} (cm ³ /g)	V_t (cm ³ /g)	V_{mic}/V_t	Δ (Å)
SS 950	103	0.043	0.100	0.143	0.301	56
SS950-H ₂ O	100	0.041	0.095	0.136	0.302	55

TABLE 20-continued

Structural parameters						
Sample	S_{BET} (m ² /g)	V_{mic} (cm ³ /g)	V_{mes} (cm ³ /g)	V_t (cm ³ /g)	V_{mic}/V_t	Δ (Å)
W950	128	0.047	0.363	0.414	0.114	130
WO950-H ₂ O	109	0.040	0.390	0.431	0.093	158
WOSS950	192	0.077	0.279	0.356	0.216	74
WOSS950-H ₂ O	174	0.068	0.301	0.369	0.184	85
WOSS650	108	0.043	0.317	0.356	0.121	132
WOSSO650-H ₂ O	199	0.077	0.253	0.332	0.232	67

EXAMPLE 8

[0107] Equilibrium studies for adsorption of copper were conducted in a series of 100 ml Erlenmeyer flasks at 20° C. Each flask was filled with 10 ml of copper chloride solution with concentrations between 10-1000 mg/l. After equilibration, the samples were filtrated, analyzed for their coppers content and the equilibrium adsorption capacity was calculated. The equilibrium data was fitted to the so-called Langmuir-Freundlich single solute isotherm. The results are presented in Table 21. The variable q_m is the adsorption capacity per unit gram of adsorbent, K is the Langmuir-type equilibrium constant, and the exponential term n is the heterogeneity parameter of the site energy. The adsorption capacity, especially for samples obtained at 650° C. is much higher than that on activated carbon.

TABLE 21

Fitting parameters of copper (Cu ²⁺) adsorption isotherms to Langmuir-Freundlich Equation				
Sample	q_m [mg Cu ²⁺ /g]	K [l/mg]	n	R^2
SS650	63.48	0.009	0.65	0.9985
WO650	74.28	0.025	0.72	0.9964
WOSS650	69.72	0.018	0.78	0.9978
SS950	34.01	0.001	0.51	0.9970
WO950	15.88	0.006	0.92	0.9834
WOSS950	47.08	0.001	0.43	0.9957

EXAMPLE 9

[0108] The content of Fe, Ca, Cu, Zn, and Mg was determined in the single component samples, and based on the composition of the mixed samples, the content of these elements was evaluated. The results are presented in Table 22.

TABLE 22

Sample	Fe [%]	Ca [%]	Mg [%]	Cu [%]	Zn [%]	Cr [ppm]
SS650	4.9	4.8	1.3	0.13	0.19	58
SS950	6.1	5.1	1.1	0.17	0.09	90
WO650	3.2	4.0	11.0	0.20	0.54	140
WO950	3.7	5.1	8.4	0.25	0.51	280
MS950	2.2	14	0.46	0.77	0.16	6700
WOSS650*	4.0	4.4	6.15	0.16	0.36	99
WOSS950*	4.9	5.1	4.75	0.21	0.3	185
WOSSMS950*	4.4	6.9	3.89	0.32	0.27	1488

*evaluated assuming the same yield of each component (50%).

EXAMPLE 10

Materials

[0109] Two industrial sludges, waste oil sludge (WO) and metal sludge (M) from Newport News Shipyard were mixed with dry tobacco compost, homogenized, dried at 120° C. for 48 hours and then carbonized at 650° C. and 950° C. in nitrogen in a horizontal furnace. The heating rate was 10 deg/min with a one hour holding time. The weight of the wet industrial sludges (they contain 75% water) was adjusted to have 10% and 50% industrial sludge component based on the dry mass. The names of the adsorbents obtained, their compositions along with the yield, ash content and bulk density are collected in Table 23. Tobacco waste is referred to as TC.

[0110] The waste oil sludge was treated with CaCl₂, Na₃PO₄, NaOH and alum. Metal sludge treatment history includes addition of sulfuric acid and sodium hydroxide for pH adjustments, Al₂SO₄ for coagulation, anionic and cationic polymers, sodium bisulfide for chromium reduction, lime and CaCl₂. Thus, besides alkaline or alkaline earth element-containing compounds and iron, the waste oil sludge also contains 0.4% Cu, 2% Zn and between 200 and 1000 ppm of chromium, lead and nickel. In metal sludge there are less than 1% each of cadmium, chromium, copper, lead, manganese, selenium, vanadium and zinc. The content of volatile compounds in both waste oil sludge and metal sludge reaches 40% their dry mass, while the content of water in as-received materials is about 75%.

TABLE 23

Names of the adsorbents, their compositions, pyrolysis temperature, yield, bulk density and ash content					
Sample	Dry waste composition	Pyrolysis Temperature [° C.]	Yield [%]	Bulk Density [g/cm ³]	Ash [%]
CTCA	TC: 100%	650	52	0.63	67
CTCB	TC: 100%	950	51	0.52	76
CWOB	WO: 100%	950	30	0.48	92
CMB	M: 100%	950	47	0.58	ND
CTCWO-1A	TC 90%; WO 10%	650	52	0.42	72
CTCWO-2A	TC 50%; WO 50%	650	53	0.41	67
CTCWO-1B	TC 90%; WO 10%	950	45	0.40	78
CTCWO-2B	TC: 50%; WO 50%	950	38	0.40	86
CTCM-1A	TC 90%; M 10%	650	55	0.55	63
CTCM-2A	TC 50%; M 50%	650	65	0.52	86
CTCM-1B	TC 90%; M 10%	950	58	0.58	95
CTCM-2B	TC 50%; M 50%	950	57	0.30	96

Evaluation of H₂S Sorption Capacity

[0111] A custom-designed dynamic test was used to evaluate the performance of adsorbents for H₂S adsorption from gas streams as described above. Adsorbent samples were ground (1-2 mm particle size) and packed into a glass column (length 370 mm, internal diameter 9 mm, bed volume 6 cm³), and pre-humidified with moist air (relative humidity 80% at 25° C.) for one hour. The amount of water adsorbed was estimated from an increase in the sample weight. Moist air (relative humidity 80% at 25° C.) containing 0.3% (3,000 ppm) of H₂S was passed through the column of adsorbent at 0.5 L/min. The flow rate was controlled using Cole Parmer flow meters. The breakthrough of H₂S was monitored using MultiRae photoionization sen-

sor. The test was stopped at the breakthrough concentration of 100 ppm. The adsorption capacities of each adsorbent in terms of mg of hydrogen sulfide per g of adsorbent were calculated by integration of the area above the breakthrough curves, and from the H₂S concentration in the inlet gas, flow rate, breakthrough time, and mass of sorbent. For each sample the test was repeated at least twice. Besides H₂S the content of SO₂ in the outlet gas was also monitored using MultiRae photoionization sensor. The adsorbents exhausted after H₂S adsorption are designated by adding an additional letter E to their names.

Characterization of Pore Structure of Adsorbents

[0112] On the materials obtained sorption of nitrogen at its boiling point was carried out using ASAP 2010 (Micromeritics). Before the experiments, the samples were outgassed at 120° C. to constant vacuum (10⁻⁴ torr). From the isotherms, the surface areas (BET method), total pore volumes, V_t (from the last point of isotherm at relative pressure equal to 0.99), volumes of micropores, V_{mic} (DR), mesopore volume V_{mes}, total pore volume, V_t, along with pore size distributions were calculated (DFT).

pH

[0113] The pH of a carbonaceous sample suspension provides information about the acidity and basicity of the surface. A sample of 0.4 g of dry carbon powder was added to 20 mL of distilled water and the suspension was stirred overnight to reach equilibrium. Then the pH of suspension was measured.

Thermal Analysis

[0114] Thermal analysis was carried out using TA Instrument Thermal Analyzer. The instrument settings were: heating rate 10° C./min and a nitrogen atmosphere with 100 mL/min flow rate. For each measurement about 25 mg of a ground adsorbent sample were used. For analysis of the results the derivative thermogravimetric curves (DTG curves) are used. Ash content was determined from the residue left at 800° C. after heating the samples in air.

Elemental Analysis

[0115] Metal content in the adsorbents was determined using ICP in LSL labs, Syracuse, N.Y.

XRD

[0116] X-ray diffraction measurements were conducted using standard powder diffraction procedure. Adsorbents were ground with methanol in a small agate mortar. Grinding of the adsorbents by hand ensures particle sizes between 5-10 μm, which prevents line broadening in diffraction peaks. The mixture was smear-mounted onto the zero-background quartz window of a Phillips specimen holder and allow to air dry. Samples were analyzed by Cu K_α radiation generated in a Phillips XRG 300 X-ray diffractometer. A quartz standard slide was run to check for instrument wander and to obtain accurate location of 2θ peaks.

[0117] The H₂S breakthrough curves are presented in FIG. 13 and 14. As seen based on the steep rise in the breakthrough curves all tobacco based materials have short diffusion zone and almost immediately after H₂S is detected in the outlet gas, the adsorbents stop to work allowing the challenge gas to pass chemically undisturbed through the bed. No SO₂ concentration was detected which indicates that

all H₂S is converted to sulfur. In the case of metal and oil sludge derived materials small concentrations of sulfur dioxide, up to few ppm were measured at the same time when hydrogen sulfide appeared in the outlet gas. Even after mixing 50% tobacco waste and 50% waste oil, the kinetics of hydrogen sulfide retention characteristic to tobacco were still predominant since the shape of the slope of the curve does not resemble the one obtained for waste oil derived adsorbent.

[0118] The results of the H₂S breakthrough capacity measurements are summarized in Table 24 where besides the capacity expressed unit mass per gram of the adsorbents and per unit volume of the bed, the amount of water adsorbed during the prehumidification and the pH of the surface before and after adsorption process are reported.

[0119] As seen from Table 24, the highest capacity is found for tobacco waste oil sludge compositions pyrolyzed at 950° C. Although higher content of oil sludge is beneficial for the performance, even only 10% waste oil sludge increases the performance about 100% compared to pure tobacco waste based material. For CTC. material the high temperature of pyrolysis also significantly enhances the capacity. The results suggest the predominant influence of the tobacco waste on the performance since the waste oil sludge derived materials were reported to have best capacity at low temperature. In fact comparison of the capacity obtained for both tobacco and waste oils sludge based materials obtained at 950° C. clearly shows the synergetic effect; the capacity obtained for the mixture is much higher than for either one of its components.

TABLE 24

Sample	H ₂ S breakthrough capacity, amount of water adsorbed and the pH values of adsorbent surfaces.				
	H ₂ S breakthrough capacity		water adsorbed	pH	
	[mg/g]	[mg/cm ³]	[mg/g]	initial	exhausted
CWOB	40.2	21.1	11	10.7	10.2
CMB	5.0	2.9	0	11.2	11.2
CTC-A	6.6	4.2	51.8	11.2	10.7
CTC-B	23.1	12.1	38.2	11.3	11.3
CTCWO-1A	16.1	6.7	45.4	10.6	9.6
CTCWO-2A	0.9	0.4	82.0	9.2	9.2
CTCWO-1B	42.6	17.8	35.4	10.0	9.8
CTCWO-2B	90.2	36.4	43.3	10.3	9.3
CTCM-1A	13.0	7.2	29.6	10.6	10.5
CTCM-2A	22.5	11.7	11.2	9.4	9.3
CTCM-1B	23.1	13.5	21.5	11.2	11.1
CTCM-2B	18.9	5.7	10.8	10.8	10.6

[0120] As seen from Table 24, the highest capacity is found for tobacco waste oil sludge mixtures pyrolyzed at 950° C. Although higher content of oil sludge is beneficial for the performance, even only 10% waste oil sludge increases the performance about 100% compared to pure tobacco waste based material. For CTC. material, the high temperature of pyrolysis also significantly enhances the capacity. These results suggest the predominant influence of the tobacco waste on the performance since the waste oil sludge derived materials were reported to have best capacity at low temperature. In fact comparison of the capacity obtained for both tobacco and waste oils sludge-based materials obtained at 950° C. clearly shows the synergetic

effect; the capacity obtained for the mixture is much higher than for either one of its components.

[0121] Pyrolysis of waste oil sludge/tobacco mixture at 650° C. with a high content of waste oil sludge component has a detrimental effect on the capacity. Although on the surface of this sample the high amount of water is adsorbed, the capacity is negligible. Since the materials from waste oil sludge pyrolyzed at 650° C. had a very high capacity (reaching 30% wt.), the tobacco component hinders the capacity when low temperature treatment is applied. On the other hand, when metal sludge is used and mixture is pyrolyzed at low temperature, the capacity is enhanced compared to pure tobacco or pure metal sludge. Pyrolyzing those two mixtures at high temperature enhances capacity for low sludge content indicating once again the importance of the tobacco phase for hydrogen sulfide removal on composite adsorbents.

[0122] Taking into account variations in the behavior of the samples within their pyrolysis temperature, the relationship between the amount of water preadsorbed and the H₂S breakthrough capacity was analyzed. As seen from FIG. 15, for the samples pyrolyzed at low temperature have a detrimental effect on the H₂S breakthrough capacity. This may be linked to the low degree of mineralization and reactivity of the surface. It is likely that exposure to water causes its reaction with metal oxides and formation of hydroxides, which was observed previously. If the small pores are present, those hydroxides may block their entrances and thus decrease the available space for H₂S adsorption and sulfur storage. This problem is readdressed below where the porosity is discussed.

[0123] In the case of samples pyrolyzed at 950° C., water apparently enhances the capacity. This might be linked to its physical retention on the surface and formation of water film, in which the basic pH exists. This enables high concentration of HS⁻ ions and thus their oxidation to elemental sulfur.

[0124] All samples have basic pH, which helps with in hydrogen sulfide removal. The lowest pH is found for the CTCWO-2A sample, which has also the very low H₂S removal capacity. That pH is much lower than the pH of its components. The reason for this might be either in oxidation of the carbon phase or specific chemistry formed as a result of synergetic effect between the composite components.

[0125] Checking the synergetic effect on the H₂S breakthrough capacity, the measured values were compared to those calculated assuming the physical mixtures of the components, and taking into account their yields. The results presented in FIG. 16. While in the case of metal sludge only slight enhancement in the capacity is observed as a result of mixing, for the waste oil sludge/tobacco composites a significant synergetic effect is found with four fold increase in the capacity for CTCWO-2B.

[0126] That synergetic effect might be the result of either new catalytic phases formed when the materials are mixed and exposed to high temperature, formation of new pores enhancing physical adsorption and storage of oxidation products, an increased dispersion of catalytic phase, or more likely, the combination of all of these factors.

[0127] Using X-ray diffraction one may see both, the changes in the degree of crystallinity of the adsorbents and

the formation of new phases as a result of solid state reaction. FIG. 17 shows the comparison of XRD patterns for CTC adsorbents obtained at 650 and 950° C. As seen from the analysis of the ash content (Table 23) all adsorbents, even those derived from only tobacco waste have the majority of the inorganic phase. In the case of CTC A only quartz, and magnesian of ferrosilite ((Fe,Mg)SiO₃) are identified. Heating at 950° C. results in formation of more crystalline phases identified as bayerite (Al(OH)₃), ordered anorthite (CaAl₂Si₂O₈), anthophyllite ((Mg, Fe)₇Si₈O₂₂(OH)₂), and barrigerite (Fe₂P). Some of these minerals such as barrigerite, were also identified in sewage sludge derived materials in which enhanced H₂S adsorption was found. Magnesium, calcium and iron from these minerals can contribute to catalytic oxidation of hydrogen sulfide to sulfur. In the case of CWOB metallic iron, bornite (Cu₅FeS₄), hibonite (CaAl₁₂O₁₉), zincite (ZnO) and ankerite (Ca(Fe Mg)(CO₃)₂) are detected (FIG. 18). Heating metal sludge to 950° C. resulted in formation of numerous crystalline phases (multipeak pattern) from which pyrrhotite (Fe_{1-x}S), troilite (FeS), pyrope (Mg₃Al₂(SiO₄)₃), and metallic copper, zinc and iron have high probability to exist.

[0128] A multipeak pattern is also observed for the mixtures of tobacco with metal sludge of various compositions and pyrolyzed at two different temperatures. Comparison of FIGS. 17, 18 and 19 clearly shows that new phases are detected. Examples of these new phases for CTCM-1A are spinel (MgAl₂O₄), margarite (CaAl₂(Si₂Al₂)O₁₀(OH)₂), malachite (Cu₂CO₃(OH)₂), calcite (CaCO₃), cordierite (Mg₂Al₄Si₅O₁₈), pigeonite (Fe,Mg,Ca)SiO₃, corundum (Al₂O₃), tenorite (CuO), magnesioferrite (MgFe₂O₄), moissanite (SiC) and metallic iron. By pyrolyzing at 950° C., the mixture containing more metal sludge derived phase results in even more complex chemistry with predominant structures of mixed calcium iron and magnesium silicates and aluminosilicates. Some of them, as ferrocilite, anorthite were present in CTC-A. Examples are forsterite (Mg₂SiO₄), huntite (Mg₃Ca(CO₃)₄), aragonite (CaCO₃), wollastonite (CaSiO₃), dolomite (CaMg(CO₃)₂), cohenite, (Fe₃C) fersilicite (FeSi), covelite (CuS), bornite (Cu₅FeS₄), grunerite (Fe₇Si₈O₂₂(OH)₂), hardystonite (Ca₂ZnSi₂O₇) or akermanite (Ca₂MgSi₂O₇). In this case, compared to the sample pyrolyzed at 650° C., more carbonates are present, likely the result of gasification of carbon, less aluminum is involved in crystalline phase, and more two element-compounds appear.

[0129] Very complex and different form parent compound structure is obtained for CTCWO-2B (FIG. 19). In this case,

besides significant amount of quartz, over 50 new compounds were detected. They are mainly aluminosilicate with magnesium, calcium, iron, sodium, copper and lead. Examples include: sodian of anorthite ((Ca, Na) (Al, Si)₂Si₂O₈), forsterite (Mg₂SiO₄), albite (CaAl₂Si₂O₈), richterite (KNaCaMg₅Si₈O₂₂(OH)₂), renhahnite (Ca₃(Si₃O₈(OH)₂), Dahlite (Ca_{9.35}Na_{1.07}(PO₄)_{5.46}CO₃), rockbridgeite (Fe₅(PO₄)₃(OH)₅).

[0130] Although surface chemistry can play a crucial role in the process of hydrogen sulfide oxidation on the surface of materials studied, its effects cannot be discussed in isolation from the description of porous structure. The nitrogen adsorption isotherms are collected in FIGS. 20 and 21. Their shapes and nitrogen uptakes indicate differences in the sizes and volume of pores. While tobacco derived adsorbents are both very microporous, addition of waste oil sludge and metals sludge component contributes to the development of mesoporosity. The structural parameters calculated from nitrogen adsorption isotherms are collected in Table 25. Either waste oil sludge or metal sludge addition increase the surface areas of samples obtained at 950° C. in spite of the fact that the surface areas of both components pyrolyzed separately are much smaller. This indicates the beneficial synergetic effect. That development of porosity can be caused by gasification of carbon phase by alkaline earth metals present in the sludges, which can be considered as self-activation. Adding more waste oil sludge increases surface area, volume of micropores and volume of mesopores. Although the latter are present in much higher volume in the CWOB adsorbent, the new volume of micropores is the result of activation during pyrolysis. On the other hand, addition of metal sludge, even in only small quantity seems to be most beneficial for tobacco/metal sludge mixtures. These materials have a new volume of mesopores formed, which do not exist in either tobacco or metal sludge only based materials. Gasification can be important here. Much more alkaline earth metals than in waste oil sludge results (Table 26) in formation of larger pores in the carbonaceous deposit. It is interesting that the smallest surface area and pore volume are obtained for metal sludge tobacco mixture with 50/50 ratio of composition pyrolyzed at 650° C. This is consistent with this sample low capacity for hydrogen sulfide removal. Since both tobacco derived samples have almost identical structural parameters the differences in their performance as hydrogen sulfide adsorbents must be attributed to differences in surface chemistry mentioned above.

TABLE 25

Structural parameters calculated from nitrogen adsorption								
Sample	S _{BET} [m ² /g]	V _{mic} [cm ³ /g]	V _{meso} [m ² /g]	V _t [cm ³ /g]	V _{mic} /V _t	D _{BJH} [Å]	D _{DA} [Å]	E _o [kJ/mol]
CTCA	73	0.037	0.016	0.053	0.698	69	15	25.06
CTCAE	0	0	0	0	0	0	0	0
CTCB	78	0.039	0.020	0.059	0.661	41	16	21.82
CTCB-E	42	0.017	0.039	0.056	0.304	44	17	19.28
CTCWO-1A	71	0.041	0.051	0.092	0.446	95	16	23.80
CTCWO-1AE	33	0.014	0.088	0.102	0.137	100	17	17.62
CTCWO-2A	35	0.015	0.165	0.180	0.083	123	21	10.09
CTCWO-2AE	13	0.009	0.127	0.136	0.066	144	21	9.61
CTCWO-1B	120	0.055	0.096	0.151	0.364	56	16	20.65
CTCWO-1BE	37	0.019	0.072	0.091	0.209	68	17	17.55

TABLE 25-continued

Structural parameters calculated from nitrogen adsorption								
Sample	S_{BET} [m ² /g]	V_{mic} [cm ³ /g]	V_{meso} [m ² /g]	V_t [cm ³ /g]	V_{mic}/V_t	D_{BIH} [Å]	D_{DA} [Å]	E_o [kJ/mol]
CTCWO-2B	162	0.069	0.180	0.249	0.277	61	17	20.01
CTCWO-2BE	59	0.026	0.163	0.189	0.138	85	18	15.45
CTCM-1A	77	0.035	0.071	0.106	0.330	63	15	23.94
CTCM-1AE	8	0.006	0.047	0.053	0.113	138	17	18.79
CTCM-2A	74	0.031	0.144	0.175	0.177	79	17	18.67
CTCM-2AE	24	0.013	0.115	0.128	0.102	124	18	16.36
CTCM-1B	96	0.043	0.113	0.156	0.276	62	16	20.53
CTCM-1BE	46	0.018	0.097	0.115	0.157	99	18	15.62
CTCM-2B	59	0.031	0.061	0.092	0.337	82	16	20.19
CTCM-2BE	49	0.022	0.109	0.131	0.168	107	18	16.67

[0131] After H₂S removal the surface area and volumes of micropores significantly decrease. For the majority of samples, but CTC-BE, CTCWO-1AE and CTCM-2BE the volume of mesopores increases. This phenomenon was observed before and was attributed to formation of new pores within either sulfur deposit in large pores, if capacity was high, or/and formation of hydroxides on the surface as a result of exposure to water during prehumidification. Although in the case of CTCM-2BE only small amount of water was adsorbed with relatively high amount of H₂S, taking into account the small surface area of the samples, a significant, almost 100% increase in the volume of mesopores can be attributed to that sulfur deposit. The surface in large pores of the materials must be active since extensive gasification helped in high dispersion on the catalysts on the surface. For CTCWO-1AE, that increase can be attributed to the formation of hydroxides, since the surface is active and large amounts of water are adsorbed, and also to sulfur deposit. These hydroxides can totally block the porosity in the carbon deposit when more sludge derived phase is present and sample is exposed to moisture from the atmosphere. This likely happens in the case of CTCWO-2A, which was totally inactive in the process of H₂S adsorption, contrary to only waste oil sludge based sample whose capacity was found significant previously and it was attributed to the high volume of mesopores, which, owing to their large sizes, cannot be blocked by hydroxides. As seen from Table 25 the average pore sizes calculated using Dubinin-Astakhov method are related to the values of the characteristic energy of adsorption, which is the highest for CTC-A, CTCWO-1A, and CTCM-1A. These materials are obtained at low temperature so they can be considered as chars or “underactivated” carbons.

TABLE 26

Content of catalytic metals						
Sample	Fe [%]	Ca [%]	Mg [%]	Cu [%]	Zn [%]	Cr [ppm]
CWOB	3.7	5.1	8.4	0.25	0.51	280
CMB	22	14	0.46	0.77	0.16	6700
CTCB	1.45 × 10 – 4	0.0115	0.00255	1.55 × 10 ⁻⁵	2 × 10 ⁻⁵	ND

[0132] Details about the differences in the porosity of our samples are presented in FIGS. 22, 23A & B and 24A & B as pore size distributions. For all samples on the distribu-

tions two regions can be seen. One consists of micropores which are much more heterogeneous in their sizes for CTC. and CTWO series of samples than for CTCM. On the other hand, the heterogeneity of mesopores is much greater for the latter group of samples. After H₂S adsorption the smallest pores are not seen anymore indicating that sulfur is deposited either there, or at their entrances, and the new pores appears, especially with the range of sizes between 50-200 Å. In some cases it happens with the expense of macropores. This shows importance of large porosity with catalytically active surface to the process of hydrogen sulfide oxidation. If only physical adsorption were predominant those pores would not play any role and would have a negative effect on the performance of materials based on the unit volume of the bed. Thus in the case of this groups of materials very light adsorbents can be used which may increase the cost effectiveness of the removal process.

[0133] The synergetic effect of the porosity development in our materials is presented in FIGS. 25 and 26 where the measured volumes of micro and mesopores are compared to those calculated assuming the physical mixture of the components and taking into account the yield of materials. As discussed above, the synergetic effects of the sludge components on activation of the final products is clearly seen with the most pronounced effects of waste oil sludge on the volume of micropores and metal sludge—on the volume of mesopores.

[0134] To check the role of porosity for H₂S adsorption, the dependence of the capacity on the volume of pores was analyzed. The results are presented in FIG. 27. As seen, a good relationship is found for the volume of micropores. They have their origin likely in the tobacco derived carbon phase thus this component of the H₂S adsorption process has to have similar mechanism on all tobacco containing samples. Linear trend is also noticed for the volume of mesopores but only for materials obtained at 950° C. As it was shown above, water has a detrimental effect on the chemistry of low temperature pyrolyzed samples, thus the linear trend in his case is not expected. The linear relationship between the capacity and volume of mesopores indicates the activity of large pores in the process of hydrogen sulfide catalytic oxidation.

[0135] The comparison of DTG curves before and after adsorption of hydrogen sulfide is presented in FIGS. 28, 29, and 30. The peaks on the curves represent weight loss due to the decomposition/desorption of surface species. For

some initial samples as CTCB, CTCM-1A, CTCM-1B an increase in weight (negative peaks) is observed between 150 and 400° C. and between 600 and 800° C. The latter negative peak is also found for CTCWO-2B. This strange behavior was noticed previously for some metal sludge, waste oil sludge and even sewage sludge-based adsorbents. Since only nitrogen was present formation of nitrides was given as the only plausible explanation. After H₂S adsorption a negative peak is present only at high temperature range for CTCM-2BE. For other samples it is compensated by weight loss caused by removal of deposited sulfur between 200-400° C. Although this weight loss/peak intensity should be proportional to the amount of hydrogen sulfide deposited on the surface in the case of material pyrolyzed at 650° C. addition to the weight loss occurs as a result of dehydroxylation of surface at temperature smaller than 600° C. The hydroxides were formed when samples were exposed to water during prehumidification and H₂S adsorption.

[0136] Pyrolysis of waste tobacco compost and industrial sludges from heavy industries leads to the development of effective catalyst for desulfurization of air. An important role of carbonaceous phase derived from waste tobacco is in its relatively high carbon content. That carbon contributes to the development of porosity in both, micro and mesopore ranges. This happens via self-activation of carbon material by alkaline earth metals and water released from the decomposition of inorganic matter during heat treatment. As a result of solid state reactions at high temperature new catalytic species are formed on the surface of adsorbent as a result of synergy between the components of sludges. Location of these species in mesopores is beneficial for the desulfurization process. The surface of those pores retain water film where hydrogen sulfide can dissociate in the basic environment, Sulfur formed in oxidation reaction can be stored there in large quantity without rapid deactivation of the catalytic centers by sterical hindrances. High temperature of pyrolysis is beneficial for the adsorbents due to the enhanced activation of carbonaceous phase and chemical stabilization of inorganic phase. Samples obtained at low temperature are sensitive to water, which deactivates their catalytic centers.

[0137] The present invention is not to be limited in scope by the specific embodiments described herein. Indeed, various modifications of the invention in addition to those described herein will become apparent to those skilled in the art from the foregoing description and the accompanying figures. Such modifications are intended to fall within the scope of the appended claims.

[0138] It is further to be understood that all values are approximate, and are provided for description.

[0139] Patents, patent applications, publications, product descriptions, and protocols are cited throughout this application, the disclosures of which are expressly incorporated herein by reference in their entireties for all purposes.

We claim:

1. An adsorbent derived from one of compost or compost materials and sludge comprising:

- a) 20-30% porous carbon with incorporated organic nitrogen species; and
- b) 70-80% inorganic matter,

wherein the sludge is a at least one of industrial or municipal sludge.

2. The adsorbent of claim 1, wherein the inorganic matter includes highly dispersed catalytic oxides.

3. The adsorbent of claim 2, wherein the catalytic oxides are one or more of copper oxide, zinc oxide, iron oxide, calcium oxide, silica and alumina.

4. The adsorbent of claim 1, wherein the nitrogen species comprises amine or pyridine groups.

5. The adsorbent of claim 1, wherein the surface area of the adsorbent is 100-500 m²/g.

6. The adsorbent of claim 5, wherein the surface area of the adsorbent is 100-200 m²/g.

7. The adsorbent of claim 1, wherein the adsorbent contains micropores and the volume of the micropores are at least 0.03 cm³/g.

8. The adsorbent of claim 1, wherein the pH of the adsorbent is greater than 10.

9. The adsorbent of claim 1, wherein the pH of the adsorbent is between 7 and 10.

10. The adsorbent of claim 1, wherein the pH of the adsorbent is between 4 and 7.

11. A method of making an adsorbent which comprises the steps of:

- a) composting compost materials;
- b) thermally drying dewatered sewage sludge to form granulated organic fertilizer;
- c) mixing the organic fertilizer and the compost; and
- b) pyrolyzing the mixture at temperatures between 600° C. and 1000° C.

12. The method of claim 11, wherein the heating rate is between 5 and 10° C./minute and the hold time is between 60 and 90 minutes.

13. The method of claim 11, wherein the temperature of pyrolysis is between 800 and 1000° C.

14. The method of claim 13, wherein the temperature of pyrolysis is between 900 and 1000° C.

15. The method of claim 11, wherein the temperature of pyrolysis is between 600 and 900° C. and the adsorbent is further treated with 15-20% HCl.

16. The method of claim 15, wherein the temperature of pyrolysis is between 800 and 900° C.

17. The method of claim 11, further comprising the step of treating the mixture with between about 5 and about 30 wt % mineral oil, and wherein the mineral oil is selected from light mineral oil, heavy mineral oil, natural mineral oil, synthetic mineral oil, spent motor oil, and combinations thereof.

18. The process of removing acidic gases from wet air streams comprising putting an adsorbent comprising 20-30% porous carbon with incorporated organic nitrogen species and 70-80% inorganic matter derived from sewage sludge in contact with the wet air stream and allowing the adsorbent to adsorb the acidic gases.

19. The process of claim 18, wherein the acidic gases are one or more of hydrogen sulfide, sulfur dioxide, hydrogen cyanide, and nitrogen dioxide.

20. The process of claim 18, wherein the acidic gas is hydrogen sulfide which reacts with inorganic matter to be oxidized to sulfur dioxide or elemental sulfur and salt forms thereof.

21. The process of claim 18, wherein the wet air stream is effluent from a sewage treatment plant, gaseous fuel, or gases from hydrothermal vents.

22. The process of removing acidic gases from wet air streams comprising:

composting compost materials;

forming an adsorbent by thermally drying dewatered sewage sludge to form granulated organic fertilizer;

mixing the compost with the organic fertilizer; and

pyrolyzing said mixture at temperatures between 600-1000° C., putting said adsorbent in contact with the wet air stream, and allowing the adsorbent to adsorb the acidic gases.

23. The process of claim 22, wherein the acidic gases are one or more of hydrogen sulfide, sulfur dioxide, hydrogen cyanide, and nitrogen dioxide.

24. The process of claim 22, wherein the temperature of pyrolysis is between 800 and 1000° C.

25. The process of claim 24, wherein the temperature of pyrolysis is between 900 and 1000° C.

26. The process of claim 22, wherein the temperature of pyrolysis is between 600 and 900° C. and the adsorbent is further treated with 15-20% HCl.

27. The process of claim 26, wherein the temperature of pyrolysis is between 800 and 900° C.

28. The process of claim 22, wherein the adsorbent may be regenerated by heating to 300-500° C. to remove elemental sulfur and sulfur dioxide.

29. A method for producing an adsorbent, comprising the steps of:

combining a first sludge and at least one of a second sludge and a compost material to form a mixture;

thermally drying the mixture;

pyrolyzing the mixture at a temperature between about 600° C. and 1,100° C.; and

forming at least one of wurtzite, ferroan, chalcocite, spinel, feroxyhite, bornite, hibernite, zincite, ankerite, pyrope, perrotite, chalcocopyrite, triolite, fersilicite, sapphirine, maghemite, cohenite, lawsonite, smithsonite, sphalerite, goethite, huntite, anorthite, diaspore, vaterite, lepidirocrite, bayerite, moghemite, pyrohotite, hematite, sphalerite, almandine, and hematite during the pyrolyzing step.

30. The method of claim 29, wherein the compost material is at least one of tobacco waste, waste paper and wood char, or a combination thereof,

wherein the first sludge is a municipal sludge or an industrial sludge, and

wherein the second sludge is a municipal sludge or an industrial sludge and different from the first sludge.

* * * * *