




US 20080135099A1

(19) **United States**(12) **Patent Application Publication**
Yu et al.(10) **Pub. No.: US 2008/0135099 A1**(43) **Pub. Date: Jun. 12, 2008**(54) **SOLUTION-BASED FABRICATION OF
PHOTOVOLTAIC CELL****Publication Classification**(51) **Int. Cl.**
H01L 31/0216 (2006.01)(52) **U.S. Cl.** **136/264**; 106/31.92; 136/265(57) **ABSTRACT**

An ink for forming CIGS photovoltaic cell active layers is disclosed along with methods for making the ink, methods for making the active layers and a solar cell made with the active layer. The ink contains a mixture of nanoparticles of elements of groups IB, IIIA and (optionally) VIA. The particles are in a desired particle size range of between about 1 nm and about 500 nm in diameter, where a majority of the mass of the particles comprises particles ranging in size from no more than about 40% above or below an average particle size or, if the average particle size is less than about 5 nanometers, from no more than about 2 nanometers above or below the average particle size. The use of such ink avoids the need to expose the material to an H₂Se gas during the construction of a photovoltaic cell and allows more uniform melting during film annealing, more uniform intermixing of nanoparticles, and allows higher quality absorber films to be formed.

(76) Inventors: **Dong Yu**, Fremont, CA (US);
Jacqueline Fidanza, San Francisco,
CA (US); **Brian M. Sager**, Menlo
Park, CA (US)

Correspondence Address:

Director of IP
5521 Hellyer Avenue
San Jose, CA 95138(21) Appl. No.: **11/933,407**(22) Filed: **Oct. 31, 2007****Related U.S. Application Data**(63) Continuation of application No. 10/782,017, filed on
Feb. 19, 2004.




FIG. 1




FIG. 2

SOLUTION-BASED FABRICATION OF PHOTOVOLTAIC CELL

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This application is a continuation of U.S. patent application Ser. No. 10/782,017 filed Feb. 19, 2004. This application is also related to commonly-assigned co-pending application Ser. No. 10/782,545, titled "HIGH THROUGH-PUT SURFACE TREATMENT ON COILED FLEXIBLE SUBSTRATES" (Attorney Docket No. NSL-025) filed Feb. 19, 2004. Both applications are fully incorporated herein by reference for all purposes.

FIELD OF THE INVENTION

[0002] This invention is related to photovoltaic cells and more particularly to fabrication of IB-III A-VIA active layers for such cells.

BACKGROUND OF THE INVENTION

[0003] Low-cost production of solar cells on flexible substrates using printing or web coating technologies is promising highly cost-efficient alternative to traditional silicon-based solar cells. Recently, solution-based solar cells fabricated from alloys of copper (Cu) and indium (In) with selenium (Se) or sulfur (S) have been developed. Such CIGS solar cells have been fabricated using a non-vacuum process in which a water-based precursor ink is formulated containing mixed oxides of Cu, In and Ga, which is then coated on rigid or flexible substrates (see U.S. Pat. No. 6,127,202, issued October 2000 to Kapur et. al., and U.S. Pat. No. 6,268,014 issued July 2001 to Eberspacher and Pauls). The resulting oxide mixture was then subject to reduction in H_2/N_2 mixture and selenization in an H_2Se/N_2 mixture at high temperatures between 400 to 500° C. The resulting CIGS solar cells typically have efficiency in the range of 8 to 11%. Another alternative ink-based approach used metallic powder paste to coat on substrates followed by selenization under H_2Se/N_2 at high temperature to form a CIS (or CIGS cell) solar cell (Kapur, V. K., et. al. *Sol. Energy Mater. Sol. Cells*, 60 (2000) 127-134 and Kapur et al, *Thin Solid Films*, 431-432 (2003) 53-57 and also Kaelin, M., Meyer, T., Kurdesau, F., Rudmann, D., Zogg, H. and A. N. Tiawri. Low Cost Cu(m, Ga)Se₂ Absorber Layers from Selenization of Precursor Materials, 3rd World Conference on Photovoltaic Energy Conversion, Osaka, Japan, 2003). Unfortunately, the high temperature reduction and selenization steps used in each of these solar cell fabrication processes are neither cost effective nor easily scaled to high-volume production. Specifically, the H_2Se gas used is both highly toxic and flammable. Thus, when H_2Se is used at high temperatures, safety, environmental impact, and overall cost are serious concerns in the manufacturing process. Furthermore, the high temperature reduction and selenization steps make it impractical to make CIGS solar cells on inexpensive polymer or metallized polymer substrates that would warp, melt, or otherwise degrade at such high temperatures in the presence of reducing and/or oxidizing agents.

[0004] Although it is possible to make CIGS-based inks without using oxides, such inks have been produced in the prior art have several drawbacks for high-volume, roll-to-roll processing. For instance, the use of bulk $CuInSe_2$ as a starting material is challenging as bulk $CuInSe_2$ has a melting point around 1000° C. However, since most of the flexible sub-

strates such as Al foils and plastic foils cannot withstand such a high temperature, it is not possible to melt bulk material directly onto a substrate. Even glass will have serious warping problems at this temperature and substrate warping typically leads to inefficient cell performance—so even with deposition onto glass, it is very difficult to create high-performance solar cells by melting bulk material. Moreover, the energy requirements needed for high temperature manufacturing at 1000° C. will incur substantial cost. Consequently, processes occurring at much lower temperatures are preferred. However, annealing at a lower temperature tends to hinder the manner of crystal grain growth that is critical for the proper electronic properties of CIGS solar cell. Certain fluxing agents have been used to reduce the melting point and sintering temperature for $CuInSe_2$ (A. Vervae et al. in 9th European Communities PV Solar Energy Conference, 1989, 480). Unfortunately, such fluxing agents can introduce unwanted crystalline phases and alter the electronic properties of CIGS, thus lowering the efficiency of a CIGS solar cell.

[0005] Thus, there is a need in the art, for a non-oxide based precursor ink that overcomes the above disadvantages.

BRIEF DESCRIPTION OF THE DRAWINGS

[0006] The teachings of the present invention can be readily understood by considering the following detailed description in conjunction with the accompanying drawings, in which:

[0007] FIG. 1 is a schematic diagram of a spay co-precipitation apparatus for fabrication of nanoparticles according to an embodiment of the present invention.

[0008] FIG. 2 is a schematic diagram of a photovoltaic cell according to an embodiment of the present invention.

DESCRIPTION OF THE SPECIFIC EMBODIMENTS

[0009] Although the following detailed description contains many specific details for the purposes of illustration, anyone of ordinary skill in the art will appreciate that many variations and alterations to the following details are within the scope of the invention. Accordingly, the exemplary embodiments of the invention described below are set forth without any loss of generality to, and without imposing limitations upon, the claimed invention.

[0010] As used herein, the following terms have the following meanings:

[0011] "Elemental" refers to a material in substantially pure form as opposed to combined with other elements as in an alloy or in a chemical compound.

[0012] "Non-oxide" refers to a chemical moiety substantially devoid of oxygen.

[0013] Embodiments of the present invention provide several key features of a liquid ink that impact cell structure and function. The liquid ink includes particles containing elements of groups IB, III A and (optionally) VIA, e.g., copper and indium (with or without gallium) and selenium or sulfur. The particles may be between about 0.1 and about 500 nm. The decreased particle size can significantly lower both the melting point and the sintering temperature required (see e.g., C R M Wronski, "The Size Dependence of the Melting point of Small Particles of Tin" in the British Journal of Applied Physics vol. 18 No. 12, (December 1967) pp 1731-1737, IOP Publishing, Bristol, UK; L. H. Allen, "Nanocalorimetry Studies of Materials: Melting Point Depression and Magic Nanostructures" NNUN Abstracts 2002/Materials, Physics, Pro-

cesses & Characterization, pp 40; Zhang et al., 2000. "Size-dependent melting point depression of nanostructures: Nanocalorimetric measurements." Phys. Rev. B 62 (15): 548-557; Lisecki et al. 2000. "Annealing Process of Anisotropic Copper Nanocrystals." 2. Rods. Langmuir 16: 8807-8808). Generally, reduction in the melting point is inversely proportional to the particle radius, i.e., the smaller the nanoparticles, the lower the melting point. Smaller particles also tend to pack closer together and make better contact with each other. Reduction in size from bulk material to particles in about the 500 nm regime can already show significant differences in melting point and other altered physical and chemical properties. With much smaller particle sizes, e.g. in the nanometer size range, the surface area of particles will increase and nanoparticles will be in intimate contact with each other. In addition, in the nanometer size range, the reactivity of the particles and interaction between nanoparticles will be enhanced. This will help particles fuse together much easier thus enhancing the cohesion of the resulting CIGS layer (W. H. Qi, et al. in "China—EU Forum on Nanosized Technology" Beijing, P. R. China. December 2002. pp 86-92). This promotes coalescence between neighboring particles during sintering.

[0014] The particle sizes in the ink are typically distributed over a relatively narrow range, e.g. with the majority of particles of a given type being within about 40% of an average particle size for that type. Note that for an ink containing particles of different chemical types, e.g., different elemental metals, or different binary combinations, the different types of particles may have different average sizes so that the particles in the ink all melt at about the same temperature. By appropriately adjusting the particle size distribution amongst the particles of different materials in the mixture, it is possible for all the particles to melt at about the same temperature during sintering and yield more uniform crystalline phases. This enhances the electronic properties of the crystals in the resulting CIGS film. By contrast, in the prior art, CuInSe_2 powders generated, e.g., by a milling or nebulizing process to create powder precursors have typically contained a mixture of both small and large particles, resulting in a relatively broad size distribution. The presence of such a broad size distribution results in poor film formation. In particular, smaller particles tend to melt first while big particles remain unmelted. Further, particles of different sizes can non-uniformly distribute within a film. This heterogeneity leads to defects in film growth, decreases the uniformity and size of crystal grains, and negatively impacts the electronic properties (e.g., resistivity, bandgap, and carrier transport) of the CIGS layer upon incorporation into a photovoltaic device such as a solar cell. Although the prior art has addressed the advantages of a smaller average particle size in IB-III-VI nanoparticle inks (see e.g., U.S. Pat. No. 6,126,740 to Schulz), the resulting active layers made by annealing such inks have often been of relatively poor quality. The inventors have recognized that the problem is not just the particle size but also the particle size distribution, an issue that Schultz does not address.

[0015] Therefore, according to embodiments of the present invention, an ink for forming an active layer for a photovoltaic cell can be fabricated by forming liquid containing nanoparticles (e.g., elemental metal nanoparticles, non-oxide quantum nanoparticles, or metallic nanoparticles) of about 0.1-nm to about 500-nm diameter containing elements from groups IB, IIIA and VIA. A film of the ink can be spread onto a

substrate, and annealed to form a layer of IB-III-VI material. The nanoparticles may have a narrow size distribution characterized by an average nanoparticle size D . For example, the nanoparticles used to make up the film may have sizes within about 40% of D . If the average particle size is less than about 5 nm, then the variation can be bigger, e.g., between about 1 nm and about 2 nm. In this case, the resulting range of melting points is still sufficiently small to be considered to have a narrow particle size distribution. By way of example, the particles in the liquid may include Cu with In or Ga and Se or S in a stoichiometric ratio of approximately $\text{CuIn}_{1-x}\text{Ga}_x(\text{S}, \text{Se})_2$, where x is between 0 and 1.

[0016] Quantum nanoparticles are an important class of nanoparticles that can be used to make inks according to embodiments of the present invention. The electronic and optical properties of metals and semiconductors can change dramatically as the particulates of the materials are reduced to approach the nanometer size range of dimensions. At such size levels, the physical dimensions of the material generally impact the electronic, optical, chemical, and/or physical behavior of the material. The restriction of an electronic wave function to smaller and smaller regions of space within a particle of material (the resonance cavity) is referred to as "quantum confinement". Metal or semiconductor structures in the nanometer size range, exhibiting the characteristics of quantum confinement, are commonly referred to as "quantum dots" when the confinement is in three dimensions, "quantum wires" or "quantum rods" when the confinement is in two dimensions, and "quantum wells" when the confinement is in one dimension.

[0017] Quantum nanoparticles generally form in a size regime where the average particle diameter is less than about 10 nm. This small size results in new quantum phenomena that can change dramatically relative to a corresponding bulk material in part because quantum effects arise from the confinement of electrons and "holes" in the material (a hole represents the absence of an electron; the hole behaves as though it were a positively charged particle). The small particle size also changes other material properties, such as the electrical and nonlinear optical properties of a material, making them very different from those of the material's bulk form. For example, the optical bandgap of a quantum nanoparticle can often differ significantly from that of the material's bulk form. Further, the increased surface area to volume ratio of quantum nanoparticles renders them more reactive than the material's bulk form, often resulting for example in a dramatic melting point depression.

[0018] It should also be understood that group IB, IIIA, and VIA elements other than Cu, In, Ga, Se, and S may be included in the description of the IB-III-VI alloys described herein, and that the use of a hyphen ("—" e.g., in Cu—Se or Cu—In—Se) does not indicate a compound, but rather indicates a coexisting mixture of the elements joined by the hyphen. Where several elements can be combined with or substituted for each other, such as In and Ga, or Se, and S, in embodiments of the present invention, it is not uncommon in this art to include in a set of parentheses those elements that can be combined or interchanged, such as (m, Ga) or (Se, S). The descriptions in this specification sometimes use this convenience. Finally, also for convenience, the elements are discussed with their commonly accepted chemical symbols. Group IB elements suitable for use in the method of this invention include copper (Cu), silver (Ag), and gold (Au). Preferably the group IB element is copper (Cu). Group IIIA

elements suitable for use in the method of this invention include gallium (Ga), indium (In), aluminum (Al), and thallium (Tl). Preferably the group IIIA element is gallium (Ga) or indium (In). Group VIA elements of interest include selenium (Se), sulfur (S), and tellurium (Te), and preferably the group VIA element is either Se or S.

[0019] A nanoparticle-based CIGS ink has great utility for low cost web coating of ink-based photovoltaic cells. Methods to make nanoparticles of the desired materials having the desired narrow particle size distribution include controlling the reaction conditions under which the nanoparticles are made or using size-selective precipitation and other techniques (such as ultrafiltration and membrane emulsification). Nanoparticles in different categories may be incorporated into CIGS inks. These categories include but are not limited to: (1) Ternary nanoparticles such as CuInSe_2 or CuInG nanoparticles; (2) Binary nanoparticles such as CuSe and In_2Se_3 nanoparticles; (3) Metallic nanoparticles such as Cu and In nanoparticles; (4) A suspension made using one or more liquid metals, such as Ga; (5) A liquid made using one or more organometallic precursors. Significantly, each of these approaches may be implemented without selenization of the particles, film or IB-IIIA-VIA layer using H_2Se ; (6) Metal halides dissolved in chelating agents; and (7) Metal salts. All of these techniques may be used to form a liquid ink. In addition, the use of non-oxide or elemental metal particles avoids having to reduce the particles, film or IB-IIIA-VIA layer with H_2 .


[0020] The following examples illustrate several different ways, among others for creating nanoparticles with a narrow size distribution in the desired size range.

1. Ternary IB-IIIA-VIA Non-Oxide Quantum Nanoparticles (e.g., Cu(m, Ga)Se(S)_2)


[0021] According to one set of embodiments of the present invention, ternary, non-oxide quantum nanoparticles (e.g., quantum dots or quantum rods) for making a IB-IIIA-VIA ink may be fabricated by several different approaches.

1.1 Preparation of Organic Capped CuInSe_2 Non-Oxide Quantum Nanoparticles

[0022] Non-oxide quantum nanoparticles of CuInSe_2 may be fabricated according to a chemical reaction of the type:



where IB refers to an element of group IB, IIIA refers to an element of group IIIA, VIA refers to an element of group VIA and Hal refers to a halogen, preferably iodine (I) or chlorine (Cl). By way of example, IB can be Cu, IIIA can be Ga or In and VIA can be Se or S. In a particular example, among others, the reaction may be of the form:




[0023] The size distribution of the particles may be adjusted by controlling the reaction conditions under which the nanoparticles are made. By way of example, Trioctylphosphine oxide (TOPO) (20 g) may be heated to about 100°C ., followed by degassing and flushing with nitrogen. An equimolar solution of InCl_3 (2.20 g, 0.01 mol) and CuCl (1.0 g, 0.01 mol) in Trioctylphosphine (TOP) (15 mL) is injected into the hot TOPO at 100°C . The colorless TOPO turned bright yellow after injection, and the temperature drops to 80°C . The reaction may proceed for about 30 min to

one hour, after which the temperature is increased to 250°C ., and then 1.0 M trioctylphosphine selenide (TOPSe) (20 mL) is injected into the TOPO solution (a mixture of Se powder (1.66 g) and TOP (20 mL) is stirred at room temperature for 48 h to give a clear solution (1 M) of TOPSe. There may be an initial drop in temperature to 220°C ., after which the reaction stabilizes at about 250°C . and proceeds for 24-36 h. The reaction mixture is then cooled to about 60°C ., followed by the addition of excess methanol to flocculate the particles. There may be no immediate visible precipitation on the addition of methanol. A fine precipitate typically appears after stirring overnight. The precipitate may be separated by centrifugation and washed with methanol to remove the excess TOPO and then dissolved in toluene. (See e.g., M. A. Malik et. al. *Adv. Mater.* 1999, 11(17), 1441). Nanoparticles in the desired size distribution may be obtained from the precipitate, e.g., by size-selective precipitation or ultrafiltration. TOPO-capped CuInSe_2 nanoparticles may be mixed with water and an optional dispersant in an aqueous liquid to form a CIGS ink. The ratio of nanoparticles to water in weight percentage may be between about 10% and about 60%, e.g. about 40%. After coating a substrate with a film of the ink, the TOPO may be decomposed when heated at elevated temperature. At the same time, CuInSe_2 nanoparticles sinter together to form a polycrystalline film.


1.2 Preparation of CuInSe_2 Non-Oxide Quantum Nanoparticles with a Volatile Capping Agent

[0024] TOPO is a relatively large organic molecule, and since it can be difficult to completely remove large molecules like TOPO by simple thermal decomposition, so carbon contamination can be a potential issue in device fabrication. To overcome this disadvantage, a more preferred embodiment uses a smaller molecule with a lower boiling point, such as pyridine, as a coordinating ligand and solvent. In prior art, pyridine has been demonstrated to retard nanoparticle growth and narrow the size distribution in the case of CdSe nanoparticles. In that prior art, pyridine loosely caps the nanoparticles and ripens the nanoparticles continuously. This same principle can be applied to CIGS nanoparticles, which may be fabricated according to a reaction of the type:



where IB, IIIA, VIA and Hal have the meanings described above. As used herein, a capping agent can be broadly defined as a compound that binds to metal. General classes of ligands/capping agents include, but are not limited to phosphines, amines, alcohols, thiols, ethers, water, and glycols. By way of example, the ligand/capping agent can be pyridine, trioctylphosphine oxide (TOPO), trioctylphosphine sulfide, trioctylphosphine selenide, trioctylphosphine (TOP), triphenylphosphine, pyridine, alcohols (methanol, ethanol, propanol, butanol), thiols, ethane thiol, tetrahydrofuran, ethers, ammonia, amines (methyl amine, ethylamine, ethanolamine, ethylenediamine, trioctyl amine), ethylenediamine-tetraacetic acid (EDTA), glycols, amines, diketones, carboxylic acids, and/or acetonitrile. In a preferred embodiment, the ligand/capping agent is pyridine.

[0025] By way of example, the reaction may be of the type:



[0026] By way of example, and without limitation, CuCl (or CuI or CuCl_2) and InCl_3 (or InI_3) with a Cu/In molar ratio

ranging from 0.8 to 1.0 may be mixed in alcohol (methanol or ethanol). The concentrations for Cu and In ions may range from about 5 to 10 mM. Na_2Se may also be prepared in alcohol with a concentration double that of the Cu ions. The two alcoholic solutions are then added into a round-bottom reaction flask with pyridine. The precipitated nanoparticles are collected by filtration or centrifugation. The nanoparticles are then washed with organic solvents and redissolved in pyridine. The resulting CuInSe_2 nanoparticles are nanometer in size, with a narrow particle size distribution. Since pyridine is volatile, upon heating the coated film made from this nanoparticle ink has carbon-free nanocrystals, with minimal carbon contamination. Further sintering and annealing at lower temperature yields crystalline grains with uniform phases. (see e.g., B. A. Ridley et. al. *Science*, 1999, 286, 746).

1.3. Preparation of Non-Oxide Quantum Nanoparticles From Single-Source Precursors

[0027] In other embodiments of the present invention, ternary IB-III A-VIA nanoparticles may be prepared from single-source precursors. For instance, CuInS_2 nanoparticles may be prepared using the precursor $(\text{PPh}_3)_2\text{CuIn}(\text{SEt})_4$. By way of example, dioctyl phthalate (10 mL) may be heated to about 125° C. under vacuum for about 1 h to dry and degas the solvent. The flask may be back-filled with argon and cooled to room temperature prior to adding the precursor. $(\text{PPh}_3)_2\text{CuIn}(\text{SEt})_4$ (2.0 g, 2.0 mmol) is then added to the reaction flask and heating is resumed. At approximately 150° C. the precursor dissolved to form a transparent yellow solution. Typically, no further change is observed with time at this temperature. At about 150° C., the precursor remains, for the most part, intact.

[0028] Upon increase of the temperature to about 200° C. a red powder begins to precipitate within a few minutes. A reaction time of about 2-3 hours may be employed to complete the precipitation and maximize the yield. After cooling to room temperature under argon, toluene (40 ml) may be added to the reaction mixture to lower the viscosity of the reaction mixture and the red powder may be isolated by centrifugation. The powder may be consecutively washed with toluene and then methanol to remove any reaction byproducts and unreacted starting material, and then dried under vacuum at about 60-80° C. The washing and centrifugation steps may be carried out in ambient atmosphere. Then the product may be collected and stored in a nitrogen-filled glovebox. A portion of the product (100 mg) may be placed in a flask containing fresh dioctyl phthalate (10 mL), heated to higher temperatures, e.g. 250 to 300° C., and held at that temperature for about 1 hour. At a temperature of about 250° C., a brown/black powder (CuInS_2) is obtained. At about 300° C. the resulting powder is black and contains a CuInS_2 nanoparticulate. (See, e.g., S. L. Castro et. al. *Chem. Mater.* 2003, 15, 3142)

[0029] Approximately the same procedure as outlined above may be followed for a CuInSe_2 precursor. The precursor may be dissolved in the dioctyl phthalate at 138° C. For example, $(\text{PPh}_3)_2\text{CuIn}(\text{SePh})_4$ (1.951 g, 1.47 mmol) may be dissolved in about 10 mL of dioctyl phthalate. A red powder (0.523 g) may be collected after about 2 hours of heating at 200 to 300° C. This powder contained a $\text{CuInS}(\text{Se})_2$ nanoparticulate.

[0030] The size distributions of the CuInS_2 or $\text{CuIn}(\text{Se})_2$ nanoparticulates may be adjusted by size-selective precipitation, ultrafiltration and the like.

1.4. Preparation of $\text{CuInS}(\text{Se})_2$ Nanoparticles using Spray Co-Precipitation


[0031] An alternative embodiment to reduce particle size and narrow the particle size distribution utilizes a spray co-precipitation technique. In the prior art, ZnGa_2O_4 nanocrystals with a mean particle size less than 10 nm have been made using spray co-precipitation. In a spraying co-precipitation apparatus **100**, as shown in FIG. 1, compressed inert gas, e.g., nitrogen from gas sources **102**, **103** drives reactants from reactant sources **104**, **106** very quickly through stainless steel pipelines **108**, **110**. The flow rate can be adjusted by a flow-meter from about 5 to about 20 m/s. In general, one of the reactants may include one or more metal salts. As used herein the term metal salts includes metal halides, metal acetates, metal sulfates, metal nitrates, metal alcoholates, metal carbonates, metal phenolates and/or organometallics. In a particular example, the reactants may include, a metal halide, such as CuHal/InHal (where Hal refers to I or Cl) and thiourea or selenourea. The reactants mix and react at a T joint **112** of the two pipelines **108**, **110** and then spray into a beaker **114** with solvents (e.g., water or alcohols). The molar ratio of Cu, In and thiourea or selenourea may be adjusted e.g., by controlling the flow of the reactants with valves **116**, **118**, **120**, **122** to form CuInS_2 nanocrystals **124**. The size distributions of the nanocrystals **124** may be adjusted by size-selective precipitation, ultrafiltration and the like. For further information see Z. Jiao et. al. *Sensors* 2003, 15, 3142.

2. Production of Binary Nanoparticles

[0032] Some of the embodiments described above can be modified to produce binary non-oxide quantum nanoparticles, e.g., IB-VIA or IIIA-VIA or IB-VIA nanoparticles. These may be mixed together in the liquid to provide the desired ratios of IB, IIIA and VIA elements. By way of example there are several different approaches to producing CuSe and In_2Se_3 .


2.1. TOPO-Capped CuSe Non-Oxide Quantum Nanoparticles

[0033] In another embodiment, quantum dots with nearly uniform size may be fabricated by solvothermal methods according to a reaction of the type:



where IB, IIIA, VIA and TOPO have the meanings describe above. By way of example IB may be Cu, and VIA may be Se or S.

[0034] In a particular example, the quantum dots may be fabricated using a reaction of the type:




[0035] Quantum dots and rods of this type have been synthesized in the range of about 5 to about 15 nm using Solvothermal or solution reaction methods (see, e.g., M. A. Malik et. al. "A Novel Route for the Preparation of CuSe and CuInSe_2 Nanoparticles," in *Advanced Materials*, Vol 11, No. 17, pp 1441-1444, 1999). By way of example, and without limitation, CuSe Quantum Dots may be fabricated as follows. $\text{Cu}(\text{Et}_2\text{CNSe}_2)_2$ (0.5 to 2 g) may be dissolved in tri-n-oc-


tylphosphine TOP (10 to 30 mL). This solution is then injected into hot tri-n-octylphosphine oxide TOPO (10 to 20 g) at 250° C. A decrease in temperature of 20-30° C. may be observed. The solution is then allowed to stabilize at about 250° C. and is heated for about 60 min at this temperature. The solution is then cooled to approximately 70° C., and after an excess of methanol was added, a flocculant precipitate forms. The solid may be separated by centrifugation, washed with methanol, and redispersed in toluene. The toluene may then be removed under a vacuum to give pale yellow TOPO-capped CuSe nanoparticles. The particles may be washed three times with methanol and redissolved in toluene. Size-selective precipitation may then be carried out on the particles to obtain a collection of quantum dots of the desired average particle size and size distribution.

2.2. CuSe Non-Oxide Quantum Nanoparticles Prepared in Volatile Solvent

[0036] Pyridine-capped binary nanoparticles (e.g., CuSe) may be prepared according to a reaction of the type:




[0037] By way of example, IB may be Cu, Hal may be Cl or I, VIA may be Se or S. The ligand/capping agent may be any ligand that is co-processable with the metal salts used. By way of example, the ligand/capping agent may be pyridine, trioctylphosphine oxide, trioctylphosphine, triphenylphosphine, pyridine, alcohols (methanol, ethanol, propanol, butanol), ethane thiol, tetrahydrofuran, ethers, ammonia, amines (methyl amine, ethylamine, ethylenediamine) and/or acetonitrile. In a particular example, the reaction may be of the type:




[0038] The conditions for this reaction are similar to those described in section 1.2 except that there is no In ion involved in the reaction.

2.3. In₂Se₃ Non-Oxide Quantum Nanoparticles Prepared in Volatile Solvent

[0039] In₂Se₃ nanoparticles may be prepared according to a reaction of the type



[0040] Where IIIA, VIA and Hal can be any of the appropriate elements described above. By way of example, the reaction may be of the type



[0041] The conditions for this reaction are similar to those described in section 1.2 except that there is no Cu ion involved in the reaction.

2.4. Sonochemical Synthesis of CuSe In₂Se₃ or CuInSe₂ Non-Oxide Quantum Nanoparticles


[0042] In the prior art, ZnSe nanoparticles with a mean size of 3 nanometers have been prepared using a sonochemical method (see, e.g., J. Zhu et. al. *Chem. Mater.* 2000, 12, 73). According to an alternative embodiment of the invention, the same sonochemical method can be applied to forming CuSe or In₂Se₃ or CuInSe₂ nanoparticles for a CIGS-based ink. By way of example, and without limitation, Cu(Ac)₂ (445 mg) and/or In(Ac)₃ (720 mg) and 240 mg of selenourea may be

dissolved in 70 mL of doubly distilled water and sonicated for about 1 hour under an atmosphere of argon, at room temperature. A round-bottom Pyrex glass vessel (total volume 70 mL) may be used for the ultrasound irradiation. The temperature of the mixture rises gradually to about 80° C. during ultrasonic irradiation. After about 1 hour of sonication, the solution may be centrifuged, and the precipitate washed with water and then with absolute ethanol.

3. Elemental Metal Nanoparticles of Cu, In and Cu—In alloy with Se(S) Vapor or Powders

[0043] In a preferred embodiment, the nanoparticles for the ink may be prepared from a mixture of metal nanoparticles and a vapor or powder containing either Se or S. Metal nanoparticles have been prepared by a wide variety of techniques including but not limited to laser ablation, nucleation from vapor, exploding wires by electrical current surge, thermal decomposition of organometallic compounds, sonolysis, pulse radiolysis, electrochemical reduction and chemical reduction of the corresponding metal salts, and the like. Reduction of metal salts in the presence of a suitable protecting agent is a commonly used technique. Generally, a reductant, such as borohydride, hydrotriorganoborates, hydrogen or citrate, is added to a solution of the corresponding metal salt. An easily oxidized solvent may function both as the electron donor and the dispersing medium. Such particles are of particular interest for catalysis, as the metal surface is readily accessible. Alcohols and ethers have been quite extensively used for this purpose. Metal nanoparticles have a tendency to agglomerate, and therefore, it is necessary to protect them using surfactants or polymers, such as cyclodextrin, PVP, PVA, citrate or quaternary ammonium salts. In another strategy, the metal salt is reduced in micelles. A wide variety of ultra-fine colloidal surfactant-micelle protected metal nanoparticles can be successfully synthesized in solution. The size distribution of the metal nanoparticles may be controlled, e.g., by size-selective precipitation, ultrafiltration and the like.

[0044] Such metal colloids can be prepared in an ink formulation. After being mixed with Se (or S) fine powders, the ink can be coated on substrate and then subject to heat treatment to drive a reaction of the type:



[0045] By way of example, IB may be Cu, IIIA may be In and/or Ga, and VIA may be Se or S. The reaction between metal or metal alloy nanoparticles and Se (or S) powder forms CIGS (or CIS) film. The ink may include a homogeneous mixture of metallic particles and powders of group VIA materials. The individual metallic particles are generally uniformly distributed throughout a matrix of, e.g., Se or S powder. Sub-micron-sized metallic particles may be formed by methods involving mechanical comminution, e.g., milling, grinding, crushing and the desired size distribution obtained, e.g., by ultrafiltration or size-selective precipitation. In addition, nanometer-scale particles may be prepared by a gas condensation method. For example, in the gas condensation method, a metal may be heated to a vapor. The vapor then collects and condenses into particles. Such a technique may produce particles that are nominally spherical, approximately 30-40 nm in diameter and having a very tight size distribution

(e.g., ± 5 nm to ± 10 nm). See also “Ultrafine Metal Particles”, C. G. Granqvist and R. A. Buhrman, J., Appl. Phys., 47, 2200, (1976).

[0046] In another embodiment, the metal particles may be prepared by exploding fine metal wires with a surge of electrical current. For example, metal wires 7.5-25 microns in diameter may be exploded in a liquid such as water or alcohol by applying an increasing DC voltage across the wire until it explodes, e.g., at a few tens of volts. The resulting particles remain suspended in the liquid. Copper wires exploded in this fashion can produce particles about 30 to 70 nm in diameter.

[0047] The metal nanoparticles and group VIA powder may be mixed together with an optional binder to form a green microstructure. The binder serves to hold the metallic particles together, provides lubrication while the particles are mixed, and then or vaporizes completely during the sintering process leaving no trace of the binder in the final metallic product. Preferably, the binder combusts or vaporizes completely during the sintering process leaving no trace of the binder in the final CI(G)S active layer. Binders useful in conjunction with such embodiments of the invention include, but are not limited to, wax- or oil-based binders such as Acrawax® C® (Glyco), Advawax® 240, 275, 280, 290 (Carstab), Eramid® (Hexcel), Glucolube® VL (Glyco), Hostalub® FA 1 (Amer. Hoechst), HSTA 1, 3 (Hexcel), Interstab® G-8257, Kantstik® S powder (Specialty Prod.), Kemamide® W-20, W-40, E (Humko Chem.), Nopcowax® 22DS (Synthetic Prod.), Paricin®285, 220 (NL Industries), Ross Wax® 140 (Frank B. Ross), and Slip-Eze®, Slip-Quick®, Vyn-Eze® (Hexcel) and the like; lower alkanols (C_1 - C_6 alkanols, preferably C_1 - C_4 alkanols) such as ethanol, isopropanol, and the like; or traditional dispersant/binder systems used in ceramic processing, such as polymethacrylate/polyvinyl alcohol/polyethylene glycol systems. In some embodiments, the metal particles may be formed into a paste mixture comprising the elemental metal particles along with a resin, solvent, wetting agent, and flow control agent.

[0048] In addition, pastes can be made by combining elemental metals or other metallic particles with a polymer. Furthermore, a nanopowder of metal particles may be added to polymer matrix materials. Examples of suitable polymer matrix materials include poly(methyl methacrylate) (PMMA), poly(vinyl alcohol) (PVA), polycarbonates, polyalkenes, and polyaryls. In addition dispersants, binders, detergents, modifiers, or additives may be included along with the matrix material. Examples of modifiers or additives include plastisols, thickeners, or thinners to change the viscosity or change or improve the smoothness of the ink film surface. For example, “Viscosity Buster 10025VB” from Wilflex, at about a 1% concentration typically stabilizes and can improve the flow properties of ink. Additional modifiers or additives include, e.g., acids or bases to change pH of the ink or additives that lower the flash temperature of the ink and retarders or reducers to change the drying time of the ink. Potential sources of such modifiers and additives include Wilflex, Rutland Inks of Pineville, N.C., Chemical Consultants, Inc. of Corona, Calif., Union Inks of Singapore.

[0049] In the event that the nanoparticles are subject to oxide formation on the surface of the particles, for example, copper particles having a coating of copper oxide, the molding composition may additionally comprise a fluxing agent. The fluxing agent serves to substantially halt formation of the oxide layer, thereby enhancing the ability of the molding composition to form the green microstructure and aiding in

the final sintering process. Examples of common fluxing agents in general use include abietic acid, stearic acid, hydrochloric acid, amine hydrochlorides and amine resins. Either a suitable commercial flux formulation or a specially formulated fluxing agent may be utilized. Further, to minimize or eliminate oxide formation on the surface of the nanoparticles, the nanoparticles can be formed in an atmosphere that lacks oxygen, e.g. a nitrogen-filled glovebox.

4. Liquid Metal Based Inks

[0050] In another embodiment, the liquid ink may be made using one or more liquid metals. For example, an ink may be made starting with a molten mixture of Gallium and/or Indium (commercially available, e.g., from Alfa Aesar of Ward Hill, Mass.). Copper nanoparticles may then be added to the mixture, which may then be used as the ink/paste. Copper nanoparticles are available commercially, e.g., from Materials Modification Inc., of Fairfax, Va. Alternatively, the temperature of the Cu—Ga—In mixture may be adjusted (e.g. cooled) until a solid forms. The solid may be ground at that temperature until small nanoparticles (e.g., less than 5 nm) are present. Selenium may be added to the ink and/or a film formed from the ink by exposure to selenium vapor, e.g., before, during, or after annealing.

5. Organometallic Liquid Inks

[0051] In yet another embodiment, the liquid ink may be made using one or more organometallic precursors of IB, IIIA and VIA elements. For instance, examples of copper precursors include Copper II hexafluoropentanedionate (Gelest SKU#AKC253); Copper II methoxide (Gelest SKU#AKC254); Copper II ethoxide (Gelest SKU#AKC250); and Copper II ethylacetoacetate (Gelest SKU#AKC252), all of which are available from Gelest, Inc. of Morrisville, Pa. Examples of indium precursors include Indium 2,4-Pentanedionate (Gelest SKU#AKJ370), also called indium acetylacetonate; Indium Methoxyethoxide (Gelest SKU#AKJ365); and Indium methyl(trimethyl)acetylacacetate (Gelest SKU#AKJ373), also all available from Gelest. Examples of Gallium precursors: Gallium III 2,4-Pentanedionate (Gelest SKU#AKG310); and Gallium III Ethoxide (Gelest SKU#AKG320), also available from Gelest.

[0052] The precursors may be mixed as liquids to form the ink. The organic components may be burned out of the ink by heating at about 500° C., e.g., after a film of the ink is disposed on a substrate. Alternatively, a sol-gel may be formed from organometallics of e.g., Cu, In, and/or Ga. In general, the sol-gel processing involves the transition of a system from a liquid “sol” (mostly colloidal) into a solid “gel” phase. The starting materials used in the preparation of the “sol” are usually inorganic metal salts or metal organic compounds such as metal alkoxides along with water, alcohol and, optionally, a small amount of acid. For example, the ink may be fabricated by making a pseudo sol out of mixed metal organic precursors, such as alkoxides or diketones of Copper, indium, gallium in the desired stoichiometric ratio. By way of example, copper(II) ethoxide or Copper(II) ethylacetoacetate may be mixed with gallium (III) ethoxide or gallium (III) pentanedionate and with indium (III) methoxyethoxide or indium(III) 2,4 pentanedionate. A sol may be formed by adding water, an alcohol and, optionally, an acid, to the mixed metal organic precursors. The sol may be coated in

a dish (e.g. drop cast), annealed to remove labile groups, and allow drying to form a powder. Note that this process can be scaled to bulk in high volume. The metallic powder can then be milled and mixed with dispersant and then coated, and the resultant film can then be reduced by treatment with H_2 and/or N_2 at $400^\circ C.$, after which 10-50 mbar Se vapor can be introduced to selenize the film. Alternatively, the powder compounds can be first reduced to metals through exposure to H_2 gas, then mechanically milled and/or ground up mixed with dispersant and then coated.

6. Metal Halides Dissolved in Chelating Agents

[0053] In yet another embodiment, a metal halide (MCl or MI, where M is a metal) could be dissolved in any of a number of chelating agents, then (optionally) mixed in water to keep the metals in solution. The solution mixture can then serve as a basis for a precursor paste or ink. Suitable metal halides include chlorides and iodides of the group IB, IIIA and VIA metals. Suitable chelating agents include, but are not limited to, e.g. amines, diamines such as ethylene diamine, polyamines, polyethylene glycol, low molecular weight alcohols, ketones, diketones, carboxylic acids, and mixtures thereof.

7. Metal Salts

[0054] Metal salts and other metal compounds can also be used as reagents to synthesize metal nanoparticles. Provided that they exhibit proper reactivity, suitable metal salts and other metal compounds include but are not limited to metal halogenides, metal nitrates, metal nitrites, metal nitrides, metal sulfates, metal sulfites, metal sulfides, metal alcoholates, metal phosphates, metal phenolates, metal carbonates, metal carboxylates, and blends or mixtures of these salts. For example, for each element or non-oxide compound from the group IB, IIIA and VIA metals, metal salts can be synthesized or purchased (e.g., through Sigma-Aldrich of St. Louis, Mo.), formed or purified as nanoparticulates, then each of the nanoparticulates can be intermixed in the proper ration to serve as the basis for an ink for effective CIGS absorber layer function.

Photovoltaic Devices

[0055] The nanoparticles are generally mixed with an organic or inorganic solvent to form the ink. In some embodiments of the invention, the nanoparticles may be mixed with water to form an aqueous suspension that serves as the basis of the ink. Schulz, by contrast teaches non-aqueous colloidal suspensions and stresses that every effort should be made to avoid introducing even incidental amounts of water into his colloidal suspensions in order to avoid agglomeration of particles. In fact, aqueous suspensions have several advantages over non-aqueous suspensions during ink formation and deposition. First, water is an inexpensive solvent, and it is much easier to scale to high-volume production processes. In contrast, organic solvents are inherently more expensive and hazardous than water, and waste solvents and other organic byproducts incur costs resulting from waste processing. Second, a wide variety of water-compatible dispersants can easily be added to an aqueous suspension of nanoparticles, which are stabilized by the dispersant, which keeps the nanoparticles separated from each other until the annealing step melts them together. In contrast, if such water-compatible dispersants were added to an organic (non-aqueous) solution, such a

mixture may form two phases as a result of organic-inorganic partitioning in the solution. In this case, nanoparticles that were initially stabilized by capping agents may subsequently collapse and form aggregates, leading to non-uniform coatings. Examples of suitable dispersants include Tamol™ and Duramax™ from Rohm and Haas of Philadelphia, Pa. Further information on Tamol™ may be found at <http://www.rohm-haas.com/coatings/dispersants.html>. Further information about Duramax™ may be found at http://www.rhcis.com/markets_and_products/electronic.html.

[0056] Note that, as used herein, the term “aqueous suspension” refers to the ink at the end of its manufacture. The use of the term “aqueous” does not exclude the possibility that during manufacture, the particles may be dispersed in an organic solvent or some solvent other than water. For example, if the particles are capped with organic ligands and in some of the particle formation chemistries, the particles may be initially made in alcohol or another organic solvent then later precipitated or isolated for resuspension in water to form the ink. Furthermore, in some embodiments of the present invention, the particles may be so small that they form liquids, e.g., the particles may be as small as individual atoms or molecules. The liquid ink (aqueous or otherwise) may be spread in a thin film over a substrate using solution based coating techniques such as web coating, spray coating, spin coating, doctor blade coating, printing techniques including contact printing, gravure printing, microgravure printing, ink-jet printing, jet deposition, and the like. Such a film can be deposited on a flexible substrate, in a roll-to-roll manner using a commercially available web coating system. The film may then be heated to remove the solvent and to sinter the nanoparticles together to form a layer of a IB-III A-VIA alloy. The alloy may have the general formula $CuIn_{1-x}Ga_x(S, Se)_2$, where x is between 0 and 1. The reduced temperature sintering (e.g., from about $200^\circ C.$ to about $600^\circ C.$) made possible by the small particle size and narrow size distribution facilitates forming CIGS films in a high volume roll-to-roll production environment on thin flexible substrates such as metal foils or metallized plastic films. To heat and sinter the film, if deposited on a flexible substrate, the film can be wound into a coil and the coil can be heated such that the entire roll is heated at the same time, substantially increasing the scalability of the heating process through such a high-volume batch process. Examples of processing a coiled substrate are described e.g., in US patent application titled “HIGH THROUGHPUT SURFACE TREATMENT ON COILED FLEXIBLE SUBSTRATES” (Attorney Docket No. NSL-025), which has been incorporated by reference.

[0057] Some high-volume batch processes for coating the substrate with the ink, e.g., chemical bath deposition (CBD) for liquid-based deposition, and atomic layer deposition (ALD) for gas- and vapor-based deposition, could potentially coat both sides of a coiled substrate at one time. However, it may be desirable to primarily coat only one side, since double-sided coating can result in waste of valuable components of the ink, e.g., indium. To avoid such waste, two substrates may be attached together “back-to-back” to form a dual substrate having, in effect, two front sides. The dual substrate may then be wound into a coil and coated such that both front surfaces get coated while the back surfaces do not. Preferably, the substrates are attached in a manner that allows them to be separated from each other after processing. By way of example the substrates may be attached with a low-strength adhesive or electrostatic film applied to the back side

of one or both substrates. Alternatively, an edge where the two substrates join may be sealed, e.g., with a tape, so that reactants cannot reach the back sides during processing. Processing the substrate in this fashion wastes less of the ink and may increase the area of the substrate that can be coated at one time. The IB-III A-VIA alloy layer can be used in the active layer of photovoltaic cell, e.g., of the type shown in FIG. 2. The solar cell **200** generally includes a substrate or base layer **202**, a base electrode **204**, a IB-III A-VIA layer **206**, a window layer **208**, and a transparent electrode **210**. The base layer **202** may be made from a thin flexible material suitable for roll-to-roll processing. By way of example, the base layer may be made of a metal foil, such as titanium, a polymer such as polyimide or a metallized plastic. The base electrode **204** is made of an electrically conductive material. By way of example, the base electrode **204** may be a layer of stainless steel or molybdenum, e.g., about 0.5 micron to about 1 micron thick. By way of example, and without limitation, the IB-III A-VIA layer **206** may include material of the general formula $\text{CuIn}_{1-x}\text{Ga}(\text{S or Se})_2$. The IB-III A-VIA layer **206** may be fabricated by depositing a film of a nanoparticle-based ink, paste or slurry, e.g., roughly 4 to 5 microns thick when wet on the base electrode **204**. The film may be annealed by heating to a temperature sufficient to burn off any binders or cap layers on the particles and sinter the particles together. The IB-III A-VIA **206** layer may be about 1 micron to about 2 microns thick after annealing. By using nanoparticles of the average size and size distribution described above, the ink, paste or slurry may be annealed at a temperature compatible with the underlying substrate **202** and electrode **204**. An optional adhesion layer **203** may facilitate bonding of the electrode **204** to the substrate **202**. After annealing, the film may optionally be exposed to selenium vapor at about 300-500° C. for about 30-45 minutes to ensure the proper stoichiometry of Se in the film. To carry out such a Se vapor exposure, the film, if deposited on a flexible substrate, can be wound into a coil and the coil can be coated so that the entire roll is exposed at the same time, substantially increasing the scalability of the Se vapor exposure process through such a high-volume batch process, e.g., as described above. The window layer **208** is typically used to smooth out the “slope” between the bandgaps of the different materials making up the IB-III A-VIA layer **206**. By way of example, the bandgap adjustment layer may include cadmium sulfide (CdS), zinc sulfide (ZnS), or zinc selenide (ZnSe) or some combination of two or more of these. Layers of these materials may be deposited, e.g., by chemical bath deposition, to a thickness of about 50 nm to about 100 nm.

[0058] The transparent electrode **210** may include a transparent conductive oxide layer **209**, e.g., zinc oxide (ZnO) or aluminum doped zinc oxide (ZnO:Al), which can be deposited using any of a variety of means including but not limited to sputtering, evaporation, CBD, electroplating, CVD, PVD, ALD, and the like. If the substrate is flexible and the deposition technique is ALD or CBD or the like, a coiled/wound flexible substrate can be exposed so that the entire roll is processed at one time, e.g., as described above. The transparent electrode **210** may further include a layer of metal (e.g., Ni, Al or Ag) fingers **211** to reduce the overall sheet resistance.

[0059] An optional encapsulant layer (not shown) provides environmental resistance, e.g., protection against exposure to water or air. The encapsulant may also absorb UV-light to protect the underlying layers. Examples of suitable encapsu-

lant materials include one or more layers of polymers, such as polyethylene terephthalate (PET), ethylene vinyl acetate (EVA), and/or Mylar®. Mylar is a registered trademark of E. I. du Pont de Nemours and Company of Wilmington, Del. Inorganic materials, such as glass and plastic foils, metalized plastic foils, and metal foils may also be used for the encapsulant layer. The encapsulant layer may also include nitrides, oxides, oxynitrides or other inorganic materials. Alternatively, the encapsulants may include Tefzel® (DuPont), tefdel, thermoplastics, polyimides, polyamides, nanolaminate composites of plastics and glasses (e.g. barrier films), and combinations of the above. For example, a thin layer of (expensive) EVA/polyimide laminated to thick layer of (much less expensive) PET.

[0060] Embodiments of the present invention provide for low-cost, high-volume production of large area photovoltaic devices without having to undergo selenization with hazardous H_2Se or reduction of oxides in H_2 . Furthermore, embodiments of the present invention are compatible with roll-to-roll manufacturing of photovoltaic cells and modules that can be readily scaled up to high production volumes.

[0061] While the above is a complete description of the preferred embodiment of the present invention, it is possible to use various alternatives, modifications and equivalents. Therefore, the scope of the present invention should be determined not with reference to the above description but should, instead, be determined with reference to the appended claims, along with their full scope of equivalents. The appended claims are not to be interpreted as including means-plus-function limitations, unless such a limitation is explicitly recited in a given claim using the phrase “means for.”

What is claimed is:

1. A method for fabricating a liquid containing intermixed elements of groups IB and IIIA, and optionally VIA, comprising the steps of:

forming nanoparticles containing elements from group IB; and

forming nanoparticles containing elements from group IIIA; and optionally forming non-oxide nanoparticles containing elements from group VIA;

combining the nanoparticles with a liquid to form an ink; wherein the nanoparticles for the ink may be prepared from a mixture of metal nanoparticles and a vapor or powder containing either Se or S.

2. The method of claim 1 wherein forming non-oxide quantum nanoparticles includes preparing metal nanoparticles containing elements of groups IB, IIIA, VIA or a IB-III A-VIA alloy, by laser ablation, nucleation from vapor, exploding wires by electrical current surge, thermal decomposition of organometallic compounds, sonolysis, pulse radiolysis, electrochemical reduction or chemical reduction.

3. The method of claim 1 wherein the ink is formed by mixture with water.

4. The method of claim 1 wherein the ink is formed by mixture with organic solvent.

5. The method of claim 1, further comprising adding a capping agent to the non-oxide nanoparticles.

6. The method of claim 1, further comprising adding a binder to the non-oxide quantum nanoparticles.

7. The method of claim 1, further comprising adding a fluxing agent to the non-oxide quantum nanoparticles.

8. The method of claim **1**, further comprising adding one or more surfactants, polymers, dispersants, binders, modifiers, detergents or additives to the non-oxide quantum nanoparticles.

9. The method of claim **1** wherein the group IB element is copper (Cu), the group IIIA element is indium and optionally includes gallium) and the group VIA element is selenium (Se) or sulfur (S) and a stoichiometric ratio of the Cu, In and Se or S in the liquid is approximately $\text{CuIn}_{1-x}\text{Ga}_x(\text{S or Se})_2$, where x is between 0 and 1.

10. The method of claim **9** wherein a majority of the group IB nanoparticles range in size from no more than about 40% above or below an average nanoparticle size, or, if the average nanoparticle size is less than about 5 nanometers, from no more than about 2 nanometers above or below the average nanoparticle size.

11. The method of claim **9**, further comprising adjusting the temperature of the Cu—In—Ga mixture until a solid forms and then grinding the solid to form nanoparticles.

12. The method of claim **1** further comprising the step of capping the nanoparticles with an organic material.

13. The method of claim **12** wherein the organic material is a small molecule with low boiling point.

14. The method of claim **13** wherein the organic material is selected from the group of trioctylphosphine oxide, trioctylphosphine, triphenylphosphine, pyridine, alcohols (methanol, ethanol, propanol, butanol), ethane thiol, tetrahydrofuran, ethers, ammonia, amines (methyl amine, ethylamine, ethylenediamine) and acetonitrile.

15. The method of claims **14** wherein the organic material is pyridine.

16. The method of claim **1** wherein forming a mixture of non-oxide nanoparticles includes selecting particles in the desired particle size range.

17. The method of claim **16**, wherein selecting nanoparticles in the desired size range includes adjusting one or more parameters of a reaction that forms the nanoparticles, size-selective precipitation, or ultrafiltration.

18. The method of claims **1** further comprising adding a water-compatible dispersant to the liquid.

19. The method of claims **1** wherein forming the non-oxide nanoparticles includes preparing particles in a non-oxygen atmosphere.

20. The method of claim **1** wherein the size distributions of the CuInS_2 or $\text{CuIn}(\text{Se})_2$ nanoparticulates may be adjusted by size-selective precipitation, ultrafiltration and the like.

21. A photovoltaic device precursor material comprising:
a liquid ink comprising:

non-oxide metal nanoparticles containing elements from group IB, non-oxide metal nanoparticles from group IIIA; and adding one or more liquid metals containing one or more elements of group IIIA, wherein forming a mixture of non-oxide quantum nanoparticles includes reacting a single-source precursor to form particles of IB-IIIA-VIA material;
a dispersant; and
a solvent.

* * * * *