


US 20080318132A1

(19) **United States**(12) **Patent Application Publication**
Visco et al.(10) **Pub. No.: US 2008/0318132 A1**(43) **Pub. Date: Dec. 25, 2008**(54) **COMPOSITIONS AND METHODS FOR
PROTECTION OF ACTIVE METAL ANODES
AND POLYMER ELECTROLYTES**(75) Inventors: **Steven J. Visco**, Berkeley, CA
(US); **Yevgeniy S. Nimon**, Danville,
CA (US); **Bruce D. Katz**, Berkeley,
CA (US)Correspondence Address:
BEYER WEAVER LLP
P.O. BOX 70250
OAKLAND, CA 94612-0250 (US)(73) Assignee: **PolyPlus Battery Company**,
Berkeley, CA (US)(21) Appl. No.: **12/201,264**(22) Filed: **Aug. 29, 2008****Related U.S. Application Data**(63) Continuation of application No. 10/686,041, filed on
Oct. 14, 2003, now Pat. No. 7,432,017.(60) Provisional application No. 60/418,899, filed on Oct.
15, 2002.**Publication Classification**(51) **Int. Cl.**
H01M 4/58 (2006.01)
H01M 4/02 (2006.01)
B05D 5/12 (2006.01)(52) **U.S. Cl. 429/231.95; 429/209; 427/77**(57) **ABSTRACT**

Electrochemical structures with a protective interlayer for prevention of deleterious reactions between an active metal electrode and polymer electrolytes, and methods for their fabrication. The structures may be incorporated in battery cells. The interlayer is capable of protecting an active metal anode and a polymer electrolyte from deleterious reaction with one another while providing a high level of ionic conductivity to enhance performance of a battery cell in which the structure is incorporated. The interlayer has a high ionic conductivity, at least 10^{-7} S/cm, generally at least 10^{-6} S/cm, and as high as 10^{-3} S/cm or higher. The interlayer may be composed, in whole or in part, of active metal nitrides, active metal phosphides or active metal halides. These materials may be applied preformed, or they may be formed in situ by conversion of applied precursors on contact with the active metal anode material.






FIG. 1




FIG. 7




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6

COMPOSITIONS AND METHODS FOR PROTECTION OF ACTIVE METAL ANODES AND POLYMER ELECTROLYTES

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a continuation of U.S. patent application Ser. No. 10/686,041, filed on Oct. 14, 2003 entitled "Compositions And Methods For Protection Of Active Metal Anodes And Polymer Electrolytes", now pending, which in turn claims priority to U.S. Provisional Patent Application No. 60/418,899 filed Oct. 15, 2002, entitled "Ionically Conductive Composites For Protection Of Anodes And Electrolytes". These applications are incorporated herein by reference in their entirety for all purposes.

BACKGROUND OF THE INVENTION

[0002] 1. Field of the Invention

[0003] The present invention relates generally to electrode structures for use in electrochemical devices. More particularly, this invention relates to interlayers for protection of anodes and polymer electrolytes in electrochemical structures from deleterious reaction with one another, and methods for their fabrication.

[0004] 2. Description of Related Art

[0005] Lithium is an attractive material for use as an electrode component in electrochemical devices, such as batteries and capacitors, due to its very high energy density and low equivalent weight. However, lithium is highly reactive in ambient atmosphere and with a variety of other electrochemical device components, in particular polymer electrolytes, and thus its incorporation into electrochemical devices requires special processing. Typically, lithium battery manufacture is conducted in inert environments in order to guard against degradation of lithium until it is hermetically sealed within a battery cell container.

[0006] Even with these precautions, lithium may detrimentally react with incompatible materials in the processing environment. To address these problems, some researchers have proposed that the electrolyte facing side of the lithium negative electrode be coated with a "protective layer." Several types of protective layers and methods for producing them have been proposed. Prior methods have generally focused on the application of a protective layer to a preformed lithium electrode.

[0007] Some research has focused on "nitridation" of the lithium metal surface as a means for protecting lithium electrodes. In such process, a bare lithium metal electrode surface is reacted with a nitrogen plasma to form a surface layer of polycrystalline lithium nitride (Li_3N). This nitride layer conducts lithium ions and at least partially protects the bulk lithium of the negative electrode from a liquid electrolyte. A process for nitriding lithium battery electrodes is described in R&D Magazine, September 1997, p. 65 (describing the work of S. A. Anders, M. Dickinson, and M. Rubin at Lawrence Berkeley National Laboratory). Unfortunately, the surface of lithium is very rough making it almost impossible to nitride, and lithium nitride decomposes when exposed to moisture. While lithium metal batteries employ nonaqueous electrolytes, it is very difficult to remove all traces of moisture from the electrolyte. Thus, trace moisture will ultimately compromise the protective properties of the lithium nitride.

[0008] Other pre-formed lithium protective layers have been contemplated. Most notably, U.S. Pat. No. 5,314,765 (issued to Bates on May 24, 1994) describes a lithium electrode containing a thin layer of sputtered lithium phosphorus oxynitride ("LiPON") or related material. LiPON is a single ion (lithium ion) conducting glass. It is typically deposited by reactive sputtering of a lithium phosphate in the presence of nitrogen. The nitrogen, however, attacks the lithium surface, thereby making the process of direct deposition of the glass film impossible. Work in the present applicants' laboratories has developed technology for the use of glassy or amorphous protective layers, such as LiPON, in active metal battery electrodes (see, for example, U.S. Pat. Nos. 6,025,094, issued Feb. 15, 2000, 6,402,795, issued Jun. 11, 2002, 6,214,061, issued Apr. 10, 2001 and 6,413,284, issued Jul. 2, 2002, issued to Chu and Visco, et al. and assigned to PolyPlus Battery Company).

[0009] Some contemplated lithium metal protective layers are formed in situ by reaction between lithium metal and compounds in the cell's electrolyte which contact the lithium. Most of these in situ films are grown by a controlled chemical reaction after the battery is assembled. Generally, such films have a porous morphology allowing some electrolyte to penetrate to the bare lithium metal surface. Thus, they fail to adequately protect the lithium electrode. Other examples of potential protective layers may include the deposition of polymer layers that involve solvents or monomers that are incompatible with lithium.

[0010] The existing approaches do not provide for the fabrication of a lithium electrode and polymer electrolyte laminate without a barrier layer that substantially impedes ion conductivity.

[0011] Accordingly, it would be desirable to provide a protective layer having high ionic conductivity between a lithium electrode and a polymer electrolyte. In particular fabrication processing and successful operation of active metals, such as lithium, as battery electrodes would be enhanced by the provision of such a protective layer.

SUMMARY OF THE INVENTION

[0012] The present invention provides electrochemical structures with a protective interlayer for prevention of deleterious reactions between an active metal electrode and polymer electrolytes, and methods for their fabrication. The structures may be incorporated in battery cells. The interlayer is capable of protecting an active metal anode and a polymer electrolyte from deleterious reaction with one another while providing a high level of ionic conductivity to enhance performance of a battery cell in which the structure is incorporated. The interlayer has a high ionic conductivity, at least 10^{-7} S/cm, generally at least 10^{-6} S/cm, and as high as 10^{-3} S/cm or higher.

[0013] A wide variety of materials may be used in fabricating protective interlayers in accordance with the present invention, consistent with the principles described above. For example, the interlayer may be composed, in whole or in part, of active metal nitrides, active metal phosphides or active metal halides. Specific examples include Li_3N , Li_3P , LiI , LiBr , LiCl and LiF . These materials may be applied pre-formed, or they may be formed in situ by conversion of applied precursors such as metal nitrides, metal phosphides, metal halides, red phosphorus, iodine, nitrogen or phosphorus containing organics and polymers, and the like, on contact with the active metal anode material. The in situ formation of

the first layer may result from an incomplete conversion of the precursors to their lithiated analog. Nevertheless, such incomplete conversions meet the requirements of a first layer material for a protective interlayer in accordance with the present invention and are therefore within the scope of the invention.

[0014] The interlayer may be formed using a variety of techniques. These include deposition or evaporation (including e-beam evaporation) of a layer of a protective interlayer or protective interlayer precursor material. Also, as noted above, the active metal electrode adjacent layer may be formed in situ from the non-deleterious reaction of one or more precursors with the active metal electrode. For example, a CuN_3 layer may be formed on a polymer electrolyte. The precursor coated polymer electrolyte may then be contacted with a Li anode (e.g., lithium may be directly evaporated onto the precursor-coated polymer electrolyte) resulting in the formation of LiN_3 at the Li anode surface. As another example, an LiP_3 interlayer may be formed by contacting a layer of red phosphorus on formed a polymer electrolyte with an Li anode.

[0015] The invention encompasses protected anode structures composed of anodes, interlayers and polymer electrolytes. Battery cells and methods for making anode structures and battery cells are also provided.

[0016] In one aspect, the invention relates to an electrochemical device component structure. The structure includes an active metal electrode, a polymer electrolyte, and a protective interlayer between the electrode and the polymer electrolyte, the interlayer composed in whole or in part of a material conductive to ions of the active metal and chemically compatible with the active metal and the polymer electrolyte including nitrides, phosphides and halides of the active metal.

[0017] These and other features of the invention will be further described and exemplified in the detailed description below.

BRIEF DESCRIPTION OF THE DRAWINGS

[0018] FIG. 1 is a schematic illustration of an Electrochemical device structure incorporating an ionically conductive and chemically compatible protective interlayer in accordance with the present invention.

[0019] FIG. 2-6 are schematic illustrations of alternative methods of making an electrochemical device structure incorporating an ionically conductive and chemically compatible protective interlayer in accordance with the present invention.

[0020] FIG. 7 is a schematic illustration of an active metal battery cell incorporating a protective interlayer in accordance with the present invention.

DETAILED DESCRIPTION OF SPECIFIC EMBODIMENTS

[0021] Reference will now be made in detail to specific embodiments of the invention. Examples of the specific embodiments are illustrated in the accompanying drawings. While the invention will be described in conjunction with these specific embodiments, it will be understood that it is not intended to limit the invention to such specific embodiments. On the contrary, it is intended to cover alternatives, modifications, and equivalents as may be included within the spirit and scope of the invention as defined by the appended claims. In the following description, numerous specific details are set forth in order to provide a thorough understanding of the present invention. The present invention may be practiced

without some or all of these specific details. In other instances, well known process operations have not been described in detail in order not to unnecessarily obscure the present invention.

[0022] Introduction

[0023] The present invention provides electrochemical structures with a protective interlayer for prevention of deleterious reactions between an active metal electrode and polymer electrolytes, and methods for their fabrication. The structures may be incorporated in battery cells. The interlayer is capable of protecting an active metal anode and a polymer electrolyte from deleterious reaction with one another while providing a high level of ionic conductivity to enhance performance of a battery cell in which the structure is incorporated.

[0024] The interlayer is composed of a material that is both ionically conductive and chemically compatible with an active metal and a polymer electrolyte between which it is disposed. The interlayer has a high ionic conductivity, at least 10^{-7} S/cm, generally at least 10^{-6} S/cm, and as high as 10^{-3} S/cm or higher. By "chemical compatibility" (or "chemically compatible") it is meant that the referenced material does not react to form a product that is deleterious to battery cell operation when contacted with one or more other referenced battery cell components. Chemical compatibility in this aspect of the invention refers both to a material that is chemically stable and therefore substantially unreactive when contacted with an active metal electrode material. It also refers to a material that may be reactive when contacted with an active metal electrode material to produce a product that is chemically stable against the active metal electrode material and retains the desirable ionic conductivity. Such a reactive material is sometimes referred to as a "precursor" material.

[0025] It should be noted that the interlayer is inherently ionically conductive. That is, it does not depend on the presence of a liquid electrolyte or solvent or other agent for its ionically conductive properties.

[0026] Protective Interlayer Structures

[0027] FIG. 1 illustrates an electrochemical structure incorporating an ionically conductive chemically compatible protective interlayer in accordance with the present invention. The structure **100** includes an active metal electrode **102**. Active metals are highly reactive in ambient conditions and can benefit from a barrier layer when used as electrodes. They are generally alkali metals such (e.g., lithium, sodium or potassium), alkaline earth metals (e.g., calcium or magnesium), and/or certain transitional metals (e.g., zinc) and/or alloys of two or more of these. The following active metals may be used: alkali metals (e.g., Li, Na, K), alkaline earth metals (e.g., Ca, Mg, Ba), or binary or ternary alkali metal alloys with Ag, Ca, Mg, Sn, Zn, Bi, Al, Cd, Ga, In. Preferred alloys include lithium aluminum alloys, lithium silicon alloys, lithium tin alloys, lithium silver alloys, and sodium lead alloys (e.g., Na_4Pb). A preferred active metal electrode is composed of lithium.

[0028] The electrode is typically bonded on one surface with a current collector **110** composed of a conductive metal, for example copper. However, the structure need not included a current collector **110** and/or the current collector may be bonded to the exposed surface of the electrode subsequently, for example during processing to form a battery cell.

[0029] The structure **100** also includes a polymer electrolyte **104**. In general, any polymer electrolyte suitable for use in an active metal battery cell may be used. For example,

polymer electrolytes such as polyethylene oxide (PEO), polypropylene oxide (PPO), polyimide, and Nafion based membranes such as Li-ion based Nafions and fiber reinforced polymer electrolytes such as fiber reinforced PEO and fiber reinforced Nafion (i.e., GORE-SELECT, available from W.L. Gore and Associates) may be used in accordance with the present invention.

[0030] A protective interlayer **106** is disposed between the active metal electrode **102** and the polymer electrolyte **104**. The protective interlayer **106** is composed of a material that is both ionically conductive and chemically compatible with an active metal electrode material and a polymer electrolyte. The thickness of the interlayer is enough to prevent contact between the active metal anode and the polymer electrolyte, preferably about 0.1 to 5 microns, or 0.2 to 1 micron, for example about 0.25 micron.

[0031] A wide variety of materials may be used as protective interlayers in accordance with the present invention, consistent with the principles described herein. For example, the interlayer may be composed, in whole or in part, of active metal nitrides, active metal phosphides or active metal halides. Specific examples include Li_3N , Li_3P , LiI , LiBr , LiCl and LiF .

[0032] As described further below, these materials may be applied preformed, or they may be formed in situ by conversion of applied precursors such as metal nitrides, metal phosphides, metal halides, red phosphorus, iodine, nitrogen or phosphorus containing organics and polymers, and the like, on contact with the active metal anode material. The in situ formation of the interlayer may result from an incomplete conversion of the precursors to their lithiated analog. Nevertheless, such incomplete conversions meet the requirements of an interlayer material for a protective interlayer in accordance with the present invention and are therefore within the scope of the invention.

[0033] Fabrication Methods

[0034] As noted above, a protective interlayer in accordance with the present invention may be formed using a variety of methods. These include deposition or evaporation (including e-beam evaporation) of a layer of a protective interlayer or protective interlayer precursor material. Also, as noted above, the interlayer may be formed in situ from the non-deleterious reaction of one or more precursors with the active metal electrode.

[0035] Referring to FIG. 2, a first method for forming a protective interlayer in accordance with the present invention is shown. The ionically conductive chemically compatible interlayer material is directly deposited onto the polymer electrolyte. This can be done by a variety of techniques including RF sputtering, e-beam evaporation, thermal evaporation, or reactive thermal or e-beam evaporation, for example. In the particular example illustrated in the figure, lithium is evaporated into a nitrogen plasma to form a lithium nitride (Li_3N) layer on the polymer electrolyte, for example one composed of PEO, surface. This is followed by evaporation of lithium metal onto the Li_3N film. The Li_3N interlayer separates the lithium metal electrode from the polymer electrolyte, but allows Li ions to pass from the Li electrode to the polymer electrolyte. Of course, other active metal, polymer electrolyte and interlayer materials, as described herein, may be used as well.

[0036] Alternatively, referring to FIG. 3, a second method for forming a protective interlayer in accordance with the present invention is shown. The ionically conductive chemi-

cally compatible interlayer material is formed in situ following formation of a precursor layer on the polymer electrolyte. In the particular example illustrated in the figure, a surface of a polymer electrolyte, for example one composed of PEO, is coated with red phosphorus, a precursor for an active metal (in this case lithium) phosphide. Then a layer of lithium metal is deposited onto the phosphorus. The reaction of lithium and phosphorus forms Li_3P according to the following reaction: $3\text{Li} + \text{P} = \text{Li}_3\text{P}$. Li_3P is an ionically conductive material that is chemically compatible with both the lithium anode and the polymer electrolyte. In this way, the polymer electrolyte is not in direct contact with the lithium electrode. Of course, other active metal, polymer electrolyte and interlayer precursor materials, as described herein, may be used as well. Alternative precursor examples include CuN_3 , which may be formed as a thin layer on a polymer electrolyte, such as PEO and contacted with a Li anode in a similar manner according to the following reaction: $3\text{Li} + \text{Cu}_3\text{N} = \text{Li}_3\text{N} + 3\text{Cu}$; or lead iodide which may be formed as a thin layer on a polymer electrolyte and contacted with a Li anode in a similar manner according to the following reaction: $2\text{Li} + \text{PbI}_2 = 2\text{LiI} + \text{Pb}$.

[0037] In either of the forgoing methods, rather than forming a lithium (or other active metal) layer on the protective interlayer material or precursor, the protective interlayer material or precursor material may be contacted with the lithium by bonding metallic lithium to the protective interlayer material or precursor, for example by direct contact with extruded lithium metal foil. This alternative is illustrated for either of the FIG. 2 or FIG. 3 methods in FIG. 4.

[0038] In an alternative embodiment of the invention the interlayer layer may also include additional components. For instance, a suitable protective interlayer may include a polymer component to enhance its properties. For example, polymer-iodine complexes like poly(2-vinylpyridine)-iodine (P2VP-I_2), polyethylene-iodine, or tetraalkylammonium-iodine can react with Li to form an ionically conductive LiI -based film that is chemically compatible with both an active metal and a polymer electrolyte. Without intending to be bound by theory, it is expected that the use of polymer-iodine charge transfer complexes can lead to formation of composites containing LiI and polymer and having significantly higher ionic conductivity than that for pure LiI . Other halogens may also be used in this manner, for example in bromine complexes.

[0039] Referring to FIG. 5, a first embodiment of this aspect of the present invention is shown. A polymer layer and a layer of iodine are coated on a polymer electrolyte surface and allowed to react forming polymer-iodine complex.

[0040] According to this method, a thin layer of polymer may be applied to the polymer electrolyte (e.g. PEO) using brushing, dipping, or spraying. For example, a conductive glass layer may be coated with a thin (e.g. 0.5 to 2.0 micron, preferably 0.1 to 0.5 micron) layer of P2VP in this way.

[0041] One technique for applying an iodine coating is sublimation of crystalline iodine that can be achieved at room temperature (e.g., about 20 to 25° C.) in a reactor placed in the dry box or in a dry room. A sublimed layer of iodine can be made very thin (e.g., 0.05 to 1.0 microns and the rate of sublimation can be adjusted by varying the temperature or distance between the substrate and source of iodine.

[0042] Alternatively, high concentrations (e.g., 50 to 100 g/liter of iodine can be dissolved in an organic solvent, such as acetonitrile and n-heptane. Dissolved iodine can be coated on the conductive glass surface by such methods as dip coating,

spraying or brushing, among others. In this case, treatment conditions can be easily changed by varying the length of coating treatment and iodine concentrations. Examples of iodine sources for this technique include metal iodides are AgI and PbI_2 , which are known to be used as the cathode materials in solid-state batteries with Li anode and LiI-based solid electrolyte.

[0043] Then, lithium (or other active metal) is contacted with the polymer-iodine complex on the polymer electrolyte, for example by evaporation or pressing onto the electrolyte coated with this complex. The result is a LiI-containing composite protective interlayer between the Li anode and the polymer electrolyte.

[0044] Referring to FIG. 6, an alternative embodiment of this aspect of the present invention is shown. A polymer electrolyte surface is coated with a thin layer of iodine, such as by a technique described above, that can react with Li forming LiI layer (A).

[0045] Active metal, for example lithium foil, can be coated with a thin layer of polymer (B), for example as described above, and then contacted with the iodine layer on the polymer electrolyte. After assembly, iodine reacts with the polymer layer and, as a result, LiI-containing protective interlayer with reduced impedance is formed.

[0046] Battery Cells

[0047] Electrochemical structures incorporating a protective interlayer in accordance with the present invention may be incorporated in active metal-based battery cells such as are described in Applicant's prior US Patents and patent applications including U.S. Pat. No. 6,025,094 incorporated herein by reference in its entirety and for all purposes. The protected anodes may be used in primary or secondary battery cells. One preferred implementation is in lithium-sulfur batteries.

[0048] FIG. 7 illustrates a battery in accordance with the present invention. The battery cell **700** includes an electrochemical structure incorporating an ionically conductive chemically compatible protective interlayer, as described with reference to FIG. 1. The cell **700** is composed of an active metal electrode **102** on an anode current collector **110**, a polymer electrolyte **104**, and a protective interlayer **106**, as described above. The cell **700** further includes a cathode **108** connected with a cathode current collector **112**, composed of a conductive metal such as aluminum. Suitable positive electrodes to couple with the electrochemical structure in such battery cells include: for both primary and rechargeable cells, elemental sulfur-based electrodes, lithium polysulfide based electrodes, metal oxide-based electrodes (e.g., V_2O_5 , V_6O_{13} , AgV_2O_5), and metal sulfide based electrodes (e.g., FeS_2); for primary cells, metal oxide-based electrodes, such as MnO_2 , CuO , Ag_2CrO_4 and MoO_3 ; for primary cells, metal sulfide-based electrode, such as CuS and FeS ; for rechargeable cells metal oxide-based electrodes, such as Li_xCoO_2 , Li_xNiO_2 , $LiMn_2O_4$ and $LiFePO_4$; and, for rechargeable cells, a metal sulfide based electrode such as TiS_2 .

[0049] Additional materials and techniques for fabrication of active metal battery cells are described, for example, in U.S. Pat. No. 5,686,201 issued to Chu on Nov. 11, 1997. Further description of materials and techniques for fabrication of active metal battery cells having anode protective layers are described, for example, in U.S. patent application Ser. No. 09/139,601, filed Aug. 25, 1998 (now U.S. Pat. No. 6,214,061, issued Apr. 10, 2001), titled ENCAPSULATED LITHIUM ALLOY ELECTRODES HAVING BARRIER LAYERS, and naming May-Ying Chu, Steven J. Visco and

Lutgard C. DeJonge as inventors; U.S. patent application Ser. No. 09/086,665 filed May 29, 1998 (now U.S. Pat. No. 6,025,094, issued May 15, 2000), titled PROTECTIVE COATINGS FOR NEGATIVE ELECTRODES, and naming Steven J. Visco and May-Ying Chu as inventors; U.S. patent application Ser. No. 09/139,603 filed Aug. 25, 1998 (now U.S. Pat. No. 6,402,795, issued Jun. 11, 2002), titled "PLATING METAL NEGATIVE ELECTRODES UNDER PROTECTIVE COATINGS," and naming May-Ying Chu, Steven J. Visco and Lutgard C. DeJonghe as inventors; U.S. patent application Ser. No. 09/139,601 filed Aug. 25, 1998 (now U.S. Pat. No. 6,214,061, issued Apr. 10, 2001), titled "METHOD FOR FORMING ENCAPSULATED LITHIUM ELECTRODES HAVING GLASS PROTECTIVE LAYERS," and naming Steven J. Visco and Floris Y. Tsang as inventors. The active metal electrode may also be an active metal alloy electrode, as further described in U.S. patent application Ser. No. 10/189,908 filed Jul. 3, 2002, titled "ENCAPSULATED ALLOY ELECTRODES," and naming Steven J. Visco, Yevgeniy S. Nimon and Bruce D. Katz as inventors. The battery component materials, including anodes, cathodes, separators, protective layers, etc., and techniques disclosed therein are generally applicable to the present invention and each of these patent applications is incorporated herein by reference in its entirety for all purposes.

CONCLUSION

[0050] Although the foregoing invention has been described in some detail for purposes of clarity of understanding, it will be apparent that certain changes and modifications may be practiced within the scope of the appended claims. It should be noted that there are many alternative ways of implementing both the process and compositions of the present invention. Accordingly, the present embodiments are to be considered as illustrative and not restrictive, and the invention is not to be limited to the details given herein.

[0051] All references cited herein are incorporated by reference for all purposes.

What is claimed is:

1. A method of fabricating an electrochemical device component structure, the method comprising:

applying a layer of a protective interlayer precursor selected from the group consisting of metal nitrides, metal phosphides, metal halides, red phosphorus, amines, phosphines, borazine ($B_3N_3H_6$), and triazine ($C_3N_3H_3$) on a polymer electrolyte; and

applying an active metal selected from the group consisting of alkali metals, alkaline earth metals and alloys thereof to the layer of precursor on the polymer electrolyte;

whereby the precursor is converted to a reaction product formed by contact of the active metal with the precursor such that a protective interlayer conductive to ions of the active metal is formed in situ between the active metal and the polymer electrolyte.

2. The method of claim 1, wherein the active metal comprises an anode.

3. The method of claim 2, further comprising applying a current collector on a surface of the active metal anode opposite that in contact with the protective interlayer.

4. The method of claim 1, wherein the active metal is an alkali metal or alloy thereof.

5. The method of claim 4, wherein the active metal is lithium or a lithium alloy.

6. The method of claim 1, wherein the precursor is a metal nitride.

7. The method of claim 1, wherein the precursor is PbI_2 , the active metal is lithium, and the protective interlayer formed in situ on reaction with the active metal is LiI .

8. The method of claim 1, wherein the reaction product is a LiI -poly(2-vinylpyridine) complex formed by application of a poly(2-vinylpyridine) precursor to the polymer electrolyte, followed by application of iodine to the poly(2-vinylpyridine), followed by application of lithium as the active metal, whereby the LiI -poly(2-vinylpyridine) complex is formed.

9. The method of claim 8, wherein the active metal is applied by evaporation of lithium.

10. The method of claim 9, wherein the active metal is applied as a lithium foil.

11. An electrochemical device component structure, comprising:

an active metal electrode;

a polymer electrolyte;

a protective interlayer between the electrode and the polymer electrolyte, the interlayer comprising a material conductive to ions of the active metal and chemically compatible with the active metal and the polymer electrolyte, the material selected from the group consisting of nitrides, phosphides and halides of the active metal.

12. The structure of claim 11, wherein the active metal is lithium.

13. The structure of claim 11, wherein the reaction product comprises a material selected from the group consisting of Li_3N , Li_3P and LiI , LiBr , LiCl and LiF .

14. The structure of claim 11, wherein the polymer electrolyte comprises a material selected from the group consisting of polyethylene oxide (PEO), polypropylene oxide (PPO), polyimide, and Nafion based membranes.

15. The structure of claim 11, wherein the thickness of the protective interlayer is about 0.2 to 1 micron.

16. The structure of claim 11, wherein the active metal of the electrode is selected from the group consisting of alkali metals, alkaline earth metals, and transition metals.

17. The structure of claim 11, wherein the active metal electrode further comprises a current collector on a surface opposite that in contact with the reaction product.

18. The structure of claim 11, wherein the reaction product is an active metal halide complexed with a polymer.

19. The structure of claim 18, wherein the reaction product material is LiI -poly(2-vinylpyridine).

20. A battery cell, comprising:

an active metal electrode;

a polymer electrolyte;

a protective interlayer between the electrode and the polymer electrolyte, the interlayer comprising a material conductive to ions of the active metal and chemically compatible with the active metal and the polymer electrolyte, and the material selected from the group consisting of nitrides, phosphides and halides of the active metal; and

a positive electrode chosen from a sulfur-based positive electrode, a metal oxide based positive electrode, and a metal sulfide based positive electrode in contact with the polymer electrolyte.

* * * * *