

US 20090169958A1


(19) **United States**(12) **Patent Application Publication**
Lin(10) **Pub. No.: US 2009/0169958 A1**(43) **Pub. Date: Jul. 2, 2009**(54) **CERAMIC INTERCONNECT FOR FUEL
CELL STACKS****Publication Classification**(75) Inventor: **Guangyong Lin**, Shrewsbury, MA
(US)(51) **Int. Cl.**
H01M 8/10 (2006.01)
B05D 5/12 (2006.01)
H01M 6/00 (2006.01)
(52) **U.S. Cl.** **429/33; 429/30; 427/115; 29/623.1**

Correspondence Address:

**HAMILTON, BROOK, SMITH & REYNOLDS,
P.C.****530 VIRGINIA ROAD, P.O. BOX 9133
CONCORD, MA 01742-9133 (US)**(57) **ABSTRACT**(73) Assignee: **Saint-Gobain Ceramics &
Plastics, Inc.**, Worcester, MA (US)(21) Appl. No.: **12/316,806**(22) Filed: **Dec. 16, 2008****Related U.S. Application Data**(60) Provisional application No. 61/063,643, filed on Feb.
5, 2008, provisional application No. 61/009,003, filed
on Dec. 21, 2007.

A fuel cell comprises a plurality of sub-cells, each sub-cell including a first electrode in fluid communication with a source of oxygen gas, a second electrode in fluid communication with a source of a fuel gas, and a solid electrolyte between the first electrode and the second electrode. The sub-cells are connected with each other with an interconnect. The interconnect includes a first layer in contact with the first electrode of each cell, and a second layer in contact with the second electrode of each cell. The first layer includes a (La, Mn)Sr-titanate based perovskite represented by the empirical formula of $\text{La}_y\text{Sr}_{(1-y)}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$. In one embodiment, the second layer includes a (Nb,Y)Sr-titanate perovskite represented by the empirical formula of $\text{Sr}_{(1-1.5z-0.5k\pm\delta)}\text{Y}_z\text{Nb}_k\text{Ti}_{(1-k)}\text{O}_d$. In another embodiment, the interconnect has a thickness of between about 10 μm and about 100 μm , and the second layer of the interconnect includes a (La)Sr-titanate based perovskite represented by the empirical formula of $\text{Sr}_{(1-z\pm\delta)}\text{La}_z\text{TiO}_d$.

10






FIG. 1




FIG. 2




FIG. 3




FIG. 4

CERAMIC INTERCONNECT FOR FUEL CELL STACKS

RELATED APPLICATIONS

[0001] This application claims the benefit of U.S. Provisional Application No. 61/063,643, filed on Feb. 5, 2008 and U.S. Provisional Application No. 61/009,003, filed on Dec. 21, 2007. The entire teachings of the above applications are incorporated herein by reference.

BACKGROUND OF THE INVENTION

[0002] A fuel cell is a device that generates electricity by a chemical reaction. Among various fuel cells, solid oxide fuel cells use a hard, ceramic compound of metal (e.g., calcium or zirconium) oxide as an electrolyte. Typically, in the solid oxide fuel cells, an oxygen gas, such as O_2 , is reduced to oxygen ions (O^{2-}) at the cathode, and a fuel gas, such as hydrogen gas (H_2) gas, is oxidized with the oxygen ions to form water at the anode.

[0003] Interconnects are one of the critical issues limiting commercialization of solid oxide fuel cells. Currently, most companies and researchers working with planar cells are using coated metal interconnects. While metal interconnects are relatively easy to fabricate and process, they generally suffer from high power degradation rates (e.g. 10%/1,000 h) partly due to formation of metal oxides, such as Cr_2O_3 , at an interconnect-anode/cathode interface during operation. Ceramic interconnects based on lanthanum chromites ($LaCrO_3$) have lower degradation rates than metal interconnects partly due to relatively high thermodynamic stability and low Cr vapor pressure of $LaCrO_3$ compared to Cr_2O_3 formed on interfaces of the metal interconnects and electrode. However, lanthanum chromites generally are difficult to fully densify and require high temperatures, such as at or above about 1,600° C., for sintering. Although certain doped lanthanum chromites, such as strontium-doped and calcium-doped lanthanum chromites, can be sintered at lower temperatures, they tend to be either unstable or reactive with an electrolyte (e.g., a zirconia electrolyte) and/or an anode.

[0004] Therefore, there is a need for development of new interconnects for solid oxide fuel cells, addressing one or more of the aforementioned problems.

SUMMARY OF THE INVENTION

[0005] The invention is directed to a fuel cell, such as a solid oxide fuel cell (SOFC), that includes a plurality of sub-cells and to a method of preparing the fuel cell. Each sub-cell includes a first electrode in fluid communication with a source of oxygen gas, a second electrode in fluid communication with a source of a fuel gas, and a solid electrolyte between the first electrode and the second electrode. The fuel cell further includes an interconnect between the sub-cells. The interconnect includes a first layer in contact with the first electrode of each sub-cell, and a second layer in contact with the second electrode of each sub-cell. The first layer includes a (La,Mn)Sr-titanate based perovskite represented by the empirical formula of $La_xSr_{(1-y)}Ti_{(1-x)}Mn_xO_b$, wherein x is equal to or greater than zero, and equal to or less than 0.6; y is equal to or greater than 0.2, and equal to or less than 0.8; and b is equal to or greater than 2.5, and equal to or less than 3.5. In one embodiment, the second layer includes a (Nb,Y)Sr-titanate based perovskite represented by the empirical formula of $Sr_{(1-1.5z-0.5k\pm\delta k)}Y_zNb_kTi_{(1-k)}O_d$, wherein each of k

and z independently is equal to or greater than zero, and equal to or less than 0.2; d is equal to or greater than 2.5 and equal to or less than 3.5; and δ is equal to or greater than zero, and equal to or less than 0.05. In another embodiment, the interconnect has a thickness of between about 10 μm and about 100 μm , and the second layer of the interconnect includes a (Sr)La-titanate based perovskite represented by the empirical formula of $Sr_{(1-z\pm\delta)}La_zTiO_d$, wherein z is equal to or greater than zero, and equal to or less than 0.4; d is equal to or greater than 2.5, and equal to or less than 3.5; and δ is equal to or greater than zero, and equal to or less than 0.05.

[0006] In the invention, the first layer of (La,Mn)Sr-titanate based perovskite, which is in contact with the first electrode exposed to an oxygen source, can provide relatively high sinterability (e.g., sinterability to over 95% of theoretical density at a temperature lower than about 1,500° C.), stability in the oxidizing atmosphere and/or electrical conductivity. The second layer of (Nb,Y)Sr-titanate based perovskite and/or (La)Sr-titanate based perovskite, which is in contact with the second electrode exposed to a fuel source, can provide high electrical conductivity and stability in the reducing atmosphere. The (La,Mn)Sr-titanate based perovskite and the (Nb,Y)Sr-titanate based perovskite materials have similar thermal expansion coefficients with each other. For example, $La_{0.4}Sr_{0.6}Ti_{0.4}Mn_{0.6}O_3$ has an average thermal expansion coefficient of $11.9 \times 10^{-6} K^{-1}$ at 30° C.-1,000° C. in air, and $Sr_{0.86}Y_{0.08}TiO_3$ has an average thermal expansion coefficient of $11-12 \times 10^{-6} K^{-1}$ at 25° C.-1,000° C. in air. Thus, both of the first layer of (La,Mn)Sr-titanate based perovskite and the second layer of (Nb,Y)Sr-titanate based perovskite can be co-sintered at the same time, minimizing process steps.

[0007] In another embodiment, the present invention is directed to a method of forming a fuel cell that includes a plurality of sub-cells. The method includes connecting each of the sub-cells with an interconnect. Each sub-cell includes a first electrode in fluid communication with a source of oxygen gas, a second electrode in fluid communication with a source of a fuel gas, and a solid electrolyte between the first electrode and the second electrode. The interconnect includes a first layer that includes a (La,Mn)Sr-titanate-based perovskite represented by the empirical formula of $La_xSr_{(1-y)}Ti_{(1-x)}Mn_xO_b$, wherein x is equal to or greater than zero and equal to or less than 0.6, y is equal to or greater than 0.2 and equal to or less than 0.8, and b is equal to or greater than 2.5 and equal to or less than 3.5. The first layer is in contact with the first electrode of each sub-cell. The interconnect also includes a second layer that includes a (Nb,Y)Sr-titanate-based perovskite represented by the empirical formula of $Sr_{(1-1.5z-0.5k\pm\delta k)}Y_zNb_kTi_{(1-k)}O_d$, wherein each of k and z independently is equal to or greater than zero and equal to or less than 0.2, d is equal to or greater than 2.5 and equal to or less than 3.5, and δ is equal to or greater than zero and equal to or less than 0.05. The second layer is in contact with the second electrode of each sub-cell. In one embodiment, the method includes forming at least one component of each sub-cell. In another embodiment, the method includes forming at least one of the electrodes of each sub-cell, and forming the interconnect. In yet another embodiment, at least one of the electrodes of each sub-cell is formed independently from the formation of the interconnect, and at least one of the electrodes of each sub-cell is formed together with the formation of the interconnect. In one embodiment, the first electrode of a first sub-cell of the plurality of sub-cells is formed together with the first and the second layers of the interconnect, and the formation of the

first electrode, the first layer and the second layer includes disposing a second-layer material of the interconnect over the second electrode of a first sub-cell, disposing a first-layer material of the interconnect over the second-layer material, disposing a first-electrode material of a second sub-cell over the first-layer, of the interconnect, and heating the materials such that the first-layer and second-layer materials of the interconnect form the first and second layers of the interconnect, respectively, and that the first-electrode material forms the first electrode.

[0008] In another embodiment, the present invention is directed to a method of forming a fuel cell that includes a plurality of sub-cells, comprising the step of connecting each of the sub-cells with an interconnect having a thickness of between about 10 μm and about 100 μm . Each sub-cell includes a first electrode in fluid communication with a source of oxygen gas, a second electrode in fluid communication with a source of a fuel gas, and a solid electrolyte between the first electrode and the second electrode. The interconnect includes a first layer that includes a (La,Mn)Sr-titanate-based perovskite represented by the empirical formula of $\text{La}_y\text{Sr}_{(1-y)}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$, wherein x is equal to or greater than zero and equal to or less than 0.6, y is equal to or greater than 0.2 and equal to or less than 0.8, and b is equal to or greater than 2.5 and equal to or less than 3.5. The first layer is in contact with the first electrode of each sub-cell. The interconnect also includes a second layer that includes a (La)Sr-titanate based perovskite represented by the empirical formula of $\text{Sr}_{(1-z\pm\delta)}\text{La}_z\text{TiO}_d$, wherein z is equal to or greater than zero and equal to or less than 0.4, d is equal to or greater than 2.5 and equal to or less than 3.5, and δ is equal to or greater than zero and equal to or less than 0.05. The second layer is in contact with the second electrode of each sub-cell. In one embodiment, the method includes forming at least one component of each sub-cell. In another embodiment, the method includes forming at least one of the electrodes of each sub-cell, and forming the interconnect. In yet another embodiment, at least one of the electrodes of each sub-cell is formed independently from the formation of the interconnect, and at least one of the electrodes of each sub-cell is formed together with the formation of the interconnect. In one embodiment, the first electrode of a first sub-cell of the plurality of sub-cells is formed together with the first and the second layers of the interconnect, and the formation of the first electrode, the first layer and the second layer includes disposing a second-layer material of the interconnect over the second electrode of a first sub-cell, disposing a first-layer material of the interconnect over the second-layer material, disposing a first-electrode material of a second sub-cell over the first-layer of the interconnect, and heating the materials such that the first-layer and second-layer materials of the interconnect form the first and second layers of the interconnect, respectively, and that the first-electrode material forms the first electrode.

[0009] This invention has many advantages. Bi-layer ceramic interconnects of the invention meet all the major requirements for solid oxide fuel cell (SOFC) stack interconnects. (La,Mn)Sr-titanate based perovskite is stable and its electrical conductivity is high in an oxidizing atmosphere, and therefore this material can be used on the air side in the bi-layer ceramic interconnect. (Nb,Y)Sr-titanate based perovskite and (La)Sr-titanate based perovskite is stable and its electrical conductivity is high in a reducing atmosphere, and therefore this material can be used on the fuel side in the bi-layer ceramic interconnect. These materials also have the

advantage that, containing no chromium, they do not have the problems associated with lanthanum chromites (LaCrO_3). The present invention can be used in a solid oxide fuel cell (SOFC) system, particularly in planar SOFC stacks. SOFCs offer the potential of high efficiency electricity generation, with low emissions and low noise operation. They are also seen as offering a favorable combination of electrical efficiency, co-generation efficiency and fuel processing simplicity. One example of a use for SOFCs is in a home or other building. The SOFC can use the same fuel as used to heat the home, such as natural gas. The SOFC system can run for extended periods of time to generate electricity to power the home and if excess amounts are generated, the excess can be sold to the electric grid. Also, the heat generated in the SOFC system can be used to provide hot water for the home. SOFCs can be particularly useful in areas where electric service is unreliable or non-existent.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] FIG. 1 is a schematic cross-sectional view of one embodiment of the invention.

[0011] FIG. 2 is a schematic diagram of a fuel cell of the invention in a planar, stacked design.

[0012] FIG. 3 is a schematic diagram of a fuel cell of the invention in a tubular design.

[0013] FIG. 4 is a scanning electron microscopic (SEM) image of an interconnect of the invention made of $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.4}\text{Mn}_{0.6}\text{O}_{3-\delta}$ and $\text{Sr}_{0.86}\text{Y}_{0.08}\text{TiO}_{3-\delta}$ layers.

DETAILED DESCRIPTION OF THE INVENTION

[0014] The foregoing will be apparent from the following more particular description of example embodiments of the invention, as illustrated in the accompanying drawings in which like reference characters refer to the same parts throughout the different views. The drawing is not necessarily to scale, emphasis instead being placed upon illustrating embodiments of the present invention.

[0015] FIG. 1 shows fuel cell 10 of the invention. Fuel cell 10 includes a plurality of sub-cells 12. Each sub-cell 12 includes first electrode 14 and second electrode 16. Typically, first and second electrodes 14 and 16 are porous. In fuel cell 10, first electrode 14 at least in part defines a plurality of first gas channels 18 in fluid communication with a source of oxygen gas, such as air. Second electrode 16 at least in part defines a plurality of second gas channels 20 in fluid communication with a fuel gas source, such as H_2 gas or a natural gas which can be converted into H_2 gas in situ at second electrode 16.

[0016] Although, in FIG. 1, first electrodes 14 and second electrodes 16 define a plurality of gas channels 18 and 20, other types of gas channels, such as a microstructured channel (e.g., grooved channel) at each of the electrodes or as a separate layer in fluid communication with the electrode, can also be used in the invention. For example, referring to FIG. 2, first gas channel 18 is defined at least in part by first electrode 14 and by at least in part by interconnect 24, and second gas channel 20 is defined at least in part by second electrode 16 and by at least in part by interconnect 24.

[0017] Any suitable cathode materials known in the art can be used for first electrode 14. In one embodiment, first electrode 14 includes a La-manganate (e.g., $\text{La}_{1-a}\text{MnO}_3$, where a is equal to or greater than zero, and equal to or less than 0.1) or La-ferrite based material. Typically, the La-manganate or

La-ferrite based materials are doped with one or more suitable dopants, such as Sr, Ca, Ba, Mg, Ni, Co or Fe. Examples of doped La-manganate based materials include LaSr-manganates (LSM) (e.g., $\text{La}_{1-k}\text{Sr}_k\text{MnO}_3$, where k is equal to or greater than 0.1, and equal to or less than 0.3, (La+Sr)/Mn is in a range of between about 1.0 and about 0.95 (molar ratio)) and LaCa-manganates (e.g., $\text{La}_{1-k}\text{Ca}_k\text{MnO}_3$, k is equal to or greater than 0.1, and equal to or less than 0.3, (La+Ca)/Mn is in a range of between about 1.0 and about 0.95 (molar ratio)). Examples of doped La-ferrite based materials include LaSrCo-ferrite (LSCF) (e.g., $\text{La}_{1-q}\text{Sr}_q\text{Co}_{1-j}\text{Fe}_j\text{O}_3$, where each of q and j independently is equal to or greater than 0.1, and equal to or less than 0.4, (La+Sr)/(Fe+Co) is in a range of between about 1.0 and about 0.95 (molar ratio)). In one specific embodiment, first electrode **14** includes at least one of a LaSr-manganate (LSM) (e.g., $\text{La}_{1-k}\text{Sr}_k\text{MnO}_3$) and a LaSrCo-ferrite (LSCF). Common examples include $(\text{La}_{0.8}\text{Sr}_{0.2})_{0.98}\text{MnO}_{3\pm\delta}$ (δ is equal to or greater than zero, and equal to or less than 0.05) and $\text{La}_{0.6}\text{Sr}_{0.4}\text{Co}_{0.2}\text{Fe}_{0.8}\text{O}_3$.

[0018] Any suitable anode materials known in the art can be used for second electrode **16**. In one embodiment, second electrode **16** includes a nickel (Ni) cermet. As used herein, the phrase “Ni cermet” means a ceramic metal composite that includes Ni, such as about 20 wt %-70 wt % of Ni. Examples of Ni cermets are materials that include Ni and yttria-stabilized zirconia (YSZ), such as ZrO_2 containing about 15 wt % of Y_2O_3 , and materials that include Ni and Y-zirconia or Sc-zirconia. An additional example of anode materials include Cu-cerium oxide. Specific examples of Ni cermet include 67 wt % Ni and 33 wt % YSZ, and 33 wt % Ni and 67 wt % YSZ.

[0019] Typically, the thickness of each of first and second electrodes **14** and **16** is independently in a range of between about 0.5 mm and about 2 mm. Specifically, the thickness of each of first and second electrodes **14** and **16** is, independently, in a range of between about 1 mm and about 2 mm.

[0020] Solid electrolyte **22** is between first electrode **14** and second electrode **16**. Any suitable solid electrolytes known in the art can be used in the invention. Examples include ZrO_2 based materials, such as Sc_2O_3 -doped ZrO_2 , Y_2O_3 -doped ZrO_2 , and Yb_2O_3 -doped ZrO_2 ; CeO_2 based materials, such as Sm_2O_3 -doped CeO_2 , Gd_2O_3 -doped CeO_2 , Y_2O_3 -doped CeO_2 and CaO-doped CeO_2 ; Ln-gallate based materials (Ln=a lanthanide, such as La, Pr, Nd or Sm), such as LaGaO_3 doped with Ca, Sr, Ba, Mg, Co, Ni, Fe or a mixture thereof (e.g., $\text{La}_{0.8}\text{Sr}_{0.2}\text{Ga}_{0.8}\text{Mg}_{0.2}\text{O}_3$, $\text{La}_{0.8}\text{Sr}_{0.2}\text{Ga}_{0.8}\text{Mg}_{0.15}\text{Co}_{0.05}\text{O}_3$, $\text{La}_{0.9}\text{Sr}_{0.1}\text{Ga}_{0.8}\text{Mg}_{0.2}\text{O}_3$, LaSrGaO_4 , $\text{LaSrGa}_3\text{O}_7$ or $\text{La}_{0.9}\text{A}_{0.1}\text{Ga}_3$ where A=Sr, Ca or Ba); and mixtures thereof. Other examples include doped yttrium-zirconate (e.g., YZr_2O_7), doped gadolinium-titanate (e.g., $\text{Gd}_2\text{Ti}_2\text{O}_7$) and brownmillerites (e.g., $\text{Ba}_2\text{In}_2\text{O}_6$ or $\text{Ba}_2\text{In}_2\text{O}_5$). In a specific embodiment, electrolyte **22** includes ZrO_2 doped with 8 mol % Y_2O_3 (i.e., 8 mol % Y_2O_3 -doped ZrO_2).

[0021] Typically, the thickness of solid electrolyte **22** is in a range of between about 5 μm and about 20 μm , such as between about 5 μm and about 10 μm . Alternatively, the thickness of solid electrolyte **22** is thicker than about 100 μm (e.g., between about 100 μm and about 500 μm). In this embodiment employing solid electrolyte **22** having a thickness greater than about 100 μm , solid electrolyte **22** can provide structural support for fuel cell **10**.

[0022] Fuel cell **10** further includes interconnect **24** between sub-cells **12**. Interconnect **24** includes first layer **26** in contact with first electrode **14**, and second layer **28** in

contact with second electrode **16**. First layer **26** includes a (La,Mn)Sr-titanate based perovskite represented by the empirical formula of $\text{La}_y\text{Sr}_{(1-y)}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$, wherein x is equal to or greater than zero, and equal to or less than 0.6; y is equal to or greater than 0.2, and equal to or less than 0.8; and b is equal to or greater than 2.5, and equal to or less than 3.5. In one specific embodiment, the (La,Mn)Sr-titanate based perovskite is represented by the empirical formula of $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$, wherein values of x and b are as described above. Specific examples of suitable (La,Mn)Sr-titanate based perovskites include $\text{La}_{0.4}\text{Sr}_{0.6}\text{TiO}_b$, $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.8}\text{Mn}_{0.2}\text{O}_b$, $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.6}\text{Mn}_{0.4}\text{O}_b$ and $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.4}\text{Mn}_{0.6}\text{O}_b$. In another specific embodiment, a $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$ material is employed, and the material has an electrical conductivity of between about 20 S/cm and about 25 S/cm in air (e.g. about 22.6 S/cm) at about 810° C., and has an average density equal to or greater than 95% theoretical density.

[0023] Second layer **28** includes a (Nb,Y)Sr-titanate based perovskite represented by the empirical formula of $\text{Sr}_{(1-1.5z-0.5k\pm\delta)}\text{Y}_z\text{Nb}_k\text{Ti}_{(1-k)}\text{O}_d$, or a (La)Sr-titanate based perovskite represented by the empirical formula of $\text{Sr}_{(1-z\pm\delta)}\text{La}_z\text{TiO}_d$, wherein each of k and z independently is equal to or greater than zero, and equal to or less than 0.4; and d is equal to or greater than 2.5, and equal to or less than 3.5 (e.g., equal to or greater than 2.9, and equal to or less than 3.2); and δ is equal to or greater than zero, and equal to or less than 0.05. Specific examples of the (Nb,Y)Sr-titanate based perovskite include $\text{Sr}_{0.86}\text{Y}_{0.08}\text{TiO}_{3\pm\delta}$, and $\text{Sr}_{0.995}\text{Ti}_{0.99}\text{Nb}_{0.01}\text{O}_{3\pm\delta}$ (wherein δ is equal to or greater than zero, and equal to or less than 0.05). A specific example of the (La)Sr-titanate based perovskites includes $\text{Sr}_{0.67}\text{La}_{0.33}\text{TiO}_{3\pm\delta}$ (wherein δ is equal to or greater than zero, and equal to or less than 0.05). In a further specific embodiment, a $\text{Sr}_{0.86}\text{Y}_{0.08}\text{TiO}_{3\pm\delta}$ or $\text{Sr}_{0.995}\text{Ti}_{0.99}\text{Nb}_{0.01}\text{O}_{3\pm\delta}$ material is employed, and has an average density equal to or greater than 95% theoretical density. In another further specific embodiment, the $\text{Sr}_{0.86}\text{Y}_{0.08}\text{TiO}_{3\pm\delta}$ and $\text{Sr}_{0.995}\text{Ti}_{0.99}\text{Nb}_{0.01}\text{O}_{3\pm\delta}$ materials have an electrical conductivity of about 82 S/cm and 10 S/cm, respectively, in a reducing environment (oxygen partial pressure of 10^{-19} atm) at about 800° C.

[0024] As used herein, “perovskite” has the perovskite structure known in the art. The perovskite structure is adopted by many oxides that have the chemical formula of ABO_3 . The general crystal structure is a primitive cube with the A-cation in the center of a unit cell, the B-cation at the corners of the unit cell, and the anion (i.e., O^{2-}) at the centers of each edge of the unit cell. The idealized structure is a primitive cube, but differences in ratio between the A and B cations can cause a number of different so-called distortions, of which tilting is the most common one. As used herein, the term “perovskite,” with or without other terms in combination therewith (e.g., “(La,Mn)Sr-titanate based perovskite,” “(Nb,Y)Sr-titanate based perovskite,” and “(La)Sr-titanate based perovskite”) also includes such distortions. Also, as used herein, the term “(La,Mn)Sr-titanate based perovskite” means a La- and/or Mn-substituted SrTiO_3 (Sr-titanate) having the perovskite structure. In one example, La-substituted, Sr-titanate based perovskites have the perovskite structure of SrTiO_3 wherein a portion of the Sr atoms of SrTiO_3 are substituted with La atoms. In another example, Mn-substituted, Sr-titanate based perovskites have the perovskite structure of SrTiO_3 wherein a portion of the Ti atoms of SrTiO_3 are substituted with Mn atoms. In yet another example, La- and Mn-substituted, Sr-

titanate based perovskites have the perovskite structure of SrTiO_3 wherein a portion of the Sr atoms of SrTiO_3 are substituted with La atoms, and a portion of the Ti atoms of SrTiO_3 are substituted with Mn atoms. Also, as used herein, the term “(Nb,Y)Sr-titanate based perovskite” means a Nb- and/or Y-substituted, SrTiO_3 (Sr-titanate) having the perovskite structure. In one example, Y-substituted, Sr-titanate based perovskites have the perovskite structure of SrTiO_3 wherein a portion of the Sr atoms of SrTiO_3 are substituted with Y atoms. In another example, Nb-substituted, Sr-titanate based perovskites have the perovskite structure of SrTiO_3 wherein a portion of the Ti atoms of SrTiO_3 are substituted with Nb atoms. In yet another example, Nb- and Y-substituted, Sr-titanate based perovskites have the perovskite structure of SrTiO_3 wherein a portion of the Sr atoms of SrTiO_3 are substituted with Y atoms, and a portion of the Ti atoms of SrTiO_3 are substituted with Nb atoms. Also, as used herein, the term “(La)Sr-titanate based perovskite” means La-substituted SrTiO_3 (Sr-titanate) having the perovskite structure, wherein a portion of the Sr atoms of SrTiO_3 are substituted with La atoms. Generally, in the (La,Mn)Sr-titanate based perovskites, La and Sr atoms occupy the A-cation sites, while Ti and Mn atoms occupy the B-cation sites. Generally, in the (Nb,Y)Sr-titanate based perovskites, Sr and Y atoms occupy the A-cation sites, while Ti and Nb atoms occupy the B-cation sites. Generally, in the (La)Sr-titanate based perovskite, Sr and La atoms occupy the A-cation sites, while Ti atoms occupy the B-cation sites.

[0025] In a specific embodiment, first layer **26** includes $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.4}\text{Mn}_{0.6}\text{O}_{3\pm\delta}$ and second layer **28** includes $\text{Sr}_{0.86}\text{Y}_{0.08}\text{TiO}_{3\pm\delta}$. In another specific embodiment, first layer **26** includes $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.4}\text{Mn}_{0.6}\text{O}_{3\pm\delta}$ and second layer **28** includes $\text{Sr}_{0.995}\text{Ti}_{0.99}\text{Nb}_{0.01}\text{O}_{3\pm\delta}$. In yet another specific embodiment, first layer **26** includes $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.4}\text{Mn}_{0.6}\text{O}_{3\pm\delta}$ and second layer **28** includes $\text{Sr}_{0.67}\text{La}_{0.33}\text{TiO}_{3\pm\delta}$. In these embodiments, specifically, first electrode **14** includes $(\text{La}_{0.8}\text{Sr}_{0.2})_{0.98}\text{MnO}_{3\pm\delta}$ or $\text{La}_{0.6}\text{Sr}_{0.4}\text{Co}_{0.2}\text{Fe}_{0.8}\text{O}_3$, and second electrode **16** includes 67 wt % Ni and 33 wt % YSZ. In these embodiments, more specifically, first electrode **14** includes $(\text{La}_{0.8}\text{Sr}_{0.2})_{0.98}\text{MnO}_{3\pm\delta}$ or $\text{La}_{0.6}\text{Sr}_{0.4}\text{Co}_{0.2}\text{Fe}_{0.8}\text{O}_3$; second electrode **16** includes 67 wt % Ni and 33 wt % YSZ; and electrolyte **22** includes 8 mol % Y_2O_3 -doped ZrO_2 .

[0026] Typically, the thickness of each of first layer **26** and second layer **28** is in a range of between about 5 μm and about 1000 μm . Specifically, the thickness of each of first layer **26** and second layer **28** is in a range of between about 10 μm and about 1000 μm . In one specific embodiment, the thickness of second layer **28** is about 0.005 to about 0.5 of the total thickness of interconnect **24**.

[0027] Interconnect **24** can be in any shape, such as a planar shape (see FIG. 1) or a microstructured (e.g., grooved) shape (see FIG. 2). In one specific embodiment, at least one interconnect **24** of fuel cell **10** is substantially planar.

[0028] In one embodiment, the thickness of interconnect **24** is in a range of between about 10 μm and about 1,000 μm . Alternatively, the thickness of interconnect **24** is in a range of between about 0.005 mm and about 2.0 mm. In one specific embodiment, the thickness of interconnect **24** is in a range of 10 μm and about 500 μm . In another embodiment, the thickness of interconnect **24** is in a range of 10 μm and about 200 μm . In yet another embodiment, the thickness of interconnect **24** is between about 10 μm and about 100 μm . In yet another embodiment, the thickness of interconnect **24** is between

about 10 μm and about 75 μm . In yet another embodiment, the thickness of interconnect **24** is between about 15 μm and about 65 μm .

[0029] In one specific embodiment, first electrode **14** and/or second electrode **16** has a thickness of between about 0.5 mm and about 2 mm thick; and interconnect **24** has a thickness of between about 10 μm and about 200 μm , specifically between about 10 μm and about 200 μm , and more specifically between about 10 μm and about 100 μm .

[0030] In another specific embodiment, second layer **28** includes a SrLa-titanate based perovskite described above; and interconnect **24** has a thickness of between about 10 μm and about 100 μm , specifically between about 10 μm and about 75 μm , and more specifically between about 15 μm and about 65 μm .

[0031] In yet another specific embodiment, at least one cell **12** includes porous first and second electrodes **14** and **16**, each of which is between about 0.5 mm and about 2 mm thick; solid electrolyte **22** has a thickness of between about 5 μm and about 20 μm ; and interconnect **24** is substantially planar and has a thickness of between about 10 μm and about 200 μm .

[0032] In yet another specific embodiment, interconnect **24** is substantially planar; first layer **26** of interconnect **24** includes $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$ (e.g., $x=0, 0.2, 0.4$ or 0.6); and each of first and second electrodes **14** and **16** is porous.

[0033] In yet another specific embodiment, interconnect **24** is substantially planar; first layer **26** of interconnect **24** includes $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$ (e.g., $x=0, 0.2, 0.4$ or 0.6); and each of first and second electrodes **14** and **16** is porous; and first electrode **14** includes a La-manganate or La-ferrite based material described above, such as $\text{La}_{1-k}\text{Sr}_k\text{MnO}_3$ or $\text{La}_{1-q}\text{Sr}_q\text{Co}_j\text{Fe}_{1-j}\text{O}_3$ (wherein values of each of k, q and j independently are as described above).

[0034] In yet another specific embodiment, interconnect **24** is substantially planar; first layer **26** of interconnect **24** includes $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$ (e.g., $x=0, 0.2, 0.4$ or 0.6); and each of first and second electrodes **14** and **16** is porous; and first electrode **14** includes a La-manganate or La-ferrite based material (e.g., $\text{La}_{1-k}\text{Sr}_k\text{MnO}_3$ or $\text{La}_{1-q}\text{Sr}_q\text{Co}_j\text{Fe}_{1-j}\text{O}_3$, values of each of k, q and j independently are as described above), and second electrode **16** includes a Ni cermet (e.g., 67 wt % Ni and 33 wt % YSZ). In one aspect of this specific embodiment, electrolyte **22** includes 8 mol % Y_2O_3 -doped ZrO_2 .

[0035] Fuel cell **10** of the invention can include any suitable number of a plurality of sub-cells **12**. In one embodiment, fuel cell **10** of the invention includes at least 30-50 sub-cells **12**. Sub-cells **12** of fuel cell **10** can be connected in series or in parallel.

[0036] A fuel cell of the invention can be a planar stacked fuel cell, as shown in FIG. 2. Alternatively, as shown in FIG. 3, a fuel cell of the invention can be a tubular fuel cell. Fuel cells shown in FIGS. 2 and 3 independently have the characteristics, including specific variables, as described for fuel cell **10** shown in FIG. 1 (for clarity, details of cell components are not depicted in FIGS. 2 and 3). Typically, in the planar design, as shown in FIG. 2, the components are assembled in flat stacks, with air and fuel flowing through channels built into the interconnect. Typically, in the tubular design, as shown in FIG. 3, the components are assembled in the form of a hollow tube, with the cell constructed in layers around a tubular cathode; air flows through the inside of the tube and fuel flows around the exterior.

[0037] The invention also includes a method of forming fuel cells as described above. The method includes forming a plurality of sub-cells **12** as described above, and connecting each sub-cell **12** with interconnect **24**. Fabrication of sub-cells **12** and interconnect **24** can employ any suitable techniques known in the art. For example, planar stacked fuel cells of the invention can be fabricated by particulate processes or deposition processes. Tubular fuel cells of the invention can be fabricated by having the cell components in the form of thin layers on a porous cylindrical tube, such as calcia-stabilized zirconia.

[0038] Typically, a suitable particulate process, such as tape casting or tape calendaring, involves compaction of powders, such as ceramic powders, into fuel cell components (e.g., electrodes, electrolytes and interconnects) and densification at elevated temperatures. For example, suitable powder materials for electrolytes, electrodes or interconnects of the invention, are made by solid state reaction of constituent oxides. Suitable high surface area powders can be precipitated from nitrate and other solutions as a gel product, which are dried, calcined and comminuted to give crystalline particles. The deposition processes can involve formation of cell components on a support by a suitable chemical or physical process. Examples of the deposition include chemical vapor deposition, plasma spraying and spray pyrolysis.

[0039] In one specific embodiment, interconnect **24** is prepared by laminating a first-layer material of interconnect **24**, and a second-layer material of interconnect **24**, side by side at a temperature in a range of between about 50° C. and about 80° C. with a loading of between about 5 and about 50 tons, and co-sintered at a temperature in a range of 1,300° C. and about 1,500° C. for a time period sufficient to form interconnect layers having a high theoretical density (e.g., greater than about 90% theoretical density, or greater than about 95% theoretical density), to thereby form first layer **26** and second layer **28**, respectively.

[0040] Alternatively, interconnect **24** is prepared by sequentially forming first layer **26** and then second layer **28** (or forming second layer **28** and then first layer **26**). Typically, each of the first and second slurries can be sintered at a temperature in a range of 1,300° C. and about 1,500° C. For example, the first slurry of $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.4}\text{Mn}_{0.6}\text{O}_{3-\delta}$ is sintered at about 1300° C. in air, and the second slurry of $\text{Sr}_{0.86}\text{Y}_{0.08}\text{TiO}_4$ or $\text{Sr}_{0.995}\text{Ti}_{0.99}\text{Nb}_{0.01}\text{O}_4$ is sintered at about 1400° C. in air.

[0041] In the invention, sub-cells **12** are connected via interconnect **24**. In one embodiment, at least one of the electrodes of each sub-cell **12** is formed independently from interconnect **24**. Formation of electrodes **14** and **16** of each sub-cell **12** can be done using any suitable method known in the art, as described above. In one specific embodiment: i) a second-layer material of interconnect **24** is disposed over second electrode **16** of a first sub-cell; ii) a first-layer material of interconnect **24** is disposed over the second-layer material, and iii) first electrode **14** of a second sub-cell is then disposed over the first-layer material of interconnect **24**. In another specific embodiment: i) a first-layer material of interconnect **24** is disposed over first electrode **14** of a second sub-cell; ii) a second-layer material of interconnect **24** is disposed over the first-layer material of interconnect **24**; and iii) second electrode **16** of a first sub-cell is disposed over the second-layer material. In these specific embodiments, sintering the first-layer and second-layer materials forms first layer **26** and second layer **28** of interconnect **24**, respectively.

[0042] Alternatively, one or more electrodes of sub-cells **12** (e.g., electrode **14** or **16**, or electrodes **14** and **16**) are formed together with formation of interconnect **24**. In one specific embodiment, i) a second-layer material of interconnect **24** is disposed over a second-electrode material of a first sub-cell; ii) a first-layer material of interconnect **24** is then disposed over the second-layer material; iii) a first-electrode material of a second sub-cell is disposed over the first-layer of interconnect **24**; and iv) heating the materials such that the first-layer and second-layer materials of interconnect **24** form first layer **26** and second layer **28** of interconnect **24**, respectively, and that the first-electrode and second-electrode materials form first electrode **14** and second electrode **16**, respectively.

[0043] In another specific embodiment: i) a second-layer material of interconnect **24** is disposed over second electrode **16** of a first sub-cell; ii) a first-layer material of interconnect **24** is disposed over the second-layer material; iii) disposing a first-electrode material of a second sub-cell over the first-layer of interconnect **24**, and iv) heating the materials such that the first-layer and second-layer materials of the interconnect form first layer **26** and second layer **28** of interconnect **24**, respectively, and that the first-electrode material forms first electrode **14**.

[0044] The fuel cells of the invention, such as SOFCs, can be portable. Also, the fuel cells of the invention, such as SOFCs, can be employed as a source of electricity in homes, for example, to generate hot water.

EXEMPLIFICATION

Example

Bi-layer Interconnect of $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.4}\text{Mn}_{0.6}\text{O}_{3-\delta}$ ("LSTM") and $\text{Sr}_{0.86}\text{Y}_{0.08}\text{TiO}_{3-\delta}$ ("YST")

[0045] A small amount of (La,Mn)Sr-titanate, $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.4}\text{Mn}_{0.6}\text{O}_{3-\delta}$ (LSTM), powder (2.0 grams) was added on the top of (Nb,Y)Sr-titanate, $\text{Sr}_{0.86}\text{Y}_{0.08}\text{TiO}_{3-\delta}$ (YST), powder (1.0 gram). The LSTM/YST powders were die-pressed together using a steel die with a diameter of 1.125 inches at a load of 10,000 lbs. The $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{0.4}\text{Mn}_{0.6}\text{O}_{3-\delta}$ powder was binderized before die-pressing with 0.5 wt % polyethylene glycol (PEG-400) and 0.7 wt % polyvinyl alcohol (PVA 21205) in order to increase the strength of the green body for handling. The die-pressed LSTM/YST powders with a bi-layer structure were then co-sintered pressurelessly at 1350° C. for one hour in air. The LSTM/YST bi-layer structure was cross sectioned, mounted in an epoxy, and polished for SEM (scanning electron microscope) examination. FIG. 4 shows an SEM result of the fabricated LSTM/YST bi-layer structure. As shown in FIG. 4, both LSTM and YST materials were bonded very well to each other, and had a very high density. The total thickness of the LSTM-YST bi-layer structure was about 1.20 mm; the thickness of LSTM layer was about 0.72 mm, and the thickness of YST layer was about 0.48 mm. The relative densities of the LSTM layer and the YST layer were about 98% and about 94%, respectively.

EQUIVALENT

[0046] While this invention has been particularly shown and described with references to example embodiments thereof, it will be understood by those skilled in the art that various changes in form and details may be made therein without departing from the scope of the invention encompassed by the appended claims.

What is claimed is:

1. A fuel cell, comprising:
 - a) a plurality of sub-cells, each sub-cell including
 - i) a first electrode in fluid communication with a source of oxygen gas,
 - ii) a second electrode in fluid communication with a source of a fuel gas, and
 - iii) a solid electrolyte between the first electrode and the second electrode; and
 - b) an interconnect between the sub-cells, the interconnect including
 - i) a first layer that includes a (La,Mn)Sr-titanate based perovskite represented by the empirical formula of $\text{La}_y\text{Sr}_{(1-y)}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$, wherein
 - x is equal to or greater than zero and equal to or less than 0.6,
 - y is equal to or greater than 0.2 and equal to or less than 0.8, and
 - b is equal to or greater than 2.5 and equal to or less than 3.5,
 wherein the first layer is in contact with the first electrode of each sub-cell, and
 - ii) a second layer that includes a (Nb,Y)Sr-titanate based perovskite represented by the empirical formula of $\text{Sr}_{(1-1.5z-0.5k\pm\delta)}\text{Y}_z\text{Nb}_k\text{Ti}_{(1-k)}\text{O}_d$, wherein
 - each of k and z independently is equal to or greater than zero and equal to or less than 0.2,
 - d is equal to or greater than 2.5 and equal to or less than 3.5, and
 - δ is equal to or greater than zero and equal to or less than 0.05,
 wherein the second layer is in contact with the second electrode of each sub-cell.
2. The fuel cell of claim 1, wherein the (La,Mn)Sr-titanate based perovskite is represented by the empirical formula of $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$.
3. The fuel cell of claim 1, wherein each of the first and second electrodes is porous.
4. The fuel cell of claim 3, wherein the interconnect is substantially planar.
5. The fuel cell of claim 4, wherein the solid electrolyte includes at least one material selected from the group consisting of ZrO_2 based material, CeO_2 based material and lanthanide-gallate based material.
6. The fuel cell of claim 4, wherein the first electrode includes at least one of a lanthanum strontium manganate (LSM) based material and a lanthanum strontium cobalt ferrite (LSCF) based material.
7. The fuel cell of claim 4, wherein the second electrode includes a Ni cermet.
8. The fuel cell of claim 4, wherein the thickness of each of the first and second electrodes of at least one of the cells is in a range of between about 0.5 mm and about 2 mm.
9. The fuel cell of claim 8, wherein the thickness of the interconnect is in a range of between about 5 μm and about 1,000 μm .
10. The fuel cell of claim 9, wherein the thickness of the interconnect is in a range of between about 10 μm and about 500 μm .
11. The fuel cell of claim 10, wherein the thickness of the interconnect is in a range of between about 10 μm and about 200 μm .
12. The fuel cell of claim 11, wherein the thickness of the interconnect is in a range of between about 10 μm and about 100 μm .
13. A fuel cell, comprising:
 - a) a plurality of sub-cells, each sub-cell including
 - i) a first electrode in fluid communication with a source of oxygen gas,
 - ii) a second electrode in fluid communication with a source of a fuel gas, and
 - iii) a solid electrolyte between the first electrode and the second electrode; and
 - b) an interconnect between the sub-cells and having a thickness of between about 10 μm and about 100 μm , the interconnect including
 - i) a first layer that includes a (La,Mn)Sr-titanate based perovskite represented by the empirical formula of $\text{La}_y\text{Sr}_{(1-y)}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$, wherein
 - x is equal to or greater than zero and equal to or less than 0.6,
 - y is equal to or greater than 0.2 and equal to or less than 0.8, and
 - b is equal to or greater than 2.5 and equal to or less than 3.5,
 wherein the first layer is in contact with the first electrode of each sub-cell; and
 - ii) a second layer that includes a (La)Sr-titanate based perovskite represented by the empirical formula of $\text{Sr}_{(1-z\pm\delta)}\text{La}_z\text{TiO}_d$, wherein
 - z is equal to or greater than zero and equal to or less than 0.4,
 - d is equal to or greater than 2.5 and equal to or less than 3.5, and
 - δ is equal to or greater than zero and equal to or less than 0.05,
 wherein the second layer is in contact with the second electrode of each sub-cell.
14. The fuel cell of claim 13, wherein the (La,Mn)Sr-titanate-based perovskite is represented by the empirical formula of $\text{La}_{0.4}\text{Sr}_{0.6}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$.
15. The fuel cell of claim 13, wherein each of the first and second electrodes is porous.
16. The fuel cell of claim 15, wherein the interconnect is substantially planar.
17. The fuel cell of claim 16, wherein the solid electrolyte includes at least one material selected from the group consisting of ZrO_2 based material, CeO_2 based material and lanthanide-gallate based material.
18. The fuel cell of claim 16, wherein the first electrode includes at least one of a lanthanum strontium manganate (LSM) based material and a lanthanum strontium cobalt ferrite (LSCF) based material.
19. The fuel cell of claim 16, wherein the second electrode includes a Ni cermet.
20. The fuel cell of claim 16, wherein the thickness of each of the first and second electrodes of at least one of the cells is in a range of between about 0.5 mm and about 2 mm.
21. The fuel cell of claim 20, wherein the thickness of the interconnect is in a range of between about 10 μm and about 75 μm .
22. The fuel cell of claim 21, wherein the thickness of the interconnect is in a range of between about 15 μm and about 65 μm .

23. A method of forming a fuel cell that includes a plurality of sub-cells, comprising the step of connecting each of the sub-cells with an interconnect, wherein each sub-cell includes:

- i) a first electrode in fluid communication with a source of oxygen gas,
- ii) a second electrode in fluid communication with a source of a fuel gas, and
- iii) a solid electrolyte between the first electrode and the second electrode, and

wherein the interconnect includes

- i) a first layer that includes a (La,Mn)Sr-titanate-based perovskite represented by the empirical formula of $\text{La}_y\text{Sr}_{(1-y)}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$, wherein x is equal to or greater than zero and equal to or less than 0.6, y is equal to or greater than 0.2 and equal to or less than 0.8, and b is equal to or greater than 2.4 and equal to or less than 3.3, wherein the first layer is in contact with the first electrode of each sub-cell, and
- ii) a second layer that includes a (Nb,Y)Sr-titanate-based perovskite represented by the empirical formula of $\text{Sr}_{(1-1.5z-0.5k\pm\delta)}\text{Y}_z\text{Nb}_k\text{Ti}_{(1-k)}\text{O}_d$, wherein each of k and z independently is equal to or greater than zero and equal to or less than 0.2, d is equal to or greater than 2.5 and equal to or less than 3.5, and δ is equal to or greater than zero and equal to or less than 0.05, wherein the second layer is in contact with the second electrode of each sub-cell.

24. The method of claim 23, further including forming at least one component of each sub-cell.

25. The method of claim 24, further including forming at least one of the electrodes of each sub-cell, and forming the interconnect.

26. The method of claim 25, wherein at least one of the electrodes of each sub-cell is formed independently from the formation of the interconnect.

27. The method of claim 25, wherein at least one of the electrodes of each sub-cell is formed together with the formation of the interconnect.

28. The method of claim 26, wherein the first electrode of a first sub-cell of the plurality of sub-cells is formed together with the first and the second layers of the interconnect, and wherein the formation of the first electrode, the first layer and the second layer includes:

- i) disposing a second-layer material of the interconnect over the second electrode of a first sub-cell;
- ii) disposing a first-layer material of the interconnect over the second-layer material;
- iii) disposing a first-electrode material of a second sub-cell over the first-layer of the interconnect; and
- iv) heating the materials such that the first-layer and second-layer materials of the interconnect form the first and second layers of the interconnect, respectively, and that the first-electrode material forms the first electrode.

29. A method of forming a fuel cell that includes a plurality of sub-cells, comprising the step of connecting each of the

sub-cells with an interconnect having a thickness of between about 10 μm and about 100 μm , wherein each sub-cell includes:

- i) a first electrode in fluid communication with a source of oxygen gas,
- ii) a second electrode in fluid communication with a source of a fuel gas, and
- iii) a solid electrolyte between the first electrode and the second electrode, and

wherein the interconnect includes

- i) a first layer that includes a (La,Mn)Sr-titanate-based perovskite represented by the empirical formula of $\text{La}_y\text{Sr}_{(1-y)}\text{Ti}_{(1-x)}\text{Mn}_x\text{O}_b$, wherein x is equal to or greater than zero and equal to or less than 0.6, y is equal to or greater than 0.2 and equal to or less than 0.8, and b is equal to or greater than 2.5 and equal to or less than 3.5, wherein the first layer is in contact with the first electrode of each sub-cell, and
- ii) a second layer that includes a (La)Sr-titanate based perovskite represented by the empirical formula of $\text{Sr}_{(1-z\pm\delta)}\text{La}_z\text{TiO}_d$, wherein z is equal to or greater than zero and equal to or less than 0.4, d is equal to or greater than 2.5 and equal to or less than 3.5, and δ is equal to or greater than zero and equal to or less than 0.05, wherein the second layer is in contact with the second electrode of each sub-cell.

30. The method of claim 29, further including forming at least one component of each sub-cell.

31. The method of claim 30, further including forming at least one of the electrodes of each sub-cell, and forming the interconnect.

32. The method of claim 31, wherein at least one of the electrodes of each sub-cell is formed independently from the formation of the interconnect.

33. The method of claim 31, wherein at least one of the electrodes of each sub-cell is formed together with the formation of the interconnect.

34. The method of claim 33, wherein the first electrode of a first sub-cell of the plurality of sub-cells is formed together with the first and the second layers of the interconnect, and wherein the formation of the first electrode, the first layer and the second layer includes:

- i) disposing a second-layer material of the interconnect over the second electrode of a first sub-cell;
- ii) disposing a first-layer material of the interconnect over the second-layer material;
- iii) disposing a first-electrode material of a second sub-cell over the first-layer of the interconnect; and
- iv) heating the materials such that the first-layer and second-layer materials of the interconnect form the first and second layers of the interconnect, respectively, and that the first-electrode material forms the first electrode.