

US 20120031477A1

(19) **United States**

(12) **Patent Application Publication**
Fogel et al.

(10) **Pub. No.: US 2012/0031477 A1**

(43) **Pub. Date: Feb. 9, 2012**

(54) **PHOTOVOLTAIC DEVICES WITH AN
INTERFACIAL BAND-GAP MODIFYING
STRUCTURE AND METHODS FOR
FORMING THE SAME**

Publication Classification

(51) **Int. Cl.**
H01L 31/108 (2006.01)
H01L 31/18 (2006.01)

(75) **Inventors:** **Keith E. Fogel**, Hopewell Junction,
NY (US); **Jee H. Kim**, Los
Angeles, CA (US); **Devendra K.
Sadana**, Pleasantville, NY (US);
George S. Tulevski, White Plains,
NY (US); **Ahmed Abou-Kandil**,
Elmsford, NY (US); **Hisham S.
Mohamed**, Clifton Park, NY (US);
Mohamed Saad, White Plains, NY
(US); **Osama Tobail**, Elmsford, NY
(US)

(52) **U.S. Cl. 136/255; 438/92; 977/750; 977/734;
257/E31.065**


(73) **Assignees:** **EGYPT NANOTECHNOLOGY
CENTER**, Cairo-Alexandria (EG);
**INTERNATIONAL BUSINESS
MACHINES CORPORATION**,
Armonk, NY (US)

(21) **Appl. No.: 12/850,272**

(22) **Filed: Aug. 4, 2010**

(57) **ABSTRACT**

A Schottky-barrier-reducing layer is provided between a p-doped semiconductor layer and a transparent conductive material layer of a photovoltaic device. The Schottky-barrier-reducing layer can be a conductive material layer having a work function that is greater than the work function of the transparent conductive material layer. The conductive material layer can be a carbon-material layer such as a carbon nanotube layer or a graphene layer. Alternately, the conductive material layer can be another transparent conductive material layer having a greater work function than the transparent conductive material layer. The reduction of the Schottky barrier reduces the contact resistance across the transparent material layer and the p-doped semiconductor layer, thereby reducing the series resistance and increasing the efficiency of the photovoltaic device.






FIG. 1 (Prior Art)




FIG. 2 (Prior Art)




FIG. 3 (Prior Art)




FIG. 4 (Prior Art)




FIG. 5 (Prior Art)




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10A




FIG. 10B




FIG. 10C

**PHOTOVOLTAIC DEVICES WITH AN
INTERFACIAL BAND-GAP MODIFYING
STRUCTURE AND METHODS FOR
FORMING THE SAME**

BACKGROUND

[0001] The present disclosure relates to photovoltaic devices, and more particularly to photovoltaic devices including an interfacial band-gap modifying structure and methods of forming the same.

[0002] A photovoltaic device is a device that converts the energy of incident photons to electromotive force (e.m.f.). Typical photovoltaic devices include solar cells, which are configured to convert the energy in the electromagnetic radiation from the Sun to electric energy. Each photon has an energy given by the formula $E=h\nu$, in which the energy E is equal to the product of the Plank constant h and the frequency ν of the electromagnetic radiation associated with the photon.

[0003] A photon having energy greater than the electron binding energy of a matter can interact with the matter and free an electron from the matter. While the probability of interaction of each photon with each atom is probabilistic, a structure can be built with a sufficient thickness to cause interaction of photons with the structure with high probability. When an electron is knocked off an atom by a photon, the energy of the photon is converted to electrostatic energy and kinetic energy of the electron, the atom, and/or the crystal lattice including the atom. The electron does not need to have sufficient energy to escape the ionized atom. In the case of a material having a band structure, the electron can merely make a transition to a different band in order to absorb the energy from the photon.

[0004] The positive charge of the ionized atom can remain localized on the ionized atom, or can be shared in the lattice including the atom. When the positive charge is shared by the entire lattice, thereby becoming a non-localized charge, this charge is described as a hole in a valence band of the lattice including the atom. Likewise, the electron can be non-localized and shared by all atoms in the lattice. This situation occurs in a semiconductor material, and is referred to as photogeneration of an electron-hole pair. The formation of electron-hole pairs and the efficiency of photogeneration depend on the band structure of the irradiated material and the energy of the photon. In case the irradiated material is a semiconductor material, photogeneration occurs when the energy of a photon exceeds the band gap energy, i.e., the energy difference of a band gap of the irradiated material.

[0005] The direction of travel of charged particles, i.e., the electrons and holes, in an irradiated material is sufficiently random. Thus, in the absence of any electrical bias, photogeneration of electron-hole pairs merely results in heating of the irradiated material. However, an external field can break the spatial direction of the travel of the charged particles to harness the electrons and holes formed by photogeneration.

[0006] One exemplary method of providing an electric field is to form a p-i-n junction around the irradiated material. As negative charges accumulate in the p-doped region and positive charges accumulate in the n-doped region, an electric field is generated from the direction of the n-doped region toward the p-doped region. Electrons generated in the intrinsic region drift towards the n-doped region due to the electric field, and holes generated in the intrinsic region drift towards the p-doped region. Thus, the electron-hole pairs are collected systematically to provide positive charges at the p-doped

region and negative charges at the n-doped region. The p-i-n junction forms the core of this type of photovoltaic device, which provides electromotive force that can power any device connected to the positive node at the p-doped region and the negative node at the n-doped region.

BRIEF SUMMARY

[0007] A Schottky-barrier-reducing layer is provided between a p-doped semiconductor layer and a transparent conductive material layer of a photovoltaic device. The Schottky-barrier-reducing layer can be a conductive material layer having a work function that is greater than the work function of the transparent conductive material layer. The conductive material layer can be a carbon-material layer such as a carbon nanotube layer or a graphene layer. Alternately, the conductive material layer can be another transparent conductive material layer having a greater work function than the transparent conductive material layer. The reduction of the Schottky barrier reduces the contact resistance across the transparent material layer and the p-doped semiconductor layer, thereby reducing the series resistance and increasing the efficiency of the photovoltaic device.

[0008] According to an aspect of the present disclosure, a photovoltaic device is provided, which includes a stack of a transparent conductive material layer, a Schottky-barrier-reducing layer contacting the transparent conductive material layer, and a p-doped semiconductor layer contacting the p-doped semiconductor layer. The Schottky barrier across the stack has a lower contact resistance than a Schottky barrier across another stack that includes all layers of the stack less the Schottky-barrier-reducing layer.

[0009] According to another aspect of the present disclosure, a method of forming a photovoltaic device is provided. The method includes: forming a transparent conductive material layer on a substrate; forming a Schottky-barrier-reducing layer on the transparent conductive material layer; and forming a p-doped semiconductor layer on the Schottky-barrier-reducing layer. The Schottky barrier across a stack of the transparent conductive material layer, the Schottky-barrier-reducing layer, and the p-doped semiconductor layer has less contact resistance than a Schottky barrier across another stack that includes all layers of the stack less the Schottky-barrier-reducing layer.

**BRIEF DESCRIPTION OF THE SEVERAL
VIEWS OF THE DRAWINGS**

[0010] FIG. 1 is a vertical cross-sectional view of a prior art photovoltaic device structure.

[0011] FIG. 2 is an equivalent circuit for the prior art photovoltaic device structure of FIG. 1.

[0012] FIG. 3 is a schematic graph of an I-V curve of the prior art photovoltaic device structure of FIG. 1.

[0013] FIG. 4 is a band diagram of a transparent conductive material layer and a p-doped semiconductor layer in the prior art photovoltaic device structure of FIG. 1.

[0014] FIG. 5 is a graph of an I-V curve for an exemplary prior art photovoltaic device structure.

[0015] FIG. 6 is a vertical cross-sectional view of an exemplary photovoltaic device structure according to various embodiments of the present disclosure.

[0016] FIG. 7 is a band diagram of a junction of a single wall carbon nanotube and a p-doped silicon material according to the first embodiment of the present disclosure.

[0017] FIG. 8 is a graph illustrating the resistivity of aluminum-doped zinc oxide as a function of weight percentage of aluminum according to a second embodiment of the present disclosure.

[0018] FIG. 9 is a band diagram for first and second exemplary photovoltaic device structures according to the first and second embodiments of the present disclosure.

[0019] FIG. 10A is a vertical cross-sectional view of an exemplary photovoltaic device structure after formation of a transparent conductive material layer according to embodiments of the present invention.

[0020] FIG. 10B is a vertical cross-sectional view of an exemplary photovoltaic device structure after formation of a p-doped semiconductor layer according to embodiments of the present invention.

[0021] FIG. 10C is a vertical cross-sectional view of an exemplary photovoltaic device structure after formation of back reflector layers according to embodiments of the present invention.

DETAILED DESCRIPTION

[0022] As stated above, the present disclosure relates to photovoltaic devices including an interfacial band-gap modifying structure and methods of forming the same, which are now described in detail with accompanying figures. Throughout the drawings, the same reference numerals or letters are used to designate like or equivalent elements. The drawings are not necessarily drawn to scale.

[0023] As used herein, a crystal structure is “microcrystalline” if the average grain size of the material is from 1 nm to 10 microns.

[0024] As used herein, a “hydrogenated” semiconductor material is a semiconductor material including incorporated hydrogen therein, which neutralizes dangling bonds in the semiconductor material and allows charge carriers to flow more freely.

[0025] As used herein, a “semiconductor-material-containing reactant gas” refers to a gas including at least one atom of Si, Ge, or components of a compound semiconductor material.

[0026] As used herein, an element is “optically transparent” if the element is transparent in the visible electromagnetic spectral range having a wavelength from 400 nm to 800 nm.

[0027] As used herein, a “Schottky-barrier-reducing” element is an element that is located between two other elements that form a Schottky barrier, in which the presence of the Schottky-barrier-reducing element reduces a contact resistance of a structure including the two other elements and the Schottky-barrier-reducing element relative a structure including only the two other elements.

[0028] Referring to FIG. 1, a prior art photovoltaic device structure includes a material stack, from top to bottom, of a substrate 110, a transparent conductive material layer 120, a p-doped semiconductor layer 130, an intrinsic semiconductor layer 140, an n-doped semiconductor layer 150, a first back reflector layer 160, and a second back reflector layer 170. The substrate 110 typically includes an optically transparent material. The transparent conductive material layer 120 functions as a positive node of the prior art photovoltaic device, and the combination of the second back reflector layer 170 functions as a negative node of the prior art photovoltaic device. The first back reflector layer 160 can be optically transparent, and the combination of the first and second back

reflector layers (160, 170) reflect any photons that pass through the stack of the p-doped semiconductor layer 130, the intrinsic semiconductor layer 140, and the n-doped semiconductor layer 150 to enhance the efficiency of the prior art photovoltaic device.

[0029] The p-doped semiconductor layer 130 can include an amorphous p-doped hydrogenated silicon-containing material or microcrystalline p-doped hydrogenated silicon-containing material. The amorphous p-doped hydrogenated silicon-containing material or the microcrystalline p-doped hydrogenated silicon-containing material can be deposited by flowing a semiconductor-material-containing reactant in hydrogen carrier gas. In this case, hydrogen atoms are incorporated in the deposited material of the p-doped semiconductor layer 130. The p-doped semiconductor layer 130 can include an amorphous p-doped hydrogenated silicon-carbon alloy or a microcrystalline p-doped hydrogenated silicon-carbon alloy.

[0030] Referring to FIG. 2, the functionality of the prior art photovoltaic device of FIG. 1 can be approximated by an equivalent circuit that includes a current source, a diode, and two resistors. The equivalent circuit of FIG. 2 approximates a unit area of the prior art photovoltaic device of FIG. 1, which provides electrical current that is proportional to the total irradiated area of the prior art photovoltaic device. The photovoltaic current per unit area generated by the prior art photovoltaic device is referred to as a short-circuit current density J_{sc} , i.e., the current density generated by the prior art photovoltaic device if the positive node and the negative node of the prior art photovoltaic device are electrically shorted. Thus, the current source in FIG. 2 generates an electrical current with a current density of the short-circuit current density J_{sc} .

[0031] Power dissipation through internal leakage current is approximated by a shunt resistance R_{sh} . A finite value for the shunt resistance R_{sh} triggers an internal leakage current through the prior art photovoltaic device of FIG. 1, and degrades the performance of the prior art photovoltaic device. The lesser the shunt resistance R_{sh} , the greater is the internal power loss due to the internal leakage current.

[0032] Power dissipation through internal resistance of the prior art photovoltaic device of FIG. 1 is approximated by a series resistance R_s . A non-zero value for the series resistance R_s triggers Joule loss within the prior art photovoltaic device. The greater the series resistance R_s , the greater is the internal power loss due to the internal resistance of the prior art photovoltaic device.

[0033] Referring back to FIG. 1, a predominant portion of the series resistance R_s is the resistance of a Schottky barrier at the interface between the transparent conductive material layer 120 and the p-doped semiconductor layer 130. The Schottky barrier dominates the total value of the series resistance R_s unless significant defects in conductive components, e.g., the transparent conductive material layer 120 or the first and second back reflector layers (160, 170), causes the series resistance R_s to increase abnormally. Thus, in well-functioning prior art photovoltaic devices of FIG. 1, the series resistance R_s is limited by the resistance introduced by the Schottky barrier at the interface between the transparent conductive material layer 120 and the p-doped semiconductor layer 130. In case amorphous hydrogenated carbon-containing silicon alloy is employed for the p-doped semiconductor layer 130, the series resistance R_s of the prior art photovoltaic device of FIG. 1 is from 20 Ohms-cm² to 30 Ohms-cm². In case microcrystalline hydrogenated carbon-containing silicon alloy is

employed for the p-doped semiconductor layer **130**, the series resistance R_s of the prior art photovoltaic device of FIG. **1** is from 10 Ohms-cm² to 15 Ohms-cm².

[0034] The potential difference between the positive node, i.e., the p-doped semiconductor layer **130**, and the negative node, i.e., the n-doped semiconductor layer **150**, generates an internal current that flow in the opposite direction to the photocurrent, i.e., the current represented by the current source having the short-circuit current density J_{sc} . The dark current has the same functional dependence on the voltage across the current source as a diode current. Thus, the dark current is approximated by a diode that allows a reverse-direction current. The density of the dark current, i.e., the dark current per unit area of the prior art photovoltaic device, is referred to as the dark current density J_{dark} . An external load can be attached to an outer node of the series resistor and one of the nodes of the current source. In FIG. **2**, the value the impedance of the load is the value of the actual impedance of a physical load is divided by the area of the prior art photovoltaic cell because the equivalent circuit of FIG. **2** describes the functionality of a unit area of the prior art photovoltaic cell.

[0035] Referring to FIG. **3**, a schematic graph of an I-V curve of the prior art photovoltaic device structure of FIG. **1** is shown. The bias voltage V is the voltage across the load in the equivalent circuit of FIG. **2**. The open circuit voltage V_{oc} corresponds to the voltage across the load as the resistance of the load diverges to infinity, i.e., the voltage across the current source when the load is disconnected. The inverse of the absolute value of the slope of the I-V curve at $V=0$ and $J=J_{sc}$ is approximately equal to the value of the shunt resistance R_{sh} . The inverse of the absolute value of the slope of the I-V curve at $V=V_{oc}$ and $J=0$ is approximately equal to the value of the series resistance R_s . The effect of the dark current is shown as an exponential decrease in the current density J as a function of the bias voltage V around a non-zero value of the bias voltage.

[0036] The operating range of a photovoltaic device is the portion of the I-V curve in the first quadrant, i.e., when both the bias voltage V and the current density J are positive. The power density P , i.e., the density of power generated from an unit area of the prior art photovoltaic device of FIG. **1**, is proportional to the product of the voltage V and the current density J along the I-V curve. The power density P reaches a maximum at a maximum power point of the I-V curve, which has the bias voltage of V_m and the current density of J_m . The fill factor FF is defined by the following formula:

$$FF = \frac{J_m \times V_m}{J_{sc} \times V_{oc}}. \quad (\text{Eq. 1})$$

The fill factor FF defines the degree by which the I-V curve of FIG. **3** approximates a rectangle. The fill factor FF is affected by the series resistance R_s and the shunt resistance R_{sh} . The smaller the series resistance R_s , the greater the fill factor FF . The greater the shunt resistance R_{sh} , the greater the fill factor FF . The theoretical maximum for the fill factor is 1.0.

[0037] The efficiency η of a photovoltaic device is the ratio of the power density at the maximum power point to the incident light power density P_s . In other words, the efficiency η is given by:

$$\eta = \frac{J_m \times V_m}{P_s}. \quad (\text{Eq. 2})$$

Eq. 2 can be rewritten as:

$$\eta = \frac{J_{sc} \times V_{oc} \times FF}{P_s}. \quad (\text{Eq. 3})$$

Thus, the efficiency η of a photovoltaic device is proportional to the short circuit current density J_{sc} , the open circuit voltage V_{oc} , and the fill factor FF .

[0038] The efficiency η of a photovoltaic device depends on the spectral composition of the incident light. For solar cells, the efficiency is calculated under a standard radiation condition defined as 1 sun, which employs the spectrum of the sunlight.

[0039] Referring to FIG. **4**, a band diagram illustrates the band bending in the p-doped semiconductor layer **130** in the prior art photovoltaic device structure of FIG. **1** due to the transparent conductive material layer **120**. Materials currently available for the transparent conductive material layer **120** are n-type materials. A Schottky barrier exists at the interface between the transparent conductive material layer **120** and the p-doped semiconductor layer **130**. The valence band and the conduction band of the p-doped semiconductor layer **130** bend downward at the interface between the transparent conductive material layer **120** and the p-doped semiconductor layer **130**.

[0040] In case the transparent conductive material layer **120** is an aluminum-doped zinc oxide, the work function of the transparent conductive material layer **120** is about 4.5 eV. In other words, the Fermi level E_F is at 4.5 eV below the vacuum level. Other typical materials for the transparent conductive material layer **120** also have a work function of about 4.5 eV.

[0041] In case the p-doped semiconductor layer **130** includes an amorphous hydrogenated silicon carbon alloy, the band gap of the p-doped semiconductor layer **130** is around 1.85 eV. The difference between the Fermi level and the valence band of the amorphous hydrogenated silicon carbon alloy is about 1.0 eV. This is a significant energy barrier, and is the cause of the predominant component of the series resistance R_s from 20 Ohms-cm² to 30 Ohms-cm² in the prior art photovoltaic device of FIG. **1**.

[0042] Referring to FIG. **5**, the significant series resistance R_s in the prior art photovoltaic device of FIG. **1** can be manifested as humps in an I-V curve in case the p-doped semiconductor layer **130** includes an amorphous hydrogenated silicon carbon alloy. The portion of the I-V curve in the fourth quadrant can be obtained by applying an external voltage across the positive and negative terminals of the prior art photovoltaic device of FIG. **1**. The hump in the first quadrant can adversely affect the fill factor FF , and consequently affect the efficiency η adversely.

[0043] FIG. **6** is a vertical cross-sectional view of an exemplary photovoltaic device structure according to various embodiments of the present disclosure. The photovoltaic device structure includes a material stack, from top to bottom, of a substrate **10**, a transparent conductive material layer **20**, a Schottky-barrier-reducing layer **22**, a p-doped semiconduc-

tor layer **30**, an intrinsic semiconductor layer **40**, an n-doped semiconductor layer **50**, a first back reflector layer **60**, and a second back reflector layer **70**.

[0044] The substrate **10** is a structure that provides mechanical support to the photovoltaic structure. The substrate **10** is transparent in the range of electromagnetic radiation at which photogeneration of electrons and holes occur within the photovoltaic structure. If the prior art photovoltaic device is a solar cell, the substrate **10** can be optically transparent. The substrate **10** can be a glass substrate. The thickness of the substrate **10** can be from 50 microns to 3 mm, although lesser and greater thicknesses can also be employed.

[0045] The transparent conductive material layer **20** includes a material that is transparent in the range of electromagnetic radiation at which photogeneration of electrons and holes occur within the photovoltaic device structure. If the photovoltaic device structure is employed as a solar cell, the transparent conductive material layer **20** can be optically transparent. For example, the transparent conductive material layer **20** can include a transparent conductive oxide such as a fluorine-doped tin oxide ($\text{SnO}_2\text{:F}$), an aluminum-doped zinc oxide (ZnO:Al), or indium tin oxide. The thickness of the transparent conductive material layer **20** can be from 300 nm to 3 microns, although lesser and greater thicknesses can also be employed.

[0046] The Schottky-barrier-reducing layer **22** includes a material that reduces the Schottky barrier through the stack of the transparent conductive material layer **20**, the Schottky-barrier-reducing layer **22**, and the p-doped semiconductor layer **30** relative a stack (not shown) consisting of a first layer that is the same as the transparent conductive material layer **20** and a second layer that is the same as the p-doped semiconductor layer **30**. Thus, the presence of the Schottky-barrier-reducing layer **22** reduces the Schottky barrier of the stack of the transparent conductive material layer **20**, the Schottky-barrier-reducing layer **22**, and the p-doped semiconductor layer **30** relative to the stack consisting of the first layer and the second layer. Correspondingly, the contact resistance through the stack of the transparent conductive material layer **20**, the Schottky-barrier-reducing layer **22**, and the p-doped semiconductor layer **30** is less than the contact resistance of the stack consisting of the first layer and the second layer. In other words, the Schottky barrier across the stack of the transparent conductive material layer **20**, the Schottky-barrier-reducing layer **22**, and the p-doped semiconductor layer **30** has lower contact resistance than a Schottky barrier across another stack that includes all layers of the stack less the Schottky-barrier-reducing layer **22**. The various embodiments of the present disclosure differ by the composition of the material in the Schottky-barrier-reducing layer **22**.

[0047] According to a first embodiment, the Schottky-barrier inducing layer **22** is an optically transparent layer including an allotrope of carbon. In this embodiment, the exemplary photovoltaic device structure is referred to as a first exemplary photovoltaic device structure. In one case, the Schottky-barrier-reducing layer **22** can be a single wall carbon nanotube layer. A carbon nanotube is an allotrope of carbon with a cylindrical nanostructure. A single wall carbon nanotube is a carbon nanotube that does not contain any other carbon nanotube therein, and is not contained in another carbon nanotube. Thus, a single wall carbon nanotube is a single strand of carbon nanotube that stands alone by itself without including, or being included in, another carbon nanotube. The cylindri-

cal arrangement of carbon atoms in a single wall carbon nanotube provides novel properties that make the carbon nanotube potentially useful in many applications. The diameter of a single wall carbon nanotube is on the order of a few nanometers, while the length of the single wall carbon nanotube can be from tens of nanometers to tens of centimeters. The chemical bonding of a single wall carbon nanotube is composed entirely of sp^2 bonds, similar to the bonding of graphite. This bonding structure is stronger than the sp^3 bonds found in diamonds, providing the single wall carbon nanotube with their unique strength. The single wall carbon nanotube has a work function on the order of 5 eV, which is greater than the work function of most transparent conductive material employed for photovoltaic devices.

[0048] In another case, the Schottky-barrier-reducing layer **22** can be a graphene layer. Graphene is a structure consisting of carbon as a two-dimensional sheet. A graphene monolayer has a thickness of about 0.34 nm, i.e., which is approximately the atomic diameter of a single carbon atom. A graphene layer can exist as a monolayer of a two-dimensional sheet. Alternatively, a graphene layer can exist as a stack of a plurality of two-dimensional monolayers of carbon, which do not exceed more than 10 monolayers and is typically limited to less than 5 monolayers. Graphene provides excellent in-plane conductivity. Semiconductor devices employing graphene have been suggested in the art to provide high-density and high-switching-speed semiconductor circuits. Carbon atoms are arranged in a two-dimensional honeycomb crystal lattice in which each carbon-carbon bond has a length of about 0.142 nm.

[0049] According to a second embodiment, the Schottky-barrier-reducing layer **22** includes a same material as the transparent conductive material layer **20**. However, the Schottky-barrier-reducing layer **22** has a different doping than the transparent conductive material layer. The difference in the doping between the transparent conductive material layer **20** and the Schottky-barrier-reducing layer **22** is set such that the presence of the Schottky-barrier-reducing layer **22** reduces the Schottky barrier between the transparent conductive material layer **20** and the p-doped semiconductor layer **30**. In this embodiment, the exemplary photovoltaic device structure is referred to as a second exemplary photovoltaic device structure.

[0050] In one case, the transparent conductive material layer **20** includes an aluminum-doped zinc oxide having an aluminum doping at a first dopant concentration, and the Schottky-barrier-reducing layer **22** includes an aluminum-doped zinc oxide having an aluminum doping at a second dopant concentration. In this case, the first dopant concentration is greater than the second dopant concentration.

[0051] In another case, the transparent conductive material layer **20** includes a first fluorine-doped tin oxide having a fluorine doping at a first dopant concentration, and the Schottky-barrier-reducing layer **22** includes a second fluorine-doped tin oxide having a fluorine doping at a second dopant concentration. In this case, the first dopant concentration is greater than the second dopant concentration.

[0052] The p-doped semiconductor layer **30** includes an amorphous or microcrystalline p-doped semiconductor-containing material. In some cases, the p-doped semiconductor layer **30** can include a hydrogenated amorphous or microcrystalline p-doped semiconductor-containing material. The presence of hydrogen in the p-doped semiconductor layer **30**

can increase the concentration of free charge carriers, i.e., holes, by delocalizing the electrical charges that are pinned to defect sites.

[0053] A hydrogenated p-doped semiconductor-containing material can be deposited in a process chamber containing a semiconductor-material-containing reactant gas a carrier gas. To facilitate incorporation of hydrogen in the hydrogenated p-doped semiconductor-containing material, a carrier gas including hydrogen can be employed. Hydrogen atoms in the hydrogen gas within the carrier gas are incorporated into the deposited material to form an amorphous or microcrystalline hydrogenated p-doped semiconductor-containing material of the p-doped semiconductor layer **30**. The thickness of the p-doped semiconductor layer **30** can be from 3 nm to 30 nm, although lesser and greater thicknesses can also be employed.

[0054] The p-doped semiconductor layer **30** can include a silicon-containing material, a germanium-containing material, or a compound semiconductor material. In one embodiment, the p-doped semiconductor layer **30** includes a silicon-containing material. The microcrystalline p-doped hydrogenated semiconductor-containing material can be a microcrystalline p-doped hydrogenated silicon-carbon alloy. In this case, a carbon-containing gas can be flown into the processing chamber during deposition of the microcrystalline p-doped hydrogenated silicon-carbon alloy. The atomic concentration of carbon in the microcrystalline p-doped hydrogenated silicon-carbon alloy of the p-doped semiconductor layer can be from 1% to 90%, and preferably from 10% to 70%. In this case, the band gap of the p-doped semiconductor layer **30** can be from 1.7 eV to 2.1 eV.

[0055] The intrinsic semiconductor layer **40** includes an intrinsic hydrogenated semiconductor-containing material. The intrinsic hydrogenated semiconductor-containing material is deposited in a process chamber containing a semiconductor-material-containing reactant gas a carrier gas including hydrogen. Hydrogen atoms in the hydrogen gas within the carrier gas are incorporated into the deposited material to form the intrinsic hydrogenated semiconductor-containing material of the intrinsic semiconductor layer **40**. The intrinsic hydrogenated semiconductor-containing material can be amorphous or microcrystalline. Typically, the intrinsic hydrogenated semiconductor-containing material is amorphous. The thickness of the intrinsic semiconductor layer **40** depends on the diffusion length of electrons and holes in the intrinsic hydrogenated semiconductor-containing material. Typically, the thickness of the intrinsic semiconductor layer **40** is from 100 nm to 1 micron, although lesser and greater thicknesses can also be employed.

[0056] The intrinsic semiconductor layer **40** can include a silicon-containing material, a germanium-containing material, or a compound semiconductor material. In one embodiment, the intrinsic semiconductor layer **40** includes a silicon-containing material. The semiconductor material of the intrinsic semiconductor layer **40** can be amorphous intrinsic silicon.

[0057] The n-doped semiconductor layer **50** includes an n-doped semiconductor-containing material. The n-doped semiconductor layer **50** can be a hydrogenated material, in which case an n-doped hydrogenated semiconductor-containing material is deposited in a process chamber containing a semiconductor-material-containing reactant gas a carrier gas including hydrogen. The n-type dopants in the n-doped semiconductor layer **50** can be introduced by in-situ doping. Alternately, the n-type dopants in the n-doped semiconductor

layer **50** can be introduced by subsequent introduction of dopants employing any method known in the art. The n-doped semiconductor layer **50** can be amorphous or microcrystalline. The thickness of the n-doped semiconductor layer **50** can be from 6 nm to 60 nm, although lesser and greater thicknesses can also be employed.

[0058] The n-doped semiconductor layer **50** can include a silicon-containing material, a germanium-containing material, or a compound semiconductor material. In one embodiment, the n-doped semiconductor layer **50** includes a silicon-containing material. The semiconductor material of the n-doped semiconductor layer **50** can be amorphous n-doped silicon.

[0059] The first back reflector layer **60** includes a transparent conductive material that is transparent in the range of electromagnetic radiation at which photogeneration of electrons and holes occur within the photovoltaic device structure. If the photovoltaic device structure is employed as a solar cell, the first back reflector layer **60** can be optically transparent. For example, the first back reflector layer **60** can include a transparent conductive oxide such as a fluorine-doped tin oxide ($\text{SnO}_2\text{:F}$), an aluminum-doped zinc oxide (ZnO:Al), or indium tin oxide. Since such transparent conductive oxide materials are n-type materials, the contact between the first back reflector layer **60** and the n-doped semiconductor layer **50** is Ohmic, and as such, the contact resistance between the first back reflector layer **60** and the n-doped semiconductor layer **50** is negligible. The thickness of the back reflector layer **60** can be from 25 nm to 250 nm, although lesser and greater thicknesses can also be employed.

[0060] The second back reflector layer **70** includes a metallic material. Preferably, the metallic material has a high reflectivity in the range of electromagnetic radiation at which photogeneration of electrons and holes occur within the photovoltaic device structure. The metallic material can include silver, aluminum, or an alloy thereof. The thickness of the second back reflector layer **70** can be from 100 nm to 1 micron, although lesser and greater thicknesses can also be employed.

[0061] Because the resistance due to the Schottky barrier between the transparent conductive material layer **20** and the p-doped semiconductor layer **30** is the predominant component of a series resistance in properly constructed (i.e., non-defective) photovoltaic devices, the reduction of the Schottky barrier results in a dramatic reduction in the series resistance in the exemplary photovoltaic device structure according to the present disclosure compared to prior art photovoltaic device structures. For example, while the prior art photovoltaic device structure of FIG. 1 has a series resistance from 20 Ohms- cm^2 to 30 Ohms- cm^2 if an amorphous hydrogenated carbon-containing silicon alloy is employed for a p-doped semiconductor layer **130**, or has a series resistance from 10 Ohms- cm^2 to 15 Ohms- cm^2 if a microcrystalline hydrogenated carbon-containing silicon alloy is employed for the p-doped semiconductor layer **130**, photovoltaic device structures according to the present disclosure can have a series resistance less than 9 Ohms- cm^2 . Various samples of photovoltaic device structures according to the various embodiments of the present disclosure demonstrated a series resistance from 4 Ohms- cm^2 to 9 Ohms- cm^2 .

[0062] Referring to FIG. 7, a graph illustrates the J-V characteristics of a junction of single wall carbon nanotubes and a p-doped silicon material according to the first embodiment of the present disclosure. The J-V characteristics of the junction

of the single wall carbon nanotube and a p-doped silicon material approximate the J-V characteristics of the junction between the Schottky-barrier-reducing layer **22** and the p-doped semiconductor layer **30** within the first exemplary photovoltaic device structure for the case in which the Schottky-barrier-reducing layer **22** includes a layer of single wall carbon nanotubes and the p-doped semiconductor layer **30** includes the p-doped silicon material. The J-V characteristics show a diode forward voltage drop of about 0.1V and an estimated internal resistance of about 2 Ohms-cm². The J-V characteristics illustrate a lower contact resistance between the Schottky-barrier-reducing layer **22** and the p-doped semiconductor layer **30** than the contact resistance between any transparent conductive material layer known in the art and a p-doped semiconductor layer known in the art.

[0063] Referring to FIG. 7, a band diagram of a junction of a single wall carbon nanotube and a p-doped silicon layer illustrates the mechanism for the reduction in the contact resistance between the Schottky-barrier-reducing layer **22** and the p-doped semiconductor layer **30** according to the first embodiment of the present disclosure. The band bending Φ_b in the p-doped semiconductor layer **30** is the same irrespective of any selected energy level, i.e., the amount of band bending the same for the vacuum level, for the valence band E_v , and for the conduction band E_c . The various energy gaps between different energy levels in the band diagram are related by the following equations:

$$\eta = E_F - E_V \approx 0 \quad (\text{Eq. 1})$$

$$\Phi_{SWCNT} + \eta + \Phi_b - \chi_e + E_{gSi} \quad (\text{Eq. 2})$$

$$\Phi_{SWCNT} = 4.97 \text{ eV} \quad (\text{Eq. 3})$$

$$\chi_e = 4.05 \text{ eV} \quad (\text{Eq. 4})$$

$$E_{gSi} = 1.12 \text{ eV} \quad (\text{Eq. 5})$$

Solving the above equations, the value of band bending Φ_b is 0.2 eV, which is substantially smaller than an equivalent band bending of about 0.7 eV at an interface between a typical transparent conductive material and a p-doped silicon material. The smaller band bending at the interface between Schottky-barrier-reducing layer **22** and the p-doped semiconductor layer **30** reduces the Schottky barrier, and consequently the accompanying contact resistance, compared with a Schottky barrier between a transparent conductive material and a p-doped silicon material.

[0064] Single wall carbon nanotubes are transparent. See, for example, Hu et al., "Percolation in Transparent and Conducting Carbon Nanotube Networks," *Nanoletters*, 2004, Vol. 4, No. 12, pp. 2513-2517.

[0065] Referring to FIG. 8, a graph illustrates the resistivity of aluminum-doped zinc oxide as a function of weight percentage of aluminum according to a second embodiment of the present disclosure. The resistivity of aluminum-doped zinc oxide depends on the dopant concentration of aluminum. A high concentration of aluminum decreases resistivity of aluminum-doped zinc oxide, and shifts the Fermi level close to the conduction band edge. Conversely, a low concentration of aluminum increases resistivity of aluminum-doped zinc oxide, and shifts the Fermi level away from the conduction band toward the mid-gap level, i.e., the energy level midway between the valence band edge and the conduction band edge.

[0066] In case aluminum-doped zinc oxide is employed for the transparent conductive material layer **120** in the prior art

photovoltaic device structure of FIG. 1, the concentration of aluminum in the transparent conductive material layer **120** is constant. A homogeneous heavily-aluminum-doped zinc oxide layer may be employed for the transparent conductive material layer **120** in the prior art photovoltaic device structure of FIG. 1. On the one hand, if a heavily-aluminum-doped zinc oxide layer contacts a p-doped semiconductor layer **30**, the presence of the Fermi level close to the conduction band edge of the heavily-aluminum-doped zinc oxide layer causes significant the band bending in the p-doped semiconductor layer **30**, and the Schottky barrier between the p-doped semiconductor layer **30** and the heavily-aluminum-doped zinc oxide layer. At the same time, the low resistivity of the heavily-aluminum-doped zinc oxide layer reduces internal resistance of the photovoltaic device structure that includes the heavily-aluminum-doped zinc oxide layer. On the other hand, if a lightly-aluminum-doped zinc oxide layer contacts a p-doped semiconductor layer **30**, the presence of the Fermi level close to the middle of the band gap of the lightly-aluminum-doped zinc oxide layer reduces the band bending in the p-doped semiconductor layer **30** relative to the band bending in the case of a heavily-aluminum-doped zinc oxide layer. The Schottky barrier between the p-doped semiconductor layer **30** and the lightly-aluminum-doped zinc oxide layer is correspondingly decreased. However, the high resistivity of the lightly-aluminum-doped zinc oxide layer increases internal resistance of the photovoltaic device structure that includes the heavily-aluminum-doped zinc oxide layer. The thickness of the Schottky-barrier-reducing layer **22** can be from 1 nm to 10 nm in this case. When lightly-aluminum-doped zinc oxide is located at the interface between p-type semiconductor and heavily-aluminum-doped zinc oxide, the lightly-aluminum-doped zinc oxide reduces Schottky barrier heights and heavily-aluminum-doped zinc oxide reduces sheet resistance of entire zinc oxide stacks.

[0067] In one example of the second embodiment, the transparent conductive material layer **20** includes an aluminum-doped zinc oxide having an aluminum doping at a first dopant concentration, and the Schottky-barrier-reducing layer **22** includes an aluminum-doped zinc oxide having an aluminum doping at a second dopant concentration. The first dopant concentration is greater than the second dopant concentration. The high aluminum concentration of the transparent conductive material layer **20** provides low internal resistance in the second exemplary photovoltaic device structure. At the same time, the low aluminum concentration of the Schottky-barrier-reducing layer **22** provides a low Schottky barrier, and correspondingly, a low contact resistance between the Schottky-barrier-reducing layer **22** and the p-doped semiconductor layer **30**. In one example, the first dopant concentration is selected to be in the range from 2.0% atomic concentration or greater, and the second dopant concentration is selected to be in the range between 0% and 2.0%, although different ranges may be selected for the first and second dopant concentrations.

[0068] In case fluorine-doped tin oxide is employed for the transparent conductive material layer **120** in the prior art photovoltaic device structure of FIG. 1, the concentration of fluorine in the transparent conductive material layer **120** is constant. A homogeneous heavily-fluorine-doped tin oxide layer or a homogeneous lightly-fluorine-doped tin oxide layer may be employed for the transparent conductive material layer **120** in the prior art photovoltaic device structure of FIG. 1. On the one hand, if a heavily-fluorine-doped tin oxide layer

contacts a p-doped semiconductor layer **30**, the presence of the Fermi level close to the conduction band edge of the heavily-fluorine-doped tin oxide layer causes significant the band bending in the p-doped semiconductor layer **30**, and the Schottky barrier between the p-doped semiconductor layer **30** and the heavily-fluorine-doped tin oxide layer. At the same time, the low resistivity of the heavily-fluorine-doped tin oxide layer reduces internal resistance of the photovoltaic device structure that includes the heavily-fluorine-doped tin oxide layer. On the other hand, if a lightly-fluorine-doped tin oxide layer contacts a p-doped semiconductor layer **30**, the presence of the Fermi level close to the middle of the band gap of the lightly-fluorine-doped tin oxide layer reduces the band bending in the p-doped semiconductor layer **30** relative to the band bending in the case of a heavily-fluorine-doped tin oxide layer. The Schottky barrier between the p-doped semiconductor layer **30** and the lightly-fluorine-doped tin oxide layer is correspondingly decreased. However, the high resistivity of the lightly-fluorine-doped tin oxide layer increases internal resistance of the photovoltaic device structure that includes the heavily-fluorine-doped tin oxide layer. The thickness of the Schottky-barrier-reducing layer **22** can be from 1 nm to 50 in this case, although lesser and greater thicknesses can also be employed.

[0069] In another example of the second embodiment, the transparent conductive material layer **20** includes a fluorine-doped tin oxide having a fluorine doping at a first dopant concentration, and the Schottky-barrier-reducing layer **22** includes a fluorine-doped tin oxide having a fluorine doping at a second dopant concentration. The first dopant concentration is greater than the second dopant concentration. The high fluorine concentration of the transparent conductive material layer **20** provides low internal resistance in the second exemplary photovoltaic device structure. At the same time, the low fluorine concentration of the Schottky-barrier-reducing layer **22** provides a low Schottky barrier, and correspondingly, a low contact resistance between the Schottky-barrier-reducing layer **22** and the p-doped semiconductor layer **30**. In one example, the first dopant concentration is selected to be in the range from 2.0% atomic concentration or greater, and the second dopant concentration is selected to be in the range between 0% and 2.0%, although different ranges may be selected for the first and second dopant concentrations.

[0070] In some cases, the Schottky-barrier-reducing layer **22** can include a material having a higher resistivity than a material of the transparent conductive material layer **20** if the conductivity of the Schottky-barrier-reducing layer **22** increases with the dopant concentration in the Schottky-barrier-reducing layer **22**, i.e., if the resistivity of the Schottky-barrier-reducing layer **22** decreases with the dopant concentration in the Schottky-barrier-reducing layer **22**.

[0071] Referring to FIG. 9, a band diagram for first and second exemplary photovoltaic devices structure illustrates the mechanism for according to the first and second embodiments of the present disclosure. The Schottky-barrier-reducing layer **22** has a work function that is greater than a work function of the transparent conductive material layer by a work function differential Δ . The work function of the Schottky-barrier-reducing layer **22** is lesser than an absolute value of the Fermi level E_F of the p-doped semiconductor layer **30**, i.e., the energy difference between the vacuum level and the Fermi level energy E_F for the p-doped semiconductor layer **30**.

[0072] In the absence of the Schottky-barrier-reducing layer **22**, a direct contact between a transparent conductive material layer and a p-doped semiconductor layer causes an energy barrier equivalent to $\Delta + \Phi_b$, i.e., the sum of the difference in the work functions of the transparent conductive material layer **20** and the Schottky-barrier-reducing layer **22** and the band bending Φ_b at the interface between the Schottky-barrier-reducing layer **22** and the p-doped semiconductor layer **30**. Because the probability of finding a hole within the valence band of the p-doped semiconductor layer is determined by the Fermi-Dirac statistics, the probability of finding a hole in a surface region of the p-doped semiconductor layer **130** at the interface with the transparent conductive material layer **20** decreases almost exponentially with $\Delta + \Phi_b$. Thus, the Schottky barrier and the contact resistance are significant. In the present disclosure, the total energy barrier is broken into two separate barriers, each of which is less significant than a combined energy barrier. Consequently, the Schottky barrier and the contact resistance in the combined stack of the transparent conductive material layer **20**, the Schottky-barrier-reducing layer **22**, and the p-doped semiconductor layer **30** according to the first and second embodiments of the present disclosure are reduced compared to prior art.

[0073] FIG. 10A-10C are sequential vertical cross-sectional views that illustrate a manufacturing process for forming the exemplary photovoltaic device structure of FIG. 6. Referring to FIG. 10A, the substrate **10** includes a material that is transparent in the range of electromagnetic radiation at which photogeneration of electrons and holes occur within the photovoltaic structure as describe above. The transparent conductive material layer **20** is formed on the substrate **10**, for example, by deposition.

[0074] Referring to FIG. 10B, the Schottky-barrier-reducing layer **22** is deposited for example, by chemical vapor deposition, evaporation, or any other known methods of deposition. In case the Schottky-barrier-reducing layer **22** includes an allotrope of carbon, methods known in the art for forming such an allotrope of carbon can be employed. In case the Schottky-barrier-reducing layer **22** includes a transparent conductive material having a different dopant concentration than the transparent conductive material layer **20**, methods for forming the transparent conductive material layer **20** can be modified to alter the dopant concentration in the Schottky-barrier-reducing layer **22**.

[0075] Referring to FIG. 10C, the p-doped semiconductor layer **30** is deposited in a process chamber containing a semiconductor-material-containing reactant gas and a carrier gas. The p-doped semiconductor layer **30** is formed on the Schottky-barrier-reducing layer **22** in the presence of the semiconductor-material-containing reactant and the carrier gas in a chemical vapor deposition. In case the carrier gas includes hydrogen, the p-doped semiconductor layer **30** includes a hydrogenated p-doped semiconductor material. The chemical vapor deposition process can be plasma enhanced chemical vapor process (PECVD) performed at a deposition temperature from 50° C. to 400° C., and preferably from 100° C. to 350° C., and at a pressure from 0.1 Torr to 10 Torr, and preferably from 0.2 Torr to 5 Torr.

[0076] The semiconductor-material-containing reactant gas includes at least one atom of silicon, germanium, or a component semiconductor material of a compound semiconductor material such as GaAs. The p-type dopants in the p-doped semiconductor-containing material of the p-doped semiconductor layer **30** can be introduced by in-situ doping.

Alternately, the p-type dopants in the microcrystalline p-doped hydrogenated semiconductor-containing material can be introduced by subsequent introduction of dopants employing any method known in the art such as plasma doping, ion implantation, and/or outdiffusion from a disposable diffusion source (e.g., borosilicate glass).

[0077] The material of the p-doped semiconductor layer 30 can be a p-doped hydrogenated silicon-carbon alloy. In this case, a carbon-containing gas can be flown into the processing chamber during deposition of the p-doped hydrogenated silicon-carbon alloy.

[0078] Subsequently, the intrinsic semiconductor layer 40 is deposited on the p-doped semiconductor layer 30, for example, by plasma-enhanced chemical vapor deposition. In case the intrinsic semiconductor layer 40 includes an intrinsic hydrogenated semiconductor-containing material, hydrogen gas is supplied into the process chamber concurrently with a semiconductor-material-containing reactant gas. The intrinsic hydrogenated semiconductor-containing material can be amorphous or microcrystalline.

[0079] The n-doped semiconductor layer 50 is deposited on the intrinsic semiconductor layer 40, for example, by plasma-enhanced chemical vapor deposition. In case the n-doped semiconductor layer 50 includes an n-doped hydrogenated semiconductor-containing material, hydrogen gas is supplied into the process chamber concurrently with a semiconductor-material-containing reactant gas. The material of the n-doped semiconductor layer 50 can be amorphous or microcrystalline.

[0080] The n-type dopants in the n-doped semiconductor layer 50 can be introduced by in-situ doping. For example, phosphine (PH_3) gas or arsine (AsH_3) gas can be flown into the processing chamber concurrently with the semiconductor-material-containing reactant gas if the n-doped semiconductor layer 50 includes an n-doped silicon-containing material or an n-doped germanium-containing material. If the n-doped semiconductor layer 50 includes an n-doped compound semiconductor material, the ratio of the flow rate of the reactant gas for the Group II or Group III material to the flow rate of the reactant gas for the group VI or Group V material can be decreased to induce n-type doping. Alternately, the n-type dopants in the n-doped semiconductor layer 50 can be introduced by subsequent introduction of dopants employing any method known in the art.

[0081] The first back reflector layer 60 is deposited on the n-doped semiconductor layer 50 employing methods known in the art. The first back reflector layer 60 includes a transparent conductive material. The second back reflector layer 70 is subsequently deposited on the first back reflector layer 60, for example, by electroplating, electroless plating, physical vapor deposition, chemical vapor deposition, vacuum evaporation, or a combination thereof. The second back reflector layer 70 can be a metallic layer.

[0082] While the present disclosure has been particularly shown and described with respect to preferred embodiments thereof, it will be understood by those skilled in the art that the foregoing and other changes in forms and details can be made without departing from the spirit and scope of the present disclosure. It is therefore intended that the present disclosure not be limited to the exact forms and details described and illustrated, but fall within the scope of the appended claims.

What is claimed is:

1. A photovoltaic device comprising a stack of a transparent conductive material layer, a Schottky-barrier-reducing

layer contacting said transparent conductive material layer, and a p-doped semiconductor layer contacting said p-doped semiconductor layer, wherein a Schottky barrier across said stack has a lower contact resistance than a Schottky barrier across another stack that includes all layers of said stack less said Schottky-barrier-reducing layer.

2. The photovoltaic device of claim 1, wherein said Schottky-barrier-reducing layer is an optically transparent layer including an allotrope of carbon.

3. The photovoltaic device of claim 2, wherein said Schottky-barrier-reducing layer is a single wall carbon nanotube layer.

4. The photovoltaic device of claim 2, wherein said Schottky-barrier-reducing layer is a graphene layer.

5. The photovoltaic device of claim 1, wherein said Schottky-barrier-reducing layer includes a same material as said transparent conductive material layer and has a different doping than said transparent conductive material layer.

6. The photovoltaic device of claim 5, wherein said transparent conductive material layer includes an aluminum-doped zinc oxide having an aluminum doping at a first dopant concentration, and said Schottky-barrier-reducing layer includes an aluminum-doped zinc oxide having an aluminum doping at a second dopant concentration, wherein said first dopant concentration is greater than said second dopant concentration.

7. The photovoltaic device of claim 5, wherein said transparent conductive material layer includes a first fluorine-doped tin oxide having a fluorine doping at a first dopant concentration, and said Schottky-barrier-reducing layer includes a second fluorine-doped tin oxide having a fluorine doping at a second dopant concentration, wherein said first dopant concentration is greater than said second dopant concentration.

8. The photovoltaic device of claim 5, wherein said Schottky-barrier-reducing layer includes a material having a higher resistivity than a material of said transparent conductive material layer.

9. The photovoltaic device of claim 1, wherein said Schottky-barrier-reducing layer has a work function that is greater than a work function of said transparent conductive material layer and is lesser than an absolute value of a Fermi level of said p-doped semiconductor layer.

10. The photovoltaic device of claim 1, wherein a series resistance of said photovoltaic device is equal to or less than 9 Ohms-cm^2 .

11. The photovoltaic device of claim 1, wherein said p-doped semiconductor layer includes a hydrogenated p-doped semiconductor-containing material.

12. The photovoltaic device of claim 1, further comprising: an intrinsic semiconductor layer contacting said p-doped semiconductor layer; and an n-doped semiconductor layer contacting said intrinsic semiconductor layer.

13. The photovoltaic device of claim 12, wherein said intrinsic semiconductor layer includes a hydrogenated amorphous intrinsic semiconductor material.

14. The photovoltaic device of claim 12, wherein said n-doped semiconductor layer includes hydrogenated n-doped amorphous semiconductor material.

15. The photovoltaic device of claim 12, further comprising at least one back reflector layer located on said n-doped semiconductor layer.

- 16.** A method of forming a photovoltaic device comprising:
forming a transparent conductive material layer on a substrate;
forming a Schottky-barrier-reducing layer on said transparent conductive material layer; and
forming a p-doped semiconductor layer on said Schottky-barrier-reducing layer, wherein a Schottky barrier across a stack of said transparent conductive material layer, said Schottky-barrier-reducing layer, and said p-doped semiconductor layer has less contact resistance than a Schottky barrier across another stack that includes all layers of said stack less said Schottky-barrier-reducing layer.
- 17.** The method of claim **16**, wherein said Schottky-barrier-reducing layer is an optically transparent layer including an allotrope of carbon.
- 18.** The method of claim **17**, wherein said Schottky-barrier-reducing layer is a single wall carbon nanotube layer.
- 19.** The method of claim **17**, wherein said Schottky-barrier-reducing layer is a graphene layer.
- 20.** The method of claim **16**, wherein said Schottky-barrier-reducing layer includes a same material as said transparent conductive material layer and has a different doping than said transparent conductive material layer.

21. The method of claim **20**, wherein said transparent conductive material layer includes an aluminum-doped zinc oxide having an aluminum doping at a first dopant concentration, and said Schottky-barrier-reducing layer includes an aluminum-doped zinc oxide having an aluminum doping at a second dopant concentration, wherein said first dopant concentration is greater than said second dopant concentration.

22. The method of claim **20**, wherein said transparent conductive material layer includes a first fluorine-doped tin oxide having a fluorine doping at a first dopant concentration, and said Schottky-barrier-reducing layer includes a second fluorine-doped tin oxide having a fluorine doping at a second dopant concentration, wherein said first dopant concentration is greater than said second dopant concentration.

23. The method of claim **16**, wherein said Schottky-barrier-reducing layer includes a material having a higher resistivity than a material of said transparent conductive material layer.

24. The method of claim **16**, wherein said Schottky-barrier-reducing layer has a work function that is greater than a work function of said transparent conductive material layer and is lesser than an absolute value of a Fermi level energy of said p-doped semiconductor layer.

25. The method of claim **16**, wherein a series resistance of said photovoltaic device is equal to or less than 9 Ohms-cm².

* * * * *