

US 20130045049A1

(19) **United States**

(12) **Patent Application Publication**
Krzyzak

(10) **Pub. No.: US 2013/0045049 A1**

(43) **Pub. Date: Feb. 21, 2013**

(54) **PERMEABLE TRAFFIC BEARING
STRUCTURE**

Publication Classification

(71) Applicant: **Gerald Krzyzak**, Niles, IL (US)

(72) Inventor: **Gerald Krzyzak**, Niles, IL (US)

(73) Assignee: **Vulcan Materials Company**,
Birmingham, AL (US)

(21) Appl. No.: **13/661,590**

(22) Filed: **Oct. 26, 2012**

Related U.S. Application Data


(62) Division of application No. 12/713,306, filed on Feb.
26, 2010, now Pat. No. 8,297,874.

(51) **Int. Cl.**
E01C 5/22 (2006.01)
E01C 19/00 (2006.01)

(52) **U.S. Cl.** **404/31; 404/27; 404/75**

(57) **ABSTRACT**

A traffic bearing structure with a permeable pavement includes a subgrade, a base positioned on top of the subgrade, and a wear surface positioned on top of the base. The base includes aggregate compacted in a single lift, where the aggregate in the base includes different sized particles mixed together. The wear surface includes a permeable pavement. The particle size distribution of the aggregate in the base is selected to provide adequate stability and permeability for the permeable pavement.






FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5

PERMEABLE TRAFFIC BEARING STRUCTURE

[0001] This Patent Application is a divisional of U.S. patent application Ser. No. 12/713,306, filed on Feb. 26, 2010, now U.S. Pat. No. 8,297,874, the contents of which are incorporated by reference.

BACKGROUND OF THE INVENTION

[0002] a: Field of the Invention

[0003] This invention relates to traffic bearing structures such as roads and parking lots. In particular, this invention relates to traffic bearing structures having a permeable pavement for the wear surface.

[0004] b: Description of the Related Art

[0005] Traffic bearing structures have been used by man for many years. Some examples of traffic bearing structures include roads on which we drive and parking lots where we park. There are many different types of surfaces which can be used with a traffic bearing structure, and these top surfaces are often referred to as a “wearing surface” or a “wear surface.” Some examples include asphalt, concrete, block pavers, gravel, grass, and dirt. Harder wearing surfaces can support larger loads, reduce dust and dirt, and provide a smoother surface. Examples of harder wearing surfaces include asphalt, concrete, and block pavers, all of which can be referred to as pavement. Many users prefer harder wear surfaces, and are willing to pay more for them.

[0006] Historically, harder wear surfaces tend to be water-resistant or waterproof so that rainfall simply runs off, and does not soak in to any appreciable extent. When large areas are paved over with non-permeable wear surfaces, water from rainfall tends to collect quickly and large surges of water are seen in the stormwater systems adjacent to paved surfaces. Large surges of storm water can increase the chance of flash floods, and can carry trash, solids, pollutants, and debris to local waterways. In some locations, storm water is directed to waste water treatment plants, and storm water surges can overload the waste water treatment facility. The rapid run-off of rainfall from non-permeable paved surfaces is generally considered undesirable.

[0007] Certain regulations encourage the use of permeable pavements, where permeable pavements are pavements which allow water to permeate through the pavement. Some storm water regulations can require the use of holding ponds or filtration areas for new construction projects involving nonpermeable surfaces which cover a significant portion of the land. For example, if a new shopping center were to be installed and several acres of land were to be paved to provide parking, regulations may require a holding pond to collect and hold storm water runoff and thereby reduce the peak load of stormwater exiting the new shopping center. By providing a permeable pavement on the parking area, water that strikes and collects on the parking area tends to soak through the pavement and into the ground underneath. The base then serves to hold the water and allow it to slowly percolate into the earth underneath the base. This use of permeable pavement can reduce or eliminate the need for holding ponds which are regulatory required. By reducing or eliminating the need for holding ponds, more real estate is available to be developed. This can allow for more retail space and more parking, and provides a higher end use for the real estate. This allows more productive use of the land while still reducing the peak flows from stormwater.

[0008] A permeable pavement used in a traffic bearing structure, such as a parking lot, has to be able to handle the traffic load without being damaged. The permeable pavement has to be strong enough to support the cars, trucks and other vehicles traveling on the parking lot. Much of the strength of a permeable pavement comes from the base underneath it, and so a stronger, more stable base can increase the traffic load a permeable pavement can support. Roads tend to have heavier vehicles and higher traffic flow than parking lots, and often require higher load ratings. Providing a base which is strong enough to support the permeable pavement and yet capable of allowing water to flow through it can facilitate the use of permeable pavements in services which require higher load ratings, in many cases, permeable pavements have been used for driveways, certain parking lots, and other uses with limited load ratings.

[0009] The base underneath a permeable pavement is often an aggregate. Certain types of aggregate are known and available. One such aggregate is referred to as a dense graded base. Another type of aggregate available is an open graded base. The dense graded base tends to be very stable, but has relatively low permeability, whereas the open graded base tends to have higher permeability but less stability. The base used beneath many permeable pavements includes at least two different types of aggregate, where each type is independently compacted. Different types of aggregate can be differentiated by the size distribution of the particles within each type of aggregate. Providing a base which is permeable, strong, and stable for use with permeable pavements is desirable.

BRIEF SUMMARY OF THE INVENTION

[0010] A traffic bearing structure includes a subgrade, a base positioned on top of the subgrade, and a wear surface positioned on top of the base. The base includes aggregate compacted in a single lift, where the aggregate in the base includes different sized particles mixed together. The particle size distribution of the aggregate in the base is selected to provide adequate stability and permeability for the traffic bearing structure. The wear surface includes a permeable pavement.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0011] FIG. 1 is a cross sectional side view of one embodiment of a traffic bearing structure where the wear surface includes porous asphalt.

[0012] FIG. 2 is a cross sectional side view of an alternate embodiment of a traffic bearing structure including a drain line, where the wear surface includes block pavers.

[0013] FIG. 3 is a cross sectional side view of a traffic bearing structure embodiment with relatively uniform compaction of the aggregate in the base.

[0014] FIG. 4 is a cross sectional side view of a traffic bearing structure embodiment with a compaction gradient in the base, where the wear surface is porous concrete.

[0015] FIG. 5 is a schematic of screens used to size particles in an aggregate.

DETAILED DESCRIPTION OF THE INVENTION

[0016] Certain pavements have been developed which are permeable. The term “pavement” as used in this description refers to a surface designed and intended for vehicular traffic,

and does not include surfaces designed and intended for only pedestrian traffic, such as surfaces for athletic competition. These permeable pavements include porous concrete, porous asphalt, block pavers, and turf pavers. Water can pass through these permeable pavements and enter the base underneath. This slows the runoff of water and reduces the load on the adjacent stormwater systems. This can reduce peak loads on wastewater facilities when stormwater is directed to these wastewater facilities, and it can also help to improve the quality of local waters by reducing the influx of trash, solids, pollutants, and debris. When water passes through a permeable pavement and then infiltrates into the ground, the ground serves as a filter and tends to clean the water.

[0017] In order to reduce the amount of runoff from a permeable pavement, it is desired that the pavement not have too steep of an angle. This allows the water to remain on the pavement for a longer period and provides more time for the water to soak through the permeable pavement and into the base underneath. Typically, permeable pavement manufacturers recommend that the angle on a permeable pavement not exceed five degrees, although other angles are possible, and the permeable pavement will function as a traffic bearing surface even if this angle is exceeded. Also, many permeable pavement manufacturers recommend that the traffic bearing structure be installed such that soil, dirt and trash from neighboring areas do not wash onto the permeable pavement. This soil and dirt can infiltrate into the permeable pavement such that water flow through the pavement is slowed or even stopped. Permeable pavements typically have interconnected pores which allow water to work its way through the permeable pavement and be pulled down into the base by gravity. Dirt or other solids can clog some of these interconnected pores and slow or block the flow of water through the permeable pavement.

Traffic Bearing Structures

[0018] Traffic bearing structures for supporting vehicles are familiar in the United States. A traffic bearing structure **10** is often placed on a land surface such that one can walk from the traffic bearing structure **10** directly onto the adjacent land **12**, as seen in FIG. 1. The land **12** can be a wide variety of different things, including the lawn in front of a house, the fields on the side of the road, and a ditch next to a parkway. The land **12** can be sand, dirt, clay, rocks, or a wide variety of other things. The land **12** includes basically anything adjacent to a road, parking lot, or other traffic bearing structure **10**. “Traffic bearing structures” are defined to include structures designed and built to support vehicles having wheels, so traffic bearing structures **10** can include roads, parking lots, bridges, tunnels, and other structures which are designed for bearing vehicular traffic,

[0019] A traffic bearing structure **10** generally has at least three primary components. This includes the subgrade **14**, the base **16** and the wear surface **18**. The subgrade **14** can be basically the land **12**, which has been graded and prepared for use as a subgrade **14**, but the subgrade **14** can also be added material which provides a lower foundation for the traffic bearing structure **10**. This added material for the subgrade **14** can be aggregate, or it can be clay, dirt, or a wide variety of other materials which are placed on the ground to provide a foundation for the traffic bearing structure **10**.

[0020] The base **16** is typically comprised of aggregate **20**, where “aggregate” is defined to include a collection of particles **28**. The aggregate **20** is generally compacted in what is

referred to as a lift **26**. Typically, the aggregate **20** is laid down in a layer as a loose fill, leveled and smoothed, and then compacted. A lift **26** is produced when a single layer of aggregate **20** is compacted. Sometimes, different grades of aggregate **20** will be combined in the base **16**, and these are typically compacted separately. So on occasion, adjacent lifts **26** will have a distinction between one size aggregate **20** and another size aggregate **20**, as seen in the two separate lifts **26** in FIG. 1. Reference to the size of an aggregate **20** refers to the distribution of the size of the particles **28** which make up the aggregate **20**. However, in other embodiments, the same aggregate **20** material will be combined and compacted in more than one layer and more than one lift **26** as the roadway or the traffic bearing structure **10** is built. In this description, a lift **26** is referred to as each time the loose material is added and compacted, regardless of whether the aggregate **20** is the same size or different than the previous layer.

[0021] The current invention includes a wear surface **18** which is a permeable pavement **22**. This means the permeable pavement **22** allows water to flow through at a sufficient rate to minimize the runoff of water into adjacent stormwater handling systems. As a general rule of thumb in this description, a pavement is considered permeable if it has a permeability rate for water at least equal to 10 feet per day.

[0022] When it rains or when water is applied to a permeable pavement **22**, the water can go into a drainage system which results in a more gradual release of the water. Different drainage options are available for different traffic bearing structures **10** using permeable pavements **22**. In one embodiment, the water slowly percolates into the subgrade **14**, and exits from underneath the traffic bearing structure **10**. In another embodiment shown in FIG. 2, a drain line **24** can be included in the base **16** and/or subgrade **14** such that water is able to collect in the drain line **24** and flow out of the traffic bearing structure **10** through the drain line **24**. Using a single lift **26** over a drain line **24** can increase the depth of material between the compactor and the drain line **24**, and thereby reduce damage to the drain line **24** during compaction.

[0023] In yet another embodiment, one or more weirs can be included in and/or adjacent the traffic bearing structure **10** such that water will overflow from the weirs and be gradually released to the environment. A weir can be used to supplement other drainage techniques such as drainage into the subgrade **14**, or drainage with the drain line **24**. The use of a drain line **24**, a weir, drainage into the subgrade **14**, or any other water draining device or technique can be used in isolation or in combination, as desired.

[0024] The base **16** underneath the permeable pavement **22** generally serves as a storage area for water. The storage capacity of the base **16** must be large enough to hold the collected water and allow this water to be gradually released into the environment, such as by absorbing into the subgrade **14**. The water storage capacity of the base **16** must take into consideration the rate at which water leaves the base, such as the absorption rate of the subgrade **14**, the drain rate of any drain lines **24** or weirs, or any other mechanism used for allowing the water to exit from the base **16**. The water holding capacity of the base **16** also must consider the application rate of the water. For example, certain areas will receive more water than other areas, and rain will fall more rapidly in some areas. The rate at which water permeates into the base and the rate at which water exits the base must be considered in the design of traffic bearing structures **10**. A traffic bearing structure **10** in an area which tends to receive several inches of rain

within an hour will typically need a base **16** which is able to hold more water than a traffic bearing structure **10** in an area which seldom receives more than half an inch of rain at a time. The required water storage volume can be determined during the permeable pavement **22** design. Required thickness of the base **16** can be determined, in part, by using the anticipated percent voids in the base **16** at a specified density.

[0025] The water holding capacity of the lift **26** underneath the permeable pavement is generally determined by the depth of the lift **26** and also the porosity of the lift **26**. A more porous lift **26** has more open space and is able to hold more water, and a deeper lift **26** has more room for the water to accumulate. Two methods to increase the water holding capacity of a base **16** include increasing the depth of the base **16**, and increasing the void space in the base **16**. The minimum thickness of the base **16** can be calculated based on the required water storage capacity, the area of the traffic bearing surface **10**, and the porosity of the aggregate **20**. Alternative techniques can be used, such as providing a lift **26** which extends beyond the sides of a permeable pavement **22**, to increase the water holding capacity of the base **16**.

[0026] In order to facilitate the permeability of a permeable pavement **22**, the lift **26** positioned underneath the permeable pavement **22** should have a permeation rate at least as high as the permeation rate of the permeable pavement **22**. This allows water to drain out of the permeable pavement **22** into the lift **26** as fast as water will pass through the permeable pavement **22**. If the permeation rate of the lift **26** was slower than the permeable pavement **22**, water would collect at the interface and slow the rate at which water flowed through the permeable pavement **22**.

[0027] The top layer of a traffic bearing structure **10** is referred to as the wear surface **18**. There can be objects on top of the wear surface **18**, such as paint **42** or parking curbs **44**, and the material under the paint is still the wear surface **18**. Permeable pavement **22** is one type of wear surface **18**, because permeable pavement **22** is frequently used as the top layer of a traffic bearing structure **10**. One type of permeable pavement **22** is a block paver **30**. Block pavers **30** are generally a type of pavement which includes a plurality of solid blocks placed near each other to make a wear surface **18**. The individual block pavers **30** of a block paver **30** surface can include rocks, bricks, ceramics, interlocking tiles, or a wide variety of other materials. The individual block pavers **30** can be permeable and allow water to pass through the block paver **30** itself, but it is also possible to have non-permeable individual block pavers **30** that still provide a permeable pavement **22**. This is possible because the gaps between adjacent block pavers **30** can be filled with a permeable gap filling material **32**. This gap filling material **32** can be sand, small aggregate **20**, or other similar materials which serve to fill the space between individual adjacent block pavers **30**. Runoff that hits a nonpermeable block paver **30** drains to the gap between adjacent block pavers **30**, percolates down through this gap-filling material **32**, and thereby enters the base **16**. The gap filling material **32** is considered part of the wear surface **18**, and not part of the base **16**.

[0028] Another type of permeable pavement **22** is porous asphalt **38**, as seen in FIGS. 1 and 3. This is a type of asphalt which has interconnected voids such that water can percolate through the porous asphalt **38**. Porous asphalt **38** can be made by using different size stones and/or different types of binding material from those used in non-permeable asphalts. For example, screening out the fines from standard bituminous

asphalt can increase the void space and make the asphalt permeable. Yet another type of permeable pavement **22** is a porous concrete **40**, as seen in FIG. 4, with continuing reference to FIGS. 1-3. As with the porous asphalt **38**, the porous concrete **40** has interconnected voids for allowing water to pass, and the porous concrete **40** can be formed by using different size aggregates **20** and/or different amounts and/or types of binder between the aggregates **20**. Turf pavers are yet another type of permeable pavement **22**. Turf pavers include a support system for bearing weight, where the support system provides gaps where grass or other plants can grow. Porous asphalt **38**, block pavers **30**, and turf pavers can be more flexible than porous concrete **40**, and so there can be somewhat different requirements for the base **16** under each surface. The requirements of the base **16** depend somewhat on the wear surface material used.

[0029] A traffic bearing structure **10** has many uses. This includes parking lots, roads, and other surfaces which are designed for supporting vehicles and traffic. The strength of the traffic bearing surface **10** depends largely on the support underneath the wear surface **18**. Greater support from the base **16** is required for wear surfaces **18** which will be exposed to higher traffic loading. Higher traffic loading can be the result of heavier vehicles and/or more frequent vehicle traffic or movement. Permeable wear surfaces **18** used for non-vehicular traffic typically require less stability and less strength. It is also generally noted that most roads have a higher traffic loading requirement than parking lots. However, the exact traffic loading requirement for a particular project can be specified, and can vary from place to place and from one use to another.

Subgrade

[0030] Subgrade **14** is generally the bottom layers or the lowest layer of a traffic bearing surface **10**. The subgrade **14** can be the natural soil which has been excavated, cleared or formed in some way to the desired shape for the traffic bearing structure **10**. It is possible the soil or ground can be used in its natural existing shape without any grading depending on the needs for the traffic bearing structure **10** and the shape and composition of the land **12** at that particular location. It is also possible to add some material to form a subgrade **14**. This can include the addition of aggregate **20**, clay, sand, or some other material.

[0031] In many cases, it is desirable for the subgrade **14** to be permeable to water at least at some rate when designing a traffic bearing structure **10** using permeable pavement **22**. However, it is also possible to make a permeable pavement **22** with a nonpermeable subgrade **14**. Water can be stored in the base **16** and leave the base **16** through water drain lines **24**, weirs, or even through the use of capillary action and the evaporation of water from the surface of the permeable pavement **22**. The subgrade **14** can be compacted or it can be left as graded. This includes when the subgrade **14** is added aggregate **20**, clay or other material, or when the subgrade **14** is the natural soil which has been graded to the desired shape. Compacting the subgrade **14** can reduce the permeability while increasing the stability and strength. A permeable subgrade **14** may be desirable for permeable pavements, so little or no compaction of the subgrade may be desired.

[0032] The subgrade **14** generally does not provide the strength and stability for the wear surface **18** as much as the base **16**. In some instances, the subgrade **14** is considered non-structural, in that it is not a primary component for bear-

ing the weight placed on the wear surface **18**. Providing a stable base **16** can allow for a subgrade **14** which has not been compacted.

Base

[0033] The base **16** is the material positioned between the wear surface **28** on the top and the subgrade **14** on the bottom of the traffic bearing structure **10**. In some embodiments, the base **16** is comprised of at least one sized aggregate **20**. When used with a permeable pavement **22**, the base **16** is often used to hold water until accumulated water can be gradually discharged. The base **16** frequently has a structural function and provides strength for the wear surface **28**, but it is possible to have components of the base **16** which are not structural and are primarily used for permeability or for other purposes. The base **16** under a permeable pavement **22** serves the dual functions of providing stability and permeability. The base **16** under a non-permeable pavement may not require the same level of permeability to function properly.

[0034] The base **16** generally provides much of the strength and stability of the wear surface **28**. A certain strength and stability is needed to support vehicular traffic, and greater stability and strength can support higher traffic loading. The minimum stability and permeability is often specified for a particular traffic bearing structure. Higher traffic loading means loadings of heavier vehicles and/or more vehicles passing a point of the traffic bearing structure **10**. As a general rule, roads tend to require more stability than parking lots, although there can be exceptions. The base **16** under a permeable pavement **22** should provide both the necessary stability and the permeability necessary to support the traffic and to allow water to drain from the permeable pavement **22** and to be temporarily stored within the base **16**.

[0035] The base **16** is generally produced by adding a loose material such as an aggregate **20**, and then compacting that aggregate **20** into a lift **26**. The lift **26** can be compacted with vibratory devices, and this can produce a relatively consistent compaction throughout the lift **26**. The vibratory devices vibrate as they compact, and this can cause the lift **26** to become more compacted from the bottom up instead of from the surface down. This can also result in a lift **26** which has a relatively consistent compaction percentage throughout the depth of the lift **26**.

[0036] In some embodiments, a lift **26** is compacted without the use of vibratory devices. This can include the use of rollers or other compaction devices, as is known in the art. This can produce a lift **26** which has a compaction gradient **34**. Generally, a compaction gradient **34** is characterized by material near the top of the lift **26** being more compacted than material near the bottom of the lift **26**, as seen in FIGS. 1 and 4. More compacted aggregate **20** has less void space between the particles **28** than less compacted aggregate **20**. A compaction gradient **34** can involve a gradual lessening of the degree of compaction as one moves from the top to the bottom of the lift **26**. This allows one to inspect a traffic bearing structure **10** and determine the number of lifts **26** used in a base **16**. The different degrees of compaction in a compaction gradient **34** allow one to identify the different lifts **26** in a base **16** similar to the growth rings in a tree, because there is a physical difference in a base **16** depending on the number of lifts **26**.

[0037] If different types of aggregate **20** are used in a base **16**, they are often compacted separately, as seen in FIG. 1. In some embodiments, a geo-fabric or other material can be placed between different sized aggregates **20** to control par-

ticle migration. Therefore, a coarser aggregate **20** may be used underneath a finer aggregate **20**, and there would typically be at least two lifts **26** where the coarse aggregate **20** was compacted before the finer aggregate **20** was added, and then the finer aggregate **20** would be compacted afterwards. In some embodiments, a geo-fabric is not used, including some embodiments where only one sized aggregate **20** is used.

[0038] The act of compacting a lift **26** takes time and increases the overall installation cost of a traffic bearing structure **10**. The time and effort of preparing the aggregate **20** before compaction such that you have a relatively uniform surface and depth, and then the actual act of compacting the lift **26** each require time and effort. Increased construction time generally causes increased installation costs because this involves the payment of personnel and the use of equipment. A technique which reduces the number of lifts **26** and still produces a viable and functional traffic bearing structure **10** can reduce the overall cost of installing the traffic bearing structure **10**. The use of a single lift **26** in the base **16** can also provide more uniform water permeation, because the water does not pass through multiple compaction gradients in the base **16**.

[0039] In many cases, the degree of compaction for a base **16** and for each lift **26** can be specified. For example, in one embodiment using a permeable pavement **22**, the base **16** is comprised of one single lift **26**. This one single lift **26** can be compacted to between 90 and 95 percent. This compaction standard of 90 to 95 percent can be determined by the standard Proctor compaction test, ASTM test method D 698 (07), but other test methods are available, such as the AASHTO T 99 (09) test. Particular versions of a test can also be provided, so consistency can be maintained regardless of changes in a testing version, and the (07) and (09) listed after the test methods above represent the version of the test. The version can be based on the year the test was revised, so ASTM D 698 (07) indicates the ASTM D 698 test as revised in 2007. ASTM, which was originally known as the American Society for Testing and Materials, provides many standard test methods for various materials so different entities have a common measure for comparison purposes. Alternatively, a lift **26** can be compacted to the density necessary to achieve a required minimum stability with a required permeability.

[0040] In general, the greater the degree of compaction, the less the degree of void space remaining within the lift **26**. As a general rule of thumb, the less void space available in a lift **26**, the lower the permeability rate of the lift **26** and the higher the strength and stability of the lift **26**. Alternatively, the greater the void space within a lift **26**, the higher the permeability of the lift **26** and the lower the stability and strength of the lift **26**. Therefore, the use of certain sized aggregate **20** can provide a desired range of strength, stability and permeability, but this is at least somewhat dependent on the compaction standard used. In one embodiment of the current invention, if the aggregate **20** is compacted less than 80%, the void space may be too large and the strength and stability of the lift **26** can be less than specified. If the compaction is greater than 95%, the void space can be reduced to the point where the permeability rate is no longer acceptable, and the water holding capacity of the lift **26** is reduced to a point beyond that desired. Therefore, the degree of compaction required can depend on the required stability and permeability, so specifying stability and permeability can effectively dictate the degree of compaction for a particular aggregate **20**.

Aggregate

[0041] “Aggregate” **20** is generally defined as a collection of hard particles **28**. In many instances, the particles **28** are rock or stone, but it is also possible to use other materials such as shells, broken bricks, broken ceramic, cast ceramic, metal, or other materials. As a general rule, there are three broad families of aggregate **20** used in the construction of traffic bearing structures **10**. The first family is referred to as well-graded. A well-graded aggregate **20** includes particles **28** of varying sizes, and the ratio of the particles **28** of the varying sizes are somewhat proportional. With well-graded aggregate **20**, the larger the top particle size, the stronger and more stable the aggregate **20** tends to be. The various particle sizes can be essentially uniformly mixed in a well graded aggregate **20**, so a sample taken from one location has essentially the same particle size distribution as a sample taken from another location.

[0042] A second type of aggregate **20** is referred to as uniform gradation aggregate **20**. With a uniform gradation aggregate **20**, essentially all of the particles **28** are approximately the same size. The particle size is relatively consistent with uniform gradation. In some embodiments, the void space does not change significantly based on particle size. For example, for perfectly round particles **28**, the overall void space is approximately the same for large particles **28** or small particles **28**. For example, a container of basketballs will have approximately the same void space as the same container of ping pong balls, where the void space refers to the space between the balls as opposed to the space within them. The higher the void space, the lower the stability tends to be, and vice versa. As a general rule, it is unusual to find a uniform gradation aggregate **20** with a high stability.

[0043] A third type of aggregate **20** is referred to as gap graded. A gap graded aggregate **20** is a collection of particles **28** of various sizes, but there is a gap in the particle size distribution. This means that a particular size of particle **28** in the middle of a particle distribution tends to be missing. So for example, if an aggregate **20** had 25% size 1 particles, 25% size 2 particles, 0% size 3 particles, 25% size four particles, and 25% size five particles, this would be referred to as gap graded, where the particles **28** increase in size from one to five.

[0044] Particles **28** are generally sized based on the mass percentage of an aggregate **20** that will pass through different sized screens, as seen in FIG. 5, with continuing reference to FIGS. 1-4. The entire mass of the aggregate **20** will be dumped onto the first screen **36**, which is the largest size screen, and the particles **28** that do not pass through are collected, and can be weighed. The particles **28** that do pass through the first screen **36** fall to the second screen **37**. The particles **28** on the second screen **37** are then sorted based on the size of the screen, where the second screen **37** will have smaller gaps than the first screen **36**. Some particles **28** which were able to pass through the first screen **36** are too big to pass through the second screen **37**. These particles **28** are then separated and collected, and can then be weighed. The particles **28** that pass through the second screen **37** can go through another screen, and this can be repeated, for as many screens as desired.

[0045] One particular aggregate **20** has been found which is very desirable for use in the base **16** under permeable pavements **22**. This aggregate **20** has some rather loose specifications, as will be described later, and fits within the well graded aggregate family. This aggregate **20** serves the dual functions

of providing stability and permeability in a base **16**, and is referred to as “dual purpose aggregate” **20** in this description. The dual purpose aggregate **20** has some particles too large to pass through a 12 millimeter screen, and some particles small enough to pass through a 5 millimeter screen. In another embodiment, the dual purpose aggregate **20** has some particles too large to pass through a 12 millimeter screen, and some particles small enough to pass through a 1.2 millimeter screen.

[0046] In another embodiment, essentially all particles in the dual purpose aggregate **20** pass through a 37.5 millimeter screen, 90 to 100% of the particles **28** pass through a 25 millimeter screen, 60 to 90% of the particles **28** pass through a 12.5 millimeter screen, 30 to 70% of the particles **28** pass through a 4.75 millimeter screen, 7 to 40% of the particles **28** pass through a 1.18 millimeter screen, 0 to 25% of the particles **28** pass through a 0.425 millimeter screen, and 0 to 4% of the particles **28** pass through a 0.075 millimeter screen. Converting this to English units, approximately 100% of the particles **28** pass through a 1.5 inch screen, 90 to 100% of the particles **28** pass through a one-inch screen, 60 to 90% of the particles **28** pass through a ½ inch screen, 30 to 70% of the particles **28** pass through a number 4 mesh screen, 7 to 40% of the particles **28** pass through a number 16 mesh screen, 0 to 25% of the particles **28** pass through a number 40 mesh screen, and 0 to 4% of the particles **28** pass through a number 200 mesh screen.

[0047] Other general specifications which may apply to the dual purpose aggregate **20** are listed in the table below. These specifications may vary somewhat for different quarries or sources of aggregate.

Property	ASTM test method (version)	Measurement
Sulfate Soundness	C 88 (05)	15% max. loss (Na), 20% max. loss (Mg)
Clay Lumps	C 142 (04)	2.0% Maximum
LA Degradation	C 131 (06)	60% loss maximum
Crushed faces	D 5821 (06)	75% minimum with 2 crushed faces

[0048] With a well-graded aggregate **20**, the large particles **28** tend to provide permeability and relatively high void space. Smaller particles **28** tend to fill in these voids and provide increased stability. As a general rule, increased stability comes with decreased permeability and water storage. Careful selection of the particle size distribution can result in an aggregate **20** which is capable of providing the stability necessary for a permeable pavement **22** for use as a traffic bearing structure **10** and still provide the permeability necessary for water to permeate into the base **16** at an acceptable rate.

[0049] The term “stability,” as used in this description, is defined by particular tests which measure the stability. One such test is the California Bearing Ratio (CBR) test, and another test is the R value test. The ASTM test method D 1883 (07) describes the CBR test, and ASTM test method D 2844 (07) describes the R value test. The R value test is also described in the CalTrans Test 301 (00), the AASHTO T 190 (09), and other standard test methods are also available. The CBR test is also described in AASHTO T 193 (07). The number provided in brackets “()” after a referenced test

method in this description refers to the year of the latest revision, so ASTM D 1883 (07) means the ASTM D 1883 test as revised in 2007.

[0050] Selecting the proper particle size distribution can provide a dual purpose aggregate **20** with a CBR stability of at least 40, as measured by the ASTM test D 1883 (07), and a permeation rate of 30,000 millimeters per day, as measured by ASTM test D 2434 (06). Alternatively, a dual purpose aggregate **20** can be provided with a CBR stability of at least 25 and a permeability of at least 8,500 millimeters per day, using the same tests mentioned above. The stability and permeation rate are determined after a bed of the dual purpose aggregate **20** has been compacted into a lift **26**. The dual purpose aggregate **20** can therefore have an essentially known void space after the proper compaction, so a specification for the void space after compaction can be established. The dual purpose aggregate **20** can have at least 25% voids after compaction, as measured by the ASTM 698 (07) test. Alternatively, the dual purpose aggregate **20** can have a void specification of 30% after compaction, using the same test method. This lift **26** can be a single lift **26** placed directly on top of the subgrade **14**, and the wear surface **18** can be placed directly on top of the single lift **26**, so the single lift **26** directly contacts both the subgrade **14** and the wear surface **18**.

[0051] It has been found that the stability provided by the dual purpose aggregate **20** is sufficient to support a stake pounded into the dual purpose aggregate **20** after compaction. Stakes can be used as edge restraints during construction projects. It has also been found that after compaction, the dual purpose aggregate **20** is stable enough to support vehicular traffic without creating wheel ruts, and this can be beneficial for placing the permeable pavement **22**. The increased stability may decrease the required thickness of the permeable pavement **22** in the wear surface **18**, which can save on costs for the traffic bearing structure **10**.

[0052] By selecting the proper particle size distribution for the dual purpose aggregate **20**, it has been found that an increased stability can be combined with an acceptable permeability when the aggregate **20** is compacted in a single lift **26**. The exact specifications for the particle size distribution can vary for different products. For example, in a quarry which collects and crushes limestone for dual purpose aggregate **20**, the particle size distribution may be different than a quarry which collects and crushes granite for use in a dual purpose aggregate **20**. Many factors can impact the properties of an aggregate **20**. These include the particle size and the particle shape, where round particles **28** will act differently than cubical particles **28**, which will act different than any other shapes. Essentially cubically shaped particles **28** can be preferred to essentially round or needle shaped particles **28** in the dual purpose aggregate **20**. Many other factors can influence the particle size distribution for the dual purpose aggregate **20** which provides the desired stability and permeability when compacted to the specified level. The factors include the material of the particle **28**, the strength of the particle **28**, the coefficient of friction of the particle **28**, the specific gravity of the particle **28**, the surface texture of the particle **28**, and other properties. Different starting materials can result in different particle size distribution specifications to meet the permeability and stability specifications for the dual purpose aggregate **20**.

[0053] It is generally found that a permeation rate of at least 30,000 millimeters per day as measured by the ASTM D 2434 (06) test can be combined with the CBR stability of at least 40

as measured by the ASTM D 1883 (07) test, and this can be done by selecting the particle size distribution from a particular quarry. In an alternative embodiment, a permeation rate specification of at least 8,500 millimeters per day combined with a CBR stability specification of at least 25 can be obtained. The stability and permeation rate are established when the dual purpose aggregate **20** is compacted to a specified level, which is generally between a standard Proctor value of about 90% and 95% compaction as measured by the ASTM D 698 (07) test. However, in other embodiments, the compaction level is the amount of compaction necessary to obtain both the permeability and stability requirements. Too much compaction can decrease the void spaces in the dual purpose aggregate **20** and may lower the permeability to an unacceptable rate. Also, too little compaction can leave excessive void spaces and lower the stability to an unacceptable level.

[0054] The specification can require compaction be performed by rollers, as opposed to being performed by vibratory compaction equipment, but in some embodiments vibratory compaction may be acceptable. The type, weight, and number of rollers should be sufficient to obtain the required density, and the required permeability and stability. Caution should be taken when using vibration to avoid aggregate fracture. The degree of compaction can be determined using conventional methods including, but not limited, nuclear density gauge and non-nuclear devices.

[0055] Certain compaction techniques can provides a compaction gradient. A compaction gradient can be desirable because the higher portions of the lift **26** are more compacted, and therefore have less void space. The more compacted higher portions of the lift **26** are closer to the wear surface **18**, and provide increased stability directly underneath the wear surface **18**. The lower portions of the lift **26** are less compacted, have more void space, and provide for greater water holding capacity and permeability. The stability of the lower portions of the base **16** is not as important as the stability of the upper portions of the base **16**, because of the proximity to the wear surface **18**. As with the particle size distribution, the exact compaction specified can vary for different raw materials, and the compaction specification is determined in conjunction with the particle size specification for each different raw material.

[0056] Generally, each individual quarry will have at least somewhat different raw materials, and testing may be required for each quarry to determine the particle size distribution specification and the compaction specification necessary for the dual purpose aggregate **20** to have the desired stability and permeation rate. Other factors that can be considered include the hardness and/or the durability of the aggregate particle **28**. By preparing an aggregate **20** material with a pre-set particle size distribution and testing this aggregate **20** material, the particle size distribution that is necessary to give the required specifications for any particular quarry can be experimentally determined.

[0057] In general, increasing the size of the largest particles **28** will increase the strength, hardness and durability of the dual purpose aggregate **20**. Increasing the percentage of smaller particles **28** will increase the stability of the dual purpose aggregate **20**, decreasing the percentage of the smaller particles **28** will increase the permeability of the dual purpose aggregate **20**, and vice versa. Increasing the percentage of larger particles **28** will tend to increase permeability and decrease stability, and vice versa. Increases of the per-

centage of larger intermediate sized particles **28** will increase permeability and decrease stability, but to a lesser extent than increases in the largest sized particles **28**. Increases in the percentage of the smaller intermediate particles **28** tends to increase stability and decrease permeability, but to a lesser extent than increases in the percentage of the smallest particles **28**.

[0058] Overall, the specification for the particle size distribution should be set somewhat proportionally for the various sizes, because a relatively proportional particles size distribution tends to provide a better balance of dual purpose aggregate properties. The coefficient of uniformity (C_u) can be set to be greater than or equal to 5. $C_u = D_{60}/D_{10}$, where D_{60} and D_{10} are the particle grain diameters corresponding to 60 and 10 percent passing respectively. Product grading can be plotted on a 0.45 power graph with the maximum density line (MDL) drawn from the zero ordinate through the maximum aggregate size. Grading can be set to plot as an "S-shaped" curve by deviating above and below the MDL at large and smaller aggregate sizes, respectively. Grading can also be set so the grading lot only crosses the MDL once.

[0059] By performing specific tests on material taken from a quarry, a set particle size distribution can be found which provides the desired specifications for stability and permeability of the dual purpose aggregate **20**, where both properties are determined at a specified compaction ratio. Specifications can also be set for the hardness and durability of the various aggregate particles **28**. Increased hardness can increase both the permeation rate and the stability of an aggregate **20** by minimizing the number of broken or crushed particles **28**.

[0060] As a nonlimiting example, it has been found that one specific quarry, the quarry located in McCook, Ill., which was owned and operated by Vulcan Materials Company as of January, 2010, has produced an aggregate **20** with the following particle size distribution, or gradation.

Screen size in English units	Screen size in millimeters	Measured percentage
1½"	37.5 mm	100
1"	25 mm	98.3
¾"	19 mm	90.2
⅝"	16 mm	81.8
½"	12.5 mm	70.5
⅜"	9.5 mm	59.2
¼"	6.3 mm	45.7
#4	4.75 mm	37.4
#8	2.36 mm	23.7
#16	1.18 mm	14.6
#40	0.425 mm	7.9
#200	75 μm	3.44
PAN	0 μm	0

"represents inches.

mm represents millimeters.

μm represents micrometers.

[0061] Testing has been performed on aggregates taken from this quarry in McCook, Ill. Typical results include a CBR stability of 25 with a permeability of 1000 feet per day at a compacted density of approximately 90%, and a CBR stability of 40 with a permeability of 800 feet per day at a compacted density of approximately 90%, as measured by ASTM D 1883 (07), ASTM D 2434 (06), and ASTM D 698 (07). The type of stone primarily available at this quarry is dolomite.

[0062] The use of the dual purpose aggregate **20** as described herein allows the production of a traffic bearing structure **10** using permeable pavement **22** for the wear surface **18**, where the traffic bearing structure **10** has a base **16** with one single lift **26**. This also allows the use of permeable pavement **22** with traffic bearing structures **10** having a load requirement of in excess of that typically experienced on driveways and parking lots. In an alternate embodiment, the dual purpose aggregate **20** as described herein can be a top lift **46** positioned over at least one lower lift **48**, where the top lift **46** and lower lift **48** are both in the base **16**. The lower lift **48** can include a different, larger average sized aggregate **20** than the dual purpose aggregate **20**. The larger sized aggregate **20** of the lower lift **48** can provide larger void spaces for holding water and for increased permeability, and the dual purpose aggregate **20** in the top lift **46** provides the stability for relatively high traffic loading requirements with an acceptable permeability. In yet another embodiment, the dual purpose aggregate **20** as described herein can be used repeatedly in multiple lifts **26** within one base **16**.

Method of Installation

[0063] The traffic bearing structure **10** using a permeable pavement **22** can be installed as described below. The first step is the preparation of a subgrade **14**. This can be done by leveling an area with grading, smoothing this area, and preparing this area to have the general shape of the desired traffic bearing structure **10**. Preferably, the subgrade **14** should have a maximum gradient of 5%, although higher percentages are allowable with the understanding that increased water runoff may result. Methods for draining water can then be laid out on top of the subgrade **14** or embedded at least partially within the subgrade **14**. This can include drain lines **24**, pipes or tubes which can be perforated to allow the inflow of water. There can be fabric covers over these drain lines **24** to reduce the inflow of debris and dirt into these drain lines **24**. The preparation of the subgrade **14** can also include the preparation of weirs or other devices which will allow water to percolate out of the base **16** which will be positioned on top of the subgrade **14**. The subgrade **14** can be compacted to a specified compaction ratio, or left uncompacted.

[0064] The next step is to pour loose dual purpose aggregate **20** on top of the subgrade **14**. The loose dual purpose aggregate **20** should be applied and used with techniques that tend to avoid the differentiation by size of the various particles **28** within the dual purpose aggregate **20**, as is understood by those knowledgeable in the art. The next step is to grade the loose dual purpose aggregate **20** to a relatively level and smooth surface. This level and smooth surface may impact the surface structure of the permeable pavement **22**, so care should be taken to provide an acceptable surface.

[0065] The next step is to compact the dual purpose aggregate **20** in a single lift **26**. This can involve repeated passes with a compactor, but it does not involve the addition of more aggregate **20**. The compaction should be performed until the dual purpose aggregate **20** reaches the proper compaction ratio, which can be determined using ASTM test D 698 (07). After the dual purpose aggregate **20** is compacted, the permeable pavement **22** is added on top of the dual purpose aggregate **20**. Installation of the permeable pavement **22** can involve the use of motorized equipment on top of the dual purpose aggregate **20**, and the stability of the compacted dual purpose aggregate **20** can facilitate this traffic.

[0066] Different permeable pavements **22** can be placed on top of the dual purposes aggregate **20**. The step of installing the permeable pavement **22** can include placing block pavers **30** in position. The block pavers **30** can be interlocking, but they may not be interlocking. Installation of the permeable pavement **22** can also include filling the gaps between block pavers **30** with a gap filling material **32**. In an alternate embodiment, porous asphalt **38** can be applied on top of the base **16** as the permeable pavement **22**, where the porous asphalt is used in place of the block pavers **32**. The porous asphalt **38** is applied in a similar manner to standard, non-permeable asphalt. In yet another embodiment, a porous concrete **40** can be applied as the permeable pavement **22** and again, the application of the porous concrete **40** is similar to the application of standard, non-permeable concrete. Another possible embodiment includes installing turf pavers, using techniques provided by the manufacturer or techniques known to those skilled in the art. It is possible to apply one type of permeable pavement **22** on top of another, as desired.

[0067] While the invention has been described with respect to a limited number of embodiments, those skilled in the art, having benefit of this disclosure, will appreciate that other embodiments can be devised which do not depart from the scope of the invention as disclosed here. Accordingly, the scope of the invention should be limited only by the attached claims.

What is claimed is:

1. A traffic bearing structure comprising:
a subgrade;
a base positioned on top of the subgrade, where the base includes a top lift compacted to between 90 and 95% as measured by the ASTM D 698 (07) test, where the top lift includes aggregate having varying particle sizes such that essentially all the particles will pass through a 37.5 millimeter screen, some of the particles will not pass through a 12 millimeter screen, and some of the particles will pass through a 5 millimeter screen, and where the particle size distribution is selected such that the top lift has a permeability of at least 30,000 millimeters per day as measured by the ASTM D 2434 (06) test and a California Bearing Ratio (CBR) stability of at least 40 as measured by the ASTM D 1883 (07) test; and
a wear surface including a permeable pavement positioned on top of the top lift.
2. The traffic bearing structure of claim 1 where the aggregate particles are sized such that 90 to 100% of the particles pass through a 25 millimeter screen, 60 to 90% of the particles pass through a 12.5 millimeter screen, 30 to 70% of the particles pass through a 4.75 millimeter screen, and 7 to 40% of the particles pass through a 1.18 millimeter screen.
3. The traffic bearing structure of claim 1 where the permeable pavement is selected from the group consisting of block pavers, porous asphalt, and porous concrete.
4. The traffic bearing structure of claim 1 where the base includes a lower lift comprising aggregate.
5. The traffic bearing structure of claim 4 where the aggregate of the lower lift includes particles having a larger average size than the aggregate particles of the top lift.
6. The traffic bearing structure of claim 1 where the top lift has a compaction gradient.
7. A traffic bearing structure comprising:
a subgrade;
a base positioned on top of the subgrade, where the base comprises an aggregate with varying particle sizes such

that essentially all the particles will pass through a 37.5 millimeter screen, some of the particles will not pass through a 12 millimeter screen, and some of the particles will pass through a 5 millimeter screen; and

a wear surface positioned on top of the base, where the wear surface comprises a permeable pavement.

8. The traffic bearing structure of claim 7 where 90 to 100% of the aggregate passes through a 25 millimeter screen, 60 to 90% of the aggregate passes through a 12.5 millimeter screen, 30 to 70 % of the aggregate passes through a 4.75 millimeter screen, and 7 to 40% of the aggregate passes through a 1.18 millimeter screen,

9. The traffic bearing structure of claim 7 where the permeable pavement is selected from the group consisting of block pavers, porous asphalt, and porous concrete.

10. The traffic bearing structure of claim 7 where the base further comprises a compacted top lift positioned over a lower lift.

11. The traffic bearing structure of claim 7 where the base comprises one single compacted lift.

12. The traffic bearing structure of claim 7 where the lift has a permeability of at least 8,500 millimeters per day as measured by the ASTM D 2434 (06) test and a California Bearing Ratio stability of at least 25 as measured by the ASTM D 1883 (07) test.

13. The traffic bearing structure of claim 7 further comprising at least one drain line positioned within the base.

14. The traffic bearing structure of claim 7 where the aggregate is compacted to between 90 and 95% as measured by the ASTM D 698 (07) test.

15. A method for installing a traffic bearing structure comprising;

- (a) preparing a subgrade;
 - (b) installing a loose aggregate over the subgrade, where all of the aggregate will pass through a 37.5 millimeter screen, some of the aggregate will not pass through a 12 millimeter screen, and some of the aggregate will pass through a 5 millimeter screen;
 - (c) compacting the aggregate into a top lift; and
 - (d) covering the aggregate with a permeable pavement.
16. The method of claim 15 further comprising:
- (e) installing loose aggregate over the subgrade before (b); and
 - (f) compacting the aggregate into a lower lift before (b).

17. The method of claim 16 where the loose aggregate from (e) is more coarse than the loose aggregate from (b),

18. The method of claim 15 where the top lift is the only lift between the subgrade and the permeable pavement.

19. The method of claim 15 where the aggregate from (b) is sized such that 90 to 100% of the aggregate passes through a 25 millimeter screen, 60 to 90% of the aggregate passes through a 12.5 millimeter screen, 30 to 70% of the aggregate passes through a 4.75 millimeter screen, and 7 to 40% of the aggregate passes through a 1.18 millimeter screen.

20. The method of claim 15 where the top lift is compacted to between 90 and 95% as measured by the ASTM D 698 (07) test, and the particle size distribution is selected such that the top lift has a permeability of at least 30,000 millimeters per day as measured by the ASTM D 2434 (06) test and a California Bearing Ratio (CBR) stability of at least 40 as measured by the ASTM D 1883 (07) test.