


US 20140093671A1

(19) **United States**(12) **Patent Application Publication**
Bondokov et al.(10) **Pub. No.: US 2014/0093671 A1**(43) **Pub. Date: Apr. 3, 2014**(54) **LARGE ALUMINUM NITRIDE CRYSTALS
WITH REDUCED DEFECTS AND METHODS
OF MAKING THEM**(60) Provisional application No. 60/740,082, filed on Nov.
28, 2005.**Publication Classification**(71) Applicants: **Robert Bondokov**, Watervliet, NY (US);
Kenneth E. Morgan, Castleton, NY
(US); **Glen A. Slack**, Scotia, NY (US);
Leo J. Schowalter, Latham, NY (US)(51) **Int. Cl.**
C30B 29/40 (2006.01)
C30B 33/02 (2006.01)
C30B 23/02 (2006.01)(72) Inventors: **Robert Bondokov**, Watervliet, NY (US);
Kenneth E. Morgan, Castleton, NY
(US); **Glen A. Slack**, Scotia, NY (US);
Leo J. Schowalter, Latham, NY (US)(52) **U.S. Cl.**
CPC **C30B 29/403** (2013.01); **C30B 23/02**
(2013.01); **C30B 33/02** (2013.01)
USPC **428/64.1**; 423/412; 117/3(21) Appl. No.: **14/051,566**(22) Filed: **Oct. 11, 2013****Related U.S. Application Data**(63) Continuation of application No. 13/706,966, filed on
Dec. 6, 2012, now Pat. No. 8,580,035, which is a
continuation of application No. 11/605,192, filed on
Nov. 28, 2006, now Pat. No. 8,349,077.(57) **ABSTRACT**

Reducing the microvoid (MV) density in AlN ameliorates numerous problems related to cracking during crystal growth, etch pit generation during the polishing, reduction of the optical transparency in an AlN wafer, and, possibly, growth pit formation during epitaxial growth of AlN and/or AlGaIn. This facilitates practical crystal production strategies and the formation of large, bulk AlN crystals with low defect densities—e.g., a dislocation density below 10^4 cm^{-2} and an inclusion density below 10^4 cm^{-3} and/or a MV density below 10^4 cm^{-3} .






FIG. 1




FIG. 2A




FIG. 2B




FIG. 3




FIG. 4

LARGE ALUMINUM NITRIDE CRYSTALS WITH REDUCED DEFECTS AND METHODS OF MAKING THEM

CROSS-REFERENCE TO RELATED APPLICATION

[0001] The present application claims the benefits of and priority to U.S. Provisional Application Ser. No. 60/740,082, filed on Nov. 28, 2005, the entire disclosure of which is hereby incorporated by reference.

GOVERNMENT SUPPORT

[0002] This invention was made with United States Government support under 70NAINB4H3051 awarded by the National Institute of Standards and Technology (NIST). The United States Government has certain rights in the invention.

BACKGROUND

[0003] Aluminum nitride (AlN) holds great promise as a semiconductor basis material for numerous applications, e.g., opto-electronic devices such as short-wavelength LEDs and lasers, dielectric layers in optical storage media, electronic substrates, and chip carriers where high thermal conductivity is essential, among many others. In principle, the properties of AlN will allow light emission in the 200 nm wavelength region to be achieved. But many practical difficulties should be addressed for such devices to become commercially practicable.

[0004] For example, bulk AlN crystals often exhibit a substantial amount of cracking, which results in crystal separation before, during or after the crystal is formed into a wafer. If the crystal cracks or fully separates, it is very difficult or sometimes impossible to use it as a reliable substrate for device fabrication. Most of the commercially available machines for epitaxy, photolithography and other device processing require perfectly shaped, round wafers with uniform thickness. Any crack, even ones that do not result in wafer separation, will impair commercial usefulness. Therefore, the cracking problem in AlN crystal growth has crucial importance for the further development of nitride-based electronics.

[0005] In addition, many opto-electronic applications will require transparent wafers. While AlN is intrinsically transparent at optical wavelengths between 210 and 4500 nm, macroscopic defects such as cracks and inclusions significantly scatter light and reduce the apparent transparency in this important optical region. Elimination of cracks and inclusions is of critical importance to the development of ultraviolet light emitting diodes (LEDs), for example.

DESCRIPTION OF THE INVENTION

BRIEF SUMMARY OF THE INVENTION

[0006] Microvoids (MVs) in AlN single crystals are a type of crystallographic defect that can be classified as an inclusion. The lateral (i.e. parallel to the c-plane) size of the MV defects typically varies from 0.1 to 3 micrometers (μm). Under low resolution ($\leq 100\times$) optical microscopy, the MVs appear to be spherically shaped inclusions. However, under higher ($\geq 200\times$) resolution optical microscopy, as well as when imaged using Atomic Force Microscopy (AFM), the MVs appear to have a hexagonal shape well aligned with (i.e., approximately parallel to) the c-plane. During chemical treat-

ment (chemical etching or chemical-mechanical polishing), MVs intersecting an AlN surface leave shallow pits with a round or hexagonal shape. Also, AlN material with a significant density of MVs tends to etch faster (during chemical etching) than the material with somewhat lower MV density. Therefore, the MVs can behave as heterogeneous inclusions in the AlN solid phase. The MVs may be associated with a gas-phase segregation, e.g. of oxygen, nitrogen, or hydrogen. MVs containing segregated gaseous species can lower the stacking symmetry of the AlN parallel to the c-axis thus representing stacking faults. In crystals grown by sublimation-recondensation (such as described in U.S. Pat. No. 6,770,135, the entire disclosure of which is hereby incorporated by reference), the volume density can be about 10^9 cm^{-3} and the surface density of MVs (i.e., MVs which either intersect the surface after cutting or are within $1 \mu\text{m}$ of the surface) can be about 10^5 cm^{-2} .

[0007] We have found that reducing the MV density in AlN ameliorates numerous problems related to cracking during crystal growth, etch pit generation during the polishing, reduction of the optical transparency in an AlN substrate, and, possibly, growth pit formation during epitaxial growth of AlN and/or AlGaIn. The ability to address these problems by reducing MV formation facilitates practical crystal production strategies and the formation of large, bulk AlN crystals with low defect densities—e.g., a dislocation density below 10^4 cm^{-2} , an inclusion density below 10^4 cm^{-3} (MVs are a type of inclusion) and/or a MV density below 10^4 cm^{-3} . The invention also facilitates fabrication of single-crystal wafers of AlN ready for epitaxial growth and oriented within 2° of the (0001) face (c-face) with the Al polarity, and having a shallow pit density of less than 100 cm^{-2} . Embodiments of the invention further facilitate formation of single-crystal wafers of AlN that are at least 2 cm in diameter having an optical absorption coefficient of less than 1 cm^{-1} over any part of the wavelength range where AlN is intrinsically transparent spanning from 210 nm to 4,500 nm. Embodiments of the invention also permit fabrication of substantially crack-free boules of single-crystal AlN having diameters larger than 2 cm and lengths greater than 1 cm. The term “wafer,” as utilized herein, refers to a self-supporting substrate and/or portion of a boule of material such as AlN. The term “substantially crack-free,” as utilized herein, refers to a crack density of less than 5 cracks per boule or volume of single crystal material which is approximately 2 cm diameter by 1 cm in length, or less than 10 cracks per two-inch (2") diameter wafer, where the cracks are typically less than approximately 2 cm in length. Alternatively, it can refer to approximately zero cracks in a crystal boule or portion thereof, or can refer to a finite crack density insufficient to cause separation of a portion of the crystal boule during growth, cool-down, slicing, or other handling procedures.

[0008] Accordingly, in a first aspect the invention features a method of growing single-crystal AlN including providing in a crystal growth enclosure a vapor comprising Al and N_2 , and depositing the vapor as single-crystalline AlN having a microvoid density less than approximately 10^4 cm^{-3} . In an embodiment, the partial pressure of N_2 in the crystal growth enclosure may be maintained at a level greater than a stoichiometric pressure relative to the Al. The partial pressure of N_2 may be within the range of 1-50 bar.

[0009] One or more of the following features may be included. A growth rate of the single-crystalline AlN in any crystallographic direction may be within the range of

approximately 0.1 to approximately 2 mm/hr. A push rate less than or equal to the intrinsic growth rate of the single-crystalline AlN may be maintained. The push rate may be at least 0.1 mm/hr. Deposition of the single-crystalline AlN may originate at a seed crystal disposed within the crystal growth enclosure and oriented such that a direction of maximum growth rate of the single-crystalline AlN is rotated at least approximately 10° away from a c-axis of the single-crystalline AlN and toward a non-polar direction. The oxygen concentration in the vapor may be less than 300 parts per million (ppm) atomic percent, and the hydrogen concentration in the vapor may be less than 0.5%. The crystal growth enclosure may include tungsten, and the growth temperature may be less than approximately 2350°C . The crystal growth enclosure may include at least one of tantalum and carbon, and the growth temperature may be less than approximately 2750°C . The temperature gradient along a length of the crystal growth enclosure may be greater than approximately 5°C./cm and less than approximately 100°C./cm .

[0010] The method may further include, following deposition, the step of slicing an AlN wafer from the single-crystalline AlN. The cross-sectional area of the AlN wafer may be approximately equal to that of the single-crystalline AlN, and may be approximately circular with a diameter greater than approximately 2 cm.

[0011] One or more of the following features may be included. The method may include the step of annealing the AlN wafer at a first temperature and a first pressure. The first temperature may be greater than approximately 2000°C . and the first pressure may be greater than approximately 35 bar. The first temperature may be less than approximately 2350°C . After annealing, the microvoid density in a center region of the AlN wafer may be less than the density in an edge region of the AlN wafer, and may be less than approximately 10^4 cm^{-3} , or even approximately zero.

[0012] The method may include the step of polishing the AlN wafer, wherein after polishing the AlN wafer has an etch pit density less than approximately 100 cm^{-2} . In some embodiments, the method includes the step of depositing an epitaxial layer on the AlN wafer, wherein the epitaxial layer has a surface pit density less than approximately 100 cm^{-2} . In another embodiment, the microvoid density of the single-crystalline AlN is greater than zero and the single-crystalline AlN is substantially crack-free.

[0013] In another aspect, the invention features a bulk AlN crystal having a dislocation density below 10^4 cm^{-2} and an inclusion density below 10^4 cm^{-3} . In an embodiment, the microvoid density of the crystal is less than approximately 10^4 cm^{-3} .

[0014] In yet another aspect, the invention features a single-crystal wafer of AlN oriented within 2° of the (0001) face with the Al polarity, the wafer having a shallow pit density less than 100 cm^{-2} . In an embodiment, the wafer is substantially crack-free. The microvoid density in a center region of the wafer may be less than the density in an edge region of the wafer. For example, the microvoid density in a center region of the wafer may be approximately zero and the microvoid density in an edge region of the wafer may be less than approximately 10^4 cm^{-3} .

[0015] In another aspect, the invention features a single-crystal wafer of AlN having an optical absorption coefficient of less than 5 cm^{-1} at all wavelengths in the range spanning 500 nm to 3,000 nm. In an embodiment, the wafer is substantially crack-free. A microvoid density in a center region of the

wafer may be less than a microvoid density in an edge region of the wafer. The microvoid density in a center region of the wafer may be approximately zero and the microvoid density in an edge region of the wafer may be less than approximately 10^4 cm^{-3} . In an embodiment, the optical absorption coefficient may be less than 1 cm^{-1} at all wavelengths in the range spanning 500 nm to 3,000 nm. The wafer may have a diameter greater than approximately 2 cm.

[0016] In another aspect, the invention features a single-crystal wafer of AlN having an optical absorption coefficient less than 1 cm^{-1} at any wavelength in the range spanning 210 nm to 4,500 nm and a diameter greater than approximately 2 cm.

[0017] In yet another aspect, the invention features a boule of crack-free, single-crystal AlN having a diameter larger than 2 cm and a length greater than 1 cm. In an embodiment, the boule may have a microvoid density in the range of greater than zero to less than approximately 10^4 cm^{-3} .

BRIEF DESCRIPTION OF THE DRAWINGS

[0018] In the drawings, like reference characters generally refer to the same parts throughout the different views. Also, the drawings are not necessarily to scale, emphasis instead generally being placed upon illustrating the principles of the invention. In the following description, various embodiments of the present invention are described with reference to the following drawings, in which:

[0019] FIG. 1 schematically depicts a crystal growth enclosure for the growth of single-crystalline AlN;

[0020] FIGS. 2A and 2B schematically depict an AlN wafer separated from a boule of single-crystalline AlN;

[0021] FIG. 3 schematically depicts an AlN wafer exhibiting domains of differing MV density; and

[0022] FIG. 4 schematically depicts an epitaxial layer deposited on an AlN wafer.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0023] Coalescence of MVs can result in their lining up parallel to the prismatic $\{1\bar{1}00\}$ planes (i.e., m-planes) in an AlN crystal. In several cases we observed MVs creating tree-like features where the tree branches represent lining up of MVs that often evolve into a solid tree (crack or micro-crack). Another type of crack formation due to MV coalescence—a rare but still significant case—occurs when MVs form a few circles from their common center from which the crack spreads out almost to 180° . Moreover, since some of the MVs intersect the surface, they can influence the polishing process by producing etch pits.

[0024] MVs can reduce the optical transparency of an AlN substrate. To first order, the reduction in transparency can be modeled by assuming that the amount of radiation scattered by the MVs is proportional to the effective area presented by the MVs. At low densities of MVs, this means that the reduction in transmission of radiation through a slab of AlN with thickness d , will be equal to ndA where n is the numerical density of MVs and A is the effective area each MV presents to scatter the radiation. The transmission T through a uniform slab of material of thickness d is normally expressed in terms of an absorption coefficient α such that $T=e^{-\alpha d}$. In this model, the absorption coefficient will be approximately equal to nA and will be independent of wavelength. If the effective area A that the MVs present to scatter radiation is $\sim 1\text{ }\mu\text{m}^2$, then the

density of MVs is preferably below $\sim 10^8 \text{ cm}^{-3}$ in order to achieve an absorption coefficient that is less than 1 cm^{-1} . Indeed, this calculation corresponds to optical absorption measurements on AlN.

[0025] The three distinct colorations of AlN substrate wafers are observed. Depending on growth conditions, sometimes these colorations can all be observed in a single-crystal AlN wafer. The colorations can be described as:

- [0026]** 1) Dark (brownish);
- [0027]** 2) Yellow (amber); and
- [0028]** 3) Light yellow.

[0029] The dark area usually contains a high density of MVs that are easily observed. MVs are harder to observe in the yellow area due to the lack of optical contrast (MV's and amber material are both bright). Also, in some cases, the density of MVs in the yellow area is smaller than that in darker region. It is even harder to see MVs in large yellow regions, but again, that may be due to the contrast or because light yellow regions represent grains that are usually oriented strongly off-axis. It appears, however, that the most important difference between the dark and yellow regions is that MVs in the dark region are normally connected to each other, creating a network, while the MVs in the yellow areas do not exhibit this feature.

[0030] The present invention also stems from the recognition that generation of MVs during AlN crystal growth makes it easier for the AlN crystal to crack. Therefore, embodiments of the present invention prevent or reduce MV generation in order to prevent or reduce cracking. This may be accomplished through adjustment and control of one or more of:

- [0031]** 1) The expansion rate of the crystal;
- [0032]** 2) The gas mixture;
- [0033]** 3) The ambient pressure;
- [0034]** 4) The growth temperature;
- [0035]** 5) The temperature gradients;
- [0036]** 6) The push rate; and/or
- [0037]** 7) The post-growth annealing.

1) Expansion Rate.

[0038] There are two main directions of the crystal expansion during crystal growth: lateral and vertical. MV formation can be controlled by controlling the expansion rate because MVs can form due to vacancy aggregation. If the AlN crystal is grown under stoichiometric gas phase conditions (i.e., the number of Al and N atoms in the vapor phase is equal), then there will not be enough single nitrogen (N) atoms to bond to each aluminum atom in the crystal lattice due to the very high bonding energy of the N_2 molecule ($\sim 9.76 \text{ eV}$ at 0 K). The overall effect of single N atoms provided to the growth surface can be described by introducing an effective accommodation coefficient that is less than 1 if the number of single N atoms at the growing surface is less than the number of N_2 molecules arriving at the surface. When the number of single N atoms incorporated into the crystal is less than the number of the Al atoms, excess Al atoms will be trapped in the crystal.

[0039] Too high a growth rate (expansion) in any direction will result in the trapping of excess Al atoms in the crystal, thus creating N vacancies. These N vacancies, in turn, can later aggregate and generate MVs. In order to minimize or completely avoid formation of MVs, the growth rate in any crystallographic direction is preferably kept in the range from 0.1 to 2 mm/hr . The lower growth rate limit is defined by practical considerations for creating bulk crystals from vapor-phase constituents, while the upper growth limit is defined by

the desired crystalline quality of grown crystal: as the growth rate increases, the fracture of polycrystalline material increases as well. The maximum growth rate will also depend on the crystallographic orientation of the growing crystal.

[0040] It is important to note that a expansion rate may result in generating different types of point defects (vacancies) such as pairs of Al and N vacancies (see, e.g., G. A. Slack, L. J. Schowalter, D. Morelli, J. A. Freitas Jr., *J. Crystal Growth*, vol. 246, p. 287 (2002), the disclosure of which is hereby incorporated by reference), especially when oxygen is present in the vapor phase. Any vacancies can aggregate and generate MVs.

[0041] Hence, referring to FIG. 1, according to various embodiments, during growth of single-crystalline AlN, a crystal growth enclosure **100** contains a vapor mixture **110** and a single-crystal AlN boule **120**. Vapor mixture **110** includes primarily gaseous Al and N_2 , and arises from the sublimation of source **160**. Boule **120** is formed by the recondensation of vapor mixture **110** at a top end of crystal growth enclosure **100**, and may originate from a seed crystal (not pictured). The growth rate of boule **120** can be defined as the increase in size of boule **120**, for example, parallel or perpendicular to longitudinal axis **150** of crystal growth enclosure **100**. The direction of maximum growth rate of boule **120** is generally along longitudinal axis **150**. The MV density of boule **120** can be kept below a level of approximately 10^4 cm^{-3} by maintaining the growth rate of boule **120** in the range of 0.1 to 2 mm/hr . In an embodiment, the MV density of boule **120** is greater than zero. The seed crystal may be oriented such that the direction of maximum growth rate of boule **120** is oriented at least approximately 10° away from the c-axis and towards a non-polar direction, i.e., a c-axis of boule **120** may be oriented at least approximately 10° away from longitudinal axis **150**. Such a seed crystal orientation may act to suppress MV formation.

2) Gas Mixture.

[0042] The purity and the composition of the gas mixture are important parameters in controlling generation of MVs. Forming gas contains hydrogen (usually $\leq 5\%$ by volume) and is used in order to reduce possible oxygen contamination. However, hydrogen molecules can be easily trapped in the AlN material (as is the case with other semiconductors as well). By diffusion as interstitials, these hydrogen atoms can agglomerate and create MVs. Oxygen contamination may result from several sources including residual water vapor and contaminated supply gases. Once in the crystal crucible, it may be transported as Al_2O in the vapor phase and attach to the Al sites in the crystal lattice, thus creating Al vacancies. The Al vacancies can aggregate and create MVs. Accordingly, using high-purity gases with low amounts of hydrogen and oxygen will reduce the probability of MV formation. The use of UHP-grade N_2 gas, applicable in the semiconductor industry, is desirable. However, additional steps will need to be taken, including the use of nitrogen gas filters to purify the N_2 gas being introduced, as well as the use of gas flow to remove contamination from the furnace elements as they heat up. For example, the UHP-grade nitrogen gas can be passed through an Aeronex filter (model SS2500KFH4R, max flow 300 SLM , filtration $0.003 \mu\text{m}$). The delivery rate to the hot zone can be $0.125 \text{ liter per minute (LPM)}$ although the optimum gas volume delivered to the reaction zone will vary based on the specific geometry.

[0043] Thus, in an embodiment, the concentration of hydrogen in vapor mixture **110** is less than 0.5%. In another embodiment, the concentration of oxygen in vapor mixture **110** is less than 300 parts per million (ppm) atomic percent. Maintenance of low hydrogen and oxygen concentrations in vapor mixture **110** prevent formation of point defects in boule **120** that can agglomerate and form MVs. Thus, the MV density in boule **120** can be maintained below approximately 10^4 cm^{-3} . In an embodiment, the MV density of boule **120** is greater than zero.

3) Ambient Pressure.

[0044] The evaporation of AlN is nearly congruent. The equilibrium vapor phase of evaporated AlN consists almost exclusively of Al atoms and N_2 molecules at the temperatures typically used for crystal growth (1900 to 2450° C.). For the AlN crystal to grow, N_2 molecules that are adsorbed on the surface must be broken into atomic N in order to be incorporated into the growing crystal. As stated above, the lack of sufficient N atoms present at the growth surface results in generation of N vacancies that can cause formation of MVs. In order to provide a sufficient source of N atoms, the partial pressure of N_2 is preferably increased well above the stoichiometric value (or, alternatively, the growth temperature increased). The higher the ambient N_2 pressure, the higher the amount of atomic N that will be generated on the growing crystal surface and available for incorporation into the crystal. Thus, higher N_2 partial pressure reduces the probability of MV formation. The ambient N_2 pressure is preferably, therefore, kept as high as possible in order to provide sufficient atomic N flux to the growing interface; see, e.g., U.S. Pat. No. 6,770,135. The ranges needed to grow AlN crystals from vapor phase are 1-50 bar where the lower limit is defined by the lowest N_2 pressure required to obtain high quality AlN crystals, while the upper limit is defined by the reasonable growth rate as increasing the ambient pressure results in a diffusion-limited growth regime.

[0045] Thus, in an embodiment, vapor mixture **110** contains a partial pressure of N_2 greater than the stoichiometric pressure relative to the partial pressure of Al, i.e., the number of N atoms in vapor mixture **110** is greater than the number of Al atoms in vapor mixture **110**. Maintenance of this high partial pressure of N_2 relative to Al prevents the formation of N vacancies which can agglomerate and form MVs. In an embodiment, the partial pressure of N_2 in vapor mixture **110** is in the range of 1 to 50 bar. Thus, the MV density in boule **120** can be maintained below approximately 10^4 cm^{-3} . In an embodiment, the MV density of boule **120** is greater than zero.

4) Growth Temperature and 5) Temperature Gradients.

[0046] An insufficient growth temperature results in polycrystalline growth, which increases the defect density and, therefore, the formation of MVs. Moreover, lower growth temperatures decrease the surface concentrations of monatomic N and therefore lead to N vacancies, which, in turn, further contribute to MV formation. Very high temperature gradients also result in polycrystalline growth and should also be avoided in order to reduce the possibility of MV generation. The highest acceptable growth temperature is generally limited by the possible formation of eutectic solutions of AlN with the crucible, so the temperature regimes employed should be judiciously chosen. For instance, the highest pos-

sible growth temperature at 1 bar pressure would be 2330° C. (see, e.g., Glen A. Slack and T. F. McNelly, "Growth of high purity AlN crystals," *J. Cryst. Growth*, vol. 34, pp. 263-279 (1976) and Glen A. Slack, Jon Whitlock, Ken Morgan, and Leo J. Schowalter, "Properties of Crucible Materials for Bulk Growth of AlN," *Mat. Res. Soc. Symp. Proc. Vol. 798*, p. Y10.74.1 (2004) ("Slack 2004"), the entire disclosures of which are hereby incorporated by reference), since above this temperature AlN will form a liquid eutectic with the crucible and destroy it. Higher temperatures can be achieved by using other crucible materials such as suggested in Slack 2004. However, problems with contamination and leakage through the crucible walls may be anticipated. Leakage through polycrystalline crucibles may be addressed using the techniques described in U.S. Pat. No. 6,719,843 and in U.S. patent application Ser. No. 10/822,336, the entire disclosures of which are hereby incorporated by reference.

[0047] In any case, the maximum temperature of growth by sublimation-recondensation will be limited to less than approximately 2750° C. Above, this temperature, AlN has been observed to melt at an elevated nitrogen pressure of 10 megaPascals (MPa) (see V. L. Vinogradov, A. V. Kostanovskii, and A. V. Kirillin, "Determination of the Melting Parameters of Aluminium Nitride," *High Temperatures-High Pressures*, vol. 23, p. 685 (1991), the disclosure of which is herein incorporated by reference). It is anticipated that the highest temperature gradient at which MV formation will be diminished is less than approximately 100° C./cm. The temperature gradient is related to both expansion rate and vertical growth rate. In case of MV formation due to too high an expansion rate or vertical growth rate, then controlling the temperature gradients (radial and axial) can limit the MV formation as well as their further migration and agglomeration.

[0048] Referring to FIG. 1, heat source **140** surrounds crystal growth enclosure **100** and regulates the growth temperature therein. Moreover, the local temperature at various points in heat source **140**, as well as the speed of travel of crystal growth enclosure **100** through heat source **140** (i.e., the push rate described below), control the thermal gradient in boule **120**. The thermal gradient is defined herein as the change in temperature of the boule as a function of distance along the length L of the crystal growth enclosure.

[0049] In an embodiment, heat source **140** is regulated such that the growth temperature inside crystal growth enclosure **100** is less than approximately 2350° C. and crystal growth enclosure **100** is made primarily of tungsten. In a preferred embodiment, crystal growth enclosure **100** is made primarily of tungsten and the growth temperature falls within a range of 1900 to 2350° C. In another embodiment, crystal growth enclosure **100** is made primarily of niobium carbide (NbC) and the growth temperature falls within a range of 1900 to 2350° C. In another embodiment, crystal growth enclosure **100** is made primarily of tantalum carbide (TaC) or tantalum (Ta) coated with a layer of carbon (C) and the growth temperature falls within a range of 1900 to 2400° C. The layer of C may be formed on crystal growth enclosure **100** made primarily of Ta by chemical vapor deposition. In another embodiment, crystal growth enclosure **100** is made primarily of C and the growth temperature falls within a range of 1900 to 2750° C., or, preferably, within a range of 1900 to 2550° C.

[0050] In an embodiment, the thermal gradient of boule **120** is maintained at a level greater than approximately 5° C./cm and less than approximately 100° C./cm. This high thermal

gradient prevents the formation of MVs at a level greater than approximately 10^4 cm^{-3} , and maintains growth of boule **120** as a single crystal rather than as polycrystalline material. In an embodiment, the MV density of boule **120** is greater than zero.

6) Push rate.

[0051] There is an optimum push rate at which MV generation is negligible. Preferably, the push rate is slightly less than or equal to the intrinsic, or maximum, growth rate (as stated above, 0.1-2 mm/hr). If this condition is not obeyed, then the crystal growth rate in the growth direction may be too high, resulting in MV formation as explained above. Moreover, a high push rate may lead to the nucleation of AlN on the walls of a tungsten crucible, which, in turn, will increase the defect density and the possibility of MV generation. In addition, higher push rates may result in the predominate growth of other planes rather than c-planes, an effect that further contributes to MV formation.

[0052] However, the push rate should not be too low (<0.1 mm/hr) since a tungsten crucible degrades if exposed to the Al vapor for a very long time. The Al vapor attacks the crucible wall along its grain boundaries and other defects, resulting in leakage of some Al vapor and consequent pore formation in the growing material. Therefore, it is desirable to choose the push rate so as to reduce MV formation.

[0053] Referring to FIG. 1, crystal growth enclosure **100** also includes push mechanism **130**, which controls the travel of crystal growth enclosure **100** through surrounding heat source **140**, thereby controlling both the push rate and the thermal gradient along the longitudinal axis **150**. The push rate is defined as the speed at which push mechanism **130** propels crystal growth enclosure **100** through heat source **140**. In an embodiment, the push rate is maintained at a level less than or approximately equal to a maximum growth rate of boule **120** in the direction parallel to the longitudinal axis **150**. Here, the maximum growth rate is defined by the maximum rate allowed by the crystal growth temperature and the source temperature. In a preferred embodiment, the push rate is maintained at a level of approximately one-half the maximum growth rate of boule **120**. Thus, the MV density in boule **120** can be maintained below approximately 10^4 cm^{-3} . In an embodiment, the MV density of boule **120** is greater than zero.

[0054] As used herein, the push rate can also be defined as an actual growth rate maintained at a level below that enabled by the specific growth conditions, e.g., the growth temperature and the source temperature. Maintenance of a specific push rate can also be equivalently accomplished without physical movement of crystal growth enclosure **100**. For example, heat source **140** could be moved relative to a stationary crystal growth enclosure **100**, or the distance or temperature gradient between boule **120** and source **160** can be altered. Generally, any of these methods in which actual growth rate is controlled at a level below the maximum intrinsic growth rate can be utilized interchangeably with push rate.

7) Post-Growth Annealing.

[0055] Referring to FIGS. 2A and 2B, wafer **200** may be sliced from boule **120** by the use of, for example, a diamond annular saw or a wire saw. Maintaining an MV density less than approximately 10^4 cm^{-3} in boule **120** substantially prevents crack formation in both boule **120** and wafer **200**. Such cracks can result in, among other effects, separation of small portions of either boule **120** or wafer **200** during wafer slicing.

Thus, through the prevention of crack formation, a surface **210** of wafer **200** may have substantially the same shape and cross-sectional area of a surface **220** of boule **120**. In an embodiment, surface **210** may be approximately circular in shape and have a diameter of greater than approximately 2 cm. In an alternate embodiment, surface **210** may be a quadrilateral or other polygon with an area greater than approximately 3 cm^2 .

[0056] In an embodiment, a crystalline orientation of surface **210** may be within approximately 2° of the (0001) face (i.e., the c-face) and have an Al polarity. In other embodiments, surface **210** may have a N polarity or be oriented within approximately 2° of the m-face or a-face orientation.

[0057] Referring to FIG. 3, wafer **200** may be annealed to reduce the density of MVs therein. The annealing temperature may be in the range spanning 1000 to 2350° C . In a preferred embodiment, the annealing temperature is approximately 2000° C . In yet another embodiment, wafer **200** is subjected to high pressure during annealing. The annealing pressure may be selected from the range of 1 to 50 bar, and in a preferred embodiment, the annealing pressure is approximately 35 bar. In an embodiment, wafer **200** may be annealed in an ambient including N_2 gas. In another embodiment, wafer **200** may be annealed at a temperature of approximately 1200° C . and a pressure of approximately 2 bar.

[0058] Annealing of wafer **200** may reduce the MV density thereof from a level of approximately 10^3 to 10^9 cm^{-3} to a level of approximately zero to 10^3 cm^{-3} . Hence, the MV density of wafer **200** after annealing will be less than that of boule **120** from which it was sliced.

[0059] Reducing the MV density of wafer **200** may also improve its optical transparency. In an embodiment, an optical absorption coefficient of wafer **200** is less than 1 cm^{-1} at any wavelength within the range of approximately 210 nm to approximately 4,500 nm. In another embodiment, the optical absorption coefficient of wafer **200** is less than 5 cm^{-1} at all wavelengths within the range of approximately 500 nm to approximately 3,000 nm. The optical absorption coefficient may be less than 1 cm^{-1} . Wafer **200** may have a diameter larger than approximately 2 cm.

[0060] Annealing wafer **200** may also result in a non-uniform distribution of MVs across wafer **200**. Referring to FIG. 3, after annealing, a center region **300** may have a lower MV density than an edge region **320**. For example, the MV density in center region **300** may be in the range of approximately zero to approximately 10^2 cm^{-3} , and the MV density in edge region **320** may be in the range of approximately 10^3 cm^{-3} to approximately 10^4 cm^{-3} . In an embodiment, boundary area **310** separates center region **300** from edge region **320**. In an embodiment, center region **300** is approximately circular in shape and has a diameter of 1-3 mm, and edge region **320** conforms to an outer boundary of wafer **200** and has a width of approximately 3 mm to approximately 50 mm. Generally, the size of either center region **300** or edge region **320** may be larger than described above, with the other region correspondingly shrinking in size. The utilization of longer anneal times and/or higher annealing temperatures may result in the growth of center region **300** at the expense of edge region **320**, i.e., boundary region **310** may effectively move toward the outer edge of wafer **200** as MVs are eliminated from wafer **200**. In an embodiment, annealing proceeds for a time sufficient for boundary region **310** to reach the outer edge of wafer **200**, i.e., substantially all of the area of wafer **200** will have a reduced density of MVs. In an embodiment, an overall MV

density of wafer **200** may be within the range of approximately zero to approximately 10^2 cm^{-3} .

[0061] Referring to FIG. 4, epitaxial layer **400** may be deposited on a surface of wafer **200** for the purposes of subsequent device fabrication. Epitaxial layer **400** may include AlN, GaN, InN, and/or binary and tertiary alloys of each. Prior to epitaxial deposition, wafer **200** may be polished in order to improve the quality and planarity of a surface thereof. Various polishing techniques may be utilized, e.g., the methods described in U.S. patent application Ser. No. 11/448,595 and U.S. Pat. No. 7,037,838, the entire disclosures of which are hereby incorporated by reference. In an embodiment, wafer **200** is polished of chemical-mechanical polishing (CMP). Control of MV formation in wafer **200** may result in a superior post-polish surface of wafer **200**, as few MVs will intersect the surface of wafer **200** and be etched preferentially during polishing. In an embodiment, after polishing, wafer **200** will have an etch pit density less than approximately 100 cm^{-2} . Control of MV formation during crystal growth and/or etch pit formation during polishing may facilitate the deposition of epitaxial layer **400** with a shallow pit density less than approximately 100 cm^{-2} . Wafer **200**, with or without epitaxial layer **400**, desirably is substantially crack-free.

[0062] It will be seen that the techniques described herein provide a basis for improved production of AlN crystals. The terms and expressions employed herein are used as terms of description and not of limitation, and there is no intention in the use of such terms and expressions of excluding any equivalents of the features shown and described or portions thereof. Instead, it is recognized that various modifications are possible within the scope of the invention claimed.

What is claimed is:

1.-38. (canceled)

39. An AlN single crystal having at least one of (i) an optical absorption coefficient of less than 5 cm^{-1} at all wavelengths in a range spanning 500 nm to 3,000 nm or (ii) an optical absorption coefficient of less than 1 cm^{-1} at any wavelength in a range spanning 210 nm to 4,500 nm.

40. The AlN single crystal of claim **39**, wherein the AlN single crystal has an optical absorption coefficient of less than 5 cm^{-1} at all wavelengths in a range spanning 500 nm to 3,000 nm.

41. The AlN single crystal of claim **40**, wherein the AlN single crystal has an optical absorption coefficient of less than 1 cm^{-1} at any wavelength in a range spanning 210 nm to 4,500 nm.

42. The AlN single crystal of claim **39**, wherein the AlN single crystal has an optical absorption coefficient of less than 1 cm^{-1} at any wavelength in a range spanning 210 nm to 4,500 nm.

43. The AlN single crystal of claim **39**, wherein the AlN single crystal has a microvoid density less than approximately 10^4 cm^{-3} .

44. The AlN single crystal of claim **39**, wherein the AlN single crystal is substantially crack-free.

45. The AlN single crystal of claim **39**, wherein the AlN single crystal is in the form of a wafer with a surface having a crystalline orientation within 2° of the (0001) c-face and an Al polarity.

46. The AlN single crystal of claim **40**, wherein the AlN single crystal is in the form of a wafer with a surface having a crystalline orientation within 2° of the (0001) c-face and an Al polarity.

47. The AlN single crystal of claim **39**, wherein the AlN single crystal is in the form of a wafer with a surface having a crystalline orientation within 2° of the (0001) c-face and an N polarity.

48. The AlN single crystal of claim **40**, wherein the AlN single crystal is in the form of a wafer with a surface having a crystalline orientation within 2° of the (0001) c-face and an N polarity.

49. The AlN single crystal of claim **39**, wherein the AlN single crystal is in the form of a wafer with a surface having a crystalline orientation within 2° of the m-face.

50. The AlN single crystal of claim **40**, wherein the AlN single crystal is in the form of a wafer with a surface having a crystalline orientation within 2° of the m-face.

51. The AlN single crystal of claim **39**, wherein the AlN single crystal is in the form of a wafer with a surface having a crystalline orientation within 2° of the a-face.

52. The AlN single crystal of claim **40**, wherein the AlN single crystal is in the form of a wafer with a surface having a crystalline orientation within 2° of the a-face.

53. The AlN single crystal of claim **39**, wherein the AlN single crystal is in the form of a wafer having a diameter greater than approximately 2 cm.

54. The AlN single crystal of claim **40**, wherein the AlN single crystal is in the form of a wafer having a diameter greater than approximately 2 cm.

55. A method of growing single-crystal AlN, the method comprising:

providing in a crystal growth enclosure a vapor comprising Al and N_2 ;

depositing the vapor as single-crystalline AlN having a microvoid density less than approximately 10^4 cm^{-3} ; and

following deposition, annealing at least a portion of the single-crystalline AlN at a first temperature and a first pressure,

wherein the first temperature is greater than approximately 2000° C. and the first pressure is greater than approximately 35 bar.

56. The method of claim **55**, wherein the first temperature is less than approximately 2350° C.

57. The method of claim **55**, wherein depositing the vapor as single-crystalline AlN comprises pushing the crystal growth enclosure at a rate less than an intrinsic growth rate of the AlN.

58. The method of claim **55**, further comprising slicing an AlN wafer from the single-crystalline AlN.

* * * * *