

US 20150118460A1

(19) **United States**

(12) **Patent Application Publication**
MOUNT, III et al.

(10) **Pub. No.: US 2015/0118460 A1**

(43) **Pub. Date: Apr. 30, 2015**

(54) **NONCONDUCTIVE FILMS FOR LIGHTER THAN AIR BALLOONS**

(71) Applicant: **San Diego Gas & Electric Company**
c/o Semptra Energy, San Diego, CA (US)

(72) Inventors: **ELDRIDGE M. MOUNT, III, San Diego, CA (US); DENIS S. SANFORD, San Diego, CA (US)**

(73) Assignee: **San Diego Gas & Electric Company**
c/o Semptra Energy, San Diego, CA (US)

(21) Appl. No.: **14/067,878**


(22) Filed: **Oct. 30, 2013**

Publication Classification

(51) **Int. Cl.**
A63H 27/10 (2006.01)
B32B 15/20 (2006.01)

(52) **U.S. Cl.**
CPC **A63H 27/10** (2013.01); **B32B 15/20** (2013.01); **A63H 2027/1025** (2013.01)

(57) **ABSTRACT**
Non-conductive films for constructing lighter than air balloons are provided. A non-conductive film may comprise multiple layers of gas barrier polymers. An outer surface printable layer and an interior heat or ultrasonically sealable layer may also be included. Each gas barrier film may comprise multiple (e.g., from 3 to approximately 75) barrier layers. A gas barrier core has a nano-layer structure. A gas barrier core may also comprise a biodegradable film or a bio-based film. A non-conductive film may comprise a metal layer for enhancing gas barrier properties. The metal layer may be discontinuous. The metal layer may be conductive and coated with an insulating top coat.






FIG. 1A
(PRIOR ART)

FIG. 1B
(PRIOR ART)

FIG. 1C
(PRIOR ART)




FIG. 2




FIG. 3




FIG. 4A

FIG. 4B




FIG. 5A

FIG. 5B




FIG. 6A

FIG. 6B

FIG. 6C




FIG. 7




FIG. 8




FIG. 9A

FIG. 9B

FIG. 9C




FIG. 9E

FIG. 9D




FIG. 10

FIG. 11A

FIG. 11B

NONCONDUCTIVE FILMS FOR LIGHTER THAN AIR BALLOONS

TECHNICAL FIELD

[0001] The present invention relates generally to lighter than air balloons, and more particularly, some embodiments relate to non-conductive films for lighter than air balloons.

DESCRIPTION OF THE RELATED ART

[0002] Lighter than air balloons are popular and have many usages around the world such as toys, advertising media, articles in displays, etc. Lighter than air balloons are filled with lighter than air gases and remain aloft due to its buoyancy. Lighter than air balloons are made of materials that have gas barrier properties. Materials having gas barrier properties may prevent ingress and egress of gas thereby maintaining the lighter than air balloons afloat. Most of lighter than air balloons are made of materials that are electrically conductive. Lighter than air balloons may be released under supervision for various purposes. However, accidental releases may be inevitable. Released balloons may become entangled at different structures such as buildings, trees, or power transmission lines. The conductivity of the materials may cause power outages and service disruption to users, causing a negative impact to the users and economical losses.

BRIEF SUMMARY OF THE INVENTION

[0003] According to various embodiments of the invention, non-conductive films are provided. The non-conductive films may be used to construct lighter than air balloon envelopes. Various embodiments comprise multiple layers of gas barrier polymers. An outer surface printable layer and an interior heat or ultrasonically sealable layer may also be included. Each gas barrier film may comprise multiple (e.g., from 3 to approximately 75) barrier layers. In one embodiment, a gas barrier comprises from 5 to 27 barrier layers. In one embodiment, the gas barrier core has a nano-layer structure. Various embodiments comprise a bio-degradable film or a bio-based film. Further embodiments may comprise a metal layer for enhancing gas barrier properties. The metal layer may be conductive and coated with an insulating top coat. Other embodiments may comprise a metallization layer having patterned or discontinuous metal patches.

[0004] Other features and aspects of the invention will become apparent from the following detailed description, taken in conjunction with the accompanying drawings, which illustrate, by way of example, the features in accordance with embodiments of the invention. The summary is not intended to limit the scope of the invention, which is defined solely by the claims attached hereto.

BRIEF DESCRIPTION OF THE DRAWINGS

[0005] The present invention, in accordance with one or more various embodiments, is described in detail with reference to the following figures. The drawings are provided for purposes of illustration only and merely depict typical or example embodiments of the invention. These drawings are provided to facilitate the reader's understanding of the invention and shall not be considered limiting of the breadth, scope, or applicability of the invention. It should be noted that for clarity and ease of illustration these drawings are not necessarily made to scale.

[0006] FIGS. 1A-1C illustrate constructions of prior art conductive balloon envelopes.

[0007] FIG. 2 illustrates an exemplary non-conductive balloon film in accordance with an embodiment of the present application.

[0008] FIG. 3 illustrates an exemplary 7-layer non-conductive balloon films in accordance with various embodiments of the present application.

[0009] FIGS. 4A-4B illustrate exemplary 9-layer non-conductive balloon films in accordance with various embodiments of the present application.

[0010] FIGS. 5A-5B illustrated exemplary 11-layer non-conductive balloon films in accordance with various embodiments of the present application.

[0011] FIGS. 6A-6C illustrate exemplary balloon films having a barrier core with a nano-layer structure in accordance with various embodiments of the present application.

[0012] FIG. 7 illustrates an exemplary balloon film **700** having a barrier core having multiple sub-barrier cores, where each of the sub-barrier core has a nano-layer structure in accordance with an embodiment of the present application.

[0013] FIG. 8 illustrates an exemplary non-conductive balloon film in accordance with an embodiment of the present application.

[0014] FIGS. 9A-9E illustrated exemplary non-conductive balloon films in accordance with various embodiments of the present application.

[0015] FIG. 10 illustrates an exemplary non-conductive film in accordance with an embodiment of the present application.

[0016] FIGS. 11A-B illustrate exemplary non-conductive balloon films in accordance with various embodiments of the present application.

[0017] The figures are not intended to be exhaustive or to limit the invention to the precise form disclosed. It should be understood that the invention can be practiced with modification and alteration, and that the invention be limited only by the claims and the equivalents thereof.

DETAILED DESCRIPTION OF THE INVENTION

[0018] Most existing balloons are made of oriented polyester (PET) or oriented Nylon (OPA) films. The films may be single-layer or multiple-layer. Conventionally, lighter-than-air balloons are usually constructed of electrically conductive materials such as metallized Biaxially-oriented polyethylene terephthalate ("BoPET" or "Mylar".) The films are metallized to enhance the gas barrier properties and are often coated with a heat sealant to permit forming of the balloon. The balloon envelope is made by sealing, such as heat sealing peripheral portions of panels made of the above material while in a two dimension lay-flat form to any desired two-dimensional shape. The material can be a nonelastomeric polymer sheet carrying a continuous metal layer on at least one surface. PET and Nylon films are known to be very susceptible to pinhole formation in flexing (e.g., folding, creasing, or forming into pouches), which may cause a significant loss of gas barrier properties and greatly reduce a balloon's flight time.

[0019] FIGS. 1A-1C illustrate constructions of prior art conductive balloon envelopes **110**, **120**, and **130**. A metal layer (e.g., a thin metal foil such as an aluminum layer) may be laminated to or vacuum deposited directly on a film surface (e.g., an oriented Nylon film or a PET film.) The thin metal layer is impermeable to the lighter than air gas, whereas the

layer of the nonelastomeric polymer provides structural integrity for the metal as well as limiting diffusion from pinholes or imperfections that may exist in the continuous metal layer. These materials have a conductive surface.

[0020] Non-surface conductive laminations remain conductive as long as the structure comprises a continuous layer of metal. For example, two continuous nonelastomeric films having a continuous layer of vapor deposited metal sandwiched therebetween may be used. This composite may be so produced by vapor depositing the metal layer on either layer of the nonelastomeric polymer film and subsequently laminating the remaining layer of nonelastomeric film to the vapor deposited metal layer. These laminated structures may have a low surface conductivity due to the nonconductive outer polymeric layers. However, as long as the metal layer is continuous, the lamination functions as a capacitor storing charges. The balloon can become electrically conductive under high electrical field strengths due to an electrical breakdown of the nonelastic films included in the balloon film.

[0021] FIG. 2 illustrates an exemplary non-conductive film **200** in accordance with an embodiment of the present application. The non-conductive film **200** may be used to make a lighter than air balloon envelope. The illustrated non-conductive balloon film **200** is a 7-layer coextruded film. In one embodiment, each film may be 12 to 78 microns thick (0.5 to 3 mils.) The exemplary non-conductive balloon film **200** comprises multiple layers: a polyolefin layer **202**, a first adhesive layer **204**, a first gas barrier layer **206**, an Ethylene vinyl alcohol (“EVOH”) gas barrier layer **208**, a second gas barrier layer **210**, a second adhesive layer **212**, and a heat sealing layer **214**. The film **200** comprises a gas barrier core **216**. The gas barrier core **216** may comprise a set of polymeric gas barrier layers. In the illustrated example, the first gas barrier layer **206**, the EVOH layer **208**, and the second gas barrier layer **210** create the gas barrier core **216**. Each polymeric gas barrier layer has a first surface and a second surface.

[0022] Each layer of the gas barrier core **216** may be selected to control the gas barrier properties of the film **200**. For example, the first gas barrier layer **206** and the second gas barrier layer **210** may be nylon (e.g., Nylon 66, Nylon 6, Nylon MDX6, Nylon 6,10 or an amorphous nylon.) The material for the first gas barrier **206** or the second gas barrier **210** may be selected according to the gas barrier core **216**, compatibility with the EVOH used in the EVOH layer **208**, and flex crack resistance. The EVOH may be selected from various grades of copolymer with varying ethylene contents based on the gas barrier levels of the EVOH for the film **200**. For the gas barrier core **216** of the illustrated example, the EVOH layer **208** is sandwiched between the first gas barrier **206** and the second gas barrier **210**.

[0023] In other embodiments, a gas barrier core may have a structure such that a nylon barrier layer is sandwiched between a first EVOH layer and a second EVOH layer. The gas barrier core may be constructed with alternating EVOH layers and nylon layers. The total number of the EVOH and the nylon layers may vary thereby affecting the physical and barrier properties of a non-conductive film such as the film **200**. The use of nylon layers in combination with the EVOH layers enhances the overall gas barrier properties of the film **200** due to the inherent gas barrier characteristics of the nylon material. In addition, this structure may further improve the EVOH durability. The nylon materials included may selec-

tively absorb moisture from the film **200** acting as a desiccant for the EVOH and maintaining the superior gas barrier property of the EVOH.

[0024] The illustrated exemplary non-conductive film **200** comprises a first surface that is the polyolefin layer **202** and a second surface that is the heat sealing layer **214**. The polyolefin layer **202** may be used for decoration purposes and the heat sealing layer **214** may form an enclosed balloon envelope. The polyolefin layer **202** may be a functionalized polymer or a mix of polymers. The polyolefin layer **202** may be functionalized by a variety of surface treatment methods (e.g., corona, flame, atmospheric plasma, or chemical treatment), which may enhance the surface receptivity to decorative methods such as inks, coatings, or metal layers. The first adhesive layer **204** affixes the gas barrier core **216** to the polyolefin layer **202**. The second adhesive layer **212** affixes the gas barrier core **216** to the heat sealing layer **214**.

[0025] In various embodiments, the first adhesive layer **204** may be different from the second adhesive layer **212** as the surfaces of the barrier core **216** may be made of different polymers. In various embodiments, the relative bond strengths required for affixing the gas barrier core **216** to the first surface (i.e., the polyolefin layer **202**) and the second surface (i.e., the heat sealing layer **214**) may be different due to the fact that the first surface and the second surface may be of different materials. Depending on the relative bond strengths desired of a non-conductive film **200**, the first adhesive layer **204** and the second adhesive layer **212** may be the same or different. In various embodiments, the first adhesive layer **204** and the second adhesive layer **212** each may comprise multiple layers as a single bonding layer composition may be inadequate to affix the barrier core **216** to either the polyolefin layer **202** or the heat sealing layer **214**.

[0026] Various embodiments may comprise a decoration layer. In some embodiments, the polyolefin layer may be the decoration layer. The polyolefin layer **202** may be selected according to the decoration method to be used. It may be selected as such to be resistant to abrasion, puncture, surface slip and/or antiblocking properties. The polyolefin layer **202** may carry an opaque pigment, a transparent color, or tint, and may be receptive to metal deposition or solution and emulsion coating. Decorations may be applied to the interior surface of the polyolefin layer **202** by lamination. In further embodiments where the polyolefin layer **202**, the first adhesive layer **204**, the gas barrier core **216**, and the second adhesive layer are transparent, decorations may be applied to the heat sealing layer **214**.

[0027] The surface polyolefins are selected to enhance heat sealing properties and graphic art properties to permit decorative images and messages to be applied to the balloon envelope. The decoration layer may be constructed of a resin material. Exemplary resin materials include polyolefin resins, copolymers of polyolefins (e.g., polyethylene, polypropylene, copolymers of polyethylene with minor amounts of other C4-10 olefins, particularly C4-8 polyolefins), or polymer resins (e.g. polyamides, polyesters, copolymers of ethylene and vinyl alcohol and the like.) Polyethylenes may include HPLDPE resins, or LLDPE resins having a density of from about 0.925 to about 0.945 g/cm³. Polymers may include polypropylenes, preferably isotactic, having a density of from about 0.89 to about 0.91 g/cm³. The polyolefin layer **202** may include any of several anti-cling, slip or anti-block additives (e.g., silicas, talcs, diatomaceous earth, silicates, or lubricants) to improve the slip characteristics of the layer.

These additives are generally blended with the resin material in a predetermined amount (e.g., from about 100 to about 20,000 ppm.)

[0028] The heat sealable outer layer **214** allows the non-conductive balloon film to form a gas tight seal by heat or ultrasonic sealing of the balloon envelope. The heat sealable outerlayer **214** may be made of a resin such as polypropylene (PP), ethylene propylene copolymers, low density polyethylene (LDPE), linear low density polyethylene (LLDPE), medium density polyethylene (MDPE), high density polyethylene (HDPE), metallocene-catalyzed polyethylene (mPE), very low density polyethylene (VLDPE), or ultralow density polyethylene (ULDPE). The resin may also be blended to achieve a desired range of sealing, hot tack, physical or mechanical properties of the final film product. Homopolymers, terpolymers, or copolymers of ethylene and alpha-olefins such as metallocene catalyzed linear low density polyethylene (mLLDPE) may also be used. In various embodiments of copolymers, the weight percentage of the alpha-olefins resins may range between 4 and 15% (e.g., from 6 to 12% or from 6 to 10%) by weight. Alpha-olefin comonomers include propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, and 1-octene may also be used. The alpha-olefins range from about C3 to C20 (e.g., from C3 to C10, or from C3 to C8.)

[0029] Some embodiments may comprise a metal layer. The metal layer may be vapor deposited and used for graphic or gas barrier purposes. The metal layer may be applied by various deposition methods such as vapor deposition, sputtering, electron beam evaporation, printing or coating using a reflective metal bearing ink and deposition using wet deposition systems using silver and copper bearing solutions mixed with a reducing agent to produce a silver or copper deposition on a surface. The metal layer may be coated with a non-sealable and non-conductive polymeric overcoating.

[0030] In various embodiments, the polymeric overcoating may be added by an in-chamber coating process. The monomeric materials utilized may be relatively low in molecular weight, between 150 and 1000, and preferably in the range 200 to 300. In one embodiment, polyfunctional acrylates or mixtures of monofunctional acrylates and polyfunctional acrylates are used. In various embodiments, the monomers or monomer mixtures have an average of about two or more double bonds (i.e., a plurality of olefinic groups) and have vapor pressure in the range of 1.times.10.sup.-6 Torr to 1.times.10.sup.-1 Torr at standard temperature and pressure, (i.e., relatively low boiling materials). In one embodiment, the monomers or monomer mixtures have a vapor pressure of approximately 10.sup.-2 Torr at standard temperature and pressure. These high-vapor-pressure monomers can be flash vaporized at relatively low temperatures and thus are not degraded (cracked) by the heating process. The deposited monomer is reactive and cures to form an integral film when exposed to a radiation source. Accordingly, a substantially continuous coating is provided even though the deposited film may be very thin.

[0031] A vacuum chamber may be evacuated until the pressure is less than 1.times.10.sup.-1 Torr, and preferably 1.times.10.sup.-5 Torr. In various embodiments, the vacuum chamber includes a substrate support such as a rotating drum. The support may be removable or interchangeable and has a surface of which the temperature is maintained sufficient to permit condensation onto the metallized substrate surface of a material that is being deposited thereon. The temperature

may be in the range of 40° C. to 70° C., depending on the monomer or the monomer mixture used. The curable monomer may be metered to a heated flash vaporizer system where the material is atomized, vaporized, and condensed on the surface of the movable metallized film, which travels at a speed between 1 and 1000 cm per second. In one embodiment, the vapor outlet of a flash vaporizer and the curing means may be mounted such that the metallized film is exposed to the flash vaporizer prior to being treated by the curing means. The curing is accomplished by opening the double bonds of the reactant molecules, such as by using an energy source (e.g., an apparatus that emits infra-red, electron beam, thermionic, or ultra violet radiation.) The condensed film is less than 4 microns thick.

[0032] In other embodiments, the metal layer may be coated with a non-conductive film layer such as via an out of line solution, emulsion, extrusion coating or related printing process, a spray coating process or by adhesive, thermal or extrusion lamination process.

[0033] In various embodiments, the metallized film is unwound (e.g., by tension) and guided into a coating machine. The coating machine may clean or pretreat the metal surface to aid adhesion of subsequently applied coatings. The metallized film may subsequently pass a coating station where the coating solution or ink is applied. The coating solution or ink may be applied by the coating and printing methods such as direct or indirect gravure, air knife coating, Myer rod coating, spray coating or the like. The surface of the coated metallized film may further be dried by a method suitable for the applied coating or ink.

[0034] The metallized film may be placed on an unwind station close to the coating station such that the metal surface is not contacted by the roller surfaces prior to the nip point. A separate extruder may be used to prepare a continuous supply of the molten polymer (e.g., LDPE) to be used as a coating layer. The metallized film is unwound, passed into the extrusion coater, passed over a nip roller, and pressed against a temperature-controlled roller adjacent to the nip. With the nip closed, the molten LDPE coating is extruded from a die as a thin molten membrane. The thin molten membrane may be dropped between the metallized film and the temperature controlled roll surface, which are adhered together at the nip point. The coated film may be cooled by a temperature controlled roller to a uniform temperature. The coated film may be subsequently wound into rolls to create balloons. In various embodiments, the coated LDPE layer may be opaque, clear, or pigmented.

[0035] In another embodiment, a laminating film, that is, a film to be laminated onto the metallized surface may be placed on a separate unwind station. The laminating film and the metallized film may be simultaneously unwound and passed into the laminator. Applying an adhesive, the two films may be adhered together by the lamination adhesive at a nip. The lamination adhesive may be a one or two part adhesive. In one embodiment, a one-part adhesive is diluted with solvent and applied to the lamination films. In another embodiment, a two part adhesive is mixed and applied to the lamination film. The lamination process continues with the film being passed through a curing oven and heated to initiate the adhesives curing reaction and cooled. The lamination adhesive may be a multiple layer coextrusion designed to enhance lamination adhesion and/or barrier properties.

[0036] In a further embodiment, a thermal laminating film, that is, the film to be thermally laminated to the metallized

surface is placed on a separate unwind station. The thermal laminating film is passed over a temperature-controlled roller adjacent to the laminating nip to activate the thermal adhesive layer. The metallized film is passed over the laminating nip. With the laminating nip closed, the thermally activated adhesive is pressed against the metal surface of the metallized film to form a bond. The lamination continues with the film being passed around the temperature controlled roller and subsequently to a second temperatures controlled roll cool the thermally laminated film to a uniform temperature.

[0037] In further embodiments, a reflective film may be applied to or deposited on an outer surface of the non-conductive film such as the decoration layer **202**. The reflective film may be discontinuous or patterned metal. The patterned vapor deposition may enhance the gas barrier properties of the film, and may also enhance the graphic appeal by adding a highly reflective surface while eliminating conduction across the balloon surface. The metal layer may be produced by processes for producing patterned metal deposits. For example, the use of aluminum or copper vapor deposition with a moving mask, masking bands to shadow the film surface, an oil-printing roll producing printed or patterned oil layers placed on the film surface to prevent adhesion of the aluminum or copper vapors on the film surface. As such, a plurality of individual, physically isolated aluminum or copper deposits may be created.

[0038] The discontinuous or patterned, metal layer may be created by various processes. In one embodiment, the moving substrate may be printed with an organic liquid to form a base pattern. A metal layer may be deposited to cover the printed substrate thereby creating a plurality of complementary metal pattern areas covering the printed substrate. The substrate is subsequently heated to vaporize the base pattern leaving the complementary metal patterns applied to the film. In another embodiment, a metal pattern may be created by selective chemical etching, or printing and etching a metallized film with a 100% metal surface coverage. The metallized film may be printed with an etchant, such as a caustic material, to selectively remove the metal deposit from the film surface in the printed area to leave a complementary metal pattern, washing the etchant from the film surface and drying the film prior to winding. Alternatively, the metallized film may be printed to form an image with a material resistant to the chemical attack of an etchant. The printed film may be subsequently passed through a bath of etchant material for a period of time sufficient to remove the metal layer not protected by the etchant resistant material. The etched material may be washed to remove excess etchant and dried prior to winding.

[0039] In a further embodiment, a film may be coated with a water soluble varnish applied over the entire film surface using a rotogravure printing machine or a similar coater. The film may be vacuum metallized to deposit a metal layer over the entire surface of the film, coated with the varnish. The metallized surface of the film may be printed with clear or pigmented water resistant inks using a rotogravure or similar printing system to create a printed image. Subsequently, the printed metallized varnished film may be washed with water to remove the areas not protected with the water resistant coatings to remove the water soluble varnish and the metal layer applied to it, followed by drying. As such, a patterned metallized film may be obtained. The film thus created has clear un-metallized areas as well as printed areas with the

metal layer under the printed image. The printed image may be made of multicolored inks or clear inks.

[0040] In yet a further embodiment, a patterned metallized film may be prepared with a complementary metal oxide pattern. A preexisting metallized film may be printed with a pattern of hydrophobic ink to the metal surface. The printed, metallized film may be immersed into water heated to a temperature of approximately 80° C. or greater. As such, the warm water converts the metal layer not covered by the hydrophobic ink to the non-conductive metal oxide.

[0041] In various embodiments, each of the isolated metallized areas of the instant invention comprise a two-dimensional pattern of continuous deposits of the metal layer, which are continuous layers of vapor deposited metal physically separated by clear film areas. The metal deposits are essentially two-dimensional patterns or islands of, isolated, continuous, conductive deposits of metal, physically isolated from other deposits by physical spacing's of non-conductive areas formed in the metal layer. The films are non-conductive due to the presence of un-metallized areas surrounding and electrically isolating the two-dimensional metal deposits from adjacent metallized areas. The isolating nonconductive areas may be clear, metal free areas such as those formed by chemical etching, or from the formation of nonconductive oxide layers produced on the metallized film. The width of the spacing creates the loss of conduction and prevents electrical breakdown at a defined voltage applied to the discontinuous metal deposit. The exact dimensions of the non-conductive areas separating the individual conductive areas may be a function of the voltage applied to exposed pattern metallized surfaces and the polymer surface on which the metal is deposited. The dimensions of the non-conductive areas are to be chosen based upon the substrate polymer and the maximum voltage to which they are to be exposed. The films produced with a plurality of individual, physically isolated metal (e.g., aluminum or copper) deposits are non-conductive over large areas of the film. The bright reflective characteristics are maintained due to the multiplicity of individual continuous layers of reflective metal deposits, and electrical conduction across the surface when exposed to the physical separation of the individual physically isolated deposits is prevented.

[0042] In further embodiments, a nonconductive polymer film may be deposited onto the reflective film thereby reducing the potential for high voltage electrical conductance. This nonconductive polymer film may be deposited by an in chamber coating process, via an out of line solution, emulsion, extrusion coating or related printing process, a spray coating process or by an adhesive or extrusion lamination process. In some embodiments, the patterned metal deposition can also be applied to the inner surface of a non-conductive balloon film such as the heat sealing layer **214** illustrated in FIG. 2. The patterned deposition may be applied in register to a predefined balloon envelope shape to prevent diminishing the sealing functions of the inner sealing layer of the balloon envelop. In other embodiments, the deposited pattern can be designed such that the gas tight nature of the heat sealing area is not effected.

[0043] In various embodiments, the thickness of the films range from approximately 0.25 mil (25 gauge, or 6.25 microns) to 4 mil (400 gauge, 100 microns). In some embodiments, the thickness of the films range between 0.5 mil (50 gauge, or 12.5 microns) to 3 mil (300 gauge, 75 microns). In further embodiments, the thickness of the films range between 0.7 mil (70 gauge, or 18 microns) to 1.5 mil (150

gauge, 38 microns). The thickness of the gas barrier layer may be dependent on the structure of the envelop films, the desired flight times and the barrier polymer compositions chosen for any particular film design. The films may have a barrier layer thickness ranging from 80% to 25% of the total film thickness, tie layer thicknesses ranging from 10% to 40% of the total film thickness and surface sealing layers ranging from 5% to 40% of the total film thickness.

[0044] The optimum thickness of the balloons envelope film and total barrier layer thickness may be determined by the volume of the balloon envelope, the buoyancy produced by the volume of helium and the helium permeability requirements based on the flight time requirements. Flight times may be determined from loss in buoyancy due to helium permeability through the films as long as the weight and helium permeability of a balloon film are known. If flight time is specified for a given envelope size, the required helium permeability may be determined and the barrier structure (e.g., the selection of polymer, the layer structure, and the barrier layer thickness) of the envelope film can be selected.

[0045] The barrier layer composition, thickness and structure may be determined by balloon envelope size. Although larger volume balloons may have more buoyancy than smaller balloons and can lift a larger mass of film than smaller balloons, the surface area for diffusion of helium is larger which requires an increased thickness of the barrier polymer. Consequently, the envelope film weight, determined by the composite film density, thickness and envelop area must vary based on the balloon volume.

[0046] The optimum sealing layer thickness is determined by the sealant polymers ability to form hermetic seals at a given layer thickness and may be less sensitive to total envelope thickness. The sealant layer thickness may range from approximately 0.10 mils (2.5 microns) to 1.0 mil (25 microns). In some embodiments, the sealant layer thickness may range from 0.16 mil (4.0 microns) to 0.75 mil (19 microns). In further embodiments, the sealant layer thickness ranges from 0.24 mil (6.0 microns) to 0.50 mil (12.5 microns). The thickness of metallized barrier films range from approximately 0.25 mil (25 gauge, or 6.25 microns) to 4 mil (400 gauge, 100 microns). In some embodiments, the thickness ranges from 0.5 mil (50 gauge, or 12.5 microns) to 3 mil (300 gauge, 75 microns). In further embodiments, the thickness ranges from 0.7 mil (70 gauge, or 18 microns) to 1.5 mil (150 gauge, 38 microns). FIG. 3 illustrates an exemplary 7-layer non-conductive films **300** in accordance with various embodiments of the present application. The illustrated non-conductive balloon film **300** comprises a polyolefin layer **302**, a first adhesive layer **304**, a gas barrier core **316**, a second adhesive layer **312**, and a heat sealing layer **314**. The gas barrier core **316** comprises a first EVOH gas barrier layer **306**, an adhesive layer **308**, and a second EVOH gas barrier layer **310**. The EVOH barrier layers **306** and **310** may affect the gas barrier properties of the film **300**. In particular, the specific ethylene content of a EVOH copolymer may affect the gas barrier properties of the film **300**. The EVOH barrier layers **306** and **310** may be determined according to a predetermined level of barrier and flex crack resistance. In addition, the polyolefin layer **302** and the adhesive layers **304**, **308**, and **312** may affect the flex crack resistance. For embodiments that do not comprise a nylon layer such as the illustrated non-conductive film **300**, moisture level of the EVOH may be controlled according to the inherent moisture barrier of the polyolefin layer **302** and the adhesive layers **304**, **308**, and

312. In other embodiments, the EVOH layers included in the illustrated film **300** may be replaced by nylon layers.

[0047] FIGS. 4A-4B illustrate exemplary 9-layer non-conductive films **400** and **450** in accordance with various embodiments of the present application. The film **400** comprises a gas barrier core **420** made of nylon whereas the film **450** comprises a gas barrier core **470** made of EVOH. The film **400** is similar to the 7-layer structure of the film **200** illustrated in FIG. 2 where the gas barrier core is composed by alternating gas barrier layers (e.g., a nylon layer) and EVOH layers. The film **450** is similar to the 7-layer structure of the film **300** illustrated in FIG. 3 where the gas barrier core is composed by alternating EVOH layers and adhesive layers or alternating nylon layers and adhesive layers.

[0048] FIGS. 5A-5B illustrated exemplary 11-layer non-conductive balloon films **500** and **550** in accordance with various embodiments of the present application. The film **500** comprises a gas barrier core **524** comprising nylon gas barrier layers whereas the film **550** comprises a gas barrier core **570** comprising EVOH gas barrier layers. The film **500** comprises a nylon print and barrier layer **502**, which is affixed to the polyolefin layer **506** by the adhesive layer **504**. The film **550** comprises a nylon print and barrier layer **552**, which is affixed to the polyolefin layer **556** by the adhesive layer **554**. The gas barrier core **524** is further affixed to the polyolefin layer **506** by an adhesive layer **508** and the gas barrier core **574** is affixed to the polyolefin layer **556** by an adhesive layer **558**. The gas barrier core **524** comprises alternating EVOH layers and nylon gas barriers. The gas barrier core **574** comprises alternating EVOH gas barrier layers and adhesive layers. The gas barrier core **524** may be further affixed to the heat sealing layer **522** by the adhesive layer **520** and the gas barrier core **574** may be further affixed to the heat sealing layer **572** by the adhesive layer **570**.

[0049] The adhesive layers **504**, **508**, and **520** may be different from each other, and the adhesive layers **554**, **558**, **562**, **566**, and **570** may be different from each other. Each of the adhesive layers may be selected to be the optimum for affixing the adjacent two layers. The relative thickness of the polyolefin layers **506** and **556** may control the placement of the barrier cores **524** and **574** to the centerline of the films **500** and **550**, respectively. In various embodiments, the barrier cores **524** and **574** are placed closer to the heat sealing layers **522** and **572** than the centerline of the films **500** and **550**, respectively. A thicker polyolefin layer may provide a better barrier against moisture because the gas barrier layer may be sensitive to moisture from the environment.

[0050] FIGS. 6A-6C illustrate exemplary non-conductive films **600**, **620**, and **640** having a barrier core with a nano-layer structure in accordance with various embodiments of the present application. In various embodiments, a barrier core such as the barrier core **216** illustrated in FIG. 2, may comprise a set of gas barrier layers. Any two gas barrier layers of the set of barrier layers may be separated by a polymer layer. For example, in the illustrated example of FIG. 2, the barrier core **216** comprises a first gas barrier layer **206** and a second gas barrier layer **210**, separated by a polymer layer, that is, the EVOH layer **208**. In various embodiments, at least one barrier layer of the set of barrier layers may have a nano-layer structure. For example, the barrier layer having a nano-layer structure may comprise a set of sub-barrier layers, where any two adjacent sub-barrier layers may be separated by a sub-polymer layer. In one embodiment, a barrier layer may comprise at least eight (8) sub-barrier layers, where the

adjacent sub-barrier layers are separated by a sub-polymer layer. The sub-polymer layer may be a barrier resin or a non-barrier resin.

[0051] In the illustrated examples, the non-conductive balloon film **600** comprises a barrier core **606** having a nano-layer structure. The barrier core **606** comprises a set of nylon layers and a set of adhesive layers, where the set of nylon layers and the set of adhesive layers are arranged as a nano-structure. In various embodiments, the illustrated barrier core **606** may have a nano-layer structure of 16 to 64 alternating nylon and adhesive layers. The nylon material included in the barrier core **606** may be selected according to a predetermined gas barrier required such that to control the float time of a balloon.

[0052] The non-conductive balloon film **620** comprises a set of EVOH layers and a set of adhesive layers, where the set of EVOH layers and the set of adhesive layers form a nano-structure. The barrier core **626** may comprise a nano-layer structure of 16 to 64 alternating EVOH and adhesive layers. The EVOH included in the barrier core **626** may be selected according to a predetermined gas barrier required such that to control the float time of a balloon.

[0053] Further embodiments may comprise a barrier core made of nylon and EVOH blending materials. EVOH provide a better gas barrier capability than nylon but the cost of EVOH is higher than the cost of nylon. A material made by blending nylon with EVOH (e.g., with a nylon composition of 20% to 40%) may improve the EVOH ductility without compromising the EVOH gas barrier capabilities. The barrier core **646** may comprise a nano-layer structure of 16 to 64 nylon and EVOH blended layers.

[0054] The non-conductive balloon film **640** comprises a nano-layer barrier core **646** comprising a set of alternating EVOH layers and nylon layers. Each of the set of EVOH layer is a gas barrier layer and each of the set of nylon layers is a synergistic or adhesive layer. Sandwiching an EVOH layer between two nylon layers may improve the durability of the EVOH layer. In addition, a nylon layer may function as a desiccant layer to maintain the EVOH layer at a lower moisture content thereby maintaining the gas barrier property of the EVOH layer as a nylon layer absorbs and binds more moisture than an EVOH layer. Nevertheless, a EVOH layer cannot be too thin such that the Nylon layer affects the crystalline development of the EVOH layer and decrease the EVOH gas barrier layer giving a sudden loss in gas barrier with the increase in the number of layers.

[0055] In some embodiments, a gas barrier core having a nano-layer structure may be located centrally in a non-conductive balloon film or off centered towards either of the surfaces. In other embodiments, a gas barrier core may comprise a set of sub-gas barrier cores. FIG. 7 illustrates an exemplary balloon film **700** having a barrier core having multiple sub-barrier cores, where each of the sub-barrier core has a nano-layer structure in accordance with an embodiment of the present application. The non-conductive balloon film comprises a barrier core **720**. The barrier core **720** comprises a first barrier core **706** and a second barrier core **714**. The first barrier core **706** and the second barrier core **714** are separated by a polyolefin layer **710**. The polyolefin layer **710** may comprise multiple layers of polymers. The first barrier core **706** and the second barrier core **714** each may have a nano-structure with 16 to 32 alternating EVOH and adhesive layers. In other embodiments, the first barrier core and the second barrier may have a nano-structure with 16 to 32 alternating

nylon and adhesive layers. Alternatively, the first nanolayer barrier core may have a nano-structure with 16 to 32 alternating Nylon layers while the second nanolayer barrier core may have a nano-structure with 16 to 32 alternating EVOH layers. The first barrier core and the second barrier may each have a nano-structure with 16 to 32 alternating nylon and EVOH layers.

[0056] Various embodiments comprise a biodegradable or bio-based film. In some embodiments, each layer of the non-conductive balloon film is biodegradable, compostable, or bio-based. The biodegradable film or bio-based film is a polymer film where at least 80% of the polymer film by weight is derived from a non-petroleum or biorenewable feedstock. Up to about 20% of a biodegradable, compostable, or bio-based film may be a polymer sourced from petroleum. The biodegradable or bio-based films may be made of materials such as polyhydroxybutyrate-valerate (“PHBV”), polylactide (“PLA”), or polyhydroxy-alkanoate (“PHA”). In some embodiments, a biodegradable or bio-based film may be made of polylactic acid (also known as “PLA.”) The PLA is a compostable, thermoplastic, and aliphatic polyester derived from lactic acid, and may have physical properties similar to PET and excellent clarity. The PLA may be produced in a high molecular weight form through ring-opening polymerization of lactide or lactic acid by use of a catalyst and heat. The PLA may be made from plant-based feedstock (e.g., soybeans, corn, wheat, or sugar beets) or from the fermentation of agricultural by-products (e.g., corn starch) or other plant-based feedstock. The PLA can be processed like most thermoplastic polymers into a film. PLA films degrade into carbon dioxide and water at temperatures above its glass transition temperature. In one embodiment, the bio-based film layer comprises at least about 90% polylactic acid.

[0057] In some embodiments, the biodegradable or bio-based film is made of PHA, which is a polymer belonging to the polyesters class and can be produced by microorganisms as a form of energy storage. Microbial biosynthesis of PHA may start with the condensation of two molecules of acetyl-CoA to create acetoacetyl-CoA, which may be subsequently reduced to hydroxybutyryl-CoA. Hydroxybutyryl-CoA may be used as a monomer to PHA such as polymerize Polyhydroxybutyrate (“PHB”).

[0058] Various embodiments including PLA, PHA (e.g., PHB), or polyhydroxybutyrate-valerate (“PHBV”) can be produced by coextruding the biodegradable, bio-based polymers into a film sheet in combination with a gas-barrier core. The bio-based films may replace polyolefin resins included in a non-conductive film, such as those used in the synergistic, the intermediate layers and the surface layers of the film. Various embodiments may be cast or blown or oriented in the machine direction or the transverse direction. In one embodiment, the bio-based film comprises a biaxially oriented film. In one embodiment, PHBV rich blend resin may be coextruded onto a surface of a bio-based film to form a surface layer, upon which graphics may be printed. Heat sealable surface layers of PHBV, PHB or PLA may also be used to form the heat sealing surface of a non-conductive balloon film. A biodegradable or bio-based film may also be solvable in water and extrudable, such as polyglycolide or Polyglycolic acid (“PGA”), or similar natural barrier polymers.

[0059] FIG. 8 illustrates an exemplary non-conductive balloon film **800** in accordance with an embodiment of the present application. The non-conductive balloon film **800** comprises a ceramic layer **802**, a high barrier deposition skin

804, a gas barrier core **806**, and a heat sealing layer **808**. The gas barrier core **806** may comprise a set of oriented nylon, PET, or OPP sheets. The ceramic layer **802** may be materials such as SiO₂, SiO_x, Al₂O₃, CeO₂, Ce₂O₃, or AlO_xNy, and the ceramic layer **802** may be deposited onto the high barrier deposition skin **804**. The high barrier deposition skin **804** may be the decorating surface of the non-conductive balloon film **800**. The high barrier deposition skin **804** may be made of materials such as an amorphous nylon, amorphous PET, EVOH, PET or flame treated HDPE may optimize the barrier properties of the ceramic layer **802**. The deposition skin **804** may be selected according to the materials of the ceramic to provide an optimum surface for optimizing the gas barrier property of the ceramic selected. In various embodiments, the ceramic layer **802** may be top coated or laminated. In another embodiment, the ceramic layer **802** may be replaced with a metal deposited layer. The metal-deposited layer **802** may be materials such as, Al, Cu, Ag, Au, Ni.

[0060] FIGS. 9A-9E illustrated exemplary non-conductive balloon films **900**, **920**, **940**, **960**, and **980** in accordance with various embodiments of the present application. The non-conductive balloon film **900** comprises a laminated film layer **902**, a lamination layer **904**, a metal layer **906**, a gas barrier core **908**, and a heat sealing layer **910**. The metal layer **906** may be a layer of continuous metal deposited on the gas barrier core **908**. In one embodiment, the metal layer **906** is a vapor deposited aluminum layer. The metal layer **906** may enhance the gas barrier properties of the film **900** and may further increase the balloon float time. The laminated film layer **902** may be surface or reverse printed, and may be PET or OPP based. The lamination layer **904** is affixed to the surface of the metal layer **906** by adhesive, thermal, or extrusion lamination. The adhesives may be one or two part adhesives, and the extrusion adhesive layer may be LDPE. The laminated film layer **902** may be affixed to the metal deposition by using the 12 micron PE extrusion lamination. The laminated film layer **902** may be a non-conductive polymer film and may insulate the metal layer **906**. In various embodiments, the thickness of the laminated film layer **902** may be in the range of 8 to 18 microns.

[0061] Similar to the non-conductive film **900**, the non-conductive films **920** and **940** may comprise a metal layer **924** and a gas barrier core layer **926**, respectively. The coating layers **922** and **942** may be applied to the metal layer **924** and the metal layer **926**, respectively. The coating layer **922** or **942** may be a polyolefin extrusion coating layer having a thickness in the range of 8 to 24 microns. The coating layers **902**, **922**, and **942** may be surface printed. Each of the coating layers **902**, **922**, and **942** may be a solution coated layer using any liquid born film forming polymer and be applied by coating methods such as gravure, airknife, Myer rod or spray.

[0062] The coating layers **902**, **922**, and **942** may be non-conductive polymer (e.g., a polyolefin film or acrylic polymer) and applied to the metal surface via liquid solution or emulsion coating or lamination such as extrusion, adhesive or thermal laminations. As such, the non-conductive layer is directly applied to the metal surface by extrusion coating or liquid coating. The extrusion coating extrudes a molten layer of the polyolefin onto the metal surface, whereas the liquid coating applies a polymer solution or emulsion and removes the solvent by drying leaving an insulating polymer layer. The metal layer is thereby insulated from any electrical current by the resistance of the non-conductive polymer layer deposited on the metal even though the metal layer itself remains con-

ductive. The composition, thickness and defect concentration of the applied polymer films determine the electric breakdown of the non-conductive coating layer.

[0063] The films **960** and **980** each comprise a metal deposition **964** and **984**, respectively. Further, the surfaces of the metal deposition **964** and **984** are treated by adding a non-conductive polymer film **962** and **982**, respectively. As such, the films **960** and **980** are insulated. The non-conductive polymer films **962** and **982** may be applied as a vapor or coated as a liquid to the metal coating layer and subsequently polymerized by UV, Electron or other actinic radiation within the metallization chamber. The gas barrier may be further enhanced by including a second coating layer to the other surface of the metal layer, such as illustrated in FIG. 9E. The gas barrier core layer **988** may be deposited with the coating layer **986** prior to the metal layer **964** being deposited onto the coating layer **986**.

[0064] FIG. 10 illustrates an exemplary non-conductive film **1000** in accordance with an embodiment of the present application. The film **1000** comprises a metal layer **1002** that is deposited onto a surface of the gas barrier core **1004**. The metal layer **1002** may be a patterned metal layer such that the metal film is discontinuous. Accordingly, the surface of the film **1000** is not conductive. The addition of the patterned metal deposit may enhance the gas barrier properties of the film **1000** by decreasing the area of surface diffusion from the film. The metal layer may be further coated similar to the embodiments illustrated in FIGS. 9A-E to improve its graphics capabilities or to protect the metal deposit layer **1002**. The metal layer **1002** may be patterned in a wide range of geometric shapes and carry information such as texts or graphics.

[0065] FIGS. 11A-B illustrate exemplary non-conductive films **1100** and **1120** in accordance with various embodiments of the present application. The films **1100** and **1120** include biodegradable or compostable films to minimize the environmental impact of lost or released balloons. The gas barrier property of the film **1100** may be enhanced by a barrier primer layer **1104** applied by coextrusion. The film **1100** comprises a PETG film skin for high barrier metallization, and the film **1120** comprises a PVOH/EAA inline coated high barrier metallization primer for high barrier metallization. The gas barrier property of the film **1120** may be enhanced by the application a barrier primer layer **1124** by an inline coating process. The heat sealing layers **1108** and **1128** may be amorphous PLA, PHA, PHVB, or other similar materials.

[0066] Various embodiments may be produced by coextrusion. Non-conductive films may be produced by cast coextrusion or blown coextrusion. Films may further be oriented to enhance the physical and gas barrier properties. The films are extensible for balloon envelopes of various shapes when inflated. The embodiments having a nano-layer structure may be produced from alternating barrier resin pairs or by alternating a barrier resin and a non-barrier or synergistic layer resin. The synergistic layer resin may be a resin with either a high or a low chemical bonding with the barrier resin that may enhance a specific mechanical property of the film (e.g., a polyolefin, a tie or bonding resin, or a blend of a mix of polyolefin and bonding resin.) The primary barrier resin may be nylon, EVOH, or a mix of nylon and EVOH. A primary barrier resin may be copolymers of ethylene and vinyl alcohol with an average ethylene content of between 25 mol % to 48 mol %. Other exemplary copolymers may include acrylonitrile copolymers, polyurethane engineering plastics, ethylene vinyl alcohol copolymers, polyvinylidene chloride, liquid

crystal polymers, amorphous nylons, VINEX poly (vinyl alcohol), and Polyglycolic acid or polymethylpentene resins.

[0067] A synergistic layer may comprise a polyolefin, a tie, adhesive, or bonding resin, or a mix of a polyolefin and bonding resin, or a nylon if used in conjunction with an EVOH barrier layer. Exemplary resins include polyolefin resins, or copolymers of polyolefins (e.g., polyethylene, polypropylene, or a combination of thereof). A polymer resin may additionally include copolymers of polyethylene with minor amounts of other C_{4-10} olefins, particularly C_{4-8} polyolefins. In some embodiments, polyethylenes include HPLDPE resins, or LLDPE resins having a density of from about 0.925 to about 0.945 g/cm³. In some embodiments, polymers include polypropylenes such as isotactic, that have a density of from about 0.89 to about 0.91 g/cm³. In other embodiments, an adhesive resin is a modified olefinic polymer containing carboxyl groups obtained by combining chemically (e.g. by addition reaction, graft reaction, etc.) Exemplary olefinic polymers include polyolefins such as polyethylene (low-density, medium-density, high-density), linear low-density polyethylene, polypropylene, polybutene, or a copolymer of an olefin and a comonomer copolymerizable (e.g. vinyl esters, unsaturated carboxylic acid esters etc.) Exemplary copolymers include ethylene-vinyl acetate copolymer and ethylene-ethyl acrylate copolymer. Some embodiments comprise the ethylene-vinyl acetate copolymer (vinyl acetate content 5-55% by weight) and the ethylene-ethyl acrylate copolymer (ethyl acrylate concentration 8-35% by weight).

[0068] The ethylenically unsaturated carboxylic acid or its anhydride includes ethylenically unsaturated monocarboxylic acids, esters thereof, ethylenically unsaturated dicarboxylic acids, mono- or di-esters thereof, and anhydrides thereof. Some embodiments use the anhydrides of the ethylenically unsaturated dicarboxylic acids. For example, maleic acid, fumaric acid, itaconic acid, maleic anhydride, itaconic anhydride, monoethyl maleate, monoethyl maleate, diethyl maleate, or methyl fumarate may be used. One embodiment uses the maleic anhydride. The amount of the ethylenically unsaturated carboxylic acid or its anhydride to be added or grafted to the olefinic polymer. The amount in various embodiments is generally 0.01-15% by weight. In one embodiment, the amount is 0.02-10% by weight.

[0069] In various embodiments, one or more adhesive resins may be used. The adhesives resins may be used singly, as a mixture of two or more thereof, or blended with other synergistic polymers. As such, various embodiments provide excellent flexing endurance. In various embodiments, the thickness of each adhesive resin layer is preferably 2-10 micro-meters (m).

[0070] As used herein, the terms less than, less than or equal to, greater than, and greater than or equal to, may be used herein to describe the relations between various objects or members of ordered sets or sequences; these terms will be understood to refer to any appropriate ordering relation applicable to the objects being ordered.

[0071] While various embodiments of the present invention have been described above, it should be understood that they have been presented by way of example only, and not of limitation. Likewise, the various diagrams may depict an example architectural or other configuration for the invention, which is done to aid in understanding the features and functionality that can be included in the invention. The invention is not restricted to the illustrated example architectures or

configurations, but the desired features can be implemented using a variety of alternative architectures and configurations. Indeed, it will be apparent to one of skill in the art how alternative functional, logical or physical partitioning and configurations can be implemented to implement the desired features of the present invention. Also, a multitude of different constituent module names other than those depicted herein can be applied to the various partitions. Additionally, with regard to flow diagrams, operational descriptions and method claims, the order in which the steps are presented herein shall not mandate that various embodiments be implemented to perform the recited functionality in the same order unless the context dictates otherwise.

[0072] Although the invention is described above in terms of various exemplary embodiments and implementations, it should be understood that the various features, aspects and functionality described in one or more of the individual embodiments are not limited in their applicability to the particular embodiment with which they are described, but instead can be applied, alone or in various combinations, to one or more of the other embodiments of the invention, whether or not such embodiments are described and whether or not such features are presented as being a part of a described embodiment. Thus, the breadth and scope of the present invention should not be limited by any of the above-described exemplary embodiments.

[0073] Terms and phrases used in this document, and variations thereof, unless otherwise expressly stated, should be construed as open ended as opposed to limiting. As examples of the foregoing: the term “including” should be read as meaning “including, without limitation” or the like; the term “example” is used to provide exemplary instances of the item in discussion, not an exhaustive or limiting list thereof; the terms “a” or “an” should be read as meaning “at least one,” “one or more” or the like; and adjectives such as “conventional,” “traditional,” “normal,” “standard,” “known” and terms of similar meaning should not be construed as limiting the item described to a given time period or to an item available as of a given time, but instead should be read to encompass conventional, traditional, normal, or standard technologies that may be available or known now or at any time in the future. Likewise, where this document refers to technologies that would be apparent or known to one of ordinary skill in the art, such technologies encompass those apparent or known to the skilled artisan now or at any time in the future.

[0074] The presence of broadening words and phrases such as “one or more,” “at least,” “but not limited to” or other like phrases in some instances shall not be read to mean that the narrower case is intended or required in instances where such broadening phrases may be absent. The use of the term “module” does not imply that the components or functionality described or claimed as part of the module are all configured in a common package. Indeed, any or all of the various components of a module, whether control logic or other components, can be combined in a single package or separately maintained and can further be distributed in multiple groupings or packages or across multiple locations.

[0075] Additionally, the various embodiments set forth herein are described in terms of exemplary block diagrams, flow charts and other illustrations. As will become apparent to one of ordinary skill in the art after reading this document, the illustrated embodiments and their various alternatives can be implemented without confinement to the illustrated examples. For example, block diagrams and their accompa-

nying description should not be construed as mandating a particular architecture or configuration.

What is claimed is:

1. A film for lighter than air balloons, comprising:
a gas barrier core comprising a set of gas barrier layers and adhesive layers, the gas barrier core having a first surface and a second surface, the gas barrier core comprising a set of polymeric gas barrier layers;
a metal layer deposited onto the first surface of the gas barrier core; and
a heat sealing layer affixed to the second surface of the gas barrier core.
2. The film of claim 1, wherein the metal layer comprises a sheet of continuous metal.
3. The film of claim 2, wherein the metal layer is a vapor deposited aluminum layer.
4. The film of claim 2, further comprising a lamination layer affixed to the metal layer.
5. The film of claim 3, wherein the lamination layer is affixed to the metal layer by adhesive or extrusion lamination.
6. The film of claim 2, further comprising a laminated film layer affixed to the lamination layer, wherein the laminated film layer comprises a non-conductive polymer film.
7. The film of claim 6, wherein the thickness of the laminated film layer is between 8 and 18 microns.
8. The film of claim 2, wherein the metal layer is coated with a layer of non-conductive polymer.
9. The film of claim 1, wherein the metal layer is discontinuous and comprises a set of isolated metal patches.
10. The film of claim 8, wherein the layer of non-conductive polymer comprises polyfunctional acrylates.
11. The film of claim 10, wherein the layer of non-conductive polymer comprises a mixture of polyfunctional acrylates and polyfunctional acrylates.
12. The film of claim 11, wherein the layer of non-conductive polymer comprises a monomer having at least two double bonds.

13. The film of claim 12, wherein the monomer has vapor pressure in the range of 1×10^{-6} Torr to 1×10^{-1} Torr.

14. A method of creating a film for lighter than air balloons, comprising
printing on a substrate to create a pattern;
depositing a metal layer on the substrate to cover the pattern; and
heating the substrate to vaporize the pattern thereby creating a discontinuous metal layer on the substrate.

15. The method of claim 14, wherein the substrate comprises a gas barrier core comprising a set of gas barrier layers and adhesive layers, the gas barrier core having a first surface and a second surface, the gas barrier core comprising a set of polymeric gas barrier layers, wherein the discontinuous metal layer is the first surface.

16. The method of claim 15, further comprising affixing a heat sealing layer to the second surface of the gas barrier core.

17. A method of creating a film for lighter than air balloons, comprising
depositing a metal layer on a first surface of a substrate;
coating the metal layer with a varnish;
printing on the varnish such that a set of regions of the varnish is not covered by an ink; and
removing the set of regions of the varnish.

18. The method of claim 17, wherein the substrate comprises a gas barrier core comprising a set of gas barrier layers and adhesive layers, the gas barrier core having a first surface and a second surface, the gas barrier core comprising a set of polymeric gas barrier layers, wherein the discontinuous metal layer is the first surface.

19. The method of claim 18, further comprising affixing a heat sealing layer to the second surface of the gas barrier core.

20. The method of claim 17, wherein the ink is water resistant.

* * * * *