

(19) **United States**

(12) **Patent Application Publication**
Qiao et al.

(10) **Pub. No.: US 2016/0126535 A1**

(43) **Pub. Date: May 5, 2016**

(54) **MITIGATING THERMAL RUNAWAY IN LITHIUM ION BATTERIES USING DAMAGE-INITIATING MATERIALS OR DEVICES**

Related U.S. Application Data

(60) Provisional application No. 61/831,437, filed on Jun. 5, 2013.

Publication Classification

(71) Applicant: **THE REGENTS OF THE UNIVERSITY OF CALIFORNIA,**
Oakland, CA (US)

(72) Inventors: **Yu Qiao**, San Diego, CA (US); **Weiyi Lu**, La Jolla, CA (US); **Yang Shi**, La Jolla, CA (US); **Anh Lee**, La Jolla, CA (US)

(73) Assignee: **THE REGENTS OF THE UNIVERSITY OF CALIFORNIA,**
Oakland, CA (US)

(51) **Int. Cl.**
H01M 2/34 (2006.01)
H01M 10/0525 (2006.01)
H01M 10/058 (2006.01)
H01M 2/12 (2006.01)

(52) **U.S. Cl.**
CPC **H01M 2/348** (2013.01); **H01M 2/1247** (2013.01); **H01M 10/0525** (2013.01); **H01M 10/058** (2013.01); **H01M 2200/10** (2013.01); **H01M 2220/20** (2013.01)

(21) Appl. No.: **14/893,893**

(22) PCT Filed: **Jun. 5, 2014**


(86) PCT No.: **PCT/US14/41051**


§ 371 (c)(1),
(2) Date:

Nov. 24, 2015

(57) **ABSTRACT**

A method of manufacturing a battery includes introducing a first material to the battery, providing an anode, a cathode and a separator of the battery; and assembling the anode, the separator and the cathode. The first material is configured and arranged to increase the internal impedance of the battery upon mechanical or thermal loading.








FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5C




FIG. 5B




FIG. 5D




FIG. 5E




FIG. 5F




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 7A




FIG. 7B




FIG. 7D




FIG. 7C




FIG. 7E




FIG. 7F




FIG. 7G




FIG. 7H




FIG. 7I




FIG. 7J




FIG. 7K




FIG. 8A




FIG. 8B




FIG. 8D




FIG. 8C




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 10A




FIG. 10B




FIG. 11A




FIG. 11B




FIG. 12A




FIG. 12B




FIG. 12C




FIG. 13B




FIG. 13C




FIG. 14A




FIG. 14B




FIG. 15A




FIG. 15B




FIG. 15C




FIG. 15D




FIG. 15E




FIG. 15F




FIG. 15G




FIG. 15H




FIG. 16A




FIG. 16B




FIG. 16C




FIG. 16D




FIG. 17A




FIG. 17B




FIG. 17C




FIG. 17D




FIG. 17E




FIG. 17F

Fig. 18A




Fig. 18B





Fig. 18C






Fig. 19A




Fig. 19B




Fig. 20A




Fig. 20B




Fig. 21A




Fig. 21B

2112




Fig. 21C




Fig. 22A




Fig. 22B




Fig. 23B




Fig. 23D




Fig. 23A




Fig. 23C




Fig. 24A




Fig. 24B

MITIGATING THERMAL RUNAWAY IN LITHIUM ION BATTERIES USING DAMAGE-INITIATING MATERIALS OR DEVICES

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims priority to U.S. application Ser. No. 61/831,437 filed on Jun. 5, 2013, which is incorporated herein by reference. This patent application is related to U.S. application Ser. No. 61/831,455 filed Jun. 5, 2013, and entitled, “Non-Straight, Hollow, and/or Frictional Battery Cells/Structures as Protection and Structural Components”, and PCT application filed on the same day as this application, titled “Rate-sensitive and self-releasing battery cells and battery-cell structures as structural and/or energy-absorbing vehicle components”, both of which are hereby incorporated by reference.

FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

[0002] The invention was made with government support under DE-AR0000396 awarded by the Department of Energy. The government has certain rights in this invention.

BACKGROUND

[0003] Lithium-ion batteries are widely used because of their high energy density. However, their safety, especially when subjected to mechanical or thermal abuse, is a major concern. For instance, as a Li-ion battery is impacted or involved in a collision, internal shorting, e.g., direct contact of cathode and anode due to rupture of membrane separator, can happen, which can lead to thermal runaway.

[0004] Chemically protective techniques such as the use of advanced cathode materials, such as LiMn_2O_4 , LiFePO_4 , which release less or no oxygen during decomposition, help to improve the safety of Li-ion batteries. Similarly, alternative anode materials, e.g. $\text{Li}_4\text{Ti}_5\text{O}_{12}$, which reduce heat generation at elevated temperature and even absorb oxygen have also been used. Multifunctional components, such as flame retardant and/or self-healing materials can also be added into the battery housing.

[0005] In addition, mechanically protective techniques, such as the use of protective battery pack mount and housing, can reduce physical damages caused by external loadings. Low aspect ratio tube cell structure, which enhances air flow in the battery module and pack, can facilitate better thermal management.

[0006] Some techniques use phase change materials (PCM) to absorb heat; or use positive temperature coefficient (PTC) elements, which expand to increase impedance once the internal temperature of the battery cell reaches a threshold value; or use phase transition materials that initiate local volume mismatch operate after thermal runaway has begun. Low-melting-point membrane separators or particles can block ion transport paths operate after thermal runaway has begun.

SUMMARY

[0007] More efficient methods that include thermal runaway shutdown mechanisms that can be triggered either mechanically or thermally, or simultaneously, as battery damage happens (i.e., before or shortly after thermal runaway

starts) are desired. The present systems and techniques can operate before or shortly after thermal runaway has begun. Mechanisms that operate before thermal runaway has begun offer better control of material behavior and obviate the need for a relatively high local temperature to be achieved before mitigation mechanisms are deployed.

[0008] The methods and systems disclosed herein have working temperatures that are below the boiling points of flammable liquids in Li ion batteries (e.g. ethyl methyl carbonate), and the effectiveness of the methods disclosed herein has been validated. The methods and systems disclosed herein can work directly under mechanical loading when battery cell is subjected to mechanical abuse (e.g. impact or collision). The materials used in the systems disclosed herein do not have negative effects on the electrochemical performance of battery, and, are therefore relevant to high-power batteries.

[0009] When a battery is subjected to dynamic loading, such as an impact, or high-pressure quasi-static loading, its internal structure can be damaged, causing internal shorting. Under this extreme condition, the above mentioned technique may not fully prevent thermal runaway. New techniques to mitigate thermal runaway simultaneously as or even before internal shorting takes place (that is, before the temperature increases) while the batteries are under mechanical abuse, are desired.

[0010] As a mechanical load is applied to the battery, damage initiators can trigger widespread damage or destruction of the electrode, so that the internal resistance increases significantly to mitigate thermal runaway even before it can happen. The damage of electrodes can be induced under a wide range of loading modes.

[0011] For example, hollow carriers containing fire extinguishing agents (FEA), thermal runaway retarders (TRR), electrolyte absorbers (EA), and/or gas generation agents (GGA), can be broken once the battery is subjected to mechanical loading, so that FEA, TRR, EA, and/or GGA can be released to suppress thermal runaway and reduce the risk of fires.

[0012] The hollow carriers of FEA, TRR, EA, or GGA may also act as cracking/voiding promoters. For instance, FEA, TRR, EA, or GGA can be sealed in micro-capsules or hollow fibers. When an external force applied on the battery exceeds a threshold value, a sealing layer in the hollow carriers is broken and FEA, TRR, EA, or GGA would be released to interrupt transmission of oxygen or ions. The size, materials, and the strength of the capsules can be adjusted.

[0013] Granular materials, fibers, arrays or meshes, and elastic energy storage materials (e.g. springs) can also be mixed with electrode materials or be placed near the electrode materials. When external loadings are applied to the cell, widespread cracking, rupture, and/or voiding can be initiated. Consequently, internal resistance increases significantly, suppressing electro-chemical reactions. In other words, the granular materials, fibers, arrays or meshes, and pre-stressed elastic energy storage materials serve as damage initiators (DI). They can be porous or hollow and carry FEA, TRR, EA, or GGA in them. The type of materials, the amount, the porosity, the size, the shape, the surface properties, and the locations and distributions of the damage initiators can be adjusted.

[0014] The charge collectors, separation membranes, and battery cell cases can be specially designed to act as DI. For instance, as the charge collectors are wavy or have a certain

surface patterns, as the battery cell is deformed local shearing, bending, torsion, or compression can be promoted in electrodes, so that widespread damage of electrodes is achieved.

[0015] The above damage initiators can also be thermally responsive, enhancing the thermal-runaway mitigation performance. For instance, the porous or hollow carriers of FEA, TRR, EA, or GGA can melt or soften at a threshold temperature, so as to expose the FEA, TRR, EA, or GGA to the battery system and retard electrochemical reactions. FEA, TRR, EA, or GGA, with or without carriers, can be mixed with electrodes or placed near electrodes, and retard electro-chemical reactions as temperature rises to a threshold point. The damage initiators can be confined or triggered by devices or carriers that melt or soften at a threshold temperature. The thermally responsive processes of damage initiators take place after thermal runaway has begun. The working temperature can be readily adjustable to close to or lower than the boiling points of flammable liquids in lithium ion batteries.

[0016] The disclosed methods and apparatus work under various types of external or internal loadings, and have broad applicability and are particularly useful for various vehicles (e.g., electric vehicles (EV)), military devices, and large-scale energy storage units that use batteries.

[0017] In one aspect, methods described herein include introducing a first material to the battery, providing an anode, a cathode, charge collectors, and a separator of the battery; and assembling the anode, the separator and the cathode. The first material is configured and arranged to reduce a mechanical strength of the battery upon mechanical loading.

[0018] Implementations can include one or more of the following features. The first material includes a first device. Reducing the mechanical strength includes causing damages or configuration change of the battery upon mechanical loading. The first material is configured and arranged to increase an internal impedance of the battery upon mechanical loading. The first material includes a particle, a fiber, a tube, a layer, or a platelet, the first material formed of one or more of carbon, a glass, ceramic materials, metallic materials, polymer materials, or composites produced from combinations thereof. The first material includes an array or a mesh or a truss, or a layer stack, the first material formed of one or more of carbon, a glass, ceramic materials, metallic materials, polymer materials, or composites produced from combinations thereof.

[0019] The first material includes expandable graphite, the expandable graphite configured and arranged to expand and cause cracks or voids in the battery when heated to or beyond a critical temperature. The first material includes a shape or volume changing material, the shape or volume changing material having a first shape or volume below a transition temperature and a second shape or volume at or above the transition temperature.

[0020] The first material includes a binder of the cathode, the anode, or both, and introducing the first material to the battery comprises reducing a binder content of the cathode, the anode, or both of the battery or reducing a molecular weight of the binder.

[0021] The first material is deposited in aggregates or distribute non-uniformly inside the battery. The first material is distributed non-uniformly inside the battery.

[0022] The first material has anisotropic properties and promotes widespread damages in the electrode upon mechanical loading due to stiffness mismatch and local bending. The first material comprises a non-uniformly distributed damage ini-

tiators placed inside or near an electrode of the battery. The methods include anisotropically deforming or displacing the damage initiators to cause widespread damage in the electrode. The damage initiators include a charge collector, a membrane separator, or a battery case having a heterogeneous or anisotropic shape or material.

[0023] The methods include providing a soft impact promotion component in the battery to promote widespread damages in the electrode.

[0024] In one aspect, methods described herein include introducing a first device to the battery, providing an anode, a cathode, a separator and an electrolyte of the battery; and assembling the anode, the separator and the cathode. The first device is configured and arranged to promote damages in electrodes or to change configurations of the electrolyte upon mechanical or thermal loading. The first device includes a first material that is stable and non-reactive under battery operation conditions.

[0025] The first device includes a container, the container encloses a second material, the container being configured to release or to expose the second material upon thermal loading. The container includes a hollow or porous particle, or tube and the second material includes fire-extinguishing agents, thermal runaway retarders, electrolyte absorbers, gas generation agents, or combinations of them.

[0026] The fire-extinguishing agents, thermal runaway retarders, electrolyte absorbers, and gas generation agents include solid or liquid materials, foaming materials that generate bubbles. The fire-extinguishing agents and thermal runaway retarders include materials that change solvation structures of ions or materials that change viscosity of electrolyte solutions.

[0027] In one aspect, methods described herein include increasing an internal impedance of the battery upon mechanical loading or thermal loading to reduce or eliminate thermal runaway in the battery. The methods include reducing heat generation or internal shorting in the battery upon mechanical or thermal loading.

[0028] Increasing the internal impedance includes causing cracks and/or voids in the battery. The methods include causing a first material in the battery to change from a first shape or volume to a second shape or volume upon thermal loading to cause in-plane or out-of-plane cracks, or voids in the battery, the shape or volume-changing material having a first shape or volume below a transition temperature and a second shape or volume at or above the transition temperature. Increasing the internal impedance of the battery includes causing a first material to release a second material upon mechanical or thermal loading.

[0029] The methods include placing an elastic energy storage material inside or near an electrode of the battery. The elastic energy storage material is confined by a locking component that weakens and releases elastic energy upon mechanical or thermal loading. The methods include directly releasing elastic energy from the elastic energy storage material into the electrode to displace a plurality of damage initiators, and causing widespread damage in the electrode. The plurality of damage initiators in the electrode deforms upon mechanical or thermal loading when aided by another material.

[0030] The elastic energy storage material includes a part of a prestressed charge collector, a part of a prestressed membrane separator, or a part of a prestressed battery case.

[0031] In one aspect, batteries described herein include electrodes, a membrane, an electrolyte, charge collectors, and a first material configured and arranged to increase an internal impedance of the battery upon mechanical or thermal loading to reduce or eliminate thermal runaway.

[0032] Implementations can include one or more of the following features. The first material is embedded in the one or more of the electrodes, the first material configured to create cracks or voids in the one or more electrodes upon mechanical or thermal loading. The first material includes a shape or volume changing material embedded in the one or more electrodes, the shape or volume-changing material changing from a first shape or volume below a transition temperature to a second shape or volume at or above the transition temperature upon thermal loading to cause in-plane or out-of-plane cracks, or voids in the battery.

[0033] The first material includes a container, the container encloses a second material, the container being configured to release or expose the second material upon mechanical or thermal loading, the first material being deposited in one or more of the electrodes, the electrolytes, or the membrane. The second material includes fire-extinguishing agents, thermal runaway retarders, electrolyte absorbers, gas generation agents, or a combination of them, the fire-extinguishing agents comprise solid or liquid chemicals, and the thermal runaway retarders and gas generation agents comprise foaming materials that generate bubbles.

[0034] The gas generation agents include materials that generate gas phase or gas bubbles, and the gas generation agents are provided in the one or more electrodes, the membrane separators, or the electrolyte. The thermal runaway retarders include materials that change solvation structures of ions in the electrolytes, materials that dilute the electrolytes, materials that change viscosity of the electrolytes. The second material includes elastomers that expand upon release from the first material. The first material includes a binder of the one or more electrodes, the binder configured to crack upon mechanical loading.

[0035] The batteries can include materials that absorb an electrolyte, prevent electrolyte from being available for ion transport, or materials that isolate the electrolyte from a region of the battery.

[0036] The details of one or more embodiments of the subject matter described in this specification are set forth in the accompanying drawings and the description below. Other features, aspects, and advantages of the invention will become apparent from the description, the drawings, and the claims.

BRIEF DESCRIPTION OF THE DRAWINGS

[0037] FIG. 1 shows a schematic of a battery.

[0038] FIG. 2A shows a reference cylindrical rod before mechanical loading.

[0039] FIG. 2B shows a cylindrical rod having embedded activated carbon before mechanical loading.

[0040] FIG. 2C shows a cylindrical rod having embedded solid silica particles before mechanical loading.

[0041] FIG. 2D shows a cylindrical rod having embedded porous silica particles before mechanical loading.

[0042] FIG. 2E shows cathode sheets.

[0043] FIG. 2F shows ground cathode particles.

[0044] FIG. 3 shows a schematic of a system used to fabricate a cylindrical electrode.

[0045] FIG. 4A shows a small-scale drop tower apparatus.

[0046] FIG. 4B shows a hammer

[0047] FIG. 5A shows an SEM (scanning electron microscope) image of an edge of a reference cylindrical rod after mechanical loading.

[0048] FIG. 5B shows an SEM image of a center portion of a reference cylindrical rod after mechanical loading.

[0049] FIG. 5C shows an SEM image of an edge of a cylindrical rod containing solid silica powders after mechanical loading.

[0050] FIG. 5D shows an SEM image of a center portion of a cylindrical rod containing solid silica powders after mechanical loading.

[0051] FIG. 5E shows an SEM image of a cylindrical rod containing porous silica after mechanical loading.

[0052] FIG. 5F shows an SEM image of a close up of a cylindrical rod containing porous silica after mechanical loading.

[0053] FIG. 6A shows a cylindrical rod containing electrode material that has been soaked by a solvent

[0054] FIG. 6B shows a cylindrical rod containing activated carbon and electrode material that has been soaked by a solvent.

[0055] FIG. 6C shows a cylindrical rod containing porous silica particles and electrode material that has been soaked by a solvent.

[0056] FIG. 7A shows an SEM image of a cylindrical rod containing electrode material that has been soaked by a solvent before mechanical loading.

[0057] FIG. 7B shows an SEM image of an edge of a cylindrical rod containing electrode material that has been soaked by a solvent after mechanical loading.

[0058] FIG. 7C shows an SEM image of a center portion of a cylindrical rod containing electrode material that has been soaked by a solvent after mechanical loading.

[0059] FIG. 7D: shows an SEM image of an edge of a cylindrical rod containing activated carbon and electrode material that has been soaked by a solvent after mechanical loading.

[0060] FIG. 7E: shows an SEM image of a center portion of a cylindrical rod containing activated carbon and electrode material that has been soaked by a solvent after mechanical loading.

[0061] FIG. 7F shows an SEM image of cracks around an activated carbon in an edge of the cylindrical rod.

[0062] FIG. 7G shows an SEM image of cracks around an activated carbon in a center portion of the cylindrical rod

[0063] FIG. 7H: shows an SEM image of an edge of a cylindrical rod containing porous silica and electrode material that has been soaked by a solvent after mechanical loading.

[0064] FIG. 7I: shows an SEM image of a center portion of a cylindrical rod containing porous silica and electrode material that has been soaked by a solvent after mechanical loading.

[0065] FIG. 7J shows an SEM image of a center portion of an impacted porous silica modified cylindrical rod.

[0066] FIG. 7K shows an SEM image of an edge portion of a cylindrical rod which contains cracks around silica filler.

[0067] FIG. 8A shows a reference cylindrical rod containing anode material.

[0068] FIG. 8B shows the cylindrical rod of FIG. 8A before impact.

[0069] FIG. 8C shows an edge of the cylindrical rod of FIG. 8A after impact.

[0070] FIG. 8D shows a center portion of the cylindrical rod of FIG. 8A after impact.

[0071] FIG. 9A shows a cylindrical rod containing porous silica particles.

[0072] FIG. 9B shows cracks in the rod of FIG. 9A after impact.

[0073] FIG. 9C shows cracks in the rod of FIG. 9A after impact.

[0074] FIG. 10A shows an electrode containing single wall carbon nanotubes after mechanical loading.

[0075] FIG. 10B shows an electrode containing multiple wall carbon nanotube after mechanical loading.

[0076] FIG. 11A shows an electrode containing expandable graphite before a thermal trigger.

[0077] FIG. 11B shows cracks in the electrode of FIG. 11A after a thermal trigger.

[0078] FIG. 12A shows an electrode containing a shape memory material before a thermal trigger.

[0079] FIG. 12B shows cracks in the electrode of FIG. 12A after thermal trigger.

[0080] FIG. 12C shows out of plane cracks in the electrode of FIG. 12A after thermal trigger.

[0081] FIG. 13A shows a schematic diagram of a battery that includes containers.

[0082] FIG. 13B shows electrodes containing hydrophilic hollow microfibers after mechanical loading.

[0083] FIG. 13C shows electrodes containing hydrophobic hollow microfibers after mechanical loading.

[0084] FIG. 14A shows electrodes containing hollow hydrophilic glass fibers after mechanical loading.

[0085] FIG. 14B shows electrodes containing hollow hydrophobic glass fibers after mechanical loading.

[0086] FIG. 15A shows an empty miniature hollow capsule.

[0087] FIG. 15B shows a miniature hollow capsule containing water.

[0088] FIG. 15C shows a miniature hollow capsule containing a surfactant.

[0089] FIG. 15D shows an electrode before mechanical loading.

[0090] FIG. 15E: shows an electrode after mechanical loading.

[0091] FIG. 15F: shows an electrode after mechanical loading.

[0092] FIG. 15G shows an electrode after mechanical loading.

[0093] FIG. 15H shows an electrode after mechanical loading.

[0094] FIG. 16A shows an empty miniature hollow capsule.

[0095] FIG. 16B shows a miniature hollow capsule containing porous silica particles.

[0096] FIG. 16C shows an electrode before mechanical loading.

[0097] FIG. 16D shows the electrode of FIG. 16C after mechanical loading.

[0098] FIG. 17A shows electrodes having high molecular weight binder after mechanical loading.

[0099] FIG. 17B shows electrodes having low molecular weight binder after mechanical loading.

[0100] FIG. 17C shows electrodes having 6 wt % binder.

[0101] FIG. 17D shows electrodes having 5 wt % binder.

[0102] FIG. 17E shows electrodes having 4.5 wt % binder.

[0103] FIG. 17F shows electrodes having 4 wt % binder.

[0104] FIG. 18A shows a wavy nitinol wire.

[0105] FIG. 18B shows an embedded wire.

[0106] FIG. 18C shows cracks caused by an embedded wire.

[0107] FIG. 19A shows a prestressed coil spring.

[0108] FIG. 19B shows damages in an electrode,

[0109] FIG. 20A shows a copper wire with knots

[0110] FIG. 20B shows damages caused by the copper wire of FIG. 20A

[0111] FIG. 21A shows copper wires as damage initiators.

[0112] FIG. 21B shows damages in an electrode layer.

[0113] FIG. 21C shows debonding.

[0114] FIG. 22A shows a wavy shaped substrate.

[0115] FIG. 22B shows damages in an electrode.

[0116] FIG. 23A shows nanoporous carbon.

[0117] FIG. 23B shows nanoporous carbon that is soaked with an electrolyte.

[0118] FIG. 23C shows nanoporous particles.

[0119] FIG. 23D shows nanoporous particles that are soaked with an electrolyte.

[0120] FIG. 24A shows a solution.

[0121] FIG. 24B shows bubbles in the solution of FIG. 24A.

DETAILED DESCRIPTION

[0122] FIG. 1 shows a schematic of a battery 100. Battery 100 includes an anode 110, a cathode 120, a separator 130, electrolytes 140, a first charge collector 111 for the anode 110, and a second charge collector 121 for the cathode 120, all of which are enclosed in a housing 150. Electrical connections 160 connect the anode 110 and the cathode 120 to either an external load 162 or to a charging source 164. Electrons flow along the direction 166 from the anode 110 to the cathode 120 when the battery 100 discharges to power the external load 162. When the battery 100 powers an electric vehicle (EV), the load 160 would be the EV. During charging, electrons flow from the cathode 120 to the anode 110 along direction 168. The electrolytes 140 allow for ionic conductivity. The separator 130 separates the anode 110 and the cathode 120 to prevent a short circuit. Examples of the cathode include lithium cobalt oxide (LCO), lithium (nickel cobalt manganese) oxide (NCM), lithium (nickel cobalt aluminum) oxide (NCA), lithium manganese oxide (LMO), lithium iron phosphate (LFP). Examples of anode includes graphite, graphene, carbon nanotubes (CNT), Li-alloy, Si, TiO₂ and Sn. Examples of electrolytes include LiPF₆, LiBF₄ or LiClO₄ in organic solvent such as ethylene carbonate (EC), ethyl methyl carbonate (EMC), dimethyl carbonate (DMC) and diethyl carbonate (DEC). Examples of separator include polyethylene (PE), polypropylene (PP), trilayer PP/PE/PP, and any combination of them.

[0123] In general, the anode 110 and the cathode 120 can include binders such as polyvinylidene fluoride (PVDF) and poly(methyl methacrylate) (PMMA), and conductors such as active carbon.

[0124] Electrochemical reactions that operate in the battery 100 are exothermic. Thermal runaway occurs when the reaction rate increases due to an increase in temperature, causing a further increase in temperature and hence a further increase in the reaction rate. Thermal runaway can be a process by which an exothermic reaction goes out of control (e.g., when accelerated by a temperature rise), often resulting in an explosion or fire.

[0125] Lithium (Li) ion batteries, while providing higher capacity, are more reactive and have lower thermal stability,

compared with other batteries such as lead-acid batteries. This makes Li ion batteries susceptible to thermal runaway in cases of abuse such as high temperature operation (e.g. $>130^{\circ}\text{C}$.) or overcharging. At elevated temperatures, electrode decomposition generates oxygen, which then reacts with the organic electrolyte of the cell. This is a safety concern due to the magnitude of this highly exothermic reaction, which can spread to adjacent cells or ignite nearby combustible material.

[0126] In order to mitigate (e.g., reduce or eliminate) thermal runaway, damage initiators **180** can be introduced to electrodes (e.g., the cathode **110**, the anode **120**, or both), or be placed near electrodes so that as the battery **100** is subjected to external mechanical loading or overheating the damage initiators modify the electrode and/or the electrolyte to cause an increase in internal impedance. Examples of mechanical loading include impact, collision, crushing, penetration, tension, compression, torsion, bending, and indentation. Examples of overheating include temperature increases caused by electro-chemical reactions or caused by the environment. As the internal impedance increases, exothermic electrochemical reactions are reduced, leading to reduced heat generation rate.

[0127] An example of such damage imitators is passive damage initiators. Passive damage initiators initiate cracking or voiding in electrodes upon external loading, and such cracks and/or voids increase the internal impedance of the electrode. Such additives are also known as cracks or voids initiators (CVIs). The electrode damages can be caused by debonding of CVI-electrode interfaces, fracture and rupture of CVI, stress concentration caused by CVI, and/or local shear, bending, torsion, compression and tension caused by stiffness mismatch of CVI and electrode. Examples of passive additives include solid or porous particles, solid or hollow/porous fibers and tubes, solid or hollow/porous platelets, arrays, clusters, trusses, and layers or layer stacks formed by these materials. Passive additives can be formed from carbon materials such as graphite, carbon nanotubes, activated carbons, and carbon blacks. Passive damage initiators can also be formed from ceramic materials such as silica, alumina, Al_2TiO_5 , ALN, B_4C , BaTiO_3 , BeO, $\text{Bi}_{12}\text{SiO}_{20}$, Bi—Sr—Ca—Cu—O, BN, cBN, CdS/ Cu_2S , CdTe, CeO_2 , CIGS, CoOx, cordierite, CrO_2 , Fe_2O_3 , GaAs, GaN, hBN, hydroxy apatite, La—Ba—Cu—O, LaCrO_3 , Li silicate, Li—Al silicate, LiNbO_2 , LiNbO_3 , LiTaO_3 , MgO, mica, MoS, MoSi_2 , NiOx, PbTiO_3 , PLZT, PZT, Si_3N_4 , SiC, SnO_2 , SrTiO_3 , TiB, TiC, UC, UO_2 , V_2O_5 , $\text{Y}_2\text{O}_2\text{S}$, Y_2O_3 , Y—Ba—Cr—O, zeolite, ZnO, ZnS and ZrO_2 . Passive damage initiators of metallic materials such as iron, steel, ferrous metals, aluminum, copper, zinc, titanium, other nonferrous metals, alloys of these materials, copper based shape memory alloys, NiTi and their derivatives are also possible. Polymer materials such as epoxy, polyester resins, elastomers, thermoplastics such as butyl rubber, polyethylene, polyurethane are also suitable. Other suitable polymers can include thermoplastics, thermosets and elastomers, such as derivatives of natural products which include naturally occurring resins, derivative of cellulose, derivatives of vegetal proteins; polyaddition resins which include polyolefins such as polyethylene, polypropylene and polybutylene, polyvinyls such as polyvinyl ethers, polyvinyl chloride and polyvinyl fluoride, polyvinylidenes such as polyvinylidene chloride and polyvinylidene fluoride, polyvinyl derivatives such as polyvinyl alcohol and polyacetals, styrenics such as polystyrene, acrylonitrile-butadiene-styrene and styrene-butadiene, fluorocarbons such as polytet-

rafluoroethylene and fluorinated ethylene propylene, acrylics such as polymethylmethacrylate, coumarone-indenes; polycondensation resins which include phenolics such as phenol-formaldehyde and pesorcinol formaldehyde, aminoplastics such as urea-formaldehyde, melamine-formaldehyde and melamine-phenolics, furan resins such as phenol-furfural, polyesters such as alkyd resins and polycarbonates, polyethers such as polyformaldehydes and polyglycols, polyurethanes, polyamides, polyimides, polyaramides, sulfones such as polysulfones, polyethersulfone and polyphenylsulfone, epoxy resins, polysiloxanes such as silicones. In general, composites made of any combination of above materials can be used to form passive additives. The sizes of these passive additives can span from less than 1 nanometer to the electrode thickness.

[0128] In addition to the passive additives, the mechanical strength of electrodes can also be reduced by reducing the percentage content of binder in the electrode or by using binders having a lower molecular weight. When the mechanical strength of electrodes is reduced, the binder itself effectively becomes a CVI.

[0129] In addition, as the shapes of membrane separator, battery case, or charge collector are non-uniform, they can promote local shear, bending, tension, compression, or torsion of electrodes when the battery is deformed, and thus cause damages (e.g., widespread damages) in electrodes. As the widespread damage is promoted, the non-uniform shaped membrane separators, battery cases, and charge collectors themselves become CVIs.

[0130] Another type of additives are active damage initiators which damage electrodes, electrolyte, or membrane separator as the battery is subjected to external thermal or mechanical loadings. As mechanical loading or temperature reaches a threshold value, the active damage initiators actively deform, change volume, move, decompose, melt, soften, or break; they may release chemicals such as FEA, TRR, EA, or GGA, or absorb electrolyte. These thermally or mechanically triggered active additives form cracks and/or voids in electrodes, interact or react with an electrolyte or an electrode, interact or react with a membrane separator, interact or react with a charge collector and a battery cell case, change electrode conductivity, generate gas or change conductivity of electrolyte, absorb electrolyte, change configuration of membrane separator, change an internal environment in a battery cell, and/or change the configuration of electrodes, which would increase the internal impedance of the battery and, thus, reduce heat generation associated with possible internal shorting.

[0131] An active damage initiator can produce a significant volume or shape change upon a mechanical or thermal loading. Active damage initiators can include solid or porous particles, solid or hollow beads, solid or hollow/porous fibers and tubes, solid or hollow/porous layers and platelets, arrays, clusters, trusses, and layers or layer stacks formed by shape or volume changing materials. Active damage initiators can be formed from shape-memory alloys such as Ni—Ti, Ni—Ti—Pd, Ni—Ti—Pt, Ni—Ti—Hf, Ni—Ti—Zr, Ni—Ti—Cu, Ni—Ti—Nb, Cu—Al—Ni, Cu—Al—Nb/Ag, Co—Al, Co—Ni—Al/Ga, Fe—Mn—Si, Ni—Al, Ni—Mn, Ni—Mn—Ga, Zr—Cu, Ti—Nb, U—Nb, Ti—Au, Ti—Pd, Ti—Pt—Ir, Ta—Ru or Nb—Ru alloys. The active damage initiators can also be formed from shape-memory polymers and elastomers such as polyurethanes, epoxy, copolyesterurethane, polynorbornene, poly(trans-isoprene), polystyrene,

polybutadiene, polyester, poly(methyl methacrylate), ethylene vinyl acetate-nitrile rubber, ethylene vinyl acetate-chlorosulfonated polyethylene, poly-caprolactone, polyethylene terephthalate-polyethylene glycol, polyethylene terephthalate, poly ethylene oxide, polyvinyl chloride, poly (ketone-co-alcohol), polytetramethylene glycol, and copolymers containing these components. Shape-memory ceramics and glasses, such as ceria-zirconia, yttria-zirconia, magnesia-zirconia, dicalcium silicate, lanthanum niobium oxide, yttria niobium oxide, lanthanide sesquioxide, and enstatites can also form active damage initiators. The active damage initiators can also include ionic solids such as KCl, KI, NaCl, NaClO₃, and NaBrO₃. Thermally or mechanically responsive carbon materials, such as expandable graphite can be used. The active damage initiators can also include elastic energy storage materials, such as springs. The spring configurations include coils, rings, clips, and folded or curved wires and sheets. The active damage initiators can be moved, deformed, or broken by elastic energy storage materials inside or near electrodes. The active damage initiators can contain low-melting-point polymers, metals/alloys, and ceramics, such as bismuth alloys. The damage initiators can be formed by using a mechanically or thermally expandable, deformable, or breakable carrier to contain functional fillers, such as phase change materials, large-thermal-expansion-coefficient materials, or swelling materials that can be involved in physical or chemical processes of large volume/shape changes; such processes include melting, boiling, or chemical reactions leading to large volume changes. The carrier is optional if the fillers are stable and non-reactive under battery operation conditions. The damage initiators can be modified, coated, or decorated by carbon, metallic, or glass materials, such as particles and fibers or carbon blacks, carbon nanotubes, metallic fibers, activated carbons. The active damage initiators can be placed inside or near electrodes. If membrane separate, charge collector, or battery case is made of these materials, the membrane separator, charge collector, or battery case essentially becomes an active damage initiator. The damage initiators can be placed in or near the membrane separator to block ion transport.

[0132] Mechanical loading of rods fabricated using only cathode materials and rods having embedded passive additives are investigated. FIG. 2A shows a rod **210** fabricated using only cathode material, without any passive additives. The cathode material was collected from a cathode sheet **212** (shown in FIG. 2E) used in cylindrical **18650** cells and ground into fine particles **214** (shown in FIG. 2F). The cathode sheet **212** was obtained from American Lithium Energy Co. of Vista, Calif.

[0133] FIG. 3 shows a system **300** used for fabricating cylindrical rods. The fine particles **214** were compressed into the cylindrical rod **210** by, for example, first placing the particles in a stainless steel cell **310** using two pistons **312** and **314**. In the examples shown below, an inner diameter **318** of the stainless steel cell and the outer diameter **316** of the piston **314** were 0.5" (12.7 mm). The pistons **312** and **314** were used to compress the cell **310** by a machine **320** (e.g., an Instron 5582 machine) with the piston velocity of 5 mm/min. Once the force impacted on the fine particles **214** reaches 4 kN, the piston force was removed.

[0134] A similar process is used to form a cylindrical rod **220** shown in FIG. 2B. Cathode material is mixed with activated carbon (AC) particles to form the cylindrical rod **220**. The AC particles can act as damage initiators, or CVI. The AC

particles can be introduced in lower mass ratio than the cathode material, for example, a ratio of cathode material to AC of 30:1, 20:1, 10:1, or 5:1 may be used. The mass ratio of cathode material to AC was 10:1 in cylindrical rod **220**. AC having small particle size can be used, for example, sizes of 500 microns or less, 200 microns or less, 100 microns or less, or 50 microns or less. The AC particles in cylindrical rod **220** were around 150 microns. The AC powders were obtained from J. T. Baker (Product No: E343), a division of Avantor Performance Materials of Center Valley, Pa. The mixture containing the cathode material and the AC powders was placed in the stainless steel cell **310** and compressed using the apparatus **300** as outlined above in reference to the cylindrical rod **210**. A few samples are shown in FIG. 2B.

[0135] Cathode material is mixed with solid silica particles to form a cylindrical rod **230** shown in FIG. 2C using a similar method as described above in reference to cylindrical rod **220**. The solid silica powders can act as damage initiators, or CVI. The solid silica powders can be introduced in lower mass ratio than the cathode material, for example, a ratio of cathode material to solid silica powders of 30:1, 20:1, 10:1, or 5:1 may be used. The mass ratio of cathode material to solid silica powders was 10:1 in cylindrical rod **230**. Solid silica powders having small particle size can be used, for example, sizes of 500 microns or less, 200 microns or less, 100 microns or less, 50 microns or less, or 20 microns or less. The solid silica powders in cylindrical rod **230** were around 44 microns. The solid silica powders were obtained from Sigma-Aldrich Co. of St. Louis, Mo. (Product No.: 342890). No cracks could be observed after cylindrical rod **230** was formed using the apparatus of **300**. The total mass of the rod was 1.91 g, and the rod has a height of 7.20 mm.

[0136] Cathode material is mixed with porous silica particles to form a cylindrical rod **240** shown in FIG. 2D using a similar method as described above in reference to cylindrical rod **220**. The porous silica particles can act as damage initiators, or CVI. The porous silica particles can be introduced in lower mass ratio than the cathode material, for example, a ratio of cathode material to porous silica particles of 30:1, 20:1, 10:1, or 5:1 may be used. The mass ratio of cathode material to porous silica particles was 10:1 in cylindrical rod **240**. Porous silica particles having small particle size can be used, for example, sizes of 500 microns or less, 200 microns or less, 100 microns or less, 50 microns or less, 20 microns or less, 10 microns or less, 5 microns or less, or 1 micron or less. The average particle size of the porous silica particles in cylindrical rod **240** were around 2 microns. The porous silica particles were obtained from Performance Process Inc., of Mundelein, Ill. No cracks could be observed after cylindrical rod **240** was formed using the apparatus of **300**. The total mass of the rod was 1.69 g, and the rod has a height of 7.38 mm.

[0137] Table 1 summarizes the parameters used to fabricate the cylindrical rods shown in FIGS. 2A-2D.

FIG.	2A	2B	2C	2D
CVI	None	Activated carbon (AC),	Solid silica particles	Porous silica
Size of CVI	—	150 micron	44 micron	2 micron
Ratio of cathode material:CVI	—	10:1	10:1	10:1

[0138] The cylindrical rod **210** without any AC particles was quite strong. In contrast, the cylindrical rod **220** containing the AC particles cracked easily as a small mechanical loading below 0.5 MPa was applied, as shown in FIGS. 5C-5F, indicating that AC particles weakened the electrode sample.

[0139] A small-scale drop tower apparatus **400** as shown in FIG. 4A was used to impact each of the rods **220-240**. The apparatus **400** includes a titanium (Ti) hammer **410** (shown in FIG. 4B), which was dropped on the top of the sample (i.e., each of rods **220-240**) placed at a location **420** under the hammer **410**. A drop distance **430** measured from a lower end of the hammer **410** to a top surface of each of the rods **220-240** was 100 mm. The mass of the titanium hammer **410** was 473 g. The Ti hammer has a diameter of 22.45 mm and a height of 265.4 mm.

[0140] After each drop-tower test for a corresponding one of the cylindrical rods **220-240**, the rods **220-240** were observed under a SEM.

[0141] FIG. 5A shows an edge **510** of the cylindrical rod **210**, which does not contain any CVI, after the drop-tower test. While there were a few cracks **512** and **514** near the edge **510** of the cylindrical rod **210**, a central part **516**, shown in FIG. 5B was free of cracks.

[0142] FIG. 5C shows an edge **518** of the cylindrical rod **230**, which contains solid silica powders after the drop-tower test. A number of cracks **520**, **522** were observed at the center of the cylindrical rod **230** (shown in FIG. 5D), and more cracks **524**, **526** were observed near the edge **518**.

[0143] FIG. 5E shows a number of cracks **540** having crack sizes and crack density that were larger than those of cylindrical rod **230** containing solid silica powders. The cracks **540** were developed around the porous silica particles **542** as shown in FIG. 5F.

[0144] Cylindrical rods containing cathode materials that have been soaked in a solvent are also investigated. Ground anode particles were mixed with AC particles, and the AC particles can be introduced in lower mass ratio than the cathode material, for example, a ratio of cathode material to AC particles powders may be 30:1, 20:1, 10:1, or 5:1. The mass ratio of cathode material to AC particles was 19:1 in a cylindrical rod **620**. The AC powders were obtained from J. T. Baker (Product No: E343) a division of Avantor Performance Materials of Center Valley, Pa., with a particle size was around 150 microns. Various solvents can be used, 2 mL of propylene carbonate anhydrous (Sigma-Aldrich Co. of St. Louis, Mo., 310328), were added in the mixture. The presence of the solvent in the cylindrical rod **620** is used to better approximate the working conditions of an electrode.

[0145] The mixture containing the solvent was sealed using the apparatus **300** similar to the method described in reference to rod **220**. No cracks could be observed in cylindrical rod **620**. A reference cylindrical rod **610** (shown in FIG. 6A) was prepared using a similar process with only the cathode material and the solvent (i.e., without the addition of AC particles). The mass of the reference cylindrical rod **610** was 1.11 g and has a diameter of 12.86 mm and a height of 3.16 mm. The mass of the porous silica modified cylindrical rod **620** was 1.30 g and has a diameter of 12.90 mm and a height of 4.06 mm.

[0146] The ground cathode particles were mixed with porous silica particles to form cylindrical rod **630** shown in FIG. 6C. The porous silica particles can be introduced in lower mass ratio than the cathode material, for example, a

ratio of cathode material to porous silica particles may be 30:1, 20:1, 10:1, or 5:1. The mass ratio of cathode material to porous silica was 9:1 in cylindrical rod **630**. The porous silica powders, which served as CVI, were received from Performance Process Inc., of Mundelein, Ill. The average particle size was around 2 microns. Two mL electrolyte solvent, propylene carbonate anhydrous (Sigma-Aldrich Co. of St. Louis, Mo., 310328), were added in the mixture to resemble the wet state of electrodes in a working battery. No cracks could be observed in cylindrical rod **630**, as shown in FIG. 6C when the rod **630** was removed from the apparatus **300**. The total mass of the cylindrical rod **630** was 1.36 g and has a diameter of 12.85 mm and a height of 4.74 mm.

[0147] Table 2 summarizes the parameters of cylindrical rods containing cathode materials that have been soaked in a solvent.

FIG.	6A	6B	6C
Damage Initiator	None	AC	Porous silica
Size of damage initiator	—	150 microns	2 microns
Ratio of cathode material:Damage initiator	—	19:1	9:1
Solvent	Propylene carbonate anhydrous	Propylene carbonate anhydrous	Propylene carbonate anhydrous
Amount of Solvent	2 ml	2 ml	2 ml
Mass of Rod	1.11 g		1.36
Dimension of Rod	12.86 mm × 3.16		12.85 × 4.74

[0148] FIG. 7A shows an SEM image of the reference cylindrical rod **610** before the drop-tower test. After the drop-tower test, few cracks **710** could be observed in the SEM image in FIG. 7B at the edge **712** of the reference cylindrical rod **610**. FIG. 7C is the SEM image of a center **714** portion of the cylindrical rod **610**. The center portion **714** was generally free of cracks. In contrast, a large number of cracks **716** were observed at the center of the cylindrical rod **620** shown in FIG. 7E and more cracks **718** were observed near an edge **720** as shown in FIG. 7D. The cracks **718** were developed around an AC particle **722** as shown in FIGS. 7F and 7G. FIG. 7F shows the edge **720** of the cylindrical rod **620** while FIG. 7G shows a center portion of the cylindrical rod **620**.

[0149] FIG. 7H is an SEM image of an edge **724** of the cylindrical rod **630** that contains porous silica particles **726** after the drop-tower test. FIG. 7I is an SEM image of a center portion of the cylindrical rod **630** after the drop-tower test, a large number of cracks **728** were observed and the size and density of the cracks were much larger than those of the cylindrical rod **620**. The cracks were developed around the porous silica particles **726**, as shown in FIGS. 7J and 7I. FIG. 7J is a close up of cracks **728** around a porous silica particle **726** near the edge **724** of the cylindrical rod **620**. FIG. 7K is a close up of cracks **728** around a porous silica particle **726** in the center portion of the cylindrical rod **620**.

[0150] Cylindrical rods containing anode materials that were soaked in a solvent are also investigated. Anode materials for the cylindrical rod **910** shown in FIG. 9A were collected from an anode sheet obtained from American Lithium Energy Co. of Vista, Calif. The anode sheet was grounded and the ground anode particles were mixed with porous silica particles at a mass ratio of anode material to porous silica of 9:1. The porous silica powders were received from Performance Process Inc., of Mundelein, Ill. The aver-

age particle size was around 2 microns. Two mL electrolyte solvent, propylene carbonate anhydrous (Sigma-Aldrich Co. of St. Louis, Mo., 310328), were added in the mixture to resemble the wet state of electrodes in a working battery. The mixture of anode materials, porous silica particles and solvent were compressed to form cylindrical rod **910** using the apparatus **300** in a similar fashion as that used to form cylindrical rod **620** described above. No cracks could be observed in cylindrical rod **910** after it was formed using apparatus **300**. A reference cylindrical rod **810**, as shown in FIG. **8A** was prepared through a similar process by using only the anode material and the solvent, without the addition of porous silica particles. The mass of the reference cylindrical rod **810** was 1.28 g, and the rod has a diameter of 13.02 mm and a height of 5.55 mm. The mass of the cylindrical rod **910** was 1.33 g, and its diameter was 12.97 mm and its height was 6.22 mm. A 46-range digital multimeter from RadioShack of Fort Worth, Tex., was used to measure an electrical resistance of the cylindrical rod **910** containing the porous silica. Before impact, the measured resistance was about 200 k Ω . After the impact test, the electrical resistance was 28.7 M Ω , which is a few hundred times higher than the resistance before the impact test. In contrast, the electrical resistance of the reference cylindrical rod **810** without porous silica fillers did not vary much.

[0151] Table 3 summarizes the parameters used to fabricate the cylindrical rods shown in FIGS. **8A** and **9A**.

FIG.	8A	9A
CVI	None	Porous silica
Size of CVI	—	2 microns
Ratio of anode material:CVI	—	9:1
Solvent	Propylene carbonate anhydrous	Propylene carbonate anhydrous
Amount of Solvent	2 ml	2 ml
Mass of Rod	1.28 g	1.33
Dimension of Rod	13.02 mm \times 5.55	12.97 mm \times 6.22

[0152] Before impact, there were no cracks in the reference cylindrical rod **810** as shown in FIG. **8B**. After impact, cracks **812** were observed near the edge **814** of the reference cylindrical rod **810**, as shown in FIG. **8C**. However, the center portion **816** of the sample was free of cracks, as shown in FIG. **8D**.

[0153] In the cylindrical rod **910** containing porous silica particles, a large number of cracks **912** were observed in a center area **914** of the cylindrical rod **910**, as shown in FIG. **9B**, and more cracks **912** were observed near an edge **916** as shown in FIG. **9C**. The cracks **912** were developed around silica particles **918** as shown in FIGS. **9B** and **9C**.

[0154] After the impact test, the electrical resistance of the cylindrical rod **910** containing porous silica increased significantly by more than a few hundred times than before the impact test; while that of the reference cylindrical rod **810** without porous silica fillers did not vary much.

[0155] Carbon nanotubes (CNT) can also be used as CVI to modify electrodes. In some embodiments, polyvinylidene fluoride (PVDF) can be used as a binder in the electrode. A binder in an electrode is typically a polymer adhesive that holds the particles of active materials together. The binder amount is usually 3-6% of electrode mass. An exemplary preparation method includes using an active material, either

NCM-04ST $\text{LiNi}_{0.5}\text{Mn}_{0.3}\text{Co}_{0.2}\text{O}_2$ (NMC532) obtained from TODA America of Battle Creek, Mich. (for cathode samples) or EQ-Lib-CMSG graphite obtained from MTI Corp. of Richmond, Calif. (for anode samples), and mixing the active material with polyvinylidene fluoride (PVDF) obtained from Sigma-Aldrich Co. of St. Louis, Mo. (Product No. 182702) and CENERGY-C65 conductive carbon (C) obtained from Timcal of Cleveland, Ohio. The mixture was soaked up in 1-Methyl-2-pyrrolidinone (NMP) (Sigma-Aldrich Co. of St. Louis, Mo., Product No. 328634). The weight ratios of the solid components were NMC532: PVDF: C=93:4:3 and Graphite: PVDF: C=93:6:1 for cathode and anode samples, respectively. For each 0.2 g of PVDF, 5 ml NMP was used. The solid components and NMP was thoroughly mixed in a 50 ml beaker at room temperature by a mechanical stirrer (PCVSI, IKA) at 400 rpm for 30 minutes, and then conductive carbon was added, stirred at 500 rpm for another 30 minutes. After that, the active material was added, which was further homogenized by stirring at 600 rpm for 90 minutes. Cathode slurry was cast on a 15 μm thick aluminum foil (MTI EQ-bcaf-15u-280) by a film casting doctor blade (MTI EQ-Se-KTQ-150A) with the slurry thickness of 400 nm. Anode slurry was cast on a 9 nm thick copper foil (MTI EQ-bccf-9u) with the slurry thickness of 200 μm . The electrode sample was dried in vacuum at 80° C. for 24 hours. After drying, the thickness of the electrode sample was about 150 μm for cathode and 100 μm for anode, respectively. The dried sample was compressed by two flat stainless steel plates in a Type-5582 Instron machine at 30 MPa, with the loading rate of 0.5 mm/min. In the following sections, all electrode samples were processed through similar procedures, except that extra functional components might be added and special configurations might be employed. During testing, the electrode samples were soaked in an electrolyte, to simulate the working condition in a battery cell. The electrolyte was 1 M LiFP_6 dissolved in ethylene carbonate (EC) and ethyl methyl carbonate (EMC). The mass ratio of EC:EMC was 1:1.

[0156] The electrode sample was impacted by a stainless steel rod with a length of 305 mm and the mass of 7.7 kg, from a drop distance in the range from 4-22 mm.

[0157] FIG. **10A** is an optical microscope image of the electrode containing SWCNT after impact. Cracks **1090** were observed. Under similar impact conditions, a reference electrode (not shown) prepared using a similar procedure but without the addition of CVI showed no evidence of damage.

[0158] FIG. **10B** shows various electrode samples modified by 3 wt % MWCNT after impact tests. Ten electrodes formed a layer stack and was impacted simultaneously, labeled as samples 1-10, respectively. The drop distance was 12 mm. Multiple cracks **1090** are visible in most of the electrode layers.

[0159] In addition to the passive additives described above, active additives that are thermally triggered have also been investigated.

[0160] Expandable graphite (EG) can be employed as a thermally triggered CVI. The thickness of EG can expand by a few times when it is heated to or above a critical temperature. FIG. **11A** shows an electrode **1010** containing expandable graphite (EG) before the application of heat. The electrode **1010** includes 5 wt % of conductive EG particles, obtained from ACS Material LLC of Medford, Mass.; Products No. EG-110-230, having a size of 80 mesh. NCM532 is the cathode materials for electrode **1010**. The selected EG has an critical temperature at about 110° C. The modified cathode

layers were dried at 40° C. for 72 hours. The low drying temperature prevents premature damages. The electrode **1010** was then heated to 120° C. and kept for 20 minutes. The graphite expanded and generated cracks/voids **1020** as expected upon heating, as shown in FIG. **11B**.

[0161] Shape memory materials (SMM) can also be used as a thermally triggered CVI. A SMM can be deformed below the transition temperature and recover to the original shape above the transition temperature. FIG. **12A** is an optical microscope image of an originally straight SMM wire from Fort Wayne Metals; Products No.: 82909 that was cut into segments that are 10 mm long. The transition temperature was about 90° C. At room temperature, the wire segments were bent into coils **1110**, and embedded into 150 μm thick cathode layers to form an electrode **1112**. The electrode **1112** was heated to 120° C. and kept for 5 minutes. After heating, the SMM coils **1110** tend to change back to straight, either causing in-plane cracking and voiding **1114** as shown in FIG. **12B** or causing out-of-plane damages **1116** as shown in FIG. **12C**.

[0162] Hollow or porous beads, particles, tubes, pipes, fibers, plates, pads, pouches, boxes, and other containers with sizes ranging from a few nanometers to the battery cell size can be used to hold fire-extinguishing agents (FEA), thermal runaway retarders (TRR), electrolyte absorbers (EA), and/or gas generation agents (GGA). Upon mechanical loading or thermal loading (when temperature rises) FEA, TRR, EA, or GGA can be released from the hollow or porous containers into the battery system to put out fire and/or reduce heat generation rate in the battery. Such containers can be placed in the cathode, anode, electrolyte, membrane, or other locations, both inside or outside the battery cells. The containers can be distributed uniformly, or form aggregates that have either random or textured distribution patterns.

[0163] Thermal runaway retarders (TRR) can include chemicals that can change salvation structures of ions, such as aromatic amine, N,N-Diethylaniline, N,N-diethyl-p-phenylenediamine, 2-(2-methylaminoethyl)pyridine, 5-amino-1,3,3-trimethylcyclohexanemethylamine, (1R,2R)-(+)-1,2-diphenylethylenediamine, N,N'-diphenylethylenediamine, tryptamine, 2-benzylimidazoline, 1,2,3,4-tetrahydro-9H-pyrido[3,4-b]indole, 4,4'-diaminodiphenylmethane, 1-(N-boc-aminomethyl)-4-(aminomethyl)benzene and pyridine; lightly cross-linked polymers, which include but not limited to epoxy, polyester, poly (vinyl ester), polyurethane, bakelite, polyimide, urea methanal and melamine, or co-polymers containing these components.

[0164] TTR can also include surfactants, such as sodium lauryl sulfate, sodium dodecylbenzenesulfonate, oleic acid, Span™ series, Atlas™ G series, Tween™ series, Solulan™ series, Splulan™ series, Brij™ series, Arlacel™ series, Emcol™ series, Aldo™ series, Atmul™ series surfactant.

[0165] TTR can also include chemicals that can change the viscosity of electrolyte solutions. These TTR can include solid state aromatic amine such as n,n'-diphenylethylenediamine, 4,4'-diaminodiphenylmethane and 1-(N-Boc-aminomethyl)-4-(aminomethyl)benzene; nonionic surfactants such as 2,4,7,9-Tetramethyl-5-decyne-4,7-diol, polyethylene glycol hexadecyl ether, polyoxyethylene nonylphenyl ether, sorbitan laurate and polyethylene glycol sorbitan monolaurate; viscous liquids such as glycerol, glycerin, and other polyols.

[0166] TTR can also be chemicals such as acid, bases, ketone, alcohol and organic phosphorus compounds as well as their halogenated derivatives.

[0167] The gas generation agents (GGA) and associated processes can include catalytic decomposition of hydroxyl peroxide with potassium iodine or manganese dioxide as catalyst; polyurethane foaming; extinguishing agents in fire extinguishing processes such as ammonium sulfate with sodium bicarbonate solution; organic solvents having boiling points ranging from 60-250° C. such as acetone, methanol, ethanol, acetonitrile, benzene, carbon tetrachloride, cyclohexane, ethyl acetate, isopropyl alcohol, tert-butyl alcohol and triethylamine; thermal decomposition of ionic solids, e.g. carbonates such as sodium bicarbonate and potassium bicarbonate; thermal decomposition of permanganate salts such as silver permanganate, ammonium permanganate, nickel permanganate and copper permanganates; thermal decomposition of ammonium salts such as ammonium nitrate, ammonium chromates, ammonium citrate, ammonium carbonate and ammonium bicarbonate; thermal decomposition of coordination compounds such as diaquaamminecobalt chloride, diaquaamminecobalt bromide, cobalt amines chloride, cobalt amines nitrate, chromium amines thiocyanate and nickel amines chloride; thermal decomposition of perchlorates such as nitronium/nitrosonium perchlorates; thermal decomposition of oxalates such as silver oxalate; thermal decomposition of azide such as sodium azide, potassium azide, lithium azide and ammonium azide; thermal decomposition of organic compounds such as azodicarbonamide, azobisisobutyronitrile, n,n'-dinitrosopentamethylenetetramine, 4,4'-oxydibenzene-sulfonyl hydrazide, p-toluenesulfonyl hydrazide; thermal decomposition of hydrated salts such as ammonium copper sulfate hexahydrate, nickel sulfate hexahydrate, calcium sulfate hemihydrate, lithium sulfate monohydrate, sodium carbonate monohydrate, borax, nickel oxalate dehydrate, sodium carbonate perhydrate, alkali (Na, K, Rb, NH₄) oxalate perhydrate and calcium sulfite.

[0168] Gas generation agents (GGA) can also include bubble generation promoters (BGP), materials that promote bubble nucleation and growth when the electrolyte is heated, such as particles, fibers, rods, layers and layer stacks, platelets of rough, cracked, or dimpled surfaces or surface coatings. BGP can be inside or near electrodes, inside or near membrane separator. If the membrane separator can promote bubble generation as electrolyte is heated, the membrane separator essentially becomes a BGP.

[0169] The electrolyte absorbers (EA) can include particles, platelets, beads, tubes, fibers, membranes, disks, and monoliths of metallic materials, glass materials, carbon materials, ceramics, polymers, elastomers, alumina, zeolites, polyelectrolytes, polymers with charged or polar side groups, silica and aerogels, and composite materials. These materials can be porous, hollow, or solid. The electrolyte absorbers (EA) can also include superabsorbents such as poly (sodium acrylate), poly acrylic acid-sodium styrene sulfonate (AA-SSS), poly acrylic acid and 2-acrylamido-2-methylpropane sulfonic acid (AA-AMPS), 2-Acrylamido-2-methylpropane sulphonic acid and poly(ethylene glycol) copolymer, poly (potassium, 3-sulfopropyl acrylate-acrylic acid) gels, poly (AMPS-TEA-co-AAm), (poly ethylene glycol methyl ether methacrylate-acrylic acid) copolymers, methacrylamidopropyltrimethyl ammonium chloride (MAPTAC). The electrolyte absorbers (EA) can include particles, platelets, tubes, membranes, disks, and monoliths of polyelectrolytes including proteins such as bovine serum albumin, casein, lactoferrin; polycations containing aromatics or having a charged backbone such as poly(-vinylpyridine) (PVP), x,y-ionene,

poly(N,N-diallyl-N,N-dimethyl-ammonium chloride) (PDMDAAC); polycations with quaternary ammonium side chains such as poly(trimethylammonio ethylmethacrylate) (PTMAEMA) and its copolymers; polycations without steric stabilizer such as modified polyaspartamide (PAsp), poly(amidoamine)s (PA) with different side groups, poly(N-isopropylacryl amide) (PNIPAM) and derivatives, poly(dimethylaminoethyl-L-glutamine) (PDMAEG) and copolymers, Poly(methyl methacrylate) (PMMA) and methacrylamide derivatives, poly[2-(dimethylamino)ethyl methacrylamide] (PDMAEMA) and derivatives; polycations with steric stabilizer such as poly(L-lysine) (PLL) and derivatives, amino acid-based polymers; Amphiphilic polycations such as poly(N-ethyl-4-vinylpyridinium bromide) (PEVP) and copolymers, poly(-vinylpyridine) (PVP) copolymers; Polyamphoters such as modified poly(1,2-propylene H-phosphonate), silica and aerogels, and composite materials. These materials can be porous or solid. The electrolyte absorbents (EA) can also include superabsorbents such as poly (sodium acrylate), poly acrylic acid-sodium styrene sulfonate (AA-SSS), poly acrylic acid and 2-acrylamido-2-methylpropane sulfonic acid (AA-AMPS), 2-Acrylamido-2-methylpropane sulphonic acid and poly(ethylene glycol) copolymer, poly (potassium, 3-sulfopropyl acrylate-acrylic acid) gels, poly (AMPS-TEA-co-AAm), (poly ethylene glycol methyl ether methacrylate-acrylic acid) copolymers, methacrylamidopropyltrimethyl ammonium chloride (MAPTAC), or co-polymers containing these components.

[0170] Fire-extinguishing agents (FEA) include dry chemicals such as sodium bicarbonate, monoammonium phosphate, potassium bicarbonate, potassium bicarbonate and urea complex, potassium chloride; foams such as Aqueous Film Forming Foam (AFFF), Alcohol-Resistant Aqueous Film Forming Foams (AR-AFFF), Film Forming Fluoroprotein (FFP), Compressed Air Foam System (CAFS);

[0171] FEA can be class D fire extinguishing powders such as sodium chloride, copper, graphite based, sodium carbonate based powders.

[0172] The containers of FEA, TRR, EA, or GGA can be weakened, softened, melted, broken apart upon mechanical or thermal loading. For FEA, TRR, EA, or GGA that are stable under normal battery operation conditions (i.e. operating at a normal battery operation temperature range, or without intense mechanical loading), or for FEA, TRR, EA, or GGA that do not interact with active materials and the electrolyte in the battery, the containers are optional. The containers can be hollow carriers; organic surface coatings, inorganic surface coatings, blockers, tubes, pouches, boxes, beads, particles, disks, layers, stoppers, and surface layers of absorbed or adsorbed particles, carbon nanotubes or other tubes, fibers, rods, and platelets. The containers can be made of fusible alloys such as bismuth alloys, polymers such as paraffin and polyethylene, elastomers, glass materials, gelatin, carbon materials, ceramics, smart materials such as smart alloys, polymers, elastomers, and ceramics, e.g. Ti—Ni alloy, and hydrogels; and composite materials. The containers can be either electrically conductive or nonconductive. The containers can be either thermally conductive or nonconductive. The containers can be used to carry the damage initiators disclosed above, or additives such as positive thermal coefficient materials, phase change materials, and membrane blocking materials. Multiple layers or sections of containers can be used.

[0173] FIG. 13A shows a battery 1300 having an anode 1301 and a cathode 1302 both of which includes containers 1304. The containers 1304 can hold FEA, TRR, EA, or GGA. In FIG. 13A, the containers are uniformly distributed in the electrodes. However, the containers can be aggregates distributed in a random pattern or aggregates that are distributed in a specific pattern.

[0174] Containers for holding FEA, TRR, EA, or GGA can be, for example, hollow microfibers (HMF). HMF alone can also serve as a CVI. The processing and testing procedure for exemplary electrodes were similar with that of CNT modified electrodes described above in FIGS. 10A and 10B, except that the CNT was replaced by HMF. The HMF can be either clear fused quartz (CFQ) fibers, for example, obtained from Pro-dustrial of Fredon, N.J. (Product No. 134316), which have an inner diameter (ID) of 50 microns and an outer diameter (OD) of 80 microns; or borosilicate glass fibers of similar ID and OD, provided by Pro-dustrial of Fredon, N.J. (Product No. 134270). The HMF content was either 3 wt % or 5 wt % of electrode mass.

[0175] At a HMF content of 3 wt %, pronounced cracks 1310 are observed after impact test done at a drop distance of 12 mm as shown in FIG. 13B. Ten layers of HMF modified electrodes (samples 1-10) form a layer stack, and are impacted by the hammer. Extensive cracking are observed in most of the layers.

[0176] FIG. 14A shows a series of three optical microscope images of electrodes containing 3% hollow hydrophilic glass fibers when impacted at a drop distance of 7 mm. FIG. 14B shows a series of three optical microscope images of electrodes containing 3% hollow hydrophobic glass fibers 1410 when impacted at a drop distance of 7 mm. As shown in FIGS. 14A and B, the fibers are broken, and any chemicals initially contained inside would be released.

[0177] FIG. 15A shows a glass tube 1510 having an OD of 1.69 mm, ID of 1.55 mm, height of 5.65 mm, and mass of 0.010 g that can contain FEA, TRR, EA, or GGA and be embedded in the battery.

[0178] FIG. 15B shows a miniature capsule 1520 filled with 7 mg of neat water, which serves as an analog of functional chemicals such as FEA, TRR, EA, or GGA. The liquid was sealed in the capsules by thin layers of epoxy adhesive 1522 at both ends.

[0179] FIG. 15C shows a miniature capsule 1530 filled with 9 mg of a surfactant, Adogen 464 obtained from Sigma-Aldrich Co. of St. Louis, Mo. (Product No. 856576), which is another analog of functional chemicals such as FEAs.

[0180] The filled miniature capsules 1520 and 1530 were embedded into cathode material cluster saturated with solvent, to form a cylindrical rod 1540, as shown in FIG. 15D. The sample preparation procedure is similar with that of FIG. 6A, except the additives are filled miniature capsules.

[0181] FIG. 15E shows the impacted cylindrical rod 1550 containing broken miniature capsules 1552 and the sealed liquids were released.

[0182] FIG. 15F shows the impacted cylindrical rod 1550 being shattered into small pieces 1560 after being impacted by the hammer at a drop distance of 12 mm. The shattering of the rods indicates that the capsules acted as damage initiators, as the electrode samples without the capsules had few cracks.

[0183] The mechanical impacted samples were also characterized by optical microscope and typical photos are shown in FIGS. 15G and 15H. A broken empty capsule 1564 is shown in FIG. 15H.

[0184] FIG. 16A shows a glass tube **1610** having an OD of 3.97 mm, ID of 2.40 mm, a height of 3.97 mm, and a mass of 0.091 g. The glass tube forms a miniature capsules **1620** when filled by 7 mg of porous silica particles obtained from Performance Process Inc., of Mundelein, Ill., as shown in FIG. 16B. The porous silica particles are analogs of condensed aerosol fire suppression agent. The solid agent was sealed in the capsule by thin layer of epoxy adhesives **1622** from both ends.

[0185] The filled miniature capsules **1620** were embedded into cathode material soaked up by solvent, to form cylindrical rod **1630** as shown in FIG. 16C. The cylindrical rod **1630** was then impacted by the drop tower **400**.

[0186] As shown in FIG. 16D, the miniature capsules **1620** were broken and the sealed porous silica particles **1624** were released and exposed.

[0187] In general, a damage initiator needs not be an additive. For example, reducing the amount or the molecular weight (MW) of the binder in electrodes can also weaken (i.e., reduce) the mechanical strength of the electrode upon mechanical impact. In other words, the reduced binder phase effectively becomes the CVI.

[0188] An example of the binder is PVDF. The processing and testing procedures for fabricating an electrode in this case are similar as before, except that no CVI particles are added.

[0189] FIG. 17A shows the impact result from an electrode having a high molecular weight (MW) binder. The MW in this case was 540 k and was obtained from Sigma-Aldrich Co. of St. Louis, Mo. Ten layers of electrodes form a layer stack (samples 1-10) and are impacted by the hammer simultaneously. FIG. 17B shows impact results from an electrode having a low molecular weight (MW) binder. The mass ratio of binders to CB to active material remained the same as that used in the electrodes shown in FIG. 17A but the MW of the binder was reduced to 180 k, which is also provided by Sigma-Aldrich Co. of St. Louis, Mo. (Product No. 427152). The MW of the electrodes shown in FIG. 17B is lower than the MW of the binder used for the electrodes shown in FIG. 17A by $\frac{1}{3}$. FIG. 17B show that the electrodes with lower MW binder suffer more cracking when subjected to an impact from a drop distance of 12 mm while the electrodes made from the larger MW binders were not damaged.

[0190] FIGS. 17C-F show samples made from different binder amounts of 6 wt % i.e., a mass ratio of binder:CB:active material was 6:1:93, 5 wt % (i.e., binder:CB:active material of 5:1:94), 4.5 wt % (i.e., binder:CB:active material of 4.5:1:94.5) and 4 wt % (i.e., binder:CB:active material of 4:1:95), respectively when subjected to an impact from a drop distance of 12 mm. FIGS. 17D and 17A show that electrodes having the lowest (4 wt %) amount of binder exhibit extensive cracking damages after impact, while electrodes having the highest (6 wt %) amount of binder were not damaged.

[0191] While this specification contains many implementation details, these should not be construed as limitations on the scope of the invention or of what may be claimed, but rather as descriptions of features specific to particular embodiments of the invention. Certain features that are described in this specification in the context of separate embodiments can also be implemented in combination in a single embodiment. Conversely, various features that are described in the context of a single embodiment can also be implemented in multiple embodiments separately or in any suitable subcombination. Moreover, although features may be described above as acting in certain combinations and even

initially claimed as such, one or more features from a claimed combination can in some cases be excised from the combination, and the claimed combination may be directed to a subcombination or variation of a subcombination.

[0192] The damage initiators can be triggered mechanically or thermally; that is, damage initiators can deform, displace, break, melt or soften, and/or expose FEA/TRR/EA/GGA to the interior of battery, and/or absorb electrolytes upon thermal or mechanical loading.

[0193] FIG. 18A shows a wavy nitinol wire **1800** (Niti#5, FWMetal) having a diameter of 75 microns and a phase transition temperature of 95° C. was embedded in electrode **1820**, as shown in FIG. 18B. The nitinol wire is straight at temperatures over 95° C. and has a wavy shape at room temperature. The nitinol wire was placed on a charge collector before slurry casting, and subsequently vacuum dried together with the slurry. The nitinol wire could also be directly compressed into the dried electrode at 30 MPa, as the electrode sample was compressed after drying. The electrode with embedded nitinol wire was heated by a hotplate to 100° C. In a few minutes, cracks **1804** caused by the shape change of the embedded nitinol wire are observed, as shown in FIG. 18Cs.

[0194] Damage initiators can be an elastic energy storage material/device (EESMD), such as a spring. An EESMD can be prestressed and be confined by a locking component, which can be weakened, softened, broken, or melt upon mechanical or thermal loading before releasing the stored elastic energy to cause damages in an electrode. EESMD can be placed in an electrode or near an electrode. If charge collectors, membrane separators, or battery cases are prestressed and the associated stored elastic energy can be released upon mechanical or thermal loading, they essentially become EESMD. EESMD can include pre-stressed or pre-compressed particles, fibers, tubes, rods, strings, layers, layer stacks, platelets of polymers, elastomers, metals and alloys, ceramics, glass materials, carbon materials, polyurethane, natural rubber, polybutadiene, thermoset resins, epoxy, polyester, and co-polymers containing these components.

[0195] EESMD can include springs, rings, wires, strings, beads, rods, beams, meshes, arrays, and trusses that can be deformed and pre-stressed elastically. They can be made of polymers, elastomers, ceramic materials, metallic materials, glass materials, carbon materials, or composite materials. They can be confined by locking components, which can include hollow carriers, coatings, blockers, and stoppers. The materials of above mentioned confining methods/materials can be metallic materials, polymers, elastomers, wax, epoxy, gelatin, glass materials, carbon materials, ceramics, and composite materials.

[0196] As the elastic energy is released from an EESMD, it can directly cause damages in electrode, or deform or displace other damage initiators in electrode, indirectly causing damages (e.g., widespread damages) in electrode. The damage initiators can be threads, meshes, arrays, and multilayers with various dimensions, surface properties and features, and shapes and configurations. The materials of the damage initiators can include polymers, elastomers, glass materials, carbon materials, metals and alloys, ceramics, and composite materials.

[0197] FIG. 19A shows a prestressed coil spring **1904** embedded in a cathode sample **1902**. The coil spring **1904** was made from a stainless steel wire having a diameter of 125 microns (9882K11, from McMaster-Carr of Santa Fe

Springs, Calif.). The curvature of the coil spring **1904** was about 1 mm. One end of the coil spring was initially fixed on an aluminum charge collector by duct tape. The other end of the coil spring was fixed by the locking component **1906**, which can be, for example, a drop of paraffin having a melting point below 100° C. Initially, the coil spring **1904** was pre-stressed, so that its curvature can be changed by about 10%. Cathode slurry was casted on top of the prestressed spring, dried and compressed at 30 MPa. The electrode sample was then soaked up by 20 ml ethyl methyl carbonate (EMC) (from Sigma-Aldrich Co. of St. Louis, Mo., product number 754935), and covered by a 0.5 mm thick, 20 mm×10 mm glass plate. The electrode sample was heated by a Cimatec digital HP 131125 hot plate from Thermo Scientific of Waltham, Mass., to 100° C., and the paraffin melted. The stored elastic energy in the spring was released and it relaxes to a position **1908** shown in FIG. 9, causing evident damages in the electrode, such as cracks **1910**, as shown in FIG. 19B. The resistivity of the damaged electrode increased by more than 4 times compared to an undamaged electrode.

[0198] Other damage initiators, such as strings, threads, meshes, and arrays and layer stacks of them, can be deformed or displaced by elastic energy storage materials/devices upon mechanical or thermal loading. The dimensions, surface features and properties, and shapes and configuration of the damage initiators can be controlled in broad ranges. The damage initiators can also be deformed or displaced by thermally or mechanically responsive components other than EESMD.

[0199] FIG. 20A shows a copper wire with knots **2002**, embedded in an electrode sample **2004**. The wire has a diameter of 80 microns. The electrode sample **2004** was processed using standard procedures, except that in the final compression step the wire was compressed into the dried electrode sample at 30 MPa by an Instron 5582 machine. After compression, the electrode sample soaked up 200 microliter of electrolyte. Damages **2006** observed in the electrode sample **2004**, as shown in FIG. 20B, were caused by displacement of the wire, as the wire was pulled by a coil spring placed next to the electrode sample. FIG. 20B Damages in electrode caused by displacing the copper-wire damage initiator. The resistivity of the damaged electrode increased by more than 4 times compared to an undamaged electrode.

[0200] Damage initiators (DI) can be distributed non-uniformly inside an electrode or near an electrode. DI can have heterogeneous and/or anisotropic materials, components, or shapes and configurations. Upon mechanical loading, such damage initiators or the electrode materials near such damage initiators deform or displace differently in different areas and/or along different directions, so that local compression, tension, shear, torsion, bending, cracking, voiding, or debonding are promoted. Such heterogeneous or anisotropic damage initiators can be fibers, wires, wedges, strips, tubes, meshes, arrays, and trusses. When a charge collector, a membrane separator, or a battery case has heterogeneous or anisotropic shapes, surface features, configurations, or materials or components, which can trigger internal damages in battery, they essentially become damage initiators. Such damage initiators and their components can be made of metallic materials, polymers, elastomers, carbon materials, glass materials, ceramics, and composite materials.

[0201] FIG. 21A shows an example of an aluminum (Al) sheet **2108** having copper (Cu) wires **2106** as damage initiators. The diameter of the Cu wire can be 500 microns and the

spacing between the wires can also be about 500 microns. The Cu wires were firmly glued on the Al substrate **2108**. A cathode sample was processed using standard procedures on an Al charge collector **2104**. The cathode sample thickness was about 150 microns. The size of the electrode sample was 10×10 mm. The electrode layer **2102** soaked up 20 microliter of an electrolyte. The electrode sample was placed on top of an array of copper wires **2106**. This setup was impacted using the same table top drop tower as shown in FIG. 4A. The drop weight and distance were 405 g and 15 mm, respectively. Upon impact, as the electrode layer **2102** was forced to bend and shear around the Cu wires **2106**. Damages (e.g., cracks **2110**) in an electrode layer and debonding (e.g., region **2112** in FIG. 21C) between the electrode layer **2102** and the charge collector **2104** were observed, as shown in FIG. 21B and FIG. 21C, respectively. The resistivity of the damaged electrode increased by more than 3 times compared to the resistivity of an undamaged electrode. Using a soft impactor, e.g. a polyurethane hammer, helps promote widespread damage. The soft impactor models soft inner layers of battery case or other soft components near electrodes. If the shape or surface pattern of a charge collector or a battery case is non-flat and wavy, such as S-shaped or dotted-shaped, similar electrode damages can be achieved.

[0202] A wavy shaped substrate, e.g. a charge collector **2202**, as shown in FIG. 22A, was tested as damage initiator. To control the shape of the charge collector **2202**, two arrays of copper wires sandwich a copper foil. The copper wire has a diameter of 500 microns, and the spacing between adjacent wires was also 500 microns. The top and bottom arrays were misaligned so that the top array can move into the gaps of the bottom array when an external compression force is applied through a steel plate. After the charge collector **2202** was deformed, the steel plate and the top array of copper wires were removed. A cathode sample was prepared on the wavy charge collector **2202** using standard procedures, except that the final compression at 30 MPa was performed by a 10 mm thick polyurethane plate, instead of a steel plate. After compression, the electrode sample soaked up 20 ml of EMC. Then, the bottom array of copper wires was removed, as shown in FIG. 22A. A wavy electrode film **2204** was impacted by the table top drop tower shown in FIG. 4A. The drop weight and distance were 405 g and 30 mm, respectively. After impact, a large number of cracks **2206** were observed in the electrode sample, as shown in FIG. 22B. The resistivity of the damaged electrode increased by more than 2 times than compared to the electrode prior to the impact.

[0203] Upon mechanical or thermal loading, if gas generation agents (GGA) can be released or exposed to an electrode, an electrolyte, and/or a membrane separator, GGA can generate gas inside the battery and block ion transport. In one example, ammonium carbonate was employed as GGA. About 50 mg of ammonium carbonate was immersed in 5 ml 50% ethyl methyl carbonate (EMC) solution of ethylene carbonate (EC). The system was heated to 100° C. Ammonium carbonate thermally decomposed and generated carbon dioxide gas, beginning at about 80° C. A large number of gas bubbles were generated.

[0204] In one example, 10 mg of ammonium carbonate powders, with the average particle size of about 80 μm, were compressed onto a cathode film, using a type 5582 Instron machine at 30 MPa. The cathode diameter was 16 mm, and its thickness was about 150 μm. The cathode film was supported by a copper (Cu) disk charge collector. The Cu disk diameter

was 18 mm, and its thickness was 3 mm. A 25 μm thick Celgard 2325 PP/PE/PP membrane separator was firmly compressed on the top of the cathode film. The lateral surface of the cathode and the membrane separator was strengthened by a layer of Devcon 5 min epoxy glue. The glue layer thickness was nearly 30 μm . About 0.5 ml electrolyte, 1 M LiPF₆ dissolved in EC:EMC (1:1 by weight), was dropped on the electrode-membrane system by a plastic disposable pipette. A second Cu disk charge collector with a diameter of 16 mm and a thickness of 3 mm was placed on top of the membrane separator. The two Cu charge collectors were connected by a RadioShack 22-812 multimeter, to measure the impedance of the electrode-membrane system. This setup could be heated by a Barnstead Cimarec digital HP 131125 hot plate from Thermo Scientific of Waltham, Massachusetts. The impedance was measured at both room temperature (25° C.) and 100° C. It could be clearly observed that as temperature increased, gas bubbles generated between the membrane and the electrode block ion transport and, increase an impedance of the system. At room temperature, the measured impedance was 5 k Ω ; at 100° C., the impedance increased by more than 2 times to 12 k Ω . The gas bubble size was around a few hundred microns.

[0205] Upon mechanical or thermal loading, if electrolyte absorbers (EA) can be released or be exposed to an electrolyte, the amount of electrolyte available for ion transport would be reduced, creating the condition of “electrolyte starvation” (ES) in membrane separator and/or in electrodes, or both. The flammability of the electrolyte absorbed in EA is also reduced, as it is isolated from the environment.

[0206] FIG. 23A shows nanoporous carbon **2302** (BP2000 obtained from Cabot Corporation of Boston, Mass.) that can be used to absorb electrolyte. The particles have nanopores of nanometer scale a specific surface area that is around 2000 m²/g, and a porosity of 80%. As the particles **2302** are exposed to the electrolyte solution, the nanopores **2304** are filled by the liquid spontaneously. Thereafter, electrolyte starvation is developed in other areas. About 0.1 g of BP 2000 particles were placed in a sample glass container. About 0.4 mL 1 M LiPF₆ in EC/EMC electrolyte (LP 50, BASF) was dropped onto the particles. The electrolyte was completely absorbed by the BP 2000 particles in a few seconds. Similar to carbon black particles, porous silica or silica gel can be used as electrolyte absorber. In one example, iTNM-b **2306** was used as EA. The raw material was obtained from JLK Industries of Coopersburg, Pa. (Product No. PP-35-HP-HS-18). The received nanoporous silica particles were heated in vacuum at 450° C. for 12 h. The nanoporous silica particles have the pore size around 100 nm. About 0.1 g of nanoporous silica particles were placed in a glass container. About 0.4 mL 1 M LiPF₆ in EC/EMC electrolyte (LP 50 from BASF of Ludwigshafen, Germany) was dropped onto the particles. The electrolyte was completely absorbed by the nanoporous silica particles in a few seconds to form electrolyte soaked nanoporous silica particle **2308**.

[0207] FIG. 24A shows a solution **2402** of 0.05 g ammonium carbonate in 5 ml of 50% ethyl methyl carbonate (EMC) and 50% ethylene carbonate (EC) before and after heating at 100° C. A larger amount of liquid was used to show more clearly the generated gas bubbles **2404**. Ammonium carbonate thermally decomposed and generated carbon dioxide, beginning at about 80° C., as shown in FIG. 24B.

[0208] Similarly, while operations are depicted in the drawings in a particular order, this should not be understood as

requiring that such operations be performed in the particular order shown or in sequential order, or that all illustrated operations be performed, to achieve desirable results. In addition, the systems and techniques described above can be combined with the subject matter of the patent application entitled, “Rate-sensitive and self-releasing battery cells and battery-cell structures as structural and/or energy-absorbing vehicle components”, filed on the same day. For example, a non-chemical approach to developing low-cost, robust, and multifunctional battery systems for electric vehicles can be enabled.

[0209] The first material/device includes an elastic energy storage material or device. The elastic energy storage material or device can be placed inside or near electrode.

[0210] The elastic energy storage material or device can be confined by a locking component. Upon mechanical or thermal loading, the locking component can be weakened, softened, or broken part, so as to release elastic energy.

[0211] The elastic energy storage material or device can directly release elastic energy into the electrode, or deform or displace other damage initiators. Both cause widespread damage in electrode.

[0212] The damage initiators in electrode can deform, displace, debond, or fracture or rupture upon mechanical or thermal loading, aided by another material or device.

[0213] The elastic energy storage material or device can be charge collector, membrane separator, battery case, or a part of them, as they are prestressed and released upon mechanical or thermal loading.

[0214] The first material/device includes a heterogeneous or nonuniformly distributed, or anisotropic damage initiators. The damage initiators can be placed inside or near electrodes.

[0215] Upon mechanical loading, the damage initiators or electrode materials near such damage initiators deform or displace heterogeneously or anisotropically (i.e. differently in different areas or along different directions), causing widespread damage, as local bending, torsion, shear, compression, tension, debonding, cracking, or voiding is promoted. As charge collectors, membrane separators, or battery case have heterogeneous or anisotropic shapes or surface patterns or materials/components, they can become such damage initiators.

[0216] Using a soft impact promotion layer helps promote widespread damaging.

[0217] The electrolyte absorbers include materials that can absorb electrolyte, materials that prevent electrolyte from being available for ion transport, materials that isolate electrolyte from the rest of battery system.

[0218] The gas generation agents include materials that generate gas phase or gas bubbles, which can be placed in electrode, membrane separator, or electrolyte.

[0219] The container can be used to house any materials that mitigate thermal runaway. The container of the second material is optional if the second material is stable and non-reactive under battery operation condition.

[0220] The first material includes an elastic energy storage material or device. The elastic energy storage material or device can be placed inside or near electrode.

[0221] The elastic energy storage material or device can be confined by a locking component. Upon mechanical or thermal loading, the locking component can be weakened, softened, or broken, so as to release elastic energy.

[0222] The elastic energy storage material or device can directly release elastic energy into the electrode, or deform or displace other damage initiators, causing widespread damage in electrode.

[0223] The damage initiators in or near electrode can deform, displace, debond, or fracture or rupture upon mechanical or thermal loading.

[0224] The damage initiators in or near electrode can deform, displace, debond, or fracture or rupture upon mechanical or thermal loading, aided by another material or device in battery.

[0225] The elastic energy storage material or device can be charge collector, membrane separator, battery case, or a part of them, as they are prestressed and released upon mechanical or thermal loading.

[0226] The first material includes a heterogeneous or non-uniformly distributed, or anisotropic damage initiators, which can be placed inside or near electrodes.

[0227] Upon mechanical loading, the damage initiators or electrode materials near such damage initiators deform or displace heterogeneously or anisotropically (i.e. differently in different areas or along different directions), causing widespread damage, as local bending, torsion, shear, compression, tension, debonding, cracking, or voiding is promoted. Charge collectors, membrane separators, or battery case having heterogeneous or anisotropic shapes or surface patterns or materials/components can become such damage initiators.

[0228] Using soft impact promotion components helps promote widespread damaging. Particular embodiments of the invention have been described.

[0229] Changing a configuration of an electrolyte can include creating bubbles, absorbing liquids, increasing resistivity, or changing viscosity.

[0230] Other embodiments are within the scope of the following claims. For example, the actions recited in the claims can be performed in a different order and still achieve desirable results.

1. A method of manufacturing a battery, the method comprising:

- introducing a first material to the battery;
- providing an anode, a cathode, charge collectors, and a separator of the battery; and
- assembling the anode, the separator and the cathode, wherein the first material is configured and arranged to increase the impedance of the battery upon mechanical loading.

2-4. (canceled)

5. The method of claim 1, wherein the first material comprises a particle, a fiber, a tube, a layer, or a platelet, the first material formed of one or more of carbon, a glass, ceramic materials, metallic materials, polymer materials, liquids, gels, or composites produced from combinations thereof.

6. The method of claim 1, wherein the first material comprises an array or a mesh or a truss, or a layer stack, the first material formed of one or more of carbon, a glass, ceramic materials, metallic materials, polymer materials, liquids, gels, or composites produced from combinations thereof.

7. (canceled)

8. The method of claim 1, wherein the first material comprises a shape or volume changing material, the shape or volume changing material having a first shape or volume below a transition temperature and a second shape or volume at or above the transition temperature.

9-11. (canceled)

12. The method of claim 1, wherein the first material has anisotropic properties and promotes damages in the electrode upon mechanical loading due to stiffness mismatch and local bending.

13-16. (canceled)

17. A method of manufacturing a battery, the method comprising:

- introducing a first device to the battery;
- providing an anode, a cathode, a separator, charge collectors, binders, an electrolyte, and a case of the battery; and

assembling the anode, the separator and the cathode, wherein the first device is configured and arranged to promote damages in electrodes or to change configurations of the electrolyte upon mechanical or thermal loading.

18. The method of claim 17, wherein the first device comprises a first material that is stable and non-reactive under battery operation conditions.

19. The method of claim 17, wherein the first device comprises a container, the container encloses a second material, the container being configured to release or to expose the second material upon mechanical or thermal loading.

20. (canceled)

21. The method of claim 19, wherein the fire-extinguishing agents, thermal runaway retarders, electrolyte absorbers, and gas generation agents comprise solid, gel or liquid materials, foaming materials that generate gas or bubbles.

22. (canceled)

23. A method of reducing or eliminating thermal runaway in a battery, the method comprising:

- increasing an internal impedance of the battery upon mechanical loading or thermal loading to reduce or eliminate thermal runaway in the battery.

24. (canceled)

25. The method of claim 23, wherein increasing the internal impedance comprises causing cracks, voids, or debonding in the battery.

26. The method of claim 23, further comprising causing a first material in the battery to change from a first shape or volume to a second shape or volume upon thermal loading to cause cracks, voids or debonding in the electrodes, charge collector, electrolyte, or membrane of the battery, the shape or volume-changing material having a first shape or volume below a transition temperature and a second shape or volume at or above the transition temperature, or the shape or volume-changing material having the first shape or volume before mechanical loading and the second shape or volume upon mechanical loading.

27-29. (canceled)

30. The method of claim 26, further comprising directly releasing elastic energy from the elastic energy storage material into the electrode to displace a plurality of damage initiators, and causing damage in the electrode.

31. The method of claim 30, wherein the plurality of damage initiators in the electrode deforms upon mechanical or thermal loading when aided by another material.

32. (canceled)

33. A battery comprising:

- electrodes;
- a membrane;
- an electrolyte;
- charge collectors; and

a first material configured and arranged to increase an internal impedance of the battery upon mechanical or thermal loading to reduce or eliminate thermal runaway.

34. The battery of claim **33**, wherein the first material is embedded in the one or more of the electrodes, charge collectors, or membrane, the first material configured to create cracks or voids or debonding in the one or more electrodes, membrane, electrolyte, or charge collectors, upon mechanical or thermal loading.

35-36. (canceled)

37. The battery of claim **33**, wherein a second material comprises fire-extinguishing agents, thermal runaway retarders, electrolyte absorbers, gas generation agents, or a combination of them, the fire-extinguishing agents comprise solid or liquid chemicals, and the thermal runaway retarders and gas generation agents comprise foaming materials that generate bubbles.

38. The battery of claim **33**, wherein the gas generation agents comprise materials that generate gas phase or gas bubbles, and the gas generation agents are provided, as particles, layers, or aggregates, in or on one or more electrodes, the charge collectors, the case, the membrane separators, or the electrolyte.

39-40. (canceled)

41. The battery of claim **22**, wherein the first material comprises a binder of the one or more electrodes, the binder configured to crack upon mechanical loading, or thermal abuse.

42. (canceled)

43. The method of claim **19**, wherein the second material comprises fire-extinguishing agents, thermal runaway retarders, electrolyte absorbers, and gas generation agents.

* * * * *