



US 20230352437A1

(19) **United States**

(12) **Patent Application Publication**  
**Brodoceanu et al.**

(10) **Pub. No.: US 2023/0352437 A1**

(43) **Pub. Date: Nov. 2, 2023**

(54) **HYBRID INTERCONNECT FOR LASER BONDING USING NANOPOROUS METAL TIPS**

(71) Applicant: **Meta Platforms Technologies, LLC**,  
Menlo Park, CA (US)

(72) Inventors: **Daniel Brodoceanu**, Cork (IE); **Zheng Sung Chio**, Cork (IE); **Oscar Torrents Abad**, Cork (IE); **Jeb Wu**, Redmond, WA (US); **Ali Sengül**, Zurich (CH)

(21) Appl. No.: **17/867,467**

(22) Filed: **Jul. 18, 2022**

**Related U.S. Application Data**

(62) Division of application No. 16/783,580, filed on Feb. 6, 2020, now Pat. No. 11,424,214.

(60) Provisional application No. 62/913,645, filed on Oct. 10, 2019.


**Publication Classification**

(51) **Int. Cl.**  
*H01L 23/00* (2006.01)  
*H01L 25/16* (2006.01)  
*H01L 25/18* (2006.01)  
*H01L 25/00* (2006.01)

(52) **U.S. Cl.**  
CPC ..... *H01L 24/80* (2013.01); *H01L 25/167* (2013.01); *H01L 25/18* (2013.01); *H01L 24/05* (2013.01); *H01L 25/50* (2013.01); *H01L 2224/81895* (2013.01); *H01L 2224/05644* (2013.01); *H01L 2224/81009* (2013.01); *H01L 2224/80203* (2013.01); *H01L 2224/80224* (2013.01); *H01L 2224/80895* (2013.01); *H01L 2224/80815* (2013.01); *H01L 2224/80009* (2013.01); *H01L 2224/8112* (2013.01); *H01L 2224/8012* (2013.01); *H01L 2924/12041* (2013.01); *H01L 2224/81203* (2013.01); *H01L 2224/05541* (2013.01)

(57) **ABSTRACT**

Embodiments relate to using nanoporous metal tips to establish connections between a first body and a second body. The first body is positioned relative to the second body to align contacts protruding from a first surface of the first body with electrodes protruding from a second surface of the second body. The second surface faces the first surface. The contacts, the electrodes, or both comprise nanoporous metal tips. A relative movement is made between the first body and the second body after positioning the first body to approach the first body to the second body. The contacts and the electrodes are bonded by melting and solidifying the nanoporous metal tips after approaching the first body and the second body.






FIG. 1




FIG. 2



300




FIG. 3

400




FIG. 4




FIG. 5A

FIG. 5B

600




FIG. 6






FIG. 7A




FIG. 7B






FIG. 8A

FIG. 8B




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 9D



1000




FIG. 10






FIG. 11A




FIG. 11B




FIG. 12



**HYBRID INTERCONNECT FOR LASER  
BONDING USING NANOPOROUS METAL  
TIPS**

CROSS-REFERENCE TO RELATED  
APPLICATION

[0001] This application is a divisional application of U.S. patent application Ser. No. 16/783,580, filed Feb. 6, 2020, which claims the benefit of U.S. Provisional Application No. 62/913,645 filed Oct. 10, 2019, which are hereby incorporated by reference in its entirety.

FIELD OF THE INVENTION

[0002] This disclosure relates generally to micro light emitting diodes (micro-LEDs) for a display, and more specifically to establishing hybrid interconnections between micro-LEDs and control circuits in display devices using nanoporous metal tips.

BACKGROUND

[0003] Various types of light sources are used in many electronic display devices, such as televisions, computer monitors, laptop computers, tablets, smartphones, projection systems, and head-mounted devices (e.g., virtual reality (VR) devices, augmented reality (AR) devices, and/or mixed-reality (MR) devices). Modern displays may include well over ten million individual light sources that may be arranged in rows and columns on one or more backplanes. When assembling the display, it is typically required to electrically couple, bond, or affix (i.e., establish an interconnection with) each of the light sources to the backplane.

SUMMARY

[0004] Embodiments relate to a hybrid interconnection for laser bonding of a first body to a second body using nanoporous metal tips. The first body has a first surface with contacts protruding from the first surface. The second body has a second surface with corresponding electrodes protruding from the second surface. The second surface faces the first surface. The contacts, the electrodes, or both comprise nanoporous metal tips. The contacts bond with corresponding electrodes by melting and solidifying the nanoporous metal tips.

[0005] Embodiments also relate to using nanoporous metal tips to establish connections between a first body and a second body. The first body is positioned relative to the second body to align contacts protruding from a first surface of the first body with electrodes protruding from a second surface of the second body. The second surface faces the first surface. The contacts, the electrodes, or both comprise nanoporous metal tips. A relative movement is made between the first body and the second body after positioning the first body to approach the first body to the second body. The contacts and the electrodes are bonded by melting and solidifying the nanoporous metal tips after approaching the first body and the second body.

BRIEF DESCRIPTION OF THE DRAWINGS

[0006] FIG. 1 is a block diagram of an artificial reality system including a near-eye display, in accordance with one or more embodiments.

[0007] FIG. 2 is a perspective view of a near-eye display in the form of a head-mounted display (HMD) device, in accordance with one or more embodiments.

[0008] FIG. 3 is a perspective view of a near-eye display in the form of a pair of glasses, in accordance with one or more embodiments.

[0009] FIG. 4 illustrates an optical see-through augmented reality system including a waveguide display, in accordance with one or more embodiments.

[0010] FIG. 5A illustrates an example of a near-eye display device including a waveguide display, in accordance with one or more embodiments.

[0011] FIG. 5B illustrates an example of a near-eye display device including a waveguide display, in accordance with one or more embodiments.

[0012] FIG. 6 illustrates an image source assembly in an augmented reality system, in accordance with one or more embodiments.

[0013] FIG. 7A illustrates a light emitting diode (LED) having a vertical mesa structure, in accordance with one or more embodiments.

[0014] FIG. 7B is a cross-sectional view of a LED having a parabolic mesa structure, in accordance with one or more embodiments.

[0015] FIG. 8A illustrates a method of die-to-wafer bonding for arrays of LEDs, in accordance with one or more embodiments.

[0016] FIG. 8B illustrates a method of wafer-to-wafer bonding for arrays of LEDs, in accordance with one or more embodiments.

[0017] FIGS. 9A-9D illustrates a method of hybrid bonding for arrays of LEDs, in accordance with one or more embodiments.

[0018] FIG. 10 illustrates a LED array with secondary optical components fabricated thereon, in accordance with one or more embodiments.

[0019] FIGS. 11A and 11B are cross-sectional views of bonding contacts and electrodes using nanoporous metal tips as a hybrid interconnect, in accordance with one or more embodiments.

[0020] FIG. 12 is a flowchart illustrating a process for interconnecting a first body to a second body via contact and electrodes using nanoporous metal tips, in accordance with one or more embodiments.

[0021] The figures depict various embodiments for purposes of illustration only. One skilled in the art will readily recognize from the following discussion that alternative embodiments of the structures and methods illustrated herein may be employed without departing from the principles described herein.

DETAILED DESCRIPTION

[0022] Embodiments relate to a hybrid interconnection for bonding electrodes with corresponding contacts using nanoporous metal tips. The contacts, the electrodes, or both have nanoporous metal tips. The contacts bond with corresponding electrodes by melting and solidifying the nanoporous metal tips. The contacts and/or the electrodes are heated so that nanoporous metal at the tip may melt to have spherical surfaces. By having the nanoporous metal located only at the tips of the contacts and/or the electrodes, the resulting interconnection after the laser bonding takes place between the contacts and the electrodes has less variations and reduces the likelihood of creating a short. For instance,



a contact and/or electrode comprised of nanoporous metal (i.e., nanoporous metal located throughout the entire contact and/or electrode) may convert from a cylindrical shape to a spherical droplet upon laser bonding. The volume and shape change may result in significant height variations that may lead to bonding failure (e.g., shorts or opens).

[0023] FIG. 1 is a block diagram of an artificial reality system 100 including a near-eye display 120, in accordance with one or more embodiments. The artificial reality system environment 100 shown in FIG. 1 may include the near-eye display 120, an optional external imaging device 150, and an optional input/output interface 140, each of which may be coupled to an optional console 110. While FIG. 1 shows an example of the artificial reality system environment 100 including one near-eye display 120, one external imaging device 150, and one input/output interface 140, any number of these components may be included in the artificial reality system environment 100, or any of the components may be omitted. For example, there may be multiple near-eye displays 120 monitored by one or more external imaging devices 150 in communication with a console 110. In some configurations, the artificial reality system environment 100 may not include the external imaging device 150, the optional input/output interface 140, and the optional console 110. In alternative configurations, different or additional components may be included in the artificial reality system environment 100.

[0024] The near-eye display 120 may be a head-mounted display that presents content to a user. Examples of content presented by the near-eye display 120 include one or more of images, videos, audio, or any combination thereof. In some embodiments, audio may be presented via an external device (e.g., speakers and/or headphones) that receives audio information from the near-eye display 120, the console 110, or both, and presents audio data based on the audio information. The near-eye display 120 may include one or more rigid bodies, which may be rigidly or non-rigidly coupled to each other. A rigid coupling between rigid bodies may cause the coupled rigid bodies to act as a single rigid entity. A non-rigid coupling between rigid bodies may allow the rigid bodies to move relative to each other. In various embodiments, the near-eye display 120 may be implemented in any suitable form-factor, including a pair of glasses. Some embodiments of the near-eye display 120 are further described below with respect to FIGS. 2 and 3. Additionally, in various embodiments, the functionality described herein may be used in a headset that combines images of an environment external to the near-eye display 120 and artificial reality content (e.g., computer-generated images). Therefore, the near-eye display 120 may augment images of a physical, real-world environment external to the near-eye display 120 with generated content (e.g., images, video, sound, etc.) to present an augmented reality to a user.

[0025] In various embodiments, the near-eye display 120 may include one or more of display electronics 122, display optics 124, and an eye-tracking unit 130. In some embodiments, the near-eye display 120 may also include one or more locators 126, one or more position sensors 128, and an inertial measurement unit (IMU) 132. The near-eye display 120 may omit any of the eye-tracking unit 130, the locators 126, the position sensors 128, and the IMU 132, or include additional elements in various embodiments. Additionally, in some embodiments, the near-eye display 120 may include

elements combining the function of various elements described in conjunction with FIG. 1.

[0026] The display electronics 122 may display or facilitate the display of images to the user according to data received from, for example, the console 110. In various embodiments, the display electronics 122 may include one or more display panels, such as a liquid crystal display (LCD), an organic light emitting diode (OLED) display, an inorganic light emitting diode (ILED) display, a micro light emitting diode (micro-LED) display, an active-matrix OLED display (AMOLED), a transparent OLED display (TOLED), or some other display. For example, in one implementation of the near-eye display 120, the display electronics 122 may include a front TOLED panel, a rear display panel, and an optical component (e.g., an attenuator, polarizer, or diffractive or spectral film) between the front and rear display panels. The display electronics 122 may include pixels to emit light of a predominant color such as red, green, blue, white, or yellow. In some implementations, the display electronics 122 may display a three-dimensional (3D) image through stereoscopic effects produced by two-dimensional (2D) panels to create a subjective perception of image depth. For example, the display electronics 122 may include a left display and a right display positioned in front of a user's left eye and right eye, respectively. The left and right displays may present copies of an image shifted horizontally relative to each other to create a stereoscopic effect (i.e., a perception of image depth by a user viewing the image).

[0027] In certain embodiments, the display optics 124 may display image content optically (e.g., using optical waveguides and couplers) or magnify image light received from the display electronics 122, correct optical errors associated with the image light, and present the corrected image light to a user of the near-eye display 120. In various embodiments, the display optics 124 may include one or more optical elements, such as, for example, a substrate, optical waveguides, an aperture, a Fresnel lens, a convex lens, a concave lens, a filter, input/output couplers, or any other suitable optical elements that may affect image light emitted from the display electronics 122. The display optics 124 may include a combination of different optical elements as well as mechanical couplings to maintain relative spacing and orientation of the optical elements in the combination. One or more optical elements in the display optics 124 may have an optical coating, such as an anti-reflective coating, a reflective coating, a filtering coating, or a combination of different optical coatings.

[0028] Magnification of the image light by the display optics 124 may allow the display electronics 122 to be physically smaller, weigh less, and consume less power than larger displays. Additionally, magnification may increase a field of view of the displayed content. The amount of magnification of image light by the display optics 124 may be changed by adjusting, adding, or removing optical elements from the display optics 124. In some embodiments, the display optics 124 may project displayed images to one or more image planes that may be further away from the user's eyes than the near-eye display 120.

[0029] The display optics 124 may also be designed to correct one or more types of optical errors, such as 2D optical errors, 3D optical errors, or any combination thereof. Two-dimensional errors may include optical aberrations that occur in two dimensions. Example types of 2D errors may



include barrel distortion, pincushion distortion, longitudinal chromatic aberration, and transverse chromatic aberration. Three-dimensional errors may include optical errors that occur in three dimensions. Example types of 3D errors may include spherical aberration, comatic aberration, field curvature, and astigmatism.

[0030] The locators **126** may be objects located in specific positions on the near-eye display **120** relative to one another and relative to a reference point on the near-eye display **120**. In some implementations, the console **110** may identify the locators **126** in images captured by the external imaging device **150** to determine the artificial reality headset's position, orientation, or both. A locator **126** may be an LED, a corner cube reflector, a reflective marker, a type of light source that contrasts with an environment in which the near-eye display **120** operates, or any combination thereof. In embodiments where the locators **126** are active components (e.g., LEDs or other types of light emitting devices), the locators **126** may emit light in the visible band (e.g., about 380 nm to 750 nm), in the infrared (IR) band (e.g., about 750 nm to 1 mm), in the ultraviolet band (e.g., about 10 nm to about 380 nm), in another portion of the electromagnetic spectrum, or in any combination of portions of the electromagnetic spectrum.

[0031] The external imaging device **150** may include one or more cameras, one or more video cameras, any other device capable of capturing images including one or more of the locators **126**, or any combination thereof. Additionally, the external imaging device **150** may include one or more filters (e.g., to increase signal to noise ratio). The external imaging device **150** may be configured to detect light emitted or reflected from the locators **126** in a field of view of the external imaging device **150**. In embodiments where the locators **126** include passive elements (e.g., retroreflectors), the external imaging device **150** may include a light source that illuminates some or all of the locators **126**, which may retro-reflect the light to the light source in the external imaging device **150**. Slow calibration data may be communicated from the external imaging device **150** to the console **110**, and the external imaging device **150** may receive one or more calibration parameters from the console **110** to adjust one or more imaging parameters (e.g., focal length, focus, frame rate, sensor temperature, shutter speed, aperture, etc.).

[0032] The position sensors **128** may generate one or more measurement signals in response to motion of the near-eye display **120**. Examples of position sensors **128** may include accelerometers, gyroscopes, magnetometers, other motion-detecting or error-correcting sensors, or any combination thereof. For example, in some embodiments, the position sensors **128** may include multiple accelerometers to measure translational motion (e.g., forward/back, up/down, or left/right) and multiple gyroscopes to measure rotational motion (e.g., pitch, yaw, or roll). In some embodiments, various position sensors may be oriented orthogonally to each other.

[0033] The IMU **132** may be an electronic device that generates fast calibration data based on measurement signals received from one or more of the position sensors **128**. The position sensors **128** may be located external to the IMU **132**, internal to the IMU **132**, or any combination thereof. Based on the one or more measurement signals from one or more position sensors **128**, the IMU **132** may generate fast calibration data indicating an estimated position of the near-eye display **120** relative to an initial position of the

near-eye display **120**. For example, the IMU **132** may integrate measurement signals received from accelerometers over time to estimate a velocity vector and integrate the velocity vector over time to determine an estimated position of a reference point on the near-eye display **120**. Alternatively, the IMU **132** may provide the sampled measurement signals to the console **110**, which may determine the fast calibration data. While the reference point may generally be defined as a point in space, in various embodiments, the reference point may also be defined as a point within the near-eye display **120** (e.g., a center of the IMU **132**).

[0034] The eye-tracking unit **130** may include one or more eye-tracking systems. Eye tracking may refer to determining an eye's position, including orientation and location of the eye, relative to the near-eye display **120**. An eye-tracking system may include an imaging system to image one or more eyes and may optionally include a light emitter, which may generate light that is directed to an eye such that light reflected by the eye may be captured by the imaging system. For example, the eye-tracking unit **130** may include a non-coherent or coherent light source (e.g., a laser diode) emitting light in the visible spectrum or infrared spectrum, and a camera capturing the light reflected by the user's eye. As another example, the eye-tracking unit **130** may capture reflected radio waves emitted by a miniature radar unit. The eye-tracking unit **130** may use low-power light emitters that emit light at frequencies and intensities that would not injure the eye or cause physical discomfort. The eye-tracking unit **130** may be arranged to increase contrast in images of an eye captured by the eye-tracking unit **130** while reducing the overall power consumed by the eye-tracking unit **130** (e.g., reducing power consumed by a light emitter and an imaging system included in the eye-tracking unit **130**). For example, in some implementations, the eye-tracking unit **130** may consume less than 100 milliwatts of power.

[0035] The near-eye display **120** may use the orientation of the eye to, e.g., determine an inter-pupillary distance (IPD) of the user, determine gaze direction, introduce depth cues (e.g., blur image outside of the user's main line of sight), collect heuristics on the user interaction in the VR media (e.g., time spent on any particular subject, object, or frame as a function of exposed stimuli), some other functions that are based in part on the orientation of at least one of the user's eyes, or any combination thereof. Because the orientation may be determined for both eyes of the user, the eye-tracking unit **130** may be able to determine where the user is looking. For example, determining a direction of a user's gaze may include determining a point of convergence based on the determined orientations of the user's left and right eyes. A point of convergence may be the point where the two foveal axes of the user's eyes intersect. The direction of the user's gaze may be the direction of a line passing through the point of convergence and the mid-point between the pupils of the user's eyes.

[0036] The input/output interface **140** may be a device that allows a user to send action requests to the console **110**. An action request may be a request to perform a particular action. For example, an action request may be to start or to end an application or to perform a particular action within the application. The input/output interface **140** may include one or more input devices. Example input devices may include a keyboard, a mouse, a game controller, a glove, a button, a touch screen, or any other suitable device for receiving action requests and communicating the received



action requests to the console **110**. An action request received by the input/output interface **140** may be communicated to the console **110**, which may perform an action corresponding to the requested action. In some embodiments, the input/output interface **140** may provide haptic feedback to the user in accordance with instructions received from the console **110**. For example, the input/output interface **140** may provide haptic feedback when an action request is received, or when the console **110** has performed a requested action and communicates instructions to the input/output interface **140**. In some embodiments, the external imaging device **150** may be used to track the input/output interface **140**, such as tracking the location or position of a controller (which may include, for example, an IR light source) or a hand of the user to determine the motion of the user. In some embodiments, the near-eye display **120** may include one or more imaging devices to track the input/output interface **140**, such as tracking the location or position of a controller or a hand of the user to determine the motion of the user.

[0037] The console **110** may provide content to the near-eye display **120** for presentation to the user in accordance with information received from one or more of the external imaging device **150**, the near-eye display **120**, and the input/output interface **140**. In the example shown in FIG. 1, the console **110** may include an application store **112**, a headset tracking module **114**, an artificial reality engine **116**, and an eye-tracking module **118**. Some embodiments of the console **110** may include different or additional modules than those described in conjunction with FIG. 1. Functions further described below may be distributed among components of the console **110** in a different manner than is described here.

[0038] In some embodiments, the console **110** may include a processor and a non-transitory computer-readable storage medium storing instructions executable by the processor. The processor may include multiple processing units executing instructions in parallel. The non-transitory computer-readable storage medium may be any memory, such as a hard disk drive, a removable memory, or a solid-state drive (e.g., flash memory or dynamic random access memory (DRAM)). In various embodiments, the modules of the console **110** described in conjunction with FIG. 1 may be encoded as instructions in the non-transitory computer-readable storage medium that, when executed by the processor, cause the processor to perform the functions further described below.

[0039] The application store **112** may store one or more applications for execution by the console **110**. An application may include a group of instructions that, when executed by a processor, generates content for presentation to the user. Content generated by an application may be in response to inputs received from the user via movement of the user's eyes or inputs received from the input/output interface **140**. Examples of the applications may include gaming applications, conferencing applications, video playback application, or other suitable applications.

[0040] The headset tracking module **114** may track movements of the near-eye display **120** using slow calibration information from the external imaging device **150**. For example, the headset tracking module **114** may determine positions of a reference point of the near-eye display **120** using observed locators from the slow calibration information and a model of the near-eye display **120**. The headset

tracking module **114** may also determine positions of a reference point of the near-eye display **120** using position information from the fast calibration information. Additionally, in some embodiments, the headset tracking module **114** may use portions of the fast calibration information, the slow calibration information, or any combination thereof, to predict a future location of the near-eye display **120**. The headset tracking module **114** may provide the estimated or predicted future position of the near-eye display **120** to the artificial reality engine **116**.

[0041] The artificial reality engine **116** may execute applications within the artificial reality system environment **100** and receive position information of the near-eye display **120**, acceleration information of the near-eye display **120**, velocity information of the near-eye display **120**, predicted future positions of the near-eye display **120**, or any combination thereof from the headset tracking module **114**. The artificial reality engine **116** may also receive estimated eye position and orientation information from the eye-tracking module **118**. Based on the received information, the artificial reality engine **116** may determine content to provide to the near-eye display **120** for presentation to the user. For example, if the received information indicates that the user has looked to the left, the artificial reality engine **116** may generate content for the near-eye display **120** that mirrors the user's eye movement in a virtual environment. Additionally, the artificial reality engine **116** may perform an action within an application executing on the console **110** in response to an action request received from the input/output interface **140**, and provide feedback to the user indicating that the action has been performed. The feedback may be visual or audible feedback via the near-eye display **120** or haptic feedback via the input/output interface **140**.

[0042] The eye-tracking module **118** may receive eye-tracking data from the eye-tracking unit **130** and determine the position of the user's eye based on the eye tracking data. The position of the eye may include an eye's orientation, location, or both relative to the near-eye display **120** or any element thereof. Because the eye's axes of rotation change as a function of the eye's location in its socket, determining the eye's location in its socket may allow the eye-tracking module **118** to more accurately determine the eye's orientation.

[0043] FIG. 2 is a perspective view of a near-eye display in the form of a head-mounted display (HMD) device **200**, in accordance with one or more embodiments. The HMD device **200** may be a part of, e.g., a VR system, an AR system, an MR system, or any combination thereof. The HMD device **200** may include a body **220** and a head strap **230**. FIG. 2 shows a bottom side **223**, a front side **225**, and a left side **227** of the body **220** in the perspective view. The head strap **230** may have an adjustable or extendible length. There may be a sufficient space between the body **220** and the head strap **230** of the HMD device **200** for allowing a user to mount the HMD device **200** onto the user's head. In various embodiments, the HMD device **200** may include additional, fewer, or different components. For example, in some embodiments, the HMD device **200** may include eyeglass temples and temple tips as shown in, for example, FIG. 3 below, rather than the head strap **230**.

[0044] The HMD device **200** may present to a user media including virtual and/or augmented views of a physical, real-world environment with computer-generated elements. Examples of the media presented by the HMD device **200**



may include images (e.g., 2D or 3D images), videos (e.g., 2D or 3D videos), audio, or any combination thereof. The images and videos may be presented to each eye of the user by one or more display assemblies (not shown in FIG. 2) enclosed in the body **220** of the HMD device **200**. In various embodiments, the one or more display assemblies may include a single electronic display panel or multiple electronic display panels (e.g., one display panel for each eye of the user). Examples of the electronic display panel(s) may include, for example, an LCD, an OLED display, an ILED display, a micro-LED display, an AMOLED, a TOLED, some other display, or any combination thereof. The HMD device **200** may include two eye box regions.

**[0045]** In some implementations, the HMD device **200** may include various sensors (not shown), such as depth sensors, motion sensors, position sensors, and eye tracking sensors. Some of these sensors may use a structured light pattern for sensing. In some implementations, the HMD device **200** may include an input/output interface for communicating with a console. In some implementations, the HMD device **200** may include a virtual reality engine (not shown) that can execute applications within the HMD device **200** and receive depth information, position information, acceleration information, velocity information, predicted future positions, or any combination thereof of the HMD device **200** from the various sensors. In some implementations, the information received by the virtual reality engine may be used for producing a signal (e.g., display instructions) to the one or more display assemblies. In some implementations, the HMD device **200** may include locators (not shown, such as the locators **126**) located in fixed positions on the body **220** relative to one another and relative to a reference point. Each of the locators may emit light that is detectable by an external imaging device.

**[0046]** FIG. 3 is a perspective view of a near-eye display **300** in the form of a pair of glasses, in accordance with one or more embodiments. The near-eye display **300** may be a specific implementation of the near-eye display **120** of FIG. 1, and may be configured to operate as a VR display, an AR display, and/or a MR display. The near-eye display **300** may include a frame **305** and a display **310**. The display **310** may be configured to present content to a user. In some embodiments, the display **310** may include display electronics and/or display optics. For example, as described above with respect to the near-eye display **120** of FIG. 1, the display **310** may include an LCD display panel, an LED display panel, or an optical display panel (e.g., a waveguide display assembly).

**[0047]** The near-eye display **300** may further include various sensors **350a**, **350b**, **350c**, **350d**, and **350e** on or within the frame **305**. In some embodiments, the sensors **350a-350e** may include one or more depth sensors, motion sensors, position sensors, inertial sensors, or ambient light sensors. In some embodiments, the sensors **350a-350e** may include one or more image sensors configured to generate image data representing different fields of views in different directions. In some embodiments, the sensors **350a-350e** may be used as input devices to control or influence the displayed content of the near-eye display **300**, and/or to provide an interactive VR/AR/MR experience to a user of the near-eye display **300**. In some embodiments, the sensors **350a-350e** may also be used for stereoscopic imaging.

**[0048]** In some embodiments, the near-eye display **300** may further include one or more illuminators **330** to project

light into the physical environment. The projected light may be associated with different frequency bands (e.g., visible light, infra-red light, ultra-violet light, etc.), and may serve various purposes. For example, the illuminator(s) **330** may project light in a dark environment (or in an environment with low intensity of infra-red light, ultra-violet light, etc.) to assist the sensors **350a-350e** in capturing images of different objects within the dark environment. In some embodiments, the illuminator(s) **330** may be used to project certain light pattern onto the objects within the environment. In some embodiments, the illuminator(s) **330** may be used as locators, such as the locators **126** described above with respect to FIG. 1.

**[0049]** In some embodiments, the near-eye display **300** may also include a high-resolution camera **340**. The camera **340** may capture images of the physical environment in the field of view. The captured images may be processed, for example, by a virtual reality engine (e.g., the artificial reality engine **116** of FIG. 1) to add virtual objects to the captured images or modify physical objects in the captured images, and the processed images may be displayed to the user by the display **310** for AR or MR applications.

**[0050]** FIG. 4 illustrates an optical see-through augmented reality system **400** including a waveguide display, in accordance with one or more embodiments. The augmented reality system **400** may include a projector **410** and a combiner **415**. The projector **410** may include a light source or image source **412** and projector optics **414**. In some embodiments, the light source or image source **412** may include one or more micro-LED devices described above. In some embodiments, the image source **412** may include a plurality of pixels that displays virtual objects, such as an LCD display panel or an LED display panel. In some embodiments, the light source **412** may include a light source that generates coherent or partially coherent light. For example, the light source **412** may include a laser diode, a vertical cavity surface emitting laser, an LED, and/or a micro-LED described above. In some embodiments, the light source **412** may include a plurality of light sources (e.g., an array of micro-LEDs described above) each emitting a monochromatic image light corresponding to a primary color (e.g., red, green, or blue). In some embodiments, the light source **412** may include three 2D arrays of micro-LEDs, where each 2D array of micro-LEDs may include micro-LEDs configured to emit light of a primary color (e.g., red, green, or blue). In some embodiments, the light source **412** may include an optical pattern generator, such as a spatial light modulator. The projector optics **414** may include one or more optical components that can condition the light from the light source **412**, such as expanding, collimating, scanning, or projecting light from the light source **412** to the combiner **415**. The one or more optical components may include, for example, one or more lenses, liquid lenses, mirrors, apertures, and/or gratings. For example, in some embodiments, the light source **412** may include one or more one-dimensional arrays or elongated 2D arrays of micro-LEDs, and the projector optics **414** may include one or more one-dimensional scanners (e.g., micro-mirrors or prisms) configured to scan the one-dimensional arrays or elongated 2D arrays of micro-LEDs to generate image frames. In some embodiments, the projector optics **414** may include a liquid lens (e.g., a liquid crystal lens) with a plurality of electrodes that allows scanning of the light from the light source **412**.



[0051] The combiner **415** may include an input coupler **430** for coupling light from the projector **410** into a substrate **420** of the combiner **415**. The combiner **415** may transmit at least 50% of light in a first wavelength range and reflect at least 25% of light in a second wavelength range. For example, the first wavelength range may be visible light from about 400 nm to about 650 nm, and the second wavelength range may be in the infrared band, for example, from about 800 nm to about 1000 nm. The input coupler **430** may include a volume holographic grating, a diffractive optical element (DOE) (e.g., a surface-relief grating), a slanted surface of the substrate **420**, or a refractive coupler (e.g., a wedge or a prism). The input coupler **430** may have a coupling efficiency of greater than 30%, 50%, 75%, 90%, or higher for visible light. Light coupled into the substrate **420** may propagate within the substrate **420** through, for example, total internal reflection (TIR). The substrate **420** may be in the form of a lens or a pair of eyeglasses. The substrate **420** may have a flat or a curved surface, and may include one or more types of dielectric materials, such as glass, quartz, plastic, polymer, poly(methyl methacrylate) (PMMA), crystal, or ceramic. A thickness of the substrate **420** may range from, for example, less than about 1 mm to about 10 mm or more. The substrate **420** may be transparent to visible light.

[0052] The substrate **420** may include or may be coupled to a plurality of output couplers **440** configured to extract at least a portion of the light guided by and propagating within the substrate **420** from the substrate **420**, and direct extracted light **460** to an eye **490** of the user of the augmented reality system **400**. As the input coupler **430**, the output couplers **440** may include grating couplers (e.g., volume holographic gratings or surface-relief gratings), other DOEs, prisms, etc. The output couplers **440** may have different coupling (e.g., diffraction) efficiencies at different locations. The substrate **420** may also allow light **450** from the environment in front of the combiner **415** to pass through with little or no loss. The output couplers **440** may also allow the light **450** to pass through with little loss. For example, in some implementations, the output couplers **440** may have a low diffraction efficiency for the light **450** such that the light **450** may be refracted or otherwise pass through the output couplers **440** with little loss, and thus may have a higher intensity than the extracted light **460**. In some implementations, the output couplers **440** may have a high diffraction efficiency for the light **450** and may diffract the light **450** to certain desired directions (i.e., diffraction angles) with little loss. As a result, the user may be able to view combined images of the environment in front of the combiner **415** and virtual objects projected by the projector **410**.

[0053] FIG. 5A illustrates an example of a near-eye display device **500** including a waveguide display **530**, in accordance with one or more embodiments. The near-eye display device **500** may be an example of the near-eye display **120**, the augmented reality system **400**, or another type of display device. The near-eye display device **500** may include a light source **510**, projection optics **520**, and a waveguide display **530**. The light source **510** may include multiple panels of light emitters for different colors, such as a panel of red light emitters **512**, a panel of green light emitters **514**, and a panel of blue light emitters **516**. The red light emitters **512** are organized into an array; the green light emitters **514** are organized into an array; and the blue light emitters **516** are organized into an array. The dimensions and

itches of the light emitters in the light source **510** may be small. For example, each light emitter may have a diameter less than 2  $\mu\text{m}$  (e.g., about 1.2  $\mu\text{m}$ ) and the pitch may be less than 2  $\mu\text{m}$  (e.g., about 1.5  $\mu\text{m}$ ). As such, the number of light emitters in each of the red light emitters **512**, the green light emitters **514**, and the blue light emitters **516** can be equal to or greater than the number of pixels in a display image, such as 960 $\times$ 720, 1280 $\times$ 720, 1440 $\times$ 1080, 1920 $\times$ 1080, 2160 $\times$ 1080, or 2560 $\times$ 1080 pixels. Thus, a display image may be generated simultaneously by the light source **510**. A scanning element may not be used in the near-eye display device **500**.

[0054] Before reaching the waveguide display **530**, the light emitted by the light source **510** may be conditioned by the projection optics **520**, which may include a lens array. The projection optics **520** may collimate or focus the light emitted by the light source **510** to the waveguide display **530**, which may include a coupler **532** for coupling the light emitted by the light source **510** into the waveguide display **530**. The light coupled into the waveguide display **530** may propagate within the waveguide display **530** through, for example, total internal reflection as described above with respect to FIG. 4. The coupler **532** may also couple portions of the light propagating within the waveguide display **530** out of the waveguide display **530** and towards a user's eye **590**.

[0055] FIG. 5B illustrates an example of a near-eye display device **550** including a waveguide display **580**, in accordance with one or more embodiments. In some embodiments, the near-eye display device **550** may use a scanning mirror **570** to project light from a light source **540** to an image field where a user's eye **590** may be located. The near-eye display device **550** may be an example of the near-eye display **120**, the augmented reality system **400**, or another type of display device. A light source **540** may include one or more rows or one or more columns of light emitters of different colors, such as multiple rows of red light emitters **542**, multiple rows of green light emitters **544**, and multiple rows of blue light emitters **546**. For example, the red light emitters **542**, the green light emitters **544**, and the blue light emitters **546** may each include N rows, each row including, for example, 2,560 light emitters (pixels). The red light emitters **542** are organized into an array; the green light emitters **544** are organized into an array; and the blue light emitters **546** are organized into an array. In some embodiments, the light source **540** may include a single line of light emitters for each color. In some embodiments, the light source **540** may include multiple columns of light emitters for each of red, green, and blue colors, where each column may include, for example, 1,080 light emitters. In some embodiments, the dimensions and/or pitches of the light emitters in the light source **540** may be relatively large (e.g., about 3-5  $\mu\text{m}$ ) and thus the light source **540** may not include sufficient light emitters for simultaneously generating a full display image. For example, the number of light emitters for a single color may be fewer than the number of pixels (e.g., 2560 $\times$ 1080 pixels) in a display image. The light emitted by the light source **540** may be a set of collimated or diverging beams of light.

[0056] Before reaching the scanning mirror **570**, the light emitted by the light source **540** may be conditioned by various optical devices, such as collimating lenses or a freeform optical element **560**. The freeform optical element **560** may include, for example, a multi-facets prism or



another light folding element that may direct the light emitted by the light source **540** towards the scanning mirror **570**, such as changing the propagation direction of the light emitted by the light source **540** by, for example, about 90° or larger. In some embodiments, the freeform optical element **560** may be rotatable to scan the light. The scanning mirror **570** and/or the freeform optical element **560** may reflect and project the light emitted by the light source **540** to the waveguide display **580**, which may include a coupler **582** for coupling the light emitted by the light source **540** into the waveguide display **580**. The light coupled into the waveguide display **580** may propagate within the waveguide display **580** through, for example, total internal reflection as described above with respect to FIG. 4. The coupler **582** may also couple portions of the light propagating within the waveguide display **580** out of the waveguide display **580** and towards the user's eye **590**.

**[0057]** The scanning mirror **570** may include a microelectromechanical system (MEMS) mirror or any other suitable mirrors. The scanning mirror **570** may rotate to scan in one or two dimensions. As the scanning mirror **570** rotates, the light emitted by the light source **540** may be directed to different areas of the waveguide display **580** such that a full display image may be projected onto the waveguide display **580** and directed to the user's eye **590** by the waveguide display **580** in each scanning cycle. For example, in embodiments where the light source **540** includes light emitters for all pixels in one or more rows or columns, the scanning mirror **570** may be rotated in the column or row direction (e.g., x or y direction) to scan an image. In embodiments where the light source **540** includes light emitters for some but not all pixels in one or more rows or columns, the scanning mirror **570** may be rotated in both the row and column directions (e.g., both x and y directions) to project a display image (e.g., using a raster-type scanning pattern).

**[0058]** The near-eye display device **550** may operate in predefined display periods. A display period (e.g., display cycle) may refer to a duration of time in which a full image is scanned or projected. For example, a display period may be a reciprocal of the desired frame rate. In the near-eye display device **550** that includes the scanning mirror **570**, the display period may also be referred to as a scanning period or scanning cycle. The light generation by the light source **540** may be synchronized with the rotation of the scanning mirror **570**. For example, each scanning cycle may include multiple scanning steps, where the light source **540** may generate a different light pattern in each respective scanning step.

**[0059]** In each scanning cycle, as the scanning mirror **570** rotates, a display image may be projected onto the waveguide display **580** and the user's eye **590**. The actual color value and light intensity (e.g., brightness) of a given pixel location of the display image may be an average of the light beams of the three colors (e.g., red, green, and blue) illuminating the pixel location during the scanning period. After completing a scanning period, the scanning mirror **570** may revert back to the initial position to project light for the first few rows of the next display image or may rotate in a reverse direction or scan pattern to project light for the next display image, where a new set of driving signals may be fed to the light source **540**. The same process may be repeated as the scanning mirror **570** rotates in each scanning cycle. As such, different images may be projected to the user's eye **590** in different scanning cycles.

**[0060]** FIG. 6 illustrates an image source assembly **610** in a near-eye display system **600**, in accordance with one or more embodiments. The image source assembly **610** may include, for example, a display panel **640** that may generate display images to be projected to the user's eyes, and a projector **650** that may project the display images generated by the display panel **640** to a waveguide display as described above with respect to FIGS. 4-5B. The display panel **640** may include a light source **642** and a driver circuit **644** for the light source **642**. The light source **642** may include, for example, the light source **510** or **540**. The projector **650** may include, for example, the freeform optical element **560**, the scanning mirror **570**, and/or the projection optics **520** described above in FIGS. 5A-5B. The near-eye display system **600** may also include a controller **620** that synchronously controls the light source **642** and the projector **650** (e.g., the scanning mirror **570**). The image source assembly **610** may generate and output an image light to a waveguide display (not shown in FIG. 6), such as the waveguide display **530** or **580**. As described above, the waveguide display may receive the image light at one or more input-coupling elements, and guide the received image light to one or more output-coupling elements. The input and output coupling elements may include, for example, a diffraction grating, a holographic grating, a prism, or any combination thereof. The input-coupling element may be chosen such that total internal reflection occurs with the waveguide display. The output-coupling element may couple portions of the total internally reflected image light out of the waveguide display.

**[0061]** As described above, the light source **642** may include a plurality of light emitters arranged in an array or a matrix. Each light emitter may emit monochromatic light, such as red light, blue light, green light, infra-red light, and the like. While RGB colors are often discussed in this disclosure, embodiments described herein are not limited to using red, green, and blue as primary colors. Other colors can also be used as the primary colors of the near-eye display system **600**. In some embodiments, a display panel in accordance with an embodiment may use more than three primary colors. Each pixel in the light source **642** may include three subpixels that include a red micro-LED, a green micro-LED, and a blue micro-LED. A semiconductor LED generally includes an active light emitting layer within multiple layers of semiconductor materials. The multiple layers of semiconductor materials may include different compound materials or a same base material with different dopants and/or different doping densities. For example, the multiple layers of semiconductor materials may include an n-type material layer, an active region that may include hetero-structures (e.g., one or more quantum wells), and a p-type material layer. The multiple layers of semiconductor materials may be grown on a surface of a substrate having a certain orientation. In some embodiments, to increase light extraction efficiency, a mesa that includes at least some of the layers of semiconductor materials may be formed.

**[0062]** The controller **620** may control the image rendering operations of the image source assembly **610**, such as the operations of the light source **642** and/or the projector **650**. For example, the controller **620** may determine instructions for the image source assembly **610** to render one or more display images. The instructions may include display instructions and scanning instructions. In some embodiments, the display instructions may include an image file (e.g., a bitmap file). The display instructions may be



received from, for example, a console, such as the console **110** described above with respect to FIG. **1**. The scanning instructions may be used by the image source assembly **610** to generate image light. The scanning instructions may specify, for example, a type of a source of image light (e.g., monochromatic or polychromatic), a scanning rate, an orientation of a scanning apparatus, one or more illumination parameters, or any combination thereof. The controller **620** may include a combination of hardware, software, and/or firmware not shown here so as not to obscure other aspects of the present disclosure.

[0063] In some embodiments, the controller **620** may be a graphics processing unit (GPU) of a display device. In other embodiments, the controller **620** may be other kinds of processors. The operations performed by the controller **620** may include taking content for display and dividing the content into discrete sections. The controller **620** may provide to the light source **642** scanning instructions that include an address corresponding to an individual source element of the light source **642** and/or an electrical bias applied to the individual source element. The controller **620** may instruct the light source **642** to sequentially present the discrete sections using light emitters corresponding to one or more rows of pixels in an image ultimately displayed to the user. The controller **620** may also instruct the projector **650** to perform different adjustments of the light. For example, the controller **620** may control the projector **650** to scan the discrete sections to different areas of a coupling element of the waveguide display (e.g., the waveguide display **580**) as described above with respect to FIG. **5B**. As such, at the exit pupil of the waveguide display, each discrete portion is presented in a different respective location. While each discrete section is presented at a different respective time, the presentation and scanning of the discrete sections occur fast enough such that a user's eye may integrate the different sections into a single image or series of images.

[0064] An image processor **630** may be a general-purpose processor and/or one or more application-specific circuits that are dedicated to performing the features described herein. In one embodiment, a general-purpose processor may be coupled to a memory to execute software instructions that cause the processor to perform certain processes described herein. In another embodiment, the image processor **630** may be one or more circuits that are dedicated to performing certain features. While the image processor **630** in FIG. **6** is shown as a stand-alone unit that is separate from the controller **620** and the driver circuit **644**, the image processor **630** may be a sub-unit of the controller **620** or the driver circuit **644** in other embodiments. In other words, in those embodiments, the controller **620** or the driver circuit **644** may perform various image processing functions of the image processor **630**. The image processor **630** may also be referred to as an image processing circuit.

[0065] In the example shown in FIG. **6**, the light source **642** may be driven by the driver circuit **644**, based on data or instructions (e.g., display and scanning instructions) sent from the controller **620** or the image processor **630**. In one embodiment, the driver circuit **644** may include a circuit panel that connects to and mechanically holds various light emitters of the light source **642**. The light source **642** may emit light in accordance with one or more illumination parameters that are set by the controller **620** and potentially adjusted by the image processor **630** and the driver circuit **644**. An illumination parameter may be used by the light

source **642** to generate light. An illumination parameter may include, for example, source wavelength, pulse rate, pulse amplitude, beam type (continuous or pulsed), other parameter(s) that may affect the emitted light, or any combination thereof. In some embodiments, the source light generated by the light source **642** may include multiple beams of red light, green light, and blue light, or any combination thereof.

[0066] The projector **650** may perform a set of optical functions, such as focusing, combining, conditioning, or scanning the image light generated by the light source **642**. In some embodiments, the projector **650** may include a combining assembly, a light conditioning assembly, or a scanning mirror assembly. The projector **650** may include one or more optical components that optically adjust and potentially re-direct the light from the light source **642**. One example of the adjustment of light may include conditioning the light, such as expanding, collimating, correcting for one or more optical errors (e.g., field curvature, chromatic aberration, etc.), some other adjustments of the light, or any combination thereof. The optical components of the projector **650** may include, for example, lenses, mirrors, apertures, gratings, or any combination thereof.

[0067] The projector **650** may redirect image light via its one or more reflective and/or refractive portions so that the image light is projected at certain orientations toward the waveguide display. The location where the image light is redirected toward may depend on specific orientations of the one or more reflective and/or refractive portions. In some embodiments, the projector **650** includes a single scanning mirror that scans in at least two dimensions. In other embodiments, the projector **650** may include a plurality of scanning mirrors that each scan in directions orthogonal to each other. The projector **650** may perform a raster scan (horizontally or vertically), a bi-resonant scan, or any combination thereof. In some embodiments, the projector **650** may perform a controlled vibration along the horizontal and/or vertical directions with a specific frequency of oscillation to scan along two dimensions and generate a 2D projected image of the media presented to user's eyes. In other embodiments, the projector **650** may include a lens or prism that may serve similar or the same function as one or more scanning mirrors. In some embodiments, the image source assembly **610** may not include a projector, where the light emitted by the light source **642** may be directly incident on the waveguide display.

[0068] FIG. **7A** illustrates a light emitting diode (LED) **700** having a vertical mesa structure, in accordance with one or more embodiments. The LED **700** may be a light emitter in the light source **510**, **540**, or **642**. The LED **700** may be a micro-LED made of inorganic materials, such as multiple layers of semiconductor materials. The layered semiconductor light emitting device may include multiple layers of III-V semiconductor materials. A III-V semiconductor material may include one or more Group III elements, such as aluminum (Al), gallium (Ga), or indium (In), in combination with a Group V element, such as nitrogen (N), phosphorus (P), arsenic (As), or antimony (Sb). When the Group V element of the III-V semiconductor material includes nitrogen, the III-V semiconductor material is referred to as a III-nitride material. The layered semiconductor light emitting device may be manufactured by growing multiple epitaxial layers on a substrate using techniques such as vapor-phase epitaxy (VPE), liquid-phase epitaxy (LPE), molecular beam epitaxy (MBE), or metalorganic chemical



vapor deposition (MOCVD). For example, the layers of the semiconductor materials may be grown layer-by-layer on a substrate with a certain crystal lattice orientation (e.g., polar, nonpolar, or semi-polar orientation), such as a GaN, GaAs, or GaP substrate, or a substrate including, but not limited to, sapphire, silicon carbide, silicon, zinc oxide, boron nitride, lithium aluminate, lithium niobate, germanium, aluminum nitride, lithium gallate, partially substituted spinels, or quaternary tetragonal oxides sharing the beta-LiAlO<sub>2</sub> structure, where the substrate may be cut in a specific direction to expose a specific plane as the growth surface.

[0069] In the example shown in FIG. 7A, the LED 700 may include a substrate 710, which may include, for example, a sapphire substrate or a GaN substrate. A semiconductor layer 720 may be grown on the substrate 710. The semiconductor layer 720 may include a III-V material, such as GaN, and may be p-doped (e.g., with Mg, Ca, Zn, or Be) or n-doped (e.g., with Si or Ge). One or more active layers 730 may be grown on the semiconductor layer 720 to form an active region. The active layer 730 may include III-V materials, such as one or more InGaN layers, one or more AlInGaP layers, and/or one or more GaN layers, which may form one or more heterostructures, such as one or more quantum wells or MQWs. A semiconductor layer 740 may be grown on the active layer 730. The semiconductor layer 740 may include a III-V material, such as GaN, and may be p-doped (e.g., with Mg, Ca, Zn, or Be) or n-doped (e.g., with Si or Ge). One of semiconductor layer 720 and semiconductor layer 740 may be a p-type layer and the other one may be an n-type layer. The semiconductor layer 720 and the semiconductor layer 740 sandwich the active layer 730 to form the light emitting region. For example, the LED 700 may include a layer of InGaN situated between a layer of p-type GaN doped with magnesium and a layer of n-type GaN doped with silicon or oxygen. In some embodiments, the LED 700 may include a layer of AlInGaP situated between a layer of p-type AlInGaP doped with zinc or magnesium and a layer of n-type AlInGaP doped with selenium, silicon, or tellurium.

[0070] In some embodiments, an electron-blocking layer (EBL) (not shown in FIG. 7A) may be grown to form a layer between the active layer 730 and at least one of the semiconductor layer 720 or the semiconductor layer 740. The EBL may reduce the electron leakage current and improve the efficiency of the LED. In some embodiments, a heavily-doped semiconductor layer 750, such as a P+ or P++ semiconductor layer, may be formed on the semiconductor layer 740 and act as a contact layer for forming an ohmic contact and reducing the contact impedance of the device. In some embodiments, a conductive layer 760 may be formed on the heavily-doped semiconductor layer 750. The conductive layer 760 may include, for example, an indium tin oxide (ITO) or Al/Ni/Au film. In one example, the conductive layer 760 may include a transparent ITO layer.

[0071] To make contact with the semiconductor layer 720 (e.g., an n-GaN layer) and to more efficiently extract light emitted by the active layer 730 from the LED 700, the semiconductor material layers (including the heavily-doped semiconductor layer 750, the semiconductor layer 740, the active layer 730, and the semiconductor layer 720) may be etched to expose the semiconductor layer 720 and to form a mesa structure that includes the layers 720-760. The mesa structure may confine the carriers within the device. Etching the mesa structure may lead to the formation of mesa

sidewalls 732 that may be orthogonal to the growth planes. A passivation layer 770 may be formed on the sidewalls 732 of the mesa structure. The passivation layer 770 may include an oxide layer, such as a SiO<sub>2</sub> layer, and may act as a reflector to reflect emitted light out of the LED 700. A contact layer 780, which may include a metal layer, such as Al, Au, Ni, Ti, or any combination thereof, may be formed on the semiconductor layer 720 and may act as an electrode of the LED 700. In addition, another contact layer 790, such as an Al/Ni/Au metal layer, may be formed on the conductive layer 760 and may act as another electrode of the LED 700.

[0072] When a voltage signal is applied to the contact layers 780 and 790, electrons and holes may recombine in the active layer 730, where the recombination of electrons and holes may cause photon emission. The wavelength and energy of the emitted photons may depend on the energy bandgap between the valence band and the conduction band in the active layer 730. For example, InGaN active layers may emit green or blue light, AlGaN active layers may emit blue to ultraviolet light, while AlInGaP active layers may emit red, orange, yellow, or green light. The emitted photons may be reflected by the passivation layer 770 and may exit the LED 700 from the top (e.g., the conductive layer 760 and the contact layer 790) or bottom (e.g., the substrate 710).

[0073] In some embodiments, the LED 700 may include one or more other components, such as a lens, on the light emission surface, such as the substrate 710, to focus or collimate the emitted light or couple the emitted light into a waveguide. In some embodiments, an LED may include a mesa of another shape, such as planar, conical, semi-parabolic, or parabolic, and a base area of the mesa may be circular, rectangular, hexagonal, or triangular. For example, the LED may include a mesa of a curved shape (e.g., paraboloid shape) and/or a non-curved shape (e.g., conic shape). The mesa may be truncated or non-truncated.

[0074] FIG. 7B is a cross-sectional view of a LED 705 having a parabolic mesa structure, in accordance with one or more embodiments. Similar to the LED 700, LED 705 may include multiple layers of semiconductor materials, such as multiple layers of III-V semiconductor materials. The semiconductor material layers may be epitaxially grown on a substrate 715, such as a GaN substrate or a sapphire substrate. For example, a semiconductor layer 725 may be grown on the substrate 715. The semiconductor layer 725 may include a III-V material, such as GaN, and may be p-doped (e.g., with Mg, Ca, Zn, or Be) or n-doped (e.g., with Si or Ge). One or more active layers 735 may be grown on the semiconductor layer 725. The active layer 735 may include III-V materials, such as one or more InGaN layers, one or more AlInGaP layers, and/or one or more GaN layers, which may form one or more heterostructures, such as one or more quantum wells. A semiconductor layer 745 may be grown on the active layer 735. The semiconductor layer 745 may include a III-V material, such as GaN, and may be p-doped (e.g., with Mg, Ca, Zn, or Be) or n-doped (e.g., with Si or Ge). One of the semiconductor layer 725 and the semiconductor layer 745 may be a p-type layer and the other one may be an n-type layer.

[0075] To make contact with the semiconductor layer 725 (e.g., an n-type GaN layer) and to more efficiently extract light emitted by the active layer 735 from the LED 705, the semiconductor layers may be etched to expose the semiconductor layer 725 and to form a mesa structure that includes



the layers **725-745**. The mesa structure may confine carriers within the injection area of the device. Etching the mesa structure may lead to the formation of mesa side walls (also referred to herein as facets) that may be non-parallel with, or in some cases, orthogonal, to the growth planes associated with crystalline growth of the layers **725-745**.

[0076] As shown in FIG. 7B, the LED **705** may have a mesa structure that includes a flat top. A dielectric layer **775** (e.g., SiO<sub>2</sub> or SiNx) may be formed on the facets of the mesa structure. In some embodiments, the dielectric layer **775** may include multiple layers of dielectric materials. In some embodiments, a metal layer **795** may be formed on the dielectric layer **775**. The metal layer **795** may include one or more metal or metal alloy materials, such as aluminum (Al), silver (Ag), gold (Au), platinum (Pt), titanium (Ti), copper (Cu), or any combination thereof. The dielectric layer **775** and the metal layer **795** may form a mesa reflector that can reflect light emitted by the active layer **735** toward the substrate **715**. In some embodiments, the mesa reflector may be parabolic-shaped to act as a parabolic reflector that may at least partially collimate the emitted light.

[0077] An electrical contact **765** and an electrical contact **785** may be formed on the semiconductor layer **745** and the semiconductor layer **725**, respectively, to act as electrodes. The electrical contact **765** and the electrical contact **785** may each include a conductive material, such as Al, Au, Pt, Ag, Ni, Ti, Cu, or any combination thereof (e.g., Ag/Pt/Au or Al/Ni/Au), and may act as the electrodes of the LED **705**. In the example shown in FIG. 7B, the electrical contact **785** may be an n-contact, and the electrical contact **765** may be a p-contact. The electrical contact **765** and the semiconductor layer **745** (e.g., a p-type semiconductor layer) may form a back reflector for reflecting light emitted by the active layer **735** back toward the substrate **715**. In some embodiments, the electrical contact **765** and the metal layer **795** include same material(s) and can be formed using the same processes. In some embodiments, an additional conductive layer (not shown) may be included as an intermediate conductive layer between the electrical contacts **765** and **785** and the semiconductor layers.

[0078] When a voltage signal is applied across the electrical contacts **765** and **785**, electrons and holes may recombine in the active layer **735**. The recombination of electrons and holes may cause photon emission, thus producing light. The wavelength and energy of the emitted photons may depend on the energy bandgap between the valence band and the conduction band in the active layer **735**. For example, InGaN active layers may emit green or blue light, while AlInGaP active layers may emit red, orange, yellow, or green light. The emitted photons may propagate in many different directions, and may be reflected by the mesa reflector and/or the back reflector and may exit the LED **705**, for example, from the bottom side (e.g., the substrate **715**) shown in FIG. 7B. One or more other secondary optical components, such as a lens or a grating, may be formed on the light emission surface, such as the substrate **715**, to focus or collimate the emitted light and/or couple the emitted light into a waveguide.

[0079] One or 2D arrays of the LEDs described above may be manufactured on a wafer to form light sources (e.g., the light source **642**). Driver circuits (e.g., the driver circuit **644**) may be fabricated, for example, on a silicon wafer using CMOS processes. The LEDs and the driver circuits on wafers may be diced and then bonded together, or may be

bonded on the wafer level and then diced. Various bonding techniques can be used for bonding the LEDs and the driver circuits, such as adhesive bonding, metal-to-metal bonding, metal oxide bonding, wafer-to-wafer bonding, die-to-wafer bonding, hybrid bonding, and the like.

[0080] FIG. 8A illustrates a method of die-to-wafer bonding for arrays of LEDs, in accordance with one or more embodiments. In the example shown in FIG. 8A, an LED array **801** may include a plurality of LEDs **807** on a carrier substrate **805**. The carrier substrate **805** may include various materials, such as GaAs, InP, GaN, AlN, sapphire, SiC, Si, or the like. The LEDs **807** may be fabricated by, for example, growing various epitaxial layers, forming mesa structures, and forming electrical contacts or electrodes, before performing the bonding. The epitaxial layers may include various materials, such as GaN, InGaN, (AlGaIn)P, (AlGaIn)AsP, (AlGaIn)AsN, (AlGaIn)Pas, (Eu:InGa)N, (AlGaIn)N, or the like, and may include an n-type layer, a p-type layer, and an active layer that includes one or more heterostructures, such as one or more quantum wells or MQWs. The electrical contacts may include various conductive materials, such as a metal or a metal alloy.

[0081] A wafer **803** may include a base layer **809** having passive or active integrated circuits (e.g., driver circuits **811**) fabricated thereon. The base layer **809** may include, for example, a silicon wafer. The driver circuits **811** may be used to control the operations of the LEDs **807**. For example, the driver circuit for each of the LEDs **807** may include a 2T1C pixel structure that has two transistors and one capacitor. The wafer **803** may also include a bonding layer **813**. The bonding layer **813** may include various materials, such as a metal, an oxide, a dielectric, CuSn, AuTi, and the like. In some embodiments, a patterned layer **815** may be formed on a surface of the bonding layer **813**, where the patterned layer **815** may include a metallic grid made of a conductive material, such as Cu, Ag, Au, Al, or the like.

[0082] An LED array **801** may be bonded to the wafer **803** via the bonding layer **813** or the patterned layer **815**. For example, the patterned layer **815** may include metal pads, bumps, and/or interconnects made of various materials, such as CuSn, AuSn, or nanoporous metal, that may be used to align the LEDs **807** of the LED array **801** with corresponding driver circuits **811** on the wafer **803**. In one example, the LED array **801** may be brought toward the wafer **803** until the LEDs **807** come into contact with respective metal pads, bumps, and/or interconnects corresponding to the driver circuits **811**. Some or all of the LEDs **807** may be aligned with the driver circuits **811**, and may then be bonded to the wafer **803** via the patterned layer **815** by various bonding techniques, such as metal-to-metal bonding. After the LEDs **807** have been bonded to the wafer **803**, the carrier substrate **805** may be removed from the LEDs **807**.

[0083] FIG. 8B illustrates a method of wafer-to-wafer bonding for arrays of LEDs, in accordance with one or more embodiments. As shown in FIG. 8B, a first wafer **802** may include a substrate **804**, a first semiconductor layer **806**, one or more active layers **808**, and a second semiconductor layer **810**. The substrate **804** may include various materials, such as GaAs, InP, GaN, AlN, sapphire, SiC, Si, or the like. The first semiconductor layer **806**, the active layers **808**, and the second semiconductor layer **810** may include various semiconductor materials, such as GaN, InGaN, (AlGaIn)P, (AlGaIn)AsP, (AlGaIn)AsN, (AlGaIn)Pas, (Eu:InGa)N, (AlGaIn)N, or the like. In some embodiments, the first



semiconductor layer **806** may be an n-type layer, and the second semiconductor layer **810** may be a p-type layer. For example, the first semiconductor layer **806** may be an n-doped GaN layer (e.g., doped with Si or Ge), and the second semiconductor layer **810** may be a p-doped GaN layer (e.g., doped with Mg, Ca, Zn, or Be). The active layers **808** may include, for example, one or more GaN layers, one or more InGaN layers, one or more AlInGaP layers, and the like, which may form one or more heterostructures, such as one or more quantum wells or MQWs.

[0084] In some embodiments, the first wafer **802** may also include a bonding layer **812**. The bonding layer **812** may include various materials, such as a metal, an oxide, a dielectric, CuSn, AuTi, nanoporous metal, or the like. In one example, the bonding layer **812** may include p-contacts and/or n-contacts (not shown). In some embodiments, other layers may also be included on the first wafer **802**, such as a buffer layer between the substrate **804** and the first semiconductor layer **806**. The buffer layer may include various materials, such as polycrystalline GaN or AlN. In some embodiments, a contact layer may be between the second semiconductor layer **810** and the bonding layer **812**. The contact layer may include any suitable material for providing an electrical contact to the second semiconductor layer **810** and/or the first semiconductor layer **806**.

[0085] The first wafer **802** may be bonded to a wafer **803** that includes driver circuits **811** and a bonding layer **813** as described above, via the bonding layer **813** and/or the bonding layer **812**. The bonding layer **812** and the bonding layer **813** may be made of the same material or different materials. The bonding layer **812** and the bonding layer **813** may be substantially flat. The first wafer **802** may be bonded to the wafer **803** by various methods, such as metal-to-metal bonding, eutectic bonding, metal oxide bonding, anodic bonding, thermo-compression bonding, ultraviolet (UV) bonding, and/or fusion bonding.

[0086] As shown in FIG. **8B**, the first wafer **802** may be bonded to the wafer **803** with the A-side (e.g., the second semiconductor layer **810**) of the first wafer **802** facing down (i.e., toward the wafer **803**). After bonding, the substrate **804** may be removed from the first wafer **802**, and the first wafer **802** may then be processed from the n-side. The processing may include, for example, the formation of certain mesa shapes for individual LEDs, as well as the formation of optical components corresponding to the individual LEDs.

[0087] FIGS. **9A-9D** illustrates a method of hybrid bonding for arrays of LEDs, in accordance with one or more embodiments. The hybrid bonding may generally include wafer cleaning and activation, high-precision alignment of contacts of one wafer with contacts of another wafer, dielectric bonding of dielectric materials at the surfaces of the wafers at room temperature, and metal bonding of the contacts by annealing at elevated temperatures. FIG. **9A** shows a substrate **910** with passive or active circuits **920** manufactured thereon. As described above with respect to FIGS. **8A-8B**, the substrate **910** may include, for example, a silicon wafer. The circuits **920** may include driver circuits for the arrays of LEDs and various electrical interconnects. A bonding layer may include dielectric regions **940** and contact pads **930** connected to the circuits **920** through electrical interconnects. The contact pads **930** may include solid metal and/or nanoporous metal, for example, the metals may include Cu, Ag, Au, Al, W, Mo, Ni, Ti, Pt, Pd, or the like. Dielectric materials in the dielectric regions **940**

may include SiCN, SiO<sub>2</sub>, SiN, Al<sub>2</sub>O<sub>3</sub>, HfO<sub>2</sub>, ZrO<sub>2</sub>, Ta<sub>2</sub>O<sub>5</sub>, or the like. The bonding layer may be planarized and polished using, for example, chemical mechanical polishing, where the planarization or polishing may cause dishing (a bowl like profile) in the contact pads. The surfaces of the bonding layers may be cleaned and activated by, for example, an ion (e.g., plasma) or a fast atom (e.g., Ar) beam **905**. The activated surface may be atomically clean and may be reactive for formation of direct bonds between wafers when they are brought into contact, for example, at room temperature.

[0088] FIG. **9B** illustrates a wafer **950** including an array of micro-LEDs **970** fabricated thereon as described above with respect to, for example, FIGS. **7A-8B**. The wafer **950** may be a carrier wafer and may include, for example, GaAs, InP, GaN, AlN, sapphire, SiC, Si, or the like. The micro-LEDs **970** may include an n-type layer, an active region, and a p-type layer epitaxially grown on the wafer **950**. The epitaxial layers may include various III-V semiconductor materials described above, and may be processed from the p-type layer side to etch mesa structures in the epitaxial layers, such as substantially vertical structures, parabolic structures, conic structures, or the like. Passivation layers and/or reflection layers may be formed on the sidewalls of the mesa structures. P-contacts **980** and n-contacts **982** may be formed in a dielectric material layer **960** deposited on the mesa structures and may make electrical contacts with the p-type layer and the n-type layers, respectively. Dielectric materials in the dielectric material layer **960** may include, for example, SiCN, SiO<sub>2</sub>, SiN, Al<sub>2</sub>O<sub>3</sub>, HfO<sub>2</sub>, ZrO<sub>2</sub>, Ta<sub>2</sub>O<sub>5</sub>, or the like. The p-contacts **980** and the n-contacts **982** may include solid metal and/or nanoporous metal, for example, the metals may include Cu, Ag, Au, Al, W, Mo, Ni, Ti, Pt, Pd, or the like. The top surfaces of the p-contacts **980**, the n-contacts **982**, and the dielectric material layer **960** may form a bonding layer. The bonding layer may be planarized and polished using, for example, chemical mechanical polishing, where the polishing may cause dishing in the p-contacts **980** and the n-contacts **982**. The bonding layer may then be cleaned and activated by, for example, an ion (e.g., plasma) or the fast atom (e.g., Ar) beam **915**. The activated surface may be atomically clean and reactive for formation of direct bonds between wafers when they are brought into contact, for example, at room temperature.

[0089] FIG. **9C** illustrates a room temperature bonding process for bonding the dielectric materials in the bonding layers. For example, after the bonding layer that includes the dielectric regions **940** and the contact pads **930** and the bonding layer that includes the p-contacts **980**, the n-contacts **982**, and the dielectric material layer **960** are surface activated, the wafer **950** and the micro-LEDs **970** may be turned upside down and brought into contact with the substrate **910** and the circuits formed thereon. In some embodiments, compression pressure **925** may be applied to the substrate **910** and the wafer **950** such that the bonding layers are pressed against each other. Due to the surface activation and the dishing in the contacts, the dielectric regions **940** and the dielectric material layer **960** may be in direct contact because of the surface attractive force, and may react and form chemical bonds between them because the surface atoms may have dangling bonds and may be in unstable energy states after the activation. Thus, the dielec-



tric materials in the dielectric regions **940** and the dielectric material layer **960** may be bonded together with or without heat treatment or pressure.

[0090] FIG. 9D illustrates an annealing process for bonding the contacts in the bonding layers after bonding the dielectric materials in the bonding layers. For example, the contact pads **930** and the p-contacts **980** or the n-contacts **982** may be bonded together by annealing at, for example, about 200-400° C. or higher. During the annealing process, heat **935** (e.g., emitted by a laser) may cause the contacts to expand more than the dielectric materials (due to different coefficients of thermal expansion), and thus may close the dishing gaps between the contacts such that the contact pads **930** and the p-contacts **980** or the n-contacts **982** may be in contact and may form direct metallic bonds at the activated surfaces.

[0091] In some embodiments where the two bonded wafers include materials having different coefficients of thermal expansion (CTEs), the dielectric materials bonded at room temperature may help to reduce or prevent misalignment of the contact pads caused by the different thermal expansions. In some embodiments, to further reduce or avoid the misalignment of the contact pads at a high temperature during annealing, trenches may be formed between micro-LEDs, between groups of micro-LEDs, through part or all of the substrate, or the like, before bonding.

[0092] After the micro-LEDs are bonded to the driver circuits, the substrate on which the micro-LEDs are fabricated may be thinned or removed, and various secondary optical components may be fabricated on the light emitting surfaces of the micro-LEDs to, for example, extract, collimate, and redirect the light emitted from the active regions of the micro-LEDs. In one example, micro-lenses may be formed on the micro-LEDs, where each micro-lens may correspond to a respective micro-LED and may help to improve the light extraction efficiency and collimate the light emitted by the micro-LED. In some embodiments, the secondary optical components may be fabricated in the substrate or the n-type layer of the micro-LEDs. In some embodiments, the secondary optical components may be fabricated in a dielectric layer deposited on the n-type side of the micro-LEDs. Examples of the secondary optical components may include a lens, a grating, an antireflection (AR) coating, a prism, a photonic crystal, or the like.

[0093] FIG. 10 illustrates a LED array **1000** with secondary optical components fabricated thereon, in accordance with one or more embodiments. The LED array **1000** may be made by bonding an LED chip or wafer with a silicon wafer including electrical circuits fabricated thereon, using any suitable bonding techniques described above with respect to, for example, FIGS. 8A-9D. In the example shown in FIG. 10, the LED array **1000** may be bonded using a wafer-to-wafer hybrid bonding technique as described above with respect to FIG. 9A-9D. The LED array **1000** may include a substrate **1010**, which may be, for example, a silicon wafer. Integrated circuits **1020**, such as LED driver circuits, may be fabricated on the substrate **1010**. The integrated circuits **1020** may be connected to p-contacts **1074** and n-contacts **1072** of micro-LEDs **1070** through contact pads **1030**, where the contact pads **1030** may form metallic bonds with the p-contacts **1074** and the n-contacts **1072**. A dielectric layer **1040** on the substrate **1010** may be bonded to a dielectric layer **1060** through fusion bonding.

[0094] The substrate (not shown) of the LED chip or wafer may be thinned or may be removed to expose the n-type layer **1050** of the micro-LEDs **1070**. Various secondary optical components, such as a spherical micro-lens **1082**, a grating **1084**, a micro-lens **1086**, an antireflection layer **1088**, and the like, may be formed in or on top of the n-type layer **1050**. For example, spherical micro-lens arrays may be etched in the semiconductor materials of the micro-LEDs **1070** using a gray-scale mask and a photoresist with a linear response to exposure light, or using an etch mask formed by thermal reflowing of a patterned photoresist layer. The secondary optical components may also be etched in a dielectric layer deposited on the n-type layer **1050** using similar photolithographic techniques or other techniques. For example, micro-lens arrays may be formed in a polymer layer through thermal reflowing of the polymer layer that is patterned using a binary mask. The micro-lens arrays in the polymer layer may be used as the secondary optical components or may be used as the etch mask for transferring the profiles of the micro-lens arrays into a dielectric layer or a semiconductor layer. The dielectric layer may include, for example, SiCN, SiO<sub>2</sub>, SiN, Al<sub>2</sub>O<sub>3</sub>, HfO<sub>2</sub>, ZrO<sub>2</sub>, Ta<sub>2</sub>O<sub>5</sub>, or the like. In some embodiments, the micro-LED **1070** may have multiple corresponding secondary optical components, such as a micro-lens and an anti-reflection coating, a micro-lens etched in the semiconductor material and a micro-lens etched in a dielectric material layer, a micro-lens and a grating, a spherical lens and an aspherical lens, and the like. Three different secondary optical components are illustrated in FIG. 10 to show some examples of secondary optical components that can be formed on the micro-LEDs **1070**, which does not necessarily imply that different secondary optical components are used simultaneously for every LED array.

[0095] FIGS. 11A and 11B are cross-sectional views of bonding contacts **1120** and electrodes **1140** using nanoporous metal tips (i.e., tips **1125** and tips **1145**) as a hybrid interconnect, in accordance with one or more embodiments. FIG. 11A shows a first body **1110** and a second body **1130** prior to being adjoined, according to an embodiment. The first body **1110** has a first surface **1115** with a plurality of contacts **1120** protruding from the first surface **1115**. In this embodiment, illustrated in FIG. 11A, the contacts **1120** include nanoporous metal tips **1125** formed on top of a base layer **1127**. The base layer **1127** may be made of a solid metal (e.g., Ti, Au, or other alloy). In some embodiments (not shown), the contacts **1120** do not include nanoporous metal tips **1125**. The nanoporous metal tips **1125** may be formed on the contacts **1120** using fabrication methods well known in the art. An example nanoporous metal tip fabrication method known to one skilled in the art is further described in “Nanoporous interconnects” by Herman Oppermann, Lothar Dietrich, Matthias Klein, and Bernhard Wunderle and published by *3rd Electronics System Integration Technology Conference ESTC* in September 2010, which is hereby incorporated by reference in its entirety for all purposes. The first body **1110** may also include a backplane substrate with CMOS periphery circuits. The first body **1110** may be a die or a wafer, as described above with reference to FIGS. 8A-9D.

[0096] The second body **1130** may comprise a substrate on which an array of light sources (e.g., an array of LEDs, such as an array of  $\mu$ LEDs) is formed. The array of light sources has a light-emission side and a side opposite the light-



emission side. The second body **1130** has a second surface **1135** that faces the first surface **1115** of the first body **1110**. In one example, the second surface **1135** is the side opposite the light-emission side. The second surface **1135** has a plurality of electrodes **1140** protruding from the second surface **1135** that are connected to electrical components or conductive traces in the second body **1130**. In this embodiment, illustrated in FIG. **11A**, the electrodes **1140** include nanoporous metal tips **1145** formed on top of a base layer **1147**. The base layer **1147** may be made of a solid metal (e.g., Au). In some embodiments (not shown), the electrodes **1140** do not include nanoporous metal tips **1145**. In one example, the first surface **1115** and/or the second surface **1135** may include a top insulation layer or a top passivation layer. The second body **1130** may be a die or a wafer separate from the first body **1110**, as described above with reference to FIGS. **8A-9D**.

[0097] As shown in FIG. **11A**, the contacts **1120** and the corresponding electrodes **1140** are not in contact or adjoined, but are aligned such that if either the first surface **1115** or the second surface **1135** were moved towards the other along a linear path, each contact **1120** would engage with a corresponding electrode **1140**. In another embodiment, the first body **1110** comprises one or more LEDs and the second body **1130** comprises a circuit to operate the one or more LEDs. The LEDs may have a size of less than 100  $\mu\text{m}$  (i.e., the LEDs may be micro-LEDs).

[0098] FIG. **11B** illustrates the first body **1110** and the second body **1130** bonded using a laser beam **1150**, according to one embodiment. In one embodiment, the laser beam **1150** may be applied to at least one of the contacts **1120** and the electrodes **1140** at a time. In some embodiments, the laser beam **1150** may be projected onto a subset of the contacts **1120** and the electrodes **1140** at a time. In one embodiment, the laser beam **1150** may be applied to the first body **1110**. In some embodiments, the laser beam **1150** may be applied to the second body **1130**. The laser beam **1150** may be scanned across either the first body **1110** or the second body **1130**. As the contacts and the electrodes are exposed to the laser beam **1150**, the nanoporous metal tips (i.e., the tips **1125** and the tips **1145**, respectively) melt and form bonding metal **1160**. The bonding metal **1160** is the melted and solidified nanoporous metal tips **1125**, **1145**. The bonding metal **1160** establishes an interconnection between the contacts and the electrodes and bonds the first body **1110** to the second body **1130**. In one example, the laser beam **1150** emits light with a wavelength of 360 nm (i.e., an ultraviolet ray) and forms a spot of 1.5-2 mm on the first body **1110**. In this example, a whole 3×4 mm chip may be bonded in a few seconds. In another example, the laser beam **1150** emits light with a wavelength of below 360 nm and forms a spot of 1 mm.

[0099] In one embodiment, the interconnection formed between the contacts **1120** and the electrodes **1140** (i.e., where bonding metal **1160** is formed) may connect the electrodes of the light sources of the second body **1130** with the CMOS periphery circuits in the backplane substrate of the first body **1110**. The CMOS periphery circuits may supply electrical current to the light sources through the interconnection. The number of the interconnections established may be less than the number of light sources in the array of light sources as one interconnection may be used to enable sending data to operate multiple light sources.

[0100] FIG. **12** is a flowchart illustrating a process for interconnecting a first body to a second body via contact and electrodes using nanoporous metal tips, in accordance with one or more embodiments. The process may include different or additional steps than those described in conjunction with FIG. **12** in some embodiments or perform steps in difference orders than the order described in conjunction with FIG. **12**.

[0101] As illustrated in FIGS. **11A** and **11B**, the first body of the interconnect (i.e., the first body **1110**) on which contacts protrude from a first surface is positioned **1210** relative to the second body (i.e., the second body **1130**) to align the contacts with corresponding electrodes on the second body. The electrodes protrude from a second surface on the second body. The second surface faces the first surface. The contacts, the electrodes, or both comprise nanoporous metal tips. After the first body and the second body are positioned, the first body approaches **1220** the second body such that the position of the first body is moved towards the second body until the contacts and the electrodes are separated by less than a predetermined distance. The contacts and the electrodes bond **1230** establishing an interconnect between the first body and the second body. The bond takes place by melting and solidifying the nanoporous metal tips.

[0102] In some embodiments, the contacts and the electrodes are mounted to the opposite bodies of the interconnect compared to the above description. For example, the contacts are formed on the second body (specifically, on the second surface of the second body) and the electrodes are formed on the first body (specifically, on the first surface of the first body).

[0103] The methods, systems, and devices discussed above are examples. Various embodiments may omit, substitute, or add various procedures or components as appropriate. For instance, in alternative configurations, the methods described may be performed in an order different from that described, and/or various stages may be added, omitted, and/or combined. Also, features described with respect to certain embodiments may be combined in various other embodiments. Different aspects and elements of the embodiments may be combined in a similar manner. Also, technology evolves and, thus, many of the elements are examples that do not limit the scope of the disclosure to those specific examples.

What is claimed is:

1. An electronic device comprising:

a first body comprising contacts protruding from a first surface of the first body;

a second body comprising electrodes protruding from a second surface of the second body facing the first surface; and

bonding metal of the contacts and electrodes formed by melting and solidifying nanoporous metal tips on at least one of the contacts and the electrodes.

2. The electronic device of claim 1, wherein the nanoporous metal tips are nanoporous gold tips.

3. The electronic device of claim 1, wherein each of the contacts and each of the electrodes comprise a solid metal base on the first body or the second body.

4. The electronic device of claim 7, wherein one of the first body and the second body comprises a light emitting diode (LED) with a size that is less than 100 micrometers ( $\mu\text{m}$ ) and the other of the first body and the second body comprises a circuit to operate the LED.

\* \* \* \* \*