

[54] **MNO₂ DERIVED FROM LIMN₂O₄**
 [75] Inventor: **James C. Hunter**, Berea, Ohio
 [73] Assignee: **Union Carbide Corporation**, New York, N.Y.
 [21] Appl. No.: **180,616**
 [22] Filed: **Aug. 25, 1980**

Related U.S. Application Data

[62] Division of Ser. No. 947,120, Sep. 29, 1978, Pat. No. 4,246,253.
 [51] Int. Cl.³ **H01M 4/50**
 [52] U.S. Cl. **429/191; 429/194; 429/224**
 [58] Field of Search **429/224, 191, 194; 423/605; 204/290 R, 291; 252/500**

[56] **References Cited**
U.S. PATENT DOCUMENTS
 3,959,021 5/1976 Nishino et al. 423/605
 4,121,018 10/1978 Danilovich et al. 429/224 X
 4,125,638 11/1978 Watanabe et al. 429/224 X
 4,133,856 1/1979 Ikeda et al. 429/224 X
 4,197,366 4/1980 Tamura et al. 429/197
 4,216,247 8/1980 Ikeda et al. 429/224 X
 4,221,853 9/1980 Tye et al. 429/224

Primary Examiner—Anthony Skapars
Attorney, Agent, or Firm—David Fink

[57] **ABSTRACT**
 A new form of manganese dioxide having an x-ray diffraction pattern resembling none of the x-ray patterns of the known forms of manganese dioxide is manufactured by acid treatment of LiMn₂O₄.

6 Claims, 1 Drawing Figure





FIG. 1



MNO₂ DERIVED FROM LIMN₂O₄

This is a division of our prior U.S. application Ser. No. 947,120, filing date: Sept. 29, 1978, now U.S. Pat. No. 4,246,253.

This invention relates to a new form of manganese dioxide and a method for preparing the same. In particular this invention relates to a new form of manganese dioxide having an x-ray diffraction pattern not heretofore exhibited by any previously known forms of manganese dioxide.

This invention provides a novel form of manganese dioxide which is made by acid treatment of the known material LiMn₂O₄.

Manganese dioxide (MnO₂) is a well-known substance commonly used in electrochemical cells, such as dry cell batteries, as an active cathode material. Manganese dioxide has been known to exist in various crystalline forms among which pyrolusite and nsutite are commonly found in nature. Ramsdellite is also found in nature, but to a lesser extent. Other forms of manganese dioxide are known, either naturally occurring or man-made, but none of these alone or in combination has the x-ray diffraction pattern of the manganese dioxide of this invention.

LiMn₂O₄, a spinel, is reported by Wickham and Croft (D. G. Wickham & W. J. Croft, *J. Phys. Chem. Solids*, 7, 351 (1958)) to form whenever lithium carbonate and any oxide of manganese are taken in a 2:1 molar ratio of Mn/Li, and heated at 800°-900° C. in air. The product LiMn₂O₄ (a blue colored material) contains equal amounts of Mn(III) and Mn(IV), and accordingly has a manganese peroxidation value of 75% (% peroxidation is defined as the degree to which the manganese oxidation state has been raised from Mn(II) to Mn(IV). Thus, MnO has 0% peroxidation and MnO₂ has 100% peroxidation). Wickham and Croft also reported that using excess Li in the reaction led to formation of a mixture of LiMn₂O₄ and Li₂MnO₃ (a red material), while excess Mn led to a mixture containing Mn₂O₃ in addition to the LiMn₂O₄. It should be noted that other preparative techniques are possible for preparing LiMn₂O₄, in addition to those described by Wickham and Croft. Other lithium or manganese compounds can be used as starting materials provided they decompose to lithium or manganese oxides under the reaction conditions used.

The novel manganese dioxide of this invention is made by acid treatment of LiMn₂O₄. The product of the acid treatment is a substantially pure MnO₂ whose x-ray pattern is nearly identical to that of the starting material LiMn₂O₄, a spinel. The x-ray pattern of the MnO₂ of this invention differs from that of LiMn₂O₄ in that there is a slight shift in peak positions, indicating a lattice contraction upon formation of the novel form of manganese dioxide, which we shall refer to hereinafter as "λMnO₂." The "λ" designation, to the best of our knowledge, has not been used in the art to designate a form of MnO₂. Thus, while LiMn₂O₄ is a cubic spinel with $a_D=8.24 \text{ \AA}$, λMnO₂ appears to have a closely related structure with $a_D=8.07 \text{ \AA} \pm 0.02 \text{ \AA}$. The term "a_D" as used herein is the well-known term used in crystallography which refers to the edge dimension of the cubic unit cell. A range of compositions intermediate between LiMn₂O₄ and λ-MnO₂ can be produced by controlling the acid treating conditions, and such compositions can be represented by the empirical formula

Li_xMn₂O₄ where $0 < \lambda < 1$, and have x-ray patterns with characteristics of both LiMn₂O₄ and λ-MnO₂.

X-ray diffraction is a well-known and reliable test method for the determination of the structure of crystals. When a crystalline structure is bombarded with x-rays, some of the x-rays are scattered and changes in the phase relations between the rays scattered by different atoms in the crystal result in a diffraction pattern characteristic of the spatial arrangement of the atoms in the crystal. The positions of the diffraction lines in a typical x-ray pattern are often referred to as d-values, indicated in Angstroms (Å), and correspond to the plane spacings in the bombarded crystal. These plane spacings and the relative intensities of the lines are characteristic of the structure of a given crystal. Identification of a substance by its x-ray diffraction pattern may be achieved by direct comparison with the patterns of known substances, which is made easier through the use of published x-ray patterns classified in the card index of the American Society for Testing and Materials (ASTM).

For the determination of the x-ray patterns of the materials described herein conventional powder diffraction techniques were used. The radiation was Fe Kα, or Cu Kα, and a conventional scintillation counter detector was used, with the resulting peaks displayed on a strip chart recorder. d-values for the diffraction lines were calculated from the line positions and the wavelength of the impinging radiation, using standard tables.

The ideal starting material for preparing λ-MnO₂ is LiMn₂O₄, which has a Mn peroxidation value of 75%. However, in practice, it has been found that satisfactory results are obtained over a range of Mn peroxidation values, where the Mn/Li ratio in the starting mixture used to form LiMn₂O₄ varies somewhat from the ideal 2:1. As explained by Wickham and Croft, for Mn/Li of less than 2:1 (i.e. excess Li) some Li₂MnO₃ forms. This is a distinctively red material, containing Mn(IV). It is not affected by acid treatment, and it is of very low electrochemical activity. Even at a 2:1 Mn/Li ratio some of this material is often seen, probably due to incomplete reaction to form LiMn₂O₄, because of localized variations of the Mn/Li ratio in the starting mixture. The use of a slight (up to 10%) excess Mn in the initial mixture used to form LiMn₂O₄ tends to prevent formation of Li₂MnO₃ and ultimately results in λ-MnO₂ of good activity. Thus, the optimum material for forming λ-MnO₂ is a LiMn₂O₄ prepared in such a way as to be free of Li₂MnO₃, and where some excess Mn₂O₃ can be tolerated; where the peroxidation is in the range of 70-75%.

In accordance with the present invention there is provided a new crystalline form of manganese dioxide with an x-ray diffraction pattern having d-values of 4.64 Å, 2.42 Å, 2.31 Å, 2.01 Å, 1.84 Å, 1.55 Å and 1.42 Å, ±0.02 Å in each instance.

In accordance with the present invention there is also provided a method for producing the manganese dioxide of this invention which encompasses acid-treating LiMn₂O₄ under conditions specified in more detail hereinafter.

The treatment procedure typically involves suspending LiMn₂O₄ in water at room temperature by stirring, and then adding acid while continuing to stir and while monitoring the pH of the solution phase. For satisfactory conversion, on the order of greater than about 90% of the LiMn₂O₄ to the λ-MnO₂ of this invention, acid treatment should continue until the pH of the solution

phase stabilizes at below about pH 2.5, preferably below about 2. If a manganese oxide ore containing large amounts of impurities is used as a starting material to make the LiMn_2O_4 , then a more severe acid treatment, (i.e., stronger acid and/or higher temperature) may be required to remove the acid-soluble impurities while achieving the desired conversion to the $\lambda\text{-MnO}_2$.

The acids which are suitable for treating LiMn_2O_4 in the practice of this invention include, but are not limited to acids such as H_2SO_4 , HCl , or HNO_3 ; other suitable acids selected by those skilled in the art may be employed. The acids may be used in dilute concentrations generally on the order of about 1 to about 10 normality.

The manganese dioxide of this invention is suitable for use in a number of applications where manganese dioxide has been employed in the past. The most extensive use of manganese dioxide has been in electrochemical cells, in particular in dry cell batteries, which typically comprise a manganese dioxide cathode, a zinc

400 mls water added, and while stirring, 15% H_2SO_4 was slowly added until the solution phase pH stabilized at 2. After allowing solid material to settle the supernatant liquid was decanted and the remaining solid was washed by decantation until the wash solutions were neutral. The solid was then collected on a sintered glass filter funnel and dried in an oven at about 85°C . An x-ray diffraction pattern of the resulting dried product was obtained which was almost identical to that of LiMn_2O_4 , but shifted to lower d-values. Table 1 presents the x-ray diffraction pattern for the LiMn_2O_4 prepared above, and the above dried, acid-treated product. Also presented in the Table for comparison are data from the ASTM card 18-736, for LiMn_2O_4 as compiled by the "American Society for Testing and Materials." Chemical analysis, by conventional methods, of the acid-treated product indicated that the LiMn_2O_4 had been converted to substantially pure MnO_2 . The results of the chemical analysis are presented in Table 2.

TABLE 1

X-RAY DIFFRACTION d-VALUES AND RELATIVE INTENSITIES $\text{Fe K}\alpha$ RADIATION							
LiMn_2O_4 prepared in Example I	4.73Å(s)	2.48Å(s)	2.38Å(w)	2.06Å(s)	1.89Å(w)	1.58Å(w)	1.46Å(m)
Dried, acid treated product of Example I	4.64Å(s)	2.42Å(s)	2.31Å(w)	2.01Å(s)	1.84Å(w)	1.55Å(w)	1.42Å(m)
ASTM card 18-736 for LiMn_2O_4	4.72Å(s)	2.47Å(s)	2.37Å(w)	2.05Å(s)	1.88Å(w)	1.58Å(m)	1.45Å(s)

s = strong
m = medium
w = weak

anode, and an aqueous electrolyte (such as aqueous NH_4Cl and ZnCl_2 solutions). While the most widely used electrolytes in dry cells have been in aqueous form, the manganese dioxide of this invention is especially useful with non-aqueous electrolytes, such as those comprising organic solutions of light metal salts such as LiBF_4 in propylene carbonate-dimethoxyethane, or LiAsF_6 in methylformate-propylene carbonate, and should also be useful with solid electrolytes such as lithium-substituted beta-alumina.

In the drawing:

FIG. 1: is a graph showing discharge behavior of $\lambda\text{-MnO}_2$ in comparison with that of heat treated EMD in a non-aqueous electrolyte as explained more fully in Example IV hereinafter.

The following examples are set forth as being merely illustrative of the invention and are not intended in any manner to be limitative thereof. Unless otherwise indicated, all parts and percentages are by weight.

EXAMPLE I

This example illustrates the preparation of $\lambda\text{-MnO}_2$.

20 gms of $\beta\text{-MnO}_2$ (reagent grade pyrolusite) were ground together with 4.25 gms of Li_2CO_3 , heated in air to 835°C . for 10 minutes, cooled, and then reheated to 850°C . in air for one hour, and cooled to room temperature. The resulting reaction product was a blue powder found to be substantially pure LiMn_2O_4 . About 15 gms of this reaction product were placed in a beaker, about

TABLE 2

	% Mn	% MnO_2	% Peroxidation	% Li
Theoretical for LiMn_2O_4	60.77	72.12	75	3.83
LiMn_2O_4 of Example I	62.54	72.53	74	3.0
Dried, acid-treated product	60.39	93.22	99	0.27

EXAMPLE II

This example illustrates a preferred method of making LiMn_2O_4 and also illustrates the use of different acids to convert LiMn_2O_4 to the $\lambda\text{-MnO}_2$ of this invention.

140.23 gms Li_2CO_3 and 600 gms Mn_2O_3 were ground together, heated in air at 850°C . for 1 hour; then cooled to room temperature, reground, then reheated at 850°C . for $\frac{1}{2}$ hour.

Three 15 gm samples of the resulting LiMn_2O_4 were placed in beakers with 500 ml H_2O , and treated with 3N HCl , 4.7N H_2SO_4 , and 4N HNO_3 , respectively, to a pH of slightly below 2. The samples were then water washed until neutral, filtered and dried at $\sim 95^\circ\text{C}$. X-ray results (Table 3) and analytical results (Table 4) confirm that in all cases the LiMn_2O_4 was converted to substantially pure $\lambda\text{-MnO}_2$.

TABLE 3

X-RAY DIFFRACTION d-VALUES AND INTENSITIES ($\text{Cu K}\alpha$ RADIATION)								
LiMn_2O_4 , prepared in Example II	4.79Å(s)	2.49Å(m)	2.39Å(w)		2.07Å(m)	1.89Å(w)	1.59Å(w)	1.46Å(w)
Dried, HCl treated product	4.62Å(s)	2.41Å(m)	2.32Å(w)	2.05Å(w)	2.01Å(m)	1.84Å(w)	1.55Å(w)	1.42Å(w)
Dried, H_2SO_4 treated product	4.64Å(s)	2.42Å(m)	2.31Å(w)	2.05Å(w)	2.01Å(m)	1.84Å(w)	1.55Å(w)	1.42Å(w)

TABLE 3-continued

X-RAY DIFFRACTION d-VALUES AND INTENSITIES (Cu K α RADIATION)								
Dried, HNO ₃ treated product	4.64Å(s)	2.42Å(m)	2.32Å(w)	2.05Å(w)	2.01Å(m)	1.86Å(w)	1.55Å(w)	1.42Å(w)

s = strong
m = medium
w = weak

Note:

The additional weak 2.05 Å peaks occurring in the acid treated products, are probably due to tiny amounts of unconverted LiMn₂O₄ remaining in the products.

TABLE 4

	% Mn	% MnO ₂	% Peroxidation
Theoretical for LiMn ₂ O ₄	60.77	72.12	75
LiMn ₂ O ₄ Prepared in Example II	60.36	70.91	75
Dried, H ₂ SO ₄ treated Product	62.10	95.79	99
Dried, HCl treated Product	62.67	95.62	98
Dried, HNO ₃ treated Product	62.08	95.55	97

EXAMPLE III

This example illustrates the use of an elevated temperature acid treatment. 60 gms African MnO₂ ore containing about 74% MnO₂ was ground with 10.3 gms Li₂CO₃, then heated at 850° C. in air for 1 hour. The sample was cooled, reground, then reheated at 850° C. for 1 hour more. The product showed the x-ray pattern of LiMn₂O₄, and had 51.76% Mn, 57.04% MnO₂, 70% peroxidation. The analytical results indicated that impurities were present, carried over from the ore.

Treating a 15 gm sample of the LiMn₂O₄ product with H₂SO₄ to a pH of 2 resulted in a product which had 75.82% MnO₂, 92% peroxidation, and which showed the λ -MnO₂ x-ray pattern, indicating conversion to the new form of MnO₂. However, the low % MnO₂ seen in the analytical results indicated that the ore impurities remained high in the product.

A second 15 gm sample of the Li₂CO₃-treated ore was acid-treated, again to a pH of 2, but this time the treating solution was heated to 90° C. and maintained at that temperature for 30 minutes prior to washing with water. The resultant product now had 84.3% in MnO₂ and 97% peroxidation and still showed the λ -MnO₂ x-ray pattern.

EXAMPLE IV

An 8.2 mg sample of λ -MnO₂ made according to the process described in Example II above, using H₂SO₄,

was placed on a porous nickel substrate and discharged versus a lithium anode in an electrolyte consisting of 1 M LiBF₄ in 1:1 (volume ratio) propylene carbonate-dimethoxyethane. The current drain was 500 microamperes. For comparison, a similar sized (7.8 mg) sample of EMD (electrolytic manganese dioxide), heat treated for 8 hours at 350°-360° C. to optimize its performance in the non-aqueous electrolyte, was also discharged under the same conditions.

The results are graphed in FIG. 1; the horizontal axis is expressed in ampere-hours per gram, allowing the normalization of the curves for differing sample weights. The vertical axis shows the cell voltages during discharge. The resulting discharge curves show that the λ -MnO₂ has about the same total ampere-hour capacity as the EMD, but operates at a much higher voltage for the first half of the discharge.

Although the present invention has been described and set forth in some detail, it should be further understood that the same is susceptible to changes, modifications and variations without departing from the scope and spirit of the invention.

What is claimed is:

1. An electrochemical cell comprising an anode, a cathode, and an electrolyte, at least a portion of said cathode comprising λ -MnO₂.
2. The electrochemical cell of claim 1 wherein said electrolyte is a non-aqueous electrolyte.
3. The electrochemical cell of claim 2 wherein said non-aqueous electrolyte is 1 molar LiBF₄ in 1:1 (volume ratio) propylene carbonate-dimethoxyethane.
4. The electrochemical cell of claim 3 wherein said anode is a Li anode.
5. The electrochemical cell of claim 2 wherein said electrolyte is an aqueous electrolyte.
6. The electrochemical cell of claim 2 wherein said electrolyte is a solid electrolyte.

* * * * *

50

55

60

65