

[54] DYESTUFFS AND THEIR USE IN PHOTOGRAPHIC MATERIAL

[75] Inventor: William E. Long, Brentwood, England

[73] Assignee: Ciba-Geigy AG, Basel, Switzerland

[21] Appl. No.: 487,352

[22] Filed: Apr. 22, 1983

[51] Int. Cl.³ C07D 401/00; C07D 211/00; C07D 295/00

[52] U.S. Cl. 546/211; 546/184; 546/279; 546/348

[58] Field of Search 546/211, 279, 184, 348

[56] References Cited

U.S. PATENT DOCUMENTS

2,506,654	5/1980	Stein	546/211
3,686,171	8/1972	Swett et al.	546/211
4,021,428	5/1977	Farutachi et al.	546/211


FOREIGN PATENT DOCUMENTS

1091366	11/1967	United Kingdom	548/327
1292454	11/1972	United Kingdom	546/184
2014598	8/1979	United Kingdom	546/211

Primary Examiner—Paul F. Shaver
Attorney, Agent, or Firm—Joseph G. Kolodny

[57] ABSTRACT

The new compounds of the general formula



where R₁ is hydrogen, alkyl or cyclic alkyl, R₂ and R₃ are each hydrogen, alkyl, a carboxylic acid, ester or amide group or cyano, and R₄, R₅ and R₆ are each alkyl or aryl, are useful as antihalation dyes and as image dyes in photographic materials for dye-bleaching processes.


4 Claims, No Drawings

DYESTUFFS AND THEIR USE IN PHOTOGRAPHIC MATERIAL

This application is a continuation of application Ser. No. 236,488, filed 2/23/81.

This invention relates to novel dyestuffs and to their use in photographic materials.

According to the present invention there is provided a dyestuff of the formula



where R_1 is hydrogen, optionally substituted alkyl or cyclic alkyl, R_2 and R_3 are each hydrogen, optionally substituted alkyl, a carboxylic acid, ester or amide group, or cyano, and R_4 , R_5 and R_6 are each optionally substituted alkyl or optionally substituted aryl.

R_1 is alkyl having from 1 to 12 carbon atoms. The alkyl radicals can be straight or branched. Examples are methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl and dodecyl, further isomers of these radicals such as *i*-propyl, *i*-butyl, *t*-butyl, *i*-pentyl or *i*-octyl. These radicals can be substituted by halogen, such as chlorine or bromine, hydroxyl, methoxy, ethoxy, propoxy, butoxy, or a carboxylic acid ($-\text{COOH}$) group. Preferred substituents are hydroxyl and the carboxylic acid group. Most preferably, R_1 is ethyl, hydroxyethyl, propyl, butyl or *t*-butyl. Further, R_1 is cyclic alkyl. These cyclic radicals can have 5 or 6 ring members. Preferred are cyclopentyl and cyclohexyl.

R_2 and R_3 are each hydrogen or alkyl. The alkyl groups can have 1 to 8 carbon atoms, e.g. methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl or isomers thereof which radicals are optionally substituted by hydroxyl, a carboxylic acid group, cyano or nitro. Further, R_2 and R_3 are cyano, a carboxylic acid, a carboxylic amide ($-\text{CONH}_2$) or a carboxylic ester group having 2 to 5 carbon atoms, preferably 3 or 5. R_2 and R_3 are preferably hydrogen, methyl, cyano or a carboxylic acid or a carboxylic amide group. Cyano is the most suitable group. R_2 and R_3 can have the same or a different meaning.


R_4 , R_5 and R_6 are each alkyl. These alkyl groups can have 1 to 6 carbon atoms e.g. methyl, ethyl, propyl, butyl, pentyl or hexyl or isomers thereof, and are optionally substituted with halogen, such as chlorine or bromine, hydroxyl, alkoxy having 1 to 4 carbon atoms such as methoxy, or ethoxy or butoxy, or a carboxylic acid group. Preferably, the alkyl group are unsubstituted. Suitable alkyl radicals have 1 to 4 carbon atoms. Methyl is most preferred. R_4 , R_5 and R_6 are further each aryl, e.g. phenyl or naphthyl, optionally substituted by halogen, such as chlorine or bromine, hydroxyl, cyano, nitro or a carboxylic acid group. Preferably, R_4 , R_5 and R_6 are phenyl, optionally substituted with chlorine, hydroxyl or cyano. Phenyl is the most suitable radical

for R_4 , R_5 and R_6 . R_4 , R_5 and R_6 can have the same or a different meaning.


In suitable compounds of formula (1), R_3 , R_4 and R_5 are all methyl and R_6 is phenyl.

The dyes of formula (1) are mauve or purple in colour. The actual colour is largely controlled by the nature of the group R_2 . In particular, when R_2 is cyano the dyes are of bluish-purple shades, and when R_2 is a carboxamide group or hydrogen, the dyes are reddish-purple shades.

The dyes of formula (1) may be prepared by reaction of a hydroxy-pyridone of formula




where R_1 , R_2 and R_3 have the meanings assigned above, with a nitroso compound of formula



where R_4 , R_5 and R_6 have the meanings assigned above.

Alternatively, and this is preferable, an amino compound of formula




where R_4 , R_5 and R_6 have the meanings assigned above, may be oxidised in the presence of a hydroxypyridone of formula (2). This oxidation may be carried out in an aqueous alkaline solution at temperatures of below 30°C . down to the freezing point. Suitable oxidising agents include sodium or ammonium persulphate or potassium ferricyanide.

It is to be understood that the compounds of formula (1) when R_1 is hydrogen may exist in different tautomeric forms, and that the compounds of formula (2) may also undergo tautomerisation.

The dyes of formula (1) are useful in photographic processes and in particular they are useful as antihalation dyes and as image dyes in photographic materials for dye-bleaching processes, e.g. in bleach-development processes. Preferably in this photographic use the dyes are coated as a solid dispersion in a gelatin or other suitable binder, the dispersions being produced by precipitation from an organic solvent, or by grinding techniques. Such grinding produces advantageous broadening or shifting of the visible absorption spectrum.

The dyes are of use in photographic processes because they are bleached by developing compositions, for example hydroquinone, especially in the presence of sulphite. Therefore these dyes are of use as bleachable underlayer, filter or backing dyes in photographic assemblies. However, the dyes are especially useful in photographic processes where the bleaching of the dye is achieved by the counterimagewise diffusion of developing agent which occurs when a silver halide latent image is being developed. Under these conditions, the dye is bleached where there is no silver image, leaving the residual dye to reinforce the silver image, giving useful reductions in the silver coating weight of photographic products. Example 2 below describes this usage.

Dyes of particular interest are for example:



EXAMPLE 1

Synthesis of the dyes:

Method A

Compound of formula (5)

10.31 g of 1-butyl-3-cyano-6-hydroxy-4-methylpyrid-2-one and 2 g of sodium hydroxide in 75 ml of water are mixed with 10 g of 4-amino-antipyrine in 250 ml of water. The solution is cooled, and oxidised with 66 g of potassium ferricyanide and 7.8 g of sodium carbonate in 200 ml of water during 10 minutes with efficient stirring. After 10 minutes the mauve precipitate is filtered off and then suspended in 300 ml of water, filtered again and washed with water till the washings give no Prussian blue colour with ferric chloride. Yield: 19.8 g (98%), m.p.: 185°-186° C., λ max (ethanol): 545 nm.

Method B

Compound of formula (6)

0.97 g of 3-Cyano-6-hydroxy-1-(2-hydroxyethyl)-4-methyl-pyrid-2-one, 1 g of 4-aminoantipyrine and 0.2 g of sodium hydroxide are cooled to 5° C. in 10 ml of water. The solution is oxidised with 4.6 g of ammonium persulphate and 0.78 g of sodium carbonate in 20 ml of water over about 20 minutes. After warming to room temperature, the mauve precipitate is filtered off and washed well with water. Yield: 1.68 g, m.p. 201°-202° C., λ max (ethanol): 548 nm.

The dyes of the following Table are synthesised by the same methods. R₄ and R₅ denote methyl and R₆ is phenyl, in all examples.

TABLE

Compound	R ₁	R ₂	R ₃	Method	m.p. (°C.)	λ max (ethanol)
(7)	C ₂ H ₅	CN	CH ₃	A	194-197	548 nm
(8)	C ₆ H ₁₁	CN	CH ₃	B	126-130	534 nm
(9)	H	CN	CH ₃	A	>290	550 nm
(10)	C ₆ H ₁₃	CN	CH ₃	B	168-171	548 nm
(11)	C ₂ H ₅	CONH ₂	CH ₃	A	178-183	512 nm
(12)	C ₂ H ₅	H	CH ₃	A	150 (d)	520 nm
(13)	C ₅ H ₁₁	CN	CH ₃	A	165-169	512 nm
(14)	H	H	COOH	B	>300	512 nm

EXAMPLE 2

A sample of photographic material is prepared which comprises as a support a 0.1 mm thick uncoloured transparent cellulose triacetate film strip. There is coated on this support in order a gelatin layer containing 2.0 g/m² of the dye of formula (5) in gelatin having a coating weight of 4 g/m², then a photosensitive silver halide emulsion layer containing silver iodobromide (Br \ominus 98.4%, I \ominus 1.6%), silver coating weight 10 mg/m² and finally a supercoat layer containing 1.0 g/m² of gelatin.

Three strips (strip A, B and C) of this sample of photographic material imagewise exposed and then processed for 1 minute in a silver halide developing solution of the following composition:

hydroquinone	50 g/liter
1-phenyl-3-pyrazolidinone	2.5 g/liter
sodium carbonate	30 g/liter
sodium bicarbonate	5 g/liter
sodium sulphite	10 g/liter
water to	1 liter
pH about 10	

In strip A the unexposed silver halide is removed by fixing for 1 minute in a 20% ammonium thiosulphate solution and the silver image is bleached by treatment in a 5% solution of cupric bromide for 5 minutes. A clear dark purple dye image is obtained.

5


In strip B the unexposed silver halide is removed by fixing for 1 minute in a 20% ammonium thiosulphate solution. A dark silver and dye reinforced image is obtained in this strip.

In strip C the silver development process is prolonged by a further two minutes and the unexposed silver halide removed by fixing for 1 minute in a 20% ammonium thiosulphate solution. In this case all the dye in the dye layer is bleached by the processing solution because after full development of the latent image the developing agent does not become exhausted in the silver image areas and is able to diffuse down to the underlying dye layer.

These tests show that the dyes of formula (1) may be used in photographic material to obtain a dye image only for a bleach-developing process (strip A), to obtain a dyereinforced silver image (strip B) in a bleach-development process and as an overall bleachable dye for example as an anti-halation underlayer (strip C).

I claim:

1. A dyestuff of the formula



6

where R₁ is hydrogen, alkyl having 2 to 10 carbon atoms which is unsubstituted or substituted by chlorine, bromine, hydroxyl, alkoxy having 1 to 4 carbon atoms or a carboxylic acid (—COOH) group, or R₁ is cyclopentyl or cyclohexyl, R₂ and R₃ are each hydrogen, alkyl having 1 to 8 carbon atoms which is unsubstituted or substituted by hydroxyl, a carboxylic acid (—COOH) group, cyano or nitro, or R₂ and R₃ are each a carboxylic acid (—COOH) group, a carboxylic ester group having 2 to 5 carbon atoms, a carboxylic amide (—CONH₂) group or cyano, and R₄, R₅ and R₆ are each alkyl having 1 to 6 carbon atoms which is unsubstituted or substituted by chlorine, bromine, hydroxyl, alkoxy having 1 to 4 carbon atoms or a carboxylic acid (—COOH) group, or R₄, R₅ and R₆ are each phenyl which is unsubstituted or substituted by chlorine, bromine, hydroxyl, cyano, nitro or a carboxylic acid (—COOH) group.

2. A dyestuff according to claim 1 where R₁ is alkyl having 2, 3 or 4 carbon atoms optionally substituted by hydroxyl or a carboxylic acid (—COOH) group, cyclopentyl or cyclohexyl.

3. A dyestuff according to claim 1 where R₂ and R₃ are each hydrogen, alkyl having 1 to 4 carbon atoms, optionally substituted by hydroxyl, a carboxylic acid (—COOH) group, cyano or nitro; cyano, a carboxylic acid (—COOH), a carboxylic (—CONH₂) amide or a carboxylic ester group having 2 to 5 carbon atoms.

4. A dyestuff according to claim 1 where R₄, R₅ and R₆ are each alkyl having 1 to 4 carbon atoms, optionally substituted by halogen, hydroxyl, alkoxy having 1 to 4 carbon atoms, or a carboxylic acid (—COOH) group; or phenyl, optionally substituted by halogen, hydroxyl, cyano, nitro or a carboxylic acid (—COOH) group.

35

* * * * *

40

45

50

55

60

65

UNITED STATES PATENT AND TRADEMARK OFFICE
CERTIFICATE OF CORRECTION

PATENT NO. : 4,482,716
DATED : November 13, 1984
INVENTOR(S) : William E. Long

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

Title page, under No. "[73]"

Insert:

--Related U.S. Application Data

[62] Continuation of Ser. No.
236,488, Feb. 23, 1981, Aban-
doned

[30] Foreign Application
Priority Data

Feb. 28, 1980 Great Britain
8006849--

Title page, under "U.S. Patent

Delete "Farutachi et al." and
substitute --Furutachi
et al--

Signed and Sealed this
Seventeenth Day of December 1985

[SEAL]

Attest:

Attesting Officer

DONALD J. QUIGG

Commissioner of Patents and Trademarks