

United States Patent [19]
Poirier

[11] **Patent Number:** **4,617,062**
[45] **Date of Patent:** **Oct. 14, 1986**

[54] **ROOFING ASPHALT COMPOSITIONS
CONTAINING HYDROCRACKED PITCH**

[75] **Inventor:** **Marc-Andre Poirier, Ottawa, Canada**

[73] **Assignee:** **Her Majesty in right of Canada as
represented by the Minister of
Energy, Mines and Resources,
Ottawa, Canada**

[21] **Appl. No.:** **733,781**

[22] **Filed:** **May 14, 1985**

[51] **Int. Cl.⁴** **C08L 95/00**

[52] **U.S. Cl.** **106/273 R; 106/284;
208/23**

[58] **Field of Search** **106/273 R, 284; 208/23**

[56] **References Cited**

U.S. PATENT DOCUMENTS

3,374,104	3/1968	Baum et al.	106/273
3,462,359	8/1969	Fauber	208/23
3,986,887	10/1976	Pitchford	106/273
4,268,318	5/1981	Stone	106/284
4,373,961	2/1983	Stone	404/72

Primary Examiner—Amelia B. Yarbrough
Attorney, Agent, or Firm—Wegner & Bretschneider

[57] **ABSTRACT**

The present invention relates to a roofing grade asphalt composition which comprises a blend of (a) a petroleum pitch obtained as a residue in the hydrocracking of hydrocarbon oils and (b) as a diluent therefor preferably a paving grade asphalt cement of 150–200 penetration.

8 Claims, No Drawings

ROOFING ASPHALT COMPOSITIONS CONTAINING HYDROCRACKED PITCH

BACKGROUND OF THE INVENTION

This invention relates to bituminous compositions and, more particularly, asphaltic compositions which are suitable for use as roofing materials.

Asphalt is a natural constituent of crude oils and is typically produced from the distillation residues of refining feedstocks. This product is of very significant industrial importance since it is widely used in the construction of roads, building materials and other industrial applications. This asphalt has normally been obtained from conventional petroleum oils.

With the changing economics of the petroleum industry, there is a trend toward the conversion of heavy hydrocarbon oils, such as the distillation residues, to light and intermediate naphthas of good quality for reforming feedstock, fuel oil and gas oils. These residues represent the normal sources of asphalts.

Roofing asphalts are also obtained from distillation residues, but normally require considerable air blowing to attain the desired properties for binding, adhesion, water proofing etc. Diverse applications of air blown bitumen have resulted in the development of standard specifications for various uses.

Asphalt specifications for roofing purposes are given in Table I below:

TABLE I

Property	Asphalt requirements for roofing purposes					
	Type 1		Type 2		Type 3	
	Min.	Max.	Min.	Max.	Min.	Max.
Softening Point (R & B, °C.)	60	68	75	83	90	98
Flash Point (C.O.C. °C.)	230	—	230	—	230	—
Penetration						
0° C., 200 g, 60 s	10	—	10	—	8	—
25° C., 100 g, 5 s	30	45	20	30	15	25
45° C., 50 g, 5 s	—	160	—	80	—	55
Thin film oven test pen., % of original	80	—	80	—	80	—
Loss of volatiles, %	—	1.0	—	1.0	—	1.0
Solubility in trichloroethylene, %	99	—	99	—	99	—

It is the object of the present invention to develop a blended roofing asphalt which can utilize unwanted processing residues, while avoiding the need of the costly air blowing process.

SUMMARY OF THE INVENTION

In accordance with this invention, it has been found that an asphalt product matching the characteristics of the traditional air blown residues can be produced by blending (a) a petroleum pitch obtained as a residue in the hydrocracking of hydrocarbon oils and (b) as a diluent therefor a vacuum residuum with a penetration of 60–400, preferably a paving grade asphalt cement.

DETAILED DESCRIPTION

The pitches that are used in the present invention are residues of hydrocracking which usually boil above 524° C. and they may come from the hydrocracking of regular crude oils or from the hydrocracking of heavy hydrocarbon oils, including heavy bituminous oils extracted from tar sands. While the pitches which can be used may be derived from processes providing a wide

range of pitch conversions, they are usually derived from processes having a pitch conversion of at least 40% and preferably in excess of 80% pitch conversion, such as that described in Canadian Pat. No. 1,151,579, issued Aug. 9, 1983.

The diluents are preferably paving grade asphalt cements. Typical asphalt cement specifications for road paving purposes are given in Table 2 below:

TABLE 2

Grade Requirements	Asphalt cement specifications for road purposes (16-GP-3M)						ASTM Method
	85–100		120–150		150–200		
	Min.	Max.	Min.	Max.	Min.	Max.	
15 Penetration (25° C., 100 g, 5 s)	85	100	120	150	150	200	D 5
Flash point (CO C, °C.)	230	—	220	—	220	—	D 92
20 Ductility (25° C., 5 cm/min, cm)	100	—	100	—	100	—	D 113
Thin film oven test (Pen. of residue % of original Pen.)	47	—	42	—	40	—	D 1745
25 Solubility in Trichloroethylene (wt %)	99.0	—	99.0	—	99.0	—	D 2042

It is preferable to use a road asphalt of 150–200 penetration, although it is possible to use some asphalt of 85–100 penetration. However, softer grade road asphalt of 200 penetration is not suitable because physical properties such as softening point and penetration cannot be raised sufficiently to meet Type 1 roofing asphalt specifications.

The processed pitch and the paving grade asphalt cement can be blended in widely varying proportions, provided the resulting blend meets the specifications of Table 1. However, the composition of this invention is particularly valuable in its ability to accept large proportions of pitches derived from high pitch conversion processes. Preferably at least 25% processed pitch is utilized in the compositions of this invention. According to a particularly preferred embodiment, at least 30% by weight of a pitch obtained from a greater than 80% pitch conversion process is combined with a 150–200 penetration road asphalt cement.

Throughout this specification, certain terms of art are used which are defined as follows:

Deasphalting

The asphaltene portion was precipitated by the addition of twenty volumes of n-heptane to one volume of asphalt blend. The slurry was agitated for 15 min. in an ultrasonic bath and the asphaltenes (n-heptane insolubles), were separated by filtration on a Whatman filter paper (No. 1). The asphaltenes were washed with 10 volumes of n-heptane, dried at 50° C. under reduced pressure. The maltenes (n-heptane solubles) and washings were combined and the solvent removed using a Buchi-Rotavapor. The asphaltenes obtained by this method would also contain the toluene insolubles.

Compound Type Separation

The deasphalted blend (about 1.4 g) was separated into compound-type concentrates of saturates,

monodiaromatics, polynuclear aromatics and resins on a dual packed silica-gel alumina column. The column consists of a vertical stainless steel tube (137×1.25 cm o.d.) packed in its lower half with 37 g of activated silica gel D-12 and top half with 47 g of activated alumina F-20. The following eluant sequence was used to elute the corresponding compound-type concentrates: n-pentane (330 mL), n-pentane/benzene 10% (500 mL), benzene/ethyl acetate 5% (130 mL) and methanol (200 mL) followed by benzene (100 mL) and 100 mL of pentane. A Lapp pump LS-30 was used with a flow rate of about 5 mL/min.

Molecular Weight Determination by Gel Permeation Chromatography

The Gel Permeation Chromatography (GPC) work was performed on a Beckman Model 112 High Performance Liquid Chromatograph. The molecular weight determination were made using two GPC systems—one system using 500 Å and 100 Å Ultrastyrigel columns

- Asphalt cement, 150–200 penetration, obtained from Petro-Canada, Taylor Refinery, B.C. composed of Boundary Lake and B.C. light distillation residues.
- Asphalt cement, 150–200 penetration, obtained from another petroleum refinery.

Pitches

- Light Arabian pitch, 76% pitch conversion (82-CG-37).
- Blend 24 pitch, 87% pitch conversion (84-CG-210).
- IPPL pitch, 80% pitch conversion (84-CG-216).

Type 1 Commercial Roofing Asphalts

- Type 1 roofing asphalt, 30–45 penetration, obtained from Petro-Canada, Montreal East Refinery.
- Type 1 roofing asphalt, 30–45 penetration, obtained from another petroleum refinery.

The above blending materials had the chemical analyses and physical properties shown in Tables 3 and 4 below:

TABLE 3

	Ultimate analysis of processed residues and asphalt cements					
	Sample No.					
	1	2	3	4	5	6
Specific gravity 15/15° C.	1.024	1.008	1.022	1.144	1.190	1.179
Carbon, wt %	84.19	86.62	83.66	84.06	84.2	83.98
Hydrogen, wt %	9.84	7.81	10.22	7.54	6.82	7.02
Sulphur, wt %	4.21	2.24	3.52	3.54	3.09	3.25
Nitrogen, wt %	0.53	0.65	1.04	1.20	1.43	1.28
R.C.R., wt %	19.0	19.9	16.8	45.4	57.9	57.7
Heptane solubles, wt %	80.6	91.5	84.0	52.3	42.5	45.0
Heptane insolubles, wt %	19.4	8.5	16.0	33.7	57.5	55.0
Toluene insolubles, wt %	0.3	0.4	0.1	6.0	25.8	22.4
Vanadium, ppm	514	243	157	231	1967	405
Nickel, ppm	87	82	73	156	310	236
Ash, wt %	0.09	0.05	0.04	0.95	3.49	5.69

(Waters Associates) in series and other systems with 1000 Å and 100 Å Ultrastyrigel columns in series. Tetrahydrofuran (THF) (Burdick and Jackson "distilled in glass") was used at 1 mL/min. flow rate as mobile phase. The concentrations of the samples in THF were limited to 0.1–0.25% in order to avoid "concentration effects" on the retention results. The column eluate was monitored with a Schoeffel Model SF770 UV-vis detector operating at 254 nm and the data were recorded on a Spectra Physics SP4100 printer plotter.

Elemental Analysis and Physical Tests

The samples were analyzed for C, H, N on a Perkin Elmer model 240 Analyzer and the sulphur was determined on a LECO.

The physical tests, viscosity, penetration, ductility, solubility in trichloroethylene and softening point were performed according to the ASTM procedures.

Certain preferred features of the present invention will be better understood from consideration of the experimental data in the following examples.

EXAMPLE 1

A variety of blending products were prepared as follows:

Diluents

- Asphalt cement, 150–200 penetration, obtained from Petro-Canada, Montreal East Refinery, composed of light Saskatchewan blend, Agha Jari, Mexican and other crude distillation residues.

TABLE 4

	Physical properties of processes residues and asphalt cement					
	Sample No.					
	1	2	3	4	5	6
Penetration 25° C., 100 g, 5 s	157	168	140	0	0	0
Viscosity, 135° C. Kn, cSt	217	205	240	—	—	—
Softening Point (R & B, °C.)	43	43	39	102	134	119
Flash Point (C.O.C., °C.)	310	332	330	327	340	340
Solubility in trichloroethylene, %	99.9	99.9	99.9	99.0	85.8	85.8

It will be seen from the physical properties that the blending materials by themselves are not suitable for road asphalts as they do not meet the specifications set out in Table 1 above.

BLENDING

Different blends were prepared using as one component of each blend one of the pitches described above and as the other component a diluent selected from the three asphalt cements. These blends were prepared to meet the Type 1 penetration specification of Table 1. The different amounts of pitch used in the different blends are set out in Table 5 below.

In the blending procedure used, the samples were preheated and conditioned to enable pouring and weighing. The components were then blended to

5

achieve a penetration of 30–45 as required for a Type 1 roofing asphalt. The blend was then reheated on a hot plate at the softening point of the pitch for conditioning and agitating to yield a homogeneous mixture.

TABLE 5

Processed residue	Weight percent of processed residue in blend mixture to obtain Type 1 roofing asphalt		
	Asphalt Cement		
	1	2	3
4	29* (38)	29 (31)	29 (35)
5	24 (37)	—	25 (32)
6	26 (38)	—	—

*Penetration is indicated in brackets.

The chemical analyses and the physical properties of six different blends that were prepared and two commercial roofing asphalts are shown in Tables 6 and 7 below.

TABLE 6

	Ultimate analysis of blended roofing asphalts							
	Sample No.							
	1-4	2-4	3-4	1-5	3-5	1-6	7	8
Specific gravity 15/15° C.	1.051	1.053	1.052	1.057	1.055	1.061	1.025	1.027
Carbon, wt %	85.50	86.45	84.67	84.63	84.13	83.86	85.21	84.19
Hydrogen, wt %	9.52	9.75	9.44	9.14	9.30	9.27	10.01	9.95
Sulphur, wt %	4.09	2.56	4.40	3.80	4.12	3.78	3.52	4.53
Nitrogen, wt %	0.62	0.72	0.54	0.78	0.74	0.69	0.63	0.37
Heptane solubles, wt %	74.2	83.3	77.9	73.9	71.4	72.1	74.6	72.8
Heptane insolubles, wt %	25.8	16.7	22.1	26.1	28.6	27.9	25.4	27.2
Toluene insolubles, wt %	0.2	0.2	0.2	1.7	1.4	2.5	0.1	0.1
Vanadium, ppm	355	175	115	1123	671	414	427	174
Nickel, ppm	66	55	59	176	140	129	108	78
Ash, wt %	0.04	0.05	0.06	0.53	0.98	1.23	0.08	0.04

TABLE 7

	Physical properties of blended roofing asphalts							
	Sample No.							
	1-4	2-4	3-4	1-5	3-5	1-6	7	8
Penetration								
0° C., 200 g, 50 s	15	11	15	15	12	14	19	21
25° C., 100 g, 5 s	38	31	35	37	31	38	40	42
45° C., 50 g, 5 s	162	166	191	155	134	164	123	125
Viscosity at 135° C.	315	381	366	683	636	404	762	1097
Kn, cSt								
Softening point (R & B, °C.)	55	57	52	57	56	56	61	62
Flash point, °C. (C.O.C.)	>300	>300	>300	>300	>300	>300	>300	>300
Solubility in trichloroethylene, %	99.9	99.9	99.8	98.3	98.6	97.6	99.9	99.9
Thin film oven test	83	83	82	82	81	85	80	81
Penetration, % of original								
Loss on heating, %	0.03	0.06	0.05	0.01	0.05	0.01	0.06	0.19
Sweatability test	0.747	0.404	0.368	1.282	0.402	0.618	0.802	0.586
Stability number								

It will be noted from the above tables that the H/C ratio of the blends are lower than the roofing asphalts, indicating that they are more hydrogen deficient. The n-heptane insolubles content of the blends are in the same range as the roofing asphalts. Typical roofing asphalts contain from 20 to 30 wt % of n-heptane insolubles. The toluene insolubles contents are relatively low and comparable to roofing asphalts. However, blends 1–5, 3–5 and 1–6 contain higher toluene insolubles be-

6

cause of the high toluene insolubles content of the corresponding pitches.

Table 7 shows two major differences in the physical properties of the blends compared with refinery asphalts. The softening points and the viscosity values are slightly lower. This can be explained by the lower molecular weight of the compound types as presented in Tables 8 and 9 below.

TABLE 8

Sample	Molecular weight distribution of processed residues and asphalt cements		
	Average Molecular Weight		
	Total Sample	Maltenes	Asphaltenes
1	1600	1200	3320
2	1340	1230	2750
3	1575	975	4230
4	400	390	525
5	300	340	325
6	360	390	385

TABLE 9

Sample	Molecular weight distribution of blended asphalts		
	Average Molecular Weight		
	Total Sample	Maltenes	Asphaltenes
1-3	1040	600	2530
2-4	760	640	1810

TABLE 9-continued

Sample	Molecular weight distribution of blended asphalts		
	Average Molecular Weight		
	Total Sample	Maltenes	Asphaltenes
3-4	1120	690	2700
1-5	800	620	1380
3-5	940	670	1910
1-6	910	725	1530
7	2220	1080	7040
8	3690	1090	9760

Although the softening points are slightly lower than the minimum value of 60, the blends are still acceptable as supported by the sweatability results as shown in Table 7 above. The sweatability test allows the determination of the oils that have separated from the mixture in the roofing asphalt and low values indicate a better performance. It will be noted that blend 3-4 does not meet other specifications and, therefore, is not acceptable.

As shown in Table 8, the molecular weight of the pitches and corresponding asphaltenes are lower than 1,000. The molecular weight of the processing pitch decreased with increasing pitch conversion.

The major difference in the blends of this invention compared to air-blown asphalts is the molecular weight. As shown in Table 9, the molecular weight of the asphaltenes in the blends ranges from 1380 to 2700 compared with from 7040 to 9760 in the air-blown asphalts. This trend is observed both for the total sample and the maltenes. Lower molecular weight does not seem to affect the performance as shown by the TFOT and sweatability results. Therefore, the results suggest that the physical properties except viscosity and softening point are mainly governed by the asphaltene content rather than the molecular weight.

The chemical composition of asphalts is important since it determines the rheological properties. The compound-type distribution results of the processed residues and asphalts cements are presented in Tables 10 and 11 below.

TABLE 10

Sample	Compound-type distribution of processed residues and asphalt cements (n-heptane solubles, wt %)			
	Saturates	Mono-diaromatics	Polyaromatics	Resins
1	19.1	21.4	26.0	33.5
2	24.5	23.1	28.5	23.0
3	23.1	20.2	27.0	29.7
4	11.8	11.0	30.1	47.1
5	22.5	7.9	33.9	35.7
6	22.4	8.2	34.4	35.0

TABLE 11

Sample	Compound-type distribution of processed residues and asphalt cements (wt %)			
	Saturates	Aromatics	Resins	*Asphaltenes
1	15.5	38.3	27.1	19.1
2	23.4	47.4	21.1	8.1
3	19.4	39.7	29.7	16.0
4	7.8	27.3	31.2	33.7
5	9.6	17.7	15.2	57.5
6	10.1	19.2	15.7	55.0

*Asphaltenes correspond to the n-heptane insolubles content.

The results in Table 10 in the n-heptane soluble portion of the processed residues shows less saturates and monodiaromatics contents compared with the asphalt cements. The resin content is also higher for the pitches. However, the polynuclear aromatics content is about the same. Table 11 shows a higher asphaltene content for the pitches. Mixing of the pitches with the asphalt

cements results in increasing the viscosity of the mixture and lowering of the average molecular weight.

The compound-type distribution of the blended samples of this invention is given in pages 12 and 13 below.

TABLE 12

Sample	Compound-type distribution of blended roofing asphalts (n-heptane solubles, wt %)			
	Saturates	Mono-diaromatics	Polyaromatics	Resins
1-4	21.7	21.4	27.7	29.2
2-4	20.9	22.5	28.6	28.0
3-4	21.6	17.3	29.8	31.3
1-5	22.5	19.2	27.5	30.8
3-5	21.3	18.6	30.0	30.1
1-6	18.6	19.6	28.4	33.4
7	26.4	22.0	26.2	25.4
8	27.2	22.6	28.1	22.1

TABLE 13

Sample	Compound-type distribution of blended roofing asphalts (wt %)			
	Saturates	Aromatics	Resins	Asphaltenes
1-4	16.1	36.4	21.7	25.8
2-4	17.4	42.6	23.3	16.7
3-4	16.8	36.7	24.4	22.1
1-5	16.6	34.5	22.8	26.1
3-5	15.2	34.7	21.5	28.6
1-6	13.4	34.6	24.1	27.9
7	19.7	36.0	18.9	25.4
8	19.8	36.9	16.1	27.2

In general, the composition of all blends is similar to the composition of roofing asphalts. The blends have somewhat lower saturates content and higher resins content compared with roofing asphalts. The major portion of the saturates in the blends is provided by the asphalt cements and the major portion of the resins is provided by the processed residues. Table 12 shows the whole compositions (including the toluene insolubles) of the blends and roofing asphalts. The overall results show an increase of resins content at the expense of saturates content for the blends compared with conventional roofing asphalts.

I claim:

1. A roofing grade asphalt composition comprising a blend of:

- a processed residue boiling above 524° C. and obtained from high pitch conversion hydrocracking of hydrocarbon oils and
- as a diluent therefor a vacuum residuum having a penetration at 25° C. of 60-400.

2. A composition according to claim 1 wherein the diluent is a paving grade asphalt cement.

3. A composition according to claim 2 wherein the paving grade asphalt cement has a penetration at 25° C. of less than 200.

4. A composition according to claim 2 wherein the paving grade asphalt cement has a penetration at 25° C. of 150-200.

5. A composition according to claim 3 wherein the processed residue is present in the composition in an amount of at least 25% by weight of the total composition.

6. A composition according to claim 3 wherein the hydrocracked pitch is present in the composition in an amount of at least 30% by weight of the total composition.

7. A composition according to claim 2 wherein the pitch conversion is at least 80%.

8. A composition according to claim 2 wherein the heavy hydrocarbon oil is a tar sand bitumen.

* * * * *