

United States Patent [19]

Brown et al.

[11] Patent Number: 4,726,864

[45] Date of Patent: Feb. 23, 1988

[54] HECTOGRAPH MASTER WEBS AND SHEETS, AND METHOD

[75] Inventors: Albert E. Brown, Locust Valley; Robert T. Emerson, Manhasset, both of N.Y.

[73] Assignee: Leedall Products Incorporated, New York, N.Y.

[21] Appl. No.: 880,681

[22] Filed: Jun. 30, 1986

Related U.S. Application Data

[63] Continuation-in-part of Ser. No. 657,203, Oct. 3, 1984, abandoned.

[51] Int. Cl.⁴ B41M 5/02; B44C 1/17

[52] U.S. Cl. 156/234; 101/473; 156/334

[58] Field of Search 101/473; 156/334, 234

[56] References Cited

U.S. PATENT DOCUMENTS

2,610,939	9/1952	Fisher	156/334
3,117,101	1/1964	Moyer	156/334
3,410,711	11/1968	Hoge	101/473
4,018,162	4/1977	Sharkey	101/473
4,456,649	6/1984	Clarke	156/334

FOREIGN PATENT DOCUMENTS

189846 11/1982 Japan 156/334

906934	9/1962	United Kingdom	.
1113695	5/1968	United Kingdom	.
1124082	8/1968	United Kingdom	.
1324796	7/1973	United Kingdom	.

Primary Examiner—Clyde I. Coughenour
Attorney, Agent, or Firm—Thomas L. Tully; Marley R. Perman; Clarence A. Green

[57] ABSTRACT

Hectograph master webs and sheets formulated to provide sharper, more-complete transfer under reduced imaging pressures, and sharper, more-numerous duplicate copies in the hectograph duplicating process and resistance to adhesion and coating-transfer under the pressures exerted by a hectograph duplicating machine. The receptive surface formed on the master sheet comprises a hard, pressure-adhesive coating consisting by weight essentially of 45 to 65 percent paraffinic wax, 5 to 20 percent hard wax and 15 to 40 percent polybutene polymer having a Staudinger molecular weight of from 10,400 to 12,300 which bonds to the hectograph transfer layer under relatively low, localized imaging pressure but which is sufficiently hard to resist adhesion, sticking and pick-over to hectograph copy sheets during the hectograph copying processes. The receptive coating also provides a barrier against the migration of the hectograph composition and/or of the spirit duplicating fluid into the master sheet.

8 Claims, No Drawings

HECTOGRAPH MASTER WEBS AND SHEETS, AND METHOD

The present application is a continuation-in-part of 5
copending application Ser. No. 657,203 filed Oct. 3,
1984 now abandoned.

BACKGROUND OF THE INVENTION

Hectograph transfer sheets and master sheets and 10
webs are well-known in the art. Conventional hecto-
graph transfer sheets and webs carry a layer of pressure-
transferable duplicating composition, and conventional
master sheets and webs are designed to receive mirror-
reverse images of hectograph composition from the 15
transfer sheet under the effects of writing or typing
pressure applied against the rear surface of the master
sheet. The imaged master sheet or web is mounted on a
hectograph duplicating machine, generally a spirit du-
plicating machine, and a plurality of correct-reading 20
duplicate copies are produced. Generally, the hecto-
graph composition contains undissolved hectograph
dye and the copy sheets are moistened with a liquid
spirit solvent such as an alcohol. However, in some
cases the hectograph composition is microporous and 25
contains pressure-exudable fluid ink, and the copies are
made by pressing the imaged master against dry copy
sheets.

It is desirable to be able to duplicate an imaged master 30
sheet or web from time to time as additional copies are
required, such as of printed forms, instruction sheets,
clothing patterns, and the like. This is not possible with
conventional hectograph master sheets and webs, with-
out substantial loss of copy quality, because the images
on the hectograph master migrate into and/or over the 35
master paper surface during periods of storage so that
subsequent reduplication efforts produce weak copies
and/or blurred copies, i.e., copies of unsatisfactory
color intensity and sharpness.

It has been proposed by U. S. Pat. No. 4,018,162 to 40
apply an oil-barrier coating to both surfaces of a contin-
uous master web in order to prevent the master paper
from absorbing the oily ink from porous duplicating
images applied to the master web, either directly or
when the imaged web is rolled up. Such coatings are 45
designed to prevent the master images from drying out
during storage. However, they are solvent-applied coat-
ings which are not pressure-adhesive, and which con-
tain porous filler to make them receptive and which are
not inert to the conventional spirit solvents. Thus, they 50
have an affinity for the spirit solvents, absorb such sol-
vents to cause the master sheet to swell and curl, and
cause soluble dye to be dissolved out of the master
images to form broadened or filled-in master images
which produce duplicate images which are less sharp or 55
have a blurred appearance.

It is also desirable to be able to image hectograph 60
master webs and sheets in modern automatic line-pres-
sure scribing machines such as plotters, scanners or
drafting machines. Such machines have a mechanical
stylus pen which is automatically guided over a copy
sheet to form images or pictures corresponding to those
on a remote original sheet or instructions from a com-
puter program. It has not been found possible to use
liquid hectograph ink in such stylus pens to produce 65
masters which can be duplicated. Also, attempts to
image conventional hectograph master units using the
pressure applied by such stylus pens have been unsuc-

cessful, because the pressure is too low to produce any
satisfactory transfer of hectograph composition from
the transfer layer to the master sheet, even in cases
where the hectograph transfer layer carries an adhesive
supercoating.

Attempts to improve the pressure-sensitivity of hec-
tograph master webs and sheets by applying conven-
tional pressure-adhesive soft coatings to the receptive
surface thereof have resulted in the creation of other
problems, particularly in the case of imaged masters
which are duplicated by means of pressure, as in U.S.
Pat. No. 4,018,162. Conventional soft pressure-adhesive
coatings, such as those consisting of paraffin wax and
mixtures thereof with lesser amounts polyisobutylene
resin, are so soft and adhesive that they stick to and
transfer to the master web or sheet, or to parts of the
pressure-duplicating machine, so as to be useless for
such purpose.

SUMMARY OF THE INVENTION

The present invention relates to novel hectograph
master sheets and webs and to the production of recep-
tive master paper which carries a thin pressure-adhesive
hard receptive coating which is an inert barrier with
respect to the ingredients of the transfer composition of
the transfer sheet and also with respect to spirit dupli-
cating fluids, the pressure-adhesive properties of the
master coating producing a strong bond with a hec-
tograph transfer layer, even under reduced localized im-
aging pressures, but being resistant to adhesion and
transfer to copy sheets and machine parts under the
overall pressures applied during the copying step.

Applicants have discovered that while hectograph
master papers have been formulated and/or coated to
give them wet strength, image-receptivity, oil resistance
or other properties, prior-known hectograph master
papers have not been coated with a receptive layer
which is adhesive under the effects of localized imaging
pressure but is not so adhesive under the effects of the
overall pressures exerted by the pressure rolls of a hec-
tograph duplicating machine as to stick to and transfer
to the surfaces of the hectograph copy sheets and/or
machine rollers, and to produce an imaged master sheet
or web having an inert, hard barrier layer which pre-
vents any of the ingredients of the images from migrat-
ing into or over the surface of the master sheet, and
which further prevents the spirit duplicating fluids from
penetrating or wetting the master sheet coating. This
prevents the master sheet from swelling or curling, and
prevents soluble dye from being dissolved out of the
master images onto adjacent areas of the master sheet
surface to produce broadened master images having
deteriorated duplication properties.

The pressure-adhesive master coating compositions
used according to the present invention are hot-melt
applied compositions comprising a major amount by
weight of a paraffinic wax, a minor amount by weight of
one or more harder waxes which are compatible there-
with, and a minor amount by weight of a tacky, normal-
ly-solid polybutene resin, including polyisobutylene
resin, which is compatible with and meltable with said
wax mixture to form a homogeneous molten coating
composition at temperatures within the range of from
about 170° F. to 200° F. Such molten compositions are
blade coated over a suitable master paper stock in a
weight of between about 0.5 and 5.0 pounds per ream,
3300 square feet, to form a continuous inert hard barrier
layer which is not sticky-to-the-touch or under overall

or broad pressures but which is at least slightly adhesive under the effects of localized imaging pressure so as to be receptive to the pressure-transfer of hectograph transfer compositions even under low imaging pressures.

The most critical ingredient of the present inert coating compositions is the solid polybutene resin, which comprises from about 15% to about 40% by weight of the composition. The polybutene resin is permanently tacky or adhesive, has sufficient viscosity to prevent it from being absorbed into the master paper, and is inert with respect to oils, dyes, spirit duplicating fluids and water. Suitable polybutene resins are commercially-available under the trademarks Vistanex LMMS and Vistanex LMMH, both of which are solid polyisobutylene polymers of extremely viscous, soft, gummy consistency. The former has an average Staudinger molecular weight of 10,400 to 10,900 and the latter has an average Staudinger molecular weight of 11,600 to 12,300. Similar polybutenes are available under the trademarks Isolene and Oppanol. However, the lower molecular weight liquid polybutenes such as Indopol, molecular weight between 300 and 2600, are unsatisfactory. A minor portion of the polybutene resin may be replaced with another viscous adhesive resin or polymer such as hydrogenated wood rosin provided that the latter is also compatible with the other ingredients. Generally, such secondary resins constitute from about 0% to 15% of the total resin content, preferably no more than about 10% by weight thereof.

The main ingredient of the present compositions, in terms of weight percentage, is the paraffinic wax which preferably comprises from about more than 50% up to about 65% by weight of the coating composition. The paraffinic wax reduces the viscosity of the molten composition to a coatable level, and reduces the adhesive nature of the polybutene in the composition.

While paraffinic waxes possess a degree of tackiness, per se, such tackiness is not sufficient to accomplish the objectives of the present invention in the absence of the polybutene polymer. The latter increases the adhesive properties of the mixture and also the cohesive properties thereof so that the imaged areas of the transfer layer are pulled over to the master coating when the sheets are separated, rather than vice-versa.

The present receptor compositions also contain a minor amount of at least one hard wax which is compatible with both the paraffinic wax and the polybutene polymer, such as carnauba wax or oxidized waxes. Generally, such hard waxes constitute from about 5% to 20% by weight of the total composition, preferably no more than about 15% by weight thereof. Paraffinic waxes are poor solvents or vehicles for tint color additives such as methyl violet isostearate and, therefore, the secondary waxes permit trace amounts of such color additives to impart a tint color to the receptive coated surface of the master sheet to distinguish said surface from the rear or obverse surface of the master sheet.

The essential ingredients of the present compositions form a diluted homogeneous molten mixture or solution which cools and solidifies to form a solid, hard coating which is not sticky-to-the-touch and which will not stick to the contacting surface of the transfer layer of the hectograph transfer sheet, or to an interposed barrier sheet, when the present units are packaged and stored in large numbers, and/or will not stick to the rear surface of the master sheet in the case of continuous masters which are wound on a roller. Essentially, it is

the compatible hard wax, such as carnauba wax, which reduces or masks the adhesive properties of the other ingredients to the point that the receptor layer is adhesive under the effects of localized imaging pressure but is not sufficiently adhesive under the effects of overall or broad pressures, as applied by the pressure duplicating rollers or by the winding of the master web in a roll, to cause sticking or transfer of the receptor coating to the hectograph copy sheets, or to the machine rollers or to the back of the master web.

The following example is given as illustrative of compositions which are suitable master sheet coatings for use according to the present invention.

EXAMPLE 1

The following ingredients are combined in the amounts shown and heated to a temperature of 180° F. to 200° F. to form a homogeneous molten coating composition:

Ingredients	% By Weight	Range
Paraffinic wax	53	45-65
Polyisobutylene polymer (Vistanex LMMS)	25	15-40
Carnauba wax	7	5-20
Polybutene resin (high viscosity)	8	0-15
Hydrogenated wood rosin (Staybelite Ester #10)	7	0-15

The molten composition has a viscosity between about 200 and 600 centipoises and is blade-coated in a weight of about 3 pounds per ream, 3300 square feet, as a continuous layer to one surface of a master paper web. Thereafter, the coating is cooled to provide the solidified surface layer which is dry and not sticky-to-the-touch but which has a slight stickiness if the thumb is pressed hard thereon against a hard surface.

The coated master web may be cut into sheet lengths or web widths for use with hectograph transfer sheets or webs of similar size, the hectograph transfer layer being positioned against the receptive coated surface of the master sheet or web.

The present units are found to provide excellent transfer of the hectograph composition, such as those disclosed in aforementioned U.S. Pat. No. 4,018,162, to the coated master sheet under the effects of a stylus carrying a weight of 16 ounces, whereas a unit consisting of the same hectograph transfer sheet and a conventional hectograph master sheet provides little or no transfer under the same conditions.

The present hot-melt-coated master sheets and webs produce improved imaging and duplicating results when used in association with conventional hectograph transfer sheets of all types, including hot-melt wax hectograph transfer compositions, solvent-coated, resin-based hectograph transfer compositions and solvent-coated or hot-melt coated microporous transfer compositions, as disclosed in U.S. Pat. No. 4,018,162, which produce master images which produce duplicate copies under the effects of pressure and in the absence of duplicating fluids.

Variations and modifications of the present invention will be apparent to those skilled in the art within the scope of the present claims.

Having thus described the invention, what is claimed is:

1. A pressure-sensitive imaged master sheet or web having thereon a plurality of migration-resistant duplicating images applied thereto under the effects of imaging pressure, said master sheet comprising a flexible paper foundation having an image-receptive surface coating comprising from about 0.5 to 5 pounds per 3300 sq. ft. of a thin, hard receptive layer of a hot-melt-applied composition consisting essentially of from 45% to 65% by weight of paraffinic wax, 5% to 20% by weight of a hard wax which is compatible with said paraffinic wax, and from 15% to 40% by weight of a normally-solid polybutene polymer having a Staudinger molecular weight of from 10,400 to 12,300, said receptive layer having on the surface thereof said plurality of duplicating images, and being nonsticky to the touch or to overall broad pressures but being sufficiently tacky under the effects of relatively low localized imaging pressure to bond to a frangible layer of duplicating composition and to pull over a substantial imagewise portions of said frangible layer to said master sheet in the form of said plurality of duplicating images when said sheets are separated, said receptive layer being an inert barrier with respect to the ingredients of said duplicating images and being resisting to sticking to copy sheets pressed thereagainst in a duplicating machine.

2. A master or web according to claim 1 in which said receptive layer comprises over 50% by weight of a paraffinic wax, and 5% to 15% by weight of a hard wax.

3. A master sheet or web according to claim 2 in which said hard wax comprises carnauba wax.

4. A master sheet or web according to claim 2 in which said receptive layer also comprises up to 15% by weight of rosin.

5. A method for improving the pressure transferability of a hectograph transfer layer to a hectograph mas-

ter sheet or web under the effects of localized imaging pressure and for producing migration-resistant hectograph duplicating images on said master sheet, comprising the step of coating said hectograph master sheet with from about 0.5 to 5 pounds per 3300 sq. ft. of a thin layer of a hot-melt composition consisting essentially of from 45% to 65% by weight of a paraffinic wax from 5% to 20% by weight of a compatible hard wax and, from 15% to 40% by weight of a normally-solid polybutene polymer having a Staudinger molecular weight of from 10,400 to 12,300, and cooling said layer of form a hard receptive layer which is not sticky to the touch or to overall board pressures which is sufficiently tacky under the effects of relatively low localized imaging pressure to bond to a hectograph transfer layer and pull over substantial imagewise portions thereof, said receptor layer being an inert barrier with respect to the ingredients of said hectograph transfer layer, superposing said master sheet with its receptive layer in contact with the hectograph transfer layer of a hectograph transfer sheet, and applying imaging pressure against said master sheet by means of a relatively light weight stylus to cause substantial imagewise portions of said transfer layer to bond to said receptive layer and to transfer thereto in the form of migration-resistant hectograph duplicating images when said master sheet and transfer sheet are separated.

6. Method according to claim 5 in which said receptive layer comprises over 50% by wight of a paraffinic wax, and 5% to 15% by weight of a hard wax.

7. Method according to claim 6 in which said hard wax comprises carnauba wax.

8. Method according to claim 6 in which said receptive layer also comprises up to 15% by weight of rosin.

* * * * *

40

45

50

55

60

65