



US005561830A

**United States Patent** [19][11] **Patent Number:** **5,561,830**

Weinl et al.

[45] **Date of Patent:** **\*Oct. 1, 1996**[54] **METHOD OF PRODUCING A SINTERED CARBONITRIDE ALLOY FOR FINE MILLING**[75] Inventors: **Gerold Weinl, Älvsjö; Rolf Oskarsson, Rönninge**, all of Sweden[73] Assignee: **Sandvik AB**, Sandviken, Sweden

[\*] Notice: The term of this patent shall not extend beyond the expiration date of Pat. No. 5,552,108.

4,769,070	9/1988	Tobioka et al. ....	75/238
4,857,108	8/1989	Brandt et al. ....	75/238
4,904,445	2/1990	Iyori et al. ....	419/13
4,944,800	7/1990	Kolaska et al. ....	75/238
4,973,356	11/1990	von Holst et al. ....	75/233
4,985,070	1/1991	Kitamura et al. ....	75/238
5,032,174	7/1991	Ekemar et al. ....	75/354
5,041,261	8/1991	Buljam et al. ....	419/11
5,041,399	8/1991	Fukaya et al. ....	501/87
5,053,038	7/1991	Ariura ....	407/26
5,110,949	5/1992	Westergren et al. ....	75/233
5,137,565	8/1992	Theelin et al. ....	75/238
5,147,831	9/1992	Zeiringer ....	501/96

[21] Appl. No.: **438,990**[22] Filed: **May 11, 1995****Related U.S. Application Data**

[63] Continuation of Ser. No. 78,239, filed as PCT/SE93/00884, Dec. 19, 1991, published as WO92/11392, Jul. 9, 1992, abandoned.

[30] **Foreign Application Priority Data**

Dec. 21, 1990 [SE] Sweden ..... 9004115

[51] Int. Cl.<sup>6</sup> ..... **B22F 3/12**[52] U.S. Cl. .... **419/13; 419/10; 419/11; 419/12; 419/14; 419/38; 419/39; 415/15; 415/23; 415/33; 415/36**

[58] Field of Search ..... 75/238; 419/10-15, 419/23, 33, 36, 38, 39

[56] **References Cited****U.S. PATENT DOCUMENTS**

3,971,656	7/1976	Rudy .....	75/203
3,994,692	11/1976	Rudy .....	29/182.5
4,049,876	9/1977	Yamamoto et al. ....	428/932
4,145,213	3/1979	Oskarsson et al. ....	75/238

**FOREIGN PATENT DOCUMENTS**

56-5946	1/1981	Japan .
8902306	6/1980	Sweden .


*Primary Examiner*—Donald P. Walsh*Assistant Examiner*—John N. Greaves*Attorney, Agent, or Firm*—Burns, Doane, Swecker & Mathis, L.L.P.[57] **ABSTRACT**



According to the invention there now is provided a method of producing a sintered titanium based carbonitride alloy with 325 weight-% binder phase with extremely good properties at extremely fine machining with high cutting speeds and low feeds. The method relates to the use of a raw material comprising a complex cubic carbonitride containing the main part of the metals from groups IV and V of the periodic system and carbon and nitrogen to be found in the finished alloy whereby said alloy has the composition

$$0.87 \leq X_{IV} \leq 0.99$$

$$0.66 \leq X_C \leq 0.76$$

where  $X_{IV}$  is the molar ratio of the group IV elements of the alloy and  $X_C$  is the molar ratio of carbon.

**17 Claims, 1 Drawing Sheet**



## METHOD OF PRODUCING A SINTERED CARBONITRIDE ALLOY FOR FINE MILLING

This application is a continuation of application Ser. No. 08/078,239, filed as PCT/SE93/00884 on Dec. 19, 1991, published as WO92/11392 on Jul. 9, 1992, now abandoned.

The present invention relates to a method of producing a sintered carbonitride alloy with titanium as main constituent with exceptional properties at extremely fine machining with high cutting speeds and low feeds.

Sintered carbonitride alloys based on mainly titanium usually referred to as cermets have during the last years increased their use at the expense of more traditional cemented carbide i.e. tungsten based alloys.

U.S. Pat. No. 3,971,656 discloses the production of an alloy with a duplex hard constituent where the core has a high content of Ti and N and the surrounding rim has a lower content of these two elements which is compensated for by a higher content of group VIa metals i.e. in principle Mo and W and by higher carbon content. The higher content of Mo, W and C has inter alia the advantage that the wetting against the binder phase is improved i.e. the sintering is facilitated. As a raw material a carbonitride of titanium and a group VIa metal is used.

By changing the raw material it is possible to vary the core-rim-composition. In e.g. Swedish Patent Specification 459 862 it is shown how it is possible to use (Ti,Ta)C as a raw material to get a duplex structure with cores with a high content of titanium and tantalum but low content of nitrogen. The surrounding rims have higher contents of group VI-metals, i.e. molybdenum and tungsten and higher contents of nitrogen than the cores. This leads inter alia to an improved resistance against plastic deformation.

Furthermore, it has in Swedish Patent Application 8902306-3 been shown how by mixing various types of core-rim structures in one and the same alloy advantages and drawbacks can be balanced out in such a way that optimized alloys are obtained.

It has now turned out that if sintered titaniumbased carbonitride alloys are produced using complex cubic carbonitride raw material which contains the main part, preferably >90%, most preferably >95% of the metals at least two preferably at least three from the groups IV and V in addition to carbon and nitrogen being part of the finished sintered carbonitride alloy unique structures as well as unique properties are obtained. Preferably all of the nitrogen shall be present in the mentioned carbonitride raw material.

In particular of the above-mentioned metals all titanium and tantalum shall be present in the raw material according to the invention. Preferably also vanadium, niobium and suitably also zirconium and hafnium are present if they are part of the finished sintered alloy. Metals from group VI, Cr, Mo and W, shall, if they are present, be added as multiple carbides, single carbides and/or as metal+carbon, but they may also be part of the raw material according to the invention provided that the raw material remains cubic.

As mentioned interesting properties of a sintered carbonitride alloy are obtained if the special raw materials according to this invention are used. Thus, it has turned out that a carbonitride alloy with extremely positive properties at fine milling particularly at high cutting speeds, >250 m/s, for carbon steel and low alloyed steel, and low feeds, <0.3 mm/rev, is obtained, if a complex raw material with e.g. the composition  $(\text{Ti}_{0.95}, \text{Ta}_{0.05})(\text{C}_{0.7}, \text{N}_{0.3})$  is used. This effect is further increased if in addition vanadium is added whereby the corresponding formula will be  $(\text{Ti}_{0.91}, \text{Ta}_{0.04},$

$\text{V}_{0.05})(\text{C}_{0.72}, \text{N}_{0.28})$ . Corresponding inserts made from simple raw materials and in exactly the same equipment give considerably worse properties in toughness inter alia greater spread at the same wear resistance. This means that the reliability of such inserts is considerably worse which means that they are much worse when producing with limited manning a production form with increased importance due to increasing labour costs.

One of the reasons for this positive behaviour has turned out to be that a considerably lower porosity level is obtained with this complex raw material compared to conventional raw materials without having to use any other means such as HIP and this with even lower compaction pressure than for conventional material. This is a great advantage from production point of view inter alia due to reduced tool wear and considerably lower risk for unfavourable pressing cracks.

The invention thus relates to a method of producing a titanium based carbonitride alloy with 3-25% by weight binder phase based on Co, Ni and/or Fe according to which hard constituents of metals from the groups IV, V and/or VI are added in the form of the above mentioned complex raw material. This raw material is milled together with possible carbides from group VI and binder phase elements and possible carbon addition and minor additions of e.g. TiC, TiN, TaC, VC or combinations thereof due to small deviations in composition of the complex raw material whereafter compaction and sintering is performed according to known technique.

FIG. 1 shows the 'window' in the composition diagram for Group IV-Group V-C-N, expressed in molar ratio, of the complex raw material which shows the above mentioned advantages in high magnification, whereas FIG. 2 shows where in the total molar ratio diagram this small area is situated.

Group IV metals are Ti, Zr and/or Hf and Group V metals are V, Nb and/or Ta.

As is evident from FIG. 1 the window comprises the Composition area:

$$0.87 \leq X_{IV} \leq 0.99$$

$$0.66 \leq X_C \leq 0.76$$

and in particular:

$$0.89 \leq X_{IV} \leq 0.97$$

$$0.68 \leq X_C \leq 0.74$$

The latter restricted window can be divided into two, one without other group V metals than Ta:

$$0.93 \leq X_{IV} \leq 0.97$$

$$0.68 \leq X_C \leq 0.74$$

and another one with other group V elements than Ta i.e. V and Nb:

$$0.89 \leq X_{IV} \leq 0.93$$

$$0.68 \leq X_C \leq 0.74$$

Particularly good properties are obtained for the compositions

$$0.93 \leq X_{IV} \leq 0.97$$

$$0.68 \leq X_C \leq 0.72$$

respectively

$$0.89 \leq X_{IV} \leq 0.93$$

$$0.70 \leq X_C \leq 0.74$$

For titanium the following applies  $x_{Ti} > 0.7$  preferably  $x_{Ti} > 0.75$ .

In the above given molar ratios for carbon and nitrogen usual amounts of oxygen may be present i.e. substitute carbon and nitrogen even if it is desirable to keep such amounts of oxygen low <0.8%, preferably <0.5%. The invention comprises stoichiometric as well as usually sub-stoichiometric carbonitrides.

## EXAMPLE

Titanium-based carbonitride alloys with 12% Ni+Co binder phase were produced with the use of a complex raw material according to the invention  $(\text{Ti}_{0.91}, \text{Ta}_{0.04}, \text{V}_{0.05})(\text{C}_{0.72}, \text{N}_{0.28})$  as well as with the use of simple raw material: TiN, TiC and VC. In both cases also WC and  $\text{Mo}_2\text{C}$  were added in addition to Co and Ni. The following compaction pressure and porosity after milling and sintering to the same grain size were obtained:

The complex carbonitride raw material can be described as  $(\text{A}_x\text{B}_{1-x})(\text{C}_y\text{N}_{1-y})$ , where A is one or more metals from Group IV of the periodic system and B is one or more metals from Groups V or VI of the periodic system with  $0.87 \leq x \leq 0.99$  and  $0.66 \leq y \leq 0.76$ .

	Porosity	Compaction pressure, N/mm <sup>2</sup>
Alloy according to the invention	A00	131
Simple raw materials	A04-A06	164

We claim:

1. A method of producing a sintered titanium-based carbonitride alloy with 3-25 weight percent binder phase, comprising steps of:

milling a complex carbonitride raw material and said binder phase to form a mixed powder composite, said complex carbonitride raw material comprising  $(\text{A}_x\text{B}_{1-x})(\text{C}_y\text{N}_{1-y})$  where A is one or more elements from Group IV and B is one or more elements from Group V, with  $0.87 \leq x \leq 0.99$  and  $0.66 \leq y \leq 0.76$ ; and

sintering the powder composite to produce said sintered titanium-based carbonitride alloy, all of the Group IV and V elements in the alloy being added via the complex raw material.

2. The method according to claim 1, wherein  $0.89 \leq x \leq 0.97$  and  $0.68 \leq y \leq 0.74$ .

3. The method according to claim 1, wherein said complex carbonitride raw material is cubic.

4. The method according to claim 1, wherein A consists essentially of Ti.

5. The method according to claim 1, wherein B comprises at least two Group V metals.

6. The method according to claim 1, wherein the complex raw material comprises  $(\text{Ti}_{0.9}\text{Ta}_{0.04}\text{V}_{0.05})(\text{C}_{0.72}\text{N}_{0.28})$  or  $(\text{Ti}_{0.95}\text{Ta}_{0.05})(\text{C}_{0.7}\text{N}_{0.3})$ .

7. The method according to claim 1, wherein the binder phase comprises Co, Ni, Fe or mixture thereof.

8. The method according to claim 1, wherein the complex raw material is milled with additions comprising at least one addition selected from carbides of Group VI metals and combinations thereof.

9. The method according to claim 1, wherein the sintering step is carried out by compaction and heating in an inert atmosphere.

10. The method according to claim 1, wherein the complex raw material comprises essentially equiaxial grains with a narrow grain size distribution and a mean grain size of 0.8-3.0  $\mu\text{m}$ .

11. The method according to claim 1, wherein the complex raw material comprises essentially equiaxial grains with a narrow grain size distribution and a mean grain size of 1-2  $\mu\text{m}$ .

12. The method according to claim 1, wherein the complex raw material includes Ti and Ta.

13. The method according to claim 1, wherein the complex raw material includes V, Nb, Zr, Hf or combinations thereof.

14. The method according to claim 1, wherein the complex raw material includes  $\leq 0.8$  weight % oxygen.

15. The method according to claim 1, wherein the complex raw material includes  $\leq 0.5$  weight % oxygen.

16. The method according to claim 1, wherein the raw material is produced directly by carbonitriding metals, metal oxides or mixtures thereof.

17. The method according to claim 1, wherein all of the N in the alloy is added via the complex raw material.

\* \* \* \* \*