



US006087630A

# United States Patent [19]

[11] Patent Number: **6,087,630**

Miller et al.

[45] Date of Patent: **Jul. 11, 2000**

[54] **METHOD FOR HEATING A SOLID SURFACE SUCH AS A FLOOR, WALL, ROOF, OR COUNTERTOP SURFACE**

[75] Inventors: **Charles G. Miller**, Branford, Conn.; **John A. Rolls**, Armonk, N.Y.; **Otis H. Hastings**, Mahwah, N.J.

[73] Assignee: **Thermion Systems International**, Stratford, Conn.

[21] Appl. No.: **09/457,053**

[22] Filed: **Dec. 7, 1999**

### Related U.S. Application Data

[60] Continuation of application No. 09/311,219, May 13, 1999, Pat. No. 6,015,965, which is a division of application No. 09/633,965, Apr. 19, 1996, Pat. No. 5,932,124.

[51] **Int. Cl.<sup>7</sup>** ..... **H05B 1/00; H05B 3/10; H01C 1/02**

[52] **U.S. Cl.** ..... **219/213; 338/255; 219/548**

[58] **Field of Search** ..... **219/213, 548, 219/549; 338/255, 257, 256; 165/47**

### [56] References Cited

#### U.S. PATENT DOCUMENTS

- 2,876,326 3/1959 Akmentin .
- 2,912,555 11/1959 Jamison .
- 2,961,522 11/1960 Hammer .
- 2,997,568 8/1961 Leipold et al. .
- 3,069,522 12/1962 Jamison .
- 3,129,316 4/1964 Glass et al. .
- 3,539,767 11/1970 Eisler .
- 3,626,149 12/1971 Cartney et al. .
- 3,657,516 4/1972 Fujihara .
- 3,683,152 8/1972 Laing .
- 3,694,622 9/1972 Bentley .
- 3,697,728 10/1972 Stirzenbecher .
- 3,766,644 10/1973 Davis .
- 3,859,504 1/1975 Motokawa et al. .
- 3,973,103 8/1976 Tadewald .
- 4,039,720 8/1977 Cherenko et al. .
- 4,110,151 8/1978 Morse .
- 4,245,149 1/1981 Fairlie .
- 4,250,397 2/1981 Grey et al. .

- 4,250,398 2/1981 Ellis et al. .
- 4,282,049 8/1981 Morse .
- 4,321,459 3/1982 Miyahara et al. .
- 4,534,886 8/1985 Kraus et al. .
- 4,574,186 3/1986 Sakai et al. .
- 4,650,960 3/1987 Bergersen .
- 4,717,812 1/1988 Makita .
- 4,734,231 3/1988 Morita et al. .
- 4,737,618 4/1988 Barbier et al. .
- 4,878,332 11/1989 Drake .
- 4,899,031 2/1990 Dyer .
- 4,942,078 7/1990 Newman et al. .
- 4,972,197 11/1990 McCauley .
- 4,990,747 2/1991 Kondo .
- 5,250,228 10/1993 Bairgrie et al. .
- 5,344,696 9/1994 Hastings et al. .
- 5,361,183 11/1994 Wiese .
- 5,528,249 6/1996 Gafford .

### FOREIGN PATENT DOCUMENTS


- 285171 10/1988 European Pat. Off. .
- 2493090 4/1982 France .
- 2681753 3/1993 France .
- 2619466 11/1977 Germany .
- 2620602 12/1977 Germany .
- 4221455 1/1994 Germany .
- 55-166892 12/1980 Japan .
- 60-165083 8/1985 Japan .
- 5126347 5/1993 Japan .
- 6151044 5/1994 Japan .
- 6297632 10/1994 Japan .
- 7302683 11/1995 Japan .
- 9104447 4/1991 WIPO .
- 9515670 6/1995 WIPO .

*Primary Examiner*—Teresa Walberg  
*Assistant Examiner*—Daniel Robinson  
*Attorney, Agent, or Firm*—White & Case LLP

### [57] ABSTRACT

A method is provided for heating the surface of a material such as a floor, wall, roof, or countertop. The method comprises providing a laminated heater element, disposing the heater element at a predetermined depth in the material and energizing the element at prescribed intervals and temperatures which are effective to heat the surface of the material.

**2 Claims, 6 Drawing Sheets**






FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6

## METHOD FOR HEATING A SOLID SURFACE SUCH AS A FLOOR, WALL, ROOF, OR COUNTERTOP SURFACE

This application is a continuation of application Ser. No. 09/311,219, filed May 13, 1999 now U.S. Pat. No. 6,015,965, which is a divisional of application Ser. No. 09/633,965, filed Apr. 19, 1996, now U.S. Pat. No. 5,932,124, issued Aug. 3, 1999.

### BACKGROUND OF THE INVENTION

#### 1. Field of the Invention

The present invention generally relates to methods of heating various solid surfaces. Specifically, the invention relates to methods of heating floors, walls, roofs, or countertops by applying a heater element, such as a laminated composite heater element to the particular surface and energizing the heater element.

#### 2. Description of the Prior Art

A variety of heater elements exist in the prior art. U.S. Pat. No. 4,534,886, to Kraus et al., discloses an electrically conductive web composed of a non-woven sheet of conductive fibers and non-conductive fibers. The sheet is saturated with a dispersion containing conductive particles and is then dried. The Kraus et al. heater element is used primarily in heating pads.

International Application No. PCT/US94/13504 (Publication No. WO95/15670) discloses an electrically conductive composite heating assembly. The assembly has an electrically conductive non-woven fiber layer laminated between layers of fiberglass and other dielectric material. The assembly further has an abrasion resistant outer layer. The heater element is used on aerospace structures as an ice protection system to withstand the repeated mechanical stress and thermal cycles encountered in extremely harsh aerospace environments.

U.S. Pat. No. 5,344,696 to Hastings et al. discloses an integrally bonded laminate that is used to thermally control a surface of an aircraft to which the laminate is bonded.

None of the prior art heater elements, however, have been successfully applied to floors, walls, roofs, or countertops.

### SUMMARY OF THE INVENTION

The present invention comprises a method for heating the surface of a solid material, such as a floor, wall, roof, or countertop. The method comprises providing a heater element, disposing the heater element at a predetermined depth in the material, and energizing the heater element at prescribed intervals and temperatures, effective to heat the surface of the material.

### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 depicts the construction of a composite heater element of the invention in a mold.

FIG. 2 depicts a typical tile/paver floor containing the heater element as described in the present invention.

FIG. 3 depicts a Formica™ counter top containing the heater element as described in the present invention.

FIG. 4 depicts a typical heater element of the present invention embedded within a solid surface material.

FIG. 5 depicts a roof ice dam heater of the present invention.

FIG. 6 depicts a typical inlaid concrete walkway containing a heater element as described in the present invention.

## DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The present invention comprises a method for heating the surface of a solid material, such as a floor, wall, roof, or countertop. The method comprises providing a heater element, disposing the heater element at a predetermined depth and location in the material and energizing the element at prescribed intervals and temperatures which are effective to heat surface of the material.

The heater element of the present invention is a laminated composite, impermeable to water, and is of the type disclosed in U.S. Pat. No. 5,344,696 (Hastings et al.), which is incorporated herein by reference. As disclosed in the Hastings et al. patent, the heater element comprises a durable outer ply, which is resistant to abrasion and impermeable to water, bonded to and through a conductive layer of fibers, and an integrally enveloping adhesive, which is adhered to the surface of a vessel. The conductive layer is connected to a source of electrical energy, and control means are adapted to control the temperature of the surface of the vessel. This laminated structure is considered preferable; however, it is contemplated that other structures may be used. For example, the heater element need not be a laminated structure. Rather, the heater element may comprise merely a layer of conductive fibers. This structure of the heater element is particularly-useful if the material into which the heater element is embedded has dielectric properties that will evenly distribute the heat generated by the element.

The preferred heater element is available under the trademark Thermion™, which is manufactured by Aerospace Safety Technologies, Inc. Thermion™ is thin, light, flexible and may be translucent. The material is a laminate that provides even heating and can be conformed to surfaces having a variety of different contours and shapes. operational power can be derived from low or high voltage AC or DC power supplies.

As discussed above, the heater element may comprise a layer of conductive fibers that are directly embedded into the material. However, in this instance, the material must possess sufficient dielectric properties to evenly distribute the heat generated by the fibers to the surface of the material. Thermoplastic materials typically possess these properties.

The heater element is disposed at a predetermined location and depth in the material. The depth and location may vary according to the particular material and type of heating required.

#### 1. Residential/Commercial Building Use

The thin, unobtrusive nature of the heater element makes it suitable for use in ceramic and marble tile, solid surface materials, Formica, linoleum, and any other floor, wall, roof, or counter covering available. The essential steps of the method of the present invention can be performed in several different ways.

A first variation in the method involves installing in the surface a pre-made panel, usually configured on a mold table for easy transfer to the final surface. As shown in FIG. 1, the pre-made panel comprises a fiberglass resin encapsulated heater element **1**, further encapsulated in two fiberglass/resin cloths **5** and **5'**. The pre-made panel also contains electrical leads attached to the heater element (not shown). The electrical leads extend outside of the panel and are attached to an electrical power supply. The laminate optionally can be constructed with multiple layers of the fiberglass resin encapsulated heater element **1**. The multiple-layered heater element can provide greater control over the heat output from the assembly.



FIG. 1 shows how a single layer pre-made panel is formed on a transfer table. The fiberglass resin encapsulated heater element **1** is placed on top of a mold table surface **9**. A mold release wax **15** is disposed between the encapsulated heater element **1** and the table surface **9**. A peel ply **19** is placed above the encapsulated heater element **1**. A release ply **21** is disposed above the peel ply **19** and a bleeder cloth **25** is disposed over the release ply **21**. Finally, a vacuum bag **29** is disposed over the release ply **21**. A seal tape **11** surrounding the layers on the mold is attached to the table top surface **9**, and can adhere to the vacuum bag **29** to create a tight seal. A vacuum supply **33** is used to evacuate the air between the layered material in order to bring the layers into close contact with each other and cure the resin, bonding the layers to create the laminate.

Referring to FIG. 2, a pre-formed panel may be installed below a variety of covering surfaces, such as ceramic, marble, or similar paver tiles. In a tile and grout environment **101**, the sub-base, whether a floor or countertop, may first be covered by a particle board underlayment **100**. Some builders choose not to use an underlayment, but its purpose is to aid in leveling the floor and build uniformity. A vapor barrier and one or more concrete base products are then applied over the underlayment set. At a minimum, the concrete **102** should be at least  $\frac{1}{2}$  inch thick for standard wet/dry environments, such as kitchen and bathroom floors and counters (see FIGS. 2 and 3). For standing water conditions, such as showers and exterior areas, the layer must be at least twice this thickness. Concrete serves a dual purpose. It limits the surface flexing and also acts as a water barrier. The vapor barrier further prevents water from passing to the wood below either by sweating or cracking of the concrete. A heater element **104** is disposed above the concrete base **102**. The heater element **104** optionally contains a syntactic film layer **106** on the back/bottom side for bonding the element **104** to the concrete base **102**. Film layer **106** replaces the mastic that would otherwise be required to set heater element **104** in place. Without a bonding film layer, the installer would smear the concrete base with a thin layer of mastic, alternatively referred to as **105**, apply the heater element from edge to edge, minimizing air pockets, and roll the element flat against the concrete base **102**. Once the heater element **104** is set, the normal process of installing tiles **101** can continue. If necessary, the panel may be punched with suitable tools to create holes or other shapes, as needed, and edge finished to protect against electrical shock. The holes, depending on their relative size and location, will have minimal to moderate effect on the heat output of the device.

As depicted in FIG. 3, the heater element **104** can be installed under a countertop layer **108**, such as a Formica or linoleum top layer, in a manner similar to tile, although the concrete base and vapor barrier are no longer required. In addition, Formica/linoleum installation generally utilizes contact adhesives which require additional processing known to those skilled in the art.

A second variation in the method of the present invention involves simultaneously constructing the composite heater element **104** at the time the floor, wall, roof, or countertop material is constructed. For instance, the composite in FIG. 3 may be constructed on the subsurface **109** simultaneously as the other layers of material are applied over the heater element **104**. This second method is particularly useful in the construction of formica and metal countertops. This-method is advantageous in that custom-shaped heater elements may be easily incorporated below the finished surface of the material. For example, in the case of wood/concrete substrates, custom-shaped heater elements may be bonded

under the finished surface of the material. In carrying out this method, the heater element is disposed on a solid, clean surface, and epoxy resin is applied to bond the element to the material. The composite may also be vacuum cured and heated, if desired. The vacuum process regulates the heater resin content in conjunction with the fiberglass selected. After the curing process is complete, the top surface of the material may be finished, as desired. In the case of Formica, a contact adhesive is applied between the element and the top surface before they are joined. Thereafter, the composite is rolled to complete the process.

As depicted in FIG. 4, a third variation in the method of the present invention involves providing a heater element **104** without the fiberglass outer layers or resin and encapsulating the element **104** within the finished material at the factory/production level. Such an installation is suitable for solid surface **112** materials such as Corion®, or any other thermoplastic formed item that has sufficient dielectric strength to isolate the electric heater element from the surface, and that allows cohesive bonding through the heating element. Most structures developed by liquid process molding are excellent candidates. The placement of the heater element **104** can be accurately controlled providing heat as near to the surface as is practical and safe. Using standard counter depths, the heaters can be pre-formed to run front to back allowing the surface to be cut to length, and end finished. A front to back orientation refers to the direction of current flow.

Different configurations of heater placement and orientation may be accomplished at the time of production, allowing for custom needs. Some circumstances may require surface heating in localized areas, for instance, the areas around a sink or other fixtures. The heater element may, therefore, be pre-cut to any particular pattern and may contain holes or cuts, as is necessary. For a field modification to a solid surface application, the surface could be cored within certain dimensions and edge finished, having minimal to moderate effect on the heater's performance.

Additional residential/commercial building applications include roof de-icing as shown in FIG. 5 and concrete walkways as shown in FIG. 6. These applications could use the pre-made panels for convenience and quick installation. Such roof applications are suitable for neoprene, hot mopped, shingled or even metal style roofs. FIG. 5 shows a typical application of the heater element **104** to a roof. Listed from bottom layer to top layer, the typical heater roof comprises a wood sheeting substrate **109**, felt paper **113**, heater mastic **111**, the heater element **104**, and the finished roof layer **115**. The finished roof layer **115** may be of typical roof finish materials such as, neoprene rubber, metal, or the like.

Application of the heater element in a concrete walkway is depicted in FIG. 6. The walkway contains a perforated panel **114**, laid during construction over and above, or in place of, a rebar **116**. The heater element **104** is disposed over the perforated panel **114**. Finally, a top layer of concrete is disposed above the element.

The heater element may also be applied to rain gutters. Such application may be completed by use of any of the methods discussed. The particular method chosen depends on the installation and gutter product selected.

Additionally, the heater element may be applied to mirrors. Mirror application to prevent fogging is an example of a simple back side bonding. The heater may be a pre-formed panel or a formed-in-place installation. For radiant heat applications the methods are no different only the object

**5**

selected to encase the material vary. Besides the possibility of heated pavers, diffused panels for a green house can incorporate the heated panels. The panels can be of simple or complex design and may provide winter environmental control and snow removal. Additional greenhouse installations could provide local heating as well for particular applications, such as lighting pairs for ice/snow protection and for heating/environmental control.

What is claimed is:

1. A method for heating a wall, comprising;

providing a pre-formed panel heater element to the wall, wherein said pre-formed panel heater element consists of an inner layer composed of a fabric of electrically conductive fibers encapsulated between two fiberglass/resin layers: two outer fiberglass/resin layers disposed

**6**

on opposing surfaces of said inner layer and encapsulating said inner layer; and electrical leads connected to said conductive fibers and adapted to receive power from a power source;

5 disposing the pre-formed panel heater element at a pre-determined depth in the wall; and

energizing the conductive fibers of the pre-formed panel heater element at prescribed intervals and temperatures which are effective to distribute heat evenly on the surface of the wall.

10 2. The method of claim 1, wherein the wall comprises ceramic, paver or marble tiles.

\* \* \* \* \*