



US006143227A

United States Patent [19]

[11] Patent Number: **6,143,227**

Heiden et al.

[45] Date of Patent: **Nov. 7, 2000**

[54] **METHOD FOR INJECTION MOLDING AN ARTICLE HAVING FILM COVERED FLANGES**

[75] Inventors: **James Heiden**, Clinton; **Mark Alan Harris**, Dexter; **Dale Moore**, Plymouth; **Zinoviy Chernyak**, Farmington Hills, all of Mich.

[73] Assignee: **Visteon Global Technologies, Inc.**, Dearborn, Mich.

[21] Appl. No.: **08/903,078**

[22] Filed: **Jul. 30, 1997**

[51] Int. Cl.⁷ **B29C 45/16**

[52] U.S. Cl. **264/267; 264/318; 264/334; 475/127; 475/129.1; 475/438; 475/442; 475/DIG. 58**

[58] Field of Search 264/267, 328, 264/334; 475/129.1, 577, 438, 442, 443, DIG. 58, 112, 117, 127

[56] **References Cited**

U.S. PATENT DOCUMENTS

3,668,034	6/1972	Nicholas et al. .	
4,136,150	1/1979	Darnall, Jr. .	
4,650,533	3/1987	Parker et al. .	
4,769,100	9/1988	Short et al. .	
4,822,553	4/1989	Marshall	264/318
4,854,849	8/1989	Sudo	264/318
4,902,557	2/1990	Rohrbacher .	
4,913,760	4/1990	Benson et al. .	
4,956,142	9/1990	Mangone, Jr.	425/442
4,976,896	12/1990	Short et al. .	
5,034,077	7/1991	Pata .	
5,034,269	7/1991	Wheeler .	
5,037,680	8/1991	Papendick et al. .	
5,055,346	10/1991	Rohrbacher .	
5,114,789	5/1992	Reafler .	
5,125,994	6/1992	Harasta et al. .	
5,183,615	2/1993	Zushi .	

5,192,609	3/1993	Carroll, Jr. .	
5,208,081	5/1993	Gübitz et al. .	
5,215,811	6/1993	Reafler et al. .	
5,215,826	6/1993	Shimanski et al. .	
5,248,364	9/1993	Liu et al. .	
5,271,352	12/1993	Wilson .	
5,342,666	8/1994	Ellison et al. .	
5,350,473	9/1994	Weder et al. .	
5,435,865	7/1995	Lee et al. .	
5,500,169	3/1996	Kondo et al.	264/46.5
5,514,427	5/1996	Ellison et al. .	
5,536,539	7/1996	Ellison et al. .	
5,538,576	7/1996	Knop et al. .	
5,585,187	12/1996	Shinonaga et al. .	
5,599,608	2/1997	Yamamoto et al. .	
5,650,115	7/1997	Proos et al.	264/400

FOREIGN PATENT DOCUMENTS


0 042 782	12/1981	United Kingdom .
0 161 589	11/1985	United Kingdom .
0 510 414	10/1992	United Kingdom .



Primary Examiner—Jan H. Silbaugh
Assistant Examiner—Edmund H. Lee
Attorney, Agent, or Firm—Larry I. Shelton

[57] **ABSTRACT**

A method and apparatus for manufacturing a film-covered flange having the following steps. An injection molding press having a mold cavity and a core receives a pre-molded thermoformed film. The film is formed to have an in-turned flange portion that will form the covering for the final article. The film is placed within the mold cavity. The core has a slide movable between retracted and extended positions. The slide is retracted and the core is moved within the mold cavity. After the press is closed the slide is moved from the retracted position to the extended position. The slide includes a recessed portion that lies opposite the flange portion to create a space therebetween. A molten plastic material is injected into the space. The plastic material adheres to the flange portion and forms an article having a covered flange.

1 Claim, 5 Drawing Sheets








Fig-3




Fig-4




Fig-5




Fig-6




Fig-7




Fig-8




Fig-9

METHOD FOR INJECTION MOLDING AN ARTICLE HAVING FILM COVERED FLANGES

RELATIVE APPLICATIONS

This application is related to commonly assigned U.S. patent application Ser. No. 08/903,113, now abandoned, titled: "METHOD AND APPARATUS FOR MANUFACTURING AN ACUTE ANGLE FILM-COVERED FLANGE", filed on even date herewith and incorporated by reference.

BACKGROUND OF INVENTION

1. Field of the Invention

Present invention is directed to a method and apparatus for forming a film-covered flange. More specifically, the present invention is directed to providing a core with a moveable slide that overlies a flange portion of the film to form the film-covered flange.

2. Description of the Related Arts

It is also known to manufacture molded articles using flexible films wherein the film is placed within a mold and a polymer is injected behind the film to heat and soften the film backing. The film backing fuses to the polymer to form a molded article. An example of this type of method is taught in U.S. Pat. No. 3,668,034. One difficulty in manufacturing molded articles using pre-molded flexible films, is properly positioning the flexible film within the mold so that it is free of wrinkles or creases and is precisely positioned in the cavity to register with the contours to form the desired article. Heretofore, proper placement of the pre-molded film within the cavity has been a major stumbling block to widespread application of pre-molded films. The problem is especially acute when handling pre-molded thin films for large automotive applications such as bumper facias. The entire surface area of the film must be properly positioned within the cavity to produce a defect-free article. Slight misalignments will cause wrinkles or defects and make the article unusable.

It is necessary to precisely place the film between the operable core and cavity pieces of a molding press. Because these operable pieces open and close, it is advantageous to provide a mechanism which allows the pre-molded film to be robotically placed within the mold cavity rather than manual placement by an operator. It is a further desired result of the present invention to utilize existing equipment for removing the molded article from the core in the method for placing the pre-molded film within the mold. It is also desired that the method and apparatus utilize existing molding equipment to the maximum extent possible. This includes utilizing a mold press and core with a limited opening there between. It is further desirable to manufacture an article having a flange in a tool that is subject to "die-lock" conditions. Die-lock conditions occur when either the mold cannot be opened or when the part cannot be removed from the mold.

It is desirable to form articles with flange portions. The flange acts as a mechanism to attach the article and to provide the article with additional strength or rigidity. When used in exterior automotive applications such as bumper facias, the flange is abutted an adjacent component. A portion of the flange remains visible. The appearance of the flange should match that of adjacent components. In most cases, these flange portions are painted to match the rest of the facia. A difficulty arises when manufacturing these

components using a pre-painted film. The film must wrap around the flange.

It is known to form a covered edge using in-mold films. An example of this construction is illustrated in U.S. Pat. No. 5,599,608. A film having a re-entrant edge portion is placed within a mold. A mold is moved to contact the core. The core engages the re-entrant portions and folds them within the mold cavity. Molten plastic is injected into the mold cavity and the combination of closing the mold combined with the pressure of the molten plastic material forces the re-entrant edge portions against the mold wall to form the covered edge of the molded article.

The method described in U.S. Pat. No. 5,599,608 is limited to forming an edge portion having a width equal to the thickness of the substrate. This is useful when forming a part having a covered edge, but not useful when forming a part having a covered flange. A flange requires a space behind it. This space is known as an undercut. The 5,599,608 patent does not teach forming parts having an undercut.

It is also known to include pins or slides in the core to assist in removing the article from the mold. The plastic forms around the pin or slide and the article remains with core when the press is opened. What has not been shown, is the use of a slide to provide both an undercut and to assist in removing the article from a mold.

These deficiencies and problems are overcome by the present invention.

SUMMARY OF THE INVENTION

The present invention is directed to a method of manufacturing a film-covered flange comprising the following steps. An injection molding press having a mold cavity and a core receives a pre-molded thermoformed film. The film is formed to have an in-turned flange portion that will form the covering for the final article. The film is placed within the mold. The core has a slide movable between retracted and extended positions. The slide is retracted and the core is moved within the mold. After the press is closed, the slide is moved from the retracted position to the extended position. The slide includes a recessed portion that lies opposite the flange portion to create a space there between. A molten plastic material is injected into the space. The plastic material adheres to the flange portion of the pre-molded thermoformed film and forms an article having a covered flange.

The invention also includes an apparatus for forming an article having a film-covered flange. The apparatus includes a moveable press having a mold cavity and a core. The core has a slide movable between retracted and extended positions. The slide includes a recessed portion. The cavity receives a thermoformed film having a flange portion. The slide includes a recessed portion that is opposite the flange portion when the press is closed and when the slide is moved to the extended position. The recessed portion and flange portion define a space. A resin inlet injects a molten plastic material into the space. The molten plastic material adheres to the flange portion to form an article having a film-covered flange.

The slide may be moved linearly or in an arcuate path. The slide retains the article on the core and removes the article from the mold. The slides retract releasing the molded article.

In an alternative embodiment of the present invention, the mold cavity is subject to die-lock and the core extends and retracts to withdraw the article from the mold cavity. The article flexes to pass through the die-lock and is removed from the cavity.

The invention enables the manufacture of film-covered articles having a covered flange portion. It is another advantage of the present invention to provide a core with moveable slides that forms the flange and retains the article on the core.

These and other desired objects of the present invention will become more apparent in the course of the following detailed description and appended claims. The invention may best be understood with reference to the accompanying drawings wherein illustrative embodiments are shown.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a cross-sectional view of an open mold.

FIG. 2 is a cross-sectional view of the mold illustrated in FIG. 1 in the closed position injecting molten plastic behind a film.

FIG. 3 is a cross-sectional view of the mold illustrated in FIG. 1 in the open position and retaining the molded article on the core.

FIG. 4 is a cross-sectional view of the mold illustrated in FIG. 1 with the slides retracted and releasing the molded article.

FIGS. 5 and 6 are cross-sectional views of an alternative embodiment of the present invention using slides that move in an arcuate path.

FIGS. 7-9 are cross-sectional views of yet another alternative embodiment of the present invention using a mold cavity having a die-lock condition.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention will be described through a series of drawings, which illustrate a molding of a flexible film having an in-turned flange portion using a core having one or more moveable slides. The invention will be illustrated as molding an automotive bumper facia. Other components such as instrument and door panels may be manufactured using the same or similar technique and equipment and are included within the invention described herein. The following items are a word list of the items described in the drawings and are reproduced to aid in understanding the invention:

10	press
12	mold cavity
12'	mold cavity
14	core
14'	core
16	cavity surface
18	film
20	painted surface
22	backing sheet
24	flange portion
26	flange portion
28	main body
30	linear slide
30'	arcuate slide
30"	linear slide
32	linear slide
32'	arcuate slide
32"	linear slide
34	recessed portion
34'	recessed portion
36	recessed portion
36'	recessed portion
38	piston

-continued

40	piston
42	injecting space
44	resin inlet
46	article
48	covered flange
50	covered flange

Illustrated in FIG. 1 is a moveable mold press **10** having a cavity **12** and a moveable core **14**. The mold cavity **12** has an interior surface **16** that imparts a shape on a molded article. The mold cavity **12** receives a pre-molded flexible thermoformed film **18**. The film **18** may be either a thin film such as Avloy™ manufactured by Avery Dennison or ISF™ manufactured by 3M/Rexam. Alternatively, the film may be a thick film such as polyvinyl chloride or thermoplastic urethane as is normally used in automotive trim applications. Other types of film are also useful in the present invention. The film **18** has a painted surface **20** and a backing sheet **22**. The film **18** is placed within the mold cavity **12** using an automated film loader (not shown). An example of a suitable automated film loader is illustrated and described in co-pending U.S. patent application Ser. No. 08/903,523 titled: METHOD AND APPARATUS FOR LOADING A PRE-MOLDED FILM INTO A MOLD, which is incorporated herein by reference. The painted surface **20** is juxtaposed the cavity surface **16**.

The film **18** includes two in-turned flange portions **24, 26**. The flange portions **24, 26** are formed on the film **18** during the thermoforming operation (not shown). The flange portions **24, 26** cover a flange on the finished molded article. The space between the flange portions **24, 26** is generally smaller than the cavity opening. The flange portions **24, 26** are relatively fragile and are easily damaged by contact with the core **14**.

The core **14** includes the main body **28** and moveable slides **30, 32**. The slides **30, 32** include recessed portions **34, 36**. The recessed portions **34, 36** form an undercut for the article flange. The slides **30, 32** are retracted as illustrated in FIG. 1 to provide a narrow profile that allows the core **14** to pass between the flange portions **24, 26**. After the core **14** is moved within the mold cavity **12** and the press **10** is closed, the slides **30, 32** are extended as illustrated in FIG. 2.

The slides **30, 32** move linearly by the pistons **38, 40**. The recessed portions **34, 36** are positioned opposite the flange portions **24, 26** to create a injecting space **42** there between. A resin inlet **44** injects molten plastic material into the injecting space **42**. The plastic material heats and softens the backing sheet **22** and adheres thereto. The plastic material forms an article **46** having covered flanges **48, 50**.

After the article **46** cools, the press **10** is opened as illustrated in FIGS. 3 and 4. The article **46** remains on the core **14** because the flanges **48, 50** are contained within the recessed portions **34, 36**. It is desirable that the article **46** remain on the core **14** because it enables removing the article **46** using existing automated unloading equipment. After the press **10** is moved to the open position, the pistons **38, 40** move the slides **30, 32** to the retracted position as illustrated in FIG. 4. The article **46** is released from the core **14** and removed from the press **10**.

The invention as illustrated in FIGS. 1-4 uses linearly moving slides **30, 32**. In some applications, it may be preferable to use slides that move in an arcuate path as illustrated in FIGS. 5, 6. The slides **30', 32'** are hinged to the main body **28**. The slides **30', 32'** are moved between retracted and extended positions by the pistons **38, 40**.

5

The embodiment illustrated in FIGS. 7-9 uses a mold cavity 12' that has a die-lock condition. The cavity 12' includes recessed portions 30", 32" that form the flange portions on the molded article. The core 14' includes movable slides 30", 32". The slides 30", 32" move forwardly and inwardly of the main body 28 to create a narrower profile to fit within the mold cavity 12' as shown in FIG. 7. The slides 30", 32" are in a retracted position and to an extended position when the core 14' is moved to the closed position as shown in FIG. 8. After the article is molded, the core 14' is moved to the open position as shown in FIG. 9. As the core 14' moves to the open position, the slides are moved to the retracted position. To remove the article from the cavity 12', the covered flanges 48, 50 are retained on the slides 30", 32" by pins as is well known in the art. The flanges 48, 50 bend inwardly on the slides 30", 32" to have a narrower profile to be removed from the cavity 12'.

It is thus seen that the objects of this invention have been fully and effectively accomplished. It will be realized, however, that the foregoing preferred embodiments have been shown and described for the purpose of illustrating the functional and structural principles of this invention and are subject to change and modification by those skilled in the art without departing from the principles described. Therefore, this invention includes all modifications encompassed within the spirit and scope of the following claims:

What is claimed is:

1. A method of manufacturing an article having film-covered flanges comprising the steps of:

6

providing a moveable press having a mold with a cavity and a core, said core having two spaced slides movable between retracted and extended positions, said slides including recessed portions;

placing a thermoformed film within said cavity, said film having two inwardly turned spaced flange portions, the space between said flange portions defining a flange spacing;

positioning said slides in said retracted position so that the space between said recessed portions of the retracted slides is narrower than said flange spacing;

closing said press and moving said core into said cavity while said slides are in said retracted position;

moving said slides from said retracted position to said extended position in said cavity, said recessed portions of said slides thereby contacting said flange portions, said core with said slides in said extended position and thermoformed film with said flange portions defining an injecting space therebetween, said injecting space extending between said flange portions and said slides; and

injecting a molten plastic material into said injecting space, said plastic material adhering to said flange portions and forming said article having film-covered, inwardly turned flanges.

* * * * *